



(86) Date de dépôt PCT/PCT Filing Date: 2006/07/07
(87) Date publication PCT/PCT Publication Date: 2007/01/18
(45) Date de délivrance/Issue Date: 2016/11/29
(85) Entrée phase nationale/National Entry: 2008/01/08
(86) N° demande PCT/PCT Application No.: FI 2006/050322
(87) N° publication PCT/PCT Publication No.: 2007/006863
(30) Priorité/Priority: 2005/07/08 (EP05106243.8)

(51) Cl.Int./Int.Cl. *F16L 47/22* (2006.01),
B29C 45/00 (2006.01), *B29C 65/68* (2006.01)


(72) Inventeurs/Inventors:
SMAHL, JARMO, FI;
HAUKI, PETER, SE;
LARSSON, THOMAS, SE;
LUNDEQUIST, YNGVE, SE;
HALLEN, MATS, SE

(73) Propriétaire/Owner:
UPONOR INNOVATION AB, SE

(74) Agent: CASSAN MACLEAN

(54) Titre : RACCORD DE TUYAUX

(54) Title: PIPE CONNECTION



(57) Abrégé/Abstract:

A pipe connection comprises a connecting piece (2), a pipe (1) and a clamping ring (6). The pipe (1) and the clamping ring (6) are made of a material having memory properties. An end of the pipe (1) and the clamping ring (6) have been reversibly expanded co-jointly and firmly and sealingly shrunk to the connecting piece (2) by back shrinkage. Preferably the clamping ring (6) is made from a cross-linked polyolefin by injection molding.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 January 2007 (18.01.2007)

PCT

(10) International Publication Number
WO 2007/006863 A1

(51) International Patent Classification:

F16L 47/22 (2006.01) *B29C 45/00* (2006.01)
B29C 65/68 (2006.01)

(21) International Application Number:

PCT/FI2006/050322

(22) International Filing Date: 7 July 2006 (07.07.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

05106243.8 8 July 2005 (08.07.2005) EP

(71) Applicant (for all designated States except US): **UPONOR INNOVATION AB** [SE/SE]; Industrivägen, S-51381 Fristad (SE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **SMAHL, Jarmo** [FI/FI]; Satukaari 10, FI-15550 Nastola (FI). **HAUKI, Peter** [SE/SE]; Strandvägen 22, S-730 61 Virsbo (SE). **LARSSON, Thomas** [SE/SE]; Skäfruna Grenadjärtorpet, S-736 91 Kungsör (SE). **LUNDEQUIST, Yngve** [SE/SE]; Enebbavägen 12, S-73061 Virsbo (SE). **HÄLLEN, Mats** [SE/SE]; Persbovägen 4, SE-730 61 Virsbo (SE).

(74) Agent: **KOLSTER OY AB**; Iso Roobertinkatu 23, P.O. Box 148, FI-00121 Helsinki (FI).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PIPE CONNECTION



(57) Abstract: A pipe connection comprises a connecting piece (2), a pipe (1) and a clamping ring (6). The pipe (1) and the clamping ring (6) are made of a material having memory properties. An end of the pipe (1) and the clamping ring (6) have been reversibly expanded co-jointly and firmly and sealingly shrunk to the connecting piece (2) by back shrinkage. Preferably the clamping ring (6) is made from a cross-linked polyolefin by injection molding.

WO 2007/006863 A1

Pipe connection

The invention relates to a method and arrangement in connection with a pipe connection, a clamping ring for a pipe connection, and a pipe connection.

It is known to provide a pipe connection between one end of a pipe made of a plastic material that has memory properties and a connecting piece. The memory properties mean that plastic pipes with a memory capacity automatically strive to return essentially to their original shape and form after having been expanded. For example plastic pipes that are manufactured from cross-linked polyethylene possess an active memory capacity at temperatures as low as room temperature. Pipes of this nature are joined together by widening one end of the pipe and inserting into the widened pipe-end a flanged connector which forms a part of the pipe connecting piece, normally made of metal, and which is retained in said pipe-end until the pipe has shrunk to an extent at which it is able to firmly hold the connecting piece. A clamping ring made of elastic material, which may be the same plastic material as that from which the pipe is made, is expanded and shrunk over the pipe end, in order to further enhance the holding and sealing pressure at the pipe connection region. The clamping ring is expanded at the same time as the pipe-end is expanded, with the clamping ring in position around said pipe-end. Such a solution has been disclosed for example in EP 0 530 387. The clamping ring has been made from an extruded pipe by cutting the pipe into a short enough part to form a clamping ring.

There is now provided an enhanced solution for making a pipe connection. This solution may be achieved by a method, an arrangement, a clamping ring and a pipe connection, which are characterized by what is disclosed in the independent claims. Some embodiments of the invention are set for the independent claims.

According to one aspect the pipe connection comprises a connection piece, a pipe and a clamping ring. The pipe and the clamping ring are made of a material having memory properties, wherein an end of the pipe and the clamping ring have been reversibly expanded co-jointly and firmly and sealingly shrunk to the connecting piece by back shrinkage. The connection piece comprises a nipple end. The clamping ring is formed such that it is used for protecting the nipple end of the connecting piece. The clamping ring is

slipped over the nipple end during storage and transportation before the pipe connection is made. Thus the clamping ring protects the nipple end from being damaged during storage and transportation.

According to one embodiment the clamping ring is made from a cross-linked polyolefin by injection molding. By making the clamping rings with injection molding it is possible to optimize the properties of the clamping ring for each pipe connection. For example the wall thicknesses and the design of the clamping ring can be made as per need. It is also possible to make markings into the clamping ring to give information on the clamping ring to an end user.

According to another embodiment, the clamping ring is formed such that the total length of a weld line / weld lines in the radial direction in the injection molded clamping ring is larger than an average wall thickness of the clamping ring. The clamping ring is for example formed such that at a point where the weld line resides, the wall thickness is larger than the average wall thickness. Another possibility to increase the total length of the weld lines is to provide an injection molding mold into which the material is fed from two or more injection gates, such that the clamping ring comprises two or more weld lines. Also in this connection all the weld lines may be positioned such that they are formed at a position where the wall thickness is larger than the average wall thickness. Typically, the weld line is the weakest spot of an injection molded particle that is made from a cross-linked polyethylene. However, when the total length of the weld line is larger than the average wall thickness, the strength of the clamping ring is increased. Thus, the risk for cracks in the weld line during an expansion procedure is minimized. According to yet another embodiment, one end of the clamping ring is provided with a stop edge. This stop edge ensures that the clamping ring remains positioned at a correct position on the pipe-end when the pipe connection is being made and after the pipe connection has been made.

Brief description of the figures

In the following, the invention will be described in greater detail by means of preferred embodiments with reference to the accompanying drawings, in which

Figure 1 schematically shows a cross-sectional side view of a pipe connection,

Figure 2 schematically shows a cross-sectional end view of a clamping ring,

Figure 3 shows an end view of the clamping ring as seen from an end other than that in Figure 2,

Figure 4 schematically shows a cross-sectional side view of a clamping ring and

Figure 5 schematically shows a cross-sectional side view of another clamping ring.

Detailed description of the invention

Figure 1 shows a pipe 1, which is comprised of a plastic material having memory properties, for instance a cross-linked polyethylene PEX or any other cross-linked polyolefin, and a connecting piece 2 made of metal. The connecting piece 2 comprises a nipple end 3. The nipple end 3 comprises radially projecting flanges 4. The nipple end 3 is terminated with a radial abutment surface 5. The nipple end 3 has an outer diameter which exceeds the inner diameter of the unexpanded pipe 1. An elastic clamping ring 6 is mounted on an end of the pipe 1. In its relaxed state, the clamping ring 6 has an inner diameter which corresponds to the outer diameter of the unexpanded pipe 1.

Preferably the inner surface of the clamping ring 6 is conical as shown in Figure 4. This feature enables the clamping ring 6 to be positioned on the end of the pipe 1 with a tight fitting. Thus, because of the conical shape, it is easy to position the clamping ring on the end of the pipe 1 and further, because of the conical shape, the inner surface of the clamping ring 6 presses against the outer surface of the pipe 1 and the clamping ring 6 remains with a tight fitting on the end of the pipe 1. Thus it is easy to establish the pipe connection because the risk of the clamping ring 6 to drop off from the pipe end is thus minimized. The coning angle α of the inner surface of the clamping ring 6 can be in the range of $0,1^\circ$ to 2° , for example.

The inner surface of the clamping ring 6 can be made conical also such that first at the outer end of the clamping ring 6 there is a first larger coning angle β and thereafter a second smaller coning angle α as shown in Figure 5. The first larger coning angle β provides the advantage that the positioning of the clamping ring on the end of the pipe 1 is extremely easy. Because of the second smaller coning angle α the clamping ring 6 remains with a tight fitting on the end of the pipe 1. The first coning angle β can be in the range of 3° to

7° and the second coning angle α can be in the range of 0,1° to 2°, for example.

When establishing the pipe connection shown in Figure 1, the end of pipe 1 and the surrounding clamping ring 6 are expanded simultaneously by an expander tool. The nipple end 3 is then immediately inserted into the end of the pipe until the abutment surface 5 is in abutment with the end of the pipe 1 and with the clamping ring 6. The end of the pipe 1 and the clamping ring 6 then shrink or contract automatically, so as to obtain a sealing contact between the inner surface of the pipe 1 and the flange 4 in particular. The sealing contact is also obtained between the inner surface of the pipe 1 and the outer surface of the nipple end 3.

Figure 2 shows a cross-section of the clamping ring. When the ring is injection molded, the material is fed into a mold. The clamping ring shown in Figure 2 is made such that the mold comprises two injection gates. Thus, the material is fed into the mold from each sides of the mold, which in Figure 2 is depicted with arrows. The two material flows flow into the mold and they come into contact with each other. Therefore, a weld line 7 is formed at a point where the material flows unite. Because in Figure 2 the material has been fed through two injection gates, two weld lines 7 exist in the clamping ring. If the material is fed from only one injection gate, the weld line 7 is formed substantially on the opposite side of the injection gate. Typically, no weld lines 7 can be seen in an injection molded object, but in Figure 2 the weld lines 7 have been indicated with narrow lines.

Typically, a weld line is the weakest spot of an injection molded ring, especially when the ring is made from a cross-linked polyolefin. However, the total length of the weld line 7 in the radial direction is made larger than the average wall thickness of the clamping ring 6. The total length of the weld lines can be made larger for example by using more than one injection gate, such that the ring comprises two or more weld lines 7.

Also, if only one injection gate is provided and, therefore, only one weld line, the weld line can be made longer such that the wall thickness of the clamping ring is made larger at a position where the weld line resides. Thus, this means that the wall of the clamping ring is at its thickest at the weld line.

Also, if several weld lines are provided, the wall thickness at the weld line can be made larger, as is also shown in Figure 2.

Thus, the thicker wall at the weld line strengthens the clamping ring. Further, a mold with two or more, e.g. three or four, up to six, injection gates, gives more weld lines. When several weld lines are provided, the expansion force per one weld line is lower and thus the clamping ring is stronger.

The diameter of the clamping ring may vary e.g. between 15 to 50 mm. The length of the clamping ring 6 may be e.g. substantially equal to the diameter of the clamping ring. The length of the clamping ring may also be dimensioned such that it is substantially equal to the length of the nipple end 3 of the connecting piece 2. An average wall thickness of the clamping ring may vary e.g. between 2 to 6 mm. The wall thickness of the clamping ring determines the contraction force of the clamping ring. Thus, the wall thickness of the clamping ring is dimensioned such that the contraction force is sufficient. If the wall is made thicker at the weld line 7, the wall may be e.g. 0.3 to 2 mm thicker than the average wall thickness.

The clamping ring 6 is made from a cross-linked polyolefin. The clamping ring may be made e.g. of a cross-linked polyethylene PEX or cross-linked polypropylen. Preferably, the clamping ring 6 is made from a PEX-B material, i.e. a silane PEX. When a PEX-B material is used, cross-linking starts by the effect of heat. Therefore, a PEX-B material is advantageous in connection with injection molding.

One end of the clamping ring is provided with a stop edge 8. The stop edge 8 ensures that the end of the pipe 1 is at a correct position with respect to the clamping ring 6. The stop edge 8 extends inwards. The stop edge 8 comprises inward extending protrusions 9, which are also seen in Figure 3. The protrusions 9 ensure that the pipe 1 stops at a correct position with respect to the clamping ring 6. Further, the protrusions 9 are made high enough for the clamping ring to be used for protecting the nipple end 3 of the connecting piece before the pipe connection is made. The inner diameter of the clamping ring, when the clamping ring 6 is in its original form and shape, is larger than the outer diameter of the nipple end 3. However, the protrusions are high enough to extend to a circumference that is smaller than the outer diameter of the flanges 4 of the nipple end 3. Thus, the clamping ring 6 can be snapped on the nipple end 3, such that the protrusions 9 and the flange 4 hold the clamping ring 6 on the nipple end 3. Thus, the clamping ring 6 protects the nipple end from being damaged, which could cause leakage problems. Thus, during storage and transportation the nipple end is not damaged.

Instead of the protrusions 9, the means for holding the clamping ring 6 on the nipple end 3 can be a radially inward protruding ring which has been made thin enough such that it yields when the clamping ring 6 is snapped on the nipple end 3, for example.

Instead of injection molding the clamping ring can be made from an extruded pipe by cutting the pipe in to a short enough part to form a clamping ring, for example. After cutting, the appropriate protrusions and other needed forms can be formed to the clamping ring by thermoforming, for example.

In some cases the features shown in this description can be used as such irrespective of other features. Then again the features shown in this description may if necessary be combined in order to form different combinations.

It is obvious to a person skilled in the art that in the course of technical progress, the basic idea of the invention can be carried out in numerous ways. Thus, the invention and its embodiments are not limited by the previous examples, but they may vary within the scope of the appended claims. Further, the clamping ring may e.g. comprise a hole, through which it can be detected whether the pipe is pushed correctly inside the clamping ring 6.

What is claimed is

1. A clamping ring for a pipe connection, the clamping ring being made from a cross-linked polyolefin having memory properties, such that after expansion, the clamping ring automatically returns to pre-expansion shape and form.

2. A clamping ring as claimed in claim 1, characterized in that the clamping ring comprises at least one weld line, a total length of which in a radial direction is larger than an average wall thickness of the clamping ring.

3. A clamping ring as claimed in claim 2, characterized in that the weld line is formed at a position where the wall thickness of the clamping ring is larger than the average wall thickness of the clamping ring.

4. A clamping ring as claimed in claims 2 or 3, characterized in that the clamping ring is formed such that it comprises two or more weld lines.

5. A clamping ring as claimed in any one of claims 1 to 2, characterized in that the clamping ring at its one end comprises an inward extending stop edge.

6. A clamping ring as claimed in claim 5, characterized in that the stop edge comprises an inward extending protrusion.

7. A clamping ring as claimed in any one of the claims 1 to 6, characterized in that the clamping ring is made from a PEX-B material.

8. A clamping ring as claimed in any one of the claims 1 to 7, characterized in that the inner surface of the clamping ring is conical.

9. A clamping ring as claimed in claim 8, characterized in that the conical inner surface of the clamping ring is formed such that at the outer end of the clamping ring there is a first larger coning angle and thereafter there is a second smaller coning angle.

10. A pipe connection comprising a connecting piece, a pipe, and a clamping ring, the pipe and the clamping ring being made of a cross-linked polyolefin having memory properties, such that after expansion, the pipe and the clamping ring automatically return to pre-expansion shape and form; and

wherein an end of the pipe and the clamping ring have been reversibly expanded co-jointly and firmly and sealingly shrunk to the connecting piece by back shrinkage.

11. A pipe connection as claimed in claim 10, characterized in that the clamping ring comprises at least one weld line, a total length of which is larger in a radial direction than an average wall thickness of the clamping ring.

12. A pipe connection as claimed in claim 11, characterized in that the weld line is formed at a position where the wall thickness of the clamping ring is larger than the average wall thickness of the clamping ring.

13. A pipe connection as claimed in claims 11 or 12, characterized in that the clamping ring is formed such that it comprises two or more weld lines.

14. A pipe connection as claimed in any one of the claims 10 to 13, characterized in that the clamping ring at its one end comprises an inward extending stop edge.

15. A pipe connection as claimed in claim 14, characterized in that the stop edge comprises inward extending protrusions.

16. A pipe connection as claimed in any one of the claims 10 to 15, characterized in that the clamping ring is made from a PEX-B material.

17. A pipe connection as claimed in any one of the claims 10 to 16, characterized in that the inner surface of the clamping ring is conical.

18. A pipe connection as claimed in claim 17, characterized in that the conical inner surface of the clamping ring is formed such that at the outer end of the clamping ring there is a first larger coning angle and thereafter there is a second smaller coning angle.

19. A clamping ring for a pipe connection, the clamping ring comprising:

a tubular ring of cross-linked polyolefin material with memory properties such that after expansion, the tubular ring automatically returns to

pre-expansion shape and form; wherein the tubular ring has a smooth inner surface and an inner circumference and a first end and a second end;

a stop edge along one of said ends of said ring wherein said stop edge has a smaller circumference than said inner circumference of said ring; and

wherein said ring is in a contracted state at ambient temperature, expands to an expanded state for said pipe connection and returns to said contracted state after installation.

1/2




FIG. 1




FIG. 2




FIG. 3

2/2




FIG. 4




FIG. 5

