

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 June 2003 (26.06.2003)

PCT

(10) International Publication Number
WO 03/051786 A1

- (51) International Patent Classification⁷: **C03C 3/095**, 4/02, 4/08
- (21) International Application Number: PCT/EP02/13965
- (22) International Filing Date: 5 December 2002 (05.12.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2001/0817 14 December 2001 (14.12.2001) BE
2002/0445 18 July 2002 (18.07.2002) BE
- (71) Applicant (for all designated States except US):
GLAVERBEL [BE/BE]; Chaussée de la Hulpe 166,
B-1170 Brussels (Watermael-Boitsfort) (BE).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **COSTER, Dominique** [BE/BE]; Glaverbel, Centre R & D, 2, rue de l'Aurore, B-6040 Jumet (BE). **DELMOTTE, Laurent** [BE/BE]; Glaverbel, Centre R & D, 2, rue de l'Aurore, B-6040 Jumet (BE). **VAN DEN NESTE, Marc** [BE/BE]; Glaverbel, Centre R & D, 2, rue de l'Aurore, B-6040 Jumet (BE).
- (74) Agents: **LE VAGUERESE, Sylvain** et al.; Glaverbel Centre R & D, Département Propriété Intellectuelle, Rue de l'Aurore 2, B-6040 Jumet (BE).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 03/051786 A1

(54) Title: COLOURED SODA-LIME GLASS

(57) Abstract: The present invention relates to a coloured soda-lime glass which comprises iron in a quantity which, expressed in weight of the oxide Fe₂O₃ in relation to the total weight of glass, is greater than or equal to 0.5, and less than or equal to 1.0% (quantity of total iron), a ratio of Fe²⁺/total Fe (redox ratio) in the range of between 20 and 65%, cerium in a quantity which, expressed in weight of CeO₂ in relation to the total weight of glass, is greater than or equal to 0.1%, and titanium in a quantity which, expressed in weight of TiO₂ in relation to the total weight of glass, is greater than or equal to 0% and less than 0.2%. This glass has a light transmission (TLA4) in the range of between 15 and 55%, a total transmission in the ultraviolet (TUV4) of less than or equal to 30%, and a dominant wavelength in transmission (λ_D) of less than or equal to 491 nm. This glass can be used, for example, as side glazing, rear-view window, roof glazing or opening roof of a motor vehicle.

Coloured Soda-Lime Glass

The present invention relates to a coloured soda-lime.

Soda-lime glass can be clear or coloured, for example, green, grey or blue in transmission.

The expression "soda-lime glass" is used here in the wide sense and relates to any glass which is likely to contain the following principal glass-forming constituents (in percentages by weight):

	SiO ₂	60 to 75%
	Na ₂ O	10 to 20%
	CaO	0 to 16%
10	K ₂ O	0 to 10%
	MgO	0 to 10%
	Al ₂ O ₃	0 to 5%
	BaO	0 to 2%
	BaO + CaO + MgO	10 to 20%
15	K ₂ O + Na ₂ O	10 to 20%.
	B ₂ O ₃	0 to 5%

In some cases, soda-lime glass can have a total percentage by weight of BaO, CaO and MgO greater than 10%, and even greater than 12%.

This type of glass is very widely used in the field of glazing for automobiles or buildings, for example. It is usually manufactured in the form of a ribbon by the float process. Such a ribbon can be cut into sheets which can then be bent or can undergo treatment to improve their mechanical properties, e.g. a thermal toughening step.

It is generally necessary to relate the optical properties of a glass sheet to a standard illuminant. In the present description, two standard illuminants are used: illuminant C and illuminant A defined by the Commission Internationale de l'Eclairage (C.I.E.). Illuminant C represents average daylight having a colour temperature of 6700 K. This illuminant is especially useful for evaluating the optical properties of glazing intended for buildings. Illuminant A represents the radiation of a

Planck radiator with a temperature of about 2856 K. This illuminant describes the light emitted by car headlights and is essentially intended to evaluate the optical properties of glazings intended for automobiles.

The Commission Internationale de l'Eclairage has also published a document entitled "Colorimétrie, Recommandations Officielles de la C.I.E. [Colorimetry and Official Recommendations of the C.I.E.]" (May 1970) which describes a theory in which the colorimetric coordinates for light of each wavelength of the visible spectrum are defined so that they can be represented on a diagram having orthogonal axes x and y , called the C.I.E. trichromaticity plot 1931. This trichromaticity plot shows the locus representative of light of each wavelength (expressed in nanometers) of the visible spectrum. This locus is called the "spectrum locus" and light having coordinates lying on this spectrum locus is said to have 100% excitation purity for the appropriate wavelength. The spectrum locus is closed by a line called the purple boundary which connects the points of the spectrum locus, the coordinates of which correspond to wavelengths of 380 nm (violet) and 780 nm (red). The area lying between the spectrum locus and the purple boundary is that available for the trichromaticity coordinates of any visible light. The coordinates of the light emitted by illuminant C, for example, correspond to $x = 0.3101$ and $y = 0.3162$. This point C is regarded as representing white light, and consequently has an excitation purity equal to zero for any wavelength. Lines may be drawn from point C to the spectrum locus at any desired wavelength and any point lying on these lines may be defined not only by its x and y coordinates, but also as a function of the wavelength corresponding to the line on which it lies and of its distance from point C relative to the total length of the wavelength line. Consequently, the colour of the light transmitted by a coloured glass sheet may be described by its dominant wavelength (λ_D) and its excitation purity (P) expressed as a percentage.

The C.I.E. coordinates of light transmitted by a coloured glass sheet will depend not only on the composition of the glass but also on its thickness. In the present description, as in the claims, all the values of the excitation purity P and the dominant wavelength λ_D of the transmitted light are calculated from the spectral

specific internal transmissions (SIT_{λ}) of a glass sheet 5 mm in thickness with illuminant C from a solid viewing angle of 2° . The spectral specific internal transmission of a glass sheet is governed solely by the absorption of the glass and can be expressed by the Beer-Lambert law:

$$5 \quad SIT_{\lambda} = e^{-E \cdot A_{\lambda}}$$

where A_{λ} is the absorption coefficient (in cm^{-1}) of the glass at the wavelength in question and E the thickness (in cm) of the glass. In a first approximation, SIT_{λ} may also be represented by the formula:

$$(I_3 + R_2)/(I_1 - R_1)$$

10 where I_1 is the intensity of the incident visible light on a first face of the glass sheet, R_1 is the intensity of the visible light reflected by this face, I_3 is the intensity of the visible light transmitted from the second face of the glass sheet and R_2 is the intensity of the visible light reflected by this second face towards the interior of the sheet.

15 The following are also used in the following description and the claims:

- for illuminant A, the total light transmission (TLA) measured for a thickness of 4 mm (TLA4) from a solid viewing angle of 2° . This total transmission is the result of the integration between the 380 and 780 nm wavelengths of the expression: $\sum T_{\lambda} \cdot E_{\lambda} \cdot S_{\lambda} / \sum E_{\lambda} \cdot S_{\lambda}$ in which T_{λ} is the transmission at wavelength λ , E_{λ} is
20 the spectral distribution of illuminant A and S_{λ} is the sensitivity of the normal human eye as a function of wavelength λ ;

- the total energy transmission (TE) measured for a thickness of 4 mm (TE4). This total transmission is the result of the integration between the 300 and 2500 nm wavelengths of the expression: $\sum T_{\lambda} \cdot E_{\lambda} / \sum E_{\lambda}$. The energy distribution E_{λ} is
25 the spectral energy distribution of the sun at 30° above the horizon with an air mass equal to 2 and an inclination of the glazing of 60° relative to the horizontal. This distribution, called "Moon distribution", is defined in the standard ISO 9050;

- the selectivity (SE) measured as the ratio of the total light transmission for illuminant A to the total energy transmission (TLA/TE);

- the total transmission in the ultraviolet, measured for a thickness of 4 mm (TUV4). This total transmission is the result of the integration between 280 and 380 nm of the expression: $\Sigma T_{\lambda} \cdot U_{\lambda} / \Sigma U_{\lambda}$ in which U_{λ} is the spectral distribution of the ultraviolet radiation that has passed through the atmosphere, defined in the standard
5 DIN 67507;

- the Fe^{2+} /total Fe ratio, sometimes called the redox ratio, which represents the value of the ratio of weight of atoms of Fe^{+2} to the total weight of iron atoms present in the glass and is obtained by the formula:

$$Fe^{2+}/total\ Fe = [24.4495 \times \log(92/\tau_{1050})]/t_{Fe_2O_3}$$

10 where τ_{1050} represents the specific internal transmission of the 5 mm thick glass at the 1050 nm wavelength, $t_{Fe_2O_3}$ represents the total iron content expressed in the form of oxide Fe_2O_3 and measured by X-ray fluorescence.

Coloured glass can be used in architectural applications and as glazing for railway carriages and motor vehicles. In architectural applications, glass sheets 4
15 to 6 mm in thickness are generally used, while in the automotive field thicknesses of 1 to 5 mm are normally employed, particularly for the production of monolithic glazing, and thicknesses of between 1 and 3 mm in the case of laminated glazing, especially for windscreens, two glass sheets of this thickness then being bonded together by means of an interlayer film, generally made of polyvinyl butyral (PVB).

20 One of the objects of the invention is to provide a soda-lime glass of low light transmission, preferably blue in colour, which enables the unpleasing discolouration of the objects located inside areas enclosed by this glass to be restricted.

The European patent application EP 0 101 36 20 A1 and the
25 international application PCT/EP01/06861 describe highly selective glasses containing iron with a high redox ratio (Fe^{2+} /total iron), and also cobalt and/or chromium and/or vanadium respectively. However, to promote a high redox ratio may be detrimental to other optical properties such as total transmission in the ultraviolet which is responsible for the discolouration of objects located inside areas
30 enclosed by such glasses.

The invention proposes glass compositions which have all the desired properties and in particular that of a filter for ultraviolet solar radiation.

The present invention provides a coloured soda-lime glass which comprises the principal glass-forming constituents and colouring agents comprising:

- 5 ♦ iron in a quantity which, expressed in weight of the oxide Fe_2O_3 in relation to the total weight of glass, is greater than or equal to 0.5, and less than or equal to 1.0% (quantity of total iron),
- ♦ ferrous iron in a quantity which, expressed in weight of atoms of Fe^{2+} in relation to the total weight of iron atoms present in the glass,
10 lies in the range of between 20 and 65% (ratio of Fe^{2+} /total Fe),
- ♦ cerium in a quantity which, expressed in weight of CeO_2 in relation to the total weight of glass, is greater than or equal to 0.1%,
- ♦ titanium in a quantity which, expressed in weight of TiO_2 in relation to the total weight of glass, is greater than or equal to 0% and less than
15 0.2%,
and the glass has:
- ♦ a light transmission, measured for illuminant A and calculated for a thickness of 4 mm (TLA4), which lies in the range of between 15 and 55%,
- 20 ♦ a total transmission in the ultraviolet measured for a thickness of 4 mm (TUV4) of less than or equal to 30%,
- ♦ a dominant wavelength in transmission (λ_D) of less than or equal to 491 nm.

It has been found that such a glass allows commercially desirable
25 considerations relating to both aesthetics and energy to be met. In the automotive sector in particular a coloured glass according to the invention can have a blue tint, with a wavelength in transmission of less than or equal to 491 nm, which is appreciated by motor vehicle manufacturers, a low light transmission and a low total transmission in the ultraviolet enabling the unpleasing discolouration of the objects
30 located inside areas enclosed by this glass to be restricted.

The presence of cerium in a quantity which, expressed in weight of CeO_2 in relation to the total weight of glass is greater than or equal to 0.1%, combined with the composition criteria relating to iron, allows a glass to be produced with a wavelength in transmission, light transmission and total transmission in the ultraviolet that meet present criteria relating to aesthetics and energy, especially
5 required by motor vehicle manufacturers.

Iron is present in the majority of glasses currently on the market, in particular in coloured glasses. The presence of Fe^{3+} provides the glass with a light absorption of the visible light of short wavelength (410 and 440 nm) and a very high
10 absorption band in the ultraviolet (absorption band centred at 380 nm), while the presence of Fe^{2+} ions causes a high absorption in the infrared (absorption band centred at 1050 nm). The presence of Fe^{3+} gives the glass a slight yellow coloration, generally regarded as not very pleasing, while ferrous, Fe^{2+} , ions give a pronounced blue-green coloration. A strong concentration of Fe^{2+} in the glass therefore allows the
15 energy transmission TE to be reduced and a pleasing coloration to be provided. However, the presence of iron in the bath of molten glass results in an absorption of infrared radiation which can hinder heat diffusion in the glass production furnace, and therefore make this production more difficult. Moreover, when the concentration of iron increases, the light transmission of the glass decreases.

20 The energy and optical properties of a glass, in particular its colour, its light transmission and its total transmission in the ultraviolet, result from a complex interaction between its components. The behaviour of components of the glass depends on their redox state and therefore on the presence of other components which can influence this redox state.

25 It has been found that the glass as defined in the claims enables aesthetic criteria (colour) and optical/energy criteria (light transmission and total transmission in the ultraviolet) to be responded to by easily controlling its composition, particularly in terms of iron and cerium.

30 Preferably, the quantity of total iron is less than or equal to 0.90%, and preferably less than or equal to 0.89%. This facilitates the transition of the production of clear glass to the production of coloured glass.

Preferably, the quantity of total iron is at least 0.7% or even at least 0.75%. This promotes not only the formation of a colour that is pleasing to the eye, but also the formation of a low light transmission as well as a low energy transmission.

5 Preferably, the glass according to the invention comprises ferrous iron in a quantity which, expressed in weight of atoms of Fe^{2+} in relation to the total weight of iron atoms present in the glass, lies in the range of between 20 and 65%, preferably between 35 and 55%, and advantageously between 40 and 50%. Such a ratio enables a glass to be obtained that combines a good selectivity with a low
10 transmission in the ultraviolet.

Preferably, the glass according to the invention comprises cerium in a quantity which, expressed in weight of CeO_2 in relation to the total weight of glass, is greater than 0.15%, preferably greater than 0.25%, in order to restrict as far as possible the unpleasing discoloration of objects located inside areas enclosed by the
15 glass according to the invention under the effect of ultraviolet solar radiation. The glass according to the invention preferably comprises cerium in a quantity which, expressed in weight of CeO_2 in relation to the total weight of glass, is less than 1.0%, preferably less than or equal to 0.5%. In fact, cerium, when present in too large a quantity, can cause the dominant wavelength to shift towards green and yellow,
20 which is contrary to the preferred tint.

The invention advantageously combines a high redox ratio with a quantity of cerium which enables the desired properties to be provided without the aesthetic aspect of the glass being impaired.

Preferably, the glass according to the invention comprises a quantity of
25 titanium which, expressed in weight of TiO_2 in relation to the total weight of glass, is greater than or equal to 0% and less than 0.2%, and preferably less than 0.15%, or even less than 0.10%. In fact, a high content of TiO_2 poses the risk of imparting an unwanted yellow coloration. In some cases, TiO_2 will only be contained in the glass as a result of the presence of impurities, with no intentional addition.

30 To produce a glass with a colour which is commercially desirable as it is considered to be pleasing to the eye, the glass according to the invention can

contain one or more of the following colouring agents in addition to those already mentioned.

♦ cobalt

The presence of cobalt tends to give the glass an intense blue colour.
5 Preferably, the glass according to the invention comprises cobalt in a quantity which, expressed in weight of Co in relation to the total weight of glass, is greater than 75 ppm, and even greater than 100 ppm. Preferably, the quantity of cobalt is less than or equal to 350 ppm, and advantageously less than or equal to 250 ppm. A quantity of cobalt that is too high can in fact impair the selectivity of the glass.

10 In a preferred form, the glass according to the invention comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting essentially of Fe, Ce and Co according to at least one of the ranges mentioned above. Ti may possibly be added to this composition.

In another preferred form, the glass according to the invention
15 comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting of Fe, Ce and Co according to at least one of the ranges mentioned above. Ti may possibly be added to this composition.

♦ chromium

The presence of Cr^{III} tends to give the glass a light green coloration,
20 whereas the presence of Cr^{VI} produces a very intense absorption band of 365 nm and a yellow coloration of the glass. Preferably, the glass comprises chromium in a quantity which, expressed in weight of Cr₂O₃ in relation to the total weight of glass, is at least 5 parts per million (ppm). In some cases, the glass can comprise chromium in a quantity that is greater than or equal to 50 ppm, and even greater than or equal to
25 100 ppm. Preferably the quantity of chromium is less than 1000 ppm, and advantageously less than or equal to 500 ppm.

In a preferred form, the glass according to the invention comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting essentially of Fe, Ce, Co and Cr according to at least one of the ranges
30 mentioned above. Ti may possibly be added to this composition.

In another preferred form, the glass according to the invention comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting of Fe, Ce, Co and Cr according to at least one of the ranges mentioned above. Ti may possibly be added to this composition.

5 ♦ vanadium

The presence of vanadium tends to give the glass a green tint. Preferably, the glass according to the invention comprises vanadium in a quantity which, expressed in weight of V_2O_5 in relation to the total weight of glass, is less than 1000 ppm, and advantageously less than 500 ppm. In some cases, V_2O_5 will only be
10 contained in the glass as a result of the presence of impurities, with no intentional addition.

The light transmission TLA4 of the coloured glass according to the invention lies in the range of between 15 and 55%, preferably between 20 and 45%, and advantageously between 25 and 35%. This makes this glass well suited for use,
15 for example, as glazing for motor vehicles, in particular for side glazing, rear-view windows, roof glazing or also opening roofs.

The total transmission in the ultraviolet (TUV4) of the coloured glass according to the invention is preferably less than or equal to 30%, but can be less than or equal to 25%, and advantageously less than or equal to 20%. Such values
20 for TUV4 help to prevent the unpleasing discoloration of objects located in areas enclosed by such a glass and exposed to ultraviolet solar radiation.

It is desirable if the coloured glass according to the invention has an energy transmission TE4 of less than 45%, preferably less than 35%, and advantageously less than 25%. A low energy transmission helps limit the temperature
25 increase in the internal area enclosed by the glass according to the invention, such as a building or motor vehicle, during exposure to the sun.

The glass according to the invention preferably has a selectivity greater than 1.0, preferably greater than 1.1. A high selectivity is advantageous both for applications in motor vehicles and in architectural applications, since it helps limit the
30 temperature increase associated with solar radiation, and thus increase the thermal

comfort of occupants of the vehicle or building while providing high natural illumination and visibility through the glazing.

With respect to the colour of the glass according to the invention, it is desirable if its dominant wavelength in transmission λ_D is less than or equal to 489 nm. This corresponds to a glass whose colour in transmission is generally tinted blue, which is pleasing to the human eye and is highly appreciated commercially, in particular for glazing for motor vehicles. It is advantageous if the glass has a λ_D of less than or equal to 487 nm.

The excitation purity in transmission of the glass according to the invention is preferably greater than 10%, and preferably greater than 15%. This corresponds to a pronounced tint, which is commercially desirable. In some cases, the excitation purity in transmission can be greater than or equal to 20%, and even greater than 25%.

In some cases, the glass according to the invention can comprise less than 200 parts per million (ppm), preferably less than 100 ppm, of nickel, expressed in weight of NiO in relation to the total weight of glass. The presence of nickel can impair the selectivity of the glass containing it, since it does not absorb light in the infrared range, which results in a significant energy transmission value. In addition, it gives the glass a yellow coloration. Moreover, the presence of nickel can cause difficulties in the production of glass (formation of sulphides, inclusions of nickel in the glass). In particular embodiments, the glass according to the invention is free of nickel as colouring agent.

Preferably, the glass according to the invention comprises less than 1500 parts per million, preferably less than 500 parts per million, of manganese expressed in weight of MnO₂ in relation to the total weight of glass. Manganese in the form of MnO₂ has an oxidising character which can modify the redox state of the iron and induce a green hue.

Preferably, the glass according to the invention comprises more than 2% by weight of magnesium oxide MgO in relation to the total weight of glass. The

presence of magnesium benefits the fusion of the constituents during melting of the glass.

Advantageously, the glass according to the invention comprises less than 30 parts per million of selenium, preferably less than 20 parts per million by weight of Se in relation to the total weight of glass. The presence of selenium as
5 colouring agent can promote a low light transmission, but if present in too large a quantity, it can give the glass an unwanted pink or red coloration.

According to a preferred form of the invention, the colouring agents are present in a quantity corresponding to the following proportions (expressed as a
10 percentage of the total weight of glass in the form indicated):

	Fe ₂ O ₃	0.5 - 1.0%
	CeO ₂	0.1 - 0.95%
	Co	130 - 160 ppm
	Cr ₂ O ₃	150 - 950 ppm
15	Se	0 - 10 ppm
	TiO ₂	0 - 0.15%
	Fe ²⁺ /total Fe	30 - 50%

This glass preferably has the following optical properties:

	TLA4	15 - 55%
20	TE4	< 45%
	TUV4	≤ 30%
	λ _D	≤ 491 nm
	P	> 10% and ≤ 35%

According to a particularly preferred form of the invention, the
25 colouring agents are present in a quantity corresponding to the following proportions (expressed as a percentage of the total weight of glass in the form indicated):

	Fe ₂ O ₃	0.7 - 0.9%
	CeO ₂	0.2 - 0.7%
	Co	135 - 150 ppm
30	Cr ₂ O ₃	300 - 500 ppm

Se 0 - 10 ppm

TiO₂ 0 - 0.15%

Fe²⁺/total Fe 35 - 45%

This glass preferably has the following optical properties:

5 TLA4 25 - 40%

TE4 20 - 30%

TUV4 10 - 20%

λ_D 480 - 490 nm

P 20 - 35%

10 According to a preferred embodiment, the glass according to the invention comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting essentially of Fe, Ce, Co, Cr and Se according to at least one of the ranges mentioned above. Ti may possibly be added to this composition.

15 In another preferred form, the glass according to the invention comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting of Fe, Ce, Co, Cr and Se according to at least one of the ranges mentioned above. Ti may possibly be added to this composition.

20 It is desirable if the glass according to the invention does not contain fluorinated compounds, or at least if these do not constitute more than 0.2% by weight of F in relation to the glass. These compounds in fact generate furnace discharges which are harmful to the environment and are, moreover, corrosive with respect to the refractory materials which line the inside of the production furnace.

25 The coloured glass according to the invention preferably forms a glazing for motor vehicles. It may, for example, be advantageously used for side glazing or rear-view windows of a vehicle or roof glazing or opening roofs.

The glass according to the invention may be coated with a layer. For example, this can be a layer of metal oxides, which reduce the temperature increase resulting from solar radiation and consequently the temperature increase inside the passenger compartment of a vehicle using such glass as glazing.

30 The glasses according to the invention can be manufactured by conventional processes. As batch materials, it is possible to use natural materials,

recycled glass, slag or a combination of these materials. The colouring agents are not necessarily added in the form indicated, but this manner of giving the amounts of colouring agents added in equivalents in the forms indicated corresponds to standard practice. In practice, iron is added in the form of red iron oxide, cobalt is added in the form of hydrated sulphate, such as $\text{CoSO}_4 \cdot 7\text{H}_2\text{O}$ or $\text{CoSO}_4 \cdot 6\text{H}_2\text{O}$ and chromium is added in the form of dichromate such as $\text{K}_2\text{Cr}_2\text{O}_7$. Cerium is often introduced in oxide or carbonate form, and vanadium in the form of vanadium oxide or sodium vanadate. Selenium, when present, can be added in elemental form or in selenite form such as Na_2SeO_3 or ZnSeO_3 .

Other elements are sometimes present as a result of impurities in the batch materials used to manufacture the glass according to the invention, whether these are natural materials, recycled glass or slag, which are increasingly used, but when these impurities do not give the glass properties outside the limits defined above, these glasses are regarded as complying with the present invention.

The present invention shall now be illustrated by the following examples:

EXAMPLES 1 to 143

Table I specifies by way of non-restrictive indication the base composition of the glass. It should be understood that a glass with the same optical and energy properties can be obtained with a base composition having amounts of oxides lying within the ranges of percentages by weight given at the beginning of the present description.

The glasses according to the examples comprise less than 100 parts per million (ppm) of NiO, less than 500 ppm of MnO_2 and, unless specified otherwise, less than 3 ppm of Se, less than 0.1% of TiO_2 and more than 2% of MgO.

Table I

Analysis of the base glass	
SiO_2	71.5 - 71.9%
Al_2O_3	0.8%
CaO	8.8%
MgO	4.2%

Na ₂ O	14.1%
K ₂ O	0.1%
SO ₃	0.05 - 0.45%

The following table gives the concentrations of the components, the optical and energy properties of glasses according to the invention. The concentrations are determined by X-ray fluorescence of the glass and are converted into the indicated molecular state.

Table II

Ex .	Fe ₂ O ₃ (%)	Fe ²⁺ /Fe tot (%)	CeO ₂ (%)	Co (ppm)	Cr ₂ O ₃ (%)	Se (ppm)	TLA4 (%)	TUV4 (%)	λ _D (nm)	TE4 (%)	P (%)	SE
1	0.875	32.73	0.29	150	351		32.9	12.6	483.3	25.9	30.2	1.27
2	0.873	35.42	0.49	146	352		33.0	11.8	483.4	24.9	30.2	1.32
3	0.893	41.52	0.10	152	352		31.4	15.8	482.9	22.4	33.3	1.40
4	0.874	33.58	0.49	147	354		32.8	11.2	483.5	25.5	29.8	1.29
5	0.871	33.28	0.39	145	355		32.7	11.7	483.6	25.7	29.7	1.27
6	0.870	32.72	0.49	147	362		32.7	11.1	483.6	25.8	29.6	1.27
7	0.848	24.12	0.97	142	359		34.9	8.3	484.4	31.4	25.3	1.11
8	0.890	39.35	0.10	152	343		31.7	16.0	482.8	23.1	33.0	1.37
9	0.867	35.19	0.48	146	352		32.4	11.7	483.4	24.8	30.5	1.31
10	0.873	39.08	0.29	141	347		32.4	13.8	483.3	23.5	31.3	1.38
11	0.850	25.65	0.97	138	363		35.2	8.3	484.8	30.5	24.8	1.15
12	0.854	48.24	0.29	143	298		29.6	14.3	482.4	20.4	35.8	1.45
13	0.854	46.99	0.285	148	308		31.8	14.1	483.2	21.5	32.9	1.48
14	0.861	47.85	0.28	168	310		29.7	14.4	482.5	20.6	35.4	1.44
15	0.898	49.89	0.30	148	354		29.9	12.9	483.4	19.6	33.8	1.53
16	0.900	50.25	0.30	155	362		29.3	13.4	482.5	19.3	36.1	1.52
17	0.882	45.50	0.30	149	322		29.3	13.3	482.0	20.6	36.1	1.42
18	0.908	48.94	0.32	151	329		28.6	13.1	482.5	19.1	36.5	1.50
19	0.906	49.05	0.30	160	333		27.5	12.9	482.1	18.7	37.8	1.47
20	0.906	48.24	0.30	164	333		28.5	12.7	482.5	19.3	36.3	1.48
21	0.864	30.81	0.68	145	313		33.8	10.1	483.2	27.4	29.1	1.23
22	0.852	24.58	0.89	144	310		34.9	8.6	483.6	31.3	26.6	1.15
23	0.850	23.97	0.97	141	316		35.3	8.3	483.8	31.9	25.8	1.11

Ex .	Fe ₂ O ₃ (%)	Fe ²⁺ /Fe tot (%)	CeO ₂ (%)	Co (ppm)	Cr ₂ O ₃ (%)	Se (ppm)	TLA4 (%)	TUV4 (%)	λ _D (nm)	TE4 (%)	P (%)	SE
24	0.847	43.34	0.30	139	341		30.5	14.2	482.3	22.2	34.9	1.37
25	0.800	44.00	0.30	140	400		30.3	15.4	482.6	22.6	34.6	1.34
26	0.750	45.00	0.30	145	450		29.5	16.8	482.7	22.7	35.3	1.30
27	0.700	45.00	0.50	145	500		29.7	15.6	483.0	23.9	34.7	1.24
28	0.650	47.00	0.50	150	500		28.9	16.9	482.5	23.5	36.5	1.22
29	0.700	45.00	0.40	155	400		28.8	16.7	481.6	23.7	38.0	1.22
30	0.600	45.00	0.70	160	380		29.5	15.4	480.8	26.4	39.4	1.12
31	0.550	45.00	0.70	155	550		29.8	16.9	482.4	27.0	36.2	1.10
32	0.700	45.00	0.50	150	450		29.3	15.6	482.3	23.8	36.3	1.23
33	0.500	50.00	0.90	155	590		28.2	15.8	482.6	25.0	37.6	1.13
34	0.600	40.00	0.90	150	50		35.7	12.2	478.0	32.4	38.7	1.10
35	0.850	40.00	0.90	140	50		33.4	6.3	479.6	26.4	36.3	1.26
36	0.600	50.00	0.90	150	0		32.1	12.1	478.0	26.1	43.0	1.23
37	0.850	40.00	0.90	140	0		33.8	6.1	479.1	26.7	37.0	1.26
38	0.875	50.00	0.90	100	50		36.1	5.4	481.7	21.8	32.1	1.66
39	0.850	55.00	0.90	70	50		39.8	5.7	483.1	21.1	28.3	1.88
40	0.875	60.00	0.90	50	300		39.0	5.5	487.7	17.0	23.2	2.29
41	0.850	50.00	0.90	30	0		49.2	5.3	485.5	27.2	19.6	1.81
42	0.847	40.00	0.30	139	340		31.8	14.2	482.3	24.4	33.7	1.30
43	0.850	44.00	0.30	140	500		28.8	14.5	483.9	20.8	33.2	1.39
44	0.850	45.00	0.30	150	200		29.9	13.8	483.9	21.5	33.2	1.39
45	0.850	45.00	0.30	170	100		28.9	13.6	479.3	21.5	44.3	1.34
46	0.850	40.00	0.30	190	50		29.5	13.5	478.3	24.5	46.9	1.20
47	0.850	45.00	0.30	200	0		27.0	13.4	478.0	21.2	51.2	1.28
48	0.850	45.00	0.30	250	380		19.6	14.2	480.1	17.5	54.9	1.12
49	0.600	25.00	0.95	350	20		24.9	11.4	475.4	36.8	69.9	0.68
50	0.875	45.00	0.90	76	600		32.4	6.9	489.8	21.3	19.8	1.52
51	0.850	50.00	0.11	105	600		29.0	17.0	486.2	17.1	28.4	1.69
52	0.850	50.00	0.90	120	500		27.8	7.3	485.1	17.9	30.3	1.55
53	0.700	55.00	0.90	160	0		28.6	9.7	478.6	20.3	46.2	1.41
54	0.850	30.00	0.90	165	500		31.6	7.2	483.5	29.7	31.1	1.07
55	0.850	45.00	0.90	180	380		25.3	7.0	481.9	20.1	40.8	1.26
56	1.000	40.00	0.30	139	340		29.3	10.6	482.9	20.4	33.4	1.44

Ex .	Fe ₂ O ₃ (%)	Fe ²⁺ /Fe tot (%)	CeO ₂ (%)	Co (ppm)	Cr ₂ O ₃ (%)	Se (ppm)	TLA4 (%)	TUV4 (%)	λ _D (nm)	TE4 (%)	P (%)	SE
57	0.950	44.00	0.30	140	500		27.2	12.1	484.3	18.1	39.1	1.50
58	0.970	45.00	0.30	150	200		28.0	11.0	481.1	18.4	39.1	1.52
59	1.000	45.00	0.30	170	100		17.6	10.1	479.9	17.6	44.0	1.51
60	1.000	40.00	0.30	190	50		27.1	10.0	479.0	20.5	46.6	1.32
61	0.970	45.00	0.30	200	0		25.1	10.6	478.5	18.0	50.9	1.39
62	0.850	45.00	0.10	160	380		27.8	16.6	481.9	16.6	39.2	1.39
63	0.850	45.00	0.10	140	550		28.2	17.0	484.2	20.0	33.4	1.44
64	0.850	45.00	0.95	140	700		26.3	7.1	486.5	19.5	29.5	1.35
65	0.900	40.00	0.95	140	800		26.7	6.1	488.2	20.9	26.5	1.28
66	0.875	45.00	0.90	150	950		23.1	7.7	488.8	23.1	17.0	1.35
67	0.900	40.00	0.50	237	600		20.0	11.1	482.1	18.7	47.2	1.07
68	0.700	35.00	0.90	5	30		50.0	9.7	485.3	37.8	10.7	1.32
69	0.700	30.00	0.20	34	30		50.0	18.1	481.1	39.7	15.8	1.26
70	0.510	55.00	0.10	165	500		28.0	24.9	481.6	21.6	42.7	1.29
71	0.850	45.00	0.90	280	380		16.4	7.0	479.9	17.1	58.9	0.96
72	0.970	45.00	0.90	200	600		19.9	4.7	483.6	15.1	41.3	1.32
73	0.990	45.00	0.90	220	600		17.8	4.2	483.1	13.9	44.9	1.27
74	0.850	30.00	0.20	48	455		42.9	15.6	490.9	32.8	12.9	1.31
75	0.850	20.00	0.90	200	380		33.4	6.94	481.0	35.8	35.4	0.93
76	0.850	25.00	0.20	180	380		33.8	15.4	481.1	32.6	35.4	1.04
77	0.850	20.00	0.30	180	380		35.6	14.1	481.1	35.9	33.3	0.99
78	0.850	50.00	0.20	140	300		28.1	15.3	481.9	17.9	38.2	1.57
79	0.850	50.00	0.40	150	380		26.5	15.3	482.4	17.3	38.5	1.53
80	0.820	30.00	0.40	100	380		39.2	13.7	482.4	32.7	38.5	1.20
81	0.800	33.00	0.40	80	200		41.6	13.8	482.4	32.9	38.5	1.27
82	0.750	35.00	0.40	50	180		44.4	14.9	482.4	33.9	38.5	1.31
83	0.850	32.00	0.20	40	150		45.3	14.9	482.4	33.5	38.5	1.35
84	0.650	40.00	0.20	20	50		48.0	19.4	482.4	34.7	38.5	1.38
85	0.800	32.00	0.40	15	20		49.2	13.4	482.4	36.5	38.5	1.35
86	0.847	43.34	0.30	139	341		30.5	14.2	482.3	22.2	34.9	1.37
87	0.850	44.00	0.30	140	340	10	27.8	14.1	482.8	20.3	28.3	1.37
88	0.900	45.00	0.30	145	450	30	20.3	13.2	487.6	14.8	14.4	1.38
89	0.850	45.00	0.50	175	500	30	15.3	12.4	485.0	14.0	18.9	1.09

Ex .	Fe ₂ O ₃ (%)	Fe ²⁺ /Fe tot (%)	CeO ₂ (%)	Co (ppm)	Cr ₂ O ₃ (%)	Se (ppm)	TLA4 (%)	TUV4 (%)	λ _D (nm)	TE4 (%)	P (%)	SE
90	1.000	50.00	0.50	190	500		15.0	9.0	482.4	9.8	44.1	1.53
91	1.000	50.00	0.40	156	400	30	15.1	9.7	485.8	8.5	18.4	1.77
92	0.850	45.00	0.70	145	300	20	24.2	9.3	483.2	18.6	22.2	1.30
93	0.900	45.00	0.50	130	0	20	28.6	9.7	479.6	19.8	23.8	1.44
94	0.890	40.00	0.70	100	0	30	33.6	7.3	483.3	24.1	8.8	1.39
95	0.880	50.00	0.90	120	35	25	27.0	5.4	481.6	17.2	18.7	1.57
96	0.900	40.00	0.90	130	0	28	28.4	4.9	479.9	22.4	15.4	1.27
97	0.847	43.34	0.30	139	341		30.5	14.2	482.3	22.2	34.9	1.37
98	0.850	44.00	0.30	140	340	4	29.1	14.1	482.4	21.1	32.5	1.38
99	0.900	45.00	0.20	145	450	7	25.6	14.4	483.8	17.7	30.5	1.44
100	0.850	45.00	0.50	163	500	15	20.8	12.3	484.0	16.8	27.0	1.24
101	1.000	50.00	0.50	180	400	3	16.9	8.7	482.1	10.6	41.4	1.59
102	1.000	50.00	0.40	156	400	6	20.5	9.7	483.2	11.7	35.0	1.75
103	0.850	45.00	0.70	145	300	14	25.6	9.3	482.7	19.4	26.4	1.32
104	0.900	45.00	0.50	130	0	13	30.2	9.7	479.6	20.7	28.7	1.46
105	0.890	40.00	0.90	100	0	15	36.8	4.9	481.7	26.2	18.7	1.40
106	0.880	50.00	0.80	100	550	11	29.7	7.6	489.8	17.2	18.7	1.72
107	0.900	40.00	0.30	130	500	15	27.9	13.2	486.9	20.7	19.5	1.35
108	0.900	40.00	0.30	130	450	15	28.3	13.1	486.1	21.0	20.1	1.35
109	0.900	40.00	0.30	130	400	15	28.7	13.0	485.3	21.3	20.7	1.35
110	0.900	42.00	0.30	130	350	15	28.3	12.9	484.4	20.2	22.0	1.40
111	0.950	45.00	0.40	130	500		27.6	10.9	484.8	17.9	31.4	1.55
112	0.850	44.00	0.40	110	500		31.4	13.3	485.3	21.7	27.6	1.45
113	0.850	50.00	0.40	120	450		28.6	13.2	484.2	17.8	32.2	1.60
114	0.800	50.00	0.30	100	500		30.8	15.7	485.3	19.3	28.3	1.59
115	0.825	40.00	0.80	100	550		33.6	9.1	487.1	25.4	22.9	1.32
116	0.800	45.00	1.00	160	300		28.5	6.8	481.6	22.6	38.1	1.26
117	0.850	45.00	1.00	140	380		28.8	5.8	483.2	21.4	33.4	1.35
118	0.850	45.00	1.00	125	370		30.2	5.8	483.7	21.9	30.8	1.38
119	0.850	45.00	0.95	115	400		30.9	6.4	484.4	22.0	28.8	1.41
120	0.855	25.00	0.95	110	450		38.7	6.4	486.1	34.8	20.1	1.11
121	0.875	45.00	0.50	115	450		30.5	11.4	484.7	20.6	29.2	1.48
122	0.950	50.00	0.40	105	490		28.0	10.9	485.7	15.4	28.9	1.82

Ex .	Fe ₂ O ₃ (%)	Fe ²⁺ /Fe tot (%)	CeO ₂ (%)	Co (ppm)	Cr ₂ O ₃ (%)	Se (ppm)	TLA4 (%)	TUV4 (%)	λ _D (nm)	TE4 (%)	P (%)	SE
123	0.850	59.00	0.40	120	500		24.6	13.3	484.5	11.6	34.8	2.12
124	0.700	64.00	0.40	80	400		29.5	16.6	484.4	14.1	30.9	2.09
125	0.850	65.00	0.50	75	400		27.0	11.9	485.4	9.7	30.0	2.78
126	0.850	60.00	0.40	80	380		28.8	13.1	485.0	12.9	29.6	2.24
127	0.850	42.00	0.30	120	500		31.4	14.5	484.8	22.7	28.9	1.39
128	0.850	43.00	0.30	130	600		29.3	14.7	485.4	21.1	29.8	1.39
129	0.855	40.00	0.30	140	650		29.1	14.7	485.6	22.4	29.9	1.30
130	0.825	45.00	0.30	115	500		31.1	15.1	484.8	21.5	29.1	1.44
131	0.800	45.00	0.30	105	490		32.4	15.6	485.1	22.5	27.5	1.44
132	0.850	45.00	1.00	100	0		35.4	4.9	480.4	35.4	31.2	1.43
133	0.830	45.00	1.35	120	300		31.3	1.9	483.4	23.3	30.0	1.34
134	0.810	47.00	0.10	105	460		31.9	17.7	484.5	21.0	29.1	1.52
135	0.828	41.92	0.29	148	379		31.8	15.3	483.0	23.1	32.8	1.38
136	0.800	40.00	0.90	105	100		37.0	7.5	480.9	28.5	29.3	1.30
137	0.850	45.00	0.30	185	850		21.7	15.2	485.4	16.7	37.1	1.29
138	0.850	46.00	0.30	180	800		22.1	15.1	485.1	16.5	37.2	1.34
139	0.850	45.00	0.80	175	750		22.9	9.0	485.3	18.0	35.4	1.27
140	0.875	47.00	0.10	175	750		22.3	16.9	484.8	15.5	37.8	1.44
141	0.845	35.00	0.80	200	700		25.1	9.0	484.0	24.2	36.9	1.04
142	0.856	40.00	0.30	187	750		24.0	12.5	484.7	20.5	36.4	1.16
143	0.845	35.00	0.80	115	200		36.6	7.9	481.9	29.7	28.2	1.23

CLAIMS

1. Coloured soda-lime glass which comprises the principal glass-forming constituents and colouring agents comprising:

- ♦ iron in a quantity which, expressed in weight of the oxide Fe_2O_3 in relation to the total weight of glass, is greater than or equal to 0.5, and less than or equal to 1.0% (quantity of total iron),
 - ♦ ferrous iron in a quantity which, expressed in weight of atoms of Fe^{2+} in relation to the total weight of iron atoms present in the glass, lies in the range of between 20 and 65% (ratio of $\text{Fe}^{2+}/\text{total Fe}$),
 - ♦ cerium in a quantity which, expressed in weight of CeO_2 in relation to the total weight of glass, is greater than or equal to 0.1%,
 - ♦ titanium in a quantity which, expressed in weight of TiO_2 in relation to the total weight of glass, is greater than or equal to 0% and less than 0.2%,
- and the glass has:
- ♦ a light transmission, measured for illuminant A and calculated for a thickness of 4 mm (TLA4), which lies in the range of between 15 and 55%,
 - ♦ a total transmission in the ultraviolet measured for a thickness of 4 mm (TUV4) of less than or equal to 30%,
 - ♦ a dominant wavelength in transmission (λ_D) of less than or equal to 491 nm.

2. Coloured soda-lime glass according to Claim 1, characterised in that the quantity of total iron is less than or equal to 0.90%.

3. Coloured soda-lime glass according to Claim 2, characterised in that the quantity of total iron is less than or equal to 0.89%.

4. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the quantity of total iron is at least 0.7%.

5. Coloured soda-lime glass according to Claim 4, characterised in that the quantity of total iron is at least 0.75%.

6. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise cerium in a quantity which, expressed in weight of CeO_2 in relation to the total weight of glass, is greater than 0.15%, preferably greater than 0.25%.

5 7. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise cerium in a quantity which, expressed in weight of CeO_2 in relation to the total weight of glass, is greater than 0.10%, preferably less than or equal to 0.50%.

8. Coloured soda-lime glass according to any one of the preceding
10 claims, characterised in that the colouring agents comprise titanium in a quantity which, expressed in weight of TiO_2 in relation to the total weight of glass, is less than 0.15%.

9. Coloured soda-lime glass according to Claim 8, characterised in that the quantity of titanium is less than 0.10%.

15 10. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise cobalt in a quantity which, expressed in weight of Co in relation to the total weight of glass, is greater than 75 ppm.

11. Coloured soda-lime glass according to Claim 10, characterised in
20 that the quantity of cobalt is greater than 100 ppm.

12. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise cobalt in a quantity which, expressed in weight of Co in relation to the total weight of glass, is less than or equal to 350 ppm.

25 13. Coloured soda-lime glass according to Claim 12, characterised in that the quantity of cobalt is less than or equal to 250 ppm.

14. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise chromium in a quantity which, expressed in weight of Cr_2O_3 in relation to the total weight of glass, is at least
30 5 parts per million.

15. Coloured soda-lime glass according to Claim 14, characterised in that the quantity of chromium is greater than or equal to 50 ppm, preferably greater than or equal to 100 ppm.

5 16. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise chromium in a quantity which, expressed in weight of Cr_2O_3 in relation to the total weight of glass, is less than 1000 ppm, preferably less than or equal to 500 ppm.

10 17. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise vanadium in a quantity which, expressed in weight of V_2O_5 in relation to the total weight of glass, is less than 1000 ppm, preferably less than 500 ppm.

15 18. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise selenium in a quantity which, expressed in weight of Se in relation to the total weight of glass, is less than 30 ppm.

19. Coloured soda-lime glass according to Claim 18, characterised in that the quantity of selenium is less than 20 ppm.

20 20. Coloured soda-lime glass according to one of Claims 10 to 13, which comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting essentially of iron, cerium, titanium and cobalt.

21. Coloured soda-lime glass according to one of Claims 10 to 13, which comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting of iron, cerium, titanium and cobalt.

25 22. Coloured soda-lime glass according to one of Claims 14 to 16, which comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting essentially of iron, cerium, titanium, cobalt and chromium.

30 23. Coloured soda-lime glass according to one of Claims 14 to 16, which comprises the principal glass-forming constituents and colouring agents, the colouring agents consisting of iron, cerium, titanium, cobalt and chromium.

24. Coloured soda-lime glass according to any one of the preceding claims, characterised in that the colouring agents comprise ferrous iron in a quantity which, expressed in weight of Fe^{2+} in relation to the total weight of iron atoms present in the glass, lies in the range of between 35 and 55%, preferably between 40 and
5 50%.

25. Coloured soda-lime glass according to any one of the preceding claims, characterised in that it has an energy transmission measured according to the Moon distribution and calculated for a thickness of 4 mm (TE4) of less than 45%.

26. Coloured soda-lime glass according to Claim 25, characterised in
10 that it has a TE4 of less than 35%, preferably less than 25%.

27. Coloured soda-lime glass according to any one of the preceding claims, characterised in that its light transmission (TLA4) lies in the range of between 20% and 45%.

28. Coloured soda-lime glass according to Claim 27, characterised in
15 that its TLA4 lies in the range of between 25 and 35%.

29. Coloured soda-lime glass according to any one of the preceding claims, characterised in that it has a selectivity (SE4) greater than 1.0, preferably greater than 1.1.

30. Coloured soda-lime glass according to any one of the preceding
20 claims, characterised in that it has a total transmission in the ultraviolet, measured for a thickness of 4 mm (TUV4) of less than or equal to 25%.

31. Coloured soda-lime glass according to Claim 30, characterised in that it has a TUV4 of less than or equal to 20%.

32. Coloured soda-lime glass according to any one of the preceding
25 claims, characterised in that it has an excitation purity in transmission greater than 10%.

33. Coloured soda-lime glass according to Claim 32, characterised in that it has an excitation purity in transmission greater than 15%.

34. Coloured soda-lime glass according to any one of the preceding
30 claims, characterised in that its dominant wavelength in transmission λ_D is less than or equal to 489 nm.

35. Coloured soda-lime glass according to Claim 34, characterised in that its dominant wavelength in transmission is less than or equal to 487 nm.

36. Coloured soda-lime glass according to any one of the preceding claims, characterised in that it is covered by a layer.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 02/13965

A. CLASSIFICATION OF SUBJECT MATTER		
IPC 7 C03C3/095 C03C4/02 C03C4/08		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) IPC 7 C03C		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, PAJ		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 99 05069 A (LIBBEY OWENS FORD CO) 4 February 1999 (1999-02-04) claims; tables ---	1-10, 14-36
X	EP 0 745 566 A (NIPPON SHEET GLASS CO LTD) 4 December 1996 (1996-12-04) page 5, line 5 - line 10; claims 1-6 ---	1-36
X	US 5 897 956 A (KAMEI FUMIO ET AL) 27 April 1999 (1999-04-27) example 5 ---	1-36
A	US 5 830 814 A (COMBES JEAN-MARIE) 3 November 1998 (1998-11-03) example 18 ---	1-36
	-/--	
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the International filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *&* document member of the same patent family		
Date of the actual completion of the international search 13 February 2003		Date of mailing of the international search report 20/02/2003
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Reedijk, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/13965

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 811 581 A (NIPPON SHEET GLASS CO LTD) 10 December 1997 (1997-12-10) table 2 ---	1-36
P, X	WO 01 98221 A (FOGUENNE MARC ;GLAVERBEL (BE); COSTER DOMINIQUE (BE); DELMOTTE LAU) 27 December 2001 (2001-12-27) claims 1-16 -----	1-36

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 02/13965

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date
WO 9905069	A	04-02-1999	AU 744695 B2	28-02-2002
			AU 8580198 A	16-02-1999
			BR 9806064 A	31-08-1999
			EP 0928285 A1	14-07-1999
			JP 2001500836 T	23-01-2001
			WO 9905069 A1	04-02-1999
			US 5994249 A	30-11-1999
<hr/>				
EP 0745566	A	04-12-1996	DE 69600538 D1	24-09-1998
			DE 69600538 T2	28-01-1999
			EP 0745566 A1	04-12-1996
			JP 9048635 A	18-02-1997
			US 6017836 A	25-01-2000
<hr/>				
US 5897956	A	27-04-1999	AU 696443 B2	10-09-1998
			AU 3441595 A	09-05-1996
			CA 2161379 A1	27-04-1996
			CN 1128737 A , B	14-08-1996
			DE 69507421 D1	04-03-1999
			EP 0709344 A1	01-05-1996
			JP 3190965 B2	23-07-2001
			JP 8208266 A	13-08-1996
			US 5723390 A	03-03-1998
			ZA 9509079 A	22-05-1996
<hr/>				
US 5830814	A	03-11-1998	FR 2699526 A1	24-06-1994
			BR 9305947 A	21-10-1997
			CA 2130447 A1	07-07-1994
			CN 1092044 A , B	14-09-1994
			CZ 9402025 A3	12-04-1995
			DE 69328170 D1	27-04-2000
			DE 69328170 T2	16-11-2000
			EP 0629179 A1	21-12-1994
			ES 2145820 T3	16-07-2000
			WO 9414716 A1	07-07-1994
			JP 3325893 B2	17-09-2002
			JP 8500811 T	30-01-1996
			PT 629179 T	29-09-2000
			RU 2123479 C1	20-12-1998
<hr/>				
EP 0811581	A	10-12-1997	JP 9328332 A	22-12-1997
			DE 69715516 D1	24-10-2002
			EP 0811581 A1	10-12-1997
			US 2001021685 A1	13-09-2001
<hr/>				
WO 0198221	A	27-12-2001	AU 6753901 A	02-01-2002
			WO 0198221 A1	27-12-2001