

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
31 July 2003 (31.07.2003)

PCT

(10) International Publication Number  
**WO 03/061908 A1**

(51) International Patent Classification<sup>7</sup>: **B24C 11/00**,  
A61C 3/025, 3/06

(21) International Application Number: PCT/EP02/10692

(22) International Filing Date:  
24 September 2002 (24.09.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
020038 24 January 2002 (24.01.2002) IE

(71) Applicant (for all designated States except US): **EXA SA**  
[CH/CH]; 17, rue des Pierres du Niton, CH-1207 Geneva  
(CH).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **ROCHAT, Pierre**  
[CH/CH]; 18, chemin de la Haute Belotte, CH-1222  
Geneva (CH).

(74) Agent: **MURGITROYD & COMPANY**; Scotland  
House, 165-169 Scotland Street, Glasgow G5 8PL (GB).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.


(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A PROCESS FOR TREATING A SURFACE



(57) Abstract: A process for treating a surface (2) to clean or otherwise treat the surface (2) comprises a step of contacting the surface (2) with a particulate treating agent such that at least some of the particles (1) roll along at least a portion of the surface (2), wherein an angle of incidence of the particles (1) and the surface is between 0° and 60°. The particles (1) are dimensioned to effect a rolling movement along the surface (2). The treating agent is substantially non-aqueous. The particles (1) comprise a precipitate or agglomerate of an insoluble alkali metal carbonate. The process comprises a blasting operation or a manual application. The use of the process of the invention in dental applications such as teeth whitening and plaque removal, treating bone, and skin exfoliation, is also disclosed. Also disclosed is a treating agent which comprises a plurality of particles (1), the particles (1) being dimensioned to effect a rolling movement along a surface (2), wherein the treating agent is substantially non-aqueous.



WO 03/061908 A1

## A Process for Treating a Surface

### Technical Field

The invention relates to a process for treating a surface to clean or otherwise treat the surface, the process being of the type which employs a treating agent comprising a plurality of particles.

### Background

Cleaning of the surfaces of various types of equipment and structures is often desirable. Numerous processes and cleaning agents are known in the art. The choice of process and agent depends to a great extent on the coating to be removed and on the substrate. In addition, the working conditions and the environmental effects of the process and agent used are becoming increasingly important factors when selecting an optimal cleaning technique.

Sand blasting and other abrasive techniques are quite applicable on hard substrates, but require special arrangements to meet the specification related to environment and working conditions.

Less hard and durable substrates like aluminium, wood and composite materials require processes and cleaning agents which do not cause mechanical or chemical damage to the surface of the substrate.

International Patent Application No PCT/N093/00137 in the name of Norsk Hydro A.S discloses a wet blasting process which employs an aqueous slurry of precipitated, non-soluble, calcium carbonate. The use of such aqueous wet blasting agents has a number of disadvantages. The aqueous blasting slurries have a tendency to freeze when used in countries where severe winters are encountered. Further, the presence of water in blasting slurries can have the effect of contributing to erosion of the surface being cleaned. This problem is particularly acute when the surface being cleaned forms part of a structure or building. Moreover, the use of aqueous blasting slurries to treat surfaces having electrical components can be particularly hazardous and can cause corrosion.

It is an object of the invention to overcome at least some of the above disadvantages.

Statements of Invention

According to the invention, there is provided a process for treating a surface to clean or otherwise treat the surface, the process being of the type which employs a treating agent comprising a plurality of particles, the process comprising the step of contacting the surface with the treating agent such that at least some of the particles roll along at least a portion of the surface, wherein an angle of incidence of the particles and the surface is between 0° and 60°, wherein the particles are dimensioned to effect a rolling movement along the surface, and wherein the treating agent is preferably substantially non-aqueous.

In this specification, the term "substantially non-aqueous" as applied to treating agents should be understood as meaning treating agents having less than 5% water. A minimal amount of water is often included in the treating agent to minimise the production of dust.

In one embodiment of the invention, the treating agent comprises less than 5% water, suitably less than 4% water, typically less than 3% water, preferably less than 2% water, and ideally less than 1% water.

When the projected particle impacts the substrate at a low angle of incidence it rolls along the surface, rubbing and absorbing the coating from the surface.

In one embodiment of the invention, the treating agent includes a non-aqueous solvent such as, for example, an alcohol.

In a preferred embodiment of the invention, the particles are non-crystalline.

In one preferred embodiment of the invention, the particles comprise a precipitate or agglomerate of an insoluble alkali metal salt. Typically, the salt is a carbonate. Suitably the metal is calcium or magnesium.

Preferably, the particles are generally round. In this specification the term "generally round" as applied to particles should be understood to mean any shape which of particle which enables the particle to easily assume a rolling motion when moved along a surface. As such, while the term is primarily intended to refer to spherical particles, it is not intended to exclude other types of spheroids such as spheres having an oblong or elliptical shape. Typically, the particles will have an irregular surface configuration.

Ideally, the particles are relatively soft. Generally, the particles have an average hardness of less than 10 Mohs, typically less than 8 Mohs, and preferably less than 6 Mohs. Typically, the particles will have an average hardness of at least 1 Mohs, and preferably of at least 2 Mohs. In a

preferred embodiment of the invention, the particles will have an average hardness of about 3 Mohs. Typically, the particles have an average maximum diameter of between 30 and 1000 microns.

The process of the invention may be a blasting operation or a manual rubbing operation.

When the process of the invention is a blasting operation, various means of blasting are envisaged, such as for example, mechanical projection (i.e. centrifugal particle acceleration), pneumatic particle projection and electrostatic particle projection. A mechanical particle projecting device which is suitable for carrying out the process of the invention is described in published International Patent Application No PCT/EP00/09960. Generally speaking, dry blasting is envisaged. However, in certain circumstances wet blasting may be appropriate whereby a wet component of the treating agent is non-aqueous. Such a wet component may be a non-aqueous solvent such as, for example, an alcohol.

When the process of the invention involves manual projection of the particles along the surface, the particles may be rubbed along the surface using a cloth, by hand, or by any other means such as, for example, a mechanical polishing, brushing or rubbing apparatus or the like.

The invention also relates to the use of the process of the invention in dental applications such as teeth whitening, plaque removal and general cleaning or polishing of the teeth, buccal cavity, and prosthetic parts such as crowns, bridges and complete or partial dentures. As such, the process may involve either blast application using some form of particle accelerator, or manual application, of the treating agent. Manual application includes conventional brushing, rubbing, polishing or the like.

The invention also relates to the use of the process of the invention in treating bone.

The invention also relates to the use of the process of the invention in cosmetic application. Thus, the process may be employed to remove skin in, for example, an exfoliating application.

The invention also relates to the use of the process of the invention in treating automobiles, bikes, aeroplanes, boats, casting dies, machines and parts thereof. In addition, the process may be utilised in treating and/or maintaining equipment in petrochemical, chemical and food production facilities.

The invention also relates to an agent for treating a surface to clean or otherwise treat the surface, the agent being of the type comprising a plurality of particles, the particles comprising a precipitate

or agglomerate of an insoluble alkali metal salt, wherein the treating agent is preferably substantially non-aqueous. Typically, the salt is a carbonate. Suitably the metal is calcium or magnesium.

The invention also relates to the use of a treating agent of the invention in dental applications.

The invention also relates to the use of a treating agent of the invention to treat bone.

The invention also relates to the use of a treating agent of the invention in cosmetic applications, such as, for example, to remove skin.

The use of substantially non-aqueous treating agents has a number of advantages. Aqueous treating agents such as blasting slurries have a tendency to freeze when used in countries where severe winters are encountered. Further, the presence of water in blasting slurries can have the effect of contributing to erosion of the surface being cleaned. This problem is particularly acute when the surface being cleaned forms part of a structure or building. Moreover, the use of aqueous blasting slurries to treat surfaces having electrical components can be particularly hazardous due to corrosion. Use of the process and treating agents of the invention obviates these problems.



Use of the process of the invention has the effect of removing coatings without damaging the surface of the substrate. It should also be possible to clean complete structures and equipment having complex geometrical configurations such as valves, bridges, bearings, ballbearings etc having parts which are difficult to access with conventional cleaning equipment or conventional blasting jets.

After having cleaned or otherwise treated the substrate according to the process of the invention the treating agent is easily removed together with the removed coating. The cleaning agent itself is environmentally acceptable.

#### Brief Description of the Drawings

The invention will be more clearly understood from the following description of some embodiments thereof, given by way of example only, with reference to the following figures in which:

Fig 1 is an illustration of a particle of a treating agent according to the invention; and

Fig 2 illustrates the process of the invention.

#### Detailed Description

The present invention has been found to be effective at removing various types of coatings from

substrates having hardness from that of steel to wood (or even softer materials) without causing damage to the substrates surface. The treating agent can easily be removed by flushing with water or compressed air. The person carrying out the cleaning process is not exposed to any harm and the agent is acceptable from an environmental point of view. The agent is also available in desired qualities, particle size, hardness etc.

Referring to the drawings, and initially to Fig 1, there is illustrated a particle, indicated generally by the reference numeral 1, which is used in the process of the invention. The particle is a particle of precipitated calcium carbonate and has a generally round, and slightly irregular, shape and a rough, irregular, surface configuration.


Referring to Fig 2, the process of the invention is illustrated in which the particle 1 is projected towards a surface 2 having a coating 3 to be removed. Due to the low angle of incidence of the particle 1 and the surface 2, and the generally round shape of the particle 1, upon impact the particle 1 rolls along the surface, rubbing the surface and absorbing the coating 3 onto a surface of the particle. This has the net effect of removing the coating from the surface without causing any damage to the surface.

#### Example 1

Method of production of particles.

Production of insoluble particles  $\text{CaCO}_3$  is carried out by providing free  $\text{Ca}^{++}$  in a liquid with a PH over 7 by dissolving calcium oxide in water.

Addition of  $\text{CO}_2$  results in the precipitation  $\text{CaCO}_3$ .



Various other methods of production of particles forming part of treating agents according to the invention have been investigated using various types of substrates including plastic, metal and polymer. Examples of these methods include:

#### Chemical

There are numerous chemical methods for producing spherical powders. Generally, chemical methods result in very fine powder particle sizes. Such methods include Sol Gel, chemical precipitation, Reaction, reduction (hydrogen in an autoclave to reduce metal salts to the metal), decomposition (eg metal carbonyls) and Electrolysis.

#### Spray drying

This is the most widely used industrial process involving particle formation and drying. It is highly suited for the continuous production of dry solids in either powder, granulate or agglomerate

form from liquid feedstocks as solutions, emulsions and pumpable suspensions.

### Agglomeration

The most common method of agglomeration is where the constituents are physically mixed together with an organic binder. The solvent is then driven off and the resultant material sized. The binder should be burnt off during spraying. This process is used in the manufacture of NiAl, AlSi or polyester powders. The most common method of agglomeration is where the constituents are physically mixed together with an organic binder. The solvent is then driven off and the resultant material sized. The binder should be burnt off during spraying. This process is used in the manufacture of NiAl, AlSi-polyester powders. The use of spray drying has become another common method for the agglomeration of powders. Here, a slurry is formed with the constituents and this is then fed into a rotary spray head. Here, the slurry forms an atomised cloud which is solidified by an opposing warm air stream to produce a powder. This method is used for ceramics such as zirconia and cermets such as WC-cobalt. The powder is largely spherical but in the as spray dried state can be porous and friable. The material is often densified and stabilised by sintering and/or spray densification.

There are also methods of mechanical agglomeration (eg the Hosakawa method) where for example a hard

constituent is mechanically driven into a softer matrix particle to form a composite powder. Indeed, simple ball grinding can be used to mechanically alloy two or more constituents together. Although sintering can be used as part of the spray drying process it can also be used alone as a method to manufacture powders. The constituents are mixed together and heated to get some solid state diffusion going and then the resultant product is crushed. A number of repeated cycles can be used to promote further alloying in which case the powder is called a "reacted" powder.

#### Atomisation

There are a number of atomisation techniques which all rely on the production of a molten pool as the source. Atomisation methods include Rotating Electrode, Vibrating Electrode (arc), Centrifugal (from a melt) and Rapid Solidification (eg aluminium ribbon). However, by far the most commonly used methods are either water or gas atomisation.

#### Others

- Solid State Reduction
- Electrolysis
- Electrodeposition
- Mechanical Comminution

As described above, the process of the invention may be carried out using some form of particle

accelerator, such as that described in International Patent Application No PCT/EP00/09960 and using the operational parameters described in this Application, or by means of manual treatment of a surface.

The invention is not limited to the embodiments hereinbefore described which may be varied in both construction and process step without departing from the invention.

1     Claims

2

3     1. A process for treating a surface to clean or  
4     otherwise treat the surface, the process being of  
5     the type which employs a treating agent comprising a  
6     plurality of particles, the process comprising the  
7     step of contacting the surface with the treatment  
8     agent such that at least some of the particles roll  
9     along at least a portion of the surface, wherein an  
10    angle of incidence of the particles and the surface  
11    is between 0° and 60°, wherein the particles are  
12    dimensioned to effect a rolling movement along the  
13    surface, and wherein the treating agent is  
14    substantially non-aqueous.

15

16    2. A process as claimed in Claim 1, in which the  
17    particles are non-crystalline.

18

19    3. A process as claimed in Claim 1 or 2 in which the  
20    particles comprise a precipitate or agglomerate of  
21    an insoluble alkali metal carbonate.

22

23    4. A process as claimed in any preceding Claim in  
24    which the particles are generally round.

25

26    5. A process as claimed in any preceding Claim which  
27    is a blasting operation.

28

29    6. A process as claimed in any of Claims 1 to 4  
30    which employs manual application of the treating  
31    agent.

32

1     7. The use of the process of the invention in dental  
2     applications such as teeth whitening, plaque removal  
3     and general cleaning or polishing of the teeth,  
4     buccal cavity and prosthetic parts such as crowns,  
5     bridges and complete or partial dentures.

6

7     8. The use of the process of the invention in  
8     treating bone.

9

10    9. The use of the process of the invention to  
11    exfoliate skin.

12

13    10. An agent for treating a surface to clean or  
14    otherwise treat the surface, the agent being of the  
15    type comprising a plurality of particles, the  
16    particles being dimensioned to effect a rolling  
17    movement along a surface, wherein the treating agent  
18    is substantially non-aqueous.

19

20    11. A treating agent according to Claim 10 in which  
21    the particles comprise a precipitate or agglomerate  
22    of an insoluble alkali metal carbonate,

23

24    12. A treating agent according to Claim 10 or 11,  
25    wherein the particles are non-crystalline

26

27    13. A treating agent according to any of Claims 10  
28    to 12 for use in dental applications such as teeth  
29    whitening, plaque removal and general teeth  
30    cleaning.

31





1     14. A treating agent according to any of Claims 10  
2     to 12 for use in treating bone.

3

4     15. A cleaning agent according to any of Claims 10  
5     to 12 for use exfoliating skin.

6

Fig. 1Fig. 2

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/10692

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B24C11/00 A61C3/025 A61C3/06

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B24C B24B A61C A61B A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 00 51787 A (GAGEMARK LIMITED) 8 September 2000 (2000-09-08) page 1, line 1-10 page 6, line 33-36 page 13, line 21-30	1, 3-5, 10, 11
A	---	18
A	WO 94 07658 A (NORSK HYDRO) 14 April 1994 (1994-04-14) page 1, line 1-25 page 3, line 18 -page 4, line 11 page 5, line 23-44; figure 6	1-5, 10-12
A	US 5 827 114 A (YAM) 27 October 1998 (1998-10-27) column 5, line 35-38 column 5, line 52-57; figure 1 --- -/--	1, 5, 10



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

° Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&amp;\* document member of the same patent family

Date of the actual completion of the international search

4 February 2003

Date of mailing of the international search report

11/02/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Matzdorf, U

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/10692

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6 287 180 B1 (HERTZ) 11 September 2001 (2001-09-11) column 1, line 15-63; claim 2 ---	1,3,5-7, 10,13
A	US 5 984 678 A (BRUNS) 16 November 1999 (1999-11-16) abstract column 4, line 60-64 ---	1,3,5,7, 10,11,13
A	US 2001/023351 A1 (EILERS) 20 September 2001 (2001-09-20) abstract page 3, right-hand column, line 20-45 ---	1,6,9, 10,15
A	US 5 456 628 A (CSABAI) 10 October 1995 (1995-10-10) column 1, line 46-55 ---	1,10
A	US 2 796 338 A (RICHARD HABERL) 18 June 1957 (1957-06-18) column 2, line 9-37 -----	1,10

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/10692

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0051787	A	08-09-2000	AU 2925400 A EP 1075352 A1 WO 0051787 A1	21-09-2000 14-02-2001 08-09-2000
WO 9407658	A	14-04-1994	NO 923725 A AU 5119693 A WO 9407658 A1	28-03-1994 26-04-1994 14-04-1994
US 5827114	A	27-10-1998	NONE	
US 6287180	B1	11-09-2001	US 2002002030 A1 US 6126639 A	03-01-2002 03-10-2000
US 5984678	A	16-11-1999	US 5810587 A	22-09-1998
US 2001023351	A1	20-09-2001	AU 2055901 A WO 0139675 A1	12-06-2001 07-06-2001
US 5456628	A	10-10-1995	AT 158216 T AU 5147293 A CA 2132220 A1 WO 9408755 A1 DE 69314046 D1 DE 69314046 T2 DK 663863 T3 EP 0663863 A1 ES 2107683 T3 GR 3025642 T3	15-10-1997 09-05-1994 28-04-1994 28-04-1994 23-10-1997 30-04-1998 27-04-1998 26-07-1995 01-12-1997 31-03-1998
US 2796338	A	18-06-1957	NONE	