



(22) Date de dépôt/Filing Date: 2009/06/29

(41) Mise à la disp. pub./Open to Public Insp.: 2010/01/08

(30) Priorité/Priority: 2008/07/08 (EP08159917.7)

(51) Cl.Int./Int.Cl. *C08C 19/08* (2006.01),
C08C 19/28 (2006.01)

(71) Demandeur/Applicant:
LANXESS DEUTSCHLAND GMBH, DE

(72) Inventeurs/Inventors:
MULLER, JULIA MARIA, DE;
NUYKEN, OSKAR, DE;
OBRECHT, WERNER, DE

(74) Agent: OGILVY RENAULT LLP/S.E.N.C.R.L.,S.R.L.

(54) Titre : SYSTEMES CATALYSEURS ET LEUR APPLICATION AUX REACTIONS DE METATHESE

(54) Title: CATALYST SYSTEMS AND THEIR USE FOR METATHESIS REACTIONS

(57) **Abrégé/Abstract:**

A novel process for reducing the molecular weight of nitrile rubber in the presence of specific catalyst systems containing the metathesis catalyst and also a specific addition of fluorine-containing boron compounds is provided.

ABSTRACT

Catalyst systems and their use for metathesis reactions


A novel process for reducing the molecular weight of nitrile rubber in the presence of specific catalyst systems containing the metathesis catalyst and also a specific addition of fluorine-containing boron compounds is provided.

Catalyst systems and their use for metathesis reactions

The present invention relates to catalyst systems, their use for the catalysis of metathesis reactions and in particular a process for reducing the molecular weight of nitrile rubber by metathesis using these catalysts systems.

Metathesis reactions are used widely in chemical syntheses, e.g. in ring-closing metathesis (RCM), cross-metathesis (CM), ring-opening metathesis (ROM), ring-opening metathesis polymerizations (ROMP), cyclic diene metathesis polymerizations (ADMET), self-metathesis, reaction of alkenes with alkynes (enyne reactions), polymerization of alkynes and olefinization of carbonyls (WO-A-97/06185 and Platinum Metals Rev., 2005, 49(3), 123-137). Metathesis reactions are employed, for example, for the synthesis of olefins, for the ring-opening polymerization of norbornene derivatives, for the depolymerization of unsaturated polymers and for the synthesis of telechelic polymers.

Metathesis catalysts are known, inter alia, from WO-A-96/04289 and WO-A-97/06185. They have the following basic structure:



where M is osmium or ruthenium, the radicals R are identical or different organic radicals having a wide range of structures, X^1 and X^2 are anionic ligands and L is in each case an uncharged electron donor. The customary term "anionic ligands" is always used in the literature concerning such metathesis catalysts to describe ligands which, when viewed as removed from the metal centre, are negatively charged when they have a closed electron shell.

Metathesis reactions have recently also become increasingly important for the degradation of nitrile rubbers.

The term nitrile rubber, also referred to as "NBR" for short, refers to rubbers which are copolymers or terpolymers of at least one α,β -unsaturated nitrile, at least one conjugated diene and, if appropriate, one or more further copolymerizable monomers.

Hydrated nitrile rubber, also referred to as "HNBR" for short, is produced by hydration of nitrile rubber. Accordingly, the C=C double bonds of the copolymerized diene units are completely or

partly hydrated in HNBR. The degree of hydration of the copolymerized diene units is usually in the range from 50 to 100%. Hydrated nitrile rubber is a speciality rubber which has very good heat resistance, excellent resistance to ozone and chemicals and also an excellent oil resistance.

5 The abovementioned physical and chemical properties of HNBR are combined with very good mechanical properties, in particular a high abrasion resistance. For this reason, HNBR has found wide use in a wide variety of applications. HNBR is used, for example, for seals, hoses, belts and damping elements in the automobile sector, also for stators, well seals and valve seals in the field of oil production and also for numerous parts in the aircraft industry, the electrical industry,
10 machine construction and shipbuilding.

Most commercially available HNBR grades usually have a Mooney viscosity (ML 1+4 at 100°C) in the range from 55 to 120, which corresponds to a number average molecular weight M_n (determination method: gel permeation chromatography (GPC) against polystyrene standards) in
15 the range from about 200 000 to 700 000. The polydispersity indices PDI ($PDI = M_w / M_n$, where M_w is the weight average molecular weight and M_n is the number average molecular weight), which indicate the width of the molecular weight distribution, measured here frequently have a value of 3 or above. The residual double bond content is usually in the range from 0 to 18% (determined by NMR or IR spectroscopy). However, the term "fully hydrated grades" is used in
20 the technical field when the residual double bond content is not more than about 0.9%.

The processability of HNBR grades having the abovementioned relatively high Mooney viscosities is subject to limitations. For many applications, it is desirable to have HNBR grades which have a lower molecular weight and thus a lower Mooney viscosity, since this significantly improves the
25 processability.

Many attempts have been made in the past to shorten the chain length of HNBR by degradation. For example, it is possible to reduce the molecular weight by thermomechanical treatment (mastication), e.g. on a roll mill or also in a screw apparatus (EP A-0 419 952). However, this
30 thermomechanical degradation has the disadvantage that functional groups such as hydroxyl, keto, carboxylic acid and ester groups are built into the molecule as a result of partial oxidation and, in addition, the microstructure of the polymer is substantially altered.


The preparation of HNBR having low molar masses, corresponding to a Mooney viscosity (ML 1+4 at 100°C) in the range below 55 or a number average molecular weight M_n of
35 < 200 000 g/mol, has for a long time not been possible by means of established production processes since, firstly, a step increase in the Mooney viscosity occurs in the hydration of NBR

and, secondly, the molar mass of the NBR feedstock used for the hydration cannot be reduced at will since otherwise processing in the available industrial plants is no longer possible because of excessive high stickiness. The lowest Mooney viscosity of an NBR feedstock which can be processed without difficulties in an established industrial plant is about 30 Mooney units (ML 1+4 at 100°C). The Mooney viscosity of the hydrated nitrile rubber obtained from such an NBR feedstock is in the order of 55 Mooney units (ML 1+4 at 100°C). The Mooney viscosity is determined in accordance with ASTM Standard D 1646.

In the more recent prior art, this problem is solved by reducing the molecular weight of the nitrile rubber by degradation to a Mooney viscosity (ML 1+4 at 100°C) of less than 30 Mooney units or a number average molecular weight M_n of $< 70\,000$ g/mol before hydration. The decrease in the molecular weight is achieved by metathesis in which low molecular weight 1-olefins are usually added. The metathesis of nitrile rubber is described, for example, in WO-A-02/100905, WO-A-02/100941 and WO-A-03/002613. The metathesis reaction is advantageously carried out in the same solvent as the hydration reaction so that the degraded nitrile rubber does not have to be isolated from the solvent after the degradation reaction is complete before it is subjected to the subsequent hydration. The metathesis degradation reaction is catalysed using metathesis catalysts which are tolerant to polar groups, in particular nitrile groups.

WO-A-02/100905 and WO-A-02/100941 describe a process which comprises the degradation of nitrile rubber starting polymers by olefin metathesis and subsequent hydration to give HNBR having a low Mooney viscosity. Here, a nitrile rubber is reacted in a first step in the presence of a coolefin and specific complex catalysts based on osmium, ruthenium, molybdenum or tungsten and hydrated in a second step. In this way, it is possible to obtain hydrated nitrile rubbers having a weight average molecular weight (M_w) in the range from 30 000 to 250 000, a Mooney viscosity (ML 1+4 at 100°C) in the range from 3 to 50 and a polydispersity index PDI of less than 2.5.

For the metathesis of nitrile rubber, it is possible to use, for example, the catalyst bis(tricyclohexylphosphine)benzylidene ruthenium dichloride shown below.



Grubbs (I) catalyst

After metathesis and hydration, the nitrile rubbers have a lower molecular weight and a narrower


molecular weight distribution than the hydrated nitrile rubbers which could hitherto be prepared according to the prior art.

However, the amounts of Grubb (I) catalyst employed for carrying out the metathesis are large. In the experiments in WO-A-03/002613, they are, for example, 307 ppm and 61 ppm of Ru based on the nitrile rubber used. The reaction times necessary are also long and the molecular weights after degradation are always still relatively high (see Example 3 of WO-A-03/002613, in which $M_w = 180\,000$ g/mol and $M_n = 71\,000$ g/mol).

US 2004/0127647 A1 describes blends based on low molecular weight HNBR rubbers having a bimodal or multimodal molecular weight distribution and vulcanizates of these rubbers. According to the examples, the metathesis is carried out using 0.5 phr of Grubbs I catalyst. This corresponds to an amount of 614 ppm of ruthenium based on the nitrile rubber used.

Furthermore, WO-A-00/71554 discloses a group of catalysts which are referred to in the art as "Grubbs (II) catalysts".

If such a "Grubbs (II) catalyst", e.g. the catalyst 1,3-bis(2,4,6-trimethylphenyl)-2-imidazolidenylidene)(tricyclohexylphosphine)(phenylmethylene)ruthenium dichloride shown below, is used for the NBR metathesis (US-A-2004/0132891), this can be carried out successfully without use of a coolefin.



Grubbs (II) catalyst

After the subsequent hydration, which is preferably carried out in the same solvent, the hydrated nitrile rubber has lower molecular weights and a narrower molecular weight distribution (PDI) than when catalysts of the Grubbs (I) type are used. The metathetic degradation using catalysts of the Grubbs (II) type thus proceeds more efficiently in respect of the molecular weight and the molecular weight distribution than when using catalysts of the Grubbs (I) type. However, the amounts of ruthenium necessary for this efficient metathetic degradation are still relatively high. In addition, long reaction times are still required for carrying out the metathesis using the Grubbs (II) catalyst.


In all the abovementioned processes for the metathetic degradation of nitrile rubber, relatively large amounts of catalyst have to be used and long reaction times are required in order to prepare the desired low molecular weight nitrile rubbers by means of metathesis.

5

In the other types of metathesis reactions, too, the activity of the catalysts used is of critical importance.

In *J.Am.Chem. Soc.* 1997, 119, 3887-3897, it is stated that in the ring-closing metathesis of diethyl diallylmalonate shown below,

10



the activity of the catalysts of the Grubbs (I) type can be increased by additions of CuCl and CuCl₂. This activity increase is explained by a shift in the dissociation equilibrium as a result of which a phosphane ligand which has been released reacts with copper ions to form copper-phosphane complexes.

15

However, this activity increase brought about by copper salts in the ring-closing metathesis mentioned cannot be applied at will to other types of metathesis reactions. Our own studies have shown that although the addition of copper salts leads to an initial acceleration of the metathetic degradation of nitrile rubbers, a significant worsening of the efficiency of the metathesis is then unexpectedly observed: the molecular weights of the degraded nitrile rubbers which are ultimately achieved are substantially higher than when the metathesis reaction is carried out in the presence of the same catalyst but in the absence of the copper salts.

20

EP-A-1 825 913 describes new catalyst systems for metathesis, in which not only the actual metathesis catalyst but also one or more salts are used. This combination of one or more salts with the metathesis catalyst leads to an increase in the activity of the catalyst, a synergistic effect. The anions and cations of these salts can have a large number of meanings which can be selected from various lists. In the examples of EP-A-1 825 913, the use of lithium bromide is found to be particularly advantageous both for the metathetic degradation of rubbers such as nitrile rubbers and also for the ring-closing metathesis of diethyl diallylmalonate. Catalysts mentioned are, in particular, ones which coordinate via an oxygen-, nitrogen- or sulphur-containing substituent to the metal centre of a ruthenium- or osmium-carbene. Use is made of, for example, the Grubbs (II)

25

30

catalyst, the Hoveyda catalyst, the Buchmeiser-Nuyken catalyst and the Grela catalyst.

5 An as yet unpublished German patent application describes specific catalyst systems for metathesis, which comprise not only the actual metathesis catalyst but also alkaline earth metal chlorides, preferably magnesium or calcium chloride, as added salts.

EP-A-1 894 946 describes an increase in activity of metathesis catalysts as a result of specific phosphane additions.

10 The increase in activity of metathesis catalysts brought about by salts has likewise been studied in **Inorganica Chimica Acta 359 (2006) 2910-2917**. The influences of tin chloride, tin bromide, tin iodide, iron(II) chloride, iron(II) bromide, iron(III) chloride, cerium(III) chloride*7H₂O, ytterbium(III) chloride, antimony trichloride, gallium dichloride and aluminium trichloride on the self-metathesis of 1-octene to form 7-tetradecene and ethylene were examined. When using the
15 Grubbs (I) catalyst, a significant improvement in the conversion to 7-tetradecene was observed when tin chloride or tin bromide was added (Table 1; catalyst 1). Without addition of salt, a conversion of 25.8% was achieved; when SnCl₂*2H₂O was added, the conversion rose to 68.5% and when tin bromide was added it rose to 71.9%. Addition of tin iodide resulted in a significant decrease in the conversion from 25.8% to 4.1%. In combination with the Grubbs (II) catalyst
20 (Table 1; catalyst 2), on the other hand, all three tin salts led to only slight improvements in yield from 76.3% (reference experiment without addition) to 78.1% (SnCl₂), to 79.5% (SnBr₂) and 77.6% (SnI₂). When "phobcat" [Ru(phobCy)₂Cl₂(= ChPh)] is used (Table 1; catalyst 3), the conversion is decreased from 87.9% to 80.8% by addition of SnCl₂, to 81.6% by SnBr₂ and to 73.9% by SnI₂. When iron(II) salts are used in combination with the Grubbs (I) catalyst (Table 3;
25 catalyst 1), the increase in conversion when using iron(II) bromide is higher than when using iron(II) chloride. It may be remarked that, regardless of the type of catalyst used, the conversion when bromides are used is always higher than when the corresponding chlorides are used.

30 However, the use of tin or iron(II) bromide described in **Inorganica Chimica Acta 359 (2006) 2910-2917** is not an optimal solution for the preparation of nitrile rubbers because of the corrosive nature of the bromides.

35 In the preparation of hydrated nitrile rubbers, the solvent is usually removed by steam distillation after the hydration. If tin salts are used as part of the catalyst system, amounts of these tin salts get into the wastewater which therefore has to be subjected to costly purification. For this reason, the use of tin salts for increasing the activity of catalysts in the preparation of nitrile rubbers is not advisable from an economic point of view.

The use of iron salts is restricted by the fact that they reduce the capacity of some ion-exchange resins which are usually employed for recovering the noble metal compounds used in the hydration. This likewise adversely affects the economics of the overall process.

5

ChemBioChem 2003, 4, 1229-1231 describes the synthesis of polymers by a ring-opening metathesis polymerization (ROMP) of norbornyl oligopeptides in the presence of a ruthenium-carbene complex $\text{Cl}_2(\text{PCy}_3)_2\text{Ru}=\text{CHphenyl}$, with lithium chloride being added. The addition of lithium chloride is carried out with the declared objective of avoiding aggregation and increasing the solubility of the growing polymer chains. Nothing is said about an activity-increasing effect of the addition of the salt on the catalyst.

10

A method of carrying out a ring-opening polymerization of oligopeptide-substituted norbornenes is also known from **J. Org. Chem.** 2003, 68, 2020-2023, in which lithium chloride is used. Here too, the influence of lithium chloride as solubility-increasing additive for the peptides in nonpolar organic solvents is emphasized. For this reason, an increase in the degree of polymerization "DP" can be achieved by the addition of lithium chloride.

15

In **J. Am.Chem.Soc.** 1997, 119, 3887-3897 it is stated that when LiBr or NaI is added to a metathesis catalyst containing NHC ligands, e.g. the Grubbs (II) catalyst, the chloride ligands are replaced by bromide or iodide. Furthermore, it is shown that the catalyst activity depends on the type of halide ligands and increases in the following order: $\text{I} < \text{Br} < \text{Cl}$.

20

In **J. Am.Chem.Soc.** 1997, 119, 9130-9136 it is stated that the activity of the Grubbs (I) catalyst in the ring-closing metathesis of 1, ω -dienes can be increased by addition of tetraisopropoxytitanate and an improvement in yield can be achieved thereby. In the cyclization of the 9-decenoic ester of 4-pentenoate, a higher yield of the macrolide is achieved when tetraisopropanoxytitanate is added than when LiBr is added. There is no indication of the extent to which this effect can also be applied to other types of metathesis reactions or other metathesis catalysts.

25

30

In **Org. Biomol. Chem.** 2005, 3, 4139-4142 the cross-metathesis (CM) of acrylonitrile with itself and with other functional olefins when using [1,3-bis(2,6-dimethylphenyl)4,5-dihydroimidazol-2-ylidene] $(\text{C}_5\text{H}_5\text{N})_2(\text{Cl})_2\text{Ru}=\text{CHPh}$ is examined. The yield of the respective product is improved by addition of tetraisopropoxytitanate. This publication gives the impression that the activity-increasing effect of tetraisopropoxytitanate occurs only when using a specific catalyst having pyridine ligands. There is no suggestion of an influence of tetraisopropoxytitanate when pyridine-free catalysts are used or in other types of metathesis reactions.

35

It is known from **Synlett 2005, No.4, 670-672** that the addition of tetraisopropoxytitanate in the cross-metathesis of allyl carbamate with methyl acrylate has an adverse effect on the product yield when the Hoveyda catalyst is used as catalyst. Thus, the product yield is reduced from 28% to 0% by addition of tetraisopropoxytitanate. Addition of dimethylaluminium chloride, too, reduces the yield from 28% to 20%.

In **Synlett 2005, No.4, 670-672** it is also stated that the product yield in the cross-metathesis of low molecular weight olefins is improved when specific boric acid derivatives are used. Use is made of chlorocatecholborane (ArO_2BCl), dichlorophenylborane (PhBCl_2) and chlorodicyclohexylborane (Cy_2BCl). Depending on the boric acid derivative, the yield is improved to very different extents. To obtain appropriate improvements in yield, addition of 10-20 mol% of the boric acid derivative based on 1 equivalent of an olefin is required.

In **Synthesis 2000, No.12, 1766-1773** it is stated that the yields in the ring-closing metathesis of diethyl diallylmalonate when using the Grubbs I catalyst are not adversely affected by additions of boron trichloride and aluminium trichloride (Table 2). In a tandem enyne methathesis/Diels-Alder reaction of N-allyl-N-3-phenylprop-2-ynyl-p-toluenesulphenamide to form 4-acyl-7-phenyl-hexahydroisindole via N-tosyl-1-(1-phenylvinyl)-2,4-dihydro-2H-pyrrole (as intermediate product of the enyne methathesis), too, the yield is not influenced by whether BCl_3 is added right at the beginning together with the Grubbs (I) catalyst in a one-pot reaction or whether it is, in a sequential procedure, added only in the second step of the Diels-Alder reaction. These experiments show that the activity of the Grubbs (I) catalyst is not reduced by addition of boron trichloride or aluminium trichloride. However, there is no evidence that addition of boron trichloride or aluminium trichloride improves the catalyst activity.

Since the metathesis reaction is enjoying increasing popularity both in the field of low molecular weight chemistry and for polymers such as nitrile rubbers, there is, despite the existing prior art, a continuing need for improved catalyst systems for metathesis reactions and in particular the reduction of the molecular weight of nitrile rubber by metathesis. This applies all the more in view of the fact that, on the basis of the available prior art, results of one metathesis reaction cannot readily be applied to another.

In the light of this background, it is an **object of the present invention** to provide novel catalyst systems which can be used universally in various types of metathesis reactions, lead to activity increases for a wide variety of metathesis catalysts used as a basis and thus allow a reduction in the amount of catalyst and thus, in particular, the amounts of noble metal present therein. For the

metathetic degradation of nitrile rubber in particular, possible ways of increasing the activity of the catalyst used without gelling of the nitrile rubber should be found.

5 It has surprisingly been found that the activity of metathesis catalysts can be increased significantly when they are used in combination with fluorine-containing boron compounds. In particular, it has been found that the reduction of the molecular weight of nitrile rubber by metathesis can be significantly improved when the metathesis catalyst is used as a system in combination with fluorine-containing boron compounds. This combination increases the reaction rate of metathesis reactions and, particularly in the metathesis of NBR, significantly narrower
10 molecular weight distributions and lower molecular weights can be obtained without gelling occurring. At the same time, the amount of metathesis catalyst can be reduced by the addition of the fluorine-containing boron compounds.

The invention accordingly provides a process for the metathetic degradation of nitrile rubbers, in
15 which the nitrile rubber is subjected to a metathesis reaction in the presence of a catalyst system, wherein the catalyst system contains a metathesis catalyst which is a complex catalyst based on a metal of transition group 6 or 8 of the Periodic Table and has at least one ligand bound in a carbene-like fashion to the metal and also at least one compound of the general formula (Z)



20 where

m is 1, 2 or 3,

n is 0, 1 or 2 and at the same time

m + n = 3 and

v is 1, 2, 3, 4 or 5,

25 X is chlorine, bromine, iodine, an -OR or -NR₂ group, where the radicals R are each, independently of one another, a linear, branched, aliphatic, cyclic, heterocyclic or aromatic radical which has 1-33 carbon atoms and may optionally have from 1 to 15 further heteroatoms, and

D is a compound having at least one free electron pair, where D contains at least one
30 heteroatom which is preferably selected from the group consisting of oxygen, sulphur, nitrogen, phosphorus, arsenic and antimony.

In a preferred embodiment of the invention, compounds of the general formula (Z) in which X is chlorine, bromine or an -OR or -NR₂ group, where the radicals R are each, independently of one
35 another, straight-chain or branched C₁-C₃₀-alkyl, preferably C₁-C₂₀-alkyl, particularly preferably C₁-C₁₂-alkyl, C₃-C₂₀-cycloalkyl, preferably C₃-C₁₀-cycloalkyl, particularly preferably C₅-C₈-cycloalkyl, C₂-C₂₀-alkenyl, preferably C₂-C₁₈-alkenyl, C₂-C₂₀-alkynyl, preferably C₂-C₁₈-alkynyl,

C_6 - C_{24} -aryl, preferably C_6 - C_{14} -aryl, C_4 - C_{23} -heteroaryl, where these heteroaryl radicals have at least one heteroatom, preferably nitrogen or oxygen, or are in each case a radical of the general formula $(-CHZ^1-CHZ^1-A^2-)_p-CH_2-CH_3$, where p is an integer from 1 to 10, the radicals Z^1 are identical or different and are each hydrogen or methyl, with the radicals Z^1 located on adjacent carbon atoms preferably being different, and A^2 is oxygen, sulphur or $-NH$, are used in the catalyst system.

In a particularly preferred embodiment of the invention, compounds of the general formula (Z) in which the radicals R in the radicals OR and NR_2 are each methyl, ethyl, n -propyl, i -propyl, n -butyl, i -butyl, $tert$ -butyl, n -pentyl, i -pentyl, $tert$ -pentyl, hexyl, decyl, dodecyl, oleyl, phenyl or sterically hindered phenyl are used in the catalyst system.

In the general formula (Z), the BF_mX_n moiety is preferably BF_3 , BF_2Cl , $BFCl_2$, BF_2Br , $BFBr_2$, $BF_2(OC_2H_5)$, $BF(OC_2H_5)_2$, $BF_2(CH_3)$ and $BF(CH_3)_2$. BF_mX_n is particularly preferably BF_3 .

In the compounds of the general formula (Z), D can have the following meanings of the general formulae (2) to (16)

	OR_2	(2)
	ROH	(3)
	$R-COOH$	(4)
20	SR_2	(5)
	$O=SR_2$	(6)
	O_2SR_2	(7)
	$NHR_2, NH_2R, NR_3,$	(8a, 8b, 8c)
	YR_3, R_2Y-YR_2	(9a, 9b)
25	$O=YR_3$	(10)
	$O=Y(OR)_2$	(11)
	$O=Y(OR)_3$	(12)
	$O=CR_2$	(13)
	$S=YR_3$	(14)
30	H_2SO_4	(15)
	RSO_3H	(16)

where Y is phosphorus, arsenic or antimony and the radicals R are identical or different and are each hydrogen or a linear, branched, aliphatic, cyclic, heterocyclic or aromatic radical which has 1-33 carbon atoms and may be bridged and can optionally have from 1 to 15 further heteroatoms, preferably nitrogen or oxygen, or can optionally be substituted. Preference is given to the radicals R each being, independently of one another, hydrogen, straight-chain or branched C_1 - C_{30} -alkyl,

particularly preferably straight-chain or branched C₁-C₁₂-alkyl, C₃-C₂₀-cycloalkyl, particularly preferably C₅-C₈-cycloalkyl, straight-chain or branched C₂-C₂₀-alkenyl, particularly preferably straight-chain or branched C₂-C₁₄-alkenyl, straight-chain or branched C₂-C₂₀-alkynyl, particularly preferably straight-chain or branched C₂-C₁₄-alkynyl, C₆-C₂₄-aryl, particularly preferably C₆-C₁₄-aryl, where all the abovementioned radicals may each optionally be substituted by one or more alkyl, halogen, preferably fluorine or chlorine, alkoxy, aryl or heteroaryl radicals. If two radicals R are present in one of the formulae (2)-(16), these can also be bridged with inclusion of the common atom or atoms to which they are bound to form a cyclic group which can be aliphatic or aromatic in nature, may optionally be substituted and can additionally contain one or more heteroatoms, preferably oxygen or nitrogen.

Examples of **compounds D of the general formula (2)** are: water, dimethyl ether, diethyl ether, di-n-propyl ether, di-i-propyl ether, di-n-butyl ether, di-i-butyl ether, di-t-butyl ether, methyl t-butyl ether, dimethoxyethane, di-n-butoxyethane, diphenyl ether, methylphenyl ether, ethylphenyl ether, tetrahydrofuran, tetrahydropyran. Preference is given to water, diethyl ether, tetrahydrofuran and tetrahydropyran.

Examples of **compounds D of the general formula (3)** are: methanol, ethanol, n-propanol, i-propanol, n-butanol, t-butanol, phenol, catechol, anisole and salicylic acid.

Examples of **compounds D of the general formula (4)** are: formic acid, acetic acid, propionic acid, citric acid, trichloroacetic acid, trifluoroacetic acid and benzoic acid.

Examples of **compounds D of the general formula (5)** are: hydrogen sulphide, methyl mercaptan, n-hexyl mercaptan, t-butyl mercaptan, t-nonyl mercaptan, n-dodecyl mercaptan and t-dodecyl mercaptan, dimethyl sulphide, diethyl sulphide, diisopropyl sulphide, tetrahydrothiophene and diphenyl sulphide.

Examples of **compounds D of the general formula (6)** are dimethyl sulphoxide, diethyl sulphoxide, diisopropyl sulphoxide, butyl methyl sulphoxide and tetrahydrothiophene 1-oxide.

Examples of **compounds D of the general formula (7)** are dimethyl sulphone, diethyl sulphone, diisopropyl sulphone, butyl methyl sulphone and Sulpholane (tetrahydrothiophene 1,1-dioxide).

Examples of **compounds D of the general formulae (8a, 8b and 8c)** are: trimethylamine, triethylamine, triethanolamine, aniline, methylaniline, dimethylaniline, pyridine, pyrimidine, pyrrole, pyrrolidine, tetramethylethylenediamine, tetraethylethylenediamine, ammonia,

methylamine, ethylamine, propylamine, diethylamine and dimethylamine.

Examples of **compounds D** of the **general formula (9a)** are: phosphine, trimethylphosphine, triethylphosphine, triisopropylphosphine, tricyclohexylphosphine, triphenylphosphine and tris(sulphonophenyl)phosphane and salts thereof.

An example of a **compound D** of the **general formula (9b)** is tetraphenyldiphosphane.


Particular preference is given to using water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid as **compounds D**.

For the purposes of the present patent application and invention, all definitions mentioned above and below, in general terms or in preferred ranges, of radicals, parameters or explanations can be combined with one another, i.e. also between the respective ranges and preferred ranges, in any desired way.

The term "substituted" used in the present patent application in relation to the various types of metathesis catalysts or compounds of the general formula (Z) means that a hydrogen atom on the indicated radical or atom has been replaced by one of the groups indicated in each case, with the proviso that the valency of the indicated atom is not exceeded and the substitution leads to a stable compound.

The metathesis catalysts to be used in the process of the invention are complex catalysts based on a metal of transition group 6 or 8 of the Periodic Table. These complex catalysts have the common structural feature that they have at least one ligand which is bound to the metal in a carbene-like fashion. In a preferred embodiment, the complex catalyst has two carbene ligands, i.e. two ligands which are bound in a carbene-like fashion to the central metal of the complex. As metals of transition groups 6 and 8 of the Periodic Table, preference is given to molybdenum, tungsten, osmium and ruthenium.

Suitable catalyst systems are, for example, systems which comprise at least one compound of the general formula (Z) and also a catalyst of the general formula A),



where

M is osmium or ruthenium,

X¹ and X² are identical or different and are two ligands, preferably anionic ligands,

L represents identical or different ligands, preferably uncharged electron donors,

5 the radicals R are identical or different and are each hydrogen, alkyl, preferably C₁-C₃₀-alkyl, cycloalkyl, preferably C₃-C₂₀-cycloalkyl, alkenyl, preferably C₂-C₂₀-alkenyl, alkynyl, preferably C₂-C₂₀-alkynyl, aryl, preferably C₆-C₂₄-aryl, carboxylate, preferably C₁-C₂₀-carboxylate, alkoxy, preferably C₁-C₂₀-alkoxy, alkenyloxy, preferably C₂-C₂₀-alkenyloxy, alkynyloxy, preferably C₂-C₂₀-alkynyloxy, aryloxy, preferably C₆-C₂₄-aryloxy, alkoxycarbonyl, preferably C₂-C₂₀-alkoxycarbonyl, 10 alkylamino, preferably C₁-C₃₀-alkylamino, alkylthio, preferably C₁-C₃₀-alkylthio, arylthio, preferably C₆-C₂₄-arylthio, alkylsulphonyl, preferably C₁-C₂₀-alkylsulphonyl, or alkylsulphinyl, preferably C₁-C₂₀-alkylsulphinyl, where these radicals can all optionally be substituted by one or more alkyl, halogen, alkoxy, 15 aryl or heteroaryl radicals or alternatively the two radicals R are bridged with inclusion of the common C atom to which they are bound to form a cyclic group which can be aliphatic or aromatic in nature, may optionally be substituted and can contain one or more heteroatoms.

20 In a preferred embodiment, these catalyst systems comprise a catalyst of the general formula (A) together with a compound of the general formula (Z) in which the BF_mX_n moiety is BF₃, BF₂Cl, BFCl₂, BF₂Br, BFBr₂, BF₂(OC₂H₅), BF(OC₂H₅)₂, BF₂(CH₃) and BF(CH₃)₂, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, 25 trifluoromethanesulphonic acid and toluenesulphonic acid and v = 1, 2, 3, 4 or 5, particularly preferably 1, 2 or 3.

In particularly preferred catalysts of the general formula (A), one radical R is hydrogen and the other radical R is C₁-C₂₀-alkyl, C₃-C₁₀-cycloalkyl, C₂-C₂₀-alkenyl, C₂-C₂₀-alkynyl, C₆-C₂₄-aryl, C₁-C₂₀-carboxylate, C₁-C₂₀-alkoxy, C₂-C₂₀-alkenyloxy, C₂-C₂₀-alkynyloxy, C₆-C₂₄-aryloxy, C₂-C₂₀-alkoxycarbonyl, C₁-C₃₀-alkylamino, C₁-C₃₀-alkylthio, C₆-C₂₄-arylthio, C₁-C₂₀-alkylsulphonyl or C₁-C₂₀-alkylsulphinyl, where these radicals can all be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals.

35 In the catalysts of the general formula (A), X¹ and X² are identical or different and are two ligands, preferably anionic ligands.

X^1 and X^2 can be, for example, hydrogen, halogen, pseudohalogen, straight-chain or branched C_1 - C_{30} -alkyl, C_6 - C_{24} -aryl, C_1 - C_{20} -alkoxy, C_6 - C_{24} -aryloxy, C_3 - C_{20} -alkyldiketonate, C_6 - C_{24} -aryldiketonate, C_1 - C_{20} -carboxylate, C_1 - C_{20} -alkylsulphonate, C_6 - C_{24} -arylsulphonate, C_1 - C_{20} -alkylthiol, C_6 - C_{24} -arylthiol, C_1 - C_{20} -alkylsulphonyl or C_1 - C_{20} -alkylsulphinyl radicals.

5

The abovementioned radicals X^1 and X^2 can also be substituted by one or more further radicals, for example by halogen, preferably fluorine, C_1 - C_{10} -alkyl, C_1 - C_{10} -alkoxy or C_6 - C_{24} -aryl, where these radicals too may optionally be substituted by one or more substituents selected from the group consisting of halogen, preferably fluorine, C_1 - C_5 -alkyl, C_1 - C_5 -alkoxy and phenyl.

10

In a preferred embodiment, X^1 and X^2 are identical or different and are each halogen, in particular fluorine, chlorine, bromine or iodine, benzoate, C_1 - C_5 -carboxylate, C_1 - C_5 -alkyl, phenoxy, C_1 - C_5 -alkoxy, C_1 - C_5 -alkylthiol, C_6 - C_{24} -arylthiol, C_6 - C_{24} -aryl or C_1 - C_5 -alkylsulphonate.

15

In a particularly preferred embodiment, X^1 and X^2 are identical and are each halogen, in particular chlorine, CF_3COO , CH_3COO , CFH_2COO , $(CH_3)_3CO$, $(CF_3)_2(CH_3)CO$, $(CF_3)(CH_3)_2CO$, PhO (phenoxy), MeO (methoxy), EtO (ethoxy), tosylate (p - CH_3 - C_6H_4 - SO_3), mesylate (2,4,6-trimethylphenyl) or CF_3SO_3 (trifluoromethanesulphonate).

20

In the general formula (A), L represents identical or different ligands and preferably uncharged electron donors.

The two ligands L can, for example, each be, independently of one another, a phosphine, sulphonated phosphine, phosphate, phosphinite, phosphonite, arsine, stibine, ether, amine, amide, sulfoxide, carboxyl, nitrosyl, pyridine, thioether or imidazolidine ("Im") ligand.

25

Preference is given to the two ligands L each being, independently of one another, a C_6 - C_{24} -arylphosphine, C_1 - C_{10} -alkylphosphine or C_3 - C_{20} -cycloalkylphosphine ligand, a sulphonated C_6 - C_{24} -arylphosphine or sulphonated C_1 - C_{10} -alkylphosphine ligand, a C_6 - C_{24} -arylphosphinite or C_1 - C_{10} -alkylphosphinite ligand, a C_6 - C_{24} -arylphosphonite or C_1 - C_{10} -alkylphosphonite ligand, a C_6 - C_{24} -aryl phosphite or C_1 - C_{10} -alkyl phosphite ligand, a C_6 - C_{24} -arylarsine or C_1 - C_{10} -alkylarsine ligand, a C_6 - C_{24} -arylamine or C_1 - C_{10} -alkylamine ligand, a pyridine ligand, a C_6 - C_{24} -aryl sulfoxide or C_1 - C_{10} -alkyl sulfoxide ligand, a C_6 - C_{24} -aryl ether or C_1 - C_{10} -alkyl ether ligand or a C_6 - C_{24} -arylamide or C_1 - C_{10} -alkylamide ligand, which can all be substituted by a phenyl group which may in turn optionally be substituted by a halogen, C_1 - C_5 -alkyl or C_1 - C_5 -alkoxy radical.

35

The term "phosphine" includes, for example, PPh_3 , $P(p\text{-tolyl})_3$, $P(o\text{-tolyl})_3$, $Pphenyl(CH_3)_2$,

$P(CF_3)_3$, $P(p-FC_6H_4)_3$, $P(p-CF_3C_6H_4)_3$, $P(C_6H_4-SO_3Na)_3$, $P(CH_2C_6H_4-SO_3Na)_3$, $P(isopropyl)_3$, $P(CHCH_3(CH_2CH_3))_3$, $P(cyclopentyl)_3$, $P(cyclohexyl)_3$, $P(neopentyl)_3$ and $P(neophenyl)_3$.

5 The term "phosphinite" includes, for example, phenyl diphenylphosphinite, cyclohexyl dicyclohexylphosphinite, isopropyl diisopropylphosphinite and methyl diphenylphosphinite.

The term "phosphite" includes, for example, triphenyl phosphite, tricyclohexyl phosphite, tri-tert-butyl phosphite, triisopropyl phosphite and methyl diphenyl phosphite.

10 The term "stibine" includes, for example, triphenylstibine, tricyclohexylstibine and trimethylstiben.


The term "sulphonate" includes, for example, trifluoromethanesulphonate, tosylate and mesylate.

15 The term "sulphoxide" includes, for example, $(CH_3)_2S(=O)$ and $(C_6H_5)_2SO$.


The term "thioether" includes, for example, CH_3SCH_3 , $C_6H_5SCH_3$, $CH_3OCH_2CH_2SCH_3$ and tetrahydrothiophene.

20 For the purposes of the present patent application, the term "pyridine" serves as collective term for all nitrogen-containing ligands as are mentioned, for example, in WO-A-03/011455. Examples are: pyridine, picolines (α -, β -, and γ -picoline), lutidines (2,3-, 2,4-, 2,5-, 2,6-, 3,4- and 3,5-lutidine), collidine (2,4,6-trimethylpyridine), trifluoromethylpyridine, phenylpyridine, 4-(dimethyl-amino)pyridine, chloropyridines, bromopyridines, nitropyridines, quinoline, pyrimidine, pyrrole,
25 imidazole and phenylimidazole.

If one or both of the ligands L is an imidazolidine radical (Im), this usually has a structure of the general formula (IIa) or (IIb),



(IIa)



(IIb)


30 where

R^8 , R^9 , R^{10} , R^{11} are identical or different and are each hydrogen, straight-chain or branched C_1 - C_{30} -alkyl, C_3 - C_{20} -cycloalkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl, C_6 - C_{24} -aryl, C_1 - C_{20} -carboxylate, C_1 - C_{20} -alkoxy, C_2 - C_{20} -alkenyloxy, C_2 - C_{20} -alkynyloxy, C_6 - C_{20} -aryloxy,


C₂-C₂₀-alkoxycarbonyl, C₁-C₂₀-alkylthio, C₆-C₂₀-arylthio, C₁-C₂₀-alkylsulphonyl, C₁-C₂₀-alkylsulphonate, C₆-C₂₀-arylsulphonate or C₁-C₂₀-alkylsulphinyl.

One or more of the radicals R⁸, R⁹, R¹⁰, R¹¹ can optionally be substituted, independently of one another, by one or more substituents, preferably straight-chain or branched C₁-C₁₀-alkyl, C₃-C₈-cycloalkyl, C₁-C₁₀-alkoxy or C₆-C₂₄-aryl, where these abovementioned substituents may in turn be substituted by one or more radicals, preferably radicals selected from the group consisting of halogen, in particular chlorine or bromine, C₁-C₅-alkyl, C₁-C₅-alkoxy and phenyl.

Purely for the purposes of clarification, it may be added that the structures of the imidazolidine radical shown in the general formulae (IIa) and (IIb) in the present patent application are equivalent to the structures (IIa') and (IIb') for this imidazolidine radical (Im) which are frequently also to be found in the literature and emphasize the carbene character of the imidazolidine radical. This applies analogously to the associated preferred structures (IIIa)-(IIIf) shown below.



(IIa')



(IIb')

In a preferred embodiment of the catalysts of the general formula (A), R⁸ and R⁹ are each, independently of one another, hydrogen, C₆-C₂₄-aryl, particularly preferably phenyl, straight-chain or branched C₁-C₁₀-alkyl, particularly preferably propyl or butyl, or together with the carbon atoms to which they are bound form a cycloalkyl or aryl radical, where all the abovementioned radicals may in turn optionally be substituted by one or more further radicals selected from the group consisting of straight-chain or branched C₁-C₁₀-alkyl, C₁-C₁₀-alkoxy, C₆-C₂₄-aryl and a functional group selected from the group consisting of hydroxy, thiol, thioether, ketone, aldehyde, ester, ether, amine, imine, amide, nitro, carboxylic acid, disulphide, carbonate, isocyanate, carbodiimide, carboalkoxy, carbamate and halogen.

In a preferred embodiment of the catalysts of the general formula (A), the radicals R¹⁰ and R¹¹ are identical or different and are each straight-chain or branched C₁-C₁₀-alkyl, particularly preferably i-propyl or neopentyl, C₃-C₁₀-cycloalkyl, particularly adamantyl, C₆-C₂₄-aryl, particularly preferably phenyl, C₁-C₁₀-alkylsulphonate, particularly preferably methanesulphonate, C₆-C₁₀-arylsulphonate, particularly preferably p-toluenesulphonate.

The abovementioned radicals as meanings of R¹⁰ and R¹¹ may optionally be substituted by one or


ore further radicals selected from the group consisting of straight-chain or branched C₁-C₅-alkyl, in particular methyl, C₁-C₅-alkoxy, aryl and a functional group selected from the group consisting of hydroxy, thiol, thioether, ketone, aldehyde, ester, ether, amine, imine, amide, nitro, carboxylic acid, disulphide, carbonate, isocyanate, carbodiimide, carboxalkoxy, carbamate and halogen.

5


In particular, the radicals R¹⁰ and R¹¹ can be identical or different and are each i-propyl, neopentyl, adamantyl, mesityl or 2,6-diisopropylphenyl.

10


Particularly preferred imidazolidine radicals (Im) have the following structures (IIIa) to (IIIf), where Ph is in each case a phenyl radical, Bu is a butyl radical and Mes is in each case a 2,4,6-trimethylphenyl radical or Mes is alternatively in all cases 2,6-diisopropylphenyl.




(IIIa)




(IIIb)




(IIIc)



(IIIId)



(IIIe)



(IIIIf)

15

Various representatives of the catalysts of the formula (A) are known in principle, e.g. from WO-A-96/04289 and WO-A-97/06185.


20

As an alternative to the preferred Im radicals, one or both of the ligands L in the general formula (A) are preferably also identical or different trialkylphosphine ligands in which at least one of the alkyl groups is a secondary alkyl group or a cycloalkyl group, preferably isopropyl, isobutyl, sec-butyl, neopentyl, cyclopentyl or cyclohexyl.


25

Particular preference is given to one or both of the ligands L in the general formula (A) being a trialkylphosphine ligand in which at least one of the alkyl groups is a secondary alkyl group or a cycloalkyl group, preferably isopropyl, isobutyl, sec-butyl, neopentyl, cyclopentyl or cyclohexyl.

Particular preference is given to catalyst systems which comprise at least one compound of the general formula (Z) together with one of the following two catalysts which come under the general formula (A) and have the structures (IV) (Grubbs (I) catalyst) and (V) (Grubbs (II) catalyst), where Cy is cyclohexyl and Mes is meistyl.




(IV)



(V)

In a further embodiment, a catalyst system comprising at least one compound of the general formula (Z) together with a catalyst of the general formula (A1),



(A1)

10 where

X^1 , X^2 and L

can have the same general, preferred and particularly preferred meanings as in the general formula (A),

n

is 0, 1 or 2,

m

is 0, 1, 2, 3 or 4 and

15 the radicals R'


are identical or different and are each an alkyl, cycloalkyl, alkenyl, alkynyl, aryl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxycarbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl or alkylsulphinyl radical, which may all be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals,

20

is used in the process of the invention.

As preferred catalyst which comes under the general formula (A1), it is possible to use, for example, the catalyst of the formula (VI) below, where Mes is in each case 2,4,6-trimethylphenyl and Ph is phenyl.


25



This catalyst which is also referred to in the literature as “Nolan catalyst” is known, for example, from WO-A-2004/112951.

- 5 The particularly preferred catalyst systems comprise the catalysts of the formula (IV), (V) or (VI) together with a compound of the general formula (Z) in which the BF_mX_n moiety is BF_3 , BF_2Cl , BFCl_2 , BF_2Br , BFB_2 , $\text{BF}_2(\text{OC}_2\text{H}_5)$, $\text{BF}(\text{OC}_2\text{H}_5)_2$, $\text{BF}_2(\text{CH}_3)$ and $\text{BF}(\text{CH}_3)_2$, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and $v = 1, 2, 3, 4$ or 5 , particularly preferably $1, 2$ or 3 .
- 10

Further suitable catalyst systems are systems which comprise at least one compound of the general formula (Z) together with a catalyst of the general formula (B),



where

M is ruthenium or osmium,

X^1 and X^2 are identical or different ligands, preferably anionic ligands,

Y is oxygen (O), sulphur (S), an N-R^1 radical or a P-R^1 radical, where R^1 has the meanings mentioned below,

R^1 is an alkyl, cycloalkyl, alkenyl, alkynyl, aryl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxycarbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl or alkylsulphinyl radical, which may all optionally be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals,

$\text{R}^2, \text{R}^3, \text{R}^4$ and R^5 are identical or different and are each hydrogen or an organic or inorganic radical,

R^6 is hydrogen or an alkyl, alkenyl, alkynyl or aryl radical and

L is a ligand which has the same meanings as mentioned for the formula (A).

These catalyst systems preferably comprise the catalyst of the general formula (B) together with a compound of the general formula (Z) in which the BF_mX_n moiety is BF_3 , BF_2Cl , BFCl_2 , BF_2Br , BFBr_2 , $\text{BF}_2(\text{OEt})$, $\text{BF}(\text{OEt})_2$, $\text{BF}_2(\text{Me})$ or $\text{BF}(\text{Me})_2$, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and $v = 1, 2, 3, 4$ or 5 , particularly preferably $1, 2$ or 3 .

The catalysts of the general formula (B) are known in principle. Representatives of this class of compounds are the catalysts described by Hoveyda et al. in US 2002/0107138 A1 and *Angew. Chem. Int. Ed.* 2003, 42, 4592 and the catalysts which are described by Grela in WO-A-2004/035596, *Eur. J. Org. Chem* 2003, 963-966 and *Angew. Chem. Int. Ed.* 2002, 41, 4038 and in *J. Org. Chem.* 2004, 69, 6894-96 and *Chem. Eur. J* 2004, 10, 777-784. The catalysts are commercially available or can be prepared as described in the literature references cited.

In the catalysts of the general formula (B), L is a ligand which usually has an electron donor function and can have the same general, preferred and particularly preferred meanings as L in the general formula (A).


In addition, L in the general formula (B) is preferably a $\text{P}(\text{R}^7)_3$ radical, where the radicals R^7 are each, independently of one another, C_1 - C_6 -alkyl, C_3 - C_8 -cycloalkyl or aryl, or else a substituted or unsubstituted imidazolidine radical ("Im").

C_1 - C_6 -alkyl is, for example, methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, tert-butyl, n-pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, neopentyl, 1-ethylpropyl or n-hexyl.


C_3 - C_8 -cycloalkyl encompasses cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl and cyclooctyl.

Aryl is an aromatic radical having from 6 to 24 skeletal carbon atoms. As preferred monocyclic, bicyclic or tricyclic carbocyclic aromatic radicals having from 6 to 10 skeletal carbon atoms, mention may be made of, for example, phenyl, biphenyl, naphthyl, phenanthrenyl and anthracenyl.

The imidazolidine radical (**Im**) usually has a structure of the general formula (IIa) or (IIb),



(IIa)



(IIb)

where

R⁸, R⁹, R¹⁰, R¹¹ are identical or different and are each hydrogen, straight-chain or branched C₁-C₃₀-alkyl, C₃-C₂₀-cycloalkyl, C₂-C₂₀-alkenyl, C₂-C₂₀-alkynyl, C₆-C₂₄-aryl, C₁-C₂₀-carboxylate, C₁-C₂₀-alkoxy, C₂-C₂₀-alkenyloxy, C₂-C₂₀-alkynyloxy, C₆-C₂₀-aryloxy, C₂-C₂₀-alkoxycarbonyl, C₁-C₂₀-alkylthio, C₆-C₂₀-arylthio, C₁-C₂₀-alkylsulphonyl, C₁-C₂₀-alkylsulphonate, C₆-C₂₀-arylsulphonate or C₁-C₂₀-alkylsulphinyl.

One or more of the radicals R⁸, R⁹, R¹⁰, R¹¹ can optionally be substituted, independently of one another, by one or more substituents, preferably straight-chain or branched C₁-C₁₀-alkyl, C₃-C₈-cycloalkyl, C₁-C₁₀-alkoxy or C₆-C₂₄-aryl, where these abovementioned substituents may in turn be substituted by one or more radicals, preferably radicals selected from the group consisting of halogen, in particular chlorine or bromine, C₁-C₅-alkyl, C₁-C₅-alkoxy and phenyl.

In a preferred embodiment of the catalyst system used according to the invention, at least one compound of the general formula (Z) is used together with catalysts of the general formula (B) in which R⁸ and R⁹ are each, independently of one another, hydrogen, C₆-C₂₄-aryl, particularly preferably phenyl, straight-chain or branched C₁-C₁₀-alkyl, particularly preferably propyl or butyl, or together with the carbon atoms to which they are bound form a cycloalkyl or aryl radical, where all the abovementioned radicals may in turn optionally be substituted by one or more further radicals selected from the group consisting of straight-chain or branched C₁-C₁₀-alkyl, C₁-C₁₀-alkoxy, C₆-C₂₄-aryl and a functional group selected from the group consisting of hydroxy, thiol, thioether, ketone, aldehyde, ester, ether, amine, imine, amide, nitro, carboxylic acid, disulphide, carbonate, isocyanate, carbodiimide, carboalkoxy, carbamate and halogen.

In a further preferred embodiment of the catalyst system used according to the invention, at least one compound of the general formula (Z) is used together with catalysts of the general formula (B) in which the radicals R¹⁰ and R¹¹ are identical or different and are each straight-chain or branched C₁-C₁₀-alkyl, particularly preferably i-propyl or neopentyl, C₃-C₁₀-cycloalkyl, preferably adamantyl, C₆-C₂₄-aryl, particularly preferably phenyl, C₁-C₁₀-alkylsulphonate, particularly preferably methanesulphonate, or C₆-C₁₀-arylsulphonate, particularly preferably p-toluenesulphonate.

The abovementioned radicals as meanings of R^{10} and R^{11} may optionally be substituted by one or more further radicals selected from the group consisting of straight-chain or branched C_1 - C_5 -alkyl, in particular methyl, C_1 - C_5 -alkoxy, aryl and a functional group selected from the group consisting of hydroxyl, thiol, thioether, ketone, aldehyde, ester, ether, amine, imine, amide, nitro, carboxylic acid, disulphide, carbonate, isocyanate, carbodiimide, carboalkoxy, carbamate and halogen.

In particular, the radicals R^{10} and R^{11} can be identical or different and are each i-propyl, neopentyl, adamantyl or mesityl.

Particularly preferred imidazolidine radicals (Im) have the abovementioned structures (IIIa-III f), where Mes is in each case 2,4,6-trimethylphenyl.

In the catalysts of the general formula (B), X^1 and X^2 are identical or different and can each be, for example, hydrogen, halogen, pseudohalogen, straight-chain or branched C_1 - C_{30} -alkyl, C_6 - C_{24} -aryl, C_1 - C_{20} -alkoxy, C_6 - C_{24} -aryloxy, C_3 - C_{20} -alkyldiketonate, C_6 - C_{24} -aryldiketonate, C_1 - C_{20} -carboxylate, C_1 - C_{20} -alkylsulphonate, C_6 - C_{24} -arylsulphonate, C_1 - C_{20} -alkylthiol, C_6 - C_{24} -arylthiol, C_1 - C_{20} -alkylsulphonyl or C_1 - C_{20} -alkylsulphinyl.

The abovementioned radicals X^1 and X^2 can also be substituted by one or more further radicals, for example by halogen, preferably fluorine, C_1 - C_{10} -alkyl, C_1 - C_{10} -alkoxy or C_6 - C_{24} -aryl radicals, where the latter radicals may also optionally be substituted by one or more substituents selected from the group consisting of halogen, preferably fluorine, C_1 - C_5 -alkyl, C_1 - C_5 -alkoxy and phenyl.

In a preferred embodiment, X^1 and X^2 are identical or different and are each halogen, in particular fluorine, chlorine, bromine or iodine, benzoate, C_1 - C_5 -carboxylate, C_1 - C_5 -alkyl, phenoxy, C_1 - C_5 -alkoxy, C_1 - C_5 -alkylthiol, C_6 - C_{24} -arylthiol, C_6 - C_{24} -aryl or C_1 - C_5 -alkylsulphonate.

In a particularly preferred embodiment, X^1 and X^2 are identical and are each halogen, in particular chlorine, CF_3COO , CH_3COO , CFH_2COO , $(CH_3)_3CO$, $(CF_3)_2(CH_3)CO$, $(CF_3)(CH_3)_2CO$, PhO (phenoxy), MeO (methoxy), EtO (ethoxy), tosylate (p - CH_3 - C_6H_4 - SO_3), mesylate (2,4,6-trimethylphenyl) or CF_3SO_3 (trifluoromethanesulphonate).

In the general formula (B), the radical R^1 is an alkyl, cycloalkyl, alkenyl, alkynyl, aryl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxycarbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl or alkylsulphinyl radical, which may all optionally be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals.

The radical R^1 is usually a C_1 - C_{30} -alkyl, C_3 - C_{20} -cycloalkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl, C_6 - C_{24} -aryl, C_1 - C_{20} -alkoxy, C_2 - C_{20} -alkenyloxy, C_2 - C_{20} -alkynyloxy, C_6 - C_{24} -aryloxy, C_2 - C_{20} -alkoxycarbonyl, C_1 - C_{20} -alkylamino, C_1 - C_{20} -alkylthio, C_6 - C_{24} -arylthio, C_1 - C_{20} -alkylsulphonyl or C_1 - C_{20} -alkylsulphinyl radical, which can all optionally be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals.

R^1 is preferably a C_3 - C_{20} -cycloalkyl radical, a C_6 - C_{24} -aryl radical or a straight-chain or branched C_1 - C_{30} -alkyl radical, where the latter may optionally be interrupted by one or more double or triple bonds or one or more heteroatoms, preferably oxygen or nitrogen. R^1 is particularly preferably a straight-chain or branched C_1 - C_{12} -alkyl radical.

The C_3 - C_{20} -cycloalkyl radical is, for example, cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl or cyclooctyl.

The C_1 - C_{12} -alkyl radical can be, for example, methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, tert-butyl, n-pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, neopentyl, 1-ethylpropyl, n-hexyl, n-heptyl, n-octyl, n-decyl or n-dodecyl. In particular, R^1 is methyl or isopropyl.

The C_6 - C_{24} -aryl radical is an aromatic radical having from 6 to 24 skeletal carbon atoms. As preferred monocyclic, bicyclic or tricyclic carbocyclic aromatic radicals having from 6 to 10 skeletal carbon atoms, mention may be made of, for example, phenyl, biphenyl, naphthyl, phenanthrenyl and anthracenyl.

In the general formula (B), the radicals R^2 , R^3 , R^4 and R^5 are identical or different and can each be hydrogen, or an organic or inorganic radical.

In a useful embodiment, R^2 , R^3 , R^4 , R^5 are identical or different and are each hydrogen, halogen, nitro, CF_3 , alkyl, cycloalkyl, alkenyl, alkynyl, aryl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxycarbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl or alkylsulphinyl, which may all optionally be substituted by one or more alkyl, alkoxy, halogen, aryl or heteroaryl radicals.


R^2 , R^3 , R^4 , R^5 are usually identical or different and are each hydrogen, halogen, preferably chlorine or bromine, nitro, CF_3 , C_1 - C_{30} -alkyl, C_3 - C_{20} -cycloalkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl, C_6 - C_{24} -aryl, C_1 - C_{20} -alkoxy, C_2 - C_{20} -alkenyloxy, C_2 - C_{20} -alkynyloxy, C_6 - C_{24} -aryloxy, C_2 - C_{20} -alkoxycarbonyl, C_1 - C_{20} -alkylamino, C_1 - C_{20} -alkylthio, C_6 - C_{24} -arylthio, C_1 - C_{20} -alkylsulphonyl or C_1 - C_{20} -alkylsulphinyl, which may all optionally be substituted by one or more C_1 - C_{30} -alkyl, C_1 - C_{20} -alkoxy, halogen, C_6 - C_{24} -aryl or heteroaryl radicals.

In a particularly useful embodiment, R^2 , R^3 , R^4 , R^5 are identical or different and are each nitro, straight-chain or branched C_1 - C_{30} -alkyl, C_5 - C_{20} -cycloalkyl, straight-chain or branched C_1 - C_{20} -alkoxy or C_6 - C_{24} -aryl, preferably phenyl or naphthyl. The C_1 - C_{30} -alkyl and C_1 - C_{20} -alkoxy radicals
 5 can optionally be interrupted by one or more double or triple bonds or one or more heteroatoms, preferably oxygen or nitrogen.

Furthermore, two or more of the radicals R^2 , R^3 , R^4 and R^5 can be bridged via aliphatic or aromatic structures. For example, R^3 and R^4 together with the carbon atoms to which they are bound in the benzene ring of the formula (B) can form a few fused-on benzene ring, so that a naphthyl structure
 10 results.

In the general formula (B), the radical R^6 is hydrogen or an alkyl, alkenyl, alkynyl or aryl radical. R^6 is preferably hydrogen or a C_1 - C_{30} -alkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl or C_6 - C_{24} -aryl radical.
 15 R^6 is particularly preferably hydrogen.

Further suitable catalyst systems are those comprising at least one compound of the general formula (Z) together with a catalyst of the general formula (B1),



20 where

M , L , X^1 , X^2 , R^1 , R^2 , R^3 , R^4 and R^5 can have the general, preferred and particularly preferred meanings given for the general formula (B).

These catalyst systems preferably comprise the catalyst of the general formula (B1) together with a
 25 compound of the general formula (Z) in which the BF_mX_n moiety is BF_3 , BF_2Cl , $BFCl_2$, BF_2Br , $BFBr_2$, $BF_2(OC_2H_5)$, $BF(OC_2H_5)_2$, $BF_2(CH_3)$ and $BF(CH_3)_2$, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and $v = 1, 2, 3, 4$ or 5 , particularly
 30 preferably $1, 2$ or 3 .

The catalysts of the general formula (B1) are known in principle from, for example, US 2002/0107138 A1 (Hoveyda et al.) and can be obtained by the preparative methods indicated there.

5 Particular preference is given to catalyst systems comprising catalysts of the general formula (B1) in which

M is ruthenium,

X¹ and X² are both halogen, in particular both chlorine,

R¹ is a straight-chain or branched C₁-C₁₂ alkyl radical,

10 R², R³, R⁴, R⁵ have the general and preferred meanings given for the general formula (B) and

L has the general and preferred meanings given for the general formula (B).

Especial preference is given to catalyst systems comprising catalysts of the general formula (B1) in which



15 M is ruthenium,

X¹ and X² are both chlorine,

R¹ is an isopropyl radical,

R², R³, R⁴, R⁵ are all hydrogen and


L is a substituted or unsubstituted imidazolidine radical of the formulae (IIa) or (IIb),



where

R⁸, R⁹, R¹⁰, R¹¹ are identical or different and are each hydrogen, straight-chain or branched C₁-C₃₀-alkyl, C₃-C₂₀-cycloalkyl, C₂-C₂₀-alkenyl, C₂-C₂₀-alkynyl, C₆-C₂₄-aryl, C₁-C₂₀-carboxylate, C₁-C₂₀-alkoxy, C₂-C₂₀-alkenyloxy, C₂-C₂₀-alkynyloxy, C₆-C₂₄-aryloxy, C₂-C₂₀-alkoxycarbonyl, C₁-C₂₀-alkylthio, C₆-C₂₄-arylthio, C₁-C₂₀-alkylsulphonyl, C₁-C₂₀-alkylsulphonate, C₆-C₂₄-arylsulphonate or C₁-C₂₀-alkylsulphinyl, where the abovementioned radicals may each be substituted by one or more substituents, preferably straight-chain or branched C₁-C₁₀-alkyl, C₃-C₈-cycloalkyl, C₁-C₁₀-alkoxy or C₆-C₂₄-aryl, where these abovementioned substituents may in turn also be substituted by one or more radicals, preferably radicals selected from the group consisting of halogen, in particular chlorine or bromine, C₁-C₅-alkyl, C₁-C₅-alkoxy and phenyl.

Very particular preference is given to a catalyst system comprising at least one compound of the general formula (Z) and a catalyst which comes under the general structural formula (B1) and has the formula (VII), where Mes is in each case 2,4,6-trimethylphenyl.




(VII)

5


This catalyst (VII) is also referred to as "Hoveyda catalyst" in the literature.

Further suitable catalyst systems are those which comprise at least one compound of the general formula (Z) together with a catalyst which comes under the general structural formula (B1) and has one of the formulae (VIII), (IX), (X), (XI), (XII), (XIII), (XIV) and (XV) below, where Mes is in each case 2,4,6-trimethylphenyl.


10




(VIII)




(IX)




(X)




(XI)




(XII)



(XIII)




(XIV)



(XV)

- 5 A further catalyst system which can be used according to the invention comprises at least one compound of the general formula (Z) and a catalyst of the general formula (B2),



(B2)

where

M, L, X¹, X², R¹ and R⁶ have the general and preferred meanings given for the formula (B),
 the radicals R¹² are identical or different and have the general and preferred
 meanings given for the radicals R², R³, R⁴ and R⁵ in the formula
 (B), with the exception of hydrogen, and
 n is 0, 1, 2 or 3.

These catalyst systems preferably comprise the catalyst of the general formula (B2) together with a
 compound of the general formula (Z) in which the BF_mX_n moiety is BF₃, BF₂Cl, BFCl₂, BF₂Br,
 BFBr₂, BF₂(OC₂H₅), BF(OC₂H₅)₂, BF₂(CH₃) and BF(CH₃)₂, D is selected from the group
 consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid,
 trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid,
 trifluoromethanesulphonic acid and toluenesulphonic acid and v = 1, 2, 3, 4 or 5, particularly
 preferably 1, 2 or 3.

The catalysts of the general formula (B2) are known in principle from, for example,
 WO-A-2004/035596 (Grela) and can be obtained by the preparative methods indicated there.


Particular preference is given to using catalyst systems comprising at least one compound of the
 general formula (Z) and a catalyst of the general formula (B2) in which

M is ruthenium,
 X¹ and X² are both halogen, in particular both chlorine,
 R¹ is a straight-chain or branched C₁-C₁₂ alkyl radical,
 R¹² has the meanings given for the general formula (B2),
 n is 0, 1, 2 or 3,
 R⁶ is hydrogen and
 L has the meanings given for the general formula (B).

Especially preference is given to using catalyst systems comprising at least one compound of the
 general formula (Z) and a catalyst of the general formula (B2) in which

M is ruthenium,
 X¹ and X² are both chlorine,
 R¹ is an isopropyl radical,
 n is 0 and
 L is a substituted or unsubstituted imidazolidine radical of the formulae (IIa) or (IIb),
 where R⁸, R⁹, R¹⁰, R¹¹ are identical or different and have the meanings given for the
 especially preferred catalysts of the general formula (B1).


5 A particularly suitable catalyst system is a system comprising a catalyst of the structure (XVI) below and a compound of the general formula (Z) in which the BF_mX_n moiety is BF_3 , BF_2Cl , BFCl_2 , BF_2Br , BFBr_2 , $\text{BF}_2(\text{OC}_2\text{H}_5)$, $\text{BF}(\text{OC}_2\text{H}_5)_2$, $\text{BF}_2(\text{CH}_3)$ and $\text{BF}(\text{CH}_3)_2$, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and $v = 1, 2, 3, 4$ or 5 , particularly preferably $1, 2$ or 3 .



(XVI)

10 The catalyst (XVI) is also referred to as "Grela catalyst" in the literature.


A further suitable catalyst system comprises at least one compound of the general formula (Z) and a catalyst which comes under the general formula (B2) and has the structure (XVII) below, where Mes is in each case 2,4,6-trimethylphenyl.



(XVII)


15

An alternative embodiment relates to catalyst systems comprising at least one compound of the general formula (Z) and a dendritic catalyst of the general formula (B3),



where D^1 , D^2 , D^3 and D^4 each have a structure of the general formula (XVIII) below which is

bound via the methylene group shown at right to the silicon of the formula (B3)



(XVIII)

where

- 5 M, L, X¹, X², R¹, R², R³, R⁵ and R⁶ can have the general and preferred meanings given for the general formula (B).


These catalyst systems preferably contain the catalyst of the general formula (B3) together with a compound of the general formula (Z) in which the **BF_mX_n** moiety is BF₃, BF₂Cl, BFCl₂, BF₂Br, BFBr₂, BF₂(OC₂H₅), BF(OC₂H₅)₂, BF₂(CH₃) and BF(CH₃)₂, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and v = 1, 2, 3, 4 or 5, particularly preferably 1, 2 or 3.

15

The catalysts of the general formula (B3) are known from US 2002/0107138 A1 and can be prepared according to the information given there.

A further alternative embodiment relates to the use of a catalyst system comprising at least one compound of the general formula (Z) and a catalyst of the formula (B4),

20



(B4)

where the symbol ● represents a support.

The support is preferably a poly(styrene-divinylbenzene) copolymer (PS-DVB).

The catalysts of the formula (B4) are known in principle from *Chem. Eur. J.* 2004 10, 777-784 and can be obtained by preparative methods described there.


5

All the abovementioned catalysts of type (B) can either be used as such in the reaction mixture of the NBR metathesis or can be applied to and immobilized on a solid support. Materials suitable as solid phases or supports are materials which firstly are inert towards the reaction mixture of the metathesis and secondly do not impair the activity of the catalyst. It is possible to use, for example,

10

metals, glass, polymers, ceramic, organic polymer spheres or inorganic sol-gels, carbon black, silica, silicates, calcium carbonate and barium sulphate for immobilizing the catalyst.

A further embodiment relates to the use of catalyst systems comprising at least one compound of the general formula (Z) and a catalyst of the general formula (C),



15

where

M is ruthenium or osmium,

X¹ and X² are identical or different and are anionic ligands,

the radicals R' are identical or different and are organic radicals,

20

Im is a substituted or unsubstituted imidazolidine radical and

An is an anion.

These catalyst systems preferably contain the catalyst of the general formula (C) together with a compound of the general formula (Z) in which the BF_mX_n moiety is BF₃, BF₂Cl, BFCl₂, BF₂Br, BFB₂, BF₂(OC₂H₅), BF(OC₂H₅)₂, BF₂(CH₃) and BF(CH₃)₂, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and v = 1, 2, 3, 4 or 5, particularly preferably 1, 2 or 3.

30

The catalysts of the general formula (C) are known in principle (see, for example, *Angew. Chem. Int. Ed.* 2004, 43, 6161-6165).

X^1 and X^2 in the general formula (C) can have the same general, preferred and particularly preferred meanings as in the formulae (A) and (B).


5 The imidazolidine radical (Im) usually has a structure of one of the general formulae (IIa) and (IIb) which have already been mentioned for the catalyst type of the formulae (A) and (B) and can also have all the structures mentioned as preferred there, in particular those of the formulae (IIIa)-(IIIf).

10 The radicals R' in the general formula (C) are identical or different and are each a straight-chain or branched C_1 - C_{30} -alkyl, C_5 - C_{30} -cycloalkyl or aryl radical, where the C_1 - C_{30} -alkyl radicals may optionally be interrupted by one or more double or triple bonds or one or more heteroatoms, preferably oxygen or nitrogen.

15 Aryl is an aromatic radical having from 6 to 24 skeletal carbon atoms. As preferred monocyclic, bicyclic or tricyclic carbocyclic aromatic radicals having from 6 to 10 skeletal carbon atoms, mention may be made of, for example, phenyl, biphenyl, naphthyl, phenanthrenyl and anthracenyl.

The radicals R' in the general formula (C) are preferably identical and are preferably each phenyl, cyclohexyl, cyclopentyl, isopropyl, o-tolyl, o-xylyl or mesityl.

20 A further alternative embodiment relates to the use of a catalyst system comprising at least one compound of the general formula (Z) and a catalyst of the general formula (D),



where

M is ruthenium or osmium,

25 R^{13} and R^{14} are each, independently of one another, hydrogen, C_1 - C_{20} -alkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl, C_6 - C_{24} -aryl, C_1 - C_{20} -carboxylate, C_1 - C_{20} -alkoxy, C_2 - C_{20} -alkenyloxy, C_2 - C_{20} -alkynyloxy, C_6 - C_{24} -aryloxy, C_2 - C_{20} -alkoxycarbonyl, C_1 - C_{20} -alkylthio, C_1 - C_{20} -alkylsulphonyl or C_1 - C_{20} -alkylsulphinyl,

X^3 is an anionic ligand,

30 L^2 is an uncharged π -bonded ligand, either monocyclic or polycyclic,

L^3 is a ligand from the group consisting of phosphines, sulphonated phosphines, fluorinated phosphines, functionalized phosphines having up to three aminoalkyl,


ammonioalkyl, alkoxyalkyl, alkoxycarbonylalkyl, hydrocarbonylalkyl, hydroxyalkyl or ketoalkyl groups, phosphites, phosphinites, phosphonites, phosphinamines, arsines, stibines, ethers, amines, amides, imines, sulphoxides, thioethers and pyridines,

5 Y⁻ is a noncoordinating anion and
 n is 0, 1, 2, 3, 4 or 5.

These catalyst systems preferably contain the catalyst of the general formula (D) together with a compound of the general formula (Z) in which the BF_mX_n moiety is BF_3 , BF_2Cl , BFCl_2 , BF_2Br ,
 10 BFBr_2 , $\text{BF}_2(\text{OC}_2\text{H}_5)$, $\text{BF}(\text{OC}_2\text{H}_5)_2$, $\text{BF}_2(\text{CH}_3)$ and $\text{BF}(\text{CH}_3)_2$, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and $v = 1, 2, 3, 4$ or 5 , particularly preferably $1, 2$ or 3 .

15

A further embodiment of the invention relates to the use of a catalyst system comprising at least one compound of the general formula (Z) and a catalyst of the general formula (E),




where

20 M^2 is molybdenum or tungsten,
 R^{15} and R^{16} are identical or different and are each hydrogen, C_1 - C_{20} -alkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl, C_6 - C_{24} -aryl, C_1 - C_{20} -carboxylate, C_1 - C_{20} -alkoxy, C_2 - C_{20} -alkenyloxy, C_2 - C_{20} -alkynyloxy, C_6 - C_{24} -aryloxy, C_2 - C_{20} -alkoxycarbonyl, C_1 - C_{20} -alkylthio, C_1 - C_{20} -alkylsulphonyl or C_1 - C_{20} -alkylsulphinyl,
 25 R^{17} and R^{18} are identical or different and are each a substituted or halogen-substituted C_1 - C_{20} -alkyl, C_6 - C_{24} -aryl, C_6 - C_{30} -aralkyl radical or a silicone-containing analogue thereof.

These catalyst systems preferably contain the catalyst of the general formula (E) together with a
 30 compound of the general formula (Z) in which the BF_mX_n moiety is BF_3 , BF_2Cl , BFCl_2 , BF_2Br , BFBr_2 , $\text{BF}_2(\text{OC}_2\text{H}_5)$, $\text{BF}(\text{OC}_2\text{H}_5)_2$, $\text{BF}_2(\text{CH}_3)$ and $\text{BF}(\text{CH}_3)_2$, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid,

trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and $v = 1, 2, 3, 4$ or 5 , particularly preferably $1, 2$ or 3 .

- 5 A further alternative embodiment relates to the use of a catalyst system comprising at least one compound of the general formula (Z) and a catalyst of the general formula (F),



where

M is ruthenium or osmium,


- 10 X¹ and X² are identical or different and are anionic ligands which can have all the meanings of X¹ and X² given for the general formulae (A) and (B),



L represents identical or different ligands which can have all the meanings of L given for the general formulae (A) and (B),

- 15 R¹⁹ and R²⁰ are identical or different and are each hydrogen or substituted or unsubstituted alkyl.

These catalyst systems preferably contain the catalyst of the general formula (F) together with a compound of the general formula (Z) in which the BF_mX_n moiety is BF₃, BF₂Cl, BFCl₂, BF₂Br, BFBr₂, BF₂(OC₂H₅), BF(OC₂H₅)₂, BF₂(CH₃) and BF(CH₃)₂, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and $v = 1, 2, 3, 4$ or 5 , particularly preferably $1, 2$ or 3 .

- 25 A further alternative embodiment relates to the use according to the invention of a catalyst system comprising at least one compound of the general formula (Z) and a catalyst of the general formula (G), (H) or (K),





where

M is osmium or ruthenium,

X¹ and X² are identical or different and are two ligands, preferably anionic ligands,

L is a ligand, preferably an uncharged electron donor,

Z¹ and Z² are identical or different and are uncharged electron donors,

R²¹ and R²² are each, independently of one another, hydrogen, alkyl, cycloalkyl, alkenyl, alkynyl, aryl, carboxylate, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxy carbonyl, alkylamino, alkylthio, alkylsulphonyl or alkylsulphinyl, each of which may be substituted by one or more radicals selected from among alkyl, halogen, alkoxy, aryl and heteroaryl.

The catalysts of the general formulae (G), (H) and (K) are known in principle, e.g. from WO 2003/011455 A1, WO 2003/087167 A2, *Organometallics* 2001, 20, 5314 and *Angew. Chem. Int. Ed.* 2002, 41, 4038. The catalysts are commercially available or can be synthesized by the preparative methods indicated in the abovementioned literature references.

Z¹ and Z²

In the catalyst systems which can be used according to the invention, use is made of catalysts of the general formulae (G), (H) and (K) in which Z¹ and Z² are identical or different and are uncharged electron donors. These ligands are usually weakly coordinating. They are typically optionally substituted heterocyclic groups. These can be 5- or 6-membered monocyclic groups having from 1 to 4, preferably from 1 to 3 and particularly preferably 1 or 2, heteroatoms or be bicyclic or polycyclic structures made up of 2, 3, 4 or 5 such 5- or 6-membered monocyclic groups, where all the abovementioned groups may optionally be substituted by one or more alkyl, preferably C₁-C₁₀-alkyl, cycloalkyl, preferably C₃-C₈-cycloalkyl, alkoxy, preferably C₁-C₁₀-alkoxy, halogen, preferably chlorine or bromine, aryl, preferably C₆-C₂₄-aryl, or heteroaryl, preferably C₅-C₂₃ heteroaryl radicals, which may each be substituted in turn by one or more groups, preferably groups selected from the group consisting of halogen, in particular chlorine or bromine, C₁-C₅-alkyl, C₁-C₅-alkoxy and phenyl.

Examples of Z^1 and Z^2 encompass nitrogen-containing heterocycles such as pyridines, pyridazines, bipyridines, pyrimidines, pyrazines, pyrazolidines, pyrrolidines, piperazines, indazoles, quinolines, purines, acridines, bisimidazoles, picolylimines, imidazolidines and pyrroles.

5

Z^1 and Z^2 can also be bridged with one another to form a cyclic structure. In this case, Z^1 and Z^2 form a single bidentate ligand.

L

10

In the catalysts of the general formulae (G), (H) and (K), L can have the same general, preferred and particularly preferred meanings as L in the general formulae (A) and (B).

R^{21} and R^{22}

15

In the catalysts of the general formulae (G), (H) and (K), R^{21} and R^{22} are identical or different and are each alkyl, preferably C_1 - C_{30} -alkyl, particularly preferably C_1 - C_{20} -alkyl, cycloalkyl, preferably C_3 - C_{20} -cycloalkyl, particularly preferably C_3 - C_8 -cycloalkyl, alkenyl, preferably C_2 - C_{20} -alkenyl, particularly preferably C_2 - C_{16} -alkenyl, alkynyl, preferably C_2 - C_{20} -alkynyl, particularly preferably C_2 - C_{16} -alkynyl, aryl, preferably C_6 - C_{24} -aryl, carboxylate, preferably C_1 - C_{20} -carboxylate, alkoxy, preferably C_1 - C_{20} -alkoxy, alkenyloxy, preferably C_2 - C_{20} -alkenyloxy, alkynyloxy, preferably C_2 - C_{20} -alkynyloxy, aryloxy, preferably C_6 - C_{24} -aryloxy, alkoxycarbonyl, preferably C_2 - C_{20} -alkoxycarbonyl, alkylamino, preferably C_1 - C_{30} -alkylamino, alkylthio, preferably C_1 - C_{30} -alkylthio, arylthio, preferably C_6 - C_{24} -arylthio, alkylsulphonyl, preferably C_1 - C_{20} -alkylsulphonyl, or alkylsulphinyl, preferably C_1 - C_{20} -alkylsulphinyl, where the abovementioned substituents may be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals.

25

X^1 and X^2

In the catalysts of the general formulae (G), (H) and (K), X^1 and X^2 are identical or different and can have the same general, preferred and particularly preferred meanings as given above for X^1 and X^2 in the general formula (A).

30

Preference is given to using catalysts of the general formulae (G), (H) and (K) in which

M is ruthenium,

X^1 and X^2 are both halogen, in particular chlorine,

R^1 and R^2 are identical or different and are 5- or 6-membered monocyclic groups having from 1 to 4, preferably from 1 to 3 and particularly preferably 1 or 2, heteroatoms or bicyclic or polycyclic structures made up of 2, 3, 4 or 5 such 5- or 6-membered monocyclic groups, where all the abovementioned groups may be substituted by


35

one or more alkyl, preferably C₁-C₁₀-alkyl, cycloalkyl, preferably C₃-C₈-cycloalkyl, alkoxy, preferably C₁-C₁₀-alkoxy, halogen, preferably chlorine or bromine, aryl, preferably C₆-C₂₄-aryl, or heteroaryl, preferably C₅-C₂₃-heteroaryl radicals,

R²¹ and R²² are identical or different and are each C₁-C₃₀-alkyl, C₃-C₂₀-cycloalkyl, C₂-C₂₀-alkenyl, C₂-C₂₀-alkynyl, C₆-C₂₄-aryl, C₁-C₂₀-carboxylate, C₁-C₂₀-alkoxy, C₂-C₂₀-alkenyloxy, C₂-C₂₀-alkynyloxy, C₆-C₂₄-aryloxy, C₂-C₂₀-alkoxycarbonyl, C₁-C₃₀-alkylamino, C₁-C₃₀-alkylthio, C₆-C₂₄-arylthio, C₁-C₂₀-alkylsulphonyl, C₁-C₂₀-alkylsulphinyl and

L has a structure of one of the above-described general formulae (IIa) and (IIb), in particular the formulae (IIIa) to (IIIf).

A particularly preferred catalyst which comes under the general formula (G) has the structure (XIX),





where

R²³ and R²⁴ are identical or different and are each halogen, straight-chain or branched C₁-C₂₀-alkyl, C₁-C₂₀-heteroalkyl, C₁-C₁₀-haloalkyl, C₁-C₁₀-alkoxy, C₆-C₂₄-aryl, preferably phenyl, formyl, nitro, a nitrogen heterocycle, preferably pyridine, piperidine or pyrazine, carboxy, alkylcarbonyl, halocarbonyl, carbamoyl, thiocarbamoyl, carbamido, thioformyl, amino, dialkylamino, trialkylsilyl or trialkoxysilyl.





The abovementioned radicals C₁-C₂₀-alkyl, C₁-C₂₀-heteroalkyl, C₁-C₁₀-haloalkyl, C₁-C₁₀-alkoxy, C₆-C₂₄-aryl, preferably phenyl, formyl, nitro, a nitrogen heterocycle, preferably pyridine, piperidine or pyrazine, carboxy, alkylcarbonyl, halocarbonyl, carbamoyl, thiocarbamoyl, carbamido, thioformyl, amino, trialkylsilyl and trialkoxysilyl may each in turn be substituted by one or more halogen, preferably fluorine, chlorine or bromine, C₁-C₅-alkyl, C₁-C₅-alkoxy or phenyl radicals.

Particularly preferred embodiments of the catalyst of the formula (XIX) have the structure (XIX a) or (XIX b), where R²³ and R²⁴ have the same meanings as given for the formula (XIX).




When R^{23} and R^{24} are each hydrogen, the compound is referred to as “Grubbs III catalyst” in the literature.


Further suitable catalysts which come under the general formulae (G), (H) and (K) have the structural formulae (XX)-(XXXI) below, where Mes is in each case 2,4,6-trimethylphenyl.




- 39 -




(XXIV)




(XXV)




(XXVI)





(XXVII)




(XXVIII)



(XXIX)



A further alternative embodiment relates to the use according to the invention of a catalyst system comprising at least one compound of the general formula (Z) and a catalyst (N) which has the general structural element (N1),



where the carbon atom denoted by "*" is bound via one or more double bonds to the basic catalyst framework and

R²⁵-R³² are identical or different and are each hydrogen, halogen, hydroxyl, aldehyde, keto, thiol, CF₃, nitro, nitroso, cyano, thiocyno, isocyanato, carbodiimide, carbamate, thiocarbamate, dithiocarbamate, amino, amido, imino, silyl, sulphonate (-SO₃⁻), -OSO₃⁻, -PO₃⁻ or OPO₃⁻ or alkyl, cycloalkyl, alkenyl, alkynyl, aryl, carboxylate, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxycarbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl, alkylsulphinyl, dialkylamino, alkylsilyl or alkoxysilyl, where these radicals can all optionally be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals, or alternatively two directly adjacent radicals from the group consisting of R²⁵-R³² can be bridged with inclusion of the ring carbons to which they are bound to form a cyclic group, preferably an aromatic system, or alternatively R⁸ may be bridged to another ligand of the ruthenium- or osmium-carbene complex catalyst,

m is 0 or 1 and
 A is oxygen, sulphur, $C(R^{33}R^{34})$, $N-R^{35}$, $-C(R^{36})=C(R^{37})-$, $-C(R^{36})(R^{38})-C(R^{37})(R^{39})-$,
 where $R^{33}-R^{39}$ are identical or different and can each have the same meanings as
 the radicals $R^{25}-R^{32}$.

5


The catalysts to be used according to the invention in the catalyst systems have the structural
 element of the general formula (N1), where the carbon atom denoted by "*" is bound via one or
 more double bonds to the basic catalyst framework. If the carbon atom denoted by "*" is bound via
 two or more double bonds to the basic catalyst framework, these double bonds can be cumulated or
 conjugated.

10

Such catalysts (N) have been described in the as yet unpublished German patent application
 number **DE 102007039695**, which is hereby incorporated by reference for the definition of the
 catalysts (N) and their preparation, in so far as this is permitted by the applicable jurisdictions.

15

The catalysts (N) having a structural element of the general formula (N1) include, for example,
 those of the **general formulae (N2a) and (N2b)** below,



20

where

M is ruthenium or osmium,

X^1 and X^2 are identical or different and are two ligands, preferably anionic ligands,

L^1 and L^2 are identical or different ligands, preferably uncharged electron donors, where L^2
 can, as an alternative, also be bridged with the radical R^8 ,

25


n is 0, 1, 2 or 3, preferably 0, 1 or 2,

n' is 1 or 2, preferably 1, and



$R^{25}-R^{32}$, m and A have the same meanings as in the general formula (N1).

In the catalysts of the general formula (N2a), the structural element of the general formula (N1) is bound via a double bond ($n = 0$) or via 2, 3 or 4 cumulated double bonds (in the case of $n = 1, 2$ or 3) to the central metal of the complex catalyst. In the catalysts according to the invention of the general formula (N2b), the structural element of the general formula (N1) is bound via conjugated double bonds to the metal of the complex catalyst. In both cases, a double bond in the direction of the central metal of the complex catalyst is located on the carbon atom denoted by “*”.

The catalysts of the general formulae (N10a) and (N10b) thus comprise catalysts in which the general structural elements (N3)-(N9)



are bound via the carbon atom denoted by “*” via one or more double bonds to the basic catalyst framework of the general formula (N10a) or (N10b)



where X^1 and X^2 , L^1 and L^2 , n , n' and R^{25} - R^{39} have the meanings given for the general formulae (N2a) and (N2b).

5 The ruthenium- or osmium-carbene catalysts according to the invention are typically pentacoordinated.

In the structural element of the general formula (N1),

10 R^{15} - R^{32} are identical or different and are each hydrogen, halogen, hydroxyl, aldehyde, keto, thiol, CF_3 , nitro, nitroso, cyano, thiocyno, isocyanato, carbodiimide, carbamate, thiocarbamate, dithiocarbamate, amino, amido, imino, silyl, sulphonate ($-SO_3^-$), $-OSO_3^-$, $-PO_3^-$ or OPO_3^- or alkyl, preferably C_1 - C_{20} -alkyl, in particular C_1 - C_6 -alkyl, cycloalkyl, preferably C_3 - C_{20} -cycloalkyl, in particular C_3 - C_8 -cycloalkyl, alkenyl, preferably C_2 - C_{20} -alkenyl, alkynyl, preferably C_2 - C_{20} -alkynyl, aryl, preferably C_6 - C_{24} -aryl, in particular phenyl, carboxylate, preferably C_1 - C_{20} -carboxylate, alkoxy, 15 preferably C_1 - C_{20} -alkoxy, alkenyloxy, preferably C_2 - C_{20} -alkenyloxy, alkynyloxy, preferably C_2 - C_{20} -alkynyloxy, aryloxy, preferably C_6 - C_{24} -aryloxy, alkoxycarbonyl, preferably C_2 - C_{20} -alkoxycarbonyl, alkylamino, preferably C_1 - C_{30} -alkylamino, alkylthio, preferably C_1 - C_{30} -alkylthio, arylthio, preferably C_6 - C_{24} -arylthio, alkylsulphonyl, preferably C_1 - C_{20} -alkylsulphonyl, alkylsulphinyl, preferably C_1 - C_{20} -alkylsulphinyl, dialkylamino, preferably di(C_1 - C_{20} -alkyl)amino, alkylsilyl, preferably C_1 - C_{20} -alkylsilyl, or alkoxysilyl, preferably C_1 - C_{20} -alkoxysilyl, where 20 these radicals may all optionally be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals, or alternatively two directly adjacent radicals from the group consisting of R^{25} - R^{32} can also be bridged with inclusion of the ring carbons to which they are bound to form a cyclic group, preferably an aromatic 25 system, or alternatively R^8 may be bridged with another ligand of the ruthenium- or osmium-carbene complex catalyst,

m is 0 or 1 and

30 A is oxygen, sulphur, $C(R^{33})(R^{34})$, $N-R^{35}$, $-C(R^{36})=C(R^{37})-$ or $-C(R^{36})(R^{38})-C(R^{37})(R^{39})-$, where R^{33} - R^{39} are identical or different and can each have the same preferred meanings as the radicals R^1 - R^8 .

35 C_1 - C_6 -alkyl in the structural element of the general formula (N1) is, for example, methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, tert-butyl, n-pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, neopentyl, 1-ethylpropyl or n-hexyl.

C_3 - C_8 -cycloalkyl in the structural element of the general formula (N1) is, for example,

cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl or cyclooctyl.

C₆-C₂₄-aryl in the structural element of the general formula (N1) is an aromatic radical having from 6 to 24 skeletal carbon atoms. As preferred monocyclic, bicyclic or tricyclic carbocyclic aromatic radicals having from 6 to 10 skeletal carbon atoms, mention may be made of, for example, phenyl, biphenyl, naphthyl, phenanthrenyl and anthracenyl.

The radicals X¹ and X² in the structural element of the general formula (N1) have the same general, preferred and particularly preferred meanings given for catalysts of the general formula A.

10

In the general formulae (N2a) and (N2b) and analogously in the general formulae (N10a) and (N10b), the radicals L¹ and L² are identical or different ligands, preferably uncharged electron donors, and can have the same general, preferred and particularly preferred meanings given for the catalysts of the general formula A.

15

Preference is given to using catalysts of the general formulae (N2a) and (N2b) having a general structural unit (N1) in which

M is ruthenium,

X¹ and X² are both halogen,

20 n is 0,1 or 2 in the general formula (N2a) or

n' is 1 in the general formula (N2b),

L¹ and L² are identical or different and have the general or preferred meanings given for the general formulae (N2a) and (N2b),

R²⁵-R³² are identical or different and have the general or preferred meanings given for the general formulae (N2a) and (N2b),

25

m is either 0 or 1

and, when m = 1

A is oxygen, sulphur, C(C₁-C₁₀-alkyl)₂, -C(C₁-C₁₀-alkyl)₂-C(C₁-C₁₀-alkyl)₂-, -C(C₁-C₁₀-alkyl)=C(C₁-C₁₀-alkyl)- or -N(C₁-C₁₀-alkyl).

30

Very particular preference is given to using catalysts of the formulae (N2a) or (N2b) having a general structural unit (N1) in which

M is ruthenium,

X¹ and X² are both chlorine,

35 n is 0,1 or 2 in the general formula (N2a) or

n' is 1 in the general formula (N2b),

L¹ is an imidazolidine radical of one of the formulae (IIIa) to (IIIf),


L^2 is a sulphonated phosphine, phosphate, phosphinite, phosphonite, arsine, stibine, ether, amine, amide, sulphoxide, carboxyl, nitrosyl, pyridine radical, an imidazolidine radical of one of the formulae (XIIa) to (XII f) or a phosphine ligand, in particular PPh_3 , $P(p\text{-tol})_3$, $P(o\text{-tol})_3$, $PPh(CH_3)_2$, $P(CF_3)_3$, $P(p\text{-FC}_6\text{H}_4)_3$, $P(p\text{-CF}_3\text{C}_6\text{H}_4)_3$, $P(C_6\text{H}_4\text{-SO}_3\text{Na})_3$, $P(CH_2\text{C}_6\text{H}_4\text{-SO}_3\text{Na})_3$, $P(\text{isopropyl})_3$, $P(CHCH_3(CH_2CH_3))_3$, $P(\text{cyclopentyl})_3$, $P(\text{cyclohexyl})_3$, $P(\text{neopentyl})_3$ and $P(\text{neophenyl})_3$,

$R^{25}\text{-}R^{32}$ have the general or preferred meanings given for the general formulae (N2a) and (N2b),


m is either 0 or 1
and, when $m = 1$,

A is oxygen, sulphur, $C(C_1\text{-}C_{10}\text{-alkyl})_2$, $-C(C_1\text{-}C_{10}\text{-alkyl})_2\text{-}C(C_1\text{-}C_{10}\text{-alkyl})_2\text{-}$, $-C(C_1\text{-}C_{10}\text{-alkyl})=C(C_1\text{-}C_{10}\text{-alkyl})\text{-}$ or $-N(C_1\text{-}C_{10}\text{-alkyl})$.

If the radical R^{25} is bridged with another ligand of the catalyst of the formula N, this results, for example, in the case of the catalysts of the general formulae (N2a) and (N2b) in the following structures of the general formulae (N13a) and (N13b)



(N13a)



(N13b)

where

Y^1 is oxygen, sulphur, an $N\text{-}R^{41}$ radical or a $P\text{-}R^{41}$ radical, where R^{41} has the following meanings,

R^{40} and R^{41} are identical or different and are each an alkyl, cycloalkyl, alkenyl, alkynyl, aryl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxycarbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl or alkylsulphinyl radical, which may all optionally be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals,







p is 0 or 1 and

Y^2 where $p = 1$ is, $-(CH_2)_r\text{-}$ where $r = 1, 2$ or 3 , $-C(=O)\text{-CH}_2\text{-}$, $-C(=O)\text{-}$, $-N=CH\text{-}$, $-N(H)\text{-C(=O)\text{-}}$ or alternatively the total structural unit " $-Y^1(R^{40})\text{-}(Y^2)_p\text{-}$ " is




$(-N(R^{40})=CH-CH_2-)$, $(-N(R^{40},R^{41})=CH-CH_2-)$ and


where M, X^1 , X^2 , L^1 , R^{25} - R^{32} , A, m and n have the same meanings as in the general formulae (IIa) and (IIb).

- 5 Preferred catalyst systems contain a compound of the general formula (Z) in which the BF_mX_n moiety is BF_3 , BF_2Cl , $BFCl_2$, BF_2Br , BBr_2 , $BF_2(OC_2H_5)$, $BF(OC_2H_5)_2$, $BF_2(CH_3)$ and $BF(CH_3)_2$, D is selected from the group consisting of water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid and toluenesulphonic acid and $v = 1, 2, 3, 4$ or 5 , particularly preferably 1, 2 or 3, together with a catalyst of the formula (N) having one of the structures shown below.




15





5

Catalysts (N) can be prepared by reaction of suitable catalyst precursor complexes with suitable diazo compounds when this synthesis is carried out in a specific temperature range and at the same time the molar ratio of the starting materials is in a selected range. For this purpose, a catalyst precursor compound is, for example, reacted with a compound of the general formula (N1-Azo)



where R^{25} - R^{32} , m and A have the meanings given for the general formula (N1), with this reaction being carried out

- (i) at a temperature in the range from -20°C to 100°C , preferably in the range from $+10^{\circ}\text{C}$ to $+80^{\circ}\text{C}$, particularly preferably in the range from $+30$ to $+50^{\circ}\text{C}$, and
- (ii) at a molar ratio of the catalyst precursor compound to the compound of the general formula (N1-Azo) of from 1:0.5 to 1:5, preferably from 1:1.5 to 1:2.5, particularly preferably 1:2.

The compounds of the general formula (N1-Azo) are 9-diazafluorene or various derivatives thereof depending on the meanings of the radicals R^{25} - R^{32} and A . It is possible to use a variety of derivatives of 9-diazafluorene. In this way, a wide variety of fluorenylidene derivatives can be obtained.

The catalyst precursor compounds are ruthenium or osmium complex catalysts which do not yet contain any ligand having the general structural element (N1).

In this reaction, a ligand leaves the catalyst precursor compound and a carbene ligand containing the general structural element (N1) is taken up.


The reaction can be carried out using saturated, unsaturated and aromatic hydrocarbons, ethers and halogenated solvents. Preference is given to chlorinated solvents such as dichloromethane, 1,2-dichloroethane or chlorobenzene. The catalyst precursor compound in the form of the ruthenium or osmium precursor is usually initially charged in a preferably dried solvent. The concentration of the ruthenium or osmium precursor in the solvent is usually in the range from 15 to 25% by weight, preferably in the range from 50 to 20% by weight. The solution can subsequently be heated. It has been found to be particularly useful to heat the solution to a temperature in the range from 30 to 50°C . The compound of the general formula (N1-Azo) in a usually dried, preferably water-free solvent is then added. The concentration of the compound of the general formula (N1-Azo) in the solvent is preferably in the range from 5 to 15% by weight, preferably about 10%. To complete the reaction, the mixture is allowed to react further for from 0.5 h to 1.5 h at a

temperature which is particularly preferably in the same range as mentioned above, i.e. from 30 to 50°C. The solvent is subsequently removed and the residue is purified by extraction, for example with a mixture of hexane with an aromatic solvent.

The catalyst according to the invention is usually not obtained in pure form but in an equimolar, determined by the stoichiometry of the reaction, mixture with the reaction product of the compound of the general formula (N1-Azo) with the leaving ligand of the catalyst precursor compound used in the reaction. The leaving ligand is preferably a phosphine ligand. This reaction product can be removed in order to obtain the pure catalyst according to the invention. However, metathesis reactions can be catalysed using not only the pure catalyst according to the invention but also the mixture of this catalyst according to the invention with the abovementioned reaction product.

The above-described process is described in more detail below:

In the case of the **catalysts of the general formulae (N2a) and (N2b)**, a catalyst precursor compound of the general formula ("N2 precursor"),



where

M, X¹, X², L¹ and L² have the same general and preferred meanings as in the general formulae (N2a) and (N2b) and

LL is a "leaving ligand" and can have the same meanings as L¹ and L² in the general formulae (N2a) and (N2b), preferably a phosphine ligand having one of the meanings given for the general formulae (N2a) and (N2b),

is reacted with a compound of the general formula (N1-Azo) at a temperature in the range from -20°C to 100°C, preferably in the range from +10°C to +80°C, particularly preferably in the range from +30 to +50°C, and at a molar ratio of the catalyst precursor compound of the general formula (XVII) to the compound of the general formula (N1-Azo) of from 1:0.5 to 1:5, preferably from 1:1.5 to 1:2.5, particularly preferably 1:2. Further examples of the preparation of such catalysts of the formula (N) are given in the as yet unpublished patent application DE 102007039695.

In the catalyst system to be used according to the invention, the metathesis catalyst and the compound of the general formula (Z) are used in a molar ratio of [metathesis catalyst: compound of the general formula (Z)] = 1: (0.1-1000), preferably 1: (0.5-100) and particularly preferably 1: (1-50).

In the use according to the invention of the catalyst system in the metathesis reaction of nitrile rubbers, the compound of the general formula (Z) can be added in a solvent or dispersion medium or without solvent or dispersion medium to the complex catalyst or its solution in order to obtain the catalyst system according to the invention.

As solvent or dispersion medium in which the compound of the general formula (Z) is added to the complex catalyst or its solution, it is possible to use all known solvents or dispersion media. For the addition of the compound of the general formula (Z) to be effective, it is not necessary for the compound of the general formula (Z) to be soluble in the dispersion medium. Preferred solvents or dispersion media include, but are not restricted to, acetone, benzene, chlorobenzene, chloroform, cyclohexane, dichloromethane, diethyl ether, dioxane, dimethylformamide, dimethylacetamide, dimethylsulphone, dimethyl sulphoxide, methyl ethyl ketone, tetrahydrofuran, tetrahydropyran and toluene. The solvent or dispersion medium is preferably inert towards the complex catalyst.

The abovementioned catalyst systems are, according to the invention, used for the metathesis of nitrile rubber. Their use according to the invention is then a process for reducing the molecular weight of the nitrile rubber by bringing the nitrile rubber into contact with the catalyst system of the invention. This reaction is a cross-metathesis.

In the use according to the invention of the catalyst systems for the metathesis of nitrile rubber, the amount in which the compound of the general formula (Z) is used, based on the nitrile rubber to be degraded, is in the range from 0.0001 phr to 5 phr, preferably from 0.001 phr to 2 phr (phr = parts by weight per 100 parts by weight of rubber).

For use in the NBR metathesis, too, the compound of the general formula (Z) can be added in a solvent or dispersion medium or without solvent or dispersion medium to a solution of the complex catalyst. As an alternative, the compound of the general formula (Z) can also be added directly to a solution of the nitrile rubber to be degraded to which the complex catalyst is also added, so that the entire catalyst system according to the invention is present in the reaction mixture.

The amount of complex catalyst based on the nitrile rubber used depends on the nature and the catalytic activity of the specific complex catalyst. The amount of complex catalyst used is usually from 1 to 1000 ppm of noble metal, preferably from 2 to 500 ppm, in particular from 5 to 250 ppm, based on the nitrile rubber used.

The NBR metathesis can be carried out in the absence or presence of a coolefin. This coolefin is preferably a straight-chain or branched C₂-C₁₆-olefin. Suitable coolefins are, for example, ethylene, propylene, isobutene, styrene, 1-hexene and 1-octene. Preference is given to using 1-hexene or 1-octene. If the coolefin is liquid (as in the case of, for example, 1-hexene), the amount of coolefin is preferably in the range 0.2-20% by weight, based on the nitrile rubber used. If the coolefin is a gas, as in the case of, for example, ethylene, the amount of coolefin is selected so that a pressure in the range 1×10^5 Pa – 1×10^7 Pa, preferably a pressure in the range from 5.2×10^5 Pa to 4×10^6 Pa, is established in the reaction vessel at room temperature.

The metathesis reaction can be carried out in a suitable solvent which does not deactivate the catalyst used and also does not have an adverse effect on the reaction in any other way. Preferred solvents include, but are not restricted to, dichloromethane, benzene, toluene, methyl ethyl ketone, acetone, tetrahydrofuran, tetrahydropyran, dioxane, cyclohexane and chlorobenzene. The particularly preferred solvent is chlorobenzene. In some cases when the coolefin itself can function as solvent, e.g. in the case of 1-hexene, the addition of a further additional solvent can be dispensed with.

The concentration of the nitrile rubber used in the reaction mixture of the metathesis is not critical, but it should naturally be ensured that the reaction is not adversely affected by an excessively high viscosity of the reaction mixture and the associated mixing problems. The concentration of NBR in the reaction mixture is preferably in the range from 1 to 25% by weight, particularly preferably in the range from 5 to 20% by weight, based on the total reaction mixture.

The metathetic degradation is usually carried out at a temperature in the range from 10°C to 150°C, preferably at a temperature in the range from 20 to 100°C.

The reaction time depends on a number of factors, for example on the type of NBR, the type of catalyst, the catalyst concentration used and the reaction temperature. The reaction is typically complete within five hours under normal conditions. The progress of the metathesis can be monitored by standard analytical methods, e.g. by GPC measurements or by determination of the viscosity.

As nitrile rubbers ("NBR"), it is possible to use copolymers or terpolymers which contain repeating units of at least one conjugated diene, at least one α,β -unsaturated nitrile and, if appropriate, one or more further copolymerizable monomers in the metathesis reaction.

The conjugated diene can be of any nature. Preference is given to using (C₄-C₆)-conjugated dienes.

Particular preference is given to 1,3-butadiene, isoprene, 2,3-dimethylbutadiene, piperylene or mixtures thereof. In particular, use is made of 1,3-butadiene or isoprene or mixtures thereof. Very particular preference is given to 1,3-butadiene.

- 5 As α,β -unsaturated nitrile, it is possible to use any known α,β -unsaturated nitrile, with preference being given to (C₃-C₅)- α,β -unsaturated nitriles such as acrylonitrile, methacrylonitrile, ethacrylonitrile or mixtures thereof. Particular preference is given to acrylonitrile.

A particularly preferred nitrile rubber is thus a copolymer of acrylonitrile and 1,3-butadiene.

10

- In addition to the conjugated diene and the α,β -unsaturated nitrile, it is possible to use one or more further copolymerizable monomers known to those skilled in the art, e.g. α,β -unsaturated monocarboxylic or dicarboxylic acids, their esters or amides. As α,β -unsaturated monocarboxylic or dicarboxylic acids, preference is given to fumaric acid, maleic acid, acrylic acid and methacrylic acid. As esters of α,β -unsaturated carboxylic acids, preference is given to using their alkyl esters and alkoxyalkyl esters. Particularly preferred alkyl esters of α,β -unsaturated carboxylic acids are methyl acrylate, ethyl acrylate, butyl acrylate, butyl methacrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate and octyl acrylate. Particularly preferred alkoxyalkyl esters of α,β -unsaturated carboxylic acids are methoxyethyl (meth)acrylate, ethoxyethyl (meth)acrylate and methoxyethyl (meth)acrylate. It is also possible to use mixtures of alkyl esters, e.g. those mentioned above, with alkoxyalkyl esters, e.g. in the form of those mentioned above.
- 15
- 20

- The proportions of conjugated diene and α,β -unsaturated nitrile in the NBR polymers to be used can vary within wide ranges. The proportion of the conjugated diene or the sum of conjugated dienes is usually in the range from 40 to 90% by weight, preferably in the range from 60 to 85% by weight, based on the total polymer. The proportion of the α,β -unsaturated nitrile or the sum of α,β -unsaturated nitriles is usually from 10 to 60% by weight, preferably from 15 to 40% by weight, based on the total polymer. The proportions of the monomers in each case add up to 100% by weight. The additional monomers can be present in amounts of from 0 to 40% by weight, preferably from 0.1 to 40% by weight, particularly preferably from 1 to 30% by weight, based on the total polymer. In this case, corresponding proportions of the conjugated diene or dienes and/or the α,β -unsaturated nitrile or nitriles are replaced by proportions of the additional monomers, with the proportions of all monomers in each case adding up to 100% by weight.
- 25
- 30

- 35 The preparation of the nitrile rubbers by polymerization of the abovementioned monomers is adequately known to those skilled in the art and is comprehensively described in the literature.

Nitrile rubbers which can be used for the purposes of the invention are also commercially available, e.g. as products from the product range of the Perbunan[®] and Krynac[®] grades of Lanxess Deutschland GmbH.

5 The nitrile rubbers used for the metathesis have a Mooney viscosity (ML 1+4 at 100°C) in the range from 30 to 70, preferably from 30 to 50. This corresponds to a weight average molecular weight M_w in the range 150 000 – 500 000, preferably in the range 180 000– 400 000. Furthermore, the nitrile rubbers used have a polydispersity $PDI = M_w/M_n$, where M_w is the weight average molecular weight and M_n is the number average molecular weight, in the range 2.0 – 6.0 and
10 preferably in the range 2.0 – 4.0.

The determination of the Mooney viscosity is carried out in accordance with ASTM Standard D 1646.

15 The nitrile rubbers obtained by the metathesis process of the invention have a Mooney viscosity (ML 1+4 at 100°C) in the range 5 – 30, preferably in the range 5 – 20. This corresponds to a weight average molecular weight M_w in the range 10 000-100 000, preferably in the range 10 000– 80 000. Furthermore, the nitrile rubbers obtained have a polydispersity $PDI = M_w/M_n$, where M_n is the number average molecular weight and M_w is the weight average molecular weight, in the range
20 1.4 - 4.0, preferably in the range 1.5 – 3.0.

The metathetic degradation in the presence of the catalyst system of the invention can be followed by a hydration of the degraded nitrile rubbers obtained. This can be carried out in a manner known to those skilled in the art.

25 The hydration can be carried out using homogeneous or heterogeneous hydration catalysts. It is also possible to carry out the hydration in situ, i.e. in the same reaction mixture in which the metathetic degradation has previously taken place and without the need to isolate the degraded nitrile rubber. The hydration catalyst is simply introduced into the reaction vessel.

30 The catalysts used are usually based on rhodium, ruthenium or titanium, but it is also possible to use platinum, iridium, palladium, rhenium, ruthenium, osmium, cobalt or copper either as metal or preferably in the form of metal compounds (see, for example, US-A-3,700,637, DE-A-25 39 132, EP-A-0 134 023, DE-A-35 41 689, DE-A-35 40 918, EP-A-0 298 386, DE-A-35 29 252,
35 DE-A-34 33 392, US-A-4,464,515 and US-A-4,503,196).

Suitable catalysts and solvents for a hydration in the homogeneous phase are described below and

are also known from **DE-A-25 39 132** and **EP-A-0 471 250**.

The selective hydration can, for example, be achieved in the presence of a rhodium- or ruthenium-containing catalyst. It is possible to use, for example, a catalyst of the general formula



where M is ruthenium or rhodium is, the radicals R^1 are identical or different and are each a C_1 - C_8 -alkyl group, a C_4 - C_8 -cycloalkyl group, a C_6 - C_{15} -aryl group or a C_7 - C_{15} -aralkyl group. B is phosphorus, arsenic, sulphur or a sulfoxide group $S=O$, X is hydrogen or an anion, preferably halogen and particularly preferably chlorine or bromine, l is 2, 3 or 4, m is 2 or 3 and n is 1, 2 or 3, preferably 1 or 3. Preferred catalysts are tris(triphenylphosphine)rhodium(I) chloride, tris(triphenylphosphine)rhodium(III) chloride and tris(dimethylsulphoxide)rhodium(III) chloride and also tetrakis(triphenylphosphine)rhodium hydride of the formula $(C_6H_5)_3P)_4RhH$ and the corresponding compounds in which all or part of the triphenylphosphine has been replaced by tricyclohexylphosphine. The catalyst can be used in small amounts. An amount in the range 0.01-1% by weight, preferably in the range 0.03 to 0.5% by weight and particularly preferably in the range 0.1-0.3% by weight, based on the weight of the polymer, is suitable.

It is usually useful to use the catalyst together with a cocatalyst which is a ligand of the formula R^1_mB , where R^1 , m and B have the meanings given above for the catalyst. Preference is given to m being 3, B being phosphorus and the radicals R^1 can be identical or different. The cocatalysts preferably have trialkyl, tricycloalkyl, triaryl, triaralkyl, diarylmonoalkyl, diarylmonocycloalkyl, dialkylmonoaryl, dialkylmonocycloalkyl, dicycloalkylmonoaryl or dicyclalkylmonoaryl radicals.

Examples of cocatalysts may be found, for example, in **US-A-4,631,315**. A preferred cocatalyst is triphenylphosphine. The cocatalyst is preferably used in amounts in the range 0.1-5% by weight, preferably in the range 0.3-4% by weight, based on the weight of the nitrile rubber to be hydrated. Furthermore, the weight ratio of the rhodium-containing catalyst to the cocatalyst is preferably in the range from 1:3 to 1:55, particularly preferably in the range from 1:5 to 1:45. Based on 100 parts by weight of the nitrile rubber to be hydrated, it is appropriate to use from 0.1 to 33 parts by weight of the cocatalyst, preferably from 0.5 to 20 parts by weight and very particularly preferably from 1 to 5 parts by weight, in particular more than 2 but less than 5 parts by weight, of cocatalyst.

The practical procedure for carrying out this hydration is adequately known to those skilled in the art from **US-A-6,683,136**. The nitrile rubber to be hydrated is usually treated in a solvent such as toluene or monochlorobenzene with hydrogen at a temperature in the range from 100 to 150°C and a pressure in the range from 50 to 150 bar for from 2 to 10 hours.

For the purposes of the present invention, hydration is a reaction of at least 50%, preferably 70-100%, particularly preferably 80-100%, of the double bonds present in the starting nitrile rubber. Residual contents of double bonds in HNBR of from 0 to 8% are also particularly preferred.

5

When heterogeneous catalysts are used, these are usually supported catalysts based on palladium which are supported, for example, on carbon, silica, calcium carbonate or barium sulphate.

10

After the hydration is complete, a hydrated nitrile rubber having a Mooney viscosity (ML 1+4 at 100°C), measured in accordance with ASTM Standard D 1646, in the range 1 – 50 is obtained. This corresponds approximately to a weight average molecular weight M_w in the range 2000 - 400 000 g/mol. The Mooney viscosity (ML 1+4 at 100°C) is preferably in the range from 5 to 30. This corresponds approximately to a weight average molecular weight M_w in the range of about 20 000 – 200 000. Furthermore, the hydrated nitrile rubbers obtained have a polydispersity $PDI = M_w/M_n$, where M_w is the weight average molecular weight and M_n is the number average molecular weight, in the range 1 – 5 and preferably in the range 1.5 – 3.

15

20

However, the catalyst system cannot only be used successfully for the metathetic degradation of nitrile rubbers but can also be used universally for other metathesis reactions. In a process for ring-closing metathesis, the catalyst system of the invention is brought into contact with the appropriate acyclic starting material, e.g. diethyl diallylmalonate.

25




30

The use according to the invention of the catalyst systems comprising metathesis catalyst and the fluorine-containing boron compound of the general formula (Z) allows, at comparable reaction times, the amount of the actual metathesis catalyst and thus the amount of noble metal to be significantly reduced compared to analogous metathesis reactions in which only the catalyst is used, i.e. without addition of a fluorine-containing boron compound of the general formula (Z). When comparable noble metal contents are used, the reaction time is substantially shortened by the addition of the fluorine-containing boron compound of the general formula (Z). When used for the degradation of nitrile rubbers, degraded nitrile rubbers having significantly lower molecular weights M_w and M_n can be achieved.

EXAMPLES

When the following examples are carried out at room temperature, this is 22 +/- 2°C. In the examples below, the **complex catalysts** shown in Table 1 were used.

5 **Table 1:**

Name of catalyst	Structural formula	Molecular weight [g/mol]	Source
Grubbs II Catalyst		848.33	Materia / Pasadena; USA
Hoveyda Catalyst		626.14	Aldrich
Grela Catalyst		671.13	Prepared as described in J. Org. Chem. 2004, 69, 6894-6896

The following examples according to the invention were carried out using the compounds of the general formula (Z) shown in Table 2.

10 **Table 2:**

Name of additive	Formula	Source
Diethyl ether adduct of boron trifluoride	BF ₃ *C ₄ H ₁₀ O	Acros Organics
Ethylamine adduct of boron trifluoride	BF ₃ *EtNH ₂	Aldrich
Tetrahydrofuran adduct of boron trifluoride	BF ₃ *C ₄ H ₈ O	Aldrich
n-Propanol adduct of boron trifluoride	BF ₃ *C ₃ H ₇ OH	Aldrich
Acetic acid adduct of boron trifluoride	BF ₃ *CH ₃ COOH	Aldrich

The examples carried out on the metathetic degradation of nitrile rubber are summarized in terms

of the complex catalysts used, the compound of the general formula (Z) and the molar ratio of complex catalyst: additive used in Table 3 below.

Table 3:

Experiment		Catalyst	Additive	Molar ratio of catalyst:additive
1.0	not according to the invention	Grubbs II	-	-
1.1	according to the invention	Grubbs II	BF ₃ *Et ₂ O	1:22
1.2	according to the invention	Grubbs II	BF ₃ *Et ₂ O	1:5
1.3	according to the invention	Grubbs II	BF ₃ *Et ₂ O	1:2
1.4	according to the invention	Grubbs II	BF ₃ *Et ₂ O	1:1
1.5	according to the invention	Grubbs II	BF ₃ *EtNH ₂	1:22
1.6	according to the invention	Grubbs II	BF ₃ *THF	1:22
1.7	according to the invention	Grubbs II	BF ₃ *n-Propanol	1:22
1.8	according to the invention	Grubbs II	BF ₃ *CH ₃ COOH	1:22
2.0	not according to the invention	Grela	-	-
2.1	according to the invention	Grela	BF ₃ *Et ₂ O	1:22

5

Nitrile rubber used:

The degradation reactions described in the following examples were carried out using the nitrile rubber Perbunan® 3436 F from Lanxess Deutschland GmbH.

10 This nitrile rubber had the following characteristic properties:

Acrylonitrile content: 34.3% by weight

Mooney Viscosity (ML 1+4 at 100°C): 33 Mooney units

Residual moisture content: 1.0% by weight

M_w: 211 kg/mol

15 M_n: 82 kg/mol

PDI (M_w / M_n): 2.6

Procedure for the metathesis of the nitrile rubber:

20 The metathetic degradation was in each case carried out using 293.3 g of chlorobenzene (hereinafter referred to as "MCB"/Aldrich), which was distilled and made inert at room temperature by passing argon through it before use. To carry out the degradation, 40 g of NBR

were dissolved over a period of 12 hours while stirring at room temperature. In each case, 0.8 g (2 phr) of 1-hexene and then the boron compounds indicated in the tables (dissolved in 10 g of MCB which had been made inert) were added to the NBR-containing solution and the mixture was homogenized by stirring for 30 minutes.

5

The Ru catalysts (Grubbs II, Hoveyda and Grela catalyst) were in each case dissolved under argon in 10 g of MCB which had been made inert, with the addition of the catalyst solutions to the NBR solutions in MCB being carried out immediately after the preparation of the catalyst solutions.

10

The metathesis reactions were carried out at room temperature using the amounts of starting materials indicated in the following tables.

15

After the reaction times indicated in the tables, about 3 ml were in each case taken from the reaction solutions and the reaction was stopped by immediate addition of about 0.2 ml of ethyl vinyl ether. 0.2 ml was taken from the stopped solution and diluted with 3 ml of DMAc (N,N-dimethylacetamide (stabilized with LiBr 0.075M; from Aldrich)).

20

To carry out the GPC analysis, the solutions were in each case filtered by means of a 0.2 μ m Teflon syringe filter (Chromafil PTFE 0.2 mm; from Machery-Nagel). The GPC analysis was subsequently carried out using an instrument from Waters (Mod. 510). A combination of a precolumn (PL Guard from Polymer Laboratories) with two Resipore columns (300 $\times$ 7.5 mm, pore size: 3 μ m) from Polymer Laboratories was used for the analysis. The columns were calibrated using linear polystyrene having molar masses from 960 to 6×10^5 g/mol from Polymer Standards Services. An RI detector from Waters (Waters 410 Differential Refractometer) was used as detector. The analysis was carried out at a flow rate of 1.0 ml/min at 80°C using N,N'-dimethylacetamide as eluent. The evaluation of the GPC curves was carried out using software from Polymer Laboratories (Cirrus Multi Version 3.0).

25

Series 1: Use of the Grubbs II catalyst in combination with various fluorine-containing boron compounds in the metathetic degradation of NBR

Experiment 1.0: Use of the Grubbs II catalyst without additive (not according to the invention)

5

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M _w [kg/mol]	M _n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	139	66	2.1
							60	101	54	1.9
							185			
[g]	[mg]	[phr]	[g]	[phr]		[mg]		77	45	1.7
40	20	0.05	0.8	2.0	-	-	425	62	37	1.7

Experiment 1.1: Use of the Grubbs II catalyst in combination with BF₃*Et₂O at a molar ratio of Grubbs II/ BF₃*Et₂O = 1:22 (according to the invention)

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M _w [kg/mol]	M _n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	16	7	2.3
							60	10	6	1.7
							185			
[g]	[mg]	[phr]	[g]	[phr]		[mg]		11	6	1.8
40	20	0.05	0.8	2.0	BF ₃ * Et ₂ O	74	425	10	6	1.7

10

Experiment 1.2: Use of the Grubbs II catalyst in combination with BF₃*Et₂O at a molar ratio of Grubbs II/BF₃*Et₂O = 1:5 (according to the invention)

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M _w [kg/mol]	M _n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	115	53	2.2
							60	72	36	2.0
							185			
[g]	[mg]	[phr]	[g]	[phr]		[mg]		48	26	1.8
40	20	0.05	0.8	2.0	BF ₃ * Et ₂ O	16.7	425	34	18	1.9

Experiment 1.3: Use of the Grubbs II catalyst in combination with $\text{BF}_3 \cdot \text{Et}_2\text{O}$ at a molar ratio of Grubbs II/ $\text{BF}_3 \cdot \text{Et}_2\text{O}$ = 1:2 (according to the invention)

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M_w [kg/mol]	M_n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	129	63	2.0
							60	92	51	1.8
							185			
[g]	[mg]	[phr]	[g]	[phr]		[mg]		42	20	2.1
40	20	0.05	0.8	2.0	$\text{BF}_3 \cdot \text{Et}_2\text{O}$	7	425	35	18	1.9

5 **Experiment 1.4: Use of the Grubbs II catalyst in combination with $\text{BF}_3 \cdot \text{Et}_2\text{O}$ at a molar ratio of Grubbs II/ $\text{BF}_3 \cdot \text{Et}_2\text{O}$ = 1:1 (according to the invention)**

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M_w [kg/mol]	M_n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	136	63	2.2
							60	99	53	1.9
							185			
[g]	[mg]	[phr]	[g]	[phr]		[mg]		77	37	2.1
40	20	0.05	0.8	2.0	$\text{BF}_3 \cdot \text{Et}_2\text{O}$	3.4	425	59	30	2.0

10 **Experiment 1.5: Use of the Grubbs II catalyst in combination with $\text{BF}_3 \cdot \text{EtNH}_2$ at a molar ratio of Grubbs II/ $\text{BF}_3 \cdot \text{EtNH}_2$ = 1:22 (according to the invention)**

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M_w [kg/mol]	M_n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	110	49	2.2
							60	86	41	2.1
							185			
[g]	[mg]	[phr]	[g]	[phr]		[mg]		71	34	2.1
40	20	0.05	0.8	2.0	$\text{BF}_3 \cdot \text{EtNH}_2$	59	425	-	-	-

Experiment 1.6: Use of the Grubbs II catalyst in combination with BF₃*THF at a molar ratio of Grubbs II/ BF₃*THF = 1:22 (according to the invention)

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M _w [kg/mol]	M _n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	112	54	2.1
							60	-	-	-
							185			
[g]	[mg]	[phr]	[g]	[phr]		[mg]		-	-	-
40	20	0.05	0.8	2.0	BF ₃ *THF	73	425	-	-	-

5 **Experiment 1.7: Use of the Grubbs II catalyst in combination with BF₃*n-propanol at a molar ratio of Grubbs II/BF₃*n-propanol=1:22 (according to the invention)**

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M _w [kg/mol]	M _n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	87	44	2.0
							60	64	31	2.1
							185			
[g]	[mg]	[phr]	[g]	[phr]		[mg]		32	17	1.9
40	20	0.05	0.8	2.0	BF ₃ *n-propanol	66	425	24	14	1.7

10 **Experiment 1.8: Use of the Grubbs II catalyst in combination with BF₃*CH₃COOH at a molar ratio of Grubbs II/BF₃*CH₃COOH = 1:22 (according to the invention)**

NBR	Grubbs II catalyst		1-Hexene		Additive		Time [min.]	M _w [kg/mol]	M _n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	99	50	2.0
							60	-	-	-
							185	-	-	-
[g]	[mg]	[phr]	[g]	[phr]		[mg]		-	-	-
40	20	0.05	0.8	2.0	BF ₃ *CH ₃ COOH	98	425	-	-	-

15 In Series 1, it is shown that when using the Grubbs II catalyst, the metathetic degradation of nitrile rubber is accelerated by addition of compounds of the BF₃*D type; i.e. after the same reaction times, M_w, and M_n are significantly lower than in the reference experiment (experiment 1.0) which

was carried out without additives. In addition, it is shown that the effect according to the invention occurs at different molar ratios of Grubbs II catalyst: BF_3^*D .

Series 2: Use of the Grela catalyst in combination with $\text{BF}_3^*\text{Et}_2\text{O}$ in the metathetic degradation of NBR

Experiment 2.0: Use of the Grela catalyst without addition of boron compounds (not according to the invention)

NBR	Grela catalyst		1-Hexene		Additive		Time [min.]	M_w [kg/mol]	M_n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
							30	49	34	1.4
							60	48	31	1.6
							185			
[g]	[mg]	[phr]	[g]	[phr]		[g]		48	29	1.6
40	15.8	0.04	0.8	2.0	-	-	425	50	29	1.7

Experiment 2.1: Use of the Grela catalyst in combination with $\text{BF}_3^*\text{Et}_2\text{O}$ at a molar ratio of Grela catalyst/ $\text{BF}_3^*\text{Et}_2\text{O}$ = 1:22 (according to the invention)

NBR	Grela catalyst		1-Hexene		Additive		Time [min.]	M_w [kg/mol]	M_n [kg/mol]	PDI
Amount	Amount	Based on NBR	Amount	Based on NBR	Type	Amount	0	211	82	2.6
						[g]	30	38	20	1.9
							60	33	17	2.0
							185			
[g]	[mg]	[phr]	[g]	[phr]				33	17	1.9
40	15.8	0.04	0.8	2.0	BF_3^* Et_2O	0,0074	425	31	16	1.9

In series 2, it is shown that the metathetic degradation of nitrile rubber is accelerated when the Grela catalyst is used in combination with $\text{BF}_3^*\text{Et}_2\text{O}$; i.e. after the same reaction times, M_w , and M_n are significantly lower than in the reference experiment (experiment 2.0) which is carried out without an additive.

Claims:

1. Process for reducing the molecular weight of nitrile rubber, in which a nitrile rubber is brought into contact with a catalyst system and reacted, characterized in that the catalyst system comprises a metathesis catalyst which is a complex catalyst based on a metal of transition group 6 or 8 of the Periodic Table and has at least one ligand bound in a carbene-like fashion to the metal and also at least one compound of the general formula (Z)



where

m is 1, 2 or 3,

n is 0, 1 or 2 and at the same time

m + n = 3 and


v is 1, 2, 3, 4 or 5,

X is chlorine, bromine, iodine, an -OR or -NR₂ group, where the radicals R are each, independently of one another, a linear, branched, aliphatic, cyclic, heterocyclic or aromatic radical which has 1-33 carbon atoms and may optionally have from 1 to 15 further heteroatoms, and

D is a compound having at least one free electron pair, where D contains at least one heteroatom which is preferably selected from the group consisting of oxygen, sulphur, nitrogen, phosphorus, arsenic and antimony.

2. Process according to Claim 1, wherein a complex catalyst based on molybdenum, tungsten, osmium or ruthenium is used.

3. Process according to Claim 1, wherein compounds of the general formula (A),



where

M is osmium or ruthenium,

X¹ and X² are identical or different and are two ligands, preferably anionic ligands,

L represents identical or different ligands, preferably uncharged electron donors,


the radicals R are identical or different and are each hydrogen, an alkyl, preferably C₁-C₃₀-alkyl, cycloalkyl, preferably C₃-C₂₀-cycloalkyl, alkenyl, preferably C₂-

C₂₀-alkenyl, alkynyl, preferably C₂-C₂₀-alkynyl, aryl, preferably C₆-C₂₄-aryl, carboxylate, preferably C₁-C₂₀-carboxylate, alkoxy, preferably C₁-C₂₀-alkoxy, alkenyloxy, preferably C₂-C₂₀-alkenyloxy, alkynyloxy, preferably C₂-C₂₀-alkynyloxy, aryloxy, preferably C₆-C₂₄-aryloxy, alkoxycarbonyl, preferably C₂-C₂₀-alkoxycarbonyl, alkylamino, preferably C₁-C₃₀-alkylamino, alkylthio, preferably C₁-C₃₀-alkylthio, arylthio, preferably C₆-C₂₄-arylthio, alkylsulphonyl, preferably C₁-C₂₀-alkylsulphonyl, or alkylsulphinyl, preferably C₁-C₂₀-alkylsulphinyl, where these radicals can all optionally be substituted by one or more alkyl, halogen, preferably fluorine or chlorine, alkoxy, aryl- or heteroaryl radicals or alternatively the two radicals R are bridged with inclusion of the common C atom to which they are bound to form a cyclic group which can be aliphatic or aromatic in nature, may optionally be substituted and can contain one or more heteroatoms,


are used as catalyst.

4. Process according to Claim 3, wherein X¹ and X² are identical or different and are each hydrogen, halogen, pseudohalogen, straight-chain or branched C₁-C₃₀-alkyl, C₆-C₂₄-aryl, C₁-C₂₀-alkoxy, C₆-C₂₄-aryloxy, C₃-C₂₀-alkyldiketonate, C₆-C₂₄-aryldiketonate, C₁-C₂₀-carboxylate, C₁-C₂₀-alkylsulphonate, C₆-C₂₄-arylsulphonate, C₁-C₂₀-alkylthiol, C₆-C₂₄-arylthiol, C₁-C₂₀-alkylsulphonyl or C₁-C₂₀-alkylsulphinyl.
5. Process according to Claim 3 or 4, wherein X¹ and X² are identical or different and are each halogen, in particular fluorine, chlorine, bromine or iodine, benzoate, C₁-C₅-carboxylate, C₁-C₅-alkyl, phenoxy, C₁-C₅-alkoxy, C₁-C₅-alkylthiol, C₆-C₂₄-arylthiol, C₆-C₂₄-aryl or C₁-C₅-alkylsulphonate.
6. Process according to one or more of Claims 3 to 5, wherein X¹ and X² are identical and are each halogen, in particular chlorine, CF₃COO, CH₃COO, CFH₂COO, (CH₃)₃CO, (CF₃)₂(CH₃)CO, (CF₃)(CH₃)₂CO, PhO (phenoxy), MeO (methoxy), EtO (ethoxy), tosylate (p-CH₃-C₆H₄-SO₃), mesylate (2,4,6-trimethylphenyl) or CF₃SO₃ (trifluoromethane-sulphonate).
7. Process according to one or more of Claims 3 to 6, wherein the two ligands L are each, independently of one another, a phosphine, sulphonated phosphine, phosphate, phosphinite, phosphonite, arsine, stibine, ether, amine, amide, sulphoxide, carboxyl, nitrosyl, pyridine, thioether or imidazolidine ("Im") ligand.

8. Process according to Claim 7, wherein the imidazolidine radical (Im) has a structure of the general formulae (IIa) or (IIb),



(IIa)




(IIb)

where

R^8, R^9, R^{10}, R^{11} are identical or different and are each hydrogen, straight-chain or branched C_1 - C_{30} -alkyl, C_3 - C_{20} -cycloalkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl, C_6 - C_{24} -aryl, C_1 - C_{20} -carboxylate, C_1 - C_{20} -alkoxy, C_2 - C_{20} -alkenyloxy, C_2 - C_{20} -alkynyloxy, C_6 - C_{20} -aryloxy, C_2 - C_{20} -alkoxycarbonyl, C_1 - C_{20} -alkylthio, C_6 - C_{20} -arylthio, C_1 - C_{20} -alkylsulphonyl, C_1 - C_{20} -alkylsulphonate, C_6 - C_{20} -arylsulphonate or C_1 - C_{20} -alkylsulphinyl, where all the abovementioned radicals may optionally be substituted.

9. Process according to one or more of Claims 1 to 8, wherein catalysts of the general formula (A1),



(A1)

where

X^1, X^2 and L can have the same general, preferred and particularly preferred meanings as in the general formula (A),

n is 0, 1 or 2,


m is 0, 1, 2, 3 or 4 and

the radicals R' are identical or different and are each an alkyl, cycloalkyl, alkenyl, alkynyl, aryl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxycarbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl or alkylsulphinyl radical, which may all be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals,


are used.

10. Process according to Claim 1, wherein the catalyst has the structure (IV), (V) or (VI),

where Cy is in each case cyclohexyl, Mes is 2,4,6-trimethylphenyl and Ph is phenyl.



11. Process according to Claim 1, wherein catalysts of the general formula (B),



where

M is ruthenium or osmium,

Y is oxygen (O), sulphur (S), an N-R¹ radical or a P-R¹ radical,

X¹ and X² are identical or different ligands,

R¹ is an alkyl, cycloalkyl, alkenyl, alkynyl, aryl, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxycarbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl or alkylsulphinyl radical, which may all optionally be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals,

R², R³, R⁴ and R⁵ are identical or different and are each hydrogen or an organic or inorganic radical,


R⁶ is hydrogen or an alkyl, alkenyl, alkynyl or aryl radical and

L is a ligand which has the same meanings as the ligand L in the formula (A) set forth in Claim 3,


are used.

12. Process according to Claim 11, wherein L is a P(R⁷)₃ radical, where the radicals R⁷ are each, independently of one another, C₁-C₆-alkyl, C₃-C₈-cycloalkyl or aryl or else L is a substituted or unsubstituted imidazolidine radical ("Im") which preferably has the structure of the general formula (IIa) or (IIb) set forth in Claim 8 and particularly preferably has one of the structures (IIIa) to (IIIf) below, where Ph is in each case phenyl, Bu is butyl and Mes is a 2,4,6-trimethylphenyl radical or alternatively in each case a 2,6-diisopropylphenyl


radical.




(IIIa)




(IIIb)




(IIIc)



(IIIId)




(IIIe)



(IIIIf)

- 5 13. Process according to Claim 11 or 12, wherein X^1 and X^2 in the general formula (B) can have the meanings of X^1 and X^2 in any of Claims 4-6.
14. Process according to one or more of Claims 11 to 13, wherein catalysts of the general formula (B1),



10

where

M , L , X^1 , X^2 , R^1 , R^2 , R^3 , R^4 and R^5 have the meanings given for the general formula (B) in Claim 11,



are used.

15

15. Process according to Claim 14, wherein catalysts of the general formula (B1) in which
- M is ruthenium,
- X^1 and X^2 are both halogen, in particular chlorine,
- R^1 is a straight-chain or branched C_1 - C_{12} alkyl radical,
- 20 R^2 , R^3 , R^4 , R^5 have the meanings given for the general formula (B) in Claim 11 and

L has the meanings given for the general formula (B) in Claim 11,
are used.

16. Process according to Claim 14, wherein catalysts of the general formula (B1) in which
- 5 M is ruthenium,
X¹ and X² are both chlorine,
R¹ is an isopropyl radical,
R², R³, R⁴, R⁵ are all hydrogen and
L is a substituted or unsubstituted imidazolidine radical of the formula (IIa)
10 or (IIb),






where


R⁸, R⁹, R¹⁰, R¹¹ are identical or different and are each hydrogen, straight-chain
or branched C₁-C₃₀-alkyl, C₃-C₂₀-cycloalkyl, C₂-C₂₀-alkenyl, C₂-C₂₀-
15 alkynyl, C₆-C₂₄-aryl, C₁-C₂₀-carboxylate, C₁-C₂₀-alkoxy, C₂-C₂₀-
alkenyloxy, C₂-C₂₀-alkynyloxy, C₆-C₂₄-aryloxy, C₂-C₂₀-alkoxycarbonyl,
C₁-C₂₀-alkylthio, C₆-C₂₄-arylthio, C₁-C₂₀-alkylsulphonyl, C₁-C₂₀-
alkylsulphonate, C₆-C₂₄-arylsulphonate or C₁-C₂₀-alkylsulphinyl,

are used.


17. Process according to Claim 14, wherein a catalyst having one of the structures (VII),
(VIII), (IX), (X), (XI), (XII), (XIII), (XIV) and (XV), where Mes is in each case 2,4,6-
trimethylphenyl, is used as catalyst of the general structural formula (B1).




- 69 -




(X)




(XI)




(XII)



(XIII)




(XIV)



(XV)

- 5 18. Process according to Claim 11, wherein a catalyst of the general formula (B2),





where


M, L, X¹, X², R¹ and R⁶ have the meanings given for the general formula (B) in Claim 11, the radicals R¹² are identical or different and have the meanings given for the radicals R², R³, R⁴ and R⁵ in the general formula (B) in Claim 11, with the exception of hydrogen, and

n is 0, 1, 2 or 3,
is used.


19. Process according to Claim 18, wherein a catalyst having one of the following structures (XVI) and (XVII), where Mes is in each case 2,4,6-trimethylphenyl, is used.



20. Process according to Claim 11, wherein a catalyst of the general formula (B3),



where D^1 , D^2 , D^3 and D^4 in each case have a structure of the general formula (XVIII) shown below which is bound via the methylene group to the silicon of the formula (B3),




where

M , L , X^1 , X^2 , R^1 , R^2 , R^3 , R^5 and R^6 have the meanings given for the general formula (B) in Claim 11,

is used.


21. Process according to Claim 1, wherein a catalyst of the general formula (B4),



where the symbol $\bullet$ represents a support,
is used.

5

22. Process according to Claim 1, wherein a catalyst of the general formula (C),



where

M is ruthenium or osmium,

10

X^1 and X^2 are identical or different and are anionic ligands,

the radicals R' are identical or different and are organic radicals,


Im is a substituted or unsubstituted imidazolidine radical and

An is an anion,

is used.

15

23. Process according to Claim 1, wherein a catalyst of the general formula (D),



where

M is ruthenium or osmium,

20

R^{13} and R^{14} are each, independently of one another, hydrogen, C_1 - C_{20} -alkyl, C_2 - C_{20} -alkenyl, C_2 - C_{20} -alkynyl, C_6 - C_{24} -aryl, C_1 - C_{20} -carboxylate, C_1 - C_{20} -alkoxy, C_2 - C_{20} -alkenyloxy, C_2 - C_{20} -alkynyloxy, C_6 - C_{24} -aryloxy, C_2 - C_{20} -

alkoxycarbonyl, C₁-C₂₀-alkylthio, C₁-C₂₀-alkylsulphonyl or C₁-C₂₀-alkylsulphinyl,

X³ is an anionic ligand,

L² is an uncharged π-bonded ligand, either monocyclic or polycyclic,


5 L³ is a ligand from the group consisting of phosphines, sulphonated phosphines, fluorinated phosphines, functionalized phosphines having up to three aminoalkyl, ammonioalkyl, alkoxyalkyl, alkoxycarbonylalkyl, hydrocarbonylalkyl, hydroxyalkyl or ketoalkyl groups, phosphites, phosphinites, phosphonites, phosphinamines, arsines, stibines, ethers, amines, amides, imines, sulfoxides, thioethers and pyridines,

10 Y⁻ is a noncoordinating anion and

n is 0, 1, 2, 3, 4 or 5,

is used.

15 24. Process according to Claim 1, wherein a catalyst of the general formula (E),



where

M² is molybdenum or tungsten,


20 R¹⁵ and R¹⁶ are identical or different and are each hydrogen, C₁-C₂₀-alkyl, C₂-C₂₀-alkenyl, C₂-C₂₀-alkynyl, C₆-C₂₄-aryl, C₁-C₂₀-carboxylate, C₁-C₂₀-alkoxy, C₂-C₂₀-alkenyloxy, C₂-C₂₀-alkynyloxy, C₆-C₂₄-aryloxy, C₂-C₂₀-alkoxycarbonyl, C₁-C₂₀-alkylthio, C₁-C₂₀-alkylsulphonyl or C₁-C₂₀-alkylsulphinyl,

25 R¹⁷ and R¹⁸ are identical or different and are each a substituted or halogen-substituted C₁-C₂₀-alkyl, C₆-C₂₄-aryl, C₆-C₃₀-aralkyl radical or a silicone-containing analogue thereof,

is used.

25. Process according to Claim 1, wherein a catalyst of the general formula (F),

- 73 -



where

M is ruthenium or osmium,




X¹ and X² are identical or different and are anionic ligands which can have all the meanings of X¹ and X² given for the general formula (A) in any of Claims 4-6,

L represents identical or different ligands which can have all the meanings of L in the general formulae (A) and (B) and

R¹⁹ and R²⁰ are identical or different and are each hydrogen or substituted or unsubstituted alkyl,

is used.

26. Process according to Claim 1, wherein a catalyst of the general formula (G), (H) or (K),



where

M is osmium or ruthenium,

X¹ and X² are identical or different and are two ligands, preferably anionic ligands,

L is a ligand, preferably an uncharged electron donor,


Z¹ and Z² are identical or different and are uncharged electron donors,

R²¹ and R²² are each, independently of one another, hydrogen, alkyl, cycloalkyl, alkenyl, alkynyl, aryl, carboxylate, alkoxy, alkenyloxy,

alkynyloxy, aryloxy, alkoxy, carbonyl, alkylamino, alkylthio, alkylsulphonyl or alkylsulphinyl, each of which may be substituted by one or more radicals selected from among alkyl, halogen, alkoxy, aryl and heteroaryl,

5 is used.

27. Process according to Claim 1, characterized in that the catalyst system comprises at least one compound of the general formula (Z) and a catalyst (N) which has the general structural element (N1),



10 where the carbon atom denoted by “*” is bound via one or more double bonds to the basic catalyst framework

and

15 R²⁵-R³² are identical or different and are each hydrogen, halogen, hydroxyl, aldehyde, keto, thiol, CF₃, nitro, nitroso, cyano, thiocyno, isocyanato, carbodiimide, carbamate, thiocarbamate, dithiocarbamate, amino, amido, imino, silyl, sulphonate (-SO₃⁻), -OSO₃⁻, -PO₃⁻ or OPO₃⁻ or alkyl, cycloalkyl, alkenyl, alkynyl, aryl, carboxylate, alkoxy, alkenyloxy, alkynyloxy, aryloxy, alkoxy, carbonyl, alkylamino, alkylthio, arylthio, alkylsulphonyl, alkylsulphinyl, dialkylamino, alkylsilyl or alkoxy, silyl, where these radicals can all optionally be substituted by one or more alkyl, halogen, alkoxy, aryl or heteroaryl radicals, or alternatively two directly adjacent radicals from the group consisting of R²⁵-R³² can be bridged with inclusion of the ring carbons to which they are bound to form a cyclic group, preferably an aromatic system, or alternatively R⁸ may be bridged to another ligand of the ruthenium- or osmium-carbene complex catalyst,

25 m is 0 or 1 and

A is oxygen, sulphur, C(R³³R³⁴), N-R³⁵, -C(R³⁶)=C(R³⁷)-, -C(R³⁶)(R³⁸)-C(R³⁷)(R³⁹)-, where R³³-R³⁹ are identical or different and can each have the same meanings as the radicals R²⁵-R³².

28. Process according to one or more of Claims 1-27, wherein a compound of the general formula (Z) in which D can have the following meanings of the general formulae (2) to (16)

	OR_2	(2)
5	ROH	(3)
	R-COOH	(4)
	SR_2	(5)
	O=SR_2	(6)
	O_2SR_2	(7)
10	$\text{NHR}_2, \text{NH}_2\text{R}, \text{NR}_3$	(8a, 8b, 8c)
	$\text{YR}_3, \text{R}_2\text{Y-YR}_2$	(9a, 9b)
	O=YR_3	(10)
	O=Y(OR)_2	(11)
	O=Y(OR)_3	(12)
15	O=CR_2	(13)
	S=YR_3	(14)
	H_2SO_4	(15)
	RSO_3H	(16)

20 where Y is phosphorus, arsenic or antimony and the radicals R are identical or different and are each hydrogen or a linear, branched, aliphatic, cyclic, heterocyclic or aromatic radical which has 1-33 carbon atoms and may be bridged and can optionally have from 1 to 15 further heteroatoms, preferably oxygen or nitrogen, is used.

25

29. Process according to one or more of Claims 1-27, wherein, in the compound of the general formula (Z), D is water, diethyl ether, ethylamine, THF, n-propanol, formic acid, acetic acid, trifluoroacetic acid, trichloroacetic acid, sulphuric acid, phosphoric acid, trifluoromethanesulphonic acid or toluenesulphonic acid and $v = 1, 2$ or 3 .

30

30. Process according to one or more of Claims 1-27, wherein BF_mX_n in the general formula (Z) is BF_3 , BF_2Cl , BFCl_2 , BF_2Br , BFBr_2 , $\text{BF}_2(\text{OC}_2\text{H}_5)$, $\text{BF}(\text{OC}_2\text{H}_5)_2$, $\text{BF}_2(\text{CH}_3)$ or $\text{BF}(\text{CH}_3)_2$.

35

31. Process according to one or more of Claims 1-30, wherein the complex catalyst and the compound of the general formula (Z) are used in a molar ratio of [complex catalyst:compound of the general formula (Z)] 1: (0.1-1000), preferably 1: (0.5-100), particularly preferably 1: (1-50).

32. Process according to one or more of Claims 1-31, wherein a copolymer or terpolymer which contains repeating units of at least one conjugated diene, at least one α,β -unsaturated nitrile and, if appropriate, one or more further copolymerizable monomers is used as nitrile rubber.

33. Process according to one or more of Claims 1-32, wherein the compound of the general formula (Z) is added in a solvent or dispersion medium or alternatively without solvent or dispersion medium to the complex catalyst or a solution of the complex catalyst.

34. Process according to one or more of Claims 1-33, wherein the amount of the complex catalyst present in the catalyst system corresponds to from 1 to 1000 ppm of noble metal, preferably from 2 to 500 ppm, in particular from 5 to 250 ppm, based on the nitrile rubber used.

35. Use of a compound of the general formula (Z)



where m, n, v, X and D can have the meanings given in Claim 1, as constituent of catalyst systems for the metathesis of nitrile rubber.

36. Process according to one or more of Claims 1-34, wherein the reaction is carried out in the presence of a coolefin.