



US 20060096633A1

(19) **United States**(12) **Patent Application Publication****Chu**(10) **Pub. No.: US 2006/0096633 A1**(43) **Pub. Date: May 11, 2006**(54) **MAGNETIC FIELD ENHANCED  
PHOTOVOLTAIC DEVICE****Publication Classification**(51) **Int. Cl.**  
**H01L 31/00** (2006.01)(52) **U.S. Cl.** ..... **136/254; 136/252**(75) **Inventor: Chia-Fan Chu, Chu-Tung (TW)**


Correspondence Address:

**BIRCH STEWART KOLASCH & BIRCH  
PO BOX 747  
FALLS CHURCH, VA 22040-0747 (US)**(73) **Assignee: Industrial Technology Research Institute**(21) **Appl. No.: 11/022,794**(22) **Filed: Dec. 28, 2004**(30) **Foreign Application Priority Data**

Nov. 5, 2004 (TW)..... 93133856

(57) **ABSTRACT**

A magnetic field enhanced photovoltaic device includes a photoelectric conversion layer, a first electrode, a second electrode, a ferro-antiferromagnetic exchange coupling layer and an applied magnetic field. The first electrode and the second electrode are respectively disposed on two surfaces of the photoelectric conversion layer to collect electrons and holes generated by the photoelectric conversion layer. The first electrode is pervious to light. The incident light reaches the photoelectric conversion layer through the first electrode. The applied magnetic field polarizes the spin state of electrons. The ferro-antiferromagnetic exchange coupling layer adjoins the photoelectric conversion layer and pins the spin state of electrons.






Fig. 1




Fig. 2

## MAGNETIC FIELD ENHANCED PHOTOVOLTAIC DEVICE

### FIELD OF THE INVENTION

[0001] The invention relates to a photovoltaic device, and particularly to a magnetic field enhanced photovoltaic device.

### BACKGROUND OF THE INVENTION

[0002] A photovoltaic device (including a solar energy battery) is different from the regular battery. A photovoltaic device converts light into electrical energy, its P-N junction structure when exposed to incident light generates large quantities of electron-hole pairs, and in the meantime electrons carrying negative electricity and holes carrying positive electricity migrate to the N-type semi-conductor and P-type semi-conductor respectively. This process produces electricity.

[0003] During the conversion process, not all the incident sun-light can be absorbed and converted to electricity by the photovoltaic device. One section of the light spectrum does not contribute to the battery's output due to its low energy (which should be greater than semi-conductor's energy gap). When the photovoltaic device receives light of that particular section of the spectrum, instead of converting its energy into electron-hole generation, the photovoltaic device can only release its energy in the form of heat. In the laboratory, the photovoltaic device can almost reach the highest light-electricity-conversion level theoretically allowed, but in reality due to the complexity of the mass manufacturing process cost-effective high-efficient photovoltaic devices cannot be produced. Currently, this is the biggest bottleneck in making photovoltaic devices.

[0004] At present, the development of photovoltaic devices can be divided into two areas; one area focuses on how to capture light and convert the light energy to electricity efficiently; the other area focuses on how to reduce cost in material and manufacturing processes. The former area can be further divided into the following sub-categories: reducing incident light reflection; improving the design of the metal electrode or adding an anti-reflection layer between component layers to reduce reflection and increase the amount of light getting into the semi-conductor material; or reducing inner resistance of the photovoltaic device to increase conversion efficiency, wherein metal electrodes are imbedded in the substrate to increase the contact surface while reducing serial resistance. Two or more photovoltaic devices can be combined to form a tandem cell, where the device absorbing the high-energy spectrum is placed on top while the device absorbing the low-energy spectrum is placed on the bottom; together, they form a high voltage photovoltaic device.

### SUMMARY OF THE INVENTION

[0005] The invention incorporates a magnetic field to enhance the efficiency of the photovoltaic device. The additional magnetic field in the photovoltaic device will polarize the spin state of electrons that migrate inside the photovoltaic device. For example, a ferro-antiferromagnetic layer interfacing with a coupling layer produces an exchange coupling effect and pins the spin state of electrons, which

reduces scattering probability during electron transmission, reduces internal resistance and increases conversion efficiency.

[0006] An electron possesses two intrinsic characteristics: charge and spin, which can be considered as smallest units for electricity and magnetism. In the traditional design of a photovoltaic device, only the effect of electron's charge characteristic is considered while its spin characteristic is overlooked. Due to the latest development in nano-technology, it has become feasible to control the spin of electrons to reduce resistance and improve efficiency. The characteristic of magnetic resistance is stated in differential spin scattering theory, that is, when the spin direction of migrating electrons is parallel to that of the conducting material they are migrating through, and the probability of electron scattering is reduced. Therefore, a photovoltaic device incorporated with a magnetic field can change its overall magnetic resistance, a phenomenon called "magnetic resistance." The combination of ferro-magnetic and ferro-antiferromagnetic layers can produce an exchange coupling effect, in which the spin state of nearby migrating-through electrons is pinned by the anti-ferromagnetic layer.

[0007] A magnetic photovoltaic device, based on the above-mentioned theory to increase the photoelectric conversion efficiency, includes a photoelectric conversion layer, a first electrode, a second electrode, a ferro-antiferromagnetic exchange coupling layer and an applied magnetic field. The first electrode and the second electrode are respectively disposed on two surfaces of the photoelectric conversion layer to collect electrons and holes generated by the photoelectric conversion layer. The first electrode is pervious to light, which reaches to the photoelectric conversion layer through the first electrode, where the light energy is converted into electron-hole pairs. In the meantime, the applied magnetic field polarizes the spin state of electrons, and the ferro-antiferromagnetic exchange coupling layer adjoining the photoelectric conversion layer produces an exchange coupling effect, which creates extra magnetic bias on the junction and pins the spin state of electrons and further fixes the spin direction of electrons. Thus, if the spin directions of electrons are parallel to the direction of the magnetic field, the electron transmission resistance can be greatly reduced and its diffusion length increased. The process reduces the recombination probability of electrons and holes and hence increases photoelectric conversion efficiency. Hence, an additional hard magnetic layer in photovoltaic device provides the needed magnetic field and ensures the spin directions of electrons are the same as the direction of the magnetic field.

[0008] Further scope of the applicability of the present invention will become apparent from the detailed description given hereinafter. However, it should be understood that the detailed description and specific examples, while indicating preferred embodiments of the invention, are given by way of illustration only, since various changes and modifications within the spirit and scope of the invention will become apparent to those skilled in the art from this detailed description.

### BRIEF DESCRIPTION OF THE DRAWING

[0009] The present invention will become more fully understood from the following detailed description and the

accompanying drawings, which are given by way of illustration only, and thus are not limitative of the present invention, and in which:

[0010] **FIG. 1** is a cut-cross display of the first embodiment of the invention; and

[0011] **FIG. 2** is a cut-cross display of the second embodiment of the invention.

#### DETAILED DESCRIPTION OF THE INVENTION

[0012] Reference will now be made in detail to the preferred embodiments of the invention, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers are used in the drawings and the description to refer to the same or like parts.

[0013] A magnetic field enhanced photovoltaic device of invention can be applied to all kinds of photovoltaic devices, no matter what material is used, e.g., Single Crystal, Polycrystal, Amorphous, or Quantum dot, Nano-Wire, Nano-Rod and Quantum Well arranged with nanocrystal.

[0014] For different kinds of photovoltaic devices, such as P-N semi-conductor solar battery, nano-rod solar battery or dye photoactivated solar battery, their photoelectric conversion layers can be P-N junction semi-conductor layers, a nano-rod and high polymer mixed layer or a photoactivated layer. The first electrode has to be pervious to light, so conducting glass having a layer of FTO, ITO or IZO, etc., is used for the layer. Because the second electrode is affected by the applied magnetic field to produce the same directional spin, a magnetic layer, Iron, cobalt or nickel or other metal or alloys can be used. To increase design flexibility of the photovoltaic device, transparent strong magnetic material, such as  $\text{Nd}_2\text{Fe}_{14}\text{B}$ , can be used as the hard magnetic layer to provide the applied magnetic field. The manufacturing process of the transparent magnet  $\text{Nd}_2\text{Fe}_{14}\text{B}$  may refer to M. Gich et al, "High-coercively ultralight transparent magnets", Applied Physics Letter, Vol. 82, No. 24, 16 Jun. 2003. Since the hard magnetic layer is pervious to light, it can adjoin the first electrode. While the ferro-antiferromagnetic exchange coupling layer adjoining the photoelectric conversion layer consists of a ferro-magnetic layer and an antiferro-magnetic layer, the ferro-magnetic layer can be first formed with nickel metal, and then its surface can be oxidized to form nickel oxide as the antiferro-magnetic layer.

[0015] With reference to **FIG. 1**, on the top of substrate **100** is a first transparent  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer **110**, a nickel electrode **120** having a thickness less than 20 nm, a third P-N junction semi-conductor layer, a forth ferro/anti-ferromagnetic exchange coupling layer and a last FTO electrode **150**. Together they make up a P-N semi-conductor solar battery. The transparent  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer **110** is formed on the surface of the substrate **100**, and then the nickel electrode **120** is formed on top of the  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer. On top of the nickel electrode **120** is a P-N junction semi-conductor layer **130**. The FTO electrode **150** and the ferro/anti-ferromagnetic exchange coupling layer **140** are on the other side of the P-N junction semi-conductor layer, where the thickness of the FTO electrode **150** is less than 30 nm, and the thickness of the ferro-magnetic layer of the ferro/anti-ferromagnetic layer is less than 20 nm, which allows light to pass through. The ferro/anti-ferromagnetic exchange coupling layer **140**

consists of a nickel layer **141** and nickel oxide **142**, where the nickel layer **141** adjoins the P-N junction semi-conductor layer **130** and nickel oxide **142** is formed on the surface of the nickel layer **141**. Finally, the FTO electrode **150** lies on top of the nickel oxide layer. When sunlight passes through the FTO electrode **150**, the ferro/anti-ferromagnetic exchange coupling layer **140** reaches to the P-N junction semi-conductor layer **130**, where the light energy is converted into electrons-hole pairs. Due to the applied magnetic field of the  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer **110**, electrons and holes generated by the P-N junction have the same directional spin states before being collected by the nickel electrode **120** and the FTO electrode **150**, respectively. The exchange coupling effect created between the ferro-magnetic nickel layer **141** and the anti-ferromagnetic nickel oxide **142** pin down the spin state of those electrons when they pass through them.

[0016] In addition, if the hard magnetic layer is made of transparent  $\text{Nd}_2\text{Fe}_{14}\text{B}$ , it can be placed on the side to receive light. For example, the nano-rod solar battery in **FIG. 2** includes nickel electrode **220** having a thickness less than 20 nm on the surface of the substrate **200**, the CdSe nano-rod and poly-(3-hexylthiophene) mixed layer **230** having a thickness less than 30 nm, the ferro magnetic layer of the ferro/anti-ferromagnetic exchange coupling layer **240** having a thickness less than 20 nm, the transparent  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer **210** and the FTO electrode **250**. In more detail, the CdSe nano-rod and poly-(3-hexylthiophene) mixed layer **230** is used as a photoelectric layer to produce electrons and holes. The nickel electrode **220** lies directly on top of the substrate, the CdSe nano-rod and poly-(3-hexylthiophene) mixed layer **230** covers the nickel electrode **220** covered by the Ferro/anti-ferromagnetic exchange coupling layer **240**. The  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer **210** and the FTO electrode **250** are on the other side of the CdSe nano-rod and poly-(3-hexylthiophene) mixed layer **230** where light can pass through. The ferro/anti-ferromagnetic exchange coupling layer **240** consists of a nickel layer **241** and a nickel oxide layer **242**, where the nickel layer **241** adjoins the CdSe nano-rod and poly-(3-hexylthiophene) mixed layer **230** and a nickel oxide layer **242** is formed on the surface of the nickel layer **241**. Lastly, the  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer **210** and the FTO electrode **250** stay on top of the nickel oxide. Sunlight passes through the ferro/anti-ferromagnetic exchange coupling layer **240**, the  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer **210** and the FTO electrode **250**, reaches the CdSe nano-rod and poly-(3-hexylthiophene) mixed layer **230**, the CdSe nano-rod and poly-(3-hexylthiophene) mixed layer **230** produces electrons and holes which migrate to the nickel electrode **220** and the FTO electrode **250** respectively. Since the electrons are affected by the applied magnetic fields from the  $\text{Nd}_2\text{Fe}_{14}\text{B}$  layer **210** and the ferro/anti-ferromagnetic exchange coupling layer **240**, they have the same directional spin state.

[0017] Additionally, the above-mentioned ferro/anti-ferromagnetic exchange coupling layers are comprised of the nickel layer and a nickel oxide layer, where the nickel layer adjoins the photoelectric conversion layer and a nickel oxide layer is formed on top of the nickel layer. Because nickel oxide has a higher energy gap, it can absorb the higher energy part of the sunlight. Nickel oxide, the nickel layer and the FTO electrode together form another solar battery, absorbing different energy levels of light.

[0018] While an illustrative and presently preferred embodiment of the invention has been described in detail

herein, it is to be understood that the inventive concepts may be otherwise variously embodied and employed and that the appended claims are intended to be construed to include such variations except as limited by the prior art.

1. A magnetic field enhanced photovoltaic device, comprising:

a photoelectric conversion layer to receive incident light and produce a plurality of electrons and holes;

a first electrode and a second electrode located on two sides of said photoelectric conversion layer to collect passing electrons and holes in order to produce electrical energy, said first electrode is pervious to light and allows light to reach said photoelectric conversion layer;

an applied magnetic field, exerted on said photoelectric conversion layer to force passing electrons' spin state consistent with said applied magnetic field;

a ferro/anti-ferromagnetic exchanges coupling layer adjoining the photoelectric conversion layer, said ferro/anti-ferromagnetic exchanges coupling layer providing exchange coupling effects and providing extra magnetic bias to pin down a spin state of passing electrons generated by said photoelectric conversion layer.

2. The magnetic field enhanced photovoltaic device as claimed in claim 1, wherein said photoelectric conversion layer comprises a P-N junction semi-conductor, a nano-rod and polymer mixed layer, or a dye photoactivated layer.

3. The magnetic field enhanced photovoltaic device as claimed in claim 2, wherein said nano-rod and polymer mixed layer is a CdSe nano-rod and poly-(3-hexylthiophene) mixed layer.

4. The magnetic field enhanced photovoltaic device as claimed in claim 1, wherein said first electrode is a transparent conducting glass.

5. The magnetic field enhanced photovoltaic device as claimed in claim 4, wherein said transparent conducting glass comprises a transparent conduction layer.

6. The magnetic field enhanced photovoltaic device as claimed in claim 1, wherein said second electrode is a magnetic layer.

7. The magnetic field enhanced photovoltaic device as claimed in claim 6, wherein said second electrode is selected from the group consisting of iron, cobalt, nickel and their alloys.

8. The magnetic field enhanced photovoltaic device as claimed in claim 1, wherein said applied magnetic field is provided by a hard magnetic layer.

9. The magnetic field enhanced photovoltaic device as claimed in claim 8, wherein said applied magnetic field is provided by a hard magnetic layer which adjoins said second electrode.

10. The magnetic field enhanced photovoltaic device as claimed in claim 8, wherein said applied magnetic field is provided by a hard magnetic layer made of  $\text{Nd}_2\text{Fe}_{14}\text{B}$ .

11. The magnetic field enhanced photovoltaic device as claimed in claim 8, wherein said applied magnetic field is provided by a hard magnetic layer made of a transparent strong magnetic material.

12. The magnetic field enhanced photovoltaic device as claimed in claim 11, wherein said applied magnetic field is provided by a hard magnetic layer which adjoins said first electrode.

13. The magnetic field enhanced photovoltaic device as claimed in claim 1, wherein said ferro/anti-ferromagnetic exchanges coupling layer is made of a ferro magnetic layer and an anti-ferro magnetic layer.

14. The magnetic field enhanced photovoltaic device as claimed in claim 13, wherein said ferromagnetic layer is a nickel layer.

15. The magnetic field enhanced photovoltaic device as claimed in claim 13, wherein said anti-ferro magnetic layer is a nickel oxide layer.

\* \* \* \* \*