



US007186322B2

(12) **United States Patent**
Sato et al.

(10) **Patent No.:** US 7,186,322 B2
(45) **Date of Patent:** Mar. 6, 2007

(54) **METHODS OF PRODUCING AND POLISHING SEMICONDUCTOR DEVICE AND POLISHING APPARATUS**

(75) Inventors: **Shuzo Sato**, Kanagawa (JP); **Yuji Segawa**, Tokyo (JP); **Akira Yoshio**, Tokyo (JP); **Hiizu Ootorii**, Tokyo (JP); **Zenya Yasuda**, Kanagawa (JP); **Masao Ishihara**, Tokyo (JP); **Takeshi Nogami**, Kanagawa (JP); **Naoki Komai**, Kanagawa (JP)

(73) Assignee: **Sony Corporation** (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 567 days.

(21) Appl. No.: **10/327,860**

(22) Filed: **Dec. 26, 2002**

(65) **Prior Publication Data**

US 2003/0114004 A1 Jun. 19, 2003

Related U.S. Application Data

(62) Division of application No. 09/800,580, filed on Mar. 8, 2001, now Pat. No. 6,797,623.

(51) **Int. Cl.**
C25D 17/00 (2006.01)

(52) **U.S. Cl.** **204/198**; 204/224 M; 204/225; 204/226; 204/227

(58) **Field of Classification Search** 204/198, 204/224 M, 225, 226, 227

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,944,856 A *	7/1990	Catanese et al.	205/645
5,911,619 A *	6/1999	Uzoh et al.	451/5
6,776,693 B2 *	8/2004	Duboust et al.	451/41
6,797,623 B2 *	9/2004	Sato et al.	438/691
6,846,227 B2 *	1/2005	Sato et al.	451/288

* cited by examiner

Primary Examiner—Arun S. Phasge

(74) *Attorney, Agent, or Firm*—Rader Fishman & Grauer PLLC; Ronald P. Kananen

(57) **ABSTRACT**

A method of production and a method of polishing a semiconductor device and a polishing apparatus, capable of easily flattening an initial unevenness of a metal film, excellent in efficiency of removal of an excess metal film, and capable of suppressing damage to an interlayer insulation film below the metal film when flattening the metal film by polishing, the polishing method including the steps of interposing an electrolytic solution including a chelating agent between a cathode member and the copper film, applying a voltage between the cathode member used as a cathode and the copper film used as an anode to oxidize the surface of the copper film and forming a chelate film of the oxidized copper, selectively removing a projecting portion of the chelate film corresponding to the shape of the copper film to expose the projecting portion of the copper film at its surface, and repeating the above chelate film forming step and the above chelate film removing step until the projecting portion of the copper film is flattened.

42 Claims, 25 Drawing Sheets




FIG.1A




FIG.1B




FIG.1C




FIG.2D




FIG.2E




FIG.3F




FIG.3G




FIG. 4H




FIG. 4I




FIG. 5J




FIG. 5K




FIG. 5L




FIG. 6




FIG. 7




FIG.8A




FIG.8B




FIG. 9




FIG. 10




FIG.11




FIG.12




FIG.13




FIG.14




FIG.15




FIG.16




FIG.17




FIG. 18




FIG. 20




FIG. 21




FIG.22B

PRESENT INVENTION




FIG.22A

RELATED ART




FIG.23




FIG.24




FIG.25A




FIG.25B




FIG.25C




FIG.26D




FIG.26E




FIG.26F




FIG.27




FIG.28




FIG.29





FIG.30



METHODS OF PRODUCING AND POLISHING SEMICONDUCTOR DEVICE AND POLISHING APPARATUS

This application is a divisional application of Ser. No. 09/800,580 filed Mar. 8, 2001 now U.S. Pat. No. 6,797,623, issued on Sep. 28, 2004.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to methods and apparatus of producing and polishing a semiconductor device, more particularly relates to methods of producing and polishing a semiconductor device including a step of reducing surface unevenness accompanying the formation of a metal film, and to a polishing apparatus thereof.

2. Description of the Related Art

Along with the increase in integration and reduction of size of semiconductor devices, progress has been made in miniaturization of interconnections, reduction of interconnection pitch, and superposition of interconnections. The importance of the multilayer interconnection technology in the manufacturing process of semiconductor devices is therefore rising.

Aluminum has been frequently used as an interconnection material of a semiconductor device having a multilayer interconnection structure, but in order to reduce the propagation delay of signals in the recent 0.25 μm or less design rule, has been attempted active development of an interconnection process in that aluminum as the interconnection material is replaced by copper. When using copper for interconnections, it is beneficial that both a low resistance and a high electromigration tolerance can be obtained.

In a process using this copper for interconnections, for example, an interconnection process referred to as the damascene process for burying a metal in a groove-like interconnection pattern formed in an interlayer insulation film in advance and removing excess metal film by chemical mechanical (mechno-chemical) polishing (CMP) to form the interconnections has become influential. The damascene process has the features that etching of the interconnections become unnecessary and also a further upper interlayer insulation film becomes flat by itself, so the manufacturing steps can be simplified.

Further, by the dual damascene process, where not only grooves for the interconnections, but also the contact holes are formed as grooves in the interlayer insulation film and where the interconnections and the contact holes are simultaneously buried by the metal, a greater reduction of the interconnection steps can be achieved.

Here, an explanation will be made of an example of the process for forming copper interconnections by the dual damascene process with reference to the accompanying drawings.

First, as shown in FIG. 25A, for example, an interlayer insulation film 302 made of silicon oxide is formed by low pressure chemical vapor deposition (LP-CVD) on a silicon or other semiconductor substrate 301 on which a not illustrated impurity diffusion region is appropriately formed.

Next, as shown in FIG. 25B, contact holes CH communicating with the impurity diffusion region of the semiconductor substrate 301 and grooves M in which it will be formed a predetermined pattern of interconnections to be electrically connected to the impurity diffusion region of the substrate 301 which are formed by using well-known photolithography and etching.

Next, as shown in FIG. 25C, a barrier film 305 is formed on the surface of the interlayer insulation film 302 and in the contact holes CH and the grooves M. This barrier film 305 is formed by a material such as Ta, Ti, TaN, or TiN by well-known sputtering. When the interconnection material is copper and the interlayer insulation film 302 is silicon oxide, since copper has a large diffusion coefficient with respect to silicon oxide, it is easily oxidized. The barrier film 305 is provided to prevent this.

Next, as shown in FIG. 25D, a seed copper film 306 is formed on the barrier film 305 to a predetermined thickness by well-known sputterings.

Then, as shown in FIG. 25E, a copper film 307 is formed so as to bury the contact holes CH and the grooves M by copper. The copper film 307 is formed by the process of plating, CVD, sputtering, etc.

Next, as shown in FIG. 25F, the excess copper film 307 and barrier film 305 on the interlayer insulation film 302 are removed by CMP for flattening.

Due to the above steps, copper interconnections 308 and contacts 309 are formed.

By repeating the above process on the interconnections 308, multilayer interconnections can be formed.

Summarizing the disadvantages to be solved by the invention, in the step of removing the excess copper film 307 by CMP in the copper interconnection forming process using the dual damascene process, because the flattening technique employing conventional CMP involves applying a predetermined pressure between a polishing tool and the copper film for polishing, it suffers from a large damage given to the semiconductor substrate. Especially in a case where an organic insulation film of a small dielectric constant having a low mechanical strength is adopted for the interlayer insulation film, this damage no longer becomes negligible and may cause cracks of the interlayer insulation film and separation of the interlayer insulation film from the semiconductor substrate.

Further, the removal performance differs among the interlayer insulation film 302, the copper film 307, and the barrier film 305, therefore it suffers from the disadvantage that dishing, erosion (thinning), recesses, etc. easily occur in the interconnections 308.

Dishing is a phenomenon where, as shown in FIG. 26, when there is an interconnection 308 having a width of for example about 100 μm at for example a 0.18 μm design rule, the center portion of the interconnection is excessively removed and sinks. If this dishing occurs, the sectional area of the interconnection 308 becomes insufficient. This causes poor interconnection resistance etc. This dishing is apt to occur when copper or aluminum, which is relatively soft, is used as the interconnection material.

Erosion is a phenomenon where, as shown in FIG. 27, a portion having a high pattern density such as where interconnections with a width of 1.0 μm are formed at a density of 50% in a range of for example 3000 μm is excessively removed. When erosion occurs, the sectional area of the interconnections becomes insufficient. This causes poor interconnection resistance etc.

Recess is a phenomenon where, as shown in FIG. 28, the interconnection 308 becomes lower in level at the interface between the interlayer insulation film 302 and the interconnection 308 resulting in a step difference. In this case as well, the sectional area of the interconnection becomes insufficient, causing poor interconnection resistance etc.

Further, in the step of flattening and removing the excess copper film 307 by CMP, it is necessary to efficiently remove

the copper film. The amount removed per unit time, that is, the polishing rate, is required to be for example more than 500 nm/mm.

In order to obtain this polishing rate, it is necessary to increase the polishing pressure on the wafer. When the polishing pressure is raised, as shown in FIG. 29, a scratch SC and chemical damage CD are apt to occur in the interconnection surface. In particular, they easily occur in the soft copper. For this reason, it causes opening of the interconnections, short-circuiting, poor interconnection resistance, and other defects. Further, if the polishing pressure is raised, there is the inconvenience that the amount of the scratches, separation of interlayer insulation film, dishing, erosion, and recesses also becomes larger.

SUMMARY OF THE INVENTION

A first object of the present invention is to provide a method of producing a semiconductor device capable of easily flattening an initial unevenness, excellent in efficiency of removal of an excess metal film, and capable of suppressing damage to an interlayer insulation film below a metal film when flattening the metal film by polishing; a second object of the present invention is to provide a method of polishing the same semiconductor device; a third object of the present invention is to provide a polishing apparatus using these methods.

An object of the present invention is to provide a method of production and a method of polishing a semiconductor device capable of easily flattening an initial unevenness, excellent in efficiency of removal of an excess metal film, and capable of suppressing damage to an interlayer insulation film below a metal film when flattening the metal film by polishing and to a polishing apparatus used for these methods.

To attain the above object, according to a first aspect of the present invention, there is provided a method of producing a semiconductor device, including the steps of forming an interconnection groove in an insulation film formed on a substrate, stacking a copper film having unevenness on its surface corresponding to the step difference of the interconnection groove on the entire surface of the insulation film so as to bury the interconnection groove, interposing an electrolytic solution including a chelating agent between a cathode member and the copper film, applying a voltage between the cathode member functioning as a cathode and the copper film functioning as an anode to oxidize the surface of the copper film and form a chelate film of oxidized copper, selectively removing a projecting portion of the chelate film corresponding to unevenness of the copper film to expose the copper film of that projecting portion at its surface, and repeating the chelate film forming step and the above chelate film removing step until the projecting portion of the copper film is flattened.

According to the above method for producing a semiconductor device, the uneven copper film surface formed when burying an interconnection groove by copper film is oxidized by anodic oxidation. This oxidized copper is chelated by a chelating agent in an electrolytic solution. Therefore, a chelate film of rather low mechanical strength able to be easily removed is formed. If removing a projecting portion of the chelate film, because the further exposed copper is chelated after being oxidized by anodic oxidation, flatness of the copper film is achievable by repeating the step of removing the projecting portion of the chelate film.

Since the resistance of the chelate film is higher than copper, the copper covered by the not removed chelate film

remaining in the groove is hard to be oxidized by anodic oxidation by passing a current, so the chelation is very slow and the chelate film is formed by anodic oxidation only at the projecting portion of the copper exposed by the removal of the previous chelate film.

Further, because the current is supplied through an electrolytic solution, if the potential difference between the copper film on the anode and the cathode member of the cathode is constant, the current density becomes larger the shorter the distance between electrodes. Therefore, in the copper film exposed after removing the chelate film, the more projecting a part of the copper film is, the shorter the electrode distance to the cathode member used as the cathode and thus the higher the current density and consequently, the higher the speed of the anodic oxidation and the faster the chelation.

Accordingly, because of the accelerated chelation of the projecting portion of the copper film, it is able to achieve efficient flattening and suppression of damage to the interlayer insulation film below a copper film.

The method for producing a semiconductor device according to the present invention preferably further includes a step, after flattening the projecting portion of the copper film, of removing the chelate film formed on the surface of the copper film until removing the copper film stacked outside the interconnection groove.

Due to this, copper interconnections can be formed while suppressing damage to the interlayer insulation film below the copper film.

In the method for producing a semiconductor device according to the present invention, preferably, in the step of applying a voltage by using the cathode member as a cathode, a voltage is applied using as a cathode a conductive polishing tool for removing a projecting portion of the chelate film.

By using a polishing tool as the cathode, efficient chelation due to the anodic oxidation and efficient removal of the chelate film can be obtained.

In the method for producing a semiconductor device according to the present invention, preferably, in the step of applying a voltage by using the copper film as the anode, a voltage is applied on an anode member contacting or close to the copper film, making the copper film an anode through the electrolytic solution.

By locally passing a current from the anode member to the copper film through the electrolytic solution, a stable current can be supplied.

In this case, a current is supplied to the copper film from the anode member via the electrolytic solution and, further, from the copper film to the cathode member through the electrolytic solution, so the copper film near the cathode member is oxidized and chelated.

In the method for producing a semiconductor device according to the present invention, preferably, in the step of applying a voltage by using the cathode member as a cathode, a voltage is applied using a conductive electrode plate arranged parallel with the copper film as a cathode.

By arranging the electrode plate parallel with the copper film, as shown above, in the exposed copper films, the more projecting the portion, the shorter the electrode distance. Due to the increase of the speed of the anodic oxidation caused by the increased current density, the chelation is accelerated, so efficient flattening is achievable.

In the method for producing a semiconductor device according to the present invention, preferably, in the step of removing the chelate film, the chelate film is removed by wiping or mechanical polishing.

5

Since the chelate film has a rather low mechanical strength, mechanical polishing involving strong pressing is not necessary. It can be easily removed by wiping or mechanical polishing involving only weak pressing.

In the method for producing a semiconductor device according to the present invention, preferably, in the step of removing the chelate film, the chelate film is removed by applying vibration to the substrate. Alternatively, in the step of removing the chelate film, the chelate film is removed by flushing with the electrolytic solution.

Since the chelate film has a rather low mechanical strength, it can be easily removed not only by mechanical polishing, but also by vibration and the flushing action of the electrolytic solution.

In the method for producing a semiconductor device according to the present invention, preferably, in the chelate film forming step and the chelate film removing step, a current flowing through the cathode member and the copper film is monitored and the polishing process of the copper film is controlled in response to the magnitude of the current.

For example, by using a chelating agent forming a chelate film having a higher electrical resistance than the copper film, before the projecting portion is flattened, the current between the cathode member and the copper film increases when the projecting chelate film is removed because copper is exposed. When a chelate film is formed on the exposed copper again, the value of the current decreases. This cycle is repeated. When the copper film is flattened, because the chelate film on the copper film is removed completely and the copper film is exposed totally, the current reaches a maximum first, then the current value exhibits a new maximum at each removal.

When the barrier film is exposed, since usually the resistance of the barrier film is higher than copper, the current value begins to decrease after the chelate film is removed. Therefore, if stopping the application of voltage at the time when the current value begins to decrease, the formation of the chelate film by the anodic oxidation can be stopped after that time, thus the progress of the polishing can be controlled.

In addition, to achieve the above object, according to a second aspect of the present invention, there is provided a polishing method for polishing an object having a copper film on the surface to be polished, including the steps of interposing an electrolytic solution including a chelating agent between a cathode member and the polished surface, applying a voltage between the cathode member functioning as a cathode and the polished surface functioning as an anode to oxidize the surface of the copper film and form a chelate film of an oxidized copper film, selectively removing a projecting portion of the chelate film corresponding to the shape of the copper film to expose the copper film of that projecting portion at its surface, and repeating the above chelate film forming step and the chelate film removing step until the projecting portion of the copper film is flattened.

According to the polishing method of the present invention for polishing an object having a copper film on the surface to be polished, by interposing an electrolytic solution including a chelating agent between a cathode member and the polished surface and applying a voltage between the cathode member used as a cathode and the polished surface of the polished object used as an anode, the uneven copper surface is oxidized by the anodic oxidation. This oxidized copper is chelated by the chelating agent in the electrolytic solution, forming a chelate film of rather low mechanical strength thus able to be removed easily. If selectively removing a projecting portion of the chelate film, because

6

the copper further exposed thereby is chelated after being oxidized by the anodic oxidation, flatness of the copper film is achievable by repeating the step of selectively removing the projecting portion of the chelate film.

Since the resistance of the chelate film is higher than copper, the copper covered by the unmoved chelate film remaining in the groove is hard to be oxidized by the anodic oxidation by supplying a current, so the chelation is very slow and a chelate film is formed by the anodic oxidation only at the projecting portion of copper exposed by removing the chelate film.

Further, because the current is supplied through an electrolytic solution, if the potential difference between the copper film on the anode and the cathode member of the cathode is constant, the current density becomes larger the shorter the distance between electrodes. Therefore, in the copper film exposed after removing the chelate film, the more projecting a part of the copper film is, the shorter the electrode distance to the cathode member used as the cathode and thus the higher the current density and consequently, the higher the speed of the anodic oxidation and the faster the chelation.

Accordingly, because of the accelerated chelation of the projecting portion of the copper film, it is possible to achieve efficient flattening and suppression of damage to an interlayer insulation film below a copper film.

In addition, to achieve the above object, according to a third aspect of the present invention, there is provided a method for production of a semiconductor device, including the steps of forming at least a groove or hole in an insulation film formed on a substrate, stacking a metal film on the insulation film so as to bury the groove or hole, interposing an electrolytic solution between a cathode member and the metal film, applying a predetermined voltage between the cathode member used as a cathode and the metal film used as an anode, removing the surface of the metal film, and repeating the above step of removing the metal film until the unevenness of the surface of the metal film is reduced.

Further, the method for producing a semiconductor device of the present invention further includes a step of forming a barrier film for preventing diffusion of the metal film to the insulation film on the insulation film so as to bury the groove or hole after forming the groove or hole in the insulation film and before stacking the metal film on the insulation film, wherein the metal film is stacked on the barrier film in the step of stacking the metal film on the insulation film.

Further, in the step of removing the surface of the metal film, the step of copper film removal is repeated until the metal film stacked outside the groove or hole is removed.

According to the above method for producing a semiconductor device, when processing the surface of a metal film buried in a groove or hole, by interposing an electrolytic solution between a cathode member and the metal film and applying a predetermined voltage between the cathode member used as a cathode and the metal film used as an anode, the metal film is oxidized by the anodic oxidation, ionized in a state of metallic ions, and has a very low mechanical strength enabling it to be easily removed. If removing the oxidized metal film, the further exposed metal film is oxidized by the anodic oxidation again. By repeating the step of removing the metal film after the anodic oxidation, the step difference of the metal film can be reduced.

Further, because current is supplied through an electrolytic solution, if the potential difference between the metal film of the anode and the cathode member of the cathode is constant, the current density becomes larger the shorter the distance between electrodes. Therefore, in the copper film

exposed after removing the chelate film, the more projecting the copper film is, the shorter the electrode distance to the cathode member used as the cathode and thus the higher the current density. Consequently, the anodic oxidation of the projecting portion of the metal film is accelerated, the step difference of the metal film surface can be efficiently reduced, and the damage to the insulation film below the metal film can be suppressed.

In addition, to achieve the above object, according to a fourth aspect of the present invention, there is provided a polishing apparatus for polishing an object having a copper film on the surface to be polished, comprising a polishing tool having a polishing surface and having conductivity, a polishing tool rotating and holding means for rotating the polishing tool about a predetermined axis of rotation and holding the same, a rotating and holding means for holding a polishing object and rotating the same about a predetermined axis of rotation, a moving and positioning means for moving and positioning the polishing tool to a target position in a direction facing the polishing object, a relative moving means for making the polished surface of the polishing object and the polishing surface of the polishing tool relatively move along a predetermined plane, an electrolytic solution feeding means for feeding an electrolytic solution including a chelating agent onto the polished surface, and a current supplying means for supplying an electrolytic current flowing through the polishing tool through the electrolytic solution from the polished surface by using the polished surface as an anode and the polishing tool as a cathode.

According to the polishing apparatus of the present invention, for example, if a copper film with unevenness is formed on a polished surface of the object to be polished, the polished surface of the copper film is oxidized by the anodic oxidation by the current supplying means. This oxidized copper is chelated by a chelating agent in an electrolytic solution fed by the electrolytic solution feeding means. A chelate film of a rather low mechanical strength and able to be easily removed is thus formed.

The moving and positioning means brings the polishing surface into contact or proximity with the polished surface. The polishing tool rotating and holding means rotates the polishing surface and the polished surface in a state in contact or proximity with each other. Therefore, the projecting portion of a chelate film is removed. Further, by the relative moving means, projecting portions of the chelate film on the entire polished surface are polished and removed, therefore the polished surface can be polished efficiently at a low polishing pressure.

In the polishing apparatus of the present invention, preferably the electrolytic current supplying means comprises an anode member arranged to be able to be brought into contact or proximity with the polished surface and supply current to the polished surface using the polished surface as an anode and a DC power supply supplying a predetermined DC power between the anode member means and the polishing tool.

By locally passing a current from the anode member to the copper film through the electrolytic solution, a stable current can be supplied.

In this case, a current is supplied to the copper film from the anode member via the electrolytic solution and further from the copper film to the cathode member through the electrolytic solution, so the copper film near the polishing tool serving as a cathode is oxidized and chelated.

In the polishing apparatus according to the present invention, preferably the DC power supply outputs a pulse-like voltage of a predetermined period.

For example, setting the pulse width extremely short is effective for making the amount of the chelate film formed by the anodic oxidation per pulse very small, preventing sudden, huge anode oxidation of the copper film due to discharge due to a sudden change of the distance between electrodes in a case of contact with unevenness of the surface or the like, spark discharge due to a sudden change of electrical resistance occurring when air bubbles, particles, or the like are interposed, etc. and achieving continuity of amounts as small as possible.

In the polishing apparatus according to the present invention, preferably the anode member comprises a metal more precious than copper formed on the polished surface. Due to this, elution of the anode member to the electrolytic solution can be prevented, and the copper film can be actively oxidized by the anodic oxidation. Note since the cathode is essentially not eluted, it is not necessary to consider the preciousness of the cathode.

The polishing apparatus according to the present invention preferably further comprises a current detecting means for detecting a value of a current flowing from the polished surface to the polishing tool, more preferably further comprises a control means for controlling a position of the polishing tool in a direction substantially perpendicular with the polished surface so that the value of the current becomes constant on the basis of a detection signal of the current detecting means.

By control to make the current value constant, the current density becomes constant constantly and thereby the amount of the chelate film formed by the anode oxidation can be controlled constant.

In addition, to achieve the above object, according to a fifth aspect of the present invention, there is provided a polishing apparatus which comprises a polishing tool having a polishing surface in contact with the entire surface of the polished surface of the polishing object while rotating it and which brings the polishing object into contact with the polished surface while rotating it so as to flatten and polish the same, the polishing apparatus comprising an electrolytic solution feeding means for feeding an electrolytic solution including a chelating agent onto the polishing surface and an anode electrode and a cathode electrode capable of supplying electric power in the polishing surface and flattening the polished surface by electrolytic composite polishing which combines electrolytic polishing by the electrolytic solution and mechanical polishing by the polishing surface.

According to the polishing apparatus of the present invention, for example, by applying a voltage to the anode and cathode provided on the polishing surface, a current is supplied to the copper film on the polished surface from the anode member on the polishing surface via the electrolytic solution and furthermore from the copper film to the cathode on the polishing surface through the electrolytic solution, so the copper film of the polished surface near the cathode is oxidized.

This oxidized copper is chelated by the chelating agent in the electrolytic solution fed by the electrolytic solution feeding means, whereby a chelate film of a rather low mechanical strength able to be easily removed is formed.

By rotating the polishing surface and the polished surface respectively in a state contacting each other entirely or brought close to each other entirely, projecting portions of the chelate film on the entire polished surface are polished and removed, therefore the polished surface can be polished efficiently with a low polishing pressure.

In addition, to achieve the above object, according to a sixth aspect of the present invention, there is provided a

polishing apparatus for polishing an object having a copper film on the surface to be polished, comprising a holding means for holding the object to be polished, an electrode plate arranged parallel with the polished surface, a vibration applying means for applying vibration on the polished object, an electrolytic solution feeding means for feeding an electrolytic solution including a chelating agent between the polished surface and the electrode plate, and an electrolytic current supplying means for supplying an electrolytic current flowing through the electrolytic solution from the polished surface to the electrode plate by using the polished surface as an anode and the electrode as a cathode.

According to the polishing apparatus of the present invention, for example, if a copper film with unevenness is formed on the polished surface, the polished surface of the copper film is oxidized by the anodic oxidation by the current supplying means. This oxidized copper is chelated by the chelating agent in the electrolytic solution fed by the electrolytic solution feeding means, whereby a chelate film of a rather low mechanical strength able to be easily removed is formed.

The projecting portions of the chelate film are selectively removed by the vibration action on the polished object by the vibration applying means. This enables efficient polishing causing little damage to the polished object.

The polishing apparatus according to the present invention preferably further comprises a current detecting means for detecting a value of a current flowing from the polished surface to the polishing tool. Thereby the electrolytic current can be monitored and the polishing process controlled, so it becomes possible to correctly grasp the state of progress of the polishing process.

In addition, to achieve the above object, according to a seventh aspect of the present invention, there is provided a polishing apparatus for polishing an object having a copper film on the surface to be polished, comprising a holding means for holding the polished object, an electrode plate arranged parallel with the polished surface, an electrolytic solution feeding means for feeding an electrolytic solution including a chelating agent between the polished surface and the electrode plate, an electrolytic current supplying means for supplying an electrolytic current flowing through the electrolytic solution from the polished surface to the electrode plate by using the polished surface as an anode and the electrode as a cathode, and a flushing means for flushing the electrolytic solution between the polished surface and the electrode plate.

According to the polishing apparatus of the present invention, for example, if a copper film with unevenness is formed on the polished surface of the object to be polished, the polished surface of the copper film is oxidized by the anodic oxidation by the current supplying means. This oxidized copper at an anode is chelated by the chelating agent in the electrolytic solution fed by the electrolytic solution feeding means, whereby a chelate film of a rather low mechanical strength able to be easily removed is formed.

The projecting portions of the chelate film are selectively removed by a vibration action on the polished object by the vibration applying means. This enables efficient polishing causing little damage to the polished object.

The polishing apparatus according to the present invention preferably further comprises a current detecting means for detecting a value of a current flowing from the polished surface to the polishing tool. Therefore, the electrolytic current can be monitored and the polishing process controlled, so it becomes possible to correctly grasp the state of progress of the polishing process.

In addition, to achieve the above object, according to an eighth aspect of the present invention, there is provided a polishing apparatus for polishing an object having a metal film on the surface to be polished, comprising a holding means for holding the polished object, a wiper for wiping the surface of the polished object, an electrolytic solution feeding means for feeding an electrolytic solution on the surface of the polished object, a facing electrode arranged at a position facing the surface of the polished object, and a current supplying means for supplying a current between the surface of the polished object and the facing electrode.

In addition, to achieve the above object, according to a ninth aspect of the present invention, there is provided a polishing apparatus for polishing an object having a metal film on the surface to be polished, comprising a holding means for holding the polished object, a wiper for wiping the surface of the polished object, a relative moving means for relatively moving the surface of the polishing object and the wiper, an electrolytic solution feeding means for feeding an electrolytic solution on the surface of the polished object, a facing electrode arranged at a position facing the surface of the polished object, and a current supplying means for supplying a current between the surface of the polished object and the facing electrode.

The relative moving means presses the wiper on the surface of the polished object and rotates the wiper relative to a predetermined center axis of rotation.

Alternatively, the relative moving means presses the wiper against the surface of the polished object and horizontally moves the wiper in the surface of the polished object.

Alternatively, the relative moving means rotates the holding means relative to a predetermined center axis of rotation.

Alternatively, the relative moving means horizontally moves the holding means in a surface parallel with the surface of the wiper.

According to the above polishing apparatuses according to the present invention, for example, when a metal film is formed on the polished surface of the polishing object, an electrolytic solution is fed onto the surface of the polishing object by the electrolytic solution feeding means, and a current is supplied between the surface of the polishing object and the facing electrode by the current supplying means, so the metal film is oxidized by the anodic oxidation, ionized into a state of metallic ions, and has a very low mechanical strength enabling it to be easily removed.

Further, by wiping the surface of the oxidized metal film using a wiper, the oxidized metal is removed, therefore, the polishing object can be polished efficiently even at a low pressure.

BRIEF DESCRIPTION OF THE DRAWINGS

The above object and features of the present invention will be more apparent from the following description of the preferred embodiments given with reference to the accompanying drawings, wherein:

FIGS. 1A to 1C are sectional views of the steps of the method of production of a semiconductor device of the present invention, where FIG. 1A shows the step for forming an insulation film on a semiconductor substrate, FIG. 1B shows the step for forming contact holes and interconnection grooves, and FIG. 1C shows the step for forming a barrier film;

11

FIGS. 2D and 2E are views of the steps continuing from FIGS. 1A to 1C, where FIG. 2D shows the step of forming a copper film as a seed film, while FIG. 2E shows the step of forming a copper film;

FIGS. 3F and 3G are views of the steps continuing from FIGS. 2D and 2E, where FIG. 3F shows the step of anodic oxidation of the copper film, while FIG. 3G shows the step of forming a chelate film;

FIGS. 4H and 4I are views of the steps continuing from FIGS. 3F and 3G, where FIG. 4H shows the step of removing projecting portions of the chelate film, while FIG. 4I shows the step of re-forming a chelate film;

FIGS. 5J to 5L are views of the steps continued from FIGS. 4H and 4I, where FIG. 5J shows the step of flattening the copper film, FIG. 5K shows the step of removing excess copper film, and FIG. 5L shows the step of exposing the barrier film;

FIG. 6 is a view of the configuration of a polishing apparatus according to a first embodiment of the present invention;

FIG. 7 is an enlarged view of the internal configuration of a polishing tool holding means of a polishing apparatus according to the first embodiment of the present invention;

FIG. 8A is a bottom view of an electrode plate used in a polishing apparatus according to the first embodiment of the present invention, while FIG. 8B is an enlarged view of the vicinity of the electrode plate;

FIG. 9 is a view of the relationship between a polishing tool and a wafer;

FIG. 10 is a schematic view for explaining the electrolytic polishing of a polishing apparatus according to the first embodiment of the present invention;

FIG. 11 is an enlarged sectional view of the circular portion C of FIG. 10;

FIG. 12 is an enlarged sectional view of the circular portion D of FIG. 11;

FIG. 13 is a view of a first modification of the polishing apparatus according to the present invention;

FIG. 14 is a view of a second modification of the polishing apparatus according to the present invention;

FIG. 15 is a view of a third modification of a conventional CMP apparatus of a polishing apparatus according to the present invention;

FIG. 16 is a view for explaining an electrolytic composite polishing operation by the polishing apparatus shown in FIG. 15;

FIG. 17 is a view of another example of an electrode configuration of a polishing pad;

FIG. 18 is a view of still another example of an electrode configuration of a polishing pad;

FIG. 19 is a schematic view of the configuration of a polishing apparatus according to a second embodiment of the present invention;

FIG. 20 is a schematic view of the configuration of a polishing apparatus according to a third embodiment of the present invention;

FIG. 21 is a view of a configuration of a polishing apparatus according to a fourth embodiment of the present invention;

FIG. 22A and FIG. 22B shows measurement results in a fifth embodiment;

FIG. 23 shows measurement results in a sixth embodiment;

FIG. 24 shows measurement results in a seventh embodiment;

FIGS. 25A to 25C are sectional views of steps of the method of formation of copper interconnections by a dual

12

damascene process according to an example of the related art, where FIG. 25A shows the step of forming an insulation film, FIG. 25B shows the step of forming contact holes and interconnection grooves, and FIG. 25C shows the step of forming a barrier film;

FIGS. 26D to 26F are views of the steps continuing from FIGS. 25A to 25C, where FIG. 26D shows the step of forming a seed film, FIG. 26E shows the step of forming an interconnection layer, and FIG. 26F shows the step of forming interconnections;

FIG. 27 is a sectional view for explaining dishing occurring in polishing of a copper film by CMP;

FIG. 28 is a sectional view for explaining erosion occurring in polishing of a copper film by CMP;

FIG. 29 is a sectional view for explaining a recess occurring in polishing of a copper film by CMP; and

FIG. 30 is a sectional view for explaining a scratch SC and chemical damage CD occurring in polishing of a metal film by CMP.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Below, a description will be made of preferred embodiments of a method for producing and a method of polishing a semiconductor device and a polishing apparatus of the present invention by referring to the drawings.

First Embodiment

A description will be made of embodiments of the present invention by taking as an example the case where the present invention is applied to a process of formation of metal interconnections by a dual damascene process in a method of production of a semiconductor device.

Polishing Method

First, as shown in FIG. 1A, for example an interlayer insulation film 102 made of for example a silicon oxide film (SiO_2) is formed by a low pressure chemical vapor deposition (LP-CVD) process by using for example tetraethyl orthosilicate (TEOS) as the reaction source on a silicon or other semiconductor substrate 101 on which a not illustrated impurity diffusion region or an interconnection is suitably formed.

Note that as the interlayer insulation film 102, use can be made of a so-called low-k (low dielectric constant) material, in addition to a TEOS (tetraethyl orthosilicate) film and a silicon nitride film formed by a CVD process.

Here, the low dielectric constant materials include SiF , SiOCH , polyarylether, porous silica, or polyimide.

Next, as shown in FIG. 1B, contact holes CH communicating with the impurity diffusion region of the semiconductor substrate 101 and interconnection grooves M are formed by using well-known photolithography and etching. Note that the depth of the interconnection use grooves M is for example about 800 nm.

Next, as shown in FIG. 1C, a barrier film 103 is formed on the surface of the interlayer insulation film 102 and in the contact holes CH and the interconnection grooves M. This barrier film 103 is formed by a material such as Ta, Ti, W, Co, Si, Ni, an alloy of compounds of these metals with nitrogen or phosphor such as TaN, TiN, WN, CoW, CoWP, TiSiN, NiWP, or others, or a stack of films comprised of these materials. A barrier film comprised of these material is fabricated to a thickness of for example about 25 nm by

13

physical vapor deposition (PVD) or CVD using a well-known sputtering system, a vacuum vapor deposition system, or the like.

The barrier film **103** is provided in order to prevent the diffusion of the material comprising the interconnections into the interlayer insulation film **102** and to increase the adhesion with the interlayer insulation film **102**. Particularly, as in the present embodiment, when the interconnection material is copper and the interlayer insulation film **102** is silicon oxide, since copper has a large diffusion coefficient as compared in a silicon oxide film, it can be easily oxidized. This should be prevented.

Next, as shown in FIG. 2D, a seed film **104** made of a material the same as the material for forming the copper interconnections is formed on the barrier film **103** to a thickness of for example about 150 nm by well-known sputtering. The seed film **104** is formed for later electroplating. For example, it is formed so as to accelerate the growth of metal grains when burying the interconnection grooves and the contact holes with a metal.

Next, as shown in FIG. 2E, an interconnection layer **105** made of Al, W, WN, Cu, Au, or Ag, or an alloy film of these metals, is formed on the barrier film **103** to a thickness of for example about 1600 nm so as to bury the contact holes CH and the interconnection grooves M. The interconnection layer **105** is preferably formed by electroplating or electroless plating, but it is also possible to form the interconnection layer **105** by CVD, PVD, sputtering, or the like. Note that the seed film **104** is integrally formed with the interconnection layer **105**.

Due to the burying of the contact holes CH and the interconnection grooves M, unevenness having a height of for example about 800 nm is caused on the surface of the interconnection layer **105**.

Below, an explanation is made for example of a case where copper is stacked as the interconnection layer.

The above process is carried out in a way similar to the related art, but in the polishing method of the present invention, the excess metal film **103** present on the interlayer insulation film **102** is removed by not chemical mechanical polishing, but electrolytic composite polishing using an electrolytic action. Specifically, the copper film is oxidized by the anodic oxidation, and a chelate film is formed on the surface thereof.


The method for forming the chelate film, as shown in FIG. 3F, includes the steps of arranging a cathode member **120** parallel with the copper film **105** and interposing an electrolytic solution EL including a chelating agent for chelating copper as an electrolyte or an additive between the cathode member **120** and the copper film **105**. Note that starting from FIG. 4, the cathode member **120** and the electrolytic solution EL are not shown in the figures.

Further, a brightener, copper ions, etc. can be added to an electrolytic solution in addition to the above additives.

The temperature of the electrolytic solution EL is controlled, and the degree of oxidation of the surface of the metal film, chelating film formation, and wiping are optimized.

Here, as the chelating agent, use may be made of for example quinaldine acid of chemical formula (1), glycine of chemical formula (2), citric acid of chemical formula (3), oxalic acid of chemical formula (4), propionic acid of chemical formula (5), and so on.


14



(1)



(2)



(3)



(4)




(5)


The copper film **105** serving as the anode forms CuO by anodic oxidation. Here, the distance d_1 between a projecting portion on the surface of the copper film **105** and the cathode member **120** is shorter than the distance d_2 between a recessed portion on the surface of the copper film **105** and the cathode member **120**, so when the potential difference between the cathode member **120** and the copper film **105** is constant, the current density at the projecting portion is greater than that at the recessed portion, therefore, the anodic oxidation is accelerated.

As shown in FIG. 3G, the surface of the oxidized copper film (CuO) **105** is chelated by the chelating agent in the electrolytic solution. When quinaldine acid is used as the chelating agent, a film made from a chelated compound of the chemical formula (6) is formed. When glycine is used, a film made from a chelate compound of the chemical formula (7) is formed. Any of these chelate films **106** has an electric resistance higher than copper and a very low mechanical strength. Accordingly, after a chelate film **106** is formed on the copper film **105**, the value of the current from the copper film **105** to the cathode member **120** via the electrolytic solution EL decreases. Before the anodic oxidation, copper chelation is suppressed.

(6)



(7)



15

Next, as shown in FIG. 4H, when the projecting portions of the chelate film **106** formed on the surface of the copper film **105** are removed by wiping, mechanical polishing, etc., the electrolytic solution EL may also include a not shown slurry. Further, because the mechanical strength of the chelate film **106** is very low, it can be easily removed even by applying vibration to the substrate **101** or by jetting the electrolytic solution.

Because the projecting portion of the copper film **105** of the low electric resistance is exposed in the electrolytic solution at that time, the value of the current flowing from the copper film **105** to the cathode member **120** via the electrolytic solution EL rises.

Next, as shown in FIG. 4I, because of the low electric resistance and short distance to the cathode **120**, the projecting portion of the copper film **105** exposed in the electrolytic solution is intensively oxidized by the anodic oxidation and the oxidized copper is chelated. Then, the current flowing from the copper film **105** to the cathode member **120** via the electrolytic solution EL decreases again.

After that, the projecting portions of the chelate film **106** are selectively removed by the previously mentioned wiping, mechanical polishing, etc., the exposed copper film **105** is intensively oxidized and chelated, and the projecting portions of the chelate film **106** are selectively removed. These steps are repeated. In this process, the current from the copper film **105** flowing to the cathode member **120** via the electrolytic solution EL rises and falls together with removal and formation of the chelate film **106**, respectively.

Next, as shown in FIG. 5J, after the above step, the copper film **105** is flattened. The flattened copper film **105** is removed from the entire surface by wiping, mechanical polishing, etc., whereby the current flowing from the copper film **105** to the cathode member **120** via the electrolytic solution EL reaches its maximum once during this process.

Next, as shown in FIG. 5K, the chelate film formed by anodic oxidation on the entire surface of the flattened copper film **105** continues to be removed until the excess copper film **105** on the barrier film **103** disappears completely.

Next as shown in FIG. 5L, the entire copper film **105** is removed by for example the aforethe wiping, mechanical polishing, etc. to expose the surface of the barrier film **103**. At this time, as the barrier film **103** has a higher electric resistance than the copper film. **105**, the current starts to decline after the removal of the chelate film **106**. At the time of starting to decline (near the end), the applied current is reduced first, then the application of current is stopped to stop the chelation due to the anodic oxidation. The processes up to here complete the flattening of the initial unevenness of the surface of the copper film **105**.

Next, the barrier film **103** stacked outside the interconnection grooves is removed, whereby the copper interconnections are formed.

According to the polishing method according to the present embodiment, since the polishing rate of the polishing is assisted electrochemically assisted, the polishing is possible at a low polishing pressure compared with conventional chemical mechanical polishing. Even in comparison with simple mechanical polishing, this is highly advantageous in reducing scratches, reducing step differences, reducing dishing and erosion, etc.

Further, since the polishing is possible at a low pressure, it is extremely useful in a case where an organic film of a low dielectric constant or a porous insulation film of a low dielectric constant, which have low mechanical strengths and are easily broken by conventional chemical mechanical polishing, is used for the interlayer insulation film **102**.

16

In the chemical mechanical polishing of the related art, when using a slurry containing alumina particles etc., the alumina particles may remain without wear after contributing to the CMP processor they may be buried in the surface of the copper (particle). In the polishing method of the present invention, however, since the chelate film formed on the surface has a very low mechanical strength it can be removed effectively even by mechanical polishing or wiping using a chelating agent not containing a polishing abrasive as the electrolytic solution.

Further, by monitoring the electrolytic current, the polishing process can be controlled, so it becomes possible to correctly grasp the state of progress of the polishing process.

The polishing method according to the present invention is not limited to the above embodiment. As described above, it can also be applied to interconnections comprised of, for example, Al, W, WN, Cu, Au, or Ag, or an alloy film of these metals, in addition to copper. It can also be applied to polishing of a barrier film comprised of the above materials.

Further, the polishing method according to the present invention can also be applied to polishing of numerous metal films used for other than interconnections.

Further, various modifications can be made to the type of the chelating agent, the type of the cathode member, and so on without departing from the basic concept of the present invention.

Further, numerous modifications can be made without departing from the basic concept and scope of the invention, such as the type of the chelating agent, the type of the cathode member, and so on.

Further, the method for producing a semiconductor device is not limited to the above embodiment either. For example, the method of polishing a metal film is not limited in any way. In the present embodiment, a dual damascene process was explained as an example, but the present invention is also applicable to a single damascene process. In addition, numerous modifications can also be made without departing from the basic concept and scope of the invention in, such as, methods for fabricating contact holes or interconnection grooves and methods for fabricating a copper film and a barrier film.

Configuration of Polishing Apparatus

FIG. 6 is a view of the configuration of a polishing apparatus according to an embodiment of the present invention.

The polishing apparatus shown in FIG. 6 is provided with a polishing head H, an electrolytic power supply **61**, a controller **55** having a function of controlling the entire polishing apparatus, a slurry feeder **71**, and an electrolytic solution feeder **81**.

Note that, although not illustrated, the polishing apparatus is installed in a clean room, and a loading/unloading port for loading and unloading a wafer cassette storing wafers serving as the polishing objects in or out of the clean room is provided in the clean room. Further, a wafer conveyance robot for transferring the wafer between the wafer cassette loaded in the clean room through this loading/unloading port and the polishing apparatus is arranged between the loading/unloading port and the polishing apparatus.

The polishing head H is provided with a polishing tool holder **10** (a polishing tool rotating and holding means) for holding and rotating the polishing tool **11**, a Z-axis positioning mechanism **30** (a moving and positioning means) for positioning the polishing tool holder **10** to a target position in the Z-axial direction, and an X-axis movement mechanism **40** (a rotating and holding means and a relative moving

means) for holding and rotating a wafer as the polishing object and moving it in the X-axial direction.

The Z-axis positioning mechanism **30** has a Z-axis servo motor **31** fixed to a not illustrated column, a ball screw shaft **31a** connected to the Z-axis servo motor **31**, a Z-axis slider **32** which is connected to a holder **33** and a main shaft motor **14** and formed with a screw portion screwed into the ball screw shaft **31a**, and a guide rail **33** arranged in a not illustrated column for holding the Z-axis slider **32** so that it can freely move in the Z-axial direction.

The Z-axis servomotor **31** is supplied with a drive current from a Z-axis driver **51** connected to the Z-axis servomotor **31** to be driven to rotate. The ball screw shaft **31a** is provided along the Z-axial direction, with one end of it connected to the Z-axis servo motor **31** and with the other end rotatably held by the holding member provided in the not illustrated column, and is screwed into the screw portion of the Z-axis slider **32** between the ends.

Due to the above configuration, by being driven by the Z-axis servo motor **31**, the ball screw shaft **31a** is rotated. The polishing tool **11** held at the polishing tool holder **10** is moved and positioned via the Z-axis slider **32** to any position in the Z-axial direction. The positioning precision of the Z-axis positioning mechanism **30** is set at a resolution of about 0.1 μm .

The X-axis movement mechanism **40** has a wafer table **42** for chucking the wafer W, a holder **45** for rotatably holding the wafer table **42**, a drive motor **44** for supplying a drive force for rotating the wafer table **42**, a belt **46** for connecting the drive motor **44** and a rotation shaft of the holder **45**, a polishing pan **47** provided in the holder **45**, an X-axis slider **48** at which the drive motor **44** and the holder **45** are disposed, an X-axis servo motor **49** mounted on a not illustrated base, a ball screw shaft **49a** connected to the X-axis servo motor **49**, and a moveable member **49b** connected to the X-axis slider **48** and with a screw portion screwed into the ball screw shaft **49a** formed therein.

The wafer table **42** holds the wafer W by for example a vacuum suction means.

The polishing pan **47** is provided for collecting the used electrolytic solution and slurry or other liquid.

The drive motor **44** is connected to the table driver **53** and is driven by supply of the drive current from the table driver **53**. By controlling this drive current, the semiconductor substrate table **42** can be rotated at a predetermined rotation speed.

The X-axis servomotor **49** is driven to rotate by the drive current supplied from an X-axis driver **54** connected to the X-axis servomotor **49**. The X-axis slider **48** moves in the X-axial direction via the ball screw shaft **49a** and the moveable member **49b**. At this time, by controlling the drive current supplied to the X-axis servo motor **49**, the control of the speed of the wafer table **42** in the X-axial direction becomes possible.

The slurry feeder **71** feeds the slurry to the wafer W through a not illustrated feed nozzle. As the slurry, for polishing a copper film, for example use is made of one comprised of an aqueous solution having oxidizing power based on hydrogen peroxide, iron nitrate, potassium iodate, etc. to which aluminum oxide (alumina), cerium oxide, silica, germanium oxide, or the like is added as the polishing abrasive. Note that the slurry may be supplied only when necessary.

The electrolytic solution feeder **81** feeds an electrolytic solution EL including a chelating agent to the wafer W through a not illustrated feed nozzle.

The electrolyte can be one based on an organic solvent or an aqueous solution.

The acid used for the electrolyte may include for example copper sulfate, ammonium sulfate, phosphoric acid, and so on. Examples of alkali include ethyldiamine, NaOH, KOH, and so on.

Further, as the electrolyte, use can also be made of a dilute mixture of organic solvents including ethanol, methanol, glycerin, ethylene glycol, and so on.

The additives include Cu ion series substance, a brightener, or a chelating agent.

For the brightener, use can be made of sulphuric series, copper ion series such as copper hydroxide and copper phosphate, chlorine ion series such as hydrochloric acid and so on, benzotriazole (BTA), or polyethylene glycol.

As the chelating agent, for example, quinoline, anthranilic acid, etc., can be used in addition to the aforethe quinaldine acid, glycin, citric acid, oxalic acid, propionic acid, and so on.

FIG. 7 is a view of the internal structure of the polishing tool holder **10** of the polishing tool according to the present embodiment.

The polishing tool holder **10** is provided with the polishing tool **11**, a flange member **12** for holding the polishing tool **11**, the holder **13** for holding the flange member **12** so that it can freely rotate with respect to a main shaft **13a**, a main shaft motor **14** for rotating the main shaft **13a** held at the holder **13**, and a cylinder device **15** provided on the main shaft motor **14**.

The main shaft motor **14** is made of for example a direct drive motor. A not illustrated rotor of this direct drive motor is connected to the main shaft **13a**.

Further, the main shaft motor **14** has a through hole at its center into which a piston rod **15b** of the cylinder device **15** is inserted. The main shaft motor **14** is driven by the drive current supplied from a main shaft driver **52**.

The holder **13** is provided with for example an air bearing. The main shaft **13a** is rotatably held by this air bearing. Also, the main shaft **13a** of the holder **13** has a through hole at its center into which the piston rod **15b** is inserted.

The cylinder device **15** is fixed on the case of the main shaft motor **14** and houses a piston **15a**. The piston **15a** is driven in either direction of the arrows **A1** and **A2** by for example air pressure fed into the cylinder device **15**.

The piston rod **15b** is connected to this piston **15a**. The piston rod **15b** passes through the center of the main shaft motor **14** and the holder **13** and projects from the opening **12a** of the flange member **12**.

The front end of the piston rod **15b** has a pressing member **21** connected to this. This pressing member **21** is connected to the piston rod **15b** by a connecting mechanism that can change in posture within a predetermined range.

The pressing member **21** can abut against a circumferential edge of an opening **22a** of an insulation plate **22** arranged at a facing position and presses against the insulation plate **22** by the drive of the piston rod **15b** to the direction indicated by the arrow **A2**.

At the center portion of the piston rod **15b** of the cylinder device **15** is formed a through hole. A conductive shaft **20** is inserted into the through hole and fixed with respect to the piston rod **15b**.

The conductive shaft **20** is formed by a conductive material. An upper end side passes through the piston **15a** of the cylinder device **15** and extends to a rotary joint **16** provided on the cylinder device **15**, while a lower end side

19

passes through the piston rod **15b** and the pressing member **21** and extends to the electrode plate **23** and is connected to the electrode plate **23**.

The conductive shaft **20** is formed at its center with a through hole. This through hole forms a feed nozzle for feeding a chemical polishing agent (slurry) and the electrolytic solution containing a chelating agent onto the wafer W.

Further, the conductive shaft **20** performs the role of electrically connecting the rotary joint **16** and the electrode plate **23**.

The rotary joint **16** is electrically connected to a plus pole of the electrolytic power supply **61** and maintains the power supply to the conductive shaft **20** even when the conductive shaft **20** rotates.

The electrode plate **23** is held at its upper surface side at the insulation plate **22**, an outer circumference of the electrode plate **23** is fitted to the insulation plate **22**, and the scrub member **24** is adhered to the lower surface side.

The insulation plate **22** is formed by an insulation material such as a ceramic. This insulation plate **22** is connected to the main shaft **13a** by a plurality of rod-like connecting members **26**. The connecting members **26** are arranged at equal intervals from the center axis of the insulation plate **22** at predetermined radial positions and held moveably with respect to the main shaft **13a** of the holder **13**. For this reason, the insulation plate **22** can move in the axial direction of the main shaft **13a**.

Further, the insulation plate **22** and the main shaft **13a** are connected by an elastic member **25** made of for example a coil spring corresponding to each connecting member **26**.

By employing a configuration in which the insulation plate **22** is made moveable with respect to the main shaft **13a** of the holder **13** and in which the insulation plate **22** and the main shaft **13a** are connected by the elastic member **25**, when feeding high pressure air to the cylinder device **15** and moving the piston rod **15b** downward in the direction indicated by the arrow **A2**, the pressing member **21** pushes the insulation plate **22** downward against a recovery force of the elastic member **25**, and the scrub member **25** moves downward together with this.

When stopping the feed of the high pressure air to the cylinder device **15**, the insulation plate **22** rises due to the recovery force of the elastic member **25** and the scrub member **24** rises together with this.

The polishing tool **11** is tightly fixed to an annular lower end surface **12b** of the flange member **12**. This polishing tool **11** is formed in the shape of a wheel and provided with an annular polishing surface **11a** at its lower end surface. The polishing tool **11** has conductivity and is preferably formed by a relatively soft material. For example, it can be formed by a porous body made of carbon with a binder matrix (binding agent) itself which has conductivity or a resin such as a melamine resin, epoxy resin, or polyvinyl acetal (PVA) containing a conductive material such as sintered copper or a metal compound.

The polishing tool **11** is directly connected to the flange member **12** having conductivity and supplied with power from the conductive brush **27** contacting the flange member **12**.

Namely, the conductive member **28** provided at the main shaft motor **14** and the side surface of the holder **13** is electrically connected to the minus pole of the electrolytic power supply **61**, while the conductive brush **27** provided in the conductive member **28** is in contact with the upper end surface **12c** of the flange member **12**. Due to this, the polishing tool **11** is electrically connected to the electrolytic

20

power supply **61** via the conductive member **28**, conductive brush **27**, and the flange member **12**.

The electrolytic power supply **61** (current supplying means) is a device for applying a predetermined voltage between the rotary joint **16** and the conductive member **28** described above. By the application of voltage between the rotary joint **16** and the conductive member **28**, a potential difference occurs between the polishing tool **11** and the scrub member **24**.

The electrolytic power supply **61** is not a constant voltage power supply for continuously outputting a constant voltage. It is preferable to use a power supply outputting a voltage pulse at a constant period, for example, a DC power supply including a switching regulator circuit.

Concretely, use is made of a power supply for outputting the pulse-like voltage at the constant cycle and capable of suitably changing the pulse width. As an example, use is made of one having an output voltage of DC 150V and a maximum output current of 2 to 3A and capable of changing the pulse width to either of 1, 2, 5, 10, 20, or 50 μ s.

The pulse-like voltage output having a short width as described above is set in order to make the amount of anodic oxidation per pulse very small. Namely, it is effective for achieving a continuity of small amounts of anodic oxidation for preventing or suppressing as much as possible a sudden huge amount of anodic oxidation of the copper film due, for example, to a discharge due to a sudden change of an inter-electrode distance seen in the unevenness of the copper film formed on the surface of the wafer W or in a case of contact or the like and a spark discharge due to a sudden change of an electrical resistance occurring when air bubbles, particles, or the like are interposed.

Further, the output voltage is relatively high in comparison with the output current, therefore a certain safety margin can be obtained in setting the inter-electrode distance. Namely, even if the inter-electrode distance slightly changes, since the output voltage is high, the change in the current is small.

Note that the applied pulse-like voltage is not limited to the above example. A periodical pulse-like voltage having a rectangular, sinusoidal, sawtooth, or PAM waveform may be applied.

The electrolytic power supply **61** is provided with an ammeter **62** as a current detecting means of the present invention. This ammeter **62** is provided so as to monitor the electrolytic current flowing through the electrolytic power supply **61** and outputs a monitored current value signal **62s** to the controller **55**.

Further, the electrolytic power supply **61** may also be provided with a resistance meter as a resistance value detecting means replacing the current detecting means. Its function is the same as that of the current detecting means.

The controller **55** has the function of controlling the entire polishing apparatus. Specifically, it outputs a control signal **52s** to the main shaft driver **52** to control the rotation speed of the polishing tool **11**, outputs a control signal **51s** to the Z-axis driver **51** to control the positioning of the polishing tool **11** in the Z-axial direction, outputs a control signal **53s** to the table driver **53** to control the rotation speed of the wafer W, and outputs a control signal **54s** to the X-axis driver **54** to control the speed of the wafer W in the X-axial direction.

Further, the controller **55** controls the operation of the electrolytic solution feeder **81** and the slurry feeder **71** to control the feeding operation of the electrolytic solution EL and the slurry SL to the polishing head.

21

Further, the controller 55 is able to control the output voltage of the electrolytic power supply 61, the frequency of the output pulse, the width of the output pulse, etc.

Further, the controller 55 receives as input a current value signal 62s from the ammeter 62 of the electrolytic power supply 61. Based on the current value signal 62s, the controller 55 grasps the state of progress of the polishing of the copper film and controls the operation of the polishing apparatus. Specifically, it controls the Z-axis servo motor 31 to position the polishing tool 11 in a direction perpendicular to the polished surface by using the current value signal 62s as a feedback signal so that the electrolytic current obtained from the current value signal 62s becomes constant or controls the operation of the polishing apparatus so as to stop the polishing based on the current value specified by the current value signal 62s.

A periodical pulse-like voltage can be applied so that the current flowing through the cathode member and the metal film changes in a step-like manner. For example, at the beginning of the process of removing the metal film, a periodical pulse-like voltage is applied so that the current flowing through the cathode member and the metal film rises gradually. Due to this, application of an instantaneous high voltage at the time of starting the application and the decline thereby of the surface condition of the metal film after removal can be prevented.

Further, near the end of the process of removing a metal film, the current value signal 62s becomes small. When the current value signal 62s becomes even smaller than a predetermined threshold, control is performed to reduce the output pulsed voltage near the end. After that, a control signal is output to the electrolytic power to stop the pulse output.

A control panel 56 connected to the controller 55 is used for inputting a variety of data by an operator or displaying the monitored current value signal 62s.

Here, FIG. 8A is a bottom view of an example of the structure of the electrode plate 23, and FIG. 8B is a sectional view of the positional relationships among the electrode plate 23, conductive shaft 20, scrub member 24 (cleaning member), and insulation member (plate) 22.

As shown in FIG. 8A, a circular opening 23a (feed nozzle) is formed at the center portion of the electrode plate 23. A plurality of grooves 23b are formed radially extending in a radial direction of the electrode plate 23 around this opening 23a.

Further, as shown in FIG. 8B, the opening 23a of the electrode plate 23 has the lower end of the conductive shaft 20 fitted and fixed to it.

By employing such a configuration, the slurry and the electrolytic solution fed through a feed nozzle 20a formed at the center of the conductive shaft 20 are diffused through the grooves 23b over the entire surface of the scrub member 24.

Namely, when the slurry and the electrolytic solution are fed to the upper surface of the scrub member 24 through the feed nozzle 20a formed at the center of the conductive shaft 20 during rotation of the electrode plate 23, conductive shaft 20, scrub member 24, and the insulation member (plate) 22, the slurry and the electrolytic solution spread to the entire upper surface of the scrub member 24.

Note that the scrub member 24 and the feed nozzle 20a of the conductive shaft 20 correspond to a concrete example of the electrolytic solution feeding means of the present invention. Further, the electrode plate 23, conductive shaft 20, and the rotary joint 15 correspond to a concrete example of the power supplying means of the present invention.

22

The scrub member 24 adhered to the bottom surface of the electrode plate 23 is formed by a material capable of absorbing the electrolytic solution and the slurry and passing them from the upper surface to the lower surface. Further, this scrub member 24 has a surface for contacting and scrubbing the wafer W. It is formed by for example a soft brush-like material, sponge-like material, or a porous material so as not to cause a scratch etc. in the surface of the wafer W. For example, there can be mentioned a porous body made of a resin such as a urethane resin, a melamine resin, an epoxy resin, or polyvinyl acetal (PVA).

FIG. 9 is a view of the positional relation of the polishing tool 11 and the wafer in the course of polishing.

The center axis of the polishing tool 11, for example, is inclined with respect to the wafer W with a minute angle. Further, the main shaft 12a of the holder 13 is inclined with respect to the main surface of the wafer W in the same way as the inclination of the polishing surface 11a. For example, by adjusting an attachment posture of the holder 13 to the Z-axis slider 32, a minute inclination of the main shaft 12a can be created.

In this way, by making the center axis of the polishing tool 11 incline with respect to the main surface of the wafer W with a minute angle, when pushing the polishing surface 11a of the polishing tool 11 against the wafer W with a predetermined polishing pressure F, the effective contact area is maintained constant.

The polishing apparatus according to the present embodiment makes part of the polishing surface 11a of the polishing tool 11 partially act upon the surface of the wafer W, uniformly scans the effective contact area on the surface of the wafer W, and uniformly polishes the entire surface of the wafer W.

Next, an explanation will be made of the polishing operation (polishing method) by the polishing apparatus by taking as an example a case where the copper film formed on the surface of the wafer W is polished. FIG. 10 is a schematic view of a state where the polishing tool 11 is moved downward in the z-axial direction in the polishing apparatus 1 to be brought into contact with the surface of the wafer W.

First, the wafer W is chucked on the wafer table 42, and the wafer table 42 is driven to rotate the wafer W at a predetermined speed.

Further, the wafer table 42 is moved in the X-axial direction, the polishing tool 11 attached to the flange portion 12 is positioned at a predetermined position above the wafer W, and the polishing tool 11 is rotated at the predetermined rotation speed. When the polishing tool 11 is rotated, the insulation plate 22, electrode plate 23, and scrub member 24 connected to the flange portion 12 are driven to rotate. Further, the pressing member 21 pressing against the scrub member 24, piston rod 15b, piston 15a, and the conductive shaft 20 simultaneously rotate.

From this state, when the slurry SL and the electrolytic solution EL are fed to the feed nozzle 20a in the conductive shaft 20 from the slurry feeder 71 and the electrolytic solution feeder 81, the slurry SL and the electrolytic solution EL are fed from the entire surface of the scrub member 24.

The polishing tool 11 is moved downward in the Z-axial direction and the polishing surface 11a of the polishing tool 11 is brought into contact to the surface of the wafer W and pressed by a predetermined polishing pressure.

Further, the electrolytic power supply 61 is activated, a minus potential is applied to the polishing tool 3 through the conductive brush 27, and a plus potential is applied to the scrub member 24 through the rotary joint 16.

Further, high pressure air is fed to the cylinder device **15** to move the piston rod **15b** downward in the direction indicated by the arrow **A2** of FIG. 7, and the bottom surface of the scrub member **24** is moved up to the position to be brought into contact or proximity with the wafer **W**.

The wafer table **42** is moved in the X-axial direction with a predetermined speed pattern from this state, whereby the entire surface of the wafer **W** is uniformly polished.

FIG. **11** is an enlarged view of the area in a circle **C** of FIG. **10**, and FIG. **12** is an enlarged view of the area in a circle **D** of FIG. **11**.

As shown in FIG. **11**, the scrub member **24**, used as the anode, carries current to the copper film **MT** formed on the wafer **W** via the electrolytic solution **EL** or by direct contact. Further, the polishing tool **11**, used as the cathode, carries current to the copper film **MT** formed on the wafer **W** via the electrolytic solution **EL** or by direct contact. Note that, as shown in FIG. **11**, there is a gap δ_b between the copper film **MT** and the scrub member **24**. Further, as shown in FIG. **12**, there is a gap δ_w between the copper film **MT** and the polishing surface **11a** of the polishing tool **11**.

As shown in FIG. **11**, the insulation plate **22** is interposed between the polishing tool **11** and the scrub member **24** (electrode plate **23**), but the resistance **RO** of the insulation plate **22** is very large, accordingly, the current i_0 flowing from the scrub member **24** via the insulation plate **22** to the polishing tool **11** is substantially zero, namely no current flows to the polishing tool **11** from the scrub member **24** via the insulation plate **22**.

For this reason, the current flowing from the scrub member **24** to the polishing tool **11** is branched into a current i_1 which directly flows through a resistance **R1** in the electrolytic solution **EL** to the polishing tool **11** and a current i_2 which flows from an interior of the electrolytic solution **EL** through the copper film formed on the surface of the wafer **W** to the electrolytic solution **EL** again and to the polishing tool **11**.

When the current i_2 flows in the surface of the copper film **MT**, the copper comprising the copper film **MT** is oxidized by anodic oxidation by the electrolytic action of the electrolytic solution **EL** and is chelated by a chelating agent in the electrolytic solution **EL**.

Here, the resistance **R1** in the electrolytic solution **EL** becomes extremely large in proportion to a distance **d** between the scrub member **24** as the anode and the polishing tool **11** as the cathode. For this reason, by making the inter-electrode distance **d** sufficiently larger than the gap δ_b and the gap δ_w , the current i_1 which directly flows through the resistance **R1** in the electrolytic solution **EL** to the polishing tool **11** becomes very small, the current i_2 becomes large, and almost all of the electrolytic current passes through the surface of the copper film **MT**. For this reason, chelation of the copper comprising the copper film **MT** due to the anodic oxidation can be efficiently carried out.

Further, the magnitude of the current i_2 changes according to the size of the gap δ_b and the gap δ_w , therefore, as mentioned above, by adjusting the size of the gap δ_b and the gap δ_w , by controlling the position of the polishing tool **11** in the Z-axial direction by the controller **55**, the current i_2 can be made constant. The size of the gap δ_w can be adjusted by controlling the Z-axis servo motor **31** by using the current value signal **62s** as a feedback signal so that the electrolytic current obtained from the current value signal **62s**, that is, the current i_2 , becomes constant.

Further, the positioning precision of the polishing apparatus in the Z-axial direction is a sufficiently high resolution of 0.1 μm . In addition, the main shaft **13a** is inclined with

respect to the main surface of the wafer **W** at a fine angle, so the effective contact area is always maintained constant, therefore if the value of the electrolytic current is controlled constant, the current density can be made always constant and also the amount of chelation of the copper film due to the anodic oxidation can be made always constant.

As described above, the polishing apparatus having the above configuration is provided with an electrolytic polishing function for forming a chelating film by anodic oxidation and removing the same on the surface of the copper film **MT** formed on the wafer **W** by the electrolytic action by the electrolytic solution **EL**.

Further, the polishing apparatus having the above configuration is provided with a chemical mechanical polishing function of the usual CMP apparatus by the polishing tool **11** and the slurry **SL** in addition to this electrolytic polishing function, so the wafer **W** can also be polished by the combined action of the electrolytic polishing function and chemical mechanical polishing (hereinafter referred to as electrolytic composite polishing).

Further, the polishing apparatus having the above configuration is also able to perform the polishing by the combined action of the mechanical polishing of the polishing surface **11a** of the polishing tool **11** and the electrolytic polishing function without the use of the slurry **SL**.

According to the polishing apparatus according to the present embodiment, because the copper film can be polished by the combined action of the electrolytic polishing and the chemical mechanical polishing, the copper film can be removed with a much higher efficiency in comparison with a polishing apparatus using only chemical mechanical polishing or mechanical polishing. For the copper film, a high polishing rate can be obtained, therefore it becomes possible to keep a low polishing pressure **F** of the polishing tool **11** on the wafer **W** in comparison with a polishing apparatus using only chemical mechanical polishing or mechanical polishing and the occurrence of dishing and erosion can be suppressed.

Further, in using a slurry in the chemical mechanical polishing of the related art, if a slurry containing alumina particles or the like is used, after the polishing, the alumina particles may remain on the copper surface without wear or may even be buried in the surface. By the polishing apparatus according to the present embodiment, however, since the chelate film existing on the surface has a very low mechanical strength, it can be removed effectively even by only mechanical polishing using an electrolytic solution including a chelating agent not containing a polishing abrasive, so particles and slurry can be prevented from remaining on the wafer surface.

Further, the positioning precision of the polishing apparatus in the Z-axial direction is a sufficiently high resolution of 0.1 μm , in addition, the main shaft **13a** is inclined with respect to the main surface of the wafer **W** at a fine angle, so the effective contact area is always maintained constant, therefore if the value of the electrolytic current is controlled constant, the current density can be made always constant and also the amount of chelation of the copper film due to the anodic oxidation can be made always constant.

In the above embodiment, the absolute value of the amount of polishing of the copper film can be controlled by the cumulative amount of the electrolytic current and the time by which the polishing tool **11** passes over the wafer **W**.

Modification 1

FIG. **13** is a schematic view of a first modification of a polishing apparatus according to the present invention.

In the polishing apparatus according to the embodiment mentioned above, the current was conducted to the surface of the wafer W by the conductive plate 23 provided with the conductive polishing tool and the scrub member 24.

As shown in FIG. 13, it is also possible to give the wheel-like polishing tool 311 conductivity in the same way as the case of the aforethe polishing apparatus and to give conductivity to a wafer table 342 for chucking and rotating the wafer W. Power is supplied to the polishing tool 311 by a configuration similar to that of the embodiments.

In this case, in supplying current to the wafer table 342, electrolytic current can be supplied by providing a rotary joint 316 below the wafer table 342 and constantly maintaining the flow of current to the wafer table 342 rotating by the rotary joint 316.

Modification 2

FIG. 14 is a schematic view of a second modification of a polishing apparatus according to the present invention.

A wafer table 442 for chucking and rotating the wafer W holds the wafer W by a retainer ring 410 provided on the periphery of the wafer W.

Conductivity is imparted to a polishing tool 411, conductivity is imparted to the retainer ring 410, and power is supplied to the polishing tool 411 by a configuration similar to that of the embodiments mentioned above.

Further, the retainer ring 410 covers up to the barrier layer portion formed on the wafer W and supplies current. Further, the retainer ring 410 is supplied with power through a rotary joint 416 provided below the wafer table 442.

Note that by making the amount of inclination of the polishing tool 411 larger so that a gap more than the thickness of the retainer ring 410 can be maintained at the edge portion even if the polishing tool 411 contacts the wafer W, interference between the polishing tool 411 and the retainer ring 410 can be prevented.

Modification 3

FIG. 15 is a schematic view of a third modification of a polishing apparatus according to the present invention.

The polishing apparatus shown in FIG. 15 is obtained by adding the electrolytic polishing function of the present invention to the CMP apparatus of the related art. It flattens the surface of the wafer W by bringing the entire surface of the wafer W chucked by a wafer chuck 207 into contact with the polishing surface of the polishing tool comprised of a plate 201 to which a polishing pad (polishing fabric) 202 is adhered while rotating the wafer W.

Anode electrodes 204 and cathode electrodes 203 are alternately radially arranged on the polishing pad 202. Further, the anode electrodes 204 and the cathode electrodes 203 are electrically insulated by an insulator 206, and the anode electrodes 204 and the cathode electrodes 203 are supplied with the current from the plate 201 side. The polishing pad 202 is constituted by these anode electrodes 204, cathode electrodes 203, and insulator 206.

The wafer chuck 207 is formed by the insulation material.

This polishing apparatus is provided with a feeder 208 for feeding the electrolytic solution EL and the slurry SL to the surface of the polishing pad 202, whereby electrolytic composite polishing combining electrolytic polishing and chemical mechanical polishing becomes possible.

Here, FIG. 16 is a view for explaining the electrolytic composite polishing operation (polishing method) by the polishing apparatus having the above configuration. Note that, it is assumed that for example a copper film 210 is formed on the surface of the wafer W.

As shown in FIG. 16, DC voltage is applied between the anode electrodes 204 and the cathode electrodes 203 in the

state where the electrolytic solution EL and the slurry SL are interposed between the copper film 210 formed on the surface of the wafer W and the polishing surface of the polishing pad 202, during the electrolytic composite polishing. The current i passes through the electrolytic solution EL from the anode electrode 204, is transmitted in the copper film 210, and passes through the electrolytic solution EL again to flow to the cathode electrode 203.

At this time, near the interior of the circle G shown in FIG. 16, a chelating film is formed on the surface of the copper film 210 due to anodic oxidation. This chelating film is removed by the mechanical removal action due to the polishing pad 202 and the slurry SL, and therefore the copper film is flattened.

By employing such a configuration, effects similar to those by the polishing apparatus according to the embodiments described above are exhibited.

Note that the arrangement of the anode electrodes and the cathode electrodes provided on the polishing pad is not limited to the configuration of FIG. 15. For example, as shown in FIG. 17, it is also possible to employ a polishing pad 221 in which a plurality of linear anode electrodes 222 are vertically and laterally aligned at equal intervals, a cathode electrode 223 is arranged in each rectangular region surrounded by the anode electrodes 222, and the anode electrodes 222 and the cathode electrodes 223 are electrically insulated by an insulator 224.

The polishing apparatus according to the present invention is not limited to the above embodiments. Numerous modifications could be made thereto without departing from the basic concept and scope of the invention in, for example, the materials comprising the apparatus, methods for supplying a current to a wafer, and so on.

Further, for example, as shown in FIG. 18, it is also possible to employ a polishing pad 241 in which annular anode electrodes 242 having radii different from each other are arranged in concentric circles, cathode electrodes 243 are arranged in the annular regions formed between the anode electrodes 242, and the anode electrodes 242 and the cathode electrodes 243 are electrically insulated by an insulator 244.

Second Embodiment

FIG. 19 is a schematic view of the configuration of a polishing apparatus according to a second embodiment of the present invention. The polishing apparatus according to the present embodiment comprises a tank 501 filled with a predetermined amount of electrolytic solution EL, a wafer holding means 530 and an electrode plate 510 arranged in the electrolytic solution EL in the tank, a jet pump 520 (flowing means) for sucking the electrolytic solution EL in the tank using a tube 522 and ejecting the same as a jet using a tube 521, a power supply 561 (electrolytic current supplying means) for applying a voltage using the electrode plate 510 as a cathode and a wafer as an anode, an ammeter 562, a controller 555, and a control panel 556.

The holding means 530 comprises a first holding member 531 and a second holding member 532 having conductivity and for holding a wafer and a Z-axis positioning mechanism fixed to a not illustrated column and for fixing the first holding member and the second member to specific positions. The second holding member positioned below the wafer has a circular aperture at the portion 532a.

The electrode plate 510 is arranged parallel with the wafer in the electrolytic solution EL and is made of for example oxygen-free copper or the like.

The electrolytic solution EL for example contains a chelating agent for chelating copper. Other additives may also be included. As the chelating agent, use is made of quinaldine acid, glycin, citric acid, oxalic acid, or propionic acid. The additives may include copper sulfate for reducing the voltage applied between the wafer and the electrode plate **510**.

The electrolytic power supply **561** (electrolytic current supplying means) is not a constant voltage power supply for continuously outputting a constant voltage. It is preferable to use a power supply outputting a voltage pulse at a constant period. For example, the voltages applied by the electrolytic power supply **561** are DC pulsed voltages with a high voltage and low voltage repeated every five seconds (for example, voltage 30 to 40V, current 2.2A, and depending on the voltage tolerance of a semiconductor element, may also be set for example 10 to 20V).

The above DC pulsed power supply is preferably capable of selecting a voltage and pulse width able to most effectively remove a copper film by adjusting a distance d between the wafer and the electrode plate **510** or others.

If the distance between the electrode plate **510** and the wafer is too small, the flushing action of the electrolytic solution between the electrode plate **510** and the wafer does not function sufficiently. Preferably, the distance d is set larger than a specific value according to the setting of the above voltage.

The electrolytic power supply **561** is provided with an ammeter **562** as a current detecting means of the present invention. This ammeter **562** is provided to monitor the electrolytic current flowing to the electrolytic power supply **561** and outputs the monitored current value signal **562s** to the controller **555**.

Further, the controller **555** receives as input a current value signal **562s** from the ammeter **562** of the electrolytic power supply **561**. The controller **555** is able to control the operation of the polishing apparatus based on the current value signal **562s**. Specifically, it controls the operation of the polishing apparatus so as to stop the polishing based on the current value specified by the current value signal **562s**.

A control panel **556** connected to the controller **555** is used for inputting a variety of data by an operator or displaying the monitored current value signal **562s**.

According to the polishing apparatus configuration described above, as the polishing apparatus according to the first embodiment, for example, in a case where an uneven copper film is formed on the surface of a wafer, by applying a voltage using the wafer as an anode, the surface of the copper film on the wafer is oxidized by the anodic oxidation. The oxidized copper film is chelated by the chelating agent in the electrolytic solution EL. Because the mechanical strength of the chelate film is very low, the projecting portions of the chelate film are removed by the flushing action of the electrolytic solution from the tube **521** of the jet pump **520**, whereby the copper film is flattened.

Further, by monitoring the electrolytic current, the polishing process can be controlled, so it becomes possible to correctly grasp the state of progress of the polishing process.

According to the polishing apparatus according to the present embodiment, since the copper film can be flattened by removing the chelate film of a very low mechanical strength, the copper film can be removed with a much higher efficiency in comparison with a polishing apparatus using only chemical mechanical polishing or mechanical polishing.

Since a strong pushing force as in a polishing apparatus is not necessary, the damage to the interlayer insulation film

below the copper film can be suppressed very small and occurrence of dishing, erosion, etc. can be suppressed. Because there is no high pressure applied to the insulation film below the copper film, as the insulation film, use may be made of a low dielectric constant material having a mechanical strength lower than silicon dioxide using TEOS as a stock material.

Further, as a polishing apparatus, because the hardware configuration is simple, reduction of its size can be easily realized, maintenance is easy, and the operation rate can be improved.

Further, in the chemical mechanical polishing of the related art, when using a slurry containing alumina particles etc., the alumina particles may remain on the copper film surface without wear after polishing, or they may be buried in the surface of the copper. In the polishing method of the present invention, however, these problems do not happen.

The present invention is not limited to the above embodiments. Numerous modifications could be made thereto without departing from the basic concept and scope of the invention in for example the configuration of the jet pump, type of the electrode plate, configuration of the apparatus holding a wafer in the tank, and so on.

Third Embodiment

FIG. **20** is a schematic view of the configuration of a polishing apparatus according to a third embodiment of the present invention. The polishing apparatus according to the present embodiment comprises a vibration applying means including a pulse generator **640**, an amplifier **641**, and an oscillator **643**, a tank **601** filled with a predetermined amount of electrolytic solution EL, a wafer holding means **630** and an electrode plate **610** arranged in the electrolytic solution EL in the tank, a power supply **661** (electrolytic current supplying means) for applying a voltage using the electrode plate **610** as a cathode and a wafer as an anode, an ammeter **662**, a controller **655**, and a control panel **656**.

The holding means **630** comprises a first holding member **631** for holding the electrode plate to be parallel with the wafer W, a second holding member **632** and a third holding member **633** for pressing and fixing the wafer between them, and a fourth holding member **634** with one end attached to the second holding member **632** and the other end to the oscillator **643**.

The second holding member **632** is made of a conductive material and functions to conduct a current through the wafer serving as an anode. Further, the second holding member **632** has an aperture portion **632a** for exposing the surface of the wafer to the electrode plate **610**.

The electrolytic solution EL for example contains a chelating agent for chelating copper. Other additives may also be included. As the chelating agent, use is made of quinaldine acid, glycin, citric acid, oxalic acid, or propionic acid. The additives may include copper sulfate for reducing the voltage applied between the wafer and the electrode plate **610**.

The electrode plate **610** is arranged parallel with the wafer in the electrolytic solution EL and is made of for example oxygen-free copper or the like.

The electrolytic power supply **661** (electrolytic current supplying means) is not a constant voltage power supply for continuously outputting a constant voltage. It is preferable to use a power supply outputting a voltage pulse at a constant period. For example, the voltages applied by the electrolytic power supply **661** are DC pulsed voltages with a high voltage and low voltage repeated every five seconds (for

example, voltage 30 to 40V, current 2.2A, and depending on the voltage tolerance of a semiconductor element, may also be set for example 10 to 20V).

The above DC pulsed power supply is preferably capable of selecting a voltage and pulse width able to most effectively remove a copper film by adjusting a distance *d* between the wafer and the electrode plate **610** etc.

If the distance between the electrode plate **610** and the wafer is too small, the flowing action of the electrolytic solution between the electrode plate **610** and the wafer does not function sufficiently. Preferably, the distance *d* is set larger than a specific value according to the setting of the above voltage.

The electrolytic power supply **661** is provided with an ammeter **662** as a current detecting means of the present invention. This ammeter **662** is provided to monitor the electrolytic current flowing to the electrolytic power supply **661** and outputs the monitored current value signal **662s** to the controller **655**.

Further, the controller **655** receives as input a current value signal **662s** from the ammeter **662** of the electrolytic power supply **661**. The controller **655** is able to control the operation of the polishing apparatus based on the current value signal **662s**. Specifically, it controls the operation of the polishing apparatus so as to stop the polishing based on the current value specified by the current value signal **662s**.

A control panel **656** connected to the controller **655** is used for inputting a variety of data by an operator or displaying the monitored current value signal **662s**.

According to the polishing apparatus configuration described above, as the polishing apparatus according to the first embodiment, for example, in a case where an uneven copper film is formed on the surface of a wafer *W*, by applying a voltage using the wafer as an anode, the surface of the copper film on the wafer is oxidized by the anodic oxidation. The oxidized copper film is chelated by a chelating agent in the electrolytic solution *EL*. Because the mechanical strength of the chelate film is very low, the projecting portions of the chelate film are removed by vibration of the wafer applied by the oscillator **643**, whereby the copper film is flattened.

Further, by monitoring the electrolytic current, the polishing process can be controlled, so it becomes possible to correctly grasp the state of progress of the polishing process.

According to the polishing apparatus according to the present embodiment, since the copper film can be flattened by removing the chelate film of a very low mechanical strength, the copper film can be removed with a much higher efficiency in comparison with a polishing apparatus using only chemical mechanical polishing or mechanical polishing.

Since a strong pressing force as used in a polishing apparatus is not necessary, the damage to the interlayer insulation film below the copper film can be suppressed very small, and occurrence of dishing, erosion, etc. can be suppressed. Because there is no high pressure applied to the insulation film below the copper film, as the insulation film, use may be made of a low dielectric constant material having a mechanical strength lower than silicon dioxide using TEOS as a stock material.

Further, as a polishing apparatus, because the hardware configuration is simple, reduction of its size can be easily realized, maintenance is easy, and the operation rate can be improved.

Further, in the chemical mechanical polishing of the related art, when using a slurry containing alumina particles etc., the alumina particles may remain on the copper film

surface without wear after polishing or may be buried in the surface of the copper. In the polishing method of the present invention, however, these problems do not happen.

The present invention is not limited to the above embodiments. Numerous modifications could be made thereto without departing from the basic concept and scope of the invention in for example the configurations of the oscillator and the amplifier, type of the electrode plate, configuration of the apparatus holding a wafer in the tank, and so on.

Fourth Embodiment

FIG. **21** is a view of the configuration of the principal portion of a polishing apparatus according to the present invention.

The basic configuration is the same as the first embodiment, but in the present embodiment, a polishing tool is not used. Instead, a metal film on a wafer is removed by a wiping member **24a**.

Accordingly, for simplicity, only parts different from the first embodiment are explained.

The wiping member **24a**, for example, is made of polyvinyl acetal (PVA), urethane foam, Teflon foam, Teflon nonwoven fabric, or the like. As their electric characteristics, they need to be insulators that do not conduct electricity or ions. For this, they are formed like fibers. Accordingly, an electrolytic solution can seep through the air holes in the fiber-like wiping member and fill the space between an electrode **22** and a wafer *W*.

The wiping member **24a** requires certain strength for it and the surface of the wafer *W* to be pressed to remove a metal film on the surface of the wafer.

For example, along with an elastic strength for tolerating 20 to 100 g/cm² pressure for wiping off only projecting portions of a metal film on the surface of a wafer *W*, a soft strength not causing scratches is required.

For example, an elastoplastic material can be used for the wiping member **24**.

Further, the electrode **23**, for example, is preferably provided with an air hole for releasing the gas produced on the polished surface due to an electrolytic action of the metal film on the surface of the wafer *W*. The air hole is provided also for preventing disadvantages resulting from the non-uniformity of the electrolytic action between the electrode **23** and the wafer *W* caused by the gas.

Further, the electrode **23** may be provided to be able to be driven to rotate. As a result, the gas produced on the polished surface due to electrolytic action can be released from between the wafer *W* and the electrode **23** by the rotation of the electrode **23**.

Further, the electrode **23** may be divided into several regions, whereby the electrolytic action to the polished surface can be selectively carried out in individual regions.

The electrolytic power supply **61**, as the first embodiment, applies a predetermined pulsed voltage between the previously described rotary joint **16** and a conductive brush **710** contacting the wafer.

Here, in the present embodiment, the voltage is applied in a reverse direction, therefore, the conductive brush **710** and electrode **23** become the anode and cathode, respectively. In addition to the configuration of applying voltage by contacting the metal film on the surface of a wafer *W* using the conductive brush **710** as shown here, a configuration may also be employed which is provided with an electrode capable of being brought into proximity with the metal film on the surface of the wafer *W* for applying a voltage.

31

The conductive brush 710 conducts a current to the wafer from the electrolytic power supply 61 contacting the surface of the wafer. Therefore, the current supplied from the electrolytic power supply 61 flows from the conductive brush 710 to the metal film on the surface of the wafer W and to the electrode 22 through the electrolytic solution.

The operation of the above polishing apparatus is explained below.

First, the wafer W is chucked on the wafer table 42, and the wafer table 42 is driven to rotate the wafer W at a predetermined speed.

The wafer table 42 is moved in the X-axial direction, the wiping member 24a is positioned at a predetermined position above the wafer W, and the wiping member 24a is rotated at a predetermined speed. For example, the wiping member 24a rotates at 100 rpm.

From this state, when the slurry SL and the electrolytic solution EL are fed to the feed nozzle 20a in the conductive shaft 20 from the slurry feeder 71 and the electrolytic solution feeder 81, the slurry SL and the electrolyte EL are fed from the entire surface of the wiping member 24a.

Then, the electrolytic power supply 61 is activated, a positive voltage is applied to the metal film on the surface of the wafer through the conductive brush 27, and a negative voltage is applied to the electrode 23 through the rotary joint 16.

As a result, a positive voltage is applied directly to the metal film on the surface of the wafer through the conductive brush 27, and a current is conducted to the electrode 22 through the electrolytic solution.

Therefore, a current can be supplied through the electrolytic solution using the metal film below the wiping member 24a as the anode. The metal film is oxidized by the anodic oxidation caused by an electrolytic action of the electrolytic solution and is chelated by a chelating agent in the electrolytic solution.

In the above state, high pressure air is fed to the cylinder device 15 to move the piston rod 15b downward, and the bottom surface of the wiping member 24a is brought into contact with the surface of the wafer W.

The wafer table 42 is moved in the X-axial direction with a predetermined speed pattern from this state, whereby the entire surface of the wafer W is uniformly wiped.

As shown above, a polishing apparatus employing the above configuration is able to produce a chelating film described above by the anodic oxidation on the surface of a metal film formed on a wafer W and remove it.

According to the polishing apparatus of the present embodiment, effects similar to the one according to the first embodiment are exhibited.

Further, in the polishing apparatus according to the present embodiment, because a polishing tool is not used and the step difference of a metal film on the surface of a wafer can be reduced by only wiping using the wiping member 24a, the pressure against the wafer can be further reduced lower than in the polishing apparatus according to the first embodiment.

In the present embodiment, rotation of the wiping member was shown an example of the wiping method, but the wiping member can also be moved relative to the wafer W. For example, a wiping member can be moved by providing a horizontal moving means. In the case of wiping by horizontal movement, it is preferable to set the speed of the horizontal movement below about 15 m/min in order to prevent the electrolytic solution from spraying out.

32

Preferably, the temperature of the electrolytic solution is adjusted below 80 degree or so in order to accelerate the anodic oxidation.

Further, the electrolytic solution fed to the surface of the polishing object can be held by surface tension.

As described previously, there is no limit to the polishing object.

Next, further embodiments of the method of production and method of polishing of a semiconductor device of the present invention and a polishing apparatus using the same will be explained with reference to the drawings.

Fifth Embodiment

FIG. 22A and FIG. 22B compare the amount of copper film removed per unit time when removing a copper film on the surface of a wafer by chelation by anodic oxidation employing the polishing apparatus according to the third embodiment of the present invention and the amount of copper film removed per unit time when removing a copper film on the surface of a wafer by oxidation with hydrogen peroxide (H_2O_2) of a predetermined concentration added to the electrolytic solution EL as an oxidant of the copper film on the surface of a wafer, without applying a voltage on the wafer W, employing the polishing apparatus according to the third embodiment of the present invention.

FIG. 22A shows removal rates when removing copper by adding an oxidant without applying a voltage to oxidize the copper and then chelating it. The amount of copper film removed per unit time (removal rate) was measured using a quinaldine acid solution as the electrolytic solution at concentrations of hydrogen peroxide (H_2O_2) of 0%, 4.5%, 8%, 10.7%, respectively. Note that the volume of the electrolytic solution was 150 ml.

Further, FIG. 22B shows the removal rate when copper was removed using the polishing-apparatus according to the third embodiment of the present invention. The amount of copper film removed per unit time (removal rate) was measured when using 150 ml quinaldine acid solution not added with hydrogen peroxide (H_2O_2) as the electrolytic solution EL and when a voltage was applied so that a current of 2.2A flows to the electrode plate 610 and the wafer through the electrolytic solution EL.

When using the hydrogen peroxide for an oxidant, aqueous copper ions ($[Cu(OH)_4]^{2-}$) are formed. The aqueous copper ions are chelated by the chelating agent in the electrolytic solution EL. For example, when the chelating agent is a quinaldine acid, a chelate film of the chemical formula (6) is formed. When glycine is used, a chelate film of the chemical formula (7) is formed.

The other experimental conditions include using an eight-inch wafer, a 25 nm thick Ta as the barrier metal, a 1200 nm-thick TEOS (tetraethyl orthosilicate) film for the inter-layer insulation film, and a 1600 nm thick copper film.

In FIG. 22, it is clear that the amount of copper film removed per unit time increased because the amount of the chelate film produced by copper film oxidation increases with an increased amount of the hydrogen peroxide serving as an oxidant, but when using the polishing method by the polishing apparatus according to the third embodiment of the present invention, without adding the hydrogen peroxide and by only the anodic oxidation caused by current conducting to produce a chelate film, it is shown the removal rate is raised greatly in comparison with that caused by an oxidant.

Sixth Embodiment

FIG. 23 is a view of the measured thickness of a copper film after a chelate film is removed when a current of 2.2A is supplied for 30 seconds each time using a copper film for an anode to remove the chelate film.

The measurements; were made at 21 points on an eight-inch wafer with the wafer divided into 21 parts along a diameter direction. The first and the 21st points were 6 mm apart from the edge of the wafer, respectively.

In addition, a quinaldine acid solution was used for an electrolytic solution. The thickness of the copper film was 2000 nm. A 25 nm thick Ta was used for the barrier metal. Use was made of a wafer having a 1200 nm thick TEOS film used for the interlayer insulation film below the barrier metal.

In FIG. 23, numbers 0, 1, 2, 3, 4, 5 along the horizontal axis indicate the times of the 30-second conduction of a 2.2A current. Therefore, 0 means no current is conducted, 1 means conduction of a 2.2A current for 30 seconds, 2 for total 60 seconds, 3 for a total 9.0 seconds, 4 for a total 120 seconds, and 5 for a total 150 seconds.

The vertical axis indicates the thickness (nm) of the residual copper on the surface of the wafer after the copper removing process by current conduction.

The measurements were repeated several times under the same conditions.

It is shown from the results that each time a current is conducted for a specific time period, the thickness of the residual copper after the copper removing process decreases corresponding to the time period of current conduction. The average removal rate was 202.68 nm per minute.

Seventh Embodiment

FIG. 24 shows the results of similar measurements as those in FIG. 23 made at 21 points on an eight-inch wafer with the wafer divided into 21 parts along a diameter direction.

The current and the conduction time are the same as the sixth embodiment. Measurements were made of the thickness of the residual copper after the process of removing the copper film in a case where 30 second conduction of a 2.2A current was repeated several times.

Other conditions such as the wafer in use, the type of the electrolytic solution, etc. are the same as the second embodiment.

In FIG. 24, the numbers 1 to 21 along the horizontal axis represent the aforethe positions on the wafer, while the vertical axis represents the thickness (nm) of the residual copper after the removal. Specifically, A, B, C, D, E, F represent the thickness (nm) of the residual copper after the removal after conduction of a 2.2A current for a total of 0 second, 30 seconds, 60 seconds, 90 seconds, 120 seconds, and 150 seconds respectively at each and every point described above.

According to the present embodiment, the thickness of the copper film at each and every point decreases approximately linearly depending on the product of the current and the time. Note that the smaller thicknesses of the copper film at the first and the 21st point are due to the plating characteristics during the preceding step for forming the copper film and are irrelevant to the polishing method of the present invention.

Summarizing the effects of the present invention, according to the method for producing a semiconductor device using the polishing method of the present invention, since

the copper film is polished by the composite actions of mechanical polishing and electrolytic polishing, in comparison with the case of the flattening of the copper film by mechanical polishing, very highly efficient selective removal and flattening of the projecting portions of the copper film become possible.

Further, according to the method for producing a semiconductor device using the polishing method of the present invention, since a sufficient polishing rate is obtained even with a relatively low polishing pressure, the occurrence of scratches, dishing, or erosion in the polished metal film can be suppressed. In addition, since damage to an interlayer insulation film below a copper film can be suppressed, even in the case where an organic low dielectric constant film or porous low dielectric constant insulation film having a relatively low mechanical strength is used as the interlayer insulation film in order to reduce the dielectric constant from the viewpoint of lowering the power consumption and increasing the speed of the semiconductor device, the invention can be easily applied.

Further, according to the method for producing a semiconductor device using the polishing method of the present invention, by monitoring the electrolytic current, the polishing process can be controlled, so it becomes possible to correctly grasp the state of progress of the polishing process.

According to the polishing apparatus of the present invention, since the metal film is polished by the composite actions of mechanical polishing and electrolytic polishing, in comparison with the case of the flattening of the metal film by mechanical polishing, very highly efficient selective removal and flattening of the projecting portions of the metal film become possible.

Further, according to the polishing apparatus of the present invention, since a sufficient polishing rate is obtained even with a relatively low polishing pressure, the occurrence of scratches, dishing, or erosion in the polished metal film can be suppressed. In addition, since damage to an interlayer insulation film below a copper film can be suppressed, even in the case where an organic low dielectric constant film or porous low dielectric constant insulation film having a relatively low mechanical strength is used as the interlayer insulation film in order to reduce the dielectric constant from the viewpoint of lowering the power consumption and increasing the speed of the semiconductor device, the invention can be easily applied.

Further, according to the polishing apparatus of the present invention, by monitoring the electrolytic current, the polishing process can be controlled, so it becomes possible to correctly grasp the state of progress of the polishing process.

Further, according to the polishing apparatus of the present invention, because the configuration of the apparatus is simple, reduction of its size can be easily realized, maintenance is easy, and the operation rate can be improved.

While the invention has been described with reference to specific embodiments chosen for purpose of illustration, it should be apparent that numerous modifications could be made thereto by those skilled in the art without departing from the basic concept and scope of the invention.

What is claimed is:

1. A polishing apparatus for polishing an object having a metal film on the surface to be polished, comprising:
 - a holding means for holding the object having the surface to be polished;
 - a wiper for wiping the surface of the object;
 - an electrolytic solution feeding means for feeding an electrolytic solution on the surface of the object;

35

a facing electrode arranged at a position facing the surface of the object; and

a current supplying means for supplying a current between the surface of the object and the facing electrode,

wherein said electrolytic solution feeding means has a seepage member made of a material capable of allowing an electrolytic solution to seep out at the end thereof and feeds an electrolytic solution onto the surface of the object through the seepage member, and

further comprising a temperature adjusting means for adjusting the temperature of the electrolytic solution fed by said electrolytic solution feeding means.

2. A polishing apparatus as set forth in claim 1, wherein said metal film comprises an interconnection metal film.

3. A polishing apparatus as set forth in claim 2, wherein said metal film comprises at least one of copper, aluminum, tungsten, gold, and silver, or an alloy of them, or an oxide or nitride of any of them.

4. A polishing apparatus as set forth in claim 1, wherein said wiper is made of an elastic material.

5. A polishing apparatus as set forth in claim 1, wherein said wiper is provided with an air hole.

6. A polishing apparatus as set forth in claim 1, wherein said electrolytic solution feeding means feeds an electrolytic solution so that the electrolytic solution is contained on the surface of the polished object.

7. A polishing apparatus as set forth in claim 1, further comprising a tank formed so as to surround the periphery of said object and for containing the electrolytic solution fed by said electrolytic solution feeding means.

8. A polishing apparatus as set forth in claim 1, wherein said electrolytic solution feeding means feeds an electrolytic solution comprising an electrolyte and an additive.

9. A polishing apparatus as set forth in claim 8, wherein said additive having at least one of a brightener, a chelating agent, and copper ions.

10. A polishing apparatus as set forth in claim 8, wherein said electrolytic solution having a polishing abrasive.

11. A polishing apparatus as set forth in claim 1, wherein said facing electrode comprises a metal material at least as precious as the metal film on the surface of the object.

12. A polishing apparatus as set forth in claim 1, wherein said facing electrode comprises an air hole.

13. A polishing apparatus as set forth in claim 1, wherein said facing electrode can be driven to rotate.

14. A polishing apparatus as set forth in claim 1, wherein said facing electrode is divided into several regions.

15. A polishing apparatus as set forth in claim 1, further comprising a contact electrode for guiding a current from said current supplying means to a metal film on the surface of the object.

16. A polishing apparatus as set forth in claim 1, further comprising an electrode capable of being located selectively in proximity to the surface of said object and for guiding a current from said current supplying means to a metal film on the surface of the object.

17. A polishing apparatus as set forth in claim 1, wherein said current supplying means supplies a current by applying a periodical pulse-like voltage between the surface of said object and said facing electrode.

18. A polishing apparatus as set forth in claim 17, wherein said current supplying means supplies a current by applying a periodical pulse-like voltage having a rectangular, sinusoidal, sawtooth, or PAM waveform between the surface of said object and said facing electrode.

36

19. A polishing apparatus as set forth in claim 1, wherein said current supplying means is able to change a current flowing between the surface of said object and said facing electrode at least at the beginning and end of the polishing.

20. A polishing apparatus as set forth in claim 1, wherein said temperature adjusting means adjusts the temperature of the electrolytic solution to below 80° C.

21. A polishing apparatus for polishing an object having a metal film on the surface to be polished, comprising:

a holding means for holding the object having the surface to be polished;

a wiper for wiping the surface of the object;

a relative moving means for relatively moving the surface of the object and the wiper;

an electrolytic solution feeding means for feeding an electrolytic solution on the surface of the object;

a facing electrode arranged at a position facing the surface of the object; and

a current supplying means for supplying a current between the surface of the object and the facing electrode,

wherein said relative moving means presses said wiper against the surface of said polished object and horizontally moves the wiper on the surface of said polished object,

wherein said relative moving means horizontally moves said holding means in a surface parallel with the surface of said wiper,

wherein said electrolytic solution feeding means has a seepage member made of a material capable of allowing an electrolytic solution to seep out at the end thereof and feeds an electrolytic solution onto the surface of the polished object through the seepage member, and further comprising a temperature adjusting means for adjusting the temperature of the electrolytic solution fed by said electrolytic solution feeding means.

22. A polishing apparatus as set forth in claim 21, wherein said metal film is an interconnection metal film.

23. A polishing apparatus as set forth in claim 22, wherein said metal film comprises at least one of copper, aluminum, tungsten, gold, and silver, or an alloy of them, or an oxide or nitride of any of them.

24. A polishing apparatus as set forth in claim 21, wherein said relative moving means presses said wiper on the surface of polished object and rotates the wiper relative to a predetermined center axis of rotation.

25. A polishing apparatus as set forth in claim 21, wherein said relative moving means rotates said holding means relative to a predetermined center axis of rotation.

26. A polishing apparatus as set forth in claim 21, wherein said wiper is made of an elastic material.

27. A polishing apparatus as set forth in claim 21, wherein said wiper is provided with an air hole.

28. A polishing apparatus as set forth in claim 21, wherein said electrolytic solution feeding means feeds an electrolytic solution so that the electrolytic solution is contained on the surface of the object.

29. A polishing apparatus as set forth in claim 21, further comprising a tank formed so as to surround the periphery of said object and for containing the electrolytic solution fed by said electrolytic solution feeding means.

30. A polishing apparatus as set forth in claim 21, wherein said electrolytic solution feeding means feeds an electrolytic solution including an electrolyte and an additive.

31. A polishing apparatus as set forth in claim 30, wherein said additive having at least one of a brightener, a chelating agent, and copper ions.

37

32. A polishing apparatus as set forth in claim 30, wherein said electrolytic solution having a polishing abrasive.

33. A polishing apparatus as set forth in claim 21, wherein said facing electrode comprises a metal material at least as precious as the metal film on the surface on the object.

34. A polishing apparatus as set forth in claim 21, wherein said facing electrode comprises an air hole.

35. A polishing apparatus as set forth in claim 21, wherein said facing electrode can be driven to rotate.

36. A polishing apparatus as set forth in claim 21, wherein said facing electrode is divided into several regions.

37. A polishing apparatus as set forth in claim 21, further comprising a contact electrode for guiding a current from said current supplying means to a metal film on the surface of the object.

38. A polishing apparatus as set forth in claim 21, further comprising an electrode able to be brought into proximity with the surface of said object and for guiding a current from said current supplying means to a metal film on the surface of the object.

38

39. A polishing apparatus as set forth in claim 21, wherein said current supplying means supplies a current by applying a periodical pulse-like voltage between the surface of said object and said facing electrode.

40. A polishing apparatus as set forth in claim 39, wherein said current supplying means supplies a current by applying a periodical pulse-like voltage having a rectangular, sinusoidal, sawtooth, or PAM waveform between the surface of said object and said facing electrode.

41. A polishing apparatus as set forth in claim 21, wherein said current supplying means is able to change a current flowing between the surface of said object and said facing electrode at least at the beginning and end of polishing.

42. A polishing apparatus as set forth in claim 21, wherein said temperature adjusting means adjusts the temperature of the electrolytic solution to below 80° C.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 7,186,322 B2
APPLICATION NO. : 10/327860
DATED : March 6, 2007
INVENTOR(S) : Shuzo Sato et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Title page:

Under (*) Notice and item 45: -- This patent is subject to a terminal disclaimer -- should be included.

Column 35, Line 51:

“guiding a current form” should read -- guiding a current from --.

Column 37, Line 13:

“guiding a current form” should read -- guiding a current from --.

Signed and Sealed this

Thirty-first Day of July, 2007

A handwritten signature in black ink on a light gray dotted background. The signature reads "Jon W. Dudas" in a cursive style.

JON W. DUDAS

Director of the United States Patent and Trademark Office