




(86) **Date de dépôt PCT/PCT Filing Date:** 2011/03/24
(87) **Date publication PCT/PCT Publication Date:** 2011/09/29
(45) **Date de délivrance/Issue Date:** 2020/04/28
(85) **Entrée phase nationale/National Entry:** 2012/09/13
(86) **N° demande PCT/PCT Application No.:** IB 2011/000626
(87) **N° publication PCT/PCT Publication No.:** 2011/117719
(30) **Priorité/Priority:** 2010/03/24 (US61/317,002)

(51) **Cl.Int./Int.Cl.** **C08L 101/00** (2006.01),
C08J 3/12 (2006.01), **C08J 3/20** (2006.01),
C08J 3/24 (2006.01), **C08L 5/00** (2006.01),
A01N 25/26 (2006.01)
(72) **Inventeurs/Inventors:**
LI, FUGANG, CA;
PHAM, HUNG, CA;
ANDERSON, DARREN J., CA
(73) **Propriétaire/Owner:**
VIVE CROP PROTECTION INC., CA
(74) **Agent:** AIRD & MCBURNEY LP

(54) **Titre : METHODES DE FORMULATION DE COMPOSES ORGANIQUES NEUTRES AVEC DES NANOPARTICULES DE POLYMERES**

(54) **Title: METHODS TO FORMULATE NEUTRAL ORGANIC COMPOUNDS WITH POLYMER NANOPARTICLES**



(57) **Abrégé/Abstract:**

A composition including a collapsed, polymer nanoparticle and at least one organic, neutral compound associated with the nanoparticle, wherein the nanoparticle is less than 100 nm in diameter, and the polymer comprises a water-soluble polyelectrolyte, has a molecular weight of at least about 100,000 Dalton and is cross-linked. The organic, neutral compound is selected from the group consisting of dyes, pigments, colorants, oils, UV-light absorbing molecules, fragrances, flavoring molecules, preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, and combinations thereof.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
29 September 2011 (29.09.2011)(10) International Publication Number
WO 2011/117719 A1

(51) International Patent Classification:

C08L 101/00 (2006.01) *C08J 3/24* (2006.01)
C08J 3/12 (2006.01) *C08L 5/00* (2006.01)
C08J 3/20 (2006.01) *A01N 25/26* (2006.01)

(21) International Application Number:

PCT/IB2011/000626

(22) International Filing Date:

24 March 2011 (24.03.2011)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/317,002 24 March 2010 (24.03.2010) US

(71) Applicant (for all designated States except US): **VIVE NANO, INC.** [CA/CA]; 700 Bay Street, Suite 1100, Toronto, Ontario M5G 1Z6 (CA).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **LI, Fugang** [CA/CA]; 40 Grasslands Avenue, Richmond Hill, Ontario, L4B 4L1 (CA). **PHAM, Hung** [CA/CA]; 8 Freshmeadow Street, Brampton, Ontario L6P 2H4 (CA). **ANDERSON, Darren, J.** [CA/CA]; 781 King Street, W #302, Toronto, Ontario M5V 1N4 (CA).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD,

[Continued on next page]

(54) Title: METHODS TO FORMULATE NEUTRAL ORGANIC COMPOUNDS WITH POLYMER NANOPARTICLES




Figure 2

(57) Abstract: A composition including a collapsed, polymer nanoparticle and at least one organic, neutral compound associated with the nanoparticle, wherein the nanoparticle is less than 100 nm in diameter, and the polymer comprises a water-soluble polyelectrolyte, has a molecular weight of at least about 100,000 Dalton and is cross-linked. The organic, neutral compound is selected from the group consisting of dyes, pigments, colorants, oils, UV-light absorbing molecules, fragrances, flavoring molecules, preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, and combinations thereof.

WO 2011/117719 A1

ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI,
 NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD,
 SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR,
 TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
 SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
 GW, ML, MR, NE, SN, TD, TG).

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,

Published:

- *with international search report (Art. 21(3))*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))*

METHODS TO FORMULATE NEUTRAL ORGANIC COMPOUNDS WITH POLYMER NANOPARTICLES

CROSS REFERENCE TO RELATED APPLICATIONS

- 5 This application claims priority to United States Provisional Patent Application serial number 61/317,002 filed on March 24, 2010.

BACKGROUND OF THE INVENTION

- 10 Nanoparticles are nanometer-sized materials e.g., metals, semiconductors, polymers, organics, and the like, that can often possess unique characteristics because of their small size. Polymer nanoparticles of biologically-active and non-biologically-active active ingredients (AIs) are of particular interest because of the potential for reduced use of
15 formulants, improved availability, improved solubility/dispersibility, modified translocation, adhesion, or controlled release properties. Polymer nanoparticles with hollow interiors have found widespread use in many applications such as controlled release of drugs of pharmaceuticals, active ingredients (AIs) in agriculture, cosmetics, personal care, and foods. They are also found to protect biologically active species from degradation, and can be used remove pollutants from the environment.

20

SUMMARY OF THE INVENTION

- The present invention encompasses the discovery that various types of active ingredients can be associated with polymeric nanoparticles to improve the performance of the active ingredients. The present invention, among other things, provides several methods
25 for the production and use of improved active ingredients.

- In various aspects, the present invention provides compositions including a polymer nanoparticle and at least one active compound incorporated with the nanoparticle. In some embodiments, the nanoparticle is less than 100 nm in diameter. In some embodiments, the polymer includes a polyelectrolyte. In some embodiments, the active compound is an
30 organic compound.

In various aspects, the present invention provides compositions including a polymer nanoparticles, where the polymer nanoparticle is less than 100 nm in diameter. The polymer nanoparticle can have both relatively polar and relatively non-polar regions. The polar regions can be made up of ionizable or ionized chemical groups.

5 In some embodiments, the active compound is selected from the group consisting of an agricultural active compound like: acaricide, a fungicide, a bactericide, a herbicide, an antibiotic, an antimicrobial, a nemacide, a rodenticide, an entomopathogen, a pheromone, a chemosterilant, a virus, an attractant, a plant growth regulator, an insect growth regulator, a repellent, a plant nutrient, a phagostimulant, a germicide, and combinations thereof. In
10 some embodiments, the active ingredient is selected from the group consisting of azoxystrobin, emamectin and its salts, abamectin and its salts, thiamethoxam, glyphosate, 2,4-dichlorophenoxy)acetic acid, atrazine, picloram, imazethapyr, or thifensulfuron-methyl, and combinations thereof. In some embodiments, the active ingredient is selected from the group consisting of atrazine, neonicotinoids, photosynthesis inhibitors, amino acid synthesis
15 inhibitors, growth regulators, pyrethrins, avermectins, and strobilurins.

In some embodiments, the nanoparticles are less than 50 nm in size. In some embodiments, the nanoparticles are less than 20 nm in size. In some embodiments, the polymer includes multiple polymer molecules. In some embodiments, the polymer nanoparticle is crosslinked. In some embodiments, the crosslinking step is accomplished by
20 one of the following: electromagnetic radiation induced cross-linking, chemically induced cross-linking or thermally induced cross-linking.

In various embodiments, the present invention provides a dispersion including a polymer nanoparticle and at least one active compound incorporated with the nanoparticle, wherein the active ingredient is dispersed at a concentration higher than its solubility in the
25 absence of the polymer nanoparticle

In some embodiments, the polymer is selected from the group consisting of poly(acrylic acid), poly(methacrylic acid), poly(styrene sulfonate), chitosan, poly(dimethyldiallylammonium chloride), poly(allylamine hydrochloride), or copolymers or graft polymers thereof and combinations thereof.

30 In some embodiments, at least a portion of the active ingredient is in the interior of the polymer nanoparticle. In some embodiments, at least a portion of the active ingredient is on the surface of the polymer nanoparticle. In some embodiments, the active ingredient remains associated with the polymer nanoparticle after being exposed to a solvent

In various embodiments, the present invention provides for extended or sustained release after application. In some embodiments, the trigger for release is selected from the group consisting of pH change, temperature change, barometric pressure change, osmotic pressure change, exposure to water, exposure to a solvent, changes in shear forces, application of the formulation, exposure to a bacteria, exposure to an enzyme, exposure to electromagnetic radiation and exposure to free radicals. In some embodiments, the active ingredient is released via triggered release. In some embodiments, the polymer nanoparticle has a cavity. In some embodiments, the polymer nanoparticle has a network structure. In some embodiments, the active ingredient associated with the polymer nanoparticle has different mobility in soil than it has when not associated with the polymer nanoparticle. In some embodiments, polymer has hydrophilic and hydrophobic regions. In some embodiments, the polymer nanoparticles can be recovered in a dried form and redispersed in a suitable solvent.

In some embodiments, the active ingredient is azoxystrobin, emamectin and its salts, abermectin and its salts, thiamethoxam, glyphosate, 2,4-dichlorophenoxy)acetic acid, atrazine, picloram, imazethapyr, or thifensulfuron-methyl, and combinations thereof. In some embodiments, the active ingredient is atrazine, neonicotinoids, photosynthesis inhibitors, amino acid synthesis inhibitors, growth regulators, pyrethrins, avermectins, and strobilurins.

In various aspects, the present invention provides a method to make polymer nanoparticles, including the steps of dissolving a polyelectrolyte into an aqueous solution under solution conditions that render it charged, adding a species that is oppositely charged under these conditions to cause the polymer to collapse, and crosslinking the polymer. In some embodiments, the crosslinking step is accomplished by one of the following: electromagnetic radiation induced cross-linking, chemically induced cross-linking or thermally induced cross-linking.

In some embodiments, the oppositely charged species is an active ingredient.

In some embodiments, the oppositely charged species is removed from the polymer nanoparticle. In some embodiments, the oppositely charged species is removed from the polymer nanoparticle by pH adjustment, filtration, dialysis, or combinations thereof.

In some embodiments, the method further includes the step of associating an active ingredient with the polymer nanoparticle.

In some embodiments, the method includes the step of removing the solvent. In some embodiments, the solvent is removed by lyophilization, distillation, extraction, selective solvent removal, filtration, dialysis, or evaporation. In some embodiments, the method includes the step of redispersing the nanoparticles in a suitable solvent.

5 In some embodiments, the method includes an agricultural active compound selected from the group consisting of an acaricide, a fungicide, a bactericide, a herbicide, an antibiotic, an antimicrobial, a nemacide, a rodenticide, an entomopathogen, a pheromone, a chemosterilant, a virus, an attractant, a plant growth regulator, an insect growth regulator, a repellent, a plant nutrient, a phagostimulant, a germicide, and combinations thereof.

10 In some embodiments, the composition or method includes an active ingredient that may or may not be biologically active such as, but is not limited to, the group consisting of hydrophilic, hydrophobic, or neutral organic dyes or pigments, colorants, oils, UV light and non UV-light absorbing organic molecules, small organic molecules, fragrance and flavoring molecules, inorganic salts and complexes, neutral or charged organic complexes, solvents,
15 gases, preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, catalysts, and combinations thereof.

In some embodiments, the polymer nanoparticles are used to create a dispersion containing either a biologically active or biologically inactive active ingredient or a
20 combination thereof. The dispersion can take several forms such as aerosols, sols, emulsions and gels, where the active ingredients are made soluble or dispersible by the nanoparticle in a solvent or phase where the active ingredient would otherwise be insoluble or unable to be dispersed effectively.

In some embodiments, the method includes a nanoparticles are less than 50 nm in
25 size. In some embodiments, the method includes a nanoparticles are less than 20 nm in size. In some embodiments, the method includes multiple polymer molecules. In some embodiments, the method includes a polymer nanoparticle that is crosslinked

In some embodiments, the method includes a polymer that is selected from the group consisting of poly(acrylic acid), poly(methacrylic acid), poly(styrene sulfonate), chitosan, poly
30 (dimethyldiallylammonium chloride), poly (allylamine hydrochloride), or copolymers or graft polymers thereof and combinations thereof. In some embodiments, the method includes a portion of the active ingredient is on the surface of the polymer nanoparticle.

In some embodiments, the method includes an associating step which itself includes the steps of dissolving or dispersing the polymer nanoparticles in a suitable first solvent, swelling the polymer nanoparticles by adding a second solvent containing active ingredient, and removing the second solvent.

5 In some embodiments, the method includes an associating step which itself includes the steps of dissolving or dispersing the polymer nanoparticles and dissolving the active ingredient in a suitable first solvent, adding a second solvent, and removing the first solvent.

In some embodiments, the method includes an associating step which itself includes the steps of dissolving or dispersing the polymer nanoparticles and dissolving the active
10 ingredient in a suitable solvent, and removing the solvent.

In various aspects, the present invention provides a method to associate an active ingredient with a polymer nanoparticle, including the steps of dissolving or dispersing the polymer nanoparticles in a suitable first solvent, swelling the polymer nanoparticles by adding a second solvent containing active ingredient, and removing the second solvent.

15 In various aspects, the present invention provides a method to associate active ingredient with polymer nanoparticles including the steps of dissolving or dispersing the polymer nanoparticles and dissolving the active ingredient in a suitable first solvent, adding a second solvent and removing the first solvent.

In various aspects, the present invention provides a method to associate active
20 ingredient with polymer nanoparticles including the steps of dissolving or dispersing the polymer nanoparticles and dissolving the active ingredient in a suitable solvent and removing the solvent.

In some embodiments of the method, the first solvent is water. In some
embodiments of the method, the second solvent is not miscible in the first solvent. In some
25 embodiments of the method, the second solvent is partially miscible in the first solvent

In various aspects, the present invention provides, a method to make polymer nanoparticles including active ingredient, including the steps of dissolving a polyelectrolyte in a suitable solvent, associating an active ingredient with the polyelectrolyte, and collapsing the polyelectrolyte.

30 In some embodiments, the association of the active ingredient with the polyelectrolyte causes the collapse of the polyelectrolyte. In some embodiments, the collapse is caused by a change in solvent conditions, by a change in temperature, by a change in pH.

In some embodiments, the polymer nanoparticles including active ingredient are crosslinked. In some embodiments, the active ingredient is chemically modified.

In various aspects, the present invention provides a method of using a composition including a polymer nanoparticle and at least one active compound incorporated with the nanoparticle by applying the composition to a plant, a seed, soil, or substrate. In some
5 embodiments, the composition is sprayed as an aerosol on the crop or surface. In some
embodiments, the composition is part of a formulation with other ingredients in solution. In
some embodiments, the method of treatments is essentially free of added surfactants and
other dispersants other than the polymer nanoparticle.

10

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is an illustration of exemplary polymer nanoparticles comprising active ingredients. Active ingredients can be associated with the nanoparticle inside, or on the surface.

15

Figure 2 is an exemplary illustration of direct collapse of polyelectrolyte around the active ingredient. A: Polyelectrolyte in an extended configuration. B: Addition of active ingredient and collapse of the polyelectrolyte around the active ingredient. C: Crosslinking

Figure 3 illustrates formation of polymer nanoparticle from modified polyelectrolytes. A: Polyelectrolyte with hydrophobic groups in an extended configuration. B: collapse of modified polyelectrolytes C: Crosslinking
20

Figure 4 illustrates formation of polymer nanoparticles from inorganic metal ion. A: polyelectrolyte in an extended configuration. B: Collapse of polyelectrolyte with metal salt. C: Crosslinking the collapsed polyelectrolyte. D: Removal of metal ion. E. Polymer nanoparticle.

25

Figure 5 illustrates the formation of polymer nanoparticle from metal hydroxide nanoparticles. A: Polyelectrolyte in an extended configuration. B: Collapsing polyelectrolyte with metal hydroxide precursor ion. C. Crosslink collapsed polyelectrolyte. D: Formation of metal hydroxide. E: Removal of metal hydroxide. F: Polymer nanoparticle.

30

Figure 6 illustrates the formation of polymer nanoparticle from metal hydroxide nanoparticles. A: Polyelectrolyte in an extended configuration. B: Collapsing polyelectrolyte with metal oxide precursor ion. C: Crosslink collapsed polyelectrolyte. D: Formation of metal oxide. E: Removal of metal hydroxide. F: Polymer nanoparticle.

Figure 7 illustrates methods of active ingredients loading into hollow nanoparticles. A: Use appropriate solvent to swell nanocapsules in presence of AI. B: Use miscible solvent system to partition AI into nanocapsules. C: Use immiscible solvent to swell nanocapsules in presence of AI.

5 Figure 8: shows exemplary characterization of polymer nanoparticles formed using a diamino compound as a collapsing agent and crosslinker. TEM images of the PAA/1,8-diaminooctane mixture (a) before and (b) after refluxing for 24 hrs.

Figure 9: shows exemplary characterization of polymer nanoparticles formed using a diamino compound as a collapsing agent and crosslinker. TEM images of PAA/1,6-diaminohexane after refluxed in (a) the absence and presence of NaCl and (b) in the presence of added NaCl. The scale bar is 100 nm.

Figure 10 shows exemplary controlled release test apparatus and test results. A. Control release experimental setup. B. Control release characteristics of TMX.

15 Figure 11 shows exemplary soil mobility of Hostasol Yellow loaded polymer nanoparticles. A: UV-vis spectra of the eluent for Hostasol Yellow loaded hollow polymer nanoparticles. B: UV spectra of the eluent for Hostasol Yellow without the hollow polymer nanoparticles.

Figure 12 shows the emission spectra of pyrene in water (solid line) and pyrene in the presence of Na^+ -collapsed P(MAA-co-EA) nanoparticles (dotted lines).

20 Figure 13: Atomic force microscopy (A, B) and transmission electron microscopy (TEM) (C) images of polyelectrolyte particles (A) containing aluminum hydroxide and (B, C) after aluminum hydroxide has been removed.

DESCRIPTION OF VARIOUS EMBODIMENTS

25 In various aspects, the present invention describes methods of producing polymer particles and polymer gel particles with an average size ranging from 1 nm to 800 nm, using polyelectrolytes. These particles are generally spherical (e.g., elliptical, oblong, etc.,) in shape, swollen or not swollen, may be hollow in the center, or may contain cavities. The particles may include active ingredients.

30 Prior to further describing the present inventions, it may be helpful to provide a general discussion of the usage of terms herein.

As used herein, the term "active ingredients" refer to an active compound or a mixture of active compounds in pesticide formulations, or to an active pharmaceutical ingredient or a mixture of active pharmaceutical ingredients. It can also include substances with biological activity which are not typically considered to be active ingredients, such as

5 fragrances, flavor compounds, hormones, homo, oligo, or poly nucleic acids or peptides, and the like. It can also include substances with or without biological activity such as hydrophilic, hydrophobic, or neutral organic dyes or pigments, colorants, oils, UV light and non UV-light absorbing organic molecules, small organic molecules, fragrance and flavoring molecules, inorganic salts and complexes, neutral or charged organic complexes, solvents, gases,

10 preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, catalysts, and combinations thereof. In some embodiments the active ingredient is an organic compound. In some embodiments the active is an organic, neutral compound. In some embodiments the active ingredient is neutral at a pH between about 4 and about 10, or between about 5 and about 9,

15 or between about 6 and about 8. In some embodiments, active ingredient is neutral at a pH in the range of any of the value described above. In some embodiments the active ingredient is a non-ionic compound. In some embodiments the active ingredient is not a salt, or not a component of a salt.

Exemplary classes of active ingredient for the present invention include acaricides,

20 algicides, avicides, bactericides, fungicides, herbicides, insecticides, miticides, molluscicides, nematocides, rodenticides, virucides, algicides, bird repellents, mating disrupters, plant activators, antifeedants, insect attractants and repellants.

Active ingredients of herbicides can function as, amino acid synthesis inhibitors, cell membrane disrupters, lipid synthesis inhibitors, pigment inhibitors, seedling growth inhibitors,

25 growth regulators, photosynthesis inhibitors, .

Examples of active ingredients as amino acid synthesis inhibitors include, but are not limited to., imazethapyr (2-[4,5-dihydro-4-methyl-4-(1-methylethyl)-5-oxo-1*H*-imidazol-2-yl]-5-ethyl-3-pyridinecarboxylic acid), thifensulfuron (3-[[[(4-methoxy-6-methyl-1,3,5-triazin-2-yl)amino]carbonyl]amino]sulfonyl]-2-thiophenecarboxylic acid), thifensulfuron-methyl (methyl

30 3-[[[(4-methoxy-6-methyl-1,3,5-triazin-2-yl)amino]carbonyl]amino]sulfonyl]-2-thiophenecarboxylate), glyphosate (*N*-(phosphonomethyl)glycine).

Examples of active ingredients as cell membrane disrupters include, but are not limited to., diquat (6,7-dihydrodipyrido[1,2-*a*:2',1'-*c*]pyrazinediium), paraquat (1,1'-dimethyl-4,4'-bipyridinium).

Examples of active ingredients as lipid synthesis inhibitors include, but are not limited to,, clodinafop propargyl (2-propynyl (2*R*)-2-[4-[(5-chloro-3-fluoro-2-pyridinyl)oxy]phenoxy]propanoate), tralkoxydim (2-[1-(ethoxyimino)propyl]-3-hydroxy-5-(2,4,6-trimethylphenyl)-2-cyclohexen-1-one).

- 5 Examples of active ingredients as pigment inhibitors include, but are not limited to,, mesotrione (2-[4-(methylsulfonyl)-2-nitrobenzoyl]-1,3-cyclohexanedione), clomazone (2-[(2-chlorophenyl)methyl]-4,4-dimethyl-3-isoxazolidinone).

- Examples of active ingredients as seedling growth inhibitors include, but are not limited to,, metolachlor (2-chloro-*N*-(2-ethyl-6-methylphenyl)-*N*-(2-methoxy-1-methylethyl)acetamide), triflualin (2,6-dinitro-*N,N*-dipropyl-4-(trifluoromethyl)benzenamine),
10 diflufenzopyr (2-[1-[[[(3,5-difluorophenyl)amino]carbonyl]hydrazono]ethyl]-3-pyridinecarboxylic acid).

- Examples of active ingredients as growth regulators include, but are not limited to,, 2,4-D (2,4-dichlorophenoxy)acetic acid), dicamba (3,6-dichloro-2-methoxybenzoic acid),
15 MCPA ((4-chloro-2-methylphenoxy)acetic acid), picloram (4-amino-3,5,6-trichloro-2-pyridinecarboxylic acid), triclopyr ([[(3,5,6-trichloro-2-pyridinyl)oxy]acetic acid).

- Examples of active ingredients as photosynthesis inhibitors include, but are not limited to,, atrazine (6-chloro-*N*-ethyl-*N'*-(1-methylethyl)-1,3,5-triazine-2,4-diamine), metribuzin (4-amino-6-(1,1-dimethylethyl)-3-(methylthio)-1,2,4-triazin-5(4*H*)-one), bromacil
20 (5-bromo-6-methyl-3-(1-methylpropyl)-2,4(1*H*,3*H*)-pyrimidinedione), tebuthiuron (*N*-[5-(1,1-dimethylethyl)-1,3,4-thiadiazol-2-yl]-*N,N'*-dimethylurea), propanil (*N*-(3,4-dichlorophenyl)propanamide), bentazon (3-(1-methylethyl)-1*H*-2,1,3-benzothiadiazin-4(3*H*)-one 2,2-dioxide), bromoxynil (3,5-dibromo-4-hydroxybenzonitrile), pyridate (*O*-(6-chloro-3-phenyl-4-pyridazinyl) *S*-octyl carbonothioate).

- 25 Active ingredients of insecticides can function as, acetylcholinesterase inhibitors, GABA-gated chloride channel antagonists, sodium channel modulators, nicotinic acetylcholine receptor agonists, chloride channel activators, juvenile hormone mimics, non-specific (multi-site) inhibitors, selective homopteran feeding blockers, mite growth inhibitors, inhibitors of mitochondrial ATP synthase, uncouplers of oxidative phosphorylation via
30 disruption of the proton gradient, nicotinic acetylcholine receptor channel blockers, inhibitors of chitin biosynthesis (type 0 and 1), moulting disruptor, ecdysone receptor agonists, octopamine receptor agonists, mitochondrial complex I electron transport inhibitors, mitochondrial complex III electron transport inhibitors, mitochondrial complex IV electron

transport inhibitors, voltage-dependent sodium channel blockers, inhibitors of acetyl CoA carboxylase, ryanodine receptor modulators.

Examples of active ingredients as acetylcholinesterase inhibitors include, but are not limited to, the family of carbamates (e.g. carbofuran (2,3-dihydro-2,2-dimethyl-7-benzofuranyl methylcarbamate), carbosulfan (2,3-dihydro-2,2-dimethyl-7-benzofuranyl [(dibutylamino)thio]methylcarbamate)) and organophosphates chemicals (e.g. chlorpyrifos-methyl (O,O-dimethyl O-(3,5,6-trichloro-2-pyridinyl) phosphorothioate)).

Examples of active ingredients as GABA-gate chloride channel antagonists include, but are not limited to, chlordane (1,2,4,5,6,7,8,8-octachloro-2,3,3a,4,7,7a-hexahydro-4,7-methano-1H-indene), endosulfan (6,7,8,9,10,10-hexachloro-1,5,5a,6,9,9a-hexahydro-6,9-methano-2,4,3-benzodioxathiepin 3-oxide), ethiprole (5-amino-1-[2,6-dichloro-4-(trifluoromethyl)phenyl]-4-(ethylsulfinyl)-1H-pyrazole-3-carbonitrile), fipronil (5-amino-1-[2,6-dichloro-4-(trifluoromethyl)phenyl]-4-[(trifluoromethyl)sulfinyl]-1H-pyrazole-3-carbonitrile).

Examples of active ingredients as sodium channel modulators include, but not limited to, DDT (1,1'-(2,2,2-trichloroethylidene)bis[4-chlorobenzene]), methoxychlor (1,1'-(2,2,2-trichloroethylidene)bis[4-methoxybenzene]), pyrethrin compounds (e.g. bifenthrin ((2-methyl[1,1'-biphenyl]-3-yl)methyl (1R,3R)-rel-3-[(1Z)-2-chloro-3,3,3-trifluoro-1-propenyl]-2,2-dimethylcyclopropanecarboxylate), lambda-cyhalothrin ((R)-cyano(3-phenoxyphenyl)methyl (1S,3S)-rel-3-[(1Z)-2-chloro-3,3,3-trifluoro-1-propenyl]-2,2-dimethylcyclopropanecarboxylate), pyrethrins ((RS)-3-allyl-2-methyl-4-oxocyclopent-2-enyl (1R,3R)-2,2-dimethyl-3-(2-methylprop-1-enyl)cyclopropanecarboxylate), tetramethrin ((1,3,4,5,6,7-hexahydro-1,3-dioxo-2H-isoindol-2-yl)methyl 2,2-dimethyl-3-(2-methyl-1-propenyl)cyclopropanecarboxylate))

Examples of active ingredients as nicotinic acetylcholine receptor agonists include, but not limited to, nicotine and neonicotinoids (e.g. acetamiprid, imidacloprid, thiamethoxam).

Examples of active ingredients as chloride channel activators include, but are not limited to, milbemycins (e.g. milbemectin ((6R,25R)-5-O-demethyl-28-deoxy-6,28-epoxy-25-ethylmilbemycin B mixture with (6R,25R)-5-O-demethyl-28-deoxy-6,28-epoxy-25-methylmilbemycin B) and avermectins (e.g. abamectin (mixture of 80% (2aE,4E,8E)-(5'S,6S,6'R,7S,11R,13S,15S,17aR,20R,20aR,20bS)-6'-[(S)-sec-butyl]-5',6,6',7,10,11,14,15,17a,20,20a,20b-dodecahydro-20,20b-dihydroxy-5',6,8,19-tetramethyl-17-oxospiro[11,15-methano-2H,13H,17H-furo[4,3,2-pq][2,6]benzodioxacyclooctadecin-13,2'-[2H]pyran]-7-yl 2,6-dideoxy-4-O-(2,6-dideoxy-3-O-methyl- α -L-arabino-hexopyranosyl)-3-O-methyl- α -L-arabino-hexopyranoside and 20% (2aE,4E,8E)-

(5'S,6S,6'R,7S,11R,13S,15S,17aR,20R,20aR,20bS)-5',6,6',7,10,11,14,15,17a,20,20a,20b-dodecahydro-20,20b-dihydroxy-6'-isopropyl-5',6,8,19-tetramethyl-17-oxospiro[11,15-methano-2H,13H,17H-furo[4,3,2-pq][2,6]benzodioxacyclooctadecin-13,2'-[2H]pyran]-7-yl 2,6-dideoxy-4-O-(2,6-dideoxy-3-O-methyl- α -L-arabino-hexopyranosyl)-3-O-methyl- α -L-arabino-
 5 hexopyranoside, or avermectin B1), emamectin benzoate ((4'R)-4'-deoxy-4'-(methylamino)avermectin B1 benzoate (salt)).

Examples of active ingredients as inhibitors of mitochondrial ATP synthase include, but are not limited to, diafenthiuron (N-[2,6-bis(1-methylethyl)-4-phenoxyphenyl]-N'-(1,1-dimethylethyl)thiourea), propargite (2-[4-(1,1-dimethylethyl)phenoxy]cyclohexyl 2-propynyl
 10 sulphite), tetradifon (1,2,4-trichloro-5-[(4-chlorophenyl)sulfonyl]benzene).

Examples of active ingredients as inhibitors of chitin biosynthesis (type 0) include, but are not limited to, benzoylureas (e.g. bistrifluron (N-[[[2-chloro-3,5-bis(trifluoromethyl)phenyl]amino]carbonyl]-2,6-difluorobenzamide), diflubenzuron (N-[[[4-chlorophenyl]amino]carbonyl]-2,6-difluorobenzamide), teflubenzuron (N-[[[3,5-dichloro-2,4-
 15 difluorophenyl]amino]carbonyl]-2,6-difluorobenzamide).

Examples of active ingredients as inhibitors of acetyl CoA carboxylase include, but not limited to, tetrone and tetramic acid derivatives (e.g. spirodiclofen (3-(2,4-dichlorophenyl)-2-oxo-1-oxaspiro[4.5]dec-3-en-4-yl 2,2-dimethylbutanoate)).

Active ingredients of fungicides can target, nucleic acid synthesis, mitosis and cell
 20 division, respiration, protein synthesis, signal transduction, lipids and membrane synthesis, sterol biosynthesis in membranes, glucan synthesis, host plant defense induction, multi-site contact activity, and other unknown mode of action.

Examples of active ingredients targeted at nucleic acids synthesis include, but are not limited to, acylalanines (e.g. metalxyl-M (methyl N-(2,6-dimethylphenyl)-N-(methoxyacetyl)-D-alaninate)), isothiazolones (e.g. octhilinone (2-octyl-3(2H)-isothiazolone)).
 25

Examples of active ingredients targeted at mitosis and cell division include, but are not limited to, benzimidazoles (e.g. thiabendazole (2-(4-thiazolyl)-1H-benzimidazole)), thiophanates (e.g. thiophanate-methyl (dimethyl [1,2-phenylenebis(iminocarbonothioyl)]bis[carbamate])), toluamides (e.g. zoxamide (3,5-dichloro-
 30 N-(3-chloro-1-ethyl-1-methyl-2-oxopropyl)-4-methylbenzamide)), pyridinylmethyl-benzamides (e.g. fluopicolide (2,6-dichloro-N-[[[3-chloro-5-(trifluoromethyl)-2-pyridinyl]methyl]benzamide)).

Examples of active ingredients targeted at respiration include, but are not limited to,,
 carboxamide compounds (e.g. flutolanil (N-[3-(1-methylethoxy)phenyl]-2-
 (trifluoromethyl)benzamide), carboxin (5,6-dihydro-2-methyl-N-phenyl-1,4-oxathiin-3-
 carboxamide)), strobilurin compounds (e.g. azoxystrobin (methyl (αE)-2-[[6-(2-
 5 cyanophenoxy)-4-pyrimidinyl]oxy]-α-(methoxymethylene)benzeneacetate), pyraclostrobin
 (methyl [2-[[[1-(4-chlorophenyl)-1H-pyrazol-3-yl]oxy]methyl]phenyl]methoxycarbamate),
 trifloxystrobin (methyl (αE)-α-(methoxyimino)-2-[[[(1E)-1-[3-
 (trifluoromethyl)phenyl]ethylidene]amino]oxy]methyl]benzeneacetate), and fluoxastrobin
 ((1E)-[2-[[6-(2-chlorophenoxy)-5-fluoro-4-pyrimidinyl]oxy]phenyl](5,6-dihydro-1,4,2-dioxazin-
 10 3-yl)methanone O-methyloxime)). Examples of active ingredients targeted at multi-site
 contact activity include, but are not limited to,, dithiocarbamate compounds (e.g. thiram
 (tetramethylthioperoxydicarbonic diamide)), phthalimide compounds (e.g. captan (3a,4,7,7a-
 tetrahydro-2-[(trichloromethyl)thio]-1H-isoindole-1,3(2H)-dione)), chloronitrile compounds
 (e.g. chlorothalonil (2,4,5,6-tetrachloro-1,3-benzenedicarbonitrile)).

15 Examples of active ingredients that are not biologically active are hydrophobic dyes
 including red dye # 2, and Hostasol Yellow, small organic molecules including pyrene, and
 its derivatives, and solvents includingl nmethanol, ethanol, ethyl acetate, and toluene.

As used herein, the term "polyelectrolytes" refers to polymers containing ionized or
 ionizable groups. The ionized or ionizable groups can be either cationic, anionic, or
 20 zwitterionic. Preferred cationic groups are the amino or quaternary ammonium groups while
 preferred anionic groups are carboxylate, sulfonate and phosphates. Polyelectrolytes can
 be homopolymers, copolymers (random, alternate, graft or block). They can be synthesized
 or naturally occurred, and can be linear, branched, hyperbranched, or dendrimeric. For
 cationic polymers, examples include, but are not limited to, poly(allyamine),
 25 poly(ethyleneimine) (PEI), poly(diallyldimethylammonium chloride) (PDDA), poly(lysine),
 chitosan or a mixture of any of polycationic polymers. For anionic polymers, examples
 include, but are not limited to, poly(acrylic acid) (PAA), poly(methacrylic acid) (PMAA),
 poly(styrene sulfonic acid) (PSS), poly(glutamic acid), alginic acid, carboxymethylcellulose
 (CMC), humic acid, or a mixture of polyanionic polymers. In some embodiments the
 30 polymers are water soluble.

As used herein, the term "medium" refers to a solvent (or a mixture of solvents) used
 to form a polymeric solution. Solvents can be homogeneous or heterogeneous, but are not
 limited to, water, organic, perfluorinated, ionic liquids, or liquid carbon dioxide (CO₂), or a
 mixture of solvents, amongst others. In various embodiments, the solvent is water.

Compositions

In one aspect, the present invention provides for polymer nanoparticles comprising active ingredients. Figure 1 illustrates an exemplary nanoparticle-active ingredient composition. The polymer nanoparticle-active ingredient composite can have improved physical and chemical features that are not found in the components alone. For example, the polymer nanoparticles can improve the water solubility of the active ingredient without effecting the active ingredient's efficacy. In some embodiments, the polymer nanoparticles can increase or decrease the soil mobility of the active ingredient as compared to the active ingredient by itself, or as in typical active ingredient formulations. In some embodiments, the polymer nanoparticles can be used to control soil mobility to a targeted region of the soil. Several active ingredients, while generally effective for their indicated use, suffer from inefficiencies in use because of low water solubility, leaf spreading (or wettability on leaf surface), cuticle penetration or generally poor translocation through the plant. This requires the use of additional compounds in the formulation and higher concentrations of the active ingredient. Active ingredient formulations typically utilize surfactants (e.g., amine ethoxylates) and organic solvents to overcome these problems, however, these surfactants and organic solvents can have toxicological, environmental or other negative consequences. Polymer nanoparticles comprising active ingredients in this invention can reduce or even eliminate the need for surfactants, organic solvents, and lower the concentration requirements of the active ingredient while keeping the level of efficacy similar. In some embodiments, the polymer nanoparticles can be used to control the affinity of the active ingredient towards a surface or coating that would normally not have any affinity towards the active ingredient.

The polymer nanoparticles may comprise polyelectrolytes and may be prepared according to the methods of the current invention. The polymer nanoparticles may comprise one or more polymer molecules, which may be the same type of polymer or different polymers. The molecular weight of the polymer or polymers in the polymer nanoparticle can be approximately between 100,000 and 250,000 Dalton, approximately more than 250,000 Dalton, approximately more than 300,000 Dalton, approximately more than 350,000 Dalton, approximately more than 400,000 Dalton, approximately more than 450,000 Dalton, approximately more than 500,000 Dalton approximately between 5,000 and 100,000 Dalton, or approximately less than 5,000 Dalton. The molecular weight of the polymer or polymers in the nanoparticle can be in a range between any of the weights listed above. If multiple

polymers are used, they can be dissimilar in molecular weight; as an example, the polymer nanoparticle can comprise high molecular weight and low molecular weight poly(acrylic acid) polymers.

5 The molecular weight difference can be effective if the low molecular weight polymer and the high molecular weight polymer have complementary functional groups; e.g. the ability to participate in 'Click' chemistry as described below. In this case, the low molecular weight polymer is acting as a cross-linker of the high molecular weight polymer in the nanoparticle.

10 The polymer nanoparticles may be cross-linked, either chemically or with light or with particulate irradiation (e.g. gamma irradiation). The density of cross-linking can be modified to control the transport of material from the interior of the polymer nanoparticle to the environment of the nanoparticle. The polymer nanoparticle may comprise discrete cavities in its interior, or may be a porous network. In various embodiments, the nanoparticle has a mean diameter in one or more of the ranges between: about 1 nm to about 10 nm; about 10
15 nm to about 30 nm; about 15 nm to about 50 nm; and about 50 nm to about 100 nm; about 100 nm to about 300 nm). It is to be understood that the term "mean diameter" is not meant to imply any sort of specific symmetry (e.g., spherical, ellipsoidal, etc.) of a composite nanoparticle. Rather, the nanoparticle could be highly irregular and asymmetric.

20 The polymer nanoparticle can comprise hydrophilic (ionized, ionizable, or polar non-charged) and hydrophobic regions. In some embodiments, the polymer is amphiphilic. In some embodiments the polymer is not amphiphilic. If the polymer nanoparticle comprises a polyelectrolyte in a polar or hydrophilic solvent, the polyelectrolyte can organize itself so that its surface is enriched with ionized or ionizable groups and its interior is enriched with hydrophobic groups. In some embodiments, the polyelectrolytes are amphiphilic. In some
25 embodiments the polyelectrolytes are not amphiphilic. This can occur in relatively hydrophilic or polar solvents. In hydrophobic solvents, the inverse process can occur; that is, that the polyelectrolyte can organize itself so that its surface is enriched with hydrophobic groups and its interior is enriched with ionized or ionizable groups. This effect can be enhanced by appropriate choice of polyelectrolytes with hydrophilic and hydrophobic regions; it can also
30 be enhanced by modification of the polyelectrolyte e.g., adding hydrophobic regions to the polyelectrolyte. This process can be probed using a fluorescent probe such as pyrene and its derivatives, which have polarity-sensitive emission spectra. Higher polarity is usually associated with a more hydrophilic microenvironment, while lower polarity is associated with a more hydrophobic microenvironment. Polymer nanoparticles with a low polarity when

probed using pyrene that are still highly water soluble or dispersible are expected to have hydrophobic regions where pyrene is loaded and hydrophilic regions that solubilize or disperse the polymer nanoparticle.

Modification of the polymer can be performed by various methods, including
5 conjugation, copolymerization, grafting and polymerization, or by exposure to free radicals. Modification can be designed before, during or after the preparation of polymer nanoparticles. An example of polymer modification during the preparation of polymer nanoparticles involves with poly(acrylic acid). Under appropriate conditions, poly(acrylic acid) that is exposed to UV will decarboxylate some of its acid groups, thereby increasing
10 the hydrophobicity of the system. Similar treatment can be used with other types of polymers. Modification of the polymer can be observed using titration, spectroscopy or nuclear magnetic resonance (NMR) under suitable conditions. Polymer modification can also be observed using size exclusion or affinity chromatography. The hydrophobic and hydrophilic regions of the polymer nanoparticle can be observed using solvent effects. If the
15 nanoparticle is dispersible in a first polar solvent such as water, it is clear that it must have exposed surface hydrophilicity. This can also be ascertained using surface charge analysis such as a zeta potential measurement. If it is also possible to swell the polymer through addition of a miscible, partially miscible, or non-miscible second solvent that is more hydrophobic than the first polar solvent, this demonstrates the existence of hydrophobicity in
20 the interior of the nanoparticle. Swelling can be observed through a change in particle size observed using light scattering or by disappearance of an immiscible second solvent phase due to partitioning of the solvent into the nanoparticle. The inverse experiment with a first hydrophobic solvent and a second hydrophilic solvent can be used to observe enrichment in hydrophobic groups on the surface of the nanoparticle and hydrophilic groups in the interior
25 of the nanoparticle.

The polymer nanoparticle of the present invention comprises active ingredients. The active ingredients can be covalently bound to the polymer or physically associated with the polymer. An example method to produce polymer nanoparticle containing active ingredients chemically bound to the polymer has been described elsewhere in this specification. The
30 active ingredients can also be physically or chemically associated with the polymer of the polymer nanoparticle in a non-covalent fashion. If the polymer nanoparticle comprises multiple polymers, the active ingredients can be physically or chemically associated with one or multiple polymers in the polymer nanoparticles. Physical association is defined by non-covalent interactions such as charge-charge interactions, hydrophobic interactions, polymer-

chain entanglement, affinity pair interactions, hydrogen bonding, van der Waals forces, or ionic interactions.

Alternatively, there can be little interaction between the active ingredient and the polymer nanoparticle but the active ingredient can be trapped inside or associated with the polymer nanoparticle because it is physically precluded (e.g. sterically) from escaping from the polymer nanoparticle. The active ingredient can be primarily in the interior of the polymer nanoparticle, on the surface of the polymer nanoparticle, or throughout the polymer nanoparticle. If the polymer nanoparticle has cavities, the active ingredient can be primarily inside the cavities. If the polymer nanoparticle has hydrophobic regions, the active ingredient can be associated with the hydrophobic regions or the non-hydrophobic regions, depending on the chemical identity of the active ingredient.

The present invention also provides for formulations of polymer nanoparticles comprising active ingredients. The polymer nanoparticles comprising active ingredients of the present invention can be formulated in a variety of ways. In some cases they can be dried into a solid by freeze drying, spray drying, tray drying, air drying, vacuum drying, or other drying methods. Once dried, they can be stored for some length of time and then re-suspended into a suitable solvent when they need to be used. In certain embodiments, the dried solid can be granulated, made into tablets, for handling.

In some embodiments, polymer nanoparticles comprising active ingredient in a solvent can be formulated into a gel. This can be done by removing the solvent until gelation occurs. In some embodiments, this solvent is aqueous. Once gelation occurs, the resulting gel can be stored and delivered directly or redispersed into solvent by addition of solvent. In some embodiments, polymer nanoparticles comprising active ingredients can be formulated into a suspension, dispersion, or emulsion. This can be done using standard formulation techniques known in the art.

In some embodiments, the polymer nanoparticle can provide enhanced solubility, dispersibility, stability, or other functionality to the active ingredient associated with it. One example of this would be when a polyelectrolyte-based polymer nanoparticle comprising active ingredient is dispersed in an aqueous solvent. If the active ingredient has a lower solubility than the polyelectrolyte, its association with the polyelectrolyte nanoparticle can increase its ability to be dissolved or dispersed in the solvent. This is particularly beneficial for poorly water soluble active ingredients where a formulation or use require increased water solubility or dispersibility. In certain cases, because the polymer nanoparticle provides additional solubility, dispersibility, stability, or other functionality to the active ingredient, it is

possible to reduce or eliminate the use of certain formulation additives such as formulants, surfactants, dispersants, or adjuvants. In various embodiments, the resulting system does not need added surfactant. The polymer nanoparticles that the active ingredient is associated with may have both anionic and nonionic surfactant components. These will
5 mean that the nanoparticles may have excellent penetration through the leaf cuticle, and can also mean an increased dispersibility in either aqueous or non-aqueous dispersions, depending on the amount of non-ionic or ionic components present in the nanoparticles. Surfactants with tunable poly(ethylene oxide) moieties may decrease the amount of glyphosate necessary for weed control substantially. This increased efficacy can arise from
10 improved cuticle penetration due to increased hydration and increased movement (translocation) through the plant.

Furthermore, the amount of active ingredient applied can be increased in hard water applications, particularly for charged active ingredients such as glyphosate. This is because the active ingredient can be deactivated by hard water ions, so that more active ingredient
15 needs to be applied to have the same efficacy. If the polymer nanoparticle has ionized or ionizable groups, it will be a natural hard water ion scavengers. In various embodiments, at 700 ppm hard water they will scavenge essentially all of the hard water ions at typical application rates.

In some embodiments, polymer nanoparticles comprising active ingredients enhance
20 physical and chemical characteristics of the actives, including, e.g. soil mobility and water solubility. In certain embodiments, polymer nanoparticles comprising active ingredients can increase soil mobility of the actives. The poor soil mobility of the actives can be caused by binding of the active ingredient to a soil surface or organic matters, or by poor diffusion of the active ingredient due to poor water solubility. By providing a polymer nanoparticle
25 comprising the active ingredient, soil mobility may be enhanced. If the polymer nanoparticle comprising the active ingredient is water soluble or dispersible, it can provide enhanced diffusion through a soil column. This can be enhanced if the polymer nanoparticle is stable and does not stick to the surface of soil particles or organic matter in the soil. This effect can be caused by several phenomena, including increased water solubility or dispersibility
30 relative to the active ingredient without polymer nanoparticles, increased diffusion through the soil column due to small particle size relative to the pores in the soil.

In certain embodiments, the binding of the polymer nanoparticle can also be tuned or modified. This can be accomplished by modification of the surface chemistry of the polymer. Soil contains different charged moieties, which can include negative and positive moieties,

depending on the soil. The interaction of the polymer nanoparticle with the soil surface can be tailored by using different polyelectrolytes or blends of polymers. By changing the polymer composition of the nanoparticle, its affinity for soil surfaces can change and thus the mobility of the nanoparticle will change. As an example, if the polymer comprises groups with a high affinity for soil surfaces, they can be modified with e.g. a non-ionic surfactant-type polymer that will help to decrease their affinity for soil surfaces. Alternately, if the polymer does not comprise groups with a high affinity for soil surfaces, but it is desired to immobilize the nanoparticles in the soil, the polymer can be modified with groups with a high affinity for soil surfaces. Such groups can include but are not limited to amines, amides, quaternary ammoniums, or in certain conditions carboxyls. This can also be accomplished by providing a polymer nanoparticle comprising active ingredient that already has chemical groups with a high affinity for soil surfaces.

The polymer nanoparticles with active ingredient can also be manipulated to have triggered, slow, or controlled release of the active ingredient. If the polymer nanoparticles are formulated in a suitable solvent, release of the active ingredient from the polymer nanoparticles can occur in several ways. First, the release can be diffusion mediated. The rate of diffusion mediated release can be modified by increasing or decreasing the density of crosslinking of the polymer nanoparticle. The rate can also be modified depending on the location of the active ingredient in the polymer nanoparticle; that is, whether it is primarily in the interior of the polymer nanoparticle, primarily on the surface of the polymer nanoparticle, or dispersed throughout the polymer nanoparticle.

In certain embodiments, if there is active ingredient on the surface of the polymer nanoparticle and in the interior of the polymer nanoparticle, release can have two stages; a 'burst' release associated with release of the active ingredient on the surface of the polymer nanoparticle, followed by a slower diffusion-mediated release of active ingredient from the interior of the nanoparticle. Release rates will also be dependent on whether the active ingredient has a chemical affinity or association for the polymer or polymers that comprise the polymer nanoparticle. Stronger chemical affinity or association between active ingredient and polymer nanoparticles indicates slower release of active ingredient from polymer nanoparticles, or vice-versa. Therefore polymer nanoparticles with varied hydrophobicity can be tailored by chemical modifications to meet the requirement of loading active ingredients with different hydrophobicity based on the principle of "like dissolves like".

In some cases, the release of the nanoparticle can be triggered. Triggering mechanisms can include but are not limited to changes in pH, solvent conditions, addition or

removal of salt, changes in temperature, changes in osmotic or barometric pressure, presence of light, or addition of polymer degrading agents like enzymes, bacteria, and free radicals. As an example, if the polymer nanoparticle comprises a polyacid, and the pH of the environment of the nanoparticle changes, the polyacid may change from its protonated to its unprotonated state or vice-versa. This may modify the affinity of the active ingredient associated with the polymer nanoparticle with the polymer. If the affinity decreases, this may lead to triggered release of the active ingredient. Changes in the surrounding salt or ion concentration as well as changes in the surrounding temperature and pressure can cause reorganization of the polymer comprising the nanoparticle. The polymer reorganization can displace the associated active ingredient towards the exterior of the nanoparticle. Exposure of the nanoparticles to light (e.g., UV radiation) or other polymer degradation agents like enzymes and free radicals can initiate the release of the active ingredient through polymer degradation. Release of active ingredient from the nanoparticle can be observed by measuring the amount of active ingredient associated with the nanoparticle and comparing it to the amount of active ingredient 'free' in the nanoparticle's environment. This can be done by separately sampling the nanoparticles and their environment; i.e. by separating the nanoparticles by e.g. membrane filtration and then measuring the active ingredient in each fraction by HPLC or UV spectroscopy. One method to do this comprises the use of a tangential flow filtration capsule, as described in the Examples. In some cases, the active ingredient associated with the nanoparticles will need to be extracted by addition of solvent.

In some embodiments, an active ingredient such as pyrene and some of its derivatives can be used as an environment-sensitive fluorescent probe to characterize the relative hydrophobicity of the polymer nanoparticle microenvironment. The intensity ratio of the first and third vibronic bands (I_1/I_3) in the emission spectra of the pyrene monomer is very sensitive to the monomer's microenvironment, and can be used as a metric to gauge the hydrophobic nature of different polymer nanoparticles produced using the methods described in this patent. The hydrophobic character of the nanoparticles made using the methods described in the patent are dependent on the solution pH and the polymer used to make the polymer nanoparticles. At pH 3-6, a polymer nanoparticle microenvironment similar to o-dichlorobenzene (*Photochem. Photobiol.* 1982,35, 17) can be achieved by making polymer nanoparticles from poly(methacrylic acid) (PMAA) or poly(methacrylic acid-co-ethyl acrylate) (P(MAA-co-EA)), while a less hydrophobic microenvironment similar to dioxane can be achieved from Zn^{2+} -collapsed polyacrylic acid nanoparticles. A microenvironment similar to glycerol can be achieved by making Na^+ -collapsed polyacrylic nanoparticles. Similarly, in the pH range 6-10 different microenvironments are achievable

depending on the polymer used to make the nanoparticles. A microenvironment similar to methylene chloride can be achieved from PMMA or P(MAA-co-EA) nanoparticles while a less hydrophobic microenvironment similar to glycerol can be achieved from Na⁺ collapsed polyacrylic acid nanoparticles.

5 In some embodiments, the polymer nanoparticles can increase the dispersibility of hydrophobic molecules, such as neutral organic dyes (eg. Hostasol Yellow and Red dye #2) and other molecules in aqueous solution. These neutral organic dyes or molecules would have much lower solubility than the polymer nanoparticles in aqueous solution, but its association with the hydrophobic areas of the polymer nanoparticle can increase its ability to
10 be dissolved or dispersed in the solvent. In certain cases, because the polymer nanoparticle provides additional solubility, dispersibility, stability, or other functionality to the active ingredient, the need for additional dispersing agents to render these active ingredients soluble is unnecessary.

15 *Polymer Collapse*

The conformation of a polymer in solution is dictated by various conditions of the solution, including its interaction with the solvent, its concentration, and the concentration of other species that may be present. The polymer can undergo conformational changes depending on the pH, ionic strength, cross-linking agents, temperature and concentration.
20 For polyelectrolytes, at high charge density, e.g., when "monomer" units of the polymer are fully charged, an extended conformation is adopted due to electrostatic repulsion between similarly charged monomer units. Decreasing the charge density of the polymer, either through addition of salts or a change of pH, can result in a transition of extended polymer chains to a more tightly-packed globular i.e. collapsed conformation. The collapse transition
25 is driven by attractive interactions between the polymer segments that override the electrostatic repulsion forces at sufficiently small charge densities. A similar transition can be induced by changing the solvent environment of the polymer. This collapsed polymer is itself of nanoscale dimensions and is, itself, a nanoparticle. Similar collapse transitions can be driven for uncharged polymers using changes in solution condition, e.g., for polymers with
30 low critical solution temperatures such as poly-(n-isopropylacrylamide) ("NIPAM"). Alternately, collapse of an uncharged polymer can be caused by addition of a non-solvent under appropriate conditions. In this specification and claims the term "collapsed polymer" refers to an approximately globular form, generally as a spheroid, but also as an elongate or multi-lobed conformation collapsed polymer having nanometer dimensions. This collapsed

conformation can be rendered permanent by intra-particle cross-linking. The cross-linking chemistry includes hydrogen bond formation, chemical reaction to form new bonds, or coordination with multivalent ions. Crosslinkers can be added before or after the polymer is collapsed.

5

Conjugation

A fraction of the functional groups of a polymer such as a polyelectrolyte can be used for conjugation or can be converted to other functional groups. These functional groups can be utilized for, e.g., cross-linking, attachment sites, polymerization, intra- and inter-particle stabilization, among other uses. For example, a bifunctional molecule, 2-hydroxyethyl methacrylate (HEMA) containing an alcohol group and a latent methacrylate group can be reacted with a carboxylic acid group of poly(acrylic acid) (PAA) through ester bond formation, converting the carboxylic acid group to a methacrylate group. The methacrylate group can be crosslinked when exposed to UV radiation or an elevated temperature. As a result, a number of methacrylate groups attached along the PAA chain can be designed and thus the extent of cross-linking can be controlled. Another example, methacryloyl chloride containing an acid chloride and a latent methacrylate group can be reacted with an amine group of chitosan through amide bond formation, converting the amine group to a methacrylate group. The methacrylate group can be crosslinker when exposed to UV radiation or an elevated temperature. As a result, a number of methacrylate groups attached along the chitosan backbone can be designed and thus the extent of cross-linking can be controlled.

As another example, methoxy-terminated poly(ethylene glycol) (mPEG) containing a terminal alcohol group can be reacted with a carboxylic acid group of poly(acrylic acid) to form an ester bond, attaching a mPEG onto PAA polymer. As a result, a number of mPEG groups attached along a polymer chain can be designed and controlled. mPEG-modified polymers such as PAA have several features.

Nanoparticles formed from mPEG-modified polymers can be stabilized by electrostatic interaction from carboxylic acid groups or steric repulsion from the PEG groups, or a combination of both. As another example, allyl, vinyl, styryl, acrylate and methacrylate groups can be conjugated to a polyelectrolyte to serve as polymerizable moieties. Examples of bifunctional molecules that are capable of reacting with carboxylic acid moieties in anionic polymers and that will leave polymerizable groups for cross-linking include, but are not limited to, 2-hydroxyethyl methacrylate ("HEMA"), 2-hydroxyethyl acrylate ("HEA"), N-(2-

hydroxypropyl) methacrylamide, N-(2-aminopropyl) methacrylamide hydrochloride, N-(2-aminoethyl) methacrylamide hydrochloride, 2-aminoethyl methacrylate hydrochloride, allylamine, allyl alcohol, 1,1,1-trimethylolpropane monoallyl ether. Drug molecules, active ingredient compounds, or biomolecules can also be conjugated to a polyelectrolyte for target delivery. Fluorescent molecules can also be incorporated onto a polyelectrolyte to serve as fluorescent probes. Simple hydrophobic groups, such as short alkyl chains, can be attached to a polyelectrolyte to increase the pH sensitivity of the polymer or for other reasons. Complementary reactive groups can be also incorporated onto the same polymer chain or different polymer molecules to improve cross-linking. A combination of these molecules can be also incorporated onto the same polymer chain or different polymer molecules, with individual molecules serving different purposes. For example, a polymerizable group, HEMA, and active ingredient molecule can be modified to attach onto the same polymer chain, whereas the HEMA groups are used for cross-linking and active ingredients are used to enhance loading of active ingredient or to provide activity.

Conjugation can be performed before or after preparation of polymer nanoparticles.

Crosslinking

In certain embodiments, it is desired to crosslink the polymer particles of the present invention. Crosslinking can be induced by light, temperature, stoichiometric reagents, or the presence of a salt or a catalyst. Cross-linking may occur on surface layer or a specific location within the collapsed nanoparticles, or across the entire particle. Light-induced crosslinking can be triggered by UV and visible light of various wavelengths, in air or under an inert environment, with or without photoinitiators. Examples of photoinitiators that activate in the UV wavelength region include, but are not limited to, phenyl bis(2,4,6-trimethylbenzoyl)-phosphine oxide (IRGACURE 819, Ciba Corporation), acetophenone, and benzophenones such as 2-hydroxy-2-methylpropiophenone. Examples of photoinitiators that activate in the visible wavelength region include, but are not limited to, benzil and benzoin compounds, and camphorquinone. Cross-linking reaction can also be induced by the addition of an external crosslinker with or without the presence of a catalyst. Examples of external cross-linkers used to cross-link PAA, for example, include, but are not limited to, difunctional or polyfunctional alcohol (e.g. ethylene glycol, ethylenedioxy-bis(ethylamine), glycerol, polyethylene glycol), difunctional or polyfunctional amine (e.g. ethylene diamine, 1,6-diaminohexane, 1,8-diaminooctane, JEFFAMINE® polyetheramines (Huntsman), poly(ethyleneimine)). These multifunctional amines can be used as the collapsing agents

due to their alkaline nature, and can help impart additional functionality to the polymer, including modified hydrophobicity or polarity as characterized using pyrene as a fluorescent probe. Catalysts are often required for this reaction. Such catalysts include, but are not limited to, carbodiimide compounds, e.g., N-(3-dimethylaminopropyl)-N'-ethylcarbodiimide hydrochloride ("EDC"). Other examples of chemical cross-linkers include, but are not limited to, difunctional or polyfunctional aziridines (e.g., XAMA-7, Bayer MaterialScience LLC), difunctional or polyfunctional epoxy, or divalent or multivalent ions.

To enhance crosslinking reactions initiated by light or heat, polymerizable groups can be covalently attached along a polyelectrolyte chain. Methods of attaching the polymerizable groups to a polyelectrolyte chain are well known. Examples of such reactions include, but are not limited to e.g., esterification, amidation, addition, or condensation reactions. Examples of polymerizable groups include, allyl, vinyl, styryl, acrylate and methacrylate moiety. Examples of molecules that are capable of reacting with carboxylic acid moieties in anionic polymers and that will leave polymerizable groups for crosslinking include, but are not limited to, 2-hydroxyethyl methacrylate, 2-hydroxyethyl acrylate, N-(2-hydroxypropyl) methacrylamide, N-(2-aminopropyl) methacrylamide hydrochloride, N-(2-aminoethyl) methacrylamide hydrochloride, 2-aminoethyl methacrylate hydrochloride, allylamine, allyl alcohol, 1,1,1-trimethylolpropane monoallyl ether.

In some embodiments, a polyelectrolyte incorporated with complementary reactive pairs is used. These reactive groups can be activated and controlled under specific conditions. After forming polymer particles, these reactive groups do not react until catalysts are added. A typical reaction between an azide and an alkyne group is known as "Click reaction", and a common catalyst system for this reaction is Cu(SO₄)/sodium ascorbate. In certain embodiments, this type of reaction can be used for chemical crosslinking.

In certain embodiments, a polyelectrolyte containing carboxylates or amines can be crosslinked via carbodiimide chemistry using an appropriate di-amine or dicarboxy functional crosslinker and an activating agent. Typical agents used to activate carboxy groups toward amide formation include, but are not limited to, N-Ethyl-N'-(3-dimethylaminopropyl)carbodiimide hydrochloride, Dicyclohexylcarbodiimide, N,N'-Diisopropylcarbodiimide. Di-amine functional crosslinkers include but are not limited to Ethylenediamine, O,O'-Bis(2-aminoethyl)octadecaethylene glycol, PEG-diamine, 1,3-diaminopropane, 2,2' (ethylenedioxy)bis(ethylamine), JEFFAMINE® polyetheramines (Huntsman), poly(ethyleneimine)).

Formation of Polymer Particles by Polymer Collapse

In various aspects, the present invention describes methods of producing polymer nanoparticles including active ingredients. In one embodiment, the polymer includes a polyelectrolyte and the nanoparticle is referred to as a polyelectrolyte nanoparticle.

5 Polyelectrolyte nanoparticles including active ingredients can be produced in a variety of ways. As an example, the polyelectrolytes could be adsorbed to active ingredients using e.g. micelles, coacervation, or other similar formulation technologies to produce polyelectrolyte nanoparticles including active ingredients.

In various embodiments, the polyelectrolyte nanoparticles could also be produced
10 using collapse of the polyelectrolyte around the active ingredient. This is shown in Figure 2. For polyelectrolytes, at high charge density, e.g., when "monomer" units of the polymer are fully charged, an extended conformation is adopted due to electrostatic repulsion between similarly charged monomer units. Decreasing the charge density of the polymer by addition of salts can result in a transition of extended polymer chains to a more tightly-packed
15 globular i.e. collapsed conformation. The collapse transition is driven by attractive interactions between the polymer segments that override the electrostatic repulsion forces at sufficiently small charge densities. If desired, in some embodiments, the collapsed conformation can be rendered permanent by crosslinking the polymer. In one embodiment, a polymer nanoparticle including active ingredients can be produced using a method
20 including the steps of (a) dissolving a polyelectrolyte into an aqueous solution under solution conditions that render it charged and (b) adding an active ingredient that is oppositely charged under these conditions. If desired, the resulting polymer nanoparticle associated with active ingredient can be induced to form intra-particle crosslinks to stabilize the active ingredients associated with the nanoparticles. The extent of cross-linking can be used to
25 control the release of active ingredients into the nanoparticles' environment. In some embodiments, water can be partially removed to afford a concentrated dispersion or completely removed to generate a dry solid. In some embodiments, a second solvent can be added to the resulting dispersion to precipitate the nanoparticles containing active ingredients. In some cases, the second solvent is a non-solvent for the nanoparticles.

30 It is also possible to produce polymer particles from a polyelectrolyte in other ways. In some embodiments, this includes the steps of (a) dissolving a polymer into aqueous solution, (b) associating an active ingredient with the polymer, and (c) causing the polymer to collapse. If desired, a metal ion or other species can be used instead of an active ingredient. As an example, if an active ingredient with an affinity for the polymer is added prior to

collapse, the resulting material will be a polymer nanoparticle that includes an active ingredient. In further embodiments, water can be partially removed to afford a concentrated dispersion or completely removed to generate a dry solid. In further embodiments, a second solvent can be added to the resulting dispersion to precipitate the nanoparticles containing
5 actives. In some embodiments, the second solvent is a non-solvent for the nanoparticles.

Potential affinities between the polymer and the species associated with the polymer may include any chemical groups that are found to have affinity for one another. These can include specific or non-specific interactions. Non-specific interactions include electrostatic interactions, hydrogen bonding, van der Waals interactions, hydrophobic-hydrophobic
10 associations, π - π stackings. Specific interactions can include nucleotide-nucleotide, antibody-antigen, biotin-streptavidin, or sugar-sugar interactions, where the polymer has the functionality of one half of the affinity pair and the species (e.g. active ingredient) associated with the polymer has the other half.

Potential methods to cause the polymer to collapse around the active ingredient
15 associated or to be associated with the polymer (e.g., the active ingredient) can include decreasing the solubility of the polymer in the solvent. In some embodiments, this can be done by adding a non-solvent for the polymer. As an example, if the polymer is polyacrylic acid and the solvent is water, a high-salt ethanol solution can be added to cause the polymer to condense into a collapsed conformation and precipitate out of solution. The resulting
20 product can be recovered and re-suspended into water. Other methods to cause the polymer to collapse include modification of the solubility by changing the temperature of the solution, e.g. for systems with low critical solution temperatures such as poly-(n-isopropylacrylamide) ("NIPAM"). If the polymer is a polyelectrolyte, the polymer can also be induced to collapse by addition of salt or modification of the pH after association between the
25 active ingredient and the polymer has occurred.

In various embodiments, a similar process can be used for a hydrophobic active ingredient that can be dissolved to a limited extent in water at an elevated temperature but is relatively insoluble at room temperature. In one embodiment, the method includes the steps of (a) saturating an active ingredient in water at an elevated temperature in the presence of a
30 polymer and a salt, (b) cooling the mixture. After cooling the mixture, the active ingredient will precipitate and the polymer will collapse around the active ingredient due to specific or non-specific interactions between active ingredient and the polymer. For example, poly(sodium sulfonate) and saturated chlorothalonil (a fungicide) in solution can be mixed at elevated temperature in the presence of NaCl. Upon cooling the mixture to lower

temperature, both species precipitate, but poly(sodium sulfonate) can precipitate around chlorothalonil. If desired, the resulting polymer-encapsulated active ingredient nanoparticle can be induced to form intra-particle crosslinks to stabilize the active ingredients within the nanoparticles. The extent of crosslinking can be used to control the release of active
5 ingredients into the nanoparticle's environment.

In some embodiments, an approach to produce polymer particles from a modified polyelectrolyte includes the steps of (a) conjugating hydrophobic groups along a polyelectrolyte chain, (b) dissolving the hydrophobically modified polyelectrolyte into an aqueous solution under solution conditions that render it charged, causing the hydrophobic
10 groups to associate intramolecularly, and (c) crosslinking the polymer. When a polyelectrolyte is modified with hydrophobic groups, the collapse transition is driven by hydrophobic interactions in the absence of salt, as shown in Figure 3.

In some embodiments, an approach to produce polymer particles from a polyelectrolyte includes the steps of (a) collapsing the polyelectrolytes with a crosslinker, (b)
15 adding a salt and (c) inducing crosslinking reaction by temperature or presence of a catalyst. For example, poly(acrylic acid) can be collapsed by treating with 1,6-diaminohexane due to acid-base interaction. The crosslinking reaction forming amide bond can be triggered by refluxing the mixture.

Collapse can be monitored using, e.g., viscometry. Typically solutions of polymers
20 show a viscosity higher than that of the solvent in which they are dissolved. For polyelectrolytes in particular, the pre-collapse polymeric solution can have a very high viscosity, with a syrupy consistency. After formation of polymer-encapsulated nanoparticles of active ingredients using collapse, a well-dispersed sample of the nanoparticles may show a much lower viscosity. This decreased viscosity after and even during collapse can be
25 measured under appropriate conditions with either a vibrating viscometer or e.g. an Ostwald viscometer or other known methods in the art.

The formation of the nanoparticles can be demonstrated using dynamic light scattering (DLS), atomic force microscopy (AFM) or transmission electron microscopy (TEM). In DLS, formation of the nanoparticles is demonstrated by a decrease in average
30 particle size relative to either the particle size of a solution of active ingredient of the same concentration or the particle size of a solution of the polymer encapsulant at the same concentration. In TEM or AFM the nanoparticles can be visualized directly.

If desired, the polymer nanoparticle can be induced to form intra or inter-particle crosslinks as described above. In certain embodiments, this crosslinking can be effected to

stabilize the active ingredients or oppositely charged species associated with the polymer nanoparticle. The extent of crosslinking can be used to control the release of active ingredients or oppositely charged species into the nanoparticle's environment.

5 A redispersible solid prepared according to the present invention may be redispersed at a concentration higher than the solubility of the active ingredient under certain conditions. The redispersibility of the polymer-encapsulated nanoparticles may be determined by the solubility of the polymer encapsulant. As an example, if the polymer-encapsulant is highly water-soluble, nanoparticles of active ingredients encapsulated by that polymer will be able to be dispersed in water at high concentration, even if the active ingredient itself is not highly
10 water soluble. This can be observed by a lack of precipitation of the active ingredient when redispersed above its solubility limit. This ability to redisperse at higher concentration may have applicability in a variety of formulations.

Formation of Polymer Particles from an Inorganic Metal Salt

15 In some embodiments, a polymer nanoparticles is formed without an associated active ingredient. The active ingredient is associated with the nanoparticle after the nanoparticle is fully formed. The association step may be accomplished in several different methods, each involving several different steps.

In one embodiment, the method of producing polymer nanoparticles includes the
20 steps of (a) dissolving a polyelectrolyte into an aqueous solution under solution conditions that render it charged, (b) adding a species that is oppositely charged under these conditions, causing the polymer to collapse, (c) crosslinking, and (d) removing the oppositely charged species. A schematic describing one embodiment of this method is shown in Figure 4. The resulting polymer nanoparticles can have a hollow structure, cavities, or can be a
25 porous network structure. The polymer nanoparticles are capable of being loaded with active ingredients. In certain embodiments, the oppositely charged species is a metal ion e.g. from a metal salt. The resulting polymer nanoparticle can be crosslinked by any of the methods described above.

Examples of inorganic metal salts include, but are not limited to, the alkali and the
30 alkaline earth metal salts like NaCl, KCl, KI, NaF, LiCl, LiBr, LiI, CsCl, CsI, MgCl₂, MgBr, CaCl₂. In certain embodiments the metal salt could be a nitrate, or a chloride salt of the transition metal series. Examples of transition metal salts are, but are not limited to,, Zn(NO₃)₂, ZnCl₂, FeCl₂, FeCl₃, Cu(NO₃)₂. Other metal salts can be used as well like

aluminum nitrate, bismuth nitrate, cerium nitrate, lead nitrate. In other embodiments, the salt can be the nitrate, chloride, iodide, bromide, or fluoride salt of ammonium.

Removal of the oppositely charged species can be accomplished by adjustment of pH. For example, if the polyelectrolyte has carboxylic acids as its ionizable groups, the
5 oppositely charged species can be removed by acidification of the system by addition of a mineral or organic acid. This will displace the oppositely charged species and protonate the carboxylic acids. Similar methods can be used for ionizable species that are strong or weak acids or strong or weak bases.

Dialysis or similar membrane separation methods can be used to replace charged
10 species with different charged species, which may be more amenable to exchange or loading of active ingredient. The extent of displacement will be dependent on the affinity between the oppositely charged species and the ionizable groups, and will also be dependent on the ease of ionization (e.g. the strength or weakness of the acid or base) of the ionizable group.

The extent of displacement will also be dependent on the pH that the solution is
15 adjusted to. For example, if the polymer is a high molecular weight poly(acrylic acid), the oppositely charged species can be largely removed in water when the pH is of about 0.1 to about 3.5, in certain embodiments about 1.5 to about 2.0, and can also be removed by dialyzing against water at a similar pH value. In certain embodiments the oppositely charged
20 species can be removed and replaced with a more benign charged species that does not prevent loading of the polymer particle with an active ingredient. As an example, if Fe(III) is used as the collapsing agent, dialysis against Na^+ can displace the Fe(III) and replace it with Na^+ .

In some embodiments, the method to produce polymer nanoparticles includes the
25 steps of (a) dissolving a polyelectrolyte into an aqueous solution under solution conditions that render it charged, (b) adding a species that is oppositely charged under these conditions, causing the polymer to collapse, (c) modifying the solution conditions to form an insoluble nanoparticle from the oppositely charged species, (d) crosslinking, and (e) modifying the solution conditions to remove the nanoparticles. In certain embodiments the
30 nanoparticles are hydroxides, oxides, carbonates, or oxyhydroxides.

In certain embodiments, the oppositely charged species is a metal ion e.g. from a metal salt, and the hydroxide is a metal hydroxide, in which case step (c) can be accomplished through adjustment in pH. If the oppositely charged species is a metal ion, it can be converted to a hydroxide by adjustment of pH. The pH of the dispersion plays a

critical role in converting metal ions to metal hydroxide. Metal ions can typically be converted to metal hydroxide by making the solution basic, with pH in the range of about 7 to about 14 (e.g, from about 7.5 to about 8.5; about 8.5 to about 10; about 10 to about 14. Conversion of the metal hydroxide to the metal oxide can be effected in a variety of ways, including heating to e.g. dehydrate the hydroxide, forming the oxide. If the dehydration is partial, a mixed oxide/hydroxide, referred to as an oxyhydroxide, can result. If the heating is performed in solution, the temperature can be in the range of 25 - 100 °C; 50 - 100 °C; or 70 - 90 °C. In some embodiments, the oxide can be formed from the hydroxide by recovering a dry solid from solution including the polymer particles and the hydroxide, and heating. The temperature of heating should be high enough to cause the hydroxide to convert to the oxide, without adversely affecting the polymer (e.g., decomposing the polymer). Temperature ranges will depend on the metal and the polymer, as well as the desired result. In some embodiments, the metal hydroxide, oxide, or oxyhydroxide can be formed by decomposition of a complex. As an example, Titanium(IV) bis(ammonium lactato)dihydroxide (TALH) can be used as a precursor for the formation of TiO₂ in aqueous solution. The decomposition of TALH under acidic (pH 3) or basic (pH 10) leads to the formation of TiO₂. An example illustrating the formation of polymer nanoparticles from metal oxide nanoparticles is shown in Figure 6. If the insoluble nanoparticle is a carbonate, it can be formed by addition of a carbonate salt in step (c), and can be removed using similar techniques.

Step (e), removal of the nanoparticle, can be accomplished by adjustment of pH to conditions that would lead to the dissolution of the nanoparticle in solution. The pH of the dispersion also plays an important role in removing the nanoparticle. The metal hydroxides typically dissolve in water with acidic pH, which can include pH in the range of about 0.1 to about 2.5; about 1.5 to about 2.0; about 1 to about 6; about 2 to about 5; or about 2 to about 4. The metal hydroxides can also be dissolved by dialyzing against water at a similar pH value. Oxides, oxyhydroxides, or carbonates can be removed in a similar fashion.

Formation of Polymer Particles Using Modified Polyelectrolytes

A modified polyelectrolyte can contain more than one type of functional group along the same polymer backbone, e.g, polymerizable groups (HEMA) and active ingredient molecules, or two functional groups of a reactive pair (alkyne and azide for Click reaction), as described above. In addition, a mixture of two polyelectrolytes, each containing one reactive group of a reactive pair, can also produce polymer particles, e.g. alkyne-modified

PAA and azide-modified PAA. In one embodiment, modified polyelectrolytes can produce polymer particles. Figure 3 illustrates steps to produce these particles. These steps involve (a) modifying PAA with, e.g., HEMA, according to procedure described previously, generating a pH-sensitive polymer, (b) dissolving the HEMA-modified PAA in water at pH > 6, (c) lowering the pH (pH<6) of the solution and (d) cross-. The average size of polymer particles produced from this method ranges from 50 to 1000 nm. In some embodiments, particle size can be controlled by pH value. Large size occurred when pH value ranges from about 5 to about 6, and small size occurred when pH value ranges from about 3 to about 5.

10 *Loading Active Ingredients*

The polymer particles described in the present invention can be used to carry active ingredients. Some of the methods used to load the polymer particles with active ingredient involve dissolving the particles in a suitable solvent. In addition to it being possible to load the polymer nanoparticles if they are dissolved (e.g. found as discrete individual particles in the solvent), it is also possible to load the polymer nanoparticles if they are aggregated or in a dispersed form. In one embodiment, a method to associate active ingredients with polymer particles includes the steps of (a) dissolving the active ingredients and the dissolving or dispersing the polyelectrolyte particles in a suitable solvent, (b) removing the solvent. The resulting polymer particles with associated active ingredients can be further processed by a method including the steps of (c) re-suspending the particles in a desired solvent under suitable conditions, and optionally (d) recovering dry particles containing active ingredients from the solvent. In some embodiments, there may be an addition of an agent that can promote the association between the active ingredient and the nanoparticle. This agent can be a cross-linking agent, a coordinating agent, or an agent that modifies the chemical functionality of either the active ingredient or the nanoparticle, including changes in pH that change the charge or protonation state of the active ingredient or the nanoparticle.

In certain embodiments, the suitable solvent of step (a) is an organic solvent in which both the polyelectrolyte particles can be dissolved or dispersed and the active ingredient can be dissolved. Examples of suitable solvents include methanol, ethanol, and other polar hydrophilic solvents. In certain applications, where the active ingredient is desired to be suspended in water, the solvent in step (c) is an aqueous solvent or cosolvent. Suitable conditions for step (c) can include adjusting temperature, pH, ionic strength, or other solution conditions to effect re-suspending of the polymer particles with associated active ingredients.

For carboxy-based polymer particles containing active ingredients, the pH can be adjusted between about 5 to about 11, in some cases between about 7 to about 8. For other polyelectrolytes, suitable conditions to re-suspend them in aqueous solvents often include adjustment of pH such that enough of the ionizable groups on the polymers are ionized to allow them to re-suspend in the solvent. Step (d) is optionally used if the resulting particles need to be recovered as dry particles, this can be effected using freeze or spray drying, air drying, vacuum drying, or other approaches.

Polymer particles can be obtained from unmodified or modified polyelectrolytes, and prepared from the described procedures. They can contain metal ions, metal hydroxide or metal oxide. Their size can range from about 5 to about 300 nm. They can include only polymer particles with an empty interior, or can include cavities that may be dynamic. They can also be porous but not have discrete cavities. Alternately, they can be relatively densely packed but can be swollen or otherwise take up active ingredients.

In some embodiments, a different approach is used to associate polymer nanoparticles with active ingredients, including the steps of (a) dissolving or dispersing the polymer nanoparticles in a suitable first solvent, (b) swelling the polymer nanoparticles by adding a second solvent containing active ingredient, (c) removing the second solvent. An alternative method includes the steps of (a) dissolving or dispersing the polymer nanoparticles in a suitable first solvent, (b) swelling the polymer nanoparticles by adding a second solvent, (c) adding active ingredient, or alternatively adding additional second solvent that contains active ingredient, and (d) removing the second solvent. In certain embodiments, the first solvent can be hydrophilic and the second solvent can be more hydrophobic than the first solvent. In certain embodiments, the characteristics of the first solvent (temperature, pH, etc.) can be modified to make the polymer nanoparticles more or less hydrophilic or in a more extended or collapsed conformation. In certain embodiments, the first solvent can be aqueous. In certain embodiments, the pH of an aqueous solvent can be adjusted so that the polymer nanoparticles with ionizable groups are ionized. In certain embodiments, the pH of an aqueous solvent can be adjusted so that the polymer nanoparticles with ionizable groups are not ionized. As an example of this, a polymer nanoparticle with carboxy groups may be more susceptible to swelling under pH conditions that have the carboxy group in the acid form. In certain embodiments, the polymer nanoparticle can be dispersed in the first solvent or only partially soluble. In certain embodiments, the second solvent can be removed using evaporation, distillation, extraction, selective solvent removal, or dialysis. In certain embodiments, the second solvent has a vapor pressure higher than the first solvent. The amount of swelling of the polymer may be

dependent on the type of polymer nanoparticle. For example, a hydrophilic polymer nanoparticle's tendency to swell may be dependent on the characteristics of the second solvent. In certain embodiments, a hydrophilic polymer nanoparticle will be more swellable by a polar second solvent. In certain embodiments, a hydrophobic polymer nanoparticle will be more swellable by a hydrophobic solvent. It is also possible to enhance swelling by including chemical groups in the solvent and polymer nanoparticle that have an affinity for one another, e.g. carboxy and amine, acid and base, etc. Swelling of the polymer nanoparticles can be observed by changes in size of the particles as measured by light scattering, chromatography, cryogenic transmission electron microscopy, solution-based atomic force microscopy. Alternately, swelling of the polymer nanoparticles by an immiscible second solvent can be observed by disappearance of an observable second solvent phase due to partitioning of the solvent into the polymer nanoparticles. Swelling can also be observed by changes in viscosity. Swelling can also be observed by spectroscopy. As an exemplary embodiment, if the solvent carrying active ingredients imparts a spectral signature to the active ingredients, and that spectral signature is modified on incorporation with the polymer nanoparticle, this can demonstrate swelling and incorporation of the active ingredient. A molecule showing these characteristics is pyrene, which changes its emission characteristics depending on the hydrophobicity or hydrophilicity of its microenvironment.

Examples of suitable second organic solvents include, but are not limited to, methanol, ethanol, ethyl acetate, isopropanol, methoxy propanol, butanol, DMSO, dioxane, DMF, NMP, THF, acetone, dichloromethane, toluene, or a mixture of two or more of the solvents. Some of these solvents can be removed by evaporation. In some embodiments, the first solvent is miscible in the second solvent. In some embodiments, the first solvent and second solvent are partially miscible. In some embodiments, the first solvent and second solvent are immiscible.

In some embodiments, a different approach is used to associate polymer nanoparticles with active ingredients, including the steps of (a) dissolving or dispersing the polymer nanoparticles and dissolving the active ingredient in a suitable first solvent, (b) adding second solvent, (c) removing first solvent.

Examples of suitable first solvents include, but are not limited to, methanol, ethanol, isopropanol, methoxy propanol, butanol, DMSO, dioxane, DMF, NMP, THF, acetone, or a mixture of two or more of the solvents. These solvents can be removed by evaporation. In these embodiments, the second solvent is miscible in the first solvent, but poor solvent to active ingredients. The second solvent can be aqueous.

The active ingredients associated with the polymer nanoparticles can be dispersed throughout the polymer nanoparticle. They can also be enriched in regions of the polymer nanoparticle, either being predominantly on the surface of the polymer nanoparticle or predominantly contained within the polymer nanoparticle. If the polymer nanoparticle has one or more discrete cavities, the active ingredient can be contained within the cavities. A diagram illustrating the different methods used to load active ingredients is shown in Figure 7.

Formation of Surface-Active Agents of Active Ingredients

In various aspects, the present invention also provides methods of producing a surface-active agent of an active ingredient (e.g., surface-active, active ingredient). These surface-active active ingredients can be produced in a variety of means. In one embodiment, this would include the steps of (a) mixing a water-insoluble active ingredient containing a functional group with a water-soluble reagent containing a complementary reactive group (b) allowing the reaction to proceed to completion at room temperature or an elevated temperature with removal of side products if necessary, and optionally (c) removing the organic solvent if applied. If desired, a catalyst for the reaction can be used. Under certain conditions, the surface-active agent of an active ingredient has active properties as produced. Under other conditions, the surface-active agent of an active ingredient is only activated when there is a change in solution conditions, such as, e.g., pH, that can cause liberation of the active ingredient from the surface-active agent of the active ingredient.

The surface active agents of active ingredients can provide many functions. They can help increase the amount of active ingredient that can be loaded into a given formulation. They can also add stability to a given formulation due to their surface active agent characteristic. They can also be used as precursors or monomers to produce polymer particles that are loaded with active ingredients. They can also be used to load multiple active ingredients in a formulation, where one or both of the active ingredients are provided as a surface-active, active ingredient.

In various aspects, the present invention provides methods of producing a surface-active agent of active ingredient. These surface-active active ingredients can be produced in a variety of means, including chemical reaction between a water-soluble reagent and the water-insoluble active ingredient. In various embodiments, a chemical reaction between a functional group of a water-insoluble active ingredient with a complimentary group of a

water-soluble agent may be used. In various embodiments, the chemical reaction may be, but are not limited to, esterification.

An esterification reaction joins an alcohol group with a carboxylic acid groups, forming an ester bond. The esterification reaction conditions can be at room temperature or
5 an elevated temperature, in the presence or absence of organic solvents, in the presence or absence of a catalyst. In one embodiment, an esterification reaction can occur between a water-insoluble active ingredient containing a carboxylic acid moiety and a water-soluble agent containing an alcohol moiety. Reversibly, an esterification reaction can occur between
10 a water-soluble active ingredient containing a carboxylic acid moiety and a water-insoluble agent containing an alcohol moiety would also work.

Suitable active ingredients containing carboxylic acid group include but are not limited to herbicidal acid groups including benzoic acids, aryloxyphenoxypropionic acids, phenoxyacetic acids, phenoxypropionic acids, phenoxybutyric acids, picolinic acids, and quinolones drugs, and also include but are not limited to, cinoxacin, nalidixic acid, pipemidic
15 acid, ofloxacin, levofloxacin, sparfloxacin, tosufloxacin, clinafloxacin, gemifloxacin, moxifloxacin, gatifloxacin.

Suitable water-soluble agents include, but are not limited to suitably terminated poly(ethylene glycol) or poly(propylene glycol). In one embodiment, the esterification reaction occurred between the carboxylic acid of 2,4-dichlorophenoxyacetic acid ("2,4-
20 D") with the terminal alcohol group of methoxy-terminated poly(ethylene glycol), joining the hydrophobic 2,4-D molecule with the hydrophilic poly(ethylene glycol) through an ester bond formation, generating a surface-active agent of 2,4-D. In one embodiment, the esterification reaction was performed in toluene at reflux temperature in the presence of concentrated H_2SO_4 . In one embodiment, the esterification reaction was performed under silica gel
25 catalyst at 150 °C in the absence of an organic solvent.

Combination of Surface-Active Agents of Active Ingredients and Polymer Nanoparticles Including Active Ingredients

In various aspects, the surface-active active ingredient and the polymer-
30 nanoparticles including active ingredient can be used together to produce nanoparticles with increased loading of active ingredients and that are more stable as a dispersion. The surface-active active ingredients could be adsorbed onto nanoparticles. In various embodiments, this may include the steps of (a) synthesizing surface-active active

ingredients, (b) preparing polymer nanoparticles including active ingredients according to the present invention, (c) mixing the surface-active ingredients and a dispersion of polymer nanoparticles including active ingredients. Step (c) can be conducted in a variety of ways. Surface-active ingredients can be added directly to the nanoparticle dispersion. In various
5 embodiments, surface-active ingredients are first dissolved in water with a pH similar to that of the nanoparticle dispersions, and then added to the nanoparticle dispersion. In some embodiments, the reverse order of addition can be performed. In some embodiments, the pH of the dispersion and active ingredient solution may be between 5 and 9. The amount of surface-active ingredient that is added may be below the necessary concentration to form
10 separate micelles of surface-active ingredient that are not bound to the nanoparticles. In various embodiments, the surface-active ingredient can be added neat to the nanoparticle dispersion. In some embodiments, the surface-active ingredient can be added during the preparation of polymer nanoparticles including active ingredient.

15 *Polymers Formed From Active Ingredients*

In various aspects, the present invention provides methods of producing aqueous polymer solutions containing nanostructures including active ingredients. Aqueous polymer solutions containing nanostructures including active ingredients can be produced in a variety of ways. Examples include, but are not limited to, grafting an active ingredient onto an
20 existing water-soluble monomer, and copolymerizing randomly or controllably monomer containing active ingredient with monomer containing water-soluble moiety. In one embodiment, grafting an active ingredient onto an existing polymer would include the steps of (a) grafting an active ingredient onto an existing water-soluble polymer, and (b) dissolving the grafted polymers in a solvent. In some embodiments, this would include the steps of (a)
25 functionalizing the active ingredients, (b) grafting the active ingredients onto an existing water-soluble polymer, and (c) dissolving the grafted polymers in a solvent. In certain embodiments, the polymer is a polyelectrolyte which may or may not be capable of collapse.

The driving force behind the formation of nanostructures can be caused by one or more of: hydrogen bonding between water molecules being interrupted by the grafted active
30 ingredient; and/or the associative interaction among active ingredient groups. At a low polymer concentration, intramolecular interactions among active ingredient groups grafted on the same polymer chain can cause the polymer to collapse, forming nanoparticles. As the polymer concentration increases, intermolecular interactions of active ingredient groups from one collapsed polymer to an adjacent one can begin, bridging between two collapsed

polymers. As polymer concentrations further increase, the polymer chains can move closer to one another, and thus intermolecular interactions of active ingredient from one polymer chain to the adjacent one will dominate.

5 In some embodiments, nanoparticles can be formed by causing the polymer to collapse using the techniques described previously. In some embodiments, the polymer can include an uncharged polymer capable of collapse such as poly-(n-isopropylacrylamide) (NIPAM). The associative interaction among active ingredient groups can be intra- or intermolecular or a combination of both depending on concentrations of the polymers.

10 In some embodiments, grafting an active ingredient onto an existing polymer would include the steps of (a) functionalizing an active ingredient, i.e. monoesterification of 2,4-D with ethylene glycol, attaching a 2,4-D molecule to one end of a diol molecule, (b) grafting the synthesized active ingredient containing an alcohol group onto a carboxy-containing polymer via esterification reaction, and (c) dissolving the AI-graft polymers in water, forming nanostructures containing active ingredients.

15 In various embodiments, aqueous polymer solutions containing nanostructures including active ingredients can be produced by copolymerizing monomers containing active ingredient with monomers containing water-soluble moieties. Examples of monomers containing water-soluble moieties include, but are not limited to, N-isopropyl acrylamide (NIPAM), acrylate-terminated PEG, acrylic acid, methacrylic acid, 2-hydroxyethyl
20 methacrylate, styrene sulfonate, vinyl pyridine, allylamine, N,N-dimethylaminoethyl acrylate, N,N-dimethylaminoethyl methacrylate.

In some embodiments, an aqueous solution of random copolymer containing active ingredient could be produced using a process including the steps of (a) synthesizing a monomer containing active ingredient, (b) copolymerizing the synthesized monomer with a
25 monomer or mixture of monomers containing water-soluble moiety, and (c) dissolving the copolymer in water. Copolymerization conditions in Step (b) can be in an organic solvent at an elevated temperature in the presence of an initiator. In some embodiments, an aqueous solution of random copolymer containing active ingredient could be produced using a process including the steps of (a) synthesizing a monomer containing active ingredient, (b)
30 emulsion copolymerizing the monomer containing active ingredient with NIPAM at temperature above the low critical solution temperature of poly(NIPAM), forming copolymer particles containing active ingredient, (c) cooling the temperature of the reaction to room temperature. After cooling, the micron-scale polymer-active ingredient particles disintegrate,

the copolymers dissolve in water, and active ingredients on the same or adjacent polymers associate to form nanostructures.

In some embodiments, an aqueous solution of random copolymer containing active ingredient could be produced using a process comprising the steps of (a) synthesizing a monomer containing active ingredient, (b) emulsion copolymerizing the monomer containing active ingredient with methacrylic acid or acrylic acid at low pH, forming copolymer particles containing active ingredient, (c) and ionizing the carboxylic acid groups. Step (c) can alternately or additionally include cooling the system. The cooling or ionization steps causes the micro-scale polymer-active ingredient particles to disintegrate, the copolymers to dissolve in water, and active ingredients on the same or adjacent polymer chains to associate to form nanostructures.

In some embodiments, an aqueous solution of block copolymer containing active ingredient could be produced using a process including the steps of (a) synthesizing a monomer containing active ingredient, (b) adding a water-soluble macroinitiator, (c) polymerization of the synthesized monomer using the water-soluble macroinitiator, forming a block copolymer including one hydrophilic and one hydrophobic block. In an aqueous solution, the hydrophobic block of individual copolymers can associate, forming nanostructures including active ingredients.

20 The Use of Surface-Active Agents of Active Ingredients in Producing Polymer Particles

In various aspects, the surface-active agent of active ingredients may be used to increase active ingredients loading in the polymer solution containing nanostructures of active ingredient. Alternatively, the surface-active agent of active ingredients may be used to decrease the mean polymer diameter during the preparation of polymer particles.

25 Ultimately, the surface-active agent of active ingredients may be used to reduce viscosity of the polymer solution.

In one embodiment, this would include the steps of (a) synthesizing a monomer containing active ingredients, (b) synthesizing surface-active agent of active ingredient, (b) copolymerizing the monomer containing active ingredients with monomer containing ionic groups. The copolymerization can be an emulsion polymerization. In certain embodiments, the copolymerization can be an emulsion polymerization in water at low pH. The resulting polymer particles can then be ionized and dispersed in water, yielding an aqueous polymer

solution with polymer particles including nanostructures including active ingredients associated on the same or adjacent polymers.

EXAMPLES

5

Particle size and size distribution were measured using dynamic light scattering (DLS). The particle size was reported from at least an average of 25 measurements, and shown in volume percentage.

10 Viscosity was measured using Oswald viscometer at 21 °C. Viscosity of individual solution or dispersion was reported in time, which took the solution or dispersion traveled between two marks on the viscometer.

UV lamps were at 254nm.

Note that the nomenclature M_xN_y /PAA refers to a M_xN_y nanoparticle associated with poly(acrylic acid). The M_xN_y can also be an ion e.g. Zn^{2+} /PAA, in which case it refers to a
15 poly(acrylic acid) nanoparticle containing Zn^{2+} .

A. Formation of polymer nanoparticles using a combination of a common salt (NaCl) and UV treatment:

20 Example 1: Production of polymer nanoparticles by treating poly(acrylic acid) (PAA) solution with NaCl:

In a 250 mL beaker equipped with a magnetic stir bar, solid PAA (0.100 g, Mw = 450,000 Dalton) and deionized water (100g) were weighed. The solution was magnetically stirred until PAA completely dissolved, then the pH was adjusted to 9.63 using aqueous 1N NaOH.

25 To a separate beaker equipped with a magnetic stir bar, 50 g of the aqueous solution of PAA (0.1wt%) was transferred. While stirring, 5 mL of 3M NaCl was added dropwise. The solution remained transparent.

To two separate beakers equipped each with magnetic bars, 25 g aqueous PAA solution and 25 g aqueous PAA solution with NaCl were transferred. While stirring, the
30 solutions were exposed to UV lamps for 5 min.

Table 1: Summary results of viscosity and DLS measurements of PAA solution in the presence and absence of NaCl, with and without UV treatment.

	Viscosity (second)	DLS
PAA solution before UV treatment	681	N/A
PAA solution after UV treatment	468	N/A
PAA solution + NaCl before UV treatment	101	24 nm (99%)
PAA solution + NaCl after UV treatment	100	37 nm (13%) 10 nm (87%)
Deionized water	71	N/A

Example 2: Production of polymer nanoparticles by treating HEMA-modified PAA solution with NaCl

Synthesis of HEMA-modified PAA (low degree of HEMA grafting): To a 250 mL round bottom flask, solid PAA (3.0 g, Mw = 450,000 Dalton) and liquid DMSO (100 g) were transferred. The flask was magnetically stirred until PAA completely dissolved. Solid 4-(dimethylamino)pyridine (DMAP, 0.34 g) and liquid 2-hydroxyethyl methacrylate (HEMA, 10.8g) were transferred to the reaction flask. The reaction mixture was stirred until all DMAP was completely dissolved, then solid *N*-(3-Dimethylaminopropyl)-*N'*-ethylcarbodiimide hydrochloride (EDC, 0.53 g) was transferred. The reaction mixture was stirred at room temperature for 16 hours. After 16 hours, the mixture was added dropwise into a 1L beaker containing 700 mL 2-propanol, yielding a precipitate. The supernatant was discarded, and the precipitate was washed twice with 2-propanol (100 mL each). Removing residual 2-propanol under vacuum overnight yielded solid HEMA-modified PAA.

Preparation of aqueous HEMA-modified PAA solution (0.83 wt%): In a 100 mL beaker equipped with a magnetic stir bar, solid HEMA-modified PAA (0.332 g, Mw = 450,000 Dalton) and deionized water (40g) were weighed. While the mixture was stirring, the pH of the solution was kept constant around 8.0 by adding 1N NaOH solution. Basic pH would more quickly dissolve solid HEMA-modified PAA. After the solid polymer was completely dissolved, the solution was transparent and the pH of the solution was measured at 7.9.

PAA powder (16.6 mg, Mw=1800 D) and 133 mL DI water were added to above HEMA-modified PAA solution and stirred until the solution was transparent. The pH was 7.3.

NaCl solution (12.4 mL, 3M) was slowly added while being stirred by a magnetic stir bar. Then 2-hydroxy-2-methyl-propiophenone (1.8 mg, 97%) was added and stirred for 3h. The solution was UV-irradiated for 1 hour. The solutions, before and after UV-irradiation, were characterized by viscosity and particle size which were shown in Table 2.

5 The pH of above solution was then adjusted to 2, polymer particles were precipitated out of the solution. The precipitate was rinsed by DI water of pH 2 and centrifuged to remove supernatant. This was repeated for three times, and finally the precipitate was dissolved in water and pH was adjusted to 6.5.

10 **Table 2:** Summary results of viscosity and DLS measurements of HEMA-modified PAA solution in the presence and absence of NaCl, with and without UV treatment.

	Viscosity (cP)	DLS
HEMA-modified PAA solution before NaCl/UV treatment	4.8	N/A
	1.2	28 (22%)
HEMA-modified PAA + NaCl before UV treatment	1.0	7 (78%)
		24 (23%)
HEMA-modified PAA + NaCl after UV treatment		5 (77%)

B. Formation of polymer nanoparticles from a mixture of poly(acrylic acid) and a crosslinker and refluxing the mixture:

15 Example 3: Production of polymer nanoparticles from a mixture of poly(acrylic acid) and a crosslinker in the absence of an external salt: An aqueous solution (500 mL) of poly(acrylic acid) (Mw = 450,000 D) of 2 mg/mL was prepared in a 2 L beaker. The pH of the mixture was adjusted to 6.8 using aqueous NaOH (10 N). In another beaker (1L), solids 1,8-diaminohexane (0.4031 g) and reversed osmosis (RO) water (500 mL) were added. The
 20 diaminohexane was not completely dissolved. The pH of the mixture, monitored by a pH meter, was lowered to 3.70 using aqueous HCl (2N), and allowed to stir at room temperature for 30 minutes. The solution still contained few precipitates, which were removed by filtration through a double-layer kimwipe. The filtered diaminohexane mixture appeared transparent and was poured into the beaker containing the poly(acrylic acid) solution while the solution

was vigorously stirring. The result mixture was kept stirring for 1 h and the pH was measured at 5.80. The mixture (300 mL) was then transferred to a 500 mL one-neck reaction flask that was connected to a condenser. The reaction mixture was then refluxed for 24 hrs, allowing crosslinking reaction occurred. After 24 hrs, the reaction flask was cooled to room temperature and the pH was measured to be 5.96. Figure 8: TEM images of the PAA/1,8-diaminooctane mixture before and after refluxing for 24 hrs.

Example 4: Production of polymer nanoparticles from a mixture of poly(acrylic acid) and a crosslinker in the presence of an external salt: An aqueous solution of poly(acrylic acid) (Mw = 450,000 D, 500 mL, 2 mg/mL, pH 3.45) was prepared in a 2 L beaker. In another beaker (1L), solids 1,6-diaminohexane (0.3310 g) and reversed osmosis (RO) water (500 mL) were added. The diaminohexane was completely dissolved in minutes and the pH of the mixture was measured at 11.12. The aqueous diaminohexane was added to the poly(acrylic acid) solution with vigorous stirring for about 1 h. The pH of the mixture was measured to be 5.65, which was then increased to 6.47 by adding aqueous 2N NaOH (about 1 mL). A portion of this mixture (300 mL) was transferred to a 500 mL one-neck reaction flask and refluxed for 24 hrs. Another portion of the mixture (300 mL) was transferred to another 500 mL one-neck reaction flask and added dropwise with aqueous NaCl (2.5g of 3M NaCl + 17.5 g RO water) with vigorous stirring. The pH of the mixture was measured of 6.03, and brought to refluxing for 24 hrs. Figure 9: TEM images of PAA/1,6-diaminohexane after refluxed in the absence and presence of NaCl.

C. Formation of polymer nanoparticles with hollow structure and cavities using an inorganic metal salt and crosslinking followed by etching the resulting metal oxide / hydroxide:

Example 5: Production of polymer nanoparticles with hollow structure and cavities by treating poly(acrylic acid) solution with $\text{Al}(\text{NO}_3)_3$ (Figure 1)

Preparation of aluminum hydroxide-encapsulated PAA nanoparticles: $\text{Al}(\text{NO}_3)_3$ aq. solution (25 mM, 300 mL) was loaded in a 1 L beaker (A) equipped with a magnetic stirrer, NaOH aq solution (100 mM, 145 mL) was added slowly into the beaker by a feeding pump. Another 1 L beaker (B) was charged with polyacrylic acid aqueous solution (Mw = 450 KD, pH 7, 4 mg/mL, 300 mL) and stirred by a magnetic stirrer. The solution from the beaker (A) was slowly added into the beaker (B) by a feeding pump over 3 hours, meanwhile the pH of the solution in the beaker (B) was maintained to 7 by continuously adding NaOH aq solution (100 mM). The obtained solution was UV irradiated under an UV lamp (252 nm) for 2 hours

under stirring condition. The solution was sonicated for 10 min by using a VirSonic sonicator (at power of 50%), and then was adjusted to pH 8.5 by adding NaOH aq solution (100 mM). The above solution was concentrated 10 times by a rotary evaporator ("rotovap"). The formed PAA-encapsulated $\text{Al}(\text{OH})_3$ particles were precipitated out by adding NaCl/ethanol solution. The precipitate was centrifuged and rinsed 3 times by 70 % ethanol. The precipitate was re-suspended in DI water and freeze-dried to obtain a dry powder. The PAA-encapsulated $\text{Al}(\text{OH})_3$ particles were characterized by DLS and the average size was determined to be 20 nm.

Crosslinking reaction by EDC: PAA/ $\text{Al}(\text{OH})_3$ aq solution (5 mg/mL, 500 mL) was loaded in a 2 L beaker equipped with a magnetic stirrer. A solution of 2, 2'-(ethylenedioxy)bis(ethylamine) (2.5 mmol, 0.3705 g in 50 mL DI water) was slowly added at 0.5 mL/min feeding rate to above stirred solution. The solution was allowed to stir for another 2 hours at room temperature. Then to this mixture was added slowly a solution of 1-Ethyl-3-[3-dimethylaminopropyl]carbodiimide hydrochloride (0.985 g in 500 mL DI water) over 12 hours. The reaction mixture was allowed to stir overnight. The crosslinked polymer/inorganic particles were precipitated out by adding NaCl/ethanol solution. The precipitate was centrifuged out and rinsed 3 times by 70 % ethanol. The precipitate was re-suspended in DI water.

Removal of aluminum hydroxide particles: To a stirred aqueous solution of the crosslinked polymer/inorganic particle (15 mg/mL), was added HCl solution (2 N) until the pH reached 1.5. The obtained transparent solution was transferred into a dialysis tubing (Spectra/Por dialysis membrane, MWCO 12-14,000), and dialyzed against DI water at pH of 1.5 for 3 days with 3 water changes per day. The dialyzed solution was adjusted to pH of 8.5 by adding NaOH (0.5 N), and then dialyzed against DI water for one day with 3 water changes. The obtained solution was freeze-dried to obtain dry powder of polymer capsules. The polymer capsules were characterized by DLS, and the average size was determined to be 20 nm.

Figure 13 shows AFM images of (A) a PAA polymer particle including aluminum hydroxide nanoparticles, and (B) the polymer particles of (A) after aluminum hydroxide has been removed. The PAA containing aluminum hydroxide particles appeared to be larger and harder than those after aluminum hydroxide particles were removed. Figure 10 C also shows TEM image of the PAA particles after removing aluminum hydroxide particles.

D. Formation of polymer particles by a combination of acidification and UV/visible light treatment :

Example 6: Production of polymer particles by treating HEMA-modified poly(acrylic acid) with acid

5 Synthesis of HEMA-modified PAA (high degree of HEMA grafting): To a 250 mL round bottom flask, solid PAA (2.0 g, Mw = 450,000 Dalton) and liquid DMSO (100 g) were added. The flask was magnetically stirred until PAA completely dissolved. Solid 4-(dimethylamino)pyridine (DMAP, 0.34 g) and liquid 2-hydroxyethyl methacrylate (HEMA, 21.7 g) were added to the reaction flask. The reaction mixture was stirred until all DMAP
10 was completely dissolved, then solid *N*-(3-Dimethylaminopropyl)-*N'*-ethylcarbodiimide hydrochloride (EDC, 2.67 g) was added. The reaction mixture was stirred at room temperature for 16 hours. After 16 hours, the mixture was added dropwise into a 1L beaker containing 900 mL deionized water, yielding a precipitate. The supernatant was discarded, and the precipitate was washed twice with deionized water (500 mL each). The precipitate
15 was redissolved in deionized water (400 mL) with the aid of standard 0.100N NaOH (118 mL) which resulted the transparent solution with solids content of 0.73 wt% and pH of 9.75. From these results, the extent of HEMA grafting was calculated and obtained a value of 27 mol%.

Preparation of aqueous HEMA-modified PAA solution (0.2 wt%): In a 250 mL beaker
20 equipped with a magnetic stir bar, 27.4 g of HEMA-modified PAA solution (0.73 wt%) and deionized water (72.6g) were weighed. The resulting mixture appeared transparent and had a pH of 8.90. While the mixture was stirring, aqueous HCl (0.1N) was added dropwise. The transparent solution became translucent at pH of around 6.5 and then opaque at 6.03. The opaque nature indicated that polymer particles of large size were forming. The polymer
25 particles were characterized by DLS, and the average size was determined to be 211 nm (100% volume intensity).

Crosslinking of HEMA-modified PAA particles by UV and visible light: A portion (5 mL) of the opaque mixture was transferred to 4 vials. To one vial was added a tiny amount of a UV photoinitiator (2-hydroxy-2-methylpropiophenone, HMPP, 0.00088 g). Visible light
30 photoinitiators, Benzil (0.00137 g) and camphorquinone (0.0021 g), were added to the second and third vial. The fourth vial did not contain any photoinitiator. All 4 vials were capped, wrapped in an aluminum foil, and stirred at room temperature over 16 hours. The vial not having a photoinitiator and the vial containing the UV photoinitiator were uncapped

and exposed to UV lamp for 5 minutes. The other two vials were purged with nitrogen gas for 5 minutes and exposed to sun lamp for 10 minutes.

Table 3: Summary results of DLS measurements of polymer particles after exposed to radiation

	control	no initiator (UV)	HMPP (UV)	Benzil (visible)	Camphorquinone (visible)
pH 6.03	211 nm (100%)	269 nm (100%)	194 nm (100%)	330 nm (100%)	210 nm (100%)
adjusted to pH 10	 N/A	 N/A	 203 nm (100%)	 372 nm (100%)	 313 nm (100%)

Example 7: Production of polymer particles by treating a mixture of azide-modified PAA and alkyne-modified PAA with acid

10 Synthesis of 3-azidopropanol: In a 100 mL round bottom flask, liquid 3-chloropropanol (10.0 g, 1.0 equiv), solid sodium azide (17.19 g, 2.5 equiv) were reacted in DMF for 40 hours at 100 °C. The reaction mixture was cooled to room temperature, poured into a reparatory funnel and extracted with diethyl ether (300 mL) and brine solution (500 mL). The organic layer was separated and dried over MgSO₄. Rotary evaporation removed
15 the diethyl ether solvent at room temperature and yielded crude 3-azidopropanol (12.5 g).
¹H-NMR (δ, ppm) CDCl₃: 3.76 – 3.73 (t, 2H, HOCH₂CH₂CH₂N₃), 3.46 – 3.43 (t, 2H, HOCH₂CH₂CH₂N₃), 2.09 (br-s, 1H, OH), 1.86 – 1.80 (m, 2H, HOCH₂CH₂CH₂N₃). IR neat (cm⁻¹): 2100 (N=N=N).

Synthesis of N₃-modified PAA: To a 250 mL round bottom flask, solid PAA (2.0 g, Mw = 450,000 Dalton) and liquid DMSO (100g) were added. The flask was magnetically stirred until PAA completely dissolved. Solid 4-(dimethylamino)pyridine (DMAP, 0.34 g) and crude liquid 3-azidopropanol (12.5 g) were added to the reaction flask. The reaction mixture was stirred until all DMAP was completely dissolved, then solid *N*-(3-Dimethylaminopropyl)-*N*-ethylcarbodiimide hydrochloride (EDC, 2.67 g) was added. The reaction mixture was stirred at room temperature for 16h. After 16 hours, the mixture was added dropwise into a 1L beaker containing 900 mL deionized water, yielding a precipitate. The supernatant was discarded, and the precipitate was washed twice with deionized water (500mL each). The precipitate was redissolved in deionized water (400 mL) with the aid of 0.1N NaOH, and yielded a transparent solution with solids content of 0.78 wt% and pH of 9.70.

Synthesis of alkyne-modified PAA: To a 250 mL round bottom flask, solid PAA (2.0 g, Mw = 450,000 Dalton) and liquid DMSO (100 g) were added. The flask was magnetically stirred until PAA completely dissolved. Solid 4-(dimethylamino)pyridine (DMAP, 0.34 g) and liquid propargyl alcohol (9.34 g) were added to the reaction flask. The reaction mixture was stirred until all DMAP was completely dissolved, then solid *N*-(3-Dimethylaminopropyl)-*N*-ethylcarbodiimide hydrochloride (EDC, 2.67 g) was added. The reaction mixture was stirred at room temperature for 16 hours. After 16 hours, the mixture was added dropwise into a 1L beaker containing 900 mL deionized water, yielding a precipitate. The supernatant was discarded, and the precipitate was washed twice with deionized water (500 mL each). The precipitate was redissolved in deionized water (600 mL) with the aid of 0.1N NaOH, and yielded a transparent solution with solids content of 0.50 wt% and pH of 9.75.

Preparation of polymer particle from a mixture of N₃-modified PAA/alkyne-modified PAA and crosslinking reaction using CuSO₄/sodium ascorbate as the catalyst:

To a 250 mL beaker equipped with a stir bar, N₃-modified PAA aqueous solution (12.85 g of 0.78 wt%), alkyne-modified PAA aqueous solution (20.04 g of 0.50 wt%) and deionized water (167.11 g) were weighed. The result mixture contained 0.1 wt% of polymers with a pH value of 8.03 and a viscosity of 359 second. 50 mL of the mixture was transferred to a 100 mL beaker equipped with a stir bar. While stirring and monitoring the pH by a pH meter, aqueous HCl (1N) was added dropwise to the beaker. The transparent solution became translucent at around pH 6.2 and then opaque at around 5.7. Acidifying was stopped; viscosity of the dispersion and particle size were measured. DLS measurement determined the average particle size was 128 nm (100% volume intensity), and the viscosity was 68 second at 22 °C.

The opaque mixture (25 g) was transferred to a 50 mL beaker along with a stir bar. Freshly prepared CuSO_4 (0.050g of 0.063 M), and sodium ascorbate (0.050g of 0.16 M) were added to the mixture. The reaction mixture was stirred for 16 hours at room temperature. DLS measurements of the reacted mixture showed the average particle size was 142 nm (100% volume intensity). Increasing the pH of the dispersion to 10, the opaque mixture remained opaque, while the average particle size increased to 222 nm (100% volume intensity). Unlike the sample not treated with CuSO_4 /sodium ascorbate, the opaque mixture became transparent as the pH of the dispersion increased above 6.5. The results indicate that the presence of CuSO_4 /sodium ascorbate reagents catalyzed the crosslinking reaction between the azide and alkyne groups, and thus locked in polymer particle structure.

E. Formulation of polymer nanoparticles associated with active ingredients:

Example 8: Loading Picloram using polymer particles

2.5 mL methanol, 8.9 mg polymer particles prepared according to Example 3, and 20.64 mg Picloram (4-amino-3,5,6-trichloro-2-pyridinecarboxylic acid) were mixed in a 10 mL glass vial. The pH of the solution was maintained at 2 by adding 2 N HCl solution. The above solution was vortexed until it became transparent. The methanol was removed by evaporation. 2 mL DI water was added to dried mixture, and pH of the solution was maintained at 8 by adding 0.5 N NaOH solution. The solution was vortexed until it was transparent. This solution was freeze-dried to obtain dry powder of polymer particles loaded with Picloram. The amount of Picloram retained in each step was measured using UV-Vis spectroscopy.

Example 9: Loading Imazethapyr using polymer particles

1 mL methanol, 6.8 mg polymer particles prepared according to Example 3, and 10 mg Imazethapyr (2-[4,5-dihydro-4-methyl-4-(1-methylethyl)-5-oxo-1H-imidazol-2-yl]-5-ethyl-3-pyridinecarboxylic acid) were mixed in a 5 mL glass vial. The pH of the solution was maintained at 2 by adding 2 N HCl solution. The above solution was vortexed until it became transparent. The methanol was removed by evaporation. 1 mL DI water was added to dried mixture, and pH of the solution was maintained at 8 by adding 0.5 N NaOH solution. The solution was vortexed until it was transparent. This solution was freeze-dried to obtain

dry powder of polymer particles loaded with Imazethapyr. The amount of Imazethapyr retained in each step was measured using UV-Vis spectroscopy.

Example 10: Loading Thifensulfuron-methyl using polymer particles

8 mL methanol, 2.1 mg polymer particles prepared according to Example 3, and 18.2 mg Thifensulfuron-methyl (methyl 3-[[[(4-methoxy-6-methyl-1,3,5-triazin-2-yl)amino]carbonyl]amino]sulfonyl]-2-thiophenecarboxylate) were mixed in a 10 mL glass vial. The pH of the solution was maintained at 2 by adding 2 N HCl solution. The above solution was vortexed until it became transparent. The methanol was removed by evaporation. 1 mL DI water was added to dried mixture, and pH of the solution was maintained at 8 by adding 0.5 N NaOH solution. The solution was vortexed until it was transparent. This solution was freeze-dried to obtain dry powder of polymer particles loaded with Thifensulfuron-methyl. The amount of Thifensulfuron-methyl retained in each step was measured using UV-Vis spectroscopy.

Example 11: Loading Thiamethoxam using polymer particles

4 mL methanol, 3.1 mg polymer particles prepared according to Example 3, and 28.5 mg Thiamethoxam were mixed in a 10 mL glass vial. The pH of the solution was maintained at 2 by adding 2 N HCl solution. The above solution was vortexed until it became transparent. The methanol was removed by evaporation. 1 mL DI water was added to dried mixture, and pH of the solution was maintained at 8 by adding 0.5 N NaOH solution. The solution was vortexed until it was transparent. This solution was freeze-dried to obtain dry powder of polymer particles loaded with Thiamethoxam. The amount of Thiamethoxam retained in each step was measured using UV-Vis spectroscopy.

Example 12: Loading Thiamethoxam using polymer particles

4 mL methanol, 3.1 mg polymer particles prepared according to Example 1, and 28.5 mg Thiamethoxam (3-[(2-chloro-5-thiazolyl)methyl]tetrahydro-5-methyl-*N*-nitro-4*H*-1,3,5-oxadiazin-4-imine) were mixed in a 10 mL glass vial. The pH of the solution was maintained at 2 by adding 2 N HCl solution. The above solution was vortexed until it became transparent. The methanol was removed by evaporation. 1 mL DI water was added to dried mixture, and pH of the solution was maintained at 8 by adding 0.5 N NaOH solution. The

solution was vortexed until it was transparent. This solution was freeze-dried to obtain dry powder of polymer particles loaded with Thiamethoxam. The amount of Thiamethoxam retained in each step was measured using UV-Vis spectroscopy.

5 Example 13: Loading Thiamethoxam using HEMA-modified PAA (NaCl and UV treated)

4 mL methanol, 3.2 mg HEMA-modified PAA prepared according to Example 4, and 28.4 mg Thiamethoxam (3-[(2-chloro-5-thiazolyl)methyl]tetrahydro-5-methyl-*N*-nitro-4*H*-1,3,5-oxadiazin-4-imine) were mixed in a 10 mL glass vial. The HEMA-modified PAA was treated with UV radiation in the presence of NaCl. The pH of the solution was maintained at
10 2 by adding 2 N HCl solution. The above solution was vortexed until it became transparent. The methanol was removed by evaporation. 2 mL DI water was added to dried mixture, and pH of the solution was maintained at 8 by adding 0.5 N NaOH solution. The solution was vortexed until it was transparent. This solution was freeze-dried to obtain dry powder of HEMA-modified PAA loaded with Thiamethoxam. The amount of Thiamethoxam retained in
15 each step was measured using UV-Vis spectroscopy.

Example 14: Slow release of Thiamethoxam ("TMX") from polymer nanoparticles

10 mg of solid nanocapsule formulation prepared from Example 9, and 20 mL DI water were added to a 50 ml glass vial (with a sealing cape). Slow release testing was timed
20 upon addition of DI water. The above solution was then continuously pumped through a Minimate Tangential Flow Filtration capsule (TFF, 3K, Omega membrane, PALL). The testing device is shown in the Figure 10A below. Samples from the release medium were collected from permeate at 0.2 ml at the required time intervals, the rest of permeate was returned back to the glass vial immediately.

25 All the samples taken were diluted by DI water to appropriate concentration of TMX, and then analyzed by UV-vis to quantify its concentration of TMX from a calibration curve of TMX in water. The slow release rate at specific testing time was calculated based on the quantification of TMX in the samples taken during the test, which was demonstrated by plotting the %release as function of the respective time point. The typical slow release
30 characteristics was shown in the Figure 10B.

Example 15: Loading Atrazine using HEMA-modified PAA particles

50 μ L ethyl acetate, 1.2 mg polymer particles prepared according to Example 2, and 1 mL DI water were mixed in a 5 mL glass vial. The pH of the solution was measured at 3. The above solution was stirred until oil phase disappeared. Then 120 μ L ethyl acetate solution of Atrazine (6-chloro-*N*-ethyl-*N'*-(1-methylethyl)-1,3,5-triazine-2,4-diamine, Atrazine concentration in solution: 22 mg/mL) was added and stirred until oil phase disappeared. The ethyl acetate was removed by evaporation to form a suspension. This solution was freeze-dried to obtain dry powder of polymer particles loaded with Atrazine. The amount of Atrazine retained in each step was measured using UV-Vis spectroscopy.

Example 16: Loading Thiamethoxam using HEMA-modified PAA particles

100 μ L ethyl acetate, 1.2 mg polymer particles prepared according to Example 2, and 1 mL DI water were mixed in a 5 mL glass vial. The pH of the solution was measured at 3. The above solution was stirred until oil phase disappeared. Then 6.5 mg Thiamethoxam (TMX, 95%) was added and stirred until TMX disappeared. The ethyl acetate was removed by evaporation to form a suspension. This solution was freeze-dried to obtain dry powder of polymer particles loaded with TMX. The amount of TMX retained in each step was measured using UV-Vis spectroscopy.

Example 17: Loading Azoxystrobin using HEMA-modified PAA particles

11.32 mg polymer particles prepared according to Example 2, 5.9 mg Azoxystrobin (methyl α E)-2-[[6-(2-cyanophenoxy)-4-pyrimidinyl]oxy]- α -(methoxymethylene) benzeneacetate) and 4 mL Methanol were mixed in a 10 mL glass vial. The pH of the solution was 3. 8.15 g water was slowly added (0.119 mL/min) under stirring condition. The methanol was removed by evaporation to form a suspension. This solution was freeze-dried to obtain dry powder of polymer particles loaded with Azoxystrobin. The amount of Azoxystrobin retained in each step was measured using UV-Vis spectroscopy.

Example 18: Loading Azoxystrobin using PAA particles

3 mL methanol, 11.0 mg polymer particles prepared according to Example 3, and 5.3 mg Azoxystrobin were mixed in a 10 mL glass vial. The above solution was vortexed until it became transparent. The methanol was removed by evaporation. 5 mL DI water was added

to dried mixture, and pH of the solution was adjusted to 7 by adding 0.5 N NaOH solution. The solution was stirred to form a suspension. This solution was freeze-dried to obtain dry powder of polymer particles loaded with Azoxystrobin. The amount of Azoxystrobin retained in each step was measured using UV-Vis spectroscopy.

5

Example 19: Loading Azoxystrobin using PAA particles

12.8 mg polymer particles prepared according to Example 3, 6.0 mg Azoxystrobin and 4 mL Methanol were mixed in a 10 mL glass vial. The pH of the solution was measured at 3. 6.0 g water was slowly added (0.119 mL/min) under stirring condition. The methanol was removed by evaporation to form a suspension. This solution was freeze-dried to obtain dry powder of polymer particles loaded with Azoxystrobin. The amount of Azoxystrobin retained in each step was measured using UV-Vis spectroscopy.

10

F. Polyelectrolytes collapsed with active ingredients:

15 Example 20: Production of nanoparticles of 2,4-dichlorophenoxyacetic acid (2,4-D) coated with cationic poly(allylamine)

Solid 2,4-dichlorophenoxyacetic acid (2,4-D) (0.158 g, 0.72 mmol) and fresh deionized water (50mL) were added to a 100 mL glass beaker, along with a stir bar. The medium was connected to a pH meter and the reading was at 2.76. To the stirring dispersion, aqueous NaOH (10N) was added dropwise. As the pH increased, more solid 2,4-D dissolved the dispersion became more transparent. Eventually, all of the solid 2,4-D dissolved completely, and the solution appeared transparent. The pH and viscosity of the solution was measured at 10.76 and 0.93 cP at 25.4 °C. For the reference, the viscosity of pure water was measured using the same instrument and shown a value of 0.92 cP at 26.4 °C.

20

25

In a different beaker (250 mL) equipped with a magnetic stir bar, solid poly(allylamine) (PAH, $M_w = 70,000$) (0.5 g, 5.5 mmol) and 50 mL of deionized water were added, yielding aqueous PAH solution of 1 wt%. The solution appeared clear with pH value of 3.47 and viscosity of 3.00 cP at 26.0 °C. Then, the aqueous 2,4-D solution was fed to the stirring PAH solution via a feeding pump, producing nanoparticles of active ingredient coated with PAH. It took about 15 minutes to complete the addition. The nanoparticle dispersion appeared light yellow transparent. The pH and viscosity of the dispersion were measured and shown to have a value of 4.79 and 1.69 cP at 25.1 °C. Note that the final concentration

30

of PAH in the nanoparticle dispersion is half of the original solution. For comparison, the viscosity of PAH at this concentration was prepared, measured and obtained with a value of 2.25 cP at 24.6 °C, a value that is higher than that of the collapsed nanoparticles (1.69 cP at 25.1 °C). The result of the viscosity measurements indicated that PAH polymers collapsed from the extended configuration when charged 2,4-D was added. In addition, dynamic light scattering (DLS) analyzed by volume intensity distribution showed the mean diameter of the collapsed particles was about 7 nm.

Example 21: Production of nanoparticles of 2,4-dichlorophenoxy acetic acid (2,4-D) coated with cationic poly(diallyldimethylammonium chloride) (PDDA)

Solid 2,4- dichlorophenoxyacetic acid (2,4-D) (16.0g, 72.4mmol) was ground to fine powder before being transferred to a 2L glass beaker. Fresh deionized water (1L) was measured by a 1L graduate cylinder and transferred to the beaker, along with a stir bar. The medium was connected to a pH meter and the reading was at 2.60. To the stirring dispersion, 10N of aqueous NaOH was added dropwise. As the pH increased, more solid 2,4-D dissolved the dispersion became more transparent. Eventually, all of the solid 2,4-D dissolved completely (about 7mL of 10N NaOH was added), and the solution appeared transparent. The pH of the solution was 7.44.

In a different beaker (4L) equipped with a mechanical stirrer, cationic poly(diallyldimethylammonium chloride) (PDDA) (146.3g of 20 wt% PDDA (29.26g solids PDDA, 181.0 mmol) and 854 mL of deionized water were transferred. The solution appeared transparent. The pH was measured at 4.74. The aqueous 2,4-D solution was fed to the stirring PDDA solution via a feeding pump. It took about 3.5 hrs to complete the addition. The mixture appeared transparent and contained 8.0 g/L of active ingredient (2,4-D). The pH was measured at 6.35 and the viscosity was at 6.75 cP at 26.0 °C. Note that the final concentration of PDDA in the nanoparticle dispersion is half of the original solution. For comparison, the viscosity of PDDA this concentration was prepared, measured and obtained with a value of 9.32 cP at 25.3 °C, a value that is higher than that of the collapsed nanoparticles (6.75 cP at 26.0 °C). The result of viscosity measurements suggested that PDDA polymers collapsed from the extended configuration when charged 2,4-D was added. In addition, dynamic light scattering (DLS) analyzed by volume intensity distribution showed the mean diameter of the collapsed particles was about 7 nm.

Example 22: Production of nanoparticles of 2,4-dichlorophenoxy acetic acid (2,4-D) coated with cationic low molecular weight chitosan polymer

Solid 2,4- dichlorophenoxyacetic acid (2,4-D) (18.0g, 81.4 mmol) was ground to fine powder before transferred to a 2L glass beaker. Fresh deionized water (1062 mL) was measured by a 1L graduate cylinder and transferred to the beaker, along with a stir bar. The medium was connected to a pH meter and the pH was 2.56. To the stirring dispersion, 10N of aqueous NaOH was added dropwise. As the pH increased, more solid 2,4-D dissolved the dispersion became more transparent. Eventually, all of the solid 2,4-D dissolved completely (about 8 mL of 10N NaOH was added), and the solution appeared transparent. The pH of the solution was measured at 7.60.

In a different beaker (4L) equipped with a mechanical stirrer, solid chitosan (low molecular weight, 32.9 g, 204 mmol) and 1062 mL of deionized water were transferred. The solution appeared light yellow with low viscosity due to incompletely dissolved chitosan. Liquid acetic acid (11.0 g, 183 mmol) was added dropwise to the chitosan dispersion. The viscosity of the dispersion increased drastically as the acetic acid was added. The dispersion was kept stirring for about 1 hour until all solid chitosan was completely dissolved. Then, the aqueous 2,4-D solution was fed to the stirring chitosan solution via a feeding pump. During the addition, the solution began to foam. The addition of 2,4D solution was completed in about 3.5 hours. The mixture appeared light yellow transparent. The solution remained at room temperature overnight so allow the foam to migrated to the surface. The next days, foams were removed. The pH and viscosity were 5.16 and 17.4 cP at 23.4 °C, respectively. For comparison, the viscosity of low molecular weight chitosan alone at this concentration was 23.3 cP at 24.0 °C, a value that is higher than that of the collapsed nanoparticles (17.4 cP at 23.4 °C). The result of the viscosity measurement indicates that the chitosan polymers collapsed from their extended configuration when 2,4-D was added. Dynamic light scattering (DLS) analyzed by volume intensity distribution showed the mean diameter of the collapsed particles to be about 4 nm.

Example 23: Plant treatment using active ingredient associated with polymer nanoparticles

Aqueous polymer nanoparticles containing 2,4-D prepared in Example 20 were directly used for plant treatment. The 2,4-D concentration in this formulation is 8 g/L. Two active concentrations (8 g/L and 4 g/L) were used for testing on plants. Plants were grown in trays for 2 weeks prior to treatment and organized in a randomized block design during the treatment. One tray consisted of 6 plants (barley, barnyard grass, lambsquarters, red-root

pigweed, low cudweed and field mint), which represent various crop and weed species. The treatment was applied by misting plants with a mist bottle, calibrated by apply the spay solution at a rate equivalent to 200 liters per hectare. Visual phytotoxicity (% plant damage) rating was taken at 4, 8, 12 and 15 days after treatment. Ratings were entered into a statistical software program and analysis of variance was run on the data. Mean separation was performed when analysis of variance suggested significant differences between treatments.

Two aqueous solutions containing the same amount (8 g/L and 4 g/L) of 2,4-D prepared without chitosan polymers was used as the controls for comparison.

The result shows that the formulation containing nanoparticles of chitosan collapsed by 2,4-D provided slightly increased levels of plant damage as compared to the control.

Example 24: Production of nanoparticles of 2,4-dichlorophenoxy acetic acid (2,4-D) coated with cationic high molecular weight chitosan polymer

Solid 2,4- dichlorophenoxyacetic acid (2,4-D) (8.0 g, 36.2 mmol) was ground to a fine powder before it was transferred to a 2L glass beaker. Fresh deionized water (1L) was measured by a 1L graduate cylinder and transferred to the beaker, along with a stir bar. The medium was connected to a pH meter and the reading was 2.76. To the stirring dispersion, 10N of aqueous NaOH was added dropwise. As the pH increased, more of the solid 2,4-D dissolved and the dispersion became more transparent. Eventually, all solid 2,4-D dissolved completely, and the solution appeared transparent. The pH of the solution was 8.50.

In a different beaker (4L) equipped with a mechanical stirrer, solid chitosan (high molecular weight, 14.6 g, 90.5 mmol) and 1L of deionized water were added. The solution appeared light yellow with low viscosity due to incompletely dissolved chitosan. Liquid acetic acid (4.89 g, 81.4 mmol) was added dropwise to the chitosan dispersion. The viscosity of the dispersion increased drastically as the acetic acid was added. The dispersion was kept stirring for about 2 hours until all solid chitosan was completely dissolved. Then, the aqueous 2,4-D solution was fed to the stirring chitosan solution via a feeding pump. During the addition, the solution began to foam. The addition of 2,4D solution was completed in about 3.5 hours. The mixture appeared light yellow transparent. The solution remained at room temperature overnight so allow the foam to migrated to the surface. The next day, the foam were removed. The pH and viscosity were 5.16 and 46.3 cP at 23.3°C, respectively. For comparison, the viscosity of high molecular weight chitosan alone at this concentration

was 64.3 cP at 23.4°C, a value higher than that of the collapsed nanoparticles (46.3 cP at 23.3°C). The viscosity measurements suggest that chitosan polymers collapsed from their extended configuration when charged 2,4-D was added. In addition, dynamic light scattering analyzed by volume intensity distribution showed the mean diameter of the collapsed particles was about 4 nm.

Example 25: Production of nanoparticles of glyphosate coated with cationic PDDA.

Solid glyphosate (*N*-(phosphonomethyl)glycine) (8.0g, 94.6 mmol), and fresh deionized water (1L) were added to a 2L beaker along with a stir bar. The medium was connected to a pH meter and the reading was 2.20. To the stirring dispersion, aqueous NaOH (50 wt%) was added dropwise. As the pH increased to 3, all of the solid glyphosate completely dissolved, and the dispersion became clear. Aqueous NaOH (50 wt%) was added until the pH of the medium reached 7.2.

In a different beaker (4L) equipped with a mechanical stirrer, cationic poly(diallyldimethylammonium chloride) (PDDA) (191 g of 20 wt% PDDA in water, 237 mmol) and 819 mL of deionized water were transferred. The solution appeared transparent. The pH was 4.74. The aqueous glyphosate solution was fed to the stirring PDDA solution via a feeding pump. The addition of 2,4D solution was completed in about 3.5 hours. The mixture appeared transparent and contained 4.0g/L of active ingredient (glyphosate) with a pH of 6.75 and a viscosity of 7.42 cP at 24.0 °C. In addition, dynamic light scattering (DLS) analyzed by volume intensity showed 2 distributions with the mean diameters of the collapsed particles at 2 nm (67%) and 8 nm (33%).

G. Synthesis of surface-active agent of active ingredients, their formulations, and their uses in the increase loading of active ingredients in nanoparticles collapsed by active ingredients:

Example 26: Esterification of 2,4-D with Carbowax MPEG 350 (supplied from Dow, methoxy-terminated poly(ethylene glycol), Mn = 350) using toluene as the solvent, concentrated H₂SO₄ as the catalyst.

Solid 2,4-D (3.0g, 13.6mmol), liquid Carbowax MPEG 350 (5.0g, 14.3mmol), toluene (150mL) were added to a 250mL round bottom flask along with a stir bar. The reaction flask

was connected to a Dean-Stark trap and a condenser. The reaction mixture was refluxed for 24 hours and then cooled to room temperature. Thin layer chromatography using a mixture of ethyl acetate and toluene (50/50, v/v) as the mobile solvent was used to check for the completion of the reaction. Toluene was removed by rotary evaporator, yielded a slight yellow liquid of surface-active agent of the 2,4-D active ingredient. Residual toluene was further removed by a vacuum pump. ¹H-NMR (300 MHz, D₂O): δ 3.38 (s, 3H, CH₃-(OCH₂CH₂)_n-OCH₂CH₂-O(O)C-), 3.36 – 3.73 (m, PEG, -(CH₃-(OCH₂CH₂)_n-OCH₂CH₂-O(O)C-), 4.36 (t, 2H, CH₃-(OCH₂CH₂)_n-OCH₂CH₂-O(O)C-), 6.81 (d, 1H, aromatic-H), 7.18 (dd, 1H, aromatic-H), 7.38 (d, 1H, aromatic H).

10

Example 27: Esterification of 2,4-D with Carbowax MPEG 750 (supplied from Dow, methoxy-terminated poly(ethylene glycol), actual Mn = 756) using silica gel as the catalyst in the absence of an organic solvent at 150 °C.

Solid 2,4-D (20.0g, 90.5 mmol), liquid Carbowax MPEG 750 (68.4g, 90.5 mmol), silica gel 60Å (200 – 400 mesh) (1.0g) were added to a 250 mL round bottom flask along with a stir bar. The reaction flask was connected to a Dean-Stark trap and a condenser. The reaction mixture was heated to 150 °C under a gentle stream of nitrogen gas. During the reaction, the side product of the esterification reaction, water, was condensed and collected in the Dean-Stark trap. Thin layer chromatography was used to monitor the completion of the reaction. The reaction was complete in 3 hours. The crude product was filtered to remove silica gel, and yielded a slight yellow liquid of surface-active agent of the 2,4-D active ingredient. ¹H-NMR (300 MHz, D₂O): δ 3.38 (s, 3H, CH₃-(OCH₂CH₂)_n-OCH₂CH₂-O(O)C-), 3.36 – 3.73 (m, PEG, -(CH₃-(OCH₂CH₂)_n-OCH₂CH₂-O(O)C-), 4.36 (t, 2H, CH₃-(OCH₂CH₂)_n-OCH₂CH₂-O(O)C-), 6.81 (d, 1H, aromatic-H), 7.18 (dd, 1H, aromatic-H), 7.38 (d, 1H, aromatic H).

25

Example 28: Formulation of surface-active agent of 2,4-D

Liquid 2,4-D surfactant produced according to Example 24 (34.72 g, equivalent to 4.0 g of 2,4-D itself) and 2L deionized water were transferred to a 3L plastic beaker along with a stir bar. The 2,4-D surfactant was completely dissolved, and the solution appeared slightly yellow but transparent with a pH value of 2.76. A few drops of aqueous NaOH (10N) were added to the solution to increase the pH to 6.65. At this pH, the viscosity of the solution was

30

1.08 cP at 24.0 °C, and dynamic light scattering result obtained by volume distribution analysis showed a single distribution with the mean diameter of 252 nm.

5

H. Combinations of surface-active agents of active ingredients and polymer-encapsulated nanoparticles of active ingredients

Example 29: Production of nanoparticles containing an increased loading of 2,4-D

10 Solid 2,4- dichlorophenoxyacetic acid (2,4-D) (4.0g, 18.1 mmol) was ground to a fine powder before transferred to a 2L glass beaker. Fresh deionized water (1L) was measured by a 1L graduate cylinder and transferred to the beaker, along with a stir bar. The medium was connected to a pH meter. To the stirring dispersion, aqueous NaOH (10N) was added dropwise. As the pH increased, more solid 2,4-D dissolved the dispersion became more
15 transparent. Eventually, all solid 2,4-D dissolved completely, and the solution appeared transparent. The pH of the solution was measured at 9.20.

In a different beaker (4L) equipped with a mechanical stirrer, cationic poly(diallyldimethylammonium chloride) (PDDA) (36.57 g of 20 wt% PDDA in water, 45.2 mmol) and 900 mL of deionized water were transferred. The solution appeared transparent.
20 The aqueous 2,4-D solution was fed to the stirring PDDA solution via a feeding pump. The addition of 2,4D solution was completed in about 3.5 hours. The mixture appeared transparent and contained 2.0 g/L of active ingredient (2,4-D). The pH and viscosity of the nanoparticle dispersion were 7.06 and 3.18 cP at 24.1 °C, respectively. Dynamic light scattering (DLS) analyzed by volume intensity distribution showed the mean diameter of the
25 collapsed particles was about 3 nm. In a 250 mL beaker equipped with a stir bar, liquid of surface-active agent of active ingredient (prepared according to example 24) (17.35g) and deionized water (64 mL) were transferred. The mixture was stirred until the surface-active agent of active ingredient completely dissolved. The pH of the surface-active agent of active ingredient was measured and showed a value of 2.64. Aqueous NaOH (10N) was used to
30 increase the pH of the surface-active agent of active ingredient to 5.98. Then the surface-active agent of active ingredient solution was added dropwise to the dispersion of nanoparticles of active ingredient encapsulated by PDPA. The result mixture appeared transparent with light yellow color and has a pH value of 6.23 and the viscosity of 2.51 cP at

23.1 °C. DLS result of this polymer solution was shown a single distribution with a mean diameter of 4 nm.

5

I. Soil mobility

This example demonstrates that PAA capsules can be loaded with active ingredients and moved through Ottawa sand. A hydrophobic fluorescent dye (modified Hostasol Yellow) was used as a model active ingredient.

10

Example 30:

Standard Ottawa sand (VWR, CAS# 14808-60-7) was washed twice with deionized water and dried in air prior to use. The dried sand was used as an immobile phase in the column and to load dyes, with and without PAA capsules, onto columns.

15

Preparation samples with and without PAA capsules: In a 20 mL vial, modified Hostasol Yellow dye (0.0035g), dried Ottawa sand (2.0g) and methanol (10g) were weighed. The mixture was stirred until all dyes were completely dissolved. Methanol was completely removed by rotary evaporator. This process allowed the dyes to be adsorbed onto sand particles.

20

In a different 20 mL vial, modified Hostasol Yellow dye (0.0035g), PAA capsules (0.010g) prepared according to Example 1 and methanol (10g) were weighed. The mixture was stirred until all dyes were completely dissolved. Methanol was partially removed by rotary evaporator. Dried sand (2.0g) was added to the solution and then the methanol was removed completely.

25

Preparation columns: Two glass pipettes were used as columns. Dried sand (1.8g) was loaded into each column to a height of 2 in. Each column was washed with 10 mL deionized water. The eluted water was collected for UV analysis. Two dried samples (0.5 g each) were loaded onto the columns and eluted with deionized water (10 g). The eluent from the sample containing PAA capsules appeared yellow whereas the eluent from the sample without the capsules appeared clear. In addition, the column contained the sample without the PAA capsules was eluted with an aqueous PAA capsule dispersion (10 g deionized water, 0.010g PAA capsules). The eluent from this experiment appeared clear.

30

This result indicates that modified Hostasol Yellow was not transferred from the column to the capsules.

Figure 11: UV spectrum of A) The eluents collected from the column containing the sample loaded with PAA capsules. The modified Hostasol Yellow showed an absorption peak maximized at 480 nm, B) The eluents collected from the column containing the sample loaded without PAA capsules. Note that in this column, it was flushed after the elution test with an aqueous dispersion containing empty PAA capsules.

J. *Formulating biologically inactive active ingredients*

10 Example 31: Using Pyrene as a micro environment sensitive fluorescent probe.

The pyrene microenvironments from different polymer nanoparticles were probed for the following nanoparticles: Na⁺-collapsed polyacrylic acid (Na-PAA), ZnO/polyacrylic nanoparticles (ZnO-PAA), Zn²⁺- collapsed nanoparticles (Zn-PAA), Na⁺- collapsed PMAA nanoparticles (Na-PMAA), Na⁺- collapsed P(MAA-co-EA) nanoparticles (Na-P(MAA-EA), poly(vinyl pyrrolidone) – collapsed polyacrylic acid nanoparticles (PVP/PAA). Aqueous pyrene-nanoparticle solutions were prepared as follows. 1.0 mg pyrene was dissolved in 10 mL discholormethane and was used as the stock pyrene solution (0.1 mg/mL). To prepare the aqueous pyrene-nanoparticle solutions, 10 micro liters of the stock pyrene solution was added to a 20 mL scintillation vial and was allowed to air dry in a fume hood for one hour. 80 mg of solid nanoparticles or polymer, 10 g of deionized water and a magnetic stir bar were then added to the vial. The vial was then capped tightly, wrapped in aluminum foil, and the solution was stirred at room temperature for 2 days. The same procedure was employed for all the different nanoparticles and polymers. Aqueous HCl (0.1 N and 1 N) and NaOH (0.1 N and 1 N) were used to adjust the pH of the solutions. Emission spectra were measured on a Perkin Elmer LS 55 Luminescence Spectrometer using an excitation wavelength of 340 nm, having slit widths for both excitation and emission at 2.5 nm. Figure 12 shows the emission spectra of pyrene in water and pyrene in Na-P(MAA-co-EA) nanoparticles at low pH. The emission intensity of the first (I_1 , ~373 nm) and third (I_3 , ~384 nm) vibronic bands were recorded and the ratio (I_1/I_3) calculated for the different polymer nanoparticles systems. These ratios for the different polymer nanoparticles are presented in Table 4.

5

Table 4

 I_1/I_3 ratio

	pH 3-6	pH 6-8	pH 8-10
Pyrene – control (in water)	--	1.68	1.70
PAA 450	1.58	--	1.58
Na-PAA	1.60	--	1.61
ZnO-PAA	1.52	--	--
Zn-PAA	1.48	--	1.52
PMAA polymer	1.00	1.40	--
Na-PMAA	1.02	1.42	1.43
Na-P(MAA-co-EA)*	1.00	1.25	1.33
PVP/PAA	1.62	--	--

Table 4. Tabulated I_1/I_3 ratio for different polymer nanoparticles. Equivalent solvent microenvironment based on the (I_1/I_3) ratio from Dong and Winnik (*Photochem. Photobiol.* **1982**, 35, 17). : o-dichlorobenzene, 1.02; methylene chloride, 1.35; dioxane, 1.5; glycerol, 1.6; water, 1.8.

* Na-P(MAA-co-EA) was prepared by collapsing copoly(methacrylic acid-ethyl acrylate) (P(MAA-co-EA)) with NaCl process. P(MAA-co-EA) copolymers were prepared by emulsion polymerization using potassium persulfate as the initiator under starve-monomer conditions at low pH. The weight ratio of MAA:EA was 90:10. The weight of the total monomer to water was 5 wt%.

Example 32: Solubilization of Red Dye #2

The solubility of red dye #2 was compared to its solubility in several nanoparticle formulations to its solubility in water alone. 100 mg of nanoparticles (Na⁺-collapsed polyacrylic acid nanoparticles (Na-PAA), ZnO/polyacrylic nanoparticles (ZnO-PAA), Zn²⁺-collapsed nanoparticles (Zn-PAA), Na⁺- collapsed PMAA nanoparticles (Na-PMAA), Na⁺- collapsed P(MAA-co-EA) nanoparticles (Na-P(MAA-EA), Zn²⁺- collapsed nanoparticles (Zn-PAA)) was mixed with 0.5 mg of red dye # 2 and 30 mL of deionized water. After mixing vigorously for 1 hour, the different solutions of red dye #2 and nanoparticles were centrifuged at 3500 rpm for 10 mins to separate any undispersed dye. The supernatant

liquid from the solutions that contained the polymer nanoparticles had a bright red color while supernatant liquid from the solution that just had water was colorless. The red color of the supernatant liquids from the solutions that contained the polymer nanoparticles show that the solubility of the dye was increased by formulating them with the polymer
5 nanoparticles.

Example 33: Encapsulation of fragrance / flavor, vanillin by PAA nanoparticles

100 mg of vanillin and 100 mg of PAA particle were placed in a 2 dram glass vial. 5 ml of methanol was added to the glass vial. The solution was stirred with a stir bar in a
10 magnetic stir plate for 30 minutes. 50mL of RO water was taken in a separate 250 ml glass beaker and stirred with magnetic stir bar. The methanol mixture was dripped (1ml/min) into the stirred water. The above solution was stirred for 2 hours. The resulting solution was translucent. The methanol from solution was removed using a rotary-evaporator. The resulting solution was freeze dried to obtain a dry powder. The freeze-dried solid is re-
15 dispersed as a 200 ppm vanillin solution in RO water.

EQUIVALENTS

The foregoing has been a description of certain non-limiting embodiments of the invention. Those skilled in the art will recognize, or be able to ascertain using no more than
5 routine experimentation, many equivalents to the specific embodiments of the invention described herein. Those of ordinary skill in the art will appreciate that various changes and modifications to this description may be made without departing from the spirit or scope of the present invention, as defined in the following claims.

In the claims articles such as “a,” “an” and “the” may mean one or more than one
10 unless indicated to the contrary or otherwise evident from the context. Claims or descriptions that include “or” between one or more members of a group are considered satisfied if one, more than one, or all of the group members are present in, employed in, or otherwise relevant to a given product or process unless indicated to the contrary or otherwise evident from the context. The invention includes embodiments in which exactly
15 one member of the group is present in, employed in, or otherwise relevant to a given product or process. The invention also includes embodiments in which more than one, or all of the group members are present in, employed in, or otherwise relevant to a given product or process. Furthermore, it is to be understood that the invention encompasses all variations, combinations, and permutations in which one or more limitations, elements, clauses,
20 descriptive terms, *etc.*, from one or more of the claims or from relevant portions of the description is introduced into another claim. For example, any claim that is dependent on another claim can be modified to include one or more limitations found in any other claim that is dependent on the same base claim. Furthermore, where the claims recite a composition, it is to be understood that methods of using the composition for any of the
25 purposes disclosed herein are included, and methods of making the composition according to any of the methods of making disclosed herein or other methods known in the art are included, unless otherwise indicated or unless it would be evident to one of ordinary skill in the art that a contradiction or inconsistency would arise. In addition, the invention encompasses compositions made according to any of the methods for preparing
30 compositions disclosed herein.

Where elements are presented as lists, *e.g.*, in Markush group format, it is to be understood that each subgroup of the elements is also disclosed, and any element(s) can be

removed from the group. It is also noted that the term "comprising" is intended to be open and permits the inclusion of additional elements or steps. It should be understood that, in general, where the invention, or aspects of the invention, is/are referred to as comprising particular elements, features, steps, *etc.*, certain embodiments of the invention or aspects of the invention consist, or consist essentially of, such elements, features, steps, *etc.* For purposes of simplicity those embodiments have not been specifically set forth *in haec verba* herein. Thus for each embodiment of the invention that comprises one or more elements, features, steps, *etc.*, the invention also provides embodiments that consist or consist essentially of those elements, features, steps, *etc.*

10 Where ranges are given, endpoints are included. Furthermore, it is to be understood that unless otherwise indicated or otherwise evident from the context and/or the understanding of one of ordinary skill in the art, values that are expressed as ranges can assume any specific value within the stated ranges in different embodiments of the invention, to the tenth of the unit of the lower limit of the range, unless the context clearly
15 dictates otherwise. It is also to be understood that unless otherwise indicated or otherwise evident from the context and/or the understanding of one of ordinary skill in the art, values expressed as ranges can assume any subrange within the given range, wherein the endpoints of the subrange are expressed to the same degree of accuracy as the tenth of the unit of the lower limit of the range.

20 In addition, it is to be understood that any particular embodiment of the present invention may be explicitly excluded from any one or more of the claims. Any embodiment, element, feature, application, or aspect of the compositions and/or methods of the invention can be excluded from any one or more claims. For purposes of brevity, all of the embodiments in which one or more elements, features, purposes, or aspects is excluded are
25 not set forth explicitly herein.

What is claimed is:

1. A composition comprising a collapsed, polymer nanoparticle and at least one organic, neutral compound associated with the nanoparticle, wherein the nanoparticle is less than 100 nm in diameter and comprises multiple polymer molecules, and the polymer molecules comprise a water-soluble, random, polyelectrolyte, copolymer, that have a molecular weight of at least 100,000 Dalton and are cross-linked,

wherein the organic, neutral compound is selected from the group consisting of dyes, pigments, colorants, oils, UV-light absorbing molecules, fragrances, flavoring molecules, preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, and combinations thereof and is not an agricultural active compound.

2. The composition of claim 1, wherein the nanoparticles are less than 50 nm in diameter.

3. The composition of claim 1, wherein the nanoparticles are less than 20 nm in diameter.

4. The composition of any one of claims 1 to 3, wherein the organic, neutral compound is hydrophobic.

5. The composition of any one of claims 1 to 4, wherein the crosslinking step is accomplished by one of the following: electromagnetic radiation induced cross-linking, chemically induced cross-linking or thermally induced cross-linking.

6. The composition of any one of claims 1 to 5, wherein at least a portion of the organic, neutral compound is in the interior of the polymer nanoparticle.

7. The composition of any one of claims 1 to 6, wherein at least a portion of the organic, neutral compound is on the surface of the polymer nanoparticle.

8. The composition of any one of claims 1 to 7, wherein the organic, neutral compound remains associated with the polymer nanoparticle after being exposed to a solvent.

9. The composition of any one of claims 1 to 8 which provides for extended or sustained release after application.

10. The composition of any one of claims 1 to 9, wherein the organic, neutral compound is released via triggered release.

11. The composition of any one of claims 1 to 10, wherein the organic, neutral compound is neutral at a pH of between about 5 to about 9.
12. The composition of any one of claims 1 to 10, wherein the organic, neutral compound is neutral at a pH of between about 6 to about 8.
13. The composition of any one of claims 1 to 12, wherein the polymer molecules have a molecular weight of at least 250,000 Daltons.
14. The composition of any one of claims 1 to 13, wherein the organic, neutral compound is non-ionic.
15. The composition of any one of claims 1 to 14, wherein the organic, neutral compound is not a salt, or ion from a salt.
16. The composition of any one of claims 1 to 15, wherein the polymer nanoparticle has a cavity.
17. The composition of any one of claims 1 to 16, wherein the polymer nanoparticle has a network structure.
18. The composition of any one of claims 1 to 17, wherein the polymer nanoparticles can be recovered in a dried form and redispersed in a suitable solvent.
19. A dispersion comprising the composition of any one of claims 1 to 18, wherein the organic, neutral compound is dispersed at a concentration higher than its solubility in the absence of the polymer nanoparticle.
20. A method to associate an organic, neutral compound with polymer nanoparticles, the method comprising the steps of:
 - (a) dissolving the polymer nanoparticles in a suitable first solvent,
 - (b) swelling the polymer nanoparticles by adding a second solvent containing the organic, neutral compound; and
 - (c) removing the second solvent,wherein the organic, neutral compound is selected from the group consisting of dyes, pigments, colorants, oils, UV-light absorbing molecules, fragrances, flavoring molecules, preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, and combinations thereof and is not an agricultural active compound; and

wherein the polymer nanoparticles comprise a water-soluble, random, polyelectrolyte copolymer, having a molecular weight of at least 100,000 Dalton that is cross-linked.

21. A method to associate an organic, neutral compound with polymer nanoparticles, the method comprising the steps of:

- (a) dissolving the polymer nanoparticles and the organic, neutral compound in a suitable first solvent,
- (b) adding a second solvent; and
- (c) removing the first solvent,

wherein the organic, neutral compound is selected from the group consisting of dyes, pigments, colorants, oils, UV-light absorbing molecules, fragrances, flavoring molecules, preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, and combinations thereof and is not an agricultural active compound; and

wherein the polymer nanoparticles comprise a water-soluble, random, polyelectrolyte copolymer, having a molecular weight of at least 100,000 Dalton that is cross-linked.

22. A method to associate an organic, neutral compound with polymer nanoparticles, the method comprising the steps of:

- (a) dissolving the polymer nanoparticles and the organic, neutral compound in a suitable solvent; and
- (b) removing the solvent,

wherein the organic, neutral compound is selected from the group consisting of dyes, pigments, colorants, oils, UV-light absorbing molecules, fragrances, flavoring, molecules, preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, and combinations thereof and is not an agricultural active compound; and

wherein the polymer nanoparticles comprise a water-soluble, random, polyelectrolyte copolymer, having a molecular weight of at least 100,000 Dalton that is cross-linked.

23. The method of claim 20, 21, or 22, wherein the nanoparticles are less than 100 nm in diameter.

24. The method of claim 20, 21, or 22, wherein one solvent is water.

25. The method of claim 20 or 21, wherein the second solvent is not miscible in the first solvent.

26. The method of claim 20 or 21 wherein the second solvent is partially miscible in the first solvent.
27. The method of claim 20 or 21, further comprising the step of removing the remaining solvent.
28. The method of claim 20, 21, or 22, wherein the solvent is removed by lyophilization, distillation, extraction, selective solvent removal, filtration, dialysis, or evaporation.
29. The method of claim 28, further comprising the step of redispersing the nanoparticles in a suitable solvent.
30. The method of claim 20, 21, or 22, wherein the nanoparticles are less than 50 nm in diameter.
31. The method of claim 20, 21, or 22, wherein the nanoparticles are less than 20 nm in diameter.
32. The method of claim 20, 21, or 22, wherein the polymer comprises multiple polymer molecules.
33. The method of claim 20, 21, or 22, wherein at least a portion of the organic, neutral compound is on the surface of the polymer nanoparticle.
34. A method to make polymer nanoparticles comprising an organic, neutral compound, the method comprising the steps of:
- (a) dissolving a polyelectrolyte in a suitable solvent,
 - (b) associating the organic, neutral compound with the polyelectrolyte, and
 - (c) collapsing the polyelectrolyte,
- wherein the organic, neutral compound is selected from the group consisting of dyes, pigments, colorants, oils, UV-light absorbing molecules, fragrances, flavoring molecules, preservatives, electro-conductive compounds, thermoplastic compounds, adhesion promoters, penetration enhancers, anti-corrosive agents, and combinations thereof and is not an agricultural active compound; and
- wherein the polyelectrolyte is a random copolymer, water-soluble, and has a molecular weight of at least 100,000 Dalton and wherein the nanoparticles are less than 100 nm in diameter and comprise multiple polymer molecules.
35. The method of claim 34, wherein the association of the organic, neutral compound with the polyelectrolyte causes the collapse of the polyelectrolyte.
36. The method of claim 35, wherein the collapse is caused by a change in solvent conditions.
37. The method of claim 35, wherein the collapse is caused by a change in temperature.

38. The method of claim 35, wherein the collapse is caused by a change in pH.
39. The method of claim 34, further comprising cross-linking the polyelectrolyte.
40. The method of claim 39, wherein the crosslinking step is accomplished by one of the following: electromagnetic radiation induced cross-linking, chemically induced cross-linking or thermally induced cross-linking.
41. The method of any one of claims 34 to 40, wherein the organic, neutral compound is chemically modified.
42. The method of any one of claims 34 to 41, wherein the nanoparticles are less than 50 nm in diameter.
43. The method of any one of claims 34 to 41, wherein the nanoparticles are less than 20 nm in diameter.
44. The method of any one of claims 34 to 43, wherein at least a portion of the organic, neutral compound is on the surface of the polymer nanoparticle.
45. The method of any one of claims 34 to 43, comprising the step of removing the solvent.
46. The method of claim 45, wherein the solvent is removed by lyophilization or evaporation.
47. The method of claim 46, further comprising the step of redispersing the nanoparticles in a suitable solvent.
48. The composition of any one of claims 1 to 19 in the form of an aerosol.
49. The composition of claim 50, wherein the composition is part of a formulation with other compounds in solution.
50. The composition of claim 51, wherein the formulation is substantially free of surfactants.

1/13




Figure 1

2/13




Figure 2

3/13




Figure 3

4/13




Figure 4

5/13




Figure 5

6/13




Figure 6

7/13




Figure 7

8/13




a




b

Figure 8

9/13



a




b


Figure 9

10/13

Figure 10. Controlled release



A. Control release setup



B. Slow release profile of TXM loaded nanoparticles

Soil mobility

11/13



A

Figure 11

B

12/13




Figure 12.

13/13








Figure 13



A




Al⁺



B

(1 – 100 nm)



C