



- (51) **International Patent Classification:**  
*C08L 23/12* (2006.01)    *C08L 3/02* (2006.01)  
*C08K 5/01* (2006.01)
- (21) **International Application Number:** PCT/US2012/038373
- (22) **International Filing Date:** 17 May 2012 (17.05.2012)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**  
61/488,600    20 May 2011 (20.05.2011)    US
- (71) **Applicant (for all designated States except US):** **THE PROCTER & GAMBLE COMPANY** [US/US]; One Procter & Gamble Plaza, Cincinnati, Ohio 45202 (US).
- (72) **Inventors; and**
- (75) **Inventors/Applicants (for US only):** **ALLEN, William Maxwell** [US/US]; 5612 Safari Drive, Liberty Township, Ohio 45044 (US). **BOND, Eric Bryan** [US/US]; 253 Terwilliger's Run, Maineville, Ohio 45039 (US). **NODA, Isao** [US/US]; 1568 Hunter Road, Fairfield, Ohio 45014 (US).
- (74) **Common Representative:** **THE PROCTER & GAMBLE COMPANY**; c/o Eileen L. Hughett, Global Patent Services, 299 East Sixth Street, Sycamore Building, 4th Floor, Cincinnati, Ohio 45202 (US).
- (81) **Designated States (unless otherwise indicated, for every kind of national protection available):** AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States (unless otherwise indicated, for every kind of regional protection available):** ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
- with international search report (Art. 21(3))
  - with amended claims (Art. 19(1))



(54) **Title:** MOLDED ARTICLES OF STARCH-POLYMER-WAX-OIL COMPOSITIONS

(57) **Abstract:** Molded articles formed from compositions comprising thermoplastic starch, thermoplastic polymers, and oils, waxes, or combinations thereof are disclosed, where the oil, wax, or combination is dispersed throughout the thermoplastic polymer.

## MOLDED ARTICLES OF STARCH-POLYMER-WAX-OIL COMPOSITIONS

## FIELD OF THE INVENTION

The present invention relates to molded articles from compositions comprising intimate admixtures of thermoplastic starch, thermoplastic polymers and oils, waxes, or combinations thereof.

## BACKGROUND OF THE INVENTION

Thermoplastic polymers are used in a wide variety of applications. However, thermoplastic polymers, such as polypropylene and polyethylene, pose additional challenges compared to other polymer species, especially with respect to formation of, for example, fibers. This is because the material and processing requirements for production of fibers are much more stringent than for producing other forms, for example, films. For the production of fibers, polymer melt flow characteristics are more demanding on the material's physical and rheological properties vs other polymer processing methods. Also, the local shear/extensional rate and shear rate are much greater in fiber production than other processes and, for spinning very fine fibers, small defects, slight inconsistencies, or phase incompatibilities in the melt are not acceptable for a commercially viable process. Moreover, high molecular weight thermoplastic polymers cannot be easily or effectively spun into fine fibers. Given their availability and potential strength improvement, it would be desirable to provide a way to easily and effectively spin such high molecular weight polymers.

Most thermoplastic polymers, such as polyethylene, polypropylene, and polyethylene terephthalate, are derived from monomers (e.g., ethylene, propylene, and terephthalic acid, respectively) that are obtained from non-renewable, fossil-based resources (e.g., petroleum, natural gas, and coal). Thus, the price and availability of these resources ultimately have a significant impact on the price of these polymers. As the worldwide price of these resources escalates, so does the price of materials made from these polymers. Furthermore, many consumers display an aversion to purchasing products that are derived solely from petrochemicals. In some instances, consumers are hesitant to purchase products made from non-renewable fossil-based resources, which are non-renewable fossil based resources. Other consumers may have adverse perceptions about products derived from petrochemicals as being "unnatural" or not environmentally friendly.

Thermoplastic polymers and thermoplastic starches are often incompatible with, or have poor miscibility with additives (e.g., oils, pigments, organic dyes, perfumes, etc.) that might otherwise contribute to a reduced consumption of these polymers in the manufacture of

downstream articles. Heretofore, the art has not effectively addressed how to reduce the amount of thermoplastic polymers derived from non-renewable, fossil-based resources in the manufacture of common articles employing these polymers. Accordingly, it would be desirable to address this deficiency. Existing art has combined polypropylene with additives, with polypropylene as the minor component to form cellular structures. These cellular structures are the purpose behind including renewable materials that are later removed or extracted after the structure is formed. U.S. Patent No. 3,093,612 describes the combination of polypropylene with various fatty acids where the fatty acid is removed. The scientific paper *J. Apply. Polym. Sci* 82 (1) pp. 169-177 (2001) discloses use of diluents on polypropylene for thermally induced phase separation to produce an open and large cellular structure but at low polymer ratio, where the diluent is subsequently removed from the final structure. The scientific paper *J. Apply. Polym. Sci* 105 (4) pp. 2000-2007 (2007) produces microporous membranes via thermally induced phase separation with dibutyl phthalate and soy bean oil mixtures, with a minor component of polypropylene. The diluent is removed in the final structure. The scientific paper *Journal of Membrane Science* 108 (1-2) pp. 25-36 (1995) produces hollow fiber microporous membranes using soy bean oil and polypropylene mixtures, with a minor component of polypropylene and using thermally induced phase separation to produce the desired membrane structure. The diluent is removed in the final structure. In all of these cases, the diluent as described is removed to produce the final structure. These structures before the diluent is removed are oily with excessive amounts of diluent to produce very open microporous structures with pore sizes > 10 $\mu$ m.

A need exists for molded articles made from compositions of thermoplastic starch and thermoplastic polymers that allow for use of higher molecular weight and/or decreased non-renewable resource based materials, and/or incorporation of further additives, such as perfumes and dyes. A still further need is for molded articles from compositions that leave the additive present to deliver renewable materials in the final product and that can also enable the addition of further additives into the final structure, such as dyes and perfumes, for example.

#### SUMMARY OF THE INVENTION

In one aspect, the invention is directed to molded articles comprising a composition comprising an intimate admixture of a thermoplastic starch (TPS), a thermoplastic polymer and an oil, wax, or combination thereof present in an amount of about 5 wt% to about 40 wt%, based upon the total weight of the composition. The molded article can be in the form of a bottle, container, tampon applicator, or applicator for insertion of a medication into a

bodily orifice. The molded article can be made by a method comprising compression molding the composition. The molded article can be made by a method comprising extruding the composition. The molded article can be made by a method comprising blow molding the composition.

5           The thermoplastic polymer can comprise a polyolefin, a polyester, a polyamide, copolymers thereof, or combinations thereof. The thermoplastic polymer can comprise polypropylene, and can have a melt flow index of greater than 5 g/10 min or of greater than 10 g/10 min. The thermoplastic polymer can be selected from the group consisting of polypropylene, polyethylene, polypropylene co-polymer, polyethylene co-polymer,  
10 polyethylene terephthalate, polybutylene terephthalate, polylactic acid, polyhydroxyalkanoates, polyamide-6, polyamide-6,6, and combinations thereof. The preferred thermoplastic polymer comprises polypropylene. The polypropylene can have a weight average molecular weight of about 20 kDa to about 400 kDa. The thermoplastic polymer can be present in the composition in an amount of about 20 wt% to about 90 wt%,  
15 about 30 wt% to about 70 wt%, based upon the total weight of the composition. The thermoplastic polymer can be derived from a renewable bio-based feed stock origin, such as bio polyethylene or bio polypropylene, and/or can be recycled source, such as post consumer use.

          The oil, wax, or combination thereof can be present in the composition in an amount  
20 of about 5 wt% to about 40 wt%, about 8 wt% to about 30 wt%, or about 10 wt% to about 20 wt%, based upon the total weight of the composition. The oil, wax, or combination thereof can comprise a lipid, which can be selected from the group consisting of a monoglyceride, diglyceride, triglyceride, fatty acid, fatty alcohol, esterified fatty acid, epoxidized lipid, maleated lipid, hydrogenated lipid, alkyd resin derived from a lipid, sucrose polyester, or  
25 combinations thereof. The wax can be selected from the group consisting of a hydrogenated plant oil, a partially hydrogenated plant oil, an epoxidized plant oil, a maleated plant oil. Specific examples of such plant oils include soy bean oil, corn oil, canola oil, and palm kernel oil. The oil, wax, or combination thereof can comprise a mineral oil or wax, such as a linear alkane, a branched alkane, or combinations thereof. The oil, wax, or combination  
30 thereof can be selected from the group consisting of soy bean oil, epoxidized soy bean oil, maleated soy bean oil, corn oil, cottonseed oil, canola oil, beef tallow, castor oil, coconut oil, coconut seed oil, corn germ oil, fish oil, linseed oil, olive oil, oiticica oil, palm kernel oil, palm oil, palm seed oil, peanut oil, rapeseed oil, safflower oil, sperm oil, sunflower seed oil, tall oil, tung oil, whale oil, tristearin, triolein, tripalmitin, 1,2-dipalmitoolein, 1,3-

dipalmitoolein, 1-palmito-3-stearo-2-olein, 1-palmito-2-stearo-3-olein, 2-palmito-1-stearo-3-olein, trilinolein, 1,2-dipalmitolinolein, 1-palmito-dilinolein, 1-stearo-dilinolein, 1,2-diacetopalmitin, 1,2-distearo-olein, 1,3-distearo-olein, trimyristin, trilaurin, capric acid, caproic acid, caprylic acid, lauric acid, lauroleic acid, linoleic acid, linolenic acid, myristic acid, myristoleic acid, oleic acid, palmitic acid, palmitoleic acid, stearic acid, and combinations thereof.

The oil, wax, or combination thereof can be dispersed within the thermoplastic starch and thermoplastic polymer such that the oil, wax, or combination has a droplet size of less than 10  $\mu\text{m}$ , less than 5  $\mu\text{m}$ , less than 1  $\mu\text{m}$ , or less than 500 nm within the thermoplastic polymer. The oil, wax, or combination can be a renewable material.

The thermoplastic starch (TPS) can comprise a starch or a starch derivative and a plasticizer. The thermoplastic starch can be present in an amount about 10 wt% to about 80 wt% or about 20 wt% to about 40 wt%, based upon the total weight of the composition.

The plasticizer can comprise a polyol. Specific polyols contemplated include mannitol, sorbitol, glycerin, and combinations thereof. The plasticizer can be selected from the group consisting of glycerol, ethylene glycol, propylene glycol, ethylene diglycol, propylene diglycol, ethylene triglycol, propylene triglycol, polyethylene glycol, polypropylene glycol, 1,2-propanediol, 1,3-propanediol, 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,5-hexanediol, 1,2,6-hexanetriol, 1,3,5-hexanetriol, neopentyl glycol, trimethylolpropane, pentaerythritol, sorbitol, glycerol ethoxylate, tridecyl adipate, isodecyl benzoate, tributyl citrate, tributyl phosphate, dimethyl sebacate, urea, pentaerythritol ethoxylate, sorbitol acetate, pentaerythritol acetate, ethylenebisformamide, sorbitol diacetate, sorbitol monoethoxylate, sorbitol diethoxylate, sorbitol hexaethoxylate, sorbitol dipropoxylate, aminosorbitol, trihydroxymethylaminomethane, glucose/PEG, a reaction product of ethylene oxide with glucose, trimethylolpropane monoethoxylate, mannitol monoacetate, mannitol monoethoxylate, butyl glucoside, glucose monoethoxylate,  $\alpha$ -methyl glucoside, carboxymethylsorbitol sodium salt, sodium lactate, polyglycerol monoethoxylate, erythriol, arabitol, adonitol, xylitol, mannitol, iditol, galactitol, allitol, malitol, formamide, N-methylformamide, dimethyl sulfoxide, an alkylamide, a polyglycerol having 2 to 10 repeating units, and combinations thereof.

The starch or starch derivative can be selected from the group consisting of starch, hydroxyethyl starch, hydroxypropyl starch, carboxymethylated starch, starch phosphate, starch acetate, a cationic starch, (2-hydroxy-3-trimethyl(ammoniumpropyl) starch chloride, a starch modified by acid, base, or enzyme hydrolysis, a starch modified by oxidation, and combinations thereof.

The compositions disclosed herein can further comprise an additive. The additive can be oil soluble or oil dispersible. Examples of additives include perfume, dye, pigment, surfactant, nanoparticle, antistatic agent, filler, or combination thereof. In another aspect, provided is a method of making a composition as disclosed herein, the method comprising a) mixing the thermoplastic polymer, in a molten state, with the wax, also in the molten state, to form the admixture; and b) cooling the admixture to a temperature at or less than the solidification temperature of the thermoplastic polymer in 10 seconds or less to form the composition. The method of making a composition can comprise a) melting a thermoplastic polymer to form a molten thermoplastic polymer; b) mixing the molten thermoplastic polymer and a wax to form an admixture; and c) cooling the admixture to a temperature at or less than the solidification temperature of the thermoplastic polymer in 10 seconds or less. The mixing can be at a shear rate of greater than  $10 \text{ s}^{-1}$ , or about 30 to about  $100 \text{ s}^{-1}$ . The admixture can be cooled in 10 seconds or less to a temperature of  $50^\circ\text{C}$  or less. The composition can be pelletized. The pelletizing can occur after cooling the admixture or before or simultaneous to cooling the admixture. The composition can be made using an extruder, such as a single- or twin-screw extruder. Alternatively, the method of making a composition can comprise a) melting a thermoplastic polymer to form a molten thermoplastic polymer; b) mixing the molten thermoplastic polymer and a wax to form an admixture; and c) extruding the molten mixture to form the finished structure, for example molded articles which solidify upon cooling.

#### DETAILED DESCRIPTION OF THE INVENTION

Molded articles disclosed herein are made from compositions of an intimate admixture of a thermoplastic starch, thermoplastic polymer, and an oil, wax or combination thereof. The term "intimate admixture" refers to the physical relationship of the oil or wax, the thermoplastic starch, and thermoplastic polymer, wherein the oil or wax is dispersed within the thermoplastic polymer and/or thermoplastic starch. The droplet size of the oil or wax within in the thermoplastic polymer is a parameter that indicates the level of dispersion of the oil or wax within the thermoplastic polymer and/or thermoplastic starch. The smaller the droplet size, the higher the dispersion of the oil or wax within the thermoplastic polymer

and/or thermoplastic starch, the larger the droplet size the lower the dispersion of the oil or wax within the thermoplastic polymer and/or thermoplastic starch. The oil, wax, or both associate with the thermoplastic polymer, but are mixed into both the TPS and thermoplastic polymer during formation of the compositions as disclosed herein. As used herein, the term  
5 “admixture” refers to the intimate admixture of the present invention, and not an “admixture” in the more general sense of a standard mixture of materials.

The droplet size of the oil or wax within the thermoplastic polymer and/or thermoplastic starch is less than 10  $\mu\text{m}$ , and can be less than 5  $\mu\text{m}$ , less than 1  $\mu\text{m}$ , or less than 500 nm. Other contemplated droplet sizes of the oil and/or wax dispersed within the thermoplastic  
10 polymer and/or thermoplastic starch include less than 9.5  $\mu\text{m}$ , less than 9  $\mu\text{m}$ , less than 8.5  $\mu\text{m}$ , less than 8  $\mu\text{m}$ , less than 7.5  $\mu\text{m}$ , less than 7  $\mu\text{m}$ , less than 6.5  $\mu\text{m}$ , less than 6  $\mu\text{m}$ , less than 5.5  $\mu\text{m}$ , less than 4.5  $\mu\text{m}$ , less than 4  $\mu\text{m}$ , less than 3.5  $\mu\text{m}$ , less than 3  $\mu\text{m}$ , less than 2.5  $\mu\text{m}$ , less than 2  $\mu\text{m}$ , less than 1.5  $\mu\text{m}$ , less than 900 nm, less than 800 nm, less than 700 nm, less than 600 nm, less than 400 nm, less than 300 nm, and less than 200 nm.

15 The droplet size of the oil or wax can be measured by scanning electron microscopy (SEM) indirectly by measuring a void size in the thermoplastic polymer and/or thermoplastic starch, after removal of the oil and/or wax from the composition. Removal of the oil or wax is typically performed prior to SEM imaging due to incompatibility of the oil or wax and the SEM imaging technique. Thus, the void measured by SEM imaging is correlated to the  
20 droplet size of the oil or wax in the composition.

One exemplary way to achieve the dispersion of the oil or wax within the thermoplastic polymer and/or thermoplastic starch is by admixing the thermoplastic polymer, in a molten state, the thermoplastic starch, in the molten state, and the oil and/or wax (which is also in the molten state). Each of the thermoplastic polymer and thermoplastic starch is melted (e.g.,  
25 exposed to temperatures greater than the solidification temperature) to provide the molten thermoplastic polymer and molten thermoplastic starch, and mixed with the oil or wax. One or both of the thermoplastic polymer and thermoplastic starch can be melted prior to addition of the oil or wax or one or both can be melted in the presence of the oil or wax.

The thermoplastic polymer, thermoplastic starch, and oil or wax can be mixed, for example,  
30 at a shear rate of greater than  $10\text{s}^{-1}$ . Other contemplated shear rates include greater than 10, about 15 to about 1000, or up to  $500\text{s}^{-1}$ . The higher the shear rate of the mixing, the greater the dispersion of the oil or wax in the composition as disclosed herein. Thus, the dispersion can be controlled by selecting a particular shear rate during formation of the composition.

The oil or wax and molten thermoplastic polymer and molten thermoplastic starch can be mixed using any mechanical means capable of providing the necessary shear rate to result in a composition as disclosed herein. Non-limiting examples of mechanical means include a mixer, such as a Haake batch mixer, and an extruder (e.g., a single- or twin-screw extruder).

5 The mixture of molten thermoplastic polymer, molten thermoplastic starch, and oil or wax is then rapidly (e.g., in less than 10 seconds) cooled to a temperature lower than the solidification temperature of the thermoplastic polymer and/or thermoplastic starch. The mixture can be cooled to less than 100°C, less than 75°C, less than 50°C, less than 40°C, less than 30°C, less than 20°C, less than 15°C, less than 10°C, or to a temperature of about 0°C to  
10 about 30°C, about 0°C to about 20°C, or about 0°C to about 10°C. For example, the mixture can be placed in a low temperature liquid (e.g., the liquid is at or below the temperature to which the mixture is cooled). The liquid can be water.

### **Thermoplastic starch**

As used herein, “thermoplastic starch” or “TPS” means a native starch or a starch derivative  
15 that has been rendered thermoplastic by treatment with one or more plasticizers.

Thermoplastic starch compositions are well known and disclosed in several patents, for example: U.S. Patent Nos. 5,280,055; 5,314,934; 5,362,777; 5,844,023; 6,214,907; 6,242,102; 6,096,809; 6,218,321; 6,235,815; 6,235,816; and 6,231,970, each incorporated herein by reference.

20 Starch: The starch used in the disclosed compositions is destructured starch. The term “thermoplastic starch” refers to destructured starch with a plasticizer.

Since natural starch generally has a granular structure, it needs to be destructured before it can be melt processed like a thermoplastic material. For gelatinization, e.g., the process of destructuring the starch, the starch can be destructured in the presence of a solvent which  
25 acts as a plasticizer. The solvent and starch mixture is heated, typically under pressurized conditions and shear to accelerate the gelatinization process. Chemical or enzymatic agents may also be used to destructure, oxidize, or derivatize the starch. Commonly, starch is destructured by dissolving the starch in water. Fully destructured starch results when the particle size of any remaining undestructured starch does not impact the extrusion process,  
30 e.g., the fiber spinning process or molded article processing. Any remaining undestructured starch particle sizes are less than 30µm, preferably less 20µm, more preferably less than 10µm, or less than 5µm. The residual particle size can be determined by pressing the final formulation into a thin film (50µm or less) and placing the film into a light microscope under

cross polarized light. Under cross polarized light, the signature maltose cross, indicative of undestructured starch, can be observed. If the average size of these particle is above the target range, the destructured starch has not been prepared properly.

Suitable naturally occurring starches can include, but are not limited to, corn starch, potato starch, sweet potato starch, wheat starch, sago palm starch, tapioca starch, rice starch, soybean starch, arrow root starch, bracken starch, lotus starch, cassaya starch, waxy maize starch, high amylose corn starch, and commercial amylose powder. Blends of starch may also be used. Though all starches are useful herein, the present invention is most commonly practiced with natural starches derived from agricultural sources, which offer the advantages of being abundant in supply, easily replenishable and inexpensive in price. Naturally occurring starches, particularly corn starch, wheat starch, and waxy maize starch, are the preferred starch polymers of choice due to their economy and availability.

Modified starch may also be used. Modified starch is defined as non-substituted or substituted starch that has had its native molecular weight characteristics changed (i.e. the molecular weight is changed but no other changes are necessarily made to the starch). If modified starch is desired, chemical modifications of starch typically include acid or alkali hydrolysis and oxidative chain scission to reduce molecular weight and molecular weight distribution. Natural, unmodified starch generally has a very high average molecular weight and a broad molecular weight distribution (e.g. natural corn starch has an average molecular weight of up to about 60,000,000 grams/mole (g/mol)). The average molecular weight of starch can be reduced to the desirable range for the present invention by acid reduction, oxidation reduction, enzymatic reduction, hydrolysis (acid or alkaline catalyzed), physical/mechanical degradation (e.g., via the thermomechanical energy input of the processing equipment), or combinations thereof. The thermomechanical method and the oxidation method offer an additional advantage when carried out in situ. The exact chemical nature of the starch and molecular weight reduction method is not critical as long as the average molecular weight is in an acceptable range.

Ranges of number average molecular weight for starch or starch blends added to the melt can be from about 3,000 g/mol to about 20,000,000 g/mol, preferably from about 10,000 g/mol to about 10,000,000 g/mol, preferably from about 15,000 to about 5,000,000 g/mol, more preferably from about 20,000 g/mol to about 3,000,000 g/mol. In other embodiments, the average molecular weight is otherwise within the above ranges but about 1,000,000 or less, or about 700,000 or less.

Substituted starch can be used. If substituted starch is desired, chemical modifications of starch typically include etherification and esterification. Substituted starches may be desired for better compatibility or miscibility with the thermoplastic polymer and plasticizer.

Alternatively, modified and substituted starches can be used to aid in the destructuring  
5 process by increasing the gelatinization process. However, this must be balanced with the reduction in the rate of degradability. The degree of substitution of the chemically substituted starch is from about 0.01 to 3.0. A low degree of substitution, 0.01 to 0.06, may be preferred.

The weight of starch in the composition includes starch and its naturally occurring bound  
10 water content. The term "bound water" means the water found naturally occurring in starch and before mixing of starch with other components to make the composition of the present invention. The term "free water" means the water that is added in making the composition of the present invention. A person of ordinary skill in the art would recognize that once the components are mixed in a composition, water can no longer be distinguished by its origin.

15 The starch typically has a bound water content of about 5% to 16% by weight of starch. It is known that additional free water may be incorporated as the polar solvent or plasticizer, and not included in the weight of the starch.

Plasticizer: A plasticizer can be used in the present invention to destructure the starch and enable the starch to flow, i.e. create a thermoplastic starch. The same plasticizer may be used  
20 to increase melt processability or two separate plasticizers may be used. The plasticizers may also improve the flexibility of the final products, which is believed to be due to the lowering of the glass transition temperature of the composition by the plasticizer. The plasticizers should preferably be substantially compatible with the polymeric components of the disclosed compositions so that the plasticizers may effectively modify the properties of the  
25 composition. As used herein, the term "substantially compatible" means when heated to a temperature above the softening and/or the melting temperature of the composition, the plasticizer is capable of forming a substantially homogeneous mixture with starch.

An additional plasticizer or diluent for the thermoplastic polymer may be present to lower the polymer's melting temperature and improve overall compatibility with the thermoplastic  
30 starch blend. Furthermore, thermoplastic polymers with higher melting temperatures may be used if plasticizers or diluents are present which suppress the melting temperature of the polymer. The plasticizer will typically have a molecular weight of less than about 100,000 g/mol and may preferably be a block or random copolymer or terpolymer where one or more

of the chemical species is compatible with another plasticizer, starch, polymer, or combinations thereof.

Nonlimiting examples of useful hydroxyl plasticizers include sugars such as glucose, sucrose, fructose, raffinose, maltodextrose, galactose, xylose, maltose, lactose, mannose erythrose, glycerol, and pentaerythritol; sugar alcohols such as erythritol, xylitol, malitol, mannitol and sorbitol; polyols such as ethylene glycol, propylene glycol, dipropylene glycol, butylene glycol, hexane triol, and the like, and polymers thereof; and mixtures thereof. Also useful herein as hydroxyl plasticizers are poloxomers and poloxamines. Also suitable for use herein are hydrogen bond forming organic compounds which do not have hydroxyl group, including urea and urea derivatives; anhydrides of sugar alcohols such as sorbitan; animal proteins such as gelatin; vegetable proteins such as sunflower protein, soybean proteins, cotton seed proteins; and mixtures thereof. Other suitable plasticizers are phthalate esters, dimethyl and diethylsuccinate and related esters, glycerol triacetate, glycerol mono and diacetates, glycerol mono, di, and tripropionates, and butanoates, which are biodegradable. Aliphatic acids such as ethylene acrylic acid, ethylene maleic acid, butadiene acrylic acid, butadiene maleic acid, propylene acrylic acid, propylene maleic acid, and other hydrocarbon based acids. All of the plasticizers may be use alone or in mixtures thereof.

Preferred plasticizers include glycerin, mannitol, and sorbitol, with sorbitol being the most preferred. The amount of plasticizer is dependent upon the molecular weight, amount of starch, and the affinity of the plasticizer for the starch. Generally, the amount of plasticizer increases with increasing molecular weight of starch.

The thermoplastic starch can be present in the compositions disclosed herein in a weight percent of about 10 wt% to about 80 wt%, about 10 wt% to about 60 wt%, or about 20 wt% to about 40 wt%, based upon the total weight of the composition. Specific contemplated amounts of thermoplastic starch include about 10 wt%, about 11 wt%, about 12 wt%, about 13 wt%, about 14 wt%, about 15 wt%, about 16 wt%, about 17 wt%, about 18 wt%, about 19 wt%, about 20 wt%, about 21 wt%, about 22 wt%, about 23 wt%, about 24 wt%, about 25 wt%, about 26 wt%, about 27 wt%, about 28 wt%, about 29 wt%, about 30 wt%, about 31 wt%, about 32 wt%, about 33 wt%, about 34 wt%, about 35 wt%, about 36 wt%, about 37 wt%, about 38 wt%, about 39 wt%, about 40 wt%, about 41 wt%, about 42 wt%, about 43 wt%, about 44 wt%, about 45 wt%, about 46 wt%, about 47 wt%, about 48 wt%, about 49 wt%, about 50 wt%, about 51 wt%, about 52 wt%, about 53 wt%, about 54 wt%, about 55 wt%, about 56 wt%, about 57 wt%, about 58 wt%, about 59 wt%, about 60 wt%, about 61 wt%, about 62 wt%, about 63 wt%, about 64 wt%, about 65 wt%, about 66 wt%, about 67



More specifically, however, the thermoplastic polymers preferably include polyolefins such as polyethylene or copolymers thereof, including low, high, linear low, or ultra low density polyethylenes, polypropylene or copolymers thereof, including atactic polypropylene; isotactic polypropylene, metallocene isotactic polypropylene, polybutylene or  
5 copolymers thereof; polyamides or copolymers thereof, such as Nylon 6, Nylon 11, Nylon 12, Nylon 46, Nylon 66; polyesters or copolymers thereof, such as maleic anhydride polypropylene copolymer, polyethylene terephthalate; olefin carboxylic acid copolymers such as ethylene/acrylic acid copolymer, ethylene/maleic acid copolymer, ethylene/methacrylic acid copolymer, ethylene/vinyl acetate copolymers or combinations  
10 thereof; polyacrylates, polymethacrylates, and their copolymers such as poly(methyl methacrylates). Other nonlimiting examples of polymers include polycarbonates, polyvinyl acetates, poly(oxymethylene), styrene copolymers, polyacrylates, polymethacrylates, poly(methyl methacrylates), polystyrene/methyl methacrylate copolymers, polyetherimides, polysulfones, or combinations thereof. In some embodiments, thermoplastic polymers include  
15 polypropylene, polyethylene, polyamides, polyvinyl alcohol, ethylene acrylic acid, polyolefin carboxylic acid copolymers, polyesters, and combinations thereof.

More specifically, however, the thermoplastic polymers preferably include polyolefins such as polyethylene or copolymers thereof, including low density, high density, linear low density, or ultra low density polyethylenes such that the polyethylene density  
20 ranges between 0.90grams per cubic centimeter to 0.97 grams per cubic centimeter, most preferred between 0.92 and 0.95 grams per cubic centimeter. The density of the polyethylene will is determined by the amount and type of branching and depends on the polymerization technology and comonomer type. Polypropylene and/or polypropylene copolymers, including atactic polypropylene; isotactic polypropylene, syndiotactic polypropylene, and  
25 combination thereof can also be used. Polypropylene copolymers, especially ethylene can be used to lower the melting temperature and improve properties. These polypropylene polymers can be produced using metallocene and Ziegler-Natta catalyst systems. These polypropylene and polyethylene compositions can be combined together to optimize end-use properties. Polybutylene is also a useful polyolefin.

30 Biodegradable thermoplastic polymers also are contemplated for use herein. Biodegradable materials are susceptible to being assimilated by microorganisms, such as molds, fungi, and bacteria when the biodegradable material is buried in the ground or otherwise contacts the microorganisms (including contact under environmental conditions conducive to the growth of the microorganisms). Suitable biodegradable polymers also

include those biodegradable materials which are environmentally-degradable using aerobic or anaerobic digestion procedures, or by virtue of being exposed to environmental elements such as sunlight, rain, moisture, wind, temperature, and the like. The biodegradable thermoplastic polymers can be used individually or as a combination of biodegradable or non-biodegradable polymers. Biodegradable polymers include polyesters containing aliphatic components. Among the polyesters are ester polycondensates containing aliphatic constituents and poly(hydroxycarboxylic) acid. The ester polycondensates include diacids/diol aliphatic polyesters such as polybutylene succinate, polybutylene succinate co-adipate, aliphatic/aromatic polyesters such as terpolymers made of butylene diol, adipic acid and terephthalic acid. The poly(hydroxycarboxylic) acids include lactic acid based homopolymers and copolymers, polyhydroxybutyrate (PHB), or other polyhydroxyalkanoate homopolymers and copolymers. Such polyhydroxyalkanoates include copolymers of PHB with higher chain length monomers, such as C<sub>6</sub>-C<sub>12</sub>, and higher, polyhydroxyalkanoates, such as those disclosed in U.S. Patent Nos. RE 36,548 and 5,990,271.

An example of a suitable commercially available polylactic acid is NATUREWORKS from Cargill Dow and LACEA from Mitsui Chemical. An example of a suitable commercially available diacid/diol aliphatic polyester is the polybutylene succinate/adipate copolymers sold as BIONOLLE 1000 and BIONOLLE 3000 from the Showa High Polymer Company, Ltd. (Tokyo, Japan). An example of a suitable commercially available aliphatic/aromatic copolyester is the poly(tetramethylene adipate-co-terephthalate) sold as EASTAR BIO Copolyester from Eastman Chemical or ECOFLEX from BASF.

Non-limiting examples of suitable commercially available polypropylene or polypropylene copolymers include Basell Profax PH-835 (a 35 melt flow rate Ziegler-Natta isotactic polypropylene from Lyondell-Basell), Basell Metocene MF-650W (a 500 melt flow rate metallocene isotactic polypropylene from Lyondell-Basell), Polybond 3200 (a 250 melt flow rate maleic anhydride polypropylene copolymer from Crompton), Exxon Achieve 3854 (a 25 melt flow rate metallocene isotactic polypropylene from Exxon-Mobil Chemical), Mosten NB425 (a 25 melt flow rate Ziegler-Natta isotactic polypropylene from Unipetrol), Danimer 27510 (a polyhydroxyalkanoate polypropylene from Danimer Scientific LLC), Dow Aspun 6811A (a 27 melt index polyethylene polypropylene copolymer from Dow Chemical), and Eastman 9921 (a polyester terephthalic homopolymer with a nominally 0.81 intrinsic viscosity from Eastman Chemical).

The thermoplastic polymer component can be a single polymer species as described above or a blend of two or more thermoplastic polymers as described above.

If the polymer is polypropylene, the thermoplastic polymer can have a melt flow index of greater than 5 g/10 min, as measured by ASTM D-1238, used for measuring polypropylenes. Other contemplated melt flow indices include greater than 10 g/10 min, greater than 20 g/10 min, or about 5 g/10 min to about 50 g/10 min.

## 5 **Oils and Waxes**

An oil or wax, as used in the disclosed composition, is a lipid, mineral oil (or wax), or combination thereof. An oil is used to refer to a compound that is liquid at room temperature (e.g., has a melting point of 25°C or less) while a wax is used to refer to a compound that is a solid at room temperature (e.g., has a melting point of greater than 25°C). The wax can also  
10 have a melting point lower than the melting temperature of the highest volumetric polymer component in the composition. The term wax hereafter can refer to the component either in the solid crystalline state or in the molten state, depending on the temperature. The wax can be solid at a temperature at which the thermoplastic polymer and/or thermoplastic starch are solid. For example, polypropylene is a semicrystalline solid at 90°C, which can be above  
15 melting temperature of the wax.

The lipid can be a monoglyceride, diglyceride, triglyceride, fatty acid, fatty alcohol, esterified fatty acid, epoxidized lipid, maleated lipid, hydrogenated lipid, alkyd resin derived from a lipid, sucrose polyester, or combinations thereof. The mineral oil or wax can be a linear alkane, a branched alkane, or combinations thereof. The waxes can be partially or fully  
20 hydrogenated materials, or combinations and mixtures thereof, that were formally liquids at room temperature in their unmodified forms.

Non-limiting examples of oils or waxes contemplated in the compositions disclosed herein include beef tallow, castor oil, coconut oil, coconut seed oil, corn germ oil, cottonseed oil, fish oil, linseed oil, olive oil, oiticica oil, palm kernel oil, palm oil, palm seed oil, peanut oil,  
25 rapeseed oil, safflower oil, soybean oil, sperm oil, sunflower seed oil, tall oil, tung oil, whale oil, and combinations thereof. Non-limiting examples of specific triglycerides include triglycerides such as, for example, tristearin, triolein, tripalmitin, 1,2-dipalmitoolein, 1,3-dipalmitoolein, 1-palmito-3-stearo-2-olein, 1-palmito-2-stearo-3-olein, 2-palmito-1-stearo-3-olein, trilinolein, 1,2-dipalmitolinolein, 1-palmito-dilinolein, 1-stearo-dilinolein, 1,2-  
30 diacetopalmitin, 1,2-distearo-olein, 1,3-distearo-olein, trimyristin, trilaurin and combinations thereof. Non-limiting examples of specific fatty acids contemplated include capric acid, caproic acid, caprylic acid, lauric acid, lauroleic acid, linoleic acid, linolenic acid, myristic

acid, myristoleic acid, oleic acid, palmitic acid, palmitoleic acid, stearic acid, and mixtures thereof.

The oil or wax can be from a renewable material (e.g., derived from a renewable resource). As used herein, a “renewable resource” is one that is produced by a natural process at a rate  
5 comparable to its rate of consumption (e.g., within a 100 year time frame). The resource can be replenished naturally, or via agricultural techniques. Non-limiting examples of renewable resources include plants (e.g., sugar cane, beets, corn, potatoes, citrus fruit, woody plants, lignocellulosics, hemicellulosics, cellulosic waste), animals, fish, bacteria, fungi, and forestry products. These resources can be naturally occurring, hybrids, or genetically engineered  
10 organisms. Natural resources such as crude oil, coal, natural gas, and peat, which take longer than 100 years to form, are not considered renewable resources. Mineral oil, petroleum, and petroleum jelly are viewed as a by-product waste stream of coal, and while not renewable, it can be considered a by-product oil.

The wax number average molecular weight, as determined by gel permeation  
15 chromatography (GPC), should be less than 2kDa, preferably less than 1.5kDa, still more preferred less than 1.2kDa.

The amount of wax is determined via gravimetric weight loss method. The solidified mixture is placed, with the narrowest specimen dimension no greater than 1mm, into acetone at a ratio of 1g or mixture per 100g of acetone using a refluxing flask system. First the  
20 mixture is weighed before being placed into the reflux flask, and then the acetone and mixtures are heated to 60°C for 20hours. The sample is removed and air dried for 60 minutes and a final weight determined. The equation for calculating the weight percent wax is

$$\text{weight \% wax} = ([\text{initial mass} - \text{final mass}] / [\text{initial mass}]) \times 100\%$$

25 Because the oil may contain a distribution of melting temperatures to generate a peak melting temperature, the oil melting temperature is defined as having a peak melting temperature 25°C or below as defined when > 50 weight percent of the oil component melts at or below 25°C. This measurement can be made using a differential scanning calorimeter (DSC), where the heat of fusion is equated to the weight percent fraction of the oil.

30 The oil number average molecular weight, as determined by gel permeation chromatography (GPC), should be less than 2kDa, preferably less than 1.5kDa, still more preferred less than 1.2kDa.

The amount of oil is determined via gravimetric weight loss method. The solidified mixture is placed, with the narrowest specimen dimension no greater than 1mm, into hexane (or acetone) at a ratio of 1g of mixture per 100g of hexane using a refluxing flask system. First the mixture is weighed before being placed into the reflux flask, and then the hexane and mixtures are heated to 60°C for 20hours. The sample is removed and air dried for 60 minutes and a final weight determined. The equation for calculating the weight percent oil is

$$\text{weight \% oil} = ([\text{initial mass} - \text{final mass}] / [\text{initial mass}]) \times 100\%$$

The oil or wax, as disclosed herein, is present in the composition at a weight percent of about 5 wt% to about 40 wt%, based upon the total weight of the composition. Other contemplated wt% ranges of the oil or wax include about 8 wt% to about 30 wt%, with a preferred range from about 10 wt% to about 30 wt%, about 10 wt% to about 20 wt%, or about 12 wt% to about 18 wt%, based upon the total weight of the composition. Specific oil or wax wt% contemplated include about 5 wt%, about 6 wt%, about 7 wt%, about 8 wt%, about 9 wt%, about 10 wt%, about 11 wt%, about 12 wt%, about 13 wt%, about 14 wt%, about 15 wt%, about 16 wt%, about 17 wt%, about 18 wt%, about 19 wt%, about 20 wt%, about 21 wt%, about 22 wt%, about 23 wt%, about 24 wt%, about 25 wt%, about 26 wt%, about 27 wt%, about 28 wt%, about 29 wt%, about 30 wt%, about 31 wt%, about 32 wt%, about 33 wt%, about 34 wt%, about 35 wt%, about 36 wt%, about 37 wt%, about 38 wt%, about 39 wt%, and about 40 wt%, based upon the total weight of the composition.

## 20 **Additives**

The compositions disclosed herein can further include an additive. The additive can be dispersed throughout the composition, or can be substantially in the thermoplastic polymer portion of the thermoplastic layer, substantially in the oil portion of the composition, or substantially in the TPS portion of the composition. In cases where the additive is in the oil portion of the composition, the additive can be oil soluble or oil dispersible. Alkyd resins can also be added to the composition. Alkyd resins comprise, for example, polyols, polyacids, and/or anhydrides.

Non-limiting examples of classes of additives contemplated in the compositions disclosed herein include perfumes, dyes, pigments, nanoparticles, antistatic agents, fillers, and combinations thereof. The compositions disclosed herein can contain a single additive or a mixture of additives. For example, both a perfume and a colorant (e.g., pigment and/or dye) can be present in the composition. The additive(s), when present, is/are present in a weight percent of about 0.05 wt% to about 20 wt%, or about 0.1 wt% to about 10 wt%.

Specifically contemplated weight percentages include about 0.5 wt%, about 0.6 wt%, about 0.7 wt%, about 0.8 wt%, about 0.9 wt%, about 1 wt%, about 1.1 wt%, about 1.2 wt%, about 1.3 wt%, about 1.4 wt%, about 1.5 wt%, about 1.6 wt%, about 1.7 wt%, about 1.8 wt%, about 1.9 wt%, about 2 wt%, about 2.1 wt%, about 2.2 wt%, about 2.3 wt%, about 2.4 wt%, about 2.5 wt%, about 2.6 wt%, about 2.7 wt%, about 2.8 wt%, about 2.9 wt%, about 3 wt%, about 3.1 wt%, about 3.2 wt%, about 3.3 wt%, about 3.4 wt%, about 3.5 wt%, about 3.6 wt%, about 3.7 wt%, about 3.8 wt%, about 3.9 wt%, about 4 wt%, about 4.1 wt%, about 4.2 wt%, about 4.3 wt%, about 4.4 wt%, about 4.5 wt%, about 4.6 wt%, about 4.7 wt%, about 4.8 wt%, about 4.9 wt%, about 5 wt%, about 5.1 wt%, about 5.2 wt%, about 5.3 wt%, about 5.4 wt%, about 5.5 wt%, about 5.6 wt%, about 5.7 wt%, about 5.8 wt%, about 5.9 wt%, about 6 wt%, about 6.1 wt%, about 6.2 wt%, about 6.3 wt%, about 6.4 wt%, about 6.5 wt%, about 6.6 wt%, about 6.7 wt%, about 6.8 wt%, about 6.9 wt%, about 7 wt%, about 7.1 wt%, about 7.2 wt%, about 7.3 wt%, about 7.4 wt%, about 7.5 wt%, about 7.6 wt%, about 7.7 wt%, about 7.8 wt%, about 7.9 wt%, about 8 wt%, about 8.1 wt%, about 8.2 wt%, about 8.3 wt%, about 8.4 wt%, about 8.5 wt%, about 8.6 wt%, about 8.7 wt%, about 8.8 wt%, about 8.9 wt%, about 9 wt%, about 9.1 wt%, about 9.2 wt%, about 9.3 wt%, about 9.4 wt%, about 9.5 wt%, about 9.6 wt%, about 9.7 wt%, about 9.8 wt%, about 9.9 wt%, and about 10 wt%.

As used herein the term “perfume” is used to indicate any odoriferous material that is subsequently released from the composition as disclosed herein. A wide variety of chemicals are known for perfume uses, including materials such as aldehydes, ketones, alcohols, and esters. More commonly, naturally occurring plant and animal oils and exudates including complex mixtures of various chemical components are known for use as perfumes. The perfumes herein can be relatively simple in their compositions or can include highly sophisticated complex mixtures of natural and synthetic chemical components, all chosen to provide any desired odor. Typical perfumes can include, for example, woody/earthy bases containing exotic materials, such as sandalwood, civet and patchouli oil. The perfumes can be of a light floral fragrance (e.g. rose extract, violet extract, and lilac). The perfumes can also be formulated to provide desirable fruity odors, e.g. lime, lemon, and orange. The perfumes delivered in the compositions and articles of the present invention can be selected for an aromatherapy effect, such as providing a relaxing or invigorating mood. As such, any material that exudes a pleasant or otherwise desirable odor can be used as a perfume active in the compositions and articles of the present invention.

A pigment or dye can be inorganic, organic, or a combination thereof. Specific examples of pigments and dyes contemplated include pigment Yellow (C.I. 14), pigment Red

(C.I. 48:3), pigment Blue (C.I. 15:4), pigment Black (C.I. 7), and combinations thereof.

Specific contemplated dyes include water soluble ink colorants like direct dyes, acid dyes, base dyes, and various solvent soluble dyes. Examples include, but are not limited to, FD&C Blue 1 (C.I. 42090:2), D&C Red 6(C.I. 15850), D&C Red 7(C.I. 15850:1), D&C Red 9(C.I. 15585:1), D&C Red 21(C.I. 45380:2), D&C Red 22(C.I. 45380:3), D&C Red 27(C.I. 45410:1), D&C Red 28(C.I. 45410:2), D&C Red 30(C.I. 73360), D&C Red 33(C.I. 17200), D&C Red 34(C.I. 15880:1), and FD&C Yellow 5(C.I. 19140:1), FD&C Yellow 6(C.I. 15985:1), FD&C Yellow 10(C.I. 47005:1), D&C Orange 5(C.I. 45370:2), and combinations thereof.

10 Contemplated fillers include, but are not limited to inorganic fillers such as, for example, the oxides of magnesium, aluminum, silicon, and titanium. These materials can be added as inexpensive fillers or processing aides. Other inorganic materials that can function as fillers include hydrous magnesium silicate, titanium dioxide, calcium carbonate, clay, chalk, boron nitride, limestone, diatomaceous earth, mica glass quartz, and ceramics.

15 Additionally, inorganic salts, including alkali metal salts, alkaline earth metal salts, phosphate salts, can be used.

Contemplated surfactants include anionic surfactants, amphoteric surfactants, or a combination of anionic and amphoteric surfactants, and combinations thereof, such as surfactants disclosed, for example, in U.S. Patent Nos. 3,929,678 and 4,259,217 and in EP 20 414 549, WO93/08876 and WO93/08874.

Contemplated nanoparticles include metals, metal oxides, allotropes of carbon, clays, organically modified clays, sulfates, nitrides, hydroxides, oxy/hydroxides, particulate water-insoluble polymers, silicates, phosphates and carbonates. Examples include silicon dioxide, carbon black, graphite, grapheme, fullerenes, expanded graphite, carbon nanotubes, talc, 25 calcium carbonate, betonite, montmorillonite, kaolin, silica, aluminosilicates, boron nitride, aluminum nitride, barium sulfate, calcium sulfate, antimony oxide, feldspar, mica, nickel, copper, iron, cobalt, steel, gold, silver, platinum, aluminum, wollastonite, aluminum oxide, zirconium oxide, titanium dioxide, cerium oxide, zinc oxide, magnesium oxide, tin oxide, iron oxides ( $\text{Fe}_2\text{O}_3$ ,  $\text{Fe}_3\text{O}_4$ ) and mixtures thereof. Nanoparticles can increase strength, 30 thermal stability, and/or abrasion resistance of the compositions disclosed herein, and can give the compositions electric properties.

Additional contemplated additives include nucleating and clarifying agents for the thermoplastic polymer. Specific examples, suitable for polypropylene, for example, are

benzoic acid and derivatives (e.g. sodium benzoate and lithium benzoate), as well as kaolin, talc and zinc glycerolate. Dibenzlidene sorbitol (DBS) is an example of a clarifying agent that can be used. Other nucleating agents that can be used are organocarboxylic acid salts, sodium phosphate and metal salts (for example aluminum dibenzoate). The nucleating or  
5 clarifying agents can be added in ranges from 20 parts per million (20ppm) to 20,000ppm, more preferred range of 200ppm to 2000ppm and the most preferred range from 1000ppm to 1500ppm. The addition of the nucleating agent can be used to improve the tensile and impact properties of the finished admixture composition.

Contemplated anti-static agents include fabric softeners which are known to provide antistatic  
10 benefits. For example those fabric softeners that have a fatty acyl group which has an iodine value of above 20, such as N,N-di(tallowoyl-oxy-ethyl)-N,N-dimethyl ammonium methylsulfate.

### **Molded Articles**

Compositions as disclosed herein can be formed into molded or extruded articles. A  
15 molded article is an object that is formed when injected, compressed, or blown by means of a gas into shape defined by a female mold. Molded or extruded articles may be solid objects such as, for example, toys, or hollow objects such as, for example, bottles, containers, tampon applicators, applicators for insertion of medications into bodily orifices, medical equipment for single use, surgical equipment, or the like. Molded articles and processes for preparing  
20 them are generally described, e.g., in U.S. Patent No. 6,730,057 and U.S. Patent Publication No. 2009/0269527, each of which is incorporated by reference herein.

The composition disclosed herein is suitable for producing container articles, such as personal care products, household cleaning products, and laundry detergent products, and packaging for such articles. Personal care products include cosmetics, hair care, skin care,  
25 and oral care products, i.e., shampoo, soap, tooth paste. Accordingly, further disclosed herein is product packaging, such as containers or bottles comprising the composition described herein. A container can refer to one or more elements of a container, e.g., body, cap, nozzle, handle, or a container in its entirety, e.g., body and cap.

The products may include a container, made from the composition, and an indicia  
30 associated with the container, which educates a potential buyer about the container. Such indicia associated with the container include a label, an insert, a page in a magazine or newspaper, a sticker, a coupon, a flyer, an in-aisle or end-of-aisle display, and point-of-sale

items intended to either be taken by prospective buyers or remain in an area proximate the product.

Furthermore, the molded articles can comprise other additives, such as other polymers materials (e.g., a polypropylene, a polyethylene, a ethylene vinyl acetate, a polymethylpentene any combination thereof, or the like), a filler (e.g., glass, talc, calcium carbonate, or the like), a mold release agent, a flame retardant, an electrically conductive agent, a film anti-static agent, a pigment, an antioxidant, an impact modifier, a stabilizer (e.g., a UV absorber), wetting agents, dyes, or any combination thereof. Molded article antistatic agents include cationic, anionic, and, preferably, nonionic agents. Cationic agents include ammonium, phosphonium and sulphonium cations, with alkyl group substitutions and an associated anion such as chloride, methosulphate, or nitrate. Anionic agents contemplated include alkylsulphonates. Nonionic agents include polyethylene glycols, organic stearates, organic amides, glycerol monostearate (GMS), alkyl di-ethanolamides, and ethoxylated amines.

15

#### **Processes of Making the Compositions as Disclosed herein**

Melt mixing of the polymer, starch, and oil: The polymer, TPS, and oil and/or wax can be suitably mixed by melting the polymer and TPS in the presence of the oil and/or wax. It should be understood that when the thermoplastic polymer and TPS are melted, the wax will also be in the molten state. In the melt state, the polymer, TPS, and oil and/or wax are subjected to shear which enables a dispersion of the oil into the polymer and/or TPS. In the melt state, the oil and/or wax and polymer and/or TPS are significantly more compatible with each other.

The melt mixing of the thermoplastic polymer, TPS, and oil and/or wax can be accomplished in a number of different processes, but processes with high shear are preferred to generate the preferred morphology of the composition. The processes can involve traditional thermoplastic polymer processing equipment. The general process order involves adding the thermoplastic polymer and TPS to the system, melting the thermoplastic polymer and TPS, and then adding the oil and/or wax. However, the materials can be added in any order, depending on the nature of the specific mixing system.

For the disclosed processes, the thermoplastic starch (TPS) is prepared prior to mixing with a thermoplastic polymer and/or an oil and/or wax. U.S. Patent Nos. 7,851,391, 6,783,854 and 6,818,295 describe processes for producing TPS. However, TPS can be made in-line and the

thermoplastic polymer and oil/wax combined in the same production process to make the compositions as disclosed herein in a single step process. For example, the starch, starch plasticizer and thermoplastic polymer are combined first in a twin-screw extruder where TPS is formed in the presence of the thermoplastic polymer. Later, the oil/wax is introduced into the TPS/thermoplastic polymer mixture via a second feeding location.

Single Screw Extruder: A single screw extruder is a typical process unit used in most molten polymer extrusion. The single screw extruder typically includes a single shaft within a barrel, the shaft and barrel engineered with certain screw elements (e.g., shapes and clearances) to adjust the shearing profile. A typical RPM range for single screw extruder is about 10 to about 120. The single screw extruder design is composed of a feed section, compression section and metering section. In the feed section, using fairly high void volume flights, the polymer is heated and supplied into the compression section, where the melting is completed and the fully molten polymer is sheared. In the compression section, the void volume between the flights is reduced. In the metering section, the polymer is subjected to its highest shearing amount using low void volume between flights. For this work, general purpose single screw designs were used. In this unit, a continuous or steady state type of process is achieved where the composition components are introduced at desired locations, and then subjected to temperatures and shear within target zones. The process can be considered to be a steady state process as the physical nature of the interaction at each location in the single screw process is constant as a function of time. This allows for optimization of the mixing process by enabling a zone-by-zone adjustment of the temperature and shear, where the shear can be changed through the screw elements and/or barrel design or screw speed.

The mixed composition exiting the single screw extruder can then be pelletized via extrusion of the melt into a liquid cooling medium, often water, and then the polymer strand can be cut into small pieces. There are two basic types of molten polymer pelletization process used in polymer processing: strand cutting and underwater pelletization. In strand cutting the composition is rapidly quenched (generally much less than 10 seconds) in the liquid medium then cut into small pieces. In the underwater pelletization process, the molten polymer is cut into small pieces then simultaneously or immediately thereafter placed in the presence of a low temperature liquid which rapidly quenches and crystallizes the polymer. These methods are commonly known and used within the polymer processing industry.

The polymer strands that come from the extruder are rapidly placed into a water bath, most often having a temperature range of 1°C to 50°C (e.g., normally is about room temperature, which is 25°C). An alternate end use for the mixed composition is further processing into the

desired structure, for example fiber spinning or injection molding. The single screw extrusion process can provide for a high level of mixing and high quench rate. A single screw extruder also can be used to further process a pelletized composition into fibers and injection molded articles. For example, the fiber single screw extruder can be a 37 mm  
5 system with a standard general purpose screw profile and a 30:1 length to diameter ratio.

For example, the fiber single screw extruder is a 37mm system with a standard general purpose screw profile and a 30:1 length to diameter ratio. In the single screw extruder case, already produced TPS and thermoplastic polymer can be combined with the oil/wax, or already produced TPS can be combined with oil/wax that is already dispersed within a  
10 thermoplastic polymer. In the first case, an already produced TPS formulation can be melted and the oil/wax additive directly injected into the single screw extruder, followed directly by fiber spinning or final end-use product. The mixing is achieved directly within the single screw extruder. In a second case, the oil/wax is added into the TPS in a second step after the base TPS formulation is produced, similar to the procedure for adding it to a thermoplastic  
15 polymer, such as, for example, polypropylene.

Twin Screw Extruder: A twin screw extruder is the typical unit used in most molten polymer extrusion, where high intensity mixing is required. The twin screw extruder includes two shafts and an outer barrel. A typical RPM range for twin screw extruder is about 10 to about 1200. The two shafts can be co-rotating or counter rotating and allow for  
20 close tolerance, high intensity mixing. In this type of unit, a continuous or steady state type of process is achieved where the composition components are introduced at desired locations along the screws, and subjected to high temperatures and shear within target zones. The process can be considered to be a steady state process as the physical nature of the interaction at each location in the single screw process is constant as a function of time. This allows for  
25 optimization of the mixing process by enabling a zone-by-zone adjustment of the temperature and shear, where the shear can be changed through the screw elements and/or barrel design.

The mixed composition at the end of the twin screw extruder can then be pelletized via extrusion of the melt into a liquid cooling medium, often water, and then the polymer strand is cut into small pieces. There are two basic types of molten polymer pelletization process,  
30 strand cutting and underwater pelletization, used in polymer processing. In strand cutting the composition is rapidly quenched (generally much less than 10s) in the liquid medium then cut into small pieces. In the underwater pelletization process, the molten polymer is cut into small pieces then simultaneously or immediately thereafter placed in the presence of a low temperature liquid which rapidly quenches and crystallizes the polymer. An alternate end use

for the mixed composition is further processing into the desired structure, for example fiber spinning or injection molding.

Three different screw profiles can be employed using a Baker Perkins CT-25 25mm corotating 40:1 length to diameter ratio system. This specific CT-25 is composed of nine zones where the temperature can be controlled, as well as the die temperature. Four liquid injection sites as also possible, located between zone 1 and 2 (location A), zone 2 and 3 (location B), zone 4 and 5 (location C). and zone 6 and 7 (location D).

The liquid injection location is not directly heated, but indirectly through the adjacent zone temperatures. Locations A, B, C and D can be used to inject the additive. Zone 6 can contain a side feeder for adding additional solids or used for venting. Zone 8 contains a vacuum for removing any residual vapor, as needed. Unless noted otherwise, the melted wax is injected at location A. The wax is melted via a glue tank and supplied to the twin-screw via a heated hose Both the glue tank and the supply hose are heated to a temperature greater than the melting point of the wax (e.g., about 80°C).

Two types of regions, conveyance and mixing, are used in the CT-25. In the conveyance region, the materials are heated (including through melting which is done in Zone 1 into Zone 2 if needed) and conveyed along the length of the barrel, under low to moderate shear. The mixing section contains special elements that dramatically increase shear and mixing. The length and location of the mixing sections can be changed as needed to increase or decrease shear as needed.

Two primary types of mixing elements are used for shearing and mixing. The first are kneading blocks and the second are thermal mechanical energy elements. The simple mixing screw has 10.6% of the total screw length using mixing elements composed of kneading blocks in a single set followed by a reversing element. The kneading elements are RKB 45/5/12 (right handed forward kneading block with 45° offset and five lobes at 12mm total element length), followed by two RKB 45/5/36 (right handed forward kneading block with 45° offset and five lobes at 36mm total element length), that is followed by two RKB 45/5/12 and reversing element 24/12 LH (left handed reversing element 24mm pitch at 12mm total element length).

The Simple mixing screw mixing elements are located in zone 7. The Intensive screw is composed of additional mixing sections, four in total. The first section is single set of kneading blocks is a single element of RKB45/5/36 (located in zone 2) followed by conveyance elements into zone 3 where the second mixing zone is located. In the second

mixing zone, two RKB 45/5/36 elements are directly followed by four TME 22.5/12 (thermomechanical element with 22.5 teeth per revolution and total element length of 12mm) then two conveyance elements into the third mixing area. The third mixing area, located at the end of zone 4 into zone 5, is composed of three RKB 45/5/36 and a KB45/5/12 LH (left handed forward reversing block with 45° offset and five lobes at 12mm total element length. The material is conveyed through zone 6 into the final mixing area comprising two TME 22.5/12, seven RKB 45/5/12, followed by SE 24/12 LH. The SE 24/12 LH is a reversing element that enables the last mixing zone to be completely filled with polymer and additive, where the intensive mixing takes place. The reversing elements can control the residence time in a given mixing area and are a key contributor to the level of mixing.

The High Intensity mixing screw is composed of three mixing sections. The first mixing section is located in zone 3 and is two RKB45/5/36 followed by three TME 22.5/12 and then conveyance into the second mixing section. Prior to the second mixing section three RSE 16/16 (right handed conveyance element with 16mm pitch and 16mm total element length) elements are used to increase pumping into the second mixing region. The second mixing region, located in zone 5, is composed of three RKB 45/5/36 followed by a KB 45/5/12 LH and then a full reversing element SE 24/12 LH. The combination of the SE 16/16 elements in front of the mixing zone and two reversing elements greatly increases the shear and mixing. The third mixing zone is located in zone 7 and is composed of three RKB 45/5/12, followed by two TME 22.5.12 and then three more RKB45/5/12. The third mixing zone is completed with a reversing element SE 24/12 LH.

An additional screw element type is a reversing element, which can increase the filling level in that part of the screw and provide better mixing. Twin screw compounding is a mature field. One skilled in the art can consult books for proper mixing and dispersion. These types of screw extruders are well understood in the art and a general description can be found in: Twin Screw Extrusion 2E: Technology and Principles by James White from Hansen Publications. Although specific examples are given for mixing, many different combinations are possible using various element configurations to achieve the needed level of mixing.

For in-line production of TPS, 70wt% solids sorbitol solution can be used to destructure and plasticize the starch to produce TPS. A side feeder can be installed in Zone 6 to vent off the majority of the moisture from the starch and liquid sorbitol. The thermoplastic polymer (e.g., polypropylene or other thermoplastic polymers as described herein) can then added to the destructured starch. The oil/wax can be heated and added into the compounding system at location C or D. In the case where the TPS formulation and the oil/wax are added in the

same process, use of a longer L:D ratio extruder is preferred to increase mixing and enable the various process steps to be separated. Extruder ratio above 40:1 are contemplated, preferably up to 60:1 and even longer are considered.

### **Properties of Compositions**

- 5 The compositions as disclosed herein can have one or more of the following properties that provide an advantage over known thermoplastic compositions. These benefits can be present alone or in a combination.

Shear Viscosity Reduction: Viscosity reduction is a process improvement as it can allow for effectively higher polymer flow rates by having a reduced process pressure (lower shear  
10 viscosity), or can allow for an increase in polymer and/or TPS molecular weight, which improves the material strength. Without the presence of the oil/wax, it may not be possible to process the polymer and/or TPS with a high polymer flow rate at existing process conditions in a suitable way. Alternatively, the presence of the oil/wax can enable lower process  
15 temperatures, which can reduce degradation of the various components (for instance, the TPS component).

Sustainable Content: Inclusion of sustainable materials into the existing polymeric system is a strongly desired property. Materials that can be replaced every year through natural growth cycles contribute to overall lower environmental impact and are desired.

Pigmentation: Adding pigments to polymers often involves using expensive inorganic  
20 compounds that are particles within the polymer matrix. These particles are often large and can interfere in the processing of the composition. Using an oil and/or wax as disclosed herein, because of the fine dispersion (as measured by droplet size) and uniform distribution throughout the thermoplastic polymer and/or TPS allows for coloration, such as via  
25 traditional ink compounds. Soy ink is widely used in paper publication) that does not impact processability.

Fragrance: Because the oils and/or waxes, for example SBO or HSBO, can contain perfumes much more preferentially than the base thermoplastic polymer and/or TPS, the present composition can be used to contain scents that are beneficial for end-use. Many scented  
30 candles are made using SBO based or paraffin based materials, so incorporation of these into the polymer for the final composition is useful.

Morphology: The benefits are delivered via the morphology produced in production of the compositions. The morphology is produced by a combination of intensive mixing and rapid crystallization. The intensive mixing comes from the compounding process used and rapid

crystallization comes from the cooling process used. High intensity mixing is desired and rapid crystallization is used to preserve the fine pore size and relatively uniform pore size distribution.

Water Resistance: Adding a hydrophobic material to a TPS material improves water  
5 resistance of the starch.

Surface Feel: The presence of the oil/wax can change the surface properties of the composition, often making it feel softer.

### **Method of Making Molded Articles**

10 The molded articles of the compositions as disclosed herein can be prepared using a variety of techniques, such as injection molding, blow molding, compression molding, or extrusion of pipes, tubes, profiles, or cables.

Injection molding of a composition as disclosed herein is a multi-step process by which the composition is heated until it is molten, then forced into a closed mold where it is  
15 shaped, and finally solidified by cooling. The composition is melt processed at melting temperatures less than about 180°C, more typically less than about 160°C to minimize unwanted thermal degradation. Three common types of machines that are used in injection molding are ram, screw plasticator with injection, and reciprocating screw devices (see  
Encyclopedia of Polymer Science and Engineering, Vol. 8, pp. 102-138, John Wiley and  
20 Sons, New York, 1987 ("EPSE-3").

A ram injection molding machine is composed of a cylinder, spreader, and plunger. The plunger forces the melt in the mold. A screw plasticator with a second stage injection consists of a plasticator, directional valve, a cylinder without a spreader, and a ram. After  
25 plastication by the screw, the ram forces the melt into the mold. A reciprocating screw injection machine is composed of a barrel and a screw. The screw rotates to melt and mix the material and then moves forward to force the melt into the mold.

An example of a suitable injection molding machine is the Engel Tiebarless ES 60 TL apparatus having a mold, a nozzle, and a barrel that is divided into zones wherein each zone is equipped with thermocouples and temperature-control units. The zones of the injection  
30 molding machine can be described as front, center, and rear zones whereby the pellets are introduced into the front zone under controlled temperature. The temperature of the nozzle, mold, and barrel components of the injection molding machine can vary according to the melt

processing temperature of the compositions and the molds used, but will typically be in the following ranges: nozzle, 120-170°C; front zone, 100-160°C; center zone 100-160°C; rear zone 60-150°C; and mold, 5-50°C. Other typical processing conditions include an injection pressure of about 2100 kPa to about 13,790 kPa, a holding pressure of about 2800 kPa to about 11,030 kPa, a hold time of about 2 seconds to about 15 seconds, and an injection speed of from about 2 cm/sec to about 20 cm/sec. Examples of other suitable injection molding machines include Van Dorn Model 150-RS-8F, Battenfeld Model 1600, and Engel Model ES80.

Compression molding involves charging a quantity of a composition as disclosed herein in the lower half of an open die. The top and bottom halves of the die are brought together under pressure, and then molten composition conforms to the shape of the die. The mold is then cooled to harden the plastic.

Blow molding is used for producing bottles and other hollow objects (see EPSE-3). In this process, a tube of molten composition known as a parison is extruded into a closed, hollow mold. The parison is then expanded by a gas, thrusting the composition against the walls of a mold. Subsequent cooling hardens the plastic. The mold is then opened and the article removed.

Blow molding has a number of advantages over injection molding. The pressures used are much lower than injection molding. Blow molding can be typically accomplished at pressures of 25-100 psi between the plastic and the mold surface. By comparison, injection molding pressures can reach 10,000 to 20,000 psi (see EPSE-3). In cases where the composition has a have molecular weights too high for easy flow through molds, blow molding is the technique of choice. High molecular weight polymers often have better properties than low molecular weight analogs, for example high molecular weight materials have greater resistance to environmental stress cracking. (see EPSE-3). It is possible to make extremely thin walls in products with blow molding. This means less composition is used, and solidification times are shorter, resulting in lower costs through material conservation and higher throughput. Another important feature of blow molding is that since it uses only a female mold, slight changes in extrusion conditions at the parison nozzle can vary wall thickness (see EPSE-3). This is an advantage with structures whose necessary wall thicknesses cannot be predicted in advance. Evaluation of articles of several thicknesses can be undertaken, and the thinnest, thus lightest and cheapest, article that meets specifications can be used.

Extrusion is used to form extruded articles, such as pipes, tubes, rods, cables, or profile shapes. Compositions are fed into a heating chamber and moved through the chamber by a continuously revolving screw. Single screw or twin screw extruders are commonly used for plastic extrusion. The composition is plasticated and conveyed through a pipe die head. A haul-off draws the pipe through the calibration and cooling section with a calibration die, a vacuum tank calibration unit and a cooling unit. Rigid pipes are cut to length while flexible pipes are wound. Profile extrusion may be carried out in a one step process. Extrusion procedures are further described in Hensen, F., Plastic Extrusion Technology, p 43-100.

Tampon applicators are molded or extruded in a desired shape or configuration using a variety of molding or extrusion techniques to provide an applicator comprising an outer tubular member and an inner tubular member or plunger. The outer tubular member and plunger can be made by different molding or extrusion techniques. The outer member can be molded or extruded from a composition as disclosed herein and the plunger from another material.

Generally, the process of making tampon applicators involves charging a composition as disclosed herein into a compounder, and the composition is melt blended and processed to pellets. The pellets are then constructed into tampon applicators using an injection molding apparatus. The injection molding process is typically carried out under controlled temperature, time, and speed and involves melt processing the composition such that the melted composition is injected into a mold, cooled, and molded into a desired plastic object. Alternatively, the composition can be charged directly into an injection molding apparatus and the melt molded into the desired tampon applicator.

One example of a procedure of making tampon applicators involves extruding the composition at a temperature above the melting temperature of the composition to form a rod, chopping the rod into pellets, and injection molding the pellets into the desired tampon applicator form.

The compounders that are commonly used to melt blend thermoplastic compositions are generally single-screw extruders, twin-screw extruders, and kneader extruders. Examples of commercially available extruders suitable for use herein include the Black-Clawson single-screw extruders, the Werner and Pfleiderer co-rotating twin-screw extruders, the HAAKE.RTM. PolyLab System counter-rotating twin screw extruders, and the Buss kneader extruders. General discussions of polymer compounding and extrusion molding are disclosed

in the Encyclopedia of Polymer Science and Engineering, Vol. 6, pp. 571-631, 1986, and Vol. 11, pp. 262-285, 1988; John Wiley and Sons, New York.

The tampon applicators can be packaged in any suitable wrapper provided that the wrapper is soil proof and disposable with dry waste. Wrappers made from biodegradable materials that create minimal or no environmental concerns for their disposal are contemplated. It is also contemplated that the tampon applicators can be packaged in wrappers made from paper, nonwoven, cellulose, thermoplastic, or any other suitable material, or combinations of these materials.

Regardless of the method by which the molded article is made, the process involves an annealing cycle. The annealing cycle time is the holding time plus cooling time of the process of making the molded article. With process conditions substantially optimized for a particular mold, an annealing cycle time is a function of the composition. Process conditions substantially optimized are the temperature settings of the zones, nozzle, and mold of the molding apparatus, the shot size, the injection pressure, and the hold pressure. Annealing cycle times provided herein are at least ten seconds less than an annealing cycle time to form a molded or extruded article from a composition as disclosed herein. A dogbone tensile bar having dimensions of 1/2 inch length (L) (12.7 mm)x 1/8 inch width (W) (3.175 mm)x1/16 inch height (H) (1.5875 mm) made using an Engel Tiebarless ES 60 TL injection molding machine as provided herein provides a standard article as representative of a molded or extruded article for measuring annealing cycle times herein.

The holding time is the length of time that a part is held under a holding pressure after initial material injection. The result is that air bubbles and/or sink marks, preferably both, are not visually observable on the exterior surface, preferably both exterior and interior surfaces (if applicable), with the naked eye (of a person with 20--20 vision and no vision defects) from a distance of about 20 cm from the surface of the molded or extruded article. This is to ensure the accuracy and cosmetic quality of the part. Shrinkage is taken into account by the mold design. However, shrinkage of about 1.5% to 5%, from about 1.0% to 2.5%, or 1.2% to 2.0% can occur. A shorter holding time is determined by reducing the holding time until parts do not pass the visual test described supra, do not conform to the shape and texture of the mold, are not completely filled, or exhibit excessive shrinkage. The length of time prior to the time at which such events occur is then recorded as a shorter holding time.

The cooling time is the time for the part to become solidified in the mold and to be ejected readily from the mold. The mold includes at least two parts, so that the molded article

is readily removed. For removal, the mold is opened at the parting line of the two parts. The finished molded part can be removed manually from the opened mold, or it can be pushed out automatically without human intervention by an ejector system as the mold is being opened. Depending on the part geometry, such ejectors may consist of pins or rings, embedded in the mold, that can be pushed forward when the mold is open. For example, the mold can contain  
5 standard dial-type or mechanical rod-type ejector pins to mechanically assist in the ejection of the molded parts. Suitable size rod-type ejector pins are 1/8" (3.175 mm), and the like. A shorter cooling time is determined by reducing the cooling time until parts become hung up on the mold and cannot readily pop out. The length of time prior to the time at which the part  
10 becomes hung up is then recorded as a shorter cooling time.

Processing temperatures that are set low enough to avoid thermal degradation of the composition, yet high enough to allow free flow of the composition for molding are used. The composition is melt processed at melting temperatures less than about 180°C. or, more typically, less than about 160°C to minimize thermal degradation. In general, polymers can  
15 thermally degrade when exposed to temperatures above the degradation temperature after melt for a period of time. As is understood by those skilled in the art in light of the present disclosure, the particular time required to cause thermal degradation will depend upon the particular composition, the length of time above the melt temperature ( $T_m$ ), and the number of degrees above the  $T_m$ . The temperatures can be as low as reasonably possible to allow  
20 free-flow of the polymer melt in order to minimize risk of thermal degradation. During extrusion, high shear in the extruder increases the temperature in the extruder higher than the set temperature. Therefore, the set temperatures may be lower than the melt temperature of the material. Low processing temperatures also help to reduce cycle time. For example, without limitation, the set temperature of the nozzle and barrel components of the injection  
25 molding machine can vary according to the melt processing temperature of the polymeric material and the type of molds used and can be from about 20°C below the  $T_m$  to about 30°C above the  $T_m$ , but will typically be in the following ranges: nozzle, 120-170°C; front zone, 100-160°C; center zone, 100-160°C zone, 60-160°C. The set mold temperature of the injection molding machine is also dependent on the type of composition and the type of  
30 molds used. A higher mold temperature helps polymers crystallize faster and reduces the cycle time. However, if the mold temperature is too high, the parts may come out of the mold deformed. Non-limiting examples of the mold temperature include 5-60°C or 25-50°C.

Molding injection speed is dependent on the flow rate of the compositions. The higher flow rate, the lower viscosity, the lower speed is needed for the injection molding. Injection

speed can range from about 5 cm/sec to 20 cm/sec, in one embodiment, the injection speed is 10 cm/sec. If the viscosity is high, the injection speed is increased so that extruder pressure pushes the melt materials into the mold to fill the mold. The injection molding pressure is dependent on the processing temperature and shot size. Free flow is dependent upon the  
5 injection pressure reading not higher than about 14 Mpa.

### EXAMPLES

Polymers: U.S. Patent No. 6,783,854 provides a comprehensive list of polymers that are compatible with TPS, although not all have been tested. Current polymeric mixtures have the  
10 basic following composition, although it is not limited to the one type described below.

30wt% TPS: Is a mixture of 70wt% polypropylene and 30wt% TPS. The TPS is 70% starch and 30% sorbitol. 10wt% of the polypropylene is maleated PP, Polybond 3200. The remaining PP can be any number of materials, but those used in the present work is 50wt% Basell Profax PH-835 and 50 wt% Basell Metocene MF650W.

15 45wt% TPS: Is a mixture of 70wt% polypropylene and 30wt% TPS. The TPS is 70% starch and 30% sorbitol. 10wt% of the polypropylene is maleated PP, Polybond 3200. The remaining PP can be any number of materials, but those used in the present work is Basell Moplen HP-562T.

Oils/Waxes: Specific examples used were: Soy Bean Oil (SBO); Hydrogenated Soy Bean  
20 Oil (HSBO); Partially Hydrogenated Soy Bean Oil (PHSBO); Epoxidized Soybean Oil (ESBO); Partially Hydrogenated Palm Kernel Oil (PKPKO); candle with pigmentation and fragrance added; and Standard green Soy Bean Green Ink Pigment.

Compositions were made using a Baker Perkins CT-25 Screw twin screw extruder, with the zones set as noted in the below table:

Table

	Polymer	Oil	Ratio		Twin-Screw Temperature Profile (°C)												Melt Temp (°C)	Oil Temp (°C)	Screw RPM	Screw Type	Torque (%)
			Poly-mer	Oil	Z1	Z2	Z3	Z4	Z5	Z6	Z7	Z8	Z9	Die							
1	30wt% TPS	SBO	90	10	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	49	
2	30wt% TPS	SBO	80	20	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	81	
3	30wt% TPS	SBO	75	25	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	37	
4	30wt% TPS	ESBO	90	10	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	52	
5	30wt% TPS	ESBO	85	15	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	40	
6	30wt% TPS	ESBO	80	20	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	36	
7	30wt% TPS	HSBO	90	10	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	55	
8	30wt% TPS	HSBO	85	15	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	48	
9	30wt% TPS	HSBO	80	20	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	43	
10	30wt% TPS	PHSBO	90	10	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	57	
11	30wt% TPS	PHSBO	85	15	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	49	
12	30wt% TPS	PHSBO	80	20	40	130	170	180	180	180	180	180	170	140	140	140	140	500	Intensive	44	
13	30wt% TPS	HSBO	95	5	40	130	170	180	180	180	180	180	170	140	140	140	140	500	High	71	
14	30wt% TPS	HSBO	90	10	40	130	170	180	180	180	180	180	170	140	140	140	140	500	High	69	

	Polymer	Oil	Ratio		Twin-Screw Temperature Profile (°C)											Melt Temp (°C)	Oil Temp (°C)	Screw RPM	Screw Type	Torque (%)
			Poly-mer	Oil	Z1	Z2	Z3	Z4	Z5	Z6	Z7	Z8	Z9	Die						
15	30wt% TPS	HSBO	85	15	40	130	170	180	180	180	180	180	170	140	140	140	170	500	High	55
16	30wt% TPS	HSBO	80	20	40	130	170	180	180	180	180	180	170	140	140	140	175	500	High	48
17	30wt% TPS	HSBO	80	20	40	130	170	180	180	180	180	180	170	140	140	140	174	500	High	43
18	30wt% TPS	HSBO	75	25	40	130	170	180	180	180	180	180	170	140	140	140	175	500	High	34
19	30wt% TPS	HSBO	70	30	40	130	170	180	180	180	180	180	170	140	140	140	175	500	High	34
20	30wt% TPS	HSBO	65	35	40	130	170	180	180	180	180	180	170	140	140	140	172	500	High	29
21	30wt% TPS	SBO	95	5	40	130	170	180	180	180	180	180	170	140	140	140	172	400	High	62
22	30wt% TPS	SBO	90	10	40	130	170	180	180	180	180	180	170	140	140	140	172	400	High	58
23	30wt% TPS	SBO	85	15	40	130	170	180	180	180	180	180	170	140	140	140	174	400	High	52
24	30wt% TPS	SBO	80	20	40	130	170	180	180	180	180	180	170	140	140	140	175	400	High	45
25	30wt% TPS	SBO	75	25	40	130	170	180	180	180	180	180	170	140	140	140	175	400	High	37
26	30wt% TPS	SBO	70	30	40	130	170	180	180	180	180	180	170	140	140	140	NR	400	High	NR
27	30wt% TPS	HSBO	70	30	40	130	170	180	180	180	180	180	170	140	140	140	175	400	High	34
28	45wt% TPS	HSBO	90	10	40	130	170	180	180	180	180	180	170	140	140	140	170	400	High	43
29	45wt% TPS	HSBO	85	15	40	130	170	180	180	180	180	180	170	140	140	140	NR	400	High	NR

For examples 3, 6, and 26, it was noted that the oil was surging at the end of the CT-25 extruder. Examples 3 and 6 failed to properly pelletize. For examples 17-20, 25, and 27, vacuum eliminated blooming at strand outlet of the extruder.

5 Examples 1-29 demonstrate that one can add oils and waxes to TPS. In Examples 1-29, the TPS resin has been pre-compounded to destructure the starch. Although not required, the oil and wax in Examples 1-29 were added in a second compounding step. What was observed was that with a stable composition (e.g., able to be extruded and/or pelletized), strands from the B&P 25mm system could be extruded, quenched in a water bath at 5°C and cut via a pelletizer without interruption. The twin-screw extrudate was immediately dropped into the  
10 water bath.

During stable extrusion, no significant amount of oil/wax separated from the formulation strand (>99wt% made it through the pelletizer). Saturation of the composition can be noted by separation of the polymer and oil/wax from each other at the end of the twin-screw. The saturation point of the oil/wax in the composition can change based on the oil/wax and  
15 polymer combination, along with the process conditions. The practical utility is that the oil/wax and polymer remain admixed and do not separate, which is a function of the mixing level and quench rate for proper dispersion of the additive. Specific Examples where the extrusion became unstable from high oil/wax inclusion are Example 3 and 6.

Molded articles can be produced from a composition of any one of Examples 1-29.

20 All documents cited in the Detailed Description of the Invention are, in relevant part, incorporated herein by reference; the citation of any document is not to be construed as an admission that it is prior art with respect to the present invention. To the extent that any meaning or definition of a term in this document conflicts with any meaning or definition of the same term in a document incorporated by reference, the meaning or definition assigned to  
25 that term in this document shall govern.

While particular embodiments of the present invention have been illustrated and described, it would be obvious to those skilled in the art that various other changes and modifications can be made without departing from the spirit and scope of the invention. It is therefore intended to cover in the appended claims all such changes and modifications that are within the scope  
30 of this invention.

## CLAIMS

What is claimed is:

1. A molded article comprising a composition comprising an intimate admixture of

- (a) a thermoplastic starch;
- (b) a thermoplastic polymer; and
- (c) an oil, wax, or combination thereof present in an amount of 5 wt% to 40 wt%, based upon the total weight of the composition.

2. The molded article of claim 1, wherein the thermoplastic polymer comprises a polyolefin, a polyester, a polyamide, copolymers thereof, or combinations thereof.

3. The molded article of claim 2, wherein the thermoplastic polymer is selected from the group consisting of polypropylene, polyethylene, polypropylene co-polymer, polyethylene co-polymer, polyethylene terephthalate, polybutylene terephthalate, polylactic acid, polyhydroxyalkanoates, polyamide-6, polyamide-6,6, and combinations thereof.

4. The molded article of any one of claims 1 to 3, wherein the thermoplastic polymer comprises polypropylene.

5. The molded article of any one of claims 1 to 4, wherein the oil, wax or combination thereof comprises a lipid.

6. The molded article of claim 5, wherein the lipid comprises a monoglyceride, diglyceride, triglyceride, fatty acid, fatty alcohol, esterified fatty acid, epoxidized lipid, maleated lipid, hydrogenated lipid, alkyd resin derived from a lipid, sucrose polyester, or combinations thereof.

7. The molded article of any one of claims 1 to 4, wherein the oil, wax, or combination thereof is selected from the group consisting of soy bean oil, epoxidized soy bean oil, maleated soy bean oil, corn oil, cottonseed oil, canola oil, beef tallow, castor oil, coconut oil, coconut seed oil, corn germ oil, fish oil, linseed oil, olive oil, oiticica oil, palm kernel oil, palm oil, palm seed oil, peanut oil, rapeseed oil, safflower oil, sperm oil, sunflower seed oil, tall oil, tung oil, whale oil, tristearin, triolein, tripalmitin, 1,2-dipalmitoolein, 1,3-dipalmitoolein, 1-palmito-3-stearo-2-olein, 1-palmito-2-stearo-3-olein, 2-palmito-1-stearo-3-olein, trilinolein, 1,2-dipalmitolinolein, 1-palmito-dilinolein, 1-stearo-dilinolein, 1,2-diacetopalmitin, 1,2-distearo-olein, 1,3-distearo-olein, trimyristin, trilaurin, capric acid, caproic acid, caprylic acid, lauric acid, lauroleic acid, linoleic acid, linolenic acid, myristic

acid, myristoleic acid, oleic acid, palmitic acid, palmitoleic acid, stearic acid, and combinations thereof.

8. The molded article of any one of claims 1 to 7, wherein the thermoplastic starch comprises starch or a starch derivative and a plasticizer.

9. The molded article of claim 8, wherein the plasticizer is selected from the group consisting of glycerol, ethylene glycol, propylene glycol, ethylene diglycol, propylene diglycol, ethylene triglycol, propylene triglycol, polyethylene glycol, polypropylene glycol, 1,2-propanediol, 1,3-propanediol, 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,5-hexanediol, 1,2,6-hexanetriol, 1,3,5-hexanetriol, neopentyl glycol, trimethylolpropane, pentaerythritol, sorbitol, glycerol ethoxylate, tridecyl adipate, isodecyl benzoate, tributyl citrate, tributyl phosphate, dimethyl sebacate, urea, pentaerythritol ethoxylate, sorbitol acetate, pentaerythritol acetate, ethylenebisformamide, sorbitol diacetate, sorbitol monoethoxylate, sorbitol diethoxylate, sorbitol hexaethoxylate, sorbitol dipropoxylate, aminosorbitol, trihydroxymethylaminomethane, glucose/PEG, a reaction product of ethylene oxide with glucose, trimethylolpropane monoethoxylate, mannitol monoacetate, mannitol monoethoxylate, butyl glucoside, glucose monoethoxylate,  $\alpha$ -methyl glucoside, carboxymethylsorbitol sodium salt, sodium lactate, polyglycerol monoethoxylate, erythriol, arabitol, adonitol, xylitol, mannitol, iditol, galactitol, allitol, malitol, formamide, N-methylformamide, dimethyl sulfoxide, an alkylamide, a polyglycerol having 2 to 10 repeating units, and combinations thereof.

10. The molded article of any one of claims 8 to 9, wherein the starch or starch derivative is selected from the group consisting of starch, hydroxyethyl starch, hydroxypropyl starch, carboxymethylated starch, starch phosphate, starch acetate, a cationic starch, (2-hydroxy-3-trimethyl(ammoniumpropyl) starch chloride, a starch modified by acid, base, or enzyme hydrolysis, a starch modified by oxidation, and combinations thereof.

## AMENDED CLAIMS

received by the International Bureau on 24 September 2012 (24.09.12)

What is claimed is:

1. A molded article comprising a composition comprising an intimate admixture of
  - (a) a thermoplastic starch;
  - (b) a thermoplastic polymer; and
  - (c) an oil, wax, or combination thereof being dispersed in said thermoplastic starch and thermoplastic polymer in an amount of 5 wt% to 40 wt%, based upon the total weight of the composition, said oil, wax or combination thereof having a droplet size of less than 10  $\mu\text{m}$ .
2. The molded article of claim 1, wherein the thermoplastic polymer comprises a polyolefin, a polyester, a polyamide, copolymers thereof, or combinations thereof.
3. The molded article of claim 2, wherein the thermoplastic polymer is selected from the group consisting of polypropylene, polyethylene, polypropylene co-polymer, polyethylene co-polymer, polyethylene terephthalate, polybutylene terephthalate, polylactic acid, polyhydroxyalkanoates, polyamide-6, polyamide-6,6, and combinations thereof.
4. The molded article of any one of claims 1 to 3, wherein the thermoplastic polymer comprises polypropylene.
5. The molded article of any one of claims 1 to 4, wherein the oil, wax or combination thereof comprises a lipid.
6. The molded article of claim 5, wherein the lipid comprises a monoglyceride, diglyceride, triglyceride, fatty acid, fatty alcohol, esterified fatty acid, epoxidized lipid, maleated lipid, hydrogenated lipid, alkyd resin derived from a lipid, sucrose polyester, or combinations thereof.
7. The molded article of any one of claims 1 to 4, wherein the oil, wax, or combination thereof is selected from the group consisting of soy bean oil, epoxidized soy bean oil, maleated soy bean oil, corn oil, cottonseed oil, canola oil, beef tallow, castor oil, coconut oil, coconut seed oil, corn germ oil, fish oil, linseed oil, olive oil, oiticica oil, palm kernel oil, palm oil, palm seed oil, peanut oil, rapeseed oil, safflower oil, sperm oil, sunflower seed oil, tall oil, tung oil, whale oil, tristearin, triolein, tripalmitin, 1,2-dipalmitoolein, 1,3-dipalmitoolein, 1-palmito-3-stearo-2-olein, 1-palmito-2-stearo-3-olein, 2-palmito-1-stearo-3-olein, trilinolein, 1,2-

dipalmitolinolein, 1-palmito-dilinolein, 1-stearo- dilinolein, 1,2-diacetopalmitin, 1,2-distearo-olein, 1,3-distearo-olein, trimyristin, trilaurin, capric acid, caproic acid, caprylic acid, lauric acid, lauroleic acid, linoleic acid, linolenic acid, myristic acid, myristoleic acid, oleic acid, palmitic acid, palmitoleic acid, stearic acid, and combinations thereof.

8. The molded article of any one of claims 1 to 7, wherein the thermoplastic starch comprises starch or a starch derivative and a plasticizer.

9. The molded article of claim 8, wherein the plasticizer is selected from the group consisting of glycerol, ethylene glycol, propylene glycol, ethylene diglycol, propylene diglycol, ethylene triglycol, propylene triglycol, polyethylene glycol, polypropylene glycol, 1,2-propanediol, 1,3-propanediol, 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,5-hexanediol, 1,2,6-hexanetriol, 1,3,5-hexanetriol, neopentyl glycol, trimethylolpropane, pentaerythritol, sorbitol, glycerol ethoxylate, tridecyl adipate, isodecyl benzoate, tributyl citrate, tributyl phosphate, dimethyl sebacate, urea, pentaerythritol ethoxylate, sorbitol acetate, pentaerythritol acetate, ethylenebisformamide, sorbitol diacetate, sorbitol monoethoxylate, sorbitol diethoxylate, sorbitol hexaethoxylate, sorbitol dipropoxylate, aminosorbitol, trihydroxymethylaminomethane, glucose/PEG, a reaction product of ethylene oxide with glucose, trimethylolpropane monoethoxylate, mannitol monoacetate, mannitol monoethoxylate, butyl glucoside, glucose monoethoxylate,  $\alpha$ -methyl glucoside, carboxymethylsorbitol sodium salt, sodium lactate, polyglycerol monoethoxylate, erythriol, arabitol, adonitol, xylitol, mannitol, iditol, galactitol, allitol, malitol, formaide, N-methylformamide, dimethyl sulfoxide, an alkylamide, a polyglycerol having 2 to 10 repeating units, and combinations thereof.

10. The molded article of any one of claims 8 to 9, wherein the starch or starch derivative is selected from the group consisting of starch, hydroxyethyl starch, hydroxypropyl starch, carboxymethylated starch, starch phosphate, starch acetate, a cationic starch, (2-hydroxy-3-trimethyl(ammoniumpropyl) starch chloride, a starch modified by acid, base, or enzyme hydrolysis, a starch modified by oxidation, and combinations thereof.

INTERNATIONAL SEARCH REPORT

International application No  
PCT/US2012/038373

A. CLASSIFICATION OF SUBJECT MATTER  
 INV. C08L23/12  
 ADD. C08K5/01 C08L3/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
 C08K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
 EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2007/044803 A1 (PROCTER & GAMBLE [US]; NODA ISAO [US]; SATKOWSKI MICHAEL M [US]; ALLEN) 19 April 2007 (2007-04-19) page 26, paragraph 1 example 14 claims 1,5,6,8	1-10
X	EP 0 606 923 A2 (MCNEIL PPC INC [US]) 20 July 1994 (1994-07-20) samples 49 & 50; example 1; table 2	1-3
X	US 5 874 486 A (BASTIOLI CATIA [IT] ET AL) 23 February 1999 (1999-02-23) examples 2-6 claims 1,7,8,12,19	1,2,8-10
	----- -/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search  30 July 2012	Date of mailing of the international search report  03/08/2012
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer  Russell, Graham

## INTERNATIONAL SEARCH REPORT

International application No  
PCT/US2012/038373

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2006/199881 A1 (XU HAO [CN]) 7 September 2006 (2006-09-07) examples 3,4 claims 1-4	1-10
X	----- US 2003/100635 A1 (HO WILLIAM [US] ET AL) 29 May 2003 (2003-05-29) claims 1,4,7,10,11,13,16,19,20,22,25,26,28-30 paragraph [0034] - paragraph [0036] -----	1-4,7,8, 10

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2012/038373

Patent document cited in search report	Publication date	Patent family member(s)	Publication date			
WO 2007044803	A1	19-04-2007	AT 435886 T 15-07-2009			
			AT 449875 T 15-12-2009			
			AT 481450 T 15-10-2010			
			AT 505570 T 15-04-2011			
			CA 2625209 A1 19-04-2007			
			CA 2625237 A1 19-04-2007			
			CA 2625240 A1 19-04-2007			
			CA 2625248 A1 19-04-2007			
			CN 101283033 A 08-10-2008			
			CN 101283034 A 08-10-2008			
			CN 101283123 A 08-10-2008			
			CN 101283124 A 08-10-2008			
			EP 1934280 A1 25-06-2008			
			EP 1934389 A1 25-06-2008			
			EP 1934390 A1 25-06-2008			
			EP 1937768 A1 02-07-2008			
			JP 2009511714 A 19-03-2009			
			JP 2009511715 A 19-03-2009			
			JP 2009511765 A 19-03-2009			
			JP 2009511766 A 19-03-2009			
			US 2007079945 A1 12-04-2007			
			US 2007082573 A1 12-04-2007			
			US 2007082981 A1 12-04-2007			
			US 2007082982 A1 12-04-2007			
			WO 2007044800 A1 19-04-2007			
			WO 2007044801 A1 19-04-2007			
			WO 2007044802 A1 19-04-2007			
			WO 2007044803 A1 19-04-2007			
			EP 0606923	A2	20-07-1994	AT 236220 T 15-04-2003
						AT 252138 T 15-11-2003
AU 669025 B2 23-05-1996						
AU 688673 B2 12-03-1998						
BR 9400106 A 02-08-1994						
CA 2113521 A1 16-07-1994						
DE 69432378 D1 08-05-2003						
DE 69432378 T2 12-02-2004						
DE 69433252 D1 20-11-2003						
DE 69433252 T2 16-09-2004						
DK 0606923 T3 21-07-2003						
DK 0882765 T3 01-12-2003						
EP 0606923 A2 20-07-1994						
EP 0882765 A2 09-12-1998						
ES 2194851 T3 01-12-2003						
ES 2209012 T3 16-06-2004						
GR 1002560 B 29-01-1997						
JP 3923094 B2 30-05-2007						
JP 6322182 A 22-11-1994						
NZ 250655 A 21-12-1995						
NZ 270251 A 21-12-1995						
PT 606923 E 31-07-2003						
PT 882765 E 27-02-2004						
SG 54321 A1 16-11-1998						
US 5910520 A 08-06-1999						
US 5874486	A	23-02-1999	AT 172483 T 15-11-1998			
			AU 675954 B2 27-02-1997			
			AU 4418693 A 03-03-1994			

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2012/038373

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		CA 2141562 A1	17-02-1994
		DE 69321730 D1	26-11-1998
		DE 69321730 T2	27-05-1999
		DK 652910 T3	28-06-1999
		EP 0652910 A1	17-05-1995
		ES 2124313 T3	01-02-1999
		HK 1013302 A1	12-05-2000
		IT 1256914 B	27-12-1995
		JP 3549203 B2	04-08-2004
		JP H07509514 A	19-10-1995
		KR 100272484 B1	15-11-2000
		TW 492995 B	01-07-2002
		US 5874486 A	23-02-1999
		WO 9403543 A1	17-02-1994
-----			
US 2006199881	A1	07-09-2006	NONE
-----			
US 2003100635	A1	29-05-2003	NONE
-----			