(12) PATENT **(11)** Application No. **AU 199675511 B2**
(19) AUSTRALIAN PATENT OFFICE **(10)** Patent No. **706898**

(54) Title
Process for foam treating pile fabrics

(51)[6] International Patent Classification(s)
D06M 023/04

(21) Application No: **199675511** (22) Application Date: **1996.11.01**

(87) WIPO No: **WO97/19218**

(30) Priority Data

(31) Number	(32) Date	(33) Country
60/007344	**1995.11.20**	**US**
08/707687	**1996.09.04**	**US**

(43) Publication Date : **1997.06.11**
(43) Publication Journal Date : **1997.08.07**
(44) Accepted Journal Date : **1999.07.01**

(71) Applicant(s)
E.I. Du Pont De Nemours and Company

(72) Inventor(s)
Peter Michael Murphy

(74) Agent/Attorney
CALLINAN LAWRIE,Private Bag 7,KEW VIC 3101

(56) Related Art
WO 91/02116

US 4576112

US 4118526

OPI DATE 11/06/97 APPLN. ID 75511/96
AOJP DATE 07/08/97 PCT NUMBER PCT/US96/17525
AU9675511

(51) International Patent Classification 6 : D06M 23/04 A1

(11) International Publication Number: WO 97/19218

(43) International Publication Date: 29 May 1997 (29.05.97)

(21) International Application Number: PCT/US96/17525

(22) International Filing Date: 1 November 1996 (01.11.96)

(30) Priority Data:

60/007,344	20 November 1995 (20.11.95)	US
08/707,687	4 September 1996 (04.09.96)	US

(81) Designated States: AU, JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published

With international search report.

Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).

(72) Inventor: MURPHY, Peter, Michael; 5024 Branston Road, Ooltewah, TN 37363-8477 (US).

(74) Agent: MAYER, Nancy, S.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).

(54) Title: PROCESS FOR FOAM TREATING PILE FABRICS

(57) Abstract

An improved process for applying a treating agent in the form of a foam to fibrous material wherein the improvement comprises applying foam having a blow ratio of from about 2:1 to about 6:1 using equipment designed for the application of liquid treating agents is disclosed.

TITLE

PROCESS FOR FOAM TREATING PILE FABRICS

FIELD OF THE INVENTION

The present invention provides a process for foam treating pile fabrics, in particular, floor coverings such as carpets. The invention provides a process for foam application of various treating agents using equipment conventionally used for liquid application of such agents.

BACKGROUND OF THE INVENTION

The application of foam or foam compositions to carpet is well known. Such foams contain chemical treating agents such as dyes, antistatics, stain resist agents, fluorochemicals, and mixtures thereof. US Patent 5,223,340 teaches a typical stain resistant composition for fibers prepared by polymerizing an alpha-substituted acrylic acid or ester in the presence of a sulfonated aromatic formaldehyde condensation polymer. Various types of equipment are used to apply foams to carpets. See, for example, U.S. Patent 4,576,112 of Funger et al. disclosing equipment for application of foams to the face of carpets with a resilient seal pressed against the backing of the carpet to promote sealing. U.S. Patent 5,366,161 of Potter et al. teaches equipment for application of foam through the backing of carpet using a blow ratio of 15:1 to 60:1. The techniques using this equipment are considered improvements over earlier methods involving casting foam onto one or both sides of a carpet which is then calendered into the surface by rolls or other pressure application means, such as taught by US Patent 4,118,526.

An alternative method for application of treating agents involves liquid application at very high wet pick-up levels (the ratio of the weight of the liquid applied to the dry weight of the carpet x 100). Currently the most effective equipment used for applying liquid agents, such as stain resists, is the FLEXNIP® produced by Edward Küsters Machinenfabrik, Gladbacher Strasse, Krefeld, Germany. Treating agents applied with this equipment are distributed

AUSTRALIAN PATENT OFFICE 13

AMENDED SHEET

throughout the carpet by raising wet pick-up levels to the point where excessive fluid is used. However, this process uses excessive amounts of energy and water, and requires extracting stain resist agents before the carpet is dried.

A third alternative is to apply the treating agents by spraying the agents onto the face of the carpet after the washing and extraction steps. This method can result in uneven distribution of the chemicals through the carpet, and concentration of the chemicals along the upper portion of the carpet tufts. Thus chemicals can be lost in the shearing step during final finishing of cut pile carpets. European Patent Application 433 017 A1 discloses use of a two step process wherein a stain resistant composition is first applied by immersion or padding followed by a second application by foam.

There is a need to develop an improved process for adding treating agents to carpets which requires less water and energy, reduces effluent streams, and improves the uniformity of the chemical application. Foam application at low wet pick-up levels offers the best approach. However, to achieve the desired results, special equipment for application of foams as noted above is required. For those currently using a liquid application process, the equipment for foam application represents an expensive investment. Thus a more economical process for application of treating agents by foam is needed. The present invention provides a process for foam application of treating agents to pile fabrics such as carpets by using conventional liquid application equipment, thereby eliminating the need for equipment particular to foam applications.

SUMMARY OF THE INVENTION

The present invention comprises an improved process for applying a treating agent in the form of foam to fibrous materials wherein the improvement comprises applying foam having a blow ratio of from about 2:1 to about 6:1 using equipment designed for the application of liquid treating agents.

AUSTRALIAN PATENT OFFICE 13

AMENDED SHEET

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to a process for the foam treatment of fibrous materials such as floor coverings, in particular nylon carpets, using conventional equipment designed for liquid applications. The process involves the use of a foam having a blow ratio of about 2:1 to about 6:1, preferably 3:1 to 5:1. Such blow ratios are much lower than foams conventionally used in foam application equipment. The present invention teaches (a) the methods used to prepare such low blow ratio foams with adequate stability, (b) the method of application using conventional equipment designed for liquid application, (c) the drying and curing processes required, and (d) the tests utilized to demonstrate effective application, curing, and drying.

The use of very low blow ratio foams in equipment designed for liquid application results in economic, low energy requirements for drying, and uniformity of treatment advantages associated with foam application. The utilization of existing conventional liquid application equipment requires only minimal adaptation compared with the very high cost of foam application equipment. Additionally the costs of maintaining and operating dedicated foam application equipment are eliminated.

The blow ratio of a foam is defined as the ratio of the weight of the bath liquid to the weight of an equal volume of foam prepared from the bath liquid. The foam density in g/ml is approximately equal to the reciprocal of the blow ratio, thus a foam density of 0.2 g/ml corresponds to a blow ratio of 5:1. The stability of a foam is typically measured in terms of its half-life, the time required for the weight of a freshly-prepared foam sample to decrease to half its original weight due to liquid draining from the foam and forming a lower liquid layer. A suitable half life for the purposes of this invention is from about 2 to about 10 minutes, preferably from about 3 to about 5 minutes.

More preferable is a minimum half life equal to or greater than 3 minutes. Test Method 3 (below) describes the measurement of foam density, blow ratio, and foam stability.

Conventional high blow ratio foams, e.g., foams with blow ratios significantly higher than the 2:1 to 6:1 range of this invention, have relatively stiff foam characteristics and, when applied using conventional equipment designed for liquid application, do not adequately wick, wet, and penetrate the carpet fiber as needed for complete and uniform application. The low blow ratio foams of this invention, however, flow readily and penetrate and wet the carpet fiber thoroughly and uniformly. Wet pick up ratios of from about 50% to about 150% are employed.

Low blow ratio, high density foams as used in this invention are best prepared using a dynamic foam generator. While several dynamic foam generators are available, an example of a dynamic foam generator design would be a mechanical mixer comprising essentially a canister containing an internal rotating cylinder. The cylinder and canister have attached a series of metal pins radially aligned to provide high shearing action to the air and solution fed to the foam generator as the cylinder is rotated.

Manufacturers of such dynamic foam generating equipment include Latex Equipment Sales & Service (Dalton, Georgia), Dalton Industrial Systems (Dalton, Georgia), and Datacolor International (Atlanta, Georgia). These manufacturers provide information on dynamic foamer operation and process control. Such foam generators are typically built to custom specifications which match specific process requirements.

Another foam generator design is the static foam generator. Static foam generators generate foams by flowing air and the surfactant-containing bath solution to be foamed through a packed column. Packing material examples are glass beads, ball bearings, metal turnings

Included for example are dyes, antistatics, stain resist agents, and various fluorochemicals. In the case of a stain resist agent, the stain resist solution (conventionally termed the stain resist bath) is prepared with conventional surfactants at the required concentration and pH, and foamed using a dynamic foam generator, as described above. The pH range is from about 1.5 to about 2.5, and preferably from about 1.7 to about 2.0. The pH may be adjusted with any strong acid, including sulfuric, phosphoric, and sulfamic acids. Preferred acidifying agents are those formulated to minimize equipment corrosion and handling hazards, such as Autoacid AA10 (Peach State Labs, Rome, Georgia, a proprietary formulation based on U.S. patent 5,234,466). The stain resists useful in the present invention are those well known to those skilled in the art, and include ZELAN 300® (a stain resist formulation prepared according to U.S. Patents 4,883,839 and 4,948,650, and available from E.I. Du Pont de Nemours and Company, Wilmington, Delaware), phenolic and/or novolac resins (available from Ciba Corporation, Greensboro North Carolina and Crompton & Knowles, Charlotte, North Carolina), polymers or copolymers of maleic acid, polymers or copolymers of maleic anhydride (both available from E.I. Du Pont de Nemours and Company, Wilmington, Delaware), polymers or copolymers of methacrylic acid (available from 3M Company, Minneapolis, Minnesota) phenyl vinyl ether polymers or copolymers (available from Allied Signal, Morristown, New Jersey), polymers of sulfonated fatty acids (available from Interface Corp., LaGrange, Georgia), sulfonated fatty acids, phenolic-formaldehyde polymers, and blends of these stain resists. The preceding commercial suppliers are provided as examples, and other sources are well known to those skilled in the art.

The bath concentration and wet pick up are adjusted to apply the foam in an amount sufficient to give a concentration of from about 0.2% to about 2.0%, and preferably 0.5% to 1.0%, of the stain resist active ingredient based on the weight of the dried carpet fiber, or at the level recommended by the stain resist supplier. In the case of Küsters' FLEXNIP® equipment (Zima Corporation, Spartanburg, South Carolina

AUSTRALIAN PATENT OFFICE

described further below), for instance, the wet pick up for liquid application is typically 250% to 300%. Using a 3:1 blow ratio foam instead of liquid, the wet pick up will be one third as much, or about 80% to about 100%.

Surfactants suitable for use in the stain resist bath are also well known to those skilled in the art. The surfactants are typically anionic and include CALSOFT® AOS-40(40% aqueous solution of the sodium salts of sulfonated C_{14-16} alkanes and alkenes, from Pilot Chemical Co., Avenel New Jersey), Rohm & Haas DOSS® (50% aqueous solution of di-2-ethylhexyl sodium sulfosuccinate from Rohm & Haas Co., Philadelphia Pennsylvania), KAF® 300S (a proprietary blend of anionic surfactants and hydrotrope from Peach State Labs, Rome, Georgia), DOWFAX® 2A1 (a mixture of docecyl-(sulfophenoxy) benzenesulfonic acid and oxybis-(dodecylbenzenesulfonic acid) disodium salts from Dow Chemical Company, Midland, Michigan) and DOWFAX® 2A4 (benzene, 1,1-oxybis, tetrapropylene derivatives, sulfonated, sodium salts from Dow Chemical Company, Midland, Michigan).

Typically the stain resist formulation as purchased already contains some surfactant to wet the fibers, and which also can act as a foaming agent. To make the low blow ratio foams of this invention, additional anionic surfactant or foaming agent in an amount sufficient to yield stable foams is added to the bath, typically in amounts of from about 1 to about 5 g/L, and preferably from about 2 to about 3 g/L. Some bath factors may negatively affect foam quality, for instance salts, temperature, water hardness, and contaminants such as oil. In such cases, a higher surfactant concentration as necessary to provide the required foam blow ratio and stability is substituted.

The foams used in this invention have half-lives from about 2 to about 10 minutes, preferably from about 3 to about 5 minutes, and blow ratios of from about 2:1 to about 6:1, and preferably 3:1 to 5:1, as measured by Test Method 3, described below. Such half-lives and blow ratios are properties that permit even distribution and thorough penetration of the foam into the carpet fibers.

AUSTRALIAN PATENT OFFICE

AMENDED SHEET

The foam is applied to the pile fabric using any conventional liquid application equipment having a manifold designed to deliver a high wet pick up and to distribute the liquid evenly to the fabric. An example of such conventional equipment is the Küsters' FLEXNIP® equipment. The Küsters' FLEXNIP® was introduced in 1987 for continuous application of stain resist chemicals after dyeing and prior to drying. In the FLEXNIP®, the carpet passes vertically through a very small chemical bath with the wet pick up being controlled by the opposing pressurized air bellows at the bottom of the bath. The carpet then enters a post-steamer followed by a vacuum extractor. The stain resist chemical bath is delivered to the FLEXNIP® by a series of tubes spaced evenly between 2 to 6 inches (5-15 cm) apart on both the face and the backing sides of the moving carpet.

The typical configuration of the liquid feed module for a conventional liquid application equipment comprises essentially a liquid storage tank for the bath solution and a pump that supplies the liquid bath to the liquid feed manifold. The only adaptations required for use of such equipment in the process of this invention are the connection of a dynamic foam generator in line between the existing pump and manifold, and the supply of a regulated air supply to the dynamic foam generator.

Other appropriate equipment for the liquid application of stain resist or other treating agents using the low blow ratio foam process of this invention is manufactured by companies such as Fleissner (Charlotte, North Carolina), Latex Equipment Sales & Service (Dalton, Georgia), Dalton Industrial Systems (Dalton, Georgia), Datacolor International (Atlanta, Georgia), and Gaston County Carpet Machinery Corporation (Fort Oglethorpe, Georgia).

After passing through the liquid application equipment, the fabric is steamed, vacuum extracted, and oven dried and cured. Steam temperatures and times are well know to those skilled in the art, typically near 210°F (99°C) and 60 to 120 seconds. Oven temperatures are those sufficient to dry the carpet or as recommended by the stain resist supplier,

AUSTRALIAN PATENT OFFICE 13

typically about 270°F (132 °C) for about 60 seconds. Samples of treated fabric are tested using the Stain Resistance Test Method 1 before and after the alkaline surfactant wash described in the Shampoo Test Method 2. Test Methods are described hereinafter.

The foam application process for treating agents of this invention are readily integrated with other carpet manufacturing operations; examples of such other operations are dyeing and fluorocarbon soil resist application. An integrated operation could include the sequence dyeing, steaming, wash/rinse, vacuum extraction, stain resist application, steaming, wash/rinse, vacuum extraction, soil resist application, drying and curing. Techniques for integrating such processes are well know to those skilled in the art.

TEST METHODS

Test Method 1

Stain Resistance Test

Acid dye stain resistance was evaluated using a modified procedure based on the American Association of Textile Chemists and Colorists (AATCC) Method 175-1991, "Stain Resistance: Pile Floor Coverings". A staining solution was prepared by mixing cherry-flavored KOOL-AID® powder (from Kraft/General Foods, White Plains New York, a powdered drink mix sold under the trademark KOOL-AID® sweetened with sugar and containing, inter alia, FD&C Red No. 40) with water according to the preparation instructions on the KOOL-AID® container. The carpet sample to be tested was placed on a flat non-absorbent surface and a hollow plastic cylinder having a 2 inch (5.1 cm) diameter was placed tightly over the carpet sample. Twenty ml of the KOOL-AID® staining solution was poured into the cylinder and the solution was allowed to absorb completely into the carpet sample. The cylinder was then removed and the stained carpet sample was allowed to sit undisturbed for 24 hours, after which it was rinsed thoroughly under cold tap water, squeezed, and oven dried at 150°F (66°C).

AUSTRALIAN PATENT OFFICE

The carpet sample was then visually inspected and rated for staining according to the FD&C Red No. 40 Stain Scale described in AATCC Method 175-1991. A stain rating of 10 is excellent, showing outstanding stain resistance, whereas 1 is the poorest rating, comparable to an untreated control sample.

Test Method 2

Shampoo Test (Wash Durability)

The carpet specimen was submerged for 5 minutes at room temperature in a detergent solution consisting of DUPONOL WAQE® (2.0 oz. per gal., 15 g/L). DUPONOL WAQE® is a 30-40% aqueous solution of sodium alkane sulfonates, available from Witco Corporation, Greenwich, Connecticut). The solution was adjusted with dilute sodium carbonate to a pH of 10. The specimen was then removed, rinsed thoroughly under tap water, de-watered by squeezing, and oven dried at 150°F (66°C). The dry carpet specimen was then tested according to Test Method 1, as described above.

Test Method 3

Foam Blow Ratio and Stability Measurement

A foam sample from the foam generator was placed in a weighed graduated cylinder, the foam weight was determined by difference and the foam volume measured to determine the foam density. For typical bath solutions having a density of about 1 g/ml, the blow ratio was the reciprocal of the foam density. Using a stopwatch, the separation of liquid from the foam was observed as the appearance of a liquid layer in the bottom of the cylinder. The time required for the volume of the liquid layer corresponding to half the weight of the initial foam was observed and is the half-life of the foam. If the unfoamed bath density was significantly different from 1 g/ml, the blow ratio and separated liquid volume were calculated accordingly. Other equivalent techniques can be substituted, for instance by filling a weighed separatory funnel of known volume with foam, reweighing, then allowing the separated liquid to drain into a tared container on a balance.

AUSTRALIAN PATENT OFFICE

EXAMPLES

Example 1

A dyed residential cut-pile carpet, 40 oz./sq. yd. (1355 g/m^2) produced by a conventional mill process and composed of nylon-6,6 bulk continuous fiber (BCF) face fiber and polypropylene primary backing) was passed though a Küsters' FLEXNIP® liquid application equipment, with the application manifold adapted to feed a low blow ratio foam by inserting a dynamic foam generator equipped with a regulated air supply between the pump supplying bath liquid to the application manifold and the application manifold inlet. The Dalton laboratory dynamic foamer and regulator used comprised a dynamic foamer - electric motor (Model # 5BPB56SAA200, General Electric, Schenectady, New York) with a canister (4 liter dynamic frother, Latex Equipment Sales & Service, Dalton, Georgia) with air supply from a Dixon model # DB12-221-M3LA air regulator (Dixon Valve & Coupling Company, Chestertown, Maryland).

The stain resist bath contained 45 g/L of ZELAN® 300, (E. I. du Pont de Nemours & Company) 2 g/L of CALSOFT® AOS, (Pilot Chemical Co., Avenel, New Jersey) and the pH was adjusted to 1.7 with AUTOACID® AA10 (Peach State Labs, Rome, Georgia). The bath solution was pumped to the dynamic foam generator and fed to the FLEXNIP® application manifold at a rate sufficient to provide 0.95% ZELAN® 300 active ingredient based on the weight of the dried fiber. After passing through the FLEXNIP® using a bellows (or bladder) pressure of 7 psi (48.3 x 10^3 Pa), the carpet was steamed at 270°F (132°C) for 70 seconds, vacuum extracted, and oven dried/cured. The stain resistance was tested by Test Method 1. The shampoo resistance was measured by Test Method 2. The test results for Example 1 are shown in Table 1.

Examples 2 - 4

Examples 2 - 4 were prepared as for Example 1, but with the varied surfactant, surfactant concentration, and blow ratio, as shown in Table 1. The test results for Examples 2 - 4 are shown in Table 1.

AUSTRALIAN PATENT OFFICE

Table 1

Ex. #	ZELAN 300 %[a]	Surfactant Type[b]	Blow Ratio	Steam Time (sec)	Steam Temp. (F)[c]	Bladder Press. (psi)[d]	Staining Test Results: Average Result Test 1	Average Result Test 2	Best Result Method 1	Best Result Method 2
1	0.95	AOS	3:1	70	210	7	9.5	4	10	5
2	0.84	DOSS	5:1	120	210	7	8	2	9	2
3	0.84	AOS	4.5:1	120	210	7	9	2.5	10	3
4	0.84	AOS	4:1	80	210	7	9	3	10	4

a) ZELAN® 300 % is as active ingredient based on the dried carpet fiber weight. The active ingredient level in ZELAN® 300 as supplied is 21%

b) AOS is CALSOFT® AOS from Pilot Chemical Co., Avenel, New Jersey.
DOSS® is from Rohn & Haas Co., Philadelphia, Pennsylvania.

c) 210°F = 99°C

d) 7 psi = 48.3 x 10^3Pa

No industry-wide standards exist for acceptable stain resist performance. Typical results obtained using liquid application equipment between 250% to 300% wet pick up are 9 or 10 for test method #1 and 5 to 7 for test method #2. The results of test method #2 are a measure of the durability of the stain resist treatment to a repeated carpet cleanings. The stain resist performance after repeated carpet cleanings is generally poorer than the carpet's original performance but better than carpet which has not been treated with a stain resist agent.

Where the terms "comprise", "comprises", "comprised" or "comprising" are used in this specification, they are to be interpreted as specifying the presence of the stated features, integers, steps or components referred to, but not to preclude the presence or addition of one or more other feature, integer, step, component or group thereof.

AUSTRALIAN PATENT OFFICE

What is claimed is:

1. A process comprising applying a treating agent in the form of a foam to fibrous material said foam having a half life of from 2 to 5 minutes and said foam having a blow ratio of from about 2:1 to about 6:1 at a wet pick up of from 80% to 150% using liquid application equipment wherein said material is passed through a chemical bath of foam containing the treating agent.

2. The process of Claim 1 wherein the fibrous material is a floor covering.

3. The process of Claim 2 wherein the floor covering is nylon carpet.

4. The process of Claim 1 wherein the foam has a half life of about 3 minutes to 5 minutes.

5. The process of Claim 1 wherein the foam is applied at from 80% to 100% wet pick up.

6. The process of Claim 1 wherein the foam is generated using a dynamic foam generator.

7. The process of Claim 1 wherein the treating agent contains a stain resist agent.

8. The process of Claim 7 wherein the stain resist is selected from the group consisting of hydrolyzed polymers or copolymers of maleic anhydride, polymers or copolymers of methacrylic acid, phenolic-formaldehyde polymers, sulfonated fatty acids, and polymers of sulfonated fatty acids.

9. The process of Claim 1 further comprising steaming, vacuum extracting, drying and curing the fibrous material.

AUSTRALIAN PATENT OFFICE
13 JUN

AMENDED SHEET