



(11) **EP 4 140 973 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
28.02.2024 Bulletin 2024/09

(51) International Patent Classification (IPC):
C06C 7/00 (2006.01) F42C 19/12 (2006.01)

(21) Application number: **22020161.0**

(52) Cooperative Patent Classification (CPC):
C06C 7/00; F42B 3/128; F42C 19/12

(22) Date of filing: **08.04.2022**

(54) **SUSPENSION OF EXPLOSIVE COMPOSITION OF PILL FUSE HEAD FOR INDUSTRIAL ELECTRIC DETONATORS**

SUSPENSION EINER EXPLOSIVEN ZUSAMMENSETZUNG EINES PILLENFÖRMIGEN
ZÜNDKOPFES FÜR INDUSTRIELLE ELEKTRISCHE DETONATOREN

SUSPENSION DE COMPOSITION EXPLOSIVE DE TÊTE FUSIBLE PILULE POUR DES
DÉTONATEURS ÉLECTRIQUES INDUSTRIELS

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **12.04.2021 CZ 20210180**

(43) Date of publication of application:
01.03.2023 Bulletin 2023/09

(73) Proprietor: **Austin Detonator s.r.o.
Jasenice 712
755 01 Vsetín (CZ)**

(72) Inventor: **VALENTA, Pavel
75501 Ustí (CZ)**

(74) Representative: **Halaxová, Eva
Halaxová & Halaxová Tetrapat
Jinonická 80
158 00 Praha 5 (CZ)**

(56) References cited:
**CZ-B6- 294 317 CZ-U1- 35 228
FR-A1- 2 861 389 US-A1- 2003 110 971
US-A1- 2005 183 805**

EP 4 140 973 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

Field of the Invention

[0001] The invention concerns the suspension of explosive composition of pill fuse head for industrial electric detonators created by dipping technology on its skeleton formed by metal lamellas and a resistance wire.

State of the Art

[0002] At present, suspensions of explosive compositions in solutions of nitrocellulose or fluoroelastomer in an organic solvent are used for the technology of the production of electric pill fuse heads by dipping. Those suspensions contain an explosive based on a lead salt and other components based on lead and non-lead oxidizers, metal powders, and binders, such as mentioned nitrocellulose or fluoroelastomer.

[0003] The dipping technology is based on simultaneous immersion of several thousand electric pill skeletons, formed by metal lamellas with a resistance wire, into a suspension of explosive composition, and thus the formation of electric pill fuse heads. These wet fuse heads are then dried out to remove the organic solvent, after which the fuse heads of the electric pills are provided with a lacquer layer of conventional lacquers to ensure mechanical and dimensional strength. In the dipping technology, suspensions of explosive composition must exhibit constancy of composition and sedimentation of the individual components must not occur.

[0004] The explosive composition of the pill fuse heads, after the organic solvents have been dried out, then coats the resistance wire, which is usually made of a NiCr alloy in a weight ratio of 80/20 and whose diameter ranges from 30 to 100 micrometres, or of a CuNi alloy containing 44% Ni, with a diameter of 170 micrometres. The explosive pill composition then determines the electrical parameters of the electric pill with respect to the resistance wire, such as: safe current and ignition current.

[0005] The electric pill thus formed can be used in an electric industrial detonator, where, after passing a pre-defined electrical impulse, the resistance wire of the electric pill is heated and subsequently the pill explosive composition is initiated, the burst of flame of which then transmits the heat burst to the pyrotechnic delay composition of the industrial electric detonator.

[0006] Therefore, the explosive composition must be sufficiently sensitive to the definably heated resistance wire of the electric pill to ignite it. The created burst of flame, formed by the explosive transformation of the individual components, then must not have an excessive pressure effect, but must have the calorific capacity to initiate the delay pyrotechnic composition of the electric detonator.

[0007] The above currently used formula of suspensions of the explosive composition of electric pill fuse

heads is, however, unacceptable from the ecological point of view according to the current European legislation. CZ294317 discloses a dipping explosive mixture comprising potassium dinitrobenzofuroxanate (KDNBF), potassium perchlorate, zirconium, silica as filler and stabilizer and a solution of Viton B (fluoroelastomer binder) in butyl acetate.

Principle of the Invention

[0008] The above shortcomings are eliminated by the suspension of explosive composition of pill fuse head for industrial electric detonators according to this invention, the essence of which is that it consists of 30 - 60 wt. portions of the potassium salt of dinitrobenzofuroxane, 15 - 35 wt. portions of potassium perchlorate, 5-20 wt. portions of zirconium, 5-20 wt. portions of boron, and 5-20 wt. portions of calcium silicide in 1 - 5% solution of nitrocellulose or fluoroelastomer in an organic solvent.

[0009] For proper function, it is withal advantageous, if the organic solvent is amyl acetate, butyl acetate, propyl acetate, or isomers thereof.

[0010] Such suspension of explosive composition has suitable rheological properties because its individual components do not sediment and it is technologically processable for multiple applications to the electric pill skeleton formed by metal lamellas with the resistance wire forming a bridge, where after the drying operation forms the electric pill fuse head.

[0011] The listed formula of the suspension of explosive composition applied to the resistance wire of the electric pill then, after drying the organic solvent and providing the lacquer layer, ensures the required sensitivity of the electric pill to initiation when heating the resistance wire of varying material composition and diameter, and the formed fumes after its explosive transformation generate regular burst of flame and allow regular ignition of the pyrotechnic delay composition in the electric detonator.

[0012] The concerned composition of the fuse head of the electric pill is harmless from the point of view of ecology because it does not contain any non-ecological components and does not create such by its explosive transformation. The explosive composition and its products after the explosive transformation are thus environmentally friendly.

[0013] The mentioned explosive composition can also be used as a separate electric pill or in an electric igniter assembly also for use in fireworks.

Brief Description of the Figures in the Drawing

[0014] The invention will be further elucidated with the aid of the drawing, in which Fig. 1 shows a vertical front cross section of the electric pill and Fig. 2 shows a vertical side cross section of this pill.

Examples of the Invention Design

[0015] The electric pill in Figs. 1 and 2 is formed by two metal lamellas 4 between which a resistance wire is arranged 3. Fixation of the lamellas 4 with the attached resistance wire 3 is made by a plastic clip 5. The suspension of explosive composition 2 is applied to the resistance wire 3, or to the skeleton formed by endings of the lamellas 4 with the resistance wire 3, according to this technical solution and using the dipping technology. After drying out and removal of organic solvents, the explosive composition is provided with lacquer layer 1, in this case a nitrocellulose lacquer ensuring the mechanical strength of the electric pill fuse head thus formed.

Example 1

[0016] The suspension of the explosive composition 2 consists of 48 wt. portions of the potassium salt of dinitrobenzofuroxane, 25 wt. portions of potassium perchlorate, 9 wt. portions of zirconium, 9 wt. portions of boron, and 9 wt. portions of calcium silicide in a 1% solution of nitrocellulose in amyl acetate.

[0017] This suspension was applied by the dipping technology to a skeleton with a resistance wire 3 made of NiCr (80/20) alloy with a wire diameter of 30 micrometres, in which case the subsequently formed electric pill fuse head exhibited the parameters of safe current 0.18A and ignition current 1A.

Example 2

[0018] The suspension of explosive composition 2 consists of 48 wt. portions of the potassium salt of dinitrobenzofuroxane, 25 wt. portions of potassium perchlorate, 9 wt. portions of zirconium, 9 wt. portions of boron and, 9 wt. portions of calcium silicide in a 3% solution of fluoroelastomer in butyl acetate.

[0019] This suspension was applied by the dipping technology to a skeleton with a resistance wire 3 made of NiCr (80/20) alloy with the wire diameter of 55 micrometres, in which case the subsequently formed electric pill fuse head exhibited the parameters of safe current 0.45A and ignition current 1.5A.

Example 3

[0020] The suspension of explosive composition 2 consists of 55 wt. portions of the potassium salt of dinitrobenzofuroxane, 15 wt. portions of potassium perchlorate, 10 wt. portions of zirconium, 10 wt. portions of boron, and 10 wt. portions of calcium silicide in a 5% solution of nitrocellulose in amyl acetate.

[0021] This suspension was applied by the dipping technology to a skeleton with a resistance wire 3 made of NiCr (80/20) alloy with the wire diameter of 45 micrometres, in which case the subsequently formed electric pill fuse head exhibited the parameters of safe current

0.25A and ignition current 1.1A.

Example 4

[0022] The suspension of explosive composition 2 consists of 40 wt. portions of the potassium salt of dinitrobenzofuroxane, 15 wt. portions of potassium perchlorate, 15 wt. portions of zirconium, 15 wt. portions of boron, and 15 wt. portions of calcium silicide in a 5% solution of nitrocellulose in amyl acetate.

[0023] This suspension was applied by the dipping technology to a skeleton with a resistance wire 3 made of NiCr (80/20) alloy with the wire diameter of 100 micrometres, in which case the subsequently formed electric pill fuse head exhibited the parameters of safe current 1.2A and ignition current 3.5A.

Example 5

[0024] The suspension of explosive composition 2 consists of 55 wt. portions of the potassium salt of dinitrobenzofuroxane, 12 wt. portions of potassium perchlorate, 8 wt. portions of zirconium, 10 wt. portions of boron, and 15 wt. portions of calcium silicide in a 3% solution of nitrocellulose in butyl acetate.

[0025] This suspension was applied by the dipping technology to a skeleton with a resistance wire 3 made of CuNi (44% of Ni) alloy with the wire diameter of 170 micrometres, in which case the subsequently formed electric pill fuse head exhibited the parameters of safe current 4A and ignition current 25A.

Claims

1. The Suspension of Explosive Composition of Pill Fuse Head for Industrial Electric Detonators, **characterized by** consisting of 30 - 60 portions of the potassium salt of dinitrobenzofuroxane, 15 - 35 wt. portions of potassium perchlorate, 5 - 20 wt. portions of zirconium, 5 - 20 wt. portions of boron, and 5 - 20 wt. portions of calcium silicide in a 1 - 5% solution of fluoroelastomer in an organic solvent.
2. The Suspension of Explosive Composition of Pill Fuse Head for Industrial Electric Detonators according to Claim 1, **characterized by** the fact that the organic solvent is amyl acetate, butyl acetate, propyl acetate, or isomers thereof.

Patentansprüche

1. Suspension einer explosiven Zusammensetzung eines pillenförmigen Zündkopfes für industrielle elektrische Detonatoren, **dadurch gekennzeichnet, dass sie** aus 30 - 60 Gewichtsteilen Kaliumsalz von Dinitrobenzofuroxan, 15 - 35 Gewichtsteilen Kalium-

perchlorat, 5 - 20 Gewichtsteilen Zirkonium, 5 - 20 Gewichtsteilen Bor und 5 - 50 Gewichtsteilen Calciumsilicid in einer 1 - 5%igen Fluorelastomerlösung in einem organischen Lösungsmittel besteht.

5

2. Suspension einer explosiven Zusammensetzung eines pillenförmigen Zündkopfes für industrielle elektrische Detonatoren nach Anspruch 1, **dadurch gekennzeichnet, dass** das organische Lösungsmittel Amylacetat, Butylacetat, Propylacetat oder deren Isomere ist.

10

Revendications

15

1. Suspension de composition explosive de tête fusible pilule pour des détonateurs électriques industriels, **caractérisée par le fait qu'elle** est constituée de 30 à 60 portions du sel de potassium du dinitrobenzofuroxane, de 15 à 35 portions en poids de perchlorate de potassium, de 5 à 20 portions en poids de zirconium, de 5 à 20 portions en poids de bore et de 5 à 50 portions en poids de siliciure de calcium dans une solution de 1 à 5 % d'élastomère fluoré dans un solvant organique.
2. Suspension de composition explosive de tête fusible pilule pour des détonateurs électriques industriels selon la revendication 1, **caractérisée par le fait que** le solvant organique est l'acétate d'amyle, l'acétate de butyle, l'acétate de propyle, ou leurs isomères.

20

25

30


35

40

45


50

55



Obr.1

Fig.1



Obr.2

Fig. 2

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- CZ 294317 [0007]