



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2470836 A1 2003/07/17

(21) **2 470 836**

(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(86) Date de dépôt PCT/PCT Filing Date: 2003/01/08
(87) Date publication PCT/PCT Publication Date: 2003/07/17
(85) Entrée phase nationale/National Entry: 2004/06/16
(86) N° demande PCT/PCT Application No.: EP 2003/001211
(87) N° publication PCT/PCT Publication No.: 2003/057389
(30) Priorité/Priority: 2002/01/10 (10/043,655) US

(51) Cl.Int.⁷/Int.Cl.⁷ B22D 1/00, C21C 1/10
(71) Demandeur/Applicant:
PECHINEY ELECTROMETALLURGIE, FR
(72) Inventeur/Inventor:
MARGARIA, THOMAS, FR
(74) Agent: OGILVY RENAULT

(54) Titre : BOULETTE D'INOCULANT POUR INOCULATION TARDIVE DE FONTE
(54) Title: INOCULANT PELLET FOR LATE INOCULATION OF CAST IRON

(57) **Abrégé/Abstract:**

A pellet, intended for the late inoculation of cast irons, obtained by agglomeration of a powdered inoculant, wherein the mass proportion of the granulometric fraction 50 - 250 µm of the powdered inoculant of which the pellet is constituted is comprised between 35 and 60%, and the mass proportion of the granulometric fraction below 50 µm is lower than 25%.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
17 July 2003 (17.07.2003)

PCT

(10) International Publication Number
WO 03/057389 A3

(51) International Patent Classification⁷: **B22D 1/00**,
C21C 1/10

(21) International Application Number: PCT/EP03/01211

(22) International Filing Date: 8 January 2003 (08.01.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/043,655 10 January 2002 (10.01.2002) US

(71) Applicant: **PECHINEY ELECTROMETALLURGIE**
[FR/FR]; Tour Manhattan, F-92087 Paris La Défense
Cedex (FR).

(72) Inventor: **MARGARIA, Thomas**; 45, impasse des Clos
de Bouan, F-74190 Passy (FR).

(74) Agent: **MOUGEOT, Jean-Claude**; Pechiney, 217, cours
Lafayette, F-69451 Lyon Cedex 06 (FR).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(88) Date of publication of the international search report:
24 December 2003

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: INOCULANT PELLET FOR LATE INOCULATION OF CAST IRON

(57) Abstract: A pellet, intended for the late inoculation of cast irons, obtained by agglomeration of a powdered inoculant, wherein the mass proportion of the granulometric fraction 50 - 250 µm of the powdered inoculant of which the pellet is constituted is comprised between 35 and 60%, and the mass proportion of the granulometric fraction below 50 µm is lower than 25%.



WO 03/057389 A3

INOCULANT PELLETT FOR LATE INOCULATION OF CAST IRONField of the Invention

The invention concerns the late, so-called "in mould", treatment of liquid cast irons intended for the manufacture of parts for which it is desired to obtain a structure free from iron carbides.

The treatment concerned is mainly inoculation treatment.

"In mould" treatment consists in placing the cast iron treatment product in the liquid cast iron casting system.

Prior art

Cast iron is a well known iron-carbon-silicon alloy widely used for the manufacture of mechanical parts. It is known that in order to procure good mechanical properties for these parts, it is necessary in the end to obtain an iron + graphite structure while preventing as far as possible the formation of Fe_3C type iron carbides which embrittle the alloy.

Thus it may be preferred for the formed graphite to be spheroidal, if a spheroidal graphite cast iron called "SG iron" is required, rather than lamellar, if a lamellar graphite cast iron called "LG iron" is required, but the essential prior condition to be met is to prevent the formation of iron carbide.

To this end the liquid cast iron is subject before casting to an inoculation treatment, which will, as it cools, favour the appearance of graphite rather than that of iron carbide.

The inoculation treatment is therefore very important. It is in fact well known that inoculation, whatever the inoculants used, has on the liquid cast iron an effectiveness which reduces with time and which, generally, has already reduced by 50% after a few minutes. To obtain maximum effectiveness, the man skilled in the art generally practises progressive inoculation, applying to this end several additions of inoculants at different stages of the development of the cast iron; the final addition is made "in mould" as the moulds are fed or even in the feed conduits of the moulds by placing in the path of the liquid cast iron inserts constituted by an inoculant material. These inserts are generally used associated with a filter; in this case they generally have a perfectly defined shape in order to be able to be fixed in the filter, most often in an adapted cavity; these inserts of defined shape are known as pellets. We will denote by the name "inoculant filter" the unit constituted by the slug and the filter.

There are two types of pellets:

- "moulded" pellets obtained by moulding the molten inoculant.
- agglomerated pellets obtained from a pressed powder with generally very little binding agent, or even without binding agent.

Moulded pellets are considered, by the man skilled in the art, as being the best quality; however agglomerated pellets are often preferred to them for reasons of cost.

Object of the invention

The object of the invention is a pellet, intended for the late inoculation of cast irons, obtained by agglomeration of a powdered inoculant, characterised in that the mass proportion of the granulometric fraction 50 - 250 microns of the powdered inoculant of which the pellet is constituted is comprised between 35 and 60%, and preferably between 40 and 50%, and the mass proportion of the granulometric fraction below 50 microns is lower than 25%, and preferably 20%. The particle size of the powder is preferably lower than 1 mm.

Description of the invention

The man skilled in the art who practises inoculation at the different stages of the development of the cast iron uses products which are all the finer the later the inoculant is added in the process; the logic is that upstream the products have all the time necessary to dissolve and that when they reach the inlet of the moulds they have only a few seconds left before solidification.

In this way, the granulometry bracket 2/10mm is currently used in pre-inoculation, 0.2/2mm during ladle treatment, and 0.2/0.7mm for runner inoculation when casting the ladles. The applicant has in fact noted in the testing shop an unexpected phenomenon:

For a same dosing of inoculant, the number of graphite nuclei generated in the liquid cast iron

increases with the number of inoculant particles added to the inoculant mass unit.

Therefore if two ladles of cast iron are treated in identical conditions with a same inoculant in two different particle size distributions, the cast iron treated with the finest product will contain more graphite nuclei than that treated with the coarser product; these nuclei will also be smaller in size.

The same phenomenon has been observed during an "in mould" treatment with agglomerated slugs; the cast iron treated with a slug obtained from a finer powder will contain more graphite nuclei than that treated with a pellet obtained from a coarser powder; these nuclei will also be smaller in size.

This fairly unexpected observation may have advantageous applications since it may make it possible to control the density of the graphite nuclei in the cast iron part and therefore the structure of the manufactured part.

To obtain pellets in this way which have maximum effectiveness in terms of inoculation, the applicant has been led to prepare powders at 0/1 mm having a particular internal particle size distribution defined in the following way:

Passing to 1 mm: 100 %.

Fraction between 50 μ and 250 μ : 30% to 60%, and preferentially 40% to 50%.

Fraction below 50 μ : less than 25% and preferentially less than 20%.

A powder of this type agglomerates easily which makes it possible to operate with lower proportions of

binding agent. Thus with sodium silicate which is a well-known binding agent, doses of 0.3cm^3 for 100g of powder to 3cm^3 for 100g of powder are sufficient according to the pressures employed which may vary from 50 to 500Mpa; since the mechanical performance of the pellets is easily acquired, the pressure and binding agent percentage parameters may be used to control the dissolution speed of the pellet and not its mechanical performance.

However experience shows that the particle size distribution defined above cannot be obtained by natural crushing; the preparation of powder with this particle size distribution requires a dosing of size fractions prepared in isolation.

The inoculant composition can be obtained either by mixing powders of different elemental products, or in form of an alloy powder, or by mixing powders of different alloys.

Examples:

The following examples n° 1 to 5 deal with SG cast irons; example n° 6 deals with a case of LG cast iron.

Example 1:

A batch A of commercially available agglomerated inoculant pellets of the prior art was acquired and analysed; this analysis gave:

Si = 72.1%, Al = 2.57%, Ca = 0.52%.

Then a batch of molten inoculant of analysis as close as possible to that of the previous batch was synthesised in the induction furnace from FeSi 75 the

strength of which was corrected by adding calcium silicide, aluminium then iron; this batch of inoculant was then cast in 25g moulded pellets.

Sampling and analysis of this batch of pellets B gave:

Si = 72.4%, Al = 2.83%, Ca = 0.42%.

Example 2:

A charge of cast iron was melted in the induction furnace and treated by the Tundish Cover process by means of an alloy of the FeSiMg type with 5% Mg, 2% Ca, and 2% TR at the dose of 20kg for 1600kg of cast iron.

The analysis of this liquid cast iron gave:

C = 3.7%. Si = 2.5%, Mn = 0.09%, P = 0.03%, S = 0.003%, Mg = 0.042%.

Its eutectic temperature was 1141°C.

This cast iron was used to cast parts with a unit mass of about 1 kg, placed in clusters in a 20 part mould fed by an inflow conduit in which was placed a moulded pellet supported by a filter constituted by a refractory foam with an average pore diameter of 5 mm.

The moulded pellet employed came from batch B.

The number of graphite nodules observed by metallography on the cross-section of the parts, was 184/mm².

Example 3

Example no. 2 was reproduced in an identical way with the sole difference that the moulded pellet coming from batch B was replaced by an agglomerated pellet according to the prior art obtained by pressing a

powder to 0/2mm obtained by natural crushing of moulded pellets taken from the same batch B as the pellet used in the previous example.

The particle size distribution of this powder was:

Passing to 2mm : 100 %

Passing to 0.4mm 42%; Passing to 0.2mm 20%;

Passing to 50 μ : 10%, i.e. a particle size distribution quite close to that recommended in the Foseco patent EP 0.234.825.

The number of graphite nodules observed by metallography on the cross-section of the parts was 168/mm².

Example 4

Example no. 3 was reproduced in an identical way with the sole difference that the moulded pellet came from batch A. The number of graphite nodules observed by metallography on the cross-section of the pellets was 170/mm².

Example 5

Example no. 3 was repeated in the following conditions:

A 25kg batch of moulded pellets coming from batch B was crushed to 0/1mm.

The fractions 0.63/1mm; 0.40/0.63mm; 0.25/0.40mm; 0.050/0.25mm and 0/0.050mm were separated by sieving.

It has been obtained: 3.5kg of 0.63/1mm; 3.9kg of 0.40/0.63mm; 4.2kg of 0.25/0.40mm; 7.1kg of 0.050/0.25mm and 6.1kg of 0/0.050mm.

A powder of synthesis was prepared by blending:

2kg of 0.63/1mm, 2kg of 0.40/0.63mm, 2kg of 0.25/0.40mm, 7kg of 0.050/0.25mm, and 2kg of 0/0.050mm.

To these 15kg of powder were added: 150cm³ of sodium silicate and 150cm³ of 10N sodium hydroxide.

The blend obtained was used to manufacture cylindrically shaped agglomerated pellets 24mm in diameter, 22mm high. The pressure exerted on the pellet to shape it was 285 Mpa for 1 second.

The shaped pellets were stored at 25°C for 8 hours in a carefully ventilated location, and were then oven-dried at 110°C for 4 hours. The pellets obtained, of 25kg unit mass, constituted a batch denoted batch C.

Example n° 3 was then repeated with pellets coming from lot C assembled with a ceramic foam filter identical to that used in example no. 2.

The number of graphite nodules observed by metallography on the cross-section of the parts was 234/mm².

Example 6

Example n° 5 was repeated in the following conditions:

A charge of 1600kg of cast iron was melted in an induction furnace: a sample was taken of the liquid metal and analysed.

The analysis gave:

C = 3.15%, Si = 1.82%, Mn = 0.71%, P = 0.15%, S = 0.08%.

Its eutectic temperature was 1136°C.

This cast iron was used to cast parts with a unit mass of about 1kg, placed in clusters in a 20 part

mould fed by an inflow conduit in which was placed a moulded pellet supported by a filter constituted by a refractory foam with an average pore diameter of 5mm.

The moulded pellet employed came from batch C.

The number of eutectic cells observed by metallography on the cross-section of the parts was 310/mm².

CLAIMS

1. A pellet, intended for the late inoculation of cast irons, obtained by agglomeration of a powdered inoculant, characterised in that the mass proportion of the granulometric fraction 50 - 250 microns of the powdered inoculant of which the pellet is constituted is comprised between 35 and 60%, the mass proportion of the granulometric fraction below 50 microns is lower than 25%, and the powdered inoculant has a particle size lower than 1 mm.
2. A pellet according to claim 1, characterised in that the mass proportion of the granulometric fraction 50 - 250 microns of the powdered inoculant of which the pellet is constituted is comprised between 40 and 50%, and the mass proportion of the granulometric fraction below 50 microns is lower than 20%.
3. A pellet according to one of claims 1 or 2, characterised in that the powdered inoculant used for the preparation of the pellet is a blend of two or more inoculant powder alloys.
4. A pellet according to one of claims 1 or 2, characterised in that the powdered inoculant used for the preparation of the pellet is a blend of two or more products constituting a heterogeneous inoculant.