WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 4:

B23K 9/00, B05D 1/00

(11) International Publication Number:

WO 89/10818

(43) International Publication Date:

16 November 1989 (16.11.89)

(21) International Application Number:

PCT/US89/02053

A1

(22) International Filing Date:

12 May 1989 (12.05.89)

(30) Priority data:

193,739

13 May 1988 (13.05.88)

US

(71) Applicant: ADVANCED POLYMER SYSTEMS, INC. [US/US]; 2800 High Ridge Road, Boyn Town Beach, FL 33426 (US).

(72) Inventor: WEIDMAN, Larry, G.; 15730 Glendale Lane, Fort Myers, FL.33912 (US).

(74) Agent: COLLINS, John, M.; Hovey, William, Timmons & Collins, 1400 Mercantile Bank Tower, 1101 Walnut Street, Kansas City, MO 64106-2165 (US).

(81) Designated States: AT, AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CF (OAPI patent), CG (OAPI patent), CH, CH (European patent), CM (OAPI patent), DE, DE (European patent), DK, FI, FR (European patent), GA (OAPI patent), GB, GB (European patent), HU, IT (European patent), JP, KP, KR, LK, LU, LU (European patent), MC, MG, ML (OAPI patent), MR (OAPI patent), MW, NL, NL (European patent), NO, RO, SD, SE, SE (European patent), SN (OAPI patent), TG (OAPI patent).


Published

With international search report.

(54) Title: APPARATUS AND METHOD FOR APPLYING PLASMA FLAME SPRAYED POLYMERS

(57) Abstract

An apparatus and method for applying plasma flame sprayed polymers is provided which permits the application of a thin coating of heat fusible material onto substrate material. The apparatus is used with a conventional plasma generator (12) whereby materials such as nylon or other synthetic polymers may be injected into the plasma stream to melt the powder without overheating it. The apparatus includes a central water-cooled nozzle (58), surrounded by an open co-axial flow area within a barrel (16). The polymer is evenly distributed on the substrate due to the co-axial flow of the plasma stream and air drawn through the flow area. A source of vacuum (20) connected to the apparatus (10) draws fumes generated by the melted polymers into an opening surrounding the bore (98) at the front of the barrel (16), whereby the vacuumed gases may be filtered. The apparatus (10) may be used in a method of applying plas-



ma flame sprayed polymer compositions to a surface.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

ΑT	Austria	· FI	Finland	ML	Mali
ΑŪ	Australia	FR	France	MR	Mauritania
BB	Barbados.	GA.	Gabon	MW	Malawi
BE	Belgium	GB:	United Kingdom	NL	Netherlands
BF	Burkina Fasso	HU	Hungary	NO	Norway
BG	Bulgaria	П	Italy	RO	Romania
BJ	Benin	JP	Japan	SD	Sudan
BR-	Brazil	KP	Democratic People's Republic	SE	Sweden
CF.	Central African Republic		of Korea	SN	Senegal
CG	Congo	KR	Republic of Korea	SU	Soviet Union
CH	Switzerland	Ц	Liechtenstein	TD	Chad
CM	Cameroon	LK	Sri Lanka	TG	Togo
DE	Germany, Federal Republic of	w	Luxembourg	US	United States of America
DK	Denmark	MC	Моласо		
ES:	Spain	MG	Madagascar		

-1-

ADDADATI

APPARATUS AND METHOD FOR APPLYING PLASMA FLAME SPRAYED POLYMERS

5

10

15

20

25

30

35

1

Background of the Invention

1. Field of the Invention

An apparatus for rapidly applying a polymer coating to a variety of surfaces through plasma flame spraying is provided, enabling the user to work in relative safety and achieve a smooth, uniform coating. The apparatus hereof is particularly concerned with a hand-held device for plasma flame spraying a variety of polymers whereby a surface such as wood, fibrous glass reinforced synthetic resin, or even cardboard may be sprayed in close proximity to the front of the barrel of the apparatus without damaging the surface or exposing the operator to potentially toxic fumes resulting from the melted polymer. In its preferred method aspects, the invention involves applying a protective coating to a surface such as a boat hull by providing a electric arc, directing a gas stream through the arc thereby heating the gas stream, injecting a powdered polymer into the gas stream at at location downstream from the arc so as to melt the powder without overheating the same, and then applying the melted mixture to the surface to be coated.

2. Description of the Prior Art

Plasma flame spraying has proven to be a highly efficient and effective method of applying heat fusible materials to a variety of heat resistant surfaces. Plasma is an extremely hot substance consisting of free electrons, positive ions, atoms and molecules. Although it conducts electricity, it

1

5

10

15

20

25

30

35

electrically neutral. Plasma is usually generated at temperatures in the vicinity of 15,000 degrees Centigrade by the passage of a gas through an electric arc. In typical plasma spraying systems, a selected inert gas, such as argon or nitrogen, flows between an anode and a cathode. electrical arc is generated between the anode and cathode, both heating and propelling a heat fusible material carried with the gas. The movement of the gas beween the anode and cathode effectively lengthens the path of the arc, causing more energy to be delivered to the arc. The plasma may issue from the nozzle at subsonic to Mach II speeds, with a flame of intense brightness and heat resembling an open oxy-acetylene flame.

It may be readily appreciated that the intense heat associated with the plasma stream and the rapid flow of the plasma through the presents a highly efficient means of melting a heat fusible material and spraying it on a target sur-The plasma flame spray guns previously developed have been principally designed to apply powdered ceramics or metals which have high melting temperatures. These materials are typically injected at or near the arc to achieve the instantaneous melting required when the plasma stream is flowing at sonic or near sonic speeds. Despite the intense heat generated at the arc, the temperature of the plasma gas stream drops rapidly across the intervening distance between the electrode and the target surface. This drop is a function of gas enthalpy, energy absorption by the powdered material, and work distance.

It has become increasingly popular to attempt to apply synthetic polymers by the plasma

-3-

flame spray method. Flame sprayed polymer powders 1 are lighter in mass and have a much lower melting point than ceramics or metals. As a result, the high temperatures of the arc tend to "burn" the polymers rendering the resulting coating unsuitable. 5. Various plasma spray devices have been developed for use with polymers, such as that of U.S. Patent No. 3,676,638, which discloses a nozzle whereby powder is fed into the plasma gas stream downstream from the arc. These prior plasma spray devices have 10. been limited in the rate of application due to the low are power settings necessary to avoid "burning" the polymer, and have had a tendency to produce a somewhat uneven coating with splattering and dan-

gerous and inefficient overspray.

Nonetheless, the durabi

20

25

30

35

Nonetheless, the durability and density of plasma sprayed polymer coatings have produced a demand for devices which can effectively apply these coatings. In contrast to painted polymer coatings, which require a great deal of surface preparation and wear rapidly, plasma flame sprayed polymer coatings provide a wear-resistant coating of high density with a high bond strength generated as a result of the high velocity impact of the molten composition onto the target surface. In addition, only a nominal amount of grit blasting to slightly roughen the surface and remove any surface contamination is necessary to prepare the surface for plasma flame spraying. However, certain polymer compositions have heretofore been diffficult to use in hand held operation because of the toxic fumes released by the molten polymer in the plasma stream. Further. prior apparatus made it difficult prevent the plasma gas stream from scorching the surface during application. The high heat of the

5

plasma stream in close proximity to the user also posed a safety harzard in the event a plasma gas stream were to be inadvertently directed at the user or another person. Because of the high heat generated by the plasma gas stream, the target surface remained hot after the deposit of the coating, resulting in additional release of toxic fumes into the environment.

10

15

20

25

Summary of the Invention

The problems outlined above are in large measure solved by the present invention which provides an apparatus for plasma flame spraying polymers on a variety of target surfaces by providing a cooled, laminar flow plasma gas stream with a minimum of turbulence. The apparatus includes a conventional plasma flame generator and a novel barrel for cooling the plasma gas stream, providing a plasma gas stream having a minimum of turbulence between a nozzle and the target surface, and introducing a polymer in the plasma gas stream.

The invention hereof includes a fluidcooled plasma flame generator, a barrel, and means
for mounting the barrel to the plasma flame generator. The barrel includes a fluid-cooled nozzle
through which the plasma gas stream passes upon
exiting the plasma flame generator. An open, coaxial airflow area surrounds the nozzle and permits
air to flow from the rear of the barrel to the front
of the barrel in the same direction and substantially co-axial with the flow of the plasma gas
stream. Powder introduction tubes are mounted
exterior to the nozzle for introducing polymer,
usually in powdered form, into the plasma gas stream
downstream from the nozzle.

35

1

5

10

15

20

2.5

More particularly, the invention hereof includes a frustoconical shaped nozzle which is provided with a central bore and an interior which is adapted to receive a fluid coolant with a water-cooled plasma flame generator. The nozzle, and the barrel of which it is one component, are mounted to the plasma flame generator by an adaptor plate which permits the exchange of coolant between the generator and the nozzle. The nozzle is thus cooled both by the circulation of coolant on the interior thereof, as well as the flow of air over the exterior surface.

The barrel is provided with an hourglassinterior wall, with the waist hourglass-shaped interior wall lying in the same plane as the front end of the nozzle. The posterior margin of the interior wall abuts the posterior margin of the exterior wall to form an air seal therebeween. In contrast, the diameter of the anterior margin of the interior wall is somewhat less than the anterior margin of the exterior wall, defining an annular space therebetween. source may be attached to the barrel to both cool the target surface and draw fumes and polymer which has splattered off the target surface into the space between the interior and exterior walls of the barrel to a separate filtering device. Toxic vapors resulting from the melting of particular polymers are thereby captured, maintaining a safe environment for the operator.

30

Because of the nozzle design and the provision for coaxial flow of air and plasma gas, the plasma gas stream exits the nozzle with a minimum of turbulence and remains substantially laminar as it travels to the target surface. The sur-

1

5

rounding air cools the stream and permits the introduction of the polymer outside the nozzle, substantially in the atmosphere. The plasma gas stream is
thereby suficiently cooled to enable coating of
combustibles such as even cardboard or fibrous glass
reinforced plastic at a distance of four inches (10
centimeters). Being able to operate the apparatus
so closely to the target surface minimizes the
danger to other workers and permits accurate and
uniform coating. It also improves the effectiveness
of the vacuum in cooling the target surface and
preventing vapor and particle loss to the atmosphere, in effect maintaining a separate environment
for operation of the apparatus.

15

10)

The exterior wall of the barrel also acts as a shroud to enclose the open arc, thereby preventing eye burn to the operator or other workers in the vicinity. The absence of a "flame" extending beyond the barrel improves the safety of the device.

20

One particular polymer composition which may be used in connection with this invention and a method for applying it is shown, for example, in my U.S. Application Serial No. 193,805, (attorney's Docket No. 19615), filed concurrently herewith and entitled Protective Coating for Boat Hulls and Method of Applying the Same, the disclosure of which is incorporated herein by reference.

25

These and other advantages will be readily apparent to those skilled in the art from the disclosure recited herein.

30

Brief Description of the Drawing

Figure 1 is a side elevational view of the apparatus for applying plasma flame sprayed polymers;

1

5

10

15

Fig. 2 is a top plan view of the apparatus shown in Fig. 1;

Fig. 3 is a front elevational view showing the annular space between the interior and exterior walls of the barrel;

Fig. 4 is a rear elevational view showing the adapter plate mounted to the nozzle at the rear of the barrel, and a pair of powder introduction tubes for introducing powder into the plasma gas stream;

Fig. 5 is a front elevational view of the fluid cooled plasma flame generator hereof, and in particular a PLASMADYNE Model SG-100 with the cover plate removed to expose coolant exchange ports in the anode, and a control handle coupled thereto; and

Fig. 6 is an enlarged, horizontal sectional view along line 6-6 of Fig. 1, showing the nozzle, carrier tubes, coolant circulation path and interior and exterior barrel walls.

20

25

Detailed Description of the Drawing

Referring now to the drawing, an apparatus for applying plasma flame sprayed polymers 10, in accordance with the invention, includes a plasma flame generator 12, adaptor plate 14 and barrel 16. Barrel 16 is provided with a substantially cylindrical outer wall 18, and vacuum connection 20. As shown in Figs. 1-3, 4 and 6, a pair of carrier block assemblies 22 extend from the posterior of the barrel and are mounted therein.

30

The plasma flame generator 12 shown and described herein is a PLASMADYNE Model SG-100, which operates at power levels up to 80 kilowatts using argon, argon/hydrogen or argon/helium as the plasma gas. The Model SG-100 is water-cooled, with a water

and power inlet connection 24 at the center rear of the generator 12 and a water and power outlet connection 26 located therebeneath. The water and power outlet line 28 extends from the front of the 5 generator rearward through graspable handle Handle 30 is provided with trigger button 32 for initiating the plasma stream, and trigger button 34 for initiation of powder feed. The PLASMADYNE Model SG-100 is further provided with a plasma gas connection 36 for connection with the argon, argon/-LO hydrogen or argon/helium feed line. Powder tube 38 extends beneath the generator for passage of powder near the electrodes within the generator for use of the apparatus with ceramic or metallic powders. 15

The conventional PLASMADYNE Model SG-100 is provided with a cover plate for preventing the escape of cooling water which circulates through the generator and particularly the anode 40, as shown in Fig. 5. A series of water supply ports 42 provide a flow of water in a path toward barrel 16, while a series of larger water return ports 44 carry the water coolant toward the water and power outlet line 28, the water coolant carrying excess heat generated by the arc. In the center of the copper anode 40, a plasma orifice 46 permits the plasma gas stream to exit the generator and enter the barrel 16.

Barrel 16 is joined to generator 12 by adaptor plate 14. Adaptor plate 14 is in the nature of a flat, annular copper disc provided with a central opening 48 in front of anode 40. The adaptor plate is provided with three equally spaced countersunk holes 50 with mounting screws 52 inserted therethrough into generator 12. A second

30

20

5

10

15

20

25

30

35

series of three holes 54 are provided for mounting the barrel 16 to the adaptor plate 14.

Referring now to Figs. 3 and 4, barrel 16 includes outer wall 18, vacuum connection 20, carrier block assembly 22, inner wall 56 and nozzle 58. The inner wall 56 is hourglass-shaped, being composed of two opposed frustoconical members joined at the waist 60 of the houglass shape thereby created. The diameter of the exterior of the posterior margin 62 of the inner wall 56 is substantially the same as the interior diameter of the posterior margin 64 of the outer wall 18, thereby forming an effective fluid-tight air seal between the posterior margin 64 of the outer wall 18 and the posterior margin 62 of the inner wall 56.

In contrast, the outside diameter of the anterior margin 66 of the inner wall 56 is sufficiently less than the inside diameter of the anterior margin 68 of the outer wall 18, thereby defining an annular opening 70 between the inner wall 56 and exterior wall 18. Except at the posterior margins 64 and 62, outer wall 18 and inner wall 56 are spaced apart, defining an airway 72 therebetween. The airway 72 communicates with vacuum connection 20 by an opening in the outer wall 18 at the junction of the vacuum connection 20 and the outer wall 18, for the passage of air drawn therethrough by a vacuum source.

Carrier block assemblies 22 are mounted on opposite sides of barrel 16 between inner wall 56 and nozzle 58. The two carrier block assemblies 22 lie in approximately the same plane as each other, and occupy a portion of the otherwise continuous open coaxial airflow area 74 which substantially surrounds the nozzle 58. Each carrier block

1

5

assembly includes a copper powder introduction tube 76, a carrier block 78 and a threaded tightening screw 80. As may be seen in Fig. 6, the tightening screws 80 extend through tapped openings 82 in the carrier blocks 78, thereby permitting the tubes 76 to be removed from the carrier blocks 78 but still ensuring that the tubes 76 remain properly positioned during operation.

10

15

The carrier blocks 78 are tapered at their anterior ends 84 and posterior ends 86 as shown in Figs. 3 and 4, thereby minimizing the turbulence of the air as it flows past the carrier blocks 78 into the open coaxial flow area 74. An aperture 88 extends through the carrier blocks 78, each aperture being in the same horizontal plane and the horizontal plane bisecting the nozzle 58. The appertures 88 converge from the posterior of the barrel 16 toward the anterior of the barrel 16, each at an angle from 12 to 20 degrees and preferably 18 degrees from the flow axis A-A' of the plasma gas stream.

20

25

As may be seen in Fig. 6, the powder introduction tubes 76 are of a sufficient length that the tubes 76 extend forward of the carrier block 78 and nozzle 58. The front of the nozzle 58, anterior end 84 of the carrier block 78, and waist 60 of the inner wall 56 all lie in the same plane P. Plane P is substantially normal to plasma gas stream flow axis A-A'. Thus, the powder introduction tubes 76 are located exterior to the nozzle 58, extend beyond the nozzle 58, and direct a carrier gas and powdered polymer stream in a direction convergent with the plasma gas flow axis A-A' so that the polymer is introduced through the tubes 76 into the plasma gas stream at a location downstream from the

35

5

10

15

20

25

30

35

nozzle 58. The plasma gas stream is thus exposed to the atmosphere before intersection with the powdered polymer. The tubes 76 are threaded at their posterior end for connection to a supply line carrying a carrier gas such as nitrogen or argon and a polymer powder.

The carrier blocks 78 are secured by screws 90, 92 to the inner wall 56 and nozzle 58 and thus serve to join the nozzle 58, carrier block assemblies 22, and inner wall 56. Inasmuch as outer wall 18 and inner wall 56 are joined to the carrier block 78 adjacent their posterior margins 64, 62 by screws 96, the nozzle 58, carrier block assemblies 22, inner wall 56 and outer wall 18 substantially form the barrel 16.

The nozzle 58 is a hollow, copper frustoconical member having an exterior jacket surface 96
tapering inwardly with its center along flow axis
A-A'. The exterior diameter of the exterior jacket
96 decreases along the plasma gas stream flow from A
to A', with A being at the posterior of the barrel
16. The inner wall 56 and the exterior jacket 96
define the coaxial airflow area 74 therebetween.
The co-axial flow area 74 is substantially annular
in cross-section adjacent nozzle 58 and is adapted
to communicate air drawn through the open area
between nozzle 58 and posterior margin 62 by the
plasma gas stream to the open area at the front of
the barrel 16.

In contrast, the nozzle 58 is provided with a central bore 98 defined by interior jacket 100 of the nozzle, the diameter of the bore increasing in a direction along the plasma gas stream flow axis from A to A'. The bore 98 is frustoconical in configuration, with the axis of the bore 98 coinci-

10.

15

20

2.5

dent with the plasma gas stream flow axis A-A'. The bore 98 thus tapers outwardly in the direction of the plasma gas stream as defined by the interior jacket 100 of the nozzle 58.

The rear wall 102 of the nozzle 58, together with the exterior jacket 96 and the interior jacket 100 define a substantially open chamber 104 to receive fluid coolant therein. Water flows into the chamber 104 from water supply port 42 in the anode 40 through acesses 106, 108 and 110 at the rear of the nozzle 58. Water or other fluid coolant enters chamber 104, circulates at random and accumulates heat therein, and is forced out through accesses 106, 108 and 110 to water return ports 44 in the anode 40 by additional water furnished through water supply ports 42.

Support arms 112, 114 and 116 interconnect rear wall 102 and interior jacket 100, providing structural rigidity and maintaining the bore 98 in proper alignment. Anode 40 is provided with lips 118 and 120 to provide a channel for the cooling water and enter recessed area 122 to form a seal between the nozzle 58 and anode 40. Silicon rubber O-rings 124, 126 ensure that the seal thus created remains watertight. A raised ring portion 128 of rear wall 102 mates with adaptor ring 14 and anode 40. The difference between the outside diameter of interior jacket 100 and the inside diameter of ring portion 128 defines accesses 106, 108 and 110.

In the preferred embodiment, the upstream frustoconical portion 130 of the inner wall 56 is convergent in the direction of flow of the plasma gas stream along the axis from A to A', at an angle of approximately 20 degrees from A-A'. The down-

10

15

20

25

30

35

stream frustoconical member 132 of the hourglass-shaped interior wall 56 is divergent in the direction of plasma gas flow along axis from A to A', at an angle of approximately 25 degres from A-A'. The exterior jacket 96 of the nozzle 58 is convergent in the direction of flow of the plasma gas stream along the axis from A to A' at an angle of 20 degrees from A-A'. The interior jacket 100 of the nozzle 58 is divergent in the direction of flow of the plasma gas stream from A to A' at an angle of 5° from A-A'.

The apparatus is assembled by mounting adaptor plate 14 on generator 12 with screws 52. Barrel 16 is then mounted on adaptor plate 14 by three allen bolts 134 inserted through holes 54 spaced around the exterior of the adaptor plate 14 and threaded into corresponding threaded holes 136 around the exterior of the nozzle 58. Necessary cables and hoses are then connected at the locations corresponding to the fittings described hereinabove.

Polymers may be sprayed utilizing the apparatus described herein by the method described as follows.

A polymer such as nylon is prepared in pelletized forms of a size of approximately 325 mesh (120 microns) and placed in a powder feeder such as a Plasmatron Model 1251 powder feeder. A source of argon or other carrier gas is connected with the powder feeder and then the carrier gas - powder feed line is connected with appropriate fittings to powder introduction tube 76. A second source of gas, also preferably argon, provides the source for the plasma gas and is routed through, for example, a Plasmadyne Model powder feeder and thence to the plasma generator 12, with connections at plasma gas connection 36. Cooling water is supplied from a

5

100

15

20

25

30

35

suitable water source, with additional pressure supplied by a suitable water pump. The water hose is coaxial with a control cable and power supply cable connected at water and power inlet connection 24 by suitable coaxial hoses. The water and power return line returns water from the plasma generator to the heat exchanger. The control cable is routed through a control console, such as a Plasmatron Model 3700, into an auxiliary powder feed control, such as a Plasmatron Model 3700-200. supplied by a suitable source of 40 kilowatt powder, such as a Plasmatron Model PS-61N. Finally, a vacuum source, such as a vacuum pump is connected by a hose to vacuum connection 20. When water, power, plasma gas, carrier gas and powder, and vacuum are supplied to the apparatus, it is ready for operation.

Preferred techniques for applying a polymer coating composition include the steps of providing a high velocity flow (i.e., about Mach I or above) of a gas such as pure argon; passing gas transversely through an elongated high wattage electric arc for heating the gas and converting a portion thereof to the plasma state through plasma generator 12; introducing the powdered coating composition into the gas downstream from nozzle 58 through powder introduction tubes 76 for melting the powder without overheating the powder; directing the flow of the coating composition and associated gas into substantially one direction for minimizing overspray and misting of the composition; spraying said melted composition onto a target surface to be coated.

In a more preferred method, the plasma gas stream exits a nozzle 58 and draws with it air

-15-

1

5

10.

15

provided from an open, co-axial flow area 74 prior to the introduction of the polymer composition into the plasma gas stream. More preferably, powdered composition is introduced into the gas stream in a downstream direction and at an angle from about 12 to 20 degrees to the direction of flow of the plasma gas stream from A to A'; and most preferably the powdered composition is injected in a downstream direction at an angle of about 18 degrees to that of the plasma gas stream so as to minimize vortex formation within the stream and minimize the overspray associated with vortex formation. more preferably, the powder is injected at a distance of about 6 to 10 inches downstream from the arc (the arc being defined as the point of energy transfer between an anode and a cathode) so as to minimize overheating of the composition and so as to insure that the composition reaches maximum velocity for a corresponding maximum bond strength with the surface to be coated; and more preferably, injecting the composition into the gas stream at a location of about from 8.5 to 9 inches downstream from the arc so as to achieve the proper molten state of the composition and a particle velocity favoring inner atomic bonding of the composition with the surface

25:

3)

to be coated.

20

If injection of the powdered composition is made either through a high wattage arc or closely adjacent thereto, the composition will be overheated and rendered useless. If a lower wattage arc is employed so as to generate a temperature low enough to permit injection of the powder either through the arc or adjacent thereto, then the application rate permitted by the arc will be so low as to make large scale application economically infeasible. Thus,

5

10:

15

20.

25

30

35

introduction of the powdered composition substantially downstream from the arc is advantageous to achieve an economically feasible, high volumetric rate application technique. Also, injection of the powder downstream from the arc permits increased arc temperature, which in turn permits adequate heating of increased flows of gas thereby permitting adequate melting and particle velocity for increased powder flow rates. Yet further, the higher arc temperature and injection of the polymer powder downstream from the nozzle enables the simultaneous spraying of polymers and ceramics or metals when a carrier gas and metal or ceramic powder hose is connected at powder tube 38. To achieve the high volumetric application rates of, for example, polyamide coatings, the arc used in the method of the present invention has a preferred power level of 20 to 40 kilowatts and an associated gas temperature at the arc of approximately 12,000 to 30,000 degrees Centigrade. More preferably, the arc has a power level of 28 kilowatts and an associated gas temperature at the arc of approximately 22,500° Centigrade. The plasma gas stream is then cooled by the apparatus 10 hereof so that by the time the plasma gas stream flowing on axis A-A' has reached the junction with the carrier gas and powdered composition exiting from the powder introduction tube 76, the temperature of the plasma gas stream has dropped down to approximately 250 to 800 degrees Centigrade while travelling at 5,000 to 7,000 feet per second. Gases useful as plasma gas in this invention include H_{2} , N2, He, Ar and combinations thereof. ings made from the use of that apparatus 10 hereof when applied using the application techniques of the present invention provide coatings having applica-

-17-

10

15

20

25

30

351

tion rates, densities and bond strengths substantially greater than that of coatings applied by conventional polyamid application techniques such as fluidized bed dipping, acetyline flame spraying and electrostatic spraying.

The plasma spray method of the present invention further involves vacuuming toxic fumes in the ambient air from a periphery of the plasma gas stream adjacent the surface to be sprayed and into annular opening 70. By vacuuming the toxic fumes, the operator and the surrounding atmosphere are not subject to the toxic fumes generated during heating of certain polymer compositions which would. otherwise escape into the atmosphere. Vacuumed gases are oil filtered to remove the toxic gas The fumes are drawn into annular opening 70 and airway 72, then exit the apparatus 10 through vacuum connection 20 into a suitable vacuum hose and eventually to a filtering device to remove the toxic gas fumes and organic acid vapors. The vacuum pulls at a rate of at least 10 inches of water at 85 cubic feet per minute and preferably 150 cubic feet per minute.

The following example sets the preferred preparation of a powdered composition in accordance with the present invention, together with typical steps involved in application of the coating.

EXAMPLE

A premelt powdered coating composition such as Nylon 11 is prepared in pelletized form of a size of approximately 325 mesh (120 microns).

A supply of pure argon gas, at a flow rate of 1.42 cubic feet per minute (cfm) at 50 psi is passed through an electric arc of the plasma

-18-

1

5

100

15

20

25

generator 12 hereof having a power level of 18 kilowatts. The arc substantially heats the gas and causes some of the gas to be converted to the plasma This heated stream is then cooled as it moves away from the arc by passing through water cooled anode 40, fluid cooled nozzle 58, and a coaxial flow of air surrounding the plasma gas stream as the mach 1 plasma stream draws air through coaxial airflow area 74. The powdered polymer composition is then injected by use of a pressurized carrier gas such as nitrogen or argon through powder introduction tube 76 as described hereinabove into the heated gas stream at a location about 8.5 inches downstream from the arc and about 6 inches downstream from the rear wall of the nozzle, and at an angle of about 18 degrees to that of the general flow of the plasma gas stream along flow axis A-A'. The polymer composition and the plasma gas stream then combine to properly melt the composition and impart a substantial velocity onto the melted com-The gas and composition are then passed further downstream together in a substantially uniform direction so as to minimize overspray and then are sprayed directly onto a target surface such as an aluminum boat hull so as to form a film coating of the composition thereof. coating is then allowed to cool and bond with the surface.

•	7		
	3	Ļ,	

10

15

20

Claims:

- 1. An apparatus for applying plasma flame sprayed polymers comprising:
 - a. A fluid-cooled plasma flame generator
 - b. Mounting means attached to the plasma flame generator
 - c. A barrel mounted to the plasma flame generator by said mounting means, said barrel including:
 - i. A fluid cooled nozzle defining a bore for the passage of a plasma gas stream therewithin, said nozzle being located within said barrel
 - ii. Structure defining an open, coaxial airflow area located radially outward from the nozzle and within said barrel, said airflow area permitting the flow of air through the barrel in a direction substantially co-axial with the plasma gas stream; and
 - iii. Means for introducing a polymer into the plasma gas stream downstream from said nozzle.

25

2. An apparatus for applying plasma flame sprayed polymers as set forth in Claim 1, wherein means are provided for the circulation of the fluid coolant between the plasma flame generator and the nozzle.

5

- 3. An apparatus for applying plasma flame sprayed polymers as set forth in Claim 1, wherein the bore of the nozzle is tapered, with the diameter of the bore expanding in the direction of flow of the plasma gas stream.
- 4. An apparatus for applying plasma flame sprayed polymers as set forth in Claim 1, wherein the barrel is provided with an inner wall and an outer wall, said walls being spaced apart and defining a first space therebetween, and there being a second space between the inner wall and the nozzle defining said open co-axial flow area.
- 5. An apparatus for applying plasma flame sprayed polymers as set forth in Claim 4, wherein the exterior of the nozzle is tapered toward the downstream end thereof, with the diameter of the exterior of the nozzle decreasing in the direction of flow of the plasma gas stream.
 - 6. An apparatus as set forth in Claim 5, wherein the inner wall is constructed of upstream and downstream frustoconical members, said members being joined at a waist to present an hourglass shaped inner wall.
- 7. An apparatus as set forth in Claim 6, wherein said plasma gas stream flows along one axis, the waist of the two frustoconical members defining a plane, said plane being substantially normal to the flow axis of the plasma gas stream.

-21-

1

8. An apparatus as set forth in Claim 7, wherein the plane extends across the downstream end of the nozzle.

5

9. An apparatus as set forth in Claim 6, wherein the exterior wall of the barrel is of substantially the same diameter as and is joined together with the posterior margin of the upstream frustoconical member to form a fluid-tight seal therebetween, the anterior margin of the downstream frustoconical member and the outer wall defining an annular opening therebetween, said outer wall further including means for connecting a vacuum source thereto.

15

20

- 10. An apparatus for applying plasma flame sprayed polymers as set forth in Claim 1 including a plurality of said polymer introduction means, each of said means being oriented so that the axis of said polymer introduction means intersects a flow axis of the plasma gas stream at a point downstream from said nozzle.
- 11. An apparatus for applying plasma flame sprayed polymers as set forth in Claim 1, wherein said apparatus is provided with means for enabling the simultaneous plasma flame spraying of polymers and powdered ceramics or powdered metals.
- 12. An apparatus for applying plasma flame sprayed polymers as set forth in Claim 1, wherein the polymer introduction means is located exterior to the nozzle.

1

10

15

- 13. A method of applying a polymer composition coating to a target surface comprising the steps of:
- 5 providing an electric arc;

directing a high velocity gas stream through said arc thereby heating said gas stream and converting a portion thereof to the plasma state;

discharging the gas stream from a nozzle;
introducing a polymer composition into said gas
stream at a location downstream from the
nozzle to melt said polymer composition
without overheating said polymer composition; and

applying said melted polymer composition to a surface.

- 14. The method of Claim 13 wherein the gas is selected from a group consisting of Ar, $\rm N_2$, 20 $\rm H_2$ and He.
 - 15. The method of Claim 13 wherein the flow of said gas and said polymer composition are directed in a substantially uniform direction following injection of said composition into said gas stream.
 - 16. The method of Claim 13 wherein the heated gas stream is exposed to the atmosphere prior to introduction of said polymer composition.
 - 17. The method of Claim 16 wherein the surrounding atmosphere is drawn past the nozzle to flow co-axially with said gas stream.

30

1

5

18. The method of Claim 13, further comprising vacuuming the ambient air from a periphery of the plasma gas stream adjacent the surface to be sprayed.


19. The method of Claim 13 wherein said arc has a power level of 20 to 40 kilowatts.


- 20. The method of Claim 13 wherein said gas stream is heated to a temperature of about 12,000° to 30,000°C.
- 21. The method of Claim 20, wherein said melted polymer composition reaches a maximum temperature of about 250° to 800°C.


20

25

30







INTERNATIONAL SEARCH REPORT

International Application No. PCT/US89/02053

			international Application No. 1 C 1	70007702033				
I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) 6								
According to International Patent Classification (IPC) or to both National Classification and IPC								
IP.	C. (4):	B23K 9/00, B05D	1/00					
U.	S. CL.	: 219/121.47, 76.16,	, 121.5, 121.49,427/	34				
II. FIELDS SEARCHED								
: Minimum Documentation Searched ⁷								
Classificati	on System		Classification Symbols					
į								
U.:	S.		121.5, 121.49, 121.	51, 75				
•		427/34						
		Documentation Searched other	than Minimum Documentation					
			s are Included in the Fields Searched 8					
III. DOCE		ONSIDERED TO BE RELEVANT 9	4					
Çategory *	Citat	on of Document, 11 with indication, where app	propriate, of the relevant passages 12	Relevant to Claim No. 13				
Y	US,	A, 4,370,538 (BROWNI	NG) 25 January 1983	1-12				
	See	entire document.	-					
:								
Х	US.	A, 4,694,990 (KARLSS	ON et al) 22	13-21				
		tember 1987, See entir						
	309	,						
Y	TT C	A, 4,625,094 (MARHIE	et al) 25 November	1-12				
1		6, See entire documen		1 12				
:	190	o, see entire documen	•					
	*** 6	. 2 501 750 (474 ND)	6 Tulu 1071	1 10				
A		A, 3,591,759 (STAND)	9 Jara 1971	1-12				
	See	entire document.						
A		A, 3,740,522 (MUEHLB	ERGER) 19 June 1973	1 – 12				
	See	entire document.						
ъ л	πc	A, 4,818,837 (PFEND	FR) 4 April 1989	1-21				
P,A	500	entire document.	ER, 4 APITI 1909	1 41				
	366	entire document.						
* Specia	l categories	of cited documents: 10	"T" later document published after the	international filing date				
"A" doc	ument defin	ing the general state of the art which is not	or priority date and not in conflic cited to understand the principle	t with the application but or theory underlying the				
		e of particular relevance It but published on or after the international	invention					
	g date	t out published on or diter the international	"X" document of particular relevance cannot be considered novel or or the control of the control	e; the claimed invention cannot be considered to				
"L" doc	ument whic	involve an inventive step "Y" document of particular relevance	y the elaimed invention					
citat	tion or othe	o establish the publication date of another special reason (as specified)	cannot be considered to involve a	n inventive step when the				
	ument referi er means	ing to an oral disclosure, use, exhibition or	document is combined with one of ments, such combination being of	r more other such docu- prious to a person skilled				
"P" doc	ument publi	shed prior to the international filing date but	in the art.					
later than the priority date claimed "&" document member of the same patent family								
IV. CERTIFICATION								
Date of the	Actual Co	npletion of the International Search	Date of Mailing of this International Sea	rch Report				
			01SEP 1989					
05	Augus	1989						
International Searching Authority			Signature of Authorized Officer					
ISA/US			M. H. PASCHALL					