



US 20110049055A1

(19) **United States**(12) **Patent Application Publication**
Wang et al.(10) **Pub. No.: US 2011/0049055 A1**(43) **Pub. Date: Mar. 3, 2011**(54) **REVERSE OSMOSIS COMPOSITE
MEMBRANES FOR BORON REMOVAL****Publication Classification**(75) Inventors: **Hua Wang**, Clifton Park, NY (US);
David Allen Olson, Minneapolis,
MN (US); **Jiang Ji**, North Billerica,
MA (US); **Michael Todd Luttrell**,
Clifton Park, NY (US); **Gary**
William Yeager, Rexford, NY
(US); **Joseph Anthony Suriano**,
Clifton Park, NY (US); **Lawrence**
Charles Costa, Mansfield, MA
(US)(73) Assignee: **GENERAL ELECTRIC
COMPANY**, Schenectady, NY
(US)(21) Appl. No.: **12/550,990**(22) Filed: **Aug. 31, 2009**(51) **Int. Cl.****C02F 1/44** (2006.01)**B01D 65/00** (2006.01)**B01D 71/06** (2006.01)**B05D 3/10** (2006.01)(52) **U.S. Cl. 210/654; 210/500.21; 210/500.27;**
528/332; 427/337

(57)

ABSTRACT

Improved methods for reducing boron concentration in sea-water or brackish water, while simultaneously maintaining or improving the salt rejection of membrane and flow performance of polyamide reverse osmosis (RO) membranes include contacting the water with a composite membrane comprising moieties derived from an aromatic sulfonyl halide, a heteroaromatic sulfonyl halide, a sulfinyl halide; a sulfenyl halide; a sulfuryl halide; a phosphoryl halide; a phosphonyl halide; a phosphinyl halide; a thiophosphoryl halide; a thiophosphonyl halide, an isocyanate, a urea, a cyanate, an aromatic carbonyl halide, an epoxide or a mixture thereof.

REVERSE OSMOSIS COMPOSITE MEMBRANES FOR BORON REMOVAL

BACKGROUND

[0001] Reverse osmosis (RO) membrane desalination uses membrane technology to transform seawater and brackish water into fresh water for drinking, irrigation, and industrial applications. Such processes require substantially less energy than do thermal desalination processes such as multi-stage flash, and so, reverse osmosis membrane technology is increasingly used to produce fresh water from seawater or brackish water.

[0002] Reverse osmosis is the process of forcing a solvent from a region of high solute concentration through a membrane to a region of low solute concentration by applying a pressure in excess of the osmotic pressure. This is the reverse of an osmosis process, which is the natural movement of solvent from an area of low solute concentration, through a membrane, to an area of high solute concentration when no external pressure is applied. The membrane here is semipermeable, meaning it allows the passage of solvent but not of solute. The membranes used for reverse osmosis have a dense barrier layer in the polymer matrix where most separation occurs. The membrane is designed to allow only water to pass through this dense layer while preventing the passage of solutes such as salts. The reverse osmosis process requires that a high pressure be exerted on the high concentration side of the membrane, usually 2-17 bar (30-250 psi) for fresh and brackish water, and 40-70 bar (600-1000 psi) for seawater, which has around 24 bar (350 psi) natural osmotic pressure which must be overcome.

[0003] Over the years, better membrane technologies and energy recovery devices have made reverse osmosis more affordable and efficient. However, the RO process has not been very effective in the removal of neutral contaminants such as boron despite its capacity to efficiently remove up to 99.7% of ionic species.

[0004] Seawater in general has a boron concentration of 4 to 5 mg/L. Depending on location and seasonal effects, the boron concentration can reach up to 7 mg/L, e.g. in the Arabian Gulf. Toxicological effects of human exposure to excess boron, mostly reproductive and developmental, are well documented. Excess boron also harmful to plant growth; deleterious effects include massive leaf damages, premature ripening, and reduced crop yields.

[0005] In aqueous environments, at acidic and neutral pH, boron is mainly present as undissociated boric acid. Reverse osmosis membrane is better at removing charged species over uncharged species due to the larger apparent size of hydrated charged species. Uncharged boric acid has a molecular diameter of 2.75 Å and a molecular volume of 71.5 Å³, which is similar to urea (75.3 Å³) and other small nonelectrolytes. Thus, boric acid is significantly smaller than hydrated sodium (3.58 Å) and chloride (3.32 Å) ions, making the removal of boron significantly more difficult than sodium chloride salt.

[0006] Thin films of cross-linked aromatic polyamide RO membranes are typically composed of two types of pores, network pores having radii of about 1-3 Å, and aggregate pores, having radii of about 3.5-4.5 Å. The radius of uncharged boric acid (2.75 Å) is close to that of the network pores and substantially less than that of the aggregated pores. As a result, it is difficult for a RO membrane desalination process to achieve an average boron rejection over 90%, which is typically required to produce a permeate that meets

the requirements of the many applications. This has led to the adoption of procedures such as repeating the RO membrane treatment process twice, or mixing treated water with low boron concentration water from other sources. Although these additional treatment steps lead to reduced boron concentration, they increase costs substantially.

[0007] In recent years, specialized seawater reverse osmosis (SWRO) membranes for boron removal have been introduced. However, even with these membranes, it has been difficult for a single-pass full-scale RO process to reduce the boron level to below 0.5 mg/L, while achieving required system recovery, unless an additional treatment step is employed. For example, the SWRO plant in Ashkelon, Israel, uses a 4-stage cascade RO design to meet a boron specification of <0.3 mg/L. U.S. Pat. No. 7,279,097, assigned to Toray Industries Inc., discloses a method of treating reverse osmosis membranes with aliphatic amines and aliphatic acid halide for improving boron rejection of the membranes. Aliphatic acid halides disclosed include "methanesulfonyl chloride, acetyl chloride, propionyl chloride, butyryl chloride, oxalyl chloride, malonic acid dichloride, succinic acid dichloride, maleic acid dichloride, fumaric acid dichloride, chlorosulfonylacetyl chloride, and N,N-dimethylaminocarbonyl chloride". However, there remains a need for even better methods for making new seawater and brackish membrane products with high boron rejection and salt rejection performance.

BRIEF DESCRIPTION

[0008] The present invention relates to improved methods for reducing boron concentration and improving flow performance of polyamide reverse osmosis (RO) membranes, while simultaneously maintaining or improving the salt rejection of membrane

[0009] Briefly, in one aspect, the present invention relates to reverse osmosis methods for reducing boron concentration in water containing boron, the method comprising contacting the water with a composite membrane comprising moieties derived from an aromatic sulfonyl halide, a heteroaromatic sulfonyl halide, a sulfinyl halide; a sulfenyl halide; a sulfuryl halide; a phosphoryl halide; a phosphonyl halide; a phosphinyl halide; a thiophosphoryl halide; a thiophosphonyl halide, an isocyanate, a urea, a cyanate, an aromatic carbonyl halide, an epoxide or a mixture thereof.

[0010] In another aspect, the present invention relates to reverse osmosis methods for preparing a composite membrane by contacting under interfacial polymerization conditions an organic solution comprising a polyacid halide with an aqueous solution that includes a polyamine to form a polyamide membrane. The contacting step is carried out on a surface of a porous base membrane, and the organic solution further includes an aryl sulfonyl halide. The composite membranes so prepared may be used for reducing boron concentration, and typically display good boron rejection performance.

DETAILED DESCRIPTION

[0011] The present invention relates to reverse osmosis methods for reducing boron concentration in seawater or brackish water containing at least 5 ppm boron, in a single step, by at least 90%, preferably by at least 95% in a single step, and more preferably by at least 96% in a single step. pH of the water is typically less than or equal to about 8.5. Reverse osmosis processes are typically operated at pressures

ranging from 2-17 bar (30-250 psi) for fresh and brackish water, and 40-70 bar (600-1000 psi) for seawater.

[0012] In the reverse osmosis methods of the present invention, the seawater or brackish water is treated, by contacting it with a composite membrane comprising moieties derived from an aromatic sulfonyl halide, a heteroaromatic sulfonyl halide, a sulfinyl halide; a sulfenyl halide; a sulfuryl halide; a phosphoryl halide; a phosphonyl halide; a phosphinyl halide; a thiophosphoryl halide; a thiophosphonyl halide, an isocyanate, a urea, a cyanate, an aromatic carbonyl halide, an epoxide or a mixture thereof. In some embodiments, the moieties are derived from an aromatic sulfonyl halide, particularly 4-nitrobenzenesulfonyl chloride, 1,3-benzenedisulfonyl chloride, or 4-cyano benzenesulfonyl chloride. The composite membrane may additionally include an additional layer of cross-linked hydrophilic polymer such as polyvinyl alcohol (PVA) coated on the separating layer.

[0013] The term "composite membrane" refers to thin film composite (TFC) semipermeable membranes composed of a separating functional layer formed on a porous substrate film. The separating functional layer is thin in order to maximize membrane flux performance, and is formed on a porous support or base membrane to provide mechanical strength. Examples of TFC membranes that may be used in the methods of the present invention include, but are not limited to, reverse osmosis membranes composed of a polyamide separating functional layer formed on a porous polysulfone support, nanofiltration membranes, and other thin film composite membrane.

[0014] The composite membranes for use in the reverse osmosis methods of the present invention may be prepared by post-treatment of a TFC membrane, particularly a polyamide TFC membrane with an aromatic sulfonyl halide, a heteroaromatic sulfonyl halide, a sulfinyl halide; a sulfenyl halide; a sulfuryl halide; a phosphoryl halide; a phosphonyl halide; a phosphinyl halide; a thiophosphoryl halide; a thiophosphonyl halide, an isocyanate, a urea, a cyanate, an aromatic carbonyl halide, and/or an epoxide.

[0015] Alternately, the composite membranes may be prepared by in-situ reaction of the same compounds during fabrication of the membrane by interfacial polymerization. Accordingly, in another aspect, the present invention relates to reverse osmosis methods for preparing a composite membrane that may be used in methods for reducing boron concentration. An organic solution including a polyacid halide is contacted under interfacial polymerization conditions, on a surface of a porous base membrane, with an aqueous solution including a polyamine to form a polyamide membrane. The organic solution further includes an aryl sulfonyl halide, heteroaromatic sulfonyl halide, a sulfinyl halide; a sulfenyl halide; a sulfuryl halide; a phosphoryl halide; a phosphonyl halide; a phosphinyl halide; a thiophosphoryl halide; a thiophosphonyl halide, an isocyanate, a urea, a cyanate, an aromatic carbonyl halide, an epoxide, or a mixture thereof, preferably an aryl sulfonyl halide, more preferably 1,3-benzenedisulfonyl chloride or 1,3,6-naphthalenetrisulfonyl chloride. The aryl sulfonyl halide may be present in an amount ranging from about 0.01% to about 2% by weight.

[0016] The organic solution may additionally include a C₃-C₈ cyclic carbonyl compound. The C₃-C₈ cyclic carbonyl compound may be a cyclic ketone having from three to eight carbon atoms for example cyclooctanone, cycloheptanone, 2-methylcyclohexanone, cyclohexanone, cyclohexene-3-one, cyclopentanone, cyclobutanone, 3-ketotetrahydrofuran,

3-ketotetrahydrothiophene, and 3-ketoxetane; a cyclic ester having from three to eight carbon atoms, for example 2-methyl caprolactone, caprolactone, valerolactone, butyrolactone, diketene, and propiolactone; or a C₃-C₈ cyclic carbonate, for example ethylene carbonate, propylene carbonate, 1,2-butanediol carbonate, 1,2-pentanediol carbonate, 1,2-hexanediol carbonate, and 1,2-heptanediol carbonate. In one embodiment, the cyclic carbonyl compound is cyclohexanone.

[0017] The C₃-C₈ cyclic carbonyl compound may be present in an amount corresponding to from about 0.1 to about 3.5 weight percent of the total weight of the organic solution. In another embodiment, the C₃-C₈ cyclic carbonyl compound is present in an amount corresponding to from about 0.5 to about 2.5 weight percent of the total weight of the organic solution. In yet another embodiment, the organic solution comprises the C₃-C₈ cyclic carbonyl compound in an amount corresponding to from about 1 to about 1.5 weight percent of the total weight of the organic solution.

[0018] Suitable porous base membranes include those composed of polysulfone, polyethersulfone, polyester, polyphenyleneoxide, polyphenylenesulfide, polyvinyl chloride, polyacrylonitrile, polyvinylidene fluoride, polytetrafluoroethylene, polycarbonate, polyimide, polyetherimide, polyetherketone, and polyetheretherketone. A wide variety of suitable porous base membranes are either available commercially or may be prepared using techniques known to those of ordinary skill in the art. In one embodiment, a porous base membrane which is a polysulfone film is used. In another embodiment, the porous base membrane is a porous polyethersulfone film.

[0019] Interfacial polymerization includes contacting an aqueous solution of one or more polyamine monomers onto a porous support membrane; followed by coating an organic solution, generally in an aliphatic solvent, containing one or more polyacid halide monomers. At the interface of the two solution layers, which lies near the surface of the porous support, a thin film polymer is formed from condensation of the electrophilic and nucleophilic monomers and is adherent to the porous support. The rate of thin film formation may be accelerated by heating or addition of catalysts. The polyacid halide monomer on contact with the polyamine monomer reacts on the surface of the porous base membrane to afford a polyamide disposed on the surface of the porous support membrane. Suitable polyacid chlorides include trimesoyl chloride, terephthaloyl chloride, isophthaloyl chloride, succinic acid diacid chloride, glutaric acid diacid chloride, adipic acid diacid chloride, trans-cyclohexane-1,4-dicarboxylic acid diacid chloride, cis-cyclohexane-1,4-dicarboxylic acid diacid chloride, the triacid chloride of Kemp's triacid, and mixtures comprising two or more of these polyacid chlorides. Suitable polyamines include para-phenylene diamine (ppd), meta-phenylene diamine (mpd), 4,4'-diaminobiphenyl, ethylene diamine, 1,3-propane diamine, 1,6-hexanediamine, 1,10-decanediamine, 4,4'-diaminodiphenyl sulfone, 1,3,5-triaminobenzene, piperazine, cis-1,3,5-cyclohexanetriamine, and mixtures comprising two or more of these polyamines. Suitable organic solvents include hydrocarbon solvents, alcohol solvents, ketone solvents, ester solvents, ether solvents, amide solvents, and mixtures thereof. The interfacial polymerization reaction may be carried out at a temperature ranging from about 5° C. to about 60° C., preferably from about 10° C. to about 40° C.

[0020] In order to improve permeability and/or salt rejection, the polyamide membrane may be post-treated with an oxidizing solution, such as a sodium hypochlorite solution. The concentration of sodium hypochlorite in the solution may range from about 10 ppm to about 4000 ppm.

EXAMPLES

Examples 1-11

Post-Treatment with 4-Nitrobenzenesulfonyl Chloride

[0021] Polyamide RO membrane were cut into 6"×12" size and then clamped between two aluminum hand-frames and sealed with 6 clamps around the edges. The membrane was rinsed with water for about 10 seconds, then treated with a reagent solution containing 4-nitrobenzenesulfonyl (nosyl) chloride in methanol solution as listed in Table 1 for the specified time (between 30 and 90 seconds) at ambient temperature, and let stand for 3 minutes. The reagent mixture was poured off the membrane from the same corner that it was administered. The membrane was then dried in a ventilated oven at 55° C. for 10 minutes, cooled to ambient temperature, and stored in a refrigerator until testing on a cross-flow testing bench.

Comparative Experiments 1-3

[0022] Control RO membranes were prepared as described above, except no post-treatment was performed.

Protocol for Testing Coated RO Membranes for NaCl Rejection and Permeability

[0023] Test coupons were cut and treated with a 40000 ppm NaCl solution (in DI water) at 800 psi at 20° C. for 1 hour. After this time, the permeate was collected, weighed and its conductivity measured to obtain the salt rejection and membrane permeability. The membrane was then treated with a sodium hypochlorite solution (70 ppm free chlorine in DI water) at 225 psi at 20° C. for 30 minutes. After this time, the membrane was rinsed with DI water for 0.5-1.0 h and again treated with a 40000 ppm NaCl solution at 800 psi at 20° C. for 1 hour. The permeate was again collected, weighed and its conductivity measured to obtain the salt rejection and membrane permeability. The post-chlorination samples were also analyzed by ICP (Inductively coupled plasma mass spectrometry) or azomethine/UV method for boron rejection characterization, using the method described in the Hach DR/2400 Spectrophotometer procedures manual.

[0024] Results are shown in Table 1. Without any nosyl chloride post-treatment, the control RO membrane had a boron rejection of 86.6% to 88.6% and salt passage of to 99.4%. However, after the nosyl treatment, boron rejection increased to 91-97% and salt rejection increased to 99.6-99.9%.

TABLE 1

Membrane permeability, salt passage, and boron rejection performance (boron results characterized by ICP method)							
Ex. No.	Nosyl	TEA	Re- action time (sec)	PVA wt %	Perme- ability (A-value)	% Salt Rej.	Boron rejection %
1	1	0.1	60	1	1.1	99.6	92.8
2	1	0.3	30	1	1.1	99.8	95.6
3	1	0.3	90	1	1.2	99.7	92.3
4	1	0.3	90	3	0.9	99.9	94.4

TABLE 1-continued

Membrane permeability, salt passage, and boron rejection performance (boron results characterized by ICP method)							
Ex. No.	Post- treatment Composition Solution (wt %)	TEA	Re- action time (sec)	PVA wt %	Perme- ability (A-value)	% Salt Rej.	Boron rejection %
5	1	0.5	30	2	1.1	99.7	92.6
6	1	0.5	90	2	1.2	99.6	94.2
7	1	0.3	60	2	0.9	99.8	95.4
8	1	0.3	60	2	1.2	99.9	91.3
9	2	0.5	60	2	0.8	99.8	95.2
10	2	0.3	60	1	0.9	99.5	96.2
11	2	0.3	60	3	0.7	99.9	97.1
Comp Ex. 1	—	—	—	1	1.7	99.4	88.3
Comp Ex. 2	—	—	—	2	1.8	99.3	88.6
Comp Ex. 3	—	—	—	3	1.8	99.4	86.6

Examples 12-16

Post-Treatment with Other Agents

[0025] RO membranes were treated with 1,3-benzenedisulfonyl chloride (BDSC), 4-cyano benzenesulfonyl chloride (cyano BSC), and methanesulfonyl chloride. The membranes showed increased boron rejection compared to the control membranes.

Examples 17-31

In-Situ Treatment with Benzenedisulfonyl Chloride

Examples 17-22

Procedure for Membrane Fabrication Using Hand-frame Coating Apparatus

[0026] Composite membranes were also prepared using a handframe coating apparatus consisting of a matched pair of frames in which the porous base membrane could be fixed and subsequently coated with a polyamide coating comprising a C3-C8 cyclic carbonyl compound and a C1-C8 amide compound. The following procedure was used. The porous base membrane was first soaked in deionized water for at least 30 minutes. The wet porous base membrane was fixed between two 8 inch by 11 inch plastic frames and kept covered with water until further processed. Excess water was removed from the porous base membrane and one surface of the porous base membrane was treated with 80 grams of an aqueous solution comprising meta-phenylenediamine (MPD) (2% by weight) and triethylammonium camphorsulfonate (TEACSA) (6% by weight), the upper portion of the frame confining the aqueous solution to the surface of the porous base membrane. After a period of 120 seconds, the aqueous solution was removed from the surface of the porous base

membrane by tilting the assembly comprising the frame and the treated porous base membrane until only isolated drops of the aqueous solution could be observed on the surface of the treated porous base membrane. The treated surface was further treated by exposure to a gentle stream of air to remove isolated drops of the aqueous solution. The treated surface of the porous base membrane was then contacted with 150 grams of an organic solution comprising trimesoyl chloride (0.20% by weight) mesitylene (1.5% by weight), cyclohexanone (6% by weight) and benzenedisulfonyl chloride (weight % as shown in Table 2 below), in Isopar G solvent. Excess organic solution was then removed by tilting a corner of the frame and collecting the excess organic solution in a suitable collection vessel. The treated assembly was then placed in a drying oven and maintained at a temperature of 60° C. for a period of about 10 minutes after which the composite membrane was tested.

TABLE 2

Hand Frame Organic Coating Solutions	
Example No.	Organic Additive
17	6% cycl + 1.5% mesitylene + 0% BDSC
18	6% cycl + 1.5% mesitylene + 0.05% BDSC
19	6% cycl + 1.5% mesitylene + 0.10% BDSC
20	6% cycl + 1.5% mesitylene + 0.20% BDSC
21	0% cycl + 1.5% mesitylene + 0% BDSC
22	6% cycl + 1.5% mesitylene + 0.2% BDSC

Examples 23-31

Procedure for Membrane Fabrication Using Pilot Coater

[0027] The handframe procedure was duplicated using a pilot coating machine capable of coating a 12-inch wide web. A porous base membrane was fed through an aqueous coating bath composed of 2.9 wt % MPD and 6.6 wt % TEACSA in water. The porous base membrane coated on one side with the aqueous solution was passed through a rubber nip roller to remove excess fluid. The coated porous base membrane was then fed through an organic coating bath composed of a water-immiscible solvent, a polyacid halide, and the organic additives, as shown in Table 3. Following passage through the organic coating solution, the porous base membrane was passed through a dryer to remove solvent and water to provide the product composite membrane.

TABLE 3

Pilot Coater Organic Coating Solutions	
Example No.	Organic Additive
23	0% cycl + 1.5% mesitylene + 0% BDSC
24	1% cycl + 1.5% mesitylene + 0% BDSC
25	1% cycl + 1.5% mesitylene + 0.18% BDSC
26	1% cycl + 1.5% mesitylene + 0.36% BDSC
27	1% cycl + 1.5% mesitylene + 0.71% BDSC
28	1% cycl + 1.5% mesitylene + 0% BDSC
29	1% cycl + 1.5% mesitylene + 0.18% BDSC
30	1% cycl + 1.5% mesitylene + 0.36% BDSC
31	1% cycl + 1.5% mesitylene + 0.71% BDSC

The membranes were tested using the protocol described for Examples 1-11. Results are displayed in Table 4.

TABLE 4

Testing Conditions and Results for Examples 18-32								
Ex. No.	Rinse Pressure (psig)	Chlorination Pressure (psig)	Test Pressure (psig)	NaCl (ppm)	Pre-Chlorination		Post-Chlorination	
					Permeability (A-value)	Passage (%)	Permeability (A-value)	Passage (%)
17	225	225	225	2000	6.8	0.99	6.1	0.35
18	225	225	225	2000	6.4	0.63	5.8	0.25
19	225	225	223	2000	5.3	0.43	5.3	0.21
20	225	225	225	2000	2.8	0.31	43	0.21
21	225	225	300	32000	2.2	0.82	4.0	0.57
22	225	225	800	32000	2.1	0.30	3.8	0.30
23	115	115	115	500	2.1	0.30	12.3	0.87
24	115	115	115	500	24.4	2.91	25.3	1.27
25	115	115	115	500	14.6	0.91	26.2	0.85
26	115	115	115	500	3.9	0.78	27.4	1.26
27	115	115	113	500	6.7	0.81	27.8	0.94
28	115	115	115	500	14.1	0.37	14.3	0.69
29	115	115	115	500	7.3	1.15	16.5	0.86
30	115	115	115	500	6.3	0.72	19.3	0.69
31	115	115	115	500	5.6	1.42	23	0.94

A dramatic and simultaneous increase in % rejection and A-value after chlorination was seen in many cases when BDSC was present.

[0028] While only certain features of the invention have been illustrated and described herein, many modifications and changes will occur to those skilled in the art. It is, therefore, to be understood that the appended claims are intended to cover all such modifications and changes as fall within the true spirit of the invention.

1. A reverse osmosis method for reducing boron concentration in water containing boron, said reverse osmosis method comprising contacting the water with a composite membrane comprising moieties derived from an aromatic sulfonyl halide, a heteroaromatic sulfonyl halide, a sulfinyl halide; a sulfenyl halide; a sulfuryl halide; a phosphoryl halide; a phosphonyl halide; a phosphinyl halide; a thiophosphoryl halide; a thiophosphonyl halide, an isocyanate, a urea, a cyanate, an aromatic carbonyl halide, an epoxide or a mixture thereof.

2. A reverse osmosis method according to claim 1, wherein the moieties are derived from an aromatic sulfonyl halide.

3. A reverse osmosis method according to claim 1, wherein the moieties are derived from 4-nitrobenzenesulfonyl chloride.

4. A reverse osmosis method according to claim 1, wherein the moieties are derived from 1,3-benzenedisulfonyl chloride.

5. A reverse osmosis method according to claim 1, wherein the moieties are derived from 4-cyano benzenesulfonyl chloride.

6. A reverse osmosis method according to claim 1, wherein the composite membrane additionally comprises a cross-linked hydrophilic polymer.

7. A reverse osmosis method according to claim 6, wherein the cross-linked hydrophilic polymer is polyvinyl alcohol.

8. A method for preparing a composite membrane comprising contacting under interfacial polymerization conditions an organic solution comprising a polyacid halide with an aqueous solution comprising a polyamine to form a polyamide membrane, said contacting being carried out on a surface of a porous base membrane, said organic solution further comprising an aryl sulfonyl halide.

9. A method according to claim 8, wherein the organic solution additionally comprises a C₃-C₈ cyclic carbonyl compound.

10. A method according to claim 9, wherein the C₃-C₈ cyclic carbonyl compound is cyclohexanone.

11. A method according to claim 8, additionally comprising contacting the polyamide membrane with an oxidizing solution, such as sodium hypochlorite.

12. A method according to claim 11, wherein the concentration of free chlorine in the sodium hypochlorite solution ranges from about 10 ppm to about 4000 ppm.

13. A method according to claim 8, wherein the aryl sulfonyl halide is present in an amount ranging from about 0.01% to about 2% by weight.

14. A method according to claim 8, wherein the aryl sulfonyl halide is 1,3-benzenedisulfonyl chloride or 1,3,6-naphthalenetrisulfonyl chloride.

15. A composite membrane prepared by the method of claim 8.

16. A reverse osmosis method for reducing boron concentration in water containing boron, said reverse osmosis method comprising contacting the water with a composite membrane comprising moieties derived from an aromatic sulfonyl halide, a heteroaromatic sulfonyl halide, a sulfinyl halide; a sulfenyl halide; a sulfuryl halide; a phosphoryl halide; a phosphonyl halide; a phosphinyl halide; a thiophosphoryl halide; a thiophosphonyl halide, an isocyanate, a urea, a cyanate, an aromatic carbonyl halide, an epoxide or a mixture thereof,

wherein the composite membrane is prepared by contacting under interfacial polymerization conditions an organic solution comprising a polyacid halide with an aqueous solution comprising a polyamine to form a polyamide membrane and contacting the polyamide membrane with an oxidizing solution;

said contacting being carried out on a surface of a porous base membrane,

said organic solution further comprising a C₃-C₈ cyclic carbonyl compound and an aryl sulfonyl halide.

17. A reverse osmosis method according to claim 16, wherein the oxidizing solution is a sodium hypochlorite solution.

* * * * *