



(51) International Patent Classification:

B65D 75/58 (2006.01) *B65D 77/20* (2006.01)
B29C 59/00 (2006.01)

(21) International Application Number:

PCT/US2018/046620

(22) International Filing Date:

14 August 2018 (14.08.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

15/804,793 06 November 2017 (06.11.2017) US


(71) Applicant: **SONOCO DEVELOPMENT, INC.** [US/US];
125 W. Home Avenue, Hartsville, South Carolina 29550
(US).

(72) Inventor: **HUFFER, Scott William**; 1216 Oakhaven Circle, Hartsville, South Carolina 29850 (US).

(74) Agent: **HAYDEN, Nichole T.** et al.; Nelson Mullins Riley & Scarborough LLP, 301 S. College Street, 23rd Floor, Charlotte, North Carolina 28202 (US).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(54) Title: FLEXIBLE PACKAGING STRUCTURE WITH BUILT-IN TAMPER-EVIDENCE FEATURES AND METHOD FOR MAKING SAME



(57) Abstract: A flexible packaging laminate has built-in opening/reclose and tamper-evidence features by forming the laminate from an outer structure joined in face-to-face relation to an inner structure. Score lines are formed in both structures to enable an opening to be formed through the laminate by lifting a flap or the like out of the plane of the laminate. The score line through the outer structure defines a larger opening than the score line through the inner structure, such that a marginal region of the outer structure extends beyond the edge of the opening portion of the inner structure. A pressure-sensitive adhesive is used to re-adhere the marginal region to an underlying surface of the inner structure adjacent the opening through the laminate. The outer score line includes at least one tab positioned within a heat seal region of the laminate.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— *with international search report (Art. 21(3))*

CROSS-REFERENCE TO RELATED APPLICATIONS

5

10

15

20

25

35

and reclose feature, as described in the aforementioned '872 application. Packages made using the flexible packaging structure of the '872 application avoid the disadvantages associated with the use of labels, and have additional advantages.

Consumers feel more confident about purchasing such types of packages if the packages have a tamper-evidence capability so that the consumer can readily see whether the package has already been opened. Presently, various flexible packages have features allowing a user to determine if a package has already been opened or tampered with. Unfortunately, the tamper-evidence features of such packages may be difficult to discern upon a visual inspection of the package. Further, such tamper-evidence features often require removing a portion of the packaging, and thus, creating unwanted trash and potential choking hazards. The present disclosure is directed toward providing improved tamper-evidence capabilities.

BRIEF SUMMARY OF THE DISCLOSURE

The present disclosure addresses the above needs and achieves other advantages, by providing a flexible packaging structure and method for making same, in which the structure has opening/reclose and tamper-evidence features built into the structure. In accordance with one embodiment of the invention, the score line or die cut through the film for creating the flap includes one or more tear portions in which the flap includes a tab with an end attached to the structure, and/or an interrupted area of the flap that is not cut. When the flap is peeled back, a portion of the tab or the film in the interrupted area is torn. The tab can include an indentation and/or a prong, while the interrupted area can be formed by a transverse cut that is U-shaped or V-shaped to ensure that the tear will connect with the die cut. The presence of a tear or slit in the tab or the interrupted area indicates that the package has already been opened or tampered with.

In some embodiments, the package itself is formed to have a built-in opening and reclose feature by forming the packaging structure as a two-part structure, having an outer structure joined in face-to-face relation with an inner structure. Each of the outer and inner structures can comprise one or more layers of flexible packaging material such as polymer film, paper, metal foil, and the like. An outer line of weakness is formed in the outer structure to define an outer opening portion that can be lifted out of the plane of the outer structure. Similarly, an inner line of weakness is formed in the inner structure to define an inner opening portion that can be lifted out of the plane of the inner structure. The outer and inner opening portions are attached to each other such that the outer and inner opening portions can be lifted out of the plane as a unit, thereby creating an opening through the packaging structure defined by the inner line of weakness. The

outer line of weakness includes a tear portion whose torn or untorn condition is readily apparent from a visual inspection of the outer structure.

The outer opening portion is larger in area than the inner opening portion and has a marginal region that extends beyond the peripheral edge of the inner opening portion.

5 When the outer and inner opening portions are lifted out of the plane to create the opening, an underlying portion of the inner structure in registration with the marginal region of the outer opening portion is exposed adjacent the opening. A pressure-sensitive adhesive is applied to either the marginal region of the outer opening portion or the underlying portion of the inner structure. Therefore, after initial lifting of the outer and
10 inner opening portions, the opening through the structure can be reclosed by adhering the marginal region of the outer opening portion to the underlying portion of the inner structure via the pressure-sensitive adhesive.

In accordance with one embodiment, the pressure-sensitive adhesive is pattern-applied onto one surface of the outer structure, the pressure-sensitive adhesive forming a
15 strip having an outer perimeter and an inner perimeter, and a permanent laminating adhesive is pattern-applied onto the one surface of the outer structure such that the permanent adhesive does not cover the strip of pressure-sensitive adhesive. Next, the outer structure is adhesively joined to the inner structure via the permanent adhesive so as to form a laminate. The outer structure and inner structure in preferred embodiments
20 are coextensive with each other, and advantageously are each continuous webs drawn from respective supply rolls and laminated together to form a laminate that is a continuous web.

The laminate is then advanced to a scoring station at which an outer line of weakness (also referred to herein as a "score line") is formed through the thickness of the
25 outer structure, and an inner score line is formed through the thickness of the inner structure. Advantageously, each of the score lines is registered with respect to the strip of pressure-sensitive adhesive such that neither score line is located where there is permanent laminating adhesive between the outer and inner structures. The outer score line delineates the outer opening portion of the outer structure that is separable from the
30 outer structure along the outer score line, and the inner score line delineates the inner opening portion of the inner structure that is affixed to the outer opening portion by the permanent adhesive and is separable from the inner structure along the inner score line. The outer score line includes the interrupted area.

The score lines can be formed by laser scoring or by mechanical scoring or
35 cutting such as by die cutting or kiss cutting or the like. The adhesive(s) can be applied to the outer structure as noted, but alternatively can be applied to the inner structure. The

adhesive(s) can be applied using any suitable equipment and technique, such as by a gravure roll or the like.

The pressure-sensitive adhesive can be applied such that there is a region that is free of the adhesive, such as a tab, to form a grasping portion of the opening portion that can be readily grasped and pulled back to initiate opening.

The outer line of weakness or score line preferably penetrates through the thickness of the outer structure but not through the inner structure. Similarly, the inner score line preferably penetrates through the thickness of the inner structure but not through the outer structure.

The inner structure of the laminate advantageously includes a sealant layer forming the inner surface of the laminate. The sealant layer can comprise a heat seal material such as polyethylene, polypropylene, ionomer resin such as SURLYN®, or the like, or a cold seal material. The heat seal or cold seal layer can comprise either a film or a coating. The inner structure advantageously also includes a barrier layer providing a barrier against the passage of moisture and/or oxygen. In some applications such as the packaging of moisture-sensitive products (e.g., cookies or similar products that tend to be degraded when exposed to the environment), it is important to provide a moisture barrier. The barrier layer can comprise any of various polymer-based barrier materials including barrier polymer films such as ethylene vinyl alcohol copolymer (EVOH), polyamide, and the like; metallized polyolefin films such as polyethylene, polypropylene, oriented polypropylene, and the like; AlOx-coated polymer films; SiOx-coated polymer films; metal foil such as aluminum foil; and others. Although the term "barrier layer" is used in connection with metallized films to refer to the entire metallized film, it will be recognized that it is the layer of metal that provides the barrier function. Likewise, it is the AlOx or SiOx coating that provides the barrier function in the ceramic-coated films, but the entire film nevertheless is referred to herein as a "barrier layer".

The outer structure advantageously includes a layer of polyester such as polyethylene terephthalate, which has a desirable crisp feel and is readily printed. The polyester layer can be printed with inks to provide graphics and indicia. In preferred embodiments, the polyester layer is transparent and is reverse-printed on the surface that faces the inner structure.

The process in accordance with the present disclosure comprises an in-line process wherein the opening and reclose features and the tamper-evidence feature are formed in the packaging laminate during the production of the laminate. Accordingly, it is not necessary to ship the laminate to a converter for application of labels or the like. Thus, the waste and the various material and shipping expenses associated with the use of separate labels are avoided.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

Having thus described the disclosure in general terms, reference will now be made to the accompanying drawings, which are not necessarily drawn to scale, and
5 wherein:

FIG. 1 is a diagrammatic depiction of a first phase of a manufacturing method for making a flexible packaging structure in accordance with one embodiment of the invention;

FIG. 1a is a view of the first structure along line 1a-1a in FIG. 1;

10 FIG. 1b is a view of the first structure along line 1b-1b in FIG. 1;

FIG. 2 is a diagrammatic depiction of a second phase of the method in accordance with one embodiment of the invention;

FIG. 3 is a diagrammatic depiction of a second phase of the method in accordance with another embodiment of the invention;

15 FIG. 4 is a perspective view of a package that can be formed from a flexible packaging structure made in accordance with embodiments of the invention;

FIG. 5 shows the package of FIG. 4 after being opened;

FIG. 6 is a cross-sectional view along line 6-6 in FIG. 4;

FIG. 7 is a cross-sectional view along line 7-7 in FIG. 5;

20 FIG. 8 is a perspective view of stand-up pouch that can be formed from a flexible packaging structure with a tamper-evidence feature made in accordance with embodiments of the invention;

FIG. 9 is a perspective view of another stand-up pouch that can be formed from a flexible packaging structure with a tamper-evidence feature made in accordance with
25 embodiments of the invention;

FIG. 10 is a perspective view of yet another stand-up pouch that can be formed from a flexible packaging structure with a tamper-evidence feature made in accordance with embodiments of the invention;

30 FIG. 11 is a perspective view of an additional stand-up pouch that can be formed from a flexible packaging structure with a tamper-evidence feature made in accordance with embodiments of the invention;

FIG. 12 shows a perspective view of a package with a container body and having a temper-evidence feature in accordance with the invention;

35 FIG. 13 shows a perspective view of a package that can be formed from a flexible packaging structure made in accordance with embodiments of the invention;

FIG. 14 shows the package of FIG. 13 after being opened;

FIG. 15 is a perspective view of stand-up pouch that can be formed from a flexible packaging structure made in accordance with embodiments of the invention;

FIGS. 16A-B are top views of packaging structures that can be formed into packages in accordance with embodiments of the invention; and

5 FIGS 17A-D are cross-sectional views of a packaging structure in accordance with embodiments of the invention.

DETAILED DESCRIPTION OF THE DRAWINGS

10 The present inventions now will be described more fully hereinafter with reference to the accompanying drawings, in which some but not all embodiments of the invention are shown. Indeed, these inventions may be embodied in many different forms and should not be construed as limited to the embodiments set forth herein; rather, these embodiments are provided so that this disclosure will satisfy applicable legal requirements. Like numbers refer to like elements throughout.

15 As an initial overview of preferred embodiments of the invention, a flexible packaging laminate is constructed to have a built-in opening and reclose function and a tamper-evidence feature. The laminate is constructed as a multi-layer structure by adhesively laminating a first structure to a second structure, wherein each of the first and second structures comprise one or more layers of flexible material. Pressure-sensitive
20 adhesive is applied to one of the structures before lamination. Once the laminate is formed in this manner, scoring operations are performed on both sides of the laminate, but each scoring operation penetrates only through a part of the thickness of the laminate; in particular, a scoring operation performed on the side of the laminate adjacent the first structure results in penetration through the first structure, but without complete
25 penetration through the second structure, and preferably without any substantial penetration, and more preferably without any penetration, into the second structure. Likewise, the scoring operation performed on the side of the laminate adjacent the second structure results in penetration through the second structure, but without complete penetration through the first structure, and preferably without any substantial penetration,
30 and more preferably without any penetration, into the first structure. The scoring operation also forms the tamper-evidence feature, as further described below.

35 More particularly, with reference to FIG. 1, a first phase of the manufacturing process is depicted. A first structure **10** is advanced from a supply roll **12** by suitable web driving and handling equipment (not shown) to an optional print station **14** comprising a printing apparatus, such as a rotogravure printer or the like, for printing graphics and/or indicia on the first structure by applying inks to a surface of the first structure. The first structure **10** comprises one or more layers of flexible packaging material. Various

materials can be used for the layer(s) of the first structure, including polymers such as polyesters, polyolefins (including homopolymers and copolymers), polyamides, and others; paper; metal foil; and the like. In a preferred embodiment of the invention, the first structure **10** includes an outer layer (not illustrated) that is substantially transparent and is reverse-printed in the print station **14**, i.e., the inks are applied to the surface of the first structure **10** that is subsequently laminated to another structure, as described below, from the opposite side of the first structure, which will form an exterior of a package constructed from the packaging laminate, the inks are visible through the first structure. As an example, the first structure **10** can comprise a layer of polyester such as polyethylene terephthalate or the like.

Prior to printing the first structure in the print station, the surface of the first structure that is subsequently laminated to the other structure can be treated by a corona discharge or flame treatment apparatus **16** to render the surface more receptive to the inks and/or to render the surface more readily bondable to the pressure-sensitive adhesive that is subsequently applied to the surface as described below. Alternatively, the first structure **10** can have already been so treated prior to being wound into the supply roll **12**, such that the treatment apparatus **16** is unnecessary.

Following the optional corona/flame treatment and/or optional printing operation, and with reference to FIGS. 1 and 1a, the first structure **10** is advanced to a first adhesive application station **18** at which a pressure-sensitive adhesive **20** is applied to the first structure in a predetermined pattern **22** that recurs at regular intervals along the lengthwise direction of the first structure. The predetermined pattern **22** is generally in the form of a strip of various forms or shapes. As illustrated, a preferred shape for the strip pattern **22** is generally U-shaped, for reasons that will become apparent in the description of FIGS. 4-8; however, other shapes for the pattern **22** can be used, the invention not being limited to any particular pattern. The pattern can include a region **23** that is free of adhesive and will ultimately form a thumb tab or grasping portion of the first structure **10** as further described below. It is also possible in alternative embodiments to flood-coat the pressure-sensitive adhesive onto the entire surface of the first structure.

The pressure-sensitive adhesive **20** can comprise various compositions. Pressure-sensitive adhesives form viscoelastic bonds that are aggressively and permanently tacky, adhere without the need of more than a finger or hand pressure, and require no activation by water, solvent or heat. Pressure-sensitive adhesives are often based on non-crosslinked rubber adhesives in a latex emulsion or solvent-borne form, or can comprise acrylic and methacrylate adhesives, styrene copolymers (SIS / SBS), and silicones. Acrylic adhesives are known for excellent environmental resistance and fast-setting time when compared with other resin systems. Acrylic pressure-sensitive

adhesives often use an acrylate system. Natural rubber, synthetic rubber or elastomer sealants and adhesives can be based on a variety of systems such as silicone, polyurethane, chloroprene, butyl, polybutadiene, isoprene, or neoprene. When the packaging laminate of the invention is to be used for food packaging, the pressure-sensitive adhesive **20** generally must be a food-grade composition. Various pressure-sensitive adhesives are approved by the U.S. Food and Drug Administration for use in direct food contact, as regulated by 21 CFR Part 175.300. A preferred food-grade pressure-sensitive adhesive **20** for use in the present invention is Jonbond 743 available from Bostik Findley. Additives (e.g., particulates or the like) can be added to the pressure-sensitive adhesive **20** to reduce the tenacity of the bond to the underlying second structure **42**, if necessary, so that the pressure-sensitive adhesive **20** readily detaches from the second structure on opening (particularly on the very first opening).

When applied in a pattern as opposed to being flood-coated or applied everywhere on the first structure **10**, the pattern **22** of pressure-sensitive adhesive **20** is applied to the first structure **10** at regular intervals along the first structure **10**. The spacing or index distance *d* between the patterns **22** can correspond to a dimension, such as a length, of packages to be produced from the packaging laminate.

The adhesive application station **18** can comprise any suitable device capable of accurately applying the pressure-sensitive adhesive **20** to the first structure **10** in the desired pattern **22**, at regular intervals along the structure. For example, as shown, the adhesive application station can comprise a gravure roll **24** that picks up the pressure-sensitive adhesive **20** from a reservoir **26** on the outer surface of the roll such that the adhesive fills one or more recessed areas in the surface. A doctor blade **28** scrapes off excess adhesive so that it remains essentially only in the recessed area(s). The first structure **10** is contacted by the gravure roll **24**; a backing roll **30** provides support on the opposite side of the first structure **10**.

After application of the pressure-sensitive adhesive **20**, the first structure **10** is advanced to a dryer **31** such as an oven or the like, to dry the pressure-sensitive adhesive **20**. In the case of the pressure-sensitive adhesive **20** being pattern-applied, the first structure **10** is then advanced to a second adhesive application station **32** at which a permanent laminating adhesive **34** (FIG. 1b) is applied to the first structure **10** in such a manner that a sufficiently large proportion of the surface is covered by the permanent adhesive **34** to permit the first structure **10** to be adhesively attached to a second structure **42** at a downstream laminating station **40**. The permanent adhesive **34** does not cover the pressure-sensitive adhesive **20**. Furthermore, when the pattern of pressure-sensitive adhesive **20** includes an adhesive-free region to form a thumb tab or grasping portion **23** as previously noted, the pattern of the permanent adhesive also does

not cover the adhesive-free region. Thus, the permanent adhesive **34** must be applied by an apparatus capable of accurately applying the adhesive in a predetermined pattern, in registration with the pressure-sensitive adhesive **20** but not covering it or the adhesive-free region if present. A suitable adhesive application device **32**, as shown, can be a gravure roll **24** of the type previously described. The permanent adhesive **34** can comprise various compositions. Suitable examples include two-component polyurethane adhesive systems, such as Tycel 7900/7283 available from Henkel. After the application of the permanent adhesive **34**, the first structure **10** is advanced to a dryer **33** such as an oven or the like. Alternatively, when the pressure-sensitive adhesive **20** is applied to the entire surface of the first structure **10**, the steps of applying and drying the permanent adhesive **34** are skipped.

The first structure **10** is then advanced to a laminating station **40**, comprising a pair of rolls forming a nip therebetween. The first structure **10** is passed through the nip along with a second structure **42** that is advanced from its own supply roll **44**, and the first and second structures **10/42** are laminated to each other. The second structure **42** comprises one or more layers of flexible material, and is coextensive with the first structure **10**—i.e., the width of the second structure **42** is substantially equal to the width of the first structure **10** and the longitudinal edges of the second structure **42** substantially coincide with the longitudinal edges of the first structure **10**. The resulting laminate **46** is then advanced to a reel-up (not shown) where it is wound into a roll for subsequent processing in the second phase of the manufacturing process as described below. Alternatively, it is possible for the reel-up operation to be omitted, such that the laminate is directly advanced to the second phase.

With reference to FIGS. 2 and 6, the second phase of the process is now described. A supply roll **48** of the laminate **46** formed in the first phase of the process is shown. The laminate is advanced from the supply roll to a first scoring station **50** at which a first, or outer, score line **52** (FIG. 6) is formed through the thickness of the first structure **10**. When the pressure-sensitive adhesive **20** has been pattern-applied, the first score line **52** is in registration with (i.e., coincides with) the outer perimeter **22a** (FIG. 1a) of the strip-shaped pattern **22** of pressure-sensitive adhesive **20**. The first score line **52** extends substantially through the thickness of the first structure **10**, but preferably does not extend to any substantial extent into the second structure **42**, as illustrated in FIG. 6.

The first scoring station **50** can comprise a laser **54** as depicted in FIG. 2. The use of lasers for scoring through flexible materials is generally known, for example as described in U.S. Patent No. 5,158,499, incorporated herein by reference. The depth of the score line formed by the laser can be regulated by regulating the power output or beam intensity of the laser beam, the width or spot size of the laser beam, and the

amount of time a given spot on the film surface is irradiated by the beam. These factors generally are selected based on the characteristics of the material being scored. Some materials are more readily scored by lasers than other materials, as known in the art.

As noted, the first score line **52** must be in registration with the outer perimeter **22a** of the pressure-sensitive adhesive strip **20** (and the outer perimeter of the thumb tab **23**, if present). To accomplish this registration, the operation of the laser **54** is controlled to be synchronized with the advancement of the laminate **46**. A sensor **56** disposed adjacent the laminate **46** can be used for detecting a feature on the laminate whose location in relation to the strip of pressure-sensitive adhesive **20** is known, and the sensor's output signal can be used by a suitable controller (not shown) for controlling the laser **54**.

The first score line **52** may also include one or more tear portions **65** as a tamper-evidence feature. A tear portion **65** may comprise one or more interrupted areas **57** in which the first structure **10** is not cut or scored, and whose uncut condition is readily apparent from a visual inspection of the first structure **10**. The interrupted areas **57** are located such that when the flap or outer opening portion **86** bounded by the first score line **52** is peeled back to create an opening through the laminate, the first structure **10** tears through the interrupted areas **57** to connect the two portions of the first score line **52** on opposite sides of each interrupted area **57**. To help ensure that the two portions of the score line will be connected even if the tear line tends to wander in direction, the score line **52** at the "downstream" side of each interrupted area **57** can terminate in a U- or V-shaped portion **58** that extends generally transverse to the direction along which the score line **52** extends. The "downstream" side refers to the side of the interrupted area **57** that is located farthest along the downstream direction (generally left-to-right in FIGS. 4 and 5) in which the outer opening portion **86** is peeled back when opening the package. The first structure **10** is cut through its thickness along the transverse portions **58**, similar to the rest of the score line **52**. Accordingly, even if the tear line wanders to one side or the other, it will connect with the transverse portion **58** and thereby allow the score line **52** to continue to sever or separate as the outer opening portion **86** is peeled farther back.

Next, the laminate is advanced to a second scoring station **60** at which a second, or inner, score line **62** is formed through the thickness of the second structure **42**. When the pressure-sensitive adhesive **20** has been pattern-applied, the second score line **62** is in registration with (i.e., coincides with) the inner perimeter **22b** (FIG. 1a) of the strip-shaped pattern **22** of pressure-sensitive adhesive **20**. The second score line **62** extends substantially through the thickness of the second structure **42**, but preferably does not extend to any substantial extent into the first structure **10**, as illustrated in FIG. 6. The second score line **62** is spaced inwardly of the first score line **52** so as to define an inner

opening portion **88** of smaller area than the outer opening portion **86**. As further described below, the inner opening portion **88** is adhered to the outer opening portion **86** (either by the permanent adhesive when present, or by the pressure-sensitive adhesive **20** when it is applied everywhere between the two structures **10, 42**), such that both
5 portions **86, 88** are lifted together when opening the package.

As shown in FIGS. 4 and 5, preferably the interrupted areas **57** are located with respect to the second score line **62** such that in order to lift the outer opening portion **86** far enough to just begin lifting the inner opening portion **88** and thereby begin to create an opening into the package, the interrupted areas **57** must be torn through. In this regard,
10 the downstream side of each interrupted area **57** (which coincides with the vertex of the U- or V-shaped transverse score line **58**) preferably is not farther along the downstream direction, or at least is not substantially farther along the downstream direction, than is the most-upstream portion of the second score line **62**.

The second scoring station **60** can comprise a laser **64**. The operation of the
15 laser **64** is synchronized with the advancement of the laminate in a manner as described above. A sensor **66** can detect a feature, such as an eye mark, on the laminate whose location in relation to the pressure-sensitive adhesive strip **20** is known, and the sensor **66** output can be used for regulating the laser operation so that the second score line **62** is in registration with the inner perimeter of the pressure-sensitive adhesive strip **20**.

As an alternative to the use of lasers for scoring the laminate, the score lines **52, 62** can be formed in the laminate by mechanical scoring or cutting. For instance, as depicted in FIG. 3, a first scoring station **50'** can comprise a kiss roll **51** and backing roll **53** that form a nip through which the laminate is passed. The kiss roll **51** comprises a rotary cutting die defining a cutting edge (not shown). The kiss roll acts in conjunction
25 with the backing roll to cut partially through the thickness of the laminate starting from the outer surface of the first structure **10**, such that the first structure **10** is substantially scored through while the second structure **42** is left intact. The second scoring station **60'** likewise comprises a kiss roll **61** and backing roll **63** for scoring through the second structure **42**.

Additionally, it is within the scope of the invention to laser-score one side of the laminate and to kiss cut or otherwise mechanically score the other side. This can be advantageous, for example, when one of the structures making up the laminate is readily scored by a laser but the other structure is not. For instance, when the first structure **10** is a polyester such as PET, it can readily be scored with a laser, but if a polyethylene heat
35 seal layer is employed on the opposite side, laser scoring may not be the best choice because polyethylene does not score well with a laser. In this case, kiss cutting or other mechanical scoring can be used to score the inner structure **42**.

After the scoring operations, the laminate **46** can be sent to a reel-up (not shown) and wound into a roll for subsequent processing. The laminate can also be slit into a plurality of partial widths and wound into multiple rolls. In this latter instance, each partial width would have the recurring patterns of pressure-sensitive and permanent adhesives applied with suitably configured adhesive applicators to the full-width material, and would have the recurring score lines formed by suitably configured scoring devices acting on either the full-width laminate prior to slitting or acting on each partial-width portion after slitting.

An advantage of the invention, versus the formation of a web having discrete labels applied to a partial portion of the web surface as in the prior art, is that the laminate has a uniform thickness throughout (because the first and second structures are coextensive) and therefore winds well into good-quality rolls. In contrast, a web with labels centrally located in the width of the web tends to produce wound rolls that are soft in the radial direction at the two ends of the roll where the labels are not present. Additionally, the web with labels is much thicker than laminates made in accordance with the invention, and hence the laminates of the invention can achieve a greater square footage per roll of a given diameter. As already noted, a further drawback to the use of labels is the necessity of applying the labels to the web in an "off-line" process, which often entails shipping a roll of the web to a converter that applies the labels and then ships the roll back to the package manufacturer. In the process of the invention, the manufacture of the laminate and the incorporation of the opening/reclose and tamper-evidence features in the laminate are conducted in an in-line fashion as part of the same overall process. The process of the invention thus is much more efficient and less costly.

Additionally, the invention avoids other drawbacks associated with the use of labels. More specifically, pressure-sensitive adhesive labels typically require a release liner that is peeled off and thrown away, which represents waste, and create a potential choke hazard. Furthermore, there is the additional waste of the skeleton material left over after die-cutting the labels from the label web material. The present invention eliminates such waste and attendant costs.

Some possible applications for the resulting laminate are now explained with reference to FIGS. 4-11. FIGS. 4 and 5 show a flexible package **70**. The package includes an outer wrapper **74** that envelopes the package contents and is sealed to enclose the contents. The outer wrapper **74** comprises a packaging laminate made by a method in accordance with the invention, such as the laminate **46** previously described. The outer wrapper **74** is manipulated into a tubular shape and the longitudinal edges of the wrapper **74** are sealed together by a suitable sealant material to form a longitudinal seal (not shown), typically adjacent the bottom surface of the package. The opposing

portions of the wrapper **74** are sealed together along transverse seal lines **76**, **78** adjacent the opposite ends of the tubular wrapper. The ends of the wrapper **74** can be gusseted if desired, as known in the art.

5 In the illustrated package, the portion of the outer wrapper **74** having the score lines **52**, **62** is provided to be on the top surface of the package. The area of the wrapper **74** bounded by the score lines can constitute any fraction of the total top surface of the package, but advantageously the area is a majority of the total surface area of the top surface.

10 Based on the previous description of the laminate **46** and its formation process, it will be appreciated that the presence of the score lines **52**, **62** has little or no impact on the barrier function of the outer wrapper **74** because each score line extends only partially through the total thickness of the wrapper **74** and the score lines are not aligned with each other. Additionally, the pressure-sensitive adhesive **20** fills the space between the score lines so that even if the score lines overlap somewhat in the thickness direction,
15 there is still no open route between them. Furthermore, the score lines typically have a small width, on the order of a few thousandths of an inch.

Various materials can be used for the construction of the outer wrapper **74**. With reference to FIG. 6, in the illustrated embodiment, the first structure **10** that forms the outer surface of the wrapper **74** comprises a single layer **80** of flexible material. The layer
20 **80** can comprise various materials. A preferred material is a polyester such as polyethylene terephthalate (PET). As noted, the PET layer can be reverse-printed if desired, although alternatively it can be printed on its exterior and covered by an over-lacquer (not shown). The second structure **42** forming the inner surface of the wrapper **74** comprises a barrier layer **82** and a sealant layer **84**. The sealant layer **84** constitutes
25 the innermost surface of the wrapper **74**, and can comprise various sealant materials such as heat seals or cold seals. Heat seals generally are preferred because they provide stronger seals than cold seals typically are capable of achieving. Any suitable heat seal materials can be employed, such as polyethylene, polypropylene, ionomer resins such as SURLYN®, or others.

30 The barrier layer **82** can comprise any of various barrier materials including barrier polymer films such as: ethylene vinyl alcohol copolymer (EVOH), polyamide, and the like; metallized polyolefin films such as polyethylene, polypropylene, oriented polypropylene, and the like; AlOx-coated polymer films; SiOx-coated polymer films; metal foil; and others.

35 The barrier layer **82** and sealant layer **84** can be joined in various ways, including adhesive lamination, extrusion lamination, or coextrusion.

Advantageously, the laminate includes a metallization layer or a metal foil layer between the first structure **10** and the second structure **42**, for example by providing a

metallization layer **85** on the surface of the layer **82** that faces the first structure **10**. This is beneficial in enhancing the barrier performance of the laminate as already noted.

Additionally, however, the metallization layer or **85** metal foil layer can also be helpful when a laser is used for scoring the second structure **42**. In particular, when the sealant layer **84** comprises polyethylene, which is not as readily scored by laser as some other materials such as polyester, it can be difficult to employ a sufficiently high laser energy to score through the polyethylene sealant layer without scoring through the laminate more deeply than desired. In some cases, the entire thickness of the laminate may be scored through, which is undesirable. The metallization layer or metal foil layer can be helpful in “tuning” the laser to penetrate only up to the metallization layer **85** or foil layer.

The function of the opening/reclose and tamper-evidence features provided by the pattern-applied adhesives and the score lines will now be described. With reference to FIGS. 4 and 6, the package **70** is shown in a closed condition, for example as initially filled and sealed in a packaging plant. On the top surface of the outer wrapper **74**, the first or outer structure **10** is adhesively joined to the second or inner structure **42** via the permanent adhesive **34**. The first score line **52** bounds an outer opening portion **86** of the outer structure **10**. In this embodiment, the outer opening portion **86** has a generally U-shaped perimeter having three sides defined by the score line **52**, and is attached to the remainder of the outer wrapper **74** along a fourth side (i.e., an imaginary line extending between the free ends of the two legs of the U-shaped score line **52**). The second score line **62** is generally parallel to the first score line **52**, but is spaced inwardly of the outer score line so as to define an inner opening portion **88** of smaller area than the outer opening portion **86**; the second score line **62** can be a closed curve such as a rectangle, or can be generally U-shaped like the first score line **52**, as desired. In any event, there is a marginal region **90** of the outer opening portion **86** that extends beyond the edge of the inner opening portion **88**. The pressure-sensitive adhesive **20** is disposed between this marginal region **90** and an underlying surface **92** of the inner structure **42**. The outer opening portion **86** and inner opening portion **88** are permanently joined by the permanent adhesive **34** when present, or by the pressure-sensitive adhesive when it is applied everywhere between the structures.

The first score line **52** includes the interrupted areas **57** and transverse score lines **58** as previously described. Prior to initial opening of the package, the uncut condition of the interrupted areas **57** is readily apparent, such that the consumer can see that the package has not yet been opened.

When the outer opening portion **86** is detached from the outer wrapper along the first score line **52** and is peeled back as in FIG. 5, the outer layer of the wrapper tears through the interrupted areas **57**. The inner opening portion **88** remains affixed to the

outer opening portion and comes with it, thereby creating an opening **94** in the top surface of the outer wrapper **74** as defined by the second score line **62**. The outer and inner opening portions essentially form a flap that remains attached along a hinge line defined between the free ends of the two legs of the U-shaped score lines.

5 The package is reclosable by re-attaching the pressure-sensitive adhesive **20** to the surface **92** of the inner structure **42** to restore the package to a closed condition as shown in FIG. 6. It will, however, be readily apparent that the package has already been opened, because the film will be torn through the tear portions **65**. No amount of care in replacing the flap in its original position can erase the fact that the interrupted areas have
10 been torn through. Accordingly, the invention provides a reliable tamper-evidence feature that is not easily circumvented. Furthermore, in some embodiments, the outer structure **10** can be substantially non-transparent or opaque without compromising the functionality of the tamper-evidence feature; this is in contrast to some prior-art structures in which the outer structure must be transparent because the tamper-evidence feature is formed in the
15 inner structure and is covered by the outer structure. The non-transparent or opaque character of the outer structure **10** can be a characteristic of the film material itself, or can be achieved by a coating of ink or the like on the film.

 The outer structure **10** preferably has a greater affinity for bonding with the pressure-sensitive adhesive **20** than does the surface **92** of the inner structure **42**, and
20 hence the pressure-sensitive adhesive **20** is detached from the surface **92** and remains attached to the marginal region **90** of the outer opening portion **86** as shown in FIGS. 5 and 7. The greater bonding affinity of the outer structure **10** can be achieved in various ways. When the outer structure comprises a layer of PET and the layer **82** of the inner structure to which the pressure-sensitive adhesive is attached comprises a polyolefin
25 such as polypropylene, oriented polypropylene, or metallized oriented polypropylene, the PET will naturally have a greater affinity for bonding to the adhesive than will the polyolefin layer. Additionally or alternatively, the surface of the outer structure **10** can be treated, as previously noted, by corona discharge or flame treatment, to increase the surface energy and enhance the bonding affinity. It is also possible, as already noted, to
30 control the bond strength of the pressure-sensitive adhesive to the layer **82** by including an additive in the adhesive to reduce the bond strength, if desired.

 Although it is preferred to have the pressure-sensitive adhesive be applied to the outer structure and to remain on the outer structure upon opening, it is also within the scope of the invention to apply the pressure-sensitive adhesive to the inner structure and
35 to remain on the inner structure upon opening. This is less preferred, however, because of the greater tendency for crumbs or the like from the contained products to become adhered to the pressure-sensitive adhesive and thereby reduce its adhesiveness with

repeated openings and reclosings. It is believed that this tendency is reduced when the pressure-sensitive adhesive remains with the outer structure, since it is out of the way of the package opening when products are being removed.

It will be appreciated from the above description that laminates made in accordance with the invention provide a tamper-evidence function for a package because after opening it is impossible to replace the opening portions **86, 88** in such a way as to completely restore the package to its original unopened condition, as previously noted. When printing is included on the laminate, it is even more noticeable when the package has been opened because it is difficult to achieve perfect registration of the printed matter across the score line when reclosing the package.

The printing on the laminate can include text adjacent to the interrupted areas **57** of the first score line **52**, calling the consumer's attention to the presence of the interrupted areas and indicating that if they are torn through at a tear portion **65**, the consumer should not purchase the package.

The laminates made in accordance with the invention can be used for forming other types of packages or tamper-evidence features. For instance, FIG. 8 shows a stand-up pouch **100** constructed from the laminate **46** as described above. The first score line **52** and second score line **62** are formed in a side wall of the pouch. The opening/reclose and tamper-evidence features operate in a manner similar to that described above. An alternative form of a thumb "tab," **25** is included, wherein a corner portion of the outer flap defined by the first score line **52** is left free of pressure-sensitive adhesive **20**.

Similarly, FIG. 15 shows an embodiment of a stand-up pouch **100** constructed from the laminate as described herein. The first score line **52** and second score line **62** are formed in a side wall of the pouch. The opening/reclose and tamper-evidence features may, in an embodiment, operate in a manner similar to that described above. A pull tab **25** is included which extends from an edge of outer portion **86**. Preferably, tab **25** is defined by first score line **52** and is free from pressure sensitive adhesive **20** or lamination to the second structure **42**. Alternatively, the area of tab **25** may be deadened with respect to any adhesive positioned therein. In an embodiment, the edge **275** of tab **25** is continuous with the edge **276** of the pouch. In an embodiment, some or all of the tab **25** is positioned within the heat seal area of the pouch, adjacent the seal line **76**. In this embodiment, the end of tab **25** may be attached or anchored or along the transverse seal line **76**.

The packages illustrated in FIGS. 9, 10 and 11 show other stand-up pouches **100** with alternative types of tamper-evidence features. In particular, the stand-up pouch **100** of FIG. 9 includes a tab **25** that extends from an edge of outer portion **86**. Preferably, tab

25 is defined by first score line **52** and is free from pressure sensitive adhesive **20** or lamination to the second structure **42**. The end of the tab **25** is then attached or anchored to a portion of the outer layer **74** or along the transverse seal line **76**. The tab **25** illustrated in FIG. 9 may also include an indentation **55** between the outer portion **86** and where the end of tab **25** is attached to the stand-up pouch **100**. By forming the tab **25** in this way, a user may easily access an underside of the tab **25** with a finger and open the stand-up pouch **100** by pulling the tab generally along the downstream direction (generally top-to-bottom in FIGS. 8-10). By pulling on the tab **25** in this way, the tab **25** will tear at or near the indentation **55**, or tear portion **65**, and allow the stand-up pouch **100** to open. Thus, the stand-up pouch **100** cannot be opened without introducing a tear into the tab **25** thereby creating a tamper-evidence feature that is clearly visible.

The stand-up pouch **100** of FIGS. 10 and 11 show other embodiments of tab **25** with a tamper-evidence feature. In FIG. 10, tab **25** also is defined by first score line **52** and extends from an edge of outer portion **86**. The end of the tab **25** is attached or anchored to a portion of the outer layer **74** or along the transverse seal line **76** and is free from pressure sensitive adhesive **20** or lamination to the second structure **42**. The tab **25** in FIG. 10 includes a prong **59** extending from a side of the tab **25** between the outer portion **86** and where the end of tab **25** is attached to the stand-up pouch **100**. The presence of prong **59** facilitates the task of a user tearing through a portion of the tab **25** at a tear portion **65** before opening the stand-up pouch **100** by providing a surface that is easily grasped.

The embodiment in FIG. 11 includes two tabs **25** that include tear portions **65** in addition to a thumb tab **23**. Both tabs **23** and **25** also are defined by first score line **52** and extend from an edge of outer portion **86** and are free from pressure sensitive adhesive **20** or lamination to the second structure **42**. The end of tabs **25** are attached or anchored to a portion of the outer layer **74** or along the transverse seal line **76**. In use, tab **23** may be used to open the pouch **100** and to assist in tearing through tear portions **65** of tabs **25**.

It should be noted that the terms "line of weakness" and "score line" as used herein refer either to a complete cutting through the thickness of one or more layers of the laminate or to a partial cutting through of the thickness of such layer(s) allowing the layer(s) to be severed along the score line.

FIGS. 16A-B illustrate top view embodiments of rolls of flexible laminate **200** which may be utilized in the present invention. In roll **200**, two flexible laminate structures **210** are shown, but it should be understood that a plurality of flexible laminate structures may be present on roll **200**. In this embodiment, each laminate structure **210** contains an outer score line **252** in the outer film layer (optionally, precision overcut after lamination)

and an inner score line **262** (optionally, precision undercut after lamination) in the inner film layer. Each structure **210** additionally comprises a tab **223**. In an embodiment, the tab **223** is defined by the outer score line **252**. The outermost edge **275** of tab **223**, in an embodiment, may not be within the boundaries of the laminate (shown in FIG. 16A). That is, the outer score lines **252** may begin at one edge **277** of the laminate, sufficiently separated so as to create tab **223**. In this embodiment, the outer score lines **252** may begin substantially perpendicular to the edge **277** of the laminate, with the edge **275** of the tab **223** being between the outer score lines **252** and substantially co-extensive, continuous, and/or aligned with the edge **277**. In this embodiment, at least a portion of the tab **223**, is positioned within the heat seal area **279** of the laminate. In an embodiment, the entirety of the tab **223** is positioned within the heat seal area **279** of the laminate.

As shown in FIG. 16B, the laminate structures **210** may be positioned such that the tab edge **275** is perpendicular to the edge of the laminate **277** in some embodiments. In this embodiment, the tab **223** will still be positioned within the heat seal area **279**, but the heat seal area **279** will also be perpendicular to the edge of the laminate **277**. The heat seal area **279** may comprise a length **281** that is approximately twice that of the length **282** of the tab **223**. In this way, the heat seal can be simultaneously provided for opposite ends of the packaging. The heat seal area **279** may be cut at or near the edge **275** of the tab **223**.

FIG. 17A illustrates a side view cross section of an embodiment of a package of the invention at the location of the tab **223**, in the location of cross section A in FIG. 16A. In this view, an outer film **201** is shown adhered to an inner film **202**. An adhesive-free region **204** is illustrated between film layer **201** and film layer **202** in the location of the tab **223**. Film layers **201** and **202** may be adhered together using PSA **220** and a permanent adhesive **234**, as shown. The adhesives may be applied in a pattern as is further described herein. A cut line **262** is shown which extends through the adhesive layer and the inner film layer **202**. In some embodiments, the cut line **262** may extend fully through inner film layer **202**. In other embodiments, the cut line **262** may extend only partially through inner film layer **202**. In still other embodiments, the cut line **262** may comprise perforations in inner film layer **202**. The cut line may not extend through the PSA layer **220** in some embodiments.

The cut line **262**, in combination with the permanent adhesive **234**, allows the portion of the inner film **202** between or within the cut lines **262** to be lifted with the outer layer **201**, away from the remainder of the packaging, thereby exposing the interior **205** of the package. The outer layer **201** can then be re-adhered to the inner film **202** via the PSA region **202**. It should be noted that in any of the embodiments discussed herein, the

PSA region or the adhesive-free region may extend beyond or overlap the scored or cut lines, as shown in FIGS. 16-17, so as to ensure that the package can be opened without damage in the case of a slight misalignment of the registration during manufacture.

In an embodiment, inner layer **202** is adhered on a portion of its underside to a separate film layer (not shown), which may comprise more than one film layer. The separate film layer may comprise the bottom of the packaging structure. Film layers **202** and the separate film layer may be joined, in an embodiment, using a heat seal **279**.

In another embodiment, inner layer **202** is rolled, folded or otherwise at least partially placed against itself and heat sealed (shown in Fig. 17A). In an embodiment, the heat seal is administered in at least the region of the tab **223**. Thus in the final package, the heat seal region **279** may comprise at least the region of the tab **223**, shown in FIG. 17A between the layers of film **202**. The tab portion **223** of film layer **201** may remain unaffixed to film layer **202**, even after heat sealing the film, due to the adhesive-free region **204**. Thus, the tab **223** is located within the package heat seal region **279** and is available to be separated from the package for opening of the package after the package has been heat sealed.

FIG. 17B illustrates a front view cross section of an embodiment of a package of the invention at the location of the tab **223**, in the location of cross section B in FIG. 16A, when the package is closed. The figure illustrates the score lines **252** which comprise the outer edges of the tab **223** in outer film layer **201**. The figure also illustrates the fact that the tab is presented within the heat seal region **279** of the package. Generally speaking, the heat seal **279** is shown between two layers of inner layer **202**, which have been folded, rolled or stacked upon one another and heat sealed. In an embodiment, outer layer **201** is laminated to inner layer **202** with adhesive but is not otherwise heat sealable to inner layer **202**. Thus, when the heat seal is applied to the area of the tab **223**, the area between the two layers of **202** are heat sealed, but the tab **223** remains unaffixed to the structure.

FIG. 17C illustrates a front view cross section of an embodiment of a package of the invention at the location of the tab **223**, in the location of cross section B in FIG. 16A, when the tab **223** has been lifted away from the inner layer **202**. In this embodiment, cut lines **252** and the adhesive-free region **204** allow the tab **223** to be separated from the remainder of outer film layer **201**. The remainder of outer film layer **201** remains affixed to inner film layer **202** due to the permanent adhesive **234** disposed between the layers.

FIG. 17D illustrates a front view cross section of an embodiment of a package of the invention at the location of the tab **223**, in the location of cross section C in FIG. 16A. In this figure, the tab has been pulled further upward or backward and the package is opened, illustrating the separation of the adhered outer and inner layers **201**, **202** from

the remainder of the package, and allowing access into the interior **205** of the package. In this embodiment, cut lines **262** allow the portion of film layer **202** which is between the lines **262** to separate from the remainder of film layer **202** and, due to the permanent adhesive **234** disposed between the layers, lift with film layer **201** upward or backward from the container. The heat seal **279** is not viewable in FIG. 17C because the cross section does not illustrate the tab portion **223**.

As noted, the tab **223** area of the laminate, between film layers **201** and **202** may be adhesive-free, may contain PSA, or may contain an adhesive that has been deadened. The area between outer score line **252** and inner score line **262** may contain a layer of PSA **220**, optionally flooded or pattern applied. As shown in FIG. 17A, the PSA area **220** may extend wider than or beyond the cut lines **252**. Other than the tab **223** and the PSA area **220** discussed, the remainder of the laminate may contain a layer of permanent adhesive **234**, optionally pattern applied. In various embodiments, the outer score line **252** may end in a j-hook **293** or other mechanism which prevents the tearing of the laminate.

Presenting the tab **223** within the heat seal area **279** of the package provides many advantages. As one example, the tab **223** can be accessed more easily in this configuration. Rather than searching the top or front surface of the package, a consumer immediately knows where to look for and access the tab **223**. Because the tab **223** is aligned with the edge of the package, it can be identified, accessed, and lifted away from the package with ease, reducing customer frustrations. In addition, the laminate and packaging structures discussed herein have a lower cost of manufacture because the cutting/scoring process is less complicated and less waste is created in the manufacturing process. By aligning the edge of the tab with the laminate edge or along the cut line of the heat seal, an additional cut or angle need not be contemplated. A single cut (or no cut at all in the case of a tab aligned with a laminate edge) will suffice. Additionally, the waste created between the edge of the tab and the laminate boundaries may be reduced or eliminated.

As is known in the art, the packages described herein may be, in an embodiment, formed from the various laminate structures and then heat sealed together at one or more ends of the package. In an embodiment, the laminate structure is rolled or folded and sealed to itself to form a package. In another embodiment, the laminate structure is combined with and heat sealed to a separate web to form a package. At least one of the laminate structures may comprise components having thermoplastic properties to facilitate and improve the sealing properties of the heat seal. The heat seal may be obtained by bringing the laminate structures into contact with heat such that the thermoplastic components in the material melt and provides the heat seal. The heat seal

may alternatively be obtained using any suitable method known in the art, for example, by hot air welding or conventional heat mold sealing.

The packages described above are formed by completely enveloping the contents in the flexible laminate. Alternatively, however, it is within the scope of the invention to employ the flexible laminate as a lidding stock for forming flexible lids that can be secured (e.g., by heat-sealing or the like) to a flange of a tray or other container that contains the contents. In this manner, the lid includes a built-in opening and reclose feature as previously described. For instance, FIG. 12 shows a package **110** comprising a container body **112** having a side wall **114** and a flange **116** extending from the upper edge of the side wall. The container body **112** can comprise various materials (e.g., polymer, paper, foil, etc.) and can be formed by various methods (e.g., thermoforming, molding, etc.). The open top of the container body is closed by a lid **118** formed of a flexible laminate **46** in accordance with the invention. The lid is sealed to the flange **116** by any suitable technique, such that the lid is firmly attached to the flange. The lid includes an opening/reclose feature formed by a first score line **52** and a second score line **62** and pressure-sensitive adhesive **20**, and a tamper-evidence feature as previously described. The package **110** also includes a thumb "tab" **25** generally as described in connection with FIG. 8; alternatively, a thumb tab of the type shown in FIGS. 4 and 5 can be used.

Many modifications and other embodiments of the inventions set forth herein will come to mind to one skilled in the art to which these inventions pertain having the benefit of the teachings presented in the foregoing descriptions and the associated drawings. Therefore, it is to be understood that the inventions are not to be limited to the specific embodiments disclosed and that modifications and other embodiments are intended to be included within the scope of the appended claims. Although specific terms are employed herein, they are used in a generic and descriptive sense only and not for purposes of limitation.

WHAT IS CLAIMED IS:

1. A flexible packaging structure having built-in opening/reclose and tamper-evidence features, comprising:

an outer structure adhesively joined in face-to-face relation to an inner structure, the outer structure comprising a first flexible material and the inner structure comprising a second flexible material;

an outer line of weakness formed in the outer structure, the outer line of weakness defining an outer opening portion that is separable from the outer structure along the outer line of weakness;

an inner line of weakness formed in the inner structure, the inner line of weakness defining an inner opening portion that is separable from the inner structure along the inner line of weakness;

wherein the inner opening portion is joined to the outer opening portion such that lifting the outer opening portion out of the plane of the flexible packaging structure causes the inner opening portion to be lifted along with the outer opening portion so as to create an opening through the flexible packaging structure;

wherein a marginal region of the outer opening portion is defined between the inner and outer lines of weakness, the marginal region overlying an underlying surface of the inner structure;

wherein a pressure-sensitive adhesive is disposed on one of an overlying surface of the outer opening portion and the underlying surface of the inner structure for re-adhering the overlying surface to the underlying surface after opening; and

a tab defined by the outer line of weakness formed in the outer structure, such that the tab is disposed within a heat seal region of the packaging structure and is free from adhesion or lamination to the second structure.

2. The flexible packaging structure of claim 1, wherein the tab additionally comprises at least one tamper-evidence feature that is initially in an untorn condition prior to initial creation of the opening, and whose untorn condition is apparent from a visual inspection of the outer structure, wherein the tamper-evidence feature is torn through upon initial creation of the opening through the flexible packaging structure and wherein the tamper-evidence feature further comprises an indentation.

3. The flexible packaging structure of claim 2, wherein the tab further comprises a prong extending from a side of the tab.

4. The flexible packaging structure of claim 1 in combination with a container body having a side wall and a flange extending from an upper edge of the side wall, wherein the flexible packaging structure comprises a lid, the lid being attached to the flange to seal closed the package.
5. The flexible packaging structure of claim 1, wherein the heat seal region is perpendicular to the edge of the laminate.
6. The flexible packaging structure of claim 1, wherein the heat seal region is parallel and adjacent an edge of the laminate.
7. The flexible packaging structure of claim 1, wherein the edge of the tab is continuous with the edge of packaging structure.
8. The flexible packaging structure of claim 1, wherein the edge of the tab is outside the boundaries of the laminate.
9. The flexible packaging structure of claim 1, wherein the edge of the tab is aligned with the edge of the packaging structure.
10. A flexible packaging structure, comprising:
 - a flexible packaging laminate comprising an outer structure adhesively laminated to an inner structure;
 - an opening and reclose feature formed in the laminate, and comprising an outer flap portion formed by scoring through the outer structure along an outer score line, and an inner flap portion formed by scoring through the inner structure along an inner score line, the inner score line creating an opening into the container when the flap portions are peeled back in a first direction, a marginal region of the outer flap portion extending beyond an edge of the inner flap portion and overlying an underlying surface of the inner structure, both portions being peeled back as a unit upon opening of the container; and
 - a tab defined by the outer line of weakness formed in the outer structure, such that the tab is disposed within a heat seal region of the packaging structure.
11. The flexible packaging structure of claim 10 wherein the tab is free from adhesion or lamination to the inner structure.
12. A method of making a flexible package comprising

applying a pressure-sensitive adhesive onto one surface of a first structure comprising at least one layer of flexible material;

adhesively joining the first structure to a second structure so as to form a laminate, the second structure comprising at least one layer of flexible material, wherein one of the first and second structures comprises an outer structure and the other comprises an inner structure;




advancing the laminate to a scoring station at which an outer score line is formed through the thickness of the outer structure and an inner score line is formed through the thickness of the inner structure in registration with the outer score line, the outer score line delineating a tab disposed within a heat seal region and an outer opening portion of the outer structure that is separable from the outer structure along the outer score line, the inner score line delineating an inner opening portion of the inner structure that is affixed to the outer opening portion and is separable from the inner structure along the inner score line, wherein a region of the outer opening portion between the outer and inner score lines is attached to an underlying surface of the inner structure via the pressure-sensitive adhesive, the outer opening portion being peelable from the underlying surface of the inner structure so as to cause the inner opening portion to also be peeled back to create an opening in the laminate, and the outer opening portion being re-attachable to the underlying surface of the inner structure via the pressure-sensitive adhesive for reclosing the opening; and

heat sealing the laminate in at least one heat seal region in which the tab is disposed, to create a package.

13. The method of claim 12, wherein the laminate is heat sealed on at least two opposite ends.

14. The method of claim 12, wherein the edge of the tab aligned with the edge of the package.

15. The method of claim 12, wherein the tab is free from adhesion or lamination to the inner structure.






FIG. 1a




FIG. 1b




FIG. 4




FIG. 5




FIG. 6




FIG. 7




Fig. 8






Fig. 9








Fig. 12






FIG. 15




FIG. 16A






FIG. 16B






FIG. 17C




FIG. 17D

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2018/046620

A. CLASSIFICATION OF SUBJECT MATTER

INV. B65D75/58 B29C59/00 B65D77/20
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B65D B29C B31B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2013/114091 A1 (CADBURY UK LTD [GB]) 8 August 2013 (2013-08-08)	1,5-15
Y	page 6, line 23 - page 19, line 26 figures 1-8	2-4
Y	----- EP 2 574 570 A1 (SONOCO DEV INC [US]) 3 April 2013 (2013-04-03) paragraph [0018] - paragraph [0060] figures 1-12	2-4
X	----- WO 2010/046623 A2 (CADBURY HOLDINGS LTD [GB]; WILLEY JASON DENIS [GB]; CHEEMA PARBINDER []) 29 April 2010 (2010-04-29)	1,5-15
Y	page 10, line 14 - page 19, line 5 figures 1-22	2-4
	----- -/-	



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

17 October 2018

Date of mailing of the international search report

13/11/2018

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Rodriguez Gombau, F

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2018/046620

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 2 243 716 A1 (SONOCO DEV INC [US]) 27 October 2010 (2010-10-27) paragraph [0016] - paragraph [0083] figures 1-9 -----	4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2018/046620

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2013114091	A1	08-08-2013	
		AU 2013213933 A1	21-08-2014
		CA 2861401 A1	08-08-2013
		CN 104080714 A	01-10-2014
		CO 7020892 A2	11-08-2014
		EP 2809591 A1	10-12-2014
		RU 2014129415 A	20-03-2016
		US 2015016756 A1	15-01-2015
		WO 2013114091 A1	08-08-2013
		ZA 201405540 B	23-12-2015
EP 2574570	A1	03-04-2013	
		AU 2009220068 A1	11-09-2009
		BR PI0908549 A2	29-09-2015
		CA 2717356 A1	11-09-2009
		EP 2257479 A1	08-12-2010
		EP 2574570 A1	03-04-2013
		ES 2402329 T3	30-04-2013
		JP 5778928 B2	16-09-2015
		JP 2011513153 A	28-04-2011
		JP 2014028660 A	13-02-2014
		MX 354584 B	12-03-2018
		US 2009226117 A1	10-09-2009
		US 2013056469 A1	07-03-2013
		US 2018257294 A1	13-09-2018
		WO 2009111153 A1	11-09-2009
WO 2010046623	A2	29-04-2010	
		AU 2009306181 A1	29-04-2010
		AU 2013257493 B2	21-04-2016
		BR PI0919800 A2	16-02-2016
		CA 2738321 A1	29-04-2010
		CN 102186743 A	14-09-2011
		EP 2349866 A2	03-08-2011
		EP 2769931 A1	27-08-2014
		ES 2512690 T3	24-10-2014
		ES 2606481 T3	24-03-2017
		PL 2769931 T3	31-03-2017
		RU 2011120182 A	27-11-2012
		RU 2014132059 A	20-02-2016
		US 2011253771 A1	20-10-2011
		WO 2010046623 A2	29-04-2010
		ZA 201103666 B	25-01-2012
EP 2243716	A1	27-10-2010	
		AR 049910 A1	13-09-2006
		AU 2005254459 A1	29-12-2005
		BR PI0510773 A	20-11-2007
		CA 2569646 A1	29-12-2005
		EP 1753670 A1	21-02-2007
		EP 2243716 A1	27-10-2010
		ES 2451624 T3	28-03-2014
		ES 2490218 T3	03-09-2014
		JP 4418495 B2	17-02-2010
		JP 2008502555 A	31-01-2008
		US 2005276525 A1	15-12-2005
		US 2010113241 A1	06-05-2010
		US 2011139363 A1	16-06-2011
		US 2012267386 A1	25-10-2012
		US 2017036836 A1	09-02-2017
		WO 2005123535 A1	29-12-2005