



(19) **United States**

(12) **Patent Application Publication**

Lien et al.

(10) **Pub. No.: US 2001/0040267 A1**

(43) **Pub. Date: Nov. 15, 2001**

(54) **SEMICONDUCTOR INTEGRATED CIRCUIT
WITH AN INSULATION STRUCTURE
HAVING REDUCED PERMITTIVITY**

Publication Classification

(51) **Int. Cl.⁷ H01L 29/00**

(76) **Inventors: Chuen-Der Lien, Los Altos Hills, CA
(US); S. K. Lee, Fremont, CA (US)**

(52) **U.S. Cl. 257/522**

Correspondence Address:

**Christopher B. Allenby
Skjerven Morrill MacPherson LLP
25 Metro Drive, Suite 700
San Jose, CA 95110 (US)**

(57) **ABSTRACT**


A first insulating layer (12) overlying semiconductor substrate (10) has a plurality of conductive paths (14, 16) disposed thereon. Each of the plurality of conductive paths has at least a major portion thereof overlaid with a second insulating layer (20). A third insulating layer (26), having air gap ports (28) formed therein, overlies adjacent conductive paths and extends from one to another such that an air gap (34) is formed. A passivation layer (30) overlies third insulating layer and seals the plurality of air gaps ports to form an insulation structure (40) for a semiconductor integrated circuit, and method thereof.

(21) **Appl. No.: 09/791,316**

(22) **Filed: Feb. 23, 2001**

Related U.S. Application Data

(63) **Continuation of application No. 08/775,345, filed on
Jan. 3, 1997.**






FIG. 1




FIG. 2




FIG. 3




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 4





FIG. 11





FIG. 12

SEMICONDUCTOR INTEGRATED CIRCUIT WITH AN INSULATION STRUCTURE HAVING REDUCED PERMITTIVITY

BACKGROUND

[0001] 1. Field of Invention

[0002] The present invention relates generally to semiconductor integrated circuits and methods of fabricating such circuits. More specifically, it relates to semiconductor integrated circuits with an insulation structure having an reduced permittivity incorporated therein.

[0003] 2. Description of the Prior Art

[0004] As integrated circuits are scaled to meet the need for both higher performance levels and more complex integrated circuit solutions, the result is increased circuit density. One scaling method used is shrinking a circuit's horizontal geometries, thus reducing the spacing between features. As features such as adjacent conductive paths are brought closer to one another, capacitive coupling between the paths can become a barrier to the scaling process.

[0005] Adjacent conductive paths can be viewed as a parallel plates of a capacitor and the insulating material between them as the capacitor's dielectric. As it is known, capacitance is a function of the permittivity of the insulator (ϵ_i) divided by the thickness of the insulator (x_i).

$$C = \epsilon_i / x_i$$

[0006] Thus capacitance increases between conductive paths, for any given dielectric material, as they are brought closer together by, for example, a scaling process. This increase in capacitance results in an increase in the RC time constant which, as it is known, causes a decrease in circuit speed. Additionally, increases in capacitance between adjacent conductive paths also result in increases in inductive noise or cross-talk between the adjacent conductors.

[0007] As the above mentioned equation indicates, when the spacing between conductors decreases the capacitance will increase unless the permittivity of the dielectric is lowered. However, lower permittivity is difficult to achieve due to the limited number of materials suitable for semiconductor processing. The most common dielectric material used is silicon dioxide with $\epsilon_i=3.9$ Faradays/centimeter (F/cm). Other common dielectrics such as silicon nitride have a higher permittivity and therefore are not useful for reducing the permittivity of the dielectric.

[0008] On the other hand, vacuum has a permittivity of 1.0 F/cm and air a slightly higher 1.001 F/cm. Thus isolating adjacent conductive paths with vacuum, air or with a hybrid structure including a substantial portion of vacuum or air would be a solution. In addition, for any solution that results in a lower permittivity to have broad applicability it would also be required to be structurally sound and readily integrated into a standard semiconductor process. While several proposals for isolating adjacent conductive paths with vacuum, air or a hybrid material have been made, none meets the aforementioned requirements.

[0009] An early effort at a solution is seen in U.S. Pat. No. 3,890,636 entitled "MULTILAYER WIRING STRUCTURE OF INTEGRATED CIRCUIT AND METHOD OF PRODUCING SAME" issued to Harada et al. on Jun. 17, 1975 and assigned to Hitachi, Ltd. of Japan. Harada et al.

teach a method that requires the formation of metal stanchions between each of the multiple layers of metal to isolate adjacent conductors. Thus the formation of this stanchion requires additional metal deposition, patterning and etching steps to form the stanchions. For a dual layer metal system, three metal depositions and three photolithographic steps are required rather than two depositions and two patterning steps. In addition, all conductive paths are free standing with no additional supporting structures to provide for strength. Therefore, Harada et al. teaches that thicker and wider conductive paths are required to provide this strength. As it can be seen, the method of Harada et al. requires extra, costly processing steps and wider conductors that are adverse to sizing.

[0010] In U.S. Pat. No. 4,933,743, entitled "HIGH PERFORMANCE INTERCONNECT SYSTEM FOR AN INTEGRATED CIRCUIT" issued to Thomas et al. on Jun. 12, 1990 and assigned to Fairchild Semiconductor Corp., a free standing structure is also taught. While Thomas et al. teach enclosing each conductor in a dielectric layer, that layer is primarily proposed to allow the open structure to be back-filled with a metallic material. Additionally, the dielectric layer surrounding the conductors adds little or no strength as it is supported by the metal rather than providing such support. Thus the structure of Thomas et al. does not provide the sound structure required unless additional costly processing is used, such as backfilling with a metallic material.

[0011] U.S. Pat. No. 5,119,164 entitled "AVOIDING SPIN-ON-GLASS CRACKING IN HIGH ASPECT RATIO CAVITIES" and issued to Sliwa Jr. et al. on Jun. 2, 1992, is directed to avoiding cracks in a spin-on glass (SOG) used as an insulating layer. The method teaches the deposition of a tungsten (W) layer as a peripheral coating for conductive metal stripes. After a spin-on glass is applied, the W is uncovered by, for example, etching back the spin-on layer. Subsequently the W is removed to form a void adjacent the metal stripe. Upon hard curing of the glass, this void increases in size due to densification of the SOG. While a void is formed, this method requires the deposition of an W layer and its subsequent removal. In addition, the void formed is unpredictable in its size and is easily filled in a multilayer device structure.

[0012] U.S. Pat. No. 5,310,700 entitled "CONDUCTOR CAPACITANCE REDUCTION IN INTEGRATED CIRCUITS" was issued to Chuen-der Lien et al. on May 10, 1994 and assigned to the same assignee of the present application, Integrated Device Technology, Inc. Lien et al. disclose a method for reducing the capacitance between a first and a second conductor on a semiconductor substrate. This patent is incorporated by reference herein. Lien et al. teach the formation of a cavity at an approximate midpoint between conductive stripes due to the effect of protrusions, formed at the top of the conductive stripes, upon the filling of the space between with an insulating material such as chemical vapor (CVD) deposited silicon oxide. While the method of Lien et al. is effective, it is both process and design layout dependent and requires forming an air gap independently for each layer.

[0013] U.S. Pat. No. 5,407,860 entitled "METHOD OF FORMING AIR GAP DIELECTRIC SPACERS BETWEEN SEMICONDUCTOR LEADS" was issued to

Stoltz et al. on Apr. 18, 1995. Stoltz et al. is directed to forming an air gap through the deposition of a non-wetting material, such as Teflon, as a thin layer overlying adjacent metal stripes. Stoltz et al. teach that upon deposition of an insulating material, the surface of the non-wetting material will not be wetted by the insulating material. In this manner, voids are formed. However, Stoltz et al. require a Teflon deposition process that is non-standard and thus difficult to incorporate into a semiconductor process flow. Additionally, the effect of the non-wetting surface is layout dependent making the size of the air gaps, if any, unpredictable.

[0014] Another method is taught in U.S. Pat. No. 5,461, 003 entitled "MULTILEVEL INTERCONNECT STRUCTURE WITH AIR GAPS FORMED BETWEEN METAL LEADS" issued to Robert H. Haverman on Oct. 24, 1995. Haverman teaches the etching of a disposable dielectric layer through a porous, overlying layer. A silica-based xerogel with a porosity range of between 10-50% is taught by Haverman to be an appropriate porous layer. As it is known, the deposition of such a porous layer is not a standard semiconductor process and the porosity is a function of the removal of the dispersion medium. Thus such a process is difficult to reproducibly perform and integrate with other standard semiconductor process steps. Additionally, as this is a porous layer, additional, non-porous material must be employed to provide "improved structural support and thermal conductivity, and passivat[ion of] the porous dielectric layer" (col. 6, ln. 12-13).

[0015] Japanese Patent No. 1-189939A entitled "SEMI-CONDUCTOR INTEGRATED CIRCUIT" and issued to Shigeru Murakami on Jul. 31, 1989, is directed to reducing capacitance between wiring on two different levels. Thus Murakami teaches forming an air gap between a lower wire 4 and an upper wire 7. Additionally this gap is formed by removing a photoresist layer using a release agent and anisotropic etching with CF_4 gas. Therefore upper wire 7 must be formed over the photoresist layer. Murakami teaches forming upper wire 7 over an existing photoresist layer, which, as it is known, can lead to contamination of the wiring layer. Additionally, Murakami teaches etching with a fluorine containing gas which is a well known etchant of silicon oxide, thus potentially compromising insulating layers formed thereof.

[0016] Japanese Patent No. 1-318248 entitled "SEMI-CONDUCTOR DEVICE AND MANUFACTURE THEREOF" issued to Takahiro Tsuchitani on Dec. 12, 1989, is directed to reducing the capacitance between an upper wiring level 5 and a lower wiring level 2 through the use of an air gap. Tsuchitani teaches that where an air isolation region 4 is beyond a certain dimension, support for upper wiring level 5 can be provided by forming struts 6. Thus Tsuchitani teaches forming an added structure requiring additional processing to provide for support of the upper wiring layer 5.

[0017] It can be seen that while a variety of methods of forming air gaps have been proposed, none provides for reduced capacitance between adjacent conductors on the same level, structural support for multilevel conductors, and easy integration into a semiconductor process flow.

[0018] Therefore a need exists for such a structure that provides for a reduced capacitance between adjacent conductive paths or a single level. A need also exists for a

reduced-capacitance structure that can provide structural support for multilevel conductors. Finally, a need exists for such a solution to be easily integrated into an existing semiconductor process flow.

SUMMARY

[0019] The present invention is directed to a method for forming an insulation structure for adjacent conductive paths in a semiconductor integrated circuit, wherein the structure has a permittivity substantially less than 3.9 F/cm. Additionally, the present invention is directed towards the specific structure formed by such a method.

[0020] The present invention provides adjacent conductive paths having substantially all of their sidewalls covered with an insulating layer. Additionally, according to the present invention a disposable layer is formed between the insulating layer covered sidewalls and another insulating layer is formed overlying the disposable layer and the conductive paths to provide structural support for multilevel conductive paths.

[0021] In addition, the present invention provides a method for the removal of a disposable layer to form an embodiment of a basic structure having a permittivity of less than 3.9 F/cm. This basic structure can be repeated any number of times to generate a multilayer metal integrated circuit. Prior to each repeated structure, or a final passivation layer, an array of openings is provided to allow removal of the disposable layer at a future process step.

[0022] Thus a basic structure is shown that is alternatively a building block or a final structure. In addition a method for creating same is also shown.

BRIEF DESCRIPTION OF THE DRAWINGS

[0023] FIGS. 1-3 and 5 are simplified cross-sectional views of a portion of an integrated circuit at various stages in the fabrication of an embodiment of the present invention;

[0024] FIG. 4 is a top-down view of the cross sectional view of FIG. 3;

[0025] FIGS. 6-8 are simplified cross-sectional views of a portion of an integrated circuit at various stages in the fabrication of another embodiment of the present invention

[0026] FIGS. 9 and 10 are simplified cross-sectional views of a portion of an integrated circuit at a stage in the fabrication of still another embodiment of the present invention;

[0027] FIG. 11 is a simplified cross sectional view of a portion of an integrated circuit at a stage in the fabrication of still another embodiment of the present invention; and

[0028] FIG. 12 is a top down view of the cross-sectional view of FIG. 11.

DETAILED DESCRIPTION

[0029] Embodiments of the present invention will be described with reference to the aforementioned figures. It will be understood that these drawings are simplified for ease of understanding and description only. Various modifications will become apparent to those skilled in the art as embodiments of the present invention are described. All such modifications or variations that rely upon the teachings

of the present invention, and through which these teachings have advanced the art, are considered to be within the spirit and scope of the present invention.

[0030] FIG. 1 is a simplified cross sectional view of a portion of an integrated circuit (IC) at an early stage of fabrication of an embodiment of the present invention. The portion illustrated includes a semiconductor substrate **10**, an insulating layer **12**, a pair of closely spaced first conductive paths **14** and a spaced apart conductive path **16**.

[0031] It will be understood that semiconductor substrate **10** has a plurality of regions (not shown) that contain a variety of semiconductor device elements such as transistors, diodes, resistors and the like as are well known in the art. For ease of illustration and understanding, a single region without such devices is shown throughout the illustrations contained herein.

[0032] First insulating layer **12** overlies substrate **10** and serves to electrically isolate conductive paths **14** and **16** from substrate **10**. Typically, insulating layer **12** is a thermally grown silicon oxide layer, although other insulating materials formed in other manners can also be used. For example silicon nitride or any of the various silicon oxynitrides can be formed in place of silicon oxide. In addition, combinations of thermally grown silicon oxide and deposited insulators can also be employed for first insulating layer **12**. Closely spaced conductive paths **14** and spaced apart conductive path **16** are disposed on layer **12**. Conductive paths **14** and **16** are typically aluminum or any of the commonly used aluminum alloys. However, paths **14** and **16** can alternatively include any of the conductive materials known to those skilled in the art of IC fabrication or combinations thereof. For example, paths **14** and **16** can be polysilicon or a metal silicide or a combination thereof as an alternative to aluminum or the like.

[0033] Referring now to FIG. 2, a conformal layer **20** or second insulating layer **20** is formed overlying substrate **10**. As conformal layer **20** completely covers insulating layer **12** and conductive paths **14** and **16**, and as no etching of conformal layer **20** is done to achieve such complete coverage, layers **12** and **20** can be formed from the same material. Therefore if layer **12** is silicon oxide, second insulating layer **20** can be formed from silicon oxide using, for example, a plasma enhanced chemical vapor deposition (PECVD) process. Alternatively, different materials for layers **12** and **20** can be selected. Thus where layer **12** is silicon oxide, a layer of silicon nitride or some other dielectric material can be employed for layer **20** and formed using any of the well known methods that produce an essentially conformal layer. Selection of a specific material for layer **12** and layer **20** is design choice within the spirit and scope of the present invention.

[0034] As it is known, several factors will influence the thickness of conformal layer **20**. These will include the actual material selected, the spacing between closely spaced paths **14**, whether or not additional layers of conductive paths will be formed overlying at least a portion of conformal layer **20**, and other considerations known to those of skill in the art. In a typical double layer metal integrated circuit, second insulating layer **20** is at least approximately 100 nanometers (nm) thick.

[0035] Once conformal layer **20** has been formed, disposable layer **24** is formed. Disposable layer **24**, in one embodi-

ment of the present invention, is a polyimide material or other organic material capable of withstanding subsequent processing steps without significant change or decomposition. In another embodiment, layer **24** is a spin-on-glass having a carbon concentration of at approximately 10 weight percent (wt. %) or greater, and in still another embodiment of the present invention disposable layer **24** is a phosphorous-doped glass material having a phosphorous concentration sufficient to allow removal of layer **24** while layers **20** and **26** are essentially not etched. For example, where either or both of layers **20** and **26** are an essentially undoped oxide material, a phosphorus concentration of approximately 3 wt. % or greater has been found desirable.

[0036] Disposable layer **24** can be formed by a first process to overlie all of substrate **10**, including conductive paths **14** and **16** and conformal layer **20**. Alternatively, layer **24** can be formed by a second process to fill only the area between adjacent conductive paths **14**, **16** and thus not overlie conductive paths **14**, **16**. Where the first process is employed, a subsequent etchback step, as is well known in the art, is performed to expose at least a top portion of conductors **14** and **16** as shown in FIG. 2. Thickness **25** of disposable layer **24**, either upon deposition or after an etchback process, is selected to be approximately equal to but no greater than that of conductive paths **14** and **16**. Thus if conductive paths **14** and **16** are aluminum with a thickness of 500 nm, thickness **25** will be approximately 400 to 500 nm, although thinner layers are also acceptable. It will be understood that where an etchback is required to arrive at an appropriate thickness **25**, as discussed above, that such an etchback process should not significantly etch layer **20**. Thus an etchback process will typically have a selectivity ratio of layer **24** to layer **20** of at least approximately 10:1.

[0037] Turning to FIG. 3, a third insulating layer **26** is formed overlying substrate **10** having a plurality of air gap ports **28** formed therein. In FIG. 4, a top down view of the cross sectional view of FIG. 3, a typical arrangement of air gap ports **28** is illustrated. Thus ports **28** are disposed between conductive paths **14** and **16** in an array. The specific number and location of air gap ports **28** is determined by the specific integrated circuit design and material selected for disposable layer **24**.

[0038] Returning to FIG. 3, third layer **26** is formed of any one of a variety of materials as previously described for second dielectric layer **20**. However, typically third layer **26** is selected to be the same composition as second layer **20** to facilitate formation of contact openings or vias as will be described with respect to another embodiment of the present invention.

[0039] A photoresist masking layer (not shown) is disposed over third layer **26** and patterned to expose selected regions of layer **26**. These selected regions are then etched to form air gap ports **28** and the masking layer is removed. It will be understood that the process selected for etching air gap ports **28** will depend upon the specific material selected for formation of third insulating layer **26**. Thus any one of the commonly known etch processes for dielectric or insulating materials such as silicon oxide or silicon nitride can be selected. For example where layer **26** consists of silicon oxide, ports **28** can be formed by etching in a plasma containing C₂F₆ gas.

[0040] Once air gap ports **28** are formed, disposable layer **24** is removed. As those of ordinary skill in the art will know,

it is possible to remove the aforementioned masking layer and disposable layer **24** in one step. Thus if layer **24** consists of organic material or carbon-containing SOG, as previously described, both layer **24** and the photoresist masking layer can be removed using an oxygen plasma etch. Such oxygen plasma etch processes are well known for stripping or etching organic materials in semiconductor processing. Thus said photoresist layer is removed from a surface of layer **26** while disposable layer **24** is removed through said air gap ports **28**. Other processes may also be employed, for example, an ultra violet induced ozone stripping process is also known and can be used to remove both layer **24** and the aforementioned photoresist masking layer. If disposable layer **24** consists of a heavily doped phosphorus containing glass, it can be removed by etching with a solution containing fluoride ions as is known in the semiconductor arts.

[0041] Referring to FIG. 5, air gaps **34** have been formed by removal of disposable layer **24** as previously discussed. As it can be seen, air gaps **34** are defined in a first direction, between adjacent conductive paths, by conformal layer **20** overlying sidewalls of each conductive path. In a second direction, air gap **34** is defined by layers **20** and **12** at lower boundary and third insulating layer **26** at an upper boundary. Thus a new insulation structure **40** is formed, disposed between adjacent conductive paths on a single level, from air gaps **34**, portions of conformal layer **20** and third insulating layer **26**. Inclusion of air gap **34** in structure **40** results in a reduced permittivity over that of, for example silicon oxide. Hence, capacitance between adjacent conductive paths will be reduced. A passivation layer **30** is formed overlying third layer **26** and covering or sealing air gap ports **28**. While some material of passivation layer **30** can enter air gaps **34** by means of air gap ports **28** during a deposition process, such filling can be minimized through design of ports **28** and selection of a deposition process for passivation layer **30**. Thus, as it is known, atmospheric deposition of silicon oxide will tend to close ports **28** well before any significant filling of gaps **34** occurs.

[0042] Thus by and through the above descriptions of FIGS. 1-5, an embodiment of the present invention has been disclosed. As seen in FIG. 5, air gaps **34** form a significant portion of insulation structure **40** disposed between conductive lines **14** and **16**. Therefore, as the capacitance of structure **40** is a function of the permittivity of each component of structure **40** divided by its thickness, and whereas the largest portion is air having a permittivity of 1.001 F/cm², it can be seen that capacitance has been greatly reduced from that of a solid silicon oxide insulator, and will be less than 3.9 F/cm².

[0043] Turning now to FIG. 6, another embodiment of the present invention is illustrated wherein the structure of FIGS. 1-5 is formed by an alternative method. For ease of understanding and comparison, similar features are labeled using the numbering of FIGS. 1-5. Thus FIG. 6 shows closely spaced first conductive paths **14**, and a spaced apart conductive path **16** disposed over insulating layer **12**, which in turn is disposed over semiconductor substrate **10**. However this embodiment employs a non-conformal insulating layer **200** disposed over and between conductive paths **14** and **16**.

[0044] Referring now to FIG. 7, insulating layer **200** has been etched back to form dielectric spacers **210** which

continue to overlie a major portion of conductive paths **14** and **16**. It will be understood that while layer **200** is shown formed into discrete spacers **210**, this is not essential. Thus spacers **210** can retain some connectivity overlying layer **12** as indicated by dashed lines **220** between conductive paths **14** and **16**. Additionally, spacers **210** can be formed where a portion or all of an upper surface of conductive paths **14** and **16** remain covered by layer **200**. Layer **200** can consist of a variety of insulating materials, for example silicon oxide, silicon nitride or the like. The specific material selected is a design choice determined by a variety of factors including, but not limited to, the spacing between conductive paths, the composition of layer **12** and both the etchback process and desired profile of spacers **210**. Any and all of these design choices are intended to fall within the spirit and scope of the present invention.

[0045] Turning now to FIG. 8, a structure at a subsequent process step is shown that is equivalent to the structure previously shown in FIG. 3. Thus disposable layer **24** has been formed as previously discussed with respect to FIG. 2, as has second insulation layer **26** and air gap ports **28**. While FIG. 8 shows layer **26** directly coupled to conductive paths **14** and **16**, where layer **200** remains overlying paths **14** and **16**, as previously mentioned, layer **26** is indirectly coupled to paths **14** and **16**. In this manner paths **14** and **16** provide physical support for layer **26**. It will be understood that additional structures, equivalent to FIGS. 4 and 5, can be formed for this embodiment of the present invention. In the manner previously taught, disposable layer **24** is etched through air gap ports **28**. In this manner, an insulating structure for this embodiment is formed which includes an air gap, as a principal component, as well as spacers **210** and second insulating layer **26**. It will be understood that if spacers **210** are not formed as fully separated spacers **210**, but rather spacers **210** connected as indicated by hatched line **220**, then this additional material will be included in the insulation structure. Therefore, an alternative embodiment of the present invention shown has been shown where a capacitance significantly less than 3.9 F/cm² is provided.

[0046] Other embodiments of the present invention are also possible. Now turning to FIG. 9, an embodiment of the present invention is shown where air gaps are disposed between adjacent conductive paths **52** and **54** that form a second or upper conductive layer. As will be seen, no air gaps are formed on a lower conductive layer containing paths **14** and **16**. It will be noted that FIG. 9 is analogous to previously discussed FIG. 3.

[0047] Semiconductor substrate **10** is shown with insulating layer **12** disposed thereon. Closely spaced conductive paths **14** and spaced apart conductive path **16** are formed as previously discussed. However, rather than forming insulating structure **40**, a standard insulating structure **44** is formed. Structure **44** is illustrated as having vias **46** formed therein to provide for electrical coupling of conductors **52** and **54** to conductors **14** and **16**, respectively. The manner of forming vias **46** is well known in the semiconductor arts and not essential to this embodiment of the present invention.

[0048] As shown, second conformal layer **60** is formed overlying conductors **52** and **54**. Second conformal layer **60** can be formed using methods and materials as discussed previously with respect to conformal layer **20**. In addition, the thickness of second conformal layer **60** is a design choice

as previously discussed for layer 20; however, a typical thickness employed is approximately 100 nm. Second disposable layer 64, shown disposed between conductors 52 and 54, is formed in a manner, and of materials discussed previously with respect to disposable layer 24. As was indicated in the discussion of thickness 25, thickness of disposable layer 64 is also important. Therefore it will be understood, that second disposable layer 64 is analogous to layer 24 and has a thickness no greater than a thickness of conductive paths 52 and 54.

[0049] Fourth insulating layer 56 is disposed overlying conductive paths 52 and 54 and disposable layer 64. Layer 56 is formed in a manner, and of materials, as discussed previously with respect to third insulating layer 26. A second air gap port 58 is formed in insulating layer 56 in a manner as discussed with respect to air gap ports 28 employing a photoresist masking layer (not shown). While only one second air gap port is illustrated, it will be understood that this is for simplicity of illustration and understanding only. In an actual embodiment, many second air gap ports 58 are typically formed. Once air gap port 58 is formed, disposable layer 64 can be removed. It is possible to remove the aforementioned masking layer and disposable layer 64 in a single process step as previously discussed.

[0050] FIG. 10 illustrates this embodiment of the present invention where disposable layer 64 has been removed to form second air gap 74. Additionally, passivation layer 30 has been formed overlying substrate 12 and in particular fourth insulating layer 56, thus sealing air gap port 58. Thus, a second insulation structure 80 is formed that is analogous to embodiments of insulation structure 40 previously discussed. The benefits of reduced capacitance and structural integrity are therefore enjoyed in this alternative embodiment.

[0051] Still other embodiments of the present invention are possible. Thus an integrated circuit may be formed that incorporates an insulating structure of the present invention for both a first level of conductive paths and a second level of conductive paths. Such a structure is illustrated in FIGS. 11 and 12. FIG. 11 illustrates a simplified cross-sectional view of this multilevel embodiment and FIG. 12 illustrates a top down view of FIG. 11. It will be understood that the structures and methods previously taught are used to fabricate the structure depicted in FIGS. 11 and 12. However, it should be realized that air gap 34 of insulating structure 40 and second air gap 74 of second insulating structure 80 are formed with one process step. Referring to FIG. 12, it can be seen that this is possible without regard to placement of second level conductive paths where a sufficient array of air gap ports 28 and 58 are provided. Thus in FIG. 12 air gap ports 58 are represented having solid lines and air gap ports 28 having dashed lines. It will be understood that both FIGS. 11 and 12 are simplified drawings created for ease of understanding and description only. Therefore, air gap ports 28 and 58 can align as shown or can not align. Additionally, in some embodiments insulation structure 80 is aligned to insulation structure 40 and in other embodiments these structures are not aligned. Finally, in some embodiments a mixture of aligned and non-aligned structures such as air gap ports 28 and 58 or insulation structures 40 and 80 are possible. Such alignment and non-alignment of structures described or illustrated herein are understood to be design choices within the scope and spirit of the present invention.

[0052] Thus several embodiments of a new insulation structure having a reduced permittivity and superior structural integrity have been shown. In addition, several embodiments of methods for fabricating the new insulation structures have also been demonstrated.

[0053] The new insulation structure includes a significant amount of air thus significantly reducing the permittivity of the structure. This reduction in permittivity of the insulation structure will create a corresponding reduction-in capacitance. As a result, the RC time constant and level of cross-talk between adjacent conductive paths is reduced. Additionally, the new insulation structure provides an insulation layer having air gap ports formed therein. It will be realized that this insulation layer overlies conductive paths which provide physical support for the layer. By providing an array of air gap ports formed in this insulating layer, the layer can remain essentially continuous and thus retain sufficient structural strength to take advantage of the physical support provided by the underlying conductive paths. In this manner it is possible to support additional layers of insulating and conductive materials. Finally, the method of forming the insulating structures of the present invention allows all air gaps within such insulating structures to be formed in a single process step.

What is claimed is:

1. A semiconductor integrated circuit with an insulation structure having a reduced permittivity, said insulation structure comprising;

- a first insulating layer overlying a semiconductor substrate;
- a plurality of conductive paths overlying said first insulating layer;
- a second insulating layer overlying at least a major portion of adjacent conductive paths;
- a third insulating layer overlying each adjacent conductive path and extending from one to another;
- an air gap defined in a first direction by said second insulating layer overlying sidewalls of each adjacent conductive path and in a second direction by a lower boundary of said first and/or second insulating layer and at an upper boundary by said third insulating layers; and
- a plurality of air gap ports formed in said third insulating layer wherein each air gap port is positioned between adjacent conductive paths whereby a disposable material is removed through said plurality of air gap ports.

2. The semiconductor integrated circuit of claim 1 further comprising a passivation layer overlying said third insulating layer wherein said passivation layer seals said plurality of air gap ports.

3. The semiconductor integrated circuit of claim 1 wherein said first insulating layer is comprised of silicon oxide.

4. The semiconductor integrated circuit of claim 1 wherein said first and said second insulating layers are comprised of substantially different materials.

5. The semiconductor integrated circuit of claim 4 wherein said second insulating layer is comprised of silicon nitride or silicon oxide.

6. The semiconductor integrated circuit of claim 1 wherein said second insulating layer and said third insulating layer are comprised of substantially the same material.

7. The semiconductor integrated circuit of claim 1 wherein said third insulating layer is comprised of silicon nitride or silicon oxide.

8. The semiconductor integrated circuit of claim 1 wherein said second insulating layer is a conformal layer.

9. The semiconductor integrated circuit of claim 1 wherein said second insulating layer further comprises spacers adjacent a sidewall of each conductive path.

10. The semiconductor integrated circuit of claim 1 wherein said first insulating layer overlies a first interconnect layer.

11. The semiconductor insulated circuit of claim 1 wherein said insulation structure has a permittivity less than 3.9 F/cm².

12. A method of fabricating a semiconductor integrated circuit having an insulating structure with reduced capacitance comprising the steps of:

forming a first insulating layer overlying a semiconductor substrate;

forming a plurality of conductive paths overlying said first insulating layer wherein each of said conductive paths has a first thickness;

forming a second insulating layer overlying said first insulating layer and at least a major portion of each of said conductive paths;

forming a disposable layer overlying said second insulating layer at least adjacent said conductive paths, wherein said disposable layer has a second thickness no greater than said first thickness;

forming a third insulating layer overlying said semiconductor substrate wherein said third insulating layer is coupled to each of said conductive paths and said disposable layer;

forming a plurality of air gap ports in said third insulating layer wherein said plurality of air gap openings are disposed between adjacent conductive paths; and

removing said disposable layer wherein an air gap is formed.

13. The method of fabricating an integrated circuit of claim 12 further comprising the step of forming a passivation layer overlying said third insulating layer wherein said air gap opening are sealed.

14. The method of fabricating an integrated circuit of claim 12 wherein the step of forming a first insulating layer comprises forming an insulating layer comprised of silicon oxide or silicon nitride.

15. The method of fabricating an integrated circuit of claim 12 wherein the step of forming a plurality of conductive paths comprises forming a layer comprised of aluminum or polysilicon.

16. The method of fabricating an integrated circuit of claim 12 wherein the step of forming a second insulating layer comprises forming a conformal layer comprised of silicon oxide or silicon nitride.

17. The method of fabricating an integrated circuit of claim 12 wherein said first insulating layer and said second insulating layer are comprised of substantially different materials.

18. The method of fabricating an integrated circuit of claim 12 wherein said first insulating layer and said second insulating layer are comprised of substantially the same material.

19. The method of fabricating an integrated circuit of claim 12 wherein the step of forming a disposable layer comprises forming a layer from a material selected from the group including a carbon containing spin on glass, a polyimide material and a heavily doped phosphorous containing glass.

20. The method of fabricating an integrated circuit of claim 19 wherein said carbon containing glass has a carbon concentration of at approximately 10 percent or greater.

21. The method of fabricating an integrated circuit of claim 19 wherein said heavily doped phosphorus containing glass has a phosphorus concentration of at approximately 3 percent or greater.

22. The method of fabricating an integrated circuit of claim 12 wherein the step of forming a third insulating layer comprises forming an insulating layer comprised of silicon oxide or silicon nitride.

23. The method of fabricating an integrated circuit of claim 12 wherein said second insulating layer and said third insulating layer are comprised of substantially the same material.

24. The method of fabricating an integrated circuit of claim 12 wherein the step of removing said disposable layer comprises removing said disposable layer through said air gap ports.

25. The method of fabricating an integrated circuit of claim 24 wherein the step of removing said disposable layer comprises etching said disposable layer with an oxygen plasma.

26. The method of fabricating an integrated circuit of claim 24 wherein the step of removing said disposable layer comprises etching said disposable layer with a solution containing fluoride ions.

* * * * *