

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 December 2003 (18.12.2003)

PCT

(10) International Publication Number
WO 03/103639 A1

- (51) International Patent Classification⁷: A61K 9/48, 9/64, 9/66 (74) Agent: NICKEY, Donald, O.; Cardinal Health, Inc., 7000 Cardinal Place, Dublin, OH 43017 (US).
- (21) International Application Number: PCT/US03/17746 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 6 June 2003 (06.06.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 2002-167041 7 June 2002 (07.06.2002) JP (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): R.P. SCHERER TECHNOLOGIES, INC. a Nevada Corporation [US/US]; 2030 East Flamingo Road, Suite 260, Paradise Valley, NV 89119 (US).

- (72) Inventors; and
(75) Inventors/Applicants (*for US only*): MAKINO, Hirokazu [JP/JP]; 1-16-14, Shimomataminami, Kakegawa City, Shizuoka Prefecture, Postal Code 436-0026 (JP). SUMINO, Yoko [JP/JP]; 2-23-9, Kamenokou, Kakegawa City, Shizuoka Prefecture, Postal Code 436-0028 (JP). SUZUKI, Hideo [JP/JP]; 84-1 Umebashi, Kakegawa City, Shizuoka Prefecture, Post Code 436-0034 (JP). MASTUSHITA, Tomohisa [JP/JP]; 1521-1 Mituke, Iwata City, Shizuoka Prefecture, Post Code 436-0086 (JP).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CHEWABLE SOFT CAPSULE

(57) Abstract: A soft gelatin capsule agent and capsule made with the agent. Gelatin, typically derived from fish sources, and having sol-gel transition temperatures within certain parameters, is formulated with at least one plasticizer and at least one anti adhesion agent. Another preferred embodiment includes partially pregelatinized starch. The plasticizer may comprise polyols, particularly glycerin, sorbitol, and mixtures thereof. The anti-adhesion agent may comprise starch. Colorants may be optionally added to the mixture. The shell of the capsules manufactured from the agent may have varied water content and may optionally receive a surface coating of dusted material, typically starch, and more particularly potato or corn starch, to reduce the tendency of the capsules to stick to one another during storage. The capsules may be filled with a wide range of foodstuffs, medicaments, and other substances.



WO 03/103639 A1

CHEWABLE SOFT CAPSULES**PRIORITY CLAIM**

This application claims priority to Japanese Patent Application No.
2002/167,041 filed June 7, 2002.

TECHNICAL FIELD

The instant invention relates to soft gelatin capsule agents and capsules,
5 particularly to an agent for making soft gelatin capsules and a dusted soft fish gelatin
capsule for encapsulating medication or other consumables, exhibiting excellent
texture and chewability qualities, as well as excellent storage qualities.

BACKGROUND OF THE INVENTION

10 Experience has long shown that pharmaceuticals or other items for human or
animal consumption may be safely packaged in a hard or soft gelatin shell. Gelatin is
a substantially pure protein food ingredient, obtained by the thermal denaturation of
collagen, which is the most common structural material and most common protein in
animals. Gelatin forms thermally reversible gels with water, which gives gelatin
15 products unique properties, such as reversible sol-gel transition states at near
physiologic temperatures.

Gelatin is an amphoteric protein with an isoionic point between 5 and 9,
depending on raw material and method of manufacture. Type A gelatin, with an
isoionic point of 7 to 9, is derived from collagen with acid pretreatment. Type B

gelatin, with an isoionic point of 4.8 to 5.2, is the result of alkaline pretreatment of the collagen. Like its parent protein collagen, gelatin is unique in that it contains, approximately, 16 % proline, 26 % glycine, and 18% nitrogen. Gelatin is not a complete protein food because the essential amino acid tryptophan is missing and the amino acid methionine is present only at a low level.

There are a large number of processes used in the manufacture of gelatin and the raw materials from which it is derived, including demineralized bone, pigskin, cow hide and fish. The proteinaceous material, collagen, and hence gelatin, can be derived from any edible protein containing material. For reasons of economy, gelatin can be most practically be derived from protein sources which would normally require refining before consumption and which would otherwise make up protein-containing waste material destined for animal feeds, agricultural fertilizers, or for other industries. However, in many cultures and areas of the world, gelatin processed from mammalian origins, that is, from beef or pigs, is not acceptable.

In the fish industry, there is considerable and unavoidable waste of fish protein, especially from the fish skins that remain after processing. The fish skin which remains after processing, especially filleting, is generally inedible as such, but can be used in the glue industry or for the manufacture of animal foodstuffs, fertilizers or other commodities of low commercial value.

However, fish skins have become a vital commercial source of gelatin. In general, the fish collagen is acidified to about pH 4 and then heated stepwise from 50° C to boiling to denature and solubilize the collagen. Then, the denatured collagen or

gelatin solution has to be defatted, filtered to high clarity, concentrated by vacuum evaporation or membrane ultra-filtration treatment to a fairly high concentration for gelation, and dried by passing dry air over the gel. Finally, the dried gelatin is ground and processed into powder. The resulting gelatin has an isoionic point of 7 to 9 based
5 on the severity and duration of the acid processing of the collagen which causes limited hydrolysis of the asparagine and glutamine amino acid side chains. Pharmaceutical and other agents can be encapsulated in either a hard or soft gelatin shell. Hard gelatin capsules are filled with dry materials such as powders or time-release beadlets by introducing the material into one section of a capsule and capping
10 it with a second section.

Gelatin capsules may be classified as hard or soft, with a sub-classification, that of chewable capsules, within the soft class. Various plasticizing and hardening agents are added to the gelatin used to make capsules or microcapsules. The shell of a hard capsule is not plasticized, while a soft gelatin capsule is plasticized, often with
15 Glycerol (glycerin), a plasticizer that is very widely used to make soft gelatin capsules. Other plasticizers used with, or instead of, glycerol include various alcohols, propylene glycol, sucrose, and acacia. Sorbitol is the most widely used alcohol, but other alcohols have been explored, including various polyethylene glycols (PEGs), mannitol, ethylene glycol, and tetrahydrofuryl alcohol. Various starches can be used as
20 disintegrants, to promote break-up of the capsule, and to improve adhesion of a secondary coating. Hard capsules may use aldehydes to cross-link and stiffen the structure of gelatin.

For human consumption, hard capsules are designed to be swallowed with dissolution of the capsule and absorption of the capsule contents in the gastrointestinal tract. While gelatins for the manufacture of hard gelatin capsules were traditionally obtained from mammalian tissues, U.S. Pat. App. Pub. No. 2001/0024678 details the
5 manufacture of hard capsules from fish gelatin by means of adding a setting system comprising a hydrocolloid or mixtures of hydrocolloids and cations which may contain additional sequestering agents.

Soft gelatin capsules generally consist of a gelatin shell which is produced by casting a mixture of gelatin, plasticizer, and water into a thin sheet. The shell of a soft
10 gelatin capsule is typically produced by adding, to a gelatin, a plasticizer in an amount of 30-40 wt % with respect to the gelatin, and drying the shell until the water content becomes 5-10 wt % so as to prevent the capsule from being deformed or becoming undesirably sticky. In some typical formulations, as seen in U.S. Pat. No. 5,554,385 to Stroud, a portion of the gelatin is replaced with a high amylose starch to provide a dry
15 capsule sheath.

The soft gelatin capsule of such a formulation is relatively tough for optimal storage and handling, and is intended to dissolve after reaching the intestines so as to release its contents therein. Therefore, the capsule is not easily broken in the mouth and is not suitable for chewing.

20 Accordingly, while such gelatin capsules are comestible, they are not "edible" as the term is commonly used, to denote a material that is chewable or dissolvable in the mouth without unpleasant taste or texture sensations. The soft gelatin based

compositions commonly employed to form the shells of soft gelatin capsules often yield a gummy, unpleasant, intractable mass in the mouth. However, a gelatin shell which is chewable and edible in the sense that it is pleasant tasting and can be readily fragmented, dissolved, and swallowed, would be advantageous from a number of
5 perspectives.

For example, a person who is in medical distress from the sudden attack of a condition such as angina pectoris could achieve rapid release of the active ingredients of a capsule into the body with a truly chewable capsule. Ideally, the shell of the capsule would dissolve rapidly, without leaving any intractable, insoluble residue
10 upon which the user might choke. In other applications, a chewable capsule can provide a convenient dosage form. Children, elderly, and other users often have difficulty swallowing pills or capsules, particularly without supplemental water to drink. In non-medical applications, a chewable capsule could contain, by way of example and not limitation, confectionary or breath freshening products in an easy to
15 carry and use form.

Different routes have been used in the art to achieve the goals of a truly edible chewable gelatin capsule. For example, it is well know in the art, as described in U.S. Pat. No. 6,280,767 to Sano, et al. that increasing the amount of plasticizer, will increase the softness of the capsule. However, increasing plasticizer content is
20 associated with an increased likelihood of a capsule sticking to another soft gelatin capsule or to a container, thereby causing deterioration in storage stability and damaged product. This is particularly true in high-temperature, high-humidity areas.

Additionally, an increase in stickiness caused by increased plasticizer content creates a capsule that is more likely to stick to the teeth during mastication, an unpleasant tactile experience.

To compensate for the increased stickiness of high plasticizer formulations, one approach, seen in the '767 patent, is to supply a water insoluble cellulose in the capsule formulation. However, this leads to the unpleasant production of an insoluble residue in the mouth after chewing.

Another means to increase the softness and dissolution characteristics of a soft gelatin capsule is to increase the water content of the capsule, as seen in U.S. Pat. No. 4,935,243 to Borkan, et al. In contrast to the conventional gelatin capsule with a water content of about 7%, Borkan et al. teaches a water content of 15-30 wt %. Higher water content is also employed in U.S. Pat. No. 2,580,683 to Krueger, which discloses capsule shells of gelatin, sugar and a minimum of about 34% water. A shell composition of about 45% water is also disclosed by Krueger '683. While increasing water enables a decrease in the amount of plasticizer employed, for example to approximately 25% in the '243 patent, high water content can result in capsule deformation, stickiness and storage problems.

Accordingly, the art has needed a chewable soft gelatin capsule that exhibits excellent texture and taste characteristics when chewed, does not leave an insoluble residue in the mouth, and has optimum moisture content and melting characteristics, and possesses excellent storage characteristics.

SUMMARY OF THE INVENTION

The instant invention provides a novel agent for manufacturing a soft gelatin capsule, and for capsules made with the agent. The capsules have excellent “mouth feel”, are easily dissolvable, and produce no residue when chewed. The capsules also
5 perform well under storage conditions. The utilization, in some embodiments, of fish gelatin, is hoped to increase consumer acceptance in cultures that reject the use of mammalian gelatin.

In sum, the instant invention includes a soft gelatin capsule agent comprising a gelatin having a sol-gel transition temperature in a 10 wt.% aqueous solution of not
10 more than 22° Centigrade and a sol-gel transition temperature in a 30 wt.% aqueous solution of not more than 32° Centigrade, a plasticizer, and an anti-adhesion agent. The most desirable sol-gel transition temperatures lay between 15° and 20° C for a 10% aqueous solution and between 25° and 30° C for a 30% aqueous solution. Sol-gel transition temperatures are determined by a water bath assay detailed below.

15 The plasticizer may be a polyol, particularly a polyol selected from the group consisting of glycerin, sorbitol, or mixtures thereof. One skilled in the art will realize that a number of plasticizers may be used in gelatin capsule formation, including by way of example and not limitation; polyethylene glycol, sucrose, mannitol, corn syrup, fructose, cellulose, dioctyl-sodium sulfosuccinate, triethyl citrate, tributyl
20 citrate, 1,2-propylenglycol, mono-, di- or triacetates of glycerol, natural gums or the like as well as mixtures thereof. The anti-adhesion agent typically contains at least

one starch, and the at least one starch may be corn starch. The capsule may be formulated with varying amounts of water and colorants.

In a preferred embodiment, the capsule agent comprises a mixture of 100 parts by weight of the selected gelatin, comprises between 100 and 130 parts by weight of plasticizer, and between 10 and 45 parts by weight of anti-adhesion agent. In another preferred embodiment, the mixture also contains partially pregelatinized starch, typically comprising 10 to 30 parts by weight of the mixture.

Optimally, the resulting capsule comprises a soft gelatin shell which comprises between about 36 wt.% and about 47 wt.% gelatin having a sol-gel transition temperature in a 10 wt.% aqueous solution of not more than 22° Centigrade and a sol-gel transition temperature in a 30 wt.% aqueous solution of not more than 32° Centigrade, about 47 wt.% plasticizer, and between about 4 wt.% and about 16 wt.% anti-adhesion agent; and a soft gelatin capsule fill material. The fill material may be selected from a near limitless array of foodstuffs, medicaments, and other substances.

The shell is typically formulated with water, which comprises between about 8 wt.% and about 25 wt.% of the soft capsule shell. The capsule may further comprise a surface coating applied to the exterior of the soft gelatin shell to decrease surface stickiness. The surface coating typically includes at least one starch, which may be a potato or a corn starch.

BRIEF DESCRIPTION OF THE DRAWINGS

Without limiting the scope of the present invention as claimed below and referring now to the drawings and figures:

FIG. 1 shows a graph of the data presented in Table 8, showing the results of subjective texture evaluation over a period of six months for capsules made according to the instant invention.

FIG. 2 shows a graph of the data presented in Table 10, showing the results of subjective texture evaluation over a period of four months for capsules made according to the instant invention.

FIG. 3 shows a graph of the data presented in Table 11, showing the results of subjective texture evaluation over a period of four months for capsules made according to the instant invention.

DETAILED DESCRIPTION OF THE INVENTION

The art is well acquainted with the use of fish gelatin to form various types of hard and soft gelatin capsules. Initial experimentation sought to identify those gelatins, which in formulation with a plasticizer, starch, colorant, and sweetener, might have the desired qualities of a good mouth feel, firm chewiness without excessive hardness, excellent storage characteristics, and also be susceptible to mass production techniques for capsule manufacture. The glycerin used was Japan Food Additive Standard JFAS (Japan Food Additive Standard) 99.5 grade and the corn starch was Hohnen HS-7 high amylose corn starch.

Formulations were tested by compounding mixtures, as specified in Table 1, casting the material in a sheet 0.7-1 mm thick, and then dividing the sheet into units 1 cm square. A panel of tasters assessed the samples for seven parameters; softness, easy dissolving, elasticity, powder or granular texture, chewiness, saliva stimulation, and sol-gel nature (subjective feeling of the liquidity of the compound) on a scale wherein 0 represent neutral judgments, while negative values and positive values represented departures from a neutral value.

As summarized in Table 1, five commercially available mammalian (Nitta S#195A Acid Gel, Miyagi RP-600 Modified Gel, and Nitta SCP -5000 Collagen Peptide) and fish (Miyagi MPM Shark Fish Gel and Croda 200 B Fish Gel) gelatins provided reasonable performance to taste, but not to production parameters. Nitta S#195A Acid Gel is a mammalian derived gelatin produced from acid treated bovine bone, having a Bloom strength of 210-240. Miyagi RP-600 Modified Gel is a

mammalian derived gelatin produced by the reaction of succinic anhydride and alkali treated bone gelation, having a Bloom strength of 180-200. Nitta SCP-5000 Collagen Peptide is a hydrolyte of mammalian derived gelatin produced from acid treated porcine skin. Among the fish gelatins, Miyagi RPM Shark Fish Gel is a shark derived
5 gelatin having a Bloom strength of 110-140. Croda 200B Fish Gel is derived from fish and has a Bloom strength of 195-210. In the experimentation described below, the Croda 200B Fish Gel had a measured Bloom strength of 207.

Specifically, the gelatins tested above, exhibited adequate, although somewhat sticky texture and feel to consumers, were excessively soft and sticky for machine
10 capsule formation, making them unlikely candidates for either mass production or prolonged storage, and therefore represented inadequate commercial solutions. The shark gel produced the best subjective texture to a taste panel, but experiments 3A and 3B, as seen in Table 1, utilizing Croda 200B Fish Gel, produced the most promising combination of subjective texture and commercial handling qualities.

No.	Gelatins					Water
	Acid Gel	Modified Gel	Collagen Peptide	Fish Gel	Fish Gel	
	Nitta Acid Gel	Miyagi RP-600	Nitta SCP-5000	Miyagi MPM Shark	Croda 200B	
1		100				63
		100				113
		100				90
		100				80
		100				80
2	90		10			63
	90		10			60
	90		10			55
	90		10			58
	90		10			58
3				100		63
				100		131
				100		110
				100		100
				100		98
3A					100	100
					100	63
					100	75
					100	81
3B					100	80
					100	85

Table 1 (all samples 120 parts glycerin, 42 parts corn starch, 1 part TiO₂, 5 parts aspartame)

5 All assessed as adequate to taste assessment, but too sticky for machine production.

Accordingly, experimentation was directed to decreasing the soft and sticky nature of the gelatin mixtures by combining them with various plasticizers. Typical results are reported in Table 2. In the protocol reported, all samples consisted of an added 42 parts corn starch, 1 part titanium oxide (colorant) and 5 parts aspartame, to
5 approximate the additives most likely to be included in a commercial product. Additional additives besides the JFAS 99.5 Glycerin and corn starch previously mentioned included Propylene Glycol manufactured to Japan Food Additive Standard (JFAS) by Asahi Chemical, and Xylitol manufactured by Towa Chemical Industry Ltd., and marketed as XylitXC.

10 Glycerin, as a plasticizer, alone and in combination with propylene glycol, and glycerin in combination with Xylitol, produced good dissolution. Attempts to utilize additional additives, such as cellulose (Asahi Kasei Abcel RC-N Crystalline Cellulose, composed of 80% crystalline cellulose, 10% karaya gum, and 10%
15 dextrin), SiO₂ (JFAS grade; Fuji Chemical Cycolpege 720), and NaHCO₃ (JFAS grade; Asahi Kasei) failed to produce significant improvements in performance, as reported in Table 3. However, the addition of partially pregelatinized starch, which is known in the art to have good dissolution qualities, to a mixture of gelatin and glycerin improved mouth feel and produced good dissolution of the capsule agent at various water levels, as shown in Table 4. One particular type of partially
20 pregelatinized starch, Asahi Kasei PCSD FW-40 partially pregelatinized starch made from wheat, performed well.

Due to the promising texture tasting performed earlier with fish gelatin, attention was directed to optimizing combinations of glycerin and partially pregelatinized starch, along with fish gelatin, particularly the Croda fish gelatin which was seen to produce good results. The results are reported in Table 5. It was believed
5 that the addition of an additional anti-adhesion agent might result in improved performance.

	Acid Gel	Glycerin	Propylene Glycol	Xylitol	Water
No.	Nitta S#195A	JFAS 99.5	Asahi	Towa Xyl itXC	
4	100	60	60		80
	100	60	60		70
	100	60	60		65
5	100	116	4		80
	100	116	4		63
	100	116	4		78
6	100	90			68
	100	90			80
	100	90			83
7	100	90		30	68
	100	90		30	77
	100	90		30	83
8	100	86	4		63
	100	86	4		85
	100	86	4		65
	100	86	4		75

5 **Table 2** – (all samples 42 parts corn starch, 1 part TiO, 5 parts aspartame)

No.	Gelatin		Plasticizer	Additives			
	Acid Gel	Collagen Peptide	Glycerin	Cellulose Crystalline	SiO2	NaHCO3	Water
	Nitta S#195 A	Nitta SCP-5000	JFAS 99.5	Asahi Kasei Abcel RC-N81	Fuji Silisia Cylopege 720	Asahi Kasei	
9	50	50	120	1.5			63
9A	70	30	120	1.5			63
	70	30	120	1.5			68
11	100		120		5		63
	100		120		5		73
13	100		44			1.7	63
	100		120			1.7	63
	100		120			1.7	73

5 **Table 3** – (all samples 42 parts corn starch, 1 part TiO, 5 parts aspartame)

No.	Acid Gelatin	Plasticizer	Partial Pregelatinized Starch		Water
	Nitta S#195A	JFAS 99.5	Asahi Kasai PCSD FC-50	Asahi Kasai PCSD FW-40	
15	100	120		42	100
15A	100	120		42	100
15B	100	120		42	105
15C	100	120		42	125

Table 4 – (all samples 1 part TiO₂, 5 parts aspartame)
All observed to be easy to dissolve

	Gelatin	Plasticizer			
No.	Croda 200B	Glycerin JFAS 99.5	Partial Pregelatinized Starch Asahi Kasei PCSD FW-40	Water	Comments
16	100	120	42	100	Compared to 3A brittle and difficult to encapsulate
	100	120	42	105	
	100	120	42	125	
17	100	100	42	115	Compared to 16, sticky and judged encapsulation difficult
	100	100	42	125	
18	100	80	42	130	Compared to 17, sticky and judged encapsulation difficult

Table 5 – (all samples 1 part TiO, 5 parts aspartame)

5

The addition of additional starch, in the form of Hohnen HS-7 high amylose corn starch, along with the partially pregelatinized starch of the previous experiments, resulted in the optimal capsule formulations, as shown in Table 6. Additionally, it was discovered that a key characteristic necessary to create capsules of both good
5 subjective mouth feel and mass production characteristics lay in the sol-gel temperature characteristics of the gelatin used.

Sol-gel and gel-sol transition temperatures were assayed according to the following protocols. To assess gel-sol (solid to liquid) transition temperatures, gelatin solutions are cast in a test tube and maintained well below physiologic transition
10 temperatures, in this case at 10° C. A lead shot is placed on the surface of the firm gelatin, which due to its gel nature is capable of holding the weight of the shot. The test tube is placed in a water bath and gradually raised in temperature at the rate of 12° C per hour. The process is carefully observed while heating, and the gel-sol transition temperature, or melting point, is the temperature at which the gelatin
15 liquefies sufficiently such that the shot drops to the bottom of the test tube.

Conversely, the sol-gel (liquid to solid) transition temperature is determined as follows. Gelatin solutions are placed in a test tube at temperatures well above physiologic transition temperature, in this case at 60° C. The test tube is placed in a water bath and gradually lowered in temperature at the rate of 12° C per hour. The
20 process is carefully observed while cooling, and the sol-gel transition temperature, or setting point, is the temperature at which the gelatin hardens sufficiently such that an

adherent droplet forms on a stirring rod immersed and then withdrawn from the solution.

Gelatin formulations with acceptable characteristics were found to have a relatively narrow range of acceptable sol-gel transition temperatures. That is, optimal subjective mouth feel and mass production characteristics occurred only using fish
5 gelatin that displayed a sol-gel transition temperature, in a 10% aqueous solution, of less than 22° C (approx. 72° F), or when in a 30% aqueous solution, of less than 32° C (Approx. 90° F). The most desirable sol-gel transition temperatures lay between 15° and 20° C for a 10% aqueous solution and between 25° and 30° C for a 30% aqueous
10 solution.

By asking tasters to quantify their subjective judgments using a numerical scale, it was hoped that a certain degree of consistency could be introduced to observations made over time. As a predicate to testing sample lots after various storage times under various storage conditions, tasters were asked to rate the
15 subjective texture of several lots of experimental mixtures, formulated into both round and oval capsule shapes, from the successful formulation of Experiment 19 (see Table 6).

The gelatin capsule agent of Experiment 19 was viscosity adjusted to a viscosity of 9,000 mPa, plus or minus 2,000 mPa at 54° C (plus or minus 2°C) as
20 tested on a Brookfield Type B viscometer with a No. 4 spindle at 12 rpm. The agent was then cast into ribbons with a thickness of 0.028-0.029 inches (0.071-0.074 cm) and formed by a standard rotary die process into capsules weighing approximately

113 mg (plus or minus 7 mg). The capsules were filled using standard pharmaceutical techniques with a mixture of fractionated coconut oil (medium chain fatty acid triglyceride), mint flavoring, and aspartame sweetener. As with the previous experiments using sheet gelatin formulation samples, a panel of tasters assessed the capsules according to seven parameters; softness, easy dissolving, elasticity, powder or granular texture, chewiness, saliva stimulation, and sol-gel nature (subjective feeling of the liquidity of the compound) on a scale wherein 0 represents neutral judgments, while negative values and positive values represented departures from a neutral value. The results are shown in Table 7.

10 A test lot of capsules from the same formulation was then placed into storage at room temperature (approximately 15°-25° C), and evaluated by tasters at one, two, four, and six months after manufacture. To the degree practical, tasters remained the same throughout the experiment. The results are reported in tabular form in Table 8, and in graphic form in FIG. 1.

15 As seen in FIG. 1, there was considerable stability reported over the entire six month period of the experiment. There was a slight increase noted in hardness over time. Also, over time, the capsules were perceived as being more gelled and less liquid in nature.

	Fish Gel	Glycerin Plasticizer	Partial Pregelatinized Starch	Corn Starch		
No.	Croda 200B	JFAS 99.5	Asahi Kasei PCSD FW-40	Hohnen HS-7	Water	Comments
19	100	120	20	22	100	Good stretch, soft good dissolution in mouth.
	100	120	20	22	110	
	100	120	20	22	110	
	100	120	20	22	112	
	100	120	20	22	112	
20	100	120	10	32	100	Good in dissolution
	100	120	10	32	105	
21	100	120	30	12	100	Good
	100	120	30	12	120	
	100	120	30	12	130	

Table 6 – Formulations of the Instant Invention
 Experimental Formulation No. 19 Selected for Stability Testing

Samples were also placed in cold storage (approximately 4°-5° C) and removed for subjective testing at one and two months after manufacture. The results are reported at Table 9. Interestingly, compared to the results reported above in Table 8 and FIG. 1, the cold stored samples showed no less stability in most parameters than those that had been stored at room temperature (approximately 15°-25° C).

Additional testing was performed on two additional sample lots immediately following manufacture and after four months of storage at room temperature (approximately 15°-25° C). The first of these experiments is reported in Table 10 and FIG. 2; and the second experiment is reported in Table 11 and FIG. 3. Both experiments showed some increase in hardness and dissolvability over time, although this was judged within acceptable limits.

However, in the course of this experimentation, it was found that the residual moisture of the capsules created a tendency for them to deform and stick together during storage. Accordingly, a protocol was devised to reduce surface stickiness.

Capsules were manufactured using a rotary die process. The capsules were then tumble dried to remove water to a level of a moisture content typically in the range of 8-25%. For example experimental lot 13F839 (Tables 7, 8, and FIG. 1) had a residual shell water content of 16.0%, lot 13F840 (Table 7) had a residual shell water content of 13.4%, lot 13F955 (Tables 7, 10, and FIG. 2) had a residual shell water content of 14.9%, and lot 13F956 (Tables 7, 11, and FIG. 3) had a residual shell water content of 14.1%.

After the tumble dry process, the capsules were transferred into either a polishing pan or an automated inline dusting system whereby the product was coated with a layer of starch, typically potato or corn starch, although tapioca starch, wheat powder, waxy corn starch powder, and partial alpha starch powder were also effective. The capsules were then tumbled to produce an even coating of starch which prevented the capsules from sticking to one another.

After tumbling, the capsules were transferred onto a vibratory sieve where they were vibrated to remove excess coating material. The product was then bulk packaged.

Dusted capsules were compared with undusted controls to assess stickiness in storage under expected field conditions. Ten capsules were placed in a glass bottle and stored at 35° C for one week, followed by one day at 40° C. The capsule stickiness was observed by turning the bottle over and observing whether the capsules had adhered to each other or not. Capsules were evaluated without dusting and at levels of 0.05%, 0.1%, 0.2%, 0.5%, 1.0%, and 2.0% starch by weight of the capsules. The dusted starch percentage weights is calculated as the amount of starch that is added to a particular lot of capsules, rather than the amount of starch which actually adheres to each capsule. In one exemplary test lot, 25 g of powder was added to a lot of 15,000 capsules weighing 5 kg, producing a percentage weight of 0.5%. While there was significant stickiness of the capsules without starch, a starch level of about 0.5% provided optimal results in preventing capsule sticking.

5

Lot No.	13F839	13F840	13F955	13F956
Size	2 oval	2 round	3 round	4 round
Time Elapsed Since Manufacture Prior to Testing	1 Month	2 Months	Immediate	Immediate
Softness	1.4	0.4	1.7	2.0
Dissolvability	1.8	0.3	1.1	1.2
Elastic	1.4	0.1	0.3	0.3
Powder-like	1.4	1.1	1.3	1.0
Chewing	0.2	0.3	1.3	0.7
Saliva Stimulus	2.4	1.3	1.4	1.2
Gelling	0.0	1.6	0.1	0.3

Table 7 –Average Values of Initial Subjective Texture Questionnaires
Experimental Formulation No. 19

Croda 200B Fish Gel 100 parts/wt.

JFAS 99.5 Glycerin 120 parts/wt

Asahi Kasei PCSD FW-40 Partially Pregelatinized Starch

Hohnen HS-7 Corn Starch 22 parts/wt

10

Lot No.13F839

		Room Temp. 1 Month
		Average
①	Softness	-1.4
②	Dissolvability	-1.8
③	Elastic	1.4
④	Powder-like	-1.4
⑤	Chewing	-0.2
⑥	Saliva Stimulus	2.4
⑦	Gelling of fill material	-
		Room Temp. 2 Months (10/2/01)
		Average
①	Softness	0.0
②	Dissolvability	0.8
③	Elastic	0.8
④	Powder-like	-0.4
⑤	Chewing	0.8
⑥	Saliva Stimulus	1.8
⑦	Gelling of fill material	0.8
		Room Temp. 4 Months
		Average
①	Softness	-1.0
②	Dissolvability	-0.2
③	Elastic	1.2
④	Powder-like	-1.6
⑤	Chewing	0.6
⑥	Saliva Stimulus	1.6
⑦	Gelling of fill material	0.4
		Room Temp.6 Months
		Average
①	Softness	0.0
②	Dissolvability	0.5
③	Elastic	2.0
④	Powder-like	-2.0
⑤	Chewing	1.5
⑥	Saliva Stimulus	2.0
⑦	Gelling of fill material	2.5

Table 8 – Subjective Texture Questionnaire Results; Sample Lot 13F839; 0 to 6 Month Time

5

Cold Storage

Lot No.13F839	
Room Temp. 1 Month	
Average Value	
Softness	-1.4
Dissolvability	-1.8
Elastic	1.4
Powder-like	-1.4
Chewing	-0.2
Saliva Stimulus	2.4
Gelling of fill material	—
Cold Storage 2 Months	
Average Value	
Softness	-0.4
Dissolvability	0.2
Elastic	0.8
Powder-like	-0.4
Chewing	0.0
Saliva Stimulus	1.6
Gelling of fill material	0.6

Table 9 – Change over Time in Subjective Texture Questionnaire
Cold Storage (approximately 4°-5° C)

10

15

20

25

Changes on Storage

Lot. No. 13F955		Room Temp. 0 Months
		Average Value
	Softness	-1.7
	Dissolvability	-1.1
	Elastic	0.3
	Powder-like	-1.3
	Chewing	-1.3
	Saliva Stimulus	1.4
	Gelling of fill material	-0.1
		Room Temp. 4 Months
		Average Value
	Softness	
	Dissolvability	0.8
	Elastic	0.8
	Powder-like	-1.8
	Chewing	1.2
	Saliva Stimulus	2.0
	Gelling of fill material	0.6

5

Table 10 – Change over Time in Subjective Texture Questionnaire
Room Temperature (approximately 15°-25° C)

10

Changes with Storage

Lot No.13F956	Room Temp. 0 Months	
	Test Condition	Average Value
	Softness	-2.0
	Dissolvability	-1.2
	Elastic	0.3
	Powder-like	-1.0
	Chewing	-0.7
	Saliva Stimulus	1.2
	Gelling of fill material	-0.3
	Room Temp. 4 Months	
	Test Condition	Average Value
	Softness	-0.8
	Dissolvability	0.2
	Elastic	1.0
	Powder-like	-1.6
	Chewing	0.4
	Saliva Stimulus	2.0
	Gelling of fill material	0.2

5

Table 11 – Change over Time in Subjective Texture Questionnaire
Room Temperature (approximately 15°-25° C)

10

15

In sum, the instant invention provides a chewable soft gelatin capsule comprising a gelatin having a sol-gel transition temperature in a 10 wt.% aqueous solution of not more than 22° Centigrade and a sol-gel transition temperature in a 30 wt.% aqueous solution of not more than 32° Centigrade, a plasticizer, and an anti-
5 adhesion agent. The most desirable sol-gel transition temperatures for preferred gelatin are between 15° and 20° C for a 10% by weight aqueous solution and between 25° and 30° C for a 30% by weight aqueous solution.

The gelatin is typically a fish gelatin, although other types of gelatin having the sol-gel temperature behavior of the instant invention are also intended. The
10 plasticizer may also be, by way of example and not limitation, a polyol, particularly a polyol selected from the group consisting of glycerin, sorbitol, or mixtures thereof. One skilled in the art will realize that a number of plasticizers may be used in gelatin capsule formation, including by way of example and not limitation; polyethylene glycol, sucrose, mannitol, corn syrup, fructose, cellulose, dioctyl-sodium
15 sulfosuccinate, triethyl citrate, tributyl citrate, 1,2-propylenglycol, mono-, di- or triacetates of glycerol, natural gums or the like as well as mixtures thereof.

The anti-adhesion agent typically contains at least one starch, and the at least one starch may be corn starch. The capsule may be formulated with varying amounts of water and colorants.

20 In a preferred embodiment, the capsule agent comprises a mixture of 100 parts by weight of the selected gelatin, between 100 and 130 parts by weight of plasticizer, and between 10 and 45 parts by weight of anti-adhesion agent. In another

preferred embodiment, the mixture also contains partially pregelatinized starch, typically comprising 10 to 30 parts by weight of the mixture.

The soft gelatin capsule agent may be formulated into soft gelatin capsules by any of the means of manufacturing gelatin capsules that would be known to one skilled in the art. Optimally, the resulting capsule comprises a soft gelatin shell which further comprises between about 36 wt.% and about 47 wt.% gelatin having a sol-gel transition temperature in a 10 wt.% aqueous solution of not more than 22° Centigrade and a sol-gel transition temperature in a 30 wt.% aqueous solution of not more than 32° Centigrade, about 47 wt.% plasticizer, and between about 4 wt.% and about 16 wt.% anti-adhesion agent; and a soft gelatin capsule fill material. The most desirable sol-gel transition temperatures for gelatin are between 15° and 20° C for a 10% aqueous solution and between 25° and 30° C for a 30% by weight aqueous solution.

The soft gelatin fill material may be selected from a near limitless array of foodstuffs, medicaments, and other substances. The capsule maybe formulated with water, which typically comprises between about 8 wt.% and about 25 wt.% of the soft capsule shell.

The capsule may further comprise a surface coating applied to the exterior of the soft gelatin shell to decrease surface stickiness. The surface coating typically includes at least one starch, which may include a potato or a corn starch.

The soft gelatin capsules of the instant invention enable a significant advance in the state of the art. The preferred embodiments of the apparatus accomplish this by new and novel arrangements of elements that are configured in unique and novel

ways and which demonstrate previously unavailable but preferred and desirable capabilities.

The detailed description set forth above in connection with the drawings is intended merely as a description of the presently preferred embodiments of the invention, and is not intended to represent the only form in which the present invention may be constructed or utilized. The description sets forth the designs, functions, means, and methods of implementing the invention in connection with the illustrated embodiments. It is to be understood, however, that the same or equivalent functions and features may be accomplished by different embodiments that are also intended to be encompassed within the spirit and scope of the invention.

INDUSTRIAL APPLICABILITY

The present invention answers a long felt need for a chewable soft gelatin capsule agent that exhibits pleasant mouth feel, good chewing characteristics, good storage characteristics, and is also susceptible to conventional mass production techniques. The capsules that are manufactured from this agent may be used to store a wide range of foodstuffs, medicaments, or other substances. The utilization, in some embodiments, of fish gelatin, is hoped to increase consumer acceptance in cultures that reject the use of gelatin produced from certain animal sources.

20

WE CLAIM:

1. A soft gelatin capsule agent comprising:
 - a gelatin having a sol-gel transition temperature in a 10 wt.% aqueous solution of not more than 22° Centigrade and a sol-gel transition temperature in a 30 wt.% aqueous solution of not more than 32° Centigrade;
 - a plasticizer; and
 - an anti-adhesion agent.
2. The capsule agent of claim 1, wherein the sol-gel transition temperature for a 10% aqueous solution is between 15° and 20° and between 25° and 30° C for a 30% aqueous solution.
3. The capsule agent of claim 1, wherein the gelatin is at least one fish gelatin.
4. The capsule agent of claim 1, wherein the plasticizer is selected from the group consisting of polyols.
5. The capsule agent of claim 1, wherein the plasticizer is selected from the group consisting of glycerin, sorbitol, or mixtures thereof.
6. The capsule agent of claim 1, wherein the anti-adhesion agent is at least one starch.

7. The capsule agent of claim 6, wherein the at least one starch is corn starch.
8. The capsule agent of claim 1, further comprising water.
9. The capsule agent of claim 1, further comprising a colorant.
10. The capsule agent of claim 1, wherein,
the gelatin comprises 100 parts by weight of the agent;
the plasticizer comprises between 100 and 130 parts by weight of the agent;
and
the anti-adhesion agent comprises between 10 and 45 parts by weight of the agent.
11. A soft gelatin capsule agent comprising:
a gelatin having a sol-gel transition temperature in a 10 wt.% aqueous solution of not more than 22° Centigrade and a sol-gel transition temperature in a 30 wt.% aqueous solution of not more than 32° Centigrade,
a plasticizer;
an anti-adhesion agent; and
a partially pregelatinized starch.

12. The capsule agent of claim 11, wherein the sol-gel transition temperatures for a 10% aqueous solution is between 15° and 20° C and between 25° and 30° C for a 30% aqueous solution.
13. The capsule agent of claim 11, wherein the gelatin is at least one fish gelatin.
14. The capsule agent of claim 11, wherein the plasticizer is selected from the group consisting of polyols.
15. The capsule agent of claim 11, wherein the plasticizer is selected from the group consisting of glycerin, sorbitol, or mixtures thereof.
16. The capsule agent of claim 11, wherein the anti-adhesion agent is at least one starch.
17. The capsule agent of claim 16, wherein the at least one starch is corn starch.
18. The capsule agent of claim 11, further comprising water.
19. The capsule agent of claim 11, wherein,
the gelatin comprises 100 parts by weight of the agent;
the plasticizer comprises between 100 and 130 parts by weight of the agent;

the anti-adhesion agent comprises between 10 and 45 parts by weight of the agent; and

the partially pregelatinized starch comprises between 10 and 30 parts by weight of the agent.

20. A soft gelatin capsule comprising:

a soft gelatin shell which further comprises between about 36 wt.% and about 47 wt.% gelatin having a sol-gel transition temperature in a 10 wt.% aqueous solution of not more than 22° Centigrade and a sol-gel transition temperature in a 30 wt.% aqueous solution of not more than 32° Centigrade, about 47 wt.% plasticizer, and between about 4 wt.% and about 16 wt.% anti-adhesion agent; and

a soft gelatin capsule fill material.

21. The capsule of claim 20, wherein the sol-gel transition temperature for a 10% aqueous solution is between 15° and 20° and between 25° and 30° C for a 30% aqueous solution.

22. The capsule of claim 20, wherein the gelatin is at least one fish gelatin.

23. The capsule of claim 20, wherein the plasticizer is selected from the group consisting of polyols.

24. The capsule of claim 20, wherein the plasticizer is selected from the group consisting of glycerin, sorbitol, or mixtures thereof.
25. The capsule of claim 20, wherein the anti-adhesion agent is at least one starch.
26. The capsule of claim 25, wherein the at least one starch is corn starch.
27. The capsule of claim 20, further comprising water.
28. The capsule of claim 27, further comprising a water content of between about 8 wt.% and about 25 wt.%.
29. The capsule of claim 27, further comprising a surface coating applied to the exterior of the soft gelatin shell to decrease surface stickiness, wherein the surface coating includes at least one starch.
30. The capsule of claim 29, wherein the at least one starch is potato starch.
31. The capsule of claim 29, wherein the at least one starch is corn starch.
32. A soft gelatin capsule comprising:

a soft gelatin shell which further comprises between about 32 wt.% and about 45 wt.% gelatin having a sol-gel transition temperature in a 10 wt.% aqueous solution of not more than 22° Centigrade and a sol-gel transition temperature in a 30 wt.% aqueous solution of not more than 32° Centigrade, between about 42 wt.% and about 45 wt.% plasticizer, between about 4 wt.% and about 14 wt.% anti-adhesion agent, and between about 4 wt.% and 9 wt.% partially pregelatinized starch; and

a soft gelatin capsule fill material.

33. The capsule of claim 32, wherein the sol-gel transition temperature for a 10% aqueous solution is between 15° and 20° and between 25° and 30° C for a 30% aqueous solution.


34. The capsule of claim 32, wherein the gelatin is at least one fish gelatin.

35. The capsule of claim 32, wherein the plasticizer is selected from the group consisting of polyols.

36. The capsule of claim 32, wherein the plasticizer is selected from the group consisting of glycerin, sorbitol, or mixtures thereof.


37. The capsule of claim 32, wherein the anti-adhesion agent is at least one starch.

38. The capsule of claim 37, wherein the at least one starch is corn starch.
39. The capsule of claim 32, further comprising water.
40. The capsule of claim 39, further comprising a water content of between about 8 wt.% and about 25 wt.%.
41. The capsule of claim 40, further comprising a surface coating applied to the exterior of the soft gelatin shell to decrease surface stickiness, wherein the surface coating includes at least one starch.
42. The capsule of claim 41, wherein the at least one starch is potato starch.
43. The capsule of claim 41, wherein the at least one starch is corn starch.




Changes in Subjective Texture Questionnaire Results - Sample Lot of Table 8 (Lot No. 13F839)

FIG. 1



Changes in Subjective Texture Questionnaire Results - Sample Lot of Table 10 (Lot No. 13F955)

FIG. 2



Changes in Subjective Texture Questionnaire Results - Sample Lot of Table 11 (Lot No. 13F956)

FIG. 3

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US03/17746

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A61K 9/48, 9/64, 9/66
 US CL : 424/451, 452, 455, 456

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 U.S. : 424/451, 452, 455, 456

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
 Please See Continuation Sheet

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4,935,243 A (BORKAN et al) 19 June 1990 (19.06.1990), column 2, line 50 through column 3, line 18.	1-43
Y	US 6,280,767 B1 (SANO et al) 28 August 2001 (28.08.2001), column 2, lines 1-64.	1-43
Y	US 5,554,385 A (STROUD) 10 September 1996 (10.09.1996), column 2, line 1 through column 3, line 33.	1-43
Y	US 2,580,683 A (KRUEGER) 01 January 1952 (01.01.1952), columns 1 through 3.	1-43
Y	US 6,319,518 A (LEE et al) 20 November 2001 (20.11.2001), column 6, line 12 through column 8, line 21.	1-43

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier application or patent published on or after the international filing date
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
 "&" document member of the same patent family

Date of the actual completion of the international search

10 August 2003 (10.08.2003)

Date of mailing of the international search report

14 OCT 2003

Name and mailing address of the ISA/US
 Mail Stop PCT, Attn: ISA/US
 Commissioner for Patents
 P.O. Box 1450
 Alexandria, Virginia 22313-1450
 Facsimile No. (703)305-3230

Authorized officer
 Humera N. Sheikh

Telephone No. (703) 308-4429

INTERNATIONAL SEARCH REPORT

PCT/US03/17746

Continuation of B. FIELDS SEARCHED Item 3:

WEST

gelatin, capsule, plasticizer, polyols, starch, sol-gel transition