



US00RE35407E

United States Patent [19]

[11] E

Patent Number: Re. 35,407**Wiesenfeldt et al.**[45] **Reissued Date of Patent: Dec. 17, 1996**[54] **AZO DYE POLYMERS**

[75] Inventors: **Matthias Wiesenfeldt; Sabine Gruettner-Merten**, both of Mutterstadt; **Ruediger Sens**, Mannheim; **Karl-Heinz Etzbach**, Frankenthal; **Heike Kilburg**, Speyer, all of Germany

[73] Assignee: **BASF Aktiengesellschaft**, Ludwigshafen, Germany

[21] Appl. No.: **223,852**

[22] Filed: **Apr. 6, 1994**

Related U.S. Patent Documents

Reissue of:

[64] Patent No.: **5,264,507**
 Issued: **Nov. 23, 1993**
 Appl. No.: **949,156**
 Filed: **Sep. 23, 1992**

[30] **Foreign Application Priority Data**

Oct. 1, 1991 [DE] Germany 4132685

[51] **Int. Cl.⁶** **C08F 228/06; C08F 226/02; C08F 220/18; C08F 212/06**

[52] **U.S. Cl.** **526/256; 526/258; 526/265; 526/312; 526/329.2; 526/347**

[58] **Field of Search** **526/256, 258, 526/265, 312, 329.2, 347**

[56] **References Cited****U.S. PATENT DOCUMENTS**

3,190,860	6/1965	Fertig et al.	526/312
3,507,850	4/1970	Cohen et al.	534/573
4,239,868	12/1980	Bonnet et al.	525/279
4,505,857	3/1985	Egli	534/768
4,843,153	6/1989	Eiligsfeld et al.	534/752

FOREIGN PATENT DOCUMENTS

0201896	11/1986	European Pat. Off.
1468540	2/1966	France
2378807	8/1978	France
3108077	1/1982	Germany
91/09842	7/1991	WIPO

OTHER PUBLICATIONS

Journal of Polymer Science, Polymer Chemistry Edition, Bd. 28, 1-13, Jan. 15, 1990, New York, USA.

Chemistry & Industry, Oct. 1, 1990, pp. 600-608.

Journal of Polymer Science: Part A: Polymer Chemistry, vol. 28, pp. 1-13 (1990), Douglas R. Robello, "Linear Polymers for Nonlinear Optics I. Polyacrylates Bearing Aminonitro-Stilbene and -Azobenzene Dyes", Chemistry & Industry, Oct. 1, 1990, pp. 600-608, Carole Jones, "Polymers for Non-Linear Optical Devices".



Primary Examiner—Joseph L. Schofer

Assistant Examiner—Wu C. Cheng

Attorney, Agent, or Firm—Oblon, Spivak, McClelland, Maier & Neustadt, P.C.

[57] **ABSTRACT**

Azo dye polymers useful in nonlinear optics contain as characteristic monomer units radicals of the formulac I, II, III and IV



where

D is the radical of a heterocyclic diazo component,

R¹ and R² are each hydrogen, C₁-C₆-alkyl or substituted or unsubstituted C₁-C₆-alkoxy, and R² may also be C₁-C₄-alkanoylamino,

R³ is hydrogen, C₁-C₆-alkyl, C₅-C₇-cycloalkyl or C₃-C₄-alkenyl,

R⁴ is hydrogen, deuterium, methyl, trideuterated methyl or chlorine,

R⁵ is hydrogen or deuterium,

Y¹ and Y² are each substituted or unsubstituted C₂-C₁₀-alkylene,

W is oxygen, imino or C₁-C₄-alkylimino, and

X is hydroxyl, substituted or unsubstituted C₁-C₆-alkoxy, phenoxy, amino or mono- or di(C₁-C₄-alkyl)amino, and have an average molecular weight of from 1,000 to 100,000.





2 Claims, No Drawings

1

AZO DYE POLYMERS

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

The present invention relates to novel azo dye polymers containing as characteristic monomer units radicals of the formulae I, II, III and IV



where

D is the radical of a diazo component derived from a five-membered aromatic heterocyclic amine having one to three hetero atoms selected from the group consisting of nitrogen, oxygen and sulfur in the heterocyclic ring and optionally fused to a benzene, thiophene, pyridine or pyrimidine ring.

R¹ and R² are each independently of the other hydrogen, C₁-C₆-alkyl or C₁-C₆-alkoxy optionally substituted by phenyl or C₁-C₄-alkoxy, and R² may also be C₁-C₄-alkanoylamino,

R³ is hydrogen, C₁-C₆-alkyl, C₅-C₇-cycloalkyl or C₃-C₄-alkenyl,

R⁴ is hydrogen, deuterium, methyl, trideuterated methyl or chlorine,

R⁵ is hydrogen or deuterium,

Y¹ and Y² are each independently of the other C₂-C₁₀-alkylene optionally interrupted by 1 to 3 oxygen atoms in the other function or imino or C₁-C₄-alkylimino groups,

W is oxygen, imino or C₁-C₄-alkylimino, and

X is hydroxyl, C₁-C₆-alkoxy, trideuterated methoxy, 2,3-epoxypropoxy, phenoxy, amino or C₁-C₄-mono- or dialkylamino,

the proportion of monomer units of the formula I being from 1 to 100 mol %, the proportion of monomer units of the formula II being from 0 to 99 mol %, the proportion of monomer units of the formula III being from 0 to 99 mol % and the proportion of monomer units of the formula IV being from 0 to 75 mol %, each percentage being based on the polymer, and the average molecular weight of the polymer being from 1,000 to 100,000, to the use thereof in nonlinear

2

optics and to the use of monomeric azo dyes for preparing the novel polymers.

J. Polymer Sci., Part A, Polymer Chem. 28 (1990), 1-13, disclosed polymers with azo dye chromophores in the side chains. The azo dyes there are members of the azobenzene series. However, it has been found that such polymers are still deficient when used in nonlinear optical systems.









It is an object of the present invention to provide novel polymers which likewise possess donor/acceptor-substituted azo dyes as chromophore in the side chain and which shall be advantageous for use in nonlinear optical systems.

We have found that this object is achieved by the azo dye polymers defined at the beginning.


Suitable radicals D in the formula I are derived for example from a heterocyclic amine of the pyrrole, furan, thiophene, pyrazole, imidazole, oxazole, isoxazole, thiazole, isothiazole, triazole, oxadiazole, thiadiazole, benzofuran, benzothiophene, benzimidazole, benzoxazole, benzothiazole, benzisothiazole, pyridothiophene, pyrimidothiophene, thienothiophene or thienothiazole series.

Of particular suitability are those radicals D derived from a heterocyclic amine of the pyrrole, thiophene, pyrazole, thiazole, isothiazole, triazole, thiadiazole, benzothiophene, benzothiazole, benzisothiazole, pyridothiophene, pyrimidothiophene, thienothiophene or thienothiazole series.


Of particular note are radicals D derived from aminoheterocycles of the formulae




-continued




(Vii)




(Vlj)




(Vlk)




(Vll)



(Vlm)




(Vln)



(Vlo)

and



(Vlp)

where

L¹ is nitro, cyano, C₁-C₆-alkanoyl, benzoyl, C₁-C₆-alkylsulfonyl, substituted or unsubstituted phenylsulfonyl or a radical of the formula —CH=T, where T is the radical of an acidic CH compound,

L² is hydrogen, C₁-C₆-alkyl, halogen, hydroxyl, mercapto, unsubstituted or phenyl- or C₁-C₄-alkoxy-substituted C₁-C₆-alkoxy, substituted or unsubstituted phenoxy, unsubstituted or phenyl-substituted C₁-C₆-alkylthio, substituted or unsubstituted phenylthio, C₁-C₆-alkylsulfonyl or substituted or unsubstituted phenylsulfonyl,

L³ is cyano, C₁-C₄-alkoxycarbonyl or nitro,

L⁴ is hydrogen, C₁-C₆-alkyl or phenyl,

L⁵ is C₁-C₆-alkyl or phenyl,

L⁶ is cyano, C₁-C₄-alkoxycarbonyl, C₁-C₆-alkanoyl or halogen,

L⁷ is nitro, cyano, C₁-C₆-alkanoyl, benzoyl, C₁-C₆-alkylsulfonyl, substituted or unsubstituted phenylsulfonyl or a radical of a formula —CH=T, where T is as defined above,

L⁸ is hydrogen, C₁-C₆-alkyl, halogen, unsubstituted or phenyl- or C₁-C₄-alkoxy-substituted C₁-C₆-alkoxy,

unsubstituted or phenyl-substituted C₁-C₆-alkylthio, substituted or unsubstituted phenylthio, C₁-C₆-alkylsulfonyl, substituted or unsubstituted phenylsulfonyl or C₁-C₄-alkoxycarbonyl,

L⁹ is cyano, unsubstituted or phenyl-substituted C₁-C₆-alkyl, unsubstituted or phenyl-substituted C₁-C₆-alkylthio, substituted or unsubstituted phenyl, thienyl, C₁-C₄-alkylthienyl, pyridyl or C₁-C₄-alkylpyridyl,

L¹⁰ is phenyl or pyridyl,

L¹¹ is trifluoromethyl, nitro, C₁-C₆-alkyl, phenyl, unsubstituted or phenyl-substituted C₁-C₆-alkylthio or C₁-C₄-dialkylamino,

L¹² is C₁-C₆-alkyl, phenyl, 2-cyanoethylthio or 2-(C₁-C₄-alkoxycarbonyl)ethylthio,

L¹³ is hydrogen, nitro or halogen, and

L¹⁴ is hydrogen, cyano, nitro or halogen.

Any substituted phenyl appearing in the azo dye polymers according to the invention may have as substituents for example C₁-C₄-alkyl, C₁-C₄-alkoxy or halogen, in particular chlorine or bromine. These phenyl rings will in general have from 1 to 3 substituents.

Any alkyl, alkylene or alkenyl groups appearing in the abovementioned formulae may be not only straight-chain but also branched.

R¹, R², R³, L², L⁴, L⁵, L⁸, L⁹, L¹¹ and L¹² are each for example methyl, ethyl, propyl, isopropyl, butyl, isobutyl, sec-butyl, pentyl, isopentyl, neopentyl, tertpentyl, hexyl or 2-methylpentyl.

R² may also be for example formylamino, acetylamino, propionylamino or butynylamino.

L⁹ may also be for example benzyl or 1- or 2-phenylethyl.

L², L⁸, L⁹ and L¹¹ may each also be for example methylthio, ethylthio, propylthio, isopropylthio, butylthio, isobutylthio, pentylthio, hexylthio, benzylthio or 1- or 2-phenylethylthio.

L² and L⁸ may each also be for example phenylthio, 2-methylphenylthio, 2-methoxyphenylthio or 2-chlorophenylthio.

R¹, R², L² and L⁸ and also X may each also be for example methoxy, ethoxy, propoxy, isopropoxy, butoxy, isobutoxy, sec-butoxy, pentyloxy, isopentyloxy, neopentyloxy, tert-pentyloxy, hexyloxy or 2-methylpentyloxy.

L², L⁸, L¹³ and L¹⁴ and also L⁶ may each also be for example fluorine, chlorine or bromine.

L¹, L² and L⁸ and also L⁷ may each also be for example methylsulfonyl, ethylsulfonyl, propylsulfonyl, isopropylsulfonyl, butylsulfonyl, isobutylsulfonyl, secbutylsulfonyl, pentylsulfonyl, isopentylsulfonyl, neopentylsulfonyl, hexylsulfonyl, phenylsulfonyl, 2-methylphenylsulfonyl, 2-methoxyphenylsulfonyl or 2-chlorophenylsulfonyl.

L⁶ and L⁸ and also L³ may each also be for example methoxycarbonyl, ethoxycarbonyl, propoxycarbonyl, isopropoxycarbonyl, butoxycarbonyl, isobutoxycarbonyl or sec-butoxycarbonyl.

R¹, R², L² and L⁸ may each also be for example 2-methoxyethoxy, 2-ethoxyethoxy, 2- or 3-methoxypropoxy, 2- or 3-ethoxypropoxy, 2- or 4-methoxybutoxy, 2- or 4-ethoxybutoxy, 5-methoxypentyloxy, 5-ethoxypentyloxy, 6-methoxyhexyloxy, 6-ethoxyhexyloxy, benzyloxy or 1- or 2-phenylethoxy.

X may also be for example methylamino, ethylamino, propylamino, isopropylamino or butylamino.

L¹¹ and X may each also be for example dimethylamino, diethylamino, dipropylamino, diisopropylamino, dibutylamino or N-methyl-N-ethylamino.

L¹² may also be for example 2-methoxycarbonylethylthio or 2-ethoxycarbonylethylthio.

5

R³ may also be for example cyclopentyl, cyclohexyl, cycloheptyl, allyl or methallyl.







L⁹ may also be for example phenyl, 2-, 3- or 4-methylphenyl, 2,4-dimethylphenyl, 2-, 3- or 4-chlorophenyl, 2-, 3- or 4-methoxyphenyl, 2- or 3-methylthienyl or 2-, 3- or 4-methylpyridyl.

Y¹ and Y² are each for example (CH₂)₂, (CH₂)₃, (CH₂)₄, (CH₂)₅, (CH₂)₆, (CH₂)₇, (CH₂)₈, (CH₂)₉, (CH₂)₁₀, CH(CH₃)—CH₂, CH(CH₃)—(CH(CH₃)), C₂H₄—O—C₂H₄, C₂H₄—NH—C₂H₄, C₂H₄—N(CH₃)—C₂H₄, C₂H₄O—C₂H₄O—C₂H₄, C₂H₄—NH—C₂H₄—NH—C₂H₄ or C₂H₄—N(CH₃)—C₂H₄—N(CH₃)—C₂H₄.


W is for example methylimino, ethylimino, propylimino, isopropylimino or butylimino.

L¹, L⁶ and L⁷ may each also be for example formyl, acetyl, propionyl, butyryl, pentanoyl or hexanoyl.

When L¹ or L⁷ is the radical —CH=T wherein T is derived from an acidic CH compound H₂T, include suitable acidic CH compounds H₂T are for example compounds of the formula



or



where

Z¹ is cyano, nitro, C₁–C₄-alkanoyl, substituted or unsubstituted benzoyl, C₁–C₄-alkylsulfonyl, substituted or unsubstituted phenylsulfonyl, carboxyl, C₁–C₄-alkoxycarbonyl, C₃–C₄-alkenyloxycarbonyl, phenoxy-carbonyl, carbamoyl, mono- or di(C₁–C₄-alkyl)carbamoyl,

6

substituted or unsubstituted phenylcarbamoyl, substituted or unsubstituted phenyl, 2-benzothiazolyl, 2-benzimidazolyl, 5-phenyl-1,3,4-thiadiazol-2-yl or 2-hydroxyquinoxalin-3-yl,

Z² is C₁–C₄-alkyl, C₁–C₄-alkoxy or C₃–C₄-alkenyloxy, Z³ is C₁–C₄-alkoxycarbonyl, C₃–C₄-alkenyloxycarbonyl, phenylcarbamoyl or 2-benzimidazolyl,

Z⁴ is cyano, C₁–C₄-alkoxycarbonyl or C₃–C₄-alkenyloxycarbonyl,

Z⁵ is hydrogen or C₁–C₆-alkyl,


Z⁶ is hydrogen, C₁–C₄-alkyl or phenyl and

Z⁷ is C₁–C₄-alkyl.

Preference must be given here to the radical derived from compounds of the formula VIIa, VIIb or VIIc wherein Z¹ is cyano, C₁–C₄-alkanoyl, C₁–C₄-alkoxycarbonyl or C₃–C₄-alkenyloxycarbonyl, Z² is C₁–C₄-alkyl, C₁–C₄-alkoxy or C₃–C₄-alkenyloxy, Z³ is C₁–C₄-alkoxycarbonyl or C₃–C₄-alkenyloxycarbonyl, and Z⁴ is cyano

Particular emphasis must be given here to the radical derived from compounds of the formula VIIa, VIIb or VIIc wherein Z¹ is cyano, C₁–C₄-alkoxycarbonyl or C₃–C₄-alkenyloxycarbonyl, Z² is C₁–C₄-alkoxy or C₃–C₄-alkenyloxy, Z³ is C₁–C₄-alkoxycarbonyl or C₃–C₄-alkenyloxycarbonyl, and Z⁴ is cyano.

Preference is given to azo dye polymers which as characteristic monomer units contain radicals of the formula Ia



where D, R¹, R², R³, R⁴, Y and W are each as defined above, and of the abovementioned formula II.

Preference is further given to azo dye polymers where D in formula I is derived from an amine of the formula VIa, VIb, VIc, VIe, VIg, VIh or VIi.

Preference is further given to azo dye polymers in which the proportion of monomer units of the formula I is from 4 to 50, in particular from 8 to 25, mol %, the proportion of monomer units of the formula II is from 51 to 96, in particular from 75 to 92, mol %, the proportion of monomer units of the formula III is from 0 to 30, in particular from 0 to 15, mol % and the proportion of monomer units of the formula IV is from 0 to 50, in particular from 0 to 20 mol %, each percentage being based on the polymer, and the average molecular weight of the polymer is from 1500 to 50,000, in particular from 2000 to 25,000.

Of particular suitability are azo dye polymers in which in the formula I

R¹ is hydrogen or C₁–C₄-alkoxy,

R² is C₁–C₄-alkyl, C₁–C₄-alkoxy or acetylamino,

R³ is C₁–C₄-alkyl,

R⁴ is hydrogen or methyl, and

Y is C₂–C₈-alkylene, and in the formula II

R⁴ is hydrogen or methyl, and

X is C₁–C₄-alkoxy.


Particular preference is given to azo dye polymers in which D is derived from amines of the thiophene or thiazole series, in particular from those of the formula VIb or VIe

Of special interest are azo dye polymers in which D is derived from an amine of the formula VIb or VIe where

L¹ is nitro, cyano, C₁–C₄-alkanoyl or a radical of the formula —CH=T, where T is as defined above,

L² is hydrogen, C₁-C₄-alkyl or halogen,
 L³ is cyano, C₁-C₄-alkoxycarbonyl or nitro,
 L⁷ is nitro, cyano, C₁-C₄-alkanoyl or a radical of the
 formula —CH=T, where T is as defined above, and
 L⁸ is hydrogen, C₁-C₄-alkyl or halogen.

To prepare the polymers of the invention, it is advantageous to employ azo dyes of the formula V




where D, R¹, R², R³, R⁴, Y and W are each as defined above.

The novel polymers can be prepared by methods known per se, for example as described in J. Polymer Sci. (loc. cit.).

Conveniently, an azo dye of the formula V is reacted with an acryloyl compound of the formula VIII



where R⁴ and X are each as defined above, styrene and a cinnamic ester of the formula IX



where Y² and R⁴ are each as defined above, in the above-mentioned molar ratio in an inert solvent (for example toluene or xylene) in the presence of a free radical initiator (for example azobisisobutyronitrile).

The azo dyes of the formula V are known per se and described for example in EP-A-201,896, DE-A-3,108,077, U.S. Pat. No. 4,843,153 or GB-A-1,546,803 or can be obtained by the methods mentioned therein.

The azo dye polymers of the invention are advantageously suitable for use in nonlinear optical systems (see for example Chemistry and Industry, Oct. 1, 1990, pages 600 to 608).

They are particularly suitable for use in communications technology, electrooptical modulators (for example Mach-Zehnder Interferometers), optical switches, frequency mixing or waveguides.

The layers which contain the polymers of the present invention are prepared in the conventional manner, for example by wet or spin coating with a 5-15% by weight solution of the polymer in a solvent (for example tetrachloroethane, methylene chloride or tetrahydrofuran).

Given a suitable substitution pattern (for example an epoxy structure) the novel polymers can also be crosslinked photochemically, thermally or by the action of electron beams.

The novel polymers are notable for good processibility into thin films, high purity a narrow molecular weight distribution, good orientation in an electric field, good long-term stability, high glass transition temperatures and a high electro-optical coefficient.

The Examples which follow will further illustrate the invention.

I. PREPARATION OF MONOMERIC AZO DYES


Dye 1

a) Preparation of Coupling Component

421 g (3.05 mol) of potassium carbonate were suspended in 240 ml of water together with 40 g (0.12 mol) of

potassium iodide. With continuous stirring 169 g (1.2 mol) of N-ethyl-m-toluidine in 240 ml of isobutanol were added, followed by 260 g (1.8 mol) of 6-chlorohexanol. Then the reaction mixture was heated to the boil. After 12 hours under reflux, the reaction mixture was cooled down to room temperature, 400 ml of water were added, and the aqueous phase was separated off. The organic phase was washed three times with 400 ml of water each time and dried over sodium sulfate, and the solvent was removed under reduced pressure. The residual oil was subjected to fractional distillation (157°-158° C. at 1.0 mbar). Yield: 231 g (82%).


47 g (0.2 mol) of N-ethyl-N-(6-hydroxyhexyl)-m-toluidine were dissolved in 600 ml of dichloromethane. 42 ml of triethylamine and 2.4 g of hydroquinone were added. The reaction solution was cooled down to 0°-5° C. and 38 ml (0.4 mol) of methacryloyl chloride in 100 ml of dichloromethane were gradually added dropwise. This was followed by 2 hours stirring at that temperature, warming to room temperature and a further 50 hours' stirring. As workup, the organic phase was washed with 300 ml of saturated sodium bicarbonate solution and then twice with 300 ml of sodium chloride solution each time. After drying over sodium sulfate and concentrating of the solvent, the crude produce was purified by column chromatography over silica gel using 94:5 v/v toluene/methanol as mobile phase. Yield: 44 g (71%) of the aniline of the formula



b) Preparation of Azo Dye

6.4 (0.035 mol) of 2-amino-4-chloro-3,5-dicyanophthiophene were suspended in 100 ml of 17:3 v/v glacial acetic acid/propionic acid. Then 14 ml of 85% by weight sulfuric acid were added dropwise at room temperature and 6 ml of nitrosylsulfuric acid dropwise at 0° to 5° C. After stirring at from 0° to 5° C. for 3 hours, the resulting diazomium salt solution was added dropwise to 10.9 g (0.036 mol) of the coupling component described under a) in 300 g of ice-water, 20 ml of concentrated hydrochloric acid and 1 g of amidosulfuric acid at <5° C. and at a pH 1-1.5. The pH was maintained at 1-1.5 by the dropwise addition of 20% by weight sodium hydroxide solution. After stirring overnight at room temperature the precipitated dye was filtered off with suction, washed with water, dried and chromatographed twice over silica gel using 95:5 v/v hexane/acetone as mobile phase.


Yield: 10 g (57%) of the dye of the formula



C₂₅H₂₈N₅SO₂Cl (498.0)

calculated: C, 60.29; H, 5.67; N, 14.06; S, 6.43; O, 6.43.
 found: C, 60.31; H, 5.75; N, 13.99; S, 6.40; O, 6.43.

The same method gives the dyes of the formula










5

listed below in Table 1.

TABLE 1


Dye No	D	Q ¹	Q ²	Q ³	n
2		H	C ₂ H ₅	CH ₃	2
3		CH ₃	C ₂ H ₅	CH ₃	6
4		H	C ₂ H ₅	CH ₃	2
5		H	C ₂ H ₅	CH ₃	2
6		H	C ₂ H ₅	CH ₃	2
7		H	C ₂ H ₅	CH ₃	2
8		CH ₃	C ₂ H ₅	CH ₃	6
9		H	C ₂ H ₅	CH ₃	2
10		H	C ₂ H ₅	CH ₃	2
11		H	C ₂ H ₅	CH ₃	2
12		CH ₃	C ₂ H ₅	CH ₃	2

TABLE I-continued

Dye No	D	Q ¹	Q ²	Q ³	n
13		CH ₃	C ₂ H ₅	CH ₃	6
14		CH ₃	C ₂ H ₅	CH ₃	6
15		H	C ₂ H ₅	CH ₃	2
16		CH ₃	C ₂ H ₅	CH ₃	6
17		CH ₃	C ₂ H ₅	CH ₃	6
18		CH ₃	C ₂ H ₅	CH ₃	6
19		CH ₃	C ₂ H ₅	CH ₃	6

II) PREPARATION OF POLYMER

General polymerization method for preparing polyacrylates of the following formula:



(The indices l, m, p and q express the mole percentages of the respective monomer units, based on the polymer.)

In a Schlenk vessel, a monomer solution comprising n mol % of dye monomer and l+p+q mol % of comonomer in absolute toluene was admixed with 2 mol % of azobisisobutyronitrile. After argon had been passed through the mono-


mer mixture for 10 minutes, the monomer mixture was thermostabilized at 50° C. The polymerization was complete after 100 hours. The polymers were precipitated with metha-

nol and reprecipitated twice from hexane/methanol. (If monomer is still present, it can be separated off by column chromatography over silica gel, for example using 9:1 v/v toluene/ethyl acetate as mobile phase.) After the solvent had been removed, the polymer was dried in a high vacuum. The quantitative composition of the copolymers was determined

by means of UV spectroscopy and elemental analysis. The molecular weights were determined by gel permeation chromatography. The glass transition temperature of the polymer was determined by differential scanning calorimetry.





phenyl or C₁-C₄-alkoxy, and R² may also be C₁-C₄-alkanoylamino,

TABLE 2

Example No	l	m	p	q	Q ⁴	Q ⁵	Q ⁶	Dye No	Average molecular weight	T _g [°C.]
1	90	10	0	0	CH ₃	CH ₃	H	9	16807	125
2	90	10	0	0	CH ₃	CH ₃	H	3	22491	120
3	90	10	0	0	CH ₃	CH ₃	H	5	11594	151
4	90	10	0	0	CH ₃	CH ₃	H	10	3770	105
5	90	10	0	0	CH ₃	CH ₃	H	11	2661	95
6	80	20	0	0	CH ₃	CH ₃	H	2	13072	150
7	80	20	0	0	CH ₃	CH ₃	H	3	11062	155
8	88	12	0	0	CH ₃	CH ₃	H	3	11489	145
9	90	10	0	0	CH ₃	CH ₃	H	6		
10	90	10	0	0	CH ₃	CH ₃	H	13	14685	86
11	90	10	0	0	CH ₃		H	2	13434	125
12	90	10	0	0	CD ₃	CD ₃	D	3	18384	130
13	80	10	0	10	CH ₃	CH ₃	H	3		
14	80	10	10	0	CH ₃	CH ₃	H	3	2877	
15	50	50	0	0	CH ₃	CH ₃	H	3		
16	0	100	0	0	CH ₃	CH ₃	H	3		
17	90	10	0	0	CH ₃	CH ₃	H	17		90
18	90	10	0	0	CH ₃	CH ₃	H	18		100

We claim:

[1. An azo dye polymer containing as characteristic monomer unit radicals of the formulae I, II, III and IV



where

D is the radical of the diazo component derived from a five-membered aromatic heterocyclic amine having one to three hetero atoms selected from the group consisting of nitrogen, oxygen and sulfur in the heterocyclic ring and optionally fused to a benzene, thiophene, pyridine or pyrimidine ring,

R¹ and R² are each independently of the other hydrogen, C₁-C₆-alkyl or C₁-C₆-alkoxy optionally substituted by

30

R³ is hydrogen, C₁-C₆-alkyl, C₅-C₇-cycloalkyl or C₃-C₄-alkenyl,

(I) 35

R⁴ is hydrogen, deuterium, methyl, trideuterated methyl or chlorine,

40

R⁵ is hydrogen or deuterium,

(II)

Y¹ and Y² are each independently of the other C₂-C₁₀-alkylene optionally interrupted by 1 to 3 oxygen atoms in the ether function of imino or C₁-C₄-alkylimino groups,

45

W is oxygen, imino or C₁-C₄-alkylimino, and

(III)

X is hydroxyl, C₁-C₆-alkoxy, trideuterated methoxy, 2,3-epoxypropoxy, phenoxy, amino or C₁-C₄-mono- or -dialkylamino.

50

the proportion of monomer units of the formula I being from 1 to 100 mol %, the proportion of monomer units of the formula II being from 0 to 99 mol %, the proportion of monomer units of the formula III being from 0 to 99 mol % and the proportion of monomer units of the formula IV being from 0 to 75 mol %, each percentage being based on the polymer, and the average molecular weight of the polymer being from 1,000 to 100,000.]

55


60

[2. An azo dye polymer as claimed in claim 1, wherein D is derived from a heterocyclic amine of the pyrrole, furan, thiophene, pyrazole, imidazole, oxazole, isoxazole, thiazole, isothiazole, triazole, oxadiazole, thiadiazole, benzofuran, benzothiophene, benzimidazole, benzoxazole, benzothiazole, benzoisothiazole, pyridothiophene, pyrimidithiophene, thienothiophene or thienothiazole series.]

65


15

3. An azo dye polymer as claimed in claim 1, wherein in formula (I) D is




R¹ is hydrogen, R² is methyl, R³ is ethyl, Y¹ is hexylene, W is oxygen and R⁴ is methyl.

4. An azo dye polymer containing as characteristic monomer units radicals of the formulae I, II, III and IV




(I)

15




(II)

20



(III)

25




(IV)

30

35


wherein

D is the radical of a diazo component derived from a compound selected from the group consisting of:




(VIa)

40




(VIb)

45




(VIc)

50



(VIe)

55




(VIg)

60


65

16


-continued




(VIh)




(VIi)




(VIj)



(VIk)




(VIl)



(VIo)

and



(VIp)

wherein

L¹ is nitro, cyano, C₁-C₆-alkanoyl, benzoyl, C₁-C₆-alkyl-sulfonyl, substituted or unsubstituted phenylsulfonyl or a radical of the formula -CH=T, where T is the radical of an acidic CH compound,

L² is hydrogen, C₁-C₆-alkyl, halogen, hydroxyl, mercapto, unsubstituted or phenyl- or C₁-C₄-alkoxy-substituted C₁-C₆-alkoxy, substituted or unsubstituted phenoxy, unsubstituted or phenyl-substituted C₁-C₆-alkylthio, substituted or unsubstituted phenylthio, C₁-C₆-alkylsulfonyl or substituted or unsubstituted phenylsulfonyl,

L³ is cyano, C₁-C₄-alkoxycarbonyl or nitro,

L⁴ is hydrogen, C₁-C₆-alkyl or phenyl,

L⁵ is C₁-C₆-alkyl or phenyl,

L⁶ is cyano, C₁-C₄-alkoxycarbonyl, C₁-C₆-alkanoyl or halogen,

L¹⁰ is phenyl or pyridyl,

L¹¹ is trifluoromethyl, nitro C₁-C₆-alkyl, phenyl, unsubstituted or phenyl-substituted C₁-C₆-alkylthio or C₁-C₄-dialkylamino,

L¹² is C₁-C₆-alkyl, phenyl, 2-cyanoethylthio or 2-(C₁-C₄-alkoxycarbonyl)ethylthio, and

L¹³ is hydrogen, nitro or halogen;

R¹ and R² are each independently of the other hydrogen, C₁-C₆-alkyl or C₁-C₆-alkoxy optionally substituted by phenyl or C₁-C₄-alkoxy, and R² may also be C₁-C₄-alkanoylamino,

17

R^3 is hydrogen, C_1 - C_6 -alkyl, C_5 - C_7 -cycloalkyl or C_3 - C_4 -alkenyl,

R^4 is hydrogen, deuterium, methyl, trideuterated methyl or chlorine,

R^5 is hydrogen or deuterium,

Y^1 and Y^2 are each independently of the other C_2 - C_{10} -alkylene optionally interrupted by 1 to 3 oxygen atoms in the ether function of imino or C_1 - C_4 -alkylimino groups,

W is oxygen, imino or C_1 - C_4 -alkylimino, and

X is hydroxyl, C_1 - C_6 -alkoxy, trideuterated methoxy, 2,3-epoxypropoxy, phenoxy, amino or C_1 - C_4 -mono- or

18

-dialkylamino, the proportion of monomer units of the formula I being from 1 to 100 mol %, the proportion of monomer units of the formula II being from 0 to 99 mol %, the proportion of monomer units of the formula III being from 0 to 99 mol % and the proportion of monomer units of the formula IV being from 0 to 75 mol %, each percentage being based on the polymer, and the average molecular weight of the polymer being from 1,000 to 100,000.

* * * * *