



(86) **Date de dépôt PCT/PCT Filing Date:** 2012/05/25
(87) **Date publication PCT/PCT Publication Date:** 2012/11/29
(45) **Date de délivrance/Issue Date:** 2018/07/17
(85) **Entrée phase nationale/National Entry:** 2013/11/18
(86) **N° demande PCT/PCT Application No.:** US 2012/039576
(87) **N° publication PCT/PCT Publication No.:** 2012/162609
(30) **Priorités/Priorities:** 2011/05/25 (US61/489,893);
2011/09/12 (US61/533,544)


(51) **Cl.Int./Int.Cl.** *B01J 13/20* (2006.01),
B03D 1/001 (2006.01), *C08J 7/12* (2006.01)

(72) **Inventeurs/Inventors:**
ROTHMAN, PAUL J., US;
FERNALD, MARK R., US;
DIDDEN, FRANCIS K., US;
O'KEEFE, CHRISTIAN V., US;
KERSEY, ALAN D., US;
ADAMSON, DOUGLAS H., US

(73) **Propriétaire/Owner:**
CIDRA CORPORATE SERVICES INC., US

(74) **Agent:** GOWLING WLG (CANADA) LLP

(54) **Titre : BILLES/BULLES FONCTIONNALISEES AVEC DES MOLECULES SERVANT A ATTIRER ET A FIXER DES PARTICULES DE MINERAUX D'INTERET**
(54) **Title: SYNTHETIC BEADS/BUBBLES FUNCTIONALIZED WITH MOLECULES FOR ATTRACTING AND ATTACHING TO MINERAL PARTICLES OF INTEREST**



(57) **Abrégé/Abstract:**

A synthetic bead for use in mineral separation is described. The synthetic bead has a surface made of a synthetic material such as polymer and the synthetic material is functionalized with molecules having a functional group for attracting mineral particles to the

(57) Abrégé(suite)/Abstract(continued):

surface in a separation process. The synthetic beads can be placed in flotation cell containing a mixture of water, valuable material and unwanted material or in a pipeline where the mixture is transported from one location to another. The enriched synthetic beads carrying the mineral particles are separated from the unwanted materials in the mixture. The mineral particles are then released from the synthetic beads by means of low pH treatment, ultrasonic agitation, thermal or electromagnetic treatment.

Abstract of the Disclosure

A synthetic bead for use in mineral separation is described. The synthetic bead has a surface made of a synthetic material such as polymer and the synthetic material is functionalized with molecules having a functional group for attracting mineral particles to the surface in a separation process. The synthetic beads can be placed in flotation cell containing a mixture of water, valuable material and unwanted material or in a pipeline where the mixture is transported from one location to another. The enriched synthetic beads carrying the mineral particles are separated from the unwanted materials in the mixture. The mineral particles are then released from the synthetic beads by means of low pH treatment, ultrasonic agitation, thermal or electromagnetic treatment.

SYNTHETIC BEADS/BUBBLES FUNCTIONALIZED WITH MOLECULES FOR ATTRACTING AND ATTACHING TO MINERAL PARTICLES OF INTEREST

Background of the Invention

5 1. Technical Field

This invention relates generally to a method and apparatus for separating valuable material from unwanted material in a mixture, such as a pulp slurry.

2. Description of Related Art

10 In many industrial processes, flotation is used to separate valuable or desired material from unwanted material. By way of example, in this process a mixture of water, valuable material, unwanted material, chemicals and air is placed into a flotation cell. The chemicals are used to make the desired material hydrophobic and the air is used to carry the material to the surface of the flotation cell. When the
15 hydrophobic material and the air bubbles collide they become attached to each other. The bubble rises to the surface carrying the desired material with it.

The performance of the flotation cell is dependent on the air bubble surface area flux in the collection zone of the cell. The air bubble surface area flux is dependent on the size of the bubbles and the air injection rate. Controlling the air
20 bubble surface area flux and the bubble size distribution has traditionally been very difficult. This is a multivariable control problem and there are no dependable real time feedback mechanisms to use for control.

There is a need in the industry to provide a better way to separate valuable material from unwanted material, e.g., including in such a flotation cell, so as to
25 eliminate problems associated with using air bubbles in such a separation process.

Summary of the Invention

The present invention provides new and unique mineral separation techniques using synthetic beads or bubbles functionalized with molecules for attracting or attaching desired and/or selected mineral particles of interest, including
5 size-, weight- or magnetic-based polymer beads or bubbles.

According to some embodiments, the present invention may take the form of a synthetic bead or bubble having a solid-phase body comprising a surface in combination with a plurality of molecules attached to the surface, the molecules comprising a functional group selected for attracting or attaching one or more
10 mineral particles to the molecules. For the purpose of describing the present invention, the synthetic bead or bubble may also be referred to herein either as a synthetic bead or as a synthetic bubble.

According to some embodiments of the present invention, the solid-phase body may be made of a synthetic material comprising the molecules. By way of
15 example, the synthetic material may be selected from a group consisting of polyamides (nylon), polyesters, polyurethanes, phenol-formaldehyde, urea-formaldehyde, melamine-formaldehyde, polyacetal, polyethylene, polyisobutylene, polyacrylonitrile, poly(vinyl chloride), polystyrene, poly(methyl methacrylates), poly(vinyl acetate), poly(vinylidene chloride), polyisoprene, polybutadiene,
20 polyacrylates, poly(carbonate), phenolic resin and polydimethylsiloxane.

According to some embodiments of the present invention, the solid-phase body may include a shell providing the surface, the shell being made of a synthetic material comprising the molecules.

According to some embodiments of the present invention, the synthetic bead
25 may be configured to attract or attach to the mineral particles, e.g., in an aqueous

mixture, and the shell may comprise an interior part arranged to encapsulate a gaseous element such that the synthetic bead has a density less than the aqueous mixture.

According to some embodiments of the present invention, the synthetic bead
5 may be configured to attract or attach to the mineral particles, e.g., in an aqueous mixture, and the shell may comprise an interior part arranged to encapsulate a liquid having a chemical property different from the aqueous mixture.

According to some embodiments of the present invention, the synthetic bead
may be configured to attract or attach to the mineral particles, e.g., in an aqueous
10 mixture, and the shell may comprise an interior part arranged to encapsulate a solid-phase material different from the synthetic shell, and the solid-phase material may be selected to control the density of the synthetic bead relative to the density of the aqueous mixture.

According to some embodiments of the present invention, the shell may
15 comprise an interior part configured to encapsulate a magnetic material.

According to some embodiments of the present invention, the shell may
comprise an interior part configured to encapsulate a solid-phase material different
from the synthetic material.

According to some embodiments of the present invention, the solid-phase
20 body may comprise a core and a coating over the core for providing the surface, and the coating may be made of a synthetic material and the core is made of a core material different from the synthetic material. By way of example, the core material may be selected from a group consisting of glass, ceramic, metal and a polymer that is different from the synthetic material. The term "polymer" in this specification is

understood to mean a large molecule made of many units of the same or similar structure linked together.

According to some embodiments of the present invention, the surface of the solid-phase body may comprise physical structures configured to trap the mineral particles. By way of example, the physical structures may include grooves or dents or hair-like structures.

According to some embodiments of the present invention, the mineral particles may have a maximum size and the solid-phase body may have a body size greater than the maximum size. Alternatively, the mineral particles may have a minimum size and the solid-phase body may have a body size smaller than the minimum size.

According to some embodiments of the present invention, the functional group may be anionic for attracting or attaching the mineral particles to the surface.

According to some embodiments of the present invention, the functional group may take the form of a collector that is either ionic or non-ionic.

According to some embodiments of the present invention, the ion may be anionic or cationic. In other words, the collector may be anionic or cationic. The anion comprises an oxyhydriyl, including carboxylic, sulfates and sulfonates, and sulfhydryl bond.

According to some embodiments of the present invention, the functional group may have a covalent bond for attracting or attaching the mineral particles to the surface.

According to some embodiments of the present invention, the synthetic beads may be configured with a size depending on the particular application, or depending on the particular size of the mineral particle of interest.

According to some embodiments of the present invention, the synthetic beads may be configured with a size substantially larger than the mineral particles, with one or more mineral particles capable of attaching to a bead. According further to the invention, the beads may also be configured to have a positive buoyancy for applications related to flotation cells. According to a further embodiment of the invention, the bead may be configured to have a neutral or negative buoyancy for selecting and separating the mineral particles.

According to some embodiments of the present invention, the synthetic beads may be configured with a size substantially smaller than the mineral particles, with one or more beads capable of attaching to a mineral particle. According further to the invention, the beads may also be configured to have positive buoyancy for applications related to flotation cells. According to a further embodiment of the invention, the bead may be configured to have neutral or negative buoyancy for selecting and separating the mineral particles.

According to some embodiments of the present invention, the synthetic beads may be configured with a size substantially larger than the mineral particles, with only a portion of the surface of the bead functionalized to be attractive to and attach to one or more mineral particles. According further to the invention, the beads may also be configured to have positive buoyancy for applications related to flotation cells. According to a further embodiment of the invention, the bead may be configured to have neutral or negative buoyancy for selecting and separating the mineral particles.

According to some embodiments of the present invention, the synthetic beads may be configured with a plurality of size distribution, with some sized substantially

smaller than the mineral particles, some substantially the same size as the mineral particles, and some substantially larger than the mineral particles.

According to some embodiments of the present invention, the synthetic beads may be configured with a size less than 100 μm for attracting to the mineral particles, e.g., having a substantially similar size, smaller size or larger size, including in applications related to flotation cells. Alternatively, according to some embodiments of the present invention, the synthetic beads may be configured with a size in a range of about 1mm to 10mm for attaching to the mineral particles, including in applications related to a tailings pond. Furthermore, according to some
10 embodiments of the present invention, the synthetic beads may also be configured with a size of about 100 μm for attaching to the mineral particles, e.g., having a substantially similar size; or the synthetic beads may be configured with a size in a range of about 50-500 μm for attracting to the mineral particles, e.g., having a substantially similar size, smaller size or larger size; or the synthetic beads may be
15 configured with a size about 200 μm for attracting to the mineral particles, e.g., having a substantially similar size.

According to some embodiments of the present invention, the synthetic beads may be configured with a size in a range of about 100 μm to 10mm for attracting to the mineral particles.

20

The Method

According to some embodiments, the present invention may take the form of a method for producing a synthetic bead, comprising steps for providing a solid-phase body comprising a surface; and attaching a plurality of molecules to the

surface, the molecules comprising a functional group selected for attracting or attaching one or more mineral particles to the molecules.

According to some embodiments of the present invention, the solid-phase body may be made of a synthetic material, wherein the attaching step may comprise
5 bonding the molecules to the synthetic material.

According to some embodiments of the present invention, the solid-phase body may comprise a shell providing the surface of the solid-phase body, the shell may be made of a synthetic material, and the attaching step may comprise bonding the molecules to the synthetic material.

10 According to some embodiments of the present invention, the synthetic bead may be configured to attract or attach to the mineral particles, e.g., in an aqueous mixture, the shell may comprise an interior part, and the method may further comprise encapsulating a gaseous element in the interior part such that the synthetic bead has a density smaller than the aqueous mixture.

15 According to some embodiments of the present invention, the synthetic bead may be configured to attract or attach to the mineral particles, e.g., in an aqueous mixture, the shell may comprise an interior part, and the method may further comprise encapsulating a solid-phase material in the interior part, the solid-phase material being different from the synthetic material, and the solid-phase material
20 being selected to control the density of the synthetic bead relative to the density of the aqueous mixture.

According to some embodiments of the present invention, the synthetic bead may be functionalized to be hydrophobic, in that the functional group in the surface molecules is configured to cause the surface to be hydrophobic.

According to some embodiments of the present invention, the synthetic bead can be made of a hydrophobic polymer or coated with a hydrophobic polymer, wherein the polymer may be selected from a group consisting of polystyrene, poly(d,l-lactide), poly(dimethylsiloxane), polypropylene, polyacrylic, polyethylene, polysiloxanates, silicone alkyd copolymer, and fluoroalkylsilane. However, the list is not necessarily exhaustive.

Synthetic Beads/Bubbles Functionalized with Polymer-Based Materials

According to some embodiments, the present invention may take the form of apparatus for use in, or forming part of, a separation process to be implemented in separation processor technology, where the apparatus features synthetic bubbles or beads configured with a polymer or polymer-based material functionalized to attach to a valuable material in a mixture so as to form enriched synthetic bubbles or beads having the valuable material attached thereto, and also configured to be separated from the mixture based at least partly on a difference in a physical property between the enriched synthetic bubbles or beads having the valuable material attached thereto and the mixture.

The separation process may be implemented in separation processor technology which combines the synthetic bubbles or beads and the mixture, and which provides the enriched synthetic bubbles or beads having the valuable material attached thereto that are separated from the mixture based at least partly on the difference in the physical property between the enriched synthetic bubbles or beads having the valuable material attached thereto and the mixture.

Size-Based Separation

The separation process may be implemented using sized-based separation, where the synthetic bubbles or beads may be configured to be separated from the mixture based at least partly on the difference between the size of the enriched
5 synthetic bubbles or beads having the valuable material attached thereto in relation to the size of unwanted material in the mixture.

According to some embodiments of the present invention, the synthetic bubbles or beads may be configured either so that the size of the synthetic bubbles or beads is greater than a maximum ground ore particle size in the mixture, or so
10 that the size of the synthetic bubbles or beads is less than a minimum ground ore particle size in the mixture.

According to some embodiments of the present invention, the synthetic bubbles or beads may be configured as solid polymer bubbles or beads.

According to some embodiments of the present invention, the synthetic
15 bubbles or beads may be configured with a core material of sand, silica or other suitable material and also configured with a polymer encapsulation.

Weight-Based Separation

The separation process may be implemented using weight-based separation,
20 where the synthetic bubbles or beads are configured to be separated from the mixture based at least partly on the difference between the weight of the enriched synthetic bubbles or beads having the valuable material attached thereto in relation to the weight of unwanted material in the mixture.

According to some embodiments of the present invention, the synthetic
25 bubbles or beads may be configured so that the weight of the synthetic bubbles or

beads is greater than a maximum ground ore particle weight in the mixture, or so that the weight of the synthetic bubbles or beads is less than a minimum ground ore particle weight in the mixture.

According to some embodiments of the present invention, the synthetic
5 bubbles or beads may be configured as solid polymer bubbles or beads.

According to some embodiments of the present invention, the synthetic bubbles or beads may be configured with a core material of magnetite, air or other suitable material and also configured with a polymer encapsulation.

10 Magnetic-Based Separation

The separation process may be implemented using magnetic-based separation, where the synthetic bubbles or beads may be configured to be separated from the mixture based at least partly on the difference between the para-, ferri-, ferro-magnetism of the enriched synthetic bubbles or beads having the valuable
15 material attached thereto in relation to the para-, ferri, ferro-magnetism of unwanted material in the mixture.

According to some embodiments of the present invention, the synthetic bubbles or beads may be configured so that the para-, ferri-, ferro-magnetism of the synthetic bubbles or beads is greater than the para-, ferri-, ferro-magnetism of the
20 unwanted ground ore particle in the mixture.

According to some embodiments of the present invention, the synthetic bubbles or beads may be configured with a ferro-magnetic or ferri-magnetic core that attract and attach to paramagnetic surfaces and also configured with a polymer encapsulation.

25

Density-based Separation

The separation process may be implemented using density-based separation, where the synthetic bubbles or beads may be configured to be separated from the mixture based at least partly on the difference between the density of the enriched
5 synthetic bubbles or beads having the valuable material attached thereto and the density of the mixture, consistent with that disclosed in PCT application no. PCT/US12/39528. Alternatively, according some embodiments of the present invention, the synthetic bubbles or beads may be configured to be hollow and have substantially the same density as the mixture so as to be at least partly suspended
10 and separated using other techniques, including by magnetism, or including by heating so as to change the density of the synthetic bubbles or beads relative to the mixture.

Brief Description of the Drawing

15 Referring now to the drawing, which are not drawn to scale, the foregoing and other features and advantages of the present invention will be more fully understood from the following detailed description of illustrative embodiments, taken in conjunction with the accompanying drawing in which like elements are numbered alike:

20 Figures 1-6 show respectively sized-based beads and bubbles, weight-based polymer beads and bubbles, and magnetic-based beads and bubbles according to some embodiments of the present invention, including

Figures 1 and 2 that respectively show a size-based solid polymer bead and bubble and a size-based bead and bubble having a core material and a polymer
25 encapsulation;

Figures 3 and 4 that respectively show a weight-based solid polymer bead and bubble and a weight-based bead and bubble having a core material and a polymer encapsulation; and

Figures 5 and 6 that respectively show a magnetic-based bead and bubble having a ferro-, or ferri-, or para-magnetic core and a polymer encapsulation.

Figure 7a shows a generalized synthetic bead which can be a size-based bead or bubble, weight-based polymer bead and bubble, and magnetic-based bead and bubble, according to some embodiments of the present invention.

Figure 7b illustrates an enlarged portion of the synthetic bead showing a molecule or molecular segment for attaching a function group to the surface of the synthetic bead, according to some embodiments of the present invention.

Figure 8a illustrates a synthetic bead having a body made of a synthetic material, according to some embodiments of the present invention.

Figure 8b illustrates a synthetic bead with a synthetic shell, according to some embodiments of the present invention.

Figure 8c illustrates a synthetic bead with a synthetic coating, according to some embodiments of the present invention.

Figure 8d illustrates a synthetic bead taking the form of a porous block, according to some embodiment of the present invention.

Figure 9a illustrates a synthetic bead having an elliptical shape, according to some embodiments of the present invention.

Figure 9b illustrates a synthetic bead having a cylindrical shape, according to some embodiments of the present invention.

Figure 9c illustrates a synthetic bead having a shape of a block, according to some embodiments of the present invention.

Figure 9d illustrates a synthetic bead having an irregular shape, according to some embodiments of the present invention.

Figure 10a illustrates the surface of a synthetic bead with grooves and/or rods, according to some embodiments of the present invention.

5 Figure 10b illustrates the surface of a synthetic bead with dents and/or holes, according to some embodiments of the present invention.

Figure 10c illustrates the surface of a synthetic bead with stacked beads, according to some embodiments of the present invention.

10 Figure 10d illustrates the surface of a synthetic bead with hair-like physical structures, according to some embodiments of the present invention.

Figure 11 is a diagram of a flotation system, process or apparatus according to some embodiments of the present invention.

Figure 12 is a diagram of a flotation cell or column that may be used in place of the flotation cell or column that forms part of the flotation system, process or
15 apparatus shown in Figure 11 according to some embodiments of the present invention.

Figure 13a shows a generalized synthetic bead functionalized to be hydrophobic, wherein the bead can be a size-based bead or bubble, weight-based polymer bead and bubble, and magnetic-based bead and bubble, according to some
20 embodiments of the present invention.

Figure 13b illustrates an enlarged portion of the hydrophobic synthetic bead showing a wetted mineral particle attaching the hydrophobic surface of the synthetic bead, according to some embodiments of the present invention.

Figure 13c illustrates an enlarged portion of the hydrophobic synthetic bead showing a hydrophobic non-mineral particle attaching the hydrophobic surface of the synthetic bead, according to some embodiments of the present invention.

Figures 14a illustrates a mineral particle being attached to a number of much smaller synthetic beads at the same time.

Figures 14b illustrates a mineral particle being attached to a number of slightly larger synthetic beads at the same time.

Figures 15a illustrates a wetted mineral particle being attached to a number of much smaller hydrophobic synthetic beads at the same time.

Figures 15b illustrates a wetted mineral particle being attached to a number of slightly larger hydrophobic synthetic beads at the same time.

Figures 16a and 16b illustrate some embodiments of the present invention wherein the synthetic bead or bubble have one portion functionalized to have collector molecules and another portion functionalized to be hydrophobic.

15

Detailed Description of the Invention

Figures 1-6 show the present invention in the form of apparatus or material for use in, or forming part of, a separation process to be implemented in separation processor technology, the apparatus featuring synthetic bubbles or beads indicated by arrows 10 (Fig. 1), 20 (Fig. 2), 30 (Fig. 3), 40 (Fig. 4), 50 (Fig. 5), 60 (Fig. 6), configured with a polymer or polymer-based material 11 (Fig. 1), 21 (Fig. 2), 31 (Fig. 3), 41 (Fig. 4), 51 (Fig. 5), 61 (Fig. 6) functionalized to attach to a valuable material 12 (Fig. 1), 22 (Fig. 2), 32 (Fig. 3), 42 (Fig. 4), 52 (Fig. 5), 62 (Fig. 6) in a mixture so as to form an enriched synthetic bubble or bead generally indicated as 15 (Fig. 1), 25 (Fig. 2), 35 (Fig. 3), 45 (Fig. 3), 55 (Fig. 5), 65 (Fig. 6) having the valuable material

25

12 (Fig. 1), 22 (Fig. 2), 32 (Fig. 3), 42 (Fig. 4), 52 (Fig. 5), 62 (Fig. 6) attached thereto, consistent with that disclosed herein, and also configured to be separated from the mixture based at least partly on a difference in a physical property between the enriched synthetic bubbles or beads 15 (Fig. 1), 25 (Fig. 2), 35 (Fig. 3), 45 (Fig. 3), 55 (Fig. 5), 65 (Fig. 6) having the valuable material 12 (Fig. 1), 22 (Fig. 2), 32 (Fig. 3), 42 (Fig. 4), 52 (Fig. 5), 62 (Fig. 6) attached thereto. The mixture can be a pulp slurry, for example.

In Figure 1, the synthetic bubble or bead 10 is a size-based solid polymer bead and bubble 11 functionalized to attach to the valuable material 12 of interest in the mixture and to be separated from the mixture based on size. In Figure 2, the synthetic bubble or bead 20 is a size-based bead and bubble 20 having a core material 21 and a polymer encapsulation 23 functionalized to attach to the valuable material 22 of interest in the mixture and to be separated from the mixture based on size. By way of example, the core material 21 may include materials such as sand, silica or other suitable material either now known or later developed in the future.

Polymers or polymer-based materials that may be functionalized to attach to such a valuable material, such as valuable material 12 (Fig. 1), 22 (Fig. 2), 32 (Fig. 3), 42 (Fig. 4), 52 (Fig. 5), 62 (Fig. 6), of interest, such as copper, gold, nickel, lead or other mineral are known in the art, and the scope of the invention is not intended to be limited to any particular type or kind thereof. Embodiments are envisioned using polymers or polymer-based materials now known and later developed in the future. It should be noted that the bubbles or beads are referred herein as synthetic bubbles or beads. The term "polymer" in this disclosure may be understood to mean a large molecule made of many units of the same or similar structure linked together. The unit can be a monomer or an oligomer which forms the basis of, for example,

polyamides (nylon), polyesters, polyurethanes, phenol-formaldehyde, urea-formaldehyde, amide, melamine-formaldehyde, polyacetal, polyethylene, polyisobutylene, polyacrylonitrile, poly(vinyl chloride), polystyrene, poly(methyl methacrylates), poly(vinyl acetate), poly(vinylidene chloride), polyisoprene, 5 polybutadiene, polyacrylates, poly(carbonate), phenolic resin and polydimethylsiloxane. The list is not necessarily exhaustive. Thus, the synthetic material can be hard or rigid like plastic or soft and flexible like an elastomer. While the physical properties of the synthetic beads can vary, the surface of the synthetic beads is chemically functionalized to provide one or more functional groups to attract 10 or attach to mineral particles. Alternatively, the entire synthetic material may be functionalized, such that if the surface of the material is worn, abraded or otherwise consumed, new functionalized material is exposed to attract and attach to the mineral particles. (By way of example, the term "functional group" may be understood to be a group of atoms responsible for the characteristic reactions of a 15 particular compound, including which define the structure of a family of compounds and determine its properties.) The terms "valuable material" and "mineral particle" are used herein interchangeably.

According to the present invention, the synthetic bubbles or beads 10 or 20 in Figures 1 and 2 may be configured to be separated from the mixture based at least 20 partly on the difference between the size of the enriched synthetic bubbles or beads having the valuable material 12, 22 attached thereto in relation to the size of unwanted material in the mixture. For example, the synthetic bubble or bead 10 or 20 may be configured either so that the size of the synthetic bubbles or beads 10 or 20 is greater than a maximum ground ore particle size in the mixture, or so that the 25 size of the synthetic bubbles or beads 10 or 20 is less than a minimum ground ore

particle size in the mixture. When the particle size is large, a small bubble or bead may not be able to lift the valuable material upward. When the particle size is small, the flow around a large bubble or bead may cause the valuable material to move away from the bubble or bead. Thus, it may be more efficient to use smaller bubbles
5 or beads to collect the valuable material in a small ground.

In Figure 3, the synthetic bubble or bead 30 is a weight-based solid polymer bead and bubble 31 functionalized to attach to the valuable material 32 of interest in the mixture and to be separated from the mixture based on weight. In Figure 4, the synthetic bubbles or beads 40 is a weight-based bead and bubble 40 having a core
10 material 41 and a polymer encapsulation 43 functionalized to attach to the valuable material 42 of interest in the mixture and to be separated from the mixture based on weight. The core material 41 may be made of materials such as magnetite, air or other suitable material and also configured with a polymer encapsulation.

According to the present invention, the synthetic bubbles or beads 30, 40 may
15 be configured to be separated from the mixture based at least partly on the difference between the weight of the enriched synthetic bubbles or beads having the valuable material attached thereto in relation to the weight of unwanted material in the mixture. For example, the synthetic bubbles or beads 30, 40 may be configured so that the weight of the synthetic bubbles or beads is greater than a maximum
20 ground ore particle weight in the mixture, or so that the weight of the synthetic bubbles or beads is less than a minimum ground ore particle weight in the mixture.

In Figure 5, the synthetic bead or bubble 50 is shown as a magnetic-based bead and bubble having a ferro- or ferri-magnetic core 51 and a polymer
encapsulation 53, such that the ferro-magnetic or ferri-magnetic core 51 attracts to
25 paramagnetic surfaces. In Figure 6, the synthetic bead or bubble is shown as a

magnetic-based bead and bubble having a para-magnetic core 61 and a polymer encapsulation 63, such that the para-magnetic core attracts to magnetized surfaces.

According to the present invention, the synthetic bubbles or beads 50, 60 may be configured to be separated from the mixture based at least partly on the difference between the para-, ferri-, ferro-magnetism of the enriched synthetic bubbles or beads having the valuable material 52, 62 attached thereto in relation to the para-, ferri-, ferro-magnetism of unwanted material in the mixture.

For aiding a person of ordinary skill in the art in understanding various embodiments of the present invention, Figure 7a shows a generalized synthetic bead and Figure 7b shows an enlarged portion of the surface. The synthetic bead can be a size-based bead or bubble, weight-based polymer bead and bubble, and magnetic-based bead and bubble as described in conjunction with Figures 1 to 6. As shown in Figures 7a and 7b, the synthetic bead 70 has a bead body to provide a bead surface 74. At least the outside part of the bead body is made of a synthetic material, such as polymer, so as to provide a plurality of molecules or molecular segments 76 on the surface 74. The molecule 76 is used to attach a chemical functional group 78 to the surface 74. In general, the molecule 76 can be a hydrocarbon chain, for example, and the functional group 78 can have an anionic bond (or anion) for bonding a mineral, such as copper, to the surface 74. A xanthate, for example, has both the functional group 78 and the molecular segment 76 to be incorporated into the polymer that is used to make the synthetic bead 70. The functional group 78 is also known as a collector that is either ionic or non-ionic. The ion can be anionic or cationic. An anion includes oxyhydriyl, such as carboxylic, sulfates and sulfonates, and sulfhydryl, such as xanthates and dithiophosphates. Other molecules or compounds that can be used to provide the function group 78 include, but are not

limited to, thionocarboamates, thioureas, xanthogens, monothiophosphates, hydroquinones and polyamines.

Similarly, a chelating agent can be incorporated into or onto the polymer as a collector site for attracting a mineral, such as copper. As shown in Figure 7b, a mineral particle 72 is attached to the functional group 78 on the molecule 76. In general, the mineral particle 72 is much smaller than the synthetic bead 70. Many mineral particles 72 can be attracted to or attached to the surface 74 of a synthetic bead 70. When the mineral particles 72 are very fine, smaller synthetic beads 70 can also be used.

In some embodiments of the present invention, a synthetic bead may take the form of a solid-phase body made of a synthetic material, such as polymer. (By way of example, the term "solid-phase body" is understood herein to be a body having a cohesive force of matter that is strong enough to keep the molecules or atoms in the given positions, restraining the thermal mobility.) The polymer can be rigid or elastomeric. An elastomeric polymer can be polyisoprene, polybutadiene or natural rubber, for example. The body has a surface comprising a plurality of molecules with one or more functional groups for attracting or attaching mineral particles to the surface. A polymer having a functional group to attract or collect mineral particles is referred to as a functionalized polymer. In one embodiment, the entire body 82 of the synthetic bead 80 is made of the same functionalized material, as shown in Figure 8a. In another embodiment, the bead body is a shell, as shown in Figure 8b. The shell 84 can be formed by way of expansion, such as thermal expansion or pressure reduction.

The shell 84 can be formed as a micro-bubble or a balloon. In Figure 8b, the shell 84, which is made of functionalized material, has an interior part 86. The

interior part 86 can be filled with air or gas to aid buoyancy, for example. The interior part 86 can be used to contain a liquid to be released during the mineral separation process. The encapsulated liquid can be a polar liquid or a non-polar liquid, for example. The encapsulated liquid can contain a depressant composition for the enhanced separation of copper, nickel, zinc, lead in sulfide ores in the flotation stage, for example. The shell 84 can be used to encapsulate a powder which can have a magnetic property so as to cause the synthetic bead to be magnetic, for example. The encapsulated liquid or powder may contain monomers, oligomers or short polymer segments for wetting the surface of mineral particles when released from the beads. For example, each of the monomers or oligomers may contain one functional group for attaching to a mineral particle and one charge species for attaching the wetted mineral particle to the synthetic bead. The shell 84 can be used to encapsulate a solid core, such as Styrofoam to aid buoyancy, for example. In yet another embodiment, only the coating of the bead body can be made of functionalized polymer. As shown in Figure 8c, the synthetic bead can have a core 90 made of ceramic, glass or metal and only the surface of core 90 can have a coating 88 made of functionalized polymer. The core 90 can be a hollow core or a filled core depending on the applications. The core 90 can be a micro-bubble, a sphere or balloon. For example, a filled core made of metal makes the density of the synthetic bead to be higher than the density of the pulp slurry, for example. The core 90 can be made of a magnetic material so that the para-, ferri-, ferro-magnetism of the synthetic bead is greater than the para-, ferri-, ferro-magnetism of the unwanted ground ore particle in the mixture. According to some embodiments, the synthetic bead can be configured with a ferro-magnetic or ferri-magnetic core that attract and attach to paramagnetic surfaces. A core 90 made of glass or ceramic can be used

to make the density of the synthetic bead substantially equal to the density of the pulp slurry so that when the synthetic beads are mixed into the pulp slurry for mineral collection, the beads can be in a suspension state.

According to a different embodiment of the present invention, the synthetic
5 bead 80 can be a porous block or take the form of a sponge or foam with multiple segregated gas filled chambers. The combination of air and the synthetic beads 80 can be added to traditional naturally aspirated flotation cell.

It should be understood that the use of the term "bead" is not intended to limit the shape of the synthetic bead of the present invention to being spherical, as shown
10 in Figure 7. In some embodiments of the present invention, the synthetic bead 80 can have an elliptical shape as shown in Figure 9a. The synthetic bead can have a cylindrical shape as shown in Figure 9b. The synthetic bead can have a shape of a block as shown in Figure 9c. Furthermore, the synthetic bead can have an irregular shape, as shown in Figure 9d. In effect, the scope of the invention is not intended to
15 be limited to any particular type or kind of shape of the synthetic bead 80.

It should also be understood that the surface of a synthetic bead, according to the present invention, is not limited to an overall smooth surface as shown in Figure 7a. In some embodiments of the present invention, the surface can be irregular and rough. For example, the surface 74 can have some physical structures 92 like
20 grooves or rods as shown in Figure 10a. The surface 74 can have some physical structures 94 like holes or dents as shown in Figure 10b. The surface 74 can have some physical structures 96 formed from stacked beads as shown in Figure 10c. The surface 74 can have some hair-like physical structures 98 as shown in Figure 10d. In addition to the functional groups on the synthetic beads that attract mineral
25 particles to the bead surface, the physical structures can help trapping the mineral

particles on the bead surface. The surface 74 can be configured to be a honeycomb surface or a sponge-like surface for trapping the mineral particles and/or increasing the contacting surface. In effect, the scope of the invention is not intended to be limited to any particular type or kind of surface of the synthetic bead 80.

5 It should be noted that the synthetic beads of the present invention can be realized by a different way to achieve the same goal. Namely, it is possible to use a different means to attract the mineral particles to the surface of the synthetic beads. For example, the surface of the polymer beads or shells can be functionalized with a hydrophobic chemical molecule or compound. Alternatively, the surface of beads
10 made of glass, ceramic and metal can be coated with hydrophobic chemical molecules or compounds. Using the coating of glass beads as an example, polysiloxanates can be used to functionalize the glass beads in order to make the synthetic beads. In the pulp slurry, xanthate and hydroxamate collectors can also be added therein for collecting the mineral particles and making the mineral particles
15 hydrophobic. When the synthetic beads are used to collect the mineral particles in the pulp slurry having a pH value around 8-9, it is possible to release the mineral particles on the enriched synthetic beads from the surface of the synthetic beads in an acidic solution, such as a sulfuric acid solution. According to some embodiment, it may also be possible to release the mineral particles carried with the enriched
20 synthetic beads by sonic agitation, such as ultrasonic waves, or simply by washing it with water.

Figures 11 and 12: Flotation Apparatus

By way of example, Figure 11 shows the present invention is the form of
25 apparatus 810, having a flotation cell or column 812 configured to receive a mixture

of fluid (e.g. water), valuable material and unwanted material, e.g., a pulp slurry 814; receive synthetic bubbles or beads 70 (Fig. 7, for example) that are constructed to be buoyant when submerged in the pulp slurry or mixture 814 and functionalized to control the chemistry of a process being performed in the flotation cell or column, including to attach to the valuable material in the pulp slurry or mixture 814; and provide enriched synthetic bubble or beads 818 having the valuable material attached thereon. By way of example, the synthetic bubbles or beads 70 may be made from polymer or polymer-based materials, or silica or silica-based materials, or glass or glass-based materials, although the scope of the invention is intended to include other types or kinds of material either now known or later developed in the future. For the purpose of describing one example of the present invention, in Figure 11 the synthetic bubbles or beads are shown as polymer or polymer-based bubbles labeled 70, and the enriched synthetic bubble or beads 818 are shown as enriched polymer or polymer-based bubbles labeled 818. The flotation cell or column 812 is configured with a top portion or piping 820 to provide the enriched polymer or polymer-based bubbles 818 from the flotation cell or column 812 for further processing consistent with that set forth herein.

The flotation cell or column 812 may be configured with a top part or piping 822, e.g., having a valve 822a, to receive the pulp slurry or mixture 814 and also with a bottom part or piping 824 to receive the polymer or polymer-based bubbles 70. In operation, the buoyancy of the polymer or polymer-based bubbles 70 causes them to float upwardly from the bottom to the top of the flotation cell or column 812 through the pulp slurry or mixture 814 in the flotation cell or column 812 so as to collide with the water, valuable material and unwanted material in the pulp slurry or mixture 814. The functionalization of the polymer or polymer-based bubbles 70 causes them to

attach to the valuable material in the pulp slurry or mixture 814. As a result of the collision between the polymer or polymer-based bubbles 70 and the water, valuable material and unwanted material in the pulp slurry or mixture 814, and the attachment of the polymer or polymer-based bubbles 70 and the valuable material in the pulp
5 slurry or mixture 814, the enriched polymer or polymer-based bubbles 70 having the valuable material attached thereto will float to the top of the flotation cell 812 and form part of the froth formed at the top of the flotation cell 812. The flotation cell 812 may include a top part or piping 820 configured to provide the enriched polymer or polymer-based bubbles 818 having the valuable material attached thereto, which
10 may be further processed consistent with that set forth herein. In effect, the enriched polymer or polymer-based bubbles 818 may be taken off the top of the flotation cell 812 or may be drained off by the top part or piping 820.

The flotation cell or column 812 may be configured to contain an attachment rich environment, including where the attachment rich environment has a high pH, so
15 as to encourage the flotation recovery process therein. The flotation recovery process may include the recovery of ore particles in mining, including copper. The scope of the invention is not intended to be limited to any particular type or kind of flotation recovery process either now known or later developed in the future. The scope of the invention is also not intended to be limited to any particular type or kind
20 of mineral of interest that may form part of the flotation recovery process either now known or later developed in the future.

According to some embodiments of the present invention, the polymer or polymer-based bubbles 70 may be configured with a surface area flux by controlling some combination of the size of the polymer or polymer-based bubbles 70 and/or the
25 injection rate that the pulp slurry or mixture 814 is received in the flotation cell or

column 812. The polymer or polymer-based bubbles 70 may also be configured with a low density so as to behave like air bubbles. The polymer or polymer-based bubbles 70 may also be configured with a controlled size distribution that may be customized to maximize recovery of different feed matrixes to flotation as valuable material quality changes, including as the quality of the ore changes.

According to some embodiments of the present invention, the flotation cell or column 812 may be configured to receive the polymer or polymer-based bubbles 70 together with air, where the air is used to create a desired froth layer in the mixture in the flotation cell or column 812 in order to achieve a desired grade of valuable material. The polymer or polymer-based bubbles 70 may be configured to lift the valuable material to the surface of the mixture in the flotation cell or column.

The Thickener 828

The apparatus 10 may also include piping 826 having a valve 826a for providing tailings to a thickener 828 configured to receive the tailings from the flotation cell or column 812. The thickener 828 includes piping 830 having a valve 830a to provide thickened tailings. The thickener 828 also includes suitable piping 832 for providing reclaimed water back to the flotation cell or column 812 for reuse in the process. Thickeners like element 828 are known in the art, and the scope of the invention is not intended to be limited to any particular type or kind either now known or later developed in the future.

The Bead Recovery Process or Processor 850

According to some embodiments of the present invention, the apparatus 810 may further comprises a bead recovery process or processor generally indicated as

850 configured to receive the enriched polymer or polymer-based bubbles 818 and provide reclaimed polymer or polymer-based bubbles 852 without the valuable material attached thereon so as to enable the reuse of the polymer or polymer-based bubbles 852 in a closed loop process. By way of example, the bead recovery
5 process or processor 850 may take the form of a washing station whereby the valuable material is mechanically, chemically, or electro-statically removed from the polymer or polymer-based bubbles 818.

The bead recovery process or processor 850 may include a second flotation cell or column 854 having piping 856 with a valve 858a configured to receive the
10 enriched polymer bubbles or beads 818; and substantially release the valuable material from the polymer bubbles or beads 818, and also having a top part or piping 857 configured to provide the reclaimed polymer bubbles or beads 852, substantially without the valuable material attached thereon. The second flotation cell or column 854 may be configured to contain a release rich environment, including where the
15 release rich environment has a low pH, or including where the release rich environment results from ultrasonic waves pulsed into the second flotation cell or column 854.

The bead recovery process or processor 850 may also include piping 858 having a valve 856a for providing concentrated minerals to a thickener 860
20 configured to receive the concentrated minerals from the flotation cell or column 854. The thickener 860 includes piping 862 having a valve 862a to provide thickened concentrate. The thickener 860 also includes suitable piping 864 for providing reclaimed water back to the second flotation cell or column 854 for reuse in the process. Thickeners like element 860 are known in the art, and the scope of the

invention is not intended to be limited to any particular type or kind either now known or later developed in the future.

Embodiments are also envisioned in which the enriched synthetic beads or bubbles are placed in a chemical solution so the valuable material is dissolved off, or
5 are sent to a smelter where the valuable material is burned off, including where the synthetic beads or bubbles are reused afterwards.

The Collision Technique

Figure 12 shows alternative apparatus generally indicated as 900 in the form
10 of an alternative flotation cell 901 that is based at least partly on a collision technique between the mixture and the synthetic bubbles or beads, according to some embodiments of the present invention. The mixture 902, e.g. the pulp slurry, may be received in a top part or piping 904, and the synthetic bubbles or beads 906 may be received in a bottom part or piping 908. The flotation cell 901 may be configured to
15 include a first device 910 for receiving the mixture 902, and also may be configured to include a second device 912 for receiving the polymer-based materials. The first device 910 and the second device 912 are configured to face towards one another so as to provide the mixture 902 and the synthetic bubbles or beads 906, e.g., polymer or polymer-based materials, using the collision technique. In Figure 12, the
20 arrows 910a represent the mixture being sprayed, and the arrows 912a represent the synthetic bubbles or beads 906 being sprayed towards one another in the flotation cell 901.

In operation, the collision technique causes vortices and collisions using enough energy to increase the probability of touching of the polymer or polymer-
25 based materials 906 and the valuable material in the mixture 902, but not too much

energy to destroy bonds that form between the polymer or polymer-based materials 906 and the valuable material in the mixture 902. Pumps, not shown, may be used to provide the mixture 902 and the synthetic bubbles or beads 906 are the appropriate pressure in order to implement the collision technique.

5 By way of example, the first device 910 and the second device 912 may take the form of shower-head like devices having a perforated nozzle with a multiplicity of holes for spraying the mixture and the synthetic bubbles or beads towards one another. Shower-head like devices are known in the art, and the scope of the invention is not intended to be limited to any particular type or kind thereof either now
10 known or later developed in the future. Moreover, based on that disclosed in the instant patent application, a person skilled in the art without undue experimentation would be able to determine the number and size of the holes for spraying the mixture 902 and the synthetic bubbles or beads 906 towards one another, as well as the appropriate pumping pressure in order to provide enough energy to increase the
15 probability of touching of the polymer or polymer-based materials 906 and the valuable material in the mixture 902, but not too much energy to destroy bonds that form between the polymer or polymer-based materials 906 and the valuable material in the mixture 902.

 As a result of the collision between the synthetic bubbles or beads 906 and
20 the mixture, enriched synthetic bubbles or beads having the valuable material attached thereto will float to the top and form part of the froth in the flotation cell 901. The flotation cell 901 may include a top part or piping 914 configured to provide enriched synthetic bubbles or beads 916, e.g., enriched polymer bubbles as shown, having the valuable material attached thereto, which may be further processed
25 consistent with that set forth herein.

The alternative apparatus 900 may be used in place of the flotation columns or cells, and inserted into the apparatus or system shown in Figure 11, and may prove to be more efficient than using the flotation columns or cells.

It should be understood that the sized-based bead or bubble, weight-based bead or bubble, magnetic-based bead or bubble as described in conjunction with Figures 1 to 6 can be functionalized to be hydrophobic so as to attract mineral particles. Figure 13a shows a generalized hydrophobic synthetic bead, Figure 13b shows an enlarged portion of the bead surface and a mineral particle, and Figure 13c shows an enlarged portion of the bead surface and a non-mineral particle. As shown in Figure 13a the hydrophobic synthetic bead 170 has a polymer surface 174 and a plurality of particles 172, 172' attached to the polymer surface 174. Figure 13b shows an enlarged portion of the polymer surface 174 on which a plurality of molecules 179 rendering the polymer surface 174 hydrophobic.

A mineral particle 171 in the slurry, after combined with one or more collector molecules 73, becomes a wetted mineral particle 172. The collector molecule 73 has a functional group 78 attached to the mineral particle 171 and a hydrophobic end or molecular segment 76. The hydrophobic end or molecular segment 76 is attracted to the hydrophobic molecules 179 on the polymer surface 174. Figure 13c shows an enlarged portion of the polymer surface 174 with a plurality of hydrophobic molecules 179 for attracting a non-mineral particle 172'. The non-mineral particle 172' has a particle body 171' with one or more hydrophobic molecular segments 76 attached thereto. The hydrophobic end or molecular segment 76 is attracted to the hydrophobic molecules 179 on the polymer surface 174. The term "polymer" in this specification means a large molecule made of many units of the same or similar structure linked together. Furthermore, the polymer associated with Figures 13a-13c

can be naturally hydrophobic or functionalized to be hydrophobic. Some polymers having a long hydrocarbon chain or silicon-oxygen backbone, for example, tend to be hydrophobic. Hydrophobic polymers include polystyrene, poly(d,l-lactide), poly(dimethylsiloxane), polypropylene, polyacrylic, polyethylene, etc. The bubbles or
5 beads, such as synthetic bead 170 can be made of glass to be coated with hydrophobic silicone polymer including polysiloxanates so that the bubbles or beads become hydrophobic. The bubbles or beads can be made of metal to be coated with silicone alkyd copolymer, for example, so as to render the bubbles or beads hydrophobic. The bubbles or beads can be made of ceramic to be coated with
10 fluoroalkylsilane, for example, so as to render the bubbles and beads hydrophobic. The bubbles or beads can be made of hydrophobic polymers, such as polystyrene and polypropylene to provide a hydrophobic surface.

A Physical Property

15 For the purpose of describing and understanding the present invention, a physical property is understood to be any quality that is a measurable whose value describes a physical system's state. Changes in the physical properties of a system can be used to describe its transformations (or evolutions between its momentary states). Physical properties can be intensive or extensive, where an intensive
20 property does not depend on the size or amount of matter in the object, while an extensive property does. Physical properties are contrasted with chemical properties which determine the way a material behaves in a chemical reaction. Physical properties are properties that do not change the chemical nature of matter.

By way of example, the present invention is described in relation to physical
25 property of the synthetic beads or bubbles that take the form of size, weight,

magnetism and density. However, embodiments of the present invention are envisioned using other types or kinds of physical properties either now known or later developed in the future, including electrostatic charge, as well as other types or kinds of physical properties that would allow, or provide for, the synthetic bead
5 having the valuable material attached thereto to be separated from the mixture based at least partly on a difference in the physical property between the enriched synthetic bubbles or beads having the valuable material attached thereto and the mixture, consistent with that set forth herein.

10 Applications

The scope of the invention is described in relation to mineral separation, including the separation of copper or other minerals from ore.

By way of example, applications are envisioned to include rougher, scavenger, cleaner and rougher/scavenger separation cells in the production stream,
15 replacing, supplementing or modifying the traditional flotation machines.

Tailings scavenger cells are used to scavenge the unrecovered minerals from a tailings stream.

Tailings cleaning cell is used to clean unwanted material from the tailings stream before it is sent to the disposal pond.

20 Tailings reclamation machine that is placed in the tailings pond or otherwise used to recover valuable mineral that has been sent to the tailings pond.

In a typical mineral separation process, an ore is blasted into manageable pieces of mineral-containing rock. The blasted ore is then subjected to grinding where the rock is crushed into small particles in the order of 100 μm . The particles
25 are referred herein as mineral particles but they also contain silicate minerals or

oxide minerals of little or no value. These mineral particles, along with gangue minerals, are mixed with water into a pulp slurry. The synthetic beads, according to some embodiments of the present invention, are used to attract the mineral particles to the bead surface. The enriched synthetic beads, which are the synthetic beads
5 having the mineral particles attached thereon, are then separated from the unwanted rock or gangue minerals by means of size-based separation, weight-based separation and/or magnetic-based separation. For example, the separation can take place in a flotation cell, in a pipeline where the pulp slurry is transported from one location to another location, and in a mixing vat. Thereafter the mineral particles
10 attached to the enriched synthetic beads are released from the synthetic beads for further processing, such as smelting. The releasing of the mineral particles from the synthetic beads can be carried out in different manners. For example, the enriched synthetic beads can be configured to contact a solution with a low pH value that interrupts or weakens the bonds between the mineral particles and the bead
15 surfaces. It is also possible to submerge the enriched synthetic beads in a solution where ultrasonic waves are used to shake loose the mineral particles from the bead surface. The releasing can be carried out thermally or electromagnetically. For example, the enriched synthetic beads can be subjected to a hot-water wash to weaken the chemical bond of the functional groups. The enriched synthetic beads
20 can also be subjected to laser illumination where a selected laser frequency is used to weaken the chemical bond. After the releasing process, the reclaimed synthetic beads can be reused or discarded. The reclaimed synthetic beads may be recharged in order to replenish the functional groups lost during the separation and releasing processes. In order to determine whether the reclaimed synthetic beads
25 are reusable or worth recharging, a fluorescent chemical can be incorporated onto

the surface of the synthetic beads together with the functional groups. The fluorescent chemical is used as a tag for tracing such that the intensity of the fluorescence can be used as a gauge when the fluorescent chemical is excited.

The synthetic beads, according to some embodiments of the present invention, can also be used in a dry separation process where the crushed particles are configured to contact with the synthetic beads by dry mixing. Alternatively, the synthetic beads can be contained in a filter and the crushed particles are forced by forced air to pass through the filter. Again, the mineral particles attached on the enriched synthetic beads can be released in a low pH environment, in a ultrasonic agitation environment, in a hot water bath or in a laser illuminated area.

The synthetic beads, according to some embodiments of the present invention, can be made with different sizes in order to attract mineral particles of different sizes. For example, unlike air bubbles, the synthetic beads of a larger size can be used to attract mineral particles larger than, say, 200 μ m. Thus, the grinding of the blasted ore can be separated into different stages. In the first stage, the rock is crushed into particles in the order of 200 μ m. After the separation process using the larger synthetic beads in the slurry containing these crude particles, the remaining slurry can be subjected to a finer grinding stage where the crushed rock is further crushed into particles in the order of 100 μ m. With the slurry containing the finer mineral particles, synthetic beads with a smaller size may be more effective in interacting with the finer mineral particles. In a flotation cell application, the bead size can be smaller than 100 μ m. In a tailings pond application, the bead size can be 1mm to 10mm or larger. However, large beads would reduce the functionalized surfaces where the mineral particles can attach to the synthetic beads. Thus, according to some embodiments of the present invention, the synthetic beads are

configured with a size less than 100 μm for attracting to mineral particles having a substantially similar size, including in applications related to flotation cells; the synthetic beads are configured with a size of about 100 μm for attracting or attaching to mineral particles having a substantially similar size, smaller size or larger size; the synthetic beads are configured with a size in a range of about 50-500 μm for attracting or attaching to mineral particles having a substantially similar size, smaller size or larger size; the synthetic beads are configured with a size about 200 μm for attracting to mineral particles having a substantially similar size; the synthetic beads are configured with a size in a range of about 1mm to 10mm, including in applications related to a tailings pond. In general, the synthetic beads are configured with a size in a range of about 50 μm to 10mm. But the beads can be smaller than 50 μm and larger than 10mm.

Figure 14a illustrates a scenario where a mineral particle 72 is attached to a number of synthetic beads 74 at the same time. Thus, although the synthetic beads 74 are much smaller in size than the mineral particle 72, a number of synthetic beads 74 may be able to lift the mineral particle 72 upward in a flotation cell. Likewise, a smaller mineral particle 72 can also be lifted upward by a number of synthetic beads 74 as shown in Figure 14b. In order to increase the likelihood for this “cooperative” lifting to occur, a large number of synthetic beads 74 can be mixed into the slurry. Unlike air bubbles, the density of the synthetic beads can be chosen such that the synthetic beads may stay along in the slurry before they rise to surface in a flotation cell.

Figures 15a and 15b illustrate a similar scenario. As shown, a wetted mineral particle 172 is attached to a number of hydrophobic synthetic beads 174 at the same time, according to some embodiments of the present invention.

According to some embodiments of the present invention, the synthetic beads 74, 174 are configured to be larger than the mineral particles 72, 172 as shown in Figures 7a and 13a. As such, a plurality of mineral particles 72, 172 may attach to one synthetic bead 74, 174. According to other embodiments of the present invention, the synthetic beads 74, 174 are configured to be smaller than the mineral particles 71, 171 as shown in Figures 14a and 15a. As such, a plurality of synthetic beads 74, 174 may attach to one mineral particle 71, 171. The size of the synthetic beads 74, 174 can also be about the same as the size of the mineral particle 71, 171 as shown in Figures 14b and 15b. According to some embodiments of the present invention, only a portion of the surface of the synthetic bead 174 is functionalized to be hydrophobic (with molecules 179). This has the benefits as follows:

1. Keeps too many beads from clumping together – or limits the clumping of beads,
2. Once a mineral is attached, the weight of the mineral is likely to force the bead to rotate, allowing the bead to be located under the bead as it rises through the flotation cell;
 - a. Better cleaning as it may let the gangue to pass through,
 - b. Protects the attached mineral particle or particles from being knocked off, and
 - c. Provides clearer rise to the top collection zone in the flotation cell.

According to some embodiments of the present invention, only a portion of the surface of the synthetic bead 74 is functionalized to have a functional group being a collector 78. The collector 78 has an ion for bonding to a mineral particle. This has the benefits as follows:

Once a mineral is attached, the weight of the mineral is likely to force the bead to rotate, allowing the bead to be located under the bead as it rises through the flotation cell;

- a. Better cleaning as it may let the gangue to pass through
- 5 b. Protects the attached mineral particle or particles from being knocked off, and
- c. Provides clearer rise to the top collection zone in the flotation cell.

According to some embodiments of the present invention, one part of the synthetic bead is functionalized with collectors while another part of same synthetic
10 bead is functionalized to be hydrophobic as shown in Figures 16a and 16b. As shown in Figure 16a, a synthetic bead 74 has a surface portion where polymer is functionalized to have collector molecules 73 with functional group 78 and molecular segment 76 attached to the surface of the bead 74. The synthetic bead 74 also has a different surface portion where polymer is functionalized to have hydrophobic
15 molecules 179. In the embodiment as shown in Figure 16b, the entire surface of the synthetic bead 74 can be functionalized to have collector molecules 73, but a portion of the surface is functionalized to have hydrophobic molecules 179 render it hydrophobic.

According to some embodiments of the present invention, one part of the
20 synthetic bead is functionalized with collectors while another part of same synthetic bead is functionalized to be hydrophobic and this "hybrid" synthetic bead is configured for use in a traditional flotation cell as well. The "hybrid" synthetic bead (see Figures 16a and 16b) has a hydrophobic portion and a separate collector portion. When the "hybrid" beads are mixed with air in the flotation cell, some of them
25 will attach to the air bubbles because of the hydrophobic portion. As the "hybrid"

synthetic bead is attached to an air bubble, the collector portion of the attached bead can collect mineral particles with the functional groups. Thus, the synthetic beads, according to some embodiments of the present inventions, can be used to replace the air bubbles, or to work together with the air bubbles in a flotation process.

5 This "hybrid" synthetic bead can collect mineral particles that are wet and not wet.

 It should be noted that, the synthetic beads, according to some embodiments of the present invention, can be used in tailings scavenger cells to scavenge the unrecovered minerals from a tailings stream. The synthetic beads can also be used
10 in a disposal pond or the tailing ponds.

 It should be understood that the synthetic beads according to the present invention, whether functionalized to have a collector or functionalized to be hydrophobic, are also configured for use in oilsands separation – to separate bitumen from sand and water in the recovery of bitumen in an oilsands mining
15 operation. Likewise, the functionalized filters and membranes, according to some embodiments of the present invention, are also configured for oilsands separation.

 As described in the specification, ore mining is typically associated with copper and nickel. However, other types or kinds of valuable material or minerals of
20 interest, including gold, molybdenum, etc.

 However, the scope of the invention is intended to include other types or kinds of applications either now known or later developed in the future.

The Scope of the Invention

It should be further appreciated that any of the features, characteristics, alternatives or modifications described regarding a particular embodiment herein may also be applied, used, or incorporated with any other embodiment described
5 herein. Although the invention has been described and illustrated with respect to exemplary embodiments thereof, the foregoing and various other additions and omissions may be made therein and thereto without departing from the spirit and scope of the present invention.

10

What is claimed is:

1. A synthetic bead comprising:
a solid-phase body made of a synthetic material, the solid phase body comprising a surface; and
a coating attached to at least part of the surface, the coating comprising a plurality of molecules selected for attracting one or more mineral particles to the molecules, wherein the molecules comprise a functional group in a hydrophobic polymer selected from a group consisting of poly(dimethylsiloxane), polysiloxanates, silicone alkyd copolymer and fluoroalkylsilane.
2. The synthetic bead according to claim 1, wherein the solid-phase body comprises a shell providing the surface, the shell made of a synthetic material comprising the molecules.
3. The synthetic head according to claim 2, wherein the synthetic bead is configured to attract the mineral particles in an aqueous mixture, and wherein the shell comprises an interior part arranged to encapsulate a gaseous element such that the bead has a density smaller than the aqueous mixture.
4. The synthetic bead according to claim 2, wherein the synthetic bead is configured to attract or attach to the mineral particles in an aqueous mixture, and wherein the shell comprises an interior part arranged to encapsulate a liquid having a chemical property different from the aqueous mixture.
5. The synthetic bead according to claim 2, wherein the synthetic bead is configured to attract the mineral particles in an aqueous mixture, and wherein the shell comprises an interior part arranged to encapsulate a solid-phase material different from the synthetic material, and the solid-phase material is selected to control the density of the synthetic bead relative to the density of the aqueous mixture.
6. The synthetic bead according to claim 2, wherein the shell comprises an interior

part configured to encapsulate a magnetic material.

7. The synthetic bead according to claim 2, wherein the shell comprises an interior part configured to encapsulate a solid-phase material different from the synthetic material.

8. The synthetic bead according to claim 1, wherein the solid-phase body comprises a core and a coating over the core for providing the surface, wherein the coating is made of a synthetic material and the core is made of a core material different from said synthetic material.

9. The synthetic bead according to claim 7, wherein the core material is selected from a group consisting of glass, ceramic, metal and a polymer that is different than the synthetic material.

10. The synthetic bead according to claim 1, wherein the synthetic material is selected from a group consisting of polyamides (nylon), polyesters, polyurethanes, phenol-formaldehyde, urea-formaldehyde, melamine-formaldehyde, polyacetal, polyethylene, polyisobutylene, polyacrylonitrile, poly(vinyl chloride), polystyrene, poly(methyl methacrylates), poly(vinyl acetate), poly(vinylidene chloride), polyisoprene, polybutadiene, polyacrylates, poly(carbonate), and phenolic resin.

11. The synthetic bead according to claim 1, wherein the surface comprises physical structures configured to trap the mineral particles.

12. The synthetic bead according to claim 11, wherein the physical structures comprise grooves or dents.

13. The synthetic bead according to claim 11, wherein the physical structures comprise hair-like structures.

14. The synthetic bead according to claim 3, wherein the mineral particles have a maximum size and the solid-phase body has a body size greater than the maximum size.

15. The synthetic bead according to claim 3, wherein the mineral particles have a minimum size and the solid-phase body has a body size smaller than the minimum size.
16. The synthetic bead according to claim 1, wherein the functional group has an anion for attracting the mineral particles to the surface.
17. The synthetic bead according to claim 1, wherein the functional group is a collector that is either ionic or non-ionic.
18. The synthetic bead according to claim 17, wherein the functional group is anionic or cationic.
19. A method for producing a synthetic bead or bubble, comprising:
providing a solid-phase body made of a synthetic material, the solid-phase body comprising a surface; and
attaching a coating to the surface, the coating comprising a plurality of molecules comprising a functional group selected for attracting one or more mineral particles to the molecules, wherein the molecules comprise a functional group in a hydrophobic polymer selected from a group consisting of poly(dimethylsiloxane), polysiloxanates, silicone alkyd copolymer and fluoroalkylsilane.
20. The method according to claim 19 wherein said attaching comprises bonding the molecules to the synthetic material.
21. The method according to claim 19, wherein the solid-phase body comprises a shell providing the surface, the shell made of a synthetic material, wherein said attaching comprises bonding the molecules to the synthetic material.
22. The method according to claim 21, wherein the synthetic bead is configured to

attract the mineral particles in an aqueous mixture, and wherein the shell comprises an interior part, said method further comprising:

encapsulating a gaseous element in the interior part such that the synthetic bead has a density less than the aqueous mixture.

23. The method according to claim 21, wherein the synthetic bead is configured to attract the mineral particles in an aqueous mixture, and wherein the shell comprises an interior part, said method further comprising:

encapsulating a solid-phase material in the interior part, the solid-phase material being different from the synthetic material, and the solid-phase material is selected to control the density of the synthetic bead relative to the density of the aqueous mixture.

24. The method according to claim 19, wherein the functional group has an anionic bond for attracting the mineral particles to the surface.

25. The method according to claim 19, wherein the functional group is a collector configured to be either ionic or non-ionic.


26. The method according to claim 25, wherein the functional group comprises an ion.

27. The synthetic bead according to claim 1, wherein the synthetic beads are configured with a size of about 100 μm for attracting or attaching to mineral particles having a substantially similar size, smaller size or larger size.


28. The synthetic bead according to claim 1, wherein the synthetic beads are configured with a size in a range of about 50-500 μm for attracting or attaching to mineral particles having a substantially similar size.

29. The synthetic bead according to claim 1, wherein the synthetic beads are configured with a size about 200 μm for attracting to mineral particles having a substantially similar size.

30. The synthetic bead according to claim 1, wherein the synthetic beads are configured with a size in a range of about 50 μm to 10 mm.
31. The synthetic bead according to claim 1, wherein the functional group is configured to cause the surface to be hydrophobic.
32. The synthetic bead according to claim 1, wherein the solid-phase body comprises a porous block providing the surface, the porous block made of a synthetic material comprising the molecules.
33. The synthetic bead according to claim 1, wherein only said at least part of the surface is configured to be hydrophobic and another part of the surface comprises collectors.
34. The synthetic bead according to claim 1, wherein a part of the surface is configured to be hydrophobic.
35. The method according to claim 19, wherein the synthetic material is selected from a group consisting of polyamides (nylon), polyesters, polyurethanes, phenol-formaldehyde, urea-formaldehyde, melamine-formaldehyde, polyacetal, polyethylene, polyisobutylene, polyacrylonitrile, poly(vinyl chloride), polystyrene, poly(methyl methacrylates), poly(vinyl acetate), poly(vinylidene chloride), polyisoprene, polybutadiene, polyacrylates, poly(carbonate), and phenolic resin.
36. The method according to claim 19, wherein only said at least part of the surface is configured to be hydrophobic and another part of the surface comprises collectors.



Bead Size > Maximum Ground
Ore Particle Size
Or
Bead Size < Minimum Ground
Ore Particle Size



Sized-Based Beads And Bubbles




FIG. 3

Bead Weight > Maximum Ground
Ore Particle Weight
Or
Bead Weight < Minimum Ground
Ore Particle Weight






FIG. 4

Weight-Based Beads And Bubbles



Ferromagnetic or
Ferrimagnetic Beads
Attracted to Paramagnetic
Surfaces

FIG. 5



Paramagnetic Beads Attracted
to Magnetized Surfaces

FIG. 6

Magnetic-Based Beads And Bubbles




FIG. 7a




FIG. 7b




FIG. 8a




FIG. 8b




FIG. 8c




FIG. 8d




FIG. 9a




FIG. 9b




FIG. 9c




FIG. 9d




FIG. 10c




FIG. 10b




FIG. 10a




FIG. 10d




FIG. 11




FIG. 12: Alternative Flotation cell or Column




FIG. 13b




FIG. 13c




FIG. 13a




FIG. 14b




FIG. 14a




FIG. 15a

FIG. 15b




FIG. 16a




FIG. 16b

