

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
19 January 2012 (19.01.2012)

PCT

(10) International Publication Number
WO 2012/009484 A2

(51) International Patent Classification:
C08G 61/02 (2006.01) *C08J 5/00* (2006.01)
C08L 65/00 (2006.01)

(21) International Application Number:
PCT/US2011/043922

(22) International Filing Date:
13 July 2011 (13.07.2011)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
61/399,483 13 July 2010 (13.07.2010) US
61/400,122 22 July 2010 (22.07.2010) US
61/366,850 22 July 2010 (22.07.2010) US
61/401,832 19 August 2010 (19.08.2010) US
61/401,825 19 August 2010 (19.08.2010) US
61/404,236 29 September 2010 (29.09.2010) US
61/456,552 8 November 2010 (08.11.2010) US
61/413,878 15 November 2010 (15.11.2010) US
61/471,800 5 April 2011 (05.04.2011) US
61/499,097 20 June 2011 (20.06.2011) US

NM 87131 (US). **OGAWA, Motokatsu** [US/US]; 14426 Addison Street #3, Sherman Oaks, CA 91423 (US). **CORBITT, Thomas** [US/US]; 7716 Roberts St. N.E., Albuquerque, NM 87109 (US). **DASCIER, Dimitri** [FR/US]; 2222 Uptown Loop NE, Apt 3204, Albuquerque, NM 87110 (US). **WANG, Ying** [CN/US]; 1431 Girard Boulevard Ne, Apartment 21, Albuquerque, NM 87106 (US). **ISTA, Linnea** [US/US]; 4912 Inspiration Dr. SE, Albuquerque, NM 87108 (US).

(74) Agents: **GONZALES, Ellen** et al.; Gonzales Patent Services, 4605 Congress AVE NW, Albuquerque, NM 87114 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (for all designated States except US): **STC.UNM** [US/US]; Msc 04 2750, 801 University Blvd. Se, Suite 101, Albuquerque, NM 87106 (US).


(72) Inventors; and

(75) Inventors/Applicants (for US only): **WHITTEN, David** [US/US]; 5435 La Colonia Dr. NW, Albuquerque, NM 87120 (US). **SCHANZE, Kirk** [US/US]; 8939 SW 44TH LANE, Gainesville, FL 32611 (US). **PARTHSARAY, Anand** [IN/US]; 3009 SW Archer Road, APT-A3, Gainesville, FL 32608 (US). **Ji, Eunkyung** [SK/US]; 2222 UPTOWN LOOP NE APT #3204, Albuquerque,

[Continued on next page]

(54) Title: STRUCTURE, SYNTHESIS, AND APPLICATIONS FOR POLY (PHENYLENE) ETHYNYLENES (PPES)

Fig. 1



(57) Abstract: The present disclosure provides novel poly(phenylene ethynylene) (PPE) compounds, methods for synthesizing these compounds, and materials and substances incorporating these compounds. The various PPEs show antibacterial, antiviral and antifungal activity.

WO 2012/009484 A2

Published:

- *without international search report and to be republished upon receipt of that report (Rule 48.2(g))*

Structure, Synthesis, and Applications for Poly(Phenylene Ethynylenes) (PPEs)

Statement Regarding Government Sponsored Research

[001] This invention was made with Government support under grant number W911NF-07-0079 awarded by the Defense Threat Reduction Agency. The U.S. Government has certain rights in this invention.

Cross-reference to Related Applications

[002] The following application claims benefit of U.S. Provisional Application Nos. 61/399,483, filed July 13, 2010; 61/400,122, filed July 22, 2010; 61/366850, filed July 22, 2010; 61/401,825, filed August 19, 2010; 61/401,832, filed August 19, 2010; 61/404,236, filed September 29, 2010; 61/456,552, filed November 8, 2010; 61/413878, filed November 15, 2010; 61/471,800 filed April 5, 2011; and 61/499,097 filed June 20, 2011; each of which is hereby incorporated by reference in its entirety.

Background

[003] Poly(phenylene ethynylene) based conjugated polyelectrolytes (also referred to herein as Poly(phenylene ethynylenes) or (PPEs)) are conjugated molecules that have a wide range of applications in electrically conducting materials, bio-chemical sensors, and supramolecular assemblies. More recently, interest has developed in the antimicrobial activity of these compounds. For example, while the extensive use of antibiotics has successfully dramatically reduced the human mortality rate due to infections, it has also given rise to the acquisition of resistance genes by various organisms, making some infections increasingly hard to treat. Accordingly novel methods for infection control, including novel methods and compounds for providing antimicrobial properties to a variety of materials is greatly desired.

Summary

[004] The present disclosure provides novel poly(phenylene ethynylene) (PPE) compounds, methods for synthesizing these compounds, and materials incorporating these compounds.

[005] According to an embodiment, the PPEs of the present disclosure have the base structure shown in Fig. 1 where:

n is selected from the group consisting of the whole numbers between 5 and 200;

A is selected from the group consisting of $C_2C_6H_2$ and $C_2C_4H_2S$;

B = $C_2C_6H_2$;

C = is either C₆H₄ or not present;

X is selected from the group consisting of: H, [C₂C₆H₄]₂COOCH₂CH₃, and; [C₂C₄H₂S][C₂C₆H₄]COOCH₂CH₃.

Y is selected from the group consisting of: H and COOCH₂CH₃.

Z_A is selected from the group consisting of O(CH₂)_k(C₆H₁₂N₂)C₆H₁₃²⁺, O(CH₂)_kSO₃⁻, O(CH₂)_kN(CH₂CH₃)₃⁺, and O(CH₂)_kN(CH₃)₃⁺; where k is selected from the group consisting of the whole number between 1 and 10;

Z_B is selected from the group consisting of H and (OCH₂CH₂)₃OCH₃.

wherein:

if Z_A is O(CH₂)_k(C₆H₁₂N₂)C₆H₁₃²⁺, then Z_B is H, A= C₂C₆H₂, C, if present, is C₆H₄, and X is selected from the group consisting of H and [C₂C₆H₄]₂COOCH₂CH₃, wherein:

if X is H, then Y is H; and C is not present

if X is [C₂C₆H₄]₂COOCH₂CH₃, then Y is COOCH₂CH₃ and C is C₆H₄;

if Z_A is O(CH₂)_kSO₃⁻, Z_B is H, A= C₂C₆H₂, C is not present, and X = Y = H;

if Z_A is O(CH₂)_kN(CH₂CH₃)₃⁺, then Z_B is (OCH₂CH₂)₃OCH₃, A = C₂C₆H₂, C is not present, and X=Y=H;

if Z_A is O(CH₂)_kN(CH₃)₃⁺, and Z_B is (OCH₂CH₂)₃OCH₃, then C is not present, A = C₂C₄H₂ and X = Y = H;

if Z_A is O(CH₂)_kN(CH₃)₃⁺, Z_B is H, and C is not present, then A = C₂C₄H₂S and X = Y = H;

if Z_A is O(CH₂)_kN(CH₃)₃⁺, Z_B is H, and C is present, then Y = COOCH₂CH₃ and X is selected from the group consisting of [C₂C₆H₄]₂COOCH₂CH₃ and [C₂C₄H₂S][C₂C₆H₄]COOCH₂CH₃; wherein

if A = C₂C₆H₂, then X is [C₂C₆H₄]₂COOCH₂CH₃;

if A = C₂C₆H₂S, then X is [C₂C₄H₂S][C₂C₆H₄]COOCH₂CH₃.

Brief Description of the Drawings

[006] Fig. 1 depicts the basic structure of a PPE according to an embodiment of the present disclosure.

[007] Fig. 2 depicts the basic structure of a PPE according to another embodiment of the present disclosure.

[008] Fig. 3 is the chemical structure of PPE-DABCO.

[009] Fig. 4 is the chemical structure of PPE-SO₃.

- [010] Fig. 5 is the chemical structure of PPE-NEt₃-OR11.
- [011] Fig. 6 is the chemical structure of PPE-NMe₃-OR8.
- [012] Fig. 7 is the chemical structure of PPE-NMe₃-Th.
- [013] Fig. 8 is the chemical structure of PPE-NMe₃-n-COOEt.
- [014] Fig. 9 is the chemical structure of PPE-DABCO-n-COOEt.
- [015] Fig. 10 is the chemical structure of PPE-NMe₃-Th-n-COOEt.
- [016] Fig. 11 is a schematic illustration of the synthesis scheme for PPE-DABCO.
- [017] Fig. 12 is a schematic illustration of the synthesis scheme for PPE-SO₃.
- [018] Fig. 13 is a schematic illustration of the synthesis scheme for PPE-Net₃-OR11 and PPE-NMe₃-OR8.
- [019] Fig. 14 is a schematic illustration of the synthesis scheme for PPE-C6-NMe₃-OR8.
- [020] Fig. 15 is a schematic illustration of the synthesis scheme for PPE-NMe₃-Th.
- [021] Fig. 16 is a schematic illustration of the synthesis scheme for PPE-NMe₃-n-COOEt and PPE-NMe₃-Th-n-COOEt.
- [022] Fig. 17 is a schematic illustration of the synthesis scheme for PPE-DABCO-n-COOEt.
- [023] Fig. 18 shows an exemplary chemisorption scheme employing a step growth polymerization process.
- [024] Fig. 19 shows a PPE hidden amidst the expanded form of an SRM.
- [025] Fig. 20 shows a PPE unsheathed after exposure to a higher temperature.
- [026] Fig. 21 depicts a method of synthesis of PNIPAAm by monomer polymerization onto an initiator functionalized surface.
- [027] Fig. 22 is a plot of biocidal activity of the polymers against *Escherichia coli* (*E. coli*), where the concentration of the polymers was 1 ug/mL.
- [028] Fig. 23 is a plot of biocidal activity of the polymers against *Escherichia coli* (*E. coli*) where the concentration of the polymers was 10 ug/mL.
- [029] Fig. 24 shows the biocidal activity of the polymers as demonstrated by flow cytometry.
- [030] Fig. 25 is a graph of fluorescein leakage profiles from DOPC/cholesterol (67/33) vesicles with the addition of PPE-NMe₃-Th, PPE-NMe₃-DABCO, PPE-NMe₃-OR8 and PPE-NMe₃-SO₃. Fluorescence from vesicles incubated alone was subtracted.
- [031] Fig. 26 is a graph of fluorescein leakage profiles from DOPC/cholesterol (67/33) vesicles with the addition of OPE-1, OPE-2 and OPE-3.

[032] Fig. 27 is a graph of fluorescein leakage profiles from DOPC/cholesterol (67/33) vesicles with the addition of S-OPE-1(COOEt), S-OPE-2(COOEt), and S-OPE-3(COOEt).

[033] Fig. 28 is a graph of fluorescein leakage profiles from DOPC/cholesterol (67/33) vesicles with the addition of EO-OPE-1(C3) and EO-OPE-1(Th).

[034] Fig. 29 is a graph of fluorescein leakage profiles from DOPG/DOPE (20/80) mixed vesicles with the addition of PPE-NMe3-Th, PPE-NMe3-DABCO, PPE-NMe3-OR8 and PPE-NMe3-SO3.

[035] Fig. 30 is a graph of fluorescein leakage profiles from DOPG/DOPE (20/80) mixed vesicles with the addition of OPE-1, OPE-2 and OPE-3.

[036] Fig. 31 is a graph of fluorescein leakage profiles from DOPG/DOPE (20/80) mixed vesicles with the addition of S-OPE-1(COOEt), S-OPE-2(COOEt), and S-OPE-3(COOEt).

[037] Fig. 32 is a graph of fluorescein leakage profiles from DOPG/DOPE (20/80) mixed vesicles with the addition of EO-OPE-1(C3) and EO-OPE-1(Th).

[038] Fig. 33 is a graph of fluorescein leakage profiles from E. coli total lipid vesicles with the addition of PPE-NMe3-Th, PPE-NMe3-DABCO, PPE-NMe3-OR8 and PPE-NMe3-SO3.

[039] Fig. 34 is a graph of fluorescein leakage profiles from E. coli total lipid vesicles with the addition of OPE-1, OPE-2 and OPE-3.

[040] Fig. 35 is a graph of fluorescein leakage profiles from E. coli total lipid vesicles with the addition of S-OPE-1(COOEt), S-OPE-2(COOEt), and S-OPE-3(COOEt).

[041] Fig. 36 is a graph of fluorescein leakage profiles from E. coli total lipid vesicles with the addition of EO-OPE-1(C3) and EO-OPE-1(Th).

[042] Fig. 37 shows inactivation of bacteriophage MS2 by PPEs in the dark and under UV-light irradiation for 1 hour.

[043] Fig. 38 shows inactivation of bacteriophage T4 by OPEs in the dark and under UV-light irradiation for 1 hour.

[044] Fig. 39 is a TEM image of uranyl acetate negatively stained model T4 virus alone.

[045] Fig. 40 is a TEM image of uranyl acetate negatively stained model MS2 virus alone.

[046] Fig. 41 is a TEM image of uranyl acetate negatively stained T4 phage with PPE-DABCO, dark.

[047] Fig. 42 is a TEM image of uranyl acetate negatively stained MS2 phage with PPE-DABCO, dark.

[048] Fig. 43 is a TEM image of uranyl acetate negatively stained T4 phage with PPE-DABCO, LZC-420.

[049] Fig. 44 is a TEM image of uranyl acetate negatively stained MS2 phage with PPE-DABCO, LZC-420.

[050] Fig. 45 is a TEM image of uranyl acetate negatively stained T4 phage with EO-OPE(Th), dark.

[051] Fig. 46 is a TEM image of uranyl acetate negatively stained MS2 phage with EO-OPE(Th), dark.

[052] Fig. 47 is a TEM image of uranyl acetate negatively stained T4 phage with EO-OPE(Th), UVA.

[053] Fig. 48 is a TEM image of uranyl acetate negatively stained MS2 phage with EO-OPE(Th), UVA.

[054] Fig. 49 shows the photolysis of PPE-SO₃ in water.

Detailed Description

[055] The present disclosure provides a plurality of novel compounds generally referred to herein as poly (phenylene ethynylenes) (PPEs), methods of synthesizing PPEs and various uses for the PPEs. According to an embodiment, the present disclosure provides PPEs having the general structure shown in Fig. 1, where:

n is selected from the group consisting of the whole numbers between 5 and 200;

A is selected from the group consisting of C₂C₆H₂ and C₂C₄H₂S;

B = C₂C₆H₂;

C = is either C₆H₄ or not present;

X is selected from the group consisting of: H, [C₂C₆H₄]₂COOCH₂CH₃, and; [C₂C₄H₂S][C₂C₆H₄]COOCH₂CH₃.

Y is selected from the group consisting of: H and COOCH₂CH₃.

Z_A is selected from the group consisting of O(CH₂)_k(C₆H₁₂N₂)C₆H₁₃²⁺, O(CH₂)_kSO₃⁻, O(CH₂)_kN(CH₂CH₃)₃⁺, and O(CH₂)_kN(CH₃)₃⁺; where k is selected from the group consisting of the whole number between 1 and 10;

Z_B is selected from the group consisting of H and (OCH₂CH₂)₃OCH₃.

wherein:

if Z_A is O(CH₂)_k(C₆H₁₂N₂)C₆H₁₃²⁺, then Z_B is H, A = C₂C₆H₂, C, if present, is C₆H₄, and X is selected from the group consisting of H and [C₂C₆H₄]₂COOCH₂CH₃, wherein:

if X is H, then Y is H; and C is not present

if X is [C₂C₆H₄]₂COOCH₂CH₃, then Y is COOCH₂CH₃ and C is C₆H₄;

if Z_A is O(CH₂)_kSO₃⁻, Z_B is H, A = C₂C₆H₂, C is not present, and X = Y = H;

if Z_A is $O(CH_2)_kN(CH_2CH_3)_3^+$, then Z_B is $(OCH_2CH_2)_3OCH_3$, $A = C_2C_6H_2$, C is not present, and $X=Y=H$;

if Z_A is $O(CH_2)_kN(CH_3)_3^+$, and Z_B is $(OCH_2CH_2)_3OCH_3$, then C is not present, $A = C_2C_4H_2$ and $X = Y = H$;

if Z_A is $O(CH_2)_kN(CH_3)_3^+$, Z_B is H , and C is not present, then $A = C_2C_4H_2S$ and $X = Y = H$;

if Z_A is $O(CH_2)_kN(CH_3)_3^+$, Z_B is H , and C is present, then $Y = COOCH_2CH_3$ and X is selected from the group consisting of $[C_2C_6H_4]_2COOCH_2CH_3$ and $[C_2C_4H_2S][C_2C_6H_4]COOCH_2CH_3$; wherein

if $A = C_2C_6H_2$, then X is $[C_2C_6H_4]_2COOCH_2CH_3$;

if $A = C_2C_6H_2S$, then X is $[C_2C_4H_2S][C_2C_6H_4]COOCH_2CH_3$.

[056] The PPEs disclosed herein can exist in solution, in colloidal suspensions, and attached, for example, by modification of the carboxyester “headgroup,” to surfaces by various covalent linkages. All of the PPEs disclosed herein are fluorescent and demonstrate biocidal activity. Furthermore, some of the compounds have demonstrated viricidal and/or fungicidal activity as well.

[057] In general, the PPEs disclosed herein are formed from a single oxygen generator resonant structure core unit shown in Fig. 2 as (A and B) and a plurality of functional groups extending from the core unit. More specifically, the PPEs disclosed herein contain para-linked subunits of a conjugated aromatic oligomeric chain (A and B) with attached functional groups X and Y at the termini of the chain and functional groups Z_A , attached to the aromatic ring of subunit A and Z_B attached to the aromatic ring of subunit B. Some of the PPEs disclosed herein may include a third resonant structure C, as shown in Fig. 1, which is an optional aromatic linking unit for functional group Y .

[058] According to various embodiments, the specific PPEs of the present disclosure are obtained by various substitutes of the general structure shown in Fig. 1. Table 1 provides a list of the various substitutions that give rise to the PPEs of the present disclosure.

Table 1 – Fig. 1 Substitutions

A	B	C	X =	Y =	Z _A =	Z _B =	n =	k =
C ₂ C ₆ H ₂	C ₂ C ₆ H ₂	none	H	H	O(CH ₂) _k (C ₆ H ₁₂ N ₂)C ₆ H ₁₃ ²⁺	H	5-200	1-10
C ₂ C ₆ H ₂	C ₂ C ₆ H ₂	none	H	H	O(CH ₂) _k SO ₃ ⁻	H	5-200	1-10
C ₂ C ₆ H ₂	C ₂ C ₆ H ₂	none	H	H	O(CH ₂) _k N(CH ₂ CH ₃) ₃ ⁺	(OCH	5-200	1-10
C ₂ C ₆ H ₂	C ₂ C ₆ H ₂	none	H	H	O(CH ₂) _k N(CH ₃) ₃ ⁺	(OCH	5-200	1-10
C ₂ C ₆ H ₂	C ₂ C ₆ H ₂	none	H	H	O(CH ₂) _k N(CH ₃) ₃ ⁺	(OCH	5-200	1-10
C ₂ C ₆ H ₂	C ₂ C ₆ H ₂	C ₆ H ₄	[C ₂ C ₆ H ₄] ₂ COOCH ₂ CH ₃	COOCH ₂ CH ₃	O(CH ₂) _k N(CH ₃) ₃ ⁺	H	5-200	1-10
C ₂ C ₆ H ₂	C ₂ C ₆ H ₂	C ₆ H ₄	[C ₂ C ₆ H ₄] ₂ COOCH ₂ CH ₃	COOCH ₂ CH ₃	O(CH ₂) _k (C ₆ H ₁₂ N ₂)C ₆ H ₁₃ ²⁺	H	5-200	1-10
C ₂ C ₄ H ₂ S	C ₂ C ₆ H ₂	C ₆ H ₄	[C ₂ C ₄ H ₂ S][C ₂ C ₆ H ₄]COOCH ₂ CH ₃	COOCH ₂ CH ₃	O(CH ₂) _k N(CH ₃) ₃ ⁺	H	5-200	1-10

[059] In viewing the chart above, those of skill in the art will recognize that compounds can easily be formed to include various numbers of repeat units alkyl chain linkages to the quaternary ammonium bearing groups and/or the sulfonate bearing groups, as demonstrated, for example, by the k groups indicated above. Accordingly, while specific structures and methods of synthesis are disclosed below, it will be understood that similar structures bearing these repeat units are similarly contemplated by the present disclosure.

[060] Fig. 3 shows the chemical structure of PPE-DABCO. Suitable counter ions for PPE-DABCO include Cl⁻, Br⁻ or I⁻. An exemplary synthesis scheme for PPE-DABCO where k = 3 is shown in Fig. 11. Synthesis for the scheme shown in Fig. 11 is as described below:

[061] 1,4-diethynylbenzene was synthesized and purified as described in Takahashi, S.; Kuroyama, Y.; Sonogashira, K.; Hagihara, N. *Synthesis* (Stuttgart) 1980, 627-630.

[062] 1-Hexyl-4-aza-1-azoniabicyclo[2.2.2]octane Bromide (compound 2). Diazabicyclo[2.2.2]octane (10.0 g, 89.2 mmol) and hexyl bromide (6.3 mL, 44.6 mmol) were combined in 100 mL of ethyl acetate. The solution was stirred for 24 h, after which time, a white precipitate had formed. The solid was collected by vacuum filtration, rinsed with ethyl acetate, and dried under vacuum, yield 11.23 g (91%). ¹H NMR (DMSO-d₆; δ ppm): 0.87 (t, 3 H), 1.28 (m, 6 H), 1.64 (m, 2 H), 3.01 (t, 6 H), 3.22 (m, 2 H), 3.32 (t, 6 H).

[063] 4,4'-(2,2'-(2,5-Diiodo-1,4-phenylene)bis(oxy)bis(ethane-2,1-diyl))bis(1-hexyl-1,4-diazonia-bicyclo[2.2.2]octane) Tetrabromide. A solution of 5.8 g (10 mmol) of 1,4-diiodo-2,5-bis(2-bromoethoxy)benzene and 7.0 g (25 mmol) of 5 in 100 mL of dimethylacetamide was stirred at 110 °C for 6 h. Upon cooling, 200 mL of cold ether was added to the reaction mixture. The resulting white precipitate was collected by filtration and recrystallized twice from water, yield 9.8 g (86%). ¹H NMR (DMSO-d₆; σ ppm): 0.87 (t, 6 H), 1.32 (m, 12 H), 1.72 (m, 4 H), 3.59 (m, 4 H), 3.98 (t, 12 H), 4.14 (m, 16 H), 4.55 (m, 4 H), 7.57 (s, 1 H). ¹³C NMR (DMSO-d₆; σ ppm): 13.83, 21.25, 21.80, 25.17, 30.59, 50.27, 51.38, 62.59, 63.12,

63.33, 87.16, 123.09, 152.11. Elemental analysis calcd for C₃₄H₆₀Br₄I₂N₄O₂: C, 36.13; H, 5.35; N, 4.96. Found: C, 35.19; H, 5.60; N, 4.61.

[064] Polymerization Reactions. All of the polymers were prepared from the corresponding monomers to a similar procedure.

[065] Fig. 4 shows the chemical structure of PPE-SO₃. Suitable counter ions for PPE-DABCO include Na⁺. An exemplary synthesis scheme for PPE-SO₃ where k = 3 is shown in Fig. 12. Synthesis for the scheme shown in Fig. 12 is as described below:

[066] Starting Materials 2,5-Diiodohydroquinone and 1,4-diethynylbenzene were synthesized according to procedures published in "Fluorescent Chemosensors Based on Energy Migration in Conjugated Polymers: The Molecular Wire Approach to Increased Sensitivity", Zhou, Q.; Swager, T. M.; J. Am. Chem. Soc. 1995, 117, 12593-12602 and "A convenient synthesis of ethynylarenes and diethynylarenes", Takahashi, S.; Kuroyama, Y.; Sonogashira, K.; Hagihara, N.; Synthesis 1980, 627-630, respectively.

[067] Monomer 1 7.24 g (20.0 mmol) of 2,5-diiodohydroquinone was dissolved in a solution that contained 2.0 g (50.0 mmol) of sodium hydroxide in 200 mL of water in a Erlenmeyer flask under argon. A solution of 6.1 g (50.0 mmol) of 1,3-propanesultone in 40 mL of dioxane was added to the former solution at once. The resulting mixture was then stirred at room temperature overnight, during which time a thick pink slurry formed. The reaction mixture was then stirred at 80-100° C for another 30 minutes and then cooled in a water/ice bath. The suspension obtained was vacuum filtered, and the retained solid was washed with cold water followed by acetone, and crystallized twice from water.

[068] Yield 9.2 g (70 %) as a fine white powder

[069] C₁₂H₁₄I₂Na₂O₈S₂ (Mol. Wt.: 650.16):

[070] Analysis calc: C 22.17; H 2.17; I 39.04; S 9.86

[071] Analysis found: C 22.43; H 2.57; I 34.63; S 8.96

[072] FTIR (ν_{max}. cm⁻¹, KBr pellet): 2975, 2940, 2872, 1624, 1489, 1464, 1438, 1390, 1353, 1262, 1206, 1156, 1061, 1032, 937, 850, 795, 739, 629, 551

[073] ¹H-NMR (DMSO-d₆; ppm from TMS): 2.00 (t, 4H); 2.64 (t, 4H); 4.05 (t, 4H); 7.30 (s, 2H)

[074] ¹³C-NMR (DMSO-d₆; ppm from TMS): 25.37, 48.14, 68.96, 86.99, 122.44, 152.30

[075] PPE-SO₃⁻ 1.008 g (1.55 mmol) of monomer 1 and 0.189 g (1.50 mmol) of 1,4-diethynylbenzene were dissolved in a mixture of 20 mL of water and 20 mL of DMF at 60 °C in a Schlenk flask with a gentle flow of argon and with magnetic stirring. The resulting clear solution was deoxygenated by several cycles of vacuum-argon cycling. Another solution

comprised of 52.0 mg (45.0 μmol) of $\text{Pd}(\text{PPh}_3)_4$ and 10.0 mg (45 μmol) of CuI in a mixture of 10 mL of diisopropylamine and 10 mL of DMF was likewise deoxygenated and was subsequently added to the former solution by means of a cannula. The final mixture was again deoxygenated by vacuum-argon cycling and was then warmed to 50-55° C and stirred under a positive pressure of argon for 14 hrs. The resulting solution was viscous, brown in color and exhibited an intense blue fluorescence when illuminated with a near-UV lamp. The solution was cooled and then slowly added to 1 L of a methanol/acetone/ether mixture (10:40:50 v:v:v). The polymer precipitated as greenish fibers. It was redissolved in 200 mL of water/methanol 70:30, treated with 0.1 g of sodium sulfide (Na_2S), and then the solution was filtered through quantitative filter paper, followed by a 10-20 μm fritted glass filter, and finally through a 0.8 μm nylon membrane. The polymer was precipitated by addition to a large volume of methanol/acetone/ether (10:40:50). The polymer was dissolved in water/methanol and reprecipitated from methanol/acetone/ether four more times. Finally, the polymer was dissolved in 150 mL of water, 0.05 g of sodium cyanide was added, and the resulting solution was dialyzed against water (Millipore Nanopure™) using a 6-8 kD MWCO cellulose membrane. After the dialysis, the polymer concentration was approximately 2.1 mg-mL. The polymer was stored in this format and diluted as appropriate for spectroscopic studies. The molecular weight of PPE-SO_3^- was estimated to be 100 kD based on its ultrafiltration properties and iodine end-group analysis.

[076] Yield 535 mg (68.5%) as light yellow fibers

[077] $\text{C}_{22}\text{H}_{18}\text{Na}_2\text{O}_8\text{S}_2$ (Mol. Wt. monomeric unit: 520.48):

[078] Analysis calc: C 50.77; H 3.49; S 12.32

[079] Analysis found: C 48.98; H 4.52; I 0.12; S 8.89

[080] FTIR (ν_{max} , cm^{-1} , cast film): 2944, 2878, 1638, 1519, 1469, 1439, 1417, 1281, 1189, 1045, 835, 612, 541

[081] $^1\text{H-NMR}$ (DMSO-d_6 ; δ ppm from TMS, 100°C): 2.15 (t, 4H); 2.77 (t, 4H); 4.21 (t, 4H); 7.18 (s, 2H); 7.61 (broad, 4H)

[082] Fig. 5 shows the chemical structure of $\text{PPE-Net}_3\text{-OR11}$. Suitable counter ions for $\text{PPE-Net}_3\text{-OR11}$ include Cl^- , Br^- or I^- . Fig. 6 shows the chemical structure of $\text{PPE-NMe}_3\text{-OR8}$. Suitable counter ions for $\text{PPE-NMe}_3\text{-OR8}$ include Cl^- , Br^- or I^- . An exemplary synthesis scheme for $\text{PPE-Net}_3\text{-OR11}$ and $\text{PPE-NMe}_3\text{-OR8}$ where $k = 3$ is shown in Fig. 13. Synthesis for the scheme shown in Fig. 13 is as described below:

[083] 2,5-Diiodohydroquinone2 (1), 1,4-diiodo-2,5-bis[2-[2-(2-methoxyethoxy)ethoxy]ethoxy]benzene (2b), 1,4-diethynyl-2,5-bis[2-[2-(2-

methoxyethoxy)ethoxy]ethoxy]benzene (3b), 1,4-bis(3-bromopropoxy)-2,5-diiodobenzene (4), and 3,3'-[(2,5-diiodo-1,4-phenylene)bis(oxy)]bis[N,N,N-trimethyl-1-propanaminium] bromide salt (5a), were synthesized according to the procedures described in Zhao, X. Y.; Pinto, M. R.; Hardison, L. M.; Mwaura, J.; Muller, J.; Jiang, H.; Witker, D.; Kleiman, V. D.; Reynolds, J. R.; Schanze, K. S. *Macromolecules* 2006, 39, 6355-6366. Tan, C. Y.; Pinto, M. R.; Schanze, K. S. *Chem. Commun.* 2002, 446-447. Ogawa, K.; Chemburu, S.; Lopez, G. P.; Whitten, D. G.; Schanze, K. S. *Langmuir* 2007, 23, 4541-4548. McQuade, D. T.; Hegedus, A. H.; Swager, T. M. *J. Am. Chem. Soc.* 2000, 122, 12389-12390. Nardello, V.; Azaroual, N.; Cervoise, I.; Vermeersch, G.; Aubry, J. M. *Tetrahedron* 1996, 52, 2031-2046. Unless otherwise noted, ¹H and ¹³C NMR spectra were recorded on either a Varian Gemini 300, VXR 300, or Mercury 300 spectrometer, and chemical shifts are reported in ppm relative to TMS.

[084] 1,4-Diiodo-2,5-bis[2-(2-methoxyethoxy)ethoxy]benzene (compound 4a). 2,5-Diiodohydroquinone (compound 3) (5.79 g, 16 mmol), (2-Methoxyethoxy)ethyl tosylate (11.0 g, 40 mmol), and potassium carbonate (5.52 g, 40 mmol) were combined in a flask with 100 mL of acetone. The mixture was heated to 70°C and kept stirring for overnight. The mixture was filtered and filtrate concentrated by rotary evaporation. Water was added and product was extracted with chloroform. The product was purified by column chromatography on silica using 2:3 mixture of ethyl acetate and hexane. Solvent was removed by rotary evaporation to give yellow oil. ¹H NMR (300 MHz, CDCl₃): δ 3.40 (s, 6H), 3.58 (m, 4H), 3.78 (m, 4H), 3.88 (m, 4H), 4.11 (m, 4H), 7.23 (s, 2H). ¹³C NMR (75 MHz, CDCl₃): δ 59.5, 69.9, 70.7, 71.4, 72.4, 86.7, 123.8, 153.4.

[085] 1,4-diethynyl-2,5-bis[2-(2-methoxyethoxy)ethoxy]benzene (5a). Compound 4a (5.65 g, 10 mmol), trimethylsilylacetylene (3.1 mL, 22 mmol), CuI (57 mg, 0.3 mmol), and Pd(PPh₃)₄ (0.35 g, 0.3 mmol) were dissolved in 60 mL of THF and 40 mL of diisopropyl amine. Mixture was warmed to 70°C and kept stirring overnight. Water was added and the mixture was extracted with ether followed by several washings with water. Solvent was removed in vacuo. The product was purified by column chromatography on silica using 1:4 mixture of ethyl acetate and hexane. Solvent was removed by rotary evaporation to give white solid.

[086] The white solid was dissolved in 50 mL of methanol. To the solution, 50 mL of 1M NaOH(aq) was added and refluxed for 2 hours. Water was added to the mixture and extracted with ether. The organic layer was washed with water several times, then dried with Na₂SO₄. Solvent was removed by rotary evaporation to give reddish solid. The product was purified

column chromatography on silica using a 2:3 mixture of ethyl acetate and hexane to give white solid after evaporation of the solvent. ¹H NMR (300 MHz, CDCl₃): δ 3.32 (s, 2H), 3.38 (s, 6H), 3.56 (m, 4H), 3.75 (m, 4H), 3.87 (m, 4H), 4.15 (m, 4H), 6.99 (s, 2H). ¹³C NMR (75 MHz, CDCl₃): δ 59.4, 69.9, 69.9, 71.3, 72.4, 79.9, 83.1, 113.9, 118.6, 154.4.

[087] 3,3'-[(2,5-diiodo-1,4-phenylene)bis(oxy)]bis[N,N,N-triethyl-1-propanaminium]

bromide salt (Compound 5b). Compound 4 (3.01 g 5 mmol) was suspended in a mixture of 100 mL of triethylamine, 38 mL of 4 water, 56 mL of ethanol, and 56 mL of acetone. The mixture was refluxed overnight. The solvent was evaporated and the residue was washed with acetone several times to yield white solid. ¹H NMR (300 MHz, CD₃OD): δ 1.30 (t, 12H), 2.16 (m, 4H), 3.33 (q, 8H), 3.45 (m, 4H), 4.04 (m, 4H), 7.30 (s, 2H). ¹³C NMR (75 MHz, CD₃OD): δ 8.1, 23.3, 54.3, 55.9, 67.9, 87.2, 124.1, 154.1.

[088] PPE-Net₃-OR11. Compound 3a (362 mg, 1 mmol), compound 5a (722 mg, 1 mmol), CuI (5.7 mg, 0.03 mmol), and Pd(PPh₃)₄ (35 mg, 0.03 mmol) were dissolved in a mixture of 30 mL of DMF, 20 mL of water, and 10 mL of diisopropylamine. The mixture was heated to 70°C and kept stirring overnight. The reaction mixture was concentrated by rotary evaporation and added dropwise into 250 mL of acetone.

[089] The precipitate was dissolved in a small amount of Millipore water and filtered through quantitative filter paper, followed by a 25 μm glass filter. The solution was dialyzed against water using 6-8 kD MWCO cellulose membrane. The solution was concentrated via rotary evaporation and the polymer was precipitated with acetone. The precipitate was collected by centrifugation and washed with acetone. The product was a bright yellow powder and it was dried under vacuum for 5 hours. ¹H NMR (300 MHz, CD₃OD): δ 2.46 (br), 3.05 (br), 3.14 (br), 3.44 (br), 3.60 (br), 3.79 (br), 4.16 (br), 7.16 (br).

[090] PPE-NMe₃-OR8 was synthesized in a similar procedure using compound 3b (451 mg, 1 mmol), compound 5b (806 mg, 1 mmol) ¹H NMR (300 MHz, CD₃OD): δ 1.37 (br), 2.22 (br), 3.02 (br), 3.39 (br), 3.52 (br), 3.75 (br), 4.11 (br), 7.37 (br).

[091] As stated above, structures having various repeat units in the side chains are contemplated by the present disclosure. Accordingly, an exemplary synthesis scheme for PPE-C₆-NMe₃-OR8 (Fig. 5) where k = 6 (also referred to as PPE-C₆-NMe₃-OR8) is shown in Fig. 14. Synthesis for the scheme shown in Fig. 14 is as described below:

[092] Compound 2. 2,5-Diiodohydroquinone (2.00 g, 5.53 mmol) and diethylene glycol monomethyl ether p-toluenesulfonate (6.07 g, 22.12 mmol) in 120 mL of methylethylketone was placed under argon. To this solution K₂CO₃ (3.06 g, 22.12 mmol) and KI (0.09 g, 0.55 mmol) was added. The reaction mixture was refluxed at 100 °C for 48 hours and then cooled

to room temperature. The solvent was removed and the solid was dissolved in CH₂Cl₂ (200 mL), followed by washing with 100 mL of 10 % KOH solution, water, and saturated NaCl solution. The organic layer was dried with sodium sulfate and concentrated to give a gold color oil. Flash chromatography on silica gel (80 % CH₂Cl₂/ 10 % hexane/ 10% ethyl acetate) yielded a white solid (1.35 g, 43 %). ¹H NMR (300 MHz, CDCl₃): δ 3.40 (s, 6H), 3.58 (m, 4H), 3.78 (m, 4H), 3.88 (m, 4H), 4.11 (m, 4H), 7.23 (s, 2H). ¹³C NMR (75 MHz, CDCl₃): δ 59.5, 69.9, 70.7, 71.4, 72.4, 86.7, 123.8, 153.4.

[093] Compound 3. Schlenk flask equipped with compound 2 (1.29g, 2.27 mmol), CuI (0.013 g, 0.068 mmol), and Pd(PPh₃)₄ (0.052 g, 0.045 mmol) was placed under argon. And then 20 mL of toluene and 40 mL of diisopropylamine were added and argon bubbled through the solution for 30 minutes. To this solution, (trimethylsilyl)acetylene was added and the solution stirred at 70 °C for 3 days. The solvent was removed and the residue was dissolved in CH₂Cl₂ and filtered through one-inch silica gel using ethyl acetate. The filtrate was concentrated and purified by flash chromatography on silica gel (8 % CH₂Cl₂/ 67 % hexane/ 25% ethyl acetate) to yield a gold oil, which solidified slowly at room temperature (0.87 g, 76 %). A two-necked flask with obtained compound (0.8 g, 1.58 mmol, 1 eq.) and methanol (45 mL) was placed and argon bubbled through the solution for 30 minutes. Tetrabutylammonium fluoride (1M in THF, 3.79 mL) was then added to the flask under the argon and the mixture was stirred at room temperature for 9 hours. The solvent was removed and the solid was purified by flash chromatography on silica gel (5% methanol/95% methylene chloride) to yield a light yellow solid (0.42 g, 1.16 mmol, 73%). ¹H NMR (300 MHz, CDCl₃): δ 3.32 (s, 2H), 3.39 (s, 6H), 3.55 (m, 4H), 3.74 (m, 4H), 3.86 (t, 4H), 4.15 (t, 4H), 7.00 (s, 2H). ¹³C NMR (75 MHz, CDCl₃): δ 59.4, 69.9, 69.9, 71.3, 72.4, 79.9, 83.1, 113.9, 118.6, 154.4.

[094] Compound 4. 1,6-dibromohexane (5.66 g, 23.22 mmol), K₂CO₃ (5.35 g, 38.7 mmol), and acetone (150 mL) were added to a three-neck, round bottomed flask equipped with a condenser and an additional flask. 2,5-Diiodohydroquinone (1.4 g, 3.87 mmol) was dissolved in 150 mL of acetone and added dropwise to the mixture solution at 70 °C. The reaction was stirred overnight and cooled to room temperature. K₂CO₃ was removed by filtration through Celite and the solvent was removed. The resulting solid was dissolved in chloroform and washed with 10 % NaOH, water, and saturated NaCl solution. The organic layer was dried with sodium sulfate, filtered and concentrated. The resulting solid was crystallized from ethylacetate and hexane. The white solid was dissolved in hot ethanol and insoluble solid was removed using hot filtration. The solution was concentrated to yield a

white solid (yield 80 %). ¹H NMR (300 MHz, CDCl₃): δ 1.52 (m, 8H), 1.87 (m, 8H), 3.41 (t, 3H), 3.92 (t, 4H), 7.17 (s, 1H).

[095] Compound 5. Compound 4 (1.70 g, 2.47 mmol) was suspended in 25 % trimethylamine in water (80 mL), ethanol (120 mL), and acetone (120 mL) and heated to 120 °C. The reaction was refluxed overnight. The solvent was removed and the white solid recrystallized from ethanol to yield 91%. ¹H NMR (300 MHz, CD₃OD): δ 1.36 (m, 12H), 1.72 (m, 4H), 3.06 (s, 18H), 3.26 (m, 4H), 3.89 (t, 4H), 7.21 (s, 1H).

[096] PPE-C6-NMe₃-OR8 (16). Compound 3 (50.4 mg, 0.1mmol) and compound 5 (109.2 mg, 0.1 mmol), DMF (5 mL), and water (5 mL) were placed into a Schlenk flask and degassed with argon for 30 min. In a separate flask, CuI (1 mg, 0.005 mmol), Pd(PPh₃)₄ (4.8 mg, 0.004 mmol), DMF (2.5 mL), and triethylamine (2.5 mL) were degassed with argon for 30 minutes and added to the degassed solution containing compound 5 and compound 10. The reaction mixture was stirred at 60 °C for 22 hours. The DMF solution was added to 200 mL of acetone to form a precipitate. The collected yellow precipitate was dissolved in an aqueous solution containing NaCN, filtered using a 25 μm glass filter, and followed by dialysis against deionized water using 6-8 kD MWCO cellulose membrane for 2 days. The polymer solution was lyophilized to yield a yellow solid (Yield: 63 mg, 49%). ¹H NMR (300 MHz, DMSO-d₆): δ 1.37 (br, 18H), 3.05 (s, 18H), 3.22 (s, 6H), 3.30 (br, 4H), 3.45 (br, 4H), 3.67 (br, 4H), 3.81 (br, 4H), 4.08 (br, 4H), 4.22 (br, 4H), 7.15 (br, 4H).

[097] Fig. 7 shows the chemical structure of PPE-NMe₃-Th. Suitable counter ions for PPE-NMe₃-Th include Cl⁻, Br⁻ or I⁻. An exemplary synthesis scheme for PPE-NMe₃-Th where k = 3 is shown in Fig. 15. Synthesis for the scheme shown in Fig. 15 is as described below:

[098] Diiodohydroquinone (compound 3) 1,4-bis(3-bromopropoxy)-2,5-diiodobenzene (compound 4) and 3,3'-[(2,5-diiodo-1,4-phenylene)bis(oxy)]bis[N,N,N-trimethyl-1-propanaminium] bromide salt (compound 5) were synthesized according to the literature procedures as described in Zhou, Q.; Swager, T. M. J. Am. Chem. Soc., 1995, 117, 7017–7018, McQuade, D. T.; Hegedus, A. H.; Swager, T. M. J. Am. Chem. Soc. 2000, 122, 12389–12390, and Ogawa, K.; Chemburu, S.; Lopez, G. P.; Whitten, D. G.; Schanze, K. S. Langmuir. 2007, 23, 4541, respectively.

[099] 2,5-Bis(trimethylsilyl)ethynylthiophene (compound 6). 2,5-Dibromothiophene (4.00 g, 16.53 mmol), (compound 6) CuI (0.38 g, 1.98 mmol), Pd(PPh₃)₂Cl₂ (0.69 g, 0.98 mmol), and 120 mL of isopropylamine were placed in a Schlenk flask and the solution was degassed with stirring for 30 min under ice-bath by bubbling argon gas. To this solution was added (trimethylsilyl)acetylene (6.49 g, 66.12 mmol). The solution was stirred under an icebath for

1 h. The temperature was raised to room temperature and mixture was kept stirring for an additional hour. The resulting solution was heated to 75 °C and stirred for 20 h. The solvent was removed and the solid was purified by flash chromatography on silica gel with hexane to yield a yellow solid **7** (2.54 g, 55.5%). ¹H NMR (300 MHz, CDCl₃): δ 0.24 (s, 18H), 7.04 (s, 2H).

[0100] 2,5-Diethynylthiophene (compound **7**). To a suspension of compound **7** (0.4 g, 1.45 mmol) in deoxygenated methanol (20 mL) was added 0.1 mL of 0.5 M aqueous KOH solution. The mixture was stirred at room temperature under argon for 40 min. The solution was diluted with water (50 mL) and extracted with n-pentane (2 × 50 mL). The combined organic solution was dried over Na₂SO₄ and the solvent was removed at reduced pressure to yield **8** as a viscous oil (0.14 g, 73%). ¹H NMR (300 MHz, CDCl₃): δ 3.32 (s, 2H), 7.09 (s, 1H). ¹³C NMR (75 MHz, CDCl₃): δ 132.6, 123.6, 82.1, 76.2.

[0101] PPE-NMe₃-Th. A solution of compound **5** (100 mg, 0.15 mmol), CuI (4 mg, 0.02 mmol), and Pd(PPh₃)₄ (10 mg, 0.01 mmol) in 8.5 mL of DMF/H₂O/*i*Pr₂NH (v/v/v) 9/6/2) was deoxygenated with argon for 30 min. Then, compound **7** was added to the solution under argon. The resulting solution was heated at 70 °C for 22 h. The reaction mixture was poured into 200 mL of acetone. The precipitate was dissolved in small amount of Millipore water and treated with NaCN, filtered using 25 μm glass filter and followed by dialysis against deionized water using 6-8 kD MWCO cellulose membrane. The polymer solution was lyophilized to yield a yellow-tan solid (46 mg, 51%). ¹H NMR (300 MHz, CD₃OD): 2.38 (br), 3.21 (br), 3.63 (br), 4.22 (br), 7.23 (br), 7.33 (br). ¹³C NMR (75 MHz, CDCl₃) spectrum was not obtained due to the limited solubility of the compound.

[0102] Fig. 8 shows the chemical structure of PPE-NMe₃-n-COOEt. Suitable counter ions for PPE-NMe₃-n-COOEt include Cl⁻, Br⁻ or I⁻. Fig. 10 shows the chemical structure of PPE-NMe₃-Th-n-COOEt. Suitable counter ions for PPE-NMe₃-Th-n-COOEt include Cl⁻, Br⁻ or I⁻. An exemplary synthesis scheme for PPE-NMe₃-n-COOEt and PPE-NMe₃-Th-n-COOEt where k = 3 is shown in Fig. 16. Synthesis for the scheme shown in Fig. 16 is as described below:

[0103] Monomer **1** (1.0 mmol), monomer **3** (1.0 mmol), and a specific amount of ethyl-4-iodobenzoate (varying from 10 to 55 molar percent) were dissolved in the solvent mixture (40 mL) of THF/Et₃N (v/v = 3/2) in a Schlenk flask. The solution was degassed with argon for 30 minutes at 55 °C and followed by the addition of CuI (10 mg, 0.052 mmol) and Pd(PPh₃)₄ (32 mg, 0.028 mmol). The reaction mixture was stirred under argon at 60 °C for 24 hours. The reaction mixture was poured into 400 mL of methanol. The precipitate was collected by

vacuum filtration and further purified by one repeated cycle of dissolution in THF or chloroform and precipitation in methanol. The organic soluble polymers were quaternized according to the procedure described in Tang, Y. L.; Zhou, Z. J.; Ogawa, K.; Lopez, G. P.; Schanze, K. S.; Whitten, D. G. *Langmuir* **2009**, 25, 21. The quaternized polymers was further purified by filtration through a 25 μm glass filter and dialysis against deionized water using 3.5 or 12 kD (depending on the number of polymer repeat units) molecular weight cutoff (MWCO) cellulose membrane for 2 days.

[0104] Fig. 9 shows the chemical structure of PPE-DABCO-n-COOEt. Suitable counter ions for PPE-DABCO-n-COOEt include Cl^- , Br^- or I^- . An exemplary synthesis scheme for PPE-DABCO-n-COOEt where $k = 3$ is shown in Fig. 17. Synthesis for the scheme shown in Fig. 17 is as described below:

[0105] Monomer **2** (1.0 mmol), monomer **3** (1.0 mmol), and a specific amount of ethyl-4-iodobenzoate (**4**, varying from 10 to 30 molar percent) were dissolved in the solvent mixture (20 mL) of THF/ Et_3N ($v/v = 3/2$) in a Schlenk flask. The solution was degassed with argon for 30 minutes at room temperature and followed by the addition of CuI (10 mg, 0.052 mmol) and $\text{Pd}(\text{PPh}_3)_4$ (32 mg, 0.028 mmol). The reaction mixture was stirred at room temperature under argon for 24 hours. The reaction mixture was poured into 400 mL of methanol. The precipitate was collected by vacuum filtration and further purified by one repeated cycle of dissolution in THF or chloroform and precipitation in methanol. A solution of compound **1** (0.25 mmol) in 1 mL of DMA was added to the organic soluble polymer (0.1 mmol) solution in 3 mL of DMA. The mixture solution was stirred at 60 $^\circ\text{C}$ for 24 h. The resulting solution was poured into 100 mL of acetone. The obtained solid polymers containing diazabicyclooctane (DABCO) based alkylammonium groups (PPE-DABCO-n-COOEt) was collected by vacuum filtration and dissolved in deionized water. The polymers were further purified by filtration through a 25 μm glass filter and dialysis against deionized water using 3.5 or 12 kD (depending on the number of polymer repeat units) molecular weight cutoff (MWCO) cellulose membrane for 2 days.

[0106] Each of the PPEs described herein has been tested for and has demonstrated significant dark and light-induced biocidal activity. An exemplary study is shown and described in Examples I and II, below. (Furthermore, at least some of the PPEs described herein may have the ability to retain activity even during photobleaching, as shown in Example V, below.) Accordingly, in yet another embodiment, the present disclosure provides novel biocides formed from or otherwise incorporating the PPEs described herein. Penetration of the bacterial membrane and binding of PPEs with DNA may provide paths for

this activity. Further studies have shown that while PPEs are structurally diverse, they are generally amphiphilic due to the hydrophilic, charged side chains positioned along the rod-like hydrophobic PPE backbone. Dye leakage studies demonstrated a size dependent membrane perturbation against bacterial membrane mimics, with longer oligomers exhibiting higher activity than their smaller counterparts. Furthermore, the membrane perturbation activity appears to be selective with respect to specific types of membrane lipids – that is, most PPEs perturbed bacterial but not mammalian membrane mimics, providing specificity that enables them to be used in a variety of environments, including those in which mammalian cells are present.

[0107] Furthermore, a number of the PPEs described herein (and all of those that were tested) demonstrated significant antiviral activity, as shown in Example II, below. Accordingly, in yet another embodiment, the present disclosure provides novel antivirals formed from or otherwise incorporating the PPEs described herein.

[0108] Moreover, as shown in Example IV, below, PPE-DABCO has demonstrated significant antifungal activity. It is reasonable to assume that PPE-DABCO-n-COOEt would also have significant antifungal activity.

[0109] Accordingly, the PPEs disclosed herein are able to interfere with the pathogenicity a wide variety of pathogens, by inactivating, killing, or otherwise harming them. Thus, the PPEs described herein are suitable for attachment to, incorporation in, or association with a wide variety of substances and materials in order to prevent, reduce, or eliminate pathogens and pathogen-related harm caused to or by the substances and materials.

[0110] For example, the PPEs disclosed herein are suitable for attachment to or formation of fibrous or other materials in order to produce textiles or other (soft or hard) surfaces having antimicrobial, antiviral and/or antifungal properties. Thus, according to various embodiments, it may be desirable to have one or more of the PPEs disclosed herein functionally and robustly attached to a surface, for example via covalent linkages so that it can interfere with the pathogenicity of any pathogen the PPE comes into contact with. According to some embodiments, attachment of the PPE via chemisorption and physisorption may also be used.

[0111] In chemisorptions, a textile substrate is chemically activated with a primer or initiator and then reacted with a polymer or prepolymer to graft the conjugated polyelectrolyte to the surface in a step growth polymerization process. An exemplary chemisorption scheme employing a step growth polymerization process is shown in Fig. 18. Alternate reaction

schemes may employ a living polymerization mechanism utilizing molecule by molecule propagation starting from a single molecule initiator.

[0112] In physisorption, the textile and conjugated polyelectrolyte are mixed under appropriate conditions such that the positively charged polymer attaches to the negatively charged textile surface. Typically the PPE is dissolved in a solvent (e.g., water or methanol) and the fabric is “dyed” with the solution.

[0113] Alternatively, according to still an embodiment, an initial organosilane attachment may be used as a synthetic approach to accomplish surface grafting. See, e.g., Ogawa, K.; Chemburu, S.; Lopez, G. P.; Whitten, D. G.; Schanze, K. S. “Conjugated Polyelectrolyte-Grafted Silica Microspheres” *Langmuir*, 2007, 23, 4541-4548, which is hereby incorporated by reference. By putting an organic iodine on the substrate we have grafted PPEs on nano- and micro-particles and planar surfaces. This silane approach may also be used to graft PPEs onto fabrics. Furthermore, this approach can be easily extended to provide more robust linkages than silanes, using modified chemistries for attaching PPEs to surfaces including ester, ether and amide linkages as needed.

[0114] Accordingly, the PPEs described herein may be incorporated into or onto hard or soft surfaces using the techniques described above or, alternatively, by other known casting, electrospinning, dipping, or coating techniques. However, it is noted that the photophysical properties of PPEs are dependent on planarity which can be affected by self-assembly onto a substrate or placement in a poor solvent. Accordingly, these factors should be considered and taken into account when selecting a particular attachment or incorporation method.

[0115] As a still further embodiment, the PPEs may themselves be formed into fibers, for example via electrospinning.

[0116] It will be appreciated that any suitable fabric or material, including natural and/or synthetic fibers and materials may be used as an attachment surface for the PPEs described herein. According to some embodiments, suitable fabrics may comprise or consist of natural fibers such as cotton, silk and/or wool, or suitable blends thereof. Blended fabrics may include only natural fibers, only synthetic fibers, or both natural and synthetic fibers. In some cases, the antimicrobial polymers described herein may be incorporated into electrospun fibers for woven fabrics including, but not limited to filters. Other suitable textiles may include, but are not necessarily limited to rayon, nylon, or blends of cotton, silk, wool or other natural fabrics or fibers with synthetic fabrics or fibers of rayon or nylon.

[0117] Potential uses of fibers may include prophylaxes for potentially contaminated surfaces including mattresses and bed linens, countertop coverings, tablecloths, curtains and various

swabs, bandages, sterile mats and liners for use both inside and outside a sterile/clinical environment or in food-preparation areas. Their uses may be directed against known contamination, as in a wound infection, or applied as a deterrent to propagation of pathogenic agents in such applications as coverings for common fomites. Treatments of the compounds onto various cellulosic components would also enable their use as filter elements for water purification.

[0118] Different blends to specifically release or retain killed bacteria could be developed based on combination of polymers with the desired retention properties. This could be effected either by use of varied polymer proportions in a single layer coating or by building multiple layers with the required external affinities.

[0119] According to some embodiments, the PPEs described herein may be incorporated into materials having commercial, industrial and/or household applications. Alternatively, the PPEs described herein may be used as or incorporated into antimicrobial, antiviral or antifungal coatings for such materials. For the purposes of this application, it should be noted that the term "material" incorporates both "soft" and "hard" substances including organic and inorganic matter such as, but not limited to, natural and man-made fabrics, plant-based materials, metals, polymers, wood, stone, plastic, and the like.

[0120] Examples of suitable medical applications for the PPEs described herein include bedsheets, hospital garments, curtains, floor and wall materials, air filtration systems, medical devices, bandages, surgical instruments, gloves, masks, lab coats, gauze orthopedic prostheses, bedding, bed frames, mattress covers, surgical furniture, dividers, curtains, carts for transport of medication, linens, dental trays, incise drapes, wound dressings, and implants.

[0121] Applications for the building industry include the coating or incorporation of PPEs in wall laminates, hand rails, pulls, trims, door handles, slings, hoists, window blinds, paints, sealants, polishes, and plastics.

[0122] Other applications include coatings for keyboards, gaming devices, toys, (for example, but limited to, in a daycare environment), industrial, commercial and household kitchens, food preparation equipment and utensils or any other surface where a sterile environment is desirable.

[0123] According to various embodiments, the PPEs described herein may be incorporated into various aspects of filtration devices. For example, the antimicrobial polymers may be incorporated into filter elements for air filtration systems such as those used in commercial or residential buildings, cars, buses, trains airplane cabins etc. Alternatively or additionally, the antimicrobial polymers may be incorporated into commercial or household water or other

liquid filtration systems by application of coatings on equipment and incorporation into and/or coating on filters. Alternatively or additionally, the antimicrobial polymers described herein may be utilized in recoverable bacterial absorbents (by filtration or magnetic components) in the form of coated beads or other suitable substrates. Furthermore, they may be incorporated in separation membranes for bacterial exclusion, extraction, and/or immobilization. They may also be incorporated into or used as a coating for disposal bags for biological waste or other (potentially) contaminated materials.

[0124] Other applications include in-can or in-tank preservation of aqueous functional fluids. This may include incorporation of the presently described PPEs into polymer emulsions, paints and coatings, adhesives and sealants, mineral slurries, metal working fluids, cosmetics and personal care products and cooling and recreational water. (See, e.g., Bruns et al. "Directory of Microbiocides for the protection of materials: A Handbook Chapter 3 R&D in material protection: new biocides," Wilfried Paulus, Ed.; Springer (2005).

[0125] Specific combinations and directed multilayer constructs may lend themselves to either single use or multiple uses, depending on the sequestration properties of that given combination. For example, coatings that have a high affinity for microbial binding may lend themselves more to single use applications (i.e. bandages or wipes) and those that would release microbial material, either upon washing or other decontamination could undergo multiple uses (i.e. bed linens, tablecloths).

[0126] According to various embodiments, the PPEs disclosed herein may be used to form or otherwise incorporated into gels or other materials. These gels or other materials may further include other biologically active materials. Much recent work has been devoted to the development of materials whose properties can be altered drastically by relatively small changes in properties such as temperature, pressure, solution or suspension properties (including but not limited to pH); these "stimuli responsive materials" (SRM) are often prepared as polymers or as surfaces prepared from components that can be covalently linked or self-assembled on surfaces. Smart polymers that have found use in biotechnology and medicine have been described by I Yu Galaev in *Russian Chemical Reviews* 64: 471-489 (1995); A. S. Hoffman in *Clinical Chemistry* 46:1478-1486 (2000) and H. G. Schild, *Prog. Polym. Sci.* 17, 163 (1992), incorporated herein by reference.

[0127] Prominent examples of SRMs include poly (N-isopropyl-acrylamide) (PNIPAAm) and oligo-ethylene glycol oligomers terminated with a thiol (OEG). The former can be grown from a surface by attaching an initiator monomer to a surface and following this with in situ polymerization. Through an ATRP process; the thickness of the resulting film can be

controlled as a function of incubation time at a fixed catalyst and monomer concentration. The OEGs can be attached to a surface (usually Au) by covalent assembly as a self-assembled monolayer (SAM). For surfaces coated with either PNIPAAm or OEG there is a strong temperature dependence of the film properties. In both cases, films formed from these materials in contact with an aqueous solution exist as hydrated, expanded films at low temperatures that are relatively unreactive and non-adsorbative towards various biological species including proteins, cells, bacteria, viruses, and the like. Above a specific lower critical solution temperature (LCST) the films contract, releasing water and become very hydrophobic. At temperatures higher than the LCST films from either SRM become thinner and strongly attract proteins, cells and other biological species that do not bind below the LCST.

[0128] According to yet another embodiment, the present disclosure provides films and assemblies containing both SRM components and the PPEs described herein. In general, these assemblies provide a novel functional material that can be switched between active and inactive forms wherein, in the active form, the material is able to capture a biological species of interest and, in the inactive form, the material is able to release the biological species. In some embodiments the material can be switched between active and inactive forms repeatedly, allowing for reuse of the same material. Films containing these two functional components can be readily prepared by covalent synthesis or by a self assembly process employing a mixture of individual SRM and PPE thiols.

[0129] Viewing Figs. 19 it can be seen that at low temperatures an PPE of appropriate length is buried amidst the expanded form of the SRM and inaccessible to any biological species (such as a protein, cell, bacteria, virus, etc.) present in the aqueous media. Moreover, these species are not attracted to the surface and do not associate with it. However, as the temperature is elevated above the LCST, contraction of the SRM component “unsheathes” the PPE, as shown in Fig. 20. Both components are now hydrophobic and strongly attractive. Accordingly, the unsheathed PPE is able to form a complex with the biological species.

[0130] Accordingly, in one embodiment, the presently described structure can form a reusable biocidal material. Under low temperatures the antimicrobial activity of the PPE is masked by the extended SRMs and therefore inactive. As stated above, elevation of the temperature above the LCST unsheathes the PPE, which is then allowed to form a complex with, thereby trapping, the bacteria. The PPE's biocidal activity is then exploited to inactivate, kill or destroy the trapped species, under either dark conditions or under uv light irradiation. Following destruction of the pathogen, the film will typically be contaminated

with debris from the killed bacteria or cell. Returning the film to temperatures lower than the LCST results in expansion of the SRM, forcing the debris away from the PPEs. The result is a self-cleaning, reusable, biocidal film.

[0131] Examples of other practical uses for these mixed films include employing them as an active sensor which can be monitored by steady state fluorescence or by laser interferometry. The attachment of protein, cells or bacteria to the surface can be detected, for example, by the monitoring irradiation.

[0132] The present disclosure further provides methods of manufacturing the functional materials described herein. Thiol terminated OEG derivatives are commercially available in a wide range of structures. A method of synthesis of PNIPAAm by monomer polymerization onto an initiator functionalized surface is shown in Fig. 21.

[0133] The specific methods and compositions described herein are representative of preferred embodiments and are exemplary and not intended as limitations on the scope of the invention. Other objects, aspects, and embodiments will occur to those skilled in the art upon consideration of this specification, and are encompassed within the spirit of the invention as defined by the scope of the claims. It will be readily apparent to one skilled in the art that varying substitutions and modifications may be made to the invention disclosed herein without departing from the scope and spirit of the invention. The invention illustratively described herein suitably may be practiced in the absence of any element or elements, or limitation or limitations, which is not specifically disclosed herein as essential. The methods and processes illustratively described herein suitably may be practiced in differing orders of steps, and that they are not necessarily restricted to the orders of steps indicated herein or in the claims. The invention has been described broadly and generically herein. Each of the narrower species and subgeneric groupings falling within the generic disclosure also form part of the invention. This includes the generic description of the invention with a proviso or negative limitation removing any subject matter from the genus, regardless of whether or not the excised material is specifically recited herein. In addition, where features or aspects of the invention are described in terms of Markush groups, those skilled in the art will recognize that the invention is also thereby described in terms of any individual member or subgroup of members of the Markush group.

[0134] As used herein and in the appended claims, the singular forms "a," "an," and "the" include plural reference unless the context clearly dictates otherwise.

[0135] All patents and publications referenced below and/or mentioned herein are indicative of the levels of skill of those skilled in the art to which the invention pertains, and each such

referenced patent or publication is hereby incorporated by reference to the same extent as if it had been incorporated by reference in its entirety individually or set forth herein in its entirety. Applicants reserve the right to physically incorporate into this specification any and all materials and information from any such cited patents or publications.

Examples

Example I – Biocidal activity of PPE-NMe₃-n-COOEt

[0136] As described herein, we synthesized cationic CPEs (PPE-NMe₃-n-COOEt, n = 7, 9, 11, 14, 20, and 49) with variable chain lengths by controlling the added amount of a monofunctional “end-capping” agent, ethyl 4-iodobenzoate to the polymerization reaction.

[0137] Biocidal activity experiments were conducted under dark and light exposed conditions with two different concentrations (1 and 10 μM) of polymer solution. Two trends were found: (1) shorter chain length of polymers show stronger antimicrobial activity against *Escherichia coli* under both dark and light exposed conditions and (2) a higher concentration of polymer solution shows inner filter effect.

[0138] Figs. 22 and 23 show plots of biocidal activity based on chain length at concentrations of 1 and 10 μg/mL respectively. At a high concentration (10 μg) of the polymer solutions (n = 7 and 20) an Inner filter effect (little killing of bacteria) was seen. However, at low concentrations (1 μg) of the polymer solutions the shortest chain length of polymer shows the most effective light-induced biocidal activity. Fig. 24 shows flow cytometry results. Confocal Microscopy comparing control *E. Coli* and *E. Coli* after exposure to 1 μg/mL PPE-NMe₃-7-COOEt and 120 min UV light irradiation show significant killing of bacteria.

[0139] Accordingly, it can be seen that the series of cationic CPEs shown and described herein exhibit chain length dependent photophysical properties and complexation with oppositely charged molecules. Furthermore, the shorter chain length of polymer shows more effective light-induced biocidal activity.

Example II- Membrane perturbation by PPE-NMe₃-TH, PPE-DABCO, PPE-NMe₃-OR8, PPE-SO₃

[0140] Materials. The antimicrobial molecules were synthesized as described above. 1,2-dioleoyl-sn-glycero-3-phospho-(1'-rac-glycerol) (sodium salt) (DOPG), 1,2-dioleoyl-sn-glycero-3-phosphocholine (DO-PC), 1,2-dioleoyl-sn-glycero-3-phosphoethanolamine (DOPE), *E. coli* total lipid, and cholesterol were purchased from Avanti Polar Lipids and used as received. 5(6)-carboxyfluorescein (hereafter referred to as fluorescein) was purchased

from Sigma-Aldrich. Superfine Sephadex G-25 was obtained from GE Healthcare Bio-Science. All other chemicals were purchased from Sigma-Aldrich or Alfa Aesar. Ultrapure water was used throughout the study (Milli-Q, 18.2 MQ cm⁻¹ resistivity)

Preparation of Fluorescein-Loaded Vesicles and Vesicle Leakage Assays.

[0141] Fluorescein-loaded large unilamellar vesicles (LUV) were prepared by extrusion. See e.g., Ding, L. P.; Chi, E. Y.; Chem_buru, S.; Ji, E.; Schanze, K. S.; Lopez, G. P.; Whitten, D. G., *Langmuir* 2009, 25, 13742-13751. Briefly, a phospholipid stock solution was dried under a flow of nitrogen and then placed under vacuum overnight. The dried lipid film was then hydrated to 2-4 mM with 100 mM fluorescein in water (adjusted to pH 7 with NaOH) with strong shaking for 1 hr at a temperature above the phase transition temperature of the lipid. The resulting suspension was subjected to 4 freeze-thaw cycles. Finally, LUVs were formed by extruding the lipid solution 19 times through a 100 nm pore size polycarbonate membrane using a mini-extruder (Avanti Polar Lipids). Free fluorescein was removed from the dye-loaded vesicles by column filtration (Sephadex G-25 superfine). The mobile phase used was 200 mM NaCl containing 10 mM HEPES at pH 7. After separation, the phospholipid concentration of the dye-loaded vesicles was determined by the modified microprocedure of Barlett. (See, e.g., Bartlett, G. R., *J. Bioi. Chem.* 1959, 234, 466-468.) The hydrodynamic radii (Rh) of vesicles were determined by dynamic light scattering (DLS, DAWN HELEOS II, Wyatt Technology Corporation).

[0142] Vesicle membrane stability in the presence of PPE/OPE was evaluated by a dye-leakage assay. PPE or OPE was added to the dye-loaded vesicles at a (PPE/OPE):lipid molar ratio of 1:50 with a final lipid concentration between 0.2-0.3 mM. The concentration of polymer is based on polymer repeat unit. As the vesicle membrane is perturbed by the PPE or OPE, dye is released and the fluorescence intensity of released dye was recorded at 520 nm (excitation at 485 nm) (SpectroMax M-5 microplate reader, Molecular Devices). The CPE/OPE are not excited at this wavelength. Fluorescein leakage was calculated using equation (1):

$$\text{Fluorescein Leakage} = \frac{F - F_0}{F_{\text{max}} - F_0}$$

[0143] where F₀ is the fluorescence intensity of the vesicles before the addition of PPE/OPE, F is the fluorescence intensity of the sample after the addition of PPE/OPE, and F_{max} is the maximum fluorescence intensity of the sample, achieved by the addition of 1 μL 0.5 M Triton-XI 00 solution to 100 f.L of vesicles that caused complete lysis of the vesicles. Fluorescein leakage is taken as a measure of the extent of vesicle membrane disruption.

Results and Discussion

[0144] It is widely accepted that the naturally occurring antimicrobial peptides and their synthetic mimics mainly target the lipid bilayer of the cell membrane. The phospholipid compositions of bacterial cell walls and mammalian cell membranes are very different. The principle phospholipid components in mammalian cell membranes are phosphatidylcholine (PC), phosphatidylethanolamine (PE), cholesterol, and sphingomyelin. Human erythrocyte cells contain mostly PC and 5-10% of negatively charged phosphatidylserine (PS) lipids. Because of the asymmetric distribution of erythrocyte membrane lipids, more than 95% of PS lipids reside on the inner leaflet of the membrane. Thus, the outer leaflet of the mammalian membrane is near neutral.⁹ On the other hand, the dominant lipids in the bacterial cytoplasmic membrane are phosphatidylglycerol (PG), PE, and diphosphatidylglycerol. Most Gram-negative bacterial membranes, including *E. coli*, contain 60-70% PE and 20-30% PG. As a result, the bacterial membrane is highly negatively charged. Based on the differences in lipid composition between mammalian and bacterial membranes, three vesicle compositions were studied. The membrane perturbation activities of the PPE/OPE used in this report were evaluated by fluorescein release assays (Figs. 25-28).

[0145] Interaction with mammalian membrane mimic. V-1, composed of PC lipids and cholesterol, is used as a model for mammalian cell membranes. Only PPE-DABCO, EO-OPE-1(C3) and EO-OPE-1(Th) caused measurable membrane disruption against V-1 (Figs. 25-28). All other PPE and OPE are inactive. (Note: "inactive" and "no release" refer to no dye release in excess to that of vesicles incubated alone through the entire incubation period).

[0146] Interaction with bacteria membrane mimics. V-2, composed of DOPG and DOPE, is used as a model for bacterial membranes. Most of the cationic PPE/OPE show good activity against V-2 (Figs. 29-32). Specifically, PPE-NMe3-OR8, PPE-DABCO and EO-OPE-1(C3) induce approximately 20% dye release. PPE-NMe3-Th, OPE-2 and 3 and the three S-O PE-n oligomers cause ~ 10% release. In contrast, the anionic PPE-SO- and OPE-1, the shortest molecule tested (based on the distance along the long molecular axis), are inactive. V-3, made from *E. coli* total lipid extract, was used as a better mimic of the bacterial membrane. Dye leakage of the V-3 vesicles induced by PPE/OPE are comparable to the leakage induced in V-2 vesicles. (See Figs. 33-36.) PPE-DABCO and OPE-3 were slightly more effective in inducing leakage in V-3 vesicles compared to V-2, and EO-OPE-1 (C3) and EO-OPE-1 (Th) caused a similar amount of dye leakage in V-2 and V-3. However, S-OPE-n caused a somewhat lower dye leakage in V-3 vesicles compared to V-2. Notably, OPE-1 and PPE-SO- are still inactive against V-3 vesicles. It is worth noting that the active PPE/OPE exhibit

concentration-dependent membrane disruption against V-3; at higher PPE/OPE:lipid ratios, higher levels of dye release were observed.

[0147] Conclusion

[0148] Results from our dye release experiments show that most PPE and OPE compounds used in this study selectively interact with specific types of membrane lipids. For the polymer series, the functional groups on the side chains dominate their membrane perturbation activity. Specifically, the high charge density and hydrophobic alkyl chains of PPE-DABCO's side chains give rise to the polymer's high perturbation activity against all the vesicles used. Not surprisingly, PPE-DABCO also has poor membrane selectivity. For the three oligomers studied, molecular length greatly influences their interactions with lipid bilayers. OPE-n and S-OPE-n exhibit size-dependent activity against bacterial membrane mimics, where longer oligomers exhibit higher activity than their smaller counterparts. EO-OPE, the oligomers without side chains, exhibit high membrane perturbation activity and poor selectivity. These results give us insights into the relationship between molecular structure and membrane perturbation ability of biocidal PPE and OPE. The observation that specific oligomers and polymers have high selectivity towards model bacterial membranes and little activity towards model mammalian membranes indicates these compounds may be efficient and yet non-toxic antimicrobials.

Example III – Antiviral activity

[0149] We investigated the antiviral activity of PPEs and OPEs against MS2 and T4 bacteriophages. Bacteriophage MS2 is a non-enveloped ~27 nm RNA virus with a small genome of ~3600 single strand nucleotides, its morphology is very similar to picornaviruses, such as poliovirus and hepatovirus. Bacteriophage T4 is a relative large non-enveloped DNA virus with a 120 nm long by 86 nm wide head and approximately 100 nm long tail, it has a large genome of ~170 kbp double strand nucleotides. These bacteriophages are commonly employed for studies of environmental pollution and virus detection.

[0150] The isoelectric points of MS2 and T4 phage particles are 3.9 and 4~5 respectively, which endow them a slightly negative surface charge in a neutral buffer system, leading to ready association between phage particles and the cationic PPEs/OPEs. Previously we proposed that after exposure to UV-visible light the PPEs/OPEs can generate singlet oxygen followed by the generation of more corrosive reactive oxygen intermediates, because the conjugated pi bonding system within the backbone of PPEs/OPEs allows efficient

intersystem crossing energy transfer. $^1\text{O}_2$ is known to significantly damage protein, which can account for their high light-activated antiviral ability.

[0151] In the current study, investigation of the light-activated and dark antiviral activity of PPEs/OPEs against two model viruses was reported. The destruction effect of PPEs/OPEs on the morphology of bacteriophage was explored by transmission electron microscope (TEM). Sodium dodecyl sulfate-polyacrylamide gel electrophoresis (SDS-PAGE) provided more insights into the light-activated inactivation mechanism.

Experimental Methods

[0152] Materials. The antimicrobial molecules were synthesized as described above. Luria broth and Agar were purchased from BD Biosciences. All other chemicals were purchased from Sigma-Aldrich or Alfa Aesar. The model bacteriophages—MS2 and T4 were purchased from the American Type Culture Collection (ATCC) along with their host bacteria, *E. coli* 15577 and *E. coli* 11303. Ultrapure water was used throughout the study (Milli-Q, 18.2 M Ω cm $^{-1}$ resistivity).

[0153] Bacteriophage Preparation and Titer. *E. coli* cells were grown in the standard Luria broth. The fresh *E. coli* culture was inoculated from an overnight culture followed by approximately three hours incubation at 37°C to the exponential growth phase (O.D.₆₀₀~0.5). At this growth phase, the *E. coli* cells were collected by centrifuge and washed with *Escherichia coli* minimal medium (Glucose 5 g/L, Na₂HPO₄ 6 g/L, KH₂PO₄ 3 g/L, NH₄Cl 1 g/L, NaCl 0.5 g/L, MgSO₄ 0.12 g/L, CaCl₂ 0.01 g/L, pH 7.2) twice. The cell pellet was resuspended with minimal medium. The phage stock solutions were added into their corresponding bacterial host suspensions the phage-bacteria mixture incubated for 15 minutes at 37°C for infection. The phage-bacteria mixture was transferred into fresh *Escherichia coli* minimal medium and incubated overnight for viral replication. The phage solution was then centrifuged at 3500 rpm for 10 min, followed by filtering the supernatant with 0.22- μ m cellulose ester membrane to remove remaining bacteria and bacterial debris. The phage titer was determined by plaque forming units (PFU). For PFU measurement, the exponential growth phase *E. coli* (ATCC 15597 and 11303 for MS2 and T4 bacteriophage, respectively) cells were incubated with the various dilution tubes of the phage solutions for 15 minutes at 37°C then added into molten soft LB agar with gentle mixing. The soft agar mixture was then poured onto pre-solidified LB plates. After 6~8 hours incubation, the plaque forming units were counted and phage solutions were diluted to 10⁶~10⁷ PFU/ml with the minimal medium for further use.

[0154] Phage Inactivation. 10 ug/ml PPEs and OPEs were incubated with model virus solution in the dark or under UV-light for 1 hour. The UV-light irradiation experiments were carried out in a photoreactor (LZC-ORG, Luzchem Research Inc.). Two illumination sources were employed according to the different photophysical properties of PPEs/OPEs. UVA (centered at ~350 nm) and LZC-420 (centered at ~420 nm) were used to irradiate OPEs and PPEs respectively. The viral inactivation ability was determined by phage titer as stated above and calculated by $\log(N_0/N)$, where N is the PFU of the phage solution after exposure to PPEs/OPEs; N_0 represents the PFU of corresponding negative control (without PPEs, OPEs or UV-irradiation). The reported values were the average of duplicated measurements.

[0155] Transmission Electron Microscopy. High concentration of model viruses ($\sim 10^{11}$ PFU/ml for T4 phage, $\sim 10^{12}$ PFU/ml for MS2 phage) and PPE/OPE (50 ug/ml) was used for TEM imaging (TEM images were generated in the UNM Electron Microscopy Shared Facility using a Hitachi H7500 transmission electron microscope.) Phage samples were prepared by adding 5 uL phage solutions onto carbon-coated copper grids (freshly cleaned by plasma cleaner) and standing for 2 minutes then rinsing with pure water. The negative stain, 2% aqueous solution of uranyl acetate, was adding onto the grids and standing for 2 minutes, the excess stain was removed by filter paper. The grid was dried in air.

[0156] SDS-PAGE. The standard Laemmli protein gel electrophoresis method was used to examine the damage of phage capsid proteins. Electrophoresis was performed at 200V for 30 minutes after which the gels were stained with Coomassie brilliant blue R250 solution for 1 h.

Results and Discussion.

[0157] The phage titer assay described herein was done by a series dilution of the phage-PPEs/OPEs mixture and incubating each diluted sample with the corresponding *E. coli* host cells within molten soft LB agar. Since our previous work demonstrated that the PPEs/OPEs can strongly inactivate *E. coli* cells, which may interface the plaque assay, it is necessary to study the effect of these residual PPEs/OPEs on the *E. coli* host cells. For the control experiment without phage and PPEs/OPEs, the *E. coli* cells can form a uniform bacterial lawn on the surface of soft agar after 6 hours incubation at 37°C. Under current experimental condition, 0.33 ug/ml was the maximum concentration of PPEs/OPEs within the soft agar, which can not cause any obvious defect on the bacterial lawn at the same condition.

[0158] Phage Inactivation. Figs. 37 and 38 depict the phage inactivation under different conditions: PPEs/OPEs in the dark, UV irradiation alone and UV sensitized PPEs/OPEs. PPE-DABCO and EO-OPE-1(Th) exhibit significant dark antiviral activity against T4 phage.

PPE-Th, OPE-1 and EO-OPE-1(C3) can inactivate more than 90% T4 phage in the dark. However, no dark inactivation ability was observed for OPE-3 against T4 phage. Enhanced inactivation of T4 phage was observed by PPEs/OPEs in the presence of UV irradiation. Compared with T4 Phage, all of the PPEs/OPEs produce more efficient dark inactivation of MS2; except OPE-1 and EO-OPE-1(C3), all other compounds show more than 6-log inactivation ability against MS2. Meanwhile, enhanced inactivation of MS2 phage was observed by OPE-1 and EO-OPE-1(C3) in the presence of UV irradiation. It is worthwhile to note that the long wavelength UV-visible light (LZC-420) produce negligible inactivation of the model viruses. In contrast, UVA irradiation causes obvious inactivation of T4 phage and moderate inactivation of MS2 phage. The different effects of UVA light on the model viruses can be partially attributed to the following reasons: upon exposure to UVA irradiation, adjacent thymidine residues within T4 phage genome are covalently linked to form thymidine dimers,⁸ leading to the inactivation of T4 phage. In addition, the genome of T4 phage is almost 47 times larger than that of MS2 phage, as a result, T4 phage is more vulnerable to UVA. The T4 bacteriophage infection mechanism has been extensively studied and well established, it recognizes lipopolysaccharide and the OmpC protein on the surface of *E. coli* cell followed by the injection of phage genome into the host cell and replication of phage particle.⁹ However, the infection mechanism of MS2 phage is not quite clear, it is believed that the pilus of *E. coli* cell are the receptors for MS2 phage.¹⁰ It is reasonable to propose that the PPEs and OPEs can associate with the model viruses through electrostatic interaction followed by the damage of viral capsid and/or the inhabitation the binding of viral particle towards host *E. coli* cell, upon the direct contact between these compounds and model viruses. According to our previous work,^{3a} the enhanced antiviral activity of these compounds in the presence of UV-light can be proposed to the generation of corrosive reactive oxygen species after exposure to UV-visible light, which can strongly damage biomolecules.^{7, 11} Subsequent results confirm the damage of viral capsid caused by PPE-DABCO and EO-OPE-1(Th).

[0159] Viral Morphology Damage. To visualize the viral morphology damage by PPE-DABCO and EO-OPE-1(Th), samples immobilized on carbon-coated grids were imaged by TEM, as shown in Figs. 38-47. More than 10 images were taken for each sample to guarantee the reproducibility of the observed viral damage. The untreated T4 phage maintains its classic morphology with intact head and tail structure (Fig. 39). In contrast, serious damage happens to the PPE-DABCO and EO-OPE-1(Th) treated T4 phage (Figs. 41, 43, 45, and 47). Likewise, the shape of the intact MS2 phage is uniform and the size is very close to the

literature report value (Fig. 40). Obvious morphology change observed for the PPE-DABCO and EO-OPE-1(Th) treated MS2 phage, which are withered and formless (Figs. 42, 44, 46 and 48). Even though not conclusive, ample amounts of doubtful PPE-DABCO and EO-OPE-1(Th) aggregates are visible close to MS2 and T4 phages (data not shown), which imply the efficient association between PPEs/OPEs and model viruses.

Example IV- Antimicrobial activity

[0160] The activity of PPE-DABCO against *S. cerevisiae* was examined. *S. cerevisiae* was cultered, counted by a coulter counter and diluted 10^7 mL⁻¹ in PBS. The suspended culture was then exposed to .13 mM PPE-DABCO for 30 minutes while irradiating with Fiber-Lite 190 and then stained with SYTO 9 and PI (Fungalight™) for 30 minutes. Flow cytometry was then used to count percentage of dead yeast. A control sample (*S. cerevisiae* without exposure to PPE-DABCO) showed 10% dead while the treated samples showed 29-30% dead.

Example V – Photo-chemical self-protecting


[0161] A study of the photochemical reaction processes of a model cationic oligomer based on the p-Phenylene-Ethynylene repeat unit is performed in aqueous solution both in the presence and absence of oxygen. Clearly different reaction pathways were observed with this model compound in the presence and absence of oxygen in aqueous solution. The products of these reactions were followed spectroscopically by UV-Vis Spectroscopy and characterized by Mass Spectrometry. The results of this study revealed the photoaddition of water across the triple bond of the ethynyl group in absence of oxygen, and a possible cycloaddition of oxygen across the triple-bond in the presence of oxygen. A study of PPE-SO₃ indicates that when this material is photolyzed in water in the presence of air, the addition of oxygen can lead to a protection of the polymer from extensive photobleaching may occur via the oxygen adduct acting as a trap site still capable of reactive oxygen species generation.

[0162] As can be seen from the structure shown in Fig. 3, PPE-SO₃ has anionic side groups on each repeat unit. A photobleaching reaction was followed spectroscopically as shown in Fig. 49. There are several aspects of the limited photodegradation that are important to note. The photobleaching of the PPE-SO₃ is very clean. However the photobleaching is much slower than smaller polymers and appears to terminate before a major fraction of the long wavelength transition has disappeared. That there is no major shift in the absorption spectrum is consistent with our previous finding that p-phenylethynylene polymers likely

exist as a chain with a series of "segment chromophores" that serve to break the polymer into several isolated conjugated segments with a break in the conjugation between the "segment chromophores". For the photoreactions reported in this study there is a small, but likely significant, grow-in at wavelengths extending beyond the starting material. For the aerated solutions this is consistent with the presence of a long wavelength absorbing 1,2 - diketone that could readily be generated following cycloaddition of dioxygen to a triple bond and subsequent cleavage of the cycloadduct. A 1,2 - diketone "trap" absorbing in the visible region (biacetyl is yellow but weakly absorbing) could act as a trap and intercept either singlet or triplet excitation hopping between segment chromophores. The biacetyl triplet (ET = 57 kcal/mole)²² is sufficiently energetic to generate singlet oxygen but once biacetyl triplets are generating singlet oxygen it becomes more and more probable that the singlet oxygen is generated remote from a segment chromophore and less likely to cause a degradative reaction. Thus the photochemical generation of a trap that drains excitation energy from the segment chromophore can provide a protection of remaining segment chromophores of the polymer and attenuate photobleaching. Since the trap can generate singlet oxygen the light activated antimicrobial activity may still be retained.

[0163] What is claimed is:

1. A poly (phenylene ethynylene) (PPE) having the structure:



n is selected from the group consisting of the whole numbers between 5 and 200;

A is selected from the group consisting of $\text{C}_2\text{C}_6\text{H}_2$ and $\text{C}_2\text{C}_4\text{H}_2\text{S}$;

B = $\text{C}_2\text{C}_6\text{H}_2$;

C = is either C_6H_4 or not present;

X is selected from the group consisting of: H, $[\text{C}_2\text{C}_6\text{H}_4]_2\text{COOCH}_2\text{CH}_3$, and; $[\text{C}_2\text{C}_4\text{H}_2\text{S}][\text{C}_2\text{C}_6\text{H}_4]\text{COOCH}_2\text{CH}_3$.

Y is selected from the group consisting of: H and $\text{COOCH}_2\text{CH}_3$.

Z_A is selected from the group consisting of $\text{O}(\text{CH}_2)_k(\text{C}_6\text{H}_{12}\text{N}_2)\text{C}_6\text{H}_{13}^{2+}$, $\text{O}(\text{CH}_2)_k\text{SO}_3^-$, $\text{O}(\text{CH}_2)_k\text{N}(\text{CH}_2\text{CH}_3)_3^+$, and $\text{O}(\text{CH}_2)_k\text{N}(\text{CH}_3)_3^+$; where k is selected from the group consisting of the whole number between 1 and 10;

Z_B is selected from the group consisting of H and $(\text{OCH}_2\text{CH}_2)_3\text{OCH}_3$.

wherein:

if Z_A is $\text{O}(\text{CH}_2)_k(\text{C}_6\text{H}_{12}\text{N}_2)\text{C}_6\text{H}_{13}^{2+}$, then Z_B is H, A = $\text{C}_2\text{C}_6\text{H}_2$, C, if present, is C_6H_4 , and X is selected from the group consisting of H and $[\text{C}_2\text{C}_6\text{H}_4]_2\text{COOCH}_2\text{CH}_3$, wherein:

if X is H, then Y is H; and C is not present

if X is $[\text{C}_2\text{C}_6\text{H}_4]_2\text{COOCH}_2\text{CH}_3$, then Y is $\text{COOCH}_2\text{CH}_3$ and C is C_6H_4 ;

if Z_A is $\text{O}(\text{CH}_2)_k\text{SO}_3^-$, Z_B is H, A = $\text{C}_2\text{C}_6\text{H}_2$, C is not present, and X = Y = H;

if Z_A is $\text{O}(\text{CH}_2)_k\text{N}(\text{CH}_2\text{CH}_3)_3^+$, then Z_B is $(\text{OCH}_2\text{CH}_2)_3\text{OCH}_3$, A = $\text{C}_2\text{C}_6\text{H}_2$, C is not present, and X=Y=H;

if Z_A is $\text{O}(\text{CH}_2)_k\text{N}(\text{CH}_3)_3^+$, and Z_B is $(\text{OCH}_2\text{CH}_2)_3\text{OCH}_3$, then C is not present, A = $\text{C}_2\text{C}_4\text{H}_2$ and X = Y = H;

if Z_A is $\text{O}(\text{CH}_2)_k\text{N}(\text{CH}_3)_3^+$, Z_B is H, and C is not present, then A = $\text{C}_2\text{C}_4\text{H}_2\text{S}$ and X = Y = H;


if Z_A is $\text{O}(\text{CH}_2)_k\text{N}(\text{CH}_3)_3^+$, Z_B is H, and C is present, then Y = $\text{COOCH}_2\text{CH}_3$ and X is selected from the group consisting of $[\text{C}_2\text{C}_6\text{H}_4]_2\text{COOCH}_2\text{CH}_3$ and $[\text{C}_2\text{C}_4\text{H}_2\text{S}][\text{C}_2\text{C}_6\text{H}_4]\text{COOCH}_2\text{CH}_3$; wherein

if A = C₂C₆H₂, then X is [C₂C₆H₄]₂COOCH₂CH₃;

if A = C₂C₆H₂S, then X is [C₂C₄H₂S][C₂C₆H₄]COOCH₂CH₃.

2. The PPE of claim 1 wherein A and B = C₂C₆H₂, C is not present, X, Y, AND Z_B = H and Z_A = O(CH₂)_k(C₆H₁₂N₂)C₆H₁₃²⁺.
3. The PPE of claim 1 wherein A and B = C₂C₆H₂, C is not present, X, Y, AND Z_B = H and Z_A = O(CH₂)_kSO₃⁻.
4. The PPE of claim 1 wherein A and B = C₂C₆H₂, C is not present, X and Y = H, Z_A = O(CH₂)_kN(CH₃)₃⁺, and Z_B = (OCH₂CH₂)₃OCH₃.
5. The PPE of claim 4 wherein k = 6
6. The PPE of claim 1 wherein A and B = C₂C₆H₂, C is not present, X and Y = H, Z_A = O(CH₂)_kN(CH₃)₃⁺ and Z_B = (OCH₂CH₂)₂OCH₃.
7. The PPE of claim 1 wherein A = C₂C₆H₂S, B = C₂C₆H₂, C is not present, X and Y = H, Z_A = O(CH₂)_kN(CH₃)₃⁺ and Z_B = H.
8. The PPE of claim 1 wherein A and B = C₂C₆H₂, C = C₆H₄, X = [C₂C₆H₄]₂COOCH₂CH₃, Y = COOCH₂CH₃, Z_A = O(CH₂)_kN(CH₃)₃⁺ and Z_B = H.
9. The PPE of claim 1 wherein A and B = C₂C₆H₂, C = C₆H₄, X = [C₂C₆H₄]₂COOCH₂CH₃, Y = COOCH₂CH₃, Z_A = O(CH₂)_k(C₆H₁₂N₂)C₆H₁₃²⁺, and Z_B = H.
10. The PPE of claim 1 wherein A = C₂C₆H₂S, B = C₂C₆H₂, C = C₆H₄, X = [C₂C₆H₄]₂COOCH₂CH₃, Y = COOCH₂CH₃, Z_A = O(CH₂)_kN(CH₃)₃⁺ and Z_B = H.
11. The PPE of claims 2, 3, 4, 6, 7, 8, 9, or 10 wherein k = 3.
12. The PPE of claim 1 wherein the OPE exhibits biocidal activity.
13. The PPE of claim 1 wherein the OPE exhibits antiviral activity.

14. The PPE of claim 1 wherein the OPE exhibits antifungal activity.
15. The PPE of claim 1 functionally attached to a material or substance so that the OPE can interfere with the pathogenicity of a pathogen that contacts the OPE.
16. A material or substance incorporating the structure of claim 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, or 11.
17. A material or substance incorporating a PPE having the structure:



wherein:

n is selected from the group consisting of the whole numbers between 5 and 200;

A is selected from the group consisting of $\text{C}_2\text{C}_6\text{H}_2$ and $\text{C}_2\text{C}_4\text{H}_2\text{S}$;

$B = \text{C}_2\text{C}_6\text{H}_2$;

C = is either C_6H_4 or not present;

X is selected from the group consisting of: H, $[\text{C}_2\text{C}_6\text{H}_4]_2\text{COOCH}_2\text{CH}_3$, and; $[\text{C}_2\text{C}_4\text{H}_2\text{S}][\text{C}_2\text{C}_6\text{H}_4]\text{COOCH}_2\text{CH}_3$.

Y is selected from the group consisting of: H and $\text{COOCH}_2\text{CH}_3$.

Z_A is selected from the group consisting of $\text{O}(\text{CH}_2)_k(\text{C}_6\text{H}_{12}\text{N}_2)\text{C}_6\text{H}_{13}^{2+}$, $\text{O}(\text{CH}_2)_k\text{SO}_3^-$, $\text{O}(\text{CH}_2)_k\text{N}(\text{CH}_2\text{CH}_3)_3^+$, and $\text{O}(\text{CH}_2)_k\text{N}(\text{CH}_3)_3^+$; where k is selected from the group consisting of the whole number between 1 and 10;

Z_B is selected from the group consisting of H and $(\text{OCH}_2\text{CH}_2)_3\text{OCH}_3$.

wherein:

if Z_A is $\text{O}(\text{CH}_2)_k(\text{C}_6\text{H}_{12}\text{N}_2)\text{C}_6\text{H}_{13}^{2+}$, then Z_B is H, $A = \text{C}_2\text{C}_6\text{H}_2$, C, if present, is C_6H_4 , and X is selected from the group consisting of H and $[\text{C}_2\text{C}_6\text{H}_4]_2\text{COOCH}_2\text{CH}_3$, wherein:

if X is H, then Y is H; and C is not present

if X is $[\text{C}_2\text{C}_6\text{H}_4]_2\text{COOCH}_2\text{CH}_3$, then Y is $\text{COOCH}_2\text{CH}_3$ and C is C_6H_4 ;

if Z_A is $\text{O}(\text{CH}_2)_k\text{SO}_3^-$, Z_B is H, $A = \text{C}_2\text{C}_6\text{H}_2$, C is not present, and $X = Y = \text{H}$;

if Z_A is $O(CH_2)_kN(CH_2CH_3)_3^+$, then Z_B is $(OCH_2CH_2)_3OCH_3$, $A = C_2C_6H_2$, C is not present, and $X=Y=H$;

if Z_A is $O(CH_2)_kN(CH_3)_3^+$, and Z_B is $(OCH_2CH_2)_3OCH_3$, then C is not present, $A = C_2C_4H_2$ and $X = Y = H$;

if Z_A is $O(CH_2)_kN(CH_3)_3^+$, Z_B is H , and C is not present, then $A = C_2C_4H_2S$ and $X = Y = H$;

if Z_A is $O(CH_2)_kN(CH_3)_3^+$, Z_B is H , and C is present, then $Y = COOCH_2CH_3$ and X is selected from the group consisting of $[C_2C_6H_4]_2COOCH_2CH_3$ and $[C_2C_4H_2S][C_2C_6H_4]COOCH_2CH_3$; wherein

if $A = C_2C_6H_2$, then X is $[C_2C_6H_4]_2COOCH_2CH_3$;

if $A = C_2C_6H_2S$, then X is $[C_2C_4H_2S][C_2C_6H_4]COOCH_2CH_3$.

18. The material or substance of claim 17 wherein in the PPE, A and $B = C_2C_6H_2$, C is not present, $X, Y, AND Z_B = H$ and $Z_A = O(CH_2)_k(C_6H_{12}N_2)C_6H_{13}^{2+}$.

19. The material or substance of claim 17 wherein in the PPE, A and $B = C_2C_6H_2$, C is not present, $X, Y, AND Z_B = H$ and $Z_A = O(CH_2)_kSO_3^-$.

20. The material or substance of claim 17 wherein in the PPE, A and $B = C_2C_6H_2$, C is not present, X and $Y = H$, $Z_A = O(CH_2)_kN(CH_3)_3^+$, and $Z_B = (OCH_2CH_2)_kOCH_3$.

21. The material or substance of claim 17 wherein in the PPE, A and $B = C_2C_6H_2$, C is not present, X and $Y = H$, $Z_A = O(CH_2)_kN(CH_3)_3^+$ and $Z_B = (OCH_2CH_2)_2OCH_3$.

22. The material or substance of claim 21 wherein $k = 6$.

23. The material or substance of claim 17 wherein in the PPE, $A = C_2C_6H_2S$, $B = C_2C_6H_2$, C is not present, X and $Y = H$, $Z_A = O(CH_2)_kN(CH_3)_3^+$ and $Z_B = H$.

24. The material or substance of claim 17 wherein in the PPE, A and $B = C_2C_6H_2$, $C = C_6H_4$, $X = [C_2C_6H_4]_2COOCH_2CH_3$, $Y = COOCH_2CH_3$, $Z_A = O(CH_2)_kN(CH_3)_3^+$ and $Z_B = H$.

25. The material or substance of claim 17 wherein in the PPE, A and B = C₂C₆H₂, C = C₆H₄, X = [C₂C₆H₄]₂COOCH₂CH₃, Y = COOCH₂CH₃, Z_A = O(CH₂)_k(C₆H₁₂N₂)C₆H₁₃²⁺ and Z_B = H.

26. The material or substance of claim 17 wherein in the PPE, A = C₂C₆H₂S, B = C₂C₆H₂, C = C₆H₄, X = [C₂C₆H₄]₂COOCH₂CH₃, Y = COOCH₂CH₃, Z_A = O(CH₂)_kN(CH₃)₃⁺ and Z_B = H.

27. The material or substance of claims 18, 19, 20, 21, 22, 23, 24, or 25 wherein k = 3.

Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5





Fig. 6



2/22

Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13





Fig. 14



6/22

Fig. 15




Fig. 16





Fig. 17



9/22




Fig. 19




Fig. 20





Fig. 21



11/22

Fig. 22





Fig. 23



12/22




Fig. 24

Fig. 25





Fig. 26



14/22

Fig. 27




Fig. 28




Fig. 29




Fig. 30




Fig. 31




Fig. 32




Fig. 33




Fig. 34




Fig. 35




Fig. 36




Fig. 37




Fig. 38




Fig. 39




Fig. 40




Fig. 41




Fig. 42




Fig. 43




Fig. 44




Fig. 45




Fig. 46




Fig. 47




Fig. 48

