



(51) International Patent Classification:

B32B 1/08 (2006.01) *F16L 9/00* (2006.01)
B32B 27/30 (2006.01) *F16L 9/147* (2006.01)
C08F 214/26 (2006.01) *F16L 55/165* (2006.01)
F16L 53/00 (2006.01)

(21) International Application Number:

PCT/EP2013/056237

(22) International Filing Date:

25 March 2013 (25.03.2013)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

12161236.0 26 March 2012 (26.03.2012) EP

(71) Applicant: **SOLVAY SPECIALTY POLYMERS ITALY S.P.A.** [IT/IT]; Viale Lombardia, 20, I-20021 Bollate (Milano) (IT).

(72) Inventors: **COLAIANNA, Pasqua**; Via Luigi Varanini, 29/C, I-20100 Milano (IT). **BESANA, Giambattista**; Via Alberto da Giussano, 61, I-22066 Mariano Comense (Como) (IT). **MIRENDA, Marco**; Via Generale Armando Diaz, 20, I-20017 Rho (Milano) (IT). **MESSINA, Nicasio**; Via Padre Giacinto Burrone, 11, I-27028 Zerbolò (Pavia) (IT).

(74) Agents: **BENVENUTI, Federica** et al.; Solvay S.A., Rue de Ransbeek, 310, B-1120 Bruxelles (BE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

(54) Title: FLUOROPOLYMER PIPE

(57) Abstract: The present invention pertains to a pipe comprising at least one layer at least comprising, preferably consisting essentially of (or being made of), a tetrafluoroethylene (TFE) copolymer comprising from 0.8% to 2.5% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) here below: $\text{CF}_2=\text{CF}-\text{O}-\text{R}_f$ (I) wherein R_f is a linear or branched C_3-C_5 perfluorinated alkyl group or a linear or branched C_3-C_{12} perfluorinated oxyalkyl group comprising one or more ether oxygen atoms, said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg [polymer (F)]. The invention also pertains to use of said pipe in heat exchangers and in downhole operations including drilling operations.



Description

Fluoropolymer pipe

[0001] This application claims priority to European application No. 12161236.0 filed on 26.03.2012, the whole content of this application being incorporated herein by reference for all purposes.

Technical Field

[0002] The present invention pertains to a pipe comprising at least one fluoropolymer layer and to use of said pipe in heat exchangers and in downhole operations including drilling operations.

Background Art

[0003] Fluoropolymers derived from tetrafluoroethylene (TFE) and perfluorinated alkyl vinyl ethers (PAVEs) have found wide applications as coatings and linings of process vessels, storage tanks, pipes, valves and fittings due to their high chemical inertness, high melting points, high service temperatures and thermal stability.

[0004] In particular, pipes are typically used for conveying oils and gases at temperatures of usually above 100°C, preferably above 200°C, depending on the application. For instance, pipes used in drilling operations need to withstand high temperatures and pressures, depending where the well is drilled and how deep. The drilling operations indeed involve deeper and deeper wells and typically reach temperatures as high as 260°C or higher than 260°C, especially proximate to the bottom of the well.

[0005] Melt-processable fluoropolymers derived from tetrafluoroethylene (TFE) and perfluoroalkylvinylethers (PAVEs), which are commonly known in the art for being suitable for manufacturing shaped articles such as pipes, typically comprise from 1% to 5% by moles of recurring units derived from said PAVEs.

[0006] These fluoropolymers have generally a melting point of at least 265°C, so that they are advantageously used in applications where high operating temperatures are required. In particular, melt-processable TFE copolymers with perfluoropropylvinylether (PPVE) are most preferred because of their higher melting point, typically between 302°C and 310°C.


[0007] There is thus the need in the art for pipes which are endowed with

improved mechanical properties and improved thermal resistance at high operating temperatures, while retaining chemical resistance to corrosive chemical agents.

Summary of invention

[0008] It has been now found that the pipe of the present invention successfully enables overcoming the deficiencies of the pipes known in the art.

[0009] It is thus an object of the present invention a pipe comprising at least one layer at least comprising, preferably consisting essentially of (or being made of), a tetrafluoroethylene (TFE) copolymer comprising from 0.8% to 2.5% by weight of recurring units derived from at least one per-fluorinated alkyl vinyl ether having formula (I) here below:



wherein R_f is a linear or branched C_3 - C_5 perfluorinated alkyl group or a linear or branched C_3 - C_{12} perfluorinated oxyalkyl group comprising one or more ether oxygen atoms,

said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg [polymer (F)].

[0010] The Applicant has surprisingly found that the polymer (F) according to the present invention is successfully endowed with improved mechanical properties with respect to commercially available TFE copolymers with PAVEs, in particular higher yield strength values and lower creep strain values. It is well known in the art that these properties are related to pipes burst resistance and/or pipes decompression under the effect of pressure impacts.

[0011] The Applicant has thus found that the pipe of the present invention advantageously withstand high pressure and high temperature conditions, while retaining chemical resistance in harsh environments and thermal resistance at high temperatures.

[0012] The yield strength of the polymer (F) is a measure of the maximum stress to be applied at which the polymer (F) begins to deform plastically. The stress at which yield occurs is dependent on both the rate of deformation (strain rate) and, more significantly, on the temperature at which the

deformation occurs.

- [0013] The creep strain of the polymer (F) is a measure of its tendency to deform plastically under the influence of an applied stress. It occurs as a result of long term exposure to high levels of stress which are below the yield strength of the material. The rate of this deformation is a function of the material properties, exposure time, exposure temperature and the applied structural load.
- [0014] For the purpose of the present invention, by the term "plastic deformation" it is hereby intended to denote permanent and non-reversible deformation of the polymer (F).
- [0015] The yield strength and the creep strain of the polymer (F) are thus a measure of its tendency to deform plastically under the influence of pressure impacts, in particular at high operating temperatures.
- [0016] By the term "pipe", it is hereby intended to denote a continuous tubular pipe made of, or at least comprising, the polymer (F) as defined above or a continuous tubular pipe whose inner surface is coated with a tubular layer made of, or at least comprising, the polymer (F) as defined above.
- [0017] The pipe of the present invention may be a monolayer pipe or a multilayer pipe.
- [0018] By the term "monolayer pipe", it is hereby intended to denote a pipe consisting of one tubular layer made of, or at least comprising, a polymer (F).
- [0019] By the term "multilayer pipe", it is hereby intended to denote a pipe comprising at least two concentric layers adjacent to each other, wherein at least the inner layer comprises, or preferably consists essentially of, a polymer (F).
- [0020] Said at least one layer of the pipe of the invention at least comprises, but preferably consists essentially of polymer (F). This means that embodiments wherein said layer comprises polymer (F) in combination with other layer components are encompassed in the scope of the present invention. It is nevertheless understood that embodiments wherein polymer (F) is the sole polymer component are preferred. More particularly, embodiments wherein the layer is made from polymer (F)

possibly in admixture with minor amounts of additional ingredients like pigment, additives, lubricants, and the like which do not substantially modify the properties of polymer (F) are preferred.

[0021] The polymer (F) of the pipe of the invention is typically manufactured by aqueous emulsion polymerisation or aqueous suspension polymerisation processes.


[0022] The polymer (F) of the pipe of the invention is preferably manufactured by aqueous emulsion polymerisation.

[0023] The aqueous emulsion polymerisation is typically carried out in an aqueous medium in the presence of an inorganic water-soluble radical initiator, such as peroxide, percarbonate, persulphate or azo compounds. A reducing agent can be added so as to make easier the initiator decomposition. Non-limitative examples of suitable reducing agents include iron salts. The initiator amount used depends on the reaction temperature and on the reaction conditions. The polymerisation process is carried out at temperatures typically comprised between 50°C and 90°C, preferably between 70°C and 80°C. A chain transfer agent may also be introduced during the polymerisation reaction. Non-limitative examples of suitable chain transfer agents include ethane, methane, propane, chloroform and the like. The polymerisation may be carried out in the presence of fluorinated surfactants such as for example perfluoroalkylcarboxylic acid salts (for example ammonium perfluorocaprylate, ammonium perfluorooctanoate) or other compounds such as for example perfluoroalkoxybenzenesulphonic acid salts, as described for example in **EP 184459 A** (E.I. DU PONT DE NEMOURS AND COMPANY) 11.06.1986 . Some other fluorinated surfactants that can be used in the polymerization process are described in **US 3271341** (E. I. DU PONT DE NEMOURS AND COMPANY) 06.09.1966 , **WO 2007/011631** (3M INNOVATIVE PROPERTIES COMPANY) 25.01.2007 and **WO 2010/003929** (SOLVAY SOLEXIS S.P.A.) 14.01.2010 . It is particularly advantageous to carry out the polymerization in aqueous phase in the presence of perfluoropolyethers, which can be added in the reaction medium under the form of aqueous emulsion in the presence of a

suitable dispersing agent, as described in **EP 247379 A** (AUSIMONT S.P.A.) 02.12.1987 or, preferably, in the form of aqueous microemulsion as described in **US 4864006** (AUSIMONT S.P.A.) 05.09.1989 .

- [0024] The latex so obtained is then coagulated and the solid recovered is dried and granulated. The granules are extruded by conventional melt-processing techniques.
- [0025] The polymer (F) of the pipe of the invention is advantageously melt-processable.
- [0026] By the term "melt-processable", it is hereby intended to denote a polymer (F) which can be processed by conventional melt-processing techniques.
- [0027] The melt flow index measures the amount of polymer which can be pushed through a die, according to ASTM D1238 standard test method, at a specified temperature using a specified load weight. Thus, the melt flow index is a measure for the suitability for melt-processing the polymer (F). This typically requires that the melt flow index be more than 0.1 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.
- [0028] It is essential that the polymer (F) of the pipe of the invention has a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.
- [0029] It has been found that, when the melt flow index of the polymer (F) is lower than 0.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg, the pipe cannot be easily manufactured by melt-processing the polymer (F) using well known melt-processing techniques.
- [0030] On the other hand, it has been found that, when the melt flow index of the polymer (F) is higher than 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg, the pipe obtained therefrom does not comply with the required performances under high temperature and high temperature conditions.
- [0031] The polymer (F) of the pipe of the invention preferably has a melt flow index comprised between 0.6 and 5.5 g/10 min, more preferably between 0.7 and 4.5 g/10 min, even more preferably between 1.2 and 3.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.
- [0032] The perfluorinated alkyl vinyl ether of formula (I) of the polymer (F) of the

pipe of the invention preferably complies with formula (II) here below:



wherein R'_{f} is a linear or branched C_3 - C_5 perfluorinated alkyl group.

- [0033] Non-limitative examples of suitable perfluorinated alkyl vinyl ethers of formula (II) include, notably, those wherein R'_{f} is a $-\text{C}_3\text{F}_5$, $-\text{C}_4\text{F}_7$ or $-\text{C}_5\text{F}_9$ group.
- [0034] The perfluorinated alkyl vinyl ether of formula (I) of the polymer (F) of the pipe of the invention more preferably is perfluoropropyl vinyl ether (PPVE).
- [0035] It is essential that the polymer (F) of the pipe of the invention comprises from 0.8% to 2.5% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) as defined above.
- [0036] It has been found that, when the amount of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) is lower than 0.8% by weight, the pipes obtained therefrom do not comply with the required performances under high temperature and high pressure conditions.
- [0037] On the other hand, it has been found that, when the amount of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) is higher than 2.5% by weight, the pipes obtained therefrom suffer from plastic deformation under the influence of internal pressure impacts, in particular at high operating temperatures.
- [0038] The polymer (F) of the pipe of the invention preferably comprises from 1.2% to 2.5% by weight, more preferably from 1.4% to 2.2% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) as defined above.
- [0039] The polymer (F) of the pipe of the invention preferably comprises from 1.2% to 2.5% by weight, more preferably from 1.4% to 2.2% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) as defined above, and preferably has a melt flow index comprised between 0.6 and 5.5 g/10 min, more preferably between 0.7 and 4.5 g/10 min, even more preferably between 1.2 and 3.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.
- [0040] The polymer (F) of the pipe of the invention preferably comprises from


1.2% to 2.5% by weight, more preferably from 1.4% to 2.2% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (II) as defined above, and preferably has a melt flow index comprised between 0.6 and 5.5 g/10 min, more preferably between 0.7 and 4.5 g/10 min, even more preferably between 1.2 and 3.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.

- [0041] Good results have been obtained using a polymer (F) comprising from 1.2% to 2.5% by weight, preferably from 1.4% to 2.2% by weight of recurring units derived from perfluoropropylvinylether (PPVE), and having a melt flow index comprised between 0.6 and 5.5 g/10 min, more preferably between 0.7 and 4.5 g/10 min, even more preferably between 1.2 and 3.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.
- [0042] The polymer (F) of the pipe of the invention may further comprise recurring units derived from one or more fluorinated comonomers (F) different from the perfluorinated alkyl vinyl ether having formula (I) as defined above.
- [0043] By the term “fluorinated comonomer (F)”, it is hereby intended to denote an ethylenically unsaturated comonomer comprising at least one fluorine atoms.
- [0044] Non-limitative examples of suitable fluorinated comonomers (F) include, notably, the followings:
- (a) C₂-C₈ fluoro- and/or perfluoroolefins such as tetrafluoroethylene (TFE), hexafluoropropylene (HFP), pentafluoropropylene and hexafluoroisobutylene;
 - (b) C₂-C₈ hydrogenated monofluoroolefins, such as vinylidene fluoride (VDF), vinyl fluoride; 1,2-difluoroethylene and trifluoroethylene;
 - (c) perfluoroalkylethylenes of formula CH₂=CH-R_{f0}, wherein R_{f0} is a C₁-C₆ perfluoroalkyl group;
 - (d) chloro- and/or bromo- and/or iodo-C₂-C₆ fluoroolefins such as chlorotrifluoroethylene (CTFE);
 - (e) (per)fluoroalkylvinylethers of formula CF₂=CFOR_{f1}, wherein R_{f1} is a C₁-C₂ fluoro- or perfluoroalkyl group, e.g. -CF₃, -C₂F₅;
 - (f) (per)fluoro-oxyalkylvinylethers of formula CF₂=CFOX₀, wherein X₀ is a

C₁-C₁₂ oxyalkyl group or a C₁-C₁₂ (per)fluorooxyalkyl group having one or more ether groups, e.g. perfluoro-2-propoxy-propyl group;

(g) fluoroalkyl-methoxy-vinylethers of formula CF₂=CFOCF₂OR_{f2}, wherein R_{f2} is a C₁-C₆ fluoro- or perfluoroalkyl group, e.g. -CF₃, -C₂F₅, -C₃F₇ or a C₁-C₆ (per)fluorooxyalkyl group having one or more ether groups, e.g. -C₂F₅-O-CF₃;

(h) fluorodioxoles of formula :



wherein each of R_{f3}, R_{f4}, R_{f5} and R_{f6}, equal to or different from each other, is independently a fluorine atom, a C₁-C₆ fluoro- or per(halo)fluoroalkyl group, optionally comprising one or more oxygen atoms, e.g. -CF₃, -C₂F₅, -C₃F₇, -OCF₃, -OCF₂CF₂OCF₃.

[0045] Should one or more fluorinated comonomers (F) be present, the polymer (F) of the pipe of the invention comprises typically from 0.8% to 2.5% by weight of recurring units derived from said fluorinated comonomer (F).

[0046] Nevertheless, embodiments wherein the polymer (F) is free from said additional comonomers (F) are preferred.

[0047] The polymer (F) of the pipe of these preferred embodiments advantageously consists essentially of:

- from 1.2% to 2.5% by weight, more preferably from 1.4% to 2.2% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) as defined above, and
- from 97.5% to 98.8% by weight, more preferably from 97.8% to 98.6% by weight of recurring units derived from TFE, said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.

[0048] It is understood that chain ends, defects or other impurity-type moieties might be comprised in the polymer (F) without these impairing its

properties.

- [0049] The polymer (F) of the pipe of these preferred embodiments preferably consists essentially of:
- from 1.2% to 2.5% by weight, more preferably from 1.4% to 2.2% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) as defined above, and
 - from 97.5% to 98.8% by weight, more preferably from 97.8% to 98.6% by weight of recurring units derived from TFE;
- and preferably has a melt flow index comprised between 0.6 and 5.5 g/10 min, more preferably between 0.7 and 4.5 g/10 min, even more preferably between 1.2 and 3.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.
- [0050] The polymer (F) of the pipe of these preferred embodiments more preferably consists essentially of:
- from 1.2% to 2.5% by weight, more preferably from 1.4% to 2.2% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (II) as defined above, and
 - from 97.5% to 98.8% by weight, more preferably from 97.8% to 98.6% by weight of recurring units derived from TFE;
- and preferably has a melt flow index comprised between 0.6 and 5.5 g/10 min, more preferably between 0.7 and 4.5 g/10 min, even more preferably between 1.2 and 3.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.
- [0051] Excellent results have been obtained using a polymer (F) consisting essentially of:
- from 1.2% to 2.5% by weight, preferably from 1.4% to 2.2% by weight of recurring units derived from perfluoropropylvinylether (PPVE), and
 - from 97.5% to 98.8% by weight, preferably from 97.8% to 98.6% by weight of recurring units derived from TFE;
- and having a melt flow index comprised between 0.6 and 5.5 g/10 min, more preferably between 0.7 and 4.5 g/10 min, even more preferably between 1.2 and 3.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.

- [0052] The polymer (F) of the pipe of the invention is advantageously thermoplastic.
- [0053] By the term "thermoplastic", it is hereby intended to denote a polymer (F) existing, at room temperature (25°C), below its melting point if it is semi-crystalline or below its T_g if it is amorphous. These polymers have the property of becoming soft when they are heated and of becoming rigid again when they are cooled, without there being an appreciable chemical change. Such a definition may be found, for example, in the encyclopedia called "Polymer Science Dictionary", Mark S.M. Alger, London School of Polymer Technology, Polytechnic of North London, UK, published by Elsevier Applied Science, 1989.
- [0054] The polymer (F) of the pipe of the invention is preferably semi-crystalline.
- [0055] By the term "semi-crystalline", it is hereby intended to denote a polymer having a heat of fusion of more than 1 J/g when measured by Differential Scanning Calorimetry (DSC) at a heating rate of 10°C/min, according to ASTM D 3418.
- [0056] The polymer (F) of the pipe of the invention advantageously has a melting point comprised between 311°C and 321°C, preferably between 311°C and 318°C.
- [0057] Very good results have been obtained using a polymer (F) having a melting point comprised between 312°C and 317°C.
- [0058] Most preferred polymers (F) of the pipe of the invention comprises from 1.2% to 2.5% by weight of recurring units derived from at least one perfluoro-rinated alkyl vinyl ether having formula (II) and have:
- a melt flow index comprised between 0.6 and 5.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg, and
 - a melting point comprised between 311°C and 318°C.
- [0059] Even more preferred polymers (F) of the pipe of the invention are those consisting essentially of:
- from 1.2% to 2.5% by weight of recurring units derived from at least one perfluoro-rinated alkyl vinyl ether having formula (II) as defined above, and
 - from 97.5% to 98.8% by weight of recurring units derived from TFE;
- and having:

- a melt flow index comprised between 0.6 and 5.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg, and
- a melting point comprised between 311°C and 318°C.

- [0060] The pipe of the present invention is typically manufactured by well known melt-processing techniques such as melt extrusion.
- [0061] The Applicant has surprisingly found that, due to the advantageous inherent mechanical properties of the polymer (F), the pipe of the present invention successfully withstands temperatures up to 280°C, preferably up to 300°C.
- [0062] The Application has also found that the pipe of the invention has advantageously a smooth inner surface.
- [0063] According to a first embodiment of the invention, the multilayer pipe is a flexible riser.
- [0064] By the term “flexible riser”, it is hereby intended to denote a flexible tubular pipe wherein the constituent layers comprise polymeric sheaths for providing a sealing function and reinforcing layers intended to take up the mechanical forces and which are formed by windings of metal wires or strips or various tapes or sections made of composites.
- [0065] The flexible riser of the invention may be an unbonded flexible riser or a bonded flexible riser.
- [0066] By the term “bonded flexible riser”, it is hereby intended to denote a flexible riser wherein two or more concentric layers are adhered to each other.
- [0067] By the term “unbonded flexible riser”, it is hereby intended to denote a flexible riser comprising two or more superposed concentric layers, wherein these layers have a certain freedom to move relative to one another.
- [0068] Should the pipe of the invention be a flexible riser, it is preferably a bonded flexible riser.
- [0069] According to a first variant of this first embodiment of the invention, the flexible riser is a rough-bore flexible riser.
- [0070] By the term “rough-bore flexible riser”, it is intended to denote a flexible riser wherein the innermost element is an internal carcass which forms a

rough bore owing to gaps between the turns of the carcass that allow it to flex.

[0071] The rough-bore flexible riser of this first variant of this embodiment of the invention typically comprises, from the interior towards the exterior:

- an internal flexible metal tube, called the internal carcass, formed by a helically wound profiled member with the turns clipped together,
- an internal polymeric sheath at least comprising, preferably consisting essentially of (or being made of), a polymer (F) as defined above,
- one or more armor plies wound around the internal polymeric sheath, and
- an external polymeric sheath.

[0072] The internal polymeric sheath is typically coated over the internal carcass of the rough-bore flexible riser so that a continuous tubular layer at least comprising, preferably consisting essentially of (or being made of), a polymer (F) as defined above is obtained.

[0073] The internal polymeric sheath is preferably extruded over the internal carcass of the rough-bore flexible riser by conventional melt-processing techniques.

[0074] According to a second variant of this first embodiment of the invention, the flexible riser is a smooth-bore flexible riser.

[0075] By the term "smooth-bore flexible riser", it is hereby intended to denote a flexible riser which is free from an internal carcass, wherein the innermost element is a smooth-walled impermeable polymeric tube.

[0076] According to a second embodiment of the invention, the pipe of the invention is a pipe liner suitable for use in a process for lining a metal pipeline.

[0077] The present invention thus also pertains to a process for lining a metal pipeline, said process comprising the following steps:

- (i) providing a pipe according to the invention having an outer diameter greater than the inner diameter of a metal pipeline;
- (ii) deforming said pipe thereby providing a deformed pipe having an outer diameter smaller than the inner diameter of said metal pipeline;
- (iii) introducing the deformed pipe in said metal pipeline; and

(iv) expanding the deformed pipe so as to fit with the inner diameter of said metal pipeline.

[0078] The metal pipeline is usually an iron or steel pipeline, preferably a steel pipeline, more preferably a carbon, alloy or stainless steel pipeline.


[0079] According to a variant of this second embodiment of the invention, the metal pipeline may be an existing damaged metal pipeline. Should the metal pipeline be an existing damaged metal pipeline, the lining process of the invention is a lining rehabilitation process.

[0080] The Applicant has found that the pipe of the present invention is advantageously endowed with outstanding resistance to plastic deformation to be suitably used as pipe liner in a process for the lining of a metal pipeline wherein the expansion of the deformed pipe liner may be successfully obtained by recovery of its elastic deformation.

[0081] The process for lining a metal pipeline preferably comprises the following steps:

- (i) providing a pipe according to the invention having an outer diameter greater than the inner diameter of a metal pipeline,
- (ii) deforming said pipe thereby providing a deformed pipe having an outer diameter smaller than the inner diameter of said metal pipeline,
- (iii) introducing the deformed pipe in said metal pipeline, and
- (iv) expanding the deformed pipe so as to fit with the inner diameter of said metal pipeline,

wherein said pipe comprises at least one layer made of a tetrafluoroethylene (TFE) copolymer [polymer (F)] consisting essentially of:
- from 1.2% to 2.5% by weight, preferably from 1.4% to 2.2% by weight of recurring units derived from at least one per-fluorinated alkyl vinyl ether having formula (I) here below:



wherein R_f is a linear or branched C_3 - C_5 perfluorinated alkyl group or a linear or branched C_3 - C_{12} perfluorinated oxyalkyl group comprising one or more ether oxygen atoms, and

- from 97.5% to 98.8% by weight, more preferably 97.8% to 98.6% by weight of recurring units derived from TFE,

said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.

[0082] The pipe of the process for lining a metal pipeline is defined as above.

[0083] Pipes suitable for use in this process for lining a metal pipeline may be monolayer pipes or multilayer pipes as defined above.

[0084] For the purpose of the present invention, an elastic deformation is distinguished from a plastic deformation. By the term "elastic deformation" it is hereby intended to denote temporary and reversible deformation of the polymer (F).

[0085] Should the stress applied to the polymer (F) under step (ii) of the process for lining a metal pipeline be lower than the yield strength of said polymer (F), the deformed pipe can be advantageously expanded under step (iii) of said process by recovery of its elastic deformation.

[0086] In step (ii) of the process for lining a metal pipeline, the pipe is preferably deformed by reducing its cross-sectional area by means of radial or axial compression.

[0087] According to one type of technique, the so-called Roll Down process, the cross-sectional area of the pipe is reduced by means of radial compression typically using sets of compression rollers.

[0088] According to another type of technique, the cross-sectional area of the pipe is reduced by means of axial compression typically pulling the pipe liner through a diameter reducing die. The diameter reduction is only achieved so long as the axial tension on the pipe is maintained. The compressive strains involved are typically of about 10% to 15%. Non-limitative examples of this type of process are the techniques known as Swagelining, Die-drawing and Titeliner.

[0089] In step (iii) of the process for lining a metal pipeline, the deformed pipe is expanded to fit with the inner diameter of the pipeline typically by elastic recovery. The deformed pipe may be also expanded by heat and/or pressurisation with oils and gases.

[0090] It is also an object of the present invention a pipeline system comprising at least two coaxial pipes:

- an outer metal pipeline, and
- an inner pipe according to the invention.

[0091] The pipeline system preferably comprises two coaxial pipes, wherein the outer diameter of the inner pipe fits with the inner diameter of the metal pipeline.

[0092] The pipe of the pipeline system is defined as above.

[0093] The metal pipeline is usually an iron or steel pipe, preferably a steel pipe, more preferably a carbon, alloy or stainless steel pipeline.

[0094] Another object of the present invention is use of the pipe of the invention in heat exchangers.

[0095] Also, another object of the present invention is use of the pipe of the invention in downhole operations.

[0096] Further, another object of the present invention is use of the pipe of the invention in drilling operations.

[0097] The rough-bore flexible riser of the present invention is particularly suitable for use in downhole operations such as drilling operations where the internal carcass prevents the pipe from failing under the effect of pressure impacts.

[0098] The Applicant has surprisingly found that the pipe of the present invention is successfully endowed with higher yield stress values and lower creep strain values so that it can be advantageously used in a wide variety of applications where the pipe has to withstand high pressure and high temperature conditions, while being chemical resistant in harsh environments.

[0099] Should the disclosure of any patents, patent applications, and publications which are incorporated herein by reference conflict with the description of the present application to the extent that it may render a term unclear, the present description shall take precedence.

[0100] The invention will be now described with reference to the following examples whose purpose is merely illustrative and not limitative of the present invention.

[0101] **Measurement of the melt flow index (MFI)**

The determination of the MFI was carried out according to the ASTM

D1238 standard test method at 372°C under a load of 5 Kg.

[0102] Measurement of the second melting temperature (T(II) melting point)

The second melting temperature was determined according to the ASTM D4591 standard test method. The melting point observed at the second heating period was recorded and is hereby referred to as the melting point of the polymer.

[0103] Measurement of the percentage by weight of the perfluorinated alkyl vinyl ether (I) in the polymer

The determination of the perfluorinated alkyl vinyl ether monomer (I) was carried out by FT-IR analysis and expressed as per cent by weight.

The perfluorinated alkyl vinyl ether monomer (I) content was determined under the following conditions: the band optical density (OD) at 994 cm⁻¹ was normalized with the band optical density (OD) at 2365 cm⁻¹ by means of the following formula:

$$\text{Monomer (I) [\% by weight]} = (\text{OD at } 994 \text{ cm}^{-1}) / (\text{OD at } 2365 \text{ cm}^{-1}) \times 0.99$$

[0104] Measurement of the tensile properties

[0105] Tensile tests on polymers (F) according to Examples 1 to 3 of the invention and comparative Examples 1 and 2 were performed by an Instron 4203 machine using microtensile specimens as reported in ASTM D3307 standard test method; specimens were cut by hollow punch from compression molded sheets having a thickness of 1.5 mm and were stretched at a speed equal to 50 mm/min after 15 minutes of conditioning time at the required temperature.

Yield stress was evaluated as nominal stress at first zero slope point on the stress-strain curve.

[0106] Tensile tests on pipes made of polymers (F) according to Example 4 or 5 of the invention were performed according to ASTM D638 standard procedure using specimens of type IV having a thickness of 7 mm at a grip distance of 65 mm and a gauge length of 12.5 mm. Modulus values have been measured at a cross-head speed of 1 mm/min, whereas strain at break and stress at yield values have been measured at a cross-head speed of 50 mm/min.

Yield stress was evaluated as nominal stress at first zero slope point on

the stress-strain curve. Rupture is the point where a sharp load drop occurs and specimens break.

[0107] The higher is the yield stress value, the higher is the resistance to plastic deformation of the polymer.

[0108] Tensile creep tests on polymers (F) according to Examples 1 to 3 of the invention and comparative Examples 1 and 2 were performed according to ASTM D2990 standard test method but using specimen dimensions described in ISO 527-1A; no extensometers were used, but specimen shape correction was employed in order to get good strain evaluation. Specimens were cut by hollow punch from compression molded sheets having a thickness of 1.5 mm.

[0109] Tensile creep tests on polymers (F) according to Example 4 or 5 were performed according to ASTM D2990 standard test method but using specimen dimensions described in ISO 527-1A; no extensometers were used, but specimen shape correction was employed in order to get good strain evaluation. Specimens were cut by hollow punch from pipes having a thickness of 7 mm.

[0110] The lower is the creep strain value, the higher is the resistance to plastic deformation of the polymer.

[0111] **Processing of pipes**

The polymer was extruded in a 45 mm extruder equipped with a head to produce pipes having an external diameter of 12 mm and an internal diameter of 10 mm. The temperature profile on the machine was set between 280°C and 380°C. The cone at the exit of the head appeared transparent and the surface of the pipe so obtained was smooth without any defect.

[0112] **Measurement of the shrinkage**

The pipes were cut in a longitudinal direction to a length of 400 mm. After thermal treatment at 300°C for one hour, their length was re-measured at 23°C thus obtaining the percent variation.

[0113] **Measurement of rapid gas decompression**

Rapid gas decompression (RGD) tests on specimens cut from pipes made of polymers (F) according to Example 5 of the invention were performed

according to ISO 13628-2 standard procedure (API 17J).

The samples were preconditioned for 30 days in NORSOK[®] M710 oil at 185°C under vapour pressure and this was followed by 20 rapid gas decompression cycles at 185°C and 1000 bar using a mixture of 15% by moles of carbon dioxide in methane. The decompression rate was 70 bar per minute.

[0114] **Example 1: TFE/PPVE 98.2/1.8 (weight ratio)**

In an AISI 316 steel vertical 22 litres autoclave, equipped with a stirrer working at 400 rpm, after the vacuum was made, were introduced in sequence:

- 13.9 litres of demineralised water;
- 32.0 g of perfluoropropylvinylether (PPVE);
- 138.0 g of a microemulsion prepared according to Example 1 of **US 4864006** (AUSIMONT S.P.A.) 05.09.1989 having a pH of about 7.5.

The autoclave was then heated up to reaction temperature of 60°C and, when this temperature was reached, 0.60 bar of ethane were introduced. By a compressor a gaseous mixture of TFE/PPVE in nominal molar ratio of 99.2/0.8 was added until reaching a pressure of 21 bar.

The composition of the gaseous mixture present at the autoclave head (as determined by GC analysis) was formed of the following compounds in the indicated molar percentages: 95.9% TFE, 2.0% PPVE, 2.1% ethane.

Then, by a metering pump, 100 ml of a 0.035 M ammonium persulphate solution were fed.

The polymerization pressure was maintained constant by feeding the above mentioned monomeric mixture; when 8.8 g of the mixture were fed, the monomer feeding was interrupted. The reactor was cooled to room temperature, the latex was discharged and coagulated with HNO₃ (65% by weight) and the polymer was washed with H₂O and dried at about 220°C.

Determination of the obtained polymer:

Composition (IR analysis): PPVE: 1.8% by weight

MFI: 5.0 g/10 min

Second melting temperature (T(II) melting point): 314°C

[0115] Example 2: TFE/PPVE 98.6/1.4 (weight ratio)

The same procedure as detailed under Example 1 was followed but:

- 25.0 g of PPVE were fed;
- 0.50 bar of ethane were fed;
- a gaseous mixture of TFE/PPVE in nominal molar ratio of 99.4/0.6 was added.

The composition of the gaseous mixture present at the autoclave head (as determined by GC analysis) was formed of the following compounds in the indicated molar percentages: 96.90% TFE, 1.55% PPVE, 1.55% ethane.

Determinations on the obtained polymer:

Composition (IR analysis): PPVE: 1.4% by weight

MFI: 3.0 g/10 min

Second melting temperature (T(II) melting point): 317°C

[0116] Example 3: TFE/PPVE 98.6/1.4 (weight ratio)

The same procedure as detailed under Example 1 was followed but:

- 25.0 g of PPVE were fed;
- 0.40 bar of ethane were fed;
- a gaseous mixture of TFE/PPVE in nominal molar ratio of 99.4/0.6 was added;
- 150 ml of a 0.035 M ammonium persulphate solution were fed.

The composition of the gaseous mixture present at the autoclave head (as determined by GC analysis) was formed of the following compounds in the indicated molar percentages: 96.2% TFE, 1.7% PPVE, 2.1% ethane.

Determinations on the obtained polymer:

Composition (IR analysis): PPVE: 1.5% by weight

MFI: 2.0 g/10 min

Second melting temperature (T(II) melting point): 316°C

[0117] As shown in Table 1 here below, reporting the results of yield strength tests at 280°C, the polymers (F) according to the invention advantageously exhibited improved yield stress values at temperatures up to 280°C as compared with commercially available products of comparative Examples 1 and 2.

Table 1

Run	PPVE [% wt.]	MFI [g/10 min]	Tm [°C]	Yield stress [MPa]
Example 1	1.8	5.0	314	3.6
Example 2	1.4	3.0	317	3.5
Example 3	1.5	2.0	316	3.5
C. Example 1	3.8	2.5	307	2.8
C. Example 2	3.3	2.5	310	3.2

[0118] As shown in Table 2 here below, reporting the results of the creep strain tests, the polymers (F) according to the invention advantageously exhibited lower creep strain values as compared with commercially available product of comparative Example 2.

Table 2

Run	PPVE [% wt.]	MFI [g/10 min]	Tm [°C]	Creep strain 280°C 1.0 MPa (1000 hours)	Creep strain 300°C 1.0 MPa (1000 hours)
Example 2	1.4	3.0	317	12.0%	-
Example 3	1.5	2.0	317	9.3%	20.0%
C. Example 2	3.3	2.5	310	17.8%	> 40%

[0119] As shown in Table 3 here below, pipes were obtained using the polymer (F) according to the present invention which advantageously were endowed with shrinkage values at 300°C comparable to those of commercially available product of comparative Example 1.

Table 3

Run	PPVE [% wt.]	MFI [g/10 min]	Tm [°C]	Shrinkage 300°C
Example 3	1.5	5.0	317	2.3%
C. Example 1	3.8	2.5	307	3.0%

[0120] It has been thus found that the pipe of the present invention comprising at least one layer at least comprising, preferably consisting essentially of (or

being made of), the polymer (F) advantageously exhibits enhanced yield strength values, both in short-term and long-term trials, in particular at high operating temperatures, so that it can successfully withstand high internal pressure levels because of its improved mechanical properties.

[0121] Example 4: TFE/PPVE 97.8/2.2 (weight ratio)

The same procedure as detained under Example 1 was followed but:

- 38 g of PPVE were fed;
- 0.51 bar of ethane were fed; and
- a gaseous mixture of TFE/PPVE in nominal molar ratio of 98.8/1.2 was added.

The composition of the gaseous mixture present at the autoclave head (as determined by GC analysis) was formed of the following compounds in the indicated molar percentages: 93.0% TFE, 6.2% PPVE, 0.7% ethane.

Determinations on the obtained polymer:

Composition (IR analysis): PPVE: 2.2% by weight

MFI: 3.3 g/10 min

Second melting temperature (T(II) melting point): 311.4°C

[0122] Example 5: TFE/PPVE 97.8/2.2 (weight ratio)

The same procedure as detained under Example 1 was followed but:

- 38 g of PPVE were fed;
- 0.35 bar of ethane were fed; and
- a gaseous mixture of TFE/PPVE in nominal molar ratio of 98.8/1.2 was added.

The composition of the gaseous mixture present at the autoclave head (as determined by GC analysis) was formed of the following compounds in the indicated molar percentages: 93.5% TFE, 6.0% PPVE, 0.5% ethane.

Determinations on the obtained polymer:

Composition (IR analysis): PPVE: 2.2% by weight

MFI: 1.7 g/10 min

Second melting temperature (T(II) melting point): 311.6°C

[0123] As shown in Table 4 here below, reporting the results of tensile tests at 23°C, pipes made of the polymers (F) according to the invention as notably represented by Example 4 or 5 of the invention advantageously

exhibited a combination of mechanical properties such that said pipes can be suitably used in a process for lining a metal pipeline.

Table 4

Run	Modulus [MPa]	Yield Stress [MPa]	Stress at Break [MPa]	Strain at Break [MPa]
Example 4	424	13.3	29.6	311
Example 5	443	13.4	30.2	320

[0124] As shown in Table 5 here below, reporting the results of the creep strain tests, pipes made of the polymer (F) according to the invention as notably represented by Example 4 of the invention advantageously exhibited relatively low creep strain values without undergoing yielding failure under relatively high stress of 3.0 MPa and 4.0 MPa to be suitably used in a process for lining a metal pipeline.

Table 5

Run	PPVE [% wt.]	MFI [g/10 min]	Tm [°C]	Creep strain 200°C 3.0 MPa (1000 hours)	Creep strain 200°C 4.0 MPa (1000 hours)
Example 4	2.2	3.3	311	14.4%	33.8%

[0125] As shown in Table 6 here below, reporting the results of the rapid gas decompression (RGD) tests, pipes made of the polymer (F) according to the invention as notably represented by Example 5 advantageously exhibited no visible cracks to be suitably used in a process for lining a metal pipeline in downhole applications without undergoing decompression under the effect of pressure impacts.

Table 6

Run	Visible RGD damages
Example 5	After 20 RGD cycles: no visible cracks

[0126] The pipe of the present invention is thus particularly suitable for use in

operations where high thermal resistance at high operating temperatures is required.

Claims

1. A pipe comprising at least one layer made of a tetrafluoroethylene (TFE) copolymer consisting essentially of:
 - from 1.2% to 2.5% by weight, preferably from 1.4% to 2.2% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I) here below:
$$\text{CF}_2=\text{CF}-\text{O}-\text{R}_f \text{ (I)}$$
wherein R_f is a linear or branched C_3 - C_5 perfluorinated alkyl group or a linear or branched C_3 - C_{12} perfluorinated oxyalkyl group comprising one or more ether oxygen atoms, and
 - from 97.5% to 98.8% by weight, more preferably 97.8% to 98.6% by weight of recurring units derived from TFE,said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg, and a melting point comprised between 311°C and 321°C, preferably between 311°C and 318°C [polymer (F)].
2. The pipe according to claim 1, wherein the polymer (F) has a melt flow index comprised between 0.6 and 5.5 g/10 min, more preferably between 0.7 and 4.5 g/10 min, even more preferably between 1.2 and 3.5 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.
3. The pipe according to claim 1 or 2, wherein the per-fluor-inated alkyl vinyl ether complies with formula (II) here below:
$$\text{CF}_2=\text{CF}-\text{O}-\text{R}'_f \text{ (II)}$$
wherein R'_f is a linear or branched C_3 - C_5 perfluorinated alkyl group.
4. The pipe according to any one of claims 1 to 3, wherein the perfluorinated alkyl vinyl ether is perfluoropropyl vinyl ether (PPVE).
5. The pipe according to any one of claims 1 to 4, said pipe being a monolayer pipe or a multilayer pipe.
6. The pipe according to any one of claims 1 to 5, said pipe being a flexible riser.
7. The pipe according to claim 6, the pipe being a bonded flexible riser.
8. The pipe according to claim 6 or 7, the pipe being a rough-bore flexible riser.
9. The pipe according to claim 6 or 7, the pipe being a smooth-bore flexible riser.
10. A process for lining a metal pipeline, said process comprising the following

steps:

(i) providing a pipe comprising at least one layer at least comprising, preferably consisting essentially of (or being made of), a tetrafluoroethylene (TFE) copolymer [polymer (F)] comprising from 0.8% to 2.5% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I),

said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg,

said pipe having an outer diameter greater than the inner diameter of a metal pipeline;

(ii) deforming said pipe thereby providing a deformed pipe having an outer diameter smaller than the inner diameter of said metal pipeline;

(iii) introducing the deformed pipe liner in said metal pipeline; and

(iv) expanding the deformed pipe liner so as to fit with the inner diameter of said metal pipeline.

11. The process according to claim 10, wherein the pipe is according to any one of claims 1 to 5.

12. A pipeline system comprising at least two coaxial pipes:

- an outer metal pipeline, and

- an inner pipe comprising at least one layer at least comprising, preferably consisting essentially of (or being made of), a tetrafluoroethylene (TFE) copolymer [polymer (F)] comprising from 0.8% to 2.5% by weight of recurring units derived from at least one per-fluor-inated alkyl vinyl ether having formula (I),

said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.

13. Use of the pipe according to any one of claims 1 to 9 in heat exchangers.

14. Use of the pipe according to any one of claims 1 to 9 in downhole operations.

15. Use of the pipe according to any one of claims 1 to 9 in drilling operations.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2013/056237

A. CLASSIFICATION OF SUBJECT MATTER

INV. B32B1/08 B32B27/30 C08F214/26 F16L53/00 F16L9/00
F16L9/147 F16L55/165

ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B32B C08F F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2003/069343 A1 (SMITH PAUL [CH] ET AL) 10 April 2003 (2003-04-10) paragraphs [0001] - [0065]; claims 1-28 -----	1-12
A	US 6 774 196 B1 (TAIRA TAKAHIRO [JP] ET AL) 10 August 2004 (2004-08-10) column 1, line 1 - column 13, line 50; claims 1-12 -----	1-15
X	DE 600 21 118 T2 (3M INNOVATIVE PROPERTIES CO) 11 May 2006 (2006-05-11)	13
A	paragraphs [0001] - [0053]; claims 1-13 -----	1-12, 14, 15
X	US 2007/141285 A1 (LAHIJANI JACOB [US]) 21 June 2007 (2007-06-21) paragraphs [0001] - [0081]; claims 1-17 -----	10-12, 14, 15
	-/--	

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

11 September 2013

Date of mailing of the international search report

18/09/2013

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Ansorge, Markus

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2013/056237

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2005/229992 A1 (MCKEEN LAURENCE W [US] ET AL) 20 October 2005 (2005-10-20) paragraphs [0001] - [0099]; claims 1-28 -----	10-12, 14,15
X	US 2007/095473 A1 (FARNSWORTH KIMBERLY D [US] ET AL) 3 May 2007 (2007-05-03) paragraphs [0001] - [0087]; claims 1-22 -----	10-12, 14,15
X	WO 2012/019070 A1 (DU PONT [US]; LAHIJANI JACOB [US]) 9 February 2012 (2012-02-09) page 1, line 1 - page 37, last line; claims 1-15 -----	10-13
A,P	WO 2012/163858 A1 (SOLVAY SPECIALTY POLYMERS IT [IT]; MESSINA NICASIO [IT]; MIRENDA MARCO) 6 December 2012 (2012-12-06) claims 1-11 -----	1-15

INTERNATIONAL SEARCH REPORT

International application No.
PCT/EP2013/056237

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of Item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of additional fees.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. claims: 1-9, 11, 13-15

A pipe comprising at least one layer made of a tetrafluoroethylene (TFE) copolymer consisting essentially of from 1.2% to 2.5% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I), wherein Rf is a linear or branched C3 -C5 perfluorinated alkyl group or a linear or branched C3 -C12 perfluorinated oxyalkyl group comprising one or more ether oxygen atoms, and from 97.5% to 98.8% by weight of recurring units derived from TFE, said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg, and a melting point comprised between 311°C and 321 °C [polymer (F)].

2. claims: 10, 12

A process for lining a metal pipeline, said process comprising the following steps: (i) providing a pipe comprising at least one layer at least comprising a tetrafluoroethylene (TFE) copolymer [polymer (F)] comprising from 0.8% to 2.5% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I), said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg, said pipe having an outer diameter greater than the inner diameter of a metal pipeline; (ii) deforming said pipe thereby providing a deformed pipe having an outer diameter smaller than the inner diameter of said metal pipeline; (iii) introducing the deformed pipe liner in said metal pipeline; and (iv) expanding the deformed pipe liner so as to fit with the inner diameter of said metal pipeline; and a pipeline system comprising at least two coaxial pipes: an outer metal pipeline, and an inner pipe comprising at least one layer at least comprising a tetrafluoroethylene (TFE) copolymer [polymer (F)] comprising from 0.8% to 2.5% by weight of recurring units derived from at least one perfluorinated alkyl vinyl ether having formula (I), said TFE copolymer having a melt flow index comprised between 0.5 and 6.0 g/10 min, as measured according to ASTM D1238 at 372°C under a load of 5 Kg.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2013/056237

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2003069343	A1	10-04-2003	AU 2003223060 A1 29-09-2003 US 2003069343 A1 10-04-2003 WO 03078481 A1 25-09-2003
US 6774196	B1	10-08-2004	JP 4599640 B2 15-12-2010 JP 2001151825 A 05-06-2001 US 6774196 B1 10-08-2004 WO 0140331 A1 07-06-2001
DE 60021118	T2	11-05-2006	DE 60021118 D1 04-08-2005 DE 60021118 T2 11-05-2006
US 2007141285	A1	21-06-2007	BR PI0621105 A2 29-11-2011 CA 2628919 A1 05-07-2007 CN 101341017 A 07-01-2009 EA 200870092 A1 30-12-2009 EP 1963076 A1 03-09-2008 US 2007141285 A1 21-06-2007 US 2011232842 A1 29-09-2011 US 2012000563 A1 05-01-2012 US 2012003414 A1 05-01-2012 US 2012291942 A1 22-11-2012 WO 2007075820 A1 05-07-2007
US 2005229992	A1	20-10-2005	BR PI0508806 A 07-08-2007 CA 2560732 A1 27-10-2005 CN 1938149 A 28-03-2007 EA 200601873 A1 27-02-2007 EA 200900035 A1 28-04-2009 EP 1737649 A2 03-01-2007 US 2005229992 A1 20-10-2005 US 2010043885 A1 25-02-2010 US 2010043905 A1 25-02-2010 US 2012241086 A1 27-09-2012 WO 2005100843 A2 27-10-2005
US 2007095473	A1	03-05-2007	BR PI0619340 A2 27-09-2011 CA 2621118 A1 03-05-2007 CN 101305237 A 12-11-2008 EA 200801179 A1 29-08-2008 EP 1945992 A1 23-07-2008 US 2007095473 A1 03-05-2007 WO 2007050664 A1 03-05-2007 WO 2007050948 A2 03-05-2007
WO 2012019070	A1	09-02-2012	CA 2806922 A1 09-02-2012 CN 103068910 A 24-04-2013 EP 2601263 A1 12-06-2013 TW 201211075 A 16-03-2012 WO 2012019070 A1 09-02-2012
WO 2012163858	A1	06-12-2012	NONE