

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
3 May 2007 (03.05.2007)

PCT

(10) International Publication Number
WO 2007/050409 A1

(51) International Patent Classification:
C09K 3/14 (2006.01)

GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:
PCT/US2006/040803

(22) International Filing Date: 20 October 2006 (20.10.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/256,736 24 October 2005 (24.10.2005) US

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant: 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3m Center, Post Office Box 33427, Saint Paul, Minnesota, Minnesota 55133-3427 (US).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

(72) Inventor: KOLLOGE, Jeffrey S.;, 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(74) Agents: BAKER, James A. et al.; 3M Center, Office Of Intellectual Property Counsel Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,

WO 2007/050409 A1

(54) Title: POLISHING FLUIDS AND METHODS FOR CMP

(57) Abstract: Provided are several polishing compositions useful for modifying a surface, such as a semiconductor wafer suitable for fabrication of a semiconductor device, especially when used in fixed abrasive planarization techniques. The polishing compositions include a synergistic mixture of water, an oxidizing agent, a complexing agent, and metal ions. Also provided are various methods of surface planarization.

POLISHING FLUIDS AND METHODS FOR CMP

Technical Field

This invention relates generally to a method of modifying exposed surfaces of semiconductor wafers and particularly to a method of modifying exposed surfaces of 5 structured semiconductor wafers using an abrasive article, as well as solutions useful in polishing semiconductor wafers.

Background

During integrated circuit manufacture, semiconductor wafers used in semiconductor fabrication typically undergo numerous processing steps, including 10 deposition, patterning, and etching steps. Details of these manufacturing steps for semiconductor wafers are reported by Tonshoff, et al., "Abrasive Machining of Silicon", published in the Annals of the International Institution for Production Engineering Research, (Vol. 39/2/1990), pp. 621-635. In each manufacturing step, it is often necessary or desirable to modify or refine an exposed surface of the wafer in order 15 to prepare the wafer for subsequent fabrication or manufacturing steps.

For example, after a deposition step, the deposited material or layer on a wafer surface generally needs further processing before additional deposition or subsequent processing occurs. In another example, after an etching step, there is often a need to deposit either, or both, conducting or insulating materials in layers on the etched surface 20 areas of a wafer. A specific example of this process is used in metal Damascene processes.

In the Damascene process, a pattern is etched into an oxide dielectric layer. After etching, optional adhesion/barrier layers are deposited over the entire surface and then a metal is deposited over or on top of the adhesion/barrier layers. The deposited 25 metal layer is then modified, refined or finished by removing the deposited metal and regions of the adhesion/barrier layer on the surface. Typically, enough surface metal is removed so that the outer exposed surface of the wafer comprises both metal and an oxide dielectric material. A top view of the exposed wafer surface should reveal a planar surface with metal corresponding to the etched pattern and dielectric material 30 adjacent to the metal. The metal(s) and oxide dielectric material(s) located on the

modified surface of the wafer inherently have different physical characteristics, such as different hardness values. An abrasive article used to modify a wafer produced by the Damascene process must be carefully designed so as to simultaneously modify the materials without scratching the surface of either material. Further, the abrasive article 5 must be able to create a planar outer exposed surface on a wafer having an exposed area of a metal and an exposed area of a dielectric material.

Such a process of modifying the deposited metal layer until the oxide dielectric material is exposed on the wafer outer surface leaves little margin for error because of the submicron dimensions of the metal features located on the wafer surface. It is clear 10 that the removal rate of the deposited metal must be fast to minimize manufacturing costs. Further, metal removal from areas which were not etched must be complete. Still further, metal remaining in etched areas must be limited to discrete areas or zones, and the remaining metal must be continuous within an area or zone to ensure proper 15 conductivity. In short, the metal modification process must be uniform, controlled, and reproducible on a submicron scale.

One conventional method of modifying or refining exposed surfaces of wafers employs methods that treat a wafer surface with a slurry containing a plurality of loose abrasive particles dispersed in a liquid. Typically this slurry is applied to a polishing pad and the wafer surface is then ground or moved against the pad in order to remove or 20 take off material on the wafer surface. Generally, the slurry also contains agents which chemically react with the wafer surface. This type of process is commonly referred to as a chemical-mechanical planarization or polishing (CMP) process.

One problem with CMP slurries, however, is that the process must be carefully monitored in order to achieve a desired wafer surface topography. Another problem is 25 the mess associated with loose abrasive slurries. Another problem is that the slurries generate a large number of particles that must be removed from the surface of the wafer and disposed of following wafer treatment. Handling and disposal of these slurries involves additional processing costs for the semiconductor wafer fabricator.

Summary of the Invention

The present invention exploits the advantages afforded by use of abrasive articles to modify surfaces of semiconductor wafers to expose at least two different materials on the surface of a wafer. These materials typically have different hardness values and different abrading properties.

The present invention involves a recent alternative to CMP slurry methods and uses an abrasive article to modify or refine a semiconductor surface. This alternative CMP process is reported in U.S. Patent Nos. 5,958,794 and 6,194,317. The useful abrasive article has a textured abrasive surface that includes abrasive particles dispersed in a binder. In use, the abrasive article is contacted with a semiconductor wafer surface, often in the presence of a fluid or liquid, with a motion adapted to modify an exposed surface region of material on the wafer and provide a planar, uniform wafer surface. Using these fixed abrasive articles overcomes a significant number of problems associated with CMP slurries.

Briefly, the present invention provides a fixed abrasive chemical mechanical polishing or planarization composition useful for modifying a surface of a wafer, the composition comprising a synergistic mixture of water, an oxidizing agent, a complexing agent, and metal ions. When a majority of the complexing agent is selected from a simple monofunctional or simple difunctional acid or salt thereof, the mole ratio of complexing agent to metal ions present in the liquid is at least 3 to 1. The mixture also is substantially free of abrasive particles.

In another embodiment, the present invention provides a chemical mechanical polishing system comprising a fixed abrasive pad and a polishing composition useful for modifying a surface of a wafer, the composition comprising a synergistic mixture of water, an oxidizing agent, a complexing agent, and metal ions. When a majority of the complexing agent is a simple monofunctional or simple difunctional acid or salt thereof, the mole ratio of complexing agent to metal ions present in the liquid is at least 3 to 1. In addition, the mixture is substantially free of abrasive particles.

In one embodiment of this invention, a method of modifying a wafer may begin with a layer comprised of conductive material deployed over at least one dielectric material. The dielectric material typically has a surface etched to form a design, i.e., a

patterned surface. Such a wafer may be modified by contacting and relatively moving the exposed major surface of the wafer (e.g., exposed conductive material) with respect to the abrasive article. The abrasive article typically comprises an exposed major surface of a plurality of textured, three-dimensional abrasive composites comprising a plurality of abrasive particles fixed and dispersed in a binder. This contact and motion typically is maintained between the plurality of abrasive composites of the abrasive article and the conductive material until an exposed surface of the wafer is substantially planar and the surface comprises at least one area of exposed conductive material and at least one area of exposed dielectric material, and the exposed surfaces of conductive material and the exposed surfaces of dielectric material lies substantially in a single plane. The dielectric material may be covered by one or more intermediate materials such as an adhesion/barrier layer. Typically, the exposed dielectric material surface is essentially free of the intermediate material after removal of the conductive material. Alternatively, removal of the conductive material may expose only the surface of the intermediate material and the conductive material. Continued modification may then expose on the surface of the wafer the dielectric material and the conductive material, when desired.

The present method is particularly suitable for modifying conductive surfaces, often referred to as the second material in this document. The conductive surfaces may be made from a variety of conductive materials generally having resistivity values of less than about 0.1 ohm-cm. Presently preferred conductive materials include metals such as tungsten, copper, aluminum, aluminum copper alloy, gold, silver, titanium, titanium nitride, ruthenium or various alloys of these metals. Preferred dielectric materials generally have dielectric constants less than about 5.

In another aspect, the present invention provides methods of modifying a surface of a semiconductor wafer suited for fabrication of a semiconductor device. A method of the invention comprises providing a wafer comprising at least a first material having a surface etched to form a pattern and at least a second material deployed over the surface of the first material, contacting the second material of the wafer to a plurality of three-dimensional abrasive composites fixed to an abrasive article in the presence of a working liquid as described herein, wherein the abrasive composites

comprise a plurality of abrasive particles fixedly dispersed in a binder, and relatively moving the wafer while the second material is in contact with the plurality of abrasive composites until an exposed surface of the wafer is substantially planar and comprises at least one area of exposed first material and one area of exposed second material.

5 Another method of the invention comprises providing a wafer comprising at least one dielectric material having a surface etched to form a pattern and at least one conductive material deployed over the surface of the at least one dielectric material, contacting the conductive material of the wafer to a plurality of three-dimensional abrasive composites fixed to an abrasive article in the presence of a working liquid as
10 described herein, wherein the plurality of abrasive composites comprise a plurality of abrasive particles, fixed and dispersed in a binder, and relatively moving the wafer while the conductive material is in contact with the plurality of abrasive composites until the exposed surface of the wafer is substantially planar and comprises at least one area of exposed conductive material and at least one area of exposed dielectric material.

15 The methods of the invention also include providing a wafer comprising at least one dielectric material having a patterned surface, the dielectric material substantially covered with at least one intermediate layer, and the intermediate layer substantially covered by at least one conductive material, contacting the conductive material of the wafer to a plurality of three-dimensional abrasive composites, which are fixed to an
20 abrasive article, in the presence of a working liquid as described herein, wherein the plurality of abrasive composites comprise a plurality of abrasive particles fixed and dispersed in a binder, and relatively moving the wafer while the conductive material is in contact with the plurality of abrasive composites until the exposed surface of the wafer comprises at least one area of exposed conductive material and at least one area
25 of exposed intermediate layer or at least one area of exposed dielectric material. The intermediate layer can be, for example, a stop layer, or a conductive layer.

With the present invention, the combination of the metal ion and the other components in the inventive polishing composition (also known as a working liquid) provides a synergistic response of an improved removal rate of the conductive metal
30 surface, allowing for the use of reduced oxidizer concentrations and low metal ion concentrations. Lower oxidizer concentration in the working liquid is preferred

because the lower levels, generally, minimize corrosion of the conductive metal surfaces during CMP processing. Lower metal ion concentrations are preferred to minimize wafer surface contamination by the metal ions. Generally, the synergistic response provides better removal rate than a subset of the components or a linear

5 interpolation of the removal rates for a subset of the components. Also, it is beneficial to include a complexing agent to the working liquid or polishing composition, to not only enhance removal rates, but also to prevent premature decomposition of the oxidizing agent (extending the pot life of the mixture). A particularly useful embodiment of this invention is combining the use of a fixed abrasive pad with an

10 essentially abrasive free polishing composition. This combination provides excellent metal surface removal rates while yielding low dishing and low erosion.

One advantage of the present invention provides a fixed abrasive CMP process with a working fluid, also called a polishing fluid, useful for tungsten CMP. Other features and advantages of the invention will be apparent from the following detailed

15 description of the invention and the claims. The above summary of principles of the disclosure is not intended to describe each illustrated embodiment or every implementation of the present disclosure. The detailed description that follows more particularly exemplifies certain preferred embodiments using the principles herein.

20

Detailed Description

All numbers are herein assumed to be modified by the term “about.” The recitation of numerical ranges by endpoints includes all numbers subsumed within that range (e.g., 1 to 5 includes 1, 1.15, 2, 2.75, 3, 3.80, 4, and 5).

It was found that CPS-11 (from 3M Company, and intended for copper

25 polishing) does not remove tungsten at acceptable removal rates under a broad range of process conditions and oxidizer concentrations. Hence, a different polishing solution was sought for fixed abrasive CMP for tungsten. The present invention provides several solutions.

In one embodiment, the present invention provides a fixed abrasive chemical

30 mechanical polishing composition useful for modifying a surface of a wafer, the composition comprising a synergistic mixture of water, an oxidizing agent, a

complexing agent, and metal ions. When a majority of the complexing agent is selected from a simple monofunctional acid, a simple difunctional acid, a salt thereof, or a combination thereof, the mole ratio of complexing agent to metal ions present in the liquid is at least 3 to 1. The mixture also is substantially free of abrasive particles.

5 The polishing fluids, or working fluids, or compositions, of the invention can be used in any known method of CMP, and are known to be particularly useful in fixed abrasive CMP. More particularly, the polishing fluids of the present invention are useful in tungsten CMP. Thus, the present invention provides methods of modifying a surface of a semiconductor wafer suited for fabrication of a semiconductor device, such 10 as fixed abrasive CMP. A method of the invention comprises providing a wafer comprising at least a first material having a surface etched to form a pattern (patterned surface) and at least a second material deployed over the surface of the first material, contacting the second material of the wafer to a plurality of three-dimensional abrasive composites fixed to an abrasive article in the presence of a working liquid as described 15 herein, wherein the abrasive composites comprise a plurality of abrasive particles fixedly dispersed in a binder, and relatively moving the wafer while the second material is in contact with the plurality of abrasive composites until an exposed surface of the wafer is substantially planar and comprises at least one area of exposed first material and one area of exposed second material.

20 Another method of the invention comprises providing a wafer comprising at least one dielectric material having a surface etched to form a pattern and at least one conductive material deployed over the surface of the at least one dielectric material, contacting the conductive material of the wafer to a plurality of three-dimensional abrasive composites fixed to an abrasive article in the presence of a working liquid as 25 described herein, wherein the plurality of abrasive composites comprise a plurality of abrasive particles, fixed and dispersed in a binder, and relatively moving the wafer while the conductive material is in contact with the plurality of abrasive composites until the exposed surface of the wafer is substantially planar and comprises at least one area of exposed conductive material and at least one area of exposed dielectric material.

30 Another method of the invention includes providing a wafer comprising at least one dielectric material having a patterned surface, the dielectric material substantially

covered with at least one intermediate layer, and the intermediate layer substantially covered by at least one conductive material, contacting the conductive material of the wafer to a plurality of three-dimensional abrasive composites fixed to an abrasive article in the presence of a working liquid as described herein, wherein the plurality of abrasive composites comprise a plurality of abrasive particles fixed and dispersed in a binder, and relatively moving the wafer while the conductive material is in contact with the plurality of abrasive composites until the exposed surface of the wafer comprises at least one area of exposed conductive material and at least one area of exposed dielectric material.

10 The methods of the present invention enable one to achieve desirable removal rates for tungsten CMP, while providing low erosion and low dishing. The invention provides substantially planar surfaces, such that the surfaces are flat with respect to the underlying structure, which may be an active region of a wafer.

When practiced, the movement between the wafer and abrasive article occurs 15 under pressure in a range of at least about 0.1 pounds per square inch (psi) (0.7 kiloPascals (kPa)), more preferably at least about 0.2 psi (1.4 kPa). The maximum pressure used is generally below about 25 psi (172 kPa), more preferably below about 15 psi (103 kPa). In one embodiment of this invention, the wafer and abrasive article are rotated and/or moved against each other. For example, the abrasive article or the 20 wafer or both the abrasive article and the wafer are rotated relative to each other as well as being moved linearly along relative centers of the wafer and abrasive article. The wafer and the abrasive article may also be moved in an elliptical or a figure eight type pattern or another desired pattern such that the speed generally varies along the path. The rotational motion or speed of rotation between the wafer and abrasive article may 25 be between 1 rpm (rotation(s) per minute) to 10,000 rpm. Preferred rotational speeds for the abrasive article are when the abrasive article rotates at a speed of at least about 10 rpm, more preferably 20 rpm. Preferred rotational speeds generally are below about 1,000 rpm, and more preferably below about 250 rpm, or even lower, such as below about 120 rpm. Preferred rotational speeds for the wafer are when the wafer rotates at a 30 speed of at least about 2 rpm, more preferably at least about 50 rpm, or even higher such as at least about 100 rpm. Preferred maximum rotational speeds for the wafer

generally are below about 1,000 rpm, more preferably below about 500 rpm, and in some embodiments below about 100 rpm. Also, two or more processing conditions within a planarization process may be used. For example, a first processing segment may comprise a higher interface pressure than a second processing segment. Rotation and translational speeds of the wafer and/or the abrasive article also may be varied during the planarization process. Other tools, such as linear motion tools, can be used with correspondingly similar relative motion.

The amount of working liquid used in the CMP process depends on the type and size of wafer being polished, concentration of compounds in the working liquid and the selected CMP polishing tool. Generally, the range of working liquid used (in mL/min) is at least about 5, at least about 50, or even higher such as at least about 80. In other embodiments, the range of working liquid used (in mL/min) is about 1000 or less, below about 400, or even lower, such as below about 250.

In one embodiment, the conductive surface of the wafer is modified by the abrasive article in the presence of a working liquid, which liquid is selected based upon the composition of the wafer surface. In some applications, the working liquid typically includes water (e.g., distilled water, or deionized water).

The working liquid aids processing in combination with the abrasive article through a chemical mechanical polishing process. During the chemical portion of polishing, the working liquid (or a component therein) may react with the outer or exposed wafer surface. Then during the mechanical portion of processing, the abrasive article may remove this reaction product. During the processing of metal surfaces, it is preferred that the working liquid is an aqueous solution which includes a chemical etchant such as an oxidizing agent. For example, chemical polishing of tungsten may occur when an oxidizing agent in the working liquid, by itself or in combination with other additives in the working liquid, reacts with the tungsten to form a surface layer of oxidized tungsten. The mechanical process occurs when the abrasive article removes this oxidized metal from the wafer surface. Alternatively, the metal may first be removed mechanically before reacting with ingredients in the working fluid.

One useful working liquid is an aqueous solution that includes a variety of different additives. Suitable additives include complexing, oxidizing, or passivating agents, metal ions such as transition metal ions, or combinations of additives.

Preferred oxidizing agents that may be incorporated into a working fluid include 5 per-compounds, for example, compounds containing at least one peroxy group (-O-O-). Examples of per-compounds include hydrogen peroxide, persulfate salts of ammonium, sodium and potassium, monopersulfates, organic peroxides such as di-t-butyl peroxide.

Other useful oxidizing agents include; cupric chloride; ferric chloride; chromic-sulfuric acids; potassium ferricyanide; nitric acid, transition metal complexes such as 10 ferricyanide, ammonium ferric EDTA, ferric ammonium citrate, ferric citrate, ammonium ferric oxalate, ferric nitrate, cupric citrate, cupric oxalate, cupric gluconate, cupric glycinate, cupric tartrate, and the like. Other suitable oxidizing agents also include oxo acids of the halogens and their salts, such as the alkali metal salts. These acids are described in Cotton & Wilkinson, Advanced Inorganic Chemistry, 5th Ed.

15 The anions of these acids typically contain halide atoms such as: chlorine, bromine, or iodine. These halides are bonded to one, two, three, or four oxygen atoms. Examples include: chloric acid (HOClO₂); chlorous acid (HOClO); hypochlorous acid (HOCl); and the respective sodium salts thereof, e.g., sodium chlorate, sodium chlorite, and sodium hypochlorite. Similar bromine and iodine analogs are known. Mixtures of 20 oxidizing agents also may be used so long as they do not interfere with the desired results. The concentration of the oxidizing agent in deionized water (in percent by weight of the total fluid without abrasive, even when an abrasive is used) is typically at least about 0.2, at least about 1, or even higher. In other embodiments, this oxidizing agent concentration is below about 50%, below about 30%, or even lower.

25 The oxidation of and dissolution of the exposed, metal wafer surface can be enhanced by the addition of metal ions to the working liquid. Metals are generally described in Dickerson, Gray and Haight in Chemical Principles, 3rd Ed. Included in the definition of metal are the semi-metals and transition metals. The selection of the metal ion will depend on a variety of factors including the wafer surface to be modified, 30 as well as, the overall composition of the working liquid, particularly the oxidizing agent, with particular selection within the skill of the art when guided with the present

disclosure. Generally, it is preferred to have the reduction potential of the metal ion less than the reduction potential of the oxidizing agent and greater than the reduction potential of the metal surface(s) being modified, such that the oxidizing agent may oxidize the metal ion and the metal ion may oxidize the desired wafer surface material

5 followed by re-oxidation of the reduced metal ion by the oxidizing agent.

Additionally, it is preferred to use a metal ion of at least an oxidation state of 2+ or higher, such that, upon oxidation of the metal surface(s) by the metal ion, the lowest oxidation state of the reduced metal ion is no lower than 1+. This aspect typically prevents the metal ion from being reduced to a metal solid and precipitating into the

10 working liquid or plating out on the metal surface being modified. Examples of useful metal ions include the ions of Cu, Fe, Ag, Au, Ta, Ti, Ce, Mn, Mg, Sn, Mo, and Sb.

The metal ions are typically added to the working liquid by addition of organic and/or inorganic salts containing the corresponding metal ion. Exemplary salts include ferric nitrate, ferric sulfate, ferrous sulfate, ferrous acetate, ferric chloride, cupric chloride,

15 silver acetate and the like. Combinations of metal ions also may be used, so long as the selected combination does not interfere with the desired result. In some embodiments, Group I and Group II metals are not used. Generally, the concentration of the metal ion in the working liquid (in mmol per gram of working liquid, without abrasive, if used) is typically at least about 9×10^{-6} , 36×10^{-6} , or even higher. In other embodiments, the

20 concentration of the metal ion in the working liquid (in mmol per gram of working liquid, without abrasive, if used) is typically below about 0.036, below about 0.009, or even lower. In other embodiments, the level of metal ion in the working liquid (in parts per million (ppm) working liquid, without abrasive, if used) is typically at least about 1, 2, 10, 20, 30, 50, or even higher. In other embodiments, this amount is at least about 25 100, 175, 250, 500, or even higher. In other embodiments, this amount is below about 2,000, below about 1,000, below about 500, or even lower.

The oxidation and dissolution of a metal can be enhanced by the addition of complexing agents: ligands and/or chelating agents for the metal. These compounds can coordinate and/or bond to the metal to increase the solubility of the metal or metal oxides in water as generally described in Comprehensive Coordination Chemistry, 30 Vol. 5, Wilkinson, Gillard, McCleverty, Eds. Complexing agents often are comprised

of a carboxyl group(s) or salts thereof. Simple carboxylic acids contain the carboxyl group, -COOH, attached to hydrogen (HCOOH) or an alkyl group (RCOOH). Simple carboxylic acids may have one carboxyl group (i.e., simple monofunctional carboxylic acids) or a plurality of carboxylic acid groups (i.e., simple multifunctional carboxylic acids), e.g., simple difunctional carboxylic acids (i.e., simple dicarboxylic acids) and simple trifunctional carboxylic acids (i.e., simple tricarboxylic acids). Exemplary simple monofunctional carboxylic acids include, e.g., formic, acetic, propionic, butyric, and isobutyric acids. Exemplary simple difunctional carboxylic acids include, e.g., oxalic, malonic, methylmalonic, succinic, glutaric, and adipic acids.

10 Suitable additives that may be added to or used in the working liquid include monodentate complexing agents, such as ammonia, amines, halides, pseudohalides, carboxylates, thiolates, and the like also called ligands. Other additives that may be added to the working liquid include multidentate complexing agents, typically multidentate amines, and multidentate carboxylic acids. Suitable multidentate amines 15 include ethylenediamine, diethylene-triamine, triethylenetetramine, or combinations thereof. Suitable multidentate carboxylic acids and/or their salts include the simple dicarboxylic acids described above, citric acid, tartaric acid, gluconic acid, nitriloacetic acid, or combinations thereof. Another additive that may be added to the working liquid include hydroxy substituted mono functional carboxylic acids and salts thereof.

20 Exemplary monofunctional hydroxy-carboxylic acids include glyceric acid (i.e., 2,3-dihydroxypropanoic acid), glycolic acid, lactic acids (e.g., L-lactic, D-lactic, and DL-lactic acids), hydroxy-butanoic acid, 3-hydroxypropionic acid, methyllactic acid (e.g., 2-hydroxyisobutyric acid) and 3,4-dihydroxybenzoic acid. Combinations of the two monodentate and polydentate complexing agents include amino acids such as 25 glycine, and common analytical chelating agents such as ethylenediaminetetraacetic acid (EDTA) and its numerous analogs. Other useful chelators or complexing agents include, for example, polyphosphates, 1,3-diketones, aminoalcohols, aromatic heterocyclic bases, phenols, aminophenols, oximes, Schiff bases, ascorbic acid and similar structures, and sulfur compounds. Mixtures of the above complexing agents 30 also may be used, so long as they do not interfere with the desired results. The concentration of the complexing agent in deionized water (percent by weight) is

typically at least about 0.002, 0.02, or even higher. In other embodiments, this amount is below about 20, below about 10, or even lower.

The complexing agents may also improve solution stability, such as by inhibiting oxidizer decomposition caused by the metal ions in the working liquid. This 5 can be of particular importance if a per-compound, hydrogen peroxide for example, is the oxidizer in the working liquid. When a majority of the complexing agent is selected from a simple monofunctional, a simple difunctional acid, a salt thereof, or a combination thereof, the mole ratio of complexing agent to metal ions (Mc/Mm) present in the composition should be at least 1 to 1, preferably greater than 3 to 1, more 10 preferably greater than 4 or 5 to 1, and in some embodiments greater than 10 to 1. One preferred range is a mole ratio between 15 to 1 and 200 to 1. Other ratios can be used with other acids or salts. The above ratios correspond to a complexing agent that has from one to four complexing sites per molecule. When the number of complexing sites per molecule increases, the ratios should be adjusted correspondingly lower to account 15 for the higher number of complexing sites. If mixtures of complexing agents are used, the ratio of Mc/Mm should be calculated based on the total moles of all complexing agents present. If mixtures of metal ions are used, the ratio of Mc/Mm should be calculated based on the total moles of all metal ions present. A majority of complexing agent includes at least half the total moles of complexing agent used. In some 20 embodiments, at least about 60 mole percent (mol%), 70 mol%, or even more of the simple acid or simple acid salt is used.

Buffers may be added to the working liquid to control the pH and thus mitigate pH changes from minor dilution from rinse water and/or difference in the pH of the deionized water depending on the source. The pH can have a significant effect on the 25 nature of the tungsten surface, and the tungsten removal rate. The most preferred buffers are compatible with semiconductor, post-CMP cleaning needs as well as having reduced potential impurities such as alkali metals. In addition, the presently preferred buffers can be adjusted to span the pH range from acidic to near-neutral to basic. Polyprotic acids act as buffers, and when fully or partially neutralized with ammonium 30 hydroxide to make ammonium salts, they are representative examples including systems of phosphoric acid-ammonium phosphate; polyphosphoric acid-ammonium

polyphosphate; the boric acid-ammonium tetraborate; boric acid-ammonium pentaborate. Other suitable buffers comprise an organic acid and its corresponding salt, particularly the ammonium salt. Tri- and polyprotic protolytes and their salts, especially the ammonium salts are preferred. These may include ammonium ion buffer 5 systems based on the following protolytes, all of which have at least one pKa greater than 7: aspartic acid, glutamic acid, histidine, lysine, arginine, ornithine, cysteine, tyrosine, and carnosine.

Corrosion inhibitors for metals are known. For example, typical inhibitors for 10 copper include benzotriazole and its derivatives known as azole derivatives, such as tolyltriazole. Copper is known to be somewhat passivated by cuprous oxide, especially at neutral or mildly alkaline pH. In addition, phosphates are known in passivating agents, such as used in coatings for zinc and steel. Including a passivating agent in the CMP working fluid can protect areas of a metal surface not yet in contact with the abrasive from premature, or excessive removal by an etchant or control how much 15 oxidizing agent reacts with the exposed metal surface. An example of a passivating agent is benzotriazole. Other passivating agents are listed in Leidheiser, The Corrosion of Coppers, Tin, and Their Alloys, (1971), pp. 119-123. The amount and type of passivating agent will depend in part of the desired planarization criteria (e.g., cut rate, surface finish, and planarity). Passivating agents, or etching inhibitors, useful with 20 tungsten include 4-ethyl-2-oxazoline-4-methanol, 2,3,5-trimethylpyrazine, 2-ethyl-3,5-dimethylpyrazine, quinoxaline, pyridazine, pyrazine, glutathione (reduced), thiophene, mercaptopyridine n-oxide, thiamine hydrochloride, tetraethyl thiuram disulfide.

The working liquid may also contain other additives such as surfactants, wetting 25 agents, buffers, lubricants, soaps, and the like. These additives are chosen to provide the desired benefit without damaging the underlying semiconductor wafer surface. For example, a lubricant may be included in the working liquid in a fixed abrasive process to reduce friction between the abrasive article and the semiconductor wafer surface during planarization.

Inorganic particulates may also be included in the working liquid. These 30 inorganic particulates may aid in the cut rate. Examples of such inorganic particulates include: alumina, silica, zirconia, calcium carbonate, chromia, ceria, cerium salts (e.g.,

cerium nitrate), garnet, silicates, and titanium dioxide. The average particle size of these inorganic particulates should be less than about 1,000 Angstroms, preferably less than about 500 Angstroms, and more preferably less than about 250 Angstroms.

5 Although particulates may be added to the working liquid, the presently preferred working liquid is substantially free of inorganic particulates, e.g., loose abrasive particles which are not associated with the abrasive article. Preferably, the working liquid contains less than 1% by weight, preferably less than 0.1% by weight and in some embodiments more preferably 0% by weight inorganic particulates.

In some embodiments, the invention provides a chemical mechanical polishing system comprising a fixed abrasive pad and a polishing composition useful for modifying a surface of a wafer, the composition comprising a synergistic mixture of water; an oxidizing agent; a complexing agent; and metal ions; wherein when the complexing agent is a simple monofunctional or simple difunctional acid or salt thereof, the mole ratio of complexing agent to metal ions present in the liquid is at least 15 3 to 1; and wherein the mixture is substantially free of abrasive particles. In some aspects, this system is supplied as a kit or multi-component system with or without instructions for use, and it can be provided such that the oxidizing agent remains separate from the metal ions and the fixed abrasive pad until the day or time of use or until the polishing operation requires the composition.

20 The nature of the metal surface in contact with a solution is related to the pH of the solution as well as the electrochemical potential of the metal. For example at pH greater than about 4, tungsten tends to corrode. At a pH < 4, a self-passivating tungsten oxide coating is formed. Thus, the pH of the polishing solution can be important. For tungsten polishing, it is preferred to have a pH from about 0.5 to 7, more preferably at 25 least about 1, or at least about 1.5. In other embodiments, a preferred pH is below about 5, below about 3 or even lower. The nature of the surface being modified, e.g., metal or metal oxide, also can have a significant effect on the action of the abrasive pad. Thus, the CMP polishing system, i.e., the polishing pad and polishing solution, must be optimized together to obtain the most desirable results. If a fixed abrasive pad 30 is used, selection of the abrasive particle may be dependent on the nature of the polishing solution, for example the solution pH. Generally, it is desirable for the fixed

abrasive polishing pad to be stable in aqueous solutions, i.e., to be comprised of polymers resistant to swelling by water or hydrophobic, and to be stable to the polishing solution to maximize pad life.

The amount of the working liquid preferably is sufficient to aid in the removal 5 of metal or metal oxide deposits from the surface. In many embodiments, there is sufficient liquid from the basic working liquid and/or the chemical etchant. In other embodiments, it is preferred to have a second liquid present at the planarization interface in addition to the first working liquid. This second liquid can include components also used in the first liquid, and it can be entirely different.

10 Commercially available tungsten slurries, with the abrasive particles removed, are believed to be useful as a substantially abrasive free polishing solution for tungsten CMP with fixed abrasive polishing pads. Examples of such slurries include Microplanar® CMP3550™, CMP3510™, CMP3100™, CMP3010™, and CMP3005™ from EKC technology, DuPont Electronic Technologies; Semi-Sperse® W2000 and 15 W2585 from Cabot Microelectronics Corp.; and MSW1500 Series Slurries and MSW2000 Series Slurries from Rohm and Haas Electronic Materials. Such slurries may be, or may become, available with few or no abrasive particles. Or, one can remove the abrasive particles from the commercial slurry via any known method. One such method is filtering the slurry, such as via the method described below in the 20 Examples. In another embodiment, such a slurry liquid base can be modified or fortified by adding selected working fluid components as described above.

Generally, it is preferred that the polishing solution oxidizes tungsten at a reasonable rate. Although a preferred method for Fixed Abrasive (FA) tungsten CMP is to have a substantially abrasive free polishing solution, it is believed that small 25 quantities of an appropriate abrasive could be added to the abrasive free polishing fluid, or left in the fluid when removing much of the abrasive, while obtaining useful results.

Using the FA approach in other CMP systems provides low dishing and low erosion. Both results have been demonstrated using FA tungsten CMP as well. Tungsten removal rates of up to 5,000 Å/min can be obtained, depending on process 30 conditions (see the Examples below for further guidance). The removal rates are well within the range of those required for acceptable wafer throughput. Additionally, when

pattern STI wafers containing both silicon oxide and silicon nitride regions were polished under the identical polishing conditions using a FA pad along with an exemplary working fluid, silicon oxide and silicon nitride removal rates were both about 2 Å/min, yielding very high tungsten/silicon oxide and tungsten/silicon nitride ratios. Although Ti and TiN rates were not specifically measured in this experiment, the FA approach rapidly removed the Ti/TiN layer as determined from the tungsten thickness and total polish time.

This invention is useful in semiconductor wafer planarization involving fixed abrasive articles. Objects and advantages of this invention are further illustrated by the following examples, but the particular materials and amounts thereof recited in these examples, as well as other conditions and details, should not be construed to unduly limit this invention.

Examples

Hydrogen peroxide, described as 30% by weight in water, CMOS™, stabilized, and ferric ammonium citrate (green) were obtained from J.T. Baker (a division of 15 Mallinckrodt Baker, Inc. Phillipsburg, NJ), and where not otherwise specified, materials are available from chemical supply houses, such as Sigma-Aldrich, Inc., St. Louis, MO.

Materials

Fixed Abrasives

20 Copper (Cu) CMP fixed abrasive discs available as M6100 (MWR66) and MWR131 from the 3M Company (St. Paul, MN) were used. Both fixed abrasives had a “T63” geometry, a three-dimensional fixed abrasive having three-sided pyramids having a height of about 63 µm and each side, although not being identical, having a length of about 125 µm, and included alumina abrasive. The fixed abrasive sheets were 25 laminated to 20/90 sub-pads (a foam sheet on a polycarbonate sheet available from 3M Company) using a pressure-sensitive adhesive (available as 9671 from 3M).

Wafers

Eight inch (200mm) diameter, blanket tungsten wafers, were obtained from 30 Ramco Technology, Inc. (Los Altos, CA). The wafers were single crystal silicon coated with the following layers in order from the surface of the silicon: about 500 nm (5,000Å) tetraethylorthosilicate (TEOS), about 15 nm (150Å) titanium, about 10 nm

(100Å) titanium nitride, and about 800 nm (8,000Å) cvd tungsten. Additional wafers of similar build were obtained from the Cypress Semiconductor Corp. (San Jose, CA). Eight inch diameter (200 mm) tungsten pattern wafers with an MIT 854 type mask without dummy structures were purchased from Ramco Technology. The pattern 5 wafers had the following wafer layers: 400nm (4,000Å) PETEOS, about 15 nm (150Å) titanium, about 10 nm (100Å) titanium nitride, and about 600 nm (6,000Å) CVD tungsten.

Polishing Solutions

10 A quantity of deionized (DI) water was mixed with other ingredients (as specified in each Example), by stirring the solution with a Teflon-coated magnetic stir bar until complete dissolution was observed.

Test Procedures

Removal Rate determination

15 Removal rate was calculated by determining the change in thickness of the layer being polished from the initial thickness and the final thickness. For eight inch diameter wafers, thickness measurements were taken with a ResMap 168-4 point probe Rs Mapping Tool (Credence Design Engineering, Inc., Cupertino, CA). Eighty-one point diameter scans with 5 mm edge exclusion were employed.

Wafer Non-Uniformity Determination

20 Percent wafer non-uniformity was determined by calculating the standard deviation of the change in thickness of the layer being polished at points on the surface of the wafer (as obtained from the Removal Rate Determination), dividing the standard deviation by the average of the changes in thickness of the layer being polished, and multiplying the value obtained by 100 so results are reported as percentage.

Hydrogen Peroxide Concentration Determination

Hydrogen peroxide concentration was determined by use of peroxide test strips (EM Quant® Peroxide test strips manufactured by EM Science, a Division of EM Industries, Inc., Gibbstown, NJ). The general test procedure described on the test strip container was employed. When applicable, the working liquids were diluted with DI 30 water to the appropriate concentration range detectible by the test strips. The dilution

factor was then taken into account to determine the amount of hydrogen peroxide present in the sample.

General Polishing Procedure

Wafers were polished using a MIRRA 3400 Chemical-Mechanical Polishing System (Applied Materials, Inc., Santa Clara, CA) or an Ebara Model EPO112 CMP Tool (Ebara Technologies, Inc., Sacramento, CA). For Mirra polishing, a polishing pad, 20 inches in diameter (50.8 cm), was laminated to the platen of the polishing tool with a layer of PSA as described above. The pad was high pressure rinsed with deionized (DI) water for 10 seconds and conditioned by polishing wafer(s) for 3-8 minutes at a platen speed of 101 rpm, a carrier speed of 99 rpm, and a polishing solution flow rate of 120 mL/min. During this polish, the pressures applied to the TITAN carrier inner tube, retaining ring and membrane were 31.0 kilopascals (kPa) (4.5 psi), 34.5 kPa (5.0 psi), 31.0 kPa (4.5 psi), respectively. Pad break-in was conducted with either CPS-11 polishing solution (available from 3M Company) containing the recommended level of hydrogen peroxide and an eight-inch diameter Cu disc or a blanket tungsten wafer(s) and any one of the documented tungsten polishing solutions. After pad break-in, polishing was conducted at a solution flow rate of 150 mL/min for 60 seconds per wafer. Unless otherwise noted in the specific example, process conditions for tungsten wafer polishing were as follows: membrane pressure 27.6 kPa (4.0 psi), retaining ring pressure 34.5 kPa (5.0 psi), inner tube pressure 41.4 kPa (6.0 psi), platen speed 79 rpm, carrier speed 101 rpm using a slotted retaining ring and polishing solution delivery arm in the lock position with an MWR66 polishing pad. Comparative Examples CE-1 through CE-6 and Examples 1 through 6 were polished on the Mirra 3400.

For EPO112 polishing, a MWR66 polishing pad, 22.5" diameter, was laminated to the platen of the polishing tool with a layer of PSA as described above. The pad was rinsed with deionized (DI) water for 10 seconds. Pad break-in was conducted by polishing 8 tungsten blanket wafers for 1 minute each at a platen speed of 79 rpm, a carrier speed of 101 rpm, a top ring pressure of 41.4 kPa (6.0 psi), a back side pressure of 27.6 kPa (4.0 psi) and a polishing solution flow rate of 150 mL/min. The break-in polishing solution contained 95.854% DI water, 4.066% hydrogen peroxide and

0.080% ferric ammonium citrate (green). After pad break-in, process conditions for all tungsten wafer polishing examples were as follows: top ring pressure 27.6 kPa (4.0 psi), back side pressure 17.3 kPa (2.0 psi), platen speed 79 rpm, carrier speed 101 rpm with a solution flow rate of 195 mL/min. The polishing time was 1 minute for blanket wafers 5 and 2 minutes for pattern wafers. Comparative Examples CE-7 through CE-11 and Examples 7 through 10 were polished using this method.

Key polishing solution parameters and tungsten blanket wafer polishing results are summarized in Table 1 including: polishing solution metal ion concentration, ratio of moles of complexing agent to moles of metal ion in the polishing solution (Mc/Mm), 10 hydrogen peroxide concentration, tungsten wafer removal rate and wafer non-uniformity.

Example 1

Polishing Solution: 856.5 g DI water, 7.9g ferric ammonium citrate (green), 135.7g 30% (wt.) hydrogen peroxide. The pH was 4.5. For samples containing ferric ammonium citrate (green), the moles of metal ion present were calculated based on a weight fraction of iron in the compound of 0.15. For the Table below, the moles of 15 complexing agent present were calculated based on the assumption that the weight fraction of citrate ion present was 0.85. Hence, it represents the maximum possible weight fraction of organic complexing agent present. The value could be somewhat lower, depending on the amount of ammonium ion in the compound.

Example 2

Polishing Solution: 859.5 g DI water, 5.0g of a solution comprised of 6.66g ferric ammonium citrate (green) and 993.34g DI Water, 135.5g 30% (wt.) hydrogen peroxide.

Example 3

Polishing Solution: 1,863.7 g DI water, 0.80g ferric ammonium citrate (green), 135.5g 30% (wt.) hydrogen peroxide. The pH was 4.8.

Example 4

Polishing Solution: 1,592.7 g DI water, 0.80g ferric ammonium citrate (green), 30 406.5g 30% (wt.) hydrogen peroxide. The pH was 4.9.

Example 5

Polishing Solution: 1,626.8g DI water, 2.23g 2-hydroxyisobutyric acid, 100g of a solution comprised of 1,997.6 g DI water and 2.38g ferrous sulfate hydrate, 271g 30% (wt.) hydrogen peroxide. The pH was 2.82.

5 Example 6

Polishing Solution: 3,452.9g DI water, 0.52g iron (III) nitrate nonahydrate, 4.46g 2-hydroxyisobutyric acid, 542g 30% (wt.) hydrogen peroxide. The pH was 2.67.

Comparative Example CE-1

Polishing Solution: 25 g citric acid, 2,000 g 30% (wt.) hydrogen peroxide.

10 Polishing Pad: MWR131. Process Conditions: membrane pressure 31.0 kPa (4.5 psi), retaining ring pressure 62.1 kPa (9.0 psi), inner tube pressure 62.1 kPa (9.0 psi), platen speed 101 rpm, carrier speed 99 rpm. Process Configuration: Slotted retaining ring, polishing solution delivery arm in pad center (solution is delivered onto the pad approx. 1.25-2.5 cm (0.5-1.0 inch) from pad center). This example shows that high levels of 15 hydrogen peroxide are necessary to obtain acceptable removal rates when other components of the invention are absent.

Comparative Example CE-2

Polishing Solution: 2,850 g DI water, 150 g iron (III) nitrate nonahydrate. The pH was 1.55.

20 Comparative Example CE-3

Polishing Solution: 1863.5 g DI water, 1.45 g iron (III) nitrate nonahydrate, 135g 30% (wt.) hydrogen peroxide. The pH was 2.71. However, the rapid decomposition of the hydrogen peroxide prevented tungsten wafer polishing.

Comparative Example CE-4

25 Polishing Solution: 3,500 g DI water, 538.5 g 30% (wt.) hydrogen peroxide.

Comparative Example CE-5

Polishing Solution: 922.5 g DI water, 7.9 g ferric ammonium citrate (green). The pH was 4.6.

Comparative Example CE-6

Polishing Solution: 856 g DI water, 3.74 g iron (II) acetate anhydrous (CAS #3094-87-9 from Alfa Aesar, Karlsruhe, Germany), 135.5 g 30% (wt.) hydrogen peroxide. The pH was 3.49. However, the rapid decomposition of the hydrogen peroxide prevented tungsten wafer polishing.

Comparative Example CE-7

Polishing Solution: 1730.3 g DI water, 271 g 30% (wt.) hydrogen peroxide, with pH 5.46.

Comparative Example CE-8

Polishing Solution: 1719.8 g DI water, 9.25 g 2-hydroxyisobutyric acid, 271 g 30% (wt.) hydrogen peroxide. The pH was 2.59.

Comparative Example CE-9

Polishing Solution: 1990.4 g DI water, 0.40 g iron (III) nitrate nonahydrate, 9.25 g 2-hydroxyisobutyric acid. The pH was 2.55.

Example 7

Polishing Solution: 6,916 g of a solution comprising; 13,754.8 g DI water, 3.2 g iron (III) nitrate nonahydrate and 74.0 g 2-hydroxyisobutyric acid. 1,084 g 30% (wt.) hydrogen peroxide was then added to the 6,916 g of metal ion containing solution. The pH was 2.47.

Comparative Example CE-10

Polishing Solution: 1726.4 g DI water, 1.45 g iron (III) nitrate nonahydrate, 0.42 g methylmalonic acid, 271 g 30% (wt.) hydrogen peroxide. The solution pH was 2.40. The hydrogen peroxide decomposed too rapidly to allowing tungsten wafer polishing. One day later, the hydrogen peroxide concentration of the solution was 0 mg/L, as indicated by peroxide strips.

Comparative Example CE-11

Polishing Solution: 1726.8 g DI water, 1.45 g iron (III) nitrate nonahydrate, 0.80 g methylmalonic acid, 271 g 30% (wt.) hydrogen peroxide. The solution pH was 2.29.

Two days later, the hydrogen peroxide concentration of the solution was 2 mg/L, as indicated by peroxide strips.

Example 8

Polishing Solution: 1726.0 g DI water, 1.45 g iron (III) nitrate nonahydrate, 5 1.60 g methylmalonic acid, 271 g 30% (wt.) hydrogen peroxide. The solution pH was 2.20.

Two days later, the hydrogen peroxide concentration of the solution was about 30 g/L (approximately 3%), as indicated by peroxide strips.

Example 9

10 Polishing Solution: 3452.7 g DI water, 0.80 g iron (III) nitrate nonahydrate, 4.46 g 2-hydroxyisobutyric acid, 542 g 30% (wt.) hydrogen peroxide. The solution pH was 2.57. A blanket tungsten wafer, a pattern tungsten wafer, and an STI pattern wafer, were polished. Removal rate for the blanket wafer is shown in Table 1. The pattern wafer was clear after a two-minute polish, including the Ti and TiN layers. Dishing and 15 erosion were good. A 90% dense array (9 μ m Line/1 μ m Space), 100 μ m (isolated line) and a 10 μ m line (array) yielded total indicated runout (TIR) values of 569 \AA , 476 \AA , and 369 \AA , respectively. The pattern STI wafers was polished for two minutes. Oxide loss was 2 $\text{\AA}/\text{min}$ and nitride loss was also 2 $\text{\AA}/\text{min}$. Hence, there is a high selectivity to tungsten.

20 **Example 10**

Polishing Solution: Identical composition as Example 33. The solution was allowed to age 4 days prior to polishing. The solution pH was 2.52. A blanket tungsten wafer and a pattern tungsten wafer were polished. Removal rate for the blanket wafer is shown in Table 1. The pattern wafer was clear after the two minute polish, including 25 the Ti and TiN layers. Dishing and erosion were good. A 90% dense array (9 μ m Line/1 μ m Space), 100 μ m (isolated line) and a 10 μ m line (array) yielded TIRs of 550 \AA , 476 \AA , and 341 \AA , respectively. Comparing to the results of Example 33, the polishing solution shows excellent pot life after hydrogen peroxide addition, with little hydrogen peroxide decomposition observed via the absence of significant gas bubble 30 formation.

Comparative Example CE-12

Polishing Solution: 1728.9 g DI water, 0.14 g iron (III) nitrate nonahydrate, 346 g 30% (wt.) hydrogen peroxide. Decomposition of the hydrogen peroxide prevented tungsten wafer polishing.

5

Table 1: Polishing Solution Parameters and Tungsten Removal Results

Example	Metal Ion Conc. (ppm)	Mc/Mm	H ₂ O ₂ Conc. (wt %)	Removal Rate (Å/min.)	% Non-Uniformity
1	1180	1.6	4.07	2,410	3.9
2	5	1.6	4.06	2,396	17.9
3	60	1.6	2.03	1,508	13.2
4	60	1.6	6.10	2,965	7.4
5	12.0	50.0	4.06	2,256	6.1
6	18.0	33.3	4.06	1,518	6.9
CE-1	0.0	NA	29.6	1,912	15.3
CE-2	6,910	NA	0.0	1,219	7.7
CE-3	100	0.0	2.03	NA	NA
CE-4	0.0	NA	4.00	147	25.3
CE-5	1180	1.6	0.00	96	38.6
CE-6	1200	1.0	4.06	NA	NA
CE-7	0.0	0.0	4.06	440	59.1
CE-8	0.0	NA	4.06	705	23.2
CE-9	27.6	89.7	0.00	23	NA
7	27.6	89.7	4.06	2,745	9.3
8	100	3.8	4.06	3,127	8.9
CE-10	100	1.0	4.06	NA	NA
CE-11	100	1.9	4.06	2,789	11.6
9	27.5	90	4.05	2,945	9.4
10	27.5	90	4.05	3,355	8.7
CE-12	9.3	0.0	5.00	NA	NA

It is apparent from the above description that various modifications can be made without departing from the invention. Accordingly, the scope of the invention should be limited only by the appended claims. All publications and patents are herein incorporated by reference to the same extent as if each individual publication or patent

5 was specifically and individually indicated to be incorporated by reference.

What is claimed is:

1. A fixed abrasive chemical mechanical polishing composition useful for modifying a surface of a wafer, the composition comprising a synergistic mixture of water; an oxidizing agent; a complexing agent; and metal ions; wherein when a majority of the complexing agent is selected from a simple monofunctional acid, a simple difunctional acid, a salt thereof, or a combination thereof, the mole ratio of complexing agent to metal ions present in the composition is at least 3 to 1; and wherein the mixture is substantially free of abrasive particles.
- 10 2. The polishing composition of claim 1 wherein when a majority of the complexing agent is a simple monofunctional acid, a simple difunctional acid, a salt thereof, or a combination thereof, the mole ratio of complexing agent to metal ions present in the liquid is at least 4 to 1.
- 15 3. The polishing composition of claim 1 wherein the mixture is substantially free of a passivating agent.
4. The polishing composition of claim 1 wherein the complexing agent is multi-dentate.
5. The polishing composition of claim 1 wherein the metal ion is an ion of a metal selected from Cu, Fe, Ag, Au, Ta, Ti, Ce, Mn, Mg, Sn, Mo, Sb, and combinations thereof.
- 20 6. The polishing composition of claim 1 wherein the metal ion is an ion of Fe and/or Mn.
7. The polishing composition of claim 1 wherein the complexing agent is selected from citric acid, 2-hydroxyisobutyric acid, lactic acid, oxalic, malonic acid, methylmalonic acid, succinic acid, glutaric acid, and adipic acid, their corresponding salts and mixtures thereof.
- 25 8. The polishing composition of claim 1 wherein the oxidizing agent is at least one per-compound.

9. The polishing composition of claim 1 wherein the oxidizing agent is hydrogen peroxide.
10. A chemical mechanical polishing system comprising a fixed abrasive pad and a polishing composition useful for modifying a surface of a wafer, the composition comprising a synergistic mixture of water; an oxidizing agent; a complexing agent; and metal ions; wherein when a majority of the complexing agent is a simple monofunctional acid, a simple difunctional acid, a salt thereof, or a combination thereof, the mole ratio of complexing agent to metal ions present in the liquid is at least 3 to 1; and wherein the mixture is substantially free of abrasive particles.
11. The polishing system of claim 10 wherein the fixed abrasive pad comprises a plurality of three-dimensional abrasive composites fixed to an abrasive article, wherein the abrasive composites comprise a plurality of abrasive particles fixedly dispersed in a binder.
12. The system of claim 10 wherein the oxidizing agent remains separate from the metal ions and the fixed abrasive pad until the time of use.
13. A method of modifying a surface of a semiconductor wafer suited for fabrication of a semiconductor device comprising:
 - a) providing a wafer comprising at least a first material having a surface etched to form a pattern and at least a second material deployed over the surface of the first material;
 - b) contacting the second material of the wafer to a plurality of three-dimensional abrasive composites fixed to an abrasive article in the presence of a working liquid according to claim 1, wherein the abrasive composites comprise a plurality of abrasive particles fixedly dispersed in a binder; and
 - c) relatively moving the wafer while the second material is in contact with the plurality of abrasive composites until an exposed surface of the wafer is substantially planar and comprises at least one area of exposed first material and one area of exposed second material.

14. A method of modifying a surface of a wafer suited for fabrication of a semiconductor device comprising:
 - a) providing a wafer comprising at least one dielectric material having a patterned surface, the dielectric material substantially covered with at least one intermediate layer, and the intermediate layer substantially covered by at least one conductive material;
 - b) contacting the conductive material of the wafer to a plurality of three-dimensional abrasive composites fixed to an abrasive article in the presence of a working liquid according to claim 1, wherein the plurality of abrasive composites comprise a plurality of abrasive particles fixed and dispersed in a binder; and
 - c) relatively moving the wafer while the conductive material is in contact with the plurality of abrasive composites until the exposed surface of the wafer comprises at least one area of exposed conductive material, at least one area of exposed intermediate layer and/or at least one area of exposed dielectric material.
15. The method according to claim 14 wherein the intermediate material is an adhesion/barrier layer.
16. The method according to claim 14 wherein the conductive material, or the second material comprises tungsten.
17. The method according to claim 14 wherein the abrasive particles are silica particles or metal oxides, optionally selected from alumina particles, ceria particles, and combinations thereof.
18. The method according to claim 14 wherein the abrasive article is attached to and/or supported by a subpad, optionally wherein the subpad is a laminate, and optionally wherein the laminate comprises a polycarbonate sheet and/or polyurethane foam.
19. The method according to claim 14 claims wherein the exposed wafer surface of part (c) has an Rt value less than 4,000 Angstroms, optionally wherein the exposed surface of part (c) has an Rt value less than 1,000 Angstroms.

20. The method according to claim 14 wherein the abrasive composite further comprises at least one additive, optionally wherein the additive is selected from abrasive particle surface modification additives, passivating agents, coupling agents, fillers, expanding agents, fibers, antistatic agents, initiators, suspending agents, lubricants, wetting agents, surfactants, pigments, dyes, UV stabilizers, complexing agents, chain transfer agents, accelerators, catalysts, activators, and combinations thereof.
5
21. The method according to claim 14 wherein the wafer further comprises a barrier layer substantially covering the dielectric material.
- 10 22. The method according to claim 21 wherein the wafer further comprises a second barrier layer.

INTERNATIONAL SEARCH REPORT

International application No. PCT/US2006/040803
--

A. CLASSIFICATION OF SUBJECT MATTER

C09K 3/14(2006.01)i

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C09K, H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
Korean Patents and applications for inventions since 1975

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
STN (CA)
eKIPASS (KIPO internal), USPAT, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 98-49723 A1 (MINNESOTA MINING AND MANUFACTURING COMPANY) 5 November 1998 See pages 10-51, claims.	1-22
Y	WO 98-23408 A1 (CABOT CORPORATION) 4 June 1998 See pages 6-15, Table 7, claims 8-20.	1-22

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance
"E" earlier application or patent but published on or after the international filing date
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)
"O" document referring to an oral disclosure, use, exhibition or other means
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"&" document member of the same patent family

Date of the actual completion of the international search

27 FEBRUARY 2007 (27.02.2007)

Date of mailing of the international search report

06 MARCH 2007 (06.03.2007)

Name and mailing address of the ISA/KR



Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

OH, Se Zu

Telephone No. 82-42-481-8156



INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/US2006/040803

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
W09849723A1	05.11.1998	AU199871706B2 AU734883B2 BR9809311A CA2287404A1 CN1165975C CN1254441A EP1016133A1 JP2001523395T2 KR1020010020384 TW479285B TW479285A US6194317BA	24.11.1998 21.06.2001 04.07.2000 05.11.1998 08.09.2004 24.05.2000 05.07.2000 20.11.2001 15.03.2001 11.03.2002 11.03.2002 27.02.2001
W09823408A1	04.06.1998	AT214417E AU5460898A1 CN1131125C CN1242729 DE69710993C0 DE69710993T2 EP844290A1 EP844290B1 ES2174192T3 HK1022661A1 ID23676A IL130138A0 IL130138A1 IL153843A0 JP10265766A2 JP3822339B2 KR1998042755A KR2006087359A TW396201B TW396201A TW442364B US5980775A US6015506A US6068787A W09823697A1	15.03.2002 22.06.1998 17.12.2003 26.01.2000 18.04.2002 28.11.2002 27.05.1998 13.03.2002 01.11.2002 18.06.2004 11.05.2000 28.01.2001 12.03.2003 31.07.2003 06.10.1998 20.09.2006 17.08.1998 02.08.2006 01.07.2000 01.07.2000 23.06.2001 09.11.1999 18.01.2000 30.05.2000 04.06.1998