



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01J 20/04, 20/06, B01D 53/68	A1	(11) International Publication Number: WO 99/39819 (43) International Publication Date: 12 August 1999 (12.08.99)
(21) International Application Number: PCT/GB99/00365 (22) International Filing Date: 3 February 1999 (03.02.99) (30) Priority Data: 9802439.1 6 February 1998 (06.02.98) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chem- ical House, Millbank, London SW1P 3JF (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): BAILEY, Stephen [GB/GB]; 3 Grange Road, Norton, Cleveland TS20 2NS (GB). WILLIAMS, Brian, Peter [GB/GB]; 31 St. Marys Street, Clitheroe, Lancashire BB7 2HH (GB). GRIZARD, Sebastien [FR/GB]; 52 Essex Close, Redcar, Cleveland TS10 4BZ (GB). DORAN, Mark, Sean [GB/GB]; 17 Allison Street, Guisborough, Cleveland TS14 6NX (GB). WILSON, Robert [GB/GB]; 58 Coleton Gardens, Ingleby Barwick, Stockton on Tees, Cleveland TS17 0YA (GB). (74) Agents: GRATWICK, Christopher et al.; ICI Group Intellectual Property, P.O. Box 11, The Heath, Runcorn, Cheshire WA7 4QE (GB).		(81) Designated States: CA, IN, JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: ABSORBENTS (57) Abstract Shaped absorbent units suitable for use as chloride absorbents comprising a calcined intimate mixture of an alkali or alkaline earth, zinc and aluminium components having an alkali or alkaline earth metal to zinc atomic ratio in the range 0.5x to 2.5x and an alkali or alkaline earth metal to aluminium atomic ratio in the range 0.5x to 1.5x, where x is the valency of the alkali or alkaline earth metal, and containing from 5 to 20 % by weight of a binder. Preferred compositions are made from sodium carbonate or bicarbonate, basic zinc carbonate or zinc oxide and alumina or hydrated alumina.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Absorbents

This invention relates to absorbents, and to a process for their manufacture, in particular to absorbents suitable for removing halogen-containing contaminants such as hydrogen chloride or chlorine-containing organic compounds from gas streams.

- 5 Such absorbents are typically employed as a bed through which the gas stream to be treated is continuously passed: the contaminant is absorbed by the absorbent so that the effluent gas has a relatively low contaminant content. After a period of time, the absorbent becomes loaded with absorbed contaminant until the absorbent bed is unable to reduce the contaminant content to an acceptable level: typically it is desired to have an effluent gas containing less than a specified
- 10 amount, e.g. 0.1ppm by volume, of contaminant. When the effluent gas contains an unacceptable proportion of contaminant, "break-through" is said to have occurred... It is normally found that, when break-through has occurred, the halide content of the bed is somewhat less than the theoretical maximum: thus while samples taken from bed inlet region may have a halogen content approaching the theoretical maximum, samples taken from the bed outlet region are liable to have a halogen
- 15 content significantly below the theoretical maximum.

- Sodium and zinc compounds are effective absorbents for halogen-containing compounds. It has been proposed in US3935295 to make absorbents from a composition comprising zinc oxide, a basic calcium compound and a binder. It has also been proposed in WO95/22403 to make absorbents by granulating a mixture of sodium carbonate, or bicarbonate, alumina trihydrate, and a
- 20 binder followed by calcination at below 350°C. While such absorbents have a high halogen absorption capacity at low temperatures, e.g. below 150°C, at higher temperatures the absorption capacity decreases as a result of decomposition of the active species in the absorbent. It is thus desirable to produce an absorbent that is effective both at temperatures below 150°C and at higher temperatures, e.g. up to 300°C.

- 25 We have found that particularly effective absorbents can be made from a combination of alkali metal, and/or alkaline earth metal and zinc compounds.

 Accordingly the present invention provides shaped absorbent units comprising a calcined intimate mixture of

- a) an alumina component selected from alumina and/or hydrated alumina,
- 30 b) a zinc component and a basic metal component, said components being oxides, hydroxides, carbonates, bicarbonates and/or basic carbonates and said basic metal component comprising at least one compound of at least one alkali or alkaline earth metal, and
- c) a binder,

- 35 the basic metal to zinc atomic ratio being in the range 0.5x to 2.5x and the basic metal to aluminium atomic ratio being in the range 0.5x to 1.5x where x is the valency of the basic metal, said granules containing from 5 to 20% by weight of said binder.

Preferably the shaped units have a basic metal content such that, after ignition of a sample of the units at 900°C, the sample has a basic metal oxide content of at least 10%, particularly at least 15%, and more particularly at least 20%, by weight.

Basic metal compounds that may be employed include compounds of lithium, sodium, potassium, beryllium, magnesium, calcium, strontium and barium. Preferred compounds are compounds of sodium or calcium, particularly sodium. Particularly preferred alkali or alkaline earth compounds are carbonates and/or bicarbonates. Where an alkali metal compound is used "x"=1. Mixtures of alkali metal and alkaline earth metal compounds may be used: in this case the value of "x" will depend on the relative atomic proportions of alkali metal and alkaline earth metal.

10 The zinc component is preferably zinc oxide, carbonate or, particularly, basic carbonate. The basic metal and zinc components may be present at least partially as a mixed salt, such as sodium zinc carbonate and/or basic sodium zinc carbonate.

The shaped absorbent units preferably have an average size in the range 2-10mm, and preferably at least about 3mm as a bed of smaller units is liable to present an unacceptable resistance to flow of gas therethrough. Thus an unacceptably high pressure drop is experienced upon passage of the gas through a bed of small units.

The binder may be a suitable hydraulic cement, such as calcium aluminate cement. Alternatively, and preferably, the binder comprises a clay, for example an acicular clay such as attapulgite or sepiolite.

20 The shaped absorbent units of the present invention may be made by granulating or extruding a mixture of alumina or a hydrated alumina such as alumina trihydrate, basic metal component, zinc component and the binder, in the requisite proportions, and calcining the resultant mixture. Preferably the units are made from a mixture of hydrated alumina, sodium bicarbonate, zinc oxide or basic zinc carbonate, and a clay binder.

25 Alternatively there may be used a preformed mixed basic metal/zinc salt, e.g. sodium zinc carbonate or basic sodium zinc carbonate, e.g. as obtained by precipitation by the dropwise addition of a solution of sodium carbonate with a solution of a zinc compound such as zinc nitrate under controlled conditions of pH in the range 7-8 and temperature of about 80°C, alone, or in admixture with additional zinc and/or sodium carbonates. This mixed basic metal/zinc salt may be mixed with
30 the alumina or hydrated alumina and binder to form the shaped absorbent units.

Where hydrated alumina is used as the alumina component, the calcination results in a substantial increase in the surface area of the absorbents. For these reasons the calcination is preferably effected at temperatures in the range 200-450°C, particularly above 240°C, and most preferably above 300°C. Preferably the calcination temperature is below 500°C to minimise reaction
35 of the basic metal compound and the alumina: thus alkali or alkaline earth metal aluminates have lower absorption capacity.

The shaped absorbent units preferably have a BET surface area of at least $10\text{m}^2/\text{g}$, particularly above $50\text{m}^2/\text{g}$, and most preferably above $90\text{m}^2/\text{g}$.

By the term granulation we mean mixing the powdered ingredients, including the binder, with a little wetting agent such as water, in an amount that is insufficient to form a slurry, and forming the resultant mixture into aggregates, generally of approximate spherical configuration. Such granulation techniques are well known in the art.

As an alternative to granulation, the composition may be formed into extrudates, for example using a pellet mill, for example of the type used for pelleting animal feedstuffs, wherein the mixture to be pelleted is charged to a rotating perforate cylinder through the perforations of which the mixture is forced by a bar or roller within the cylinder. The resulting extruded mixture is cut from the surface of the rotating cylinder by a doctor knife positioned to give pellets of the desired length. It will be appreciated that other extrusion techniques may be employed.

It is preferred to employ alumina trihydrate, rather than alumina, since granulation or extrusion of alumina-containing compositions tends to present difficulties.

In order to make shaped units of adequate strength it is desirable to employ the ingredients in a finely divided form. Typically the ingredients have an average particle size in the range $1\text{-}20\mu\text{m}$, preferably in the range $5\text{-}10\mu\text{m}$.

Where an alkali metal compound is used, during the calcination step, it is believed that there is formed a highly dispersed alkali metal/zinc composite, probably an intimate mixture of alkali metal carbonate and zinc oxide, that is uniformly distributed over the alumina substrate. It appears that while zinc oxide is an effective chloride absorbent, alkali metal carbonates are less effective. For this reason the alkali metal to zinc atomic ratio of the granules should be below 2.5. When employing sodium compounds as the alkali metal component and the absorbent is used for absorption of hydrogen chloride, we have observed that a sodium zinc chloride Na_2ZnCl_4 is formed: this species has been identified by X-ray diffractometry on absorbents that have been used for absorption of hydrogen chloride. It is evident by the dry, free-flowing nature of the fully chlorided shaped absorbent units that the formation of this compound does not give rise to any of the deleterious effects associated with moisture absorption such as caking, pressure drop, and difficulties in discharge of spent absorbent. However, if the alkali metal to zinc ratio of the absorbent is too small, the granules become sticky during use, giving rise to caking of the bed of absorbent units with the consequence of the bed exhibiting an unacceptable increase in the resistance of gas flow therethrough. For this reason the alkali metal to zinc atomic ratio should preferably be above 0.8. It is preferred that the alkali metal to zinc atomic ratio is in the range from about 0.8 to 2.2.

The absorbent granules of the invention may be used at temperatures ranging from 10 to 300°C and at any convenient pressure, for example atmospheric to 100 bar abs . They are of particular utility as guard beds to absorb chloride ions from gas streams, e.g. to avoid corrosion

problems during subsequent processing of the gas stream and/or to avoid poisoning of downstream catalysts, particularly copper containing catalysts such as low temperature shift catalysts or methanol synthesis catalysts. Thus the granules may be disposed as a bed adjacent the inlet of a bed of low temperature shift or methanol synthesis catalyst. They may also be of utility in removing
5 halogen-containing organic compounds from gas streams.

The Invention is illustrated by the following examples.

Examples 1-5

Alumina trihydrate, basic zinc carbonate (hydrozincite - $\text{Zn}_5(\text{CO}_3)_2(\text{OH})_6$), sodium carbonate, and a clay binder, each in finely divided powder form having an average particle size in the range
10 5-10 μm , were dry mixed in the proportions specified in the table below. Part of the mixture (about 3kg) was charged to a Hobart mixer of 15l capacity and stirred therein. Water was slowly added while stirring until the mixture adhered to form small balls or agglomerates. Further amounts of the powder mixture and water were gradually added until all the powder mixture had formed into agglomerates. The agglomerates were then sieved to reject agglomerates having a size below
15 about 2.8mm or above about 4.8mm.

The remaining agglomerates were then calcined in air at 300°C for 2 hrs.

The hydrogen chloride absorption characteristics were assessed by passing hydrogen containing about 1% by volume of hydrogen chloride at atmospheric pressure and ambient temperature (20-25°C) down through a vertical bed of the pellets or granules of height 16cm and
20 height to diameter ratio of 7 at a space velocity of approximately 750h⁻¹. The time taken before the hydrogen chloride content of the exit gas reached 5ppm by volume was determined and is quoted in the following table as the "break-through time to 5ppm HCl". The granules were then carefully discharged from the bed and divided into 6 portions corresponding to 2.5cm bands of the bed depth. Each portion was analysed for the chloride content. The results are shown in the following table:

		Example				
		1	2	3	4	5
composition (parts by weight)	Al(OH) ₃	40	40	40	40	40
	Na ₂ CO ₃	20	25	30	35	40
	Zn ₅ (CO ₃) ₂ (OH) ₈	40	35	30	25	20
	binder	7	7	7	7	7
	Na/Zn atomic ratio	1.0	1.5	2.1	2.9	4.1
	Na/Al atomic ratio	0.7	0.9	1.1	1.3	1.5
Break-through time (hh:mm) to 5ppm HCl		13:00	11:00	13:30	6:15	<3:00
Chlorine content (% by weight of discharged absorbent)	Bed portion 1 (top)	21.8	19.2	21.7	11.4	5.3
	Bed portion 2	22.5	19.6	20.2	11.3	5.1
	Bed portion 3	nm	nm	19.1	nm	nm
	Bed portion 4	nm	nm	19.6	nm	nm
	Bed portion 5	nm	nm	18.2	nm	nm
	Bed portion 6 (bottom)	nm	nm	4.3	nm	nm

nm = not measured

It is seen that the absorption capacity deteriorates if the sodium to zinc ratio is too high.

Example 6

Example 3 was repeated but using different calcination temperatures. The BET surface area of the absorbent units was determined and was as set out in the following table.

Calcination temperature (°C)	BET surface area (m ² /g)
none	12
200	17
250	57
300	103
350	99
400	95

Example 7

Extrudates were made using the ingredients as employed for Example 3 by dry-mixing the powdered ingredients in a Kenwood mixer. The total weight of the dry ingredients used was 1000g. 200ml of distilled water was added and mixed in small aliquots to form a homogeneous mixture. The resulting paste was then extruded in a small pellet mill to give extrudates of 3.2mm diameter and about 6 mm long. The wet extrudates were calcined at 300°C for 2 hours. The procedure was repeated using 250ml of water giving a greater yield of extrudates of the requisite size. The procedure was also repeated using 2000g of the dry mixture and 550ml of water and using a pellet mill giving extrudates of 2mm diameter and length about 5mm. The yield of pellets of the requisite size and their properties are shown in the following table.

Feed weight (g)	Water (ml)	Weight of calcined product (g)	Bulk density (g/l)	BET surface area (m ² /g)
1000	200	371	-	89
1000	250	439	800	-
2000	550	1540	760	74

(The bulk density is the density of a bed of the extrudates).

The chloride contents of the extrudates when tested by the procedure employed in examples 1-5 were in the range 12.7-14.7% by weight.

Example 8

The material of Example 3 (hereinafter absorbent A) was tested as above but using a hydrogen chloride concentration of 0.1% by volume instead of 1%. The chlorine contents of the discharged portions of the bed were as follows:

	Chlorine content (% by weight of discharged absorbent)
Bed portion 1 (top)	20.9
Bed portion 2	20.4
Bed portion 3	20.1
Bed portion 4	20.6
Bed portion 5	20.2
Bed portion 6 (bottom)	8.5

Example 9

Absorbent A was tested as above using a hydrogen chloride concentration of 1% by volume but at differing temperatures. Since the space velocity (at NTP) was kept constant at 750h^{-1} , the contact time of the gas with the bed of absorbent units decreases as the temperature increases.

- 5 The approximate contact time and chlorine content of the top bed was as follows:

Test temperature (°C)	Approximate contact time (sec)	Chlorine content (% by weight of discharged absorbent)
25	4.8	20.0
50	4.3	19.7
100	3.8	19.0
200	3.0	16.1
300	2.5	11.9

Example 10

- A number of absorbents were tested for hydrogen chloride absorption using 500ml of the absorbent units disposed as a bed of height 45cm and diameter 4cm using a gas mixture of 80% by volume hydrogen and 20% natural gas containing 50ppm by volume of hydrogen chloride at a space velocity of 1756h^{-1} at a temperature of 35°C and a pressure of 20 barg. The absorbents used were as follows:

Absorbent A: (as described above)

- 15 Absorbent B: Granules of particle size within the range 3 to 5mm having a bulk density of about 0.9g/ml and a BET surface area of about $16\text{g}/\text{m}^2$ made by the procedure of Example 1 of WO 95/22403 using 50 parts by weight of sodium bicarbonate, 50 parts by weight of alumina trihydrate, and 10 parts by weight of attapulgite clay with the drying and calcining being effected in a single stage in a rotary drier at 145°C . Analysis of a sample of the granules that had been ignited at 900°C showed a sodium oxide, Na_2O , content of about 30% by weight.

- 20 Absorbent C: Commercially available alumina granules of about 3mm size impregnated with sodium carbonate and calcined at above 500°C to give granules of bulk density about 0.75g/ml and a BET surface area of about $113\text{m}^2/\text{g}$ which, after ignition at 900°C , had a sodium oxide, Na_2O , content of about 14% by weight.

- 25 Absorbent D: Commercially available activated alumina granules of about 3mm size having a bulk density of 0.83g/ml and a BET surface area of about $300\text{m}^2/\text{g}$.

The results are shown in the following table

Absorbent	Chlorine content of discharged absorbent (% by weight)					
	Bed 1	Bed 2	Bed 3	Bed 4	Bed 5	Bed 6
A	28.0	27.9	26.6	23.4	18.8	7.6
B	21.3	19.9	19.7	18.2	14.8	6.6
C	14.2	12.8	12.5	12.4	10.8	6.8
D	8.8	7.5	6.7	5.5	5.5	4.4

Example 11

30 parts by weight of alumina trihydrate, 35 parts by weight of sodium bicarbonate, 35 parts by weight of zinc oxide and 7 parts by weight of a clay binder, each in finely divided powder form having an average particle size in the range 5-10 μ m, were dry mixed, granulated, dried and calcined, by the procedure described in Examples 1-5. The sodium to zinc atomic ratio was about 1.0 and the sodium to aluminium atomic ratio was about 1.1. The BET surface area of the absorbent granules was 95m²/g. The resulting agglomerates were then tested for hydrogen chloride absorption by the procedure described in Examples 1-5. The break-through time was 14:55 (hh:mm) and the chloride content of the top portion of the absorbent bed was 32.3% by weight.

When a calcium aluminate cement was used in place of the clay as the binder, lower chloride absorption was achieved.

Granules made by a similar procedure but with sodium to zinc ratios below 0.8 became sticky and formed into a solid lump during the chloride absorbency test.

Example 12

The procedure of Example 11 was repeated using basic zinc carbonate in place of zinc oxide and 10 parts of the clay binder. The resultant absorbent was designated Absorbent E and had a sodium to zinc atomic ratio of 1.3 and a sodium to aluminium atomic ratio of 1.1. Absorbents E, B and C were tested for their ability to absorb chlorine-containing organic compounds by passing hydrogen containing about 1% by volume of 1,2 dichloropropane at atmospheric pressure and ambient temperature (20-25°C) down through a vertical bed of the absorbent of height 16cm and height to diameter ratio of 7 at a space velocity of approximately 750h⁻¹. The bed inlet and outlet 1,2 dichloropropane concentrations were monitored over a period of time and the ratio of the outlet to inlet concentrations used to give an indication of the performance of the absorbent. The results are shown in the following table.

Time (min)	1,2 dichloropropane concentration: outlet/inlet (%)		
	Absorbent B	Absorbent C	Absorbent E
0	0	0	0
30	50	5	2
60	71	42	3
90	92	76	5
120	100	93	11
150		100	86
180			93
210			100

It is seen that the absorbent in accordance with the invention, viz. absorbent E, was far more effective in absorbing 1,2-dichloropropane than the prior art absorbents.

When tested for hydrogen chloride absorption capacity by the procedure employed in Examples 1-5, the absorbent E gave a performance very similar to the absorbent of Example 11; the
5 chloride content of the top portion of the absorbent bed at hydrogen chloride breakthrough was 32.5% by weight.

Claims

1. Shaped absorbent units comprising a calcined intimate mixture of
 - a) an alumina component selected from alumina and/or hydrated alumina,
 - b) a zinc component and a basic metal component, said components being oxides, hydroxides, carbonates, bicarbonates, and/or basic carbonates and said basic metal component comprising at least one compound of at least one alkali or alkaline earth metal, and
 - c) a binder,the basic metal to zinc atomic ratio being in the range $0.5x$ to $2.5x$ and the basic metal to aluminium atomic ratio being in the range $0.5x$ to $1.5x$, where x is the valency of the basic metal, said shaped units containing from 5 to 20% by weight of said binder.
2. Shaped absorbent units according to claim 1 having a basic metal content such that, after ignition of a sample of the shaped units at 900°C , the sample has a basic metal oxide content of at least 10% by weight.
3. Shaped absorbent units according to claim 1 or claim 2 having a BET surface area above $50\text{m}^2/\text{g}$.
4. Shaped absorbent units according to any one of claims 1 to 3 wherein the basic metal component comprises one or more alkali metal compounds.
5. Shaped absorbent units according to claim 4 wherein the alkali metal to zinc atomic ratio is in the range from about 0.8 to 2.2.
6. A process for the manufacture of shaped absorbent units according to any one of claims 1 to 5 comprising forming granules or extrudates from a mixture of (i) alumina trihydrate, (ii) an alkali metal or alkaline earth metal carbonate or bicarbonate, (iii) basic zinc carbonate or zinc oxide, and (iv) a binder in such proportions that the alkali or alkaline earth metal to zinc atomic ratio is in the range $0.5x$ to $2.5x$, the alkali or alkaline earth metal to aluminium atomic ratio is in the range $0.5x$ to $1.5x$, where x is the valency of the alkali or alkaline earth metal, and the binder forms from 5 to 20% by weight of the granules or extrudates and then calcining the granules or extrudates at a temperature in the range 200 to 450°C .
7. A process for the removal of halogen-containing contaminants from a gas stream, comprising passing the gas stream through a bed of shaped absorbent units according to any one of claims 1 to 5 or made according to a process according to claim 6.

INTERNATIONAL SEARCH REPORT

national Application No
PCT/GB 99/00365

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 B01J20/04 B01J20/06 B01D53/68		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 B01D B01J		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 546 464 A (JAPAN PIONCS) 16 June 1993 see page 3, line 48 see page 3, line 57 see page 5, line 20 - line 35 ---	1,4,6,7
Y	PATENT ABSTRACTS OF JAPAN vol. 098, no. 001, 30 January 1998 & JP 09 225296 A (TOYO C C I KK; JAPAN ENERGY CORP), 2 September 1997 see abstract ---	1,4,6,7
A	WO 95 22403 A (IMPERIAL CHEMICAL INDUSTRIES PLC) 24 August 1995 cited in the application see the whole document --- -/--	1-7
☒ Further documents are listed in the continuation of box C. ☒ Patent family members are listed in annex.		
° Special categories of cited documents :		
"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
Date of the actual completion of the international search 23 April 1999		Date of mailing of the international search report 06/05/1999
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Hilgenga, K

INTERNATIONAL SEARCH REPORT

national Application No

PCT/GB 99/00365

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 2 267 096 A (MOLECULAR PRODUCTS LIMITED) 24 November 1993 see page 1, line 16 - line 17 see page 3, last paragraph - page 4, line 10 see page 5; example 3 ----	1,7
A	DATABASE WPI Section Ch, Week 8811 Derwent Publications Ltd., London, GB; Class E35, AN 88-075922 XP002101002 & SU 1 327 955 A (DANTSIG G A) , 7 August 1987 see abstract ----	1,6
A	DATABASE WPI Section Ch, Week 8128 Derwent Publications Ltd., London, GB; Class E36, AN 81-511900 XP002101003 & SU 774 575 B (BUDKINA O G) , 30 October 1980 see abstract ----	1,4,7
A	US 3 935 295 A (R.W. LA HUE) 27 January 1976 cited in the application -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

national Application No

PCT/GB 99/00365

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 546464 A	16-06-1993	DE 69218133 D	17-04-1997
		DE 69218133 T	19-06-1997
		KR 126123 B	19-12-1997
		US 5597540 A	28-01-1997
		US 5378444 A	03-01-1995
		JP 5237324 A	17-09-1993
WO 9522403 A	24-08-1995	AT 167084 T	15-06-1998
		AU 683992 B	27-11-1997
		AU 1667895 A	04-09-1995
		CA 2183319 A	24-08-1995
		DE 69502940 D	16-07-1998
		DE 69502940 T	08-10-1998
		EP 0746409 A	11-12-1996
		ES 2117404 T	01-08-1998
		JP 9508855 T	09-09-1997
		NO 963458 A	21-08-1996
		ZA 9501112 A	21-08-1995
GB 2267096 A	24-11-1993	EP 0640011 A	01-03-1995
		WO 9323159 A	25-11-1993
US 3935295 A	27-01-1976	BE 809997 A	16-05-1974
		IN 141393 A	26-02-1977
		IN 145942 A	20-01-1979
		JP 905936 C	18-04-1978
		JP 50001085 A	08-01-1975
		JP 52035036 B	07-09-1977