

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07F 17/00, C08F 10/00	A1	(11) International Publication Number: WO 97/01566 (43) International Publication Date: 16 January 1997 (16.01.97)
(21) International Application Number: PCT/EP96/02845 (22) International Filing Date: 27 June 1996 (27.06.96) (30) Priority Data: 95201766.3 28 June 1995 (28.06.95) EP (34) Countries for which the regional or international application was filed: GB et al. (71) Applicant (for all designated States except CA): SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V. [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL). (71) Applicant (for CA only): SHELL CANADA LIMITED [CA/CA]; 400 - 4th Avenue S.W., Calgary, Alberta T2P 2H5 (CA). (72) Inventors: DE BOER, Eric, Johannes, Maria; Badhuisweg 3, NL-1031 CM Amsterdam (NL). RUISCH, Bart, Johan; Badhuisweg 3, NL-1031 CM Amsterdam (NL). SCHOON, Lodewijk; Badhuisweg 3, NL-1031 CM Amsterdam (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: CATALYST COMPOSITIONS COMPRISING ORGANOMETALLIC COMPOUNDS (57) Abstract There is provided a catalyst composition comprising a first component which is an organometallic compound comprising a metal M of Group 3 to 6 of the Periodic Table or the Lanthanide series and at least one (hetero)cyclohexadienyl ligand of the general formula (I): C_5AR_n wherein A is an element chosen from Group 13 to 16 of the Periodic Table, R which can be connected to C or to A and which may form a bridge is independently hydrogen or an organic substituent which may contain one or more heteroatoms and n is 3 plus the number of valencies of A, and a second component which acts as a co-catalyst. There is further provided the use of this catalyst composition in a process for the (co)oligomerisation or (co)polymerisation of olefinically unsaturated hydrocarbons.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

- 1 -

CATALYST COMPOSITIONS COMPRISING
ORGANOMETALLIC COMPOUNDS

This invention relates to new organometallic compounds and to catalyst compositions comprising these organometallic compounds, which compositions are useful for the (co) oligomerisation and (co)polymerisation of olefinically unsaturated hydrocarbons (Ziegler-Natta type catalysis). The invention further relates to catalyst compositions comprising these new organometallic compounds and known co-catalysts.

Ziegler-Natta catalysts have a long history. The first reports on homogeneous olefin polymerisation catalysts composed of a Group 4 metal complex and an alkylaluminium compound as cocatalyst were published by Breslow and Newburg (J. Am. Chem. Soc. 79 1957 5072 and 81 1959 81). Subsequently, it was reported that the addition of small amounts of water to the above compositions increased the rate of polymerisation (W.P. Long, J. Am. Chem. Soc. 81 1959 5312; Long and Breslow, J. Am. Chem. Soc. 82 1960 1953). Later, Sinn and Kaminsky (e.g. in W. Kaminsky, Adv. Organometal Chemistry 18 1980 99) reacted the alkylaluminium with equimolar amounts of water to produce aluminoxane, which proved to be a much more effective cocatalyst. Currently, the best known aluminoxane cocatalyst is methyl aluminoxane (MAO). Still later, R.F. Jordan et al. (J. Am. Chem. Soc. 108 1986 1718 and 7410) replaced the cocatalyst by reacting the group 4 metal complex with a compound, the anion of which is substantially non-coordinating. K. Shelly and C.A. Reed (J. Am. Chem. Soc. 108 1986 3117) showed that the bulky carborate $B_{11}CH_{12}$ is "the least coordinating anion" and Turner (in EP-A 277003 and EP-A 277004) defined groups of bulky, substantially non-coordinating anions as

- 2 -

cocatalysts with Group 4 metallocene catalysts.

The Group 4 metal compounds generally are metallocenes, containing in relation to the four valencies of the metal 1-4, in particular two, cyclopentadienyl (C_5H_5) rings, and 0-3, in particular also two, alkyl or halogen radicals. Several patent publications also claim similar Group 5 and 6 metallocenes, in addition to the still preferred Group 4 metallocenes.

Illustrative examples of patent publications relating to the more modern Ziegler-Natta catalysts and disclosing their use in the polymerisation of olefins, in particular the production of solid, high-molecular polymers and copolymers of ethene, are:

EP-B 69951 to HOECHST, disclosing catalyst compositions of bis(cyclopentadienyl)zirconium-dichloride or -methylchloride with methyl aluminoxane;

EP-B 129368 to EXXON, disclosing catalyst compositions of substituted mono-, bis- and tri(cyclopentadienyl)-Group 4 metal halogenide or -hydrocarbide and an aluminoxane;

EP-A 277003 of EXXON, disclosing catalyst compositions of substituted or unsubstituted bis(cyclopentadienyl) Group 4 metal hydrocarbide with an anion containing a plurality of boron atoms which is bulky, labile and capable of stabilising the metal cation;

EP-A 277004 of EXXON, disclosing catalyst compositions of substituted or unsubstituted bis(cyclopentadienyl) Group 4 metal hydrocarbide with an anion having a plurality of lipophylic radicals around a metal or metalloid ion, which anion is bulky, labile and capable of stabilising the metal cation; and

EP-B 426637 to FINA, disclosing a process for making catalyst compositions of substituted or unsubstituted bis(cyclopentadienyl) Group 4-6 metal halogenide, hydrocarbide, amide or hydride with an anion which is

- 3 -

non-coordinated or only loosely coordinated to the metallocene cation - by reacting the metallocene with a compound of said anion and carbonium, oxonium or sulfonium cation.

5 Illustrative examples of recent patent applications which are directed to similar catalyst compositions and which disclose in particular their use for the preparation of lower-molecular, liquid (co)oligomers of ethene and (co)polymers of propene respectively are:

10 EP-A 596553 of SHELL, disclosing catalyst compositions of substituted bis(cyclopentadienyl) Group 4 metal halogenide or hydrocarbide with a bulky, labile and substantially non-coordinating anion wherein the substitution of each of the two cyclopentadienyl radicals
15 is different; and

EP-A 540108 of SHELL, disclosing a catalyst composition of substituted bis(cyclopentadienyl) Group 4 metal halogenide, hydrocarbide, hydrocarbamide or hydride with aluminoxane wherein at least one cyclopentadienyl
20 radical is substituted with a single optionally substituted aryl group.

All of the above work used the cyclopentadienyl metal complexes, known under the general name of metallocenes. While most of the above identified publications, as well
25 as further similar ones, contain in their scope substituents on the cyclopentadienyl ring, and while these substitutions in some cases may include one or more hetero-atoms, the five-ring itself remained unmodified.

By contrast to the foregoing, WO 95/04087 of SHELL
30 discloses a catalyst composition of a Group 4 or 5 metal complexed with substituted or unsubstituted hetero-cyclopentadienyl, the heteroatom in the five-ring being a Group 15 element, and a co-catalyst which may be of the non-ionic (such as aluminoxane) and/or of the bulky anion
35 type.

- 4 -

The sheer abundance of similar disclosures in the same field is evidence to the fact that the ideal Ziegler-Natta type catalyst has not been found yet. There still exists a need for active, selective, versatile and stabile olefin polymerisation catalysts.

It has now been found that by replacing at least one five-membered (hetero)cyclopentadienyl ring of the known catalyst compositions as broadly described above with a six-membered (hetero)cyclohexadienyl ring, the (hetero)-atom being chosen from Group 13 to 16, a new and exceedingly versatile group of Ziegler-Natta type catalysts can be made. The introduction of an additional atom inside the ring offers more flexibility in tuning the properties of the catalysts.

The present invention in its broadest definition therefore relates to a catalyst composition, comprising a first component which is an organometallic compound of a metal M of Group 3 to 6 of the Periodic Table or the Lanthanide series and at least one (hetero)-cyclohexadienyl ligand of the general formula (I)



wherein A is an element chosen from Group 13 to 16 of the Periodic Table, R which can be connected to C or to A and which may form a bridge is independently hydrogen or an organic substituent which may contain one or more hetero-atoms and n is 3 plus the number of valencies of A, and a second component which acts as a co-catalyst. When R forms a bridge, it preferably connects the (hetero)-cyclopentadienyl ring to a ligand which in turn is connected to the metal M via at least one carbon atom.



The Periodic Table referred to is the Periodic Table of Elements according to the IUPAC 1988 notation (IUPAC Nomenclature of Inorganic Chemistry 1990, Blackwell Publ., London).

Preferably, the metal M is chosen from the group of titanium, zirconium and hafnium and A is chosen from the

- 5 -

group of boron, quaternary carbon, silicon, germanium, nitrogen, phosphorus, arsenic, oxygen and sulphur. More preferably, the metal M is titanium or zirconium and A is boron, quaternary carbon or silicon.

5 More in particular, the novel organometallic compounds according to the present invention have the general formula (II) or III



10 wherein $C_4AR'_n$ is a (hetero)cyclopentadienyl ring analogue to the (hetero)cyclohexadienyl ring $C_5AR'_n$, A, M and n are as defined above, each R', which can be the same or different, is chosen from hydrogen or an organic substituent (optionally containing one or more hetero-

15 atoms) having from 1 to 20 carbon atoms or two substituents together forming a fused C_4 - C_6 ring, R'' is a molecular fragment bridging two dienyl rings, each Q, which can be the same or different, which can be connected to a (hetero)cyclohexadienyl ring and two of

20 which can be interconnected to form a ring, is chosen from the group of hydrogen, aryl, alkyl, alkenyl, alkylaryl, arylalkyl, alkyloxyl, aryloxyl, alkylazanyl, arylazanyl, alkylthiyl, arylthiyl, alkylphosphanyl, arylphosphanyl, alkylazanedyl, arylazanedyl, alkylphosphanedyl, arylphosphanedyl, (hetero)cyclodienyl, indenyl or fluorenyl, any of which having from 1 to

25 20 carbon atoms and optionally being further substituted, or halogen, oxygen or sulphur,

p is 0 or 1,

30 m is 1, 2, 3 or 4,

q is 1, 2, 3 or 4

and m+1 plus the sum of the valencies of the Q groups equals the valency of the metal.

The bridging molecular fragment R'', when present, may

35 be positioned between two carbon atoms of heterocyclohexadienyl rings, between a carbon and a hetero-atom A,

- 6 -

or between two hetero-atoms A.

When R" is positioned between two carbon atoms it can be chosen from the wide range known for bridging two cyclopentadienyl, indenyl or fluorenyl rings, such as those disclosed in EP-B 129368, EP-A 336127 and EP-A 528287. Well-known examples thereof are the groups of C₁-C₄ radicals chosen from alkylene, dialkyl germanium or silicone, alkyl phosphine or amine and in particular 1,2-C₂H₄, 1,3-[(CH₂)₃], (CH₃)₂Si, (CH₃)₂Si(O)₂, 1,2-[(CH₃)₂Si]₂, 1,2-(CH₂)₂C₆H₄, (CH₃)₂C, 1,3-[(CH₃)₂Si]₂O, 1,2-{(CH₃)₂SiO} and 1,3-[(CH₃)₂Si(CH₂)₂].

The preferred metals M in the present invention are titanium, zirconium and hafnium.

The preferred Q radicals are hydrogen, methyl, ethyl, neopentyl, phenyl, benzyl and chloride.

The organometal complex according to the invention may contain from 1 to 5 of the above (hetero)cyclohexadienyl rings, with from zero to four (hetero)cyclopentadienyl rings and a number balancing the valency of the metal M of the reactive groups Q which may react with a cation. Therefore, organometal complexes containing only one (hetero)cyclohexadienyl ring are expressly within the scope of the invention. However, organometal complexes containing two (hetero)cyclohexadienyl rings, and those containing one such ring and one (hetero)cyclopentadienyl ring, are preferred.

The processing of the heterocyclohexadienyls to organometallic complexes can be done along traditional synthesis routes. For example, the (hetero)cyclohexadienyl anions can be prepared and reacted with zirconium tetrachloride to afford the bis-(hetero)cyclohexadienyl zirconium dichlorides.

Preferably in formula (II) or (III), M is chosen from the group of titanium, zirconium and hafnium, x is 1 or 2 and each Q which can be the same or different and two of

- 7 -

which can be interconnected to form a ring, is chosen from the group of hydrogen, aryl, alkyl, alkenyl, alkylaryl, arylalkyl, alkyloxyl, aryloxyl, alkylazanyl, arylazanyl, alkylthiyl, arylthiyl, alkylphospharyl, arylphospharyl, alkylazanediyl, arylazanediyl, alkylphosphanediyl, arylphosphanediyl, or cyclodienyl, any of which having from 1 to 20 carbon atoms and optionally being further substituted, or halogen, oxygen or sulphur, preferably from the group of hydrogen, halogen, R', NR'₂, PR'₂, OR' or SR', wherein R' is a hydrocarbyl or a cycloalkyl, optionally containing a heteroatom.

The co-catalyst can be a hydrocarbyl aluminium compound, in particular an aluminoxane.

Aluminoxanes are well known polymeric aluminium compounds, which can be represented by the general formulae (R-Al-O)_n which represents a cyclic compound, and R(R-Al-O)_n-AlR₂, which represents a linear compound. In these general formulae R is an alkyl, preferably of 1-5 carbon atoms and n is 1-100, especially 5-20. The aluminoxanes are suitably prepared by reacting water with trialkylaluminium compounds, whereby usually a mixture of the linear and cyclic polymer is obtained.

The best known aluminoxane is methyl aluminoxane (MAO). Also effective is a mixture of methyl aluminoxane and isobutyl aluminoxane (IBAO).

Preferred organometallic complexes according to the invention (formula II) for combination with aluminoxanes contain at least two groups Q, being the same or different and chosen from hydrogen, alkyl, aryl, alkenyl, alkylaryl, arylalkyl or cyclopentadienyl, any of which having from 1 to 20 carbon atoms and optionally being further substituted, or halide.



The molar ratio of the aluminoxane to the organometallic complex according to the invention may vary between wide ranges. Suitably the molar ratio is

- 8 -

within the range of from 2 to 10000, preferably from 50 to 2000, calculated as gram atoms of aluminium per gram atom of metal M.

5 The catalyst composition of the organometal complex of the present invention with the aluminoxane may be prepared prior to the contacting with the olefinically unsaturated compounds to be polymerised, or it may be prepared in situ i.e. in the presence of the feed. It is preferred to prepare this catalyst composition by mixing
10 together the two components in solution in a solvent such as toluene to form a liquid catalyst system.

Alternatively, the co-catalyst is a compound capable of providing a bulky and substantially non-coordinating anion $[An^-]$, which co-catalyst reacts with the organo-
15 metallic compound (first component) according to the invention to form an ionic compound of the general formula (IV) or (V)





20 wherein the components of the cation are as defined hereinbefore (formula II and (III) with the proviso that at least one Q is chosen from the group of hydrogen, aryl, alkyl, alkenyl, alkylaryl, arylalkyl or cyclo-
25 dienyl, any of which having from 1 to 20 carbon atoms and optionally being further substituted and $m+1$ plus the sum of the valencies of the Q groups equals the valency of the metal -1.

It will be appreciated that the ionic catalytic compound of formula (IV) and (V) can be produced in
30 different ways.

One way to produce the ionic catalytic compound is by reacting an organometallic complex according to the invention with a compound of a bulky and substantially non-coordinating anion. The cation associated with the
35 bulky anion should be capable of abstracting an anion from the organometal complex to form a (hetero)cyclo-

- 9 -

hexadienyl ionic compound, rendering itself neutral. An illustrative example for such reactions is:



5 whereby, when the cation $[\text{Cat}^+]$ is for example $[\text{PhNH}(\text{CH}_3)_2^+]$, $\{\text{CH}_3\text{-Cat}\}$ will become $\text{CH}_4 + \text{PhN}(\text{CH}_3)_2$, and when the cation is $[\text{Ph}_3\text{C}^+]$ $\{\text{CH}_3\text{-Cat}\}$ will become $\text{Ph}_3\text{C-CH}_3$.

10 Preferably, the bulky and substantially non-coordinating anion is a carborane anion, suitably a carborane anion of the formula $[\text{B}_{11}\text{CH}_{12}^-]$. Such carboranes are known and can be prepared by methods such as that of K. Shelly et al (J. Am. Chem. Soc. 107 1985 5955. Other bulky boron containing anions are of the
15 general formula $[\text{BR}_4^-]$, wherein R is C_6H_5 , C_6F_5 , 3,5- $(\text{CF}_3)_2\text{C}_6\text{H}_3$ and 4- FC_6H_4 , such as the tetra(perfluorophenyl)boron anion.


The cation is suitably a proton-donating cation, preferably a quaternary ammonium cation such as a
20 trialkylammonium cation, for example tri-n-butylammonium cation. Alternatively, a cation may be used which is not proton-donating, such as a metal cation e.g. a silver ion, or a triphenylcarbonium ion.

The catalyst composition may be formed by mixing
25 together the organometallic complex and the compound of the bulky and substantially non-coordinating anion, preferably in solution in a suitable non-polar solvent such as toluene, chlorobenzene, an alkane or an alkene, to form a liquid catalyst system. The two components are
30 generally employed in substantially equimolar amounts, although the molar ratio of the first component to the second component may vary within the range of from 0.1 to 5.0. Such a quantity of the catalyst system is usually employed in the reaction mixture as to contain from 10^{-1}
35 to 10^{-7} gram atoms, in particular from 10^{-3} to 10^{-5} gram atoms, of the metal per mole of olefinically unsaturated

- 10 -

hydrocarbon to be reacted.

Another way to produce the ionic catalyst is by reacting a organometallic compound according to the invention with a neutral, strongly Lewis acidic compound which is capable of abstracting one of the radicals Q of the organometallic compound, thereby also contributing a bulky and substantially non-coordinating anion to the completed catalyst compound. An illustrative example of such a reaction, related to the procedure described by X. Yang et al., J. Am. Chem. Soc. 113 1991 3623, is:



Although not required for catalytic activity, further components may be added to the catalytic composition according to the invention, for example in order to increase the solubility or the lifetime of the composition. For the ionic catalytic compositions, organoaluminium compounds in relatively small amounts are efficient solubilising and scavenging agents. Examples of such organoaluminium compounds are trimethylaluminium, triethylaluminium, tri-isopropylaluminium, tri-isobutylaluminium, triphenylaluminium and diethylaluminium chloride.

The complete catalyst compositions according to the invention can be used in solution. Alternatively, the catalyst composition can be loaded on a solid carrier, in particular an inorganic oxide such as silica, alumina, silica/alumina, titania, zirconia, magnesia and the like, but resinous support materials such as polyolefins can also be used. Suitable supports are the materials, composed of aluminosilicate and silica and marketed for example by WITCO GmbH, Bergkamen, Germany. Both neutral and ionic catalytic compositions as defined hereinbefore, containing the (hetero)cyclohexadienyl organometallic complexes according to the invention, can be combined with these materials to form solid catalytically active

- 11 -

compositions.

A further aspect of the present invention is the process of (co)oligomerisation or (co)polymerisation of one or more olefinically unsaturated hydrocarbon(s) in the presence of catalyst compositions as defined hereinbefore.

The (co)oligomerisation or (co)polymerisation reaction according to the invention can be carried out in the liquid phase. When the catalyst compositions are loaded on an inert carrier the reaction is heterogeneous and can also be carried out in the gas phase. The reaction can be carried out in batch or continuous operation.

The oligomerisation or polymerisation reaction is generally, although not necessarily, carried out in an inert liquid which is suitably also the solvent for the catalyst components. The reaction is suitably carried out at an elevated temperature, preferably in the range of from 20 to 175 °C, more preferably at 50 to 150 °C. The reaction is suitably carried out under conditions of moderately elevated pressure, preferably in the range of from 100 to 10000 kPa, more preferably from 500 to 6000 kPa. The optimum conditions of temperature and pressure used in a particular reaction system in order to maximise the yield of the desired oligomers or polymers can be readily established by those skilled in the art.

The starting reactants may be supplied to the reactor together with an inert diluent, such as nitrogen or helium when the reactant is gaseous, and a liquid solvent, e.g. the same solvent as that of the catalyst components, when the reactant is in the liquid form.

The reaction is preferably carried out in the absence of air or moisture.

Reaction times of from 1 minute to 5 hours have been found to be suitable, depending on the activity of the catalyst system and on the reaction conditions. When the

- 12 -

reaction is homogeneous it can be terminated by adding to the reaction mixture a conventional catalyst deactivating agent (proton donor) such as water, methanol, or another alcohol. Alternatively, the reaction can simply be terminated by the introduction of air.

The products of the reaction are typically mixtures. They may be suitably recovered by separation techniques known in the art. If desired, unconverted starting material and products having a molecular weight outside the desired molecular weight may be recovered, processed if necessary and recycled to be used as starting material in a subsequent oligomerisation reaction.

The present invention has an outstanding versatility and the products may vary very widely in their molecular weight which may be from that of dimers of the starting olefins to polymers of over 1000000 daltons, and in their molecular composition. The properties of the products may be controlled by a proper choice of the catalyst composition, the starting material(s) and the reaction conditions. Also, when the presence of an unsaturated end group in the product is not a requirement, the molecular weight thereof can be controlled by adding hydrogen to the reaction mixture.

One example of a group of products are alkenes which are preferentially linear alpha alkenes having a chain length within the range of 5 to 24 carbon atoms, of which those having between 6 and 10 carbon atoms in the chain are currently particularly preferred. They are in great demand as intermediates for the preparation of detergents, lubricant additives and polyolefins.

Another example of a group of products are liquid atactic polymers, preferably having an olefinically unsaturated end group, more preferably a vinylidene end group, and a number average molecular weight of from 300 to 10000 daltons. Such liquid atactic vinylidene polymers, in particular those which are prepared from

- 13 -

propylene, are useful as intermediates for the preparation of dispersants for lubricating oil compositions.

Yet another group of products are solid polymers.

5 The invention will be further illustrated by the following Examples.

EXAMPLE A PREPARATION OF CATALYST PRECURSORS

A-1, Preparation of pentamethylcyclopentadienyl 1-methyl-1-boracyclohexadienyl zirconium dichloride, $\text{Cp}^*(\text{C}_5\text{H}_5\text{BMe})\text{ZrCl}_2$.

10 Lithium 1-methyl-1-boracyclohexadienyl, $\text{Li}[\text{C}_5\text{H}_5\text{BMe}]$ was prepared according to Herberich et al., *Organo-metallics* 1995, 14, 471-480. $\text{Li}[\text{C}_5\text{H}_5\text{BMe}]$, 150 mg, was dissolved in diethylether, 20 ml, and to the solution pentamethylcyclopentadienyl zirconium trichloride, Cp^*ZrCl_3 , 500 mg, was added slowly. The reaction mixture was stirred for 24 hours and subsequently the volatiles removed under vacuum. The residue was dissolved in dichloromethane and the precipitate filtered off after centrifugation. The remaining solution was evaporated to dryness and the resulting solid material, A-1, isolated, 90 mg.

20 $^1\text{H-NMR}$ (CD_2Cl_2 , δ , ppm): 7.3-7.45(dd), 6.2(d), 6.07(t) (all resonances show additional small couplings), 2.0(s), 0.75(s).

25 $^{11}\text{B-NMR}$ (CD_2Cl_2 , δ , ppm): 45.87.

A-2, Preparation of cyclopentadienyl 1-methyl-1-boracyclohexadienyl zirconium dichloride, $\text{Cp}(\text{C}_5\text{H}_5\text{BMe})\text{ZrCl}_2$.

30 Lithium 1-methyl-1-boracyclohexadienyl, $\text{Li}[\text{C}_5\text{H}_5\text{BMe}]$ was prepared according to Herberich et al., *Organo-metallics* 1995, 14, 471-480. $\text{Li}[\text{C}_5\text{H}_5\text{BMe}]$, 50 mg, was dissolved in diethylether and to the solution cyclopentadienyl zirconium trichloride, CpZrCl_3 , 134 mg, was added slowly. The reaction mixture was stirred for 4 hours and subsequently the volatiles removed under vacuum. The residue was dissolved in dichloro-

- 14 -

methane/pentane mixture and the precipitate filtered off after centrifugation. The remaining solution was evaporated to dryness and the resulting solid material, A-2, isolated, 130 mg.

5 $^1\text{H-NMR}$ (CD_2Cl_2 , δ , ppm): 7.78-7.74(dd), 6.76(m), 6.48(s), 6.22(d), 0.98(s)

$^{11}\text{B-NMR}$ (CD_2Cl_2 , δ , ppm): 45.52.

A-3, Preparation (in situ) of bis-(1-methyl-1-boracyclohexadienyl) zirconium dichloride,
10 $(\text{C}_5\text{H}_5\text{BMe})_2\text{ZrCl}_2$.

Lithium 1-methyl-1-boracyclohexadienyl, 10 mg, and zirconium tetrachloride, 11.9 mg, were reacted in C_6D_6 , 2 ml. The reaction mixture was stirred for two hours during which time a fine precipitate and yellow solution
15 formed. The reaction mixture was centrifuged, the solution decanted, and the solids washed with C_6D_6 , 1 ml. The C_6D_6 solutions were combined and analyzed by NMR. The data are in agreement with the compound being A-3.

$^1\text{H-NMR}$ (C_6D_6 , δ , ppm): 7.20-7.08(m), 6.19-5.98(m),
20 0.98(s).

$^{11}\text{B-NMR}$ (C_6D_6 , δ , ppm): 45.08.

A-4, Preparation of pentamethylcyclopentadienyl 1-sila-1,1-dimethyl-2,3,4,5-tetraphenylcyclohexadienyl zirconium dichloride, $\text{Cp}^*(1\text{-Si-1,1-Me}_2\text{-2,3,4,5-Ph}_4\text{C}_5\text{H})\text{ZrCl}_2$.

25 1-Sila-1,1-dimethyl-2,3,4,5-tetraphenylcyclohexadienyl lithium was prepared by reaction of 1-sila-1,1-dimethyl-2,3,4,5-tetraphenylcyclohexadiene (prepared from 1,4-dilithio-1,2,3,4-tetraphenylbutadienediyl and chloromethyldimethylchlorosilane, $\text{Me}_2\text{Si}(\text{Cl})\text{CH}_2\text{Cl}$, see
30 Nakadaira et al *J. Am. Chem. Soc.* **1974**, *96*, 5621-5622) with *n*-BuLi in THF at room temperature. Reaction of the silacyclohexadienyl anion, 0.15 g, with an equivalent amount of pentamethylcyclopentadienyl zirconium trichloride, Cp^*ZrCl_3 , in benzene, 30 ml, at room
35 temperature. After stirring the reaction mixture for one hour the generated precipitate was removed by centri-

- 15 -

fugation and decanting the supernatant mother liquor. From this solution the volatiles were evaporated off and the remaining product was washed with hexane. The solid obtained after drying was isolated and characterized by NMR and identified as A-4.

^1H -NMR (C_6D_6 , δ , ppm): 7.8-7.2(arom.), 6.83, 6.09, 2.75, 1.85, 0.49, 0.30.

A-5, Preparation of pentamethylcyclopentadienyl 1-sila-1,1-dimethyl-dibenzocyclohexadienyl zirconium dichloride, $\text{Cp}^*(1\text{-Si-1,1-Me}_2\text{C}_{13}\text{H}_9)\text{ZrCl}_2$.

1-Sila-1,1-dimethyl-dibenzocyclohexadiene (Fig. 1) was prepared by reaction of *o,o'*-dilithiobiphenyl with one equivalent of chloromethyldimethylchlorosilane, $\text{Me}_2\text{Si}(\text{Cl})\text{CH}_2\text{Cl}$ in THF at -78°C . The reaction mixture was slowly warmed to room temperature and subsequently all volatiles were removed under vacuum.




Fig. 1

The obtained product was characterized by NMR which indicated that the product was almost pure silacyclohexadiene with structure shown in the Figure. The so obtained silacyclohexadiene was converted into the corresponding silacyclohexadienyl anion by reaction with one equivalent of *n*-BuLi in THF at room temperature. The anion was isolated and characterized by NMR. Reaction of the anion, 0.25 g, with one equivalent of pentamethylcyclopentadienyl zirconium trichloride, Cp^*ZrCl_3 , 0.2 g, in a similar procedure as described for A-4, afforded A-5 which was characterized by NMR.

^1H -NMR (C_6D_6 , δ , ppm): 7.6-6.7(arom.), 3.79, 1.74, 0.63, 0.24.

A-6, Preparation of pentamethylcyclopentadienyl 1-*t*-butyl-1-boracyclohexadienyl zirconium dichloride.

- 16 -

Lithium 1-*t*-butyl-1-boracyclohexadienyl, Li[C₅H₅B-*t*-Bu] was prepared according to Herberich et al., *Organometallics* **1995**, 14, 471-480. Li[C₅H₅B-*t*-Bu], 10 mg, was dissolved in diethylether, 2 ml, and to the solution pentamethylcyclopentadienyl zirconium tri-chloride, Cp*ZrCl₃, 24 mg, was added slowly. The reaction mixture was stirred for 1 hour and subsequently the volatiles removed under vacuum. The residue was dissolved in benzene and the precipitate filtered off after centrifugation. The remaining solution was evaporated to dryness and the resulting solid material, A-6, isolated, 21 mg.

¹H-NMR (C₆D₆, δ, ppm): 7.1-7.2(m), 6.4(d), 5.4(t) (all resonances show additional small couplings), 1.7(s), 1.35(s).

A-7, Preparation of cyclopentadienyl 1-*t*-butyl-1-boracyclohexadienyl zirconium dichloride.

Similar to the procedure described for A-6 but with CpZrCl₃, 19 mg, as a starting material and a reaction time of 2 hours. Yield was 23 mg of A-7.

¹H-NMR (C₆D₆, δ, ppm): 7.1-7.2(m), 6.35(d), 5.9(s), 5.85(t), 1.20(s).

A-8, Preparation of bis-(1-*t*-butyl-1-boracyclohexadienyl) zirconium dichloride.

Similar to the preparation of A-6 but with ZrCl₄, 25.9 mg, and 30 mg of 1-*t*-butyl-1-boracyclohexadienyl as starting materials and a reaction time of 2 hours. Yield was 35 mg.

¹H-NMR (C₆D₆, δ, ppm): 7.0-7.1(m), 6.20(d), 5.75(t), 1.05(s).

EXAMPLE B POLYMERISATION EXPERIMENTS

B-1: Propene polymerisations

Description of polymerisation experiments.

A 1 ltr autoclave containing 200 ml of toluene and 3.5 ml of a solution containing 10% MAO was charged with 600 kPa of propene at 45 °C. The system was allowed to

- 17 -

reach equilibrium while the pressure was kept at 600 kPa. Subsequently, catalyst precursor, 0.01 mMol dissolved in 10 ml of toluene were added to the autoclave by means of a catalyst injection system. After the reaction was stopped by release of excess propylene, the autoclave contents were treated with a small amount of water, filtrated to remove the solids, dried over MgSO_4 , the volatiles removed under vacuum, and the products analysed. Alternatively, in the case of low molecular weight products, the reaction contents after reaction were weighed and the yields were calculated by subtraction of the weight of the reaction components at the start of the reaction.

B-1-1: Catalyst precursor A-1, $\text{Cp}^*(\text{C}_5\text{H}_5\text{BMe})\text{ZrCl}_2$, 0.01 mMol.

Reaction time was 60 minutes. The yield of product was 92 g. NMR analysis of the product was in agreement with an atactic product of molecular weight 250. (Turnover=200.000 Mol C_3 =/Mol Zr.hr.)

B-1-2: Catalyst precursor A-2, $\text{Cp}(\text{C}_5\text{H}_5\text{BMe})\text{ZrCl}_2$, 0.005 mMol.

Reaction time was 60 minutes. The yield of product was 56 g. NMR analysis of the product was in agreement with an atactic product of molecular weight 143. (Turnover=268.000 Mol C_3 =/Mol Zr.hr.)

B-1-3: Catalyst precursor A-3, $(\text{C}_5\text{H}_5\text{BMe})_2\text{ZrCl}_2$, 1/3 of the product prepared *in situ* as described under A-3.

Reaction time was 60 minutes. Yield of product 2.1 g. NMR analysis of the product was in agreement with an atactic product of molecular weight 160. (Turnover=5.000 Mol C_3 =/Mol Zr.hr.)

B-1-4: Catalyst precursor A-2, $\text{Cp}(\text{C}_5\text{H}_5\text{BMe})\text{ZrCl}_2$, 0.005 mMol.

Instead of cocatalyst MAO a cocatalyst was used which was a 1:1 mixture of MAO and hexameric *iso*-butylalumoxane. The Zr:Al ratio was kept at 1:500.

- 18 -

Reaction time was 60 minutes. The yield of product was 43.6 g. NMR analysis of the product was in agreement with an atactic product of molecular weight 250.

(Turnover=194.000 Mol C₃=/Mol Zr.hr.)

5 B-1-5 (Comparative example): Catalyst precursor Cp₂ZrCl₂,
0.005 mMol.

Reaction time was 60 minutes. Yield of product was 18 g. NMR analysis of the product was in agreement with an atactic product of molecular weight 910.

10 (Turnover=85.000 Mol C₃=/Mol Zr.hr.)

B-1-6: Catalyst precursor A-6, Cp*(C₅H₅B-t-Bu)ZrCl₂,
0.01 mMol.

Reaction time was 60 minutes. The yield of product was 23 g. NMR analyses of the product was in agreement with an atactic product with molecular weight of 250.

15 (Turnover=56.000 Mol C₃=/Mol Zr.hr)

B-1-7: Catalyst precursor A-7, Cp(C₅H₅B-t-Bu)ZrCl₂,
0.013 mMol.

Reaction time was 60 minutes. The yield of product was 308 g. NMR analyses of the product was in agreement with an atactic product with molecular weight of 143.

20 (Turnover=570.000 Mol C₃=/Mol Zr.hr)

B-1-8: Catalyst precursor A-8, (C₅H₅B-t-Bu)₂ZrCl₂,
0.01 mMol.

25 Reaction time was 60 minutes. Yield of product 3.0 g. NMR analyses of the product was in agreement with an atactic product of molecular weight 160.

(Turnover=7.000 Mol C₃=/Mol Zr.hr)

B-2: Ethylene polymerizations

30 Performed in a procedure similar to propylene polymerizations except that ethylene at 300 kPa was used instead of propene, and the products were isolated by filtration of the reactor contents.

B-2-1: Catalyst precursor A-1, Cp*(C₅H₅BMe)ZrCl₂,
35 0.008 mMol.

Reaction time was 7 minutes. The yield of product was

- 19 -

9.8 g. Melting point of polymer was 114 °C and M_n , determined by GPC, was 1910. (Turnover=385.000 Mol C_2 =/Mol Zr.hr.)

5 B-2-2: Catalyst precursor A-4, $Cp^*(1-Si-1,1-Me_2-2,3,4,5-Ph_4C_5H)ZrCl_2$, 0.006 mMol.

Reaction time was 30 minutes. The yield of product was 0.8 g, melting point 116.8 °C. (Turnover=6.000 Mol C_2 =/Mol Zr.hr.)

10 B-2-3: Catalyst precursor A-5, $Cp^*(1-Si-1,1-Me_2C_{13}H_9)ZrCl_2$, 0.01 mMol.

Reaction time was 30 minutes. The yield of product was 9.9 g, melting point 123.9 °C. (Turnover=71.000 Mol C_2 =/Mol Zr.hr.)

15 B-2-4: Catalyst precursor A-7, $Cp(C_5H_5B-t-Bu)ZrCl_2$, 0.006 mMol.

Reaction time was 15 minutes at a pressure of 100kPa. The yield of product was 19.6 g. of which 16.6 g. insoluble in toluene at room temperature. Melting point of the latter polymer was 109 °C and M_n 1080 (NMR). ^{13}C -
20 NMR showed the presence of branching in the polymer backbone. Calculated amount of branching: C_2 0.22, C_4 0.15, and C_6 and higher 0.12 per chain. Unsaturated end groups are vinyl and alkylidene olefins in a ratio of 3.5:1. The soluble product had M_n of 350 (NMR) and
25 similar ^{13}C -NMR characteristics as the insoluble fraction. (Turnover=437.000 Mol C_2 =/Mol Zr.hr.)

B-3: Ethylene/1-octene copolymerization

Similar to ethylene polymerizations except that octene-1 was introduced in the reactor as part of the
30 solvent. The total volume of solvent was kept constant.

B-3-1: Catalyst precursor A-1, $Cp^*(C_5H_5BMe)ZrCl_2$, 0.01 mMol.

Amount of 1-octene 20 ml, reaction time was 6.5 minutes. The yield of copolymer product was 29.4 g.
35 Melting point 116 °C. M_n determined by GPC, was 1290. (Turnover=1.000.000 Mol C_2 =/Mol Zr.hr assuming ethylene

- 20 -

as the only monomer.)

B-3-2: Catalyst precursor A-2, $\text{Cp}(\text{C}_5\text{H}_5\text{BMe})\text{ZrCl}_2$,
0.01 mMol.

5 Amount of 1-octene 20 ml, reaction time was
6.5 minutes. The yield of copolymer product was 40 g.
Melting point 114 °C. Mn, determined by GPC, was 1310.
(Turnover= 1.330.000 Mol C_2 =/Mol Zr.hr assuming ethylene
as the only monomer.)

10 B-3-3 (Comparative example): Catalyst precursor Cp_2ZrCl_2 ,
0.01 mMol.

Amount of 1-octene 20 ml, reaction time 6.5 minutes.
The yield of copolymer product was 30 g. Melting point
116.5 °C. Mn, determined by GPC, was 6600. (Turnover=
1.020.000 Mol C_2 =/Mol Zr.hr assuming ethylene as the only
15 monomer.)

B-4: 1-Octene polymerization


B-4-1: Catalyst precursor A-2, $\text{Cp}(\text{C}_5\text{H}_5\text{BMe})\text{ZrCl}_2$,
0.01 mMol.

20 1-Octene, 5 ml, were mixed with 5 mMol MAO in
toluene, 11 ml. After 15 minutes stirring at room
temperature, catalyst precursor A-2, 3.4 mg dissolved in
1.5 ml toluene, was added in one shot. The reaction
mixture was stirred 2 hour and analyzed by GC and NMR.
The analyses showed quantitative conversion of starting
25 1-octene and formation of an oligomeric product with
average molecular weight of 250 and a 2,2-disubstituted
olefinic end-group.

- 21 -

C L A I M S

1. A catalyst composition comprising a first component which is an organometallic compound of a metal M of Group 3 to 6 of the Periodic Table or the Lanthanide series and at least one (hetero)cyclohexadienyl ligand of the general formula (I)





wherein A is an element chosen from Group 13 to 16 of the Periodic Table, R which can be connected to C or to A and which may form a bridge is independently hydrogen or an organic substituent which may contain one or more hetero-atoms and n is 3 plus the number of valencies of A, and a second component which acts as a co-catalyst.

2. A catalyst composition according to claim 1, characterized in that A forms a bridge to a ligand which in turn is coordinated to the metal M via at least one carbon atom.

3. A catalyst composition wherein the first component is an organometallic compound according to claim 1 or 2, characterized in that the metal M is chosen from the group of titanium, zirconium and hafnium and A is chosen from the group of boron, quaternary carbon, silicon, germanium, nitrogen, phosphorus, arsenic, oxygen and sulphur.

4. A catalyst composition wherein the first component is an organometallic compound according to any one of claims 1-3, characterized in that it is of the general formula (II) or (III).



wherein A, M and n are as defined above, each R', which can be the same or different, is chosen from hydrogen or an organic substituent (optionally containing one or more

- 22 -

- hetero-atoms) having from 1 to 20 carbon atoms or two substituents together forming a fused C₄-C₆ ring, R" is a molecular fragment bridging two dienyl rings, each Q, which can be the same or different and two of which can be interconnected to form a ring, is chosen from the group of hydrogen, aryl, alkyl, alkenyl, alkylaryl, arylalkyl, alkyloxyl, aryloxyl, alkylazanyl, arylazanyl, alkylthioly, arylthioly, alkylphosphalyl, arylphosphalyl, alkylazanediyl, arylazanediyl, alkylphosphanediyl, arylphosphanediyl, (hetero)cyclodienyl, indenyl or fluorenyl, any of which having from 1 to 20 carbon atoms and optionally being further substituted, or halogen, oxygen or sulphur,
- p is 0 or 1,
- m is 0, 1, 2, 3 or 4,
- q is 1, 2, 3 or 4
- and m+1 plus the sum of the valencies of the Q groups equals the valency of the metal.
5. A catalyst composition according to claim 4, wherein m is 1 and p is 0.
6. A catalyst composition according to any one of claims 1-5, characterized in that the co-catalyst is a hydrocarbyl aluminium compound.
7. A catalyst composition according to claim 6, characterized in that the co-catalyst is an aluminoxane.
8. A catalyst composition according to any one of claims 1-5, characterized in that the co-catalyst is a compound capable of providing a bulky and substantially non-coordinating anion [An⁻], which co-catalyst reacts with the organonometallic compound according to any one of claims 1-5 to form an ionic compound of the general formula (IV) or (V)
- $$[(C_5AR'n-p)_mR''_p(C_5AR'n-p)MQ_q^+][An^-], \quad (IV)$$
- $$[(C_4AR'n-p)_mR''_p(C_5AR'n-p)MQ_q^+][An^-], \quad (V)$$
- wherein the components of the cation are as defined hereinbefore (formula II) with the proviso that at least

- 23 -

one Q is chosen from the group of hydrogen, aryl, alkyl, alkenyl, alkylaryl, arylalkyl or cyclodienyl, any of which having from 1 to 20 carbon atoms and optionally being further substituted and m+1 plus the sum of the valencies of the Q groups equals the valency of the metal -1.

9. A catalyst composition according to claim 8, characterized in that the anion [An-] is an organoboron compound.

10. A catalyst composition according to any one of claims 1-9, characterized in that it is loaded on a solid, inert carrier material.

11. A process for the (co)oligomerisation or (co)polymerisation of olefinically unsaturated hydrocarbons, characterized in that it is performed in the presence of a catalyst composition according to any one of claims 1-10.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 96/02845

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07F17/00 C08F10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07F C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JOURNAL OF ORGANOMETALLIC CHEMISTRY, vol. 187, 1980, pages 31-42, XP002012753 MARKL, G. ET AL.: "CIS-DICARBONYL-ETA.-1-SILACYCLOHEXA-2,4-DIEN-MOLYBDAN(0) UND -WOLFRAM(0)-KOMPLEXE, DIMERE 4-ALKYL-1-SILACYCLOHEXA-1,3-DIENE MIT 1,3-DISILACYCLOBUTANSTRUKTUR, UND 2,2'-DI-1-SILACYCLOHEXA-2,4-DIENE" see the whole document ---	1
X	CHEMISCHE BERICHTE, vol. 112, 1979, pages 607-624, XP002012754 HERBERICH, G.E. ET AL.: "KATIONISCHE BORINATOMETALL-KOMPLEXE. NUCLEOPHILE ADDITIONEN UND RINGKONTRAKTIONEN" see the whole document --- -/--	1



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but which may be used to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

6 September 1996

Date of mailing of the international search report

19.09.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rinkel, L

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 96/02845

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 101, 1979, pages 1053-1054, XP002012755 DATTA, S. ET AL.: "TETRIARY PHOSPHINE COMPLEXES OF LOW-VALENT ZIRCONIUM AND THEIR PROPERTIES" see the whole document ---	1
X	CHEMICAL ABSTRACTS, vol. 107, no. 13, 28 September 1987 Columbus, Ohio, US; abstract no. 115719m, DIMAURO, P.T. ET AL.: "NEW SANDWICH COMPLEXES CONTAINING 6,6-DIMETHYLCYCLOHAXADIENYL (DMCH): (DMCH)2M (M = TI, V, CR, FE) AND (DMCH)2M-CO" page 642; XP002012756 see abstract & ORGANOMETALLICS, vol. 6, no. 9, 1987, pages 1947-1954, -----	1