

## (19) AUSTRALIAN PATENT OFFICE

(54) Title  
Fluorinated treatment for soil resistance

(51)<sup>6</sup> International Patent Classification(s)

<b>D06M</b> 13/188	8BMEP	<b>D06M</b>
(2006.01)	13/262	
<b>D06M</b> 13/256	20060101ALI2005100	
(2006.01)	8BMEP	<b>D06M</b>
<b>D06M</b> 13/262	13/292	
(2006.01)	20060101ALI2005100	
<b>D06M</b> 13/292	8BMEP	<b>D06M</b>
(2006.01)	15/277	
<b>D06M</b> 15/277	20060101ALI2005100	
(2006.01)	8BMEP	<b>D06M</b>
<b>D06M</b> 15/295	15/295	
(2006.01)	20060101ALI2005100	
<b>D06M</b> 15/33 (2006.01)	8BMEP	<b>D06M</b>
<b>D06M</b> 15/576	15/33	
(2006.01)	20060101ALI2005100	
<b>D06M</b> 13/188	8BMEP	<b>D06M</b>
20060101AFI2005100	15/576	
8BMEP	<b>D06M</b>	20060101ALI2005100
13/256	8BMEP	
20060101ALI2005100	PCT/US2003/023815	

(21) Application No: 2003257022 (22) Application Date: 2003.07.29

(87) WIPO No: WO04/011714

(30) Priority Data

(31) Number (32) Date (33) Country  
10/207,405 2002.07.29 US

(43) Publication Date : 2004.02.16

(43) Publication Journal Date : 2004.03.25

(71) Applicant(s)

E.I. Du Pont De Nemours and Company

(72) Inventor(s)

Materniak, Joyce Monson, Murphy, Peter Michael

(74) Agent/Attorney

Callinans, 1193 Toorak Road, Camberwell, VIC, 3124

(56) Related Art

US 5728669

US 5861365

US 4043923

WO 1995/034631

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date  
5 February 2004 (05.02.2004)

PCT

(10) International Publication Number  
WO 2004/011714 A3

(51) International Patent Classification<sup>2</sup>: D06M 15/576, 15/33, 15/295, 15/277, 15/256, 13/262, 13/188, 13/292

(21) International Application Number:  
PCT/US2003/023815

(22) International Filing Date: 29 July 2003 (29.07.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

10/207,405 29 July 2002 (29.07.2002) US

(71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).

(72) Inventors: MATERNIAK, Joyce, Monson; 117 Cheltenham Road, Hockessin, DE 19707 (US). MURPHY, Peter, Michael; 5024 Branston Road, Ooltewah, TN 37363 (US).

(74) Agent: MAYER, Nancy, S.; E.I. Du Pont de Nemours And Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, DE 19805 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, IT, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report  
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:  
1 April 2004

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

A3

(54) Title: FLUORINATED TREATMENT FOR SOIL RESISTANCE

(57) Abstract: A soil resist agent comprising a dispersion of a polyfluoro organic compound having at least one of a urea, urethane or ester linkage, and at least one anionic surfactant wherein the ratio of polyfluoro organic compound to surfactant is from about 0.075:1.0 to about 5:1 for treatment of fibrous substrates is disclosed

TITLE

Fluorinated Treatment for Soil Resistance

BACKGROUND OF THE INVENTION

The following definitions are used by the American Association of  
5 Textile Chemists & Colorists (AATCC) in the AATCC Technical Manual,  
Vol. 77, pp. 409 and 413, 2002, American Association of Textile Chemists  
and Colorists, Research Triangle Park, NC.

"Detergent" is a cleaning agent containing one or more surfactants  
as the active ingredient(s). "Soil" is dirt, oil, or other substances not  
10 normally intended to be present on a substrate, such as a textile material.  
"Soiling" in textiles is a process by which a textile substrate becomes more  
or less uniformly covered with, or impregnated with, soil. "Soil resist  
agent" is a material applied to, or incorporated in, carpet face fiber that  
15 retards and/or limits the build-up of soil. "Surfactant" is a soluble or  
dispersible material that reduces the surface tension of a liquid, usually  
water.

The same source defines "Textile floor covering" as "an article  
having a use-surface composed of textile material and generally used for  
covering floors." Hereinafter the term "carpet" is used to describe such  
20 textile floor covering.

The Kirk-Othmer Concise Encyclopedia of Chemical Technology,  
3<sup>rd</sup> Edition, John Wiley & Sons, New York NY, 1985 in a discussion of  
"Surfactants and Detergent Systems" at p. 1142 states "The term  
detergent is often used interchangeably with surfactant."

25 In the prior art, residual oils or detergents left on the fiber of a  
carpet after manufacture, after the application of soil resist agents, or after  
carpet cleaning by shampooing, have been extensively reported as

causes of subsequent soiling. For instance, W. F. Taylor and H. J. Demas "The Why's of Carpet Soil", Textile Ind., November 1968, pp. 83 – 87 comment at p. 83 – 84: "Severe soiling may occur if the fiber contains an oily film. This phenomena is responsible for most resoiling problems after a carpet has been shampooed where the detergent is not completely removed. Improper lubricants on the fiber can cause this effect, as will airborne greases which settle onto the carpet surface." The authors equate oils and detergents as causes. The authors continue to list factors "thought to affect soiling of nylon carpets" and state (p. 87) "The effect of residual oily materials causing increased soiling of textile materials is well documented in the literature. Severe soiling may occur if the fiber contains an oily film." Elsewhere, W. Postman, in "Spin Finishes Explained", Textile Research Journal, Vol. 50 #7, 444 - 453 (July 1980), notes at p. 445, that "... since poor scourability can cause dyeing problems and potential soiling spots, lubricants must come off the yarn under mild scouring conditions ...."

Technical information for the carpet manufacturing trade is replete with warnings about the worsened soiling associated with, and attributed to, excessive amounts of oils or detergents. Current World Wide Web sites include:

1. [http://www.carpetbuyershandbook.com/common\\_cleaning\\_challenges.htm](http://www.carpetbuyershandbook.com/common_cleaning_challenges.htm)

Carpet Buyers Handbook web site (accessed July 25, 2002):  
"Often resoiling can be attributed to detergent residues left behind during cleaning. Detergents, by design, attract soil. By leaving detergent in carpet after cleaning, detergents rapidly attract soil."

2. <http://www.hoovercompany.com/ftp/cguide.pdf>

Hoover Consumer Guide to Carpet Cleaning web site (accessed July 25, 2002):

"Some shampoos contain oil which can contribute to resoiling; ..."

3. [http://www.carpet-rug.com/drill\\_down\\_2.cfm?page=14&sub=3](http://www.carpet-rug.com/drill_down_2.cfm?page=14&sub=3)
- 5 Carpet and Rug Institute (CRI) web site (accessed July 25, 2002):

"Rinse all detergent from the carpet to prevent accelerated resoiling."
4. <http://cms.3m.com/cms/US/en/2-78/iFeRkFQ/view.jhtml>
- 10 3M web site (accessed July 25, 2002):

"Shampooing may not only leave behind a soapy residue that often masks the carpet's protective finish, but it can attract and hold dirt."
- 15 DuPont Antron\* web site, from Section C, Deep Cleaning (accessed July 25, 2002):

"You also need to be aware that some methods use detergents that cause resoil. This happens when detergents remain on the fiber surface after cleaning. These detergents will continue to attract soil causing the carpet to look dirty."

The manufacturers of dispersed soil resist formulations have consequently striven to use only enough dispersing agent in their formulations to provide a stable dispersion in the formulation as shipped.

25 The results of this restriction are shown in Table 1 as the ratio of fluorochemical to dispersant in typical commercial carpet soil resist formulations. The calculated weight ratio of fluorochemical:dispersing agent ranges from 14:1 to 30:1 in Table 1.

Table 1. Conventional Surfactant Ratios in Commercial Soil Resists.

Prior Art Composition (Reference)	Fluoro-chemical Ingredient	Dispersant	Fluorochemical: Dispersant Ratio
Soil Resist 1 <sup>(a)</sup>	28%	2%	14:1
Soil Resist 2 <sup>(b)</sup>	22.6%	1.4%	16:1
Soil Resist 3 <sup>(c)</sup>	9.1%	0.3%	30:1
Soil Resist FCT-3 <sup>(d)</sup>	201.6 g	11 g	18.3:1
Soil Resist FCT-7 <sup>(d)</sup>	50 g	2.5 g	20:1
Soil Resist FCT-8 <sup>(d)</sup>	50 g	2.5 g	20:1

(a) Soil Resist 1 is an anionically dispersed fluorinated polyurethane soil resist prepared according to Example 1 in US Patent 5,414,111.

5 (b) Soil Resist 2 is an anionically dispersed fluorinated polyurethane soil resist prepared according to Example 1 in US Patent 5,411,766.

(c) Soil Resist 3 is an anionically-dispersed blend of fluorinated soil resist, prepared according to Example 2 in US Patent 3,923,715, except that an equivalent amount of hexamethylene diisocyanate was used instead of 1-methyl-2,4-diisocyanatobenzene in the synthesis of the 10 perfluoroalkyl citrate urethane. The citrate urethane was mixed with the poly(methylmethacrylate) latex as described in Example 2 therein.

(d) Soil Resists FCT-3, FCT-7, and FCT 8 are described in US Patent 5,714,082.

15 Typically, soil resist formulations are shipped in a concentrated form, and diluted with water at the site of application. Commercially, dispersing agent levels in such formulations are kept close to the minimum needed to assure dispersion stability during shipment, dilution, and use.

It is desirable to have improved soil resist agents for treatment of fibrous substrates such as carpets during manufacture, and for use in or after cleaning agents used on soiled carpets. Such an improved soil resist agent would provide better resistance to soiling.

5 The present invention comprises specific soil resist agents formulated in dispersions containing substantially more surfactants than are necessary to assure a stable dispersion. Despite teachings that residual oils or surfactants lead to quicker soiling of carpet, it has been found that increasing the level of surfactant present in the soil resist agent  
10 improves its performance.

#### SUMMARY OF THE INVENTION

The present invention is a soil resist agent comprising a dispersion in water or water and solvent of a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and b) at least one  
15 anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from about 0.075:1.0 to about 5:1.

The present invention further comprises a method of treating fibrous substrates for soil resistance comprising application to the fibrous substrates of a soil resist agent comprising a dispersion in water or water  
20 and solvent of a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and b) at least one anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from about 0.075:1.0 to about 5:1.

The present invention further comprises a carpet treated with a soil  
25 resist agent comprising a dispersion in water or water and solvent of a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and b) at least one anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from about 0.075:1.0 to about 5:1.

2003257022 08 Oct 2008

- 5a -

In an embodiment of the invention there is provided a soil resist agent comprising a dispersion in water or water and solvent of a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and b) at least one anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from 0.075:1.0 to 5:1 and wherein the polyfluoro organic compound is the product of the reaction of: (1) at least one organic polyisocyanate containing at least three isocyanate groups, (2) at least one fluorochemical compound which contains per molecule (a) a single functional group having one or more Zerewitinoff hydrogen atoms and (b) at least two carbon atoms each of which contains at least two fluorine atoms, and (3) water in an amount sufficient to react with from 5% to 60% of the isocyanate groups in said polyisocyanate.

In an embodiment of the invention there is provided a method of treating fibrous substrates for soil resistance comprising application to the fibrous substrates of a soil resist agent comprising a dispersion in water or water and solvent of a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and b) at least one anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from 0.075:1.0 to 5:1 and wherein the polyfluoro organic compound is the product of the reaction of: (1) at least one organic polyisocyanate containing at least three isocyanate groups, (2) at least one fluorochemical compound which contains per molecule (a) a single functional group having one or more Zerewitinoff hydrogen atoms and (b) at least two carbon atoms each of which contains at least two fluorine atoms, and (3) water in an amount sufficient to react with from 5% to 60% of the isocyanate groups in said polyisocyanate.

07/10/08,ck14578oct7speci,5

DETAILED DESCRIPTION

For the purposes of this invention, the term "dispersing agent" or "dispersant" is used to describe the surface active agent used to produce the stable dispersion of the soil resist agent, while the term "surfactant" is used to describe the additional anionic non-fluorinated surfactants used to enhance soil resist performance of the compositions of the present invention. It is recognized that the same anionic non-fluorinated surfactant may be used for both dispersant and surfactant functions.

10 The present invention is a soil resist agent comprising a dispersion of a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and b) at least one anionic non-fluorinated surfactant, in water or water and solvent, wherein the ratio of polyfluoro organic compound to surfactant is from about 0.075:1.0 to about 5:1.

15 The improved soil resist agents of this invention comprise one or more polyfluoro organic compounds combined with at least one anionic non-fluorinated surfactant at a higher level than is needed to assure a stable dispersion. Table 1 shows the fluorochemical:dispersant ratios of the prior art are in the range 14:1 to 30:1.

20 Clearly, the choice of added surfactants must be based on compatibility with the polyfluoro organic compound and with any dispersants used.

Any anionic non-fluorinated surfactant or blend of surfactants is useful in the practice of the present invention. These include anionic non-fluorinated surfactants and anionic hydrotrope non-fluorinated surfactants, including sulfonates, sulfates, phosphates and carboxylates. Commercially available anionic non-fluorinated surfactants suitable for use in the present invention include a salt of alpha olefin sulfonate, salt of alpha sulfonated carboxylic acid, salt of alpha sulfonated carboxylic ester,

salt of 1-octane sulfonate, alkyl aryl sulfate, salt of dodecyl diphenyloxide disulfonate, salt of decyl diphenyloxide disulfonate, salt of butyl naphthalene sulfonate, salt of C<sub>16</sub>-C<sub>18</sub> phosphate, salt of condensed naphthalene formaldehyde sulfonate, salt of dodecyl benzene sulfonate, 5 salt of alkyl sulfate, salt of dimethyl-5-sulfoisophthalate, and a blend of salt of decyl diphenyloxide disulfonate with salt of condensed naphthalene formaldehyde sulfonate. The sodium and potassium salts are preferred.

Preferred anionic non-fluorinated surfactants are the sodium or potassium salts of dodecyl diphenyloxide disulfonate, alkyl aryl sulfates, 10 salt of alkyl sulfate, C<sub>16</sub>-C<sub>18</sub> potassium phosphate, decyl diphenyloxide disulfonate, and a blend of decyl diphenyloxide disulfonate with condensed naphthalene formaldehyde sulfonate.


The anionic non-fluorinated surfactants are added in addition to the amount of dispersant or dispersants needed to disperse the polyfluoro 15 organic compound. Specifically, the improved soil resist agents of this invention contain a fluorochemical organic compound having at least one urea, urethane, or ester linkage (hereinafter "fluorochemical" or "FC"). The fluorochemical to surfactant (the total of surfactant and dispersant) ratio is from about 0.075:1.0 to about 5:1, preferably from about 0.2:1 to about 20 4:1, and more preferably from about 0.1:1.0 to about 4:1. Such formulations contrast clearly with conventional soil resist formulations having fluorochemical:dispersant ratios of 14:1 to 30:1 by weight as described previously.

Any suitable fluorochemical organic compound having at least one 25 urea, urethane, or ester linkage can be used herein. Fluorochemical compounds suitable for use in the soil resist agent compositions of the present invention include the polyfluoro nitrogen-containing organic compounds described by Kirchner in US Patent 5,414,111, incorporated herein by reference, and comprise compounds having at least one urea linkage per molecule which compounds are the product of the reaction of: 30 (1) at least one organic polyisocyanate or mixture of polyisocyanates

which contains at least three isocyanate groups per molecule, (2) at least one fluorochemical compound that contains per molecule (a) a single functional group having one or more Zerewitinoff hydrogen atoms and (b) at least two carbon atoms each of which contains at least two fluorine atoms, and (3) water in an amount sufficient to react with from about 5% to about 60% of the isocyanate groups in the polyisocyanate. A Zerewitinoff hydrogen is an active hydrogen [such as -OH, -COOH, -NH, and the like] contained in an organic compound. Zerewitinoff hydrogens may be quantified by reacting the compound with a  $\text{CH}_3\text{Mg}$  halide to liberate  $\text{CH}_4$ , which, measured volumetrically, gives a quantitative estimate of the active hydrogen content of the compound. Primary amines give 1 mole of  $\text{CH}_4$  when reacted in the cold; usually two moles when heated [Organic Chemistry by Paul Karrer, English Translation published by Elsevier 1938, page 135].

In a preferred embodiment, the amount of water is sufficient to react with about 10% to about 35% of the isocyanate groups in the polyisocyanate, and most preferably, between about 15% and about 30%.

A wide variety of fluorochemical compounds that contain a single functional group can be used so long as each fluorochemical compound contains at least two carbon atoms and each carbon atom is bound to at least two fluorine atoms. For example, the fluorochemical compound can be represented by the formula:



wherein

$\text{R}^f$  is a monovalent aliphatic group containing at least two carbon atoms, each of which is bound to at least two fluorine atoms;

$\text{R}$  is a divalent organic radical;

$k$  is 0 or 1; and

X is -O-, -S-, or -N(R<sup>1</sup>)- in which R<sup>1</sup> is H, alkyl containing 1 to 6 carbon atoms or a R<sup>f</sup>-R<sub>k</sub>- group.

For purposes of this invention, it is assumed that a primary amine provides one active hydrogen as defined by Zerewitinoff et al.

5 In a more specific embodiment, the fluorochemical compound that contains a single functional group can be represented by the formula:





wherein

10 R<sup>f</sup> and k are as defined above;

R is the divalent radical: -C<sub>m</sub>H<sub>2m</sub>SO-, -C<sub>m</sub>H<sub>2m</sub>SO<sub>2</sub>-, -SO<sub>2</sub>N(R<sup>3</sup>)-, or -CON(R<sup>3</sup>)- in which m is 1 to 22 and R<sup>3</sup> is H or alkyl of 1 to 6 carbon atoms;

15 R<sup>2</sup> is the divalent linear hydrocarbon radical: -C<sub>n</sub>H<sub>2n</sub>- which can be optionally end-capped by




in which n is 0 to 12, p is 1 to 50, and R<sub>4</sub>, R<sub>5</sub> and R<sub>6</sub> are the same or different H or alkyl containing 1 to 6 carbon atoms; and

5 X is -O-, -S-, or -N(R<sub>7</sub>)- in which R<sub>7</sub> is H, alkyl containing 1 to 6 carbon atoms or a R<sub>f</sub>-R<sub>k</sub>-R<sub>2</sub>- group.

More particularly, R<sub>f</sub> is a fully-fluorinated straight or branched aliphatic radical of 3 to 20 carbon atoms that can be interrupted by oxygen atoms.

In a preferred embodiment, the fluorochemical compound that contains a single functional group can be represented by the formula:

10



wherein

15 X is -O-, -S-, or -N(R<sub>7</sub>)- in which R<sub>7</sub> is H, alkyl containing 1 to 6 carbon atoms or a R<sub>f</sub>-R<sub>k</sub>-R<sub>2</sub>- group.

R<sub>f</sub> is a mixture of perfluoroalkyl groups, CF<sub>3</sub>CF<sub>2</sub>(CF<sub>2</sub>)<sub>r</sub> in which r is 2 to 18; and


q is 1, 2 or 3.

20 In a more particular embodiment, R<sub>f</sub> is a mixture of said perfluoroalkyl groups, CF<sub>3</sub>CF<sub>2</sub>(CF<sub>2</sub>)<sub>r</sub>; and r is 2, 4, 6, 8, 10, 12, 14, 16, and 18. In a preferred embodiment, r is predominantly 4, 6 and 8. In another preferred embodiment, r is predominantly 6 and 8. The former preferred embodiment is more readily available commercially and is therefore less expensive, while the latter may provide improved properties.

10

Representative fluoroaliphatic alcohols that can be used as the fluorochemical compound that contains a single functional group for the purposes of this invention are:

5                     $C_sF_{(2s+1)}(CH_2)_tOH$ ,  
 $(CF_3)_2CFO(CF_2CF_2)_uCH_2CH_2OH$ ,  
 $C_sF_{(2s+1)}CON(R^8)(CH_2)_tOH$ ,  
 $C_sF_{(2s+1)}SO_2N(R^8)(CH_2)_tOH$ ,



wherein

15                    s is 3 to 14;  
t is 1 to 12;  
u is 1 to 5;  
v is 1 to 5;  
each of R<sup>8</sup> and R<sup>9</sup> is H or alkyl containing 1 to 6 carbon atoms

20

In another embodiment, the fluorochemical compound that contains a single functional group can be represented by the formula:  $H(CF_2CF_2)_wCH_2OH$  wherein w is 1-10. The latter fluorochemical compound is a known fluorochemical compound that can be prepared by

reacting tetrafluoroethylene with methanol. Yet another such compound is 1,1,1,2,2,2-hexafluoro-isopropanol having the formula:  $\text{CF}_3(\text{CF}_3)\text{CHOH}$ .

In yet another embodiment of the invention, a non-fluorinated organic compound which contains a single functional group can be used in conjunction with one or more of said fluorochemical compounds. Usually between about 1% and about 60% of the isocyanate groups of the polyisocyanate are reacted with at least one such non-fluorinated compound. For example, said non-fluorinated compound can be represented by the formula:



10



wherein

15  $\text{R}10$  is a C<sub>1</sub>-C<sub>18</sub> alkyl, a C<sub>1</sub>-C<sub>18</sub> omega-alkenyl radical or a C<sub>1</sub>-C<sub>18</sub> omega-alkenoyl;

$\text{R}11$  is



20

12

in which R<sup>4</sup>, R<sup>5</sup> and R<sup>6</sup> are the same or different H or alkyl radical containing 1 to 6 carbon atoms and p is 1 to 50;


Y is -O-, -S-, or -N(R<sup>7</sup>)- in which R<sup>7</sup> is H or alkyl containing 1 to 6 carbon atoms; and

k and p are as defined above.

For example, the non-fluorinated compound can be an alkanol or a monoalkyl or monoalkenyl ether or ester of a polyoxalkylene glycol.

10 Particular examples of such compounds include stearyl alcohol, the monomethyl ether of polyoxethylene glycol, the mono-allyl or -methallyl ether of polyoxethylene glycol, the mono-methacrylic or acrylic acid ester of polyoxethylene glycol, and the like.

15 Any polyisocyanate having three or more isocyanate groups can be used for the purposes of this invention. For example, one can use hexamethylene diisocyanate homopolymers having the formula:




20

wherein x is an integer equal to or greater than 1, preferably between 1 and 8. Because of their commercial availability, mixtures of such hexamethylene diisocyanate homopolymers are preferred for purposes of


13

this invention. Also of interest are hydrocarbon diisocyanate-derived isocyanurate trimers, which can be represented by the formula:



5


wherein R<sup>12</sup> is a divalent hydrocarbon group, preferably aliphatic, alicyclic, aromatic or arylaliphatic. For example, R<sup>12</sup> can be hexamethylene, toluene or cyclohexylene, preferably the former. Other 10 polyisocyanates useful for the purposes of this invention are those obtained by reacting three moles of toluene diisocyanate with I,I,I-tris-(hydroxymethyl)-ethane or I,I,I-tris(hydroxymethyl)-propane. The isocyanurate trimer of toluene diisocyanate and that of 15 3-isocyanatomethyl-3,4,4-trimethylcyclohexyl isocyanate are other examples of polyisocyanates useful for the purposes of this invention, as is methine-tris-(phenylisocyanate). Also useful for the purposes of this invention is the polyisocyanate having the formula:



The polyfluoro organic compounds used in the invention are prepared by reacting: (1) at least one polyisocyanate or mixture of 5 polyisocyanates which contains at least three isocyanate groups per molecule with (2) at least one fluorochemical compound which contains per molecule (a) a single functional group having one or more Zerewitinoff hydrogen atoms and (b) at least two carbon atoms each of which contains at least two fluorine atoms. Thereafter the remaining isocyanate groups 10 are reacted with water to form one or more urea linkages. Usually between about 40% and about 95% of the isocyanate groups will have been reacted before water is reacted with the polyisocyanate. In other words, the amount of water generally is sufficient to react with from about 5% to about 60 of the isocyanate groups in the polyisocyanate. Preferably, 15 between about 60% and 90% of the isocyanate groups have been reacted before water is reacted with the polyisocyanate, and most preferably between about 70% and 85% of the isocyanate groups have been reacted prior to reaction of water with the polyisocyanate. Thus, in a preferred embodiment the amount of water is sufficient to react with about 10% to 20 about 35% of the isocyanate groups, most preferably between 15% and 30%.

In one embodiment, water-modified fluorochemical carbamates have been prepared by the sequential catalyzed reaction of Desmodur N-100, Desmodur N-3200 or Desmodur N-3300, or mixtures 25 thereof, with a stoichiometric deficiency of a perfluoroalkyl compound containing one functional group, and then with water. Desmodur N-100

and Desmodur N-3200 are hexamethylene diisocyanate homopolymers commercially available from Mobay Corporation. Both presumably are prepared by the process described in U.S. Patent No. 3,124,605 and presumably to give mixtures of the mono-, bis-, tris-, tetra- and higher order derivatives which can be represented by the general formula:




10 wherein x is an integer equal to or greater than 1, preferably between 1 and 8.

<u>Typical Properties</u>	<u>Avg. Equiv. Wt.</u>	<u>NCO Content. %</u>
Desmodur N-100	191	22.0
Desmodur N-3200	181	23.2

15 The typical NCO content of Desmodur N-100 approximates that listed for a SRI International Report (Isocyanates No. ID, July, 1983, Page 279) hexamethylene diisocyanate homopolymer with the following composition:

	<u>Product Composition</u>	<u>Wt. %</u>
20	Hexamethylene diisocyanate	0.1
	Monobiuret	44.5
	Bisbiuret	17.4
	Trisbiuret	9.5
	Tetrabiuret	5.4
25	Higher Mol. Wt. Derivatives	23.1
	NCO Content	21.8

Based on its average equivalent weight and NCO content, the comparative bis-, tris-, tetra-, and the like, content of Desmodur N-3200 should be less than that of the N-100 product. Desmodur N-3300 is a hexamethylene diisocyanate-derived isocyanurate trimer that can be 5 represented by the formula:



10

The water-modified fluorochemical carbamates are typically prepared by first charging the polyisocyanate, the perfluoroalkyl compound and a dry organic solvent such as methyl isobutyl ketone (MIBK) to a 15 reaction vessel. The order of reagent addition is not critical. The specific weight of aliphatic polyisocyanate and perfluoroalkyl compounds charged is based on their equivalent weights and on the working capacity of the reaction vessel and is adjusted so that all Zerewitinoff active hydrogens charged will react with some desired value between 40% and 95% of the 20 total NCO group charge. The weight of dry solvent is typically 15%-30% of the total charge weight. The charge is agitated under nitrogen and heated to 40°-70°C. A catalyst, typically dibutyltindilaurate per se, or as a solution in MIBK, is added in an amount which depends on the charge, but is usually small, e.g., 1 to 2 parts per 10,000 parts of the polyisocyanate. 25 After the resultant exotherm, the mixture is agitated at a temperature between 65° and 105°C for 2-20 hours from the time of the catalyst addition, and then, after its temperature is adjusted to between 55° and

17

90°C, is treated with water per se or with wet MIBK for an additional 1 to 20 hours.

The use of a stoichiometric excess of a polyisocyanate assures complete reaction of the fluorinated and non-fluorinated organic 5 compounds that, coupled with subsequent reaction with water, provides fluorochemical compounds that are preferred for use in the soil resist agents of the present invention.

In another embodiment the fluorochemical compounds suitable for use in the present invention include perfluoroalkyl esters and mixtures 10 thereof with vinyl polymers described by Dettre et al. in US Patent 3,923,715, incorporated herein by reference. The fluorochemical compounds disclosed by Dettre comprise an aqueous dispersion of a composition of more than 0 and up to 95 % of a non-fluorinated vinyl polymer having an adjusted Vickers Hardness of about 10 to about 20, 15 and 5 to less than 100% of a perfluoroalkyl ester of a carboxylic acid of from 3 to 30 carbon atoms. US Patent 3,923,715 disclosed that volatility is important in minimizing flammability.

Many of the known esters of fluorinated alcohols and organic acids are useful as the perfluoroalkyl ester compound useful in the invention. 20 Representative of the fluorinated alcohols that can be used to make the ester are  $(CF_3)_2CFO(CF_2CF_2)_pCH_2CH_2OH$  where p is 1 to 5;  $(CF_3)_2CF(CF_2CF_2)_qCH_2CH_2OH$  where q is 1 to 5;  $R^fSO_2N(R')CH_2OH$  where  $R^f$  is perfluoroalkyl of 4 to 12 carbons and  $R'$  is H or lower alkyl;  $C_nF_{(2n+1)}(CH_2)_m-OH$  or  $-SH$  where n is 3 to 14 and m is 1 to 12; 25  $R^fCH_2C(X)H(CH_2)_sOH$  where r is > 1 X is  $-O_2C$ -alkyl,  $-(CH_2)_sOH$ ,  $-(CH_2)_sO_2C$  alkyl or  $-OH$  wherein s is an integer of 0 to 10 and  $R^f$  is

perfluoroalkyl of 3 to 21 carbons;  $R^fCON(R)-(CH_2)_tOH$  where  $R^f$  is perfluoroalkyl of 4 to 18 carbons,  $t$  is 2 to 6 and R is an alkyl group of 4 to 10 carbons.

The preferred fluorinated esters utilize perfluoroalkyl aliphatic alcohols of the formula  $C_nF_{(2n+1)}(CH_2)_mOH$  where n is from about 3 to 14 and m is 1 to 3. Most preferred are esters formed from a mixture of the alcohols where n is predominantly 10, 8 and 6 and m is 2. These esters are formed by reacting the alcohol or mixture of alcohols with mono- or polycarboxylic acids which can contain other substituents and which contain from 3 to 30 carbons. In one method of preparing the esters, the alcohol is heated with the acid in the presence of catalytic amounts of p-toluenesulfonic acid and sulfuric acid, and with benzene, the water of reaction being removed as a codistillate with the benzene. The residual benzene is removed by distillation to isolate the ester.

The 2-perfluoroalkyl ethanols of the formula  $C_nF_{(2n+1)}CH_2CH_2OH$  wherein n is from 6 to 14, and preferably a mixture of 2-perfluoroalkylethanols whose values of n are as described above, are prepared by the known hydrolysis with oleum of 2-perfluoroalkylethyl iodides,  $C_nF_{(2n+1)}CH_2CH_2I$ . The 2-perfluoroalkylethyl iodides are prepared by the known reaction of perfluoroalkyl iodide with ethylene. The perfluoroalkyl iodides are prepared by the known telomerization reaction using tetrafluoroethylene and thus each perfluoroalkyl iodide differs by  $-(CF_2-CF_2)-$  unit.

To produce the perfluoroalkyl ester compounds useful as the fluorochemical component in the present invention wherein the number of carbon atoms in the perfluoroalkyl portion of the molecule is in the range of 6 to 14, removal of perfluoroalkyl iodides boiling below about 116° - 119°C (atmospheric boiling point of  $C_6F_{13}I$ ) and above about 93° - 97°C at 5 mm pressure (666 Pa), (5 mm pressure boiling range of  $C_{14}F_{29}I$ ) is carried out. This yields a mixture of perfluoroalkyl iodides wherein the number of carbon atoms in the perfluoroalkyl portion of the molecule is in

the range of 6 to 14 carbon atoms. Another method for preparing esters employed as the fluorochemical component in the instant invention is to react perfluoroalkylethyl bromides or iodides with an alkali metal carboxylate in an anhydrous alcohol.

5 A preferred fluoroester for use as the fluorochemical component of the invention is the citric acid urethane. Therein, the citric acid ester is modified by reacting the ester with an isocyanate compound, for example, hexamethylene diisocyanate, which reacts with the -OH group of the citric acid ester to form urethane linkages.

1.0 Perfluoroalkyl esters combined with vinyl polymers are also suitable for use herein. By vinyl polymer is meant a polymer derived by polymerization or copolymerization of vinyl monomers (vinyl compounds) including vinyl chloride and acetate, vinylidene chloride, methyl acrylate and methacrylate, acrylonitrile, styrene and vinyl esters and numerous 15 others characterized by the presence of a carbon double bond in the monomer molecule which opens during polymerization to make possible the carbon chain of the polymer. The vinyl polymer has an adjusted Vickers Hardness of about 10 to about 20. The preferred vinyl polymer is poly(methylmethacrylate) having an adjusted Vickers Hardness of 16.1.

20 The adjusted Vickers Hardness relates to the effectiveness of soil resistance. A Vickers diamond indenter is used in an Eberbach Micro Hardness Tester (Eberbach Corp., Ann Arbor, MI). The procedure follows that described in American Society of Testing Materials Standard D 1474-68 for Knoop Hardness, with the following adjustments. A Vickers 25 indenter is used instead of a Knoop indenter, a 50 g load is used instead of a 25 g load, the load is applied for 30 s instead of for 18 s, the measurement is made at  $25 \pm 10\%$  relative humidity instead of  $50 \pm 5\%$  relative humidity, and the hardness value is calculated using the Vickers formula instead of the Knoop formula.

The Vickers Hardness method is described in the American Society of Testing Materials Standard E 92-67. Description of the Vickers indenter and the calculation of Vickers Hardness is found therein.

The term "adjusted Vickers Hardness" refers to the hardness value obtained by using the Vickers formula but not the Vickers method. The vinyl polymers which function satisfactorily as component of the soil resist agent of the invention must possess an adjusted Vickers Hardness of about 10 to 20. Adjusted hardness can be determined on a polymer sample deposited on a glass plate in solvent solution, the solvent being evaporated and a smooth coating obtained by heating at about 150° to 175°C for 3 to 5 minutes. Alternatively, a smooth coating can be obtained by pressing between glass plates at 100° to 150°C after the solvent has evaporated. Any suitable solvent can be employed to dissolve the polymers, ethers, ketones and other good solvent types being particularly useful. The coating should be sufficiently thick (75 to 250 micrometers) so that the indenter used in the test does not penetrate more than 15% of the coating thickness.

Poly(methylmethacrylate) latices can be prepared by known aqueous emulsion polymerization to provide dispersions containing very fine particles of high molecular weight and narrow molecular weight distribution using an oxygen-free system and an initiator such as potassium persulfate/sodium bisulfite in combination.

The aqueous dispersion of fluorinated ester can be blended with an aqueous latex of poly(methylmethacrylate) to make a composition which is extendible in water, and can be diluted therewith for application to substrates. The dispersion before dilution will normally contain from about 5% to 15% of the fluorinated ester and 3 to 30% of the methyl methacrylate polymer.

The fluorochemical component of the present invention can be stored and/or used as prepared or after further solvent dilution, or

converted by standard technology to an aqueous dispersion using a dispersant to stabilize the dispersion. The fluorochemical component of the present invention is converted by standard technology to a dispersion in water or in a mixture of water and solvent. While it is usually desirable 5 to minimize organic solvents in soil resist agents, residual or added solvents such as low molecular weight alcohols (e.g., ethanol) or ketones (e.g., acetone or MIBK) can be used. Preferred for use in the practice of the present invention is an aqueous dispersion optionally containing solvents and dispersion stabilizers such as glycols. This fluorochemical 10 dispersion is combined with the anionic non-fluorinated surfactant to yield the soil resist agent of the present invention. The additional anionic non-fluorinated surfactant in the desired amount is added to the fluorochemical dispersion with stirring. This addition can be made to the fluorochemical dispersion in the concentrated form as shipped or at the point of 15 application when diluted for use.

In the practice of the present invention, the preferred soil resist agents comprise a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage that is the product of the reaction of: (1) at 20 least one organic polyisocyanate containing at least three isocyanate groups, (2) at least one fluorochemical compound which contains per molecule (a) a single functional group having one or more Zerewitinoff hydrogen atoms and (b) at least two carbon atoms each of which contains at least two fluorine atoms, and (3) water in an amount sufficient to react with from about 5% to about 60% of the isocyanate groups in said 25 polyisocyanate, combined with at least one anionic non-fluorinated surfactant selected from the group consisting of sodium dodecyl diphenyloxide disulfonate, alkyl aryl sulfate, sodium alkyl sulfate, C<sub>16</sub>-C<sub>18</sub> potassium phosphate, sodium decyl diphenyloxide disulfonate, and a blend of sodium decyl diphenyloxide disulfonate with condensed 30 naphthalene formaldehyde sodium sulfonate.

The present invention further comprises a method of treating fibrous substrates for soil resistance comprising application to the fibrous substrates of a soil resist agent comprising a dispersion in water or water and solvent of a) a polyfluoro organic compound having at least one of a 5 urea, urethane, or ester linkage, and b) at least one anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from about 0.075:1.0 to about 5:1.

Suitable substrates for the application of the products of this invention are films, fibers, yarns, fabrics, carpeting, and other articles 10 made from filaments, fibers, or yarns derived from natural, modified natural, or synthetic polymeric materials or from blends of these other fibrous materials. Specific representative examples are cotton, wool, silk, nylon including nylon 6, nylon 6,6 and aromatic polyamides, polyesters including poly(ethyleneterephthalate) and poly(trimethyleneterephthalate) 15 (abbreviated PET and PTT, respectively), poly(acrylonitrile), polyolefins, jute, sisal, and other cellulosics. The soil resist agents of this invention impart soil resistance and/or oil-, water-, and soil-repellency properties to fibrous substrates. The type of substrate of particular interest in accordance with the present invention is carpeting, particularly nylon 20 carpeting, to which soil resist agents of the present invention are applied.

The soil resist agents of the present invention are applied to suitable substrates by a variety of customary procedures. For the fibrous substrate end-use, one can apply them from an aqueous dispersion or an organic solvent solution by brushing, dipping, spraying, padding, roll 25 coating, foaming or the like. They can also be applied by use of the conventional beck dyeing procedure, continuous dyeing procedure or thread-line application. The soil resist agents of this invention are applied to the substrate as such or in combination with other textile finishes, processing aids, foaming agents, lubricants, anti-stains, and the like. This 30 new agent provides improved early soiling performance versus current carpet fluorochemical soil resist agents. The product is applied at a carpet

mill, by a carpet retailer or installer prior to installation, or on a newly installed carpet.

The present invention further comprises a fibrous substrate treated with a soil resist agent comprising a dispersion in water or water and 5 solvent of (a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and (b) at least one anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from about 0.075:1 to about 5:1.

The fibrous substrates of the present invention include those 10 substrates previously described. Of particular interest is carpet, especially nylon carpet. The soil resist agent used to treat the substrate of the present invention is as previously described herein. A variety of methods for application of the soil resist agent are used as described above. The treated substrate of the present invention has superior resistance to soiling 15 and/or oil-, water-, and soil repellency properties.

Contrary to the practice and teaching of the prior art, the soil resist agents of the present invention are useful to provide enhanced soil resist properties when applied to fibrous substrates.

#### **TEST METHODS**

20 Test Method 1. Accelerated Soiling Test

A drum mill (on rollers) was used to tumble synthetic soil onto the carpet. Synthetic soil was prepared as described in AATCC Test Method 123-2000, Section 8.

Preparation of soil-coated beads:

25 Synthetic soil, 3 g, and 1 liter of clean nylon resin beads (SURLYN ionomer resin beads 1/8 - 3/16 inch (0.32 – 0.48 cm) diameter were placed into a clean, empty canister. SURLYN is an ethylene/methacrylic acid copolymer, available from E. I. du Pont de Nemours and Co.,

Wilmington DE). The canister lid was closed and sealed with duct tape and the canister rotated on rollers for 5 minutes. The soil-coated beads were removed from the canister.

Preparation of carpet samples to insert into the drum:

5 Total sample size was 8 x 25 inch (20.3 x 63.5 cm) for these tests. One test item and one control item were tested at the same time. The carpet pile of all samples was laid in the same direction. The shorter side of each carpet sample was cut in the machine direction (with the tuft rows).

10 Method:

Strong adhesive tape was placed on the backside of the carpet pieces to hold them together. The carpet samples were placed in the clean, empty drum mill with the tufts facing toward the center of the drum. The carpet was held in place in the drum mill with rigid wires. Soil-coated 15 resin beads, 250 cc, and 250 cc of ball bearings (5/16 inch, 0.79 cm diameter) were placed into the drum mill. The drum mill lid was closed and sealed with duct tape. The drum was run on the rollers for 2 1/2 minutes at 105 rpm. The rollers were stopped and the direction of the drum mill reversed. The drum was run on the rollers for an additional 2 1/2 minutes 20 at 105 rpm. The carpet samples were removed and vacuumed uniformly to remove excess dirt. The soil-coated beads were discarded.

Evaluation of samples:

The Delta E color difference for the soiled carpet was measured for the test and control items versus the original unsoiled carpet.

25

#### Test Method 2. Color Measurement of Soiling Performance

Color measurement of each carpet was conducted on the carpet following the accelerated soiling test. For each control and test sample the color of the carpet was measured, the sample was soiled, and the

color of the soiled carpet was measured. The Delta E is the difference between the color of the soiled and unsoiled samples, expressed as a positive number. The color difference was measured on each item, using a Minolta Chroma Meter CR-310. Color readings were taken at five different areas on the carpet sample, and the average Delta E was recorded. The control carpet for each test item was of the same color and construction as the test item. The control carpet had been treated with the fluorochemical dispersion with no additional surfactant.

5 Delta Delta E was calculated by subtracting the Delta E of the control carpet from the Delta E of the test item. A larger negative value for Delta Delta E indicated that the test carpet had better performance and had less soiling than the control. A larger positive value for Delta Delta E indicated that the test carpet had poorer performance and had soiled more than the control.

10

#### 15 Test Method 3. Floor Traffic Soiling Test Method

Carpets were installed in a busy corridor of a school or office building and subjected to human foot traffic in a controlled test area. The corridor was isolated from exits and had substantial walk-off mats and carpeted areas prior to the soiling test area. The unit "foot traffic" was the passing of one individual in either direction and was recorded with automated traffic counters. A Delta Delta E measurement was made as in Test Method 2.

### EXAMPLES

25 Examples 1 - 13

These examples investigated the enhancement of soil resist performance of carpet by addition of significant quantities of anionic non-fluorinated surfactant, as listed in Table 2, to a dispersed fluorochemical soil resist. The surfactants were commercially available, as listed in Table 30 3. The carpet used in this example consisted of a level loop commercial

carpet (26 oz./yd<sup>2</sup>, 0.88 kg/m<sup>2</sup>), having a nylon 6,6 face fiber that had been dyed to a yellow color. The control carpet for this example was treated with a dispersed fluorochemical soil resist, available from E. I. du Pont de Nemours and Company, Wilmington DE, and which contained the

5 fluorochemical disclosed in US Patent 5,411,766 at a level of 22.6% with surfactant at a level of 1.4%, and with a ratio of fluorochemical:dispersant of 16:1. This dispersed fluorochemical soil resist was spray applied at 25% wet pick-up (wpu) and dried to a carpet face temperature of 250°F (121°C). The "wet pick-up" in textile processing is the amount of liquid,

10 and material carried by the liquid, applied to a textile, and is usually expressed as a percentage of either the dry or conditioned weight of the textile prior to processing (AATCC Technical Manual, Vol. 77, p. 414, *op. cit.*). The test compositions were made up of the same dispersed fluorochemical soil resist plus the anionic non-fluorinated surfactant as

15 listed in Table 2. Each test composition was applied to the carpet with a spray application at 25% wpu and dried to the same carpet face temperature. The application levels for control and test compositions are given in Table 6A. Carpets were tested by the accelerated soiling Test Method 1 versus control carpet that had been treated with the same

20 fluorochemical soil resist. The test carpets were evaluated according to Test Methods 1 and 2, to provide the Color Measurement of Soiling Performance shown in Table 6A.

Comparative Examples A – H

25 The procedure of Example 1 was repeated substituting cationic and nonionic surfactants, as listed in Table 4, for the anionic surfactant. The test compositions were made up of the fluorochemical soil resist described in Examples 1 - 13 plus the surfactant as listed in Table 4. The cationic and nonionic surfactants were commercially available as listed in Table 5.

30 The carpets were evaluated according to Test methods 1 and 2 and the results are shown in Table 6B.

Comparative Example I

The procedure of Examples 1 – 13 was repeated using Dowfax 2A4 at a fluororchemical:surfactant ratio of 0.05:1.0. At this ratio, the improved soil resist performance was not present, as shown in Table 6B.

5 Table 2. Non-fluorinated Surfactants Used in Examples 1 – 13.

Ex. #	Surfactant Trade Name (listed alphabetically)	Ionic Nature	Composition	% Solids
1	Alphastep MC-48	Anionic	Alpha sulfonated carboxylic acids & esters, Na salts	40
2	Bioterge PAS 8S	Anionic	1-octane sulfonate, sodium salt	40
3	Blend of Dowfax 3B2 + Petrodispersant 425	Anionic	45% 3B2 + 45% 425 PD liquid + 10% water	43
4	Cenegen 7	Anionic	Alkyl aryl sulfate	47
5	Dowfax 2A4	Anionic	Sodium dodecyl diphenyloxide disulfonate	45
6	Dowfax 3B2	Anionic	Sodium decyl diphenyloxide disulfonate	47
7		Anionic hydrotrope	Dimethyl-5-sulfoisophthalate, Na salt	100
8	Nopcosprse 9268A	Anionic	Sodium butyl naphthalene sulfonate	76
9	P-347	Anionic	C16 - C18 potassium phosphate	40
10	Petrodispersant 425 liquid	Anionic	Condensed naphthalene formaldehyde sodium sulfonate	46
11	Sulfonate AA-10	Anionic	Sodium dodecyl benzene sulfonate (branched)	97
12	Supralate WAQE	Anionic	Sodium alkyl sulfate	30
13	Witco C-6094	Anionic	Alpha olefin sulfonate	40

Table 3. Non-fluorinated Anionic Surfactant Sources.

Ex. #	Surfactant Trade Name	Type	Supplier and Location
1	Alphastep MC-48	Anionic	Stepan, Northfield IL
2	Bioterge PAS 8S	Anionic	Witco, Houston TX
4	Cenegen 7	Anionic	Yorkshire America, Charlotte NC
5	Dowfax 2A4	Anionic	Dow Chemical Co., Midland MI
6	Dowfax 3B2	Anionic	Dow Chemical Co., Midland MI
7		Anionic hydrotrope	E. I. du Pont de Nemours and Co., Wilmington DE
8	Nopcosprse 9268A	Anionic	Henkel/Cognis, Cincinnati OH
9	P-347	Anionic	Matsumoo Yushi-Seiyaka, Osaka, Japan
10	Petrodispersant 425 liquid	Anionic	Performance Chemicals Group, Houston TX
11	Sul-Fon-Ate AA-10	Anionic	Tennessee Chemical Co., Atlanta GA
12	Supralate WAQE	Anionic	Witco, Houston TX
13	Witco C-6094	Anionic	Witco, Houston TX

Table 4. Surfactants Used in the Comparative Examples A – I.

Comp. Ex. #	Surfactant Trade Name	Ionic Nature	Composition	% Solids
A	Arquad 16-29	Cationic	Trimethyl, hexadecylammonium chloride	29
B	Arquad 18-50	Cationic	Trimethyl, octadecylammonium chloride	50
C	Arquad 2C-75	Cationic	Dimethyl, dicocoammonium chloride	75
D	Avitex 2153	Cationic	mixture of amine and its HCl salt	30
E	Avitex E	Cationic	methyl sulfate quaternary salt	42
F	Brij 78	Nonionic	C18 alcohol + 20 EO	100
G	Ethoquad C/25	Cationic	Ethoxylated N-methyl, cocoamine	100
H	Tergitol NP-9	Nonionic	Nonylphenol +9EO	100
I	Dowfax 2A4	Anionic	Sodium dodecyl diphenyloxide disulfonate	45

Table 5. Surfactant Sources for Comparative Examples A – I.

Comp. Ex. #	Surfactant Trade Name	Type	Supplier and Location
A	Arquad 16-29	Cationic	Akzo Chemicals, Inc., Chicago IL
B	Arquad 18-50	Cationic	Akzo Chemicals, Inc., Chicago IL
C	Arquad 2C-75	Cationic	Akzo Chemicals, Inc., Chicago IL
D	Avitex 2153	Cationic	E. I. du Pont de Nemours & Co., Wilmington DE
E	Avitex E	Cationic	E. I. du Pont de Nemours & Co., Wilmington DE
F	Brij 78	Nonionic	Uniqema, New Castle DE
G	Ethoquad C/25	Cationic	Akzo Chemicals, Inc., Chicago IL
H	Tergitol NP-9	Nonionic	Union Carbide, Danbury CT
I	Dowfax 2A4	Anionic	Dow Chemical Co., Midland MI

Table 6A. Results for Examples 1 – 13.

Ex. #	Fluoro-chemical, % owf*, 100% Solids Basis.	Surfactant Trade Name	Ionic Nature	% owf * Surfactant, 100% Solids Basis	Nylon Carpet Drum Soil Test** versus F-Chem only. Delta Delta E	FC: Surfactant Ratio
Anionic Non-Fluorinated Surfactants of Examples 1 - 13						
1	0.2%	Alphastep MC-48	Anionic	0.2	-1.7	1.0:1.0
2	0.2%	Bioterge PAS-85	Anionic	0.2	-1.3	1.0:1.0
3	0.2%	Dowfax 3B2 + Petrodispersant 425 Blend***	Anionic	0.2	-3.4	1.0:1.0
4a	0.2%	Cenegen 7	Anionic	0.2	-4.7	1.0:1.0
4b	0.2%	Cenegen 7	Anionic	0.35	-4.7	0.6:1.0
4c	0.2%	Cenegen 7	Anionic	0.44	-4.1	0.4:1.0
5a	0.2%	Dowfax 2A4	Anionic	2.0	-1.8	0.1:1.0
5b	0.2%	Dowfax 2A4	Anionic	0.6	-2.4	0.3:1.0
5c	0.2%	Dowfax 2A4	Anionic	0.3	-4.7	0.7:1.0
5d	0.2%	Dowfax 2A4	Anionic	0.11	-2.4	1.8:1.0
5e	0.2%	Dowfax 2A4	Anionic	0.06	-1.1	3.3:1.0
6	0.2%	Dowfax 3B2	Anionic	0.2	-3.4	1.0:1.0
7	0.2%		Anionic	0.2	-1.9	1.0:1.0
8	0.2%	Nopcosprse 9268A	Anionic	0.2	-2.6	1.0:1.0
9	0.2%	P-347	Anionic	0.2	-4.2	1.0:1.0
10	0.2%	Petrodispersant 425 liquid	Anionic	0.2	-2.0	1.0:1.0
11	0.2%	Sulfonate AA-10	Anionic	0.2	-1.4	1.0:1.0
12	0.2%	Supralate WAQE	Anionic	0.2	-4.4	1.0:1.0
13	0.2%	Witco C-6094	Anionic	0.2	-1.0	1.0:1.0

FC:surfactant ratio is the ratio of the fluoroochemical to the sum of the dispersant and surfactant

Examples 4 and 5 were replicated with differing amounts of added surfactant

5 \* owf: based on the weight of the fiber.

\*\* Test methods 1 and 2.

\*\*\* Blend composition, see Table 2.

Table 6B. Results for Comparative Examples A – I.

Ex. #	Fluoro-chemical, % owf*, 100% Solids Basis.	Surfactant Trade Name	Ionic Nature	% owf * Surfactant, 100% Solids Basis	Nylon Carpet Drum Soil Test** versus F-Chem only. Delta E	FC: Surfactant Ratio
A	0.2%	Arquad 16-29	Cationic	0.2	18.7	1.0:1.0
B	0.2%	Arquad 18-50	Cationic	0.2	9.6	1.0:1.0
C	0.2%	Arquad 2C-75	Cationic	0.2	12.9	1.0:1.0
D	0.2%	Avitex 2153	Cationic	0.2	16.6	1.0:1.0
E	0.2%	Avitex E	Cationic	0.2	10.7	1.0:1.0
F	0.2%	Brij 78	Nonionic	0.2	1.8	1.0:1.0
G	0.2%	Ethoquad C/25	Cationic	0.2	11.8	1.0:1.0
H	0.2%	Tergitol NP-9	Nonionic	0.2	14.2	1.0:1.0
I	0.2%	Dowfax 2A4	Anionic	4.0	4.0	0.05:1.0

10

FC:surfactant ratio is the ratio of the fluoroochemical to the sum of the dispersant and surfactant

\* owf: based on the weight of the fiber.

\*\* Test methods 1 and 2.

The data in Tables 6A and 6B showed the lower soiling with Examples 1 – 13 having the anionic non-fluorinated surfactants present, compared with carpet treated with the same fluorochemical without the added anionic non-fluorinated surfactant. The Comparative Examples A - 5 H showed higher soiling when a cationic or nonionic non-fluorinated surfactant was added to the fluorochemical soil resist prior to application. Comparative Example I showed the improved soil resist improvement was not present at the FC:surfactant ratio of 0.05:1.0.

Example 14

10 This example investigated the enhancement of soil resist performance of carpet constructed with unscoured solution pigmented nylon 6,6 fiber by addition of a significant quantity of anionic non-fluorinated surfactant to a dispersed fluorochemical soil resist. The carpet used in this example consisted of a level loop commercial carpet (26 oz/yd<sup>2</sup>, 0.88 kg/m<sup>2</sup>),  
15 constructed with unscoured solution pigmented nylon 6,6 face fiber, which was a tan color. The control carpet for this example was treated with the same dispersed fluorochemical soil resist as used in Examples 1 – 13, which was spray applied at 25% wpu and dried to a carpet face temperature of 250°F (121°C). The test composition was made of the  
20 same dispersed fluorochemical soil resist as used in Examples 1 – 13 plus the anionic non-fluorinated surfactant CENEGEN 7, available from Yorkshire America, Charlotte NC. The test composition was applied to the carpet with a spray application at 25% wpu and dried to a carpet face temperature of 250°F (121°C). The application levels for control and test  
25 compositions are shown in Table 7. Carpets were tested by the accelerated soiling method versus control carpet which had been treated with the same dispersed fluorochemical soil resist. The test carpets were evaluated according to Test Methods 1 and 2, to provide the Color Measurement of Soiling Performance shown in Table 7.

Table 7. Results for Example 14.

Fluoro-chemical, % owf*, 100% Solids Basis.	Surfactant Trade Name	Ionic Nature	% owf * Surfactant, 100% Solids Basis	Nylon Carpet Drum Soil Test** versus F-Chem only. Delta Delta E	FC: Surfactant Ratio
0.2%	Cenegen 7	Anionic	0.36	-1.6	0.6:1.0

FC:surfactant ratio is the ratio of the fluorochemical to the sum of the dispersant and surfactant

\* owf: based on the weight of the fiber.

5        \*\* Test methods 1 and 2.

The data in Table 7 showed the lower soiling with the addition of anionic non-fluorinated surfactant to fluorochemical soil resist for carpet constructed with unscoured solution pigmented nylon 6,6 fiber, compared with carpet treated with the same fluorochemical soil resist without added 10 anionic non-fluorinated surfactant.

#### Example 15

This example investigated the enhancement of soil resist performance of carpet constructed with unscoured 3GT polyester fiber by addition of a significant quantity of anionic non-fluorinated surfactant to a 15 fluorochemical soil resist. The carpet used in this example consisted of a level loop commercial carpet (28 oz/yd<sup>2</sup>, 0.95 kg/m<sup>2</sup>), constructed with unscoured PTT polyester face fiber. The test composition was made of a dispersed fluorochemical soil resist, available from E. I. du Pont de Nemours and Company, Wilmington DE, which contained the 20 fluoroalcohol citrate urethane and poly(methylmethacrylate) mixture disclosed in Example 2 of US Patent 3,923,715 at a level of 9.1%, except that the fluoroalcohol citrate urethane was prepared with hexamethylene diisocyanate instead of 1-methyl-2,4-diisocyanatobenzene and was anionically dispersed. This dispersed fluorochemical soil resist contained 25 dispersant at a level of 0.3% and had a ratio of fluorochemical:dispersant

of 30:1. The added anionic non-fluorinated surfactant was SUPRALATE WAQE, available from Witco Company, Houston TX. The control carpet for this example was treated with the same fluorochemical soil resist which was spray applied at 25% wpu and dried to a carpet face temperature of 5 250°F (121°C). The application levels for control and test compositions are show in Table 8. The test composition was applied to the carpet with a spray application at 25% wpu and dried to a carpet face temperature of 250°F (121°C). The test carpet was tested by Test Method 3, the floor traffic soiling method, versus control carpet. The carpets were subjected 10 to 32,000 foot traffics. Then the carpets were evaluated according to Test Method 2, the Color Measurement of Soiling Performance, and the resulting data are shown,in Table 8.

Table 8. Results for Example 15.

Fluoro-chemical, % owf*, 100% Solids Basis.	Surfactant Trade Name	Ionic Nature	% owf * Surfactant, 100% Solids Basis	PTT** Polyester Carpet. Traffic Soil Test*** Delta Delta E	FC: Surfactant Ratio
0.28%	Supralate WAQE	Anionic	0.11	-1.4	2.6:1.0

15 FC:surfactant ratio is the ratio of the fluorochemical to the sum of the dispersant and surfactant

\* owf: based on the weight of the fiber.

\*\* PTT = poly(trimethyleneterephthalate) polyester fiber

\*\*\*Test methods 2 and 3.

20 The data in Table 8 showed the lower soiling with the addition of anionic non-fluorinated surfactant to fluorochemical soil resist for carpet constructed with unscoured poly(trimethyleneterephthalate) polyester fiber, compared with carpet treated with the same fluorochemical soil resist without added anionic non-fluorinated surfactant.

Example 16

This example investigated the enhancement of soil resist performance of carpet constructed with cotton fiber by addition of a significant quantity of anionic non-fluorinated surfactant to a

5     fluorochemical soil resist. The carpet used in this example consisted of a cut-pile residential carpet (40 oz/yd<sup>2</sup>, 1.36 kg/m<sup>2</sup>), constructed with cotton face fiber. The test composition was made of the same dispersed fluorochemical soil resist as in Example 15 plus anionic non-fluorinated surfactant SUPRALATE WAQE, available from Witco Company, Houston

10    TX. The control carpet for this example was treated with the same fluorochemical soil resist which was spray applied at 25% wpu and dried to a carpet face temperature of 250°F (121°C). The application levels for control and test compositions are show in Table 9. The test composition was applied to the carpet with a spray application at 25% wpu and dried to

15    a carpet face temperature of 250°F (121°C). The test carpet was tested by the accelerated soiling method (Test Method 1) versus control carpet which had been treated with the same dispersed fluorochemical. Then the carpets were evaluated according to Test Method 2, the Color Measurement of Soiling Performance, and the resulting data are shown in

20    Table 9.

Table 9. Results for Example 16.

Fluoro-chemical, % owt*, 100% Solids Basis.	Surfactant Trade Name	Ionic Nature	% owt * Surfactant, 100% Solids Basis	Cotton Carpet. Traffic Soil Test**. Delta E	FC: Surfactant Ratio
0.44%	Supralate WAQE	Anionic	0.24	-3.9	1.8:1.0

FC:surfactant ratio is the ratio of the fluorochemical to the sum of the dispersant and surfactant

2003257022 08 Oct 2008

- 37 -

\* owf: based on the weight of the fiber.

\*\*Test methods 1 and 2.

The data in Table 9 showed the lower soiling with the addition of anionic non-fluorinated surfactant to fluorochemical soil resist for carpet constructed with 5 cotton fiber, compared with carpet treated with the same fluorochemical soil resist without added anionic non-fluorinated surfactant.

Throughout this specification and the claims which follow, unless the context requires otherwise, the word "comprise", and variations such as "comprises" and

10 "comprising", will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or group of integers or steps.

The reference to any prior art in this specification is not, and should not be

15 taken as, an acknowledgment or any form or suggestion that the prior art forms part of the common general knowledge in Australia.

07/10/08,ck14578claims30sep08.37

2003257022 08 Oct 2008

- 38 -

The claims defining the invention are as follows:

1. A soil resist agent comprising a dispersion in water or water and solvent of a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and b) at least one anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from 0.075:1.0 to 5:1 and wherein the polyfluoro organic compound is the product of the reaction of: (1) at least one organic polyisocyanate containing at least three isocyanate groups, (2) at least one fluorochemical compound which contains per molecule (a) a single functional group having one or more Zerewitinoff hydrogen atoms and (b) at least two carbon atoms each of which contains at least two fluorine atoms, and (3) water in an amount sufficient to react with from 5% to 60% of the isocyanate groups in said polyisocyanate.
2. The soil resist agent of claim 1 wherein the ratio of polyfluoro organic compound to surfactant is from 0.1:1.0 to 4:1.
3. The soil resist agent of claim 1 or 2 wherein the anionic surfactant is selected from the group consisting of a sulfonate, disulfonate, sulfate, phosphate or carboxylate.
4. The soil resist agent of claim 3 wherein the anionic surfactant is selected from the group consisting of an alpha olefin sulfonate, salt of alpha sulfonated carboxylic acid, salt of alpha sulfonated carboxylic ester, salt of 1-octane sulfonate, alkyl aryl sulfate, salt of dodecyl diphenyloxide disulfonate, salt of decyl diphenyloxide disulfonate, salt of butyl naphthalene sulfonate, salt of C<sub>16</sub>-C<sub>18</sub> phosphate, salt of condensed naphthalene formaldehyde sulfonate, salt of dodecyl benzene sulfonate, salt of alkyl sulfate, salt of dimethyl-5-sulfoisophthalate, and a blend of salt of decyl diphenyloxide disulfonate with salt of condensed naphthalene formaldehyde sodium sulfonate.
5. The soil resist agent of claim 3 wherein the anionic surfactant is selected from the group consisting of sodium dodecyl diphenyloxide


07/10/08,ck14578claims30sep08.38

disulfonate, alkyl aryl sulfate, sodium alkyl sulfate, C<sub>16</sub>-C<sub>18</sub> potassium phosphate, sodium decyl diphenyloxide disulfonate, and a blend of sodium decyl diphenyloxide disulfonate with condensed naphthalene formaldehyde sodium sulfonate.

6. The soil resist agent of any one of claims 1 to 5 wherein the dispersion is an aqueous dispersion.

7. The soil resist agent of any one of claims 1 to 6 wherein the polyfluoro organic compound is the product of the reaction of (3) water in an amount sufficient to react with 10% to 35% of said isocyanate groups.

8. The soil resist agent of any one of claims 1 to 7 wherein said fluorochemical compound which contains a single functional group is represented by the formula:



in which

$R^f$  is a monovalent aliphatic group containing at least two carbon atoms, each of which contains at least two fluorine atoms:

R is a divalent organic radical:

k is 0 or 1; and

X is  $-\text{O}-$ ,  $-\text{S}-$ , or  $-\text{N}(\text{R}^1)$  — in which  $\text{R}^1$  is H, alkyl containing 1 to 6 carbon atoms or a  $\text{R}^1-\text{R}_1-$  group.

9. The soil resist agent of claim 8 wherein R<sup>f</sup> is a fully-fluorinated straight or branched aliphatic radical of 3 to 20 carbon atoms which can be interrupted by oxygen atoms.

2003257022 08 Oct 2008

- 40 -

10. The soil resist agent of claim 9 wherein X is oxygen and R<sub>k</sub> is -(CH<sub>2</sub>)<sub>2</sub>-.

11. The soil resist agent of any one of claims 1 to 7 wherein the polyfluoro organic compound having at least one of a urea, urethane or ester linkage is a perfluoroalkyl ester of a carboxylic acid of from 3 to 30 carbon atoms and further comprising a non-fluorinated vinyl polymer having an adjusted Vickers Hardness of 10 to 20.

12. The soil resist agent of Claim 11 wherein the perfluoroalkyl ester is citric acid urethane.

10 13. The soil resist agent of Claim 11 wherein the non-fluorinated vinyl polymer is poly(methylmethacrylate).

14. A method of treating fibrous substrates for soil resistance comprising application to the fibrous substrates of a soil resist agent comprising a dispersion in water or water and solvent of a) a polyfluoro organic compound having at least one of a urea, urethane, or ester linkage, and b) at least one anionic non-fluorinated surfactant, wherein the ratio of polyfluoro organic compound to surfactant is from 0.075:1.0 to 5:1 and wherein the polyfluoro organic compound is the product of the reaction of: (1) at least one organic polyisocyanate containing at least three isocyanate groups, (2) at least one fluorochemical compound which contains per molecule (a) a single functional group having one or more Zerewitinoff hydrogen atoms and (b) at least two carbon atoms each of which contains at least two fluorine atoms, and (3) water in an amount sufficient to react with from 5% to 60% of the isocyanate groups in said polyisocyanate.

15 20 25 15. The method of Claim 14 wherein the application is by spray or foam application.

07/10/08,ck14578claims30sep08.40