

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(10) International Publication Number

WO 2015/134732 A1

(43) International Publication Date  
11 September 2015 (11.09.2015)

WIPO | PCT

(51) International Patent Classification:

D04H 1/46 (2012.01)

(21) International Application Number:

PCT/US2015/018938

(22) International Filing Date:

5 March 2015 (05.03.2015)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/948,314 5 March 2014 (05.03.2014) US

(71) Applicant: SOUTHERN MILLS, INC. [US/US]; 6501 Mall Boulevard, P.O. Box 289, Union City, Georgia 30291 (US).

(72) Inventors: LIPSCOMB, Lee; 108 Castlewood Road, Tyrone, Georgia 30290 (US). SELF, Robert; 852 Southern Shore Drive, Peachtree City, Georgia 30269 (US).

(74) Agents: DOYLE, Kristin J. et al.; Kilpatrick Townsend & Stockton LLP, Suite 2800, 1100 Peachtree Street, Atlanta, Georgia 30309 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2015/134732 A1

(54) Title: FABRIC CONTAINING AN INTIMATE BLEND OF ANTISTATIC FIBERS ARRANGED IN A PATTERN

(57) Abstract: A fabric includes base yarns and antistatic spun yarns located in discrete portions of the fabric such that the fabric dissipates static electricity by way of an inductive field and complies with one or more standards for static dissipation in fabric. The antistatic spun yarns may include inductive antistatic staple fibers, and may include less than 20% antistatic fiber. The fabric may be a woven fabric with the antistatic spun yarns inserted into the fabric in both the warp and filling directions in a ratio of antistatic spun yarns to base yarns of from 1:1 to 1:40. The fabrics may be flame resistant and comply with one or more standards for flame resistant fabrics and/or may comply with one or more standards for high visibility apparel. The fabric may have a total antistatic fiber content of less than about 1%.

FABRIC CONTAINING AN INTIMATE BLEND OF ANTISTATIC FIBERS  
ARRANGED IN A PATTERN

BACKGROUND

[0001] Static electricity has a tendency to build up within and on the surface of fabrics during use. Buildup of static electricity is a nuisance in garment handling and to the wearer and may also pose a hazard to the wearer in certain environments, and in particular in flammable gas environments. As a result, it is desirable for fabrics to prevent or minimize static electricity build up.

[0002] It has been known to incorporate antistatic filament yarns into fabrics to satisfy one or more standards for static electricity in apparel, including EN 1149 (Electrostatic properties of protective clothing) and MIL-C-83429B (Military specification: cloth, plain and basket weave, aramid) (as tested in accordance with FTMS 191A Test Method 5931). One known antistatic filament yarn is available from Barnet under the trade name Nega-Stat®. The antistatic filament yarn is a conductive yarn, which dissipates (or prevents the buildup of) static electricity by conducting the electric charge along the filament yarns to a ground (such as the body of a user). The antistatic filament yarn has been incorporated into fabrics in a continuous grid pattern to facilitate conduction of static electricity through the garment. While such constructions effectively dissipate static electricity in the fabric, the filament yarn is expensive and results in a high fabric cost.

[0003] Another known method for minimizing or preventing static electricity build up in a fabric is to form a fabric from spun yarns (rather than filament) and incorporate approximately 2% or more antistatic staple fibers into the spun yarns

used in the fabric. In this manner, the antistatic staple fibers (such as 401-ECS staple fibers, available from Ascend Performance Materials under the No-Shock® line of products) are more or less evenly distributed throughout the entire fabric. 401-ECS staple fibers have a carbon-based antistatic component. It will be recognized that in such constructions, the antistatic fibers are not continuous and thus will not conduct electricity through the fabric; rather, the antistatic fibers dispersed throughout the fabric dissipate the static electricity that builds up by way of an inductive field.

**[0004]** Antistatic fibers are relatively dark as compared to typical staple fibers used in fabric constructions. As a result, the appearance of fabrics having antistatic staple fibers dispersed throughout the fabric is undesirable when light shades of fabric are desired, and in particular when it is desirable for the fabric to satisfy standards for high visibility apparel. It may not be possible, for example, to satisfy ANSI 107 (High-Visibility Safety Apparel and Headwear) when using a fabric having the relatively darker antistatic staple fibers dispersed throughout. A similar problem can occur when trying to form a fabric from dark shades, as the antistatic fibers, while darker than light shade fibers, are not as dark as commonly used dark shade fibers and will thus appear lighter against the dark background of the other staple fibers. Neither result is desirable. Visual appearance problems can also occur when using conductive antistatic filament yarns in a grid pattern due to voids or variation in the appearance of the filament in the pattern.

#### SUMMARY

**[0005]** A fabric includes base yarns and antistatic spun yarns that include antistatic staple fibers. The antistatic spun yarns are located in discrete portions of

the fabric such that the fabric complies with one or more standards for static dissipation in fabric. Such standards include but are not limited to EN 1149-5, EN 1149-3, MIL-C-83429B, and FTMS 191A Test Method 5931.

[0006] In one feature of the invention the antistatic staple fibers are inductive antistatic staple fibers. In further features the antistatic spun yarns have less than 20% inductive antistatic staple fibers.

[0007] The antistatic spun yarns may be woven or knit into the fabric in a grid pattern or a stripe pattern. In one particular feature, the fabric is a woven fabric and the antistatic spun yarns are inserted into the fabric in both the warp and filling directions. In certain features the ratio of antistatic spun yarns to base yarns in the woven fabric is from 1:1 to 1:40 in one or both of the warp and filling directions.

[0008] The base yarns may be flame resistant yarns such that the fabric complies with one or more standards for flame resistant fabrics. In addition, the fabric may comply with one or more standards for high visibility apparel.

[0009] In a particular feature, the fabric has a total antistatic fiber content of less than about 1%.

#### DETAILED DESCRIPTION

[0010] The subject matter of features of the present invention is described here with specificity to meet statutory requirements, but this description is not necessarily intended to limit the scope of the claims. The claimed subject matter may be embodied in other ways, may include different elements or steps, and may be used in conjunction with other existing or future technologies. This description should not be interpreted as implying any particular order or arrangement among or between

various steps or elements except when the order of individual steps or arrangement of elements is explicitly described.

[0011] Features of the invention relate to an antistatic fabric in which the antistatic content in the fabric is provided by an intimate blend including antistatic staple fibers formed into spun yarns, and in which the spun yarns are located in discrete portions of the fabric, such as in a grid or stripe pattern. Locating the antistatic staple fibers in discrete portions of the fabric provides inductive static dissipation properties to the fabric, while also allowing the fabric to meet high visibility requirements. The fabrics of the present invention are different from previous fabrics that included either (1) antistatic conductive filament yarns located in a grid pattern or (2) included antistatic staple fibers blended throughout the fabric.

[0012] In features of the invention, a relatively high content of antistatic staple fibers is spun into the yarns ("antistatic spun yarns") that will be located in discrete portions of the fabric, while the remainder of the yarns in the fabric (the "base yarns") may be formed of any desired spun yarns and/or filament yarns. In some features the antistatic spun yarns may include from about 2% to about 50% antistatic staple fiber, with the balance being any other desired staple fiber. In certain features the antistatic spun yarns may include from about 2% to 30% antistatic staple fiber, from about 2% to 20% antistatic staple fiber, from about 2% to 15% antistatic staple fiber, from about 2% to 10% antistatic staple fiber, from about 2% to less than or equal to about 30% antistatic staple fiber, from about 2% to less than or equal to about 20% antistatic staple fiber, from about 2% to less than or equal to about 15%

antistatic staple fiber, or from about 2% to less than or equal to about 10% antistatic staple fiber, with the balance being any other desired staple fiber. In one particular feature, the antistatic spun yarns may include from about 2% to less than or equal to about 20% antistatic staple fiber. It is notable that in some features of the invention the antistatic spun yarn may include less than 20% or even less than or equal to about 10% antistatic staple fiber and a fabric incorporating such yarns can still satisfy one or more standards for static electricity in apparel by dissipating static using an inductive field; in contrast a fabric utilizing conductive fibers would require at least 20% conductive fibers in the antistatic yarn to ensure adequate contact between the conductive fibers to ensure a conductive path for static dissipation.

**[0013]** The antistatic spun yarns, because they do not include conductive 100% continuous filament (in contrast to antistatic filament yarns), are not conductive yarns and do not provide the fabric with conductive static dissipation properties; rather, the yarns provide the fabric with inductive static dissipation properties. Fabrics of the invention formed from antistatic spun yarns located in discrete portions of the fabric (e.g., in a grid or stripe pattern) may satisfy one or more standards for static electricity in apparel, including but not necessarily limited to EN 1149 (Electrostatic properties of protective clothing) and MIL-C-83429B (Military specification: cloth, plain and basket weave, aramid) (as tested in accordance with FTMS 191A Test Method 5931).

**[0014]** The discovery that fabrics formed from antistatic spun yarns located in discrete portions of the fabric could satisfy these standards—as contrasted with fabrics having antistatic staple fibers distributed throughout the fabric—was

surprising. It was previously thought that such fabrics would not provide the fabric with sufficient static dissipation properties because (1) the antistatic spun yarns are not conductive (in contrast to antistatic filament yarns) and (2) the antistatic staple fibers are not distributed throughout all of the yarns in the fabric and would thus not be expected to allow the fabric to form a strong enough inductive field to dissipate the static electricity formed therein.

[0015] Another benefit of the fabrics of the present invention is that, because the relatively dark antistatic staple fiber is located in only discrete portions of the fabric, the rest of the fabric can include base yarns (spun yarns or filament yarns) having a lighter shade, or yarns that are dyeable to a lighter shade, such that the fabrics can still satisfy a high visibility standard such as that found in ANSI 107 (High-Visibility Safety Apparel and Headwear). In addition, because the fabrics of the present invention do not include antistatic filament yarns and the defects found therein (noted above), the fabrics of the present invention are free from these visual defects.

[0016] The fabrics of the present invention, having a relatively high content of antistatic staple fibers spun into yarns located in discrete portions of the fabric, may have a total antistatic fiber content in the fabric of from about 0.125% to about 5%, and in some features from about 0.125% to about 2%, about 1% or even about 0.5%. In yet other features, the fabric has a total antistatic fiber content of less than or equal to about 5%, less than or equal to about 2%, less than or equal to about 1% or less than or equal to about 0.5%. As discussed above, it was surprising that these fabrics, having such a low total content of antistatic staple fibers located in only discrete

portions of the fabric, would have acceptable static electricity properties. For purposes of comparison, previously known fabrics including conductive antistatic filament yarns had an antistatic content of at least 1%, and fabrics including an intimate blend of antistatic staple fibers dispersed throughout the entire fabric had an antistatic content of at least 2%.

[0017] The antistatic spun yarns may be located in discrete portions of the fabric in any desirable pattern. In some exemplary features, the antistatic spun yarns are woven or knit into the fabric in a grid pattern or a stripe (e.g., horizontal or vertical) pattern. Any desirable weave (e.g., plain, twill) or knit (e.g., single, double, plain, interlock) pattern may be used. Further, the antistatic spun yarns may be located in either the warp or filling direction in the fabric or, when incorporated into the fabric in, e.g., a grid pattern, in both the warp and filling directions.

[0018] The antistatic spun yarns may also be plied with one or more other antistatic spun yarns and/or with one or more non-antistatic yarns (spun or filament) to form a thicker plied yarn.

[0019] In some features, the fabric is a woven fabric and no more than one antistatic spun yarn is inserted into the fabric for every 40 base yarns in either or both of the warp and filling directions. In other words, the ratio of antistatic spun yarn to base yarn in the fabric is no more than 1:40. In some features, the ratio of antistatic spun yarn to base yarns is from 1:1 to 1:40 in either or both of the warp and filling directions, or in other features from 1:1 to 1:35, or from 1:1 to 1:30, from 1:1 to 1:25, from 1:5 to 1:40, from 1:5 to 1:35, from 1:5 to 1:30, from 1:5 to 1:25, from 1:10 to 1:40, from 1:10 to 1:35, from 1:10 to 1:30, from 1:10 to 1:25, from 1:15 to 1:40, from 1:15

to 1:35, from 1:15 to 1:30, or from 1:15 to 1:25 in either or both of the warp and filling directions.

[0020] As mentioned above, the antistatic spun yarns can include any other desirable staple fiber in addition to the antistatic staple fiber, and the remainder of the yarns in the fabric (base yarns) can include any desired spun yarns and/or filament yarns. In some features of the invention the fabric includes no antistatic fibers (filament or spun) other than the antistatic staple fibers located in the antistatic spun yarns, although it will be recognized that the base yarns could include a small amount of antistatic fibers which could enhance the inductive static dissipation properties of the fabric without substantially affecting the high visibility performance of the fabric.

[0021] The antistatic staple fiber can be any suitable antistatic fiber. One such fiber is 401-ECS, available from Ascend Performance Materials under the No-Shock® line of products. 401-ECS staple fibers are inductive antistatic staple fibers, as they have a core/sheath construction with a carbon-containing core and a nonconductive polyamide sheath. Even though the 401-ECS staple fibers have a carbon-containing core (carbon dispersed in a polymeric matrix), the fibers are not conductive because the relatively large amount of nonconductive sheath in the fiber prevents the carbon-containing core from contacting the cores of other antistatic fibers when the fibers are spun into the yarn with other non-antistatic fibers, which prevents the antistatic spun yarns from conducting electricity. Thus, rather than functioning as conductive yarns, the antistatic spun yarns, when formed into a fabric in accordance with features described herein, provide the fabric with inductive static dissipation

properties. Accordingly, in some features of the invention the antistatic staple fiber may be an inductive antistatic staple fiber. In yet other features the antistatic staple fiber may be a conductive staple fiber such as carbon fiber or stainless steel.

**[0022]** In some features, the fabric is a protective fabric suitable for use in personal protective apparel. In certain features, the fabric is a flame resistant fabric that satisfies one or more standards for flame resistant fabrics, including but not limited to NFPA 2112 (Standard on Flame-Resistant Garments for Protection of Industrial Personnel Against Flash Fire).

**[0023]** Exemplary suitable fibers for use in the base yarn of the present invention include, but are not limited to, flame resistant fibers such as para-aramid fibers, polybenzoxazole (PBO) fibers, PBI fibers, modacrylic fibers, poly{2,6-diimidazo[4,5-b:40; 50-e]-pyridinylene-1,4(2,5-dihydroxy)phenylene} (“PIPD”) fibers, and natural and synthetic flame resistant cellulosic fibers (either naturally flame resistant or treated to make them flame resistant), such as but not limited to lyocell and FR rayon. Examples of para-aramid fibers include KEVLAR™ (available from DuPont), TECHNORA™ (available from Teijin Twaron BV of Arnhem, Netherlands), and TWARON™ (also available from Teijin Twaron BV). An example of a PIPD fiber includes M5 (Dupont). In some features, the base yarns are formed entirely from these fibers. For example, all of the base yarns in the fabric may be formed with 100% of a single type of these fibers or alternatively a blend of different types of these fibers. Moreover, base yarns formed entirely from these fibers may be all or an intimate blend of staple fibers, filaments, or a combination of filaments and staple fibers.

[0024] In other features, the base yarns in the fabric include fibers such as those disclosed above and one or more types of secondary fibers that are used to enhance a secondary property of the fabric other than flame resistance (e.g., comfort, dyeability/printability, etc.) (referred to as “secondary fibers”). For example, some features of the fabric may be formed from yarns having 100% flame resistant fibers (such as those disclosed above) and yarns that include one or more types of secondary fibers (either in addition to, or to the exclusion of, the flame resistant fibers described above). In other features, yarns forming the fabric are formed from a blend of one or more flame resistant fibers (such as those disclosed above) and one or more types of secondary fibers. The blended yarns may be a combination of spun fibers, filaments, or a combination of filaments and staple fibers.

[0025] Such secondary fibers can be selected to enhance a property of the fabric, such as, but not limited to, the comfort, durability, and/or dyeability/printability of the fabric. The secondary fibers may also be flame resistant.

[0026] Secondary fibers that enhance the comfort of the fabric (i.e., have higher moisture regain, soft hand, etc.) are referred to herein as “comfort fibers.” “Comfort fibers” as used herein include, but are not limited to, cellulosic fibers, polybenzimidazole (PBI) fibers, TANLON™ (available from Shanghai Tanlon Fiber Company), rayon, wool, and blends thereof. Examples of cellulosic fibers include cotton, rayon, acetate, triacetate, and lyocell fibers (as well as their flame resistant counterparts FR cotton, FR rayon, FR acetate, FR triacetate, and FR lyocell). Examples of suitable rayon fibers are Viscose™ and Modal™ by Lenzing, available

from Lenzing Fibers Corporation. Examples of lyocell fibers include TENCEL G100™ and TENCEL A100™, both available from Lenzing Fibers Corporation. An example of an FR rayon fiber is Lenzing FR™, also available from Lenzing Fibers Corporation.

**[0027]** Secondary fibers that enhance the dyeability/printability of the fabric are referred to herein as “dyeable fibers” and include fibers that are dyeable and dyestuff printable (as opposed to pigment printable). “Dyeable fibers” as used herein include, but are not limited to, modacrylic fibers, cellulosic fibers, meta-aramid fibers, polybenzimidazole (PBI) fibers, melamine fibers, TANLON™ (available from Shanghai Tanlon Fiber Company), rayon, polyester, polyvinyl alcohol, wool, polyetherimide, polyethersulfone, polyamide, and blends thereof. An example of a suitable modacrylic fiber is PROTEX™ available from Kaneka Corporation of Osaka, Japan. Examples of cellulosic fibers include cotton, rayon, acetate, triacetate, and lyocell fibers (as well as their flame resistant counterparts FR cotton, FR rayon, FR acetate, FR triacetate, and FR lyocell). Examples of suitable rayon fibers are Viscose™ and Modal™ by Lenzing, available from Lenzing Fibers Corporation. Examples of lyocell fibers include TENCEL G100™ and TENCEL A100™, both available from Lenzing Fibers Corporation. An example of an FR rayon fiber is Lenzing FR™, also available from Lenzing Fibers Corporation. Examples of meta-aramid fibers include NOMEX™ (available from DuPont), CONEX™ (available from Teijin), and Kermel (available from Kermel). An example of melamine fibers is BASOFIL™ (available from Basofil Fibers).

[0028] Additional secondary fibers suitable for use in the base yarns of the invention include, but are not limited to ultra-high density polyethylene fibers, carbon fibers, silk fibers, polyamide fibers, and polyester fibers. Examples of ultra-high density polyethylene fibers include Dyneema and Spectra. An example of a polyester fiber is VECTRAN™ (available from Kuraray).

[0029] Fabrics according to the invention can have any desirable weight. In some features, single or multi-layer fabrics can have a weight of from about 1 to 20 osy, or from about 3 to 15 osy, or even 3 to 12 osy or 4 to 9 osy.

[0030] As discussed above, the antistatic spun yarns can include any other desirable staple fiber in addition to the antistatic staple fiber. Such staple fibers include, but are not limited to, any of the flame resistant or secondary fibers described above, including blends thereof.

[0031] The present invention is further illustrated by the following examples which illustrate specific features of the invention but are not meant to limit the invention.

#### Example 1

[0032] Sample fabrics having the following construction were prepared and tested against various standards for static electricity in apparel (fiber content listed as a percentage):

Sample	Construction
A	AS: 38/30/12/20 (modacrylic/lyocell/para-aramid/antistat) Base: 48/37/15 (modacrylic/lyocell/para-aramid) Total: 47/37/15/1 (modacrylic/lyocell/para-aramid/antistat) Const: 2-ply AS/2-ply Base twill weave; AS yarns inserted in a grid pattern with an AS yarn inserted

	every 21 <sup>st</sup> yarn in warp direction and every 18 <sup>th</sup> yarn in filling direction Fabric weight: 5.8 osy
B	AS: 44/33/13/10 (modacrylic/lyocell/para-aramid/antistat) Base: 48/37/15 (modacrylic/lyocell/para-aramid) Total: 47.5/37/15/0.5 (modacrylic/lyocell/para-aramid/antistat) Const: 2-ply AS/2-ply Base twill weave; AS yarns inserted in a grid pattern with an AS yarn inserted every 21 <sup>st</sup> yarn in warp direction and every 18 <sup>th</sup> yarn in filling direction Fabric weight: 5.8 osy
C	AS: 46/35/14/5 (modacrylic/lyocell/para-aramid/antistat) Base: 48/37/15 (modacrylic/lyocell/para-aramid) Total: 47.75/37/15/0.25 (modacrylic/lyocell/para-aramid/antistat) Const: 2-ply AS/2-ply Base twill weave; AS yarns inserted in a grid pattern with an AS yarn inserted every 21 <sup>st</sup> yarn in warp direction and every 18 <sup>th</sup> yarn in filling direction Fabric weight: 5.8 osy
D (Control)	AS: N/A Base: 48/37/15 (modacrylic/lyocell/para-aramid) Total: 48/37/15 (modacrylic/lyocell/para-aramid) Const: 2-ply Base twill weave Fabric weight: 5.8 osy

AS: Antistatic spun yarns

Base: Base yarns

Total: Total content of fiber in fabric

Const: fabric construction

antistat: 401-ECS staple fiber

[0033] All of the sample fabrics satisfied the high visibility requirements of ANSI 107.

#### Static Decay

[0034] Static decay testing was conducted for each fabric for compliance with MIL-C-83429B (as tested in accordance with FTMS 191A Test Method 5931), copies of which are appended, with the following results:

Before wash:	Sample				Requirement
	A	B	C	D	
Warp					
+5k A/C	5000	5000	5000	5000	4000 min
Avg Decay Time (sec)	0.04	0.08	0.24	2.14	0.5 sec max
-5k A/C	4750	4833	4750	4583	4000 min
Avg Decay Time (sec)	0.05	0.09	0.28	2.47	0.5 sec max
Filling					
+5k A/C	5000	5000	5000	5000	4000 min
Avg Decay Time (sec)	0.05	0.17	0.28	3.32	0.5 sec max
-5k A/C	4750	4750	4667	4750	4000 min
Avg Decay Time (sec)	0.05	0.15	0.32	3.98	0.5 sec max

[0035] All fabrics including antistatic spun yarns (Samples A, B and C)

satisfied the static decay requirement, while the control (Sample D) did not.

#### Induction Decay

[0036] Induction decay testing was conducted for fabrics A, B and C for compliance with EN 1149-5 (2008) and EN 1149-3 (2004 Method 2 Induction decay).

Each fabric was conditioned and tested at  $23 \pm 1$  °C and  $25 \pm 5\%$  r.h. A cleansing pretreatment of five wash/dry cycles according to EN ISO 6330 (2012 Procedure 5M) was conducted at 50 °C with tumble drying (Procedure F, max. 60 °C outlet temperature). The results are summarized below:

	Sample			EN 1149-5 Standard
	A	B	C	
Gap between threads, mm (mean)	8.0	8.0	8.0	≤ 10 mm
Shielding factor, S (mean)	0.57	0.48	0.36	$S > 0.2$ and/or $t_{50}$ less than 4 seconds
Half decay time ( $t_{50}$ ), seconds (mean)	< 0.01	< 0.01	0.19	

[0037] As can be seen from the test results, each of Samples A, B and C

satisfied the EN 1149-5 requirements for induction decay.

[0038] The induction decay test results can be compared to known prior art

antistatic fabrics, including those including conductive antistatic filament yarns

(Comparative Fabric A) and an intimate blend of antistatic fibers dispersed

throughout the fabric (Comparative Fabric B). Induction decay test results of these

fabrics are provided below for comparison.

[0039] Comparative Fabric A: 47/37/15/1 (modacrylic/lyocell/para-

aramid/Nega-stat® antistatic filament (total content in fabric). Fabric weight: 5.8

osy.

[0040] Comparative Fabric B: 47/36/14/3 (modacrylic/lyocell/para-

aramid/No-Shock® antistatic staple fiber (total content in fabric). Fabric weight: 5.8

osy.

	Comparative Fabric		EN 1149-5 Standard
	A	B	
Gap between threads, mm (mean)	9.0	N/A	≤ 10 mm
Shielding factor, S (mean)	0.67	0.87	S > 0.2 and/or t <sub>50</sub> less than 4 seconds
Half decay time (t <sub>50</sub> ), seconds (mean)	< 0.01	< 0.01	

[0041] Comparative Fabrics A and B, like Samples A, B and C, each satisfied

the EN 1149 requirements as expected. It is notable, however, that the total antistatic

content in the fabrics was 1% (Comparative Fabric A) and 3% (Comparative Fabric

B). As seen above, however, fabrics according to the present invention can be made

with a substantially lower antistatic fiber content while still satisfying the EN 1149

requirements. The reduction in antistatic fiber content reduces the cost of the fabric and makes it easier for the fabric to satisfy high visibility requirements because less of the relatively darker antistatic fibers are included in the fabric. Further, when used in darker shades, fabrics according to the present invention provide a more visually desirable fabric because less of the relatively lighter antistatic fibers are present in the fabric (as compared to the darker base fibers in the fabric).

### Example 2

**[0042]** Another sample fabric having a higher weight and the following construction was prepared and tested for induction decay (fiber content listed as a percentage):

Sample	Construction
E	AS: 38/30/12/20 (modacrylic/lyocell/para-aramid/antistat) Base: 48/37/15 (modacrylic/lyocell/para-aramid) Total: 47/37/15/1 (modacrylic/lyocell/para-aramid/antistat) Const: 2-ply AS/2-ply Base twill weave; AS yarns inserted in a grid pattern with an AS yarn inserted every 25 <sup>th</sup> yarn in warp direction and every 18 <sup>th</sup> yarn in filling direction Fabric weight: 7.4 osy

AS: Antistatic spun yarns

Base: Balance of fabric

Total: Total content of fiber in fabric

Const: fabric construction

antistat: 401-ECS staple fiber

**[0043]** Induction decay testing was conducted for fabric E for compliance with EN 1149-5 (2008) and EN 1149-3 (2004 Method 2 Induction decay). The fabric was conditioned and tested at  $23 \pm 1$  °C and  $25 \pm 5$  % r.h. A cleansing pretreatment of five wash/dry cycles according to EN ISO 6330 (2012 Procedure 4N) was conducted at  $40 \pm 3$  °C with tumble drying (Procedure F, max. 60 °C outlet temperature). Washing

was performed in a Wascator Machine (Type A1) using reference detergent 3. Type III, 100% polyester was utilized as the ballast, and the total air-dry mass of the specimens and ballast was 2.01 kg. The results are summarized below:

	Sample E	EN 1149-5 Standard
Gap between threads, mm (mean)	9.0	≤ 10 mm
Shielding factor, S (mean)	0.64	$S > 0.2$ and/or $t_{50}$ less than 4 seconds
Half decay time ( $t_{50}$ ), seconds (mean)	< 0.01	

[0044] As can be seen from the test results, Sample E satisfied the EN 1149-5 requirements for induction decay.

[0045] Different arrangements of the components depicted in the drawings or described above, as well as components and steps not shown or described are possible. Similarly, some features and subcombinations are useful and may be employed without reference to other features and subcombinations. Features of the invention have been described for illustrative and not restrictive purposes, and alternative features will become apparent to readers of this patent. Accordingly, the present invention is not limited to the features described above or depicted in the drawings, and various features and modifications can be made without departing from the scope of the claims below.

## CLAIMS

We claim:

1. A fabric comprising:

base yarns; and

antistatic spun yarns comprising inductive antistatic staple fibers,

wherein the antistatic spun yarns are located in discrete portions of the fabric such that the fabric complies with one or more standards for static dissipation in fabric.

2. The fabric according to claim 1, characterized in that the standards comprise at least one of EN 1149-5, EN 1149-3, MIL-C-83429B, and FTMS 191A Test Method 5931.

3. The fabric according to any one of claims 1 and 2, characterized in that the antistatic spun yarns comprise less than 20% inductive antistatic staple fibers.

4. The fabric according to any one of the previous claims, characterized in that the antistatic spun yarns are woven or knit into the fabric in a grid pattern or a stripe pattern.

5. The fabric according to any one of the previous claims, characterized in that the fabric is a woven fabric and the antistatic spun yarns are inserted into the fabric in both the warp and filling directions.

6. The fabric according to any one of the previous claims, characterized in that the fabric is a woven fabric and the antistatic spun yarns are woven into the fabric in one or more of the warp and filling directions in a ratio of antistatic spun yarns to base yarns of from 1:1 to 1:40.
7. The fabric according to any one of the previous claims, characterized in that the base yarns are flame resistant yarns and the fabric complies with one or more standards for flame resistant fabrics.
8. The fabric according to any one of the previous claims, characterized in that the fabric complies with one or more standards for high visibility apparel.
9. The fabric according to any one of the previous claims, characterized in that the fabric has a total antistatic fiber content of less than about 1%.
10. The fabric according to any one of the previous claims, characterized in that:
  - the base yarns are flame resistant yarns and the fabric complies with one or more standards for flame resistant fabrics;
  - the fabric complies with one or more standards for high visibility apparel;
  - the antistatic spun yarns comprise from about 2% to 10% inductive antistatic staple fiber, with the balance being non-antistatic fibers;

the total antistatic fiber content in the fabric is from about 0.125% to about 2%;  
and

the fabric is a woven fabric and the antistatic spun yarns are woven in the  
fabric in both the warp and filling directions in a ratio of antistatic spun yarns to  
base yarns of from 1:15 to 1:25.

11. A fabric comprising:

base yarns; and  
antistatic spun yarns comprising less than 20% antistatic staple fibers,  
wherein the antistatic spun yarns are located in discrete portions of the fabric  
such that the fabric complies with one or more standards for static dissipation in  
fabric.

12. The fabric according to claim 11, characterized in that the standards comprise  
at least one of EN 1149-5, EN 1149-3, MIL-C-83429B, and FTMS 191A Test Method  
5931.

13. The fabric according to any one of claims 11 and 12, characterized in that the  
antistatic staple fibers comprise inductive antistatic staple fibers.

14. The fabric according to any one of claims 11 to 13, characterized in that the  
antistatic spun yarns are woven or knit into the fabric in a grid pattern or a stripe  
pattern.

15. The fabric according to any one of claims 11 to 14, characterized in that the fabric is a woven fabric and the antistatic spun yarns are inserted into the fabric in both the warp and filling directions.
16. The fabric according to any one of claims 11 to 15, characterized in that the fabric is a woven fabric and the antistatic spun yarns are woven into the fabric in one or more of the warp and filling directions in a ratio of antistatic spun yarns to base yarns of from 1:1 to 1:40.
17. The fabric according to any one of claims 11 to 16, characterized in that the base yarns are flame resistant yarns and the fabric complies with one or more standards for flame resistant fabrics.
18. The fabric according to any one of claims 11 to 17, characterized in that the fabric complies with one or more standards for high visibility apparel.
19. The fabric according to any one of claims 11 to 18, characterized in that the fabric has a total antistatic fiber content of less than about 1%.
20. The fabric according to any one of claims 11 to 19, characterized in that: the base yarns are flame resistant yarns and the fabric complies with one or more standards for flame resistant fabrics;

the fabric complies with one or more standards for high visibility apparel;  
the antistatic spun yarns comprise from about 2% to 10% inductive antistatic  
staple fiber, with the balance being non-antistatic fibers;  
the fabric has a total antistatic fiber content of from about 0.125% to about 2%;  
and  
the fabric is a woven fabric and the antistatic spun yarns are woven in the  
fabric in both the warp and filling directions in a ratio of antistatic spun yarns to  
base yarns of from 1:15 to 1:25.

# INTERNATIONAL SEARCH REPORT

International application no.

PCT/US 15/18938

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(8) - D04H 1/46 (2015.01)

CPC - D04H 1/46; D04H 13/003; B32B 5/26

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

CPC - D04H 1/46; D04H 13/003; B32B 5/26; IPC(8) - D04H 1/46 (2015.01);

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched  
USPC - 442/402,382

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

PubWEST(USPT,PGPB,EPAB,JPAB); PatBase; Google Scholar.

Search Terms: antistatic spun yarn fabric staple FTMS 191A Test Method 5931 MIL-C-83429B EN 1149-3 EN 1149-5 inductive discharge dissipate

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2014/0041107 A1 (ROSE et al.) 13 February 2014 (13.02.2014), abstract; paras [0007], [0030], [0035], [0042]	1-3, 11-13
A	US 5,030,508 A (Kuhn et al.) 09 July 1991 (09.07.1991) entire document	1-3, 11-13

Further documents are listed in the continuation of Box C.

\* Special categories of cited documents:

“A” document defining the general state of the art which is not considered to be of particular relevance

“E” earlier application or patent but published on or after the international filing date

“L” document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

“O” document referring to an oral disclosure, use, exhibition or other means

“P” document published prior to the international filing date but later than the priority date claimed

“T” later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

“X” document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

“Y” document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

“&” document member of the same patent family

Date of the actual completion of the international search

17 April 2015 (17.04.2015)

Date of mailing of the international search report

**28 MAY 2015**

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US, Commissioner for Patents  
P.O. Box 1450, Alexandria, Virginia 22313-1450

Faxsimile No. 571-273-8300

Authorized officer:

Lee W. Young

PCT Helpdesk: 571-272-4300

PCT OSP: 571-272-7774

**INTERNATIONAL SEARCH REPORT**

PCT/US 15/18938

**Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)**

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1.  Claims Nos.: because they relate to subject matter not required to be searched by this Authority, namely:
  
2.  Claims Nos.: because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
  
3.  Claims Nos.: 4-10, 14-20 because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

**Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)**

This International Searching Authority found multiple inventions in this international application, as follows:

1.  As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2.  As all searchable claims could be searched without effort justifying additional fees, this Authority did not invite payment of additional fees.
3.  As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
  
4.  No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

**Remark on Protest**

- The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- No protest accompanied the payment of additional search fees.