



(86) Date de dépôt PCT/PCT Filing Date: 2003/01/24
(87) Date publication PCT/PCT Publication Date: 2003/08/07
(85) Entrée phase nationale/National Entry: 2004/07/23
(86) N° demande PCT/PCT Application No.: US 2003/002263
(87) N° publication PCT/PCT Publication No.: 2003/065472
(30) Priorités/Priorities: 2002/01/25 (10/057,394) US;
2002/01/25 (60/351,691) US; 2002/03/29 (60/368,832) US;
2002/07/31 (60/400,289) US; 2002/11/19 (60/427,642) US

(51) Cl.Int.⁷/Int.Cl.⁷ H01L 51/20, H01G 9/20


(71) Demandeur/Applicant:
KONARKA TECHNOLOGIES, INC., US

(72) Inventeurs/Inventors:
GAUDIANA, RUSSELL A., US;
LI, LIAN, US;
ECKERT, ROBERT, US;
MONTELLO, ALAN, US;
MONTELLO, EDMUND, US;
RYAN, JAMES, US;
BECKENBAUGH, BILL, US

(74) Agent: SMART & BIGGAR

(54) Titre : STRUCTURES ET SUBSTANCES POUR COLORER DES PILES SOLAIRES

(54) Title: STRUCTURES AND MATERIALS FOR DYE SENSITIZED SOLAR CELLS



(57) Abrégé/Abstract:

Materials of, structures of, and methods of forming photovoltaic cells and modules are described. In particular, the invention, in one embodiment, provides wires to interconnect conductive layers of a cell or module. The photoactive layer may be sintered on a metal foil at either high or low temperatures to form a flexible photovoltaic cell or module. In addition, photovoltaic cells or modules may be formed on rigid substrates to enhance the longevity and durability of the cell or module. Discrete photovoltaic cells or modules may be formed by parting an electrically conductive coating on a polymeric substrate and melting a least a portion of the polymeric substrate, thus encapsulating any debris formed when the conductive layer is parted. In addition, a method of using an ultrasonic slitting device to cut and seal the edges of photovoltaic cells and modules is described.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
7 August 2003 (07.08.2003)

PCT

(10) International Publication Number
WO 2003/065472 A3

(51) International Patent Classification⁷: **H01L 51/20**,
H01G 9/20

(21) International Application Number:
PCT/US2003/002263

(22) International Filing Date: 24 January 2003 (24.01.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/057,394 25 January 2002 (25.01.2002) US
60/351,691 25 January 2002 (25.01.2002) US
60/368,832 29 March 2002 (29.03.2002) US
60/400,289 31 July 2002 (31.07.2002) US
60/427,642 19 November 2002 (19.11.2002) US

(71) Applicant: **KONARKA TECHNOLOGIES, INC.**
[US/US]; 100 Foot of John Street-Boott Mill-South, Third
Floor, Lowell, MA 01852 (US).

(72) Inventors: **GAUDIANA, Russell, A.**; 2 Penrose Lane,
Merrimack, NH 03054 (US). **LI, Lian**; 733 Wellman

Avenue, North Chelmsford, MA 01863 (US). **ECKERT, Robert**; 70 Burlington Street, Lexington, MA 02420 (US).
MONTELLO, Alan; 10 Albion Lane, W. Newbury, MA
01985 (US). **MONTELLO, Edmund**; 1 Back Beach Way,
Rockport, MA 01966 (US). **RYAN, James**; 15 Hayden
Street, Marlboro, MA 01752 (US). **BECKENBAUGH, Bill**; 12 Old Bay Road, New Castle, NH 03854 (US).


(74) Agent: **BIANCO, John, V.**; Testa, Hurwitz & Thibault,
LLP, High Street Tower, 125 High Street, Boston, MA
02110 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC,
VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,

[Continued on next page]

(54) Title: STRUCTURES AND MATERIALS FOR DYE SENSITIZED SOLAR CELLS



(57) Abstract: Materials of, structures of, and methods of forming photovoltaic cells and modules are described. In particular, the invention, in one embodiment, provides wires to interconnect conductive layers of a cell or module. The photoactive layer may be sintered on a metal foil at either high or low temperatures to form a flexible photovoltaic cell or module. In addition, photovoltaic cells or modules may be formed on rigid substrates to enhance the longevity and durability of the cell or module. Discrete photovoltaic cells or modules may be formed by parting an electrically conductive coating on a polymeric substrate and melting a least a portion of the polymeric substrate, thus encapsulating any debris formed when the conductive layer is parted. In addition, a method of using an ultrasonic slitting device to cut and seal the edges of photovoltaic cells and modules is described.

WO 2003/065472 A3

WO 2003/065472 A3



ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(88) Date of publication of the international search report:
15 April 2004

Published:

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Structures and Materials for Dye Sensitized Solar Cells

Cross-reference to Related Applications

[0001] This application claims the benefits of and priority to U.S. Patent Application Serial No. 10/057,394 filed on January 25, 2002, to U.S. Provisional Patent Application
5 Serial No. 60/351,691 filed on January 25, 2002, to U.S. Provisional Patent Application Serial No. 60/368,832 filed on March 29, 2002, to U.S. Provisional Patent Application Serial No. 60/400,289 filed on July 31, 2002, and to U.S. Provisional Patent Application Serial No. 60/427,642 filed on November 19, 2002, all of which are owned by the assignee of the instant application and the disclosures of which are incorporated herein by
10 reference in their entireties.

Field of the Invention

[0002] The invention relates generally to the field of photovoltaic devices, and more specifically to structures and materials for constructing and methods for interconnecting photovoltaic cells to form photovoltaic modules.

15 Background of the Invention

[0003] Thin film solar cells composed of percolating networks of liquid electrolyte and dye-coated sintered titanium dioxide were developed by Dr. Michael Grätzel and coworkers at the Swiss Federal Institute of Technology. These photovoltaic devices fall within a general class of cells referred to as dye-sensitized solar cells ("DSSCs").
20 Conventionally, fabrication of DSSCs requires a high temperature sintering process (> about 400 °C) to achieve sufficient interconnectivity between the nanoparticles and enhanced adhesion between the nanoparticles and a transparent substrate. Although the photovoltaic cells of Grätzel are fabricated from relatively inexpensive raw materials, the high temperature sintering technique used to make these cells limits the cell substrate to
25 rigid transparent materials, such as glass, and consequently limits the manufacturing to batch processes and the applications to those tolerant of the rigid structure. In addition,

the high-temperature sintering technique precludes the use of tempered glass, which is significantly more resistant to thermal and mechanical stresses and strains than ordinary glass, but which loses its temper at the temperatures inherent to a high-temperature sintering technique.

5 **Summary of the Invention**

[0004] The invention, in one embodiment, addresses the deficiencies of the prior art by providing methods and structures for interconnecting flexible photovoltaic cells using a continuous manufacturing process. More particularly, one or more wires in conjunction with an adhesive strip serve as electrically conductive connectors between the photoactive
10 layers of a photovoltaic cell or module. The wire interconnects are compatible with a continuous manufacturing process, such as a roll-to-roll or web process.

[0005] The invention, in one embodiment, also addresses the deficiencies of the prior art by providing a method of scoring a coated base material on which a flexible photovoltaic cell or module is formed. More particularly, in one embodiment, a heated
15 stylus is used to score a coated base material to part the coating and to melt at least a portion of the base material. One advantage of the invention is that any debris that forms in the wake of the heated stylus is encapsulated in the base material when it cools. Therefore, any scoring-related debris cannot interfere with the performance of a photovoltaic cell or module formed using this process.

20 [0006] The invention also provides methods and structures for forming flexible photovoltaic cells and modules. More particularly, an interconnected photosensitized nanoparticle material is formed on a metal foil that is resistant to high-temperature sintering techniques, unlike flexible substrates that deform at high temperatures. The metal foil is then disposed between two flexible substrates to complete the flexible
25 photovoltaic cell or module. Photovoltaic cells and modules may be formed by interconnecting nanoparticles at relatively low temperature (< about 300 °C) on rigid substrates. More particularly, the durability and longevity of photovoltaic cells and modules is enhanced by their fabrication on tempered glass substrates.

[0007] During a continuous manufacturing process, the continuous stream of
30 photovoltaic cells formed on a single substrate is divided into individual photovoltaic

modules that include a plurality of photovoltaic cells. The invention, in one embodiment, provides a method of performing this division using an ultrasonic slitting device. More particularly, ultrasonic energy cuts and seals the leading and trailing edges of a photovoltaic module, thus forming a leak-free, air-tight module.

5 **[0008]** In one aspect, the invention provides a method of connecting a plurality of photovoltaic cells within a photovoltaic module including (i) providing a first base material including a substrate having a first conductive layer; (ii) disposing a photosensitized interconnected nanoparticle material and a charge carrier material on the first conductive layer; (iii) providing a wire; and (iv) joining a second base material
10 including a substrate having a second conductive layer to the first base material, such that the first and second conductive layers are in electrical contact with the wire. In one embodiment, the method includes of claim 1, wherein joining step comprises laminating the conductive layers by disposing an adhesive layer therebetween such that, following the lamination, the wire is embedded in the adhesive layer

15 **[0009]** In another aspect, the invention provides a photovoltaic module that includes (i) a first base material including a substrate having a first conductive layer; (ii) a photosensitized interconnected nanoparticle layer and a charge carrier material disposed on the first conductive layer; (iii) a wire; and (iv) a second base material including a substrate having a second conductive layer. The second base material is joined to the first
20 base material such that the first and second conductive layers are in electrical contact with the wire. In one embodiment, the photovoltaic module includes an adhesive layer disposed between the first and second conductive layers, such that the wire is embedded in the adhesive layer.

25 **[0010]** In one embodiment of the photovoltaic module, the photosensitized interconnected nanoparticle material includes particles with an average size substantially in the range of about 5 nm to about 80 nm. The photosensitized interconnected nanoparticle material may be, for example, titanium oxides, zirconium oxides, zinc oxides, tungsten oxides, niobium oxides, lanthanum oxides, tin oxides, tantalum oxides, or terbium oxides, or one or more combinations thereof. The photosensitized
30 interconnected nanoparticle material may include a photosensitizing agent such as a

xanthine, cyanine, merocyanine, phthalocyanine, and/or pyrrole. The photosensitizing agent may include a metal ion, such as divalent or trivalent metals. The photosensitizing agent may also include at least one of a ruthenium transition metal complex, an osmium transition metal complex, and an iron transition metal complex. In one embodiment of the photovoltaic cell, the charge carrier material includes a redox electrolyte system. In another embodiment, the charge carrier material is a polymeric electrolyte. According to one feature, the charge carrier material transmits at least about 60% of incident visible light.

[0011] In one embodiment of the photovoltaic module, at least one of the first and second base materials is scored. At least one of the first and second base materials may be significantly light transmitting (e.g., a polyethylene terephthalate or polyethylene naphthalate material). At least one of the first and second base materials may be flexible. In one embodiment, the photovoltaic module includes a catalytic media layer disposed between the first and second base materials. The catalytic media layer is, for example, platinum. In one embodiment, the wire is electrically conductive (e.g., a metal wire such as stainless steel, titanium, or copper). A plurality of wires may be disposed between the first and second base materials.

[0012] In one embodiment, the adhesive layer includes a hot melt adhesive. The adhesive may require a curing process. Examples of adhesives include, but are not limited to, epoxies, thermoplastic, thermoset, and ethylene maleic anhydride. In one embodiment, the wire includes a coating of a second metal (e.g., tin or bismuth). The metal may have a melting temperature in the range of about 50 °C to 250 °C, and preferably in the range of about 75 °C to 180 °C. In one embodiment, the metal coated wire may be itself coated with an adhesive prior to joining step. The adhesive may have a lower melting temperature than the second metal.

[0013] In one aspect, the invention provides a method of scoring. The method includes the steps of providing a first coated base material, and scoring the first coated base material at a temperature sufficiently elevated to part the coating and melt at least a portion of the base material.

[0014] According to another aspect, the invention provides a method of forming a photovoltaic module. This method includes the steps of providing a first coated base material, scoring the first coated base material at a temperature sufficiently elevated to part the coating and melt at least a portion of the first base material, providing a second
5 base material, scoring the second coated base material at a temperature sufficiently elevated to part the coating and melt at least a portion of the first coated base material, and joining the first and second coated base materials to form a photovoltaic module.

[0015] According to one embodiment, the melting of the coated base materials disrupts electrical continuity of the base material. According to a further embodiment, the
10 scoring step is performed mechanically, using for example, a heated stylus or a soldering iron tip.

[0016] In another embodiment, the method includes applying a photosensitized interconnected nanoparticle material and a charge carrier material to the coating of the first and/or second base materials. According to one feature of this embodiment, the
15 photosensitized interconnected nanoparticle material includes nanoparticles linked by a polymeric linking agent. According to another feature of this embodiment, the photosensitized interconnected nanoparticle material includes nanoparticles in the range of about 5 nm to about 80 nm. In one feature of this embodiment, the photosensitized interconnected nanoparticle material is selected from the group consisting of titanium
20 oxides, zirconium oxides, zinc oxides, tungsten oxides, niobium oxides, lanthanum oxides, terbium oxides, tantalum oxides, tin oxides, and combinations thereof.

[0017] According to a further embodiment, the photosensitized interconnected nanoparticle material includes a photosensitizing agent that includes a molecule selected from the group consisting of xanthenes, cyanines, merocyanines, phthalocyanines and
25 pyrroles. According to one feature of this embodiment, the photosensitizing agent further includes a metal ion selected from the group consisting of divalent and trivalent metals. According to another feature of this embodiment, the photosensitizing agent includes at least one of a ruthenium transition metal complex, an osmium transition metal complex, and an iron transition metal complex.

[0018] In another embodiment, the charge carrier material includes a redox electrolyte system. In a further embodiment, the charge carrier includes a polymeric electrolyte. Preferably, the charge carrier material transmits at least about 60% of incident visible light.

5 **[0019]** According to one embodiment, the coatings of the first and second base materials include a conductive (or alternatively, semi-conductive) material. According to one feature of this embodiment, at least one of the first and second base materials includes a polyethylene terephthalate or polyethylene naphthalate material. According to another feature, at least one of the first and second base materials is
10 significantly light transmitting and flexible. In one embodiment, the at least one of the coatings of the first and second base materials includes indium tin oxide

[0020] In another aspect, the invention provides a photovoltaic module including a first coated base material having therein a first discontinuity disrupting electrical continuity of its coating; a second coated base material having therein a second
15 discontinuity disrupting electrical continuity of its coating, and a photosensitized interconnected nanoparticle material and a charge carrier material disposed between the coatings of the first and second coated base materials. Preferably, the first and second coated base materials are joined to the photosensitized interconnected nanoparticle material and the charge carrier material such that the first and second base materials are in
20 electrical communication.

[0021] In one aspect, the invention provides a method of forming a photovoltaic cell. The method includes providing a metal foil, applying a nanoparticle material to the metal foil, heating the nanoparticle material to form an interconnected nanoparticle material, and disposing between first and second flexible substrates the metal foil coated with the
25 interconnected nanoparticle material. The method may include disposing a conductive layer between the metal foil and the first flexible substrate, providing a wire; and joining the first and second flexible substrates, such that the conductive layers and the metal foil are in electrical contact with the wire. In one embodiment, the joining step includes laminating the first and second conductive layers by disposing an adhesive layer between
30 them such that, following the lamination, the wire is embedded in the adhesive layer. In

various embodiments, the interconnected nanoparticle material is interconnected using a polylinker at temperatures less than about 300 °C, less than about 150 °C, or at room temperature.

[0022] In another aspect, the invention is directed to a method of forming a photovoltaic module, the method including the steps of: providing a metal foil; applying a nanoparticle material to discrete portions of the metal foil; heating the nanoparticle material to form an interconnected nanoparticle material; slitting the foil to mechanically separate the discrete portions ; and disposing the discrete portions of the metal foil between first and second flexible substrates to form a photovoltaic module.

[0023] According to another aspect, the invention is directed to a photovoltaic cell including a metal foil and an interconnected nanoparticle material formed on the metal foil, the metal foil and the interconnected nanoparticle material formed on the metal foil both being disposed between first and second flexible substrates. In one embodiment, the photovoltaic cell includes a conductive layer disposed between the metal foil and the first flexible substrate, and a wire placed so that the conductive layers of the first and second flexible substrates are in electrical contact with the wire.

[0024] In various aspects of the above mentioned photovoltaic cell and module and methods of forming the same, the interconnected nanoparticle material includes a photosensitized interconnected nanoparticle material. The interconnected nanoparticle material may include particles with an average size in the range of about 5 nm to about 80 nm, or preferably, about 10 nm to about 40 nm. In one embodiment, the photosensitized interconnected nanoparticle material includes, for example, titanium oxide, zirconium oxide, zinc oxide, tungsten oxide, niobium oxide, lanthanum oxide, tantalum oxide, tin oxide, terbium oxide, or one or more combinations thereof. The photosensitized interconnected nanoparticle material may include a photosensitizing agent such as a xanthine, cyanine, merocyanine, phthalocyanine, or pyrrole. The photosensitizing agent may include a metal ion, such as divalent or trivalent metals. The photosensitizing agent may also include at least one of a ruthenium transition metal complex, an osmium transition metal complex, and an iron transition metal complex.

[0025] In one embodiment, a charge carrier material is disposed between the first and second substrates. The charge carrier material may include a redox electrolyte system. In another embodiment, the charge carrier material is a polymeric electrolyte. According to one feature, the charge carrier material transmits at least about 60% of incident visible
5 light.

[0026] In one embodiment, the photovoltaic module and/or cell includes a catalytic media layer disposed between the first and second flexible substrates. The catalytic media layer is, for example, platinum. In one embodiment, at least one of the conductive layers includes indium tin oxide. In one embodiment, the wire is electrically conductive (e.g., a
10 metal wire such as stainless steel or platinum). In another embodiment, a plurality of wires is disposed between the first and second base materials. In one embodiment, the adhesive layer includes a hot melt adhesive. The adhesive may be an epoxy, and the adhesive may require a curing process. In one embodiment, the wire is coated with adhesive prior to laminating.

15 [0027] In another embodiment, at least one of the first and second flexible substrates is significantly light transmitting (e.g., a polyethylene naphthalate or a polyethylene terephthalate material). The first and second flexible substrates may be significantly light-transmitting. In one embodiment, the metal foil includes titanium.

[0028] According to one embodiment, the nanoparticle material is interconnected
20 using a polylinker at temperatures less than about 300 °C. In a further embodiment, the nanoparticle material is interconnected using a polylinker at temperatures less than about 150 °C.

[0029] In one aspect, the invention provides a photovoltaic cell including a charge carrier material and a photosensitized interconnected nanoparticle material including
25 nanoparticles linked by a polymeric linking agent, both disposed between first and second rigid, significantly light-transmitting substrates. The charge carrier material and the photosensitized interconnected nanoparticle material may be disposed between flexible, significantly light-transmitting substrates that are themselves disposed between the first and second rigid, significantly light-transmitting substrates. In one embodiment of the
30 photovoltaic cell, the photosensitized interconnected nanoparticle material includes

particles with an average size substantially in the range of about 5 nm to about 80 nm. The photosensitized interconnected nanoparticle material may include, for example, titanium oxides, zirconium oxides, zinc oxides, tungsten oxides, niobium oxides, lanthanum oxides, tantalum oxides, terbium oxides, tin oxides, or one or more combinations thereof. The photosensitized interconnected nanoparticle material may include a photosensitizing agent such as a xanthine, cyanine, merocyanine, phthalocyanine, and/or pyrrole. The photosensitizing agent may include a metal ion, such as a divalent or trivalent metal. The photosensitizing agent may also include at least one of a ruthenium transition metal complex, an osmium transition metal complex, and an iron transition metal complex. In one embodiment of the photovoltaic cell, the charge carrier material includes a redox electrolyte system involving, for example, a polymeric electrolyte.

[0030] In one embodiment, at least one of the first and second flexible, significantly light-transmitting substrates includes a polyethylene terephthalate or polyethylene naphthalate material. At least one of the first and second rigid, significantly light-transmitting substrates may be tempered glass. In one embodiment, the photovoltaic module includes a catalytic media layer disposed between the first and second rigid, significantly light-transmitting substrates. The catalytic media layer is, for example, platinum. In one embodiment, the photovoltaic cell also includes an electrical conductor material applied to at least one of the first and second rigid, significantly light-transmitting substrates. The electrical conductor material may include indium tin oxide.

[0031] In another aspect, the photovoltaic cell includes a charge carrier material and a photosensitized interconnected nanoparticle material including nanoparticles linked by a polymeric linking agent, both disposed between a rigid, significantly light-transmitting substrate and a flexible, significantly light-transmitting substrate.

[0032] In another aspect, the invention provides a method of interconnecting nanoparticles at low temperatures on a rigid substrate. The method includes providing a rigid substrate, applying a solution comprising a polymeric linking agent and a solvent to the rigid substrate, and contacting a plurality of metal oxide nanoparticles with the solution at a temperature below about 300°C to interconnect at least a portion of the

plurality of metal oxide nanoparticles. In various embodiments, the temperature is below about 200 °C, below about 100°C, or about room temperature. The polymeric linking agent may include a long chain macromolecule, which has (i) a backbone structure substantially similar to a chemical structure of the plurality of metal oxide nanoparticles, and (ii) one or more reactive groups chemically bonded to the backbone structure. In one embodiment, the plurality of metal oxide nanoparticles includes a chemical structure, M_xO_y , where x and y are integers. M may be Ti, Zr, Sn, W, Nb, Ta, and Tb. In one embodiment, the polymeric linking agent is poly(n-butyl titanate). The solvent may be n-butanol. In one embodiment, the rigid substrate is significantly light-transmitting (e.g., tempered glass). The plurality of metal oxide nanoparticles may include titanium oxide, zirconium oxide, zinc oxide, tungsten oxide, niobium oxide, lanthanum oxide, tin oxide, tantalum oxide, terbium oxide, and combinations thereof.

[0033] In one aspect, the invention provides a method of manufacturing photovoltaic modules. The method includes advancing a plurality of photovoltaic cells, and ultrasonically dividing a subset of the plurality of photovoltaic cells into one or more photovoltaic modules. In one embodiment, the dividing step includes substantially and concurrently cutting and sealing the subset of photovoltaic cells into one or more photovoltaic modules. The plurality of photovoltaic cells may include a substantially continuous flexible sheet of photovoltaic cells. In various embodiments, the advancing step is performed as part of a continuous manufacturing process (e.g., a roll-based process). The plurality of photovoltaic cells may be flexible. In one embodiment, cutting and sealing forms a leading edge on a proximal portion of the one or more photovoltaic modules. Cutting and sealing may form a trailing edge on a distal portion of the one or more photovoltaic modules as well.

[0034] Other aspects and advantages of the invention will become apparent from the following drawings, detailed description, and claims, all of which illustrate the principles of the invention, by way of example only.

Brief Description of the Drawings

[0035] The foregoing and other objects, features, and advantages of the invention described above will be more fully understood from the following description of various

illustrative embodiments, when read together with the accompanying drawings. In the drawings, like reference characters generally refer to the same parts throughout the different views. The drawings are not necessarily to scale, and emphasis instead is generally placed upon illustrating the principles of the invention.

5 [0036] Figure 1 depicts an exemplary chemical structure of an illustrative embodiment of a polylinker for nanoparticles of an oxide of metal M, in accordance with the invention;

[0037] Figure 2 depicts another exemplary chemical structure of an illustrative embodiment of a polylinker, according to the invention, for nanoparticles of an oxide of
10 metal M;

[0038] Figure 3A shows an exemplary chemical structure for an interconnected nanoparticle film with a polylinker, according to an illustrative embodiment of the invention;

[0039] Figure 3B shows the interconnected nanoparticle film of Figure 3A attached to
15 a substrate oxide layer, according to an illustrative embodiment of the invention;

[0040] Figure 4 depicts the chemical structure of poly(n-butyl titanate);

[0041] Figure 5A shows the chemical structure of a titanium dioxide nanoparticle film interconnected with poly(n-butyl titanate), according to the invention;

[0042] Figure 5B shows the interconnected titanium dioxide nanoparticle film of
20 Figure 5A attached to a substrate oxide layer, according to an illustrative embodiment of the invention;

[0043] Figure 6 is a cross-sectional view of a flexible photovoltaic cell, according to an illustrative embodiment of the invention;

[0044] Figure 7 depicts an illustrative embodiment of a continuous manufacturing
25 process that may be used to form the flexible photovoltaic cell shown in Figure 6;

[0045] Figure 8 depicts a current-voltage curve for an exemplary solar cell, according to the invention;

[0046] Figure 9 shows a current-voltage curve for an exemplary solar cell, according to an illustrative embodiment of the invention;

[0047] Figure 10 shows current-voltage curves for two additional exemplary solar cells, according to an illustrative embodiment of the invention;

[0048] Figure 11 depicts the chemical structure of gelation induced by a complexing reaction of Li^+ ions with complexable poly(4-vinyl pyridine) compounds, in accordance
5 with an illustrative embodiment of the invention;

[0049] Figure 12 shows the chemical structure of a lithium ion complexing with polyethylene oxide segments, according to another illustrative embodiment of the invention;

[0050] Figures 13A-13C depict chemical structures for exemplary co-sensitizers,
10 according to illustrative embodiments of the invention;

[0051] Figures 14A-14B depict additional exemplary chemical structures of co-sensitizers, according to illustrative embodiments of the invention;

[0052] Figure 15 shows a graph of the absorbance of the 455 nm cut-off filter (GC455) used to characterize photovoltaic cells according to the invention;

15 [0053] Figure 16 shows a graph of the absorbance of diphenylaminobenzoic acid;

[0054] Figure 17 depicts an illustrative embodiment of the coating of a semiconductor primer layer coating, according to the invention;

[0055] Figures 18A and 18B show side elevation views of interconnected photovoltaic modules in unflexed and flexed states, respectively, according to an
20 illustrative embodiment of the invention;

[0056] Figure 19 depicts a cross-sectional view of a photovoltaic cell formed using rigid substrates, according to an illustrative embodiment of the invention;

[0057] Figures 20A and 20B show the scoring of the base material of a photovoltaic cell or module, according to the invention;

25 [0058] Figure 21 depicts a base material suitable for forming a photovoltaic cell or module using wire interconnects, according to the invention;

[0059] Figures 22A and 22B show an exemplary photovoltaic module formed using wire interconnects, according to the invention;

[0060] Figure 23 shows a photovoltaic module formed using a metal foil coated with
30 a photosensitized nanoparticle material, according to the invention;

[0061] Figure 24 depicts an exemplary photovoltaic module capable of receiving radiation through two surfaces, according to the invention.

[0062] Figure 25 depicts a metal wire coated with a metal having a low melting temperature, according to the invention; and

5 [0063] Figure 26 shows an exemplary photovoltaic module with a wire interconnect including a metal coated wire, according to the invention.

Description of the Illustrative Embodiments

A. Low temperature interconnection of nanoparticles

[0064] As discussed in the summary above, the invention, in one embodiment,
10 provides a polymeric linking agent (hereinafter a “polylinker”) that enables the fabrication of thin film solar cells at relatively low “sintering” temperatures (< about 300 °C). Although the term “sintering” conventionally refers to high temperature (> about 400 °C) processes, as used herein, the term “sintering” is not temperature specific, but instead refers generally to the process of interconnecting nanoparticles at any suitable
15 temperature. In one illustrative embodiment, the invention provides a method for using polylinkers to interconnect nanoparticles in a thin film solar cells. According to another illustrative embodiment, the relatively low temperature sintering process enables the manufacture of such photovoltaic cells using flexible polymer substrates. By employing flexible substrates, the invention also enables a continuous roll-to-roll or web
20 manufacturing process to be employed.

[0065] Figures 1 and 2 schematically depict chemical structures of illustrative polylinkers, according to the invention. The particular polylinker structures depicted are for use with nanoparticles of the formula M_xO_y , where M may be, for example, titanium (Ti), zirconium (Zr), tungsten (W), niobium (Nb), lanthanum (La), tantalum (Ta), terbium
25 (Tb), or tin (Sn) and x and y are integers greater than zero. According to the illustrative embodiment of Figure 1, the polylinker **100** includes a backbone structure **102**, which is similar in structure to the metal oxide nanoparticles, and $(OR)_i$ reactive groups, where R may be, for example, acetate, an alkyl, alkene, alkyne, aromatic, or acyl group; or a hydrogen atom and i is an integer greater than zero. Suitable alkyl groups include, but are
30 not limited to, ethyl, propyl, butyl, and pentyl groups. Suitable alkenes include, but are

not limited to, ethene, propene, butene, and pentene. Suitable alkynes include, but are not limited to, ethyne, propyne, butyne, and pentyne. Suitable aromatic group include, but are not limited to, phenyl, benzyl, and phenol. Suitable acyl groups include, but are not limited to, acetyl and benzoyl. In addition, a halogen including, for example, chlorine, bromine, and iodine may be substituted for the (OR)_i reactive groups.

[0066] Referring to Figure 2, the polylinker **110** has a branched backbone structure that includes two -M-O-M-O-M-O- backbone structures, which include (OR)_i reactive groups and (OR)_{i+1} reactive groups, where R may be, for example, one of the atoms, molecules, or compounds listed above and i is an integer greater than zero. The two backbone structures have similar structures to the metal oxide nanoparticles. Collectively, the structure depicted in Figure 2 can be represented by -M(OR)_i-O-(M(OR)_i-O)_n-M(OR)_{i+1}, where i and n are integers greater than zero.

[0067] Figure 3A depicts schematically the chemical structure **300** resulting from interconnecting the M_xO_y nanoparticles **302** with a polylinker **304**. In various embodiments, the polylinker **304** has the chemical structure of the polylinkers **100** and **110** depicted in Figures 1 and 2, respectively. According to the illustrative embodiment, the nanoparticles **302** are interconnected by contacting the nanoparticles **302** with a polylinker **304** at or below room temperature or at elevated temperatures that are less than about 300 °C. Preferably, the polylinker **304** is dispersed in a solvent to facilitate contact with the nanoparticles **302**. Suitable solvents include, but are not limited to, various alcohols, chlorohydrocarbons (e.g., chloroform), ketones, cyclic and linear chain ether derivatives, and aromatic solvents among others. It is believed that the reaction between surface hydroxyl groups of the nanoparticles **302** with alkoxy groups on the polymer chain of the polylinker **304** leads to bridging (or linking) the many nanoparticles **302** together through highly stable covalent links, and as a result, to interconnecting the nanoparticles **302**. It also is believed that since the polylinker **304** is a polymeric material with a chemical structure similar to that of the nanoparticles **302**, even a few binding (or linking) sites between the nanoparticles **302** and the polylinker **304** leads to a highly interconnected nanoparticle film with a combination of electrical and mechanical properties superior to those of a non-sintered or non-interconnected nanoparticle film.

The electrical properties include, for example, electron and/or hole conducting properties that facilitate the transfer of electrons or holes from one nanoparticle to another through, for example, π -conjugation. The mechanical properties include, for example, improved flexibility.

5 **[0068]** Still referring to Figure 3A, at low concentrations of the polylinker **304**, a single polylinker **304** polymer can link many nanoparticles **302** forming a cross-linked nanoparticle network. However, by increasing the concentration of the polylinker **304** polymer, more polylinker **304** molecules may be attached to the surface of the nanoparticles **302** forming polymer-coated nanoparticles **300**. Such polymer-coated
10 nanoparticles **300** may be processed as thin films due to the flexibility of the polymer. It is believed that the electronic properties of the polymer-coated nanoparticles are not affected to a significant extent due to the similar electronic and structural properties between the polylinker polymer and the nanoparticles.

[0069] Figure 3B depicts the chemical structure **306** of an illustrative embodiment of
15 the interconnected nanoparticle film **300** from Figure 3A formed on a flexible substrate **308** that includes an oxide layer coating **310**, which is an electrical conductor. In particular, the polylinkers may be used to facilitate the formation of such nanoparticle films **300** on flexible, significantly light transmitting substrates **308**. As used herein, the term “significantly light transmitting substrate” refers to a substrate that transmits at least
20 about 60% of the visible light incident on the substrate in a wavelength range of operation. Examples of flexible substrates **308** include polyethylene terephthalates (PETs), polyimides, polyethylene naphthalates (PENs), polymeric hydrocarbons, cellulosics, combinations thereof, and the like. PET and PEN substrates may be coated with one or more electrical conducting, oxide layer coatings **310** of, for example, indium
25 tin oxide (ITO), a fluorine-doped tin oxide, tin oxide, zinc oxide, and the like.

[0070] According to one preferred embodiment, by using the illustrative polylinkers, the methods of the invention interconnect nanoparticles **302** at temperatures significantly below 400 °C, and preferably below about 300 °C. Operating in such a temperature range enables the use of the flexible substrates **308**, which would otherwise be destructively
30 deformed by conventional high temperature sintering methods. In one illustrative

embodiment, the exemplary structure **306** is formed by interconnecting the nanoparticles **302** using a polylinker **304** on a substrate **308** at temperatures below about 300 °C. In another embodiment, the nanoparticles **302** are interconnected using a polylinker **304** at temperatures below about 100 °C. In still another embodiment, the nanoparticles **302** are
5 interconnected using a polylinker **304** at about room temperature and room pressure, from about 18 to about 22 °C and about 760 mm Hg, respectively.

[0071] In embodiments where the nanoparticles are deposited on a substrate, the reactive groups of the polylinker bind with the substrate, substrate coating and/or substrate oxide layers. The reactive groups may bind to the substrate, substrate coating
10 and/or substrate oxide layers by, for example, covalent, ionic and/or hydrogen bonding. It is believed that reactions between the reactive groups of the polylinker with oxide layers on the substrate result in connecting nanoparticles to the substrate via the polylinker.

[0072] According to various embodiments of the invention, metal oxide nanoparticles are interconnected by contacting the nanoparticles with a suitable polylinker dispersed in
15 a suitable solvent at or below room temperature or at elevated temperatures below about 300 °C. The nanoparticles may be contacted with a polylinker solution in many ways. For example, a nanoparticle film may be formed on a substrate and then dipped into a polylinker solution. A nanoparticle film may be formed on a substrate and the polylinker solution sprayed on the film. The polylinker and nanoparticles may be dispersed together
20 in a solution and the solution deposited on a substrate. To prepare nanoparticle dispersions, techniques such as, for example, microfluidizing, attritting, and ball milling may be used. Further, a polylinker solution may be deposited on a substrate and a nanoparticle film deposited on the polylinker.

[0073] In embodiments where the polylinker and nanoparticles are dispersed together
25 in a solution, the resultant polylinker-nanoparticle solution may be used to form an interconnected nanoparticle film on a substrate in a single step. In various versions of this embodiment, the viscosity of the polylinker-nanoparticle solution may be selected to facilitate film deposition using printing techniques such as, for example, screen-printing and gravure-printing techniques. In embodiments where a polylinker solution is deposited
30 on a substrate and a nanoparticle film deposited on the polylinker, the concentration of the

polylinker can be adjusted to achieve a desired adhesive thickness. In addition, excess solvent may be removed from the deposited polylinker solution prior to deposition of the nanoparticle film.

[0074] The invention is not limited to interconnection of nanoparticles of a material of formula M_xO_y . Suitable nanoparticle materials include, but are not limited to, sulfides, selenides, tellurides, and oxides of titanium, zirconium, lanthanum, niobium, tin, tantalum, terbium, and tungsten, and combinations thereof. For example, TiO_2 , $SrTiO_3$, $CaTiO_3$, ZrO_2 , WO_3 , La_2O_3 , Nb_2O_5 , SnO_2 , sodium titanate, and potassium niobate are suitable nanoparticle materials.

[0075] The polylinker may contain more than one type of reactive group. For example, the illustrative embodiments of Figures 1-3B depict one type of reactive group OR. However, the polylinker may include several types of reactive groups, e.g., OR, OR', OR'', etc.; where R, R' and R'' are one or more of a hydrogen, alkyl, alkene, alkyne, aromatic, or acyl group or where one or more of OR, OR', and OR'' are a halide. For example, the polylinker may include polymer units of formulas such as, $-[O-M(OR)_i(OR')_j]-$, and $-[O-M(OR)_i(OR')_j(OR'')_k]-$, where i, j and k are integers greater than zero.

[0076] Figure 4 depicts the chemical structure of a representative polylinker, poly(n-butyl titanate) **400** for use with titanium dioxide (TiO_2) nanoparticles. Suitable solvents for poly(n-butyl titanate) **400** include, but are not limited to, various alcohols, chlorohydrocarbons (e.g., chloroform), ketones, cyclic and linear chain ether derivatives, and aromatic solvents among others. Preferably, the solvent is n-butanol. The poly(n-butyl titanate) polylinker **400** contains a branched $-Ti-O-Ti-O-Ti-O-$ backbone structure with butoxy (OBu) reactive groups.

[0077] Figure 5A depicts the chemical structure of a nanoparticle film **500**, which is constructed from titanium dioxide nanoparticles **502** interconnected by poly(n-butyl titanate) polylinker molecules **504**. It is believed that the reaction between surface hydroxyl groups of the TiO_2 nanoparticles **502** with butoxy groups **506** (or other alkoxy groups) of the polylinker **504** leads to the bridging (or linking) of many nanoparticles **502** together through highly stable covalent links, and as a result, interconnecting the

nanoparticles **502**. Furthermore, it is believed that since the polylinker **504** is a polymeric material with a chemical structure similar to that of TiO_2 , even a few binding (or linking) sites between nanoparticles **502** and polylinker **504** will lead to a highly interconnected nanoparticle film **500**, with electronic and mechanical properties superior to those of a non-sintered or non-interconnected nanoparticle film.

[0078] Figure 5B depicts the chemical structure **508** of the nanoparticle film **500** from Figure 5A formed on a substrate **510**, which includes an electrically-conducting oxide layer coating **512**, by applying the polylinker solution to the substrate **510** and then depositing the nanoparticles **502** on the polylinker **504**. In the illustrative example using titanium dioxide nanoparticles **502**, a polylinker solution including poly(n-butyl titanate) **504** is dissolved in n-butanol and applied to the substrate **510**. The concentration of the polylinker **504** can be adjusted to achieve a desired adhesive thickness for the polylinker solution. A titanium dioxide nanoparticulate film **500** is then deposited on the polylinker coated substrate **510**. Reaction between the surface hydroxyl groups of the TiO_2 nanoparticles with reactive butoxy groups **506** (or other alkoxy groups) of poly(n-butyl titanate) **504** results in interconnecting the nanoparticles **502**, as well as connecting nanoparticles **502** with the oxide layers **512** on the substrate **510**.

[0079] Figure 6 depicts a flexible photovoltaic cell **600**, in accordance with the invention, that includes a photosensitized interconnected nanoparticle material **603** and a charge carrier material **606** disposed between a first flexible, significantly light transmitting substrate **609** and a second flexible, significantly light transmitting substrate **612**. In one embodiment, the flexible photovoltaic cell further includes a catalytic media layer **615** disposed between the first substrate **609** and second substrate **612**. Preferably, the photovoltaic cell **600** also includes an electrical conductor **618** deposited on one or both of the substrates **609** and **612**. The methods of nanoparticle interconnection provided herein enable construction of the flexible photovoltaic cell **600** at temperatures and heating times compatible with such substrates **609** and **612**.

[0080] The flexible, significantly light transmitting substrates **609** and **612** of the photovoltaic cell **600** preferably include polymeric materials. Suitable substrate materials include, but are not limited to, PET, polyimide, PEN, polymeric hydrocarbons,

cellulosics, or combinations thereof. Further, the substrates **609** and **612** may include materials that facilitate the fabrication of photovoltaic cells by a continuous manufacturing process such as, for example, a roll-to-roll or web process. The substrate **609** and **612** may be colored or colorless. Preferably, the substrates **609** and **612** are clear and transparent. The substrates **609** and **612** may have one or more substantially planar surfaces or may be substantially non-planar. For example, a non-planar substrate may have a curved or stepped surface (e.g., to form a Fresnel lens) or be otherwise patterned.

[0081] According to the illustrative embodiment, an electrical conductor **618** is deposited on one or both of the substrates **609** and **612**. Preferably, the electrical conductor **618** is a significantly light transmitting material such as, for example, ITO, a fluorine-doped tin oxide, tin oxide, zinc oxide, or the like. In one illustrative embodiment, the electrical conductor **618** is deposited as a layer between about 100 nm and about 500 nm thick. In another illustrative embodiment, the electrical conductor **618** is between about 150 nm and about 300 nm thick. According to a further feature of the illustrative embodiment, a wire or lead line may be connected to the electrical conductor **618** to electrically connect the photovoltaic cell **600** to an external load.

[0082] The photosensitized interconnected nanoparticle material **603** may include one or more types of metal oxide nanoparticles, as described in detail above.. In one embodiment, the photosensitized interconnected nanoparticle material **603** includes nanoparticles with an average size of between about 2 nm and about 100 nm. In another embodiment, the photosensitized nanoparticle material **603** includes nanoparticles with an average size of between about 10 nm and about 40 nm. Preferably, the nanoparticles are titanium dioxide particles having an average particle size of about 20 nm.

[0083] A wide variety of photosensitizing agents may be applied to and/or associated with the nanoparticles to produce the photosensitized interconnected nanoparticle material **603**. The photosensitizing agent facilitates conversion of incident visible light into electricity to produce the desired photovoltaic effect. It is believed that the photosensitizing agent absorbs incident light resulting in the excitation of electrons in the photosensitizing agent. The energy of the excited electrons is then transferred from the excitation levels of the photosensitizing agent into a conduction band of the

interconnected nanoparticles **603**. This electron transfer results in an effective separation of charge and the desired photovoltaic effect. Accordingly, the electrons in the conduction band of the interconnected nanoparticles are made available to drive an external load electrically connected to the photovoltaic cell.

5 In one illustrative embodiment, the photosensitizing agent is sorbed (e.g., chemisorbed and/or physisorbed) on the interconnected nanoparticles **603**. The photosensitizing agent may be sorbed on the surfaces of the interconnected nanoparticles **603**, throughout the interconnected nanoparticles **603**, or both. The photosensitizing agent is selected, for example, based on its ability to absorb photons in a wavelength range of operation, its
10 ability to produce free electrons (or electron holes) in a conduction band of the interconnected nanoparticles **603**, and its effectiveness in complexing with or sorbing to the interconnected nanoparticles **603**. Suitable photosensitizing agents may include, for example, dyes that include functional groups, such as carboxyl and/or hydroxyl groups, that can chelate to the nanoparticles, e.g., to Ti(IV) sites on a TiO₂ surface. Examples of
15 suitable dyes include, but are not limited to, anthocyanins, porphyrins, phthalocyanines, merocyanines, cyanines, squarates, eosins, and metal-containing dyes such as, for example, *cis*-bis(isothiocyanato)bis(2,2'-bipyridyl-4,4'-dicarboxylato)-ruthenium(II) ("N3 dye"); tris(isothiocyanato)-ruthenium(II)-2,2':6,2''-terpyridine-4,4',4''-tricarboxylic acid; *cis*-bis(isothiocyanato)bis(2,2'-bipyridyl-4,4'-dicarboxylato)-ruthenium(II) bis-
20 tetrabutylammonium; *cis*-bis(isocyanato) (2,2'-bipyridyl-4,4' dicarboxylato) ruthenium (II); and tris(2,2'-bipyridyl-4,4'-dicarboxylato) ruthenium (II) dichloride, all of which are available from Solaronix.

[0084] The charge carrier material **606** portion of the photovoltaic cells may form a layer in the photovoltaic cell, be interspersed with the material that forms the
25 photosensitized interconnected nanoparticle material **603**, or be a combination of both. The charge carrier material **606** may be any material that facilitates the transfer of electrical charge from a ground potential or a current source to the interconnected nanoparticles **603** (and/or a photosensitizing agent associated therewith). A general class of suitable charge carrier materials can include, but are not limited to solvent based liquid
30 electrolytes, polyelectrolytes, polymeric electrolytes, solid electrolytes, n-type and p-type

transporting materials (e.g., conducting polymers), and gel electrolytes, which are described in more detail below.

[0085] Other choices for the charge carrier material **606** are possible. For example, the electrolyte composition may include a lithium salt that has the formula LiX , where X is an iodide, bromide, chloride, perchlorate, thiocyanate, trifluoromethyl sulfonate, or hexafluorophosphate. In one embodiment, the charge carrier material **606** includes a redox system. Suitable redox systems may include organic and/or inorganic redox systems. Examples of such systems include, but are not limited to, cerium(III) sulfate/cerium(IV), sodium bromide/bromine, lithium iodide/iodine, $\text{Fe}^{2+}/\text{Fe}^{3+}$, $\text{Co}^{2+}/\text{Co}^{3+}$, and viologens. Furthermore, an electrolyte solution may have the formula M_iX_j , where i and j are ≥ 1 . X is an anion, and M is selected from the group consisting of Li, Cu, Ba, Zn, Ni, lanthanides, Co, Ca, Al, and Mg. Suitable anions include, but are not limited to, chloride, perchlorate, thiocyanate, trifluoromethyl sulfonate, and hexafluorophosphate.

[0086] In some illustrative embodiments the charge carrier material **606** includes a polymeric electrolyte. In one version, the polymeric electrolyte includes poly(vinyl imidazolium halide) and lithium iodide. In another version, the polymeric electrolyte includes poly(vinyl pyridinium salts). In still another embodiment, the charge carrier material **606** includes a solid electrolyte. In one version, the solid electrolyte includes lithium iodide and pyridinium iodide. In another version, the solid electrolyte includes substituted imidazolium iodide.

[0087] According to some illustrative embodiments, the charge carrier material **606** includes various types of polymeric polyelectrolytes. In one version, the polyelectrolyte includes between about 5% and about 100% (e.g., 5-60%, 5-40%, or 5-20%) by weight of a polymer, e.g., an ion-conducting polymer, about 5% to about 95%, e.g., about 35-95%, 60-95%, or 80-95%, by weight of a plasticizer and about 0.05 M to about 10 M of a redox electrolyte, e.g., about 0.05 M to about 10 M, e.g., 0.05-2 M, 0.05-1 M, or 0.05-0.5 M, of organic or inorganic iodides, and about 0.01 M to about 1 M, e.g., 0.05-5 M, 0.05-2 M, or 0.05-1 M, of iodine. The ion-conducting polymer may include, for example, polyethylene oxide (PEO), polyacrylonitrile (PAN), polymethylmethacrylate (acrylic) (PMMA), polyethers, and polyphenols. Examples of suitable plasticizers include, but are not limited

to, ethyl carbonate, propylene carbonate, mixtures of carbonates, organic phosphates, butyrolactone, and dialkylphthalates.

[0088] Preferably, the flexible photovoltaic cell 600 also includes a catalytic media layer 615 disposed between the substrates 609 and 612. According to the illustrative
5 embodiment, the catalytic media layer 615 is in electrical contact with the charge carrier material 606. The catalytic media 615 may include, for example, ruthenium, osmium, cobalt, rhodium, iridium, nickel, activated carbon, palladium, platinum, or hole transporting polymers (e.g., poly(3,4-ethylene dioxythiophene and polyaniline). Preferably, the catalytic media 615 further includes titanium, or some other suitable metal,
10 to facilitate adhesion of the catalytic media to a substrate and/or substrate coating. Preferably, the titanium is deposited in regions or a layer about 10 Å thick. In one embodiment, the catalytic media 615 includes a platinum layer between about 13 Å and about 35 Å thick. In another embodiment, the catalytic media 615 includes a platinum layer between about 15 Å and about 50 Å thick. In another embodiment, the catalytic
15 media 615 includes a platinum layer between about 50 Å and about 800 Å thick. Preferably, the catalytic media 615 includes a platinum layer about 25 Å thick.

[0089] In another aspect, the invention also provides methods of forming a layer of interconnected metal oxide nanoparticles on a substrate using a continuous manufacturing process, such as, for example, a roll-to-roll or web process. These methods may be used,
20 for example, to produce DSSCs. The current processes for producing DSSCs in large numbers, for example using a continuous and cost effective assembly line process, are extremely difficult at best. The difficulties associated with a continuous assembly process for a DSSC may arise from the cell support or substrate, which is generally rigid and typically includes thermally resistant materials such as glass and metal. The primary
25 reason for this is related to the high temperature sintering process for producing fused nanocrystals (typically about 400-500 °C). Rigid substrate materials, by their very nature, generally do not lend themselves to a continuous process for manufacture, but rather to a more expensive batch process.

[0090] Figure 7 depicts an illustrative embodiment of a continuous manufacturing
30 process 700 that may be used to form the photovoltaic cell shown in Figure 6. According

to the illustrative embodiment, an interconnected nanoparticle film is formed on an advancing substrate sheet **705**, which may be continuously advanced, periodically advanced, and/or irregularly advanced during a manufacturing run using rollers **708**. In this illustrative embodiment, the electrical conductor material **710**, which serves as the basis for one electrode of a photovoltaic cell, is deposited on the advancing substrate **705**. In various embodiments, the electrical conductor material **710** may be deposited on a target region of the substrate **705** by thermal evaporation or low temperature sputtering. In addition, the electrical conductor material **710** may be deposited, for example, by vacuum deposition.

10 **[0091]** According to the illustrative embodiment shown in Figure 7, the photosensitized nanoparticle material **715** is then deposited. As described above, the photosensitized nanoparticle material **715** may be formed by applying a solution having a polylinker and metal oxide nanoparticles onto the advancing substrate sheet **705**. The polylinker-nanoparticle solution may be applied by any suitable technique including, but not limited to, dip tanks, extrusion coating, spray coating, screen printing, and gravure printing. In other illustrative embodiments, the polylinker solution and metal oxide nanoparticles are separately applied to the advancing substrate sheet **705** to form the photosensitized nanoparticle material **715**. In one illustrative embodiment, the polylinker solution is applied to the advancing substrate **705** and the metal oxide nanoparticles (preferably dispersed in a solvent) are disposed on the polylinker. In another illustrative embodiment, the metal oxide nanoparticles (preferably dispersed in a solvent) are applied to the advancing substrate **705** and the polylinker solution is applied to the nanoparticles to form the photosensitized nanoparticle material **715**. As described above with regard to Figure 6, a wide variety of photosensitizing agents may be applied to and/or associated with the nanoparticles to produce the photosensitized nanoparticle material **715**.

25 **[0092]** After deposition of the photosensitized nanomatrix material **715**, the substrate sheet **705** may proceed to further processing stations depending on the ultimate product desired. According to this illustrative embodiment, the charge carrier material **720**, which facilitates the transfer of electrical charge from a ground potential or a current source to the photosensitized nanoparticle material **715**, is deposited. The charge carrier material

30

720 may be applied by, for example, spray coating, roller coating, knife coating, or blade coating. The charge carrier media 720 may be prepared by forming a solution having an ion-conducting polymer, a plasticizer, and a mixture of iodides and iodine. The polymer provides mechanical and/or dimensional stability; the plasticizer helps the gel/liquid
5 phase transition temperature; and the iodides and iodine act as redox electrolytes.

[0093] Still referring to Figure 7, the catalytic media layer 725, which facilitates the transfer of electrons ejected by the photoexcited molecules within the photovoltaic cell, is then deposited. Subsequently, a second electrical conductor layer 730 is deposited. The second electrical conductor layer 730 serves as the basis for a second electrode of the
10 photovoltaic cell. A second, flexible substrate 735 is then unwound and applied to the advancing sheet 705 to complete the photovoltaic cell using the continuous manufacturing process 700. An ultrasonic slitting device 740 may be employed to simultaneously cut and seal a leading and trailing edge of a plurality of photovoltaic cells, thus forming photovoltaic modules. The ultrasonic slitting procedure is discussed in more detail
15 below.

[0094] Further illustrative examples of the invention in the context of a DSSC including titanium dioxide nanoparticles are provided below. The following examples are illustrative and not intended to be limiting. Accordingly, it is to be understood that the invention may be applied to a wide range of nanoparticles including, but not limited to,
20 SrTiO_3 , CaTiO_3 , ZrO_2 , WO_3 , La_2O_3 , Nb_2O_5 , sodium titanate, and potassium niobate nanoparticles. In addition, it should be realized that the invention is generally applicable to formation of interconnected nanoparticles for a wide variety of applications in addition to DSSC, such as, for example, metal oxide and semiconductor coatings.

Example 1. Dip-Coating Application of Polylinker

25 [0095] In this illustrative example, a DSSC was formed as follows. A titanium dioxide nanoparticle film was coated on a $\text{SnO}_2\text{:F}$ coated glass slide. The polylinker solution was a 1% (by weight) solution of the poly(n-butyl titanate) in n-butanol. In this embodiment, the concentration of the polylinker in the solvent was preferably less than 5% by weight. To interconnect the particles, the nanoparticle film coated slide was
30 dipped in the polylinker solution for 15 minutes and then heated at 150 °C for 30 minutes.

The polylinker treated TiO₂ film was then photosensitized with a 3×10^{-4} N3 dye solution for 1 hour. The polylinker treated TiO₂ film coated slide was then fabricated into a 0.6 cm² photovoltaic cell by sandwiching a triiodide based liquid redox electrolyte between the TiO₂ film coated slide a platinum coated SnO₂:F glass slide using 2 mil SURLYN
5 1702 hot melt adhesive available from DuPont. The platinum coating was approximately 60 nm thick. The cell exhibited a solar conversion efficiency of as high as 3.33% at AM 1.5 solar simulator conditions (i.e., irradiation with light having an intensity of 1000 W/m²). The completed solar cells exhibited an average solar conversion efficiency (“ η ”) of 3.02%; an average open circuit voltage (“V_{oc}”) of 0.66 V; an average short circuit
10 current (“I_{sc}”) of 8.71 mA/cm², and an average fill factor of 0.49 (0.48 to 0.52). Figure 8 depicts a graph 800 that shows the current-voltage curve 802 for the dip-coated photovoltaic cell.

Example 2. Polylinker-Nanoparticle Solution Application

[0096] In this illustrative example, a 5.0 mL suspension of titanium dioxide (P25,
15 which is a titania that includes approximately 80% anatase and 20% rutile crystalline TiO₂ nanoparticles and which is available from Degussa-Huls) in n-butanol was added to 0.25 g of poly(n-butyl titanate) in 1 mL of n-butanol. In this embodiment, the concentration of the polylinker in the polylinker-nanoparticle solution was preferably less than about 50% by weight. The viscosity of the suspension changed from milk-like to toothpaste-like with
20 no apparent particle separation. The paste was spread on a patterned SnO₂:F coated glass slide using a Gardner knife with a 60 μ m thick tape determining the thickness of wet film thickness. The coatings were dried at room temperature forming the films. The air-dried films were subsequently heat treated at 150 °C for 30 minutes to remove solvent, and sensitized overnight with a 3×10^{-4} M N3 dye solution in ethanol. The sensitized
25 photoelectrodes were cut into desired sizes and sandwiched between a platinum (60 nm thick) coated SnO₂:F coated glass slide and a tri-iodide based liquid electrolyte. The completed solar cells exhibited an average η of 2.9% (2.57% to 3.38%) for six cells at AM 1.5 conditions. The average V_{oc} was 0.68 V (0.66 to 0.71 V); the average I_{sc} was 8.55 mA/cm² (7.45 to 10.4 mA/cm²); and the average fill factor was 0.49 (0.48 to 0.52).

Figure 9 depicts a graph 900 showing the current-voltage curve 902 for the photovoltaic cell formed from the polylinker-nanoparticle solution.

Example 3. DSSC Cells Formed Without Polylinker

[0097] In this illustrative example, an aqueous titanium dioxide suspension (P25) containing about 37.5 % solid content was prepared using a microfluidizer and was spin coated on a fluorinated SnO₂ conducting electrode (15 Ω/cm²) that was itself coated onto a coated glass slide. The titanium dioxide coated slides were air dried for about 15 minutes and heat treated at 150 °C for 15 minutes. The slides were removed from the oven, cooled to about 80 °C, and dipped into 3 x 10⁻⁴ M N3 dye solution in ethanol for about 1 hour. The sensitized titanium dioxide photoelectrodes were removed from dye solution rinsed with ethanol and dried over a slide warmer at 40 °C. The sensitized photoelectrodes were cut into small pieces (0.7 cm x 0.5-1 cm active area) and sandwiched between platinum coated SnO₂:F-transparent conducting glass slides. A liquid electrolyte containing 1 M LiI, 0.05 M iodine, and 1 M t-butyl pyridine in 3-methoxybutyronitrile was applied between the photoelectrode and platinized conducting electrode through capillary action. Thus constructed photocells exhibited an average solar conversion efficiency of about 3.83 % at AM 1.5 conditions. The η at AM 1.5 conditions and the photovoltaic characteristics I_{sc}, V_{oc}, voltage at maximum power output ("V_m"), and current at maximum power output ("I_m") of these cells are listed in Table 1 under column A. Figure 10 depicts a graph 1000 showing the current-voltage curve 1002 for the photovoltaic cell formed without the polylinker.

Table 1

	A	B	C	D	E	
	Untreated	0.1 % poly- mer soln.	0.4 % poly- mer soln.	1 % poly- mer soln.	2 % poly- mer soln.	
5	η (%)	Avg = 3.83 (3.37-4.15)	Avg. = 4.30 (4.15-4.55)	Avg = 4.55 (4.4-4.82)	Avg = 4.15 (3.48-4.46)	Avg = 4.15 (3.7-4.58)
10	I_{sc} (mA/cm ²)	Avg = 10.08 (8.88-10.86)	Avg = 10.96 (10.44-11.5)	Avg = 10.60 (9.79-11.12)	Avg = 11.00 (10.7-11.28)	Avg = 11.24 (10.82-11.51)
	V_{oc} (V)	Avg = 0.65 (0.65-0.66)	Avg = 0.66 (0.6-0.7)	Avg = 0.71 (0.69-0.74)	Avg = 0.7 (0.69-0.71)	Avg = 0.69 (0.68-0.71)
15	V_m (V)	Avg = 0.454 (0.43-0.49)	Avg = 0.46 (0.43-0.477)	Avg = 0.50 (0.47-0.53)	Avg = 0.45 (0.4-0.47)	Avg = 0.44 (0.42-0.46)
	I_m (mA/cm ²)	Avg = 8.4 (7.5-8.96)	Avg = 9.36 (8.75-9.71)	Avg = 9.08 (8.31-9.57)	Avg = 9.14 (8.70-9.55)	Avg = 9.28 (8.66-9.97)

20 *Example 4. DSSC Cells Formed With Various Concentrations of Polylinker Solution*

[0098] In this illustrative example, a P25 suspension containing about 37.5 % solid content was prepared using a microfluidizer and was spin coated on fluorinated SnO₂ conducting electrode (15 Ω /cm²) coated glass slide. The titanium dioxide coated slides were air dried for about 15 minutes and heat treated at 150 °C for 15 minutes. The

25 titanium dioxide coated conducting glass slide were dipped into a polylinker solution including poly(n-butyl titanate) in n-butanol for 5 minutes in order to carry out interconnection (polylinking) of nanoparticles. The polylinker solutions used were 0.1 wt% poly(n-butyl titanate), 0.4 wt% poly(n-butyl titanate), 1 wt% poly(n-butyl titanate), and 2 wt% poly(n-butyl titanate). After 5 minutes, the slides were removed from the

30 polylinker solution, air dried for about 15 minutes and heat treated in an oven at 150 °C for 15 minutes to remove solvent. The slides were removed from the oven, cooled to about 80 °C, and dipped into 3 x 10⁻⁴ M N3 dye solution in ethanol for about 1 hour. The sensitized titanium dioxide photoelectrodes were removed from dye solution, rinsed with ethanol, and dried over a slide warmer at 40 °C. The sensitized photoelectrodes were cut

35 into small pieces (0.7 cm x 0.5-1 cm active area) and sandwiched between platinum coated SnO₂:F-transparent conducting glass slides. A liquid electrolyte containing 1 M

LiI, 0.05 M iodine, and 1 M t-butyl pyridine in 3-methoxybutyronitrile was applied between the photoelectrode and platinized conducting electrode through capillary action. The η at AM 1.5 conditions and the photovoltaic characteristics I_{sc} , V_{oc} , V_m , and I_m of the constructed cells are listed in Table 1 for the 0.1 wt% solution under column B, for the 0.4
5 wt% solution under column C, for the 1 wt% solution under column D, and for the 2 wt% solution under column E. Figure 10 depicts the current-voltage curve 1008 for the photovoltaic cell formed with the polylinker.

Example 5. Modifier Solutions

[0099] In this illustrative example, titanium dioxide coated transparent conducting
10 oxide coated glass slides were prepared by spin coating process as described in Example 4. The titanium oxide coated conducting glass slides were treated with polylinker solution including a 0.01 M poly(n-butyl titanate) solution in n-butanol for 5 minutes to interconnect the nanoparticles. The slides were air dried for about 5 minutes after removing from the polylinker solution. The slides were later dipped into a modifier
15 solution for about 1 minute. The modifier solutions used were 1:1 water/ethanol mixture, 1 M solution of t-butyl pyridine in 1:1 water/ethanol mixture, 0.05 M HCl solution in 1:1 water/ethanol mixture. One of the slides was treated with steam from humidifier for 15 seconds. The slides were air dried for 15 minutes and heat-treated at 150 °C for 15 minutes to remove solvent and then sensitized with a 3×10^{-4} M N3 dye solution for 1
20 hour. The sensitized photoelectrodes were sandwiched between platinized $\text{SnO}_2\text{:F}$ coated glass slides and studied for photovoltaic characteristics using a liquid electrolyte containing 1 M LiI, 0.05 M iodine, and 1 M t-butyl pyridine in 3-methoxybutyronitrile. Acid seems to help in increasing the photoconductivity and efficiency of these photocells. The η at AM 1.5 conditions and the photovoltaic characteristics of the cells of this
25 example are listed in Table 2 as follows: slides not dipped into a modifier solution and not treated with polylinker solution (column A); slides not dipped into a modifier, but treated with polylinker solution (column B); slides were first treated with polylinker solution and then dipped in 1:1 water/ethanol mixture (column C); slides were first treated with polylinker solution and then dipped in 1 M solution of t-butyl pyridine in 1:1
30 water/ethanol mixture (column D); slides were first treated with polylinker solution and

then dipped in 0.05 M HCl solution in 1:1 water/ethanol mixture (column E); and slides were first treated with polylinker solution and then treated with steam from humidifier (column F).

Table 2

5		A	B	C	D	E	F
		Untreated	Treated with 0.01M TiBut	Treated with 1:1 EtOH/H ₂ O	Treated with 1M t-BuPy/1:1 EtOH/H ₂ O	Treated with 0.05M HCl/1:1 EtOH/H ₂ O	Steam from Humidifier for 15 sec.
10	η (%)	Avg = 3.92 (3.75-4.15)	Avg =4.41 (4.12-4.74)	Avg = 4.11 (4.06-4.15)	Avg = 4.34 (4.27-4.38)	Avg = 4.67 (4.61-4.73)	Avg = 4.41 (4.38-4.45)
15	V _{oc} (V)	Avg = 0.66 (0.66-0.67)	Avg = 0.66 (0.65-0.66)	Avg = 0.65 (0.64-0.65)	Avg = 0.65 (0.64-0.66)	Avg = 0.66 (0.65-0.66)	Avg = 0.66 (0.66-0.67)
20	I _{sc} (mA/cm ²)	Avg = 9.97 (9.48-10.56)	Avg =12.57 (11.7-13.22)	Avg =11.85 (11.21-12.49)	Avg =11.85 (11.21-12.49)	Avg =12.51 (12.15-12.87)	Avg =11.63 (11.25-12.01)
	V _m (V)	Avg =0.468 (0.46-0.48)	Avg =0.434 (0.4-0.457)	Avg = 0.44 (0.43-0.45)	Avg = 0.45 (0.44-0.456)	Avg =0.457 (0.453-0.46)	Avg = 0.45 (0.44-0.46)
25	I _m (mA/cm ²)	Avg = 8.36 (7.85-8.89)	Avg =10.08 (9.57-10.37)	Avg = 9.27 (9.01-9.53)	Avg = 9.52 (9.22-9.75)	Avg =10.23 (10.17-10.29)	Avg = 9.67 (9.38-9.96)

Example 6. Post-Interconnection Heating to 150 °C

[00100] In this illustrative example, a titanium-dioxide-coated, transparent-conducting-oxide-coated glass slide was prepared by a spin coating process as described in Example 4. The slide was dipped into 0.01 M poly(n-butyl titanate) in n-butanol for 30 seconds and was air-dried for 15 minutes. The slide was later heat treated at 150 °C for 10 minutes in an oven. The heat-treated titanium oxide layer was sensitized with N3 dye solution for 1 hour, washed with ethanol, and warmed on a slide warmer at 40 °C for 10 minutes. The sensitized photoelectrodes were cut into 0.7 cm x 0.7 cm active area photocells and were sandwiched between platinized conducting electrodes. A liquid electrolyte containing 1 M LiI, 0.05 M iodine, and 1 M t-butyl pyridine in 3-methoxybutyronitrile was applied between the photoelectrode and platinized conducting electrode through capillary action. The photocells exhibited an average η of 3.88 % (3.83, 3.9 and 3.92), an average V_{oc} of 0.73 V (0.73, 0.74 and 0.73 V), and an average I_{sc} of 9.6 mA/cm² (9.88, 9.65 and 9.26), all at AM 1.5 conditions.

15 *Example 7. Post-Interconnection Heating to 70 °C*

[00101] In this illustrative example, a titanium-dioxide-coated, transparent-conducting-oxide-coated glass slide was prepared by a spin coating process as described in Example 4. The slide was dipped into 0.01 M poly(n-butyl titanate) in n-butanol for 30 seconds and was air-dried for 15 minutes. The slide was later heat treated at 70 °C for 10 minutes in an oven. The heat-treated titanium oxide layer was sensitized with N3 dye solution for 1 hour, washed with ethanol, and warmed on a slide warmer at 40 °C for 10 minutes. The sensitized photoelectrodes were cut into 0.7 cm x 0.7 cm active area photocells and were sandwiched between platinized conducting electrodes. A liquid electrolyte containing 1 M LiI, 0.05 M iodine, and 1 M t-butyl pyridine in 3-methoxybutyronitrile was applied between the photoelectrode and platinized conducting electrode through capillary action. The photocells exhibited an average η of 3.62 % (3.55, 3.73 and 3.58), an average V_{oc} of 0.75 V (0.74, 0.74 and 0.76 V), and average I_{sc} of 7.96 mA/cm² (7.69, 8.22 and 7.97), all at AM 1.5 conditions.

Example 8. Formation on a Flexible, Transparent Substrate

[00102] In this illustrative example, a PET substrate about 200 μm thick and about 5 inches by 8 feet square was coated with ITO and loaded onto a loop coater. An 18.0 mL suspension of titanium dioxide (P25 with 25% solid content) in n-butanol and 0.5 g of poly(n-butyl titanate) in 10 mL of n-butanol were in-line blended and coated onto the ITO coated PET sheet. After deposition, the coating was heated at about 50 °C for about 1 minute. The interconnected nanoparticle layer was then dye-sensitized by coating with a 3×10^{-4} M solution of N3 dye in ethanol.

B. Gel electrolytes for DSSCs

10 [00103] According to further illustrative embodiments, the invention provides electrolyte compositions that include multi-complexable molecules (i.e., molecules containing 2 or more ligands capable of complexing) and redox electrolyte solutions, which are gelled using metal ions, such as lithium ions. The multi-complexable compounds are typically organic compounds capable of complexing with a metal ion at a plurality of sites. The electrolyte composition can be a reversible redox species that may be liquid by itself or solid components dissolved in a non-redox active solvent, which serves as a solvent for the redox species and does not participate in reduction-oxidation reaction cycle. Examples include common organic solvents and molten salts that do not contain redox active ions. Examples of redox species include, for example,

15 iodide/triiodide, $\text{Fe}^{2+}/\text{Fe}^{3+}$, $\text{Co}^{2+}/\text{Co}^{3+}$, and viologens, among others. The redox components are dissolved in non-aqueous solvents, which include all molten salts. Iodide based molten salts, e.g., methylpropylimidazolium iodide, methylbutylimidazolium iodide, methylhexylimidazolium iodide, etc., are themselves redox active and can be used as redox active liquids by themselves or diluted with non-redox active materials like common organic solvents or molten salts that do not undergo oxidation-reduction reaction cycles. Multi-dendate inorganic ligands may also be a source of gelling compounds.

[00104] Figure 11 depicts an illustrative embodiment of an electrolyte gelled using metal ions. Lithium ions are shown complexed with poly(4-vinyl pyridine). The lithium ions and the organic compounds, in this instance poly(4-vinyl pyridine) molecules capable of complexing at a plurality of sites with the lithium ions, can be used to gel a suitable

25
30

electrolyte solution. An electrolyte composition prepared in accordance with the invention may include small amounts of water, molten iodide salts, an organic polymer, and other suitable compound gels upon the addition of a metal ion such as lithium. Gelled electrolytes may be incorporated into individual flexible photovoltaic cells, traditional solar cells, photovoltaic fibers, interconnected photovoltaic modules, and other suitable devices. The dotted lines shown in Figure 11 represent the type of bonding that occurs in a photovoltaic gel electrolyte when the constituent electrolyte solution and organic compounds gel after the introduction of a suitable metal ion.

[00105] A non-exhaustive list of organic compounds that are capable of complexing with the metal ion at a plurality of sites, and which are suitable for use in the invention, include various polymers, starburst/dendrimeric molecules, and other molecules containing multiple functional groups, e.g., urethanes, esters, ethylene/propylene oxide/imines segments, pyridines, pyrimidines, N-oxides, imidazoles, oxazoles, triazoles, bipyridines, quinolines, polyamines, polyamides, ureas, β -diketones, and β -hydroxy ketones.

[00106] More generally, the multi-complexable molecules employed in various embodiments may be polymeric or small organic molecules that possess two or more ligand or ligating groups capable of forming complexes. Ligating groups are functional groups that contain at least one donor atom rich in electron density, e.g., oxygen, nitrogen, sulfur, or phosphorous, among others and form monodentate or multidentate complexes with an appropriate metal ion. The ligating groups may be present in non-polymeric or polymeric material either in a side chain or part of the backbone, or as part of a dendrimer or starburst molecule. Examples of monodentate ligands include, for example, ethyleneoxy, alkyl-oxy groups, pyridine, and alkyl-imine compounds, among others. Examples of bi- and multidentate ligands include bipyridines, polypyridines, urethane groups, carboxylate groups, and amides.

[00107] According to various embodiments of the invention, dye-sensitized photovoltaic cells having a gel electrolyte 1100 including lithium ions are fabricated at or below room temperature or at elevated temperatures below about 300 °C. The temperature may be below about 100 °C, and preferably, the gelling of the electrolyte

solution is performed at room temperature and at standard pressure. In various illustrative embodiments, the viscosity of the electrolyte solution may be adjusted to facilitate gel electrolyte deposition using printing techniques such as, for example, screen-printing and gravure-printing techniques. The complexing of lithium ions with various ligands can be broken at higher temperatures, thereby permitting the gel electrolyte compositions to be easily processed during DSSC based photovoltaic module fabrication. Other metal ions may also be used to form thermally reversible or irreversible gels. Examples of suitable metal ions include: Li^+ , Cu^{2+} , Ba^{2+} , Zn^{2+} , Ni^{2+} , Ln^{3+} (or other lanthanides), Co^{2+} , Ca^{2+} , Al^{3+} , Mg^{2+} , and any metal ion that complexes with a ligand.

5 [00108] Figure 12 depicts a gel electrolyte **1200** formed by the complexing of an organic polymer, polyethylene oxide (PEO), by lithium ions. The PEO polymer segments are shown as being complexed about the lithium ions and crosslinked with each other. In another embodiment, the metal ion complexed with various polymer chains can be incorporated into a reversible redox electrolyte species to promote gelation. The gel electrolyte composition that results from the combination is suitable for use in various photovoltaic cell embodiments such as photovoltaic fibers, photovoltaic cells, and electrically interconnected photovoltaic modules.

15 [00109] Referring back to Figure 6, the charge carrier material **606** can include an electrolyte composition having an organic compound capable of complexing with a metal ion at a plurality of sites; a metal ion such as lithium; and an electrolyte solution. These materials can be combined to produce a gelled electrolyte composition suitable for use in the charge carrier material **606** layer. In one embodiment, the charge carrier material **606** includes a redox system. Suitable redox systems may include organic and/or inorganic redox systems. Examples of such systems include, but are not limited to, cerium(III) sulfate/cerium(IV), sodium bromide/bromine, lithium iodide/iodine, $\text{Fe}^{2+}/\text{Fe}^{3+}$, $\text{Co}^{2+}/\text{Co}^{3+}$, and viologens.

25 [00110] Further illustrative examples of the invention in the context of a DSSC having a gel electrolyte composition are provided below. The photoelectrodes used in the following illustrative examples were prepared according to the following procedure. An aqueous, titania suspension (P25, which was prepared using a suspension preparation

30

technique with total solid content in the range of 30-37 %) was spun cast on SnO₂:F coated glass slides (15 Ω/cm²). The typical thickness of the titanium oxide coatings was around 8 μm. The coated slides were air dried at room temperature and sintered at 450 °C for 30 minutes. After cooling the slides to about 80 °C, the slides were immersed into
 5 3×10⁻⁴ M N3 dye solution in ethanol for 1 hour. The slides were removed and rinsed with ethanol and dried over slide a warmer at 40 °C for about 10 minutes. The slides were cut into about 0.7 cm × 0.7 cm square active area cells. The prepared gels were applied onto photoelectrodes using a glass rod and were sandwiched between platinum-coated, SnO₂:F coated, conducting glass slides. The cell performance was measured at AM 1.5 solar
 10 simulator conditions (i.e., irradiation with light having an intensity of 1000 W/m²).

Example 9. Effect of Lithium Iodide in Standard Ionic Liquid Based Electrolyte Composition

[00111] In this illustrative example, the standard, ionic, liquid-based redox electrolyte composition that was used contained a mixture containing 99 % (by weight) imidazolium
 15 iodide based ionic liquid and 1 % water (by weight), combined with 0.25 M iodine and 0.3 M methylbenzimidazole. In various experimental trials, electrolyte solutions with at least a 0.10 M iodine concentration exhibit the best solar conversion efficiency. In a standard composition, butylmethylimidazolium iodide (MeBuImI) was used as the ionic liquid. Photovoltage decreased with increases in iodine concentration, while
 20 photoconductivity and conversion efficiency increased at least up to 0.25 M iodine concentration. Adding lithium iodide to the standard composition enhanced the photovoltaic characteristics V_{oc} and I_{sc} and the η. Therefore, in addition to lithium's use as a gelling agent, it may serve to improve overall photovoltaic efficiency. Table 3 summarizes the effect of LiI on photovoltaic characteristics.

25

Table 3

	Standard	Standard + 1 wt% LiI	Standard + 2 wt% LiI	Standard + 3 wt% LiI	Standard + 5 wt% LiI
η (%)	2.9 %	3.57	3.75	3.70	3.93
V _{oc} (V)	0.59	0.61	0.6	0.6	0.61
I _{sc} (mA/ cm ²)	10.08	11.4	11.75	11.79	12.62
V _m (V)	0.39	0.4	0.39	0.4	0.39
Im (mA/ cm ²)	7.44	9.02	9.64	9.0	10.23

[00112] The fill factor ("FF") is referenced below and can be calculated from the ratio of the solar conversion efficiency to the product of the open circuit voltage and the short circuit current, i.e., $FF = \eta/[V_{oc} * I_{sc}]$.

Example 10. The Effect of Cations on the Enhancement in Photovoltaic Characteristics

5 [00113] In order to ascertain whether the enhancement in photovoltaic characteristics was due to the presence of lithium or iodide, controlled experimental trials using various iodides in conjunction with cations including lithium, potassium, cesium and tetrapropylammonium iodide were conducted. The iodide concentration was fixed at 376 $\mu\text{mols/gram}$ of standard electrolyte composition. The standard composition used was a
10 mixture containing 99 % MeBuImI and 1 % water, combined with 0.25 M iodine and 0.3 M methylbenzimidazole. 376 μmols of various iodide salts per gram of standard electrolyte composition were dissolved in the electrolyte. The complete dissolution of LiI was observed. The other salts took a long time to dissolve and did not dissolve completely over the course of the experimental trial. DSSC-based photovoltaic cells were
15 fabricated using prepared electrolytes containing various cations. Table 4 shows the effect of the various cations on the photovoltaic characteristics. It is apparent from the second column of Table 4 that Li^+ ion shows enhanced photovoltaic characteristics compared to the standard formula, while the other cations do not appear to contribute to the enhancement of the photovoltaic characteristics.

20

Table 4

	Standard	Standard + LiI	Standard + NPR_4I	Standard + KI	Standard + CsI
η (%)	3.23	4.39	2.69	3.29	3.23
V_{oc} (V)	0.58	0.65	0.55	0.58	0.6
I_{sc} (mA/ cm^2)	10.96	12.03	9.8	9.91	10.14
V_m (V)	0.36	0.44	0.36	0.4	0.4
I_m (mA/ cm^2)	8.96	9.86	7.49	8.25	8.32

Example 11. Effect of Ionic Liquid Type

[00114] In one aspect of the invention, MeBuImI-based electrolyte compositions have been found to perform slightly better than MePrImI based electrolytes. In addition, experimental results demonstrate that a 1/1 blend of MeBuImI and MePrImI exhibit better performance than MeBuImI, as shown in Table 5.

Table 5

	<u>376 μmoles of LiI per 1 gram of MeBuImI based standard electrolyte composition.</u>	<u>376 μmoles of LiI per 1 gram of MeBuImI/MePrImI based standard electrolyte composition.</u>
η (%)	3.64	3.99
V_{oc} (V)	0.63	0.63
I_{sc} (mA/ cm^2)	11.05	11.23
V_m (V)	0.42	0.42
I_m (mA/ cm^2)	8.69	9.57

Example 12. Using Li-induced Gelling in Composition A Instead of a Dibromocompound

10 [00115] In this illustrative example, a Composition A was prepared by dissolving 0.09 M of iodine in a mixed solvent consisting of 99.5% by weight of 1-methyl-3-propyl imidazolium iodide and 0.5% by weight of water. Then, 0.2 g of poly(4-vinylpyridine) ("P4VP"), a nitrogen-containing compound, was dissolved in 10 g of the Composition A. Further, 0.2 g of 1,6-dibromohexane, an organic bromide, was dissolved in the resultant
15 Composition A solution, so as to obtain an electrolyte composition, which was a precursor to a gel electrolyte.

[00116] Gelling occurred quickly when 5 wt % of lithium iodide (376 μ moles of lithium salt per gram of standard electrolyte composition) was used as the gelling agent in an electrolyte composition containing (i) 2 wt % P4VP and (ii) a mixture containing 99.5 %
20 MePrImI and 0.5% water. The gel did not flow when a vial containing the Li-induced gel was tilted upside down. One approach using a dibromo compound produced a phase-segregated electrolyte with cross-linked regions suspended in a liquid, which flows (even after gelling at 100 °C for 30 minutes). A comparison of the photovoltaic characteristics

of Composition A, with and without LiI, is presented in the following Tables 6 and 7. The results demonstrate that functional gels suitable for DSSC-based photovoltaic cell fabrication can be obtained using lithium ions, while also improving the photovoltaic characteristics.

5

Table 6

	Composition A with dibromohexane	Composition A with 2 wt.% P4VP	MeBuImI based electrolyte+ 2 wt.% P4VP+5 wt.% LiI
η (%)	2.6	3.04	3.92
V_{oc} (V)	0.59	0.58	0.65
I_{sc} (mA/ cm ²)	9.73	10.0	11.45
V_m (V)	0.38	0.38	0.42
I_m (mA/ cm ²)	6.82	8.04	9.27

10

Table 7

	(a) Composition A where MePrImI:water is 99.5:0.5 and with 2 % P4VP and 0.09 M Iodine	(b) Same composition as (a), but with 5 wt % of LiI
Physical Properties	Reddish fluid; flows well	Non-scattering Gel; does not flow; can be thinned by applying force using a glass rod.
Efficiency	2.53 %	3.63 %
V_{oc}	0.55 V	0.62 V
I_{sc}	9.82 mA/cm ²	12.29 mA/cm ²
V_m	0.343 V	0.378 V
FF	0.47	0.47

Example 13. Effect of Anions of Lithium Salts on the Efficiency and Photovoltage of DSSCs

- 15 [00117] Experiments were performed to study the effect of counter ions on lithium, given lithium's apparent role in enhancing the overall efficiency of DSSCs. 376 μ moles of LiI, LiBr, and LiCl were used per gram of the electrolyte composition containing MePrImI, 1 % water, 0.25 M iodine and 0.3 M methylbenzimidazole in order to study the

photovoltaic characteristics of the cells. The photovoltaic characteristics of cells containing these electrolytes are presented in Table 8.

Table 8

	Electrolyte composition with LiI	Electrolyte composition with LiBr	Electrolyte composition with LiCl
Efficiency	3.26 %	3.64 %	3.71 %
V_{oc}	0.59 V	0.62 V	0.65 V
I_{sc}	10.98 mA/cm ²	11.96 mA/cm ²	11.55 mA/cm ²
V_m	0.385 V	0.4 V	0.40 V
FF	0.5	0.49	0.49

5 *Example 14. Passivation and Improved Efficiency and Photovoltage of DSSCs*

[00118] In the field of photovoltaic cells, the term passivation refers to the process of reducing electron transfer to species within the electrolyte of a solar cell. Passivation typically includes treating a nanoparticle layer by immersion in a solution of t-butylpyridine in methoxypropionitrile or other suitable compound. After the nanomatrix layer, such as a titania sponge, of a photovoltaic cell has been treated with a dye, regions in the nanomatrix layer where the dye has failed to adsorb may exist. A passivation process is typically performed on a DSSC to prevent the reversible electron transfer reaction from terminating as result of reducing agents existing at the undyed regions. The typical passivation process does not appear to be necessary when ionic liquid compositions containing various lithium salts and/or other alkali metal salts are used in the DSSCs. A photovoltage greater than 0.65 V was achieved using a chloride salt of lithium without a passivation process.

[00119] In this illustrative example, a DSSC was passivated by immersing it in a solution containing 10 wt % of t-butylpyridine in methoxypropionitrile for 15 minutes. After passivation, the DSSC was dried on a slide warmer maintained at 40 °C for about 10 minutes. Electrolyte compositions containing MePrImI, 1% water, 0.3 M methylbenzimidazole, and 0.25 M iodine were gelled using 376 μ moles of LiI, LiBr, and LiCl per gram of standard electrolyte composition used during this study. Adding a t-

butylpyridine-based passivation agent to the electrolyte enhanced the DSSC's photovoltage, but decreased the efficiency of the DSSC by decreasing the photoconductivity. Table 9 summarizes the effects of passivation on photovoltaic characteristics of electrolytes containing various lithium halides.

5

Table 9

	Electrolyte gelled with LiI	Electrolyte gelled with LiBr	Electrolyte gelled with LiCl
Efficiency	3.5 %	3.65 %	3.85 %
V_{oc}	0.61 V	0.63 V	0.65 V
I_{sc}	10.96 mA/cm²	11.94 mA/cm²	11.75 mA/cm²
V_m	0.395 V	0.4 V	0.405 V
FF	0.52	0.49	0.5

Example 15. Lithium's Role in Gelling the Electrolyte Compositions Containing Polyvinylpyridine and the Effect of Other Alkali Metal Ions on Gelability

[00120] Lithium cation appears to have a unique effect in gelling ionic liquid composition containing complexable polymers, e.g., P4VP, in as small an amount as 2 wt %.

Other alkali metal ions such as sodium, potassium, and cesium were used to carry out gelling experiments. Alkali metal salts such as lithium iodide, sodium chloride, potassium iodide, cesium iodide were added to portions of electrolyte composition containing propylmethylimidazolium iodide (MePrImI), 1% water, 0.25 M iodine, and 0.3 M methylbenzimidazole. Only compositions containing lithium iodide gelled under the experimental conditions used. The remaining three compositions containing sodium, potassium, and cesium did not gel at the experimental conditions used. Divalent metal ions, such as calcium, magnesium, and zinc, or trivalent metals, such as aluminum or other transition metal ions, are other potential gelling salts.

Example 16. Effect of Iodine and Lithium Concentration on Ionic Liquid Electrolyte Gels

[00121] In this illustrative example, gels were prepared by adding lithium salts to an electrolyte composition containing MeBuImI, iodine, and 2 wt % P4VP. The photovoltaic characteristics of the gels were tested using high-temperature sintered, N3

dye sensitized titanium-oxide photoelectrodes and platinized $\text{SnO}_2\text{:F}$ coated glass slides. Both LiI and LiCl gelled the ionic liquid-based compositions that contained small amounts (2 % was sufficient) of complexable polymers like P4VP. In compositions lacking methylbenzimidazole, the lithium did not effect the photovoltage. 5 wt% corresponds to a composition including about 376 μmoles of lithium salt per gram of ionic liquid and a mixture of 99 wt% butylmethylimidazolium iodide, 1 wt% water, 0.3 M methyl benzimidazole, and 0.25 M iodine. Therefore, 1 wt% corresponds to a $376/5 \cong 75$ μmoles of lithium salt per gram of ionic liquid composition. The photovoltaic characteristics are summarized in Table 10.

10

Table 10

	5 % LiI	2.5 % LiI	5 % LiCl	2.5 % LiCl
0.05 M Iodine	$\eta = 1.6 \%$ $V_{oc} = 0.6 \text{ V}$ $I_{sc} = 4.89 \text{ mA}$ $FF = 0.54$ $V_m = 0.445 \text{ V}$	$\eta = 1.23 \%$ $V_{oc} = 0.59 \text{ V}$ $I_{sc} = 4.21 \text{ mA}$ $FF = 0.495$ $V_m = 0.415 \text{ V}$	$\eta = 0.64 \%$ $V_{oc} = 0.59 \text{ V}$ $I_{sc} = 2.95 \text{ mA}$ $FF = 0.36$ $V_m = 0.4 \text{ V}$	$\eta = 1.19 \%$ $V_{oc} = 0.58 \text{ V}$ $I_{sc} = 3.87 \text{ mA}$ $FF = 0.53$ $V_m = 0.426 \text{ V}$
0.1 M Iodine	$\eta = 1.22 \%$ $V_{oc} = 0.48 \text{ V}$ $I_{sc} = 6.46 \text{ mA}$ $FF = 0.39$ $V_m = 0.349 \text{ V}$	$\eta = 1.29 \%$ $V_{oc} = 0.56 \text{ V}$ $I_{sc} = 5.12 \text{ mA}$ $FF = 0.45$ $V_m = 0.386 \text{ V}$	$\eta = 2.83 \%$ $V_{oc} = 0.57$ $I_{sc} = 9.04 \text{ mA}$ $FF = 0.55$ $V_m = 0.422 \text{ V}$	$\eta = 2.06 \%$ $V_{oc} = 0.58$ $I_{sc} = 7.14 \text{ mA}$ $FF = 0.5$ $V_m = 0.42 \text{ V}$
0.25 M Iodine	$\eta = 2.58 \%$ $V_{oc} = 0.55 \text{ V}$ $I_{sc} = 11.49 \text{ mA}$ $FF = 0.41$ $V_m = 0.338 \text{ V}$	$\eta = 3.06 \%$ $V_{oc} = 0.55 \text{ V}$ $I_{sc} = 10.78 \text{ mA}$ $FF = 0.52$ $V_m = 0.36 \text{ V}$	$\eta = 3.4 \%$ $V_{oc} = 0.56 \text{ V}$ $I_{sc} = 11.32 \text{ mA}$ $FF = 0.54$ $V_m = 0.369 \text{ V}$	$\eta = 2.6 \%$ $V_{oc} = 0.56 \text{ V}$ $I_{sc} = 10.18 \text{ mA}$ $FF = 0.46$ $V_m = 0.364 \text{ V}$

Example 17. Effect of Polymer Concentration on Gelability and Photovoltaic Characteristics of Redox Electrolyte Gels

[00122] In this illustrative example, polymer concentration was varied to study its effect on gel viscosity and photovoltaic characteristics. The electrolyte composition used for this study was a mixture containing 99 % MeBuImI, 1 % water, 0.25 M iodine, 0.6 M LiI, and 0.3 M methylbenzimidazole. The concentration of the polymer, P4VP was varied from 1% to 5%. The electrolyte composition with 1% P4VP did flow slowly when the vial containing the gel was tilted down. The gels with 2%, 3%, and 5% did not flow. The gel with 5% P4VP appeared much more solid when compared to the 2% P4VP

preparation. Table 11 summarizes the photovoltaic characteristics of the gels containing the various P4VP contents that were studied.

[00123] The results show that the photovoltaic characteristics do not vary with the increases in viscosity achieved by increasing the P4VP content. Therefore, the viscosity of the gel can be adjusted without causing degradation to the photovoltaic characteristics. Methylbenzimidazole may be necessary to achieve high η . Increasing the iodine concentration up to 0.25 M also increased the efficiency. Beyond 0.25 M, the photovoltage decreased drastically, reducing the overall efficiency. Other metal ions or cations like cesium, sodium, potassium or tetraalkylammonium ions were not found to contribute to the efficiency enhancement and did not cause gelling of the electrolyte solutions. Furthermore, chloride anion was found to enhance the efficiency along with lithium, by improving the photovoltage without causing decreased photoconductivity in compositions containing methylbenzimidazole.

Table 11

Photovoltaic Characteristics	1 % P4VP	2 % P4VP	3 % P4VP	5 % P4VP
η (%)	3.23	3.48	3.09	3.19
I_{sc} (mA/cm ²)	10.74	10.42	12.03	10.9
V_{oc} (V)	0.59	0.59	0.6	0.61
V_m (V)	0.39	0.4	0.38	0.40
I_m (mA/cm ²)	8.27	8.69	8.07	8.03
FF	0.51	0.57	0.43	0.48

15

C. Co-sensitizers

[00124] According to one illustrative embodiment, the photosensitizing agent described above includes a first sensitizing dye and second electron donor species, the “co-sensitizer.” The first sensitizing dye and the co-sensitizer may be added together or separately to form the photosensitized interconnected nanoparticle material 603 shown in Figure 6. As mentioned above with respect to Figure 6, the sensitizing dye facilitates conversion of incident visible light into electricity to produce the desired photovoltaic

20

effect. In one illustrative embodiment, the co-sensitizer donates electrons to an acceptor to form stable cation radicals, which improves the efficiency of charge transfer from the sensitizing dye to the semiconductor oxide nanoparticle material and reduces back electron transfer to the sensitizing dye or co-sensitizer. The co-sensitizer preferably includes (1) conjugation of the free electron pair on a nitrogen atom with the hybridized orbitals of the aromatic rings to which the nitrogen atom is bonded and, subsequent to electron transfer, the resulting resonance stabilization of the cation radicals by these hybridized orbitals; and (2) a coordinating group, such as a carboxy or a phosphate, the function of which is to anchor the co-sensitizer to the semiconductor oxide. Examples of suitable co-sensitizers include, but are not limited to, aromatic amines (e.g., such as triphenylamine and its derivatives), carbazoles, and other fused-ring analogues.

[00125] Once again referring back to Figure 6, the co-sensitizer is electronically coupled to the conduction band of the photosensitized interconnected nanoparticle material **603**. Suitable coordinating groups include, but are not limited to, carboxylate groups, phosphates groups, or chelating groups, such as, for example, oximes or alpha keto enolates.

[00126] Tables 12-18 below present results showing the increase in photovoltaic cell efficiency when co-sensitizers are co-adsorbed along with sensitizing dyes on the surface of high temperature sintered or low temperature interconnected titania. In Tables 12-18, characterization was conducted using AM 1.5 solar simulator conditions (i.e., irradiation with light having an intensity of 1000 W/m^2). A liquid electrolyte including 1 M LiI, 1 M t-butylpyridine, 0.5 M I_2 in 3-methoxypropanitrile was employed. The data shown in the tables indicates an enhancement of one or more operating cell parameters for both low-temperature-interconnected (Tables 15, 17 and 18) and high-temperature-sintered (Tables 12, 13, 14 and 16) titania nanoparticles. The solar cells characteristics listed include η , V_{oc} , I_{sc} , FF, V_m , and I_m . The ratios of sensitizer to co-sensitizer are based on the concentrations of photosensitizing agents in the sensitizing solution.

[00127] In particular, it was discovered that aromatic amines enhance cell performance of dye sensitized titania solar cells if the concentration of the co-sensitizer is below about 50 mol% of the dye concentration. An example of the general molecular structure of the

preferred aromatic amines is shown in Figures 13 and 14. Preferably, the concentration of the co-sensitizer is in the range of about 1 mol% to about 20 mol%, and more preferably in the range of about 1 mol% to about 5 mol%.

[00128] Figure 13A depicts a chemical structure **1300** that may serve as a co-sensitizer.

5 The molecule **1300** adsorbs to the surface of a nanoparticle layer via its coordinating group or chelating group, A. A may be a carboxylic acid group or derivative thereof, a phosphate group, an oxime or an alpha ketoenolate, as described above. Figure 13B depicts a specific embodiment **1310** of the structure **1300**, namely DPABA (diphenylaminobenzoic acid), where A = COOH. Figure 13C depicts another specific
10 amine **1320** referred to as DEAPA (N', N-diphenylaminophenylpropionic acid), with A as the carboxy derivative COOH.

[00129] Figure 14A shows a chemical structure **1330** that may serve as either a co-sensitizer, or a sensitizing dye. The molecule does not absorb radiation above 500 nm, and adsorbs to a surface of the nanoparticle layer via its coordinating or chelating groups,

15 A. A may be a carboxylic acid group or derivative thereof, a phosphate group, an oxime or an alpha ketoenolate. R₁ and R₂ may each be a phenyl, alkyl, substituted phenyl, or benzyl group. Preferably, the alkyl may contain between 1 and 10 carbons. Figure 14B depicts a specific embodiment **1340** of the structure **1330**, namely DPACA (2,6 bis (4-benzoicacid)-4-(4-N,N-diphenylamino) phenylpyridine carboxylic acid), where R₁ and R₂
20 are phenyl and A is COOH.

[00130] DPACA **1340** may be synthesized as follows. 1.49 g (9.08 mmol) of 4-acetylbenzoic acid, 1.69 g (6.18 mmol) of 4-N,N- diphenylbenzaldehyde, and 5.8 g (75.2 mmol) of ammonium acetate were added to 60 ml of acetic acid in a 100 ml round bottom flask equipped with a condenser and stirring bar. The solution was heated to reflux with
25 stirring under nitrogen for 5 hours. The reaction was cooled to room temperature and poured into 150 ml of water, which was extracted with 150 ml of dichloromethane. The dichloromethane was separated and evaporated with a rotary evaporator, resulting in a yellow oil. The oil was then eluted on a silica gel column with 4% methanol/dichloromethane to give the product, an orange solid. The solid was washed
30 with methanol and vacuum dried to give 0.920 g of 2,6 bis (4-benzoicacid)-4-(4-N,N-

diphenylamino)phenylpyridine (DPACA). The melting point was 199°-200 °C, the λ_{max} was 421 nm, and the molar extinction coefficient, E was 39,200 L mole⁻¹ cm⁻¹. The structure was confirmed by NMR spectroscopy.

- [00131] Table 12 shows the results for high-temperature-sintered titania; photosensitized by overnight soaking in solutions of 1 mM N3 dye and three concentrations of DPABA. Table 12 also shows that the average η is greatest for the preferred 20/1 (dye/co-sensitizer) ratio.

Table 12

General conditions	I-V CHARACTERIZATION								
	Conditions	Cell area cm ²	V _{oc} V	I _m mA/cm ²	V _m V	I _{sc} mA/cm ²	FF	η %	σ
Adsorption Temp. RT °C	1 mM N3/EtOH, Overnight CONTROL	0.44	0.62	6.69	0.44	8.38	0.56	2.91	
		0.52	0.64	6.81	0.43	8.59	0.54	2.94	
Solvent of Dye		0.54	0.63	6.95	0.41	8.72	0.52	2.84	
EtOH	Average	0.50	0.63	6.82	0.43	8.56	0.54	2.90	0.05
Dye Concen. N3, DPABA	1 mM N3, 0.05 mM DPABA in EtOH for Overnight; 20/1	0.50	0.64	7.70	0.45	9.31	0.58	3.43	
		0.53	0.64	7.40	0.45	9.30	0.56	3.31	
Sintering Temp 450 °C, 30 minutes		0.50	0.64	7.70	0.45	9.38	0.57	3.44	
	Average	0.51	0.64	7.60	0.45	9.33	0.57	3.39	0.07
Thickness of Film TiO ₂ , ~10 μ m	1 mM N3, 1 mM DPABA in EtOH for Overnight; 1/1	0.53	0.63	7.21	0.41	8.58	0.55	2.96	
		0.50	0.63	6.75	0.44	8.23	0.57	2.97	
		0.42	0.63	7.11	0.44	8.67	0.57	3.13	
	Average	0.48	0.63	7.02	0.43	8.49	0.56	3.02	0.10
Electrolyte AM 1.5D, 1 Sun	1 mM N3, 10 mM DPABA in EtOH for Overnight; 1/10	0.33	0.58	4.95	0.42	6.02	0.60	2.08	
		0.52	0.60	5.51	0.42	6.67	0.58	2.31	
		0.49	0.60	5.53	0.42	6.72	0.58	2.32	
Film pretreatment	Average	0.45	0.59	5.33	0.42	6.47	0.58	2.24	0.14

- 10 [00132] Table 13 shows the results of using a cut-off filter (third and fourth entries) while irradiating a cell to test its I-V characteristics. Table 13 also shows that the

efficiency of the cell still improves when DPABA is present, indicating that its effect when no filter is present is not simply due to absorption of UV light by DPABA followed by charge injection. Figure 15 shows a plot 1350 of the absorbance versus wavelength for the cut-off filter used to characterize the photovoltaic cells, according to an illustrative embodiment of the invention. Figure 16 shows a plot 1360 of the absorbance versus wavelength for DPABA, which absorbs below 400 nm. Because the absorbance of the cut-off filter is large, little light reaches the absorption bands of DPABA.

Table 13

Conditions	I-V CHARACTERIZATION							
	Cell area cm ²	V _{oc} V	I _m mA/cm ²	V _m V	I _{sc} mA/cm ²	FF	η %	σ
1 mM N3 in EtOH Overnight control	0.49	0.70	8.62	0.46	11.02	0.51	3.97	
	0.49	0.70	8.13	0.45	10.20	0.51	3.66	
	0.49	0.73	7.93	0.51	9.69	0.57	4.04	
Average	0.49	0.71	8.23	0.47	10.30	0.53	3.89	0.20
1mM N3 0.05mM DPABA in EtOH, 20/1 Overnight	0.49	0.71	9.05	0.46	11.53	0.51	4.16	
	0.49	0.71	9.24	0.46	11.56	0.52	4.25	
	0.49	0.71	9.39	0.46	11.50	0.53	4.32	
Average	0.49	0.71	9.23	0.46	11.53	0.52	4.24	0.08
1 mM N3 in EtOH Overnight control	0.49	0.69	6.35	0.47	7.83	0.55	4.26	455nm cut off filter used, 70 mW/cm ²
	0.49	0.69	6.05	0.46	7.44	0.54	3.98	
	0.49	0.72	5.74	0.52	6.94	0.60	4.27	
Average	0.49	0.70	6.05	0.48	7.40	0.56	4.17	0.17
1mM N3 0.05mM DPABA in EtOH, 20/1 Overnight	0.49	0.70	6.73	0.47	8.21	0.55	4.52	455nm cut off filter used, 70 mW/cm ²
	0.49	0.70	6.74	0.47	8.19	0.55	4.53	
	0.49	0.70	6.74	0.49	8.25	0.57	4.72	
Average	0.49	0.70	6.74	0.48	8.22	0.56	4.59	0.11

[00133] Table 14 shows that the addition of triphenylamine itself (i.e., no titania complexing groups such as carboxy) does not significantly enhance efficiency under the stated conditions.

Table 14

Conditions	I-V CHARACTERIZATION							
	Cell area cm ²	V _{oc} V	I _m mA/cm ²	V _m V	I _{sc} mA/cm ²	FF	η %	σ
0.5 mM N3 in EtOH, Overnight	0.49	0.70	7.96	0.45	9.82	0.52	3.58	
	0.49	0.71	8.09	0.48	9.58	0.57	3.88	
	0.49	0.70	7.47	0.48	8.83	0.58	3.59	
Average	0.49	0.70	7.84	0.47	9.41	0.56	3.68	0.17
0.5 mM N3, 0.025 mM TPA in EtOH Overnight 20/1	0.49	0.69	7.44	0.45	9.21	0.53	3.35	
	0.49	0.69	7.61	0.47	9.75	0.53	3.58	
	0.49	0.69	6.98	0.45	8.56	0.53	3.14	
Average	0.49	0.69	7.34	0.46	9.17	0.53	3.36	0.22
0.5 mM N3, 2.0 mM TPA in EtOH Overnight ¼	0.49	0.68	4.62	0.44	5.66	0.53	2.03	
	0.49	0.66	4.18	0.45	5.38	0.53	1.88	
	0.49	0.66	4.51	0.45	5.82	0.53	2.03	
Average	0.49	0.67	4.44	0.45	5.62	0.53	1.98	0.09

5

[00134] Table 15 shows that the effect is present using low temperature interconnected titania and that the 20/1 (dye/co-sensitizer) ratio is preferred.

Table 15

	I-V CHARACTERIZATION							
Conditions	Cell area cm ²	V _{oc} V	I _m mA/cm ²	V _m V	I _{sc} mA/cm ²	FF	η %	σ
0.5 mM N3/EtOH, overnight, control	0.49	0.73	8.32	0.50	10.56	0.54	4.16	
	0.51	0.72	8.13	0.49	10.30	0.54	3.98	
	0.50	0.72	8.56	0.47	10.65	0.52	4.02	
Average	0.50	0.72	8.34	0.49	10.50	0.53	4.06	0.09
0.5 mM N3, 0.0125 mM DPABA in EtOH, 40/1, overnight	0.49	0.73	8.55	0.51	10.48	0.57	4.36	
	0.53	0.72	8.53	0.50	11.00	0.54	4.27	
	0.49	0.74	8.08	0.54	10.96	0.54	4.36	
Average	0.50	0.73	8.39	0.52	10.81	0.55	4.33	0.06
0.5 mM N3, 0.017mM DPABA in EtOH, 30/1, overnight	0.49	0.73	9.07	0.49	11.31	0.54	4.44	
	0.49	0.75	8.64	0.52	10.97	0.55	4.49	
	0.52	0.73	8.19	0.52	10.88	0.54	4.26	
Average	0.50	0.74	8.63	0.51	11.05	0.54	4.40	0.12
0.5 mM N3, 0.025 mM DPABA in EtOH, 20/1, overnight	0.50	0.75	8.57	0.52	11.56	0.51	4.46	
	0.49	0.74	8.88	0.52	11.45	0.54	4.62	
	0.53	0.74	9.01	0.51	12.08	0.51	4.60	
Average	0.51	0.74	8.82	0.52	11.70	0.52	4.56	0.09
0.5 mM N3, 0.5 mM DPABA in EtOH, 1/1, overnight	0.49	0.72	8.85	0.48	10.78	0.55	4.25	
	0.51	0.74	8.62	0.47	10.37	0.53	4.05	
	0.50	0.75	8.38	0.49	10.02	0.55	4.11	
Average	0.50	0.74	8.62	0.48	10.39	0.54	4.14	0.10
0.5 mM N3, 5mM DPABA in EtOH, 1/10, overnight	0.49	0.68	7.56	0.44	9.09	0.54	3.33	
	0.51	0.69	7.62	0.46	9.34	0.54	3.51	
	0.49	0.67	7.25	0.45	8.84	0.55	3.26	
Average	0.50	0.68	7.48	0.45	9.09	0.54	3.36	0.13

[00135] Table 16 shows results for high-temperature-sintered titania sensitized with a high concentration of N3 dye while maintaining a 20/1 ratio of dye to co-sensitizer.

Entries 1 and 2 show the increase in cell performance due to co-sensitizer. Entry 3 shows the effect of DPABA alone as a sensitizer, demonstrating that this material acts as a sensitizer by itself when irradiated with the full solar spectrum, which includes low-intensity UV radiation.

Table 16

General Conditions	I-V CHARACTERIZATION								
	Conditions	Cell area cm ²	V _{oc} V	I _m mA/cm ²	V _m V	I _{sc} mA/cm ²	FF	η %	σ
Adsorption Temp. RT °C	8mM N3/aprotic polar solvent, 1 hour CONTROL average	0.49	0.68	8.51	0.44	10.07	0.55	3.74	
		0.49	0.67	8.28	0.44	9.75	0.56	3.64	
Solvent of Dye		0.49	0.68	9.16	0.42	10.80	0.52	3.85	
Aprotic polar solvent		0.49	0.68	8.65	0.43	10.21	0.54	3.74	0.10
	8mM N3, 0.4 mM DPABA in aprotic polar solvent, 20/1 1 hour average	0.49	0.68	9.52	0.44	11.18	0.55	4.19	
		0.49	0.68	9.96	0.44	11.59	0.56	4.38	
		0.49	0.65	9.81	0.42	12.13	0.52	4.12	
		0.49	0.67	9.76	0.43	11.63	0.54	4.23	0.14
	5mM DPABA in aprotic polar solvent Overnight	0.49	0.55	1.02	0.42	1.22	0.64	0.43	
		0.49	0.55	0.94	0.41	1.13	0.62	0.39	
		0.49	0.58	0.89	0.44	1.07	0.63	0.39	
		0.49	0.56	0.95	0.42	1.14	0.63	0.40	0.02

[00136] Table 17 shows results for low-temperature-interconnected titania. Entry 5 shows the affect of DPACA alone as a sensitizer, demonstrating that this material acts as a sensitizer by itself when irradiated with the full solar spectrum, which includes low-intensity UV radiation.

Table 17

I-V CHARACTERIZATION								
Conditions	Cell area cm ²	V _{oc} V	I _m mA/cm ²	V _m V	I _{sc} mA/cm ²	FF	η %	σ
0.5 mM N3/EtOH, overnight, control	0.51	0.73	8.40	0.50	10.84	0.53	4.20	
	0.53	0.72	8.13	0.49	10.30	0.54	3.98	
	0.50	0.72	8.77	0.47	10.87	0.53	4.12	
average	0.51	0.72	8.43	0.49	10.67	0.53	4.10	0.11
0.5 mM N3, 0.01 mM DPACA in EtOH, 50/1, overnight	0.49	0.73	8.10	0.51	10.39	0.54	4.13	
	0.50	0.74	7.95	0.50	10.01	0.54	3.98	
	0.49	0.72	8.10	0.50	9.85	0.57	4.05	
average	0.49	0.73	8.05	0.50	10.08	0.55	4.05	0.08
0.5 mM N3, 0.02 mM DPACA in EtOH, 25/1, overnight	0.49	0.74	8.38	0.50	10.48	0.54	4.19	
	0.52	0.73	8.18	0.48	9.74	0.55	3.93	
	0.49	0.76	8.08	0.54	9.45	0.61	4.36	
average	0.50	0.74	8.21	0.51	9.89	0.57	4.16	0.22
0.5 mM N3, 0.5 mM DPACA in EtOH, 1/1, overnight	0.49	0.73	9.07	0.46	11.31	0.51	4.17	
	0.49	0.75	7.41	0.53	9.24	0.57	3.93	
	0.52	0.76	7.93	0.52	9.12	0.59	4.12	
average	0.50	0.75	8.14	0.50	9.89	0.56	4.07	0.13
0.5 mM N3, 5.0 mM DPACA in EtOH, 1/10, overnight	0.56	0.73	6.36	0.49	7.59	0.56	3.12	
	0.52	0.73	6.63	0.49	7.84	0.57	3.25	
	0.50	0.72	6.53	0.49	7.59	0.59	3.20	
average	0.53	0.73	6.51	0.49	7.67	0.57	3.19	0.07
5.0 mM DPACA in EtOH, overnight	0.43	0.65	3.12	0.49	3.77	0.62	1.53	
	0.45	0.65	2.93	0.49	3.51	0.63	1.44	
	0.49	0.66	2.83	0.49	3.40	0.62	1.39	
average	0.46	0.65	2.96	0.49	3.56	0.62	1.45	0.07

[00137] Table 18 shows results for low-temperature-interconnected titania. Entry 6 shows the affect of DEAPA alone as a sensitizer, demonstrating that this material acts as a sensitizer by itself when irradiated with the full solar spectrum, which includes low-intensity UV radiation.

5

Table 18

General conditions	I-V CHARACTERIZATION								
	Conditions	Cell area cm ²	V _{oc} V	I _m mA/cm ²	V _m V	I _{sc} mA/cm ²	FF	η %	σ
Adsorption Temp. RT °C	0.5 mM N3/EtOH, overnight, control	0.51	0.72	8.67	0.49	10.60	0.56	4.25	
Solvent of Dye EtOH		0.49	0.75	8.15	0.47	10.50	0.49	3.83	
		0.49	0.74	8.74	0.44	10.63	0.49	3.85	
	average	0.50	0.74	8.52	0.47	10.58	0.51	3.97	0.24
Dye Concen. N3, DEAPA	0.5 mM N3, 0.01 mM DEAPA in EtOH, 50/1, overnight	0.49	0.70	8.68	0.44	11.00	0.50	3.82	
Sintering Temp 120 °C, 10 minutes		0.52	0.71	8.57	0.45	11.11	0.49	3.86	
		0.50	0.72	8.40	0.45	10.61	0.49	3.78	
	average	0.50	0.71	8.55	0.45	10.91	0.49	3.82	0.04
Thickness of Film TiO ₂ , ~7 μm	0.5 mM N3, 0.02 mM DEAPA in EtOH, 25/1, overnight	0.51	0.74	8.90	0.44	10.92	0.48	3.92	
Liquid		0.53	0.73	8.76	0.44	10.51	0.50	3.85	
		0.49	0.73	8.40	0.45	10.21	0.51	3.78	
	average	0.51	0.73	8.69	0.44	10.55	0.50	3.85	0.07
	0.5 mM N3, 0.5 mM DEAPA in EtOH, 1/1, overnight	0.49	0.71	8.94	0.43	10.78	0.50	3.84	
Electrolyte		0.51	0.71	8.83	0.44	10.37	0.53	3.89	
AM 1.5D, 1 Sun		0.50	0.70	8.18	0.42	9.71	0.51	3.44	
Film pretreatment	average	0.50	0.71	8.65	0.43	10.29	0.51	3.72	0.25
	0.5 mM N3, 5.0 mM DEAPA in EtOH, 1/10, overnight	0.52	0.60	0.88	0.45	1.08	0.61	0.40	
		0.49	0.59	0.71	0.44	0.85	0.62	0.31	
		0.49	0.59	0.75	0.44	0.91	0.61	0.33	
	average	0.50	0.59	0.78	0.44	0.95	0.62	0.35	0.04
	5.0 mM DEAPA in CHCl ₃ , overnight	0.49	0.54	0.41	0.42	0.49	0.65	0.17	
		0.49	0.54	0.35	0.39	0.46	0.55	0.14	
		0.51	0.52	0.45	0.40	0.52	0.67	0.18	
	average	0.50	0.53	0.40	0.40	0.49	0.62	0.16	0.02

D. Semiconductor Oxide Formulations

[00138] In a further illustrative embodiment, the invention provides semiconductor oxide formulations for use with DSSCs formed using a low temperature semiconductor oxide nanoparticle interconnection, as described above. The semiconductor oxide formulations may be coated at room temperature and, upon drying at temperatures between about 50 °C and about 150 °C, yield mechanically stable semiconductor nanoparticle films with good adhesion to the transparent conducting oxide (TCO) coated plastic substrates. In one embodiment, the nanoparticle semiconductor of the photosensitized interconnected nanoparticle material 603 is formed from a dispersion of commercially available TiO₂ nanoparticles in water, a polymer binder, with or without acetic acid. The polymer binders used include, but are not limited to, polyvinylpyrrolidone (PVP), polyethylene oxide (PEO), hydroxyethyl cellulose (HOEC), hydroxypropyl cellulose, polyvinyl alcohol (PVA) and other water-soluble polymers. The ratio of semiconductor oxide particles, e.g., TiO₂, to polymer can be between about 100:0.1 to 100:20 by weight, and preferably is between about 100:1 to 100:10 by weight. The presence of acetic acid in the formulation helps to improve the adhesion of the coating to the TCO coated substrate. However, acetic acid is not essential to this aspect of the invention and semiconductor oxide dispersions without acetic acid perform satisfactorily. In another embodiment, the TiO₂ nanoparticles are dispersed in an organic solvent, such as, e.g., isopropyl alcohol, with polymeric binders such as, e.g., PVP, butvar, ethylcellulose, etc.

[00139] In another illustrative embodiment, the mechanical integrity of the semiconductor oxide coatings and the photovoltaic performance of the dye sensitized cells based on these coatings can be further improved by using a crosslinking agent to interconnect the semiconductor nanoparticles. The polylinkers described above may be used for this purpose. These crosslinking agents can be applied, e.g., in the titania coating formulation directly or in a step subsequent to drying the titania coating as a solution in an organic solvent such as ethanol, isopropanol or butanol. For example, subsequent heating of the films to temperatures in the range of about 70 °C to about 140 °C leads to the formation of TiO₂ bridges between the TiO₂ nanoparticles. Preferably, the concentration

of the polylinker in this example ranges from about 0.01 to about 20 weight % based on titania.

E. Semiconductor Primer Layer Coatings

[00140] In another illustrative embodiment, the invention provides semiconductor oxide materials and methods of coating semiconductor oxide nanoparticle layers on a base material to form DSSCs. Figure 17 depicts an illustrative embodiment **1370** of the coating process, according to the invention. In this illustrative embodiment, a base material **1376** is coated with a first primer layer **1382** of a semiconductor oxide, and then a suspension of nanoparticles **1388** of the semiconductor oxide is coated over the primer layer **1382**. The primer layer **1382** may include a vacuum-coated semiconductor oxide film (e.g., a TiO_2 film). Alternatively, the primer layer **1382** may include a thin coating with fine particles of a semiconductor oxide (e.g. TiO_2 , SnO_2). The primer layer **1382** may also include a thin layer of a polylinker or precursor solution, one example of which is the Ti (IV) butoxide polymer **400** shown in Figure 4 above. According to one illustrative embodiment of the invention, the base material **1376** is the first flexible, significantly light transmitting substrate **609** referred to in Figure 6. Additionally, the base material **1376** is a transparent, conducting, plastic substrate. According to this illustrative embodiment, the suspension of nanoparticles **1388** is the photosensitized interconnected nanoparticle material **603** of Figure 6. Numerous semiconducting metal oxides, including SnO_2 , TiO_2 , Ta_2O_5 , Nb_2O_5 , and ZnO , among others, in the form of thin films, fine particles, or precursor solutions may be used as primer layer coatings using vacuum coating, spin coating, blade coating or other coating methods.

[00141] The primer layer **1382** improves the adhesion of nano-structured semiconductor oxide films, like layer **1388**, to the base material **1376**. Enhancements in the performance of DSSCs with such primer layers have been observed and will be described below. The enhancement arises from an increase in the adhesion between the semiconductor oxide nanoparticles (or photoelectrodes) and the transparent conducting oxide coated plastic substrates, as well as from higher shunt resistance.

[00142] Examples of various illustrative embodiments of this aspect of the invention, in the context of a DSSC including a titanium dioxide nanoparticle layer, are as follows.

Example 18. Vacuum Coated TiO₂ as Prime Layers for Nanoparticle TiO₂ Photoelectrodes

[00143] In this illustrative example, thin TiO₂ films with thicknesses ranging from 2.5 nm to 100 nm were sputter-coated under vacuum on an ITO layer coated on a polyester (here, PET) substrate. A water based TiO₂ (P25, with an average particle size of 21 nm) slurry was spin-coated on both the ITO/PET with sputter-coated thin TiO₂ and on the plain ITO/PET (i.e., the portion without sputter-coated thin TiO₂). The coated films were soaked in poly [Ti(OBu)₄] solution in butanol and then heat treated at 120 °C for 2 minutes. The low- temperature reactively interconnected films were placed into an aprotic, polar solvent-based N3 dye solution (8 mM) for 2 minutes. Photovoltaic cells were made with platinum (Pt) counter-electrodes, an I⁻/I₃⁻ liquid electrolyte, 2 mil SURLYN, and copper conducting tapes. I-V characterization measurements were performed with a solar simulator.

[00144] Adhesion of nanostructured TiO₂ films from the P25 slurry coated on the ITO/PET with sputter-coated, thin TiO₂ was superior to films on the plain ITO/PET. Better photovoltaic performance was also observed from the PV cells prepared on the ITO/PET with sputter-coated, thin TiO₂ as compared to those on the plain ITO/PET. Improvement on the fill-factor was achieved as well. A FF as high as 0.67 was measured for the photovoltaic cells made on the ITO/PETs with sputter-coated, thin TiO₂. For the photovoltaic cells made on the plain ITO/PET, the FF observed was not greater than 0.60. Higher photovoltaic conversion efficiencies (about 17 % higher than the photoelectrodes made from the plain ITO/PET) were measured for the photoelectrodes prepared on the ITO/PET with thin sputter-coated TiO₂. Improvement in shunt resistance was also observed for the photovoltaic cells made on the ITO/PET with thin sputter-coated TiO₂.

Example 19. Fine Particles of TiO₂ as Primer Layer for TiO₂ Suspensions

[00145] In this illustrative example, fine particles of TiO₂, small enough such that they would stick in the valleys between spikes of ITO on the PET substrate, were prepared by hydrolyzing titanium (IV) isopropoxide. The fine particles were then spin coated at 800 rpm onto the ITO layer. A 37% TiO₂ (P25) suspension of approximately 21 nm average particle size was then spin coated at 800 rpm onto the fine particle layer. The coated TiO₂

was low temperature interconnected by dipping in 0.01 molar Ti (IV) butoxide polymer in butanol for 15 minutes followed drying on a slide warmer at 50 °C before heating at 120 °C for 2 minutes. The interconnected coating was dyed with N3 dye by dipping into an 8 mM aprotic polar solvent solution for 2 minutes, then rinsed with ethanol and dried on a slide warmer at 50 °C for 2 minutes. Control coatings were prepared in the same way, except without the fine particle prime coat. The cells' performance characteristics were measured using a solar simulator. Results for test and control are listed below in Table 19. Fine particles of tin oxide as primer coating for TiO₂ suspensions yielded similar improvements.

10

Table 19

	V _{oc}	I _{sc}	η	FF
Control	0.64	4.86	1.67%	0.54
Invention	0.66	6.27	2.36%	0.57

Example 20. Titanium (IV) Butoxide Polymer in Butanol (Precursor Solution) as Primer Layer for TiO₂

[00146] In another test, titanium (IV) butoxide polymer in butanol at 0.01 molar was spin coated on an ITO/PET plastic base at 800 rpm. A 43% TiO₂ (P25) suspension of approximately 21 nm average particle size was spin coated at 800 rpm. The coated TiO₂ was interconnected at low temperature by dipping in 0.01 M titanium (IV) butoxide polymer in butanol for 15 minutes and then drying on a slide warmer at 50 °C before heating at 120 °C for 2 minutes. The sintered coating was dyed with N3 dye by dipping into an 8 mM aprotic, polar solvent solution for 2 minutes, then rinsed with ethanol and dried on a slide warmer at 50 °C for 2 minutes. Control coatings were prepared in the same way only without the primer layer coating. The I-V properties of the cells were measured with a solar simulator. Results for test and control are listed below in Table 20.

Table 20

	V_{oc}	I_{sc}	η	FF
Control	0.66	7.17	2.62%	0.56
Invention	0.70	8.11	3.38%	0.59

F. Photovoltaic cell interconnection

[00147] Figure 18A depicts an illustrative embodiment of an interconnected photovoltaic module **1400** that includes a plurality of photovoltaic cells **1402a**, **1402b**, and **1402c** (collectively “**1402**”). Three photovoltaic cells **1402** are shown for illustrative purposes only; the photovoltaic module **1400** is not restricted to that number. Figure 18B shows the photovoltaic module **1400** in a flexed state. The photovoltaic module **1400** is suited for display arrangements where illumination may be incident on either the top **1404** or bottom **1406** surfaces. Referring to Figures 18A and 18B, the plurality of photovoltaic cells **1402** are disposed between a first electrical connection layer **1408** and a second electrical connection layer **1410**. Preferably, the photovoltaic cells and electrical connection layers **1408** and **1410** are in turn disposed between a first substrate **1414** and a second substrate **1420**. The photovoltaic cells **1402** include a photosensitized nanomatrix layer **1425** and a charge carrier medium **1430**. Preferably, the photovoltaic cells also include a catalytic medium **1435**. The electrical connection layers **1408** and **1410** include conductive regions **1440** and/or insulative regions **1445**. In one illustrative embodiment, the electrical connection layers **1408** and **1410** also include linking conductive regions **1450**. It is preferable in practice to minimize the width of the insulative regions **1445** and/or linking conductor regions **1450** relative to the conductive regions **1440**.

[00148] The conductive **1440** and insulative **1445** regions of the electrical connection layers **1408** and **1410** may include transparent materials, such as, for example, ITO, a fluorine-doped tin oxide, tin oxide, zinc oxide, and the like. In one illustrative embodiment, the conductive regions **1440** of the electrical connection layers **1408** and **1410** range in thickness between about 100 nm and about 400 nm. In another embodiment, the conductive regions **1440** are between about 150 nm and about 300 nm

thick. According to an additional feature of the illustrative embodiment, a wire or lead line is connected to one or more conductive regions **1440** to electrically connect the photovoltaic module **1400** to an external load.

[00149] Preferably, the photovoltaic module **1400** is significantly light-transmitting.

5 This is accomplished in some embodiments by forming all of the constituent layers and regions of the photovoltaic module **1400** from significantly light-transmitting materials. In other illustrative embodiments, the photovoltaic module **1400** is formed to be significantly light-transmitting even though some of the individual regions of the photovoltaic module's **1400** constituent layers are not significantly light-transmitting.

10 Furthermore, the conductive regions **1440** of at least one of the electrical connection layers **1408** and **1410** may be significantly light-transmitting.

[00150] The electrical connection layers **1408** and **1410** may include a linking conductor region **1450** deposited between two or more of the conductive regions **1440**.

15 Preferably, the linking conductor region **1450** includes a conductive material, such as, for example, copper, silver, gold, platinum, nickel, palladium, iron, and alloys thereof. Other suitable conductive materials include, but are not limited to, ITO and conductive polymers such as polyaniline and aniline. In one illustrative embodiment, one or more of the linking conductor regions **1450** are substantially transparent. Alternatively, one or more of the linking conductive regions **1450** are opaque.

20 **[00151]** According to one feature, the photosensitized nanomatrix layer **1425** includes photosensitized nanoparticles, e.g., metal oxide nanoparticles, as discussed above. In one embodiment, the photosensitized nanomatrix layer **1425** includes nanoparticles with an average size of between about 2 and about 400 nm. More particularly, the nanoparticles have an average size of between about 10 nm and about 40 nm. In a preferred
25 embodiment, the nanoparticles are titanium dioxide particles having an average particle size of about 20 nm.

[00152] In another illustrative embodiment, the photosensitized nanomatrix layer **1425** includes a heterojunction composite material. Examples of suitable heterojunction composite materials are fullerenes (e.g., C₆₀), fullerene particles, and carbon nanotubes.

30 The heterojunction composite material may be dispersed in polythiophene or some other

hole transport material. The fullerene particles may have an average size of between about 100 nm and about 400 nm. Other examples of suitable heterojunction composite materials are composites that include conjugated polymers, such as polythiophene and polyquinoline, and composites of conjugated polymers, such as polyphenylene vinylene,
5 in conjunction with non-polymeric materials.

[00153] The charge carrier medium 1430 is preferably a polymeric and relatively viscous, e.g., jelly-like, material. In other embodiments, the charge carrier medium 1430 is a liquid. As a result, the charge carrier medium 1430 can be applied using various techniques suitable for applying gels and liquids known to those skilled in the art. These
10 techniques include, for example, spray coating, roller coating, knife coating, and blade coating. The charge carrier medium 1430 may be prepared by forming a solution having an ion-conducting polymer, a plasticizer, and a mixture of iodides and iodine. The polymer provides mechanical and/or dimensional stability; the plasticizer helps the gel/liquid phase transition temperature, and the iodides and iodine act as redox
15 electrolytes.

[00154] In one illustrative embodiment, the charge carrier medium 1430 includes about 10% of polyethylene oxide, about 90% of 1:1 by weight mixture of ethyl carbonate: propylene carbonate, about 0.05 M iodine, and about 0.5 M lithium tetramethylammonium iodide. This polymeric electrolyte typically has a relatively long
20 shelf life (e.g., up to a few years), experiences minimal phase segregation during processing or while the photovoltaic module is in use, and may be used without processing, such as melting, prior to deposition.

G. Rigid Substrates

[00155] According to another illustrative embodiment, the invention provides
25 photovoltaic cells or modules with substantially rigid substrates or a combination of a substantially rigid substrate and a flexible substrate. For example, the low-temperature (< about 300 °C) sintering technique discussed above using polylinkers may be used to construct DSSCs utilizing substantially rigid substrates such as tempered glass plates. Alternatively, flexible photovoltaic cells, also made using the low temperature sintering
30 technique, may be disposed upon or incorporated between one or more substantially rigid

substrates. That is, flexible and substantially rigid substrates can be combined with the other DSSC constituent elements described above to form a flexible or substantially rigid DSSC. One suitable substantially rigid substrate is the tempered glass product SOLARTEX (available from Ajiya Safety Glass, Johor, Malaysia). Generally,

5 substantially rigid substrates are materials which possess physical durability characteristics similar to SOLARTEX. Materials that only lose their durability and other structurally desirable characteristics when exposed to temperatures outside the range of the low-temperature sintering processes described above are also suitable for use as substantially rigid substrates.

10 **[00156]** Tempered glass is significantly more resistant to thermal and mechanical stresses and strains than untempered glass. The application of dye-sensitized titania photovoltaic cells to glass plates requires sintering temperatures in excess of 400°C using conventional methods. If the glass substrate includes tempered glass, the high

15 temperatures required for sintering remove the temper from the glass plate and convert it to ordinary glass. This results in a substrate which can be shattered much more easily upon application of either a thermal or a mechanical stress. Given the breath of photovoltaic applications, substrate strength and structural integrity can be an important feature of a photovoltaic cell or module. Specifically, DSSC longevity and durability can be enhanced through the inclusion of substantially rigid substrates in the low-temperature

20 sintering context. The low temperature range at which DSSCs can be fabricated allows tempered glass and other substrates to be used in various embodiments of the invention.

[00157] Referring back to Figure 6, two rigid substrates may be substituted for the substrates **609** and **612** to form the photovoltaic cell **600**, as described above. An anti-reflective coating may be applied to the rigid substrates to increase their ability to transmit

25 radiation. Alternatively, tempered glass may be coated with a suspension of titania in the presence of a polylinker. The sintering is preferably accomplished at temperatures below about 150°C. This low-temperature range facilitates use of a broad class of substantially rigid substrates that would otherwise undergo physical and chemical changes at higher temperatures, which would diminish the intrinsic material strength of many substrates.

[00158] After sequentially adding sensitizing dye and electrolyte to the sintered titania, a second tempered glass plate, bearing a counter electrode (e.g., a very thin coating of platinum), is laminated to the first plate, thus forming a complete photovoltaic cell or module. A photovoltaic cell **600** may be formed using one rigid and one flexible
5 substrate as well, according to the invention. In various embodiments, the substantially rigid substrate(s) is/are about 3 mm or less thick. In other embodiments, the substantially rigid substrate(s) may range in thickness from about 3 mm to about 0.5 inches in thickness.

[00159] Figure 13 depicts another illustrative embodiment in which the photovoltaic
10 cell **600** from Figure 6 is sandwiched between two substantially rigid substrates **1500** and **1504** to form a rigid photovoltaic cell **1508**. The remaining layers are described in detail above with reference to Figure 6. The overall durability of the photovoltaic cell **600** shown in Figure 6 is increased using this methodology. For example, the combination of a high speed, low cost, roll-to-roll manufacturing process with the shock resistance and
15 gas barrier properties of tempered glass creates a unique photovoltaic system, suitable for outdoor applications. In a further illustrative embodiment, a suspension of titania is coated on a plastic substrate and sintered at low temperature by means of heating (< about 150°C) in the presence of a polylinker, according to the invention. Sensitizing dye and electrolyte are added sequentially by standard coating techniques, and a counter electrode
20 including a very thin coating of platinum on a coating of inert metal on a flexible plastic substrate is laminated to the first electrode, thereby creating a photovoltaic cell or module. The flexible cell or module is then laminated between two tempered glass plates or one tempered glass top plate (defined as the plate facing the light source) and a second support plate of another material.

25 [00160] Another advantage of the plastic-based PV module/tempered glass combination manifests itself in a lamination step. Typically, lamination of crystalline silicon cells and tempered glass is accomplished by applying vacuum while pressing the two materials together. In the illustrative embodiments described above, the lamination of the flexible photovoltaic cells or module to the tempered glass top plate may be
30 performed at atmospheric pressure and room temperature (or elevated temperature) by

applying an adhesive onto the glass plate with a laminating roller, without the requirement of vacuum. Thermal setting or photocuring of the adhesive is accomplished during or after the lamination step. Thus, substantially rigid substrates can provide both structural and manufacturing enhancements to existing DSSCs.

5 **H. Methods for Scoring for Fabricating DSSCs**

[00161] In another illustrative embodiment, the invention provides methods that reduce the likelihood of cell contamination from debris when fabricating flexible photovoltaic cells and modules using a continuous manufacturing process, such as the one depicted in Figure 7. Figure 20A depicts a base material **1510** for a photovoltaic cell or module,
10 where the base material **1510** is formed as a sheet or strip of material that includes a polymeric substrate **1515** and a conductive layer **1520**. A heated stylus **1530** scores the polymeric substrate **1515** and the conductive layer **1520** by parting the conductive layer **1520** and, to some depth, melting the polymeric material of the substrate **1515**. Scoring interrupts the electrical continuity of the otherwise continuous conductive layer **1520**, and
15 to a certain extent, encapsulates any debris from the conductive layer **1520** in the wake of the heated stylus **1530** when the polymeric substrate **1515** cools. Coating and entrapping conductive debris that may be in the melt of the polymeric substrate **1515** prevents these debris from interfering with the performance of the photovoltaic cell or module. The conductive layer **1520** may be semiconductive.

20 [00162] According to one illustrative embodiment, the heated stylus **1530** (which may be a soldering iron tip or a heated razor blade) is held in position by a fixed support system. For example, referring to Figures 7 and 20A, the heated stylus **1530** may be positioned to contact the advancing substrate **705** prior to the deposition of the photosensitized nanoparticle material **715**. Preferably, by monitoring the temperature and
25 geometry of the heated stylus **1530**, the distance from the heated stylus **1530** to the advancing substrate **705**, the pressure of the heated stylus **1530** on the advancing substrate **705**, and the rate at which the advancing substrate **705** advances, the width and depth of the score mark **1540**, for example as depicted in Figure 20B, is determined.

[00163] Suitable polymeric substrate materials **1515**, as described above, include, for
30 example, PET, polyacrylonaphthalates, polyimides, PEN, polymeric hydrocarbons,

cellulosics, and combinations thereof. Conductive layer **1520** materials include, but are not limited to, ITO and conductive polymers such as polyaniline and aniline, as described above. In various illustrative embodiments, the conductive layers **1520** are between about 0.5 microns and about 5 microns thick. Preferably, the conductive layers **1520** are
5 between about 0.5 micron and about 1 micron thick. In addition, the conductive layers **1520** scored using this method may include a photosensitized nanomatrix layer, according to the invention.

I. Wire Interconnects for Fabricating DSSCs

[00164] In another illustrative embodiment, the invention provides methods of
10 interconnecting photovoltaic cells (e.g., in parallel, in series, or combinations of both) to form photovoltaic modules using wire interconnects as part of a continuous manufacturing process, such as the one shown in Figure 7. Figure 21 depicts a base material **1550** suitable for forming a photovoltaic cell or module using wire interconnects. The base material **1550** includes a polymeric substrate **1555** and a conductive layer **1560**,
15 both in accordance with the invention. A portion of the base material **1550** is coated with a photoconductive layer **1565** (e.g., a photosensitized interconnected nanoparticle layer). A strip of hot melt adhesive **1570** is tacked to the conductive layer **1560**, and a wire **1575** is placed over the strip of hot melt adhesive **1570**.

[00165] Figures 22A and 22B depict another illustrative embodiment of a photovoltaic
20 module formed using wire interconnects. A first base material **1600** includes a polymeric substrate **1610** and a conductive layer **1620**, as described above. A heated stylus, as described above, forms a score mark **1630** in the base material **1600**, so that a plurality of discrete photovoltaic cells may be formed on a single base material **1600**. The methods and structures described in detail above with respect to Figures 7 and 18 are used to
25 complete the photovoltaic cells on the base material **1600**. A strip of hot melt adhesive **1640** is then tacked to the conductive layer **1620**, and a wire **1650** is placed over the strip of hot melt adhesive **1640**.

[00166] Referring to Figure 22B, the photovoltaic module **1660** is completed by placing a second base material **1670**, including a polymeric substrate **1610**, a conductive
30 layer **1620**, a score mark **1630**, and a strip of hot melt adhesive **1640**, on top of the first

base material. The photovoltaic module **1660** is laminated together under heat and pressure to complete the structure. Under appropriate process conditions, the wire **1640** forces its way through the molten adhesive **1630**, thus achieving electrical contact with both conductive layers **1620**. After cooling, the adhesive **1630** solidifies, thereby trapping
5 the wire **1650** in place. This results in a strong and conductive bond.

[00167] In one illustrative example, the thermal laminating step was performed with an aluminum strip machined to an appropriate size to match the size of the adhesive strips. The aligned sheets were placed in a thermal laminator and pressed together for 10 seconds at moderate pressure. The photovoltaic module **1660** was then moved to align the next
10 adhesive strip with the press, and the process was repeated for each adhesive strip until the photovoltaic module **1660** was finished. The same adhesive and laminating procedure (without the wire interconnect) was used for the side seals of the photovoltaic module.

[00168] The embodiment illustrated in Figures 22A and 22B has been used to construct a working three stripe photovoltaic module. In one illustrative example, stripes of N3-
15 dyed titania nanoparticles were coated onto an ITO coated polyester substrate. Score marks were made in the ITO to break the electrical continuity between the cells. Score marks were also made in the appropriate places in the conductive coating of a platinum/titanium counter electrode on the complimentary polyester substrate. The adhesive used was THERMO-BOND 615 adhesive (available from the 3M Corporation)
20 in 2.5 mm thickness. THERMO-BOND 615 adhesive is a polyester-based hot melt adhesive supplied as a coated film on release paper. Strips of THERMO-BOND adhesive 615 were pretacked onto a platinum sheet by a brief cycle in a hot press at 120 °C. The release paper was removed, and one strand of 3 mm 316 stainless steel wire was lightly pressed into the exposed adhesive strips between the cells.

25 [00169] The wire **1575** or **1650** is an electrical conductor, and preferably a metal electrical conductor. Suitable wire materials include, but are not limited to, copper, silver, gold, platinum, nickel, palladium, iron, and alloys thereof. In another illustrative embodiment, more than one wire is used for each interconnection. Further, although the wire is illustrated in Figures 22A and 22B as having a substantially circular cross-section,
30 the cross-sectional shape of the wire is not limited to a substantially circular cross-section.

Other suitable cross-sectional shapes of the wire include, those that are substantially square, rectangular, elliptical, triangular, trapezoidal, polygonal, arcuate, and even irregular shapes. In addition, the wire may be a single stranded wire or a multi-stranded wire (e.g., a plurality of wires twisted together).

5 [00170] The hot melt adhesive 1570 and 1640 is not limited to THERMO-BOND adhesive 615. Other hot melt adhesives (e.g., BYNEL adhesive available from DuPont) that are thermally activated may be applied as a strip or film. The wire 1575 and 1650 may be coated with the adhesive 1570 and 1640, applied under the adhesive 1570 and 1640, over the adhesive 1570 and 1640, or pre-embedded in a strip of adhesive 1570 and 10 1640. In addition, curing adhesives (e.g., epoxies) may be used. Preferably, the interconnection region is held in the desired final configuration during the cure cycle when curing adhesives are used.

[00171] Wire interconnects are typically quite tolerant with respect to alignment. Furthermore, the wire providing the interconnection is protected by a nonconductive 15 adhesive. As a result, if a minor misalignment occurs and the adhesive bridges are scored, an electrical short will not result. Wire interconnects also facilitate the reduction of gaps between cells, which typically leads to higher overall photovoltaic module efficiency.

J. DSSCs with metal foil

20 [00172] According to another illustrative embodiment, a flexible photovoltaic module is formed using conventional methods (i.e., temperatures > about 400 °C) by first forming the interconnected nanoparticle layer on a flexible, metal foil, which is then laminated to a flexible substrate. The nanoparticle layer may be interconnected at low temperatures (< about 300 °C) as well. In either temperature range, a continuous manufacturing process, 25 such as a roll-to-roll process, may be used. Figure 23 depicts a photovoltaic module 1700 including a metal foil 1704. More particularly, the metal foil 1704 is laminated to a first flexible substrate 1708 using a first adhesive 1712. Score marks 1716 formed in the metal foil 1704 using a heated stylus serve to break the electrical continuity of the metal foil 1704, thus enabling a plurality of photovoltaic cells to be formed on a single substrate. A 30 photosensitized nanoparticle material 1720, according to the invention, is disposed on the

metal foil 1704. According to the illustrative embodiment, the photovoltaic module 1700 includes wire interconnects 1724 embedded in a second adhesive layer 1728 to form an electrical connection between the metal foil 1704 and a platinum-coated 1732 counter electrode 1733. The photovoltaic module 1700 also includes a charge carrier material 1736 and a conductive layer 1740 coated on a second substrate 1744. The metal foil 1704 may be any suitable conductive metal such as, for example, titanium, copper, silver, gold, platinum, nickel, palladium, iron, and alloys thereof. Suitable materials for the adhesive layer 1728 include BYNEL and THERMO-BOND, which are described above.

Thermoplastic and thermoset may also be used as the adhesive layer. According to one illustrative embodiment, the counter electrode 1733 includes a patterned-semiconductor, an adhesive layer, and a wire interconnect all formed on a flexible, transparent substrate.

[00173] According to the illustrative embodiment and using methods described above, a nanoparticle layer is coated on the metal foil 1704 in a continuous, intermittent, or patterned format. The nanoparticle layer is sintered at either low or high temperatures.

The metal foil 1704 is then scored to break the electrical continuity. The separated metal foil 1704 strips are thereupon laminated, according to the invention, to the non-conductive substrate 1708. A sensitizing dye and/or co-sensitizer may be applied to the nanoparticle layer to complete the photosensitized nanoparticle material 1720. A charge carrier material 1736 is coated over the photosensitized nanoparticle material 1720, and an adhesive layer 1728 and wire interconnect 1724 are added to couple the metal foil 1704 to the counter electrode 1733. A second flexible substrate coated with a conductive layer is laminated to complete the photovoltaic module.

[00174] In a preferred embodiment, the metal foil 1704 is titanium, the photosensitized nanoparticle material 1720 includes sintered titania, the conductive layer 1740 is ITO, and the second substrate 1744 is PET. The photovoltaic module may be constructed using a continuous manufacturing process, such as the one depicted in Figure 7. Such a process (e.g., a roll-to-roll process) includes the step of (1) coating a titania dispersion continuously, intermittently, or in a patterned format (e.g., to discrete portions) on the metal foil; (2) in line high or low temperature sintering of the titania coated metal foil; (3) in line sensitization of the titania coating; (4) slitting (e.g., by an ultrasonic slitting

technique described in more detail below) the metal foil into strips; (5) separating the strips, or ribbons, to a finite spacing by using a sequentially positioned series of guide roller or by simply conveying the slit strips over a contoured roll that provides lateral spreading and separation of the strips at a finite distance; and (6) laminating the strips to a first flexible, substrate. An electrolyte, counter electrode, and second substrate including a conductive layer may be laminated to the metal-foil-coated first substrate to complete the photovoltaic cell or module.

[00175] Figure 24 depicts, according to another illustrative embodiment, a metal-foil photovoltaic module **1800** that includes two photovoltaic modules **1804** and **1808** sandwiched together, thus permitting radiation **1812** to be received through two surfaces. The photovoltaic module **1800** may be formed using a continuous manufacturing process. According to the illustrative embodiment, a metal foil **1816** includes a photosensitized nanoparticle material **1820** disposed on two surfaces. The metal foil **1816** is scored as indicated at **1824** to disrupt the electrical continuity, and an electrolyte **1828**, an adhesive layer **1832**, a wire interconnect **1836**, and a platinum-coated **1840** counter electrode **1841** are all disposed between the metal foil **1816** and two flexible substrates **1844** and **1848**, thus completing the two photovoltaic modules. According to one illustrative embodiment, a conductive layer **1852** is disposed on the flexible substrates **1844** and **1848**. In a preferred embodiment, the metal foil **1816** is titanium, the photosensitized nanoparticle material **1820** includes sintered titania, the conductive layer **1852** is ITO, and the two flexible substrates **1844** and **1848** are PET.

K. Ultrasonic welding

[00176] According to another illustrative embodiment, an ultrasonic slitting device is used to slit the leading and the trailing edge of a flexible photovoltaic module as it advances during a continuous manufacturing process, such as the one depicted in Figure 7. For example, the slitting device **740** may be translated across the advancing sheet of photovoltaic cells or modules after the second flexible substrate **735** is applied to the advancing substrate sheet **705**. In one illustrative embodiment, the photovoltaic cell or modules include a metal foil coated with a photosensitized nanomatrix material.

[00177] The ultrasonic slitting device **740** may be a Branson Model FS-90. Preferably, the FS-90 is set to an amplitude of 50%, a pressure of 50-60 PSI, a speed of 5-10, and an anvil specification of 90°. The device **740** creates friction that melts the photovoltaic cell or module, thus simultaneously cutting and sealing the material. This prevents the electrolyte from leaking and precludes the atmosphere from penetrating the photovoltaic cell or module. Furthermore, the process interrupts conductive layers coated on the substrate.

L. Wire interconnects with metal coatings

[00178] In another illustrative embodiment, the invention provides a method of coating a wire interconnect with a metal or metal alloy with a low melting temperature. The metal or metal alloy melts during the lamination process, providing a more uniform contact between the two joined substrates. The improved contact enhances both the mechanical adhesion and the electrical connection. Figure 25 depicts a cross-section of a wire **1901** coated with a surrounding layer of a metal **1902** with a low melting temperature. The metal **1902** may be a metal alloy. According to one illustrative embodiment, the coated wire is substituted for the uncoated wire shown in Figures 21, 22, or 23.

[00179] Figure 26 depicts exemplary photovoltaic module **2000** including a metal foil **2004**. More particularly, the metal foil **2004** is laminated to a first flexible substrate **2008** using a first adhesive **2012**. Score marks **2016** formed in the metal foil **2004** using a heated stylus to break the electrical continuity of the metal foil **2004**, thus enabling a plurality of photovoltaic cells to be formed on a single substrate. A photosensitized nanoparticle material **2020**, according to the invention, is disposed on the metal foil **2004**. According to the illustrative embodiment, the photovoltaic module **2000** includes wire interconnects **2024** embedded in a second adhesive layer **2028** to form an electrical connection between the metal foil **2004** and a counter electrode **2033** coated with platinum **2032**. The wire **2024** is coated with a low melting temperature metal **2034**. During lamination, the metal **2034** melts and flows, thus forming a more uniform contact with the metal foil **2004** and the counter electrode **2033**. The photovoltaic module **2000**

also includes a charge carrier material **2036** and a conductive layer **2040** coated on a second substrate **2044**.

[00180] The wire **2024**, as describe above, may be copper, titanium, stainless steel, or other suitable wire. In a preferred embodiment, the wire is a 3 mil copper wire, and is
5 coated with a eutectic mixture of bismuth-tin. The melting temperature of bismuth-tin is 138 °C. A thin sheet of BYNEL adhesive (ethylene maleic anhydride) is disposed between the metal foil and the counter electrode. The melting temperature of the adhesive is 126 °C. The adhesive and coated metal wire are then thermally laminated (hot bar laminator at a temperature of about 150 °C) between two PET substrates with ITO
10 conductive layers. Suitable metals have melting temperatures in the range of about 50 °C to about 250 °C. Preferably, the melting temperatures are in the range of about 75 °C to about 180 °C, and the adhesive melts at a lower temperature than the metal coating.

[00181] While the invention has been particularly shown and described with reference to specific illustrative embodiments, it should be understood that various changes in form
15 and detail may be made without departing from the spirit and scope of the invention as defined by the appended claims. By way of example, any of the disclosed features may be combined with any of the other disclosed features to form a photovoltaic cell or module.

What is claimed is:

Claims

- 1 1. A method of connecting a plurality of photovoltaic cells within a photovoltaic
2 module, the method comprising the steps of:
3 providing a first base material including a substrate having a first conductive layer;
4 disposing a photosensitized interconnected nanoparticle material and a charge
5 carrier material on the first conductive layer;
6 providing a wire; and
7 joining a second base material including a substrate having a second conductive
8 layer to the first base material such that the first and second conductive layers are in
9 electrical contact with the wire.
- 1 2. The method of claim 1, wherein at least one of the first and second base materials
2 is scored.
- 1 3. The method of claim 1, wherein the photosensitized interconnected nanoparticle
2 material comprises nanoparticles linked by a polymeric linking agent.
- 1 4. The method of claim 1, wherein the photosensitized interconnected nanoparticle
2 material comprises particles with an average size substantially in the range of about 5 nm
3 to about 80 nm.
- 1 5. The method of claim 1, wherein the photosensitized interconnected nanoparticle
2 material is selected from the group consisting of titanium oxides, zirconium oxides, zinc
3 oxides, tungsten oxides, niobium oxides, lanthanum oxides, tantalum oxides, terbium
4 oxides, tin oxides, and combinations thereof.
- 1 6. The method of claim 1, wherein the photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises a molecule selected from the
3 group consisting of xanthenes, cyanines, merocyanines, phthalocyanines, and pyrroles.

- 1 7. The method of claim 1, wherein the photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises a metal ion selected from the
3 group consisting of divalent and trivalent metals.
- 1 8. The method of claim 1, wherein photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises at least one of a ruthenium
3 transition metal complex, an osmium transition metal complex, and an iron transition
4 metal complex.
- 1 9. The method of claim 1, wherein the charge carrier material comprises a redox
2 electrolyte system.
- 1 10. The method of claim 1, wherein the charge carrier material comprises a polymeric
2 electrolyte.
- 1 11. The method of claim 1, wherein the charge carrier material transmits at least about
2 60% of incident visible light.
- 1 12. The method of claim 1, wherein at least one of the first and second base materials
2 comprises a polyethylene terephthalate material.
- 1 13. The method of claim 1, wherein at least one of the first and second base materials
2 is significantly light transmitting.
- 1 14. The method of claim 1, wherein at least one of the first and second base materials
2 is flexible.
- 1 15. The method of claim 1, further comprising disposing a catalytic media layer
2 between the first and second base materials.

- 1 16. The method of claim 15, wherein the catalytic media layer comprises platinum.
- 1 17. The method of claim 1, wherein at least one of the first and second conductor
2 layers comprises indium tin oxide.
- 1 18. The method of claim 1, wherein the wire is electrically conductive.
- 1 19. The method of claim 1, wherein the wire comprises a first metal.
- 1 20. The method of claim 19, wherein the first metal comprises stainless steel.
- 1 21. The method of claim 19, wherein the first metal comprises copper.
- 1 22. The method of claim 19, wherein the first metal comprises titanium.
- 1 23. The method of claim 1, further comprising disposing a plurality of wires between
2 the first and second base materials.
- 1 24. The method of claim 1, wherein joining step comprises laminating the first and
2 second conductive layers by disposing an adhesive layer therebetween such that,
3 following the lamination, the wire is embedded in the adhesive layer.
- 1 25. The method of claim 24, wherein the adhesive layer comprises a hot melt
2 adhesive.
- 1 26. The method of claim 24, wherein the adhesive layer comprises a polyester
2 material.
- 1 27. The method of claim 1, further comprising coating the wire with adhesive prior to
2 joining.

1 28. The method of claim 24, wherein the adhesive layer comprises an epoxy.

1 29. The method of claim 24, further comprising curing the adhesive layer.

1 30. The method of claim 24, wherein the adhesive layer comprises a thermoplastic.

1 31. The method of claim 24, wherein the adhesive layer comprises a thermoset.

1 32. The method of claim 24, wherein the adhesive layer comprises ethylene maleic
2 anhydride copolymer.

1 33. The method of claim 1, wherein the wire comprises a coating of a second metal.

1 34. The method of claim 28, wherein the second metal has a melting temperature in
2 the range of about 50 °C to about 250 °C.

1 35. The method of claim 28, wherein the second metal has a melting temperature in
2 the range of about 75 °C to about 180 °C.

1 36. The method of claim 33, further comprising coating the metal coated wire with an
2 adhesive prior to the joining step.

1 37. The method of claim 36, wherein the adhesive has a lower melting temperature
2 than the second metal.

1 38. The method of claim 33, wherein the second metal comprises bismuth.

1 39. The method of claim 33, wherein the second metal comprises tin.

1 40. A photovoltaic module comprising:

2 a first base material including a substrate having a first conductive layer;
3 a photosensitized interconnected nanoparticle layer and a charge carrier material
4 disposed on the first conductive layer;
5 a wire; and
6 a second base material including a substrate having a second conductive layer, the
7 second base material being joined to the first base material such that the first and second
8 conductive layers are in electrical contact with the wire.

1 41. The photovoltaic module of claim 40, wherein at least one of the first and second
2 base materials is scored.

1 42. The photovoltaic module of claim 40, wherein the photosensitized interconnected
2 nanoparticle material comprises nanoparticles linked by a polymeric linking agent.

1 43. The photovoltaic module of claim 40, wherein the photosensitized interconnected
2 nanoparticle material comprises particles with an average size substantially in the range of
3 about 5 nm to about 80 nm.

1 44. The photovoltaic module of claim 40, wherein the photosensitized interconnected
2 nanoparticle material is selected from the group consisting of titanium oxides, zirconium
3 oxides, zinc oxides, tungsten oxides, niobium oxides, lanthanum oxides, tin oxides,
4 terbium oxides, tantalum oxides, and combinations thereof.

1 45. The photovoltaic module of claim 40, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises a molecule
3 selected from the group consisting of xanthenes, cyanines, merocyanines, phthalocyanines,
4 and pyrroles.

1 46. The photovoltaic module of claim 40, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises a metal ion
3 selected from the group consisting of divalent and trivalent metals.

1 47. The photovoltaic module of claim 40, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises at least one of a
3 ruthenium transition metal complex, an osmium transition metal complex, and an iron
4 transition metal complex.

1 48. The photovoltaic module of claim 40, wherein the charge carrier material
2 comprises a electrolyte redox system.

1 49. The photovoltaic module of claim 40, wherein the charge carrier material
2 comprises a polymeric electrolyte.

1 50. The photovoltaic module of claim 40, wherein the charge carrier material
2 transmits at least about 60% of incident visible light.

1 51. The photovoltaic module of claim 40, wherein at least one of the first and second
2 base materials comprises a polyethylene terephthalate material.

1 52. The photovoltaic module of claim 40, wherein at least one of the first and second
2 base materials is significantly light transmitting.

1 53. The photovoltaic module of claim 40, wherein at least one of the first and second
2 base materials is flexible.

1 54. The photovoltaic module of claim 40, further comprising a catalytic media layer
2 disposed between the first and second base materials.

- 1 55. The photovoltaic module of claim 54, wherein the catalytic media layer comprises
2 platinum.
- 1 56. The photovoltaic module of claim 40, wherein at least one of the first and second
2 conductor layers comprises indium tin oxide.
- 1 57. The photovoltaic module of claim 40, wherein the wire is electrically conductive.
- 1 58. The photovoltaic module of claim 40, wherein the wire comprises a first metal.
- 1 59. The photovoltaic module of claim 40, wherein the first metal comprises stainless
2 steel.
- 1 60. The photovoltaic module of claim 40, wherein the metal comprises titanium.
- 1 61. The photovoltaic module of claim 40, wherein the metal comprises copper
- 1 62. The photovoltaic module of claim 40 further comprising an adhesive layer
2 disposed between the first and second conductive layers, such that the wire is embedded
3 in the adhesive layer.
- 1 63. The photovoltaic module of claim 62, wherein the adhesive layer comprises a hot
2 melt adhesive.
- 1 64. The photovoltaic module of claim 62, wherein the adhesive layer comprises a
2 polyester material.
- 1 65. The photovoltaic module of claim 62, wherein the adhesive layer comprises an
2 epoxy.

- 1 66. The photovoltaic module of claim 62, wherein the adhesive layer comprises a
2 thermoplastic.
- 1 67. The photovoltaic module of claim 62, wherein the adhesive layer comprises a
2 thermoset.
- 1 68. The photovoltaic module of claim 62, wherein the adhesive layer comprises
2 ethylene maleic anhydride copolymer.
- 1 69. The photovoltaic module of claim 40, wherein the wire comprises a coating of a
2 second metal.
- 1 70. The photovoltaic module of claim 69, wherein the second metal has a melting
2 temperature in the range of about 50 °C to about 250 °C.
- 1 71. The photovoltaic module of claim 69, wherein the second metal has a melting
2 temperature in the range of about 75 °C to about 180 °C.
- 1 72. The photovoltaic module of claim 69, wherein the metal coated wire is coated
2 with an adhesive prior to joining.
- 1 73. The photovoltaic module of claim 72, wherein the adhesive has a lower melting
2 temperature than the second metal.
- 1 74. The photovoltaic module of claim 69, wherein the second metal comprises
2 bismuth.
- 1 75. The photovoltaic module of claim 69, wherein the second metal comprises tin.

1 76. The photovoltaic module of claim 40, wherein at least one of the first and second
2 base materials comprises a polyethylene naphthalate material.

1 77. A method of scoring comprising the steps of:
2 providing a first coated base material; and
3 scoring the coating of the first coated base material at a temperature sufficiently
4 elevated to part the coating and melt at least a portion of the first base material.

1 78. The method of claim 77, wherein the parting of the coating and the melting of the
2 first base material disrupts electrical continuity of the coating of the first base material.

1 79. The method of claim 77, wherein the scoring step is performed using a heated stylus.

1 80. The method of claim 77, wherein the scoring step is performed using a soldering iron
2 tip.

1 81. The method of claim 77, wherein the scoring step is performed mechanically.

1 82. The method of claim 77, further comprising applying a photosensitized interconnected
2 nanoparticle material and a charge carrier material to the coating of the first base material.

1 83. The method of claim 82, wherein the photosensitized interconnected nanoparticle
2 material comprises nanoparticles linked by polymeric linking agent.

1 84. The method of claim 82, wherein the photosensitized interconnected nanoparticle
2 material comprises particles with an average size in the range of about 5 nm to about 80
3 nm.

1 85. The method of claim 82, wherein the photosensitized interconnected nanoparticle
2 material is selected from the group consisting of titanium oxides, zirconium oxides, zinc

3 oxides, tungsten oxides, niobium oxides, lanthanum oxides, terbium oxides, tantalum
4 oxides, tin oxides, and combinations thereof.

1 86. The method of claim 82, wherein the photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises a molecule selected from the
3 group consisting of xanthenes, cyanines, merocyanines, phthalocyanines, and pyrroles.

1 87. The method of claim 82, wherein the photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises a metal ion selected from the
3 group consisting of divalent and trivalent metals.

1 88. The method of claim 82, wherein the photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises at least one of a ruthenium
3 transition metal complex, an osmium transition metal complex, and an iron transition
4 metal complex.

1 89. The method of claim 82, wherein the charge carrier material comprises a redox
2 electrolyte system.

1 90. The method of claim 82, wherein the charge carrier material comprises a polymeric
2 electrolyte.

1 91. The method of claim 82, wherein the charge carrier material transmits at least about
2 60% of incident visible light.

1 92. The method of claim 77, wherein the coating of the first base material comprises a
2 conductive layer.

1 93. The method of claim 77, wherein the first base material comprises a polyethylene
2 terephthalate material.

1 94. The method of claim 77, wherein the first base material is significantly light
2 transmitting.

1 95. The method of claim 77, wherein the first base material is flexible.

1 96. The method of claim 77, wherein the coating of the first base material comprises
2 indium tin oxide.

1 97. A method of forming a photovoltaic module, the method comprising the steps of:
2 providing a first coated base material;
3 scoring the coating of the first coated base material at a temperature sufficiently
4 elevated to part the coating and melt at least a portion of the first base material;
5 providing a second coated base material;
6 scoring the coating of the second coated base material at a temperature sufficiently
7 elevated to part the coating and melt at least a portion of the second base material; and
8 joining the first and second coated base materials to form a photovoltaic module

1 98. The method of claim 97, wherein the joining is performed such that the coatings of the
2 first and second base materials are sandwiched between the first and second base
3 materials, and the first and second base materials are in electrical communication with
4 each other.

1 99. The method of claim 97, wherein the melting of the first coated base material disrupts
2 electrical continuity of the coating of the first base material.

1 100. The method of claim 97, wherein the melting of the second coated base material
2 disrupts electrical continuity of the coating of the second base material.

1 101. The method of claim 97, wherein the joining comprises laminating.

- 1 102. The method of claim 97, wherein the scorings of the first and second coated base
2 materials are substantially aligned when joined.
- 1 103. The method of claim 97, wherein the scoring steps are performed using a heated
2 stylus.
- 1 104. The method of claim 97, wherein the scoring steps are performed using a
2 soldering iron tip.
- 1 105. The method of claim 97, wherein the scoring steps are performed mechanically.
- 1 106. The method of claim 97, further comprising disposing a photosensitized
2 interconnected nanoparticle material and a charge carrier material between the coatings of
3 the first and second base materials.
- 1 107. The method of claim 106, wherein the photosensitized interconnected nanoparticle
2 material comprises nanoparticles linked by polymeric linking agent.
- 1 108. The method of claim 106, wherein the photosensitized interconnected nanoparticle
2 material comprises particles with an average size in the range of about 5 nm to about 80
3 nm.
- 1 109. The method of claim 106, wherein the photosensitized interconnected nanoparticle
2 material is selected from the group consisting of titanium oxides, zirconium oxides, zinc
3 oxides, tungsten oxides, niobium oxides, lanthanum oxides, terbium oxides, tantalum
4 oxides, tin oxides, and combinations thereof.
- 1 110. The method of claim 106, wherein the photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises a molecule selected from the
3 group consisting of xanthenes, cyanines, merocyanines, phthalocyanines, and pyrroles.

1 111. The method of claim 106, wherein the photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises a metal ion selected from the
3 group consisting of divalent and trivalent metals.

1 112. The method of claim 106, wherein the photosensitized interconnected nanoparticle
2 material comprises a photosensitizing agent that comprises at least one of a ruthenium
3 transition metal complex, an osmium transition metal complex, and an iron transition
4 metal complex.

1 113. The method of claim 106, wherein the charge carrier material comprises a redox
2 electrolyte system.

1 114. The method of claim 106, wherein the charge carrier material comprises a
2 polymeric electrolyte.

1 115. The method of claim 106, wherein the charge carrier material transmits at least
2 about 60% of incident visible light.

1 116. The method of claim 97, wherein the coatings of the first and second base
2 materials comprises a conductive material.

1 117. The method of claim 97, wherein at least one of the first and second base materials
2 comprise a polyethylene terephthalate material.

1 118. The method of claim 116, wherein at least one of the first and second base
2 materials are significantly light transmitting.

1 119. The method of claim 116, wherein at least one of the first and second base
2 materials is flexible.

1 120. The method of claim 116, wherein the conductive material comprises indium tin
2 oxide.

1 121. The method of claim 97, further comprising applying a catalytic media layer to at
2 least one of the coatings of the first and second base materials.

1 122. The method of claim 121, wherein the catalytic media layer comprises platinum.

1 123. The method of claim 97, wherein at least one of the first and second base materials
2 comprise a polyethylene naphthalate material.

1 124. The method of claim 77, wherein the first base material comprises a polyethylene
2 naphthalate material.

1 125. A method of forming a photovoltaic cell, the method comprising the steps of:
2 providing a metal foil;
3 applying a nanoparticle material to the metal foil;
4 heating the nanoparticle material to form an interconnected nanoparticle material;
5 and
6 disposing between first and second flexible substrates the metal foil coated with
7 the interconnected nanoparticle material.

1 126. The method of claim 125, further comprising the steps of:
2 disposing a conductive layer between the metal foil and the first flexible substrate;
3 providing a wire; and
4 joining the first and second flexible substrates, such that the conductive layer and
5 the metal foil are in electrical contact with the wire.

1 127. The method of claim 126, wherein joining step comprises laminating the first and
2 second conductive layers by disposing an adhesive layer therebetween such that,
3 following the lamination, the wire is embedded in the adhesive layer.

1 128. The method of claim 125, further comprising photosensitizing the interconnected
2 nanoparticle material with a photosensitizing agent.

1 129. The method of claim 125, wherein the interconnected nanoparticle material
2 comprises particles with an average size in the range of about 5 nm to about 80 nm.

1 130. The method of claim 125, wherein the interconnected nanoparticle material is
2 selected from the group consisting of titanium dioxide, zirconium oxides, zinc oxides,
3 tungsten oxides, niobium oxides, lanthanum oxides, tin oxides, terbium oxides, tantalum
4 oxides, and combinations thereof.

1 131. The method of claim 128, wherein the photosensitizing agent comprises a
2 molecule selected from the group consisting of a xanthine, cyanine, merocyanine,
3 phthalocyanine, and pyrrole.

1 132. The method of claim 128, wherein the photosensitizing agent comprises a metal
2 ion selected from the group consisting of divalent and trivalent metals.

1 133. The method of claim 128, wherein the photosensitizing agent comprises at least
2 one of a ruthenium transition metal complex, an osmium transition metal complex, and an
3 iron transition metal complex.

1 134. The method of claim 125, further comprising disposing a charge carrier material
2 between the first and second flexible substrates.

1 135. The method of claim 134, wherein the charge carrier material comprises a redox
2 electrolyte system.

1 136. The method of claim 134, wherein the charge carrier material comprises a
2 polymeric electrolyte.

1 137. The method of claim 125, further comprising disposing a catalytic media layer
2 between the first and second flexible substrates.

1 138. The method of claim 137, wherein the catalytic media layer comprises platinum.

1 139. The method of claim 126, wherein the conductor layer comprises indium tin
2 oxide.

1 140. The method of claim 126, wherein the wire is electrically conductive.

1 141. The method of claim 126, wherein the wire comprises a metal.

1 142. The method of claim 141, wherein the metal comprises stainless steel.

1 143. The method of claim 126, further comprising disposing a plurality of wires
2 between the first and second flexible substrates.

1 144. The method of claim 127, wherein the adhesive layer comprises a hot melt
2 adhesive.

1 145. The method of claim 127, wherein the adhesive layer comprises a polyester
2 material.

1 146. The method of claim 126, further comprising coating the wire with adhesive prior
2 to laminating.

1 147. The method of claim 127, wherein the adhesive layer comprises an epoxy.

1 148. The method of claim 127, further comprising curing the adhesive layer.

1 149. The method of claim 125, wherein at least one of the first and second flexible
2 substrates is significantly light transmitting.

1 150. The method of claim 125, wherein the metal foil comprises titanium.

1 151. The method of claim 125, wherein the interconnected nanoparticle material is
2 interconnected using a polylinker at temperatures less than about 300 °C.

1 152. The method of claim 125, the interconnected nanoparticle material is
2 interconnected using a polylinker at temperatures less than about 150 °C.

1 153. The method of claim 125, wherein the interconnected nanoparticle material is
2 interconnected using a polylinker at room temperature.

1 154. A photovoltaic cell comprising:
2 a metal foil; and
3 an interconnected nanoparticle material formed on the metal foil, the metal foil
4 and the interconnected nanoparticle material both being disposed between first and second
5 flexible substrates.

1 155. The photovoltaic cell of claim 154, further comprising:
2 a conductive layer disposed between the metal foil and the first flexible substrate;
3 and

4 a wire placed such that the conductive layer and the metal foil are in electrical
5 contact with the wire.

1 156. The photovoltaic cell of claim 154, wherein the interconnected nanoparticle
2 material comprises a photosensitized interconnected nanoparticle material.

1 157. The photovoltaic cell of claim 154, wherein the interconnected nanoparticle
2 material comprises particles with an average size in the range of about 5 nm to about 80
3 nm.

1 158. The photovoltaic cell of claim 154, wherein the interconnected nanoparticle
2 material is selected from the group consisting of titanium oxides, zirconium oxides, zinc
3 oxides, tungsten oxides, niobium oxides, lanthanum oxides, tantalum oxides, terbium
4 oxides, tin oxides, and combinations thereof.

1 159. The photovoltaic cell of claim 156, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises a molecule
3 selected from the group consisting of xanthenes, cyanines, merocyanines, phthalocyanines,
4 and pyrroles.

1 160. The photovoltaic cell of claim 156, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises a metal ion
3 selected from the group consisting of divalent and trivalent metals.

1 161. The photovoltaic cell of claim 156, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises at least one of a
3 ruthenium transition metal complex, an osmium transition metal complex, and an iron
4 transition metal complex.

1 162. The photovoltaic cell of claim 154 further comprising a charge carrier material
2 disposed between the first and second flexible substrates.

1 163. The photovoltaic cell of claim 162, wherein the charge carrier material comprises
2 a redox electrolyte system.

1 164. The photovoltaic cell of claim 162, wherein the charge carrier material comprises
2 a polymeric electrolyte.

1 165. The photovoltaic cell of claim 162, wherein the charge carrier material transmits at
2 least about 60% of incident visible light.

1 166. The photovoltaic cell of claim 154, further comprising a catalytic media layer
2 disposed between the first and second base materials.

1 167. The photovoltaic cell of claim 166, wherein the catalytic media layer comprises
2 platinum.

1 168. The photovoltaic cell of claim 155, wherein the first conductive layer comprises
2 indium tin oxide.

1 169. The photovoltaic cell of claim 155, wherein the wire is electrically conductive.

1 170. The photovoltaic cell of claim 155, wherein the wire comprises a metal.

1 171. The photovoltaic cell of claim 170, wherein the metal comprises stainless steel.

1 172. The photovoltaic cell of claim 170, wherein the metal comprises platinum.

1 173. The photovoltaic cell of claim 154 further comprising an adhesive layer disposed
2 between the first and second conductive layers, such that the wire is embedded in the
3 adhesive layer.

1 174. The photovoltaic cell of claim 173, wherein the adhesive layer comprises a hot
2 melt adhesive.

1 175. The photovoltaic cell of claim 173, wherein the adhesive layer comprises a
2 polyester material.

1 176. The photovoltaic cell of claim 173, wherein the adhesive layer comprises an
2 epoxy.

1 177. The photovoltaic cell of claim 154, wherein the metal foil comprises titanium.

1 178. A method of forming a photovoltaic module, the method comprising the steps of:
2 providing a metal foil;
3 applying a nanoparticle material to discrete portions of the metal foil;
4 heating the nanoparticle material to form an interconnected nanoparticle material;
5 slitting the foil to mechanically separate the discrete portions;
6 disposing the discrete portions of the metal foil between first and second flexible
7 substrates to form a photovoltaic module.

1 179. The method of claim 178, wherein in the discrete portions of the metal foil having
2 the nanoparticle material disposed thereon are selectively spaced between the first and
3 second flexible substrates.

1 180. The method of claim 178, wherein in the slitting step includes slitting the discrete
2 portions of metal foil having the nanoparticle material disposed thereon into strips.

- 1 181. The method of claim 178, further comprising the steps of:
2 disposing a conductive layer between the discrete portions of metal foil and the
3 first flexible substrate;
4 providing a wire; and
5 joining the first and second flexible substrates, such that the conductive layer and
6 the metal foil are in electrical contact with the wire.
- 1 182. The method of claim 181, wherein the joining step comprises laminating the first
2 and second conductive layers by disposing an adhesive layer therebetween such that,
3 following the lamination, the wire is embedded in the adhesive layer.
- 1 183. The method of claim 178, further comprising photosensitizing the interconnected
2 nanoparticle material with a photosensitizing agent.
- 1 184. The method of claim 178, wherein the interconnected nanoparticle material
2 comprises particles with an average size in the range of about 5 nm to about 80 nm.
- 1 185. The method of claim 178, wherein the interconnected nanoparticle material is
2 selected from the group consisting of titanium dioxide, zirconium oxides, zinc oxides,
3 tungsten oxides, niobium oxides, lanthanum oxides, tin oxides, terbium oxides, tantalum
4 oxides, and combinations thereof.
- 1 186. The method of claim 183, wherein the photosensitizing agent comprises a
2 molecule selected from the group consisting of a xanthine, cyanine, merocyanine,
3 phthalocyanine, and pyrrole.
- 1 187. The method of claim 183, wherein the photosensitizing agent comprises a metal
2 ion selected from the group consisting of divalent and trivalent metals.

1 188. The method of claim 183, wherein the photosensitizing agent comprises at least
2 one of a ruthenium transition metal complex, an osmium transition metal complex, and an
3 iron transition metal complex.

1 189. The method of claim 178, further comprising disposing a charge carrier material
2 between the first and second flexible substrates.

1 190. The method of claim 189, wherein the charge carrier material comprises a redox
2 electrolyte system.

1 191. The method of claim 189, wherein the charge carrier material comprises a
2 polymeric electrolyte.

1 192. The method of claim 178, further comprising disposing a catalytic media layer
2 between the first and second flexible substrates.

1 193. The method of claim 192, wherein the catalytic media layer comprises platinum.

1 194. The method of claim 178, wherein the conductor layer comprises indium tin
2 oxide.

1 195. The method of claim 181, wherein the wire is electrically conductive.

1 196. The method of claim 181, wherein the wire comprises a metal.

1 197. The method of claim 196, wherein the metal comprises stainless steel.

1 198. The method of claim 181, further comprising disposing a plurality of wires
2 between the first and second flexible substrates.

1 199. The method of claim 182, wherein the adhesive layer comprises a hot melt
2 adhesive.

1 200. The method of claim 182, wherein the adhesive layer comprises a polyester
2 material.

1 201. The method of claim 181, further comprising coating the wire with adhesive prior
2 to laminating.

1 202. The method of claim 182, wherein the adhesive layer comprises an epoxy.

1 203. The method of claim 182, further comprising curing the adhesive layer.

1 204. The method of claim 178, wherein at least one of the first and second flexible
2 substrates is significantly light transmitting.

1 205. The method of claim 178, wherein the metal foil comprises titanium.

1 206. The method of claim 178, wherein the interconnected nanoparticle material is
2 interconnected using a polylinker at temperatures less than about 300 °C.

1 207. The method of claim 178, the interconnected nanoparticle material is
2 interconnected using a polylinker at temperatures less than about 150 °C.

1 208. The method of claim 178, wherein the interconnected nanoparticle material is
2 interconnected using a polylinker at room temperature.

1 209. A photovoltaic module comprising:
2 first and second flexible substrates;
3 a plurality of discrete portions of metal foil; and

4 an interconnected nanoparticle material formed on each of the discrete portions of
5 the metal foil, the discrete portions of the metal foil having the interconnected
6 nanoparticle material disposed thereon each being disposed between the first and second
7 flexible substrates to form a photovoltaic module.

1 210. The photovoltaic module of claim 209, wherein in the discrete portions of the
2 metal foil having the nanoparticle material disposed thereon are selectively spaced
3 between the first and second flexible substrates.

1 211. The photovoltaic module of claim 209, wherein in the discrete portions of metal
2 foil having the nanoparticle material disposed thereon are shaped as strips.

1 212. The photovoltaic module of claim 209, further comprising:
2 a conductive layer disposed between the metal foil and the first flexible substrate;
3 and
4 a wire placed such that the conductive layer and the metal foil are in electrical
5 contact with the wire.

1 213. The photovoltaic module of claim 209, wherein the interconnected nanoparticle
2 material comprises a photosensitized interconnected nanoparticle material.

1 214. The photovoltaic module of claim 209, wherein the interconnected nanoparticle
2 material comprises particles with an average size in the range of about 5 nm to about 80
3 nm.

1 215. The photovoltaic module of claim 209, wherein the interconnected nanoparticle
2 material is selected from the group consisting of titanium oxides, zirconium oxides, zinc
3 oxides, tungsten oxides, niobium oxides, lanthanum oxides, tantalum oxides, terbium
4 oxides, tin oxides, and combinations thereof.

1 216. The photovoltaic module of claim 213, wherein the photosensitized
2 interconnected nanoparticle material comprises a photosensitizing agent that comprises a
3 molecule selected from the group consisting of xanthenes, cyanines, merocyanines,
4 phthalocyanines, and pyrroles.

1 217. The photovoltaic module of claim 213, wherein the photosensitized
2 interconnected nanoparticle material comprises a photosensitizing agent that comprises a
3 metal ion selected from the group consisting of divalent and trivalent metals.

1 218. The photovoltaic module of claim 213, wherein the photosensitized
2 interconnected nanoparticle material comprises a photosensitizing agent that comprises at
3 least one of a ruthenium transition metal complex, an osmium transition metal complex,
4 and an iron transition metal complex.

1 219. The photovoltaic module of claim 209 further comprising a charge carrier material
2 disposed between the first and second flexible substrates.

1 220. The photovoltaic module of claim 219, wherein the charge carrier material
2 comprises a redox electrolyte system.

1 221. The photovoltaic module of claim 219, wherein the charge carrier material
2 comprises a polymeric electrolyte.

1 222. The photovoltaic module of claim 219, wherein the charge carrier material
2 transmits at least about 60% of incident visible light.

1 223. The photovoltaic module of claim 209, further comprising a catalytic media layer
2 disposed between the first and second base materials.

- 1 224. The photovoltaic module of claim 223, wherein the catalytic media layer
2 comprises platinum.
- 1 225. The photovoltaic cell of claim 212, wherein the conductive layer comprises
2 indium tin oxide.
- 1 226. The photovoltaic cell of claim 212, wherein the wire is electrically conductive.
- 1 227. The photovoltaic module of claim 212, wherein the wire comprises a metal.
- 1 228. The photovoltaic module of claim 103, wherein the metal comprises stainless
2 steel.
- 1 229. The photovoltaic module of claim 103, wherein the metal comprises platinum.
- 1 230. The photovoltaic module of claim 212 further comprising an adhesive layer
2 disposed between the first and second conductive layers, such that the wire is embedded
3 in the adhesive layer.
- 1 231. The photovoltaic module of claim 230, wherein the adhesive layer comprises a hot
2 melt adhesive.
- 1 232. The photovoltaic module of claim 230, wherein the adhesive layer comprises a
2 polyester material.
- 1 233. The photovoltaic module of claim 230, wherein the adhesive layer comprises an
2 epoxy.
- 1 234. The photovoltaic module of claim 209, wherein the metal foil comprises titanium.

1 235. The photovoltaic module of claim 209, wherein at least one of the first and
2 second flexible substrates comprises a polyethylene terephthalate material.

1 236. The photovoltaic module of claim 209, wherein at least one of the first and second
2 flexible substrates comprises a polyethylene naphthalate material.

1 237. A photovoltaic module capable of receiving electromagnetic radiation via two
2 sides, the photovoltaic module comprising:

3 a plurality of discrete portions of metal foil, each of the discrete portions having first
4 and second surfaces;

5 an interconnected nanoparticle material applied to each of the first and second
6 surfaces;

7 a first flexible substrate disposed on top of the interconnected nanoparticle material
8 disposed on the first surface of each of the discrete portions of metal foil; and

9 a second flexible substrate disposed on top of the interconnected nanoparticle
10 material disposed on the second surface of each of the discrete portions of the metal foil
11 to form a photovoltaic module.

1 238. The photovoltaic module of claim 237, wherein the discrete portions of the metal
2 foil having the nanoparticle material disposed thereon are selectively spaced between the
3 first and second flexible substrates.

1 239. The photovoltaic module of claim 237, wherein in the discrete portions of metal
2 foil having the nanoparticle material disposed thereon are shaped as strips.

1 240. The photovoltaic module of claim 237, further comprising:

2 a first conductive layer disposed between the first surface of the discrete portions
3 and the first flexible substrate;

4 and

5 a first wire placed such that the first conductive layer and the first surface of the
6 discrete portions are in electrical contact with the first wire.

1 241. The photovoltaic module of claim 240, further comprising:
2 a second conductive layer disposed between the second surface of the discrete
3 portions and the second flexible substrate; and
4 a second wire placed such that the second conductive layer and the second surface
5 of the discrete portions are in electrical contact with the first wire.

1 242. The photovoltaic module of claim 237, wherein at least one of the first and second
2 flexible substrates comprises a polyethylene terephthalate material.

1 243. The photovoltaic module of claim 237, wherein at least one of the first and second
2 flexible substrates comprises a polyethylene naphthalate material.

1 244. A method of forming a photovoltaic module capable of receiving electromagnetic
2 radiation via two sides, the method comprising:
3 providing a plurality of discrete portions of metal foil, each of the discrete portions
4 having first and second surfaces;
5 applying an interconnected nanoparticle material to each of the first and second
6 surfaces;
7 disposing a first flexible substrate on top of the interconnected nanoparticle material
8 disposed on the first surface of each of the discrete portions of metal foil; and
9 disposing a second flexible substrate on top of the interconnected nanoparticle
10 material disposed on the second surface of each of the discrete portions of the metal foil
11 to form a photovoltaic module.

1 245. The method of claim 244 comprising, selectively spacing the discrete portions of
2 the metal foil having the nanoparticle material disposed thereon between the first and
3 second flexible substrates.

1 246. The method of claim 244, wherein in the discrete portions of metal foil having the
2 nanoparticle material disposed thereon are shaped as strips.

1 247. The method of claim 244, further comprising:
2 disposing a first conductive layer between the first surface of the discrete portions
3 and the first flexible substrate; and
4 disposing a first wire such that the first conductive layer and the first surface of the
5 discrete portions are in electrical contact with the first wire.

1 248. The photovoltaic module of claim 244, wherein at least one of the first and second
2 flexible substrates comprises a polyethylene terephthalate material.

1 249. The photovoltaic module of claim 244, wherein at least one of the first and second
2 flexible substrates comprises a polyethylene naphthalate material.

1 250. A photovoltaic cell comprising a charge carrier material and a photosensitized
2 interconnected nanoparticle material including nanoparticles linked by a polymeric
3 linking agent, both disposed between first and second rigid, significantly light-
4 transmitting substrates.

1 251. The photovoltaic cell of claim 250, wherein the charge carrier material and the
2 photosensitized interconnected nanoparticle material are disposed between a first and
3 second flexible, significantly light-transmitting substrate that are themselves disposed
4 between the first and second rigid, significantly light-transmitting substrates.

1 252. The photovoltaic cell of claim 250, wherein the photosensitized interconnected
2 nanoparticle material comprises particles with an average size substantially in the range of
3 about 5 nm to about 80 nm.

1 253. The photovoltaic cell of claim 250, wherein the photosensitized interconnected
2 nanoparticle material is selected from the group consisting of titanium oxides, zirconium
3 oxides, zinc oxides, tungsten oxides, niobium oxides, lanthanum oxides, tin oxides,
4 tantalum oxides, terbium oxides, and combinations thereof.

1 254. The photovoltaic cell of claim 250, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises a molecule
3 selected from the group consisting of xanthenes, cyanines, merocyanines, phthalocyanines,
4 and pyrroles.

1 255. The photovoltaic cell of claim 250, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises a metal ion
3 selected from the group consisting of divalent and trivalent metals.

1 256.. The photovoltaic cell of claim 250, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises at least one of a
3 ruthenium transition metal complex, an osmium transition metal complex, and an iron
4 transition metal complex.

1 257. The photovoltaic cell of claim 250, wherein the charge carrier material
2 comprises a redox electrolyte system.

1 258. The photovoltaic cell of claim 250, wherein the charge carrier material
2 comprises a polymeric electrolyte.

1 259. The photovoltaic cell of claim 251, wherein at least one of the first and second
2 flexible, significantly light-transmitting substrates comprises a polyethylene terephthalate
3 material.

1 260. The photovoltaic cell of claim 250, wherein at least one of the first and second
2 rigid, significantly light-transmitting substrates comprises tempered glass.

1 261. The photovoltaic cell of claim 250, further comprising a catalytic media layer
2 disposed between the first and second rigid, significantly light-transmitting substrates.

1 262. The photovoltaic cell of claim 261, wherein the catalytic media layer
2 comprises platinum.

1 263. The photovoltaic cell of claim 250, further comprising an electrical conductor
2 material applied to at least one of the first and second rigid, significantly light-
3 transmitting substrates.

1 264. The photovoltaic cell of claim 263, wherein the electrical conductor material
2 comprises indium tin oxide.

1 265. The photovoltaic cell of claim 251, wherein at least one of the first and second
2 flexible, significantly light-transmitting substrates comprises a polyethylene naphthalate
3 material.

1 266. A photovoltaic cell comprising a charge carrier material and a photosensitized
2 interconnected nanoparticle material including nanoparticles linked by a polymeric
3 linking agent, both disposed between a rigid, significantly light-transmitting substrate and
4 a flexible, significantly light-transmitting substrate.

1 267. The photovoltaic cell of claim 266, wherein the photosensitized interconnected
2 nanoparticle material comprises particles with an average size substantially in the range of
3 about 5 nm to about 80 nm.

1 268. The photovoltaic cell of claim 266, wherein the photosensitized interconnected
2 nanoparticle material is selected from the group consisting of titanium oxides, zirconium
3 oxides, zinc oxides, tungsten oxides, niobium oxides, lanthanum oxides, tin oxides,
4 tantalum oxides, terbium oxides, and combinations thereof.

1 269. The photovoltaic cell of claim 266, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises a molecule
3 selected from the group consisting of xanthenes, cyanines, merocyanines, phthalocyanines,
4 and pyrroles.

1 270. The photovoltaic cell of claim 266, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises a metal ion
3 selected from the group consisting of divalent and trivalent metals.

1 271. The photovoltaic cell of claim 266, wherein the photosensitized interconnected
2 nanoparticle material comprises a photosensitizing agent that comprises at least one of a
3 ruthenium transition metal complex, an osmium transition metal complex, and an iron
4 transition metal complex.

1 272. The photovoltaic cell of claim 266, wherein the charge carrier material
2 comprises a redox electrolyte system.

1 273. The photovoltaic cell of claim 266, wherein the charge carrier material
2 comprises a polymeric electrolyte.

1 274. The photovoltaic cell of claim 266, wherein the flexible, significantly light-
2 transmitting substrate comprises a polyethylene terephthalate material.

1 275. The photovoltaic cell of claim 266, wherein the rigid, significantly light-
2 transmitting substrate comprises tempered glass.

1 276. The photovoltaic cell of claim 266, wherein the flexible, significantly light-
2 transmitting substrate comprises a polyethylene naphthalate material.

1 277. A method of interconnecting nanoparticles at low temperatures on a rigid
2 substrate, the method comprising the steps of:
3 providing a rigid substrate;
4 applying a solution comprising a polymeric linking agent and a solvent to the rigid
5 substrate; and
6 contacting a plurality of metal oxide nanoparticles with the solution at a
7 temperature below about 300°C to interconnect at least a portion of the plurality of
8 metal oxide nanoparticles.

1 278. The method of claim 277, wherein the temperature is below about 200 °C.

1 279. The method of claim 277, wherein the temperature is below about 100°C

1 280. The method of claim 277, wherein the temperature is about room temperature.

1 281. The method of claim 277, wherein the polymeric linking agent comprises a
2 long chain macromolecule.

1 282. The method of claim 281, wherein the long chain macromolecule comprises:
2 a backbone structure substantially similar to a chemical structure of the plurality of
3 metal oxide nanoparticles; and
4 one or more reactive groups chemically bonded to the backbone structure.

1 283. The method of claim 277, wherein the plurality of metal oxide nanoparticles
2 comprise a chemical structure, M_xO_y , wherein x and y are integers.

1 284. The method of claim 283, wherein M comprises one of the group comprising
2 Ti, Zr, Sn, W, Nb, Ta, and Tb.

1 285. The method of claim 277, wherein the polymeric linking agent comprises
2 poly(n-butyl titanate).

1 286. The method of claim 277, wherein the solvent of the solution comprises n-
2 butanol.

1 287. The method of claim 277, wherein the rigid substrate is significantly light-
2 transmitting.

1 288. The method of claim 277, wherein the rigid substrate comprises tempered
2 glass.

1 289. The method of claim 277, wherein the plurality of metal oxide nanoparticles is
2 selected from the group consisting of titanium oxides, zirconium oxides, zinc oxides,
3 tungsten oxides, niobium oxides, lanthanum oxides, tin oxides, tantalum oxides, terbium
4 oxides, and combinations thereof.

1 290. A method of manufacturing photovoltaic modules, the method comprising the
2 steps of:
3 advancing a plurality of photovoltaic cells; and
4 ultrasonically dividing a subset of the plurality of photovoltaic cells into one or
5 more photovoltaic modules.

1 291. The method of claim 290, wherein dividing step includes substantially and
2 concurrently cutting and sealing the subset of photovoltaic cells into one or more
3 photovoltaic modules.

1 292. The method of claim 290, wherein the plurality of photovoltaic cells comprises a
2 substantially continuous flexible sheet of photovoltaic cells.

1 293. The method of claim 290, wherein advancing step is performed as part of a
2 continuous manufacturing process.

1 294. The method of claim 293, wherein the continuous manufacturing process
2 comprises a roll-based process.

1 295. The method of claim 290, wherein the plurality of photovoltaic cells is flexible.

1 296. The method of claim 291, wherein cutting and sealing forms a leading edge on a
2 proximal portion of the one or more photovoltaic modules.

1 297. The method of claim 291, wherein cutting and sealing forms a trailing edge on a
2 distal portion of the one or more photovoltaic modules.




Figure 1




Figure 2




Figure 3A




Figure 3B




Figure 4




Figure 5A




Figure 5B




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10





Figure 11

1100 ↗



1200

Figure 12




Figure 13A




Figure 13B




Figure 13C




Figure 14A




Figure 14B




Figure 15




Figure 16




Figure 17




Figure 18A




Figure 18B




Figure 19




Figure 20A




Figure 20B




Figure 21




Figure 22A




Figure 22B




Figure 23




Figure 24




Figure 25






Figure 26



A



B

1630