

**(12) PATENT**  
**(19) AUSTRALIAN PATENT OFFICE**

**(11) Application No. AU 200017783 B2**  
**(10) Patent No. 767803**

(54) Title  
Derivatized polycarboxylate dispersants

(51) 6 International Patent Classification(s)  
C08F 008/32 C04B 024/32  
C04B 024/26 C04B 028/04

(21) Application No: 200017783 (22) Application Date: 1999.11.29

(87) WIPO No: W000/35965

(30) Priority Data

(31) Number (32) Date (33) Country  
09/212652 1998.12.16 US

(43) Publication Date : 2000.07.03

(43) Publication Journal Date : 2000.08.31

(44) Accepted Journal Date : 2003.11.27

(71) Applicant(s)  
MBT Holding AG

(72) Inventor(s)  
Lynn E. Brower; Jeffery R. Bury; Runhai Lu; John  
Moreau; Jesse Osborne; Rainer Packe-Wirth; John  
Pickett; Samy M. Shendy; Thomas M. Vickers

(74) Agent/Attorney  
Cullen and Co, GPO Box 1074, BRISBANE QLD 4001

(56) Related Art  
WO 98/51640  
WO 97/47566  
EP 306449

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

17783/00



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>7</sup> :		(11) International Publication Number:	WO 00/35965
C08F 8/32, C04B 24/26, 24/32, 28/04		A1	(43) International Publication Date: 22 June 2000 (22.06.00)
(21) International Application Number:		PCT/EP99/09276	
(22) International Filing Date:		29 November 1999 (29.11.99)	
(30) Priority Data:		09/212,652 16 December 1998 (16.12.98) US	
(71) Applicant:		MBT HOLDING AG [CH/CH]; Vulkanstrasse 110, CH-8048 Zürich (CH).	
(72) Inventors:		BROWER, Lynn, E.; 6390 Creekside Trail, Solon, OH 44139 (US). BURY, Jeffery, R.; 873 Iroquois Trail, Macedonia, OH 44056 (US). LIU, Runhai; 5329 Camden Drive, Stow, OH 44224 (US). MOREAU, John; 325 Huntsford Drive, Macedonia, OH 44056 (US). OSBORNE, Jesse; 4711 East 94th Street, Garfield Heights, OH 44125 (US). PACKE-WIRTH, Rainer; 3000 Edgehill Road, Cleveland Heights, OH 44118 (US). PICKETT, John; 7456 Oakhill Road, Bedford, OH 44146 (US). SHENDY, Samy, M.; 3285 Bailey Road, Cuyahoga Falls, OH 44221 (US). VICKERS, Thomas, M.; 10140 Weathersfield Drive, Concord Township, OH 44060 (US).	
(74) Agent:		McSTEA, John, Anthony; MBT (Schweiz) AG, Patents and Trade Marks, Vulkanstrasse 110, CH-8048 Zürich (CH).	
(54) Title: DERIVATIZED POLYCARBOXYLATE DISPERSANTS			
(57) Abstract			
<p>The present invention is directed to derivatized polycarboxylate dispersants for cementitious mixtures, including those mixtures with high percentages of pozzolan cement replacement and dry cast applications. In particular, the invention is directed to a cementitious mixture comprising cement, including cements with high percentages of pozzolan cement replacement, water, coarse aggregate, fine aggregate, and including a dispersant, wherein said dispersant is a derivatized polycarboxylate dispersant, or combination of polycarboxylate dispersants, which is a derivatized polymer comprising a backbone having moieties derived from (a) an unsaturated hydrocarbon; (b) at least one of a substituted carboxylic acid monomer, a substituted ethylenically unsaturated monomer, and maleic anhydride; and (c) optionally including an N-polyoxyalkylene succinimide; and wherein derivative moieties are pendant to the backbone monomer by at least one ester linkage and at least one amide linkage. The derivatized polycarboxylate dispersant provides for a longer shelf life dispersant, improved dispersability of cementitious mixtures, water reduction in cementitious mixtures, and is an effective dispersant in high pozzolan replaced cementitious mixtures.</p>			

**DERIVATIZED POLYCARBOXYLATE DISPERSANTS****FIELD OF THE INVENTION**

5 The present invention is directed to dispersants for cementitious compositions. More particularly, the present invention is directed to a derivatized polycarboxylate dispersant for dispersing cementitious mixtures with improved solution performance stability.

**10 BACKGROUND OF THE INVENTION**

Dispersants have been used in the construction industry to disperse cementitious mixtures. Dispersants such as sulfonated melamine formaldehyde condensate (SMF) and sulfonated naphthalene formaldehyde condensate (BNS) are commonly used as 15 dispersants. However, an undesirably large amount of these compounds is required to achieve a desired level of concrete workability or water reduction. In addition, these materials do not achieve full range (Type A to Type F) water-reducing capability, as defined in ASTM C494.

20 It is important that dispersants be used in concrete situations where strength and durability are involved. Dispersants are a necessary component in high strength and high durability concretes. Due to the use of low water amounts in high performance concretes, high dispersant amounts are sometimes necessary to achieve workable 25 concretes. High BNS levels can lead to undesirable retardation of set and may not provide the required workability retention over time.

It is desirable to provide a material that is several times more efficient as a cement or concrete dispersant than the traditional materials such as BNS and SMF. Improving efficiency reduces the amount of material required to achieve a desired level 30 of concrete workability or water reduction. With respect to the presently-used dispersants, BNS and SMF, it is also desirable to improve slump retention while maintaining normal setting characteristics. Provision of a dispersant with full-range (Type A to F) water-reducing capability is also desirable.

By "cementitious mixture" is meant pastes, mortars, and concrete compositions comprising a hydraulic cement binder. Cementitious mixtures may also include high percentages of pozzolan cement replacement. Pastes are defined as mixtures composed of a hydraulic cement binder, either alone or in combination with 5 pozzolans such as fly ash, silica fume, or blast furnace slag, and water. Mortars are defined as pastes that additionally include fine aggregate. Concretes additionally include coarse aggregate. These compositions may additionally include other admixtures such as set retarders, set accelerators, defoaming agents, air-entraining or air-detaining agents, corrosion inhibitors, water-reducing agents, pigments, and any 10 other admixture that does not adversely affect the advantageous results obtained by the admixtures of the present invention.

Certain prior art polymer dispersants have inadequate long term solution stability. As time progresses, these prior art polymers become less effective as a 15 dispersant.

Over the years, the use of pozzolanic materials as a partial replacement for portland cement in concrete has become an increasingly attractive alternative to portland cement alone. The desire to increase the use of fly ash, blast furnace slag, and 20 natural pozzolanic cement in concrete mixtures can be attributed to several factors. These include cement shortages, economic advantages of portland cement replacement, improvements in permeability of the concrete product, and lower heats of hydration.

The growth in the use of higher amounts of pozzolanic cement replacements, 25 such as fly ash, in concrete has been impaired by the potential incompatibility exhibited by these materials, especially when used at high percentages, in combination with water reducing admixtures. Water reducers are desirable for decreasing the amount of water required in the preparation of the cementitious mixtures, and to increase the strength of the resulting concrete. However, the incompatibility of the pozzolan replacement 30 materials with certain water-reducing admixtures can result in the significant retardation of the initial and final setting of the concrete containing both these materials.

Despite the cost and performance advantages of fly ash, slag and natural pozzolans as partial replacements of portland cement in concrete, there are practical

limitations to the amount at which they can be used in the cementitious mixture. Using these materials at higher levels, such as above about 10 to 15 weight percent based on the weight of the portland cement, can result in a retarded setting time of the concrete of up to several hours, and perhaps longer depending upon the ambient temperature. This 5 incompatibility puts a burden of increased costs and time on the end user which is unacceptable.

While it is known to use set time accelerators in concrete mixtures, these accelerator admixtures have been ineffective in solving the compatibility problem that 10 exists in high pozzolan replacement/portland cement mixtures, particularly when used with water-reducing admixtures, so that set time is not able to be decreased to an acceptable level. The use of accelerators with water reducers, such as naphthalene sulfonate formaldehyde condensates (BNS), lignin and substituted lignins, sulfonated melamine formaldehyde condensates (SMF) and the like, has been ineffective in 15 producing an acceptable high pozzolanic replacement-containing hydraulic cement-based cementitious mixture with normal setting characteristics and an acceptable resulting concrete.

U.S. Patent Nos. 4,373,956 and 4,473,405 disclose various admixture 20 compositions for incorporation into hydraulic cement mixes to accelerate the rate of hardening and setting. U.S. Patent No. 4,337,094 discloses combinations of additives which can be used to accelerate the setting time of portland type cements. These additives, when used in cementitious mixtures containing portland cement and high proportions of pozzolan cement replacements, as well as a water-reducer, cannot 25 compensate for the retardation of setting time induced in the mixtures by the cement replacement and water reducer, and thus do not acceptably accelerate the mixture to setting.

U.S. Patent No. 5,556,458 discloses a cementitious composition containing a 30 high percentage of fly ash and hydraulic cement, but in which a fly ash containing a particular calcium oxide content is required and a water-reducing admixture is not present. The composition is useful for quick-setting repair mortar-type products.

A cementitious dry cast mixture refers to pastes, mortars, and concrete compositions comprising a hydraulic cement binder having consistencies ranging from stiff to extremely dry as defined in ACI 211.3R, Table 2.3.1.

5       Cementitious dry cast mixtures are used to form many articles, for example, concrete pipe, roof tile, masonry units, paver units, extruded plank, and any other preformed cementitious articles, in a mould or from an extrusion die. Each of these applications has basic desired characteristics that are critical in terms of producing quality finished units.

10       In masonry block applications, production speed, sufficient green strength, and the ability to resist slumping, sagging or deforming when stripped from the mould are critical, since stripping occurs immediately after casting. The same is true for concrete pipe or roof tile with the additional desired property of improved surface 15 appearance with reduced surface imperfections and reduced roller and/or die wear on equipment producing extruded pieces.

20       It is desired to reduce the cycle time of the manufacture of each article. The reduction of cycle time reduces the cost of manufacture for each article and increases 25 the number of articles that can be produced in a given time. Cycle time is defined as the time to complete one full cycle from the beginning of a feed to the beginning of the next feed. The beginning of a feed is when the dry cast mixture is fed from a collection hopper into the process. It is also desired to improve the compaction and consolidation of the cementitious dry cast mixture without altering the consistency of the mixture.

30       Green strength refers to the stability of the article in retaining its shape once the article is removed from the mould or extruder. Green strength is dependent on the consistency of the cementitious dry cast mixture, the amount of fines in the cementitious dry cast mixture, and the mouldability of the cementitious dry cast mixture.

Currently, the water to cement (W/C) ratio used in present dry cast mixtures is from about 0.25 to about 0.40. It is desired to minimize the amount of water needed

in a cementitious dry cast mixture to achieve consolidation and no sag or deformation in an article produced from the cementitious dry cast mixture.

Another limiting factor in the improvement of dry cast mixtures is the type and amount of dispersant used. Conventional dispersant chemistries such as naphthalene sulfonates, melamine sulfonates, and lignosulfonates have a lower limit to their effective dosage, below which they are not effective. At levels above the effective dosage of these dispersants, the dry cast mixture becomes critically sensitive to very slight changes in water or moisture content. This makes the use of these dispersants impractical.

A further limitation in the present art is the compressive strength of articles produced from cementitious dry cast mixtures. Compressive strength is directly related to the density of the article.

15

What is required by the industry, however, is a cementitious mixture capable of forming concrete with a dispersant that is more effective than SMF or BNS at lower effective dosages and which provides Type A to Type F water-reducing effect. Also required by the industry is a cementitious mixture capable of forming concrete which contains a significant percentage of cement replacement material (to replace a portion of the hydraulic cement, such as portland cement) for performance and cost considerations, and water reducers to decrease water usage and increase compressive strength and durability, the components in such cementitious mixtures being compatible and which mixtures set in an industry-acceptable time period. Also required by the industry is a cementitious dry cast mixture containing a dispersant that has a low effective dosage, that is not critically sensitive to changes in water or moisture content, that functions in mixtures having a slump of less than about one (1) inch (2.54 cm), that permits mixture consolidation and compaction in response to vibration energy, that has increased green strength and compressive strength, and that provides for reduced cycle time in the manufacture of articles from dry cast mixtures.

16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30

## SUMMARY OF THE INVENTION

The present invention is directed to a derivatized polycarboxylate dispersant which is derivatized polymer comprising a backbone having moieties derived from (a) an unsaturated hydrocarbon; (b) at least one of a substituted carboxylic acid monomer, a substituted ethylenically unsaturated monomer, and maleic anhydride, wherein at least one substituent comprises a random copolymer of oxyethylene units and oxypropylene units of the general formula  $-(CH_2C(R_1)HO)_mR_2$  where  $m=10$  to  $500$  and wherein the amount of oxyethylene by weight in the random copolymer is from  $60\%$  to  $100\%$  and the amount of oxypropylene by weight in the random copolymer is from  $0\%$  to  $40\%$ ; and (c) 5 optionally including an N-polyoxyalkylene succinimide; and wherein derivative moieties are pendant to the backbone monomer by at least one ester linkage and at least one amide linkage.

10

The invention further provides a compatibilizing admixture for cementitious mixtures containing hydraulic portland cement and greater than  $10$  percent pozzolanic cement replacement by weight of the portland cement and cement replacement, additionally including a derivatized polycarboxylate dispersant as hereinabove described.

15

The invention further provides a cementitious dry cast mixture comprises cement, water, coarse aggregate, fine aggregate, and the derivatized polycarboxylate dispersant of the present invention.

20

The invention further provides a method of preparing a cementitious material comprising mixing a hydraulic cement with a pozzolanic cement replacement selected from fly ash, slag, natural pozzolans, and mixtures thereof, and a compatibilizing admixture as hereinabove described, optionally including mixing aggregate with the cement and cement replacement and including additionally mixing water in an amount sufficient to effect hydraulic setting of the cement, cement replacement and aggregate mixture.

25

30


The invention further provides a method for making a dry cast cementitious article comprising:

- a. providing a mixture of hydraulic cement, water, coarse aggregate, fine aggregate, and including the derivatized polycarboxylate dispersant of claim 1; and
- b. forming the article from the mixture.

5

## DETAILED DESCRIPTION OF THE INVENTION

The present invention is directed to derivatized polycarboxylate dispersants for cementitious mixtures. In particular, the invention is directed to a dispersant which is a derivatized polycarboxylate dispersant, or combination of polycarboxylate dispersants, 10 which is a derivatized polymer comprising a backbone having moieties derived from (a) an unsaturated hydrocarbon; (b) at least one of a substituted carboxylic acid monomer, a substituted ethylenically-unsaturated monomer, and maleic anhydride, wherein at least one substituent comprises a random copolymer of oxyethylene units and oxypropylene units of the general formula  $-(CH_2C(R_1)HO)_nR_4$  where  $n=10$  to 500 and wherein the 15 amount of oxyethylene by weight in the random copolymer is from 60% to 100% and the amount of oxypropylene by weight in the random copolymer is from 0% to 40%; and (c) optionally including an N-polyoxyalkylene succinimide; and wherein derivative moieties are pendant to the backbone monomer by at least one ester linkage and at least one amide linkage. Preferably, the derivatized polycarboxylate dispersant is a random copolymer of 20 the general structural units shown below:



wherein:

the "b" structure is one of a substituted carboxylic acid monomer, a substituted ethylenically unsaturated monomer, and maleic anhydride wherein an acid anhydride group  $-(CO-O-CO-)$  is formed in place of the groups Y and Z between the carbon atoms to which the groups Y and Z are bonded respectively, and the "b" structure must include at least one moiety with a pendant ester linkage and at least one moiety with a pendant amide linkage;

X = H, CH<sub>3</sub>, C<sub>2</sub> to C<sub>6</sub> alkyl, phenyl, or substituted phenyl such as p-methyl phenyl, p-ethyl phenyl, carboxylated phenyl, sulfonated phenyl and the like;  
 Y = H, -COOM, -COOH, or W;  
 W = a hydrophobic defoamer represented by the formula R<sub>5</sub>-(CH<sub>2</sub>CH<sub>2</sub>O)<sub>s</sub>-(CH<sub>2</sub>C(CH<sub>3</sub>)HO)<sub>t</sub>-(CH<sub>2</sub>CH<sub>2</sub>O)<sub>u</sub> where s, t, and u are integers from 0 to 200 with the proviso that t>(s+u) and wherein the total amount of hydrophobic defoamer is present in an amount less than 10% by weight of the derivatized polycarboxylate dispersant;  
 Z = -OR<sub>3</sub>, -COOR<sub>3</sub>, -CH<sub>2</sub>OR<sub>3</sub>, or -CONHR<sub>3</sub>;  
 R<sub>4</sub> = H, or CH<sub>3</sub>;  
 R<sub>2</sub>, R<sub>3</sub>, are each independently a random copolymer of oxyethylene units and oxypropylene units of the general formula -(CH<sub>2</sub>C(R<sub>1</sub>)HO)<sub>m</sub>R<sub>4</sub> where m=10 to 500 and wherein the amount of oxyethylene by weight in the random copolymer is from 60% to 100% and the amount of oxypropylene by weight in the random copolymer is from 0% to 40%;  
 R<sub>4</sub> = H, methyl, or C<sub>2</sub> to C<sub>8</sub> alkyl;  
 R<sub>5</sub> = C<sub>1</sub> to C<sub>18</sub> alkyl or C<sub>6</sub> to C<sub>18</sub> alkyl aryl;  
 M = alkali metal, alkaline earth metal, ammonia, amine, substituted amine such as monoethanolamine, diethanolamine, triethanolamine, morpholine, imidazole and the like;  
 a = 0.01-0.8, preferably 0.01-0.6, and most preferably 0.01-0.5;  
 b = 0.2-0.99, preferably 0.3-0.99, and most preferably 0.4-0.99;  
 c = 0-0.5, preferably 0-0.3, and most preferably 0-0.1; and  
 wherein a, b, c represent the mole fraction of each unit and the sum of a, b, and c, is 1.  
 25

Preferably, the "a" structure includes a styrene moiety and a sulfonated styrene.

30 The alkali metal in the dispersant of the present invention is preferably lithium, sodium, or potassium. The alkaline earth metal in the dispersant of the present invention is preferably magnesium or calcium.

Representative monomers for use in this invention for the "a" component include, but are not limited to, styrene, ethylene, propylene, or sulfonated styrene. Representative monomers for use in this invention for the "b" component include, but are not limited to, alkoxypolyoxyalkylene esters of acrylic acid, alkoxypolyoxyalkylene esters of methacrylic acid, methoxypolyoxyalkylene vinyl ether, methoxypolyoxyalkylene allyl ether, alkoxypolyoxyalkylene vinyl ether, or alkoxypolyoxyalkylene allyl ether.

Component "c" can be formed from a post reaction from the grafting of the side chains on to the polymer backbone such as a polyacrylate or maleic anhydride copolymer. The reaction to form component "c" is related to the temperature of the grafting reaction. If the temperature is high enough, the imide (succinimide) component "c" is formed. Component "c" is formed from a single monomer which is a component "b" with Y as COOH and Z as CONHR<sub>3</sub>. A condensation reaction occurs wherein water condenses and the ring closes to form component "c".

15

20



25



30

The derivatized polycarboxylate dispersant of the present invention preferably includes a hydrophobic substituent functioning as a defoamer. The hydrophobic defoamer is present in an amount of less than 10% by weight of the derivatized polycarboxylate dispersant, and is preferably present in an amount of less than 5%.

5 Besides being grafted or chemically linked on to the derivatized polycarboxylate dispersant by attaching via an ester linkage to a "b" group in the polymer structure above, the hydrophobic defoamer can be formulated into a mixture with the derivatized polycarboxylate dispersant. When grafted or chemically linked on to the dispersant, the defoamer is represented by the following formula (which is

10 represented by "W" in the above polymer structure):  $R_5-(CH_2CH_2O)_s-(CH_2C(CH_3)HO)_t-(CH_2CH_2O)_u$ , where s, t, and u are integers from 0 to 200 with the proviso that  $t > (s+u)$  and where  $R_5$  is a  $C_1$  to  $C_{18}$  alkyl or  $C_6$  to  $C_{18}$  alkyl aryl group. The total quantity of hydrophobic defoamer which is either grafted or chemically linked on to the derivatized polycarboxylate dispersant or which is formulated into a

15 mixture with the derivatized polycarboxylate dispersant is less than 10% by weight of the derivatized polycarboxylate dispersant.

The following defoamers are examples of hydrophobic defoamers which can be formulated into the polymer solution: polyoxyalkylene glycols, such as those sold under the trademark PLURONIC from BASF, acetylene glycols, and alkoxyated acetylene alcohols, such as those sold under the trademark SURFYNOL from Air Products, fatty acid alkoxylates, such as alkoxylated lauric or oleic acid, or alkoxylated fatty amines, such as an alkoxylated lauric or oleylamine formulated defoamers. These defoamers can be added alone or in combination.

25 It has been found that the incorporation of amide or imide linkages between the copolymer, such as styrene-maleic main chain polymer, and the alkoxy polyoxyalkylene side chain can improve the chemical and performance stability of graft polymer solutions. Incorporation of nitrogen-based linkages between main chain and side chain stabilizes side chain degrafting which slowly occurs with maleic mono-ester linkages during solution storage. Improved solution stability leads to better long-term performance behavior from aged polymer solutions. In applications where the polymer is used as a cement dispersant, the improvement produces better

dispersibility of cement from aged solutions and better maintenance of cement in a dispersed state.

It is not necessary that all linkages between the side chain and polymer backbone be through an amide or imide nitrogen. On the contrary, according to the present invention, it is preferred that the linkages be mixed between ester (or oxygen) and amide or imide. The combination of ester (or oxygen) and amide or imide linkages improves the long term performance, for example stability, of the polymer solution and lowers the cost relative to the all-amide or -imide pendant linkages.

10

The advantage of this invention is that it provides at least one of the following:

- a cement or concrete dispersant that has increased solution storage life.

15

- a cement or concrete dispersant material that is several times more efficient than the traditional dispersants such as BNS and SMF.


- a cement or concrete dispersant material with improved efficiency which reduces the amount of material required to achieve a desired level of concrete workability or water reduction.

- a cement or concrete dispersant material to improve concrete slump retention while maintaining normal setting characteristics.

25

- a cement or concrete dispersant material capable of providing a Type A to Type F water-reducing effect.

- a cementitious mixture which contains a significant proportion of pozzolan cement replacement materials for hydraulic cement, such as portland cement, as well as water-reducing materials, which have acceptable or improved compressive strength.



- a cementitious mixture which contains a significant proportion of pozzolan cement-replacement materials for hydraulic cement, such as portland cement, as well as water-reducing materials, which set in an industry-acceptable time period.

5

- a method for preparing a cementitious material which contains a significant proportion of pozzolan cement-replacement materials for hydraulic cement, such as portland cement, as well as water-reducing materials, which have acceptable or improved compressive strength and which set in an industry-acceptable time period.

10 - a compatibilizing admixture for cementitious mixtures which contain a significant proportion of pozzolan cement-replacement materials for hydraulic cement, such as portland cement, which admixtures provide water-reducing means for imparting acceptable or improved compressive strength, and set-accelerating means for inducing the mixture to set in an industry-acceptable time period.

15 - a cementitious dry cast mixture that consolidates and compacts in response to vibration energy.

20


- a reduction in the cycle time of manufacturing a cementitious dry cast mixture article to reduce the cost of manufacture of the article.



25 - a cementitious dry cast mixture article that has increased green strength and increased compressive strength.

- a cementitious dry cast mixture article that has increased density.

30 - a cementitious dry cast mixture that has improved surface appearance because the increased density and compaction reduces the air pockets and imperfections that form as a result of poor consolidation.



- sufficient dispersion of uncompacted silica fume or partially-

compacted silica fume in the cementitious dry cast mixture without altering the consistency of the mixture and without increasing the required water content of the mixture.

5    Examples

The molecular weights herein are number-average molecular weights.

Derivatized polycarboxylate dispersants of the present invention are prepared as a solution comprising neutralized polymer at about 40% solids by weight and neutral pH. The sample O-linked #1 contains methoxy polyoxyalkylene glycol with a MW of about 1100, Sample O-linked #2 contains methoxy polyoxyalkylene glycol with a MW of about 1100, and Sample N-linked contains methoxy polyoxyalkylene amine with a MW of about 1000. The solutions are tested as fresh and aged at room temperature for a given time. The solutions are added to a cement paste at a dose of 0.1% by weight of cement with a water/cement (W/C) ratio of 0.35. The resulting cement paste is tested for flow and spread.

TABLE I

20	Mix	Graft Polymer Dispersant	Fresh Dispersant Solution		Aged Dispersant Solution		Dispersant Solution Age
			Flow	Spread	Flow	Spread	
			(g/s)	(cm)	(g/s)	(cm)	
25	1	O-linked #1	49	12.5	22	8.6	22
	2	O-linked #2	80	18.5	32	4.3	17
	3	N-linked	58	13.2	52	11.2	19

A Gel Permeability Chromatography (GPC) analysis of the fresh and aged dispersant from Table 1 is performed. The results in Table 2 show the percent ungrafted side chains present in the dispersant solution. Fewer nitrogen-linked side chains de-grafted over the course of the test.

5

TABLE 2

Mix	Graft Polymer Dispersant	Fresh Solution ungrafted side chain (% of total solids)	Aged Solution ungrafted side chain (% of total solids)	Dispersant Solution Age
4	O-linked #1	21	42	22
5	O-linked #2	13	35	17
6	N-linked	7	15	19

A dispersibility comparison for dispersants with O-linked side chain, a methoxy polyoxyalkylene glycol with a MW of 1100, a first preparation of a mixed 10 O/N-linked side chain dispersant, a methoxy polyoxyalkylene glycol with a MW of 1100 and a methoxy polyoxyalkylene amine with a MW of 2000 and a molar ratio of O:N of about 2:1, and a second preparation of a mixed O/N-linked side chain dispersant, a methoxy polyoxyalkylene glycol with a MW of 1100 and a methoxy polyoxyalkylene amine with a MW of 2000 and a molar ratio of O:N of about 2:1, are 15 compared to reference dispersants and tested in a cement paste formulation comprising Medusa Type 1 cement. In all mixes, the dispersant is added at 0.1% by weight of cement, and the water/cement ratio is 0.35. The final flow and final spread are tested about 20 minutes after the initial values are tested. Mixes 7, 8, and 9 are 20 tested as freshly prepared, and Mixes 7a, 8a, and 9a are tested after being stored for six months. The results are listed in Table 3, and show similar performance when freshly prepared solutions are tested. After six months, the mixed linked dispersants shows improved flow and spread as compared to the O-linked dispersant.

15  
TABLE 3

Mix	Dispersant	Yield (mPa)	Viscosity (mPas)	Initial Flow (g/s)	Final Flow (g/s)	Initial Spread (cm)	Final Spread (cm)
7	O-linked	3015	802	84	68	15.6	15.4
8	Mixed linked #1	2384	614	101	80	17.1	16.6
9	Mixed linked #2	2468	864	72	60	15.1	15.1
7a	O-linked	4795	1160	59	23	11.8	10.2
8a	Mixed linked #1	3409	1118	72	31	12.6	11.1
9a	Mixed linked #2	3902	1067	75	41	13.3	12.4

A dispersibility comparison for dispersants with O-linked and mixed O/N-linked side chains are tested in a concrete formulation comprising the dispersant, 5 cement, coarse aggregate and fine aggregate. A plain concrete mixture is compared to a reference dispersant, a derivatized acrylic dispersant, an O-linked (methoxy polyoxyalkylene glycol), a N-linked (methoxy polyoxyalkylene amine), and a mixed O/N-linked (methoxy polyoxyalkylene glycol and methoxy polyoxyalkylene amine with a molar ratio of O:N of about 2:1). In the samples with the dispersant, the 10 dispersant is added at 0.256% by weight of cement. Solutions of the test dispersants are aged for 2 weeks prior to being prepared in the concrete mixture. Mixes 10, 11, 12, 13, and 14 are tested as freshly prepared, and Mixes 10a, 11a, 12a, 13a, and 14a 15 are tested after eight months of storage. The results of the comparison are listed in Table 4. The results show that after storage, the mixed O/N-dispersant shows improved performance over the O-linked dispersant.

16  
TABLE 4

Mix		Slump at 5/10/15 minutes (cm)	Air at 5/10/15 minutes (%)	Water Reduction (%)
10	plain	21.0/--/--	0.9/--/--	---
11	ref.	21.6/19.0/8.9	2.2/3.3/3.6	33
12	O-linked	16.5/4.5/3.8	3.0/2.4/2.4	30
13	mixed O/N	21.6/21.0/4.5	1.4/1.4/1.7	31
14	N-linked	19.7/7.6/3.8	1.5/1.9/2.5	33
10a	plain	20.3/--/--	1.2/--/--	----
11a	ref.	22.9/19.7/15.9	1.8/3.3/4.3	32
12a	O-linked	20.3/11.4/8.3	3.8/3.0/3.3	24
13a	mixed O/N	22.2/12.7/10.8	1.4/2.3/3.9	30
14a	N-linked	21/9.5/6.4	1.7/2.5/3.3	31

The polymers used in the derivatized polycarboxylate dispersant of the present invention can be made by methods known in the art, such as those referenced in U.S.

5 Patent Nos. 5,661,206; 5,393,343; 5,158,996; 5,047,087; 4,972,025; 4,968,734; 4,473,406; and 4,471,100 all of which are hereby incorporated by reference herein as if fully written out below.

Specific nonlimiting examples of synthesizing the derivatized polycarboxylate

10 dispersants of the present invention are described below.

Synthesis Example Number 1

Sixteen grams of styrene maleic anhydride copolymer (SMA), SMA-1000 from Atochem with a 2500 MW, is dissolved in 53.1g of tetrahydrofuran (THF).

15 Next, 39.6g of methoxy polyoxyalkylene amine, XTJ-506 from Huntsman Corporation with a 1000 MW, and 4.8g of triethyl amine are dissolved in 60.6g of THF. The amine solution is drip-fed into the stirred SMA solution over a period of about 30 minutes. The mixture is stirred for about 45 minutes at room temperature and then heated to about 45°C. The mixture is reacted for about 2 hours. The THF

solvent is removed from the mixture and the mixture is dried to a constant weight leaving polymer. The polymer is dissolved in an aqueous caustic solution and the resulting solution is adjusted to about 40% solids and a pH of about 7.0.

5 Synthesis Example Number 2

One hundred grams of styrene maleic anhydride copolymer (SMA), SMA-1000 from Atochem with a 2500 MW, is dissolved in 310g of tetrahydrofuran (THF). Next, 321g of methoxy polyoxyalkylene amine, XTJ-508 from Huntsman Corporation, is delivered to the stirred SMA solution over a period of about 45 to 10 about 60 minutes under nitrogen pressure. The mixture is heated to about 45°C and reacted for about 1 hour. The THF solvent is removed from the mixture and the mixture is dried to a constant weight leaving polymer. The polymer is dissolved in an aqueous caustic solution and the resulting solution is adjusted to about 40% solids and a pH of about 7.0.

15

Synthesis Example Number 3

One hundred twenty-eight grams of styrene-maleic anhydride copolymer (SMA), SMA-1000 from Atochem with a 2500 MW, is dissolved in 128g of methyl isobutyl ketone (MIBK) under nitrogen pressure and stirring at 100°C. An addition of 20 a mixture comprising 53g of methoxy polyoxyethylene glycol (mPEG-OH) with a 1100 MW and 1g of dimethylaminopyridine (DMAP) is added to the stirred SMA solution. This addition is followed by 50.25g of methoxy polyoxyalkylene amine, XTJ-508 from Huntsman Corporation with a 2000MW, to the SMA solution. Three more identical additions of mPEG-OH/DMAP followed by methoxy polyoxyalkylene 25 amine are added to the stirred SMA solution. The resulting mixture is reacted for about 4.5 hours. The MIBK solvent is removed from the mixture and the mixture is dried to a constant weight leaving polymer. The polymer is dissolved in an aqueous caustic solution and the resulting solution is adjusted to about 40% solids and a pH of about 7.0.

30

Synthesis Example Number 4

Six and four tenths grams of styrene-maleic anhydride copolymer (SMA), SMA-1000 from Atochem with a 2500 MW, is dissolved in 9.4g of methyl isobutyl ketone (MIBK) under nitrogen atmosphere and stirring at 100°C. Next, 15.9g of

18

methoxy polyethylene glycol (mPEG-OH) with a 1100 MW and 0.2g of dimethylaminopyridine (DMAP) are added to the stirred SMA solution. The resulting mixture is reacted for about 4.5 hours. The MIBK solvent is removed from the mixture and the mixture is dried to a constant weight leaving polymer. The polymer 5 is dissolved in an aqueous caustic solution and the resulting solution is adjusted to about 40% solids and a pH of about 7.0.

The inventive derivatized polycarboxylate dispersant is capable of providing a Type A to Type F water-reducing effect, as defined in ASTM C494, Standard 10 Specification for Chemical Admixtures for Concrete.

The derivatized polycarboxylate dispersants of the invention are added to mixtures of cementitious materials in amounts from about 0.01 to about 3%, preferably about 0.05 to about 1% by weight based on the weight of the cement. For 15 example, the dispersant is preferably added prior to, during, or after initial mixing, to a cementitious composition mixture of a hydraulic cement, water, and aggregate, in which a reduced amount of water can be used compared to mixtures not containing the dispersant. The proportion of cement, water, and aggregate (if any) used in the cementitious composition mixture depends upon the end use desired, and is within the 20 knowledge of the skilled artisan for a selected use.

In one aspect of the present invention, the derivatized polycarboxylate dispersant maybe formulated into a compatibilizing admixture for cementitious mixtures containing hydraulic portland cement and greater than 10 percent 25 pozzolanic cement replacement by weight of the portland cement and cement replacement.

In one embodiment, the present invention is an additive formulation, or an admixture, for incorporation in hydraulic cement mixtures, such as concretes, mortars and grouts, containing portland cement and pozzolanic cement replacement. By 30 "portland cement" is meant all cementitious compositions which have a high content of tricalcium silicate, and thus are portland cement or are chemically similar or analogous to portland type cement, the specification for which is set forth in ASTM specification C-150-80.

Pozzolanic replacement materials for hydraulic, or portland-type, cement which can be used in high proportion according to the present invention include silica fume, fly ash, both Class C and Class F, blast furnace slag, and natural pozzolan materials.

5 These replacement materials can be used in a proportion, based on the weight of the hydraulic cement and the cement replacement, of greater than 10 weight percent, preferably greater than 15 weight percent, and most preferably greater than 20 weight percent. It is most preferred, however, that the cementitious mix contain at least 50 weight percent portland cement, based upon the total weight of portland cement and pozzolanic replacement material, combined.

10

As discussed above, the addition of high proportions of the pozzolanic material to the cementitious mixture in combination with a conventional water-reducing admixture (which water reducer increases compressive strength), results in a significant retarding of the setting time for the cementitious mixture.

15

The present invention provides a novel compatibilizing admixture for the high pozzolanic replacement material containing hydraulic cement, as well as a novel cementitious mixture containing the pozzolanic replacement and the compatibilizing admixture, and a method for preparing the cementitious material. The present invention 20 significantly reduces, and in many instances eliminates, the retardation of concrete containing high proportions of pozzolanic replacement materials for the hydraulic, or portland type, cement.

This embodiment of the present invention includes a cementitious mixture 25 comprising a hydraulic cement; greater than 10% by weight of a pozzolanic cement replacement selected from fly ash, slag, natural pozzolans, and mixtures thereof based on the total of said hydraulic cement and cement replacement; and a compatibilizing admixture, wherein the compatibilizing admixture comprises the derivatized polycarboxylate dispersant, described above, in combination with an accelerator for 30 concrete.

While the use of the derivatized polycarboxylate polymer dispersants with conventional accelerators, including calcium chloride, bromide or other halide, is effective to overcome the set time-retarding effects of the high pozzolan content

cementitious mixture, the present invention is particularly effective in avoiding the use of chloride, bromide or other halide-containing accelerators, and thus avoids corrosion problems often associated with them.

5 Preferably, the accelerator according to the present invention comprises at least one of

- a) a nitrate salt of an alkali metal, alkaline earth metal, or aluminum;
- b) a nitrite salt of an alkali metal, alkaline earth metal, or aluminum;
- c) a thiocyanate of an alkali metal, alkaline earth metal, or aluminum;
- 10 d) an alkanolamine;
- e) a thiosulfate of an alkali metal, alkaline earth metal, or aluminum;
- f) a hydroxide of an alkali metal, alkaline earth metal, or aluminum;
- g) a carboxylic acid salt of an alkali metal, alkaline earth metal, or aluminum; or,
- 15 h) a polyhydroxylalkylamine.

The salts of nitric acid have the general formula  $M(NO_3)_a$  where M is an alkali metal, or an alkaline earth metal or aluminum, and where a is 1 for alkali metal salts, 2 for alkaline earth salts, and 3 for aluminum salts. Preferred are nitric acid salts of Na, K, Mg, Ca and Al.

Nitrite salts have the general formula  $M(NO_2)_a$  where M is an alkali metal, or an alkaline earth metal or aluminum, and where a is 1 for alkali metal salts, 2 for alkaline earth salts, and 3 for aluminum salts. Preferred are nitric acid salts of Na, K, Mg, Ca and Al.

The salts of the thiocyanic acid have the general formula  $M(SCN)_b$ , where M is an alkali metal, or an alkaline earth metal or aluminum, and where b is 1 for alkali metal salts, 2 for alkaline earth salts and 3 for aluminum salts. These salts are variously known as sulfocyanates, sulfocyanides, rhodanates or rhodanide salts. Preferred are thiocyanic acid salts of Na, K, Mg, Ca and Al.

Alkanolamine is a generic term for a group of compounds in which trivalent nitrogen is attached directly to a carbon atom of an alkyl alcohol. A representative


21

formula is  $N[H]_c[(CH_2)_dCH_2OH]_e$ , where c is 3-e, d is 1 to about 5 and e is 1 to about 3. Examples include, but are not limited to, are monoethanolamine, diethanolamine and triethanolamine.

5 The thiosulfate salts have the general formula  $M_f(S_2O_3)_g$  where M is alkali metal or an alkaline earth metal or aluminum, and f is 1 or 2 and g is 1, 2 or 3, depending on the valencies of the M metal elements. Preferred are thiosulfate acid salts of Na, K, Mg, Ca and Al.

10 The carboxylic acid salts have the general formula  $RCOOM$  wherein R is H or  $C_1$  to about  $C_{10}$  alkyl, and M is alkali metal or an alkaline earth metal or aluminum. Preferred are carboxylic acid salts of Na, K, Mg, Ca and Al. A preferred carboxylic acid salt is calcium formate.

15 A preferred polyhydroxylalkylamine has the general formula



wherein h is 1 to 3, i is 1 to 3, j is 1 to 3, and k is 0 to 3. Preferred is tetrahydroxyethylethylenediamine.

20 A conventional chloride-containing accelerator may be used in combination with the polycarboxylate dispersant to form a compatibilizing admixture according to the present invention, for product applications in which corrosion of reinforcing steel is not an issue, for example, in concrete block production.

25 The cementitious mixture additionally may contain water in an amount sufficient to effect hydraulic setting of the cement and aggregate mixture, and if desired, an additional material such as silica fume or metakaolin. The term "aggregate" includes both fine aggregate such as sand and coarse aggregate such as gravel as is common in the art. The proportion of fine and coarse aggregate will vary depending on the desired

properties of the mortar or concrete. The amount of water generally should be enough to effect hydraulic setting of the cement component and to provide a desired degree of workability to the mix before hardening.

5 In the practice of the present invention, the compatibilizing admixture components described above are incorporated into hydraulic cement mixes in amounts sufficient to compatibilize the pozzolanic replacement material and the hydraulic cement, to accelerate the rate of hardening and setting of the mixes and to reduce water to increase compressive strength after hardening, thereby enhancing overall durability  
10 of the product. The admixture is preferably incorporated into the mix as an aqueous solution comprising a portion of the water used in mixing the hydraulic cement, pozzolanic replacement material, aggregate, and any additional additives. Representative admixture formulations are set forth in Table 5A, below. (Percentages are by weight.)

15

Table 5A

Component	Percentage	Preferred Percentage
Nitrate salt	0 - 60	20 - 40
Nitrite salt	0 - 60	20 - 40
20 Thiocyanate	0 - 10	1 - 4
Alkanolamine	0 - 10	0 - 1
Polyhydroxylalkylamine	0 - 5	0 - 4
Dispersant	1 - 20	3 - 8
Thiosulfate	0 - 10	
25 Carboxylic acid salt	0 - 20	
Hydroxide	0 - 10	

The remainder of the admixture solution comprises water. By way of example, but not of limitation, the amount of active admixture material delivered per 100 pounds of  
30 cementitious material (cement + cement replacement) in aqueous solution is preferably calculated as follows in Table 5B.

23  
Table 5B

Admixture Solution		Active Components	
	(Fl. oz.)	(ml/100 kg)	(% by wt. cementitious material)
5	2.5	160	0.09
	5	320	0.18
	10	650	0.36
	20	1300	0.72
	30	1960	1.08
10	40	2600	1.44
	50	3260	1.80

Additionally, the derivatized polycarboxylate dispersant of the present invention is directed to cementitious dry cast mixtures for forming cementitious articles. The cementitious dry cast mixture comprises cement, water, coarse aggregate, fine aggregate, and the derivatized polycarboxylate dispersant of the present invention.

While polycarboxylate dispersants in general are known in the industry to be highly effective and efficient at producing highly flowable concrete, the derivatized polycarboxylate dispersants of the present invention may be advantageously used at low to extremely low levels, 0.005 to 0.120% by weight of cement, to improve the paste phase response to vibration or other energy applied to the cementitious dry cast mixture during consolidation. Consolidation and compaction of the dry cast mixture results in increased compressive strengths, higher density, lower water absorption or permeability, and better surface appearance of the finished unit (reduced imperfections and holes). Additionally, the reduced levels of dispersants result in a reduced cost for materials for the cementitious dry cast mixture.

Cementitious dry cast mixtures of the present invention generally comprise hydraulic cement, the dispersant, fine aggregate, coarse aggregate, and optionally silica fume, pozzolans such as fly ash, and pigments. Water is added to form the cementitious mixture into a paste.

The hydraulic cement can be a portland cement, high alumina cement, or any other suitable hydraulic binder. The coarse aggregate can be silica, quartz, crushed round marble, glass spheres, granite, limestone, calcite, feldspar, alluvial sands, any other durable aggregate, and mixtures thereof. The fine aggregate can be sand, any other suitable aggregate, and mixtures thereof.

5       Cementitious dry cast mixtures have been found to respond to vibration or applied energy when the mixture is properly proportioned. The derivatized polycarboxylate dispersants improve the mobility of the paste when under stress from 10 vibration or energy. When the mould is subjected to vibration or other energy, the paste fraction of the mixture functions as the vehicle/lubricant by which the solid aggregate particles move and orient themselves during consolidation.

15       The derivatized polycarboxylate dispersants of the present invention permit reduced water content, minimize the effect of the variation in size of the aggregate particles, and allow the incorporation of additional fines such as fumed silica in the mixture. All of these factors in turn improve the green strength of the articles formed from cementitious dry cast mixtures.

20       The reduced water content provides cementitious dry cast mixtures with stiff to extremely dry consistencies, with typical W/C ratios at or below 0.36, preferably at or below 0.30. Without being limited by theory, it is theorized that the reduced water content allows the cementitious dry cast mixture to set faster which increases the green strength of an article formed from the cementitious dry cast mixture. This is 25 also thought to result in reduced slump, sagging and deformation when the article is removed from a mould or is extruded from a die. Additionally, the cementitious dry cast mixtures of the present invention have the appearance of dry to almost dry.

30       The derivatized polycarboxylate dispersants of the present invention minimize the effect of the variation in size of the aggregate particles by improving the lubricity of the thin paste layer covering the aggregate, allowing improved movement during consolidation. This effect is typically obtained by increasing the cement content, the water content, or both. Minimizing water content and maximizing cement efficiency

in turn increases the green strength of an article formed from the cementitious dry cast mixture.

Addition of silica fume increases the cohesiveness of the cementitious dry cast

5 mixture which then increases the green strength of an article formed from the cementitious dry cast mixture. Silica fume used in the present invention can be uncompacted or can be partially compacted. Silica fume additionally reacts with the hydration byproducts of the cement binder which provides for increased strength of the finished articles and decreases the permeability of the finished articles. The silica  
10 fume, or other pozzolans such as fly ash, can be added to the cementitious dry cast mixture in an amount from 5% to 30% based on the weight of cement.

By allowing for a reduced W/C ratio, improved paste lubricity and increased green strength, the cycle time of producing an individual article from a cementitious

15 dry cast mixture is reduced. Compared to dry cast mixtures of the prior art, cycle time reductions are improved by 50 to 100%. By allowing articles to be removed from the moulds in a shorter period of time or by increasing the rate of extrusion, the cycle time for producing each article is reduced. Additionally, more articles can now be produced in the same equipment. These factors combine to reduce the cost of  
20 manufacture of each article, such as masonry blocks.

Additionally, the additive dosage of the derivatized polycarboxylate dispersant of the present invention can be slightly increased (but still in the range of 0.005 to 0.120% by cement weight) in combination with a reduction of the W/C ratio to

25 provide further improvements without changing the dry consistency of the mixture. As the dispersant level is increased, the W/C ratio can be decreased. The W/C ratio and dispersant level can be varied to optimize the production of each type of dry cast article from a cementitious dry cast mixture.

30 For masonry block, the compacted density and compressive strength of dry cast concrete mixtures have been shown to be increased over a plain reference at the same W/C ratio by using a derivatized polycarboxylate additive at 0.01 to 0.03% by weight of cement. The compaction speed, consolidation and resulting compressive strength of masonry block has been shown to be improved by using a derivatized

26

polycarboxylate additive, most preferably at 0.03% by weight of cement. The compressive strength of a dry cast mixture of the present invention is increased by up to 30%. The basic desired characteristics of the dry cast mixture for masonry block, which are sharp corners, sharp edges, no web cracking, controlled swipe, no sagging or deformation, are not negatively affected by these improvements.

For pipe and roof tile, the increased density and compaction of the cementitious dry cast mixture additionally results in reduced imperfections in an article produced from the cementitious dry cast mixture. Typically, a cementitious dry cast mixture has air pockets that are retained in the mixture after the mixture has set. On the surface of an article, these holes are called bugholes and they detract from the aesthetic value of the article. Other imperfections referred to as honeycombs, which are zones of poorly compacted mixture, decrease the compressive strength of the article and increase the permeability of the article. The increased density and compaction, according to the invention, reduce or eliminate these problems. Additionally, other surface defects are eliminated by the vibratory consolidation of the cementitious dry cast mixtures of the present invention.

The derivatized polycarboxylate additive can be combined with other chemical or mineral additives typically used in the various applications such as set accelerators, set retarders, defoaming agents, air-entraining or air-detaining agents, water-repellant agents, water-reducing agents, and any other conventional additives for cementitious mixtures. The basic properties of a cementitious dry cast mixture are not negatively affected by the use of the derivatized polycarboxylate dispersants of the present invention.

The inventive derivatized polycarboxylate dispersant may be added to many different types of cementitious mixtures, and is not limited to the mixtures described above. Cementitious mixes in which the inventive derivatized polycarboxylate dispersant can be used as additives are paste slurries, mortars and concretes. The hydraulic binder used in the cementitious composition may be portland cement, alumina cement, or blended cement, for example pozzolanic cement, slag cement, or other types, portland cement being the preferred. Conventional admixtures in cement

technology, such as set accelerators or retarders, frost protection agents, pigments, and the like, may also be present in the cementitious mixes of the invention.

As demonstrated above, the present invention achieves the objects of the 5 invention. The present invention therefore provides a dispersant with increased storage life.

Also, the present invention provides a hydraulic cement or concrete dispersant material that is several times more efficient than the traditional dispersants such as BNS 10 and SMF. The present invention further provides a cement or concrete dispersant material with improved efficiency which reduces the amount of material required to achieve a desired level of concrete workability or water reduction.

In addition, the present invention provides a cement or concrete dispersant 15 material to improve concrete slump retention while maintaining normal setting characteristics. The present invention further provides a cement or concrete dispersant material capable of providing a Type A to Type F water-reducing effect.

Additionally, a cementitious mixture is provided which contains a significant 20 proportion of pozzolan cement replacement materials for hydraulic cement, such as portland cement, as well as water-reducing materials, which have acceptable or improved compressive strength, and which set in an industry-acceptable time period. A method is provided for preparing a cementitious material which contains a significant proportion of pozzolan cement replacement materials for hydraulic cement, such as 25 portland cement, as well as water-reducing materials, which have acceptable or improved compressive strength and which set in an industry-acceptable time period. The objects are achieved through the inventive compatibilizing admixture for cementitious mixtures which contain a significant proportion of pozzolan cement replacement.

30

Also, the compatibilizing admixture acts as a mid-range water reducer (permitting a reduction of mix water of from about 5% to about 15%. Compressive strength and durability of the resulting product are improved. Significant replacement of hydraulic cement by pozzolanic materials is achieved, with setting times for the


cementitious mixture containing the replacement, such as both Class C and Class F fly ash, equivalent to or less than set times for conventional mixtures without the replacement materials. Set times of the inventive cementitious mixtures are significantly accelerated over untreated concrete containing high amounts of fly ash,  
5 blast furnace slag or pozzolanic cement.

Additionally, the present invention provides a derivatized polycarboxylate dispersant for a cementitious dry cast mixtures to allow for reduced water usage, consolidation and compaction of the dry cast mixture, providing for increased  
10 compressive strength and reduced cycle time of dry cast formation.

It should be appreciated that the present invention is not limited to the specific embodiments described above, but includes variations, modifications and equivalent embodiments defined by the following claims.

1. A derivatized polycarboxylate dispersant which is a derivatized polymer comprising a backbone having moieties derived from (a) an unsaturated hydrocarbon; (b) at least one of a substituted carboxylic acid monomer, a substituted ethylenically unsaturated monomer, and maleic anhydride, wherein at least one substituent comprises a random copolymer of oxyethylene units and oxypropylene units of the general formula  $-(CH_2C(R_1)HO)_mR_4$  where  $m=10$  to  $500$  and wherein the amount of oxyethylene by weight in the random copolymer is from  $60\%$  to  $100\%$  and the amount of oxypropylene by weight in the random copolymer is from  $0\%$  to  $40\%$ ; and (c) optionally including an N-polyoxalkylene succinimide; and wherein derivative moieties are pendant to the backbone monomer by at least one ester linkage and at least one amide linkage.

5 10 15 2. The derivatized polycarboxylate dispersant of claim 1, wherein the derivatized polymer is a random copolymer of general structural units shown below:



20 wherein:

20 the "b" structure is one of a substituted carboxylic acid monomer, a substituted ethylenically unsaturated monomer, and maleic anhydride wherein an acid anhydride group (-CO-O-CO-) is formed in place of the groups Y and Z between the carbon atoms to which the groups Y and Z are bonded respectively, and the "b" structure must include at least one moiety with a pendant ester linkage and at least one moiety with a pendant amide linkage;

25 X = H, CH<sub>3</sub>, C<sub>2</sub> to C<sub>6</sub> alkyl, phenyl, or substituted phenyl;  
Y = H, -COOM, -COOH, or W;

## 30

W = a hydrophobic defoamer represented by the formula  $R_5-(CH_2CH_2O)_s-(CH_2C(CH_3)HO)_t-(CH_2CH_2O)_u$ , where s, t, and u are integers from 0 to 200 with the proviso that  $t > (s+u)$  and wherein the total amount of hydrophobic defoamer is present in an amount less than 10% by weight of the derivatized polycarboxylate dispersant;

5 Z = -OR<sub>3</sub>, -COOR<sub>3</sub>, -CH<sub>2</sub>OR<sub>3</sub>, or -CONHR<sub>3</sub>;

R<sub>1</sub> = H, or CH<sub>3</sub>;

10 R<sub>2</sub>, R<sub>3</sub>, are each independently a random copolymer of oxyethylene units and oxypropylene units of the general formula -(CH<sub>2</sub>C(R<sub>1</sub>)HO)<sub>m</sub>R<sub>4</sub> where m=10 to 500 and wherein the amount of oxyethylene by weight in the random copolymer is from 60% to 100% and the amount of oxypropylene by weight in the random copolymer is from 0% to 40%;

R<sub>4</sub> = H, methyl, or C<sub>2</sub> to C<sub>8</sub> alkyl;

R<sub>5</sub> = C<sub>1</sub> to C<sub>18</sub> alkyl or C<sub>6</sub> to C<sub>18</sub> alkyl aryl;

15 M = alkali metal, alkaline earth metal, ammonia, amine, or substituted amine;

a = 0.01-0.8;

b = 0.2-0.99;

c = 0-0.5; and

20 wherein a, b, c represent the mole fraction of each unit and the sum of a, b, and c, is 1.

3. The derivatized polycarboxylate dispersant of claim 2, wherein the "a" structure includes at least one of a styrene moiety and a sulfonated styrene.
4. A cementitious mixture comprising hydraulic cement, water, and the derivatized polycarboxylate dispersant of claim 1.
- 25 5. A compatibilizing admixture for cementitious mixtures containing hydraulic portland cement and greater than 10 percent pozzolanic cement replacement by weight of the portland cement and cement replacement, comprising the derivatized polycarboxylate dispersant of claim 1, in combination with an accelerator for concrete.
- 30 6. A cementitious mixture comprising hydraulic cement; greater than 10% by weight of a pozzolanic cement replacement selected from fly ash, slag, natural

AMENDED SHEET

31

pozzolans, and mixtures thereof based on the weight of said hydraulic cement and cement replacement; and a compatibilizing admixture as in claim 5, optionally including at least one of aggregate, silica fume, and metakaolin.

7. A method of preparing a cementitious material comprising mixing a hydraulic cement with a pozzolanic cement replacement selected from fly ash, slag, natural pozzolans, and mixtures thereof, and a compatibilizing admixture as in claim 5 optionally including mixing aggregate with the cement and cement replacement and including additionally mixing water in an amount sufficient to effect hydraulic setting of the cement, cement replacement and aggregate mixture.
- 5 10
8. A cementitious dry cast mixture comprising hydraulic cement, coarse aggregate, fine aggregate, and including the derivatized polycarboxylate dispersant of claim 1.
9. A method for making a dry cast cementitious article comprising:
  - 15 a. providing a mixture of hydraulic cement, water, coarse aggregate, fine aggregate, and including the derivatized polycarboxylate dispersant of claim 1; and
  - b. forming the article from the mixture.