

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
18 January 2007 (18.01.2007)

PCT

(10) International Publication Number  
**WO 2007/008288 A2**

(51) International Patent Classification:

**C10G 11/00** (2006.01)    **C07C 5/333** (2006.01)  
**C07C 7/163** (2006.01)    **C07C 5/25** (2006.01)  
**C07C 2/68** (2006.01)    **C07C 5/23** (2006.01)

7-14-1 Shinomiya, Hiratsuka-shi, Kanagawa 254-0014 (JP). **AOI, Nobuyuki** [JP/JP]; Nikki-U, 7-14-1 Shinomiya, Hiratsuka-shi, Kanagawa 254-0014 (JP).

(21) International Application Number:

PCT/US2006/019846

(74) Common Representative: **UOP LLC**; John G. Tolomei, Assistant Secretary-Patent Matters, 25 East Algonquin Road, P.O. Box 5017, Des Plaines, IL 60017-5017 (US).

(22) International Filing Date: 23 May 2006 (23.05.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

11/137,189                      25 May 2005 (25.05.2005)    US

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(71) Applicant (for all designated States except US): **UOP LLC** [US/US]; John G. Tolomei, Assistant Secretary-Patent Matters, 25 East Algonquin Road, P.O. Box 5017, Des Plaines, IL 60017-5017 (US).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **RENDE, Dean, E.** [US/US]; UOP LLC, 25 East Algonquin Road, P.O. Box 5017, Des Plaines, IL 60017-5017 (US). **REKOSKE, James, E.** [US/US]; UOP LLC, 25 East Algonquin Road, P.O. Box 5017, Des Plaines, IL 60017-5017 (US). **BRICKER, Jeffery, C.** [US/US]; UOP LLC, 25 East Algonquin Road, P.O. Box 5017, Des Plaines, IL 60017-5017 (US). **BOIKE, Jeffrey, L.** [US/US]; UOP LLC, 25 East Algonquin Road, P.O. Box 5017, Des Plaines, IL 60017-5017 (US). **TAKAYAMA, Masao** [JP/JP]; Nikki-U, 7-14-1 Shinomiya, Hiratsuka-shi, Kanagawa 254-0014 (JP). **HARA, Kouji** [JP/JP]; Nikki-U,

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: LAYERED COMPOSITION AND PROCESSES FOR PREPARING AND USING THE COMPOSITION

(57) Abstract: A layered composition which can be used in various processes has been developed. The composition comprises an inner core such as a cordierite core and an outer layer comprising a refractory inorganic oxide, a fibrous component and an inorganic binder. The refractory inorganic oxide layer can be alumina, zirconia, titania, etc. while the fibrous component can be titania fibers, silica fibers, carbon fibers, etc. The inorganic oxide binder can be alumina, silica, zirconia, etc. The layer can also contain catalytic metals such as gold and platinum plus other modifiers. The layered composition is prepared by coating the inner core with a slurry comprising the refractory inorganic oxide, fibrous component, an inorganic binder precursor and an organic binding agent such as polyvinyl alcohol. The composition can be used in various hydrocarbon conversion processes.

WO 2007/008288 A2

LAYERED COMPOSITION AND PROCESSES FOR  
PREPARING AND USING THE COMPOSITION

BACKGROUND OF THE INVENTION

[0001] Numerous commercial processes are carried out using a catalyst. This is especially true of various hydrocarbon conversion processes. These catalysts comprise one or more catalytic element deposited onto a relatively high surface area support. Further, the catalytic element or component can be evenly dispersed throughout the support, be dispersed on the surface of the support or present as a band below the surface.

[0002] The art also discloses catalysts containing an inert core or layer and an active outer layer or shell. For example, US-A-3,145,183 discloses spheres having an impervious center and a porous shell. Although it is disclosed that the impervious center can be small, the overall diameter is 1/8" or larger. It is stated that for smaller diameter spheres (less than 1/8"), uniformity is hard to control. US-A- 5,516,740 discloses a thin outer shell of catalytic material bonded to an inner core of catalytically inert material. The outer layer can have catalytic metals such as platinum dispersed on it. The '740 patent further discloses that this catalyst is used in an isomerization process. Finally, the outer layer material contains the catalytic metal prior to it being coated onto the inner core.

[0003] US-A-4,077,912 and US-A-4,255,253 disclose a catalyst having a base support having deposited thereon a layer of a catalytic metal oxide or a combination of a catalytic metal oxide and an oxide support. US 5,935,889 discloses a catalyst which comprises a catalytically inert core material on which is deposited and bonded a thin shell of material containing active sites. Finally, US 6,177,381 B1 discloses a layered catalyst composition containing an inner core, an outer layer bonded to the inner core and where the outer layer has dispersed thereon a platinum group metal, a promoter metal and a modifier metal.

[0004] One problem associated with the layered compositions of the prior art is that the strength or attrition resistance was not sufficient for certain applications. Applicants have discovered that adding a fibrous component to the outer layer greatly increases its strength. The fibrous components can be either inorganic fibers such as silica or mullite fibers or organic fibers such as carbon fibers.

## DETAILED DESCRIPTION OF THE INVENTION

[0005] One element of the layered composition of the present invention is an inner core. One characteristic of the materials which can be used for the inner core is the ability to be formed into a desired shape. Examples of materials which can be used include but are not limited to metals, refractory inorganic oxides and silicon carbide. Refractory inorganic oxides are preferred with non-limiting examples being aluminas, cordierite, mullite, montmorillonite, silica, zirconia, titania and mixtures thereof. Aluminas include gamma, theta, delta and alpha alumina. A preferred inorganic oxide is cordierite. When the inner core is a refractory inorganic oxide, it is necessary that it be different from the outer layer refractory inorganic oxide.

[0006] Further, when the outer layer will have additional components, e.g. metals or metal oxides, which are deposited thereon by impregnation means, it is preferred that the inner core have a lower adsorptive capacity relative to the outer layer. This adsorptive capacity is with respect to solvents which may be used to impregnate the outer layer with a compound of a catalytic component. The inner core should also have a substantially lower capacity for the compounds themselves versus the outer layer.

[0007] These materials which form the inner core can be formed into a variety of shapes such as pellets, extrudates, spheres, hollow tubes or irregularly shaped particles although not all materials can be formed into each shape. Preparation of the inner core can be done by means known in the art such as oil dropping, pressure molding, metal forming, pelletizing, granulation, extrusion, rolling methods and marumerizing. A spherical inner core is preferred. The inner core whether spherical or not has an effective average diameter of 0.05 mm to 15 mm and preferably from 0.5 mm to 10 mm. For a non-spherical inner core, effective diameter is defined as the diameter the shaped article would have if it were molded into a sphere. Once the shaped inner core is formed it is optionally calcined at a temperature of 400°C to 1500°C.

[0008] The inner core is now coated with a layer of a refractory inorganic oxide which is different from the inorganic oxide which may be used as the inner core and will be referred to as the outer refractory inorganic oxide. This outer refractory oxide is one which has good porosity, has a surface area of at least 2 m<sup>2</sup>/g, and preferably at least 20 m<sup>2</sup>/g and most preferably at least 30 m<sup>2</sup>/g, an apparent bulk density of 0.2 g/ml to 1.8 g/ml. Non-limiting examples of the refractory inorganic oxides which can be used are gamma alumina, delta alumina, eta alumina,

theta alumina, silica/alumina, zeolites, non-zeolitic molecular sieves (NZMS), titania, zirconia and mixtures thereof. It should be pointed out that silica/alumina is not a physical mixture of silica and alumina but means an acidic and amorphous material that has been cogelled or coprecipitated. This term is well known in the art, see e.g., US-A-3,909,450, US-A-3,274,124 and US-A-4,988,659. Examples of zeolites include, but are not limited to, zeolite Y, zeolite X, zeolite L, zeolite beta, ferrierite, MFI, UZM-4(see US 6,776,975 B1), UFI, UZM-8(US 6,756,030 B1), UZM-9(US 6,713,041 B1), mordenite and erionite. Non-zeolitic molecular sieves (NZMS) are those molecular sieves which contain elements other than aluminum and silicon and include silicoaluminophosphates (SAPOs) described in US-A-4,440,871, ELAPOs described in US-A-4,793,984, MeAPOs described in US-A-4,567,029 all of which are incorporated by reference. Preferred refractory inorganic oxides are gamma, eta alumina and zirconia.

**[0009]** The refractory inorganic oxide is applied to the inner core by first forming a slurry comprising the refractory inorganic oxide. The slurry is formed by admixing a solvent with the refractory inorganic oxide to form a mixture and milling the mixture for a time sufficient to form a slurry. The solvent which is usually used is water although organic solvents can also be used. The mixture can also contain an agent which will aid in forming the slurry such as but not limited to nitric acid, hydrochloric acid, sulfuric acid and acetic acid. The slurry will also contain an inorganic binder precursor which is usually, a sol, a gel or a compound of a metal which on heating will decompose to form an inorganic oxide binder. The inorganic binders which can be used include but are not limited to alumina, silica, zirconia, titania, aluminum phosphate, etc. Nonlimiting examples of binder precursors which can be added to the slurry are:  $ZrO(C_2H_3O_2)_2$ ;  $ZrO(NO_3)_2$ ;  $ZrO(OH)Cl \cdot nH_2O$ ; zirconia sol;  $ZrOCO_3$ ;  $ZrO(OH)_2$ ;  $Zr(C_5H_8O_2)_4$ ;  $Zr(SO_4)_2 \cdot 4H_2O$ ; alumina sol; silica sol; aluminum nitrate and boehmite.

Although in some cases it is preferred that the binder give the same refractory oxide as the outer layer oxide, generally any inorganic binder can be used with any outer layer refractory oxide. For example, an alumina binder can be used when the outer layer is a zeolite, titania, silica or alumina. However, it has been found that when zirconia is the outer refractory inorganic layer, it is preferred to have a zirconia binder. The amount of inorganic binder precursor present in the slurry is that amount which will provide from 1 wt.% to 99 wt.% inorganic binder on the deposited outer layer. Preferably the amount of binder precursor present is that amount which

will give from 2 to 40 wt.% of the outer layer of inorganic binder and most preferably the amount which will provide from 5 to 30 wt.% of the outer layer.

[0010] Another necessary component of the slurry is a fibrous component. Suitable fibrous components include those that comprise fibers that are elongated, thread-like objects or structures or filaments. The types of fibers which can be used include both inorganic and organic fibers either of which can be natural or synthetic. Generally fibers can comprise a large array of materials including without limitation glasses, minerals, metal oxides, ceramics, metals, polymers and carbons. Specific examples of inorganic fibers include but are not limited to titania fibers, potassium titanate fibers, zirconia fibers, mullite fibers, alumina fibers, silicon carbide fibers, glass wool, boron fibers, aluminum fibers, silica fibers and cordierite fibers. A preferred fiber which is mostly silica (60% SiO<sub>2</sub>, 33% CaO and 6% MgO) is Superwool™ manufactured and sold by Thermal Ceramics. Nonlimiting examples of organic fibers are graphite fibers, carbon fibers and polymeric fibers such as polyethylenes, polyesters, polyurethanes, polyamides, aromatic polyamides (e.g. Kevlar™), polystyrenes (e.g. syndiotactic polystyrene), polytetrafluoroethylenes (e.g. Teflon™). Furthermore, combinations of materials may be used in the fibers as well as combinations of fibers in the fibrous component. It should be pointed out that when organic fibers are used, the subsequent treating temperatures and the process temperature that it will be used at must be below the combustion temperature of the organic fibers. Obviously the inorganic fibers will not combust, but the operating temperature must be below its melting temperature. Furthermore, fibers may be further treated (e.g. coated) to accentuate desirable characteristics (e.g. treated to increase decomposition or melting temperature). While the fibrous component may include fibers that are woven, braided or otherwise entangled or connected in an unwoven manner, the fibers may also be free of connections with other fibers.

[0011] Although the length of the fibers is not critical, usually the fibers have a length from 1 to 10,000 micrometers, preferably from 2 to 1,000 micrometers and most preferably from 5 to 300 micrometers. The fibers also have varying diameters which again is not critical. Smaller diameter fibers are more easily dispersed and thus are preferred. Since both the length and diameter of the fibers can be varied, a preferred length/diameter (L/D) ratio can be determined experimentally. This L/D ratio is different for different fibers.

[0012] The amount of fibers which can be added to the slurry can vary considerably and is usually that amount which will give from 1 to 30 wt.% of the final layer weight, preferably from 1 to 20 wt.% and most preferably from 3 to 10 wt.%.

[0013] It is also necessary that the slurry contain an organic bonding agent which aids in the adhesion of the layer material to the inner core. Examples of this organic bonding agent include but are not limited to polyvinyl alcohol (PVA), hydroxy propyl cellulose, methylcellulose and carboxy methylcellulose. The amount of organic bonding agent which is added to the slurry will vary considerably from 0.1 wt. % to 5 wt. % of the slurry.

[0014] As stated, the slurry is milled using any of a variety of mills known in the art such as ball milling, impact milling, etc. Milling is carried out to ensure adequate blending of the various components and to optionally reduce the particle size of the refractory inorganic oxide powder and/or fibers. Milling is usually carried out for a time of 2 to 8 hours.

[0015] Coating of the inner core with the slurry can be accomplished by means such as rolling, dipping, spraying, etc. One preferred technique involves using a fixed fluidized bed of inner core particles and spraying the slurry into the bed to coat the particles evenly. The thickness of the layer can vary considerably, but usually is from 40 to 400 micrometers preferably from 40 to 300 micrometers and most preferably from 50 to 200 micrometers. It should be pointed out that the optimum layer thickness depends on the use for the catalyst and the choice of the outer refractory oxide. Once the inner core is coated with the layer of outer refractory inorganic oxide, the resultant layered composition is dried at a temperature of 100°C to 150°C for a time of 1 to 24 hours and then calcined at a temperature of at least 200°C for a time of 0.5 to 10 hours to effectively bond the outer layer to the inner core and provide a layered composition. The calcination conditions are chosen to not only effectively bond the outer layer to the inner core but to optimize the characteristics of the outer layer, e.g. surface area of the layer, integrity of the fibers, pore volume of the inorganic oxide etc. As stated above, if organic fibers are used the calcination temperature must be below their combustion temperature. Thus, preferred calcination temperatures are from 200°C to 1500°C and most preferably from 400°C to 1100°C. Finally, the drying and calcining steps can be combined into one step. It should also be pointed out that in some cases it may be necessary to carry out the layering process more than once in order to obtain the desired layer thickness. Intermediate calcining steps may not be

necessary with a drying step being sufficient to ensure that the first layer does not dissolve during the subsequent layering step.

[0016] In one embodiment of the invention, the layered composition comprises more than one layer. Successive layers are applied to the coated composition after the first (or subsequent 5 layer) has been calcined. Coating of a layered core is carried out as described above for the first layer. The second layer of refractory inorganic oxide is different from the first layer and will be different from the third layer (if any), although the first and third layer can be the same inorganic oxide. Thus, it is only necessary that adjacent layers be of different refractory inorganic oxides. The thickness of each layer is as stated for the first layer and the number of additional layers can 10 vary from 1 to 5 layers or more.

[0017] As stated the use of fibers in the outer layer greatly improves the strength or attrition resistance of the resultant layered composition. The strength of the layered composition was determined by measuring its impact breakage (IB). Impact breakage was determined by taking an amount of layered composition (about 50 cc) after calcination, placing them in a flat drum 15 and rotating the drum at 25 rpm for 10 minutes. The fines were collected, weighted and the IB determined from the following equation:

$$IB = (\text{Weight of Fines} / \text{Total Weight of Layered Composition}) \times 100\%$$

[0018] The layered composition of the invention will have an IB of preferably less than 10 wt.%, more preferably less than 5 wt.% and most preferably less than 3 wt.%. Ranges within 20 the above stated ranges are also contemplated.

[0019] Although the layered composition described above can be used as is to catalyze various reactions, it is usually used as a support for various catalytic components. These catalytic components are selected from the group consisting of Groups 3-12 of the Periodic Table of the Elements using the IUPAC system of numbering the groups and as set forth at 25 <http://pearl1.lanl.gov/periodic/default.htm>. Preferred catalytic elements or metals are the noble metals or platinum group metals which include platinum, palladium, rhodium, ruthenium, osmium and iridium. Gold and silver are also preferred catalytic metals. Combinations of catalytic components are also preferred, such as palladium used in combination with gold and/or rhodium.

[0020] These catalytic metal components can be deposited on the layered support in any 30 suitable manner known in the art. One method involves impregnating the layered composition

or support with a solution (usually aqueous, although organic solvents can be used) of a decomposable compound of the catalytic metal or metals. By decomposable is meant that upon heating the metal compound is converted to the metal or metal oxide with the release of byproducts. Examples of the compounds which can be used include without limitation chlorides, other halides, nitrates, nitrites, hydroxides, oxides, oxalates, acetates, sulfates and amines. Illustrative examples of decomposable compounds of the platinum group metals are chloroplatinic acid, ammonium chloroplatinate, bromoplatinic acid, dinitrodiamino platinum, sodium tetranitroplatinate, rhodium trichloride, hexa-amminerhodium chloride, rhodium carbonylchloride, sodium hexanitrorhodate, chloropalladic acid, palladium chloride, palladium nitrate, diamminepalladium hydroxide, tetraamminepalladium chloride, hexachloroiridate (IV) acid, hexachloroiridate (III) acid, ammonium hexachloroiridate (III), ammonium aquohexachloroiridate (IV), ruthenium tetrachloride, hexachlororuthenate, hexa-ammineruthenium chloride, osmium trichloride and ammonium osmium chloride. Examples of other palladium compounds include but are not limited to  $\text{Na}_2\text{PdCl}_4$ ,  $\text{Pd}(\text{NH}_3)_4(\text{NO}_2)_2$ ,  $\text{Pd}(\text{NH}_3)_4(\text{OH})_2$ ,  $\text{Pd}(\text{NH}_3)_4(\text{NO}_3)_2$ ,  $\text{Pd}(\text{NH}_3)_4(\text{OAc})_2$ ,  $\text{Pd}(\text{NH}_3)_2(\text{OAc})_2$ ,  $\text{Pd}(\text{OAc})_2$  in KOH and/or  $\text{NMe}_4\text{OH}$  and/or NaOH,  $\text{Pd}(\text{NH}_3)_4(\text{HCO}_3)_2$  and palladium oxalate. Examples of gold and silver compounds include but are not limited to  $\text{AuCl}_3$ ,  $\text{HAuCl}_4$ ,  $\text{NaAuCl}_4$ ,  $\text{KAuO}_2$ ,  $\text{NaAuO}_2$ ,  $\text{NMe}_4\text{AuO}_2$ ,  $\text{Au}(\text{OAc})_3$ ,  $\text{HAu}(\text{NO}_3)_4$ ,  $\text{AgNO}_3$ ,  $\text{AgC}_2\text{H}_3\text{O}_2$  and  $\text{AgClO}_3$ . Solubility modifiers may be utilized to aid in solubilizing the decomposable compound of the catalytic metal or metals. For example, acids or bases may be used to facilitate the catalytic compound going into solution. In one embodiment, KOH and/or  $\text{NMe}_4\text{OH}$  is used in combination with  $\text{Au}(\text{OAc})_3$  or nitric acid is used with  $\text{HAu}(\text{NO}_3)_4$ .

**[0021]** Multiple solutions containing the catalytic compounds may be impregnated onto the layered composition or support simultaneously (e.g. co-impregnation) or sequentially and may be impregnated through the use of one or multiple solutions.

**[0022]** One or more calcining steps may be used, such that at any point after at least one catalytic component compound is contacted with the layered composition or refractory inorganic oxide, it may be calcined. For example, the calcining step is carried out at a temperature in the range of  $100^\circ\text{C}$  to  $700^\circ\text{C}$ , preferably between  $200^\circ\text{C}$  and  $500^\circ\text{C}$  in a non-reducing atmosphere. Calcination times may vary but preferably are between 1 and 5 hours. The degree of decomposition of the catalytic component compound depends on the

temperature used and length of time the impregnated catalyst is calcined and can be followed by monitoring volatile decomposition products.

[0023] Preferably, the last calcining step occurs before contact of the gold catalytic component to a zirconia containing layered composition. Alternately, calcining of a zirconia containing support composition containing gold is conducted at temperatures below 300°C. Exemplary protocols including a calcining step include: a) impregnating with palladium followed by calcining followed by impregnating with gold; b) co-impregnating palladium and rhodium followed by calcining followed by impregnating with gold; c) impregnating with palladium followed by calcining followed by impregnating with rhodium followed by calcining followed by impregnating with gold; or d) impregnating with palladium and rhodium, followed by impregnating with gold, followed by calcination.

[0024] One impregnation procedure involves the use of a steam-jacketed rotary dryer. The layered composition is immersed in the impregnating solution containing the desired metal compound(s) contained in the dryer and the support is tumbled therein by the rotating motion of the dryer. Evaporation of the solution in contact with the tumbling support is expedited by applying steam to the dryer jacket. The resultant composite is allowed to dry under ambient temperature conditions, or dried at a temperature of 80° to 110°C, followed by calcination, thereby converting the metal compound to the metal or metal oxide.

[0025] Another impregnation procedure is spray impregnation which is well known in the art and is presented here only for completeness. The layered composition is loaded into a drum and a spray nozzle is inserted into the opening of the drum. The support is tumbled and the metal containing solution is delivered through the spray nozzle for 15 to 30 minutes. The amount of solution can be varied to determine the depth of penetration into the support. The support is dried at 110°C to 150°C and additional metals can be added by repeating the above procedure or the support can be calcined to convert the metal compounds to the metal or metal oxide.

[0026] The dispersion of the catalytic metals can either be done as described above after the refractory inorganic oxide has been applied to the inner core or the refractory inorganic oxide can first be impregnated with the desired solution, dried, calcined, slurried and then applied to the inner core. If the layered composition contains more than one layer, all the layers need not have catalytic metals dispersed thereon. For example, the first layer can have one or more

catalytic metal dispersed thereon, while the second layer does not have any catalytic metals thereon or vice versa. Alternatively, the first layer can have one or more catalytic metal while the second layer has different catalytic metal(s).

[0027] In addition to the catalytic components, various promoters and modifiers can also be dispersed on the layered composition. Promoters and modifiers can be any elements selected from the group consisting of alkali metals, alkaline earth metals, tin, germanium, rhenium, gallium, bismuth, lead, indium, cerium, zinc, boron and mixtures thereof. One preferred promoter for use in vinyl acetate production is an alkali metal, which may be provided in the form of an acetate such as KOAc. The addition of the alkali metal may be referred to as activating the catalyst.

[0028] The promoter and modifier components can be dispersed onto the layered support in the same way as described for the catalytic component. All the components can be impregnated using one common solution or they can be sequentially impregnated in any order, but not necessarily with equivalent results. Additionally, these promoters and modifiers can be present in one layer, but not in another layer. They can also be present in a layer where there are no catalytic metals or only in layers where there are catalytic metals.

[0029] When it is stated that the catalytic components, promoters and modifiers are "dispersed or deposited on" the outer layer it is meant that they can be dispersed either on the surface of the layer, throughout the layer or even below the outer surface in a tight band. It should be pointed out that when the inner core comprises a material that has some adsorptive property, a small fraction of the catalytic component, promoter and/or modifier can be found on or throughout the core.

[0030] The catalysts of the present invention may be utilized to produce alkenyl alkanoates from an alkene, alkanolic acid and an oxygen containing gas in the presence of a catalyst. Preferred alkene starting materials contain from two to four carbon atoms (e.g. ethylene, propylene and n-butene). Preferred alkanolic acid starting materials used in the process of this invention for producing alkenyl alkanoates contain from two to four carbon atoms (e.g., acetic, propionic and butyric acid). Preferred products of the process are vinyl acetate, vinyl propionate, vinyl butyrate, and allyl acetate. The most preferred starting materials are ethylene and acetic acid with the vinyl acetate being the most preferred product. Thus, the present invention is useful in the production of olefinically unsaturated carboxylic

esters from an olefinically unsaturated compound, a carboxylic acid and oxygen in the presence of a catalyst. Other methods of making alkenyl alkanoates may be found in US 2005/0181940 A1.

5 [0031] When vinyl acetate is produced using the catalyst of the present invention, a stream of gas, which contains ethylene, oxygen or air, and acetic acid is passed over the catalyst. The composition of the gas stream can be varied within wide limits, taking into account the zone of flammability of the effluent. For example, the molar ratio of ethylene to oxygen can be 80:20 to 98:2, the molar ratio of acetic acid to ethylene can be 100:1 to 1:100, preferably 10:1 to 1:10, and most preferably 1:1 to 1:8. The gas stream may also contain gaseous alkali metal acetate  
10 and/or inert gases, such as nitrogen, carbon dioxide and/or saturated hydrocarbons. Reaction temperatures which can be used are elevated temperatures, preferably those in the range of 125-220°C. The pressure employed can be a somewhat reduced pressure, normal pressure or elevated pressure, preferably a pressure of up to 2026 kPa (20 atmospheres gauge).

[0032] A vinyl acetate catalyst according to the present invention preferably comprises  
15 between 1 to 10 grams of palladium, and 0.5 to 10 grams of gold per liter of catalyst. The amount of gold is preferably from 10 to 125 wt % based on the weight of palladium. Further, the catalyst preferably contains 10 to 70, preferably 20 to 60 grams of promoter (e.g. KOAc) per liter of catalyst.

[0033] In one application, a layered catalytic composite is used to produce vinyl acetate  
20 from the reaction of ethylene with acetic acid and oxygen. In this particular case, the inner core preferably comprises cordierite and the refractory oxide layer is a zirconia layer having fibers such as mullite, Superwool or TiO<sub>2</sub>. The layered composition has dispersed thereon palladium, gold and potassium with rhodium being optional. A preferred method of dispersing the metals onto the support is to first impregnate the layered support with an  
25 aqueous solution comprising a palladium compound such as Pd(NH<sub>3</sub>)<sub>4</sub>(OH)<sub>2</sub> and then calcining the impregnated layered composition. Next the calcined composition is impregnated with a solution comprising a gold compound such as KAuO<sub>2</sub>, drying, calcining, and finally reducing the catalyst at a temperature from ambient to 550°C for a time of 1 to 5 hours. Reduction is carried out under hydrogen or other reducing atmospheres. Addition of a  
30 promoter may be carried out before or after the reduction step.

[0034] The layered composition of the invention with catalytic metals thereon can also be used for other hydrocarbon conversion processes such as hydrocracking, cracking, isomerization, hydrogenation, dehydrogenation, oxidation and alkylation of both aromatic and isoparaffin hydrocarbons. The desirable catalytic metals for these reactions are the platinum group metals, as described above. Promoter metals selected from the group consisting of Sn, Ge, Re, Ga, Bi, Pb, In, Ce, Zn and mixtures thereof can also be present as well as modifier metals selected from the group consisting of alkali metals, alkaline earth metals and mixtures thereof can also be dispersed on the layered support. Methods of dispersing these various components onto the layered support are as set forth above. As described in US 6,280,608 B1, a halogen component can also be present on the layered catalytic component.

[0035] Although in the above embodiments all three metals are uniformly dispersed in the outer layer of refractory oxide and substantially present only in the outer layer, it is also within the bounds of this invention that the modifier metal can be present both in the outer layer and the inner core. This is owing to the fact that the modifier metal can migrate to the inner core, when the core is other than a metallic core.

[0036] Although the concentration of each metal component can vary substantially, it is desirable that the platinum group metal be present in a concentration of 0.01 to 5 weight percent on an elemental basis of the entire weight of the catalytic composition and preferably from 0.05 to 2.0 wt.%. The promoter metal is present in an amount from 0.05 to 10 wt.% of the entire catalytic composition while the modifier metal is present in an amount from 0.1 to 5 wt.% and preferably from 2 to 4 wt.% of the entire catalytic composition.

[0037] The conditions necessary to carry out alkylation of aromatic compounds are well known and are disclosed, for example, in US-A-3,965,043 and US-A-3,979,331 which are incorporated by reference. Generally the process can be carried out in a batch type or a continuous type operation. In a batch type process, the catalyst, aromatic compound and alkylating agent are placed in an autoclave and the pressure increased, if necessary, in order to effect the reaction in the liquid phase. An excess amount of aromatic compound should be present, preferably in a range of 2:1 to 20:1 moles of aromatic compound per mole of alkylating agent. The reaction is carried out at an elevated temperature since the rate of alkylation is undesirably low at room temperature. Preferably the temperature is in the range of 40°C to

200°C. The process is carried out for a time of 0.5 to 4 hours, after which the product is separated from the starting materials by conventional means.

[0038] If it is desired to carry out the process in a continuous manner, the catalyst is placed in a reactor which is heated to the desired operating temperature and the pressure increased  
5 above atmospheric, if necessary. The aromatic compound and alkylating agent are flowed over the catalyst bed at a predetermined liquid hourly space velocity sufficient to effect alkylation. The effluent is continuously withdrawn and conventional separation means used to isolate the desired product.

[0039] Hydrocracking conditions typically include a temperature in the range of 240°C to  
10 649°C (400°F - 1200°F), preferably between 316°C and 510°C (600-950°F). Reaction pressures are in the range of atmospheric to 24,132 kPag (3,500 psig), preferably between 1,379 and 20,685 kPag (200 - 3,000 psig). Contact times usually correspond to liquid hourly space velocities (LHSV) in the range of 0.1 hr<sup>-1</sup> to 15 hr<sup>-1</sup>, preferably between 0.2 and 3 hr<sup>-1</sup>.

Hydrogen circulation rates are in the range of 178 to 8,888 standard cubic meters per cubic  
15 meter of charge (1,000 to 50,000 standard cubic feet (scf) per barrel of charge) preferably between 355 to 5,333 std. m<sup>3</sup>/m<sup>3</sup> (2,000 and 30,000 scf per barrel of charge).

[0040] The reaction zone effluent is normally removed from the catalyst bed, subjected to partial condensation and vapor-liquid separation and then fractionated to recover the various  
20 components thereof. The hydrogen and, if desired some or all of the unconverted heavier materials, are recycled to the reactor. Alternatively, a two-stage flow may be employed with the unconverted material being passed into a second reactor. Catalysts of the subject invention may be used in just one stage of such a process or may be used in both reactor stages.

[0041] Catalytic cracking processes are preferably carried out with the catalyst composition using feedstocks such as gas oils, heavy naphthas, deasphalted crude oil residua, etc. with  
25 gasoline being the principal desired product. Temperature conditions of 454°C to 593°C (850° to 1100°F,) LHSV values of 0.5 to 10 hr<sup>-1</sup> and pressure conditions of from 0 to 345 kPag (50 psig) are suitable.

[0042] Isomerization reactions are carried out in a temperature range of 371°C to 538°C  
30 (700 - 1000°F). Olefins are preferably isomerized at temperatures of 260°C to 482°C (500°F to 900°F), while paraffins, naphthenes and alkyl aromatics are isomerized at temperatures of 371°C to 538°C (700°F to 1000°F). Hydrogen pressures are in the range of 689 to 3,445 kPag

(100 to 500 psig). Contact times usually correspond to liquid hourly space velocities (LHSV) in the range of  $0.1 \text{ hr}^{-1}$  to  $10 \text{ hr}^{-1}$ . Hydrogen to hydrocarbon molar ratios in the range of 1 to 20, preferably between 4 and 12.

**[0043]** In a dehydrogenation process, dehydrogenatable hydrocarbons are contacted with the catalyst of the instant invention in a dehydrogenation zone maintained at dehydrogenation conditions. This contacting can be accomplished in a fixed catalyst bed system, a moving catalyst bed system, a fluidized bed system, etc., or in a batch-type operation. A fixed bed system is preferred. In this fixed bed system the hydrocarbon feed stream is preheated to the desired reaction temperature and then flowed into the dehydrogenation zone containing a fixed bed of the catalyst. The dehydrogenation zone may itself comprise one or more separate reaction zones with heating means there between to ensure that the desired reaction temperature can be maintained at the entrance to each reaction zone. The hydrocarbon may be contacted with the catalyst bed in either upward, downward or radial flow fashion. Radial flow of the hydrocarbon through the catalyst bed is preferred. The hydrocarbon may be in the liquid phase, a mixed vapor-liquid phase or the vapor phase when it contacts the catalyst. Preferably, it is in the vapor phase.

**[0044]** Hydrocarbons which can be dehydrogenated include hydrocarbons with 2 to 30 or more carbon atoms including paraffins, isoparaffins, alkylaromatics, naphthenes and olefins. A preferred group of hydrocarbons is the group of normal paraffins with 2 to 30 carbon atoms.

Especially preferred normal paraffins are those having 2 to 15 carbon atoms.

**[0045]** Dehydrogenation conditions include a temperature of from  $400^{\circ}\text{C}$  to  $900^{\circ}\text{C}$ , a pressure of from 1 to 1013 kPa and a liquid hourly space velocity (LHSV) of from  $0.1$  to  $100 \text{ hr}^{-1}$ . Generally for normal paraffins the lower the molecular weight the higher the temperature required for comparable conversion. The pressure in the dehydrogenation zone is maintained as low as practicable, consistent with equipment limitations, to maximize the chemical equilibrium advantages.

**[0046]** The effluent stream from the dehydrogenation zone generally will contain unconverted dehydrogenatable hydrocarbons, hydrogen and the products of dehydrogenation reactions. This effluent stream is typically cooled and passed to a hydrogen separation zone to separate a hydrogen-rich vapor phase from a hydrocarbon-rich liquid phase. Generally, the hydrocarbon-rich liquid phase is further separated by means of either a suitable selective

adsorbent, a selective solvent, a selective reaction or reactions or by means of a suitable fractionation scheme. Unconverted dehydrogenatable hydrocarbons are recovered and may be recycled to the dehydrogenation zone. Products of the dehydrogenation reactions are recovered as final products or as intermediate products in the preparation of other compounds.

5 [0047] The dehydrogenatable hydrocarbons may be admixed with a diluent material before, while or after being flowed to the dehydrogenation zone. The diluent material may be hydrogen, steam, methane, ethane, carbon dioxide, nitrogen, argon and the like or a mixture thereof. Hydrogen is the preferred diluent. Ordinarily, when hydrogen is utilized as the diluent it is utilized in amounts sufficient to ensure a hydrogen to hydrocarbon mole ratio of 0.1:1 to 10:1, with best results being obtained when the mole ratio range is 1:1 to 10:1. The diluent hydrogen stream passed to the dehydrogenation zone will typically be recycled hydrogen separated from the effluent from the dehydrogenation zone in the hydrogen separation zone.

10 [0048] Water or a material which decomposes at dehydrogenation conditions to form water such as an alcohol, aldehyde, ether or ketone, for example, may be added to the dehydrogenation zone, either continuously or intermittently, in an amount to provide, calculated on the basis of equivalent water, 1 to 20,000 weight ppm of the hydrocarbon feed stream. One to 10,000 weight ppm or water addition gives best results when dehydrogenating paraffins having from 2 to 30 or more carbon atoms.

20 [0049] Hydrogenation processes including selective hydrogenation of dienes and trienes can be carried out using reactors and hydrogenation zones similar to the dehydrogenation process described above. Specifically, hydrogenation conditions include pressures of 0 kPag to 13,789 kPag, temperatures of 30°C to 280°C, H<sub>2</sub> to hydrogenatable hydrocarbon mole ratios of 5:1 to 0.1:1 and LHSV of 0.1 to 20 hr<sup>-1</sup>.

25 [0050] The layered catalysts of this invention can also be used in oxidation reactions. These oxidation reactions include:

- 1) partial oxidation of hydrocarbon streams, such as naphtha or methane, to generate synthesis gas (CO +H<sub>2</sub>);
- 2) selective oxidation of hydrogen produced from endothermic dehydrogenation reactions such as ethylbenzene to styrene; and,
- 30 3) oxidation of methane, ethane or carbon monoxide to clean up flue gas emissions from combustion processes.

[0051] The layered sphere catalyst will be of most benefit to processes where the activity or selectivity of the catalyst is limited by intraparticle diffusional resistance of product or reactants.

[0052] The conditions for the oxidation process depend on the individual process application but are generally 350°C to 800°C, 40 kPa to 2030 kPa, with a diluent present in the feedstream such as N<sub>2</sub>, CO<sub>2</sub>, HO to control the reaction. Hydrogen may also be present as a diluent and also a reactant. For the selective oxidation of hydrogen, the molar ratio of oxygen to H<sub>2</sub> may vary from 0.05 to 0.5. The diluent level is generally from 0.1 to 10 moles of diluent per mole of hydrocarbon. For example, the steam to ethylbenzene molar ratio may be from 5:1 to 7:1 during the dehydrogenation of ethylbenzene. Typical space velocity for oxidation is between 0.5 to 50 hr<sup>-1</sup> LHSV.

[0053] The following examples are presented in illustration of this invention and are not intended as undue limitations on the generally broad scope of the invention as set out in the appended claims.

#### EXAMPLE 1

[0054] A slurry was prepared by adding to a vessel 634.2g of deionized water, 110g of 15% of poly-vinyl alcohol (PVA) solution and 11.1g of acetic acid. The subsequent mixture was stirred and to it there were added 221.8g of zirconia powder followed by 272.8g of zirconia sol binder. The resultant mixture was milled for 8 hours.

[0055] This resultant slurry was used to spray 700g of 7 mm diameter cordierite spheres using a coating apparatus to give a layer having an average thickness of 200 micrometer. The coated spheres were unloaded from the coating chamber and heated in air up to 600°C where they were calcined for 4 hours under dry air. The calcined spheres were tested for attrition resistance by taking 50cc of the calcined spheres, placing them in a flat drum and rotating the drum at 25rpm for 10 minutes. The impact breakage (IB) was determined as the weight percent fines generated versus the total weight of the spheres. The IB for this sample was found to be 17.5 wt. %.

#### EXAMPLE 2

[0056] Into a container there were added 1,021.6g of deionized water, 205.9g of a 15% PVA solution and 21.2g of acetic acid. The mixture was stirred and to it there were added

27.3g of mullite fibers comprising 80% Al<sub>2</sub>O<sub>3</sub>, 20% SiO<sub>2</sub> with an average fiber length of 200 micrometers and an average diameter of 3 micrometers. Next, 426.2g of zirconia powder was added followed by 469.8g of zirconia sol binder. The mixture was then ballmilled for 6 hours.

- 5 [0057] The resultant slurry from above was sprayed onto 711g of 7mm diameter cordierite spheres using a slurry coating apparatus to obtain wet spheres having an outer layer of 200 micrometers thick. The wet spheres were heated in air to 600°C and calcined at 600°C for 4 hours under dry air. The calcined spheres were tested for impact breakage and were found to have an IB of 3.3 wt.%.

10

## EXAMPLE 3

- [0058] A slurry was formed by adding 1,121.7g of deionized water and 225.5g of a 15% PVA solution and 23.2g of acetic acid into a vessel. The resultant mixture was stirred and to it there were added 29.9g of mullite fibers as described in Example 2 followed by the addition of 463.9g of zirconia powder and then 514.5g of zirconia sol binder. The resultant slurry was ballmilled for 6 hours.

15

- [0059] The resultant slurry was used to deposit a layer onto 800g of 7mm diameter cordierite spheres using a slurry coating apparatus thereby producing wet spheres having a layer with an average thickness of 100 micrometers. The wet spheres were calcined at 600°C for 4 hours under dry air and were found to have an IB of 3.0 wt.%.

20

## EXAMPLE 4

- [0060] Into a mixing vessel there were added 602.8g of deionized water, 122.5g of a 15% PVA solution and 12.6g of acetic acid. The mixture was stirred and to it there were added 15.3g of titania fibers having an average length of 3 micrometers and an average diameter of 0.3 micrometers. Next 253.7g of zirconia powder were added followed by 279.6g of zirconia sol binder. The resulting slurry was ballmilled for 6 hours.

25

- [0061] The slurry described above was used to deposit a layer onto 730g of 7mm diameter cordierite spheres by spraying the slurry onto the spheres using a slurry coating apparatus to give wet spheres having an outer layer of with an average thickness of 200

micrometers. The wet spheres were calcined at 600°C under dry air for 4 hours. The calcined spheres were tested and were found to have an IB of 2.0 wt.%.

#### EXAMPLE 5

[0062] Into a mixing vessel there were added 622.1g of deionized water, 129g of 15%  
5 PVA solution and 13.1g of acetic acid. The mixture was stirred and to it there were added 35.8g of titania fibers as described in Example 4 followed by the addition of 263.8g of zirconia powder and finally 310.4g of zirconia sol binder. The resultant slurry was ballmilled for 6 hours. The slurry contained approximately 10 wt.% titania fibers.

[0063] A portion of the slurry was deposited onto 730g of 7mm diameter cordierite  
10 spheres using a slurry coating system to give a layer having an average thickness of 200 micrometers. The wet spheres were calcined at 600°C for 4 hours under dry air and were found to have an IB of 1.4 wt. %.

[0064] It will be further appreciated that functions or structures of a plurality of  
15 components or steps may be combined into a single component or step, or the functions or structures of one-step or component may be split among plural steps or components. The present invention contemplates all of these combinations. Unless stated otherwise, amounts, dimensions and geometries of the various components depicted herein are not intended to be restrictive of the invention, and other amounts, dimensions or geometries are possible. It will also be appreciated from the above that the fabrication of the unique catalysts herein and the  
20 use thereof also constitute methods in accordance with the present invention. The present invention also encompasses intermediate (e.g. pre-catalysts) and end products resulting from the practice of the methods herein. The use of “comprising”, “having”, “containing” or “including” also contemplates embodiments that “consist essentially of” or “consist of” the recited feature.

[0065] The explanations and examples presented herein are intended to acquaint others  
25 skilled in the art with the invention, its principles, and its practical application. Those skilled in the art may adapt and apply the invention in its numerous forms, as may be best suited to the requirements of a particular use. Accordingly, the specific embodiments of the present invention as set forth are not intended as being exhaustive or limiting of the invention. The  
30 scope of the invention should, therefore, be determined not with reference to the above

description, but should instead be determined with reference to the appended claims, along with the full scope of equivalents to which such claims are entitled. The disclosures of all articles and references, including patents, patent applications and publications, are incorporated by reference for all purposes.

## CLAIMS:

1. A layered composition comprising an inner core and, an outer layer over the inner core, the outer layer comprising a refractory inorganic oxide, a fibrous component and an inorganic binder.
- 5 2. The composition of claim 1 where the layered composition has an impact breakage of less than 10 wt. %.
3. The composition of claim 1 further comprising a catalytic component dispersed on the outer layer and selected from the group consisting of an element from Groups 3-12 of the Periodic Table of the Elements (IUPAC) and mixtures thereof.
- 10 4. The composition of claim 4 further comprising a modifier component dispersed on the outer layer and selected from the group consisting of alkali metals, alkaline earth metals, tin, germanium, rhenium, gallium, bismuth, lead, indium, cerium, zinc, boron and mixtures thereof.
5. The composition of claim 1 or 3 where the outer layer has deposited thereon from one to  
15 5 additional layers and where adjacent layers comprise different inorganic oxides.
6. The composition of claim 5 where at least one of the additional layers has a catalytic component dispersed thereon and where the catalytic component is selected from the group consisting of an element from Groups 3-12 of the Periodic Table of the Elements (IUPAC) and mixtures thereof.
- 20 7. A process for preparing a layered composition comprising an inner core, and an outer layer over the inner core, the outer layer comprising a refractory inorganic oxide, a fibrous component and an inorganic binder, the process comprising:  
coating an inner core with a slurry comprising an outer refractory inorganic oxide, a  
fibrous component, an inorganic binder precursor, an organic bonding agent and a  
25 solvent to give a coated core; and  
calcining the coated core at a temperature of at least 200°C for a time sufficient to bond the outer layer to the inner core and provide a layered composition.
8. The process of claim 7 further comprising impregnating the layered composition with a solution comprising a catalytic metal compound to provide an impregnated layered  
30 composition and calcining the impregnated layered composition at a temperature of

200°C to 700°C for a time sufficient to provide a catalytic metal component on the outer refractory inorganic oxide layer and where the catalytic metal is selected from the group consisting of an element from Groups 3-12 of the Periodic Table of the Elements (IUPAC).

- 5 9. The process of claim 8 where the solution further comprises a modifier component compound and where the modifier component is selected from the group consisting of alkali metals, alkaline earth metals, tin, germanium, rhenium, gallium, bismuth, lead, indium, cerium, zinc, boron and mixtures thereof.
10. The process of claim 7 where the coating and calcining steps are repeated from 1 to 5  
10 times to provide multiple layers.
11. A hydrocarbon conversion process comprising contacting a hydrocarbon stream with the layered composition of claim 1 or 2 or 3 or 4 or 5 or 6 at hydrocarbon conversion conditions to give a converted product.