






- (51) **International Patent Classification:**
C07D 413/04 (2006.01) *C07D 307/81* (2006.01)
C07D 307/79 (2006.01) *H01L 51/00* (2006.01)
C07D 307/80 (2006.01)
- (21) **International Application Number:**
PCT/EP2015/066664
- (22) **International Filing Date:**
21 July 2015 (21.07.2015)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
14306182.8 21 July 2014 (21.07.2014) EP
- (71) **Applicants:** **UNIVERSITÉ DE STRASBOURG** [FR/FR]; 4 rue Blaise Pascal, F-67000 Strasbourg (FR). **UNIVERSITE DE NANTES** [FR/FR]; 1, quai de Tourville, F-44000 Nantes (FR). **CENTRE NATIONAL DE LA RECHERCHE SCIENTIFIQUE (C.N.R.S)** [FR/FR]; 3, rue Michel Ange, F-75016 Paris (FR).
- (72) **Inventors:** **BENELHADJ, Karima**; 1, Rue D'eguisheim, F-67100 Strasbourg (FR). **MASSUE, Julien**; 1, Rue de Sarreguemines, F-67000 Strasbourg (FR). **ULRICH, Gilles**; 30 rte de Bischwiller, F-67460 Souffelweyersheim (FR). **ZIESSEL, Raymond**; 3, rue des Cailles, F-67460 Souffelweyersheim (FR). **JACQUEMIN, Denis**; 89 rue de la Jonelière, F-44300 Nantes (FR). **LAURENT, Adèle**; 18 rue Gustave Charpentier, F-44300 Nantes (FR).
- (74) **Agents:** **BLOT, Philippe** et al.; Cabinet Lavoix, 2, place d'Estienne d'Orves, F-75009 Paris (FR).
- (81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

[Continued on next page]

(54) **Title:** MOLECULES PRESENTING DUAL EMISSION PROPERTIES



(57) **Abstract:** The present invention concerns compound of formula (I); wherein: - A represents an electron-withdrawing group; - D represents an electron-donating group; - X is selected from the group consisting of: O, S and NR, wherein R is selected from the group consisting of: H, an alkyl group preferably comprising from 1 to 20 carbon atoms, an aryl group preferably comprising from 6 to 22 carbon atoms, and a heteroaryl group; - n is an integer from 1 to 4; - m is an integer from 1 to 6, preferably from 1 to 4; - formula (II) represents a condensed bicyclic aromatic radical comprising from 6 to 22 carbon atoms, and from 1 to 3 heteroatom(s) selected from the group consisting of: N, S and O; the OH group being in ortho position of the condensed bicyclic aromatic radical relative to the formula (III) radical. The present invention also concerns its uses, and light devices comprising them.



(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE,

SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— *with international search report (Art. 21(3))*

Molecules presenting dual emission properties**[Field of the Invention]**

The present invention relates to new molecules exhibiting dual emission properties, and more particularly white light emission properties, and their method of preparation.

The present invention also concerns their applications, notably as fluorescent probes in ratiometric detection, or white light emitting sources.

[Background of the Invention]

Fluorescent probes are typically used for qualitative and/or quantitative titrations in various fields such as immunology, molecular biology, medical diagnostic.... An ideal condition for a compound to be used as fluorescent probe, and thus allow the titration of a target analyte, is to display dual emission properties varying depending upon the conditions (presence or not of the analyte, pH...). Such compounds allow, for example, ratiometric titrations leading to the determination of the analyte concentration, whatever the fluorescent probe concentration.

In the field of luminescent devices, the use of compounds having dual emission properties can lead to the production of polychromatic fluorescence such as white light, without requiring several polychromatic emitters.

Only few systems using a single molecule are known to exhibit dual emission.

However, dual emission, and more particularly white light emission, from a single molecule is an important chemical target because of the possibility of innovative applications to new classes of displays and light sources, such as low-cost, large-area flat-panel displays. Most of the white organic light-emitting devices (WOLEDs) reported so far relied on the use of a combination of several organic components that emit different colors of light (e.g. red/blue/green luminophores) to cover the visible range from 400 to 700 nm.

Therefore, the search for new molecules that can exhibit dual emission properties, and more particularly white light emission properties, is of obvious interest and importance.

[Aim of the Invention]

One aim of the present invention is to provide new compounds with dual emission properties, more particularly in solution and/or in solid state.

Another aim of the present invention is to provide new white light emitting compounds.

One aim of the present invention is to provide new compounds displaying broad and tunable dual emission.

The present invention also aims to provide such compounds with good luminescent properties, such as fluorescent or electroluminescent properties.


5 The present invention aims to provide such compounds with acceptable quantum yields.

The present invention also aims to provide devices for ratiometric detection.

The present invention also aims to provide devices emitting white light.

10 [Description of the Invention]

The present invention concerns a compound of formula (I):




15 wherein:

- A represents an electron-withdrawing group;
- D represents an electron-donating group;
- X is selected from the group consisting of: O, S and NR, wherein R is selected from the group consisting of: H, an alkyl group preferably comprising from 1 to 20 carbon atoms, an aryl group preferably comprising from 6 to 22 carbon atoms, and a heteroaryl group;


- n is an integer from 1 to 4;

- m is an integer from 1 to 6, preferably from 1 to 4;




- represents a condensed bicyclic aromatic radical comprising from 6 to 22 carbon atoms, and optionally from 1 to 3 heteroatom(s) selected from the group consisting of: N, S and O;

the OH group being in ortho position of the condensed bicyclic aromatic radical relative to




The present invention concerns a compound of formula (I):

3




wherein:

- 5 - A represents an electron-withdrawing group;
- D represents an electron-donating group;
- X is selected from the group consisting of: O, S and NR, wherein R is selected from the group consisting of: H, an alkyl group preferably comprising from 1 to 20 carbon atoms, an aryl group preferably comprising from 6 to 22 carbon atoms, and a heteroaryl group;
- 10 - n is an integer from 1 to 4;
- m is an integer from 1 to 6, preferably from 1 to 4;




- represents a condensed bicyclic aromatic radical comprising from 6 to 22 carbon atoms, and from 1 to 3 heteroatom(s) selected from the group consisting of: N, S and O;
- 15 the OH group being in ortho position of the condensed bicyclic aromatic radical relative to




In one embodiment, in the compound of formula (I):

- 20 is not a quinoline, in particular is not :



In one embodiment, the compound of formula (I) is not the following compound:

4



In one particular embodiment, in the formula (I) above-mentioned, X is O.


In one particular embodiment, in the formula (I) above-mentioned, X is NH.

5 In one particular embodiment, in the formula (I) above-mentioned, X is NR, wherein R is an alkyl group preferably comprising from 1 to 20 carbon atoms.


In one particular embodiment, in the formula (I) above-mentioned, X is NR, wherein R is an aryl group preferably comprising from 6 to 22 carbon atoms.

In one particular embodiment, in the formula (I) above-mentioned, X is NR, wherein
10 R is a heteroaryl group preferably comprising from 6 to 22 atoms.


In one particular embodiment, in the formula (I) above-mentioned, X is S.




In one embodiment, in the formula (I) above-mentioned,
15 represents a condensed bicyclic aromatic radical comprising from 6 to 22 carbon atoms, preferably 8 carbon atoms, and 1 heteroatom selected from the group consisting of: N, S and O, preferably O.



In particular, in the formula (I) above-mentioned,
represents a condensed bicyclic aromatic radical comprising from 6 to 22 carbon atoms, preferably 8 carbon atoms, and 1 heteroatom selected from the group consisting of: S and O.



In particular, represents



20

In one embodiment, in the formula (I) above-mentioned, n is 1 or 2.

In one embodiment, in the formula (I) above-mentioned, m is 1 or 2.

For sake of clarity, electron-withdrawing group A is not an alkyl group, such as for example tertio-butyl. Thus, compounds 9 and 10 disclosed in Massue et al., "Fluorescent 2-(2'-hydroxybenzofuran)benzoxazole borate complexes: synthesis, optical properties and theoretical calculations", Tetrahedron Letters, 2014, 55, 4136-41-40" do not fall within the compounds of formula (I) of the present invention.

In one embodiment, the electron-donating group D is selected from the group consisting of:

- O⁻;
 - 10 - OR_a, wherein R_a is H or an alkyl group preferably comprising from 1 to 20 carbon atoms, in particular OMe;
 - NR_bR_c, wherein R_b and R_c are, independently of each other, selected from the group consisting of:
 - o H;
 - 15 o alkyl group preferably comprising from 1 to 20 carbon atoms, preferably from 1 to 4 carbon atoms; and
 - o aryl group preferably comprising from 6 to 22 carbon atoms, preferably a phenyl group;
 - NHC(O)R_d, wherein R_d is selected from the group consisting of:
 - 20 o alkyl group preferably comprising from 1 to 20 carbon atoms preferably from 1 to 4 carbon atoms; and
 - o aryl group preferably comprising from 6 to 22 carbon atoms, preferably a phenyl group;
 - an aryl group preferably comprising from 6 to 22 carbon atoms, preferably a phenyl
 - 25 group; and
 - an alkyl group preferably comprising from 1 to 20 carbon atoms;
- said alkyl and aryl groups being optionally substituted with at least one electron-donating group, preferably selected from: O⁻, OR_a, NR_bR_c and -NHC(O)R_d, R_a, R_b, R_c and R_d being as defined according to the present invention.

30

In one embodiment, the electron-donating group D is selected from the group consisting of:

- O⁻;
- OR_a, wherein R_a is H or an alkyl group preferably comprising from 1 to 20 carbon
- 35 atoms;
- NHC(O)R_d, wherein R_d is selected from the group consisting of:

6

- alkyl group preferably comprising from 1 to 20 carbon atoms preferably from 1 to 4 carbon atoms; and
- aryl group preferably comprising from 6 to 22 carbon atoms, preferably a phenyl group;

5 - an aryl group preferably comprising from 6 to 22 carbon atoms, preferably a phenyl group; and

 - an alkyl group preferably comprising from 1 to 20 carbon atoms;


said alkyl and aryl groups being optionally substituted with at least one electron-donating group, preferably selected from: O^- , OR_a , NR_bR_c and $-NHC(O)R_d$, R_a , R_b , R_c and R_d being as defined according to the present invention.

10

In one embodiment, the electron-donating group D comprises a π -electron conjugated chain comprising for example one or several alkynyl or alkenyl groups, the conjugation being possible by means of alternating alkenylene or alkynylene groups. Such π -electron conjugated chain allows the delocalization of π -electrons across all the adjacent aligned p-orbitals. The presence of such π -electron conjugated chain inside the group D does not change the electron-donating feature of said group D.

15

For example, an electron-donating group D comprising a π -electron conjugated




20

In one embodiment, the electron-donating group D is an aryl group comprising from 6 to 22 carbon atoms, preferably a phenyl group, optionally substituted with at least one electron-donating group preferably selected from: O^- , OR_a , NR_bR_c and $-NHC(O)R_d$, R_a , R_b , R_c and R_d being as defined according to the present invention.

In one embodiment, the electron-donating group D has the following formula (A):


25



wherein Y is selected from: O^- , OR_a , NR_bR_c and $-NHC(O)R_d$, R_a , R_b , R_c and R_d being as defined above.


In particular, the electron-donating group D is:

30




7

In particular, the electron-donating group D is:




In one embodiment, the electron-donating group D has the following formula (B):



5 wherein Y_1 , Y_2 and Y_3 represent, independently of each other, OR_a , R_a being as defined above.

In particular, the electron-donating group D is:




10 In one embodiment, the electron-withdrawing group A is selected from the group consisting of:

- halogen such as Br, Cl, F or I;
- $C(O)R_e$, R_e being selected from the group consisting of:
 - o Cl;
 - o H;
 - 15 o OR_f , R_f being H or an alkyl group preferably comprising from 1 to 20 carbon atoms; and
 - o an alkyl group preferably comprising from 1 to 20 carbon atoms;
- NO_2 ;
- $SO_2NR_gR_h$, R_g and R_h representing, independently of each other, an alkyl group preferably comprising from 1 to 20 carbon atoms or an aryl group preferably comprising from 6 to 22 carbon atoms;
- CN;
- CF_3 ;
- alkyl group, preferably comprising from 1 to 20 carbon atoms, substituted with at least one group selected from: halogen such as F, NO_2 , CN, $C(O)R_e$, $SO_2NR_gR_h$ and CF_3 , wherein R_e , R_g and R_h are as defined above, said alkyl being optionally substituted with a heteroaryl, said heteroaryl being optionally substituted with a substituted heteroaryl; aryl

group, preferably comprising from 6 to 22 carbon atoms, substituted with at least one group selected from: halogen such as F, NO₂, CN, C(O)R_e, SO₂NR_gR_h and CF₃, wherein R_e, R_g and R_h are as defined above;

- S(O)₂-W, W being a heteroaryl being optionally substituted with a substituted heteroaryl;

- SO₃H;



- a radical having the following formula : ; and

- N⁺R_iR_jR_kR_l, wherein R_i, R_j, R_k, and R_l are, independently of each other, H or an alkyl group preferably comprising from 1 to 20 carbon atoms, said alkyl group being optionally substituted with at least one group selected from: halogen such as F, NO₂, CN, C(O)R_e, SO₂NR_gR_h and CF₃, wherein R_e, R_g and R_h are as defined above.

In one embodiment, the electron-withdrawing group A is selected from the group consisting of:

- halogen such as Br, Cl, F or I;

- C(O)R_e, R_e being selected from the group consisting of:

o Cl;

o H;

o OR_f, R_f being H or an alkyl group preferably comprising from 1 to 20 carbon atoms; and

o an alkyl group preferably comprising from 1 to 20 carbon atoms;

- NO₂;

- SO₂NR_gR_h, R_g and R_h representing, independently of each other, an alkyl group preferably comprising from 1 to 20 carbon atoms or an aryl group preferably comprising from 6 to 22 carbon atoms;

- CN;

- CF₃;

- alkyl group, preferably comprising from 1 to 20 carbon atoms, substituted with at least one group selected from: halogen such as F, NO₂, CN, C(O)R_e, SO₂NR_gR_h and CF₃, wherein R_e, R_g and R_h are as defined above;

- aryl group, preferably comprising from 6 to 22 carbon atoms, substituted with at least one group selected from: halogen such as F, NO₂, CN, C(O)R_e, SO₂NR_gR_h and CF₃, wherein R_e, R_g and R_h are as defined above;

- SO₃H; and


- $N^+R_iR_jR_kR_l$, wherein R_i , R_j , R_k , and R_l are, independently of each other, H or an alkyl group preferably comprising from 1 to 20 carbon atoms, said alkyl group being optionally substituted with at least one group selected from: halogen such as F, NO_2 , CN, $C(O)R_e$, $SO_2NR_gR_h$ and CF_3 , wherein R_e , R_g and R_h are as defined above.

5

In one embodiment, the electron-withdrawing group A comprises a π -electron conjugated chain comprising for example one or several alkynyl or alkenyl groups, the conjugation being possible by means of alternating alkenylene or alkynylene groups. Such π -electron conjugated chain allows the delocalization of π -electrons across all the adjacent aligned p-orbitals. The presence of such π -electron conjugated chain inside the group A does not change the electron-withdrawing feature of said group A.

10

For example, an electron-withdrawing group A comprising a π -electron conjugated



15

In one embodiment, the electron-withdrawing group A is $-C(O)H$.

In one embodiment, the electron-withdrawing group A is $-C(O)OH$.

In one embodiment, the electron-withdrawing group A is $-C(O)Cl$.

In one embodiment, the electron-withdrawing group A is NO_2 .

In one embodiment, the electron-withdrawing group A is NH_4^+ .

20

In one embodiment, the electron-withdrawing group A is an aryl group comprising from 6 to 22 carbon atoms substituted with at least one nitro group, preferably a phenyl group substituted with at least one nitro group.

In one embodiment, the electron-withdrawing group A is an aryl group comprising from 6 to 22 carbon atoms substituted with at least one fluorine atom, preferably a phenyl group substituted with at least one fluorine atom.

25

In one particular embodiment, the electron-withdrawing group A is CN.

In one particular embodiment, the electron-withdrawing group A is CF_3 .


In one particular embodiment, the electron-withdrawing group A is $-C(O)OMe$.

In one particular embodiment, the electron-withdrawing group A is F.


30

In one particular embodiment, the electron-withdrawing group A is Br.


In one embodiment, the electron-withdrawing group A is selected from the group consisting of the following radicals:



and



5 The present invention also relates to a compound of formula (II):



wherein:

- R₁, R₂, R₃ and R₄ represent, independently of each other, H or an electron-withdrawing group A;

10 - R₅, R₆, R₇ and R₈ represent, independently of each other, H or an electron-donating group D;

or R₅ and R₆ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom selected from the group consisting of: N, O and S, and said cycle being optionally substituted by at least one electron-donating group D;

15

or R₆ and R₇ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom selected from the group consisting of: N, O and S, and said being optionally substituted by at least one electron-donating group D;

20

or R₇ and R₈ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom selected from the group consisting of: N, O and S, and said being optionally substituted by at least one electron-donating group D;

5 - X, A and D being as defined according to the present invention;

at least one of R₅ and R₆, or R₆ and R₇, or R₇ and R₈, form said at least partially unsaturated cycle;

at least one of R₁, R₂, R₃ and R₄ is an electron-withdrawing group A; and

said compound of formula (II) comprising at least one electron-donating group D.

10

In one embodiment, in the formula (II) above-mentioned, X is O.

In one embodiment, in the formula (II) above-mentioned, X is NH.

In one particular embodiment, in the formula (II) above-mentioned, X is NR, wherein R is an alkyl group preferably comprising from 1 to 20 carbon atoms.

15 In one particular embodiment, in the formula (II) above-mentioned, X is NR, wherein R is an aryl group preferably comprising from 6 to 22 carbon atoms.

In one particular embodiment, in the formula (II) above-mentioned, X is NR, wherein R is a heteroaryl group.

In one embodiment, in the formula (II) above-mentioned, X is S.

20 In one embodiment, in the formula (II) above-mentioned, R₂ is an electron-withdrawing group A.

In one embodiment, in the formula (II) above-mentioned, R₁, R₃ and R₄ are H.

In one embodiment, in the formula (II) above-mentioned, R₁ is an electron-withdrawing group A.

25 In one embodiment, in the formula (II) above-mentioned, R₄ is Br.

In one embodiment, in the formula (II) above-mentioned, R₅ and R₈ are H.

In one embodiment, in the formula (II) above-mentioned, R₅ and R₆ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom selected from the group consisting of: N, O and S, and said being optionally substituted by at least one electron-donating group D. In particular, R₅ and R₆ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising 5 atoms, said cycle comprising one oxygen atom and being substituted with one electron-donating group D.


35 In one embodiment, in the formula (II) above-mentioned, R₇ and R₈ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising

from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom selected from the group consisting of: N, O and S, and said being optionally substituted by at least one electron-donating group D. In particular, R₇ and R₈ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising 5 atoms,
 5 said cycle comprising one oxygen atom and being substituted with one electron-donating group D.

In one embodiment, in the formula (II) above-mentioned, R₆ and R₇ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom
 10 selected from the group consisting of: N, O and S, and said being optionally substituted by at least one electron-donating group D. In particular, R₆ and R₇ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising 5 atoms, said cycle comprising one oxygen atom and being substituted with one electron-donating
 group D.

15

The present invention also relates to a compound having the following formula (III):



wherein:

- R₉ and R₁₀ represent, independently of each other, H or an electron-donating group
 20 D;
- R₁, R₂, R₃, R₄, R₅, R₈, X and D being as defined according to the present invention.

The compound of formula (III) corresponds notably to a compound of formula (II) wherein R₆ and R₇ form, together with the carbon atoms carrying them, a furan substituted
 25 with R₉ and R₁₀.

In one embodiment, in the formula (III) above-mentioned, X is O.

In one embodiment, in the formula (III) above-mentioned, X is NH.

In one particular embodiment, in the formula (I) above-mentioned, X is NR, wherein
 30 R is an alkyl group preferably comprising from 1 to 20 carbon atoms.

In one particular embodiment, in the formula (I) above-mentioned, X is NR, wherein R is an aryl group preferably comprising from 6 to 22 carbon atoms.

In one particular embodiment, in the formula (I) above-mentioned, X is NR, wherein R is a heteroaryl group.

5 In one embodiment, in the formula (III) above-mentioned, X is S.

In one embodiment, in the formula (III) above-mentioned, R₂ is an electron-withdrawing group A.

In one embodiment, in the formula (III) above-mentioned, R₁ is an electron-withdrawing group A.

10 In one embodiment, in the formula (III) above-mentioned, R₄ is Br.


In one embodiment, in the formula (III) above-mentioned, R₁, R₃ and R₄ are H.

In one embodiment, in the formula (III) above-mentioned, R₅ and R₈ are H.

In one embodiment, in the formula (III) above-mentioned, R₉ is H.


In one embodiment, in the formula (III) above-mentioned, R₁₀ is an electron-donating
15 group D as defined according to the invention.

In one embodiment, the compound of formula (III) corresponds to a compound of formula (III-a) having the following formula:



20 R₁, R₂, R₃, R₄, R₅, R₈, R₉, R₁₀ and D being as defined according to the invention.


The present invention also relates to a compound having the following formula (IV):



25 wherein:

- R₁₁ represents H or an electron-donating group D;
- R₁, R₂, R₃, R₄, R₅, R₈, X and D being as defined according to the invention.

The compound of formula (IV) corresponds notably to a compound of formula (III)




wherein R₉ is H, and R₁₀ is

- 5 In one embodiment, in the formula (IV) above-mentioned, X is O.
 In one embodiment, in the formula (IV) above-mentioned, X is NH.
 In one particular embodiment, in the formula (IV) above-mentioned, X is NR, wherein R is an alkyl group preferably comprising from 1 to 20 carbon atoms.
 In one particular embodiment, in the formula (IV) above-mentioned, X is NR,
 10 wherein R is an aryl group preferably comprising from 6 to 22 carbon atoms.
 In one particular embodiment, in the formula (IV) above-mentioned, X is NR, wherein R is a heteroaryl group.
 In one embodiment, in the formula (IV) above-mentioned, X is S.
 In one embodiment, in the formula (IV) above-mentioned, R₂ is an electron-
 15 withdrawing group A as defined according to the invention.
 In one embodiment, in the formula (IV) above-mentioned, R₁, R₃ and R₄ are H.
 In one embodiment, in the formula (IV) above-mentioned, R₅ and R₈ are H.
 In one embodiment, in the formula (IV) above-mentioned, R₁₁ is an electron-donating
 group D as defined according to the invention.

20


The present invention also relates to a compound having the following formula (V):



wherein:

- R' and R'' represent, independently of each other, H or an alkyl group preferably
 25 comprising from 1 to 20 carbon atoms;
 - R₃, R₅, R₈ and X being as defined according to the invention.


The present invention also relates to a compound having the following formula (IV-bis):



wherein:


- R₁₂, R₁₃ and R₁₄, independently of each other, represents an electron-donating group D;
- 5 - R₁, R₂, R₃, R₄, R₅, R₈, X and D being as defined according to the invention.



The present invention also relates to a compound having the following formula (IV-bis-1):










- 10 wherein R₁, R₂, R₃, R₄, R₅, R₈, X and D being as defined according to the invention.

In one embodiment, among the compounds of formulae (I), (II), (III), (IV), (IV-bis), (IV-bis-1) and (V), mention may be made to the following ones:






5





The present invention also relates to the process of preparation of a compound of formula (I) above-mentioned, said process comprising reacting a compound of formula (VI):

5



with a compound of formula (VII):



wherein , A, X, D, n and m are as defined according to the invention.

10


In one embodiment, the reaction between the compound of formula (VI) and the compound of formula (VII) is carried out in presence of a base, KCN, and a boronic acid, such as for example $\text{PhB}(\text{OH})_2$. In a particular embodiment, the reaction is carried out in a polar solvent, such as for example methanol, preferably at room temperature (about 25°C), notably under atmospheric pressure.

15


In another embodiment, the reaction between the compound of formula (VI) and the compound of formula (VII) is carried out in a polar solvent, such as for example ethanol, under reflux. Then, 2,3-dichloro-5,6-dicyano-1,4-benzoquinone is added to the reaction mixture, and the reaction medium was mixed at room temperature (about 25°C).

20

In one embodiment, in the process above-mentioned, the compound of formula (VI) is a compound of formula (VI-a):




and the compound of formula (VII) is a compound of formula (VII-a):




wherein R₁, R₂, R₃, R₄, R₅, R₈, R₉, R₁₁ are as defined according to the invention.

In one embodiment, the compound of formula (VII-a) results from the reaction of a
5 compound of formula (VIII-a):



with a compound of formula (IX-a):



wherein R₅, R₈ and R₁₁ are as defined above, *via* a Sonogashira cross-coupling, preferably carried out in presence of CuI, PdCl₂(PPh₃)₂ and a base.

15 [Definitions]

As used herein, the term "condensed bicyclic aromatic radical" means a radical having two aromatic rings which are fused to each other. Examples of such radical are benzofuran, benzothiophene, indene, purine, isoquinoline, quinoline, indole, naphthalene. In particular, the condensed bicyclic aromatic radical is benzofuran.

20

The charge distribution in a molecule is typically discussed with respect to two interacting effects:

- an inductive effect, which is a function of the electronegativity differences that exist between atoms (and groups); and
- 25 - a resonance effect, in which electrons move in a discontinuous fashion between parts of a molecule.

Typically, the strength of donor/acceptor couple can be determined by *ab initio* calculation of density difference between excited state and fundamental state. The common way to define the EDG (electron-donating group) or EWG (electron-withdrawing group) character of a function is to use the couple between the function and the hydrogen (H). The CT (charge transfer) is determined as the distance separating the barycenters of density depletion and gain following the electronic transitions. This CT distance will be correlated to the relative stability of the two tautomeric forms computed as relative free energies.

As used herein, the term "electron-withdrawing group" is also called "electron acceptor" which has its electronic density rising by going from the fundamental state to the excited state. Such term denotes the tendency of a substituent to attract valence electrons from neighboring atoms or atoms on the pi-delocalized system, *i.e.*, the substituent is electronegative with respect to neighboring atoms or atoms on the pi-delocalized system.

As used herein, the term "electron-donating group" is also called "electron donor" which has its electronic density decreasing by going from the fundamental state to the excited state. Such term denotes the tendency of a substituent to provide valence electrons to neighboring atoms or atoms on the π -delocalized system, *i.e.*, the substituent is electropositive with respect to neighboring atoms.

As used herein, the term "alkyl" means a saturated aliphatic hydrocarbon group which may be straight or branched having preferably from 1 to 20 carbon atoms in the chain, optionally comprising at least one unsaturation. Preferred alkyl groups have 1 to 12 carbon atoms in the chain. For example, the alkyl group is a methyl, a propyl, a butyl, a tertibutyl, a pentyl or an isopropyl. Such alkyl group may include substituents. Said alkyl can also be a cyclic alkyl.

As used herein, the term "aryl" refers to an aromatic monocyclic or bicyclic hydrocarbon ring system having preferably 6 to 22 carbons, more preferably from 6 to 10 carbon atoms. Examples of aryl moieties include, but are not limited to, phenyl, naphthyl, and anthracenyl. In case of electron-attracting group, substituents are preferably selected from the group consisting of those defined previously for group A. In case of electron-donating group, substituents are preferably selected from the group consisting of those defined previously for group D.

As used herein, the term "heteroaryl" refers to an aromatic 5 to 8 membered monocyclic, 8 to 12 membered bicyclic, having 1 to 3 heteroatoms if monocyclic, 1 to 6 heteroatoms if bicyclic, said heteroatoms being selected from O, N, or S. Examples of heteroaryl groups are thiophene, pyridine, furan, pyrrole, benzofuran, benzoxazole.

As used herein, the term "substituents" refers to a group "substituted" on an alkyl, aryl, or heteroaryl group at any atom of that group. Suitable substituents include, without limitation, alkyl, alkenyl, alkynyl, alkoxy, halo, ester, hydroxy, cyano, nitro, amino, dialkylamino, SO₃H, perfluoroalkyl, perfluoroalkoxy, amido, sulfonamido, aryl, heteroaryl, heterocyclyl, and cycloalkyl. The preferred substituents on alkyl, aryl or heteroaryl groups are OH, amino, dialkylamino, alkoxy, halo, perfluoroalkyl such as CF₃ and hereoaryl.

As used herein, the term "alkylene" means a divalent saturated aliphatic hydrocarbon radical, which may be linear or branched, preferably having from 1 to 24 carbon atoms in the chain.

As used herein, the term "alkenylene" means a divalent linear or branched hydrocarbon radical, preferably having 2 to 6 carbon atoms and having at least one double bond, and includes for example ethenylene-


As used herein, the term "alkynylene" means a divalent linear or branched hydrocarbon radical, preferably having 2 to 6 carbon atoms and having at least one triple bond. Preferred alkynylene groups include ethynylene (-C≡C-).

As used herein, the term "an at least partially unsaturated cycle" means that the cycle is partially unsaturated or fully unsaturated. Example of fully unsaturated cycle is phenyl. Examples of at least partially unsaturated cycle are furan, thiophene, pyrrole, phenyl, thiazole, imidazole, preferably said cycle being furan. Such aryl group may include substituents.

As used herein, the compounds of formula (I), (II), (III), (IV) or (V) are also called "emitters" or even "organic emitters".


As used herein, the term "dual emission" means that upon photoexcitation, for example at λ_{ex} (excitation wavelength) a compound will emit two distinct emission band λ_{emE} and λ_{emK} corresponding respectively to E* and K* states. .

As used herein, the term "E*" means the enol at its excited state of the compounds according to the invention, having notably the following formula:



As used herein, the term "K*" means the keto at its excited state of the compounds according to the invention, having notably the following formula:

21



As used herein, the term “fluorophore”, also called “fluorochrome” or “chromophore”, is a fluorescent chemical compound that can re-emit light upon light excitation.

5 As used herein, the term “protic solvent” means a solvent that include at least one hydrogen atom that is capable of being released in the form of a proton.

As used herein, the term “aprotic solvent” means a solvent that is considered as not being protic. In particular, such solvents are not suitable for releasing a proton or for accepting one. Examples of aprotic solvent are toluene, dimethylformamide, acetone, dimethyl sulfoxide.

10

As used herein, the term “compound according to the invention”, or “compound of the invention” corresponds to a compound of formulae (I), (II), (III), (IV), (V) or their mixtures thereof.

As used herein, the term “transparent” typically means that a person may read alphanumeric characters even the film is placed between said person and said alphanumeric characters.

15

Reference throughout the specification to “one embodiment”, “another embodiment”, “an embodiment”, and so forth, means that a particular element (e.g., feature, structure, and/or characteristic) described in connection with the embodiment is included in at least one embodiment described herein, and may or may not be present in other embodiments. In addition, it is to be understood that the described elements may be combined in any suitable manner in the various embodiments.

20

As used herein, the term “dielectric constant of a solvent” is a measure of its polarity. The higher the dielectric constant of a solvent, the more polar it is.

25 As used herein, the term “conductive polymer” means organic polymers that are able to transport charges (electrons and holes).

As used herein, the term “organic semiconductor polymer” means a polymer of an organic compound capable of exhibiting the properties of a semiconductor.

30 [Uses]

The present invention also relates to a solution comprising at least one compound according to the invention, and a solvent.

Preferably, the solvent is selected from the group consisting of: solvents with low dielectric constant and solvents with high dielectric constant.

In particular, solvents with low dielectric constant are selected from the group consisting of: toluene, cyclohexane, dichloromethane and mixtures thereof.

5 In particular, solvents with high dielectric constant are selected from the group consisting of: alcohols, dimethylsulphoxide, water, acetone, acetonitrile and mixtures thereof.

The present invention also relates to a solid material (S) comprising, or consisting of, at least one compound according to the invention.

10 In one embodiment, the solid material (S) consists of at least one compound according to the invention. In this case, the at least one compound according to the invention is in a solid state, such as for example in powder form.

In one specific embodiment, said solid material or compound according to the invention is a crystal, for example a monocrystal.

15 In one embodiment, the solid material further comprises an inorganic solid for example selected from the group consisting of: KBr matrix pellets, alumine, silica, zeolithe, clays, titanium oxide and titanium silicium. In particular, the at least one compound according to the invention is combined with or introduced into said inorganic solid.

20 In particular, the at least one compound according to the invention is dispersed as a solid powder into KBr matrix pellets.

The invention also relates to a material (M) comprising at least one compound according to the invention, and at least one polymer and/or polymeric material and/or an organic matrix, said organic matrix may optionally comprise an inorganic material such as dopants. In one embodiment, the compound(s) according to the invention is(are)
25 encapsulated in said polymer and/or polymeric material and/or organic matrix.

In one embodiment, the material (M) comprises at least one compound according to the invention, and at least one organic matrix.

In one embodiment, the material (M) is an organic semiconductor material.

30 In one embodiment, the material (M) is a plastic material, especially a transparent plastic material. For example said plastic material is a plastic film, especially a transparent plastic film.

In one embodiment, the material (M) is a conductive plastic.

The present invention thus also relates to a film, especially a transparent film, comprising at least one compound according to the invention.

35 There is no particular limitation on the method to produce a film. A film according to the invention generally comprises at least one polymer and/or polymeric material, and at

least one compound according to the invention. Additional elements may be present in the film, without particular limitation.

According to the invention, the at least one compound according to the invention may be present in the film at various concentrations. Typically the concentration by weight of the at least one compound according to the invention is more than 0.01% with respect to the weight of the final film (w/w). This concentration may range from 0.05% to 90% (w/w). In one embodiment, the concentration of one or more compounds according to the invention is at least 0.5% (w/w).

Advantageously, the emission spectra of the fluorescent film can be tuned by changing the concentrations of the compound(s) according to the invention in the film. The invention therefore, relates to a dual light emitting film, more particularly to a white-light emitting film.

In one embodiment, the polymer is a conductive polymer.

In one embodiment, the polymer is an organic semiconductor polymer.

In one embodiment, the polymer is selected from the group consisting of: polymers containing acrylate-containing units, for example polyalkylacrylate, polyalkylmethacrylate especially polymethylmethacrylate (PMMA) ; polymers containing siloxane units, for example polyalkylsiloxane, especially polydimethylsiloxane (PDMS), polymers containing hydroxide groups-containing units, for example polyvinyl alcohol (PVA); polystyrene (PS); and any mixture thereof. In particular, the polymer is a mixture of PMMA and PS.

In one embodiment, the polymeric material is cellulose or latex.

A film can be prepared for example from a liquid phase containing at least one polymer and/or polymeric material suitable for forming a film and at least one compound according to the invention. A film may be prepared for example from such a liquid phase by evaporation, preferably slow evaporation, of the liquid phase to yield a film. Solvents of polymer and/or polymeric materials for preparing such a liquid phase are typically organic solvents but may also consist of or contain water. Typically, the liquid phase is a solution containing at least one polymer and/or polymeric material suitable for forming a film and at least one compound according to the invention. The liquid phase may also be a dispersion or an emulsion. Evaporation may be performed for example at room temperature in a container. If needed, the fluorescent film maybe subjected to further solvent elimination. For example the fluorescent film may be dried under vacuum, to remove remaining solvent.

Films can be shaped according to the techniques of the art. The shape of the transparent fluorescent films can be for example controlled by the shape of the container (glass sample tube: cylinder; glass plate substrate: quadrangle). Films can present a very

wide range of thicknesses, typically from 10 nanometers (nm) to 1000 micrometers (μm) or more, preferably from 20 nm to 200 μm .

In one embodiment, the invention relates to a PMMA/PS film containing at least one
5 compound according to the invention, for example at a concentration ranging from 0.5% (w/w) by weight with respect to the total film weight.


Light emission of the film may be obtained by excitation of the films by a physical stimulus, such as an electromagnetic radiation, typically a light radiation, a magnetic radiation or an electric radiation.

10 Upon photoexcitation, the inventors advantageously found that the compounds exhibit intense dual emission with contribution from the enol (E^*) and the keto (K^*) emission, K^* being formed through excited state intramolecular proton transfer (ESIPT).

The ratio of dual emission intensity R_{DU} may be defined in the present invention by the ratio between the intensity of the λ_{max} (maximum emission wavelength) of the less
15 intense emission band over the intensity of the λ_{max} of the more intense emission band. For example, depending of the compound of the invention, the less intense emission band may be the one of the Enol form (E^*) or the one of the Keto form (K^*).

According to the invention, the compounds of the invention present significant dual emission properties when R_{DU} is higher than 0.15, preferably higher than 0.2, and more
20 preferably higher than 0.5. In particular, R_{DU} is higher than 0.8.

Typically, ESIPT is a photophysical process that features a photoinduced proton transfer in the excited-state of specific π -conjugated compounds. The following scheme 1 is a representation of the ESIPT process in the compounds of the invention:



In particular in ES IPT process, upon absorption of light, a very fast
 5 phototautomerization process occurs (in the order of a sub-picosecond timescale) leading
 either to the sole emission of the tautomer or to a dual emission if the proton transfer is
 not quantitative. As a result of this sizeable reorganization of the molecular structure upon
 photoexcitation, large Stokes' shifts may be obtained due to the red-shifted emission of
 the keto tautomer (K^* , in the case of a keto-enol tautomerism) as compared to that of the
 10 normal enol form (E^*).

In particular, the inventors advantageously found that the ratio of emission intensity
 R_{DU} is tunable. The compounds of the invention advantageously display broad and
 tunable dual emission.

The compounds according to the invention advantageously display dual emission,
 15 and more particularly white light emission, as a single compound in solution and/or in the
 solid state, and/or when incorporated in a material, such as a polymeric film or a solid
 material.

More particularly, the inventors found that when the compounds of the invention are
 in solution, they display dual emission in different type of solvents, such as protic and
 20 aprotic solvents.

Thus, the compounds according to the invention advantageously exhibit good luminescent properties, such as for example fluorescent or electroluminescent properties.

According to the CIE 1931 XYZ color space, created by the Commission Internationale de l'éclairage (CIE) in 1931, the CIE chromaticity coordinates for pure white light are (0.33, 0.33).

The compounds according to the invention provide an acceptable quantum yield, which is defined as the quotient of the number of photons emitted divided by the number of photons absorbed. The quantum yield represents the emission efficiency of a given compound.

10 An acceptable quantum yield is considered to be over 1.9%, preferably over 5%, and more preferably at least 10%. In particular, the quantum yield of the compounds of the invention is at least 15%.

In one embodiment, when the compounds of the invention are in solid-state, they exhibit a quantum yield higher than 7%, preferably at least 10%, and more preferably at least 20%.

Lifetime (τ) is defined as the average length of time for the molecules to decay from one state to another. When a molecule absorbs a photon of appropriate energy, a chain of photophysical events ensues, such as internal conversion, fluorescence, intersystem crossing, and phosphorescence, as shown in the Jablonski diagram. Each of the processes occurs with a certain probability, characterized by decay rate constants (k). Lifetime (τ) is reciprocally proportional to the rate of decay: $\tau = 1/k$. The lifetime can be considered as a state function because it does not depend on excitation wavelength.

The lifetime of a compound of the invention ranged typically from 0.2 to 10 nanoseconds, more specifically from 0.3 to 5 nanoseconds.

25 The present invention also relates to a light emitting device comprising at least one compound according to the invention, or a solid material (S) as defined according to the present invention or a material (M) as defined according to the present invention

In one embodiment, the light emitting device is a luminescence device or an electroluminescence device.

30 Examples of light emitting device are Organic leds (OLEDs).

In one embodiment, the light emitting device is a white light emitting device. Example of such device is WOLED (White organic light emitting diodes).

The present invention also relates to a device for ratiometric analysis comprising at least one compound according to the invention or a solid state material (S) as mentioned above or a material (M) as mentioned above.

The ratio of the optical signals (at two distinct wavelengths) may be used to monitor the association equilibrium and to calculate analyte concentrations. Ratiometric measurements eliminate distortions of data caused by photobleaching and variations in probe loading and retention, as well as by instrumental factors such as illumination stability.

The present invention also relates to the use of at least one compound according to the invention, or a solid state material (S) as defined according to the present invention or a material (M) as defined according to the present invention, as fluorescent probe, in particular for ratiometric analysis. The compound according to the invention are thus useful for medical applications.

The present invention also relates to the use of at least one compound according to the invention, or a solid state material (S) as defined according to the present invention or a material (M) as defined according to the present invention, for emitting white light.

The inventors have discovered that the compounds according to the invention, namely compounds of formulae (I), (II), (III), (IV) and (V), and materials comprising them (for example film or solid material), advantageously exhibit dual emitting properties, and more particularly white light emitting properties.

The compounds according to the invention may also be used as pigments or dyes, in particular in paints or textiles, notably for clothes. In particular, the compounds are used in liquid or solid form, such as in powder form.

In one embodiment, the compounds according to the invention are encapsulated, notably in a matrix, such as an organic or polymeric matrix.

In one embodiment, the compounds according to the invention are used as pigment for security inks.

The security inks are well known by the skilled person. Security inks are typically used for security applications such as banknotes, official identity documents (passports, identity cards, birth certificates ...), postage stamps, tax banderoles, security labels and product markings.

Typically, the security inks fulfil the role of security in addition to their coloring function. In particular, the security inks can be used as anti-infringement labelling for different type of products or documents. In this particular case, the labelled product/document may be easily authenticated. In particular, the security inks are used for invisibly print security images having multiple authentication features.

In one embodiment, the present invention relates to security inks comprising at least one compound according to the invention, in particular the compounds being encapsulated such as in a organic or polymeric matrix.

Figures

Figure 1 corresponds to the absorption (in grey) and emission spectra (in black) in various solvents for comparative compound 5. Such data were recorded at room temperature
5 (25°C). Only K* band appears.

Figure 2 corresponds to the absorption (in grey) and emission spectra (in black) in various solvents for comparative compound 6. Such data were recorded at room temperature (25°C). Only K* band appears.

Figure 3 corresponds to the absorption (in grey) and emission spectra (in black) in various
10 solvents for compound 7. Such data were recorded at room temperature (25°C).

Figure 4 corresponds to the absorption (in grey) and emission spectra (in black) in various solvents for compound 8. Such data were recorded at room temperature (25°C).

Figure 5 corresponds to the absorption (in grey) and emission spectra (in black) in various solvents for compound 9. Such data were recorded at room temperature (25°C).

15 Figure 6 corresponds to the absorption (in grey) and emission spectra (in black) in various solvents for compound 10. Such data were recorded at room temperature (25°C).

Figure 7 corresponds to the solid-state emission spectra of compounds 7 and 8 in KBr pellets. Such data were recorded at room temperature (25°C).

20 Figure 8 corresponds to the solid-state emission spectra of compounds 7 to 10 PMMA/PS films. Such data were recorded at room temperature (25°C) using an integration sphere.

The invention is described in the foregoing by way of non-limiting examples.

Examples

25 The temperature is 25°C, unless contrary indicated.

The pressure is atmospheric pressure (101325 Pa), unless contrary indicated.

General methods and equipment: All reactions were performed under a dry atmosphere of argon using standard Schlenk techniques. Dichloromethane were distilled over P₂O₅
30 under an argon atmosphere. Thin layer chromatography (TLC) was performed on silica gel or aluminium oxide (Al₂O₃) plates coated with fluorescent indicator. Chromatographic purifications were conducted using 40-63 µm silica gel. All mixtures of solvents are given in v/v ratio. The 300 (¹H), 400 (¹H), 75.46 (¹³C), 100.3 (¹³C) MHz NMR spectra were recorded at room temperature with perdeuterated solvents with residual protonated
35 solvent signals as internal references. Mass spectra were measured with a ESI-MS mass spectrometer. Electronic absorption and emission spectra were measured under ambient

conditions using commercial instruments Shimadzu UV3600 and Horiba Jobin-Yvon Fluoromax 4P. UV-Vis spectra were recorded using a dual-beam grating spectrophotometer with a 1 cm quartz cell. Fluorescence spectra were recorded with a spectrofluorimeter using typical Fluorescence software. Solvents for spectroscopy were spectroscopic grade and were used as received. Standard parameters were used for each instrument used. All fluorescence spectra were corrected from PM response. Luminescence lifetimes were measured on a spectrofluorimeter, using software with time-correlated single photon mode coupled to a Stroboscopic system. The excitation source was a laser diode (λ 320 nm). The instrument response function was determined by using a light-scattering solution (LUDOX). The fluorescence quantum yield (Φ_{exp}) was calculated from eq (1).

$$\Phi_{\text{exp}} = \Phi_{\text{ref}} \frac{I}{I_{\text{ref}}} \frac{\text{OD}_{\text{ref}}}{\text{OD}} \frac{\eta^2}{\eta_{\text{ref}}^2} \quad (\text{eq 1})$$

15

I denotes the integral of the corrected emission spectrum, OD is the optical density at the excitation wavelength, and η is the refractive index of the medium. The reference systems used were rhodamine 6G, $\Phi = 88\%$ in ethanol $\lambda_{\text{ex}} = 488$ nm for dyes emitting between 480 and 570 nm and quinine sulfate as reference $\Phi = 0.55$ in H_2SO_4 1N, $\lambda_{\text{ex}} = 366$ nm for dyes emitting below 480 nm.

20

All chemicals were received from commercial sources (Aldrich, Alfa Aesar or Acros) and used without further purification. 4-(dimethoxy)phenyl acetylene and 4-(di-ⁿbutylamino)phenyl acetylene were synthesized according to reported procedures (Feng et al., Org. Lett., 2013, 15, p. 936-939 and Miller et al., Synlett, 2004, 1, p. 165-168).


25

A. General procedure for the synthesis of salicylaldehydes (2), (3) and (4)


(1) and $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$ (5 % molar) were dissolved in THF/triethylamine (3/1). The resulting suspension was degassed with argon for 30 minutes before the appropriate 4-substituted phenylacetylene (3 eq.) was added followed by CuI (10 % molar). The resulting mixture was stirred overnight at 60°C. The dark solution was taken up in dichloromethane, washed with water, dried (MgSO_4) and concentrated *in vacuo*. The product was purified by silica gel chromatography (CH_2Cl_2 /Pet. Ether 1:1) to afford clean salicylaldehyde (2), (3) or (4) after evaporation of the solvents *in vacuo*.

35

30


Example 1: Synthesis of the intermediate 2,4-dihydroxy-5-iodobenzaldehyde (1):

2,4-Dihydroxy-5-iodobenzaldehyde (6g, 43 mmol.) was dissolved in 50 mL of acetic acid.
 5 A solution of iodine monochloride (8,46g, 52 mmol.) in 20 mL of acetic acid was added dropwise. The resulting mixture was stirred for 12 h at room temperature before it was poured into a saturated sodium thiosulfate solution (100 mL). The crude solution was extracted four times with ethyl acetate and the solvents were evaporated *in vacuo*. The crude residue was purified by silica gel chromatography eluting with CH₂Cl₂/Pet. Ether 1:1
 10 to CH₂Cl₂ 100% leading to compound **1** as white/beige powder (4.6 g, 40%). ¹H NMR (300MHz, d₆-acetone) δ (ppm): 11.07 (br s, 1H, OH), 10.73 (br s, 1H, OH), 9.76 (s, 1H, OH), 8.05 (s, 1H, CH Ar), 6.49 (s, 1H, CH Ar). ¹³C NMR (75MHz, d₆-acetone) δ (ppm): 195.1, 164.9, 164.5, 145.7, 118.2, 103.1, 73.2.

Example 2: 2-(4-(tert-butyl)phenyl)-6-hydroxybenzofuran-5-carbaldehyde (2)

Beige powder. Yield: 56 %. ¹H NMR (300MHz, CDCl₃) δ (ppm): 11.24 (s, 1H, OH), 9.92 (s, 1H, CHO), 7.70-7.76 (m, 3H, CH Ar), 7.07 (s, 1H, CH Ar), 6.92 (s, 1H, CH Ar), 6.48 (d, 2H, J=8.6Hz, CH Ar), 1.36 (s, 9H, C(CH₃)₃). ¹³C NMR (75MHz, CDCl₃) δ (ppm): 190.0, 160.3, 160.0, 157.7, 152.5, 127.0, 126.9, 126.0, 124.8, 123.3, 118.3, 100.2, 99.5, 35.0, 31.4. Anal. Calculated for C₁₉H₁₈O₃: C, 77.53; H, 6.16; Found C, 77.37; H, 5.97. EI-MS (m/z): 294.0.

25

Example 3: 6-hydroxy-2-(4-methoxyphenyl)benzofuran-5-carbaldehyde (3)


Pale yellow powder. Yield: 60 %. ¹H NMR (300MHz, CDCl₃) δ (ppm): 11.23 (s, 1H, OH), 9.92 (s, 1H, CHO), 6.67-7.76 (m, 3H, CH Ar), 6.97-7.05 (m, 3H, CH Ar), 6.83 (s, 1H, CH Ar), 3.87 (s, 1H, CH₃). ¹³C NMR (75MHz, CDCl₃) δ (ppm): 196.0, 160.6, 160.3, 160.1,

30

31

157.7, 126.6, 123.5, 122.7, 118.4, 114.6, 99.5, 99.2, 55.6. Anal. Calculated for $C_{16}H_{12}O_4$: C, 71.64; H, 4.51; Found C, 71.79; H, 4.82. EI-MS (m/z) : 268.0.

Example 4: 2-(4-(dibutylamino)phenyl)-6-hydroxybenzofuran-5-carbaldehyde (4)



5

Orange powder. Yield: 44 %. 1H NMR (300MHz, $CDCl_3$) δ (ppm): 11.24 (s, 1H, OH), 9.87 (s, 1H, CHO), 7.57-7.64 (m, 3H, CH Ar), 7.02 (s, 1H, CH Ar), 6.65-6.69 (m, 3H, CH Ar), 3.32 (m, 4H, $J=7.7$ Hz, CH_2), 1.56-1.66 (m, 4H, CH_2), 1.33-1.45 (m, 4H, CH_2), 0.99 (t, 6H, $J=7.4$ Hz, CH_3). ^{13}C NMR (75MHz, $CDCl_3$) δ (ppm): 196.0, 159.9, 158.8, 148.8, 126.4, 125.7, 124.0, 117.7, 116.4, 111.6, 99.1, 96.7, 50.8, 29.6, 20.5, 14.1. Anal. Calculated for $C_{23}H_{27}NO_3$: C, 75.59; H, 7.45; N, 3.83 ; Found C, 75.34; H, 7.28; N, 3.50. EI-MS (m/z) : 365.2.


15 **B. Synthesis of products**

Route A: To a solution of 4- t Bu-2-aminophenol in absolute ethanol was added salicylaldehyde ((2), (3) or (4)) (1eq.). The mixture was refluxed for 5 h until an orange to red precipitate formed. After cooling down, the precipitate was filtered and redissolved in dry dichloromethane before 2,3-dichloro-5,6-dicyano-1,4-benzoquinone (DDQ) (1.2 eq.) was added as a concentrated dichloromethane solution. The resulting dark mixture was stirred at room temperature overnight. After solvent evaporation, the crude residue was purified by silica gel chromatography eluting with CH_2Cl_2 /Pet. Ether 1:1.


Route B: To a solution of 4-substituted 2-aminophenol in methanol was added the appropriate salicylaldehyde ((2), (3) or (4)) (1 eq.), phenylboronic acid (1 eq.) and potassium cyanide (3 eq.). The resulting mixture was stirred for 12 hours at room temperature before the appearance of a precipitate. After solvent concentration *in vacuo*, the precipitate was filtered and further washed with EtOH and *n*-pentane.

Route C: Salicylaldehyde (4), 4-substituted 2-aminophenol (1 equiv), phenylboronic acid (1 equiv) and potassium cyanide (3 equiv) were stirred at room temperature in methanol for 12 hours. The solvents was evaporated *in vacuo* to dryness and purified on a silica column chromatography, using CH_2Cl_2 /Petroleum ether as eluent to afford a the appropriate HBBO dye as a powder.


30

Example 5 (comparative example):

Compound (5) was synthesized through Route A. Light yellow powder. Yield: 34 %. ¹H NMR (300MHz, CDCl₃) δ (ppm): 11.76 (br s, 1H, OH), 8.20 (s, 1H, CH Ar), 7.78 (d, 2H, J=8.6Hz, CH Ar), 7.42-7.54 (m, 5H, CH Ar), 7.23 (s, 1H, CH Ar), 6.95 (br s, 1H, CH Ar), 1.42 (s, 3H, -tBu), 1.37 (s, 3H, -tBu). ¹³C NMR (75MHz, CDCl₃) δ (ppm): 158.4, 157.2, 156.8, 152.0, 148.8, 140.0, 127.5, 125.9, 124.7, 123.0, 122.7, 119.1, 115.8, 109.8, 107.7, 100.4, 99.6, 35.2, 34.9, 31.9, 31.4. Anal. Calculated for C₂₉H₂₉NO₃ : C, 79.24; H, 6.65; N, 3.19 ; Found C, 79.04; H, 6.40; N, 2.99. EI-MS (*m/z*) : 439.1.


Example 6 (comparative example):

Compound (6) was synthesized through Route A. Light green powder. Yield: 42 %. ¹H NMR (300MHz, CDCl₃) δ (ppm): 11.64 (br s, OH), 8.17 (s, 1H, CH Ar), 7.75-7.78 (m, 3H, CH Ar), 7.52 (d, 1H, J=8.8Hz, CH Ar), 7.41-7.45 (dd, 1H, J=1.8Hz, J'=8.6Hz, CH Ar), 6.97 (d, 2H, J=8.8Hz, CH Ar), 7.21 (s, 1H, CH Ar), 6.84 (s, 1H, CH Ar), 3.86 (s, 3H, CH₃), 1.42 (s, 9H, -tBu). ¹³C NMR (75MHz, CDCl₃) δ (ppm): 163.7, 160.2, 158.3, 157.1, 156.7, 148.8, 147.2, 140.1, 126.4, 123.1, 123.0, 122.9, 118.8, 115.8, 114.4, 109.8, 107.7, 99.5, 99.3, 55.5, 35.2, 31.9. Anal. Calculated for C₂₆H₂₃NO₄ : C, 75.53; H, 5.61; N, 3.39 ; Found C, 75.36; H, 5.37; N, 3.24. EI-MS (*m/z*) : 413.1.

Example 7:


Compound (7) was synthesized through Route B. Brown-yellow powder. Yield: 25 %. ^1H NMR (300MHz, CDCl_3) δ (ppm): 11.43 (s, 1H, OH), 8.11 (s, 1H, CH Ar), 7.65 (d, 2H, $J=8.9\text{Hz}$, CH Ar), 7.55-7.51 (dd, 1H, $J=4.2\text{Hz}$, $J'=8.9\text{Hz}$, CH Ar), 7.42-7.39 (dd, 1H, $J=2.7\text{Hz}$, $J'=8.3\text{Hz}$, CH Ar), 7.19 (s, 1H), 7.09 (td, 1H, $J=2.7\text{Hz}$, $J=9.0\text{Hz}$, CH Ar), 6.67-6.71 (m, 3H, CH Ar), 3.35-3.30 (m, 4H, N- CH_2), 1.66-1.56 (m, 4H, CH_2), 1.44-1.32 (m, 4H, CH_2), 0.98 (t, 6H, $J=7.9\text{Hz}$, CH_3). ^{13}C NMR (75MHz, CDCl_3) δ (ppm): 165.6, 158.5, 158.2, 156.8, 148.6, 145.6, 141.3, 141.1, 126.4, 123.6, 118.2, 117.0, 112.8, 112.4, 111.6, 111.0, 106.8, 105.9, 105.6, 99.5, 97.0, 50.9, 29.6, 20.5, 14.2. Anal. Calculated for $\text{C}_{29}\text{H}_{29}\text{FN}_2\text{O}_3$: C, 73.71; H, 6.19; N, 5.93; Found C, 73.49; H, 5.82; N, 5.64. EI-MS (m/z): 472.3 (100)

Example 8:



Compound (8) was synthesized through Route B. Yellow powder. Yield: 20 %. ^1H NMR (300MHz, CDCl_3) δ (ppm): 11.31 (s, 1H, OH), 8.13 (s, 1H, CH Ar), 8.01 (s, 1H, CH Ar), 7.72-7.63 (m, 4H, CH Ar), 7.20 (1H, s, CH Ar), 6.71-6.67 (m, 3H, CH Ar), 3.35-3.30 (m, 4H, N- CH_2), 1.61 (m, 4H, CH_2), 1.44-1.32 (m, 4H, CH_2), 0.97 (t, 6H, $J=7.2\text{Hz}$, CH_3). ^{13}C NMR (75MHz, CDCl_3) δ (ppm): Anal. Calculated for $\text{C}_{30}\text{H}_{29}\text{F}_3\text{N}_2\text{O}_3$: C, 68.95; H, 5.59; N, 5.36; Found C, 68.72; H, 5.34; N, 5.27. EI-MS (m/z): 523.4 (100)


Example 9:



Compound (9) was synthesized through Route B. Brown-yellow powder. Yield: 45 %. ^1H NMR (300MHz, CDCl_3) δ (ppm): 11.11 (s, 1H, OH), 8.07 (s, 1H, CH Ar), 7.99 (s, 1H, CH Ar), 7.68-7.62 (m, 4H, CH Ar), 7.17 (s, 1H), 6.68-6.66 (m, 3H, CH Ar), 3.32 (t, 4H, $J=7.7\text{Hz}$, N- CH_2), 1.65-1.57 (m, 4H, CH_2), 1.43-1.34 (m, 4H, CH_2), 0.98 (t, 6H, $J=7.3\text{Hz}$, CH_3). ^{13}C NMR (75MHz, CDCl_3) δ (ppm): 165.9, 158.9, 158.5, 157.0, 151.6, 148.7, 141.0, 129.2, 126.4, 123.9, 123.4, 118.7, 118.4, 116.7, 111.8, 111.6, 109.1, 105.9, 99.6, 96.7,

34

50.9, 29.6, 20.5, 14.2. Anal. Calculated for $C_{30}H_{29}N_3O_3$: C, 75.13; H, 6.10; N, 8.76; Found C, 74.84; H, 5.72; N, 8.54. EI-MS (m/z): 479.2 (100).

Example 10:


5

Compound (10) was synthesized through Route B. Yellow powder. Yield: 56 %. 1H NMR (300MHz, $CDCl_3$) δ (ppm): 11.39 (s, 1H, OH), 8.39 (s, 1H, CH Ar), 8.13-8.09 (m, 2H, CH Ar), 7.66-7.61 (m, 3H, CH Ar), 7.18 (s, 1H, CH Ar), 6.70-6.66 (m, 3H, CH Ar), 3.96 (s, 3H, OCH₃), 3.34-3.29 (m, 4H, N-CH₂), 1.65-1.55 (m, 4H, CH₂), 1.44-1.32 (m, 4H, CH₂), 0.98 (t, 6H, $J=7.2$ Hz, CH₃). ^{13}C NMR (75MHz, $CDCl_3$) δ (ppm): 166.7, 165.1, 158.6, 158.2, 156.8, 152.1, 148.6, 140.5, 127.5, 127.1, 126.4, 123.7, 120.9, 118.3, 116.9, 111.6, 110.4, 106.5, 99.5, 96.9, 50.9, 29.6, 20.5, 14.2. Anal. Calculated for $C_{31}H_{32}N_2O_5$: C, 72.64; H, 6.29; N, 5.47; Found C, 72.47; H, 6.04; N, 5.22. EI-MS (m/z): 512.1 (100).

15

The compounds **7** to **10** incorporate a strongly mesomeric electron-donating *p*-dibutylaminophenyl as a terminal group on the benzofuran moiety while the benzoxazole moiety is functionalized with several electron-withdrawing groups of increasing electronegativity (F, CF₃, CN or CO₂Me for compounds **7**, **8**, **9** and **10** respectively).

20

Example 11:


Compound (11) was synthesized through Route C. 1H NMR (400 MHz, $CDCl_3$): δ (ppm) = 12.21 (s, 1H, OH), 8.22 (s, 1H, CH Ar), 7.98 (d, 1H, $^3J = 8.3$ Hz, CH Ar), 7.76 (s, 1H, CH Ar), 7.66 (d, 2H, $^3J = 9.0$ Hz, CH Ar), 7.62 (dd, 1H, $^3J = 8.4$ Hz, $^4J = 1.7$ Hz, CH Ar), 7.16 (s, 1H, CH Ar), 6.72 (d, 2H, $^3J = 8.2$ Hz, CH Ar), 6.68 (s, 1H, CH Ar), 3.34 (t, 4H, $^3J = 7.4$ Hz, CH₂), 1.67-1.59 (m, 4H, CH₂), 1.47-1.35 (m, 4H, CH₂), 0.99 (t, 6H, $^3J = 7.3$ Hz, CH₃). ^{13}C NMR (100 MHz, $CDCl_3$): δ (ppm) = 172.4, 158.4, 156.5, 152.0, 148.8, 136.2, 129.6 (q, $^1J_{C-F} = 33.0$ Hz), 126.5, 125.7, 123.9, 123.0, 122.1, 121.8 (q, $^3J_{C-F} = 3.7$ Hz), 119.5, 119.2 (q, $^3J_{C-F} = 3.7$ Hz), 117.3, 113.3, 112.0, 99.8, 96.9, 51.1, 29.7,

30

35


20.5, 14.1. Anal. Calculated for $C_{30}H_{29}F_3N_2O_2S$: C, 66.90; H, 5.43; N, 5.20. Found C, 66.83; H, 5.69; N, 4.97. EI-MS (m/z (relative intensity)): Theoretical mass 538.19 (100); Found 540.3 (9), 539.3 (28), 538.3 (80), 497.2 (6), 496.2 (21), 495.2 (65), 455.2 (9), 454.2 (27), 453.2 (100), 438.1 (32).

5

Example 12:

Compound (12) was synthesized through Route C. 1H NMR (300 MHz, $CDCl_3$): δ (ppm) = 11.32 (s, 2H, OH), 8.10 (s, 2H, CH Ar), 7.91 (s, 2H, CH Ar), 7.66 (d, 4H, $^3J = 8.9$ Hz, CH Ar), 7.59 (d, 2H, $^3J = 8.7$ Hz, CH Ar), 7.43 (d, 2H, $^3J = 9.2$ Hz, CH Ar), 7.17 (s, 2H, CH Ar), 6.70-6.67 (m, 6H, CH Ar), 3.32 (t, 8H, $^3J = 7.2$ Hz, CH_2), 1.67-1.57 (m, 8H, CH_2), 1.46-1.34 (m, 8H, CH_2), 1.00 (t, 12H, $^3J = 7.3$ Hz, CH_3). ^{13}C NMR (75 MHz, $CDCl_3$): δ (ppm) = 165.1, 158.6, 158.3, 156.9, 149.2, 148.7, 140.6, 130.6, 127.3, 126.3, 123.7, 122.6, 121.4, 118.3, 117.0, 11.6, 110.3, 106.6, 99.4, 96.9, 50.9, 29.6, 20.5, 14.1.

15 Anal. calculated for $C_{61}H_{58}F_6N_4O_6$: C, 69.31; H, 5.53; N, 5.30. Anal. Found C, 69.05; H, 5.59; N, 5.23. EI-MS (m/z (relative intensity)): Theoretical mass 1056.43 (100); Found 1056.5 (24), 1013.4 (32), 443.4 (100).

Example 13:


20

Compound (13) was synthesized through Route C. 1H NMR (400 MHz, $CDCl_3$): δ (ppm) = 11.14 (s, 2H, OH), 8.36 (d, 2H, $^4J = 1.6$ Hz, CH Ar), 8.07 (s, 2H, CH Ar), 8.04 (dd, 2H, $^3J = 8.5$ Hz, $^4J = 1.7$ Hz, CH Ar), 7.71 (d, 2H, $^3J = 8.6$ Hz, CH Ar), 7.64 (d, 4H, $^3J = 8.8$ Hz, CH Ar), 7.17 (s, 2H, CH Ar), 6.68-6.66 (m, 6H, CH Ar), 3.31 (t, 8H, $^3J = 7.3$ Hz, CH_2), 1.63-1.56 (m, 8H, CH_2), 1.42-1.33 (m, 8H, CH_2), 0.97 (t, 12H, $^3J = 7.2$ Hz,

25


36

CH₃). ¹³C NMR (100 MHz, CDCl₃): δ (ppm) = 166.1, 158.9, 158.5, 157.0, 151.9, 148.7, 141.2, 139.0, 126.4, 125.0, 123.9, 119.3, 118.4, 116.7, 111.6, 111.5, 106.0, 99.6, 96.8, 50.9, 29.6, 20.5, 14.1. Anal. calculated for C₅₈H₅₈N₄O₈S.CH₂Cl₂: C, 71.73; H, 6.02; N, 5.77. Anal. found C, 71.56; H, 6.04; N, 5.65. EI-MS (m/z (relative intensity)): Theoretical mass 970.40 (100); Found 972.5 (8), 971.5 (20), 970.5 (30), 928.5 (40), 927.4 (55), 400.8 (100).

Example 14:

10

Compound (14) was synthesized through Route C. ¹H NMR (400 MHz, CDCl₃): δ (ppm) = 11.36 (s, 1H, OH), 8.10 (s, 1H, CH Ar), 7.86 (s, 1H, CH Ar), 7.66 (d, 2H, ³J = 8.7 Hz, CH Ar), 7.47 (s, 2H, CH Ar), 7.18 (s, 1H, CH Ar), 6.70 (s, 1H, CH Ar), 6.68 (d, 2H, ³J = 8.8 Hz, CH Ar), 3.32 (t, 4H, ³J = 7.4 Hz, CH₂), 1.64-1.57 (m, 4H, CH₂), 1.43-1.34 (m, 4H, CH₂), 0.98 (t, 6H, ³J = 7.3 Hz, CH₃). ¹³C NMR (100 MHz, CDCl₃): δ (ppm) = 165.0, 158.6, 158.2, 156.8, 148.6, 148.3, 141.9, 128.1, 126.4, 123.7, 122.1, 118.3, 117.8, 116.9, 111.8, 111.6, 106.6, 99.5, 96.9, 50.9, 29.6, 20.5, 14.2. Anal. calculated for C₂₉H₂₉BrN₂O₃: C, 65.29; H, 5.48; N, 5.25. Anal. Found C, 65.41; H, 5.49; N, 5.22. EI-MS (m/z (relative intensity)): Theoretical Mass 532.14 (100); Found 535.2 (28), 534.2 (87), 533.2 (29), 532.2 (87), 492.2 (21), 491.2 (76), 490.2 (21), 489.2 (73), 450.1 (25), 449.1 (98), 448.1 (28), 447.1 (100).

Example 15:

Compound (15) was synthesized through Route C. ¹H NMR (300 MHz, CDCl₃): δ (ppm) = 10.97 (s, 1H, OH), 7.91 (s, 1H, CH Ar), 7.65 (s, 1H, CH Ar), 7.56-7.50 (m, 3H, CH Ar), 7.06 (s, 1H, CH Ar), 6.62 (d, 2H, ³J = 8.6 Hz, CH Ar), 6.56 (s, 1H, CH Ar), 3.30 (t, 4H, ³J = 7.2 Hz, CH₂), 1.66-1.56 (m, 4H, CH₂), 1.45-1.27 (m, 4H, CH₂), 0.99 (t, 6H, ³J = 7.2 Hz, CH₃). ¹³C NMR (75 MHz, CDCl₃): δ (ppm) = 164.8, 158.7, 158.2, 156.8, 148.6, 146.7, 142.0, 130.4, 126.2, 123.7, 121.0, 118.4, 117.9, 116.8, 111.5, 105.8, 103.2,

30

99.4, 96.7, 50.9, 29.6, 20.5, 14.1. EI-MS (m/z (relative intensity)): Theoretical mass 610.05 (100); Found 614.1 (47), 612.1 (88), 610.1 (47), 571.1 (40), 569.1 (80), 567.1 (40), 529.0 (53), 527.0 (100), 525.0 (49).

5 C. Photophysical data

C.1. In solution

Photophysical data in solution in various solvents were collected and are gathered in tables 1a and 1b.

10 Table 1a: Optical data measured in solution

Compounds	λ_{abs} (nm)	ϵ ($\text{M}^{-1}\text{cm}^{-1}$)	λ_{em} (nm)	Δ_{ss} (cm^{-1})	$\Phi_{\text{f}}^{\text{a}}$	R_{Du}	τ (ns)	Solvent
5 (comparative)	360	33500	546	9400	0.05		0.4	cyclohexane
	361	37200	550	9500	0.07		0.8	toluene
	358	33700	546	9600	0.04		0.5	CH_2Cl_2
	356	32600	546	9800	0.06		0.3	acetone
6 (comparative)	363	30600	546	9200	0.05		0.6	cyclohexane
	364	33100	547	9200	0.06		0.7	toluene
	361	32300	549	9500	0.05		0.4	CH_2Cl_2
	380	32600	^b /557	8400	0.05		0.4/3.1	acetone
7	387	28200	450/560	3600	0.02/0.05	0.55	3.0/0.7	cyclohexane
	389	29900	463/565	4100	0.02/0.08	0.41	3.6/0.7	toluene
	386	30100	510/564	6300	0.08	0.83	0.9/4.4	CH_2Cl_2
	385	29000	500/588	6000	0.02	0.49	0.2/2.3	EtOH
8	391	30200	458/565	3700	0.10	0.69	0.4/0.4	cyclohexane
	393	21300	468/568	4100	0.15	0.73	0.6/0.6	toluene
	390	27100	522/560	6500	0.20	0.91	1.3	CH_2Cl_2
	389	27200	516/588	6300	0.02	0.74	0.3/2.5	EtOH
9	398	29300	463/562	3500	0.03/0.05	0.33	0.5	cyclohexane
	396	28000	481/570	4500	0.05/0.05	0.73	0.8/0.8	toluene
10	388	32200	451/562	3600	0.08	0.50	0.3/0.3	cyclohexane

38

390	32700	467/569	4200	0.12	0.38	0.5/0.5	toluene
389	34700	515/570	6300	0.13	0.80	0.8/5.3	CH ₂ Cl ₂

[a] Quantum yields determined in solution, using quinine sulfate as reference $\Phi = 0.55$ in H₂SO₄ 1N, $\lambda_{ex} = 366$ nm for dyes emitting below 480 nm, Rhodamine 6G $\Phi = 0.88$ in ethanol, $\lambda_{ex} = 488$ nm for dyes emitting between 480 and 580 nm. [b] broad shoulder [c] not soluble. [d] $R_{Du} =$
 5 Intensity of λ_{max} of less intense emission band/Intensity λ_{max} of more intense emission band.

Table 2a : Optical data measured in solution

Compounds	λ_{abs} (nm)	ϵ (M ⁻¹ .cm ⁻¹)	λ_{em} (nm)	Δ (cm ⁻¹)	Φ_f^a	τ (ns)	Solvent
12	392	45000	455/567	3500	0.12	0.3/0.4	cyclohexane
	394	61400	473/571	4200	0.06	0.6/0.5	toluene
	392	62400	507/607	5800	0.03	0.3	EtOH
13	400	67500	478/574	4100	0.14	0.9/0.8	toluene
14	393	35900	453/557	3400	0.10	0.4	cyclohexane
	394	32800	473/571	4200	0.09	0.6	toluene
	389	13300	515/587	6300	0.03	0.2	EtOH
11	410	14500	485/609	3800	0.02	0.1	cyclohexane
	413	25200	489/619	3800	0.01	0.1	toluene
15	402	28200	465/565	3400	0.09	0.6/0.6	cyclohexane
	401	27800	481/570	4100	0.13	1.1/1.1	toluene

10

In view of table 1a, the compounds 5 and 6, which are not compounds according to the invention, do not exhibit dual emission in solution.

On the contrary, compounds according to the invention, namely compounds 7, 8, 9, 10, 11, 12, 13, 14 and 15 exhibit intense dual emission properties, as seen by the
 15 presence of two emission bands (λ_{em}). Such two emissions bands correspond to both the E* and the K* emissions bands. The intensity of the dual emission was measured with the R_{Du} ratio, which is advantageously higher than 0.2, preferably higher than 0.3.

Such results also indicate that the compounds 7, 8, 9, 10, 11, 12, 13, 14 and 15 display
 20 solution dual emissions in various type of solvent, such as for example solvents having low dielectric constant and high dielectric constant.

Compounds 8 and 9 exhibit the most intense dual emission where the maximum wavelength of the two bands E* and K* are the more strongly separated.

The results show that depending on the electronic substitution of the compounds, dual emission (both E* and K* bands) is observed, whose intensity ratio depends on the electronegativity of the electron-withdrawing group present on the compounds of the invention. This outcome is related to the relative excited state stabilities of the E* and K* tautomers.

It results from these experiment that the increase of the intensity of the E* band can be correlated to the global electronegativity of the fragment attached on the benzoxazole moiety of the compounds: from strongly electron-withdrawing (CF₃ and CN in compounds **8** and **9** respectively) to mildly electrowithdrawing (F and CO₂Me in compounds **7** and **10** respectively).

Without being bound by theory, it seems that the strong electron-donating ability of the *p*-dibutylaminophenyl group present on the compounds **7**, **8**, **9**, **10**, **11**, **12**, **13**, **14** and **15**, decrease the acidity of the benzofuran-ol moiety of the compounds, increasing its pK_a which in turn stabilize the enol isomer in the excited stat. In addition, the presence of electron-withdrawing group on the benzoxazole moiety seems to increase the pK_b of said benzoxazole moiety. These combined cooperative effects favor the obtaining of dual emission and allo to tune the R_{DJ} ratio.

In addition, due to the broad emission bands covering most of the visible range, white light emission was observed, notably in cyclohexane, notably for compounds **8**, **9** and **10**.

C.2. In solid state

Photophysical properties were also investigated in the solid state dispersed in KBr matrix pellets and in PMMA/PS films. The optical properties are presented in tables 2a and 2b.

The powders were dispersed in KBr matrix as pellets or dissolved as 0.5% in PMMA/PS and transparent polymer films were prepared on glass plates by spin coating method.

Table 2a: Optical data measured in the solid-state

Compounds	λ_{exc} (nm)	λ_{em} (nm)	R_{Du}^a	Δ_{ss} (cm^{-1})	Φ_f^b	x;y (CIE 1931)	Matrices
5 (comparative)	381	535		7600	0.54	0.401; 0.577	KBr pellet
	360	546		9500	0.29	0.420 ; 0.536	film
6 (comparative)	387	551		7700	0.31	0.465 ; 0.535	KBr pellet
	363	544		9200	0.30	0.421 ; 0.540	film
7	400	476/571	0.35	4000	0.10	0.495 ; 0.458	KBr pellet
	388	467/563	0.56	4400	0.30	0.386 ; 0.398	film
8	399	501/580	0.60	5100	0.19	0.353 ; 0.479	KBr pellet
	399	481/561	0.99	4300	0.22	0.345 ; 0.398	film
	395	493/560	0.81	5000	0.32	0.338 ; 0.430	film
10	386	481/564	0.60	5100	0.23	0.387 ; 0.418	film
	386	481/564		5100	0.23	0.387 ; 0.418	film

[a] R_{Du} = Intensity of λ_{max} of less intense emission band/Intensity λ_{max} of more intense emission band [b] Absolute quantum yields determined using an integration sphere.

5

Table 2b: Optical data measured in the solid-state

Compounds	λ_{em} (nm)	Φ_f^a	CIE Coordinates	Matrices
12	463/568	0.37	0.38; 0.38	PS
	469/566	0.38	0.36; 0.40	PMMA
13	482/570	0.68	0.32; 0.37	PS
	485/569	0.39	0.34; 0.41	PMMA
14	505/586	0.11	0.37; 0.50	KBr pellet
	466/570	0.42	0.39; 0.38	PS
	465/566	0.33	0.38; 0.42	PMMA
11	525/646	0.22	0.60; 0.38	KBr pellet
15	479/579	0.50	0.31; 0.36	PS
	481/561	0.38	0.34; 0.40	PMMA

The emission profiles recorded for compounds 7, 8, 9, 10, 11, 12, 13, 14 and 15 are following the same trends as those observed in the solution-state, *i.e.* a dual intense emission corresponding to the E^* and K^* bands at high and low energies respectively. For the comparative compounds **5** and **6**, the emission spectra are quasi-identical as those

25

recorded in solution with the sole K^* band observed in KBr pellets and thin films of doped polymers respectively.

Besides, the quantum yields for compounds 7, 8, 9 and 10 are significantly higher than those recorded in solution spanning from 10 to 32%.

- 5 A more pronounced E^* emission for compounds 8-9 bearing the strongest attracting groups (CN and CF_3 for 8 and 9 respectively) was recorded. It was observed that the intensity of the E^* decreases along with the accepting ability of the group on the benzoxazole side; a feature found both in solution and in the solid-state.

10 In particular, the results show that as a consequence of the dual emission in the solid-state for compounds 7, 8, 9, 10, 11, 12, 13, 14 and 15, white light emission was observed in PMMA/PS doped films, especially for compound 8 whose CIE coordinates x;y are the closest to pure white (see table 2a).

15 These experimental results were also analyzed by Time-Dependent Density Functional Theory calculations (TD-DFT) that confirm that, on the one hand, only E^* and K^* emissions are present (no rotamer), and, on the other hand, the relative free energies of the two tautomers in the excited state guide the ratio of the E^*/K^* emission intensities.

It has been thus discovered that compounds according to the invention exhibit dual emission properties, in solution and/or especially in solid state.

20 It has been thus discovered that compounds according to the invention provide new white light emitting compounds.

It has been thus discovered that compounds according to the invention display broad and tunable dual emission upon photoexcitation.

25 It has been thus discovered that compounds according to the invention present good luminescent properties.

It has been thus discovered that compounds according to the invention present acceptable quantum yields.


The compounds according to the invention enable preparing devices for ratiometric detection and devices emitting white light.

30

D. Theoretical calculations

Theoretical calculations were performed on the following compounds: B1, B2 and B3. B1 and B2 are comparative compounds, while compound B3 is a compound according to the invention.

35



The protocol used here is PCM-M06-2X/6-31G(d), which allows the calculation of the Gibbs relative energies. Such protocol is disclosed in the publication Benelhadj, K. et al., "White emitters by tuning the excited state intramolecular proton transfer fluorescence emission in 2-(2'-hydroxybenzofuran)benzoxazole dyes", Chemistry a European Journal, 5 2014, September 21, 20(40), 12843-57.

For B₁, the enol conformation is favored by 7 kcal.mol⁻¹ in the ground state whereas the keto conformation is favored by 4 kcal.mol⁻¹ in the excited state. For B₂, the enol conformation is favored by 5 kcal.mol⁻¹ in the ground state whereas the keto conformation is favored by 4 kcal.mol⁻¹ in the excited state. For B₃, the enol conformation is favored by 14 kcal.mol⁻¹ in the ground state whereas the keto conformation is favored by 3 kcal.mol⁻¹ in the excited state.

The calculated excited-state delta G (eV) give -0.05 for B₃ which is very likely to display dual emission based on previous experimental/theory analogies.

15 B₁ and B₂ give -0.10 and -0.12 respectively which would be in favored of a single emission (quantitative proton transfer).


20

25

CLAIMS


1. Compound of formula (I):

5



wherein:


- A represents an electron-withdrawing group;
- 10 - D represents an electron-donating group;
- X is selected from the group consisting of: O, S and NR, wherein R is selected from the group consisting of: H, an alkyl group preferably comprising from 1 to 20 carbon atoms, an aryl group preferably comprising from 6 to 22 carbon atoms, and a heteroaryl group;
- 15 - n is an integer from 1 to 4;
- m is an integer from 1 to 6, preferably from 1 to 4;




- represents a condensed bicyclic aromatic radical comprising from 6 to 22 carbon atoms, and from 1 to 3 heteroatom(s) selected from the group consisting of: N, S and O;

20

the OH group being in ortho position of the condensed bicyclic aromatic radical

relative to the  radical.

2. Compound according to claim 1, having the following formula (II):



25

wherein:

- R₁, R₂, R₃ and R₄ represent, independently of each other, H or an electron-withdrawing group A;
- R₅, R₆, R₇ and R₈ represent, independently of each other, H or an electron-donating group D;

5 or R₅ and R₆ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom selected from the group consisting of: N, O and S, and said cycle being optionally substituted by at least one electron-donating group D;

10 or R₆ and R₇ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom selected from the group consisting of: N, O and S, and said being optionally substituted by at least one electron-donating group D;

15 or R₇ and R₈ form, together with the carbon atoms carrying them, an at least partially unsaturated cycle comprising from 4 to 6 atoms, preferably 5 atoms, said cycle comprising at least one heteroatom selected from the group consisting of: N, O and S, and said being optionally substituted by at least one electron-donating group D;

20 - X, A and D being as defined in claim 1;

at least one of R₅ and R₆, or R₆ and R₇, or R₇ and R₈, form said at least partially unsaturated cycle;

at least one of R₁, R₂, R₃ and R₄ is an electron-withdrawing group A; and

said compound of formula (II) comprising at least one electron-donating group D.

25

3. Compound according to any one of claim 1 or 2, wherein the electron-donating group D is selected from the group consisting of:

- O⁻;

30 - OR_a, wherein R_a is H or an alkyl group preferably comprising from 1 to 20 carbon atoms;

- NR_bR_c, wherein R_b and R_c are, independently of each other, selected from the group consisting of:

o H;


o alkyl group preferably comprising from 1 to 20 carbon atoms, preferably from 1 to 4 carbon atoms; and

35

- aryl group preferably comprising from 6 to 22 carbon atoms, preferably a phenyl group;
 - NHC(O)R_d, wherein R_d is selected from the group consisting of:
 - alkyl group preferably comprising from 1 to 20 carbon atoms preferably from 1 to 4 carbon atoms; and
 - aryl group preferably comprising from 6 to 22 carbon atoms, preferably a phenyl group;
 - an aryl group preferably comprising from 6 to 22 carbon atoms, preferably a phenyl group; and
 - an alkyl group preferably comprising from 1 to 20 carbon atoms; said alkyl and aryl groups being optionally substituted with at least one electron-donating group, preferably selected from: O⁻, OR_a, NR_bR_c and -NHC(O)R_d, R_a, R_b, R_c and R_d being as defined above.
4. Compound according to any one of claims 1 to 3, wherein the group A is selected from the group consisting of:
- halogen such as Br, Cl, F or I;
 - C(O)R_e, R_e being selected from the group consisting of:
 - Cl;
 - H;
 - OR_f, R_f being H or an alkyl group preferably comprising from 1 to 20 carbon atoms; and
 - an alkyl group preferably comprising from 1 to 20 carbon atoms;
 - NO₂;
 - SO₂NR_gR_h, R_g and R_h representing, independently of each other, an alkyl group preferably comprising from 1 to 20 carbon atoms or an aryl group preferably comprising from 6 to 22 carbon atoms;
 - CN;
 - CF₃;
 - alkyl group, preferably comprising from 1 to 20 carbon atoms, substituted with at least one group selected from: halogen such as F, NO₂, CN, C(O)R_e, SO₂NR_gR_h and CF₃, wherein R_e, R_g and R_h are as defined above, said alkyl being optionally substituted with a heteroaryl, said heteroaryl being optionally substituted with a substituted heteroaryl;
 - aryl group, preferably comprising from 6 to 22 carbon atoms, substituted with at least one group selected from: halogen such as F, NO₂, CN, C(O)R_e, SO₂NR_gR_h and CF₃, wherein R_e, R_g and R_h are as defined above;

- $-S(O)_2-W$, W being a heteroaryl being optionally substituted with a substituted heteroaryl;


- SO_3H ;




- a radical having the following formula : ; and

5 - $N^+R_iR_jR_kR_l$, wherein R_i , R_j , R_k , and R_l are, independently of each other, H or an alkyl group preferably comprising from 1 to 20 carbon atoms, said alkyl group being optionally substituted with at least one group selected from: halogen such as F, NO_2 , CN, $C(O)R_e$, $SO_2NR_gR_h$ and CF_3 , wherein R_e , R_g and R_h are as defined above.

10 5. Compound according to claim 4, wherein the group A comprises an π -electron conjugated chain, for example the group A is:



6. Compound according to any one of claims 1 to 5, having the following formula (III):



15

wherein:

- R_9 and R_{10} represent, independently of each other, H or an electron-donating group D;


- R_1 , R_2 , R_3 , R_4 , R_5 , R_8 , X and D being as defined in any one of claims 1 to 4.

20

25

47


7. Compound according to claim 6, having the following formula (IV):



wherein:

- 5
- R₁₁ represents H or an electron-donating group D;
 - R₁, R₂, R₃, R₄, R₅, R₈, X, A and D being as defined claim 6.

8. Compound according to 7, having the following formula (V):



10










wherein:



- R' and R'' represent, independently of each other, H or an alkyl group preferably comprising from 1 to 20 carbon atoms;
- R₃, R₅, R₈ and X being as defined in any one of claims 2 to 7.

15



9. Compound according to any one of claims 1 to 8, selected from the group consisting of:

48





5



10. A solid material (S) comprising or consisting of at least one compound according to any one of claims 1 to 9.
11. A material (M) comprising one or more compounds according to any one of claims 1 to 9, and at least one polymer and/or polymeric material and/or an organic matrix, said organic matrix may optionally comprise an inorganic material.
12. A light emitting device comprising at least one compound according to any one of claims 1 to 9, or a solid material (S) according to claim 10 or a material (M) according to claim 11.
13. A device for ratiometric analysis comprising at least one compound according to any one of claims 1 to 9, or a solid material (S) according to claim 10 or a material (M) according to claim 11.
14. Use of at least one compound according to any one of claims 1 to 9, or a solid material (S) according to claim 10 or a material (M) according to claim 11, for emitting white light.

15. Use of at least one compound according to any one of claims 1 to 9, or a solid material (S) according to claim 10 or a material (M) according to claim 11, as fluorescent probe, in particular for ratiometric analysis, or as a pigment in particular for security inks.

5

1/8




Figure 1

2/8




Figure 2

3/8




Figure 3

4/8




Figure 4

5/8




Figure 5

6/8




Figure 6

7/8




Figure 7

8/8




Figure 8

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2015/066664

A. CLASSIFICATION OF SUBJECT MATTER
INV. C07D413/04 C07D307/79 C07D307/80 C07D307/81 H01L51/00
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
C07D H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2013/338171 A1 (CAI SHAOPEI [US] ET AL) 19 December 2013 (2013-12-19) for example compounds of ex. 73, 79-81 in table 7 or that with RN668428-99-7 -----	1,3
X	EL-DESOKY I EL-SAYED ET AL: "Synthesis of Some Chromanone Derivatives and the Use of DNA in Evaluation of their Biological Activity", ZEITSCHRIFT FÜR NATRUFORSCHUNG B, vol. 53, 1 January 1998 (1998-01-01), pages 909-915, XP055148964, ISSN: 0932-0776 scheme 2, compound 8b ----- -/--	1-3

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search 26 August 2015	Date of mailing of the international search report 02/09/2015
---	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Gregoire, Ariane
--	--

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2015/066664

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>MASSUE JULIEN ET AL: "Fluorescent 2-(2'-hydroxybenzofuran)benzoxazole (HBB0) borate complexes: synthesis, optical properties, and theoretical calculat", TETRAHEDRON LETTERS, vol. 55, no. 30, 9 June 2014 (2014-06-09), pages 4136-4140, XP028861805, ISSN: 0040-4039, DOI: 10.1016/J.TETLET.2014.06.002 cited in the application the whole document</p> <p style="text-align: center;">-----</p>	1-15
A	<p>KLYMCHENKO A S ET AL: "A 3-hydroxychromone with dramatically improved fluorescence properties", TETRAHEDRON LETTERS, PERGAMON, GB, vol. 42, no. 45, 5 November 2001 (2001-11-05), pages 7967-7970, XP004309963, ISSN: 0040-4039, DOI: 10.1016/S0040-4039(01)01723-3 the whole document</p> <p style="text-align: center;">-----</p>	1-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2015/066664

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
US 2013338171	A1	19-12-2013	AU 2004288692 A1	26-05-2005
			AU 2004288709 A1	26-05-2005
			AU 2004289672 A1	26-05-2005
			AU 2011202249 A1	02-06-2011
			BR PI0416143 A	02-01-2007
			CA 2543820 A1	26-05-2005
			CA 2544186 A1	26-05-2005
			CA 2544492 A1	26-05-2005
			CN 102225926 A	26-10-2011
			EA 200600928 A1	26-10-2007
			EP 1682529 A2	26-07-2006
			EP 1692085 A2	23-08-2006
			EP 1699421 A2	13-09-2006
			EP 2762475 A1	06-08-2014
			ES 2486240 T3	18-08-2014
			HK 1097444 A1	19-12-2014
			IL 174471 A	27-06-2013
			IL 175385 A	28-06-2012
			JP 4724665 B2	13-07-2011
			JP 4823914 B2	24-11-2011
			JP 4890255 B2	07-03-2012
			JP 5214768 B2	19-06-2013
			JP 2007510665 A	26-04-2007
			JP 2007510668 A	26-04-2007
			JP 2007522098 A	09-08-2007
			JP 2011042687 A	03-03-2011
			JP 2011162563 A	25-08-2011
			KR 20060111520 A	27-10-2006
			KR 20070011231 A	24-01-2007
			KR 20070011241 A	24-01-2007
			MX PA06004194 A	28-06-2006
			TW 200526604 A	16-08-2005
			US 2005137399 A1	23-06-2005
			US 2005209247 A1	22-09-2005
			US 2009181979 A1	16-07-2009
			US 2012277434 A1	01-11-2012
			US 2013018058 A1	17-01-2013
			US 2013338171 A1	19-12-2013
			US 2014303182 A1	09-10-2014
			WO 2005046589 A2	26-05-2005
			WO 2005046590 A2	26-05-2005
			WO 2005047244 A2	26-05-2005