



(51) International Patent Classification:

G02F 1/155 (2006.01) *G03F 7/00* (2006.01)
H01L 51/05 (2006.01)

(21) International Application Number:

PCT/EP2012/056237

(22) International Filing Date:

4 April 2012 (04.04.2012)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/471,855 5 April 2011 (05.04.2011) US
11164936.4 5 May 2011 (05.05.2011) EP

(71) Applicants (for all designated States except US): **ACREO AB** [SE/SE]; Electrum 236, S-164 40 Kista (SE). **LINTEC CORPORATION** [JP/JP]; 23-23 Hon-cho, Itabashi-ku, Tokyo 173-0001 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ANDERSSON ERS-MAN, Peter** [SE/SE]; Södermalmsvägen 26, S-612 40 Finspång (SE). **NILSSON, David** [SE/SE]; Drättingevägen 7, S-590 48 Vikingstad (SE). **KAWAHARA, Jun** [JP/SE]; Himmelstalundsvägen 32b, S-602 16 Norrköping (SE). **KATO, Kazuya** [JP/JP]; c/o Lintec Corporation, 23-23 Hon-cho, Itabashi-ku, Tokyo 173-0001 (JP).

(74) Agent: **HAAG, Malina**; AWAPATENT AB, Södra Hamngatan 37-41, Box 11394, S-404 28 Göteborg (SE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LI, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

Published:

— with international search report (Art. 21(3))

(54) Title: PROCESS FOR MANUFACTURING AN ELECTROCHEMICAL DEVICE BASED ON SELF-ALIGNMENT ELECTROLYTES ON ELECTRODES




Fig. 1e

(57) Abstract: A process for manufacturing an electrochemically active device comprising the steps of: - providing a substrate (110) comprising an electrode receiving surface portion (111) having substantially constant wetting tension throughout said electrode receiving surface portion, - providing a plurality of first electrodes (120) directly on said electrode receiving surface portion, - leaving intermediate portions (130) of said electrode receiving surface portion (111) free from said electrodes, - providing a layer of electrolyte (140) covering said plurality of first electrodes (120) and said intermediate portions (130), and - wherein wetting tension of the surfaces of the intermediate portions (130) is arranged to act more repelling on the electrolyte compared to the wetting tension of the surfaces of the plurality of first electrodes (120), whereby, the electrolyte is concentrated to the surfaces of the plurality of first electrodes (120), and the surfaces of the intermediate portions (130) are substantially free of electrolyte.

PROCESS FOR MANUFACTURING AN ELECTROCHEMICAL DEVICE BASED ON SELF-ALIGNMENT ELECTROLYTES ON ELECTRODES

Technical Field

The invention relates to a process for manufacturing at least a part of an electrochemically active device, which comprises an electrolyte in ionic contact with an electrode. The invention also relates to a process for manufacturing a more completed electrochemically active device comprising an electrolyte sandwiched between an active electrode and a counter electrode.

Background of the invention

Printable display devices have attracted a lot of attention, and a lot of global research efforts have been carried out during the recent years. Regardless of the display performance; short or long life time, high or low resolution, short or long switching time etc., the most critical issue in order to obtain high yield at low production cost has been to establish the most simple manufacturing process by involving as few materials and processing steps as possible. Manufacturing of display devices, which sometimes consist of both pixels and addressing transistors, often requires material patterning at high accuracy on top of a flexible substrate. Such material patterning can, for example, consist of the deposition of the insulating, semiconducting and conducting materials serving as the dielectric, active and electrode materials, respectively, of a display device. One of the major objectives in order to enable manufacturing at low cost and high volume is to combine flexible polymer materials with roll-to-roll printing and/or coating equipments. Therefore, the capability of rapid and simple patterning of deposited materials at high yield is one of the most critical issues that need to be addressed within the field of printed electronics.

One example of a process for manufacturing electrochromic display devices comprising electrolyte is described in Andersson P. et al: "*Printable All-Organic Electrochromic Active-Matrix Displays*", Advanced Functional Materials, vol. 17, no. 16, 5 November 2007, pages 3074-3082. The article describes, in section 4 Experimental, the manufacturing of an electrochromic device comprising electrolyte, wherein transistor and pixel electrodes are formed on two PEDOT:PSS-covered sheets by means of subtractive patterning, i.e. predetermined portions of the PEDOT:PSS layer are removed

such that the desired PEDOT:PSS electrodes are formed. Two masks are made by cutting openings in a plastic foil. When ready, each mask is arranged on a respective one of the PEDOT:PSS-covered sheets, and the mask openings are filled with electrolyte using e.g. a screen printer squeegee. Hence, the electrolyte is arranged in ionic contact with each PEDOT:PSS layer. Finally, the two sheets are laminated together, such that ionic contact is provided between a display electrode and/or a transistor channel on the first sheet and a display counter electrode and/or a transistor gate electrode on the other sheet via the electrolyte, as is illustrated in Figure 4a in the article.

Although good results may be achieved by the above manufacturing process there is a desire to enhance the pixel resolution and preferably also to reduce the manufacturing time. However, the plastic foil limits the pixel to pixel distance. If the pixels are made substantially smaller (e.g. in the order of 1 mm²) and arranged substantially closer to each other (e.g. having a pixel to pixel distance in the order of less than 500 µm, the stability of the foil will be severely impaired due to lack of stabilizing material.

In US 20060116001, from the remote technical field of pixels devoid of electrolyte material, there is described a method wherein a stamp is arranged in contact with a substrate for a substantial amount of time (according to the example given: two days), which stamp modifies the surface energy of a substrate such that when the substrate is later dip-coated in a conjugated polymer solution, the conjugated polymer wets and spreads only on the area with higher surface energy. However, this technique is not relevant for achieving the objects of the invention, e.g. to that there is no guidance in the document as how this technique, relating to devices having a layer of semiconducting or a light emitting material applied to polymer, may be modified so as to be applicable to the manufacturing of a display comprising layers of electrolyte sandwiched between pairs of two electrodes/display elements; and also due to the substantial amount of time the stamp needs to be in contact with the substrate – the demands for high yield and short manufacturing time do not normally allow for a manufacturing step which takes days to complete. Furthermore, the requirement of a pre-patterned material layer implies an additional processing step during the display device manufacturing, which in turn increases the risk of registration errors.

Summary of the invention

One object of the invention is to overcome or at least alleviate the above mentioned drawbacks.

5 This and other objects are met by the subject matters provided in the independent claims. Preferred embodiments of the invention are presented in the dependent claims.

According to a first aspect thereof, the invention relates to a process for manufacturing of a part of at least an electrochemically active device

10 comprising:

- providing a substrate comprising an electrode receiving surface portion having substantially constant wetting properties or wetting tension throughout said electrode receiving surface portion,
- providing a plurality of first electrodes directly on said electrode receiving
- 15 surface portion having substantially constant wetting tension,
- leaving intermediate portions of said electrode receiving surface portion free from said electrodes, wherein each intermediate portion is usually arranged spatially between at least a pair of two first electrodes,
- providing a layer of electrolyte directly on each one of said plurality of
- 20 electrodes,

wherein

- the electrolyte is applied as a layer covering said plurality of first electrodes and said intermediate portions, and
- the wetting tension of the surfaces of the intermediate portions is arranged
- 25 to act more repelling on the electrolyte compared to the wetting tension of the surfaces of the plurality of first electrodes, whereby, at least after a predetermined time period and at least throughout a first portion of the substrate, the electrolyte is concentrated to the surfaces of the plurality of first electrodes, and the surfaces of the intermediate portions are substantially free
- 30 of electrolyte.

The inventors were developing a self patterning method (i.e. a method of coating an electrode carrying substrate with electrolyte, where the electrolyte initially covers both the electrodes and the portions in between the electrodes,

35 and thereafter automatically is rearranged such that it mainly covers only the electrodes and not the surfaces in between) and experimenting with different coatings to apply on the portions of the substrate not covered by electrodes in

order to achieve an efficient self patterning, when they made the surprising observation that it was possible to achieve a self patterning without any coating on the substrate at all.

- 5 The inventors tried many substrate/electrode/electrolyte combinations, but saw initially no pattern in the working and non-working combinations. They soon realised that there were a vast amount of parameters that could affect the patterning behaviour of the electrolyte (such as e.g. adhesion energy and surface free energy of the substrate and electrode material; droplet contact
10 angle, polarity, rheology, dispersing factor and hydrogen bonding for different electrolytes, and also the granular size of ingredients in the electrolytes as well as the length of the polymer chain of the different electrolyte compositions), and a prediction of how to select the substrate/electrode/electrolyte combination in order to obtain a high self
15 patterning yield was not easily identifiable.

After a thorough investigation of the results of different substrate/electrode/electrolyte combinations the inventors have come to a first conclusion that one type of working substrate/electrode/electrolyte
20 combination fulfils the following relation: the substrate have a wetting tension [N/m], which is lower than or equal to the corresponding surface tension [N/m] of the electrolyte, which in turn is lower than or equal to the wetting tension [N/m] of the electrodes. Additionally, the electrolyte is a printable electrolyte.

- 25 The inventors have also come to a second conclusion that a second type of working substrate/electrode/electrolyte combination fulfils the following conditions: the adhesion energy of the surface of the electrodes is larger than 10 mJ/m^2 relative deionized water, and test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension larger than 38 mN/m and
30 smaller than 63 mN/m are repelled from the substrate. Additionally, the electrolyte is a printable electrolyte.

The adhesion energy of a surface may be determined by arranging a water droplet of deionized water on the surface, which adhesion energy is to be
35 measured, and to tilt the surface gradually until the droplet starts to slip down; then the angle of the test surface against the horizontal ground is recorded. Finally, the adhesion energy of the test surface relative the deionized water

droplet is calculated using the formula of; $E=(mg \cdot \sin \alpha)/(2\pi r)$. Here r is the radius of the droplet on the substrate, m is the weight of the droplet, g is the acceleration of gravity and α is the angle of the tilted substrate when the droplet starts to slip down.

5

The invention resides in an insight by the inventors that it is possible to achieve self alignment of an electrolyte when producing a part for an electrochemically active device, without any local pre-treatment of the substrate surface. Thus, the invention facilitates the manufacturing of e.g. pixelated electrochemical devices, by e.g. reducing the number of processing steps and providing a way of aligning the electrolyte to the electrodes setting aside the need for registration.

In order to prevent cross-talk between the electrodes in e.g. pixelated electrochemical devices, it is preferred that all intermediate portions are substantially free of electrolyte. In other word, after the self alignment process each electrode is preferably ionically isolated from the rest of the electrodes. Further, when an electrolyte having an ideal thickness is applied, this results in all intermediate portions on the substrate being free of electrolyte. Furthermore, when a substantially thicker electrolyte is applied, this may result in that only a part of the intermediate portions become free of electrolyte. However, by selecting and/or extracting and/or isolating surface areas of the substrate where the intermediate portions are substantially free of electrolyte, these areas can be used in electrochemically active devices and provide a device which is not hampered by ionic connection between electrodes in the same plane. In other words, when producing a part of an electrochemically device, the yield of the production process may vary dependent on e.g. the thickness of the applied electrolyte layer. A yield of 100% corresponds to a device wherein all intermediate portions are substantially free of electrolyte. A yield of 70% corresponds to a device wherein 70% of the intermediate portions are substantially free of electrolyte.

When a surface area of the substrate is selected, one identifies a portion of the substrate having a desirable yield and isolates or extracts this portion from the remaining portion of the substrate, in order to provide the portion of the substrate having a desirable yield for use in an electrochemically active device. In relation to this invention the term *electrochemically active device*

35

refers to a device having at least one electrochemically active component comprising an electrolyte ionically connecting an electrochemically active material to an electrode, also referred to as a counter electrode. Basic examples of electrochemically active components, e.g. a display or a transistor, are described e.g. in Andersson P. et al: "*Printable All-Organic Electrochromic Active-Matrix Displays*", which article is discussed in more detail in the background section of this document.

In relation to this invention the term *part of an electrochemically active device* refers to an electrochemically active device, which is or is not fully assembled. In a fully assembled device the electrolyte may be sandwiched between a first and a second electrode, while in a not fully assembled device the second electrode may still not have been applied. The electrochemically active device must comprise the electrolyte and the first electrode, but there may be alternative ways of completing the device other than applying a second electrode. Moreover, the electrolyte is preferably in ionic contact with both the first electrode (121) and the second electrode (122) of the respective pairs of one first electrode (121) and one second electrode (126).

In relation to this invention the term *electrode receiving surface* refers to the portion of the substrate to which the plurality of first electrodes, or the first set of electrodes, is to be applied. The electrode receiving surface has not been exposed to a pre-treatment, resulting in a varying wetting distribution or surface energy distribution across the surface, before the electrodes are provided to the surface. One example of a pre-treatment of the substrate resulting in a varying surface energy distribution is described in US 20060116001. In other words, when the set of first electrodes is applied to the substrate, the surface energy and the wetting properties are substantially uniform throughout the entire electrode receiving surface of the substrate.

In relation to this invention the expression *a surface having a substantially constant wetting tension throughout the surface*, refers to that the wetting tension is substantially uniform all over the surface. In other words, if the electrolyte is applied directly on that surface the wetting or dewetting of the electrolyte will not result in a predetermined pattern. Instead, the electrolyte will rather rupture into a random pattern. According to one example the wetting tension of the surface does not vary more than 20 mN/m throughout the surface. According to another example it does not vary more than 15

mN/m, or more than 10 mN/m, or more than 5 mN/m, or more than 2 mN/m, or more than 1 mN/m throughout the surface having a substantially constant wetting tension.

- 5 In relation to this invention the expression that *a first object, A, is provided directly on a second object, B*, means that there is no intermediate object, C, arranged between the first and second objects A, B. However, when a first object, A, is described as being provided on a second object, B, there may be one or more intermediate objects, C, D, arranged between the first and
10 second objects A and B.

In relation to this invention the expression *a plurality of first electrodes* refers to a set of electrodes comprising at least two first electrodes, and for example at least four, or at least 5 x 7 electrodes arranged in a matrix configuration or
15 at least 25, or at least 64, or at least 128, or at least 512 or more first electrodes. The expressions *a plurality of second electrodes* and *a plurality of any other entities* are to be interpreted in an analogous manner.

In relation to this invention the term *substantially free of electrolyte* refers to
20 that the amount of electrolyte on an intermediate portion is small enough, such that the two or four electrodes neighbouring the intermediate portion may still work well enough.

According to some examples, the predetermined time period after which the
25 electrolyte is concentrated to the surfaces of the plurality of first electrodes, and the surfaces of the intermediate portions are substantially free of electrolyte is equal to 5 minutes, equal to 3 minutes, equal to 2 minutes, equal to 1 minute, equal to 30 seconds, equal to 15 seconds or equal to 10 seconds, or equal to 5 seconds or equal to 1 second. The predetermined time
30 period is measured from said electrolyte being provided directly on a set of first electrodes and said intermediate surface portions. In more detail, the expression that an area is substantially free of electrolyte at least after 5 minutes, refers to that the area is substantially free of electrolyte within a time
35 period of 0 to 5 minutes.

According to a second aspect thereof, the invention relates to a process for manufacturing of at least a part of an electrochemically active device comprising:

- providing a substrate comprising an electrode receiving surface portion
- 5 having substantially constant wetting properties or wetting tension throughout said electrode receiving surface portion,
- providing a plurality of first electrodes directly on said electrode receiving surface portion having substantially constant wetting tension,
- leaving intermediate portions of said electrode receiving surface portion free
- 10 from said electrodes, wherein each intermediate portion is usually arranged spatially between at least a pair of two first electrodes,
- providing a layer of electrolyte directly on each one of said plurality of electrodes,
- wherein
- 15 - the electrolyte is applied as a layer covering said plurality of first electrodes and said intermediate portions, and comprising
- providing a self-alignment of the electrolyte driven by a more repelling interaction between the electrolyte and the surfaces of the intermediate
- portion, compared to the interaction between the electrolyte and the surfaces
- 20 of the plurality of first electrodes, whereby at a completion of the self-alignment of the electrolyte, the electrolyte is concentrated to the surfaces of the plurality of first electrodes and the surfaces of the intermediate portions are substantially free of electrolyte.

25 In other words there is a self-controlled deposition of the electrolyte on the electrodes. In yet other words, the electrolyte will be substantially or totally confined to the electrode surfaces. Hence, there is provided a patterning method in which an electrolyte may self-separate into a predetermined pattern, which pattern is guided by the pattern or lay-out of the electrodes.

30

According to one example, the surface tension of the electrolyte and wetting tension of the first electrodes are selected such that the electrolyte is attracted to the electrodes. This is advantageous as it normally results in a higher yield.

35 According to a third aspect thereof, the invention relates to a process for manufacturing of at least a part of an electrochemically active device comprising:

- providing a substrate (110) comprising an electrode receiving surface portion (111) having a substantially constant first wetting tension throughout said electrode receiving surface portion,
 - providing a plurality of first electrodes (120) directly on said electrode receiving surface portion having a substantially constant first wetting tension, wherein the surfaces of said plurality of electrodes have a second wetting tension,
 - leaving intermediate portions (130) of said electrode receiving surface portion (111) free from said electrodes,
 - providing a printable electrolyte (140) having a first corresponding surface tension,
 - arranging said printable electrolyte as a layer of electrolyte (140) directly on each one of said plurality of electrodes,
- wherein
- the electrolyte (140) is applied as a layer covering said plurality of first electrodes (120) and said intermediate portions (130),
 - said first wetting tension of said substrate is lower than or equal to said first corresponding surface tension of said electrolyte, and
 - said second wetting tension of said electrodes is higher than said first corresponding surface tension of said electrolyte.

Hence, after a completion of the self-alignment of the electrolyte, the electrolyte is concentrated to the surfaces of the plurality of first electrodes and the surfaces of the intermediate portions are substantially free of electrolyte

According to a fourth aspect thereof, the invention relates to a process for manufacturing of at least a part of an electrochemically active device comprising:

- providing a substrate comprising an electrode receiving surface portion having substantially constant wetting properties or wetting tension throughout said electrode receiving surface portion,
- providing a plurality of first electrodes directly on said electrode receiving surface portion having substantially constant wetting tension,
- leaving intermediate portions of said electrode receiving surface portion free from said electrodes, wherein each intermediate portion is usually arranged spatially between at least a pair of two first electrodes,

- providing a layer of electrolyte directly on each one of said plurality of electrodes,

wherein

- the electrolyte is applied as a layer covering said plurality of first electrodes
5 and said intermediate portions, and

- the surface properties of the first electrodes, or the material or composition of the first electrodes are/is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension equal to 73 mN/m are attracted to the electrodes, and

10 the surface properties of the electrode receiving surface portion is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension larger than 38 mN/m and smaller than 63 mN/m are repelled from the electrode receiving surface portion.

In relation to the aspects presented above and according to one example, the
15 electrolyte has a corresponding surface tension which is higher than 38 mN/m, or higher than 42 mN/m, or higher than 50 mN/m, or higher than 60 mN/m.

In relation to the aspects presented above and according to one example the
20 electrolyte has a corresponding surface tension which is equal to or lower than 73 mN/m, or equal to or lower than 63 mN/m, or equal to or lower than 50 mN/m.

In relation to the aspects presented above and according to one example, the
25 electrolyte has a corresponding surface tension which is between 38 mN/m and 73 mN/m, or which is between 42 mN/m and 73 mN/m, or which is between 38 mN/m and 62 mN/m, or which is between 42 mN/m and 63 mN/m, or which is 43 mN/m and 73 mN/m, or which is between 43 mN/m and 63 mN/m, or which is between 42 mN/m and 62 mN/m.

30 According to one wetting tension example, the material or composition of the electrode receiving surface portion, or the surface properties of the electrode receiving surface portion, is/are selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension larger than 38
35 mN/m and smaller than 57 mN/m are repelled from the electrode receiving surface portion.

According to another wetting tension example, the material or composition of the electrode receiving surface portion, or the surface properties of the electrode receiving surface portion is/are selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension ranging from 40 to 50 mN/m are repelled from the electrode receiving surface portion.

According to a third wetting tension example, the material or composition of the electrode receiving surface portion, or the surface properties of the electrode receiving surface portion is/are selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension ranging from 40 to 45 mN/m are repelled from the electrode receiving surface portion.

The intervals mentioned above are advantageous as they normally result in high yield.

In relation to this invention the term *test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension range from xx to yy mN/m* refers to liquids prepared according to Section 5 "Test mixtures" of the ISO document, which liquids have a surface tension of xx to yy mN/m according to Table 1 of the ISO document.

According to a fifth aspect thereof, the invention relates to a process for manufacturing of a part of an electrochemically active device comprising:

- providing a substrate comprising an electrode receiving surface portion having a substantially constant wetting tension throughout said electrode receiving surface portion,
 - providing a plurality of first electrodes directly on said electrode receiving surface portion having substantially constant wetting tension,
 - leaving intermediate portions of said electrode receiving surface portion free from said electrodes, wherein each intermediate portion is usually arranged spatially between at least a pair of two first electrodes,
 - providing a layer of electrolyte directly on each one of said plurality of electrodes,
- wherein
- the electrolyte is applied as a layer covering said plurality of first electrodes and said intermediate portions, and

- the adhesion energy of the surface of the printed first electrodes is larger than 10 mJ/m^2 relative deionized water, and
- the surface properties of the electrode receiving surface portion is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension larger than 38 mN/m and smaller than 63 mN/m are repelled from the electrode receiving surface portion.

According to one example, the surface properties of the electrode receiving surface portion is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension larger than 38 mN/m and smaller than 57 mN/m are repelled from the electrode receiving surface portion.

According to another example, the surface properties of the electrode receiving surface portion is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension ranging from 40 to 50 mN/m are repelled from the electrode receiving surface portion.

According to a third example, the surface properties of the electrode receiving surface portion is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension ranging from 40 to 45 mN/m are repelled from the electrode receiving surface portion.

According to a sixth aspect thereof, the invention relates to a process for manufacturing of at least a part of an electrochemically active device comprising:

- providing a substrate comprising an electrode receiving surface portion having substantially constant wetting properties or wetting tension throughout said electrode receiving surface portion,
 - providing a plurality of first electrodes directly on said electrode receiving surface portion having substantially constant wetting tension,
 - leaving intermediate portions of said electrode receiving surface portion free from said electrodes, wherein each intermediate portion is usually arranged spatially between at least a pair of two first electrodes,
 - providing a layer of electrolyte directly on each one of said plurality of electrodes,
- wherein

the wetting tension of the electrode receiving surface portion acts repelling on said electrolyte, and the wetting tension of said electrodes acts wetting on said electrolyte.

- 5 Examples of advantageous embodiments of the aspects present above are given below.

In relation to the aspects presented above, the substrate is formed of a first composition or material having a first wetting tension. Additionally or alternatively, the electrodes are formed of a second composition or material
10 having a second wetting tension.

In relation to the aspects presented above, and at a completion of the self-alignment of the electrolyte, the electrolyte is concentrated to the surfaces of the plurality of first electrodes and the surfaces of the intermediate portions
15 are substantially free of electrolyte.

According to one example the electrodes having a thickness of e.g. between 0.01 and 100 μm , or between 0.05 and 50 μm , or between 1 and 20 μm , or between 1 and 15 μm . In other words, the thickness of the electrodes is
20 normally at least 0.05 μm , or at least 0.1 μm or at least 0.5 μm or at least 1 μm . Alternatively or additionally, the thickness of the electrodes is at most 100 μm , or at most 50 μm , or at most 30 μm or at most 15 μm , or at most 10 μm . One printed electrode layer may e.g. be between 1 and 10 μm thick and a number of layers may be printed on top of each other. In relation to this
25 invention the thickness of the electrodes are measured in a direction normal to the substrate surface.

According to one example the electrolyte has a thickness of e.g. between 1 and 200 μm , or 5 and 150 μm , or 5 and 115 μm , or 10 and 100 μm , or 10 and
30 70 μm , or 10 and 60 μm . In other words, the thickness of the electrolyte is normally at least 1 μm , or at least 5 μm , or at least 10 μm , or at least 15 μm . Additionally or alternatively, the thickness of the electrolyte is at most 200 μm , or at most 150 μm , or at most 115 μm , or at most 100 μm , or at most 70 μm , or at most 60 μm .

35

All the figures for the electrolyte thickness in the section above refer to the thickness of the electrolyte when wet (or just applied). After the electrolyte

has dried it is normally thinner. In relation to this invention the thickness of the electrolyte is measured in a direction normal to the substrate surface.

5 According to one example the viscosity of the electrolyte is lower than 7 000 mPa s, or lower than 6 000 mPa s, or lower than 3 000 mPa s, or lower than 1 000 mPa s, or lower than 500 mPa s.

According to one example said substrate is flexible. This is advantageous as it allows for e.g. a roll-to-roll production process.

10

According to one example, said layer of electrolyte is applied as one unitary layer covering said plurality of first electrodes and said intermediate portions. A unitary electrolyte layer is advantageous as it facilitates the application of the electrolyte layer.

15

Moreover, said layer of electrolyte is usually applied as a substantially uniform layer. This is advantageous as it normally produces a device having an equal amount of electrolyte on each electrode, i.e. the performance of two such electrodes are normally more similar, compared to electrodes being covered by a substantially different amount of electrolyte.

20

One way of providing a substantially unitary and uniform layer of electrolyte is by the use of wire-bar coating, which facilitates high volume manufacturing.

25 In relation to this invention the term *unitary layer* refers to a continuous layer, which is continuous at least until it starts to dewet or rupture.

In relation to this invention the term *uniform layer* refers to a layer having a substantially even thickness, at least until it starts to dewet or rupture.

30

According to one example the application of the layer of electrolyte further comprises self-alignment of said electrolyte layer, which arranges the electrolyte on the surfaces of said plurality of first electrodes and substantially not on the surfaces of the intermediate portions.

35

According to one example, a second set of electrodes is provided to said electrolyte, such that said electrolyte is sandwiched between a pair of a first

electrode and a second electrode. Moreover, the electrolyte is preferably in ionic contact with both the first electrode and the second electrode in the pair of one first electrode and one second electrode.

- 5 According to one example said plurality of first electrodes and/or said plurality of second electrodes and/or said layer of electrolyte is provided by means of printing or coating, and preferably is provided by means of a technique selected from a group comprising screen printing, wire-bar coating, knife coating, bar coating, spin coating, dip coating or spray coating. This is
10 advantageous as it normally allows for short manufacturing times.

According to one example the electrolyte is arranged such that it dissociates into smaller and substantially larger ion-complexes, where the smaller ion-complexes have a first electric charge and the larger ion-complexes have the
15 opposite electric charge. The larger ion-complexes preferably comprise long polymer chains or large molecules, and are preferably cations. In other words, according to one preferred example the electrolyte is a polyelectrolyte or an oligomeric electrolyte comprising larger cation-complexes.

- 20 According to one example the layer of electrolyte comprises cations and anions, wherein a major part of the anions have a substantially smaller molecular weight compared to the largest of the cations.

According to one example, the method further comprises the step of
25 selecting, extracting or cutting out said first portion of the substrate from the rest of the substrate, for use in an electrochemically active device. Normally, the selected first portion of the substrate comprises at least 5 x 7 electrodes arranged in a matrix configuration. It may also comprise several such 5x7 units, e.g. 25x7 electrodes, or 100x35 electrodes.

30

According to one example there is provided a process for manufacturing an electrochemically active device comprising:

- manufacturing of a part of an electrochemically active device as described above;
- 35 - providing a plurality of second electrodes, wherein said layer of electrolyte is sandwiched between pairs of one first electrode and one second electrode. In other words, in the electrochemical device respective portions of the

electrolyte layer is sandwiched between pairs of one first electrode and one second electrode. In more detail, said one first electrode is selected from said plurality of first electrodes of said electrochemically active device described above, and

- 5 said one second electrode is selected from said provided plurality of second electrodes. Furthermore, the electrolyte may provide an ionic connection between said pairs of one first electrode and one second electrode, e.g. by being arranged in direct ionic contact with first and second electrodes. The second electrodes may be provided by means of e.g. a printing method
- 10 as described for said first electrode. The second electrodes may also be applied by means of lamination, i.e. the second electrodes are printed on a separate substrate which is thereafter laminated on the substrate whereon said first electrodes are provided. In this case, the deposition of a conducting material, e.g. a transparent metal oxide or a conducting polymer, might be
- 15 required before printing said second electrodes in order to establish electrical connection to each second electrode.

- According to one example each one of said first electrodes comprises electrochemically active material or is electrochemically active. Additionally or
- 20 alternatively each one of said first electrodes comprises electrochromic material or is electrochromic. Additionally or alternatively, each one of said first electrodes is arranged of electrochemically material comprising electrochemically active material and/or electrochromic material.

25 DEFINITIONS

In addition to what have been explained above in relation to different expressions, the following also applies in relation to this invention.

- Electrochemically active: an "electrochemically active" layer or an
- 30 "electrochemically active" material according to the present invention, is a piece of a material having the ability of electrochemically altering its redox state. The change of redox state may be achieved by oxidation or reduction reactions, for example, by applying a potential difference across the electrochemically active material, wherein at least a portion of the
- 35 electrochemically active material is in ionic contact with an electrolyte. For example, the electrochemically active material may be a material which has

the ability of electrochemically altering its electrical conductivity through change of redox state thereof. The electrochemically active material may be patterned and/or printed into different shapes, and is composed of one material or a combination of materials. The material(s) may be organic or
5 inorganic, molecular or polymeric. Independent of if the electrochemically active material is composed of one material or is an ensemble of more than one material, at least one material is electronically conducting in at least one oxidation state. The electrochemically active material may also be an electrochromic material which has the ability of electrochemically altering its
10 color through change of redox state thereof. The features of the electrochemically active material may be used in e.g. sensing devices, optoelectronic devices, actuators, wettability switching, and microfluidic devices, the list is not exhaustive. The electrochemically active layer may furthermore be coupled to an electrode, being composed of the same or different
15 materials.

Electrochromic: an "electrochromic" layer or an "electrochromic" material in relation to this invention is a continuous geometrical body, which can be patterned and/or printed into different shapes, and is composed of one
20 material or a combination of materials. The material(s) may be organic or inorganic, molecular or polymeric. Such an electrochromic element, whether it is composed of one material or is an ensemble of more than one material, combines the following properties: at least one material is electrically conducting in at least one oxidation state, and at least one material is
25 electrochromic, i.e. exhibits color change as a result of electrochemical redox reactions within the material. Optionally, the electrochromic layer or material may comprise an electrochemically active material.

Contact portion: as used herein, a contact portion of an electrochemically
30 active layer is a portion of the layer which surface on at least one side of the layer is in direct contact with electrolyte, i.e. shares a common interface with an electrolyte.

Color change: when reference is made to "color change", this include changes in optical density or reflectance, so that "color change" for example takes into account changes from blue to red, blue to colorless, colorless to blue, dark blue to light blue, grey to white or dark grey to light grey alike.

5

Electrochromic display: an "electrochromic display" is in relation to this invention a device comprising a plurality of electrochromic pixel elements, wherein each pixel element comprises an electrolyte sandwiched between e.g. a pixel electrode and a counter electrode, wherein at least said pixel electrode is arranged of electrochromic and electrochemically active material. A pixel element may be operated by applying a potential difference between the pixel electrode and the counter electrode, wherein the potential difference controls an electrochemical reaction. In turn, the electrochemical reaction controls, or results in, the coloring or de-coloring of the pixel element. The pixel element is normally arranged such that a color change of the electrochromic element is visually detectable in reflection and/or in transmission.

Solidified electrolyte: for the purposes of the invention, "solidified electrolyte" means an electrolyte that is solid or semi-solid and which at the temperatures at which it is used is sufficiently rigid that particles/flakes in the bulk therein are substantially immobilized by the high viscosity/rigidity of the electrolyte and that it does not flow or leak. For example, such an electrolyte has the proper rheological properties to allow for application of this material on a support in an integral sheet or in a pattern, for example by conventional printing or coating methods. After deposition, the electrolyte formulation should solidify upon evaporation of solvent or because of a chemical cross-linking reaction, brought about by additional chemical reagents or by physical effect, such as irradiation by ultraviolet, infrared or microwave radiation, cooling or any other such. The solidified electrolyte may for example comprise an aqueous or organic solvent-containing gel, such as gelatin or a polymeric gel. However, solid polymeric electrolytes are also contemplated and fall within the scope of the present invention. Furthermore, the definition also

encompasses liquid electrolyte solutions soaked into, or in any other way hosted by, an appropriate matrix material, such as a paper, a fabric or a porous polymer.

- 5 Electrodes: "electrodes" in devices according to the invention are structures comprising electronically conducting material and which structures may be connected to e.g. a portion of an electrochemically active layer which portion in turn may be in direct contact with the electrolyte. Alternatively, at least a portion of the electrode may also be in direct contact with the electrolyte. The
- 10 electrodes of the device are typically used for connecting the device to a power source, or may also be used to connect the device as a component in an electrical circuit, or in connection with other circuit components. Electrodes may be used to facilitate a matrix configuration of a plurality of devices, such as an active matrix addressed configuration of devices. In addition, an
- 15 electrode may also be composed of the same material or similar material as the pixel electrode or the counter electrode and therefore form a continuous, or unitary, piece of material which is electrically conducting and comprises a portion that is in direct contact with the solidified electrolyte. Hence, the electrochemically active material, or layer, may at least partly form an
- 20 electrode; or a portion of an electrochemically active material may form a portion of an electrode which thereby forms a conductive path to an electrochemically active region of the device. For example, by applying a first electrical potential in an electrode of the device, such as the first electrode of the device, and applying a different potential to the second electrode of the
- 25 device, a potential difference is provided in the device and the redox state of the electrochemically active device may be controlled and switched.

Layer: according to some embodiments, the electrochemically active device has a laminate structure and consists of "layers" of different materials. These

30 layers can be continuous or patterned, and can be applied to each other (self-supporting device) or to a support or carrier (supported device). The layers may be flexible. Furthermore, the term layer may encompass all elements of the same material in the same plane, regardless whether this material is

patterned or interrupted in such a way as to form discontinuous "islands" in the plane.

Direct electrical contact: Direct physical contact (common interface) between two phases (for example between electrolyte and electrode) that allows for the exchange of charges through the interface. Charge exchange through the interface can comprise transfer of electrons between electrically conducting phases, transfer of ions between ionically conducting phases, or conversion between electronic current and ionic current by means of electrochemistry at an interface between for example active layer and electrolyte or electrolyte and electrochromic element.

Direct electronic contact: Direct physical contact (common interface) between two phases (for example active layer and electrode) that allows for the exchange of electrons through the interface. Charge exchange through the interface can comprise transfer of electrons between electrically conducting phases.

Direct ionic contact: Direct physical contact (common interface) between two phases that allows for electrochemical reactions, such as redox reactions, i.e. reduction or oxidation reactions.

Corresponding surface tension: A liquid or composition having a corresponding surface tension equal to X [N/m], will hold together for more than 2 s when arranged on a substrate having a wetting tension [N/m] higher than or equal to X [N/m] as determined in accordance with ISO 8296:2003 (E), and break up when arranged on a substrate having a wetting tension [N/m] lower than X [N/m]. The liquid or composition should be applied on the substrate in accordance with points 7.1 and 7.2 of ISO 8296:2003 (E).

30

The term corresponding surface tension is intended to be used for liquids and compositions where the viscosity is substantially higher than the viscosity of the test liquids described in ISO 8296:2003 (E). Due to the high viscosity no

simple determination/measurement of the surface tension can be made, therefore the term corresponding surface tension is used. However, the corresponding surface tension of a liquid or composition is easily determined by applying the liquid or composition on different substrates having a known wetting tension, in analogy with the same stepwise manner described in ISO 8296:2003 (E) for determining the wetting tension.

For a liquid or composition having a measurable surface tension, the corresponding surface tension of that liquid or composition is equal to the surface tension of that liquid. In general, the corresponding surface tension of a liquid/composition may be increased by adding to the liquid/composition a solvent having a higher surface tension than the liquid/composition; and decreased by removing solvent from the liquid/composition, or by adding to the liquid/composition a solvent having a lower surface tension than the liquid/composition. Naturally, the selected solvent should be compatible with the liquid/composition.

Materials

According to one example, the solidified electrolyte comprises a binder. For example, the binder has gelling properties and is e.g. selected from the group consisting of gelatine, a gelatine derivative, polyacrylic acid, polymethacrylic acid, poly(vinylpyrrolidone), polysaccharides, polyacrylamides, polyurethanes, polypropylene oxides, polyethylene oxides, poly(styrene sulphonic acid), and salts and copolymers thereof; and may optionally be cross-linked. The solidified electrolyte may further comprise an ionic salt, for example magnesium sulphate if the binder employed is gelatine. The solidified electrolyte may further contain a hygroscopic salt such as magnesium chloride to maintain the water content therein. Independent of if the solidified electrolyte comprises a binder, it may comprise a polymer having quaternary ammonium groups, such as polymers bearing imidazolium groups. Examples are polyquaternium grades, preferably copolymers with quaternized vinylimidazole units, such as Luviquat Excellence provided by BASF.

The electrochemically active device may comprise, as electrochemically active material, a polymer which may be electrically conducting and/or electrochromic in at least one oxidation state, and optionally also comprises a polyanion compound.

- 5 Electrochemically active polymers for use in the electrochemically active device of the invention are for example selected from the group consisting of polythiophenes, polypyrroles, polyanilines, polyisothianaphthalenes, polyphenylene vinylenes and copolymers thereof, such as described by J C Gustafsson et al in Solid State Ionics, 69, 145-152
10 (1994); Handbook of Oligo- and Polythiophenes, Ch 10.8, Ed D Fichou, Wiley-VCH, Weinheim (1999); by P Schottland et al in Macromolecules, 33, 7051-7061 (2000); by M Onoda in Journal of the Electrochemical Society, 141, 338-341 (1994); by M Chandrasekar in Conducting Polymers, Fundamentals and Applications, a Practical Approach, Kluwer Academic
15 Publishers, Boston (1999); and by A J Epstein et al in Macromol Chem, Macromol Symp, 51, 217-234 (1991). In an embodiment, the electrochemically active polymer is a polymer or copolymer of a 3,4-dialkoxythiophene, in which said two alkoxy groups may be the same or different or together represent an optionally substituted oxy-alkylene-oxy
20 bridge. In yet an embodiment, the polymer is a polymer or copolymer of a 3,4-dialkoxythiophene selected from the group consisting of poly(3,4-methylenedioxythiophene), poly(3,4-methylenedioxythiophene) derivatives, poly(3,4-ethylenedioxythiophene), poly(3,4-ethylenedioxythiophene) derivatives, poly(3,4-propylenedioxythiophene), poly(3,4-
25 propylenedioxythiophene) derivatives, poly(3,4-butylenedioxythiophene), poly(3,4-butylenedioxythiophene) derivatives, and copolymers therewith. Charge neutrality of the chemically doped electrochemically active polymer is maintained by, for example, a polyanion compound such as poly(styrene sulfonate) sodium salt. As is readily appreciated by the skilled man, the
30 electrochemically active layer may comprise any non-polymer material, combination of different non-polymer materials, or combination of polymer materials with non-polymer materials, which may exhibit conductivity in at least one oxidation state, and optionally electrochromic behavior. For

example, one could use a composite of an electrically conducting material and an electrochromic material, such as electrically conductive particles such as tin oxide, ITO or ATO particles with polymer or non-polymer electrochromic materials such as polyaniline, polypyrrole, polythiophene, nickel oxide, polyvinylferrocene, polyviologen, tungsten oxide, iridium oxide, molybdenum oxide and Prussian blue (ferric ferrocyanide). As non-limiting examples of electrochemically active material mention can be made of: a piece of PEDOT-PSS, being both conducting and electrochromic; a piece of PEDOT-PSS with $\text{Fe}^{2+}/\text{SCN}^-$, PEDOT-PSS being conducting and electrochromic and $\text{Fe}^{2+}/\text{SCN}^-$ being an additional electrochromic component; a piece composed of a continuous network of conducting ITO particles in an insulating polymeric matrix, in direct electrical contact with an electrochromic WO_3 -coating; a piece composed of a continuous network of conducting ITO particles in an insulating polymeric matrix, in contact with an electrochromic component dissolved in an electrolyte. According to one embodiment of the present invention, an electrochromic pixel device may comprise a further electrochromic material for realization of displays with more than one color. This further electrochromic material can be provided within the electrochromic pixel element or the solidified electrolyte, which then for example comprises an electrochromic redox system, such as the redox pair of colorless Fe^{2+} and SCN^- ions on one hand, and of red $\text{Fe}^{3+}(\text{SCN})(\text{H}_2\text{O})_5$ complex on the other. By way of further, non-limiting examples, such materials may be selected from different phenazines such as DMPA - 5,10-dihydro-5,10-dimethylphenazine, DEPA - 5,10-dihydro-5,10-diethylphenazine and DOPA - 5,10-dihydro-5,10-dioctylphenazine, from TMPD - N,N,N',N'-tetramethylphenylenediamine, TMBZ - N,N,N',N'-tetramethylbenzidine, TTF - tetrathiafulvalene, phenanthroline-iron complexes, erioglaucin A, diphenylamines, p-ethoxychrysoidine, methylene blue, different indigos and phenosafranines, as well as mixtures thereof.

The properties of the electrochemically active material in the electrochemically active device may be used for sensor applications, optoelectronic devices, actuators, wettability switching, and microfluidic devices. In addition, the electrochemically active devices according to the present

invention may find various applications in the field of printed electronics, for example ranging from sensors and single pixel devices to logic circuits and large active matrix addressed display systems, the listing is not exhaustive.

Generally, other objectives, features, and advantages of the present invention will appear from the following detailed disclosure, from the attached dependent claims as well as from the drawings.

Brief description of the drawings

The above, as well as additional objects, features and advantages of the present invention, will be better understood through the following illustrative and non-limiting detailed description of preferred embodiments of the present invention, with reference to the appended drawings, where the same reference numerals will be used for similar elements, wherein:

- figures 1a-1f are schematic drawings illustrating photos taken of the production process;
- figures 2a-2e are schematic drawings illustrating photos taken of the production process, and more specifically illustrating the alignment of the electrolyte to the electrodes,
- figures 3a-3d are photos of parts of an electrochemically active device being produced with varying electrolyte thickness,
- figure 4 is a photo of a part of an electrochemically active device,
- figure 5 illustrates four electrodes and different measures used herein,
- figures 6a and 6b illustrate two results of different electrode distances.

Detailed description of embodiments

Figures 1a-e are a schematic illustration of a process for manufacturing at least a part of an electrochemically active device 100. In all these figures a three dimensional view is presented to the left, and a cross-section of the three dimensional view to the right. In Fig. 1a, a substrate 110 is provided comprising an electrode receiving surface portion 111, which electrode receiving surface portion has a substantially uniform wetting distribution or wetting tension. According to this example the substrate is a flexible PET-foil. Thereafter, Fig. 1b, a plurality of first electrodes 120 are provided directly on the electrode receiving surface portion 111 of said substrate 110 by conventional means. The first electrodes 120 are provided in a predetermined pattern, e.g. in a matrix configuration here comprising equally spaced rows

and columns, leaving intermediate portions 130 or intermediate substrate portions 130 between the electrodes. When the electrodes are arranged in a matrix configuration as illustrated in Fig. 1b, the intermediate portions are arranged in intermediate rows separating the electrode rows from each other; and arranged in intermediate columns separating the electrode columns from each other. In a matrix configuration the distances between two adjacent rows may vary throughout the matrix, and the distances between two adjacent columns may also vary. Further, the angle between a crossing row and column may be orthogonal or non-orthogonal. In the current example there is an equal distance between all adjacent rows and columns, respectively, and the angle between all pairs of crossing rows and columns is orthogonal. The intermediate portions 130 are free of electrodes, i.e. the intermediate portions are not covered by any electrodes. Following this, an amount of electrolyte 141 is provided, as illustrated in Fig. 1c, and the electrolyte 141 is applied as a layer of electrolyte 140 covering said plurality of first electrodes 120 and said intermediate portions 130 of the substrate, as illustrated in Fig. 1d. The wetting properties or surface tension of the electrolyte 140 and the wetting properties or wetting tension of the substrate are selected such that the electrolyte is repelled from said intermediate portions of said substrate, making the intermediate portions of said substrate substantially free of electrolyte, as illustrated in Fig. 1e.

Above has been described the manufacturing process of at least a part of an electrochemically active device consisting of a substrate 110, a plurality of first electrodes 120, and a layer of electrolyte 140 covering said plurality of first electrodes, as illustrated in Figure 1e.

To obtain an electrochemically active device, which may be electrically controlled, a plurality of second electrodes 125 are provided on top of said layer of electrolyte, as illustrated in Figure 1f. In Figure 1f, each electrolyte layer portion 126 is arranged between a respective pair of one first electrode 121 and one second electrode 126. To achieve an electrochemically active device, at least one of the electrodes 121, 126 in each pair of electrodes must be arranged of electrochemically active material. In order to achieve an electrochromic pixel device or a display, at least one of the electrodes 121, 126 in each pair of electrodes must be arranged of electrochromic and

electrochemically active material. In order for the colour change to be visible, any layer covering the electrode is at least partly transparent.

Figures 2a-2e illustrates the self-controlled deposition process, or the automatic alignment process, of the electrolyte on the electrode surfaces. Figure 2a illustrates the substrate after the electrodes have been applied, i.e. the same state as illustrated in Figure 1b. At this instance, the time recording begins, $T = 0$ seconds. At $T = 5$ seconds, the application of the electrolyte is initiated; a predetermined amount of electrolyte is uniformly applied as a unitary layer on the electrode surfaces and on the intermediate substrate portions. Figure 2b illustrates the situation when the electrolyte has just been applied, $T = 6$ seconds. As can be seen in the figure the electrolyte layer has started to split up at those intermediate portions where the electrolyte was first applied, the rest of the layer is still unitary. At $T = 7$ seconds about half of the intermediate portions are substantially free of electrolyte, the electrolyte layer has started to split up at the intermediate portions which are arranged substantially at the middle of the matrix, while the electrolyte layer is still unitary at those intermediate portions where the electrolyte layer was last applied, this is illustrated in Fig. 2c. Fig. 2d illustrates the situation at $T = 9$ seconds, where substantially all the intermediate portions are free of electrolyte. Fig. 2e illustrates the situation at $T = 10$ seconds, where all intermediate portions are free of electrolyte, the electrolyte being confined to the electrode surfaces. Hence, this arrangement is the same as the one illustrated in Fig. 1e. As can be seen in the Figures the electrolyte adheres to the electrodes, which attract the electrolyte, and is repelled from the intermediate substrate portions.

EXPERIMENTS

Self-alignment test

All samples were prepared according to the following: All materials were used with neither pre-treatment nor purification. Each printed material was patterned into 64×64 squares by using screen printing, by using a 120/34 mesh consisting of 120 threads/cm with a thread diameter of $34 \mu\text{m}$, on a plastic substrate, where each square had an area of approximately $0.8 \times 0.8 \text{ mm}^2$ and a pitch equal to 1 mm. Drying or curing of the printed material, typically at 100°C during 5 minutes, was followed by bar-coating of a uniform electrolyte layer by using wire-bar #4 (manufactured by R. D. Specialties,

Inc.), which results in a wet thickness of approximately 10 μm . The electrolyte was prepared with approximately 10 wt.-% of TiO_2 powder, KRONOS 2300 manufactured by KRONOS, for whiteness and opaqueness (detailed electrolyte compositions is given below). Finally, the self-alignment capability was evaluated by observing whether the electrolyte layer could be automatically patterned on top of the squares of the printed material or not.

The substrates, printed materials and electrolytes are referred to as follows.

Substrate:

- (A) Melinex 454 PET film (manufactured by DuPont, 50 μm thickness)
- (B) DIAFOIL T100G PET foil (manufactured by Mitsubishi Polyester film Corporation, 75 μm thickness)
- (C) Coated side of the COSMOSHINE A4100 PET foil (manufactured by TOYOBO Co, Ltd., 50 μm thickness)
- (D) Uncoated side of the foil (C)

Printed material:

- (a) 7102 Carbon Conductive Composition (paste manufactured by DuPont)
- (b) ELECTRODAG PF-407A (manufactured by Acheson, conductive carbon paste)
- (c) CLEVIOS S V3 (manufactured by Heraeus, conductive PEDOT:PSS screen printing paste)
- (d) Ag5000 (manufactured by DuPont, conductive silver screen printing paste)
- (e) 20wt.% carbon black (ENSACO conductive carbon black powder manufactured by Timcal) / 20 wt.% polyvinyl butyral (MOWITAL B20H manufactured by Kuraray) / 60 wt.% dilutant (Thinner 3610 manufactured by DuPont)

Electrolyte:

- (1) Poly(vinylpyrrolidone)-co-(vinyl-3-methyl imidazolium chloride) (Luviquat Excellence distributed by BASF, 40 wt.% solid content dissolved in water, M.W. = 40000, Poly(vinylpyrrolidone)(VP)/ vinyl-3-methyl imidazolium chloride (VI) = 5/95)

- (2) Poly(diallyl dimethyl ammonium chloride) (distributed by Sigma-Aldrich, M.W. = 400000-500000, 20 wt.% solid content dissolved in water)
- (3) Sodium poly(styrene sulfonate) (distributed by Alfa Aesar, M.W. = 70000, 40 wt.% solid content dissolved in water)
- 5 (4) Poly(styrene sulfonic acid) (distributed by Polyscience, M.W. = 70000, 30 wt.% solid content dissolved in water)
- (5) (5) 1-ethyl-3-methylimidazolium ethyl sulfate, including 5 wt.% hydroxyethyl cellulose

10

By visual inspection the following conclusions were drawn with respect to the resulting yield for different combinations of substrates and electrodes, as noted in Table Ia and Ib:

Table Ia Visual inspection of self alignment test

Electrolyte 1		Substrate			
		(A) M454	(B) T-100G	(C) A4100 coat	(D) A-4100 uncoat
Electrode	(a) 7102	100	0	0	30-40
	(b) PF-407A	100	0	0	30-40
	(c) S V3	90-100	0	0	0
	(d) Ag5000	90	0	0	70-80
	(e) ENSACO C	90			

Table Ib Visual inspection of self alignment test

Substrate A		Electrolyte			
		2	3	4	5
Electrode (a) 7102		100	0	0	0

15

The values are defined in %-scale, where 0% and 100% correspond to no self-alignment and complete self-alignment, respectively.

The wetting tensions of different substrates were determined by following ISO 8296:2003 (E), and the results are indicated in Table II.

20

Table II Wetting Properties

		Adhesion energy relative water (mJ/m ²)	Wetting Tension (mN/m)
Electrode	(a) DuPont "7102 Carbon Conductive Composition"	10.9	>73.0
	(b) Acheson "ELECTRODAG PF-407A"	10.7	>73.0
	(c) Heraeus "CLEVIO S V3"	5.9	>73.0
	(d) DuPont silver conductor paste "Ag5000"	11.5	35.0
	(e) ENSACO Carbon	11.4	49.0
Substrate	(A) DuPont "Melinex454"	7.9	42.0
	(C) T-100G	4.9	>73.0
	(D) A-4100 coated surface	7.4	63.0
	(E) A-4100 PET surface	7.1	38.0

A wetting tension being referred to as >73.0 mN/m indicates that even when a test mixture having a surface tension of 73.0 mN/m was applied on the substrate, the liquid film held together for more than 2 seconds. A wetting tension of 35.0 mN/m indicates that when a test mixture having a surface tension of 35.0 mN/m or higher was applied on the substrate, the liquid film broke up in less than 2 seconds.

Also the electrodes are referred to as having a wetting tension. The wetting tension for an electrode material is determined in an analogous way as for the substrates. I.e. layers of the electrode material are applied to a surface, and the same type of test mixtures as described in ISO 8296:2003(E) are applied to the surface in accordance with the instructions therein.

15

The adhesion energy relative deionized water is measured by a dynamic contact angle meter (Dropmaster DM-701, manufactured by Kyowa Interface Science Co., Ltd.), wherein the sliding method is used for determination of the values. In more detail, in this method the adhesion energy of a test surface is measured by putting a deionized water droplet on the test surface, and gradually tilting the test surface until the droplet started to slip down; then the angle of the test surface against the horizontal ground is recorded, and finally the adhesion energy of the test surface relative deionized water is calculated using the formula of; $E = (mg \cdot \sin \alpha) / (2\pi r)$. Here r is radius of the droplet on the test surface, m is the weight of the droplet, g is the acceleration of gravity and α is the angle of the tilted test substrate when the droplet starts to slip down.

25

By visual inspection the following conclusions were drawn with respect to the resulting yield when different dilutions of Luviquat Excellence (electrolyte (1)) were used, as noted in Table III:

Amount Luviquat Excellence (%)	Solid content dissolved in water (wt.%)	Viscosity (mPa s)	Visual inspection of SEP
100.0	40.0	310	100
95.0	42.1	420	100
90.0	44.4	780	100
85.0	47.1	1650	95-100
80.0	50.0	3500	95-100
77.5	51.6	5190	95
75.0	53.3	7410	90
67.8	59.0	> 10000	0

5

Visual inspection of surface energy patterning (SEP): the values are defined in %-scale, where 0% and 100% correspond to no self-alignment and complete self-alignment, respectively.

10

As is known in the art, electrolytes having a viscosity higher than about 7 000 mPa s are not printable. In relation to this inventions, a printable electrolyte means an electrolyte which is uniformly coatable and/or uniformly printable by conventional coating and/or printing means; such printable electrolytes have a viscosity which is lower than 7 000 mPa s. Additionally, and as is readily seen in the table, the higher the viscosity the lower the yield; at least when the viscosity is higher than about 800 mPa s.

15

The experiment reported in Table III was performed by first measuring the viscosity of undiluted Luviquat Excellence, and visually determining its yield in a self alignment test when coated on a substrate type (A) carrying electrodes of type (a).

20

The viscosity was measured by means of Digital Rotoviscometer 455N/65, manufactured by Sheen Instruments, except for the electrolyte sample having a solid content of 59, which was measured by a Sine-Wave Vibro Viscometer, Sv-10. The viscosity limits for the two viscometers is approximately 7 000 mPa s and approximately 10 000 mPa s, respectively. None of the

25

instruments were able to give a result for the electrolyte sample having a solid content of 59. Hence, all that can be said of the viscosity of that electrolyte is that it is higher than 10 000 mPa s.

- 5 Additionally, measurements have been made in order to determine the corresponding surface tension of the Electrolytes (1) to (5). 5 samples of each of the Substrates (A) to (D) were provided, and one sample of each substrate was coated with a respective one of said Electrolytes (1) to (5). The applied electrolyte layer had an approximate thickness of 18 μm when wet.

10

The performance of the respective electrolytes on the respective sample is presented in Table IV.

Table IV		Electrolytes				
Substrate	Wetting tension (mN/m)	(1) LQ	(2) PDMAC	(3) PSSNa	(4) PSSH	(5) EMIES-HEC
(A) M454	42	Rupture	Rupture	Wet	Wet	Wet
(C) T-100G	>73	Wet	Wet	Wet	Wet	Wet
(D) A4100 (Ct)	63	Wet	Wet	Wet	Wet	Wet
(E) A4100 (un-Ct)	38	Rupture	Rupture	Wet	Wet	Wet

15

As explained above the wetting tension of a surface may be determined by arranging test liquids having different surface tensions on the surface, starting with a test liquid having a low surface tension, which wets the surface, and gradually applying test liquids having a higher surface tension until the liquid breaks up within 2 s after the application thereof. In other words, when the surface tension of the liquid exceeds the wetting tension of the surface, it breaks up.

20

- As can be seen in the table, electrolyte (1) breaks up when being arranged on substrate (A) having a wetting tension of 42 mN/m or substrate (E) having a wetting tension of 38 mN/m; but wets when it is arranged on substrate (C) having a wetting tension higher than 73 mN/m or substrate (D) having a wetting tension of 63 mN/m. Consequently, the corresponding surface tension of electrolyte (1) is higher than 38 and 42 mN/m; and lower than or equal to 63 and >73 mN/m, i.e. between 43 and 63 mN/m.

30

Furthermore, electrolyte (3) does not break up on any of the substrates; but wets on all of them. Consequently, the corresponding surface tension of electrolyte (3) is higher than 73 mN/m.

5 In summary, the following conclusions of the corresponding surface tension can be drawn:

Electrolytes (1) and (2) have a corresponding surface tension which is higher than 42 mN/m and lower than 63 mN/m;

10 Electrolytes (3), (4) and (5) have a corresponding surface tension which is higher than 73 mN/m.

The inventors have learnt that the thickness of the applied electrolyte has an effect on the yield of the manufacturing process is determined. The devices illustrated in Figures 3a-3d were all produced using substrate (A) Melinex 454
15 provided with electrodes (e) carbon paste 7102 and applying electrolyte (1) Luviquat. The samples were all prepared as described in relation to the self alignment-test, except that the electrolyte thickness varied for each sample. A first sample having an electrolyte wet film thickness of about 9 μm is illustrated by a photograph in Figure 3a, and with a microscope close up in
20 Figure 3a'. As can be seen in the Figures all electrodes are ionically isolated from each other, making the yield 100 %. In other words, all electrodes are useable.

A second sample having an electrolyte wet film thickness of about 27 μm is
25 illustrated by a photograph in Figure 3b, and with a microscope close up in Figure 3b'. As can be seen in the Figures all electrodes are ionically isolated from each other, making the yield 100 %.

A third sample having an electrolyte wet film thickness of about 60 μm is
30 illustrated by a photograph in Figure 3c, and with a microscope close up in Figures 3c' and 3c''. Figure 3c' illustrates an area of the sample where six electrodes are ionically isolated from each other. In Figure 3'' five of the electrodes are ionically connected to each other by the electrolyte. Most of the intermediate portions shown in Figure 3c'' are not substantially free of
35 electrolyte. In summary, as can be seen in the Figures most electrodes are ionically isolated from each other, and the yield is estimated to > 90 %. In

other words, > 90 % of the electrodes are not in ionic contact with any other electrode.

5 A fourth sample having an electrolyte wet film thickness of about 115 μm is illustrated by a photograph in Figure 3d. As can be seen in the Figures many of the electrodes are ionically isolated from each other, and the yield is estimated to 70 %. In other words, 70 % of the electrodes are not in ionic contact with any other electrode. All or some of these ionically separated electrodes may be selected, e.g. by being cut out from the rest of the
10 substrate, and used in an electrochemically active device.

In other words, the electrolyte thickness is preferably adjusted to the desired yield of the manufacturing process. Based on the teaching in this document the skilled man can easily try different thicknesses until he gets a desired
15 yield.

Figure 4 is a microscope close-up of a sample wherein the all intermediate portions are substantially free of electrolytes. As can be seen in the Figure some electrolyte is present on the intermediate portions, but it is not enough
20 to substantially affect the properties of the electrodes.

Figure 5 is used to illustrate different terms used here in. In the Figure there are four equally sized electrodes, each having a surface area of $a \cdot a = a^2$. The electrodes are separated by a distance b , i.e. the electrode-to-electrode
25 distance or the separating gap is b . The pitch of the electrodes is c . Consequently, the area ratio is $a^2/c^2 - a^2$, the length ratio is a/b and the fill factor is $a^2/c^2 \cdot 100$.

In order to determine the effect of the electrode to electrode distance two
30 samples were prepared. For both samples (A) Melinex 454 was used as the substrate, (a) carbon paste 7102 from DuPont was screen printed. The electrode areas were $1 \times 1 \text{ mm}^2$ or $1 \times 1 \text{ cm}^2$, respectively for the different samples. Both samples had a separating gap between two electrodes of 1 mm in both cases. Luviquat Excellence, into which 10 wt.-% TiO_2 was
35 immersed, was used as the white and opaque electrolyte. Wire-bar #6 (R. D. Specialties, Inc.) was used throughout this experiment, giving a wet film thickness of about 16 μm .

The sample having an electrode area of 1 cm^2 is illustrated in Figure 6a (by a microscope close up) providing a yield of 100 % and the electrodes are fully covered by electrolyte. The sample having an electrode area of 1 mm^2 is
5 illustrated in Figure 6b (by a microscope close up), providing a yield of 100 % and substantially fully covered electrodes. Consequently, the area ratio has a minor impact on the yield of the production process.

The invention has mainly been described with reference to main
10 embodiments. However, embodiments other than the ones disclosed above are equally possible within the scope of the invention, as defined by the appended patent claims. All terms used in the claims are to be interpreted according to their ordinary meaning in the technical field, unless explicitly defined otherwise herein. All references to "a/an/the [element, means,
15 component, member, unit, step etc.]" are to be interpreted openly as referring to at least one instance of said element, means, component, member, unit, step etc. The steps of the methods described herein do not have to be performed in the exact order disclosed, unless explicitly specified.

20

CLAIMS

1. A process for manufacturing of at least a part of an electrochemically active device comprising:
- 5 - providing a substrate (110) comprising an electrode receiving surface portion (111) having substantially constant wetting tension throughout said electrode receiving surface portion,
- providing a plurality of first electrodes (120) directly on said electrode receiving surface portion having substantially constant wetting tension,
- 10 - leaving intermediate portions (130) of said electrode receiving surface portion (111) free from said electrodes,
- providing a printable electrolyte composition having a first corresponding surface tension, - providing a layer of said electrolyte composition (140) directly on each one of said plurality of electrodes,
- 15 wherein
- the electrolyte (140) is applied as a layer covering said plurality of first electrodes (120) and said intermediate portions (130), and
- the wetting tension of the surfaces of the intermediate portions (130) is arranged to act more repelling on the electrolyte compared to the wetting
- 20 tension of the surfaces of the plurality of first electrodes (120), whereby, at least after a predetermined time period and at least throughout a first portion of the substrate, the electrolyte is concentrated to the surfaces of the plurality of first electrodes (120), and the surfaces of the intermediate portions (130) are substantially free of electrolyte.
- 25
2. A process for manufacturing of at least a part of an electrochemically active device comprising:
- providing a substrate (110) comprising an electrode receiving surface portion (111) having substantially constant wetting tension throughout said
- 30 electrode receiving surface portion,
- providing a plurality of first electrodes (120) directly on said electrode receiving surface portion having substantially constant wetting tension,
- wherein the
- leaving intermediate portions (130) of said electrode receiving surface
- 35 portion (111) free from said electrodes,
- arranging said printable electrolyte as a layer of electrolyte (140) directly on each one of said plurality of electrodes,

wherein

- the electrolyte (140) is applied as a layer covering said plurality of first electrodes (120) and said intermediate portions (130), and wherein the material of the first electrodes is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension equal to 73 mN/m are attracted to the electrodes, and
- the composition of the electrode receiving surface portion is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having a surface tension larger than 38 mN/m and smaller than 63 mN/m are repelled from the electrode receiving surface portion.

3. A process for manufacturing of at least a part of an electrochemically active device comprising:

- providing a substrate (110) comprising an electrode receiving surface portion (111) having a substantially constant first wetting tension throughout said electrode receiving surface portion,
 - providing a plurality of first electrodes (120) directly on said electrode receiving surface portion having a substantially constant first wetting tension, wherein the surfaces of said plurality of electrodes have a second wetting tension,
 - leaving intermediate portions (130) of said electrode receiving surface portion (111) free from said electrodes,
 - providing a printable electrolyte (140) having a first corresponding surface tension,
 - arranging said printable electrolyte as a layer of electrolyte (140) directly on each one of said plurality of electrodes,
- wherein
- the electrolyte (140) is applied as a layer covering said plurality of first electrodes (120) and said intermediate portions (130),
 - said first wetting tension of said substrate is lower than or equal to said first corresponding surface tension of said electrolyte, and
 - said second wetting tension of said electrodes is higher than said first corresponding surface tension of said electrolyte.

4. A process for manufacturing of a part of an electrochemically active device comprising:
- providing a substrate comprising an electrode receiving surface portion having substantially constant wetting tension throughout said electrode
- 5 receiving surface portion,
- providing a plurality of first electrodes directly on said electrode receiving surface portion having substantially constant wetting tension,
 - leaving intermediate portions of said electrode receiving surface portion free from said electrodes,
- 10 - providing a printable electrolyte,
- providing a layer of said printable electrolyte directly on each one of said plurality of electrodes,
- wherein
- the electrolyte is applied as a layer covering said plurality of first electrodes
- 15 and said intermediate portions, and
- the adhesion energy of the surface of the printed first electrodes is larger than 10 mJ/m^2 relative deionized water, and
 - the surface properties of the electrode receiving surface portion is selected such that test mixtures prepared according to ISO 8296:2003 (E) and having
- 20 a surface tension larger than 38 mN/m and lower than 63 mN/m are repelled from the electrode receiving surface portion.
5. A process according to any one of the preceding claims, wherein the viscosity of the electrolyte is lower than $7\,000 \text{ mPa s}$, or lower than $6\,000$
- 25 mPa s , or lower than $3\,000 \text{ mPa s}$, or lower than $1\,000 \text{ mPa s}$, or lower than 500 mPa s .
6. A process according to any one of the preceding claims, wherein the wetting tension of the electrode receiving surface portion acts repelling on
- 30 said electrolyte, and the wetting tension of said electrodes acts wetting on said electrolyte.
7. A process according to any one of the preceding claims, wherein the electrolyte has a corresponding surface tension higher than 42 mN/m , or a
- 35 corresponding surface tension between 43 mN/m and 73 mN/m .

8. A process according to any one of the preceding claims, wherein the thickness of the electrodes is between 0.01 μm and 100 μm , or between 0.05 μm and 50 μm , or between 1 μm and 20 μm .
- 5 9. A process according to any one of claims 2-8, wherein at least after a completion of the self-alignment of the electrolyte and at least throughout a first portion of the substrate, the electrolyte is concentrated to the surfaces of the plurality of first electrodes (120), and the surfaces of the intermediate portions (130) are substantially free of electrolyte.
- 10 10. A process according to any one of the preceding claims, wherein said substrate is flexible.
11. A process according to any one of the preceding claims, wherein said layer of electrolyte is applied as one unitary layer covering said plurality of first electrodes and said intermediate portions, and wherein said layer of electrolyte is preferably applied as a substantially uniform layer.
- 15 12. A process according to any one of the preceding claims, wherein the application of the layer of electrolyte further comprises self-alignment of said electrolyte layer, arranging the electrolyte on the surfaces of said plurality of first electrodes and not on the surfaces of the intermediate portions.
- 20 13. A process according to any one of the preceding claims, wherein said plurality of first electrodes and/or said layer of electrolyte is provided by means of printing or coating, and preferably is provided by means of a technique selected from a group comprising screen printing, wire-bar coating, knife coating, bar coating, spin coating, dip coating or spray coating.
- 25 14. A process according to anyone of the preceding claims, wherein the layer of electrolyte comprises smaller and substantially larger ion-complexes, where the smaller ion-complexes have a negative electric charge and the larger ion-complexes have a positive electric charge, and/or wherein said electrolyte is a polyelectrolyte comprising poly-cations.
- 30 15. A process according to anyone of claims 1 or 9 to 14, further comprising the step of extracting said first portion of the substrate from a second part of
- 35

the substrate and providing said first portion for use in an electrochemically active device.

16. A process according to anyone of the preceding claims, wherein said first
5 portion of the substrate comprises at least 5 x 7 electrodes arranged in a matrix configuration.

17. A process according to any one of the preceding claims, wherein the part
10 of an electrochemically active device is a part of an electrochromic display device.

18. A process for manufacturing an electrochemically active device comprising:
- manufacturing of a part of an electrochemically active device according to
15 any one of the preceding claims;
- providing a plurality of second electrodes (125), wherein said layer of electrolyte (140) is sandwiched between pairs of one first electrode (121) and one second electrode (126), and wherein the electrolyte is in ionic contact with both the first electrode (121) and the second electrode (126) of the
20 respective pairs of one first electrode (121) and one second electrode (126).

19. A process for manufacturing an electrochemically active device according to claim 16, wherein said one first electrode is selected from said plurality of first electrodes, and
25 said one second electrode is selected from said plurality of second electrodes.

20. A process according to claim 18 or 19, wherein each first electrode in said plurality of first electrodes (120) and/or each second electrode in said plurality of second electrodes (125) comprises electrochemically active material.
30

21. A process according to any one of claims 18 to 20, wherein each first electrode in said plurality of first electrodes (120) and/or each second electrode in said plurality of second electrodes (125) comprises
35 electrochromic material.




Fig. 1a




Fig. 1b







Fig. 1c

2/6






Fig. 2a




Fig. 2b




Fig. 2c




Fig. 2d




Fig. 2e

4/6




Fig. 3a




Fig. 3a'




Fig. 3b




Fig. 3b'

5/6




Fig. 3c




Fig. 3c'




Fig. 3c''




Fig. 3d

6/6




Fig. 4




Fig. 5




Fig. 6a




Fig. 6b

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2012/056237

A. CLASSIFICATION OF SUBJECT MATTER

INV. G02F1/155 H01L51/05 G03F7/00
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

G02F H01L G03F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, COMPENDEX, INSPEC, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	THOM I ET AL: "Replicative generation of metal microstructures by template-directed electrometallization", APPLIED PHYSICS LETTERS, AIP, AMERICAN INSTITUTE OF PHYSICS, MELVILLE, NY, US, vol. 87, no. 2, 5 July 2005 (2005-07-05), pages 24101-024101, XP012076415, ISSN: 0003-6951, DOI: 10.1063/1.1991992 the whole document	1,6,11, 12,16
A	US 2005/068603 A1 (BERGGREN MAGNUS [SE] ET AL) 31 March 2005 (2005-03-31) paragraph [0005] paragraph [0018] - paragraph [0033] paragraph [0048] paragraph [0076] - paragraph [0078] paragraph [0082] - paragraph [0086]; figure 1 ----- -/-	1,10,13, 14,17-21



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

18 May 2012

Date of mailing of the international search report

12/06/2012

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Cossu, Alessandro

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2012/056237

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2008/126574 A1 (RICOH KK [JP]; TANO TAKANORI [JP]; SUZUKI KOEI [JP]; TSUDA YUSUKE [JP]) 23 October 2008 (2008-10-23) page 13, line 19 - page 15, line 19; figure 1 page 21, line 21 - page 22, line 19 page 24, line 7 - page 26, line 11 page 27, line 23 - page 28, line 18 page 31, lines 1-20; example 1 page 44, line 8 - page 45, line 15; figure 5; example 5 page 54, line 16 - page 55, line 21; figures 7A,7B,8; examples 9-10 -----	1,6

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2012/056237

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2005068603 A1	31-03-2005	US 2005068603 A1	31-03-2005
		US 2007076287 A1	05-04-2007

WO 2008126574 A1	23-10-2008	CN 101627464 A	13-01-2010
		EP 2122672 A1	25-11-2009
		JP 2008227294 A	25-09-2008
		KR 20090117778 A	12-11-2009
		TW 200905936 A	01-02-2009
		US 2010072463 A1	25-03-2010
		WO 2008126574 A1	23-10-2008
