

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
22 March 2007 (22.03.2007)

PCT

(10) International Publication Number
WO 2007/031450 A1

(51) International Patent Classification:

C08K 5/524 (2006.01) *C08K 5/5393* (2006.01)
C08K 5/3492 (2006.01) *C08K 5/5313* (2006.01)

(21) International Application Number:

PCT/EP2006/066045

(22) International Filing Date:

6 September 2006 (06.09.2006)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

05108520.7 16 September 2005 (16.09.2005) EP

(71) Applicant (for all designated States except US): **CIBA SPECIALTY CHEMICALS HOLDING INC.** [CH/CH];
Klybeckstrasse 141, CH-4057 Basel (CH).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MÄDER, Dietmar** [DE/DE]; Katharinengasse 3, 79104 Freiburg (DE).
ROTA-GRAZIOSI, Pierre [FR/FR]; 10, Rue Reichenstein, F-68100 Mulhouse (FR).(74) Common Representative: **CIBA SPECIALTY CHEMICALS HOLDING INC.**; Patent Department, Klybeckstrasse 141, CH-4057 Basel (CH).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2007/031450 A1

(54) Title: POLYURETHANE FLAME RETARDANT COMPOSITIONS

(57) Abstract: The invention relates to a flame retardant composition, which comprises a) At least one ester of a phosphorus containing oxo acid selected from the group consisting of phosphorous and phosphorous acid; b) At least one flame retardant component based on a nitrogen compound; particularly melamine cyanurate, and c) A polyurethane polymer base.

Polyurethane flame retardant compositions

The present invention relates to a flame retardant composition, which comprises a combination of a phosphonite or a phosphite with a nitrogen containing flame retardant and polyurethane polymer base.

5 Thermoplastic polyurethanes (TPU) are useful for many technical applications. Particular reference is made to *Kunststoff-Handbuch, Vol. VII, Polyurethane, Carl Hanser Verlag D-München, 1st Edition 1966, Editors R. Vieweg and A. Höchtlen, and 2nd Edition, Editor G. Oertel.*

Many methods for preparing polyurethanes are known. High molecular weight polyhydroxy compounds, which form the flexible base, for example polyoxyalkylene glycols, such as poly-

10 oxypropylene or polyoxyethylene glycol, polyoxypropylene polyoxyethylene glycol, polyoxybutylene glycol, polyoxybutylene polyoxyethylene glycol or polyoxybutylene polyoxypropylene glycol, or polyesterdiols, such as alkanediol polyadipates, are reacted with aromatic or aliphatic diisocyanates, e.g. diphenylmethane-4,4'-diisocyanate (MDI) or hexamethylene-1,6-diisocyanate (HDI), and low molecular weight chain extenders for the formation of rigid segments, for example alkanediols or dialkylene glycols, such as 1,4-butanediol or diethylene

15 glycol. A disadvantage of TPU is their easy inflammability.

Flame retardants are added to polymeric materials (synthetic or natural) to enhance the flame retardant properties of the polymers. Depending on their composition, flame retardants may act in the solid, liquid or gas phase either chemically, e.g. as a spumescence by liberation 20 of nitrogen, and/or physically, e.g. by producing a foam coverage. Flame retardants interfere during a particular stage of the combustion process, e.g. during heating, decomposition, ignition or flame spread.

Nitrogen-containing flame retardants, especially those based on melamine, have been known for a long time and are, in some cases, commercially available. Some of those melamine derivatives also contain phosphorus. Examples of publications relating to such flame 25 retardants are, *inter alia*, EP-A-782 599, EP-A-1 095 030 and U.S. Patent Specification Nos. 4,010,137 and 3,915,777.

Combinations of nitrogen-containing flame retardants with flame retardants based on phosphorus compounds are also known. In that respect particular reference is made to, for example, DE-A-197 34 437, DE-A-197 37 727, WO-A-97/39053, EP-A-1 070 754, EP-A-6568 and 30 DE-A-196 14 424. Particular phosphates in combination with nitrogen-containing compounds are also known as flame retardants, for example from EP-A-484 832, EP-A-545 496, EP-A-707 036, WO-A-01/98401, GB-A-1 468 188 and EP-A-617 079.

There is a continuing need for flame retardants that have improved thermal and mechanical properties and that can be used in various polymer substrates. In particular, increased safety and environmental requirements mean that hitherto known flame retardants are no longer capable of satisfying all demands.

5 The use of melamine or melamine derivatives as flame retardants for TPU has been proposed in various references. As a further development, the use of melamine cyanurate in combination with organic phosphate in TPU compositions has been proposed, e.g. *U.S. Patent Specification No. 5,837,760*.

It has now been found that the use of a combination of selected flame retardants, particularly 10 flame retardants based on melamine, with esters derivative of a phosphorus containing oxo acid selected from the group consisting of phosphonous and phosphorous acid results in improved thermal and mechanical properties of TPU.

Therefore, the present invention relates to a composition, which comprises

15 a) At least one ester derivative of a phosphorus containing oxo acid selected from the group consisting of oxaphosphorinoxide, phosphonous acid and phosphorous acid;

b) At least one flame retardant component based on a nitrogen compound; and

c) A polyurethane polymer base.

According to a preferred embodiment, the present invention relates to a composition, which comprises

20 a) At least one ester derivative of a phosphorus containing oxo acid selected from the group consisting of phosphonous and phosphorous acid;

b) At least one flame retardant component based on a nitrogen compound; and

c) A polyurethane polymer base.

The compositions according to the invention attain the desirable V-0 rating, according to UL-25 94 (Underwriter's Laboratories Subject 94) and other excellent ratings in related test methods while preserving the excellent mechanical, chemical and thermal properties of thermoplastic polyurethanes, such as colour and light stability.


The composition, as defined above, comprises the following components:

Component a)

The composition according to the present invention comprises as component a) at least one ester derivative of a phosphorus containing oxo acid selected from the group consisting of oxaphosphorinoxide, phosphonous acid and phosphorous acid.


5 According to a preferred embodiment the composition according to the present invention comprises as component a) at least one ester derivative of a phosphorus containing oxo acid selected from the group consisting of phosphonous and phosphorous acid.

Oxaphosphorinoxide has a cyclic structure and is represented by the following general formula:




10

The phosphorous atom and one oxygen atom are part of a cyclic structure, particularly a five or six membered ring, as represented by the following representative compound:




15 Which can be named as 6H-dibenz[c,e][1,2]oxaphosphorin-6-oxide, 3,4:5,6-dibenzo-2H-1,2-oxaphosphorin-2-oxide or 9,10-dihydro-9-oxa-10-phosphorylphenanthrene-10-oxide, abbreviated as DOPO (C.A. RN 35948-25-5). Such compound is commercially available from Sanko HCA.

Phosphonous acid is represented by the following general formula:



20 The acid is a member of the large group of phosphorus containing oxo acids, which includes other members, such as phosphoric, phosphorous or phosphinous acid. Phosphonous acid does not exist in its free form in an aqueous solution.


Ester derivatives of phosphonous acid are represented by the following general formula




Wherein R represents an organic ester group and R' represents hydrogen or an organic substituent which is directly attached to the phosphorus atom.

In the event that R' represents hydrogen, the formula II' comprises within its scope the following tautomeric structure:

5 following tautomeric structure:




Phosphorous acid is represented by the following general formula:




10 The acid is a further member of the large group of phosphorus containing oxo acids and does not exist in aqueous solution in its free form as well.

Ester derivatives of phosphorous acid are defined by the term phosphites. They are represented by the following general formula:



Wherein R represents an organic ester group.

15 A preferred embodiment relates to compositions comprising as component a) ester derivatives of phosphorous acid as represented by the following general formulae:




Wherein


20 One of R₁, R₂ and R₃ and one of R₄, R₅ and R₆ represent hydrogen and the other ones represent C₁-C₈alkyl or aryl-C₁-C₄alkyl; or

R₁, R₂ and R₃ and R₄, R₅ and R₆ represent C₁-C₈alkyl; or

- 5 -




Wherein R and R' represent C₉-C₂₀alkyl; or



Wherein


5 R₁, R₂ and R₃ represent C₁-C₁₈alkyl; or
one or two of R₁, R₂ and R₃ represent hydrogen and the other ones represent C₁-C₁₈alkyl; or




Wherein one of R₁, R₂ and R₃ represents methyl and the other ones represent C₃-C₄alkyl; or

10 R₁, R₂ and R₃ independently of one another represent C₁-C₄alkyl; and


R_a and R_b represent methyl or ethyl; or



Wherein R₁, R₂ and R₃ independently of one another represent phenyl or C₅-C₂₀alkyl; or




15 Wherein x represents two or a numeral greater than two; y represents one or a numeral greater than one and R₁ and R₂ independently of one another represent phenyl or C₅-C₂₀alkyl; or




Wherein x represents one or a numeral greater than one and y and z represent two or a numeral greater than two.

A preferred embodiment relates to compositions comprising as component a) ester derivatives of phosphorous and phosphorous acid selected from the group consisting of


5




(Irgafos® TNPP, Doverphos® HiPure 4),




(IRGAFOS 168, DOVERPHOS S-480, S-680),



(IRGAFOS P-EPQ, Sandostab® P-EPQ),




(Ethanox®398)




(Ultranox®641),

- 7 -




,





(DOVERPHOS S-9228),


5




(IRGAFOS 12),






(ULTRANOX 626, IRGAFOS 126),





Another preferred embodiment relates to compositions comprising as component a) a cyclic 5 oxaphosphorinoxide of the formula



or an ester derivative of phosphonous or phosphorous acid selected from the group consisting of dipropylene glycol phosphite [CAS RN 40305-86-0],





P(-O-isoC₈H₁₇)₃, P(-O-C₁₈H₃₇)₃, P(-O-isoC₁₀H₂₁)₃, P(-O-C₁₂H₂₅)₃,

P(-O-2-ethylhexyl)(-O-C₆H₅)₂, (C₆H₅-O-)₂P-O-C₂H₄O-P(-O-C₆H₅)₂,

5 [(C₆H₅-O-)₂P]₂(-O-C₂H₄)₂ [CAS RN 57077-45-9],

(C₆H₅-O-)₂P-O-CH(CH₃)CH₂-O-P(-O-C₆H₅)₂,

[(C₆H₅-O-)₂P]₂(-OC₂H₅)₁₄(C₆H₅-O-P)₆ [CAS RN 67383-54-4],

[(C₆H₅-O-)₂P]₂(-OCH(CH₃)CH₂)₁₄(C₆H₅-O-P)₆ [CAS RN 80584-86-7],

and tris[2-(2-hydroxypropoxy)-1-methylethyl] phosphorous acid ester [CAS RN 13474-96-9].

10 A particularly preferred embodiment relates to compositions comprising as component a) ester derivatives of phosphonous and phosphorous acid selected from the group consisting of triphenyl phosphite, diphenylalkyl phosphite, phenyldialkyl phosphite, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-15 butylphenyl)pentaerythritol diphosphite, bis(2,4-di-cumylphenyl)pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)pentaerythritol diphosphite, diisodecyloxy pentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosphonite, 6-isoctyloxy-2,4,8,10-tetra-tert-butyl-12H-20 dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methyl phosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethyl phosphite, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, 2,2',2"-nitrilo[triethyltris(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite], 2-ethylhexyl(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl)phosphite, 5-butyl-5-ethyl-2-(2,4,6-tri-tert-butylphenoxy)-1,3,2-dioxaphosphirane.

25 A highly preferred embodiment relates to compositions comprising as component a) ester derivatives of phosphonous and phosphorous acid selected from the group consisting of aryl organo phosphites, such as tris nonylphenyl phosphite (TNPP DOVERPHOS 4), triphenyl phosphite (TPP DOVERPHOS 10) or diphenyl phosphite (DPP DOVERPHOS 213), aryl-alkyl organo phosphites, such as phenyl diisodecyl phosphite (PDDP DOVERPHOS 7), diphenyl

isodecyl phosphite (DPDP DOVERPHOS 8), diphenylisoctyl phosphite (DPIOP DOVERPHOS 9), tetraphenyl dipropylene glycol diphosphite (THOP DOVERPHOS 11), poly (dipropylene glycol) phenyl phosphite (DHOP DOVERPHOS 12) or dodecyl diphenyl phosphite (DDPP), and alkyl organo phosphites, such as triisodecylphosphite (TDP DOVERPHOS 6), tris tridecyl phosphite (TTDP DOVERPHOS 49) or trilauryl phosphite (TLP DOVERPHOS 53).

A further highly preferred embodiment of the invention relates to compositions comprising as component a) an ester derivative of phosphorous or phosphorous acid selected from the group consisting of 9,10-dihydro-9-oxa-10-phosphorylphenanthrene-10-oxide (DOPO), bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite [CAS RN 80693-00-1], $[(C_6H_5-O)_2P]_2(-O-C_2H_4)_2$ [CAS RN 57077-45-9], $[(C_6H_5-O)_2P]_2(-OC_2H_5)_{14}(C_6H_5-O-P)_6$ [CAS RN 67383-54-4] and triphenyl phosphite.


The ester derivatives of phosphorous and phosphorous acid are known compounds and are commercially available.

According to a particularly preferred embodiment the invention relates to compositions, which comprises as component a) ester derivatives of phosphorous and phosphorous acid selected from the group consisting of the commercial products IRGAFOS 126, 168, 38, PEPQ, 12, TNPP and DDPP, WESTON 618 and Mark PEP 36.




According to a particularly preferred embodiment the invention relates to compositions, wherein component a) is present in an amount equal or higher than 1% by weight based on the total weight of the composition.

Component b)


The composition according to the invention comprises as Component b) at least one nitrogen compound selected from the group consisting of:




- 11 -



5



and



Wherein in the compounds (III), (VII) and (IX):

10 R₁, R₂ or R₃ independently of one another represent substituents selected from the group consisting of C₁-C₈alkyl, C₅-C₆cycloalkyl and C₁-C₄alkyl-C₅-C₆cycloalkyl with hydroxy as an optional substituent; or represent substituents selected from the group consisting of C₂-C₈alkenyl, C₁-C₈-alkoxy, C₂-C₈alkenyl; C₁-C₈alkoxy, acyl, acyloxy, C₆-C₁₂aryl, -O-R¹ and -N(R¹)R², wherein R¹ and R² independently of one another represent hydrogen, C₁-C₄alkyl, C₅-C₆cycloalkyl, C₂-C₈alkenyl, C₂-C₄hydroxyalkyl or C₆-C₁₂aryl; or

15 One of R₁, R₂ and R₃ represents hydrogen and two of R₁, R₂ and R₃ represent the substituents as defined above; or

Two of R₁, R₂ and R₃ represent hydrogen and one of R₁, R₂ and R₃ represents a substituent as defined above;

X represents the anion of a protonic acid;

x is a numeral that represents the number of protons transferred from the latter to the triazine 5 compound; and

y is a numeral that represents the number of protons abstracted from the protonic acid;

provided that

In compounds (VII) one group is present that is capable of adding a proton; and

Compounds (III) are excluded, wherein R₁, R₂ and R₃ represent groups of the partial formula 10 -N(R¹)R² and R¹ and R² represent hydrogen;

And wherein in the compounds (IV), (V), (VI) and (VIII):

R₁, R₂, R₃, R₄ and R₅ independently of one another represent hydrogen or substituents selected from the group consisting of C₁-C₈alkyl, C₅-C₆cycloalkyl and C₁-C₄alkyl-C₅-C₆cycloalkyl with hydroxy as an optional substituent; or represent substituents selected from the group 15 consisting of C₂-C₈alkenyl, C₁-C₈-alkoxy, C₂-C₈alkenyl, C₁-C₈alkoxy, acyl, acyloxy, C₆-C₁₂aryl and -O-R¹, wherein R¹ represents hydrogen, C₁-C₄alkyl, C₅-C₆cycloalkyl, C₂-C₈alkenyl, C₁-C₄hydroxyalkyl or C₆-C₁₂aryl.

According to another embodiment of the invention the composition comprises as Component b) at least one nitrogen compound selected from the group consisting of ammonium 20 polyphosphate, melamine ammonium phosphate, melamine ammonium polyphosphate, melamine ammonium pyrophosphate, a condensation product of melamine with phosphoric acid and other reaction products of melamine with phosphoric acid and mixtures thereof.

The symbol X in formula VII represents, for example, an anion of phosphoric acid, polyphosphoric acid (linear or branched), pyrophosphoric acid, phosphinic acid, phosphonic acid or 25 boric acid.

According to a preferred embodiment the composition comprises as Component b) compounds (III), (VII) and (IX), wherein R₁, R₂ or R₃ independently of one another represent substituents selected from the group consisting of C₁-C₄alkyl, cyclopentyl, cyclohexyl, methylcyclohexyl, C₁-C₄hydroxyalkyl, C₂-C₆alkenyl, C₁-C₄alkoxy, phenyl, phenyl, which is substituted 30 by 1 to 3 substituents selected from the group consisting of methyl, methoxy and by halogen, -OR¹ and by -N(R¹)R², wherein R¹ and R² independently of one another represent hydrogen, C₁-C₄alkyl, hydroxy-C₂-C₄alkyl, cycloalkyl, methylcyclohexyl, phenyl or phenyl, which is sub-

stituted by 1 to 3 substituents selected from the group consisting of methyl, methoxy and by halogen.

According to a particularly preferred embodiment the composition comprises as Component b) compounds (III), (VII) and (IX), wherein one of R₁, R₂ and R₃ represents hydrogen

5 and two of R₁, R₂ and R₃ represent the substituents as defined above; or

two of R₁, R₂ and R₃ represent hydrogen and one of R₁, R₂ and R₃ represents a substituent as defined above.

According to another preferred embodiment the composition comprises as Component b) compounds (IV), (V), (VI) and (VIII), wherein R₁, R₂, R₃, R₄ and R₅ independently of one an-

10 other represent hydrogen or substituents selected from the group consisting of C₁-C₄alkyl, cyclopentyl, cyclohexyl, methylcyclohexyl, hydroxy-C₂-C₄alkyl, C₂-C₆alkenyl, C₁-C₄alkoxy, phenyl, phenyl, which is substituted by 1 to 3 substituents selected from the group consisting of methyl, methoxy and halogen and by -OR¹ wherein R¹ represents hydrogen, C₁-C₄alkyl, hydroxy-C₂-C₄alkyl, cycloalkyl, methylcyclohexyl, phenyl or phenyl, which is substituted by 1

15 to 3 substituents selected from the group consisting of methyl, methoxy and halogen.

According to a particularly preferred embodiment the composition comprises as Component b) a nitrogen compound selected from the group consisting of benzoguanamine (formula III, R₁ = phenyl, R₂ = R₃ = -NH₂), tris(hydroxyethyl) isocyanurate (formula IV, R₁ = R₂ = R₃ = -CH₂-CH₂-OH), allantoin (formula V, R₁ = R₂ = R₃ = R₄ = R₅ = H), glycoluril (formula VI,

20 R₁ = R₂ = R₃ = R₄ = H), melamine phosphate, dimelamine phosphate, melamine pyrophosphate, melamine polyphosphate, melamine borate (all of formula VII type), urea cyanurate (formula VIII type), melamine cyanurate (formula IX type), melam or melem phosphate, melam or melem polyphosphate, ammonium polyphosphate and melamine ammonium phosphate, pyrophosphate and polyphosphate.

25 The nitrogen compounds as defined and described above are known compounds or are obtainable by known methods. Some of them are commercially available.

According to a particularly preferred embodiment the composition comprises as Component b) a nitrogen compound selected from the group consisting of compounds (VII), compounds (IX), ammonium polyphosphate, melamine ammonium phosphate, melamine ammonium polyphosphate, melamine ammonium pyrophosphate, a condensation product of

30 melamine with phosphoric acid and other reaction products of melamine with phosphoric acid and mixtures thereof.

According to a highly preferred embodiment the composition comprises as Component b) a nitrogen compound selected from the group consisting of benzoguanamine, tris(hydroxy-

ethyl) isocyanurate, allantoin, glycoluril, melamine cyanurate, melamine phosphate, dimelamine phosphate, melamine pyrophosphate, urea cyanurate, melamine polyphosphate, melamine borate, ammonium polyphosphate, melamine ammonium polyphosphate, melamine ammonium pyrophosphate, the condensation product of melamine selected from the

5 group consisting of melem, melam, melon and higher condensed compounds and other reaction products of melamine with phosphoric acid and mixtures thereof.

Special emphasis is given to dimelamine pyrophosphate, melamine polyphosphate, melem polyphosphate, melam polyphosphate, and/or a mixed polysalt thereof, particularly melamine polyphosphate.

10 According to a highly preferred embodiment the composition comprises as Component b) melamine cyanurate, such as the ones commercially available under the designation MELAPUR MC, MC 15, MC 25, MC 50.

The ratio of components a) and b) may vary within wide limits and is dependent upon the intended use. Examples of ratios a : b (ratios by weight) are from 5 : 95 to 95 : 5, e.g. from

15 10 : 90 to 90 : 10, preferably from 20 : 80 to 80 : 20, especially from 30 : 70 to 70 : 30 and from 40 : 60 to 60 : 40.

Component c)

The composition according to the invention comprises as Component c) a polyurethane polymer base

20 The polymer base may be a thermoplastic polyurethane (TPU), a PU elastomer, artificial leather, PU skin, PU spray coating or reaction injection molding (RIM), a cast PU, a silylated polyurethane (SPUR), a PU hot melt adhesive or a PU hot melt adhesive.

The polyurethanes are obtainable, for example, by reacting polyethers, polyesters and polybutadienes which contain terminal hydroxyl groups, i.e. polyols, with aliphatic or aromatic 25 polyisocyanates.

Polyethers and polyesters having terminal hydroxyl groups are known and are prepared, for example, by polymerizing epoxides such as ethylene oxide, propylene oxide, butylene oxide, tetrahydrofuran, styrene oxide or epichlorohydrin with themselves, for example in the presence of BF_3 , or by addition reaction of these epoxides, alone or as a mixture or in succession, with starting components containing reactive hydrogen atoms, such as alcohols, ammonia or amines, for example ethylene glycol, propylene 1,3- and 1,2-glycol, trimethylolpropane, 4,4'-dihydroxydiphenylpropane, aniline, ethanolamine or ethylenediamine. Sucrose polyethers are also suitable in accordance with the invention. In many cases preference is

given to those polyethers which predominantly (up to 90% by weight, based on all OH groups present in the polyether) contain primary OH groups. Furthermore, polyethers modified by vinyl polymers, as are formed, for example, by polymerizing styrene and acrylonitrile in the presence of polyethers, are suitable, as are polybutadienes containing OH groups.

5 These compounds generally have molecular weights of 40 and are polyhydroxy compounds, especially compounds containing from two to eight hydroxyl groups, especially those of molecular weight from 800 to 10 000, preferably from 1000 to 6000, for example polyethers containing at least 2, generally 2 to 8, but preferably 2 to 4, hydroxyl groups, as are known for the preparation of homogeneous polyurethanes and cellular polyurethanes.

10 It is of course possible to employ mixtures of the above compounds containing at least two isocyanate-reactive hydrogen atoms, in particular with a molecular weight of 400 - 10 000. Suitable polyisocyanates are aliphatic, cycloaliphatic, araliphatic, aromatic and heterocyclic polyisocyanates, for example ethylene diisocyanate, 1,4-tetramethylene diisocyanate, 1,6-hexamethylene diisocyanate, 1,12-dodecane diisocyanate, cyclobutane 1,3-diisocyanate, cyclohexane 1,3- and -1,4-diisocyanate and also any desired mixtures of these isomers, 1-isocyanato-3,3,5-trimethyl-5-isocyanatomethylcyclohexane, 2,4- and 2,6-hexahydrotolylene diisocyanate and also any desired mixtures of these isomers, hexahydro-1,3- and/or -1,4-phenylene diisocyanate, perhydro-2,4'- and/or -4,4'-diphenylmethanediisocyanate, 1,3- and 1,4-phenylene diisocyanate, 2,4- and 2,6-tolylene diisocyanate, and also any desired mixtures of these isomers, diphenylmethane 2,4'- and/or -4,4'-diisocyanate, naphthylene 1,5-diisocyanate, triphenylmethane 4,4',4"-triisocyanate, polyphenyl-polymethylene polyisocyanates as are obtained by aniline-formaldehyde condensation followed by phosgenization, m- and p-isocyanatophenylsulphonyl isocyanates, perchlorinated aryl polyisocyanates, polyisocyanates containing carbodiimide groups, polyisocyanates containing allophanate groups, polyisocyanates containing isocyanurate groups, polyisocyanates containing urethane groups, polyisocyanates containing acylated urea groups, polyisocyanates containing biuret groups, polyisocyanates containing ester groups, reaction products of the above-mentioned isocyanates with acetals, and polyisocyanates containing polymeric fatty acid radicals.

15 It is also possible to employ the isocyanate group-containing distillation residues as they are or dissolved in one or more of the above-mentioned polyisocyanates, which are obtained in the course of the industrial preparation of isocyanates. It is additionally possible to use any desired mixtures of the above-mentioned polyisocyanates.

20 Particular preference is given in general to the polyisocyanates which are readily obtainable industrially, for example aromatic isocyanates such as 2,4- and 2,6-tolylene diisocyanate and

any desired mixtures of these isomers ("TDI"), polyphenyl-polymethylene-polyisocyanates as prepared by aniline-formaldehyde condensation followed by phosgenization ("crude MDI"), and polyisocyanates containing carbodiimide, urethane, allophanate, isocyanurate, urea or biuret groups ("modified polyisocyanates").

5 Polyurethane is preferably prepared from liquid starting components, i.e. the starting materials to be reacted with one another being mixed together in a one-shot process.

The polymer base of component c) may additionally contain in the form as admixtures or as copolymers a wide variety of other synthetic polymers including polyolefins, polystyrenes, polyesters, polyethers, polyamides, poly(meth)acrylates, thermoplastic polyurethanes, poly-

10 sulphones, polyacetals and PVC, including suitable compatibilizing agents. For example, the polymer base may additionally contain thermoplastic polymers selected from the group of resins consisting of polyolefins, thermoplastic polyurethanes, styrene polymers and copolymers thereof. Specific embodiments include polypropylene (PP), polyethylene (PE), polyamide (PA), polybutylene terephthalate (PBT), polyethylene terephthalate (PET), glycol-modified 15 polycyclohexylenemethylene terephthalate (PCTG), polysulphone (PSU), polymethyl-methacrylate (PMMA), thermoplastic polyurethane (TPU), acrylonitrile-butadiene-styrene (ABS), acrylonitrile-styrene-acrylic ester (ASA), acrylonitrile-ethylene-propylene-styrene (AES), styrene-maleic anhydride (SMA) or high impact polystyrene (HIPS).

A list of suitable synthetic polymers is given below:

20 1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, poly-4-methylpent-1-ene, polyvinylcyclohexane, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), high density and high molecular weight polyethylene (HDPE-HMW), high density 25 and ultrahigh molecular weight polyethylene (HDPE-UHMW), medium density polyethylene (MDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), (VLDPE) and (ULDPE). The polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

30 a) Radical polymerisation (normally under high pressure and at elevated temperature).
b) Catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either π - or σ -coordinated. These

metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, and amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler-Natta, TNZ (DuPont), metallocene or single site catalysts (SSC).

5 2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).

10 3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, 15 propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene copolymers, ethylene/octene copolymers, ethylene/vinylcyclohexane copolymers, ethylene/cycloolefin copolymers (e.g. ethylene/norbornene like COC), ethylene/1-olefins copolymers, where the 20 1-olefin is generated in-situ; propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/vinylcyclohexene copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate copolymers, ethylene/vinyl acetate copolymers or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, 25 LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EAA), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.

30 4. Hydrocarbon resins (for example C₅-C₉) including hydrogenated modifications thereof (e.g. tackifiers) and mixtures of polyalkylenes and starch;

The homopolymers and copolymers mentioned above may have a stereo structure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereo block polymers are also included.

5. Polystyrene, poly (p-methylstyrene), poly(α -methylstyrene).
6. Aromatic homopolymers and copolymers derived from vinyl aromatic monomers including styrene, α -methylstyrene, all isomers of vinyl toluene, especially p-vinyl toluene, all isomers of ethyl styrene, propyl styrene, vinyl biphenyl, vinyl naphthalene, and vinyl anthracene, and mixtures thereof. Homopolymers and copolymers may have a stereo structure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereo block polymers are also included.
 - a) Copolymers including aforementioned vinyl aromatic monomers and comonomers selected from ethylene, propylene, dienes, nitriles, acids, maleic anhydrides, maleimides, vinyl acetate and vinyl chloride or acrylic derivatives and mixtures thereof, for example styrene/butadiene, styrene/acrylonitrile, styrene/ethylene (interpolymers), styrene/alkyl methacrylate, styrene/butadiene/alkyl acrylate, styrene/butadiene/alkyl methacrylate, styrene/maleic anhydride, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer; and block copolymers of styrene such as styrene/butadiene/styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene/propylene/styrene.
 - b) Hydrogenated aromatic polymers derived from hydrogenation of polymers mentioned under 6.), especially including polycyclohexylethylene (PCHE) prepared by hydrogenating atactic polystyrene, often referred to as polyvinylcyclohexane (PVCH).
 - c) Hydrogenated aromatic polymers derived from hydrogenation of polymers mentioned under 6a). Homopolymers and copolymers may have a stereo structure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereo block polymers are also included.
7. Graft copolymers of vinyl aromatic monomers such as styrene or α -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile copolymers; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates,

styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 6), for example the copolymer mixtures known as ABS, MBS, ASA or AES polymers.

8. Halogen-containing polymers such as polychloroprene, chlorinated rubbers, chlorinated and brominated copolymer of isobutylene-isoprene (halobutyl rubber), chlorinated or sulphonchlorinated polyethylene, copolymers of ethylene and chlorinated ethylene, epichlorohydrin homo- and copolymers, especially polymers of halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof such as vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.
9. Polymers derived from α,β -unsaturated acids and derivatives thereof such as polyacrylates and polymethacrylates; polymethyl methacrylates, polyacrylamides and polyacrylonitriles, impact-modified with butyl acrylate.
10. Copolymers of the monomers mentioned under 9) with each other or with other unsaturated monomers, for example acrylonitrile/ butadiene copolymers, acrylonitrile/alkyl acrylate copolymers, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide copolymers or acrylonitrile/ alkyl methacrylate/butadiene terpolymers.
11. Polymers derived from unsaturated alcohols and amines or the acyl derivatives or acetals thereof, for example polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallyl melamine; as well as their copolymers with olefins mentioned in 1. above.
12. Homopolymers and copolymers of cyclic ethers such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.
13. Polyacetals such as polyoxymethylene and those polyoxymethylenes, which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.
14. Polyphenylene oxides and sulphides, and mixtures of polyphenylene oxides with styrene polymers or polyamides.
15. Polyamides and copolyamides derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, for example polyamide 4, polyamide 6, polyamide 6/6, 6/10, 6/9, 6/12, 4/6, 12/12, polyamide 11, polyamide 12, aromatic polyamides starting from m-xylene diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic or/and terephthalic acid and with or without an

elastomer as modifier, for example poly-2,4,4,-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide; and also block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, e.g. with polyethylene glycol, polypropylene glycol or 5 polytetramethylene glycol; as well as polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing (RIM polyamide systems).

16. Polyureas, polyimides, polyamide imides, polyether imides, polyester imides, polyhydantoins and polybenzimidazoles.

17. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids 10 or the corresponding lactones, for example polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylcyclohexane terephthalate, polyalkylene naphthalate (PAN) and polyhydroxybenzoates, as well as block copolyether esters derived from hydroxyl-terminated polyethers; and also polyesters modified with polycarbonates or MBS.

18. Polyketones.

15 19. Polysulphones, polyether sulphones and polyether ketones.

20. Blends of the aforementioned polymers (polyblends), for example PP/EPDM, Polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, 20 PA/PPO, PBT/PC/ABS or PBT/PET/PC.

The preparation of the compositions according to the invention may be carried out either by adding or applying the flame retardants consisting of components a) and b) according to the invention or, however, by adding or applying the individual components separately.

Preference is given to the use of components a) and b), each independently of the other, in a 25 concentration of from 0.1 to 30.0% by weight, for example from 0.2 to 20.0% by weight, preferably from 0.2 to 15.0 % by weight, based on weight of the polymer base.

The compositions according to the invention contain the flame retardant consisting of components a) and b) in an amount of, for example, from 0.1 to 50.0 % by weight, preferably from 0.3 to 40.0% by weight, especially from 0.3 to 30.0% by weight or from 0.8 to 30.0% by 30 weight, based on the composition.

The flame-resistant polymer compositions are suitable, *inter alia*, for the production of moulded articles, films, threads and fibres, for example by injection-moulding, extrusion or compression-moulding.

Additional Components

The instant invention further pertains to a composition, which comprises, in addition to the Components a), b) and c), as defined above, d) further additives selected from the group consisting of polymer stabilizers and additional flame-retardants selected from the group

5 consisting of phosphorus containing flame-retardants, halogenated flame-retardants and in-organic flame-retardants.

Stabilizers are preferably halogen-free and selected from nitroxyl stabilizers, nitrone stabiliz-ers, amine oxide stabilizers, benzofuranone stabilizers, phosphite and phosphonite stabiliz-ers, quinone methide stabilizers and monoacrylate esters of 2,2'-alkylidenebisphenol stabiliz-

10 ers.

Additional flame-retardants as of present component d) are known components, items of commerce or can be obtained by known methods.

Representative phosphorus containing flame-retardants, in addition to the ones defined above with regard to component a), are for example:

15 Tetraphenyl resorcinol diphosphite (FYROLFLEX® RDP, Akzo Nobel), tetrakis(hydroxy-methyl)phosphonium sulphide, triphenyl phosphate, diethyl-N,N-bis(2-hydroxyethyl)-amino-methyl phosphonate, hydroxyalkyl esters of phosphorus acids, resorcinol diphosphate oli-gomer (RDP), phosphazene flame-retardants or ethylenediamine diphosphate (EDAP).

Representative halogenated flame-retardants are, for example:

20 Polybrominated diphenyl oxide (DE-60F, Great Lakes Corp.), decabromodiphenyl oxide (DBDPO; SAYTEX® 102E), tris[3-bromo-2,2-bis(bromomethyl)propyl] phosphate (PB 370®, FMC Corp.), tris(2,3-dibromopropyl)phosphate, tris(2,3-dichloropropyl)phosphate, chlorendic acid, tetrachlorophthalic acid, tetrabromophthalic acid, poly-β-chloroethyl triphosphonate mix-ture, tetrabromobisphenol A bis(2,3-dibromopropyl ether) (PE68), brominated epoxy resin,

25 ethylene-bis(tetrabromophthalimide) (SAYTEX® BT-93), bis(hexachlorocyclopentadieno)-cyclooctane (DECLORANE PLUS®), chlorinated paraffins, octabromodiphenyl ether, hexa-chlorocyclopentadiene derivatives, 1,2-bis(tribromophenoxy)ethane (FF680), tetrabromo-bisphenol A (SAYTEX® RB100), ethylene bis-(dibromo-norbornanedicarboximide) (SAYTEX® BN-451), bis-(hexachlorocyclopentadieno) cyclooctane, PTFE, tris-(2,3-dibromopropyl)-iso-cyanurate, and ethylene-bis-tetrabromophthalimide.

The flame-retardant mentioned above are routinely combined with an inorganic oxide syner-gist. Most common for this use are zinc or antimony oxides, e.g. Sb_2O_3 or Sb_2O_5 . Boron com-pounds are suitable, too.

The above-mentioned flame-retardant classes are advantageously contained in the composition of the invention in an amount from about 0.5% to about 45.0% by weight of the organic polymer substrate; for instance about 3.0% to about 40.0%; for example about 5.0% to about 35.0% by weight of the polymer. For example, the flame-retardant of component b) is em-

5 ployed from about 0.5% to about 10.0% by weight, from about 1.0% to about 10.0%, from about 3.0% to about 10.0% or from about 5.0% to about 10.0% by weight, based on the weight of the polymer substrate. For example, component b) is employed from about 0.5% to about 8.0%, from about 0.5% to about 6.0%, from about 0.5% to about 5.0%, or from about 0.5% to about 3.0% by weight, based on the weight of the polymer substrate.

10 As mentioned above, the composition according to the invention may additionally contain one or more conventional additives, for example selected from pigments, dyes, plasticizers, antioxidants, thixotropic agents, levelling assistants, basic co-stabilizers, metal passivators, metal oxides, organophosphorus compounds, further light stabilizers and mixtures thereof, especially pigments, phenolic antioxidants, calcium stearate, zinc stearate, UV absorbers of 15 the 2-hydroxy-benzophenone, 2-(2'-hydroxyphenyl)benzotriazole and/or 2-(2-hydroxyphenyl)-1,3,5-triazine groups. More specific examples are the following components:

1. Antioxidants

1.1 Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, linear nonylphenols or nonylphenols branched in the side-chain, e.g. 2,6-dinonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)-phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)-phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)-phenol and mixtures 25 thereof.

1.2 Alkythiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-didodecylthiomethyl-4-nonylphenol.

1.3 Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-diphenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4 Tocopherols, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (Vitamin E).

1.5 Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis(3,6-di-sec-amylphenol), 4,4'-bis(2,6-dimethyl-4-hydroxyphenyl) disulphide.

1.6 Alkylidene bisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)-phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethyldenebis(4,6-di-tert-butylphenol), 2,2'-ethyldenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α , α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl] terephthalate, 1,1-bis(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7 O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxy-dibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzyl mercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzyl mercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl) dithiobenzoate, bis(3,5-di-tert-butyl-4-hydroxybenzyl) sulphide, isoctyl-3,5-di-tert-butyl-4-hydroxybenzyl mercaptoacetate.

1.8 Hydroxybenzylated malonates, for example dioctadecyl 2,2-bis(3,5-di-tert-butyl-2-hydroxybenzyl)malonate, dioctadecyl 2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)malonate, didodecylmercaptoethyl 2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, di[4-(1,1,3,3-tetramethylbutyl)phenyl] 2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9 Hydroxybenzyl aromatic compounds, for example 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10 Triazine compounds, for example 2,4-bisoctylmercapto-6-(3,5-di-tert-butyl-4-hydroxy-anilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl) isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl) isocyanurate, 2,4,6-tris-(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxy-phenylpropionyl)hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl) isocyanurate.

5 1.11 Benzylphosphonates, for example dimethyl 2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl 3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl 3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl 5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, calcium salt of 3,5-di-tert-butyl-4-hydroxybenzyl-phosphonic acid monoethyl ester.

10 1.12 Acylaminophenols, for example 4-hydroxylauric acid anilide, 4-hydroxystearic acid anilide, N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamic acid octyl ester.

15 1.13 Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or poly-hydric alcohols, for example with methanol, ethanol, n-octanol, isoctanol, octadecanol, 1,6-hexanediol, 1,9-nanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiidiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxalic acid diamide, 3-thiaundecanol, 3-thiapentadecanol, trimethyl-20 hexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospho-2,6,7-trioxabicyclo[2.2.2]octane.

1.14 Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or poly-hydric alcohols, for example with methanol, ethanol, n-octanol, isoctanol, octadecanol, 1,6-hexanediol, 1,9-nanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiidiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, 25 N,N'-bis(hydroxyethyl)oxalic acid diamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospho-2,6,7-trioxabicyclo[2.2.2]octane; 3,9-bis[2-{3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy}-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5.5]undecane.

30 1.15 Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or poly-hydric alcohols, for example with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiidiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxalic acid diamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospho-2,6,7-trioxabicyclo[2.2.2]octane.

1.16 Esters of 3,5-di-tert-butyl-4-hydroxyphenylacetic acid with mono- or poly-hydric alcohols, for example with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nona-nediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxalic acid diamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylopropane, 4-hydroxymethyl-1-phospho-2,6,7-trioxabicyclo[2.2.2]octane.

5 1.17 Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid, for example N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazide, N,N'-bis[2-(3-[3,5-di-tert-butyl-4-hydroxyphenyl]-propionyloxy)ethyl]oxamide (Naugard[®]XL-1 from Uniroyal).

1.18 Ascorbic acid (Vitamin C).

1.19 Amine-type antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-di(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulphonamido)-diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxydiphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylaminophenol, 4-nanoylaminophenol, 4-dodecanoylaminophenol, 4-octadecanoylaminophenol, di(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-di[(2-methylphenyl)amino]ethane, 1,2-di(phenylamino)propane, (o-tolyl)-biguanide, di[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, mixture of mono- and di-alkylated tert-butyl-/tert-octyl-diphenylamines, mixture of mono- and di-alkylated nonyldiphenylamines, mixture of mono- and di-alkylated dodecyldiphenylamines, mixture of mono- and di-alkylated isopropyl-/isohexyl-diphenylamines, mixtures of mono- and di-alkylated tert-butyldiphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, mixture of mono- and di-alkylated tert-butyl-/tert-octyl-phenothiazines, mixture of mono- and di-alkylated tert-octylphenothiazines, N-allylphenothiazine, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-

tetramethylpiperid-4-yl)-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl) sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV absorbers and light stabilisers

2.1 2-(2'-Hydroxyphenyl)-benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)-ben-

5 zotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-benzotriazole, 2-(5'-tert-butyl-2'-hydroxy-phenyl)-benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)-phenyl)-benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chlorobenzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)-benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)-benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)-benzotriazole, 2-(3',5'-bis(α,α-dimethylbenzyl)-2'-hydroxyphenyl)-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)-benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonylethyl)-phenyl)-benzotriazole, 2,2'-methylenebis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazol-2-yl-phenol]; transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-benzotriazole with 20 polyethylene glycol 300;
$$[R-\text{CH}_2\text{CH}_2-\text{COO}-\text{CH}_2\text{CH}_2]_2$$
 wherein R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-yl-phenyl; 2-[2'-hydroxy-3'-(α,α-dimethylbenzyl)-5'-(1,1,3,3-tetramethylbutyl)-phenyl]-benzotriazole; 2-[2'-hydroxy-3'-(1,1,3,3-tetramethylbutyl)-5'-(α,α-dimethylbenzyl)-phenyl]-benzotriazole.

2.2 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyl-25 oxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy or 2'-hydroxy-4,4'-dimethoxy derivative.

2.3 Esters of unsubstituted or substituted benzoic acids, for example 4-tert-butyl-phenyl

salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoylresorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoylresorcinol, 3,5-di-tert-butyl-4-hydroxybenzoic acid 2,4-di-tert-butyl-phenyl ester, 3,5-di-tert-butyl-4-hydroxybenzoic acid hexadecyl ester, 3,5-di-tert-butyl-4-hydroxybenzoic acid octadecyl ester, 3,5-di-tert-butyl-4-hydroxybenzoic acid 2-methyl-4,6-di-tert-butylphenyl ester.

2.4 Acrylates, for example α-cyano-β,β-diphenylacrylic acid ethyl ester or isooctyl ester, α-methoxycarbonylcinnamic acid methyl ester, α-cyano-β-methyl-p-methoxycinnamic acid

methyl ester or butyl ester, α -methoxycarbonyl-p-methoxycinnamic acid methyl ester, N-(β -methoxycarbonyl- β -cyanovinyl)-2-methyl-indoline.

2.5 Nickel compounds, for example nickel complexes of 2,2'-thio-bis[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1 : 1 or 1 : 2 complex, optionally with additional ligands, such as

5 n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyl dithiocarbamate, nickel salts of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid monoalkyl esters, such as of the methyl or ethyl ester, nickel complexes of ketoximes, such as of 2-hydroxy-4-methylphenylundecyl ketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, optionally with additional ligands.

10 2.6 Sterically hindered amines, for example bis(2,2,6,6-tetramethylpiperid-4-yl) sebacate, bis(2,2,6,6-tetramethylpiperid-4-yl) succinate, bis(1,2,2,6,6-pentamethylpiperid-4-yl) sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperid-4-yl) sebacate, n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonic acid bis(1,2,2,6,6-pentamethylpiperidyl) ester, condensation product of 1-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, linear or cyclic condensation products of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-s-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl) nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butanetetraoate, 1,1'-(1,2-ethanediyil)bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyl-oxy-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-20 3,5-di-tert-butylbenzyl) malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl) sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl) succinate, linear or cyclic condensation products of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, condensation product of 2-chloro-4,6-di(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, condensation product of 2-chloro-4,6-di(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidine-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione, mixture of 4-hexadecyloxy- and 4-stearyl-30 2,2,6,6-tetramethylpiperidine, condensation product of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, condensation product of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine and 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]); condensation product of 1,6-diaminohexane and 2,4,6-trichloro-1,3,5-triazine and also N,N-dibutylamine and 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [192268-64-7]); N-(2,2,6,6-tetrame-

thyl-4-piperidyl)-n-dodecylsuccinimide, N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimide, 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4.5]decane, reaction product of 7,7,9,9-tetramethyl-2-cycloundecyl-1-oxa-3,8-diaza-4-oxospiro[4.5]decane and epichlorohydrin, 1,1-bis(1,2,2,6,6-pentamethyl-4-piperidylloxycarbonyl)-2-(4-methoxy-phenyl)ethene, N,N'-bis-formyl-N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine, diester of 4-methoxymethylenemalonic acid with 1,2,2,6,6-pentamethyl-4-hydroxypiperidine, poly[methylpropyl-3-oxy-4-(2,2,6,6-tetramethyl-4-piperidyl)]siloxane, reaction product of maleic anhydride α -olefin copolymer and 2,2,6,6-tetramethyl-4-aminopiperidine or 1,2,2,6,6-pentamethyl-4-aminopiperidine.

5 2.7 Oxalic acid diamides, for example 4,4'-dioctyloxy oxanilide, 2,2'-diethoxy oxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butyl oxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butyl oxanilide, 2-ethoxy-2'-ethyl oxanilide, N,N'-bis(3-dimethylaminopropyl) oxalamide, 2-ethoxy-5-tert-butyl-2'-ethyl oxanilide and a mixture thereof with 2-ethoxy-2'-ethyl-5,4'-di-tert-butyl oxanilide, mixtures of o- and p-methoxy- and also of o- and p-ethoxy-di-substituted oxanilides.

10 2.8 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxy-phenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethyl-phenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxypropyloxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxypropyloxy)phenyl]-4,6-bis(2,4-dimethyl-phenyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxyphenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxypro-
20 poxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxypropoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine, 2-{2-hydroxy-4-[3-(2-ethylhexyl-1-oxy)-2-hydroxypropoxy]phenyl}-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine.

25 3. Metal deactivators, for example N,N'-diphenyloxalic acid diamide, N-salicylal-N'-salicyloylhydrazine, N,N'-bis(salicyloyl)hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenyl-propionyl)hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalic acid dihydrazide, oxanilide, isophthalic acid dihydrazide, sebacic acid bis-phenylhydrazide, N,N'-diacetyl adipic acid dihydrazide, N,N'-bis-salicyloylloxalic acid dihydrazide, N,N'-bis-salicyloylthiopropionic acid dihydrazide.

30 35

4. Hydroxylamines, for example N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine from hydrogenated tallow fatty amines.
5. Nitrones, for example N-benzyl-alpha-phenylnitrone, N-ethyl-alpha-methylnitrone, N-octyl-alpha-heptylnitrone, N-lauryl-alpha-undecylnitrone, N-tetradecyl-alpha-tridecylnitrone, N-hexadecyl-alpha-pentadecylnitrone, N-octadecyl-alpha-heptadecylnitrone, N-hexadecyl-alpha-heptadecylnitrone, N-octadecyl-alpha-pentadecylnitrone, N-heptadecyl-alpha-heptadecylnitrone, N-octadecyl-alpha-hexadecylnitrone, nitrones derived from N,N-dialkylhydroxylamines prepared from hydrogenated tallow fatty amines.
6. Thiosynergistic compounds, for example thiadipropionic acid dilauryl ester or thiadipropionic acid distearyl ester.
7. Peroxide-destroying compounds, for example esters of β -thio-dipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl ester, mercaptobenzimidazole, the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyldisulphide, pentaerythritol tetrakis(β -dodecylmercapto)propionate.
8. Polyamide stabilisers, for example copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.
9. Basic co-stabilisers, for example melamine, polyvinylpyrrolidone, dicyandiamide, triallylcyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal and alkaline earth metal salts of higher fatty acids, for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate, potassium palmitate, antimony pyrocatecholate or zinc pyrocatecholate.
10. Nucleating agents, for example inorganic substances, e.g. talc, metal oxides, such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulphates of preferably alkaline earth metals; organic compounds, such as mono- or poly-carboxylic acids and their salts, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds, for example ionic copolymerisates ("ionomers"). Special preference is given to 1,3 : 2,4-bis(3',4'-dimethylbenzylidene)sorbitol, 1,3 : 2,4-di(paramethyldibenzylidene)sorbitol and 1,3 : 2,4-di(benzylidene)sorbitol.
11. Fillers and reinforcing agents, for example calcium carbonate, silicates, glass fibres, glass beads, talc, kaolin, mica, barium sulphate, metal oxides and hydroxides, carbon black, graphite, wood powders, and powders and fibres of other natural products, synthetic fibres.

12. Benzofuranones and indolinones, for example as described in U.S. 4,325,863; U.S. 4,338,244; U.S. 5,175,312, U.S. 5,216,052; U.S. 5,252,643; DE-A-4 316 611; DE-A-4 316 622; DE-A-4 316 876; EP-A-0 589 839 or EP-A-0 591 102, or 3-[4-(2-acetoxyethoxy)phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxy-phenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(2,3-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one.

5 13. Anti-gas fading agents, for example 1,1,1',1'-tetramethyl-4,4'-(methylene-di-p-phenylene)disemicarbazide; 1,6-hexamethylene bis(N,N-dimethylsemicarbazide); 11-[6-[(2,2-dimethylhydrazino)carbonyl]amino]hexyl]-10,12-dioxo-bis(2,2-dimethylhydrazide).

10 14. Other additives, for example plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow improvers, optical brighteners, antistatics, blowing agents.

15 The further additives of Component c) are added, for example, in concentrations of 0.01 to 10.0%, relative to the total weight of the composition of this invention.

The incorporation of the additive components a) and b) and optional further components into the polymer component c) is carried out by known methods such as dry blending in the form of a powder, or wet mixing in the form of solutions, dispersions or suspensions for example in an inert solvent, water or oil. The additive components a) and b) and optional further additives may be incorporated, for example, before or after molding or also by applying the dissolved or dispersed additive or additive mixture to the polymer material, with or without subsequent evaporation of the solvent or the suspension/dispersion agent. They may be added directly into the processing apparatus (e.g. extruders, internal mixers, etc.), e.g. as a dry mixture or powder, or as a solution or dispersion or suspension or melt.

20 25

The addition of the additive components to the polymer substrate c) can be carried out in all customary mixing machines in which the polymer is melted and mixed with the additives. Suitable machines are known to those skilled in the art. They are predominantly mixers, kneaders and extruders.

30 The process is preferably carried out in an extruder by introducing the additive during processing.

Particularly preferred processing machines are single-screw extruders, contra rotating and co-rotating twin-screw extruders, planetary-gear extruders, ring extruders or co kneaders. It

is also possible to use processing machines provided with at least one gas removal compartment to which a vacuum can be applied.

Suitable extruders and kneaders are described, for example, in *Handbuch der Kunststoffextrusion, Vol. 1 Grundlagen, Editors F. Hensen, W. Knappe, H. Potente, 1989, pp. 3-7, ISBN: 5 3-446-14339-4 (Vol. 2 Extrusionsanlagen 1986, ISBN 3-446-14329-7)*.

For example, the screw length is 1 - 60 screw diameters, preferably 35-48 screw diameters. The rotational speed of the screw is preferably 10 - 600 rotations per minute (rpm), very particularly preferably 25 - 300 rpm.

The maximum throughput is dependent on the screw diameter, the rotational speed and the 10 driving force. The process of the present invention can also be carried out at a level lower than maximum throughput by varying the parameters mentioned or employing weighing machines delivering dosage amounts.

If a plurality of components is added, these can be premixed or added individually.

The additives components a) and b) and optional further additives can also be sprayed onto 15 the polymer substrate c). The additive mixture dilutes other additives, for example the conventional additives indicated above, or their melts so that they can be sprayed also together with these additives onto the polymer substrate. Addition by spraying during the deactivation of the polymerisation catalysts is particularly advantageous; in this case, the steam evolved may be used for deactivation of the catalyst. In the case of spherically polymerised polyolefins it may, for example, be advantageous to apply the additives of the invention, optionally 20 together with other additives, by spraying.

The additive components a) and b) and optional further additives can also be added to the polymer in the form of a master batch ("concentrate") which contains the components in a concentration of, for example, about 1.0% to about 40.0% and preferably 2.0% to about 25 20.0% by weight incorporated in a polymer. The polymer is not necessarily of identical structure than the polymer where the additives are added finally. In such operations, the polymer can be used in the form of powder, granules, solutions, and suspensions or in the form of lattices.

Incorporation can take place prior to or during the shaping operation. The materials containing 30 the additives of the invention described herein preferably are used for the production of molded articles, for example roto-molded articles, injection molded articles, profiles and the like, and especially a fiber, spun melt non-woven, film or foam.




Thus, present invention further pertains to a molded or extruded article, a fiber, spun melt non-woven or a foam comprising the composition of the invention.

A particularly preferred embodiment of the invention relates to a composition, which comprises


5 a) At least one ester derivative of phosphorous and phosphorous acid;
 b) Melamine cyanurate; and
 c) A polyurethane polymer base.

Another particularly preferred embodiment of the invention relates to a composition, which comprises


10 a) At least one at least one ester derivative of phosphorous and phosphorous acid selected from the group consisting of




- 33 -



,




,






,

5



,






b) Melamine cyanurate; and



c) A polyurethane polymer base.


5 A particularly preferred embodiment of the invention relates to a composition, which comprises

a) At least one ester derivative of phosphorous and phosphorous acid selected from the group consisting of



10





b) Melamine cyanurate; and

5 c) A polyurethane polymer base.

Another preferred embodiment of the invention relates to a composition, which comprises

a) At least one ester derivative of phosphorous and phosphorous acid selected from the group consisting of tris nonylphenyl phosphite (TNPP), triphenyl phosphite (TPP), di-phenyl phosphite (DPP), phenyl diisodecyl phosphite (PDDP), diphenyl isodecyl phosphite (DPDP), diphenylisooctyl phosphite (DPIOP), tetraphenyl dipropylene glycol diphosphite (THOP), poly (dipropylene glycol) phenyl phosphite (DHOP), dodecyl di-phenyl phosphite (DDPP), triisodecylphosphite (TDP), tris tridecyl phosphite (TTDP) and triauryl phosphite (TLP);

b) Melamine cyanurate; and

15 c) A polyurethane polymer base.

Another particularly preferred embodiment of the invention relates to a composition, which comprises

a) At least one ester derivative of phosphorous or phosphorous acid selected from the group consisting of 9,10-dihydro-9-oxa-10-phosphorylphenanthrene-10-oxide (DOPO), bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite [CAS RN 80693-00-1],

$[(C_6H_5-O-)_2P]_2(-O-C_2H_4)_2$ [CAS RN 57077-45-9], $[(C_6H_5-O-)_2P]_2(-OC_2H_5)_{14}(C_6H_5-O-P)_6$ [CAS RN 67383-54-4] and triphenyl phosphite;

- b) Melamine cyanurate; and
- c) A polyurethane polymer base

5 A further embodiment of the invention relates to a process for imparting flame retardancy to a polyurethane polymer base, which process comprises adding to said polymer base a mixture, which comprises

- a) At least one ester derivative of a phosphorus containing oxo acid selected from the group consisting of oxaphosphorinoxide, phosphonous acid and phosphorous acid; and

10 b) At least one flame retardant component based on a nitrogen compound.

The following examples illustrate the invention:

Example 1

Materials and Methods

4 kg of polyester thermoplastic polyurethane (TPU) pellets (Estane®GP 72 DB NAT 021 P 15 (Noveon®) are mixed to homogeneity in a tumble mixer with 5-10% bis(2,4-di-tert-butyl-phenyl)pentaerythritol diphosphite (IRGAFOS 126), 25% melamine cyanurate (MELAPUR MC 25) and pentaerythritol tetrakis 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate (IRGANOX 1066). This blend is compounded in twin-screw extruder (Berstorff®) at a temperature up to 220°C. The extrudate is granulated after drawing through a water bath and 20 cooling.

125 mm x 13 mm x 1.6 mm test panels are moulded from the granules formed by means of an injection-moulding machine (Arburg®320 S) at a temperature up to 220°C (mold temperature: 50°C).

The samples are tested for flame retardancy by the UL 94V thick section test (Underwriter's 25 Laboratories UL94 Flammability Test: UL94 Test for Flammability of Plastic Materials for parts in Devices and Appliances, 5th Edition, 1996).

Results**Table 1**

Test No.	Amounts [%]	Components	UL94 rating*)
1	25	MELAPUR MC 25	V-2
2	25 5	MELAPUR MC 25 IRGAFOS 126	V-0
3	25 10	MELAPUR MC 25 IRGAFOS 126	V-0

*) V-0: Very good; V-1: Good; V-2: Not sufficient

5 **Example 2**Materials and Methods

4 kg of polyester thermoplastic polyurethane (TPU) pellets (Estane®58311 Natural 028 P) are mixed to homogeneity in a tumble mixer with different concentrations bis(2,4-di-tert-butylphenyl)pentaerythritol diphosphite (IRGAFOS 126), different concentrations of melamine cyanurate (MELAPUR MC 25) and 1% pentaerythritol tetrakis 3-(3,5-di-tert-butyl-4-hydroxy-phenyl)propionate (IRGANOX 1066). This blend is compounded in twin-screw extruder (Bergstorf®) at a temperature up to 220°C. The extrudate is granulated after drawing through a water bath and cooling.

15 Injection molding and testing for flame retardancy are carried out in a manner analogous to Example 1.

Results**Table 2**

Test No.	Amounts [%]	Components	UL94 rating*)
1	30	MELAPUR MC 25	V-2
2	30 7.5	MELAPUR MC 25 IRGAFOS 126	V-0
3	35 7.5	MELAPUR MC 25 IRGAFOS 126	V-0
4	28 7.0	MELAPUR MC 25 IRGAFOS 126	V-0

Example 3**Materials and Methods**

4 kg of polyester thermoplastic polyurethane (TPU) pellets (Estane®58311 Natural 028 P) are mixed to homogeneity in a tumble mixer with different concentrations bis(2,4-di-tert-butylphenyl)pentaerythritol diphosphite (IRGAFOS 126), different concentrations of melamine cyanurate (MELAPUR MC 25) and the test compounds mentioned in Table 3 and 1% pentaerythritol tetrakis 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate (IRGANOX 1066). This blend is compounded in twin-screw extruder (Berstorff®) at a temperature up to 220°C. The extrudate is granulated after drawing through a water bath and cooling.

10 Injection molding and testing for flame retardancy are carried out in a manner analogous to Example 1.

Results

Table 3

Test No.	Amounts	Components	UL94 rating
1	25%	MELAPUR MC 25	V-2
2	30%	MELAPUR MC 25	V-2
3	35%	MELAPUR MC 25	V-2
4	25% 5%	MELAPUR MC 25 DOPO	V-0
5	25% 7.5%	MELAPUR MC 25 DOPO	V-0
6	30% 5%	MELAPUR MC 25 DOPO	V-0
7	30% 7.5%	MELAPUR MC 25 DOPO	V-0
8	30% 10%	MELAPUR MC 25 DOPO	V-0
9	35% 5%	MELAPUR MC 25 DOPO	V-0
10	35% 10%	MELAPUR MC 25 DOPO	V-0
11	30% 7.5%	MELAPUR MC 25 ADK STAB PEP 36	V-0
12	25% 10%	MELAPUR MC 25 THOP	V-0
13	30% 10%	MELAPUR MC 25 THOP	V-0
14	25% 7.5%	MELAPUR MC 25 DHOP	V-0
15	30% 10%	MELAPUR MC 25 DHOP	V-0
16	35% 10%	MELAPUR MC 25 DHOP	V-0
17	35% 10%	MELAPUR MC 25 TPP	V-0

(V0 = Very Good, V1 = Good, V2 = Not Sufficient)

Claims

1. A composition, which comprises

- 5 a) At least one ester derivative of a phosphorus containing oxo acid selected from the group consisting of oxaphosphorinoxide, phosphonous acid and phosphorous acid;
- b) At least one flame retardant component based on a nitrogen compound; and
- c) A polyurethane polymer base.

2. A composition, which comprises



- 10 a) At least one ester derivative of a phosphorus containing oxo acid selected from the group consisting of phosphonous and phosphorous acid;
- b) At least one flame retardant component based on a nitrogen compound; and
- c) A polyurethane polymer base.

3. A composition according to claim 1, which comprises


- 15 a) At least one ester derivative of phosphonous and phosphorous acid;
- b) Melamine cyanurate; and
- c) A polyurethane polymer base.

4. A composition according to claim 1, which comprises


- a) At least one at least one ester derivative of phosphonous and phosphorous acid selected from the group consisting of




- 41 -




,




,




,




,




- 42 -





5 b) Melamine cyanurate; and
 c) A polyurethane polymer base.
 5. A composition according to claim 1, which comprises
 a) At least one ester derivative of phosphorous and phosphorous acid selected
 from the group consisting of





- 43 -



,



5



;

b) Melamine cyanurate; and
 c) A polyurethane polymer base.

6. A composition according to claim 1, which comprises

10 a) At least one ester derivative of phosphonous and phosphorous acid selected from the group consisting of tris nonylphenyl phosphite (TNPP), triphenyl phosphite (TPP), diphenyl phosphite (DPP), phenyl diisodecyl phosphite (PDDP), diphenyl isodecyl phosphite (DPDP), diphenylisoctyl phosphite (DPIOP), tetra-phenyl dipropylene glycol diphosphite(THOP), poly (dipropylene glycol) phenyl

phosphite (DHOP), dodecyl diphenyl phosphite (DDPP), triisodecylphosphite (TDP), tris tridecyl phosphite (TTDP) and trilauryl phosphite (TLP);

- b) Melamine cyanurate; and
- c) A polyurethane polymer base.

5 7. A composition according to claim 1, which comprises

- a) At least one ester derivative of phosphorous or phosphorous acid selected from the group consisting of 9,10-dihydro-9-oxa-10-phosphorylphenanthrene-10-oxide (DOPO), bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite, $[(C_6H_5-O)_2P]_2(-O-C_2H_4)_2$, $[(C_6H_5-O)_2P]_2(-OC_2H_5)_{14}(C_6H_5-O-P)_6$ and triphenyl phosphite;
- b) Melamine cyanurate; and
- c) A polyurethane polymer base

8. A process for imparting flame retardancy to a polyurethane polymer base, which process comprises adding to said polymer base a mixture, which comprises

15

- a) At least one ester derivative of a phosphorus containing oxo acid selected from the group consisting of oxaphosphorinoxide, phosphorous acid and phosphorous acid; and
- b) At least one flame retardant component based on a nitrogen compound.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2006/066045

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08K5/524 C08K5/3492 C08K5/5393 C08K5/5313

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, BEILSTEIN Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 2002/115782 A1 (BRAUER WOLFGANG ET AL) 22 August 2002 (2002-08-22) paragraphs [0036] - [0041], [0049] - [0064]; claim 1 ----- US 2004/138351 A1 (KAPRINIDIS NIKOLAS ET AL) 15 July 2004 (2004-07-15) paragraphs [0043], [0066], [0074] - [0082]; claims 1,4; example 20 -----	1-6
Y	US 5 837 760 A (HACKL ET AL) 17 November 1998 (1998-11-17) cited in the application claims 1-10 column 6, line 24 - column 7, line 35; examples 1-7 ----- -/-	1-6
A		1-6

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
7 November 2006	14/11/2006

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Dury, Olivier
---	-------------------------------------

INTERNATIONAL SEARCH REPORT

International application No PCT/EP2006/066045

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	LEVCHIK, S.; WEIL,, E.D.: "Thermal decomposition, combustion and fire-retardancy of polyurethanes - a review of the recent literature" POLYMER INTERNATIONAL, vol. 53, 2004, pages 1585-1610, XP009056309 the whole document ----- JP 09 020743 A (MITSUI TOATSU CHEMICALS) 21 January 1997 (1997-01-21) abstract ----- US 2004/147648 A1 (CORCORAN PATRICK HENRY [US] ET AL) 29 July 2004 (2004-07-29) paragraph [0076]; claim 1; examples 3,5 -----	1-6
A		1-8
A		1-8

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2006/066045

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
US 2002115782	A1 22-08-2002	CN EP JP	1346847 A 1195395 A1 2002161203 A	01-05-2002 10-04-2002 04-06-2002
US 2004138351	A1 15-07-2004		NONE	
US 5837760	A 17-11-1998		NONE	
JP 9020743	A 21-01-1997		NONE	
US 2004147648	A1 29-07-2004		NONE	