

67 66 55

AUSTRALIA
PATENTS ACT 1990

PATENT REQUEST : STANDARD PATENT

I/We being the person(s) identified below as the Applicant(s), request the grant of a patent to the person(s) identified below as the Nominated Person(s), for an invention described in the accompanying standard complete specification.

Full application details follow:

[71/70] Applicant(s)/Nominated Person(s):

Hitachi, Ltd.

of

6, Kanda Surugadai 4-chome, Chiyoda-ku, Tokyo, 101, Japan

[54] Invention Title:

Method for producing electrically insulated coils

[72] Name(s) of actual inventor(s):

Katsuo SUGAWARA
Tohru KOYAMA
Syoichi MARUYAMA

[74] Address for service in Australia:

DAVIES COLLISON CAVE, Patent Attorneys, 1 Little Collins Street, Melbourne,
Victoria, Australia. Attorney Code: DM

Basic Convention Application(s) Details:

[31] Application Number	[33] Country	Code	[32] Date of Application
7-103943	Japan	JP	27 April 1995

DATED this NINETEENTH day of APRIL 1996

Keith Collison
.....

a member of the firm of DAVIES
COLLISON CAVE for and on
behalf of the applicant(s)

40000001 190496

AUSTRALIA
PATENTS ACT 1990
NOTICE OF ENTITLEMENT

We, Hitachi, Ltd., the applicant/Nominated Person named in the accompanying Patent Request state the following:-

The Nominated Person is entitled to the grant of the patent because the Nominated Person derives title to the invention from the inventors by assignment.

The Nominated Person is entitled to claim priority from the basic application listed on the patent request because the Nominated Person made the basic application.

DATED this NINETEENTH day of APRIL 1996


.....

a member of the firm of
DAVIES COLLISON CAVE
for and on behalf of the
applicant(s)

(DCC ref: 1815485)



AU9650765

(12) PATENT ABRIDGMENT (11) Document No. AU-B-50765/96
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 676655

- (54) Title
METHOD FOR PRODUCING ELECTRICALLY INSULATED COILS
- International Patent Classification(s)
(51)⁶ H02K 015/12 H01F 005/06 H01F 041/12 H02K 003/32
- (21) Application No. : 50765/96 (22) Application Date : 19.04.96
- (30) Priority Data
- (31) Number (32) Date (33) Country
7-103943 27.04.95 JP JAPAN
- (43) Publication Date : 07.11.96
- (44) Publication Date of Accepted Application : 13.03.97
- (71) Applicant(s)
HITACHI, LTD.
- (72) Inventor(s)
KATSUO SUGAWARA; TOHRU KOYAMA; SYOICHI MARUYAMA
- (74) Attorney or Agent
DAVIES COLLISON CAVE , 1 Little Collins Street, MELBOURNE VIC 3000
- (56) Prior Art Documents
JP 5-83905
US 4649640
JP 60-26441
- (57) Claim

1. A method of producing an electrically insulated coil having insulating layers formed by winding insulating material around an electric conductor to form an insulating substrate, then by applying impregnating varnish consisting of thermosetting resin to the insulating substrate so as to be hardened, said production method being characterised by comprising the steps of

heating the substrate at a temperature which will cause the impregnating varnish on the surface of the insulating substrate to lose its fluidity in under 30 minutes in order to preset the varnish after the insulating substrate is impregnated with the varnish, wherein the impregnating varnish is made up of acid anhydride setting epoxy resin elements that include latent accelerators and these accelerators take more than 30 days to increase their initial viscosity by three times during storage at 25 degrees centigrade, and

setting the varnish at a heat at least 10 degrees centigrade lower than the presetting temperature.

AUSTRALIA
PATENTS ACT 1990
COMPLETE SPECIFICATION

NAME OF APPLICANT(S):

Hitachi, Ltd.

ADDRESS FOR SERVICE:

DAVIES COLLISON CAVE
Patent Attorneys
1 Little Collins Street, Melbourne, 3000.

INVENTION TITLE:

Method for producing electrically insulated coils

The following statement is a full description of this invention, including the best method of performing it known to me/us:-

Background of the Invention

- 5 This invention is related to the electrically insulated coils used in rotating electrical machinery and transformers; especially electrically insulated coils for which impregnating varnish is used repeatedly for the insulating layer.
- 10 The demands for smaller and lighter rotating electrical machinery for vehicles and general industrial use is stronger than ever. The electrically insulated coils used in this machinery must be capable of insulating high voltages and have high heat
- 15 resistance.
- The insulating layers of this type of electrically insulated coil is woven or unwoven fabric made of inorganic or organic textiles (such as glass fiber or polyamide), and insulating tape material made of mica,
- 20 organic high polymer film and binder resins. These materials are wound around the conductor to the specified thickness to form the covering layer. Next a thermosetting varnish with low viscosity (such as unsaturated polyester resin, epoxy resin or silicone
- 25 resin) is vacuum or pressure impregnated in the

covering layer, and allowed to harden.

Epoxy resins are commonly used as the impregnating varnish because they have good all around properties. Although epoxy resins have many different setting properties, they all have low viscosity, good impregnating properties and are easy to handle. In addition, because the various properties of the hardened resins are good, low viscosity acid anhydride epoxies and hardening epoxies are commonly used.

Although the pot life of acid anhydride setting epoxy resins is long, their setting time is also long, so that setting accelerators are used. In general, the viscosity increase rate rises when setting accelerators are directly added to resins, so that the time the resins can be used for impregnation work (pot life) is shortened. Therefore, various types of setting accelerators with high potentials have been developed so that the pot life of impregnating varnishes stay long even after the accelerators have been added.

For example the following accelerators are well known: imidazole compounds, boron trifluoride amine compounds, quaternary phosphonium compounds, tertiary amine and epoxy addition reaction products, tetraphenylboron complexes, various metal

acetylacetonates, naphthenic acid metal salts, and octanoic acid metal salts.

Another method which has been proposed is to put accelerators in capsules, then placing these capsules
5 in the resin. These capsules are dissolved when the resin is heated to a certain temperature and the accelerator is then dissolved in the resin. The capsules tend to break when the resin is agitated, however, thereby reducing pot life, and they also tend
10 to sink to the bottom of the resin when in storage, so that accelerator effectiveness is reduced. Because of these undesirable features, this method was not satisfactory for practical use.

When setting accelerators with high potential are
15 added to impregnating varnishes, the setting times are longer because of the low setting properties of the accelerators. When these accelerators are used with conventional heat setting, the resin impregnated in the insulating layer tends to seep out.

20 For instance, the various metal acetylacetonates, naphthenic acid metal salts, and octanoic acid metal salts have very good potential, but they have inferior setting properties. In heat setting as described above, the resin impregnated in the insulating layer
25 seeps out during hardening, so that the performance of

the insulating layer is not always sufficient.

Because of these reasons, setting accelerators are commonly added to the insulating tape side, rather than adding them to the impregnating varnishes. The
5 three methods described below are used to achieve this "painting."

(1) Add setting accelerator to the binder resin when making insulating tape.

(2) Add setting accelerator to the insulating
10 tape by dipping the tape in the setting accelerator solution.

(3) After wrapping insulating tape around the coil conductor, add setting accelerator to the insulating tape layer by impregnating the insulating
15 tape layer with setting accelerator.

When an insulating coil is made with any of the above methods, however, the setting accelerator is mixed with the varnish from the surface of the coil insulating layer, so that the amount of accelerator is
20 small. As a result, the varnish on the surface of the insulating later will not set sufficiently, and, depending on the conditions, the surface of the coil will be left sticky with unset varnish. Furthermore, the amount of varnish which will be seep away from the
25 insulating layer surface will increase, so that the

- 5 -

performance of the insulating coil will not be sufficient.

Therefore, in order to cope with the diversification, increased productivity and rationalization of electrically insulated coils with impregnated varnish, it is easier to use impregnating varnish with setting accelerator added to it, rather than adding setting
5 accelerators to the insulating layer.

In the aforementioned conventional methods of producing electrically insulated coils by impregnating varnish in the insulating layer; both the method of applying setting accelerator to the insulating tape, and the method of adding high potential accelerators such as the various metal acetylacetonates, naphthenic acid metal salts, and octanoic acid metal salts to the
10 impregnating varnish, none of the methods could both satisfy the impregnating varnish pot life requirements and insulating coil performance requirements after hardening.

Summary of the Invention

According to the invention there is provided a method of producing an electrically
15 insulated coil having insulating layers formed by winding insulating material around an electric conductor to form an insulating substrate, then by applying impregnating varnish consisting of thermosetting resin to the insulating substrate so as to be hardened, said production method being characterised by comprising the steps of

heating the substrate at a temperature which will cause the impregnating varnish on the
20 surface of the insulating substrate to lose its fluidity in under 30 minutes in order to preset the varnish after the insulating substrate is impregnated with the varnish, wherein the impregnating varnish is made up of acid anhydride setting epoxy resin elements that include latent accelerators and these accelerators take more than 30 days to increase their initial viscosity by three times during storage at 25 degrees centigrade, and

25 setting the varnish at a heat at least 10 degrees centigrade lower than the presetting temperature.

Embodiments of the invention provide highly reliable electrically insulated coil production methods which maintain long impregnating varnish pot life, and reduce the amount of impregnating varnish which seeps out of the insulating coils and provides the insulating
30 coils with a uniform insulating layer.



- 6 -

Major aspects of particular forms of the invention are as follows:

(1) In the production of electrically insulated coils which make up insulating layers, insulating material is wound around an electric conductor to form an insulating substrate, then impregnating varnish consisting of thermosetting resin is applied to the insulating substrate
5 and hardened.

In this electrically insulated coil production method, the impregnating varnish is made up of acid anhydride setting epoxy resin elements that include latent accelerators. These accelerators take more than 30 days to increase their initial viscosity by three times during storage at 25 degrees centigrade. After the insulating substrate is impregnated with the
10 varnish, the substrate is heated at a temperature which will cause the impregnating varnish on the surface of the insulating substrate to lose its fluidity in under 30 minutes in order to preset the varnish. Next, the varnish is set at a heat at least 10 degrees centigrade lower than the presetting temperature. This is the feature of this production



method.

(2) An electrically insulated coils production method in which the presetting temperature is from 170 to 250 degrees centigrade.

5 The above impregnating varnish is made up of acid anhydride setting epoxy resin components with high latent accelerator added to it. In addition, the surface of the insulating layer is preset at a temperature which will cause the impregnating varnish
10 to lose its fluidity within 30 minutes after it is applied, and the rest of the setting is allowed to take place at a temperature which is at least 10 degrees centigrade lower than the presetting temperature. These have allow both a long pot life for
15 the impregnating varnish, and goo electrically insulated coil performance.

 The latent accelerator is chosen from metal acetylacetonates, metal benzoylacetonate, metallic napythenates, and metallic octanates. From 0.05 to 2
20 parts latent accelerator (preferably 0.1 to 0.5 part) is added to 100 parts of impregnating varnish. This latent accelerator is dissolved in warm acid anhydride, and then is mixed with epoxy so as to provide varnish. The insulating material of the
25 electric conductor is impregnated with this varnish,

and it is heated to preset the varnish, so that the varnish on the surface of the insulating layer loses its fluidity within 30 minutes. The heating temperature at this time is from 170 to 250 degrees centigrade, preferably from 180 to 230 degrees centigrade.

After presetting, the insulating layer is allowed to harden at a temperature which is at least 10 degrees centigrade lower than the presetting temperature.

In this invention, the impregnating varnish loses its fluidity because of the presetting temperature which is higher than the setting temperature. This prevents the varnish impregnated in the insulating layer from seeping out and, thereby, improves the performance of the insulating layer, so that a highly reliable electrically insulated coil can be produced.

In addition, the pot life of the varnish can be improved by using latent accelerators.

Detailed Description of the Preferred Embodiments

The specifics of this invention shall be explained through embodiments. The abbreviations of the epoxy resins, hardening agents and setting accelerators used in the embodiments are listed below.

[Epoxy Resins]

- 1) YL-932 (Mitsubishi Petrochemical/Shell epoxy product name): 1,1,3-tris methane [p-(2,3-epoxy propoxy) phenyl] (trifunctional): epoxy equivalent 161
- 5 2) L-2832 (Mitsubishi Petrochemical/Shell epoxy product name): Mixture of trifunctional and bifunctional bisphenol A epoxy: epoxy equivalent 180
- 3) DER-332 (Dow Chemical product name): Bifunctional bisphenol A epoxy: epoxy equivalent 175
- 10 4) EXA-4750 (Dai Nippon Ink & Chemicals Inc.): Trifunctional naphthalene ring epoxy: epoxy equivalent 187
- 5) HP-4032 (Dai Nippon Ink & Chemicals Inc.): Bifunctional naphthalene ring epoxy: epoxy equivalent 151
- 15

[Acid Anhydride Hardening Agents]

- 1) MHAC-P (Hitachi Kasei Kogyo product name): Methyl hymic acid anhydride: anhydride equivalent 178

[Malaymide]

- 20 2) MP-2000X (Mitsubishi Petrochemical product name): Multifunctional malaymide

[Setting Accelerators]

- 1) Co (III) AA (Aldrich): Cobalt (III) acetylacetonate
- 25 2) Mn (III) AA (Wako Junyaku Kogyo): Manganese

(III) acetylacetonate

3) MnNA (Nippon Kagaku Sangyo): Naphthenic acid
manganese

4) ZnNA (Nippon Kagaku Sangyo): Naphthenic acid
5 zinc

5) MnOC (Nippon Kagaku Sangyo): Octanoic acid
manganese

6) 2E4MZ (Shikoku Kasei Kogyo product name): 2-
ethyl-4-methylimidazole

10 7) 2PZ-CN (Shikoku Kasei Kogyo product name): 1-
cyanoethyl-2phenylimidazole

8) TPP-K (Tokyo Ohka Kogyo):
Tetraphenylphosphine, tetraphenylborate

9) BF₃-MEA (Hashimoto Kasei Kogyo): Boron
15 trifluoride monoethyl amine

(1) Making Insulating Tape

The binder solution for making insulating tape was
a methyl ethyl ketone (MEK) and tetrahydrofuran (THF)
solution (mix ratio: 50:50 on a weight basis) with YL-
20 932 and MP-2000X (mix ratio: 70:30 on a weight basis)
dissolved in it, so that the density of the
nonvolatile portion was about 20 percent of the
weight.

The binder solution was used to cement an unfired
25 soft laminated mica sheet and glass cloth, and the

solvents were allowed to vaporize. The glass-backed mica tape (insulating material) was made so that the nonvolatile elements of the binder made up about 10 per cent of the weight (based on the total weight of the insulating material). This insulating material was cut to make 25 mm width tape.

(2) Making Insulating Coil Impregnating Varnish
Epoxy Resin Composition (A)

The various setting accelerators were added to the acid anhydride hardening agent (MHAC-P), so that their quantity (percentage of weight) in relation to the total resin quantity was as shown in Table 1, then the hardening agent was heated and mixed to dissolve it (undissolved matter was left as is). After the hardening agent returned to room temperature, the L-2832 to DER-332 epoxy compound was mixed to a ratio of 30:70 (weight ratio). The acid anhydride hardening agent (MHAC-P) to epoxy compound mixture ratio was 1.05:1.

Epoxy Resin Composition (B)

The various setting accelerators were added to the acid anhydride hardening agent (MHAC-P), so that their quantity (percentage of weight) in relation to the total resin quantity was as shown in Table 1, then the hardening agent was heated and mixed to dissolve it.

After it returns to room temperature, the EXA-4750 to HP-4032 compound was mixed to a ratio of 20:80 (weight ratio). The acid anhydride hardening agent (MHAC-P) to epoxy compound mixture ratio was 1.1:1.

- 5 (a) Measuring the time impregnating varnish stops being fluid: The time it took for varnish in a test tube to loose fluidity when placed in a constant temperature oil bath was measured.

 (b) Impregnating varnish conditions and pot life:

- 10 Eighty ml of impregnating varnish was placed in a 100 ml screw-top bottle, and the condition of the resin when stored at a constant temperature of 25 degrees centigrade was monitored. If the setting accelerator was well distributed and did not sink to
- 15 the bottom, it was considered satisfactory. If it took the resin more than 30 days to increase its viscosity by three times, then the pot life was given an up check, and if it took less than 30 days it was given a down check.

- 20 (3) Making the Electric Insulating Coil

- The insulating tape in (1) above was wrapped five times around 50 mm wide by 10 mm thick by 250 mm long copper conductors, then pre-dried at 110 degrees centigrade for five hours. Next, the tapes were
- 25 impregnated with the impregnating varnish in (2) above

in a vacuum. These impregnated coils were placed in a heat setting furnace with the wide sides facing up and down, and left to sit with the setting conditions indicated in Tables 2 to 5 to make the insulating layers for the model coils. The temperature of the insulating layer surfaces were measured by fixing the ends of thermocouples to the upper surface of the insulating layers.

[Embodiments 1 to 5, Comparisons 1 to 5]

The furnace temperature was preset to 210 degrees centigrade. The insulated coils impregnating with varnish were placed in the furnace for one hour. Then the temperature was decreased to 180 degrees centigrade over 30 minutes, then the insulated coils were allowed to harden for 15 hours at that temperature.

The insulated coil setting conditions, the appearance of the insulating layer, and the resin content ratios in the top and bottom insulating layers are shown in Table 2.

[Embodiments 6 to 10, Comparisons 6 to 10]

The insulated coils were placed in the furnace, then the furnace temperature was increased from room temperature to 230 degrees centigrade in two hours, and the insulated coils were kept in the furnace at

that temperature for one hour. Then the temperature was decreased to 210 degrees centigrade over 30 minutes, then the insulated coils were allowed to harden for 15 hours at that temperature.

- 5 The insulated coil setting conditions, the appearance of the insulating layer, and the resin content ratios in the top and bottom insulating layers are shown in Table 3.

[Embodiments 11 to 15, Comparisons 11 to 15]

- 10 The insulated coils were placed in the furnace, and the furnace temperature was increased from room temperature to 210 degrees centigrade in 1.5 hours, then the insulated coils were allowed to harden at 210 degrees centigrade for 15 hours.

- 15 The insulated coil setting conditions, the appearance of the insulating layer, and the resin content ratios in the top and bottom insulating layers are shown in Table 4.

[Comparisons 16 to 25]

- 20 The insulated coils were placed in the furnace, and the furnace temperature was increased from room temperature to 130 degrees centigrade in one hour. After heating for five hours at 130 degrees centigrade, the temperature was increased to 150
25 degrees centigrade in 30 minutes. The insulated coils

were heated at this temperature for five hours, then the temperature was increased to 180 degrees centigrade in 30 minutes, and the coils were allowed to set at this temperature for 15 hours (conventional graded setting). After hardening, in all cases the furnaces were allowed to cool down to room temperature in five hours.

The insulated coil setting conditions, the appearance of the insulating layer, and the resin content ratios in the top and bottom insulating layers are shown in Table 5.

(a) Resin content in insulated coils

After hardening, the insulated layers were cut out, placed in pots, then heated in electric furnaces to 700 degrees centigrade. The resin content was calculated from the mica and glass cloth residues. If the resin content in the upper insulating layer was over 95 per cent of that in the lower insulating layer, then the piece passed, if not it failed.

(b) Insulating layer appearance inspection

The surfaces of the model coil insulating layers were visually checked after the above curing processes for discoloring and wrinkling. This test was passed if there was no blackening, no bubbling and no wrinkling.

Adding metal acetylacetonates, naphthenic acid

metal salts, and octanoic acid metal salts to the impregnating varnish and using the hardening methods of this invention clearly produces electrically insulated coil layers with better performance than
5 conventional techniques. This is especially true in static thermosetting in which the difference between resin content in the upper and lower insulated layers is smaller than that for conventional methods, so that highly reliable insulating layers can be created. In
10 addition, curing characteristics have been improved and the appearance is also better.

The model coils in these tests were hardened in a static state, but if they are rotated when curing, then the resin content in the insulating layers will
15 be even more uniform, so this method is desirable.

The initial temperature increasing rate and maximum temperature used to harden insulated coils will depend on the type and amount of setting accelerator used, so these can be set so that the
20 fluidity in the impregnating varnish in the insulating layer is gone in 30 minutes. In addition to the examples listed here, infrared lamps can be used to cure the surface of the insulating layers in even shorter time.

19 04 98 50785

20

15

10

5

		Impregnating varnish composition number											
		Compositions using the setting accelerators from this invention							Compositions using the setting accelerators from conventional methods				
		1	2	3	4	5	6	7	8	9	10	11	12
Epoxy resin		(A)	(A)	(A)	(A)	(A)	(B)	(B)	(A)	(A)	(A)	(A)	(A)
Setting accelerator	Co (III) AA	0.5	-	-	-	-	-	-	-	-	-	-	-
	Mn (III) AA	-	0.5	-	-	-	0.5	-	-	-	-	-	-
	MnNA	-	-	0.5	-	-	-	0.5	-	-	-	-	-
	ZnNA	-	-	-	0.5	-	-	-	-	-	-	-	-
	MnOC	-	-	-	-	0.5	-	-	-	-	-	-	-
	2E4MZ	-	-	-	-	-	-	-	0.5	-	-	-	-
	2PZ-CN	-	-	-	-	-	-	-	-	0.5	-	-	-
	TPP-K	-	-	-	-	-	-	-	-	-	0.5	-	-
	BF ₃ -MEA	-	-	-	-	-	-	-	-	-	-	0.5	-
Time it took to stop varnish fluidity (minutes). Heating temperature: 170°C		23	30	25	22	32	25	20	5	6	8	20	>500
Varnish condition *		O	O	O	O	O	O	O	O	O	x	O	O
Varnish pot life ** Storage temperature: 25°C		O	O	O	O	O	O	O	x	x	x	x	O

* O: Good

x: Sediments; faulty distribution

** O: 30 days or more

x: Less than 30 days

Table 1

Table 2

[illegible]

* (Upper side/lower side) x 100

O: 95 per cent or greater x: Less than 95 per cent

★★ O; Good

x: Insulating layer surface blackened, bubbles, wrinkles.

Table 3

[illegible]

Table 4

[illegible]

Table 5

[illegible]

In general, if the amount of setting accelerator is small the initial temperature increase rate must be quickened and made higher, but in the case of acid anhydride setting epoxy resins a maximum hardening temperature of under 250 degrees centigrade is desirable. Also, pot life is usually longer if less setting accelerator is used, but the setting time becomes longer and the various properties of the setting material tend to deteriorate.

In addition, if the initial temperature is higher than 200 degrees centigrade, conventional setting accelerators caused the resin to become black and bubble. The latent accelerators in this discovery do not blacken or bubble, and can produce good insulating layers.

In this invention, although this is dependent on the initial hardening temperature, and the type and amount of the setting accelerator, when the fluidity of the varnish on the coil surface is gone, hardening is done at a temperature at least 10 degrees lower than the initial temperature.

Although there are many different acid anhydride setting impregnating epoxy resins, when the fact that they will be hardened by quickly subjecting them to high temperatures is considered, it is necessary that

- 21 -

the resin does not degrade when hardening. Therefore, a resin with a high degrading temperature is desirable. If the acid anhydride mix is within a conventional ratio, then it is not limited to those in the embodiments.

As setting accelerators which can be directly added to impregnating varnish, metal
5 acetylacetonates, naphthenic acid metal salts, and octanoic acid metal salts allow long resin pot life and stable storage properties, but they have inferior hardening properties. Even if these are used with this invention, however, they can be prevented from seeping out of the impregnated insulating layer, so that a uniform resin layer can be obtained and a good insulating coil is possible.

10 Particular setting accelerators useful in the invention include Co (II) acetylacetonate, Co (III) acetylacetonate, Co (II) benzoylacetonate, Mn (III) acetylacetonate, Fe (III) acetylacetonate, or Zr (IV) acetylacetonate.

The embodiments gave examples in which setting accelerators were mixed with insulating varnish, however, the purposes of this invention can also be achieved by adding
15 setting accelerators to the insulating material.

This invention can prevent the seeping out of varnish impregnating insulating layers, so that producing insulating coils with uniform resin content in the upper and lower parts is possible, and electrically insulated coils with high reliability can



be obtained.

0
1
2
3

4
5

6
7

8
9

- 23 -

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:-

1. A method of producing an electrically insulated coil having insulating layers formed by winding insulating material around an electric conductor to form an insulating substrate, then by applying impregnating varnish consisting of thermosetting resin to the insulating substrate so as to be hardened, said production method being characterised by comprising the steps of

heating the substrate at a temperature which will cause the impregnating varnish on the surface of the insulating substrate to lose its fluidity in under 30 minutes in order to preset the varnish after the insulating substrate is impregnated with the varnish, wherein the impregnating varnish is made up of acid anhydride setting epoxy resin elements that include latent accelerators and these accelerators take more than 30 days to increase their initial viscosity by three times during storage at 25 degrees centigrade, and

setting the varnish at a heat at least 10 degrees centigrade lower than the presetting temperature.

2. A production method of an electrically insulated coil as defined in Claim 1, wherein



the presetting temperature is from 170 to 250 degrees centigrade.

3. A production method of an electrically insulated coil as defined in Claims 1 and 2, wherein
5 the latent accelerator in the impregnating varnish is at least one of metallic acetate, metallic naphthenic acid and metallic octanoic acid.

4. A production method of an electrically insulated coil as defined in Claim 3, wherein
10 the latent accelerator in the impregnating varnish is made up of at least one of the following: Co (II) acetylacetonate, Co (III) acetylacetonate, Co (II) benzoylacetonate, Mn (III) acetylacetonate, Fe (III) acetylacetonate, or Zr (IV) acetylacetonate.

5. A production method of an electrically insulated coil as defined in Claim 1, wherein
the latent accelerator in the impregnating varnish is based on metallic naphthenic acid or metallic octanate and the coordinating metal is at least one of
20 the following: Co, Mn, and Zn.

6. A production method of an electrically insulated coil as described in Claims 1 to 4 in which there are 0.05 to 2 parts latent accelerator added to 100 parts impregnating varnish.

7. A production method of an electrically

insulated coil as defined in Claims 1 to 6, wherein
the insulating material is insulating tape backed
with binder resin.

10
11
12
13
14
15
16
17
18
19
20

8. A method for producing electrically insulated coils substantially as hereinbefore described with reference to the examples.

9. An electrically insulated coil where produced by the method of any one of the preceding claims.

~~10. The steps, features, compositions and compounds disclosed herein or referred to or indicated in the specification and/or claims of this application, individually or collectively, and any and all combinations of any two or more of said steps or features.~~

DATED this NINETEENTH day of APRIL 1996

Hitachi, Ltd.

by DAVIES COLLISON CAVE
Patent Attorneys for the applicant(s)



Abstract of the Disclosure

In the production of electrically insulated coils which make up insulating layers, insulating material is wound around an electric conductor to form an
5 insulating substrate, then impregnating varnish consisting of thermosetting resin is applied to the insulating substrate and hardened. In this electrically insulated coil production method, the impregnating varnish is made up of acid anhydride
10 setting epoxy resin elements that include latent accelerators. These accelerators take more than 30 days to increase their initial viscosity by three times during storage at 25 degrees centigrade. After the insulating substrate is impregnated with the
15 varnish, the substrate is heated at a temperature which will cause the impregnating varnish on the surface of the insulating substrate to lose its fluidity in under 30 minutes in order to preset the varnish. Next, the varnish is set at a heat at least
20 10 degrees centigrade lower than the presetting temperature and thereby, electrically insulated coils with high reliability is obtained.