



HU000028006T2

(19) **HU****MAGYARORSZÁG**  
Szellemi Tulajdon Nemzeti Hivatala(11) Lajstromszám: **E 028 006**(13) **T2****EURÓPAI SZABADALOM**  
**SZÖVEGÉNEK FORDÍTÁSA**(21) Magyar ügyszám: **E 12 787692**(22) A bejelentés napja: **2012. 11. 09.**

(96) Az európai bejelentés bejelentési száma:

**EP 20120787692**

(97) Az európai bejelentés közzétételi adatai:

**EP 2776208 A1** **2013. 05. 16.**

(97) Az európai szabadalom megadásának meghirdetési adatai:

**EP 2776208 B1** **2015. 08. 19.**(51) Int. Cl.: **B23K 35/00** (2006.01)**B23K 35/02** (2006.01)**B23K 35/28** (2006.01)**B23K 103/10** (2006.01)**B32B 15/01** (2006.01)**C22C 21/00** (2006.01)**C22C 21/02** (2006.01)

(86) A nemzetközi (PCT) bejelentési szám:

**PCT/EP 12/072280**

(87) A nemzetközi közzétételi szám:

**WO 13068539**

(30) Elsőbbségi adatok:

**11188842****2011. 11. 11.****EP**

(72) Feltaláló(k):

**WITTEBROOD, Adrianus Jacobus, NL-1991 HB****Velserbroek (NL)****KIRKHAM, Steven, 56235 Ransbach-Baumbach (DE)****BÜRGER, Achim, 56203 Höhr Grenzhausen (DE)****Vierregge, Klaus, 56237 Nauort (DE)**

(73) Jogosult(ak):

**Aleris Rolled Products Germany GmbH, 56070****Koblenz (DE)**

(74) Képviselő:

**Dr. Kereszty Marcell, Gödölle, Kékes,****Mészáros & Szabó Szabadalmi és Védjegy****Iroda, Budapest**

(54)

**Alumíniumötvözet lemeztermék vagy extrudált termék folyatószer nélküli keményforrasztáshoz**

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.



(11) **EP 2 776 208 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
**19.08.2015 Bulletin 2015/34**

(21) Application number: **12787692.8**

(22) Date of filing: **09.11.2012**

(51) Int Cl.:  
**B23K 35/00** <sup>(2006.01)</sup> **B23K 35/02** <sup>(2006.01)</sup>  
**B23K 35/28** <sup>(2006.01)</sup> **B32B 15/01** <sup>(2006.01)</sup>  
**C22C 21/00** <sup>(2006.01)</sup> **C22C 21/02** <sup>(2006.01)</sup>  
**B23K 103/10** <sup>(2006.01)</sup>

(86) International application number:  
**PCT/EP2012/072280**

(87) International publication number:  
**WO 2013/068539 (16.05.2013 Gazette 2013/20)**

(54) **ALUMINIUM ALLOY SHEET PRODUCT OR EXTRUDED PRODUCT FOR FLUXLESS BRAZING**  
**ALUMINIUMLEGIERUNGSBLECHPRODUKT ODER EXTRUDIERTES PRODUKT FÜR**  
**FLUSSMITTELFREIES HARTLÖTEN**  
**PRODUIT EN TÔLE OU PRODUIT EXTRUDÉ D'ALLIAGE D'ALUMINIUM POUR BRASAGE SANS**  
**FONDANT**

(84) Designated Contracting States:  
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB**  
**GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO**  
**PL PT RO RS SE SI SK SM TR**

(30) Priority: **11.11.2011 EP 11188842**

(43) Date of publication of application:  
**17.09.2014 Bulletin 2014/38**

(73) Proprietor: **Aleris Rolled Products Germany**  
**GmbH**  
**56070 Koblenz (DE)**

(72) Inventors:  
• **WITTEBROOD, Adrianus Jacobus**  
**NL-1991 Hb Velserbroek (NL)**

- **KIRKHAM, Steven**  
**56235 Ransbach-Baumbach (DE)**
- **BÜRGER, Achim**  
**56203 Höhr Grenzhausen (DE)**
- **VIEREGGE, Klaus**  
**56237 Nauort (DE)**

(74) Representative: **Müller Schupfner & Partner**  
**Patent- und Rechtsanwaltspartnerschaft mbB**  
**Bavariaring 11**  
**80336 München (DE)**

(56) References cited:  
**EP-A1- 1 306 207 WO-A2-2011/034496**  
**US-A1- 2003 098 338 US-A1- 2006 102 696**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 2 776 208 B1**

## Description

## FIELD OF THE INVENTION

**[0001]** The invention relates to an aluminium alloy sheet product or extruded product suitable for fluxless brazing and comprising of an aluminium alloy core having on at least one face an Al-Si filler clad layer. Furthermore, the invention relates to a method of brazing a brazed assembly incorporating at least one member made from the brazing sheet material and/or the extruded material.

## BACKGROUND TO THE INVENTION

**[0002]** As will be appreciated herein below, except as otherwise indicated, aluminium alloy designations and temper designations refer to the Aluminium Association designations in Aluminium Standards and Data and the Registration Records, as published by the Aluminium Association in 2011 and are well known to the person skilled in the art.

**[0003]** For any description of alloy compositions or preferred alloy compositions, all references to percentages are by weight percent unless otherwise indicated. The term "up to" and "up to about", as employed herein, explicitly includes, but is not limited to, the possibility of zero weight-percent of the particular alloying component to which it refers. For example, up to about 0.15% Ti may include an alloy having no Ti.

**[0004]** There are various brazing processes in use for the industrial scale manufacturing of heat exchangers.

**[0005]** There is vacuum brazing which is carried out at relatively low atmosphere pressure in the order of about  $1 \times 10^{-5}$  mbar or less, and is an essentially discontinuous process and puts high demands on material cleanliness. To obtain the optimum conditions for joining to take place, aluminium alloys commonly used for vacuum brazing contain purposive additions of Mg of 1 % or more. The Mg destroys the hard oxide film of the filler alloy when it evaporates from the brazing sheet during brazing, and further the evaporated Mg plays the role as getter that removes oxygen and moisture remaining in the brazing furnace. There is always more magnesium present in the furnace than necessary. The excess magnesium condenses on the cold spots in the vacuum furnace and has to be removed frequently. The capital investment for suitable equipment is relatively high.

**[0006]** NOCOLOK™ (registered trademark) flux brazing has been used as the principal brazing process to braze automotive heat exchangers by many heat exchanger manufacturers. Major problems that have arisen from the NO-COLOK process have been flux costs, flux handling and the damage flux causes to the furnaces. Also, in complex shaped assemblies the application of the brazing flux prior to brazing at the interior of the assemblies is often considered very difficult and problematic. Consequently, most of the heat exchanger manufacturers have been trying to reduce flux consumption.

**[0007]** Another brazing process is controlled atmosphere brazing ("CAB") without using a brazing flux.

**[0008]** European patent document EP-1430988-A discloses that for such a process of CAB without using a brazing flux the brazing sheet product used contains Mg at least in a layer constituting the brazing sheet other than the filler alloy layer, typically the core alloy contains Mg in a range of 0.05% to 1.0 wt.%. Interposed between the core alloy and the filler alloy there is present a diffusion prevention layer such a Mg-free AA3003-series aluminium alloy.

**[0009]** European patent document EP-1306207-B1 discloses another fluxless brazing process in an inert gas atmosphere containing a very low oxygen content. Furthermore there is disclosed a brazing sheet product comprising of an aluminium core alloy on one or both sides clad with an Al-Si alloy brazing alloy containing 0.1-5% of Mg and 0.01-0.5% of Bi as an intermediate layer, and a thin covering material clad onto the Al-Si alloy brazing alloy. It is disclosed that during a brazing operation the brazing material in the intermediate layer is molten as the temperature is elevated during brazing, but oxidation of the surface of the brazing material does not occur because the surface is covered with the thin covering material which remains solid. When the temperature is further elevated, the portions with lower melting points, such as a segregation portion of the thin covering material close to the molten brazing material, are locally molten, and then the brazing material seeps and spreads over the surface of the thin covering material due to volumetric expansion. The surface of the brazing material then becomes an emerging face without an oxidation film, and new intensive oxidation does not proceed due to the inert gas atmosphere.

**[0010]** An alternative approach to EP-1306207 is disclosed in each of international application WO-2008/155067, WO-2010/000666 and WO-2010/052231, and in the preferred embodiments having the combined addition of Mg and a wetting element, preferably Bi, to the Al-Si filler alloy.

**[0011]** There is a need for further improved brazing processes and brazing sheet materials or extruded materials for use therein.

## DESCRIPTION OF THE INVENTION

**[0012]** It is an object of the invention to provide an aluminium alloy brazing sheet material and/or extruded material

that can be applied in a controlled atmosphere brazing process without applying a brazing flux.

**[0013]** This and other objects and further advantages are met or exceeded by the present invention and providing an aluminium alloy sheet product and/or extruded product for fluxless brazing, comprising of an aluminium alloy core having on at least one face an aluminium filler clad layer containing 4% to 15% of Si, the filler clad layer having an inner-surface and an outer-surface, the inner-surface is facing the aluminium alloy core and the outer-surface is facing a coating layer of 2 to 45 mg/sq.m (mg/m<sup>2</sup>) of Bi or of a Bi-based alloy, wherein the coating layer of Bi or Bi-based alloy is devoid of any further layer comprising one or more metals selected from the group comprising nickel, cobalt, palladium and iron.

#### DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

**[0014]** For the purposes of this invention, and as used hereinafter, Bi-based alloy means an alloy having Bi as its main constituent in an amount of at least 70% Bi, and preferably at least 90% Bi.

**[0015]** Furthermore, for the purposes of this invention, and as used hereinafter, the term "controlled atmosphere brazing" or "CAB" refers to a brazing process which utilizes an inert atmosphere, for example, nitrogen, argon or helium in the brazing of alloy articles, and is distinct from vacuum brazing in particular in that with CAB the brazing atmosphere in the furnace during the brazing operation is at about regular atmospheric pressure, although a slight under-pressure (for example working at a pressure of 0.1 bar or more) or having a slight over-pressure can be used to facilitate the control of the inert atmosphere and to prevent an influx of oxygen containing gas into the brazing furnace. "Core" means an aluminium alloy, e.g. a sheet or an extrusion, which is the structural support for the aluminium alloy that is used as the filler. "Filler" means an aluminium-silicon alloy which is used to braze the core or other aluminium articles. "Cladding" is used to describe the use of the filler without the applied Bi or Bi-based alloy layer when it is overlaid on one or both surfaces of the core, optionally with the application of an intermediate layer between the core and the cladding to act as a diffusion barrier or to improve on the corrosion resistance of the product after brazing. Thereafter, the clad core is called a composite or a brazing sheet. "Fillet" means a concave junction between two surfaces.

**[0016]** In accordance with the invention the brazing sheet and/or extruded material can be applied in a CAB process without applying a brazing flux. It provides for excellent and smooth filler formation during CAB brazing. Furthermore, there is no need to add the Bi to the cladding itself, which overcome the problem of edge-cracking during hot rolling when producing the liner plate when substantial amounts of Bi are present in the Al-Si alloy.

**[0017]** In an embodiment the applied coating layer of Bi or of a Bi-based alloy is at most 30 mg/sq.m.

**[0018]** In an embodiment the applied coating layer of Bi or of a Bi-based alloy is at least 4 mg/sq.m.

**[0019]** In an embodiment the filler clad layer has a composition comprising, in wt.%:

Si about 4% to 15%, preferably about 7% to 13%,

Mg 0 to 1 %, preferably 0 to about 0.4%,

Fe 0 to about 1%,

Cu 0 to about 2%,

Mn 0 to about 1.5%,

Zn 0 to about 1.5%, preferably 0 to 0.2%,

Ti 0 to about 0.2%,

Sr 0 to about 0.05%,

the balance aluminium and incidental impurities.

Typical examples of the filler clad layer alloy encompass the known cladding alloys AA4045 and AA4343.

**[0020]** The Si content in the filler alloy should be in the range of about 3% to about 15%, and preferably in the range of about 6% to about 13%. For example, the Si content is about 10% or about 12.5%.

**[0021]** The Mg content in the filler alloy can be up to 1 %, and is preferably up to about 0.4%.

**[0022]** The amount of Fe present in the filler alloy depends primarily on the origin of the alloy material and can be present up to about 1%, and preferably is not more than about 0.6%.

**[0023]** The optional addition of Cu and/or Zn results in lowering the solidus temperature of the filler alloy, whereby the solidus temperature is the onset of melting of the filler alloy.

**[0024]** As grain refiner element Ti can be present in the brazing material in a range of up to about 0.2%, preferably up to 0.15%.

**[0025]** Mn can be present in the filler alloy in a range of 0 to about 1.5%. When present as impurity it can be tolerated to 0.3%. However, it may also be purposively added in a range of 0.3% to 1.5%. A more preferred upper-limit for the Mn addition is 1.0%.

**[0026]** The balance is made by unavoidable or incidental impurities, typically each 0.05% maximum, and the total 0.15% maximum, and aluminium.

**[0027]** In an embodiment of the filler alloy it may further comprise Sr in a range of 0 to 0.05% to modify the silicon in

the filler alloy and to improve the flowability of the molten filler in the brazing operation.

**[0028]** In a preferred embodiment the filler clad layer is free of each of the elements Na, Li, K, and Ca to avoid any interference with the Bi during the brazing operation. With "free" is meant that no purposeful addition of Na, Li, K, and Ca was made to the chemical composition but that due to impurities and/or leaking from contact with manufacturing equipment, trace quantities of Na, Li, K, and Ca may nevertheless find their way into the filler alloy product.

**[0029]** Furthermore, in a preferred embodiment the filler clad layer is free of each of the elements Bi, Pb, Y, and Sb. With "free" is meant that no purposeful addition of Bi, Pb, Y, and Sb was made to the chemical composition but that due to impurities and/or leaking from contact with manufacturing equipment, trace quantities of Bi, Pb, Y, and Sb may nevertheless find their way into the filler alloy product.

**[0030]** Various techniques may be applied for the application of the coating layer of Bi or Bi-based alloy, such as thermal spraying, chemical vapour deposition ("CVD") and physical vapour deposition ("PVD") and kinetic energy metallization ("KEM") or other techniques for depositing of metal or metal alloys from a gas or vapour phase may be used. PVD is understood to include sputtering, including magnetron sputtering, electron beam (EB) evaporation, and cathodic arc deposition.

**[0031]** However, on a preferred basis the coating layer is applied using plating or electroplating.

**[0032]** In a preferred embodiment of the brazing sheet and/or the extruded component, the 2 to 45 mg/sq.m coating layer of Bi or of a Bi-based alloy is devoid of any further layer comprising one or more metals selected from the group comprising nickel, cobalt, palladium and iron. It is an important feature of the present invention that such metallic layers, e.g., Ni-, Fe-, Pd-, Co-, or alloys thereof, such as for example nickel-bismuth, nickel-lead-nickel-cobalt, nickel-bismuth-cobalt, nickel-lead-cobalt, nickel-lead-bismuth, and nickel-lead-antimony alloys, are no longer required when the filler alloy of this invention is being used in the controlled atmosphere brazing operation. This leads to considerable costs saving when producing the brazing sheet product. Furthermore, the use of for example a Ni-layer results in a reduced corrosion resistance of the product in the post-braze condition, which disadvantage does not occur in the present invention.

**[0033]** In the brazing sheet material and/or extruded material according to the invention the core alloy layer is made for an aluminium alloy. The aluminium core alloys are preferably from the 1000-, 2000-, 3000-, 5000-, 6000-, 7000-, or 8000-series aluminium alloys, for example an AA1230, AA3003, AA3103, AA3004, AA3005, AA5052, AA6060, AA6063, AA8006 or AA8011-type aluminium alloy.

**[0034]** The brazing sheet material used according to the invention has a typical thickness at final gauge in the range of about 0.02 mm to 4 mm. The brazing sheet material is preferably up to about 350 microns thick at final gauge, and more preferably in a range of about 70 microns to 260 microns thick.

**[0035]** The brazing clad material layer has preferably a thickness which is about 2% to 15% of the entire thickness of aluminium alloy brazing sheet material, e.g. 6% or 8%.

**[0036]** The wall thickness of the extruded material is dependent on the particular shape, the circumscribed circle as well as the aluminium alloy. For thin extruded material the wall thickness is preferably less than 3 mm.

**[0037]** The brazing sheet material and/or extruded material applied for the composite metal structure according to this invention can be manufactured via various techniques. For the brazing sheet material roll bonding is well known in the art and which is preferred. Alternatively the Al-Si brazing alloy layer can be applied onto the core alloy by means of thermal spraying techniques. Or alternatively the core alloy and the Al-Si alloy filler clad material can be manufactured by means of casting techniques, for example as disclosed in each of the international patent documents WO-2004/112992, WO-2010/000553, and WO-2010/114740.

**[0038]** Another aspect of the invention relates to a method of manufacturing an article, such as a heat exchanger, joined by brazing or an assembly of brazed components, comprising the steps of:

- (a) providing the components of which at least one is made from an aluminium alloy brazing sheet and/or extruded component described in this description as part of the invention;
- (b) assembling the components, such as corrugated fin stock material and other components such as tubes, into an assembly;
- (c) brazing the assembly without applying a brazing flux on the assembly of components, and brazing the whole assembly in a controlled inert gas atmosphere at a brazing temperature, typically at a temperature in a range of about 540°C to 615°C, e.g. about 600°C or about 590°C, for a period long enough for melting and spreading of a brazing material or filler joining the various components, e.g. a dwell time of 1 to 5 minutes, typically at around 2 or 3 minutes; and whereby typically the oxygen content in the brazing atmosphere should be as low as reasonable possible, and is preferably below about 200 ppm, and more preferably below about 100 ppm, for example at 15 ppm or less;
- (d) cooling of the brazed assembly, typically to below about 100°C, e.g. to ambient temperature using for example blown air.

**[0039]** The following example is provided to further illustrate the objectives and advantages of this invention. It is not intended to limit the scope of this invention in any manner, however.

#### EXAMPLE

**[0040]** Commercial available brazing sheet having an AA3003-series core alloy and on both sides provided with an AA4045 clad layer (each 10% thickness) have been treated in accordance with this invention by applying a Bi-coating onto the clad layer. All samples had been cleaned, etched and desmuted prior to the application of the Bi-coating.

**[0041]** In one comparative example a Bi-coating layer was applied via a zincate immersion treatment. The zincate solution comprised of 40 g/mol sodium hydroxide, 81 g/mol zinc oxide, 282 g/mol potassium sodium tartrate tetrahydrate ("Rochelle salt"), 85 g/mol sodium nitrate, and 466 g/mol bismuth oxide. The material was immersed for 12 s in the zincate solution at room temperature.

**[0042]** In another series of experiments a Bi-layer of varying thickness had been applied via electroplating by varying the current density and the plating time, and which parameters are summarized in Table 1. The Bi-plating bath comprised of ammonium sulphate, trisodium citrate dehydrate, sodium gluconate, and a bismuth concentration based on bismuth oxide ( $\text{Bi}_2\text{O}_3$ ), and had a pH 11.6 at 50°C.

**[0043]** The composition of the resultant plated layer was measured using ICP and is given in Table 1. ICP stands for Induced Coupled Plasma.

**[0044]** Small coupons of 25 mm x 25 mm were cut from the Bi-plated sheets. A small strip of an AA3003 alloy measuring 30 mm x 7 mm x 1 mm was bent in the centre to an angle of 45° and laid on the coupons. The strip-on-the-coupon samples were heated using a laboratory scale quartz furnace under flowing nitrogen of atmospheric pressure and having an oxygen content of less than 20 ppm, with heating from room temperature to 590°C, dwell time at 590°C for 1 minute, cooling from 590°C to room temperature. The CAB brazing process was judged on possible formation of wrinkles, capillary depression and fillet formation. An overall assessment was given as poor brazeability, fair brazeability, good brazeability, or excellent brazeability. Excellent means both legs of the reversed angle are fully brazed to the brazing substrate. The results obtained are summarised in Table 1.

**Table 1.** Results of brazing tests and ICP analysis.

| application technique       | current density [ $\text{A}/\text{dm}^2$ ] | time [s] | Zn [ $\text{mg}/\text{m}^2$ ] | Bi [ $\text{mg}/\text{m}^2$ ] | brazing result |
|-----------------------------|--------------------------------------------|----------|-------------------------------|-------------------------------|----------------|
| zincate immersion treatment | 0                                          | 12.0     | 250                           | 50                            | poor           |
| electroplating              | 1                                          | 1.0      | -                             | 24                            | excellent      |
| electroplating              | 1                                          | 0.5      | -                             | 21                            | excellent      |
| electroplating              | 1                                          | 0.2      | -                             | 11                            | excellent      |
| electroplating              | 0.5                                        | 1.0      | -                             | 19                            | excellent      |
| electroplating              | 0.5                                        | 0.5      | -                             | 14                            | excellent      |
| electroplating              | 0.5                                        | 0.2      | -                             | 9                             | excellent      |

**[0045]** All samples passed the CAB brazing test except for the sample that is prepared via the zincate immersion treatment. Possibly, zinc is oxidised to some extent, thereby deteriorating the brazing properties. All bismuth electroplated samples showed excellent brazing behaviour in a CAB environment. All bismuth electroplated samples showed excellent brazing behaviour in a CAB environment without the use of any braze-promoting elements or layers based on nickel, cobalt, palladium, and iron, or alloys thereof. Also the requirement for the addition of Mg to the filler alloy is not required in order to achieve excellent brazing behaviour in a CAB environment.

#### Claims

1. Aluminium alloy sheet product or extruded product for fluxless brazing, comprising an aluminium alloy core having on at least one face an aluminium filler clad layer containing 4% to 15% of Si, the filler clad layer having an inner-surface and an outer-surface, wherein the inner-surface is facing the aluminium alloy core and the outer-surface is facing a coating layer of 2 to 45 mg/sq.m of Bi or of a Bi-based alloy, wherein the coating layer of Bi or of a Bi-based alloy is devoid of any further layer comprising one or more metals selected from the group comprising nickel, cobalt, palladium, and iron.

2. Aluminium alloy sheet product or extruded product according to claim 1, wherein the coating layer is at most 30 mg/sq.m.
3. Aluminium alloy sheet product or extruded product according to claim 1 or 2, wherein the coating layer is at least 4 mg/sq.m.
4. Aluminium alloy sheet product or extruded product according to any one of claims 1 to 3, wherein the coating layer of Bi or of a Bi-based alloy is a plated layer.
5. Aluminium alloy sheet product or extruded product according to any one of claims 1 to 4, wherein the coating layer of Bi or of a Bi-based alloy is applied by a technique selected from the group of thermal spraying, chemical vapour deposition, physical vapour deposition, and kinetic energy metallization.
6. Aluminium alloy sheet product or extruded product according to claim 5, wherein the physical vapour deposition includes sputtering, electron beam evaporation and cathodic arc deposition.
7. Aluminium alloy sheet product or extruded product according to any one of claims 1 to 4, wherein the coating layer of Bi or of a Bi-based alloy is applied using plating or electroplating.
8. An aluminium sheet product or extruded product according to any one of claims 1 to 7, wherein the filler clad layer has a composition, in wt.%, of:

|    |             |
|----|-------------|
| Si | 4% to 15%,  |
| Mg | 0 to 1%,    |
| Fe | 0 to 1%,    |
| Cu | 0 to 2%,    |
| Mn | 0 to 1.5%,  |
| Zn | 0 to 1.5%,  |
| Ti | 0 to 0.2%,  |
| Sr | 0 to 0.05%, |

the balance aluminium and incidental impurities.

9. A method of manufacturing an article joined by brazing or an assembly of brazed components, comprising the steps of:
  - (a) providing components of which at least one is made from a brazing sheet material and/or extruded material according to any one of claims 1 to 8,
  - (b) assembling the components into an assembly,
  - (c) brazing the assembly without applying brazing flux on the assembly of components and brazing the whole assembly in an inert controlled gas atmosphere at a brazing temperature to form a brazed assembly, and
  - (d) cooling of the brazed assembly.

#### Patentansprüche

1. Blechprodukt aus Aluminiumlegierung oder extrudiertes Produkt für flussmittelfreies Hartlöten, das einen Aluminiumlegierungskern aufweist, der auf mindestens einer Seite eine Lot-Plattierschicht hat, die 4% bis 15% Si enthält, wobei die Lot-Plattierschicht eine Innenfläche und eine Außenfläche hat, wobei die Innenfläche dem Aluminiumlegierungskern und die Außenfläche einer Beschichtungsschicht aus 2 bis 45 mg/m<sup>2</sup> Bi oder aus einer Legierung auf Bi-Basis gegenüberliegt, wobei die Beschichtungsschicht aus Bi oder aus einer Legierung auf Bi-Basis keine weitere Schicht aufweist, die eines oder mehrere Metalle enthält, die aus der Nickel, Kobalt, Palladium und Eisen enthaltenden Gruppe ausgewählt werden.
2. Blechprodukt aus Aluminiumlegierung oder extrudiertes Produkt nach Anspruch 1, wobei die Beschichtungsschicht höchstens 30 mg/m<sup>2</sup> beträgt.

3. Blechprodukt aus Aluminiumlegierung oder extrudiertes Produkt nach Anspruch 1 oder 2, wobei die Beschichtungsschicht mindestens 4 mg/m<sup>2</sup> beträgt.
4. Blechprodukt aus Aluminiumlegierung oder extrudiertes Produkt nach einem der Ansprüche 1 bis 3, wobei die Beschichtungsschicht aus Bi oder aus einer Legierung auf Bi-Basis eine aufgetragene Schicht ist.
5. Blechprodukt aus Aluminiumlegierung oder extrudiertes Produkt nach einem der Ansprüche 1 bis 4, wobei die Beschichtungsschicht aus Bi oder aus einer Legierung auf Bi-Basis durch eine Technik aufgebracht wird, die aus der Gruppe des thermischen Spritzens, der chemischen Dampfabcheidung, der physikalischen Dampfabcheidung und der Metallisierung durch kinetische Energie ausgewählt wird.
6. Blechprodukt aus Aluminiumlegierung oder extrudiertes Produkt nach Anspruch 5, wobei die physikalische Dampfabcheidung Zerstäubung, Elektronenstrahlverdampfung und Kathodenzerstäubung durch Bogenentladung umfasst.
7. Blechprodukt aus Aluminiumlegierung oder extrudiertes Produkt nach einem der Ansprüche 1 bis 4, wobei die Beschichtungsschicht aus Bi oder aus einer Legierung auf Bi-Basis durch Plattieren oder Galvanisierung aufgebracht wird.
8. Blechprodukt aus Aluminiumlegierung oder extrudiertes Produkt nach einem der Ansprüche 1 bis 7, wobei die Lot-Plattierschicht eine Zusammensetzung in Gew.-% hat von:

|    |              |
|----|--------------|
| Si | 4% bis 15%,  |
| Mg | 0 bis 1%,    |
| Fe | 0 bis 1 %,   |
| Cu | 0 bis 2%,    |
| Mn | 0 bis 1,5%,  |
| Zn | 0 bis 1,5%,  |
| Ti | 0 bis 0,2%,  |
| Sr | 0 bis 0,05%, |

der Rest Aluminium und zufällige Verunreinigungen.

9. Verfahren zur Herstellung eines durch Hartlöten zusammengefügt Artikels oder einer Montageeinheit von hartgelöteten Bauteilen, das die folgenden Schritte aufweist:
  - (a) Bereitstellen von Bauteilen, von denen mindestens eines aus einem Hartlötblechmaterial und/oder einem extrudierten Material nach einem der Ansprüche 1 bis 8 hergestellt ist,
  - (b) Montieren der Bauteile in eine Montageeinheit,
  - (c) Hartlöten der Montageeinheit ohne Auftragen von Hartlötflusmittel auf die Montageeinheit von Bauteilen und Hartlöten der ganzen Montageeinheit unter kontrollierter Inertgasatmosphäre bei einer Hartlöttemperatur, um eine hartgelötete Montageeinheit zu formen, und
  - (d) Kühlen der hartgelöteten Montageeinheit.

## Revendications

1. Produit en tôle ou produit extrudé en alliage d'aluminium destiné au brasage sans flux, comprenant un coeur d'alliage d'aluminium ayant sur au moins une face une couche de parement de charge en aluminium contenant 4 % à 15 % de Si, la couche de parement de charge ayant une surface intérieure et une surface extérieure, telles que la surface intérieure est en face du coeur en alliage d'aluminium et que la surface extérieure est en face d'une couche de revêtement de 2 à 45 mg/m<sup>2</sup> de Bi ou d'un alliage à base de Bi, dans lequel la couche de revêtement de Bi ou d'un alliage à base de Bi est dépourvue d'une quelconque autre couche comprenant un ou plusieurs métaux choisis parmi le groupe comprenant nickel, cobalt, palladium et fer.
2. Produit en tôle ou produit extrudé en alliage d'aluminium selon la revendication 1, dans lequel la couche de revêtement



est au maximum de 30 mg/m<sup>2</sup>.

3. Produit en tôle ou produit extrudé en alliage d'aluminium selon la revendication 1 ou 2, dans lequel la couche de revêtement est d'au moins 4 mg/m<sup>2</sup>.

4. Produit en tôle ou produit extrudé en alliage d'aluminium selon l'une quelconque des revendications 1 à 3, dans lequel la couche de revêtement de Bi ou d'un alliage à base de Bi est une couche plaquée.

5. Produit en tôle ou produit extrudé en alliage d'aluminium selon l'une quelconque des revendications 1 à 4, dans lequel la couche de revêtement de Bi ou d'un alliage à base de Bi est appliquée par une technique choisie parmi le groupe comprenant la pulvérisation thermique, la déposition chimique en phase vapeur, la déposition physique en phase vapeur, et la métallisation par énergie cinétique.

6. Produit en tôle ou produit extrudé selon la revendication 5, dans lequel la déposition physique en phase vapeur inclut la pulvérisation cathodique, l'évaporation par faisceaux d'électrons et la déposition par arc cathodique.

7. Produit en tôle ou produit extrudé selon l'une quelconque des revendications 1 à 4, dans lequel la couche de revêtement de Bi ou d'un alliage à base de Bi est appliquée en utilisant le placage ou l'électro-placage.

8. Produit en tôle ou produit extrudé en aluminium selon l'une quelconque des revendications 1 à 7, dans lequel la couche de parement de charge a une composition, en pourcentage en poids, de

|    |            |
|----|------------|
| Si | 4 % à 15 % |
| Mg | 0 à 1 %,   |
| Fe | 0 à 1 %,   |
| Cu | 0 à 2 %,   |
| Mn | 0 à 1,5 %, |
| Zn | 0 à 1,5 %, |
| Ti | 0 à 0,2 %, |
| Sr | 0 à 0,05 % |

le reste étant de l'aluminium et des impuretés inévitables.

9. Procédé de fabrication d'un article uni par brasage, ou d'un ensemble de composants brasé, comprenant les étapes consistant à :

- (a) fournir des composants dont au moins un est réalisé en matériau en tôle de brasage et/ou en matériau extrudé selon l'une quelconque des revendications 1 à 8,
- (b) assembler les composants pour donner un assemblage,
- (c) braser l'ensemble sans appliquer de flux de brasage sur l'ensemble de composants, et braser l'ensemble entier dans une atmosphère de gaz inerte contrôlée à une température de brasage pour former un ensemble brasé, et
- (d) faire refroidir l'ensemble brasé.

**REFERENCES CITED IN THE DESCRIPTION**

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

**Patent documents cited in the description**

- EP 1430988 A [0008]
- EP 1306207 B1 [0009]
- EP 1306207 A [0010]
- WO 2008155067 A [0010]
- WO 2010000666 A [0010]
- WO 2010052231 A [0010]
- WO 2004112992 A [0037]
- WO 2010000553 A [0037]
- WO 2010114740 A [0037]

9558R

EP 2 776 208 B1

Alumínium ötvözet lemeztermék vagy extrudált termék folyatószer nélküli  
keményforrasztáshoz

Szabadalmi igénypontok

1. Alumínium ötvözet lemeztermék vagy extrudált termék folyatószer nélküli keményforrasztáshoz, amely legalább egyik felületén 4 %-tól 15 %-ig terjedhető mennyiségben Si-t tartalmazó, plattírozással felvitt alumínium töltő réteggel van ellátva, a plattírozással felvitt töltő réteg egy belső és egy külső felülettel rendelkezik, a belső felület az alumínium ötvözet mag felé néz, míg a külső felület egy 2 mg/négyzetmétertől 45 mg/négyzetméterig terjedhető mennyiségben Bi-t vagy Bi-bázisú ötvözetet tartalmazó bevonatréteg felé néz, ahol a Bi-t vagy Bi-bázisú ötvözetet tartalmazó bevonatréteg mentes minden további, a nikkelből, kobaltból, palládiumból és vasból álló csoportból kiválasztott egy vagy több fémeket tartalmazó rétegtől.
2. Az 1. igénypont szerinti alumínium ötvözet anyagú lemeztermék vagy extrudált termék, amelyben a bevonatréteg legfeljebb 30 mg/m<sup>2</sup>-es.
3. Az 1. vagy 2. igénypont szerinti alumínium ötvözet anyagú lemeztermék vagy extrudált termék, amelyben a bevonatréteg legalább 4 mg/m<sup>2</sup>-es.
4. Az 1-3. igénypontok bármelyike szerinti alumínium ötvözet anyagú lemeztermék vagy extrudált termék, amelyben a bevonatréteg Bi vagy Bi-bázisú ötvözet anyagú, plattírozással felvitt réteg.
5. Az 1-4. igénypontok bármelyike szerinti alumínium ötvözet anyagú lemeztermék vagy extrudált termék, amelyben a Bi vagy Bi-bázisú ötvözet anyagú bevonatréteg a termikus szórásból, kémiai gőzleválasztásból, fizikális gőzleválasztásból és kinetikus

energiaközléssel végzett fémezésből álló csoportból kiválasztott technológiai eljárással van felhordva.

6. Az 5. igénypont szerinti alumínium ötvözet anyagú lemeztermék vagy extrudált termék, ahol a fizikális gőzleválasztás tartalmazza a porlasztás, az elektronsugaras gőzölés és a katódíves leválasztás eljárásokat.

7. Az 1-4. igénypontok bármelyike szerinti alumínium ötvözet anyagú lemeztermék vagy extrudált termék, amelyben a Bi vagy Bi-bázisú ötvözet anyagú bevonatréteg plattírozással vagy elektroplattírozással van felvive.

8. Az 1-4. igénypontok bármelyike szerinti alumínium ötvözet anyagú lemeztermék vagy extrudált termék, amelyben a plattírozással felvitt töltőfém réteg tömegszázalékban kifejezett összetétele

4 %-tól 15 %-ig Si

0-tól 1 %-ig Mg

0-tól 1 %-ig Fe

0-tól 2 %-ig Cu

0-tól 1,5 %-ig Mn

0-tól 1,5 %-ig Zn

0-tól 0,2 %-ig Ti

0-tól 0,05 %-ig Sr

és a fennmaradó részben alumínium és véletlen szennyeződések.

9. Eljárás keményforrasztásos egyesítésű termék vagy keményforrasztott elemekből álló szerelési egység előállítására, amely eljárás az alábbi lépéseket tartalmazza:

- a) szerkezeti elemek legalább egyike az 1-8. igénypontok bármelyike szerinti keményforrasztó lemez anyagból vagy extrudált anyagból áll;
- b) a szerkezeti elemekből szerelési egységet képzünk;
- c) a szerkezeti elemekből képzett szerelési egységen keményforrasztó-folyatószer használata nélküli keményforrasztással keményforrasztott szerelési egységet állítunk

elő a komplett szerelési egység inert kontrollált gázatmoszférában, keményforrasztási hőmérsékleten való keményforrasztásával; és  
d) a keményforrasztott szerelési egységet lehűtjük.