

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 December 2006 (28.12.2006)

PCT

(10) International Publication Number
WO 2006/136594 A1

(51) International Patent Classification:
C10M 169/04 (2006.01) C10M 171/02 (2006.01)

(21) International Application Number:
PCT/EP2006/063439

(22) International Filing Date: 22 June 2006 (22.06.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
05013534.2 23 June 2005 (23.06.2005) EP

(71) Applicant (for all designated States except US): SHELL
INTERNATIONALE RESEARCH MAATSCHAPPIJ
B.V. [NL/NL]; Carel Van Bylandtlaan 30, NL-2596 HR
The Hague (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): HILKER, An-
dree [DE/DE]; Hohe-schaar Strasse 36, D-21107
Hamburg (DE). NULL, Volker Klaus [DE/DE];
Hohe-schaar-strasse 36, D-21107 Hamburg (DE).

(74) Agent: ZEESTRATEN, Albertus Wilhelmus J; C30, Po
Box 384, NL-2501 CJ The Hague (NL).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP,
KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT,
LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA,
NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC,
SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ,
UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:


— as to applicant's entitlement to apply for and be granted a
patent (Rule 4.17(ii))

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: ELECTRICAL OIL FORMULATION



(57) Abstract: Electrical oil formulation comprising a base oil component and an additive, wherein (i) at least 80 wt% of the base oil component is a paraffin base oil having a paraffin content of greater than 80 wt% paraffins and a saturates content of greater than 98 wt% and comprising a series of iso-paraffins having n, n+1, n+2, n+3 and n+4 carbon atoms and wherein n is between 20 and 35; and (ii) an anti-oxidant additive; wherein the base oil component has a flash point of at least 170 °C, as determined by ISO 2592.

WO 2006/136594 A1

ELECTRICAL OIL FORMULATION

Field of invention

The invention is related to an electrical oil formulation comprising a base oil and an additive.

Background of the invention

5 US-A-6790386 describes a dielectric fluid comprising an iso-paraffin base oil and additives. The iso-paraffin base oil is prepared by hydrotreating, hydroisomerisation and hydrogenation of a paraffinic vacuum feedstock.

10 US-A-5912212 describes oxidative stable oil lubricating formulations consisting of a hydrocracked paraffinic mineral base oil, 3-methyl-5-tert-butyl-4-hydroxy propionic acid ester, dioctylaminomethyltolyl-triazole and dilaurylthiodipropionate. The oil had a high oxidative stability.

15 WO-A-02070629 describes a process to make iso-paraffinic base oils from a wax as made in a Fischer-Tropsch process. According to this publication base oils having a kinematic viscosity at 100 °C of between 2 and 9 cSt can be used as base oil in formulations such as
20 electrical oils or transformer oils.

25 There is a desire to formulate electrical oils using a base oil having the properties of the Fischer-Tropsch derived base oil as described in WO-A-02070629. The main reasons are the excellent low-temperature properties of said base oils in combination with the relatively simple process to make said base oils as compared to similar oils prepared from mineral crude sources.

Electrical oil formulations require certain properties in order to be applicable for use. Typical requirements are that sludge formation should be low, oxidation stability should be high, cold flow properties should be adequate for its intended use, flash point should be adequate for its intended use and the dielectric dissipation factor should remain low, even after prolonged testing at elevated temperature. In particular for applications that require high performance at elevated temperatures and wherein elevated peak temperature in the electrical oil formulation are occurring, a very high flash point is required. At the same time, the formulation should still have good low temperature performance.

Applicants further found that formulating an electrical oil formulation starting from such a synthetic iso-paraffin base oil is not straightforward as compared to when starting from a mineral based paraffinic base oils. The object of the present invention is to provide an electrical oil formulation, which has adequate properties for its use. This object is achieved in the following oil formulation.

Summary of the invention

Electrical oil formulation comprising a base oil component and an additive, wherein

- (i) at least 80 wt% of the base oil component is a paraffin base oil having a paraffin content of greater than 80 wt% paraffins and a saturates content of greater than 98 wt% and comprising a series of iso-paraffins having n , $n+1$, $n+2$, $n+3$ and $n+4$ carbon atoms and wherein n is between 20 and 35; and
- (ii) an anti-oxidant additive;

wherein the base oil component has a flash point of at least 170 °C, as determined by ISO 2592

Brief description of the drawings

5 Figure 1 and 2 represent the carbon distribution of two Fischer-Tropsch derived base oils as used in the examples.

Detailed description of the invention

10 The base oil component is a paraffin base oil having a paraffin content of greater than 80 wt% paraffins and a saturates content of greater than 98 wt% and comprising a series of iso-paraffins having n, n+1, n+2, n+3 and n+4 carbon atoms and wherein n is between 20 and 35. Preferably the saturates content of the base oil as measured by IP386 is preferably greater than 98 wt%,
15 more preferably greater than 99 wt% and even more preferably greater than 99.5 wt%. The base oil furthermore has preferably a content of naphthenic compounds of between 0 to 20%, preferably of from 1 and 20 wt%. It has been found that these base oils have
20 a good additive response to the additives as listed above when aiming to improve for example oxidation stability. The base oil preferably has a kinematic viscosity at 40 °C of between 1 and 200 mm²/sec, more preferably between 1 and 50 mm²/sec and even more preferably between 1 and 15 mm²/sec. The base oil may
25 suitably have a kinematic viscosity at 100 °C of between 2 and 50 mm²/sec, more preferably between 2 and 25 mm²/sec, most preferably between 2 and 10 mm²/sec. More preferably, if the oil formulation is used as a
30 transformer oil, the base oil will preferably have a kinematic viscosity at 40 °C of between 5 and 15 mm²/sec. If the electrical oil is used as a low

temperature switch gear oil the base oil viscosity at 40 °C is preferably between 1 and 15 and more preferably between 1 and 4 mm²/sec. The pour point of the base oil is preferably below -30 °C.

5 The flash point of the base oil as measured by ASTM D92 is equal or greater than 170 °C, preferably greater than 175 °C, or more preferably even greater than 180 °C. The flash point of the base oil will depend on the application of the oil. Applicants have found that
10 the flash points of the base oils as claimed are advantageously high as compared to mineral oil derived base oils at a given viscosity. This is surprising in view of the fact that presence of isoparaffinic components should increase volatility and hence the
15 reduce the flash point. Especially base oils having a ν_{k100} of greater than 6 mm²/sec having a flash point of greater than 250 °C can be advantageously used in fire resistant electrical oil formulations. The high flash point at comparatively low viscosity of the base oil
20 component according to the present invention permits to formulate electrical oil formulations that have both low temperature performance, as well as an improved oxidation resistance. This is particularly important in applications wherein a high overall temperature exposure
25 takes place, and or wherein high peak temperatures or so-called hotspots occur in the electrical oil, and/or wherein the increase in temperature cannot be easily deferred by the electrical oil due to restrictions in size or heat exchange capacity of a device containing
30 the electrical oil formulation. Examples of such devices or applications are small high capacity transformers, or safety switches. The content of naphthenic compounds and the presence of such a

continuous series of iso-paraffins may be measured by Field desorption/Field Ionisation (FD/FI) technique. In this technique the oil sample is first separated into a polar (aromatic) phase and a non-polar (saturates) phase by making use of a high performance liquid chromatography (HPLC) method IP368/01, wherein as mobile phase pentane is used instead of hexane as the method states.

The saturates and aromatic fractions are then analyzed using a Finnigan MAT90 mass spectrometer equipped with a Field desorption/Field Ionisation (FD/FI) interface, wherein FI (a "soft" ionisation technique) is used for the determination of hydrocarbon types in terms of carbon number and hydrogen deficiency.

The type classification of compounds in mass spectrometry is determined by the characteristic ions formed and is normally classified by "z number". This is given by the general formula for all hydrocarbon species: C_nH_{2n+z} . Because the saturates phase is analysed separately from the aromatic phase it is possible to determine the content of the different iso-paraffins having the same stoichiometry or n-number. The results of the mass spectrometer are processed using commercial software (poly 32; available from Sierra Analytics LLC, 3453 Drago Park Drive, Modesto, California GA95350 USA) to determine the relative proportions of each hydrocarbon type.

The base oil having the continuous iso-paraffinic series as described above are preferably obtained by hydroisomerisation of a paraffinic wax, preferably followed by some type of dewaxing, such as solvent or catalytic dewaxing. The paraffinic wax may be a slack wax. More preferably the paraffinic wax is a Fischer-

Tropsch derived wax, because of its purity and high paraffinic content, as well as the fact that such waxes result in a product containing a continuous series of iso-paraffins having n, n+1, n+2, n+3 and n+4 carbon atoms in the desired molecular weight range. The base oils as derived from a Fischer-Tropsch wax as here described will be referred to in this description as Fischer-Tropsch derived base oils.

Examples of Fischer-Tropsch processes which for example can be used to prepare the above-described Fischer-Tropsch derived base oil are the so-called commercial Slurry Phase Distillate technology of Sasol, the Shell Middle Distillate Synthesis Process and the "AGC-21" Exxon Mobil process. These and other processes are for example described in more detail in EP-A-776959, EP-A-668342, US-A-4943672, US-A-5059299, WO-A-9934917 and WO-A-9920720. Typically these Fischer-Tropsch synthesis products will comprise hydrocarbons having 1 to 100 and even more than 100 carbon atoms. This hydrocarbon product will comprise normal paraffins, iso-paraffins, oxygenated products and unsaturated products.

If base oils are one of the desired iso-paraffinic products it may be advantageous to use a relatively heavy Fischer-Tropsch derived feed. The relatively heavy Fischer-Tropsch derived feed has at least 30 wt%, preferably at least 50 wt%, and more preferably at least 55 wt% of compounds having at least 30 carbon atoms. Furthermore the weight ratio of compounds having at least 60 or more carbon atoms and compounds having at least 30 carbon atoms of the Fischer-Tropsch derived feed is preferably at least 0.2, more preferably at least 0.4 and most preferably at least 0.55. Preferably the Fischer-Tropsch derived feed comprises a C₂₀⁺

fraction having an ASF-alpha value (Anderson-Schulz-Flory chain growth factor) of at least 0.925, preferably at least 0.935, more preferably at least 0.945, even more preferably at least 0.955. Such a Fischer-Tropsch derived feed can be obtained by any process, which yields a relatively heavy Fischer-Tropsch product as described above. Not all Fischer-Tropsch processes yield such a heavy product. An example of a suitable Fischer-Tropsch process is described in WO-A-9934917.

The Fischer-Tropsch derived product will contain no or very little sulphur and nitrogen containing compounds. This is typical for a product derived from a Fischer-Tropsch reaction, which uses synthesis gas containing almost no impurities. Sulphur and nitrogen levels will generally be below the detection limits, which are currently 5 mg/kg for sulphur and 1 mg/kg for nitrogen respectively.

The process will generally comprise a Fischer-Tropsch synthesis, a hydroisomerisation step and an optional pour point reducing step, wherein said hydroisomerisation step and optional pour point reducing step are performed as:

(a) hydrocracking/hydroisomerising a Fischer-Tropsch product,

(b) separating the product of step (a) into at least one or more distillate fuel fractions and a base oil or base oil intermediate fraction.

If the viscosity and pour point of the base oil as obtained in step (b) is as desired no further processing is necessary and the oil can be used as the base oil according to the invention. If required, the pour point of the base oil intermediate fraction is suitably further reduced in a step (c) by means of solvent or preferably

catalytic dewaxing of the oil obtained in step (b) to obtain oil having the preferred low pour point. The desired viscosity of the base oil may be obtained by isolating by means of distillation from the intermediate base oil fraction or from the dewaxed oil the a suitable boiling range product corresponding with the desired viscosity. Distillation may be suitably a vacuum distillation step.

The hydroconversion/hydroisomerisation reaction of step (a) is preferably performed in the presence of hydrogen and a catalyst, which catalyst can be chosen from those known to one skilled in the art as being suitable for this reaction of which some will be described in more detail below. The catalyst may in principle be any catalyst known in the art to be suitable for isomerising paraffinic molecules. In general, suitable hydroconversion/hydroisomerisation catalysts are those comprising a hydrogenation component supported on a refractory oxide carrier, such as amorphous silica-alumina (ASA), alumina, fluorided alumina, molecular sieves (zeolites) or mixtures of two or more of these. One type of preferred catalysts to be applied in the hydroconversion/hydroisomerisation step in accordance with the present invention are hydroconversion/hydroisomerisation catalysts comprising platinum and/or palladium as the hydrogenation component. A very much preferred hydroconversion/hydroisomerisation catalyst comprises platinum and palladium supported on an amorphous silica-alumina (ASA) carrier. The platinum and/or palladium is suitably present in an amount of from 0.1 to 5.0% by weight, more suitably from 0.2 to 2.0% by weight, calculated as element and based on total weight of carrier. If both

present, the weight ratio of platinum to palladium may vary within wide limits, but suitably is in the range of from 0.05 to 10, more suitably 0.1 to 5. Examples of suitable noble metal on ASA catalysts are, for instance, disclosed in WO-A-9410264 and EP-A-0582347. Other suitable noble metal-based catalysts, such as platinum on a fluorided alumina carrier, are disclosed in e.g. US-A-5059299 and WO-A-9220759.

A second type of suitable hydroconversion/
hydroisomerisation catalysts are those comprising at least one Group VIB metal, preferably tungsten and/or molybdenum, and at least one non-noble Group VIII metal, preferably nickel and/or cobalt, as the hydrogenation component. Both metals may be present as oxides, sulphides or a combination thereof. The Group VIB metal is suitably present in an amount of from 1 to 35% by weight, more suitably from 5 to 30% by weight, calculated as element and based on total weight of the carrier. The non-noble Group VIII metal is suitably present in an amount of from 1 to 25 wt%, preferably 2 to 15 wt%, calculated as element and based on total weight of carrier. A hydroconversion catalyst of this type, which has been found particularly suitable, is a catalyst comprising nickel and tungsten supported on fluorided alumina.

The above non-noble metal-based catalysts are preferably used in their sulphided form. In order to maintain the sulphided form of the catalyst during use some sulphur needs to be present in the feed. Preferably at least 10 mg/kg and more preferably between 50 and 150 mg/kg of sulphur is present in the feed.

A preferred catalyst, which can be used in a non-sulphided form, comprises a non-noble Group VIII metal,

e.g., iron, nickel, in conjunction with a Group IB metal, e.g., copper, supported on an acidic support. Copper is preferably present to suppress hydrogenolysis of paraffins to methane. The catalyst has a pore volume preferably in the range of 0.35 to 1.10 ml/g as determined by water absorption, a surface area of preferably between 200-500 m²/g as determined by BET nitrogen adsorption, and a bulk density of between 0.4-1.0 g/ml. The catalyst support is preferably made of an amorphous silica-alumina wherein the alumina may be present within wide range of between 5 and 96 wt%, preferably between 20 and 85 wt%. The silica content as SiO₂ is preferably between 15 and 80 wt%. Also, the support may contain small amounts, e.g., 20-30 wt%, of a binder, e.g., alumina, silica, Group IVA metal oxides, and various types of clays, magnesia, etc., preferably alumina or silica.

The preparation of amorphous silica-alumina microspheres has been described in Ryland, Lloyd B., Tamele, M.W., and Wilson, J.N., *Cracking Catalysts, Catalysis: volume VII*, Ed. Paul H. Emmett, Reinhold Publishing Corporation, New York, 1960, pp. 5-9.

The catalyst is prepared by co-impregnating the metals from solutions onto the support, drying at 100-150 °C, and calcining in air at 200-550 °C. The Group VIII metal is present in amounts of about 15 wt% or less, preferably 1-12 wt%, while the Group IB metal is usually present in lesser amounts, e.g., 1:2 to about 1:20 weight ratio respecting the Group VIII metal.

A typical catalyst is shown below:

	Ni, wt%	2.5-3.5
	Cu, wt%	0.25-0.35
5	Al ₂ O ₃ -SiO ₂ wt%	65- 75
	Al ₂ O ₃ (binder) wt%	25-30
	Surface Area	290-325 m ² /g
	Pore Volume (Hg)	0.35-0.45 ml/g
	Bulk Density	0.58-0.68 g/ml

10 Another class of suitable hydroconversion/
hydroisomerisation catalysts are those based on
molecular sieve type materials, suitably comprising at
least one Group VIII metal component, preferably Pt
and/or Pd, as the hydrogenation component. Suitable
15 zeolitic and other aluminosilicate materials, then,
include Zeolite beta, Zeolite Y, Ultra Stable Y, ZSM-5,
ZSM-12, ZSM-22, ZSM-23, ZSM-48, MCM-68, ZSM-35, SSZ-32,
ferrierite, mordenite and silica-aluminophosphates, such
as SAPO-11 and SAPO-31. Examples of suitable
20 hydroisomerisation/hydroisomerisation catalysts are, for
instance, described in WO-A-9201657. Combinations of
these catalysts are also possible. Very suitable
hydroconversion/hydroisomerisation processes are those
involving a first step wherein a zeolite beta or ZSM-48
25 based catalyst is used and a second step wherein a
ZSM-5, ZSM-12, ZSM-22, ZSM-23, ZSM-48, MCM-68, ZSM-35,
SSZ-32, ferrierite, mordenite based catalyst is used. Of
the latter group ZSM-23, ZSM-22 and ZSM-48 are
preferred. Examples of such processes are described in
30 US-A-20040065581, which disclose a process comprising a
first step catalyst comprising platinum and zeolite beta

and a second step catalyst comprising platinum and ZSM-48.

Combinations wherein the Fischer-Tropsch product is first subjected to a first hydroisomerisation step using the amorphous catalyst comprising a silica-alumina carrier as described above followed by a second hydroisomerisation step using the catalyst comprising the molecular sieve has also been identified as a preferred process to prepare the base oil to be used in the present invention. More preferred the first and second hydroisomerisation steps are performed in series flow. Most preferred the two steps are performed in a single reactor comprising beds of the above amorphous and/or crystalline catalyst.

In step (a) the feed is contacted with hydrogen in the presence of the catalyst at elevated temperature and pressure. The temperatures typically will be in the range of from 175 to 380 °C, preferably higher than 250 °C and more preferably from 300 to 370 °C.

The pressure will typically be in the range of from 10 to 250 bar and preferably between 20 and 80 bar. Hydrogen may be supplied at a gas hourly space velocity of from 100 to 10000 Nl/l/hr, preferably from 500 to 5000 Nl/l/hr. The hydrocarbon feed may be provided at a weight hourly space velocity of from 0.1 to 5 kg/l/hr, preferably higher than 0.5 kg/l/hr and more preferably lower than 2 kg/l/hr. The ratio of hydrogen to hydrocarbon feed may range from 100 to 5000 Nl/kg and is preferably from 250 to 2500 Nl/kg.

The conversion in step (a) as defined as the weight percentage of the feed boiling above 370 °C which reacts per pass to a fraction boiling below 370 °C, is at least 20 wt%, preferably at least 25 wt%, but preferably not

more than 80 wt%, more preferably not more than 65 wt%.
The feed as used above in the definition is the total
hydrocarbon feed fed to step (a), thus also any optional
recycle of a high boiling fraction which may be obtained
5 in step (b).

In step (b) the product of step (a) is preferably
separated into one or more distillate fuels fractions
and a base oil or base oil precursor fraction having the
desired viscosity properties. If the pour point is not
10 in the desired range the pour point of the base oil is
further reduced by means of a dewaxing step (c),
preferably by catalytic dewaxing. In such an embodiment
it may be a further advantage to dewax a wider boiling
fraction of the product of step (a). From the resulting
15 dewaxed product the base oil and oils having a desired
viscosity can then be advantageously isolated by means
of distillation. Dewaxing is preferably performed by
catalytic dewaxing as for example described in
WO-A-02070629, which publication is hereby incorporated
20 by reference. The final boiling point of the feed to the
dewaxing step (c) may be the final boiling point of the
product of step (a) or lower if desired.

The additive component (ii) of the oil formulation
comprises an anti-oxidant additive. It has been found
25 that especially the combination of the above described
base oil and the anti-oxidant additive improves
significantly the total acidity values of the oil as
tested in the Oxidation test IEC 61125 C. The base oil
may be combined with the anti-oxidant as the only
30 additive or in combination with other additives as
described below. The anti-oxidant may be a so-called
hindered phenolic or amine antioxidant, for example
naphthols, sterically hindered monohydric, dihydric and

trihydric phenols, sterically hindered dinuclear, trinuclear and polynuclear phenols, alkylated or styrenated diphenylamines or ionol derived hindered phenols. Sterically hindered phenolic antioxidants of particular interest are selected from the group consisting of 2,6-di-tert-butylphenol (IRGANOX™ L 140, CIBA), di tert-butylated hydroxotoluene (BHT), methylene-4,4'-bis-(2,6-tert-butylphenol), 2,2'-methylene bis-(4,6-di-tert-butylphenol), 1,6-hexamethylene-bis-(3,5-di-tert-butyl-hydroxy-hydrocinnamate) (IRGANOX™ L109, CIBA), ((3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl)methyl)thio) acetic acid, C10-C14isoalkyl esters (IRGANOX™ L118, CIBA), 3,5-di-tert-butyl-4-hydroxyhydrocinnamic acid, C7-C9alkyl esters (IRGANOX™ L135, CIBA,) tetrakis-(3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionyl-oxy)methyl)methane (IRGANOX™ 1010, CIBA), thiodiethylene bis(3,5-di-tert-butyl-4-hydroxyhydrocinnamate (IRGANOX™ 1035, CIBA), octadecyl 3,5-di-tert-butyl-4-hydroxyhydrocinnamate (IRGANOX™ 1076, CIBA) and 2,5-di-tert-butylhydroquinone. These products are known and are commercially available. Of most particular interest is 3,5-di-tert-butyl-4-hydroxyhydrocinnamic acid-C7-C9-alkyl ester.

Examples of amine antioxidants are aromatic amine anti-oxidants for example N,N'-Di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethyl-pentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methyl-pentyl)-p-phenylene-diamine, N,N'-bis(1-methyl-heptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylene-diamine, N,N'-diphenyl-p-phenylenediamine, N,N'-di(naphthyl-2-)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-


phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N'-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluene-sulfoamido)diphenylamine, 5 N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxy-diphenylamine, N-phenyl-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, e.g. p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-10 butyrylaminophenol, 4-nonanoylaminophenol, 4-dodecanoylaminophenol, 4-octadecanoylaminophenol, di(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-15 diaminodiphenylmethane, 1,2-di(phenylamino)ethane, 1,2-di[(2-methylphenyl)amino]ethane, 1,3-di(phenylamino)propane, (o-tolyl)biguanide, di[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, mixture of mono- and dialkylated tert-20 butyl-/tert-octyldiphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, N-allylphenothiazine, tert-octylated phenothiazine, 3,7-di-tert-octylphenothiazine. Also possible amine antioxidants are those according to formula VIII and IX 25 of EP-A-1054052, which compounds are also described in US-A-4,824,601, which publications are hereby incorporated by reference.

The content of the anti oxidant additive is preferably less than 2 wt% and more preferably less than 30 1 wt%. The content is preferably less than 0.6 wt% in certain applications, such as when the oil formulation is used as an electrical oil. The content of antioxidant is preferably greater than 10 mg/kg. If the anti-oxidant


is present as the only additive or at least in the absence of the sulphur or phosphorus containing compound or in the absence of such P- or S-compound and in the absence of the copper passivator then the content of anti-oxidant is preferably between 0.01 and 0.4 wt%, more preferably between 0.04 and 0.3 wt%. Yet more preferably, between 10 mg/kg and 0.3 wt% of a di-t-butylated hydroxotoluene anti-oxidant additive is present in the electrical oil formulation according to the invention.

The oil formulation preferably comprises also a copper passivator, also sometimes referred to as an electrostatic discharge depressant or metal deactivator. Examples of possible copper passivator additives are N-salicylideneethylamine, N,N'-di salicylidene-ethyldiamine, triethylenediamine, ethylenediammine-tetraacetic acid, phosphoric acid, citric acid and gluconic acid. More preferred are lecithin, thiadiazole, imidazole and pyrazole and derivates thereof. Even more preferred are zinc dialkyldithiophosphates, dialkyldithiocarbamates and benzotriazoles and their tetrahydroderivates. Most preferred are the compounds according to formula (II) or even more

preferred the optionally substituted benzotriazole compound represented by the formula (III)




(II)




(III)

wherein R4 may be hydrogen or a group represented by the formula (IV)



(IV)

5 or by the formula (V)



(V)

wherein:

c is 0, 1, 2 or 3;

R³ is a straight or branched C₁₋₄ alkyl group.

Preferably R³ is methyl or ethyl and C is 1 or 2. R⁵ is

a methylene or ethylene group. More preferably, R⁶ and R⁷ are hydrogen or the same or different straight or branched alkyl groups of 1-18 carbon atoms, preferably a branched alkyl group of 1-12 carbon atoms; R⁸ and R⁹ are the same or different alkyl groups of 3-15 carbon atoms, preferably of 4-9 carbon atoms.

Preferred compounds are 1-[bis(2-ethylhexyl)amino-methyl]benzotriazole, methylbenzotriazole, dimethylbenzotriazole, ethylbenzotriazole, ethylmethylbenzotriazole, diethylbenzotriazole and mixtures thereof. Examples of copper passivator additives as described above are described in US-A-5912212, EP-A-1054052 and in US-A-2002/0109127, which publications are hereby incorporated by reference. These benzotriazoles compounds are preferred because they also act as an electrostatic discharge depressant, which is beneficial when the oil formulation is used as an electrical oil. Copper passivator additives as those described above are commercially available under the product names IRGAMET 39, IRGAMET30 and IRGAMET 38S from CIBA Ltd Basel Switzerland, also traded under the trade name Reomet by CIBA.

The content of the above copper passivator in the oil formulation is preferably above 1 mg/kg and more preferably above 5 mg/kg. A practical upper limit may vary depending on the specific application of the oil formulation. For example, when desiring improved dielectric discharge tendencies of the oil for use as electrical oil it may be desired to add a high concentration of the copper passivator additive. This concentration may be up to 3 wt%. Applicants however found that the advantages of the invention can be achieved at concentrations below 1000 mg/kgw and more

preferably below 300 mg/kg, even more preferably below 50 mg/kg.

It has been found that when between 1 and 1000 mg/kg of a sulphur or phosphorus containing additive is also part of the additive component (ii) the desired properties are even more enhanced. Preferred sulphur and phosphorus containing compounds are sulfides, phosphides, dithiophosphates and dithiocarbamates. Preferably an organic polysulphide compound is used. With polysulphide is here meant that the organic compound comprises at least one group where two sulphide atoms are directly linked. A preferred polysulfide compound is a disulfide compound. Preferred polysulphide compounds are represented by the formula (I)



wherein:

a is 2, 3, 4 or 5;

R^1 and R^2 may be the same or different and each may be straight or branched alkyl group of 1 to 22 carbon atoms, aryl groups of 6-20 carbon atoms, alkylaryl groups of 7-20 carbon atoms or arylalkyl groups of 7-20 carbon atoms. Preferred are arylalkyl groups, more preferred are optionally substituted benzyl groups. More preferably R^1 and R^2 are independently selected from a benzyl group or a straight or branched dodecyl group. Examples of possible sulphur and phosphorus containing compounds and the preferred compounds mentioned here are described in the aforementioned US-A-5912212 as its component (b), which publication is incorporated by reference. An Examples of a suitable disulfide compounds are dibenzyl disulfide, ditertdodecyl disulfide and didodecyl disulfide. The electrical oil formulation according to the invention has a sulphur content of

below 4 wt%. The content of the organic sulphur or phosphorus additive in the oil formulation is preferably less than 0.1 wt% of the formulation, more preferably less than 800 mg/kg and even more preferably less than 400 mg/kg. The lower limit is preferably 1 mg/kg more preferably 10 mg/kg, most preferably 50 mg/kg. The oil formulation may comprise as the base oil exclusively the base oil as described above or alternatively in combination with another base oil. The additional base oil will suitably comprise less than 20 wt%, more preferably less than 10 wt% of the total electrical oil formulation. Examples of such base oils are mineral based paraffinic and naphthenic type base oils and synthetic base oils, for example esters, poly alpha olefins, poly alkylene glycols and the like. Esters are beneficial in order to improve the biodegradability of the oil formulation. Applicants found that for the low viscosity base oil, having a kinematic viscosity at 100 °C of between 1 and 3 mm²/sec, the biodegradability of the oil is qualified as readily biodegradable according to ISO 14593. It is known that Fischer-Tropsch derived base oils may have biodegradable properties as described in for example EP-A-876446. However in said publication the biodegradability was measured using the CEC-L-33-T-82 test. Applicants have now found that base oils derived from a Fischer-Tropsch product and having the properties of the base oils as disclosed in EP-A-876446 are not always readily biodegradable according to the more accurate testing method as laid down in ISO 14593. It is widely known that the CEC-L-32-T-82 test and the more recent version of this test, known as the CEC L-33-A-93, can overestimate the

biodegradability when compared to the ultimate biodegradability as measured by ISO 14593.

The content of the additional ester base oil is preferably between 1 and 30 wt%, more preferably
5 between 5 and 25 wt%. Suitable ester compounds are ester compounds derivable by the reaction of an aliphatic mono, di and/or poly carboxylic acid with iso-tridecyl alcohol under esterification conditions. Examples of said ester compounds are isotridecyl ester of octane-1,8-
10 dioic acid, 2-ethylhexane-1,6 dioic acid and dodecane-1,12-dioic acid. Preferably the ester compound is a so-called pentaerythritol tetrafattyacid ester (PET ester) as made by esterification of pentaerythritol (=PET) with branched or linear fatty acids, preferably C6-C10 acids.
15 The ester may contain di-PET as alcohol component as an impurity.

It has been found especially advantageous to use a Fischer-Tropsch derived base oil as the substantially the sole base oil component. With substantially is here
20 meant that more than 70 wt%, more preferably more than 90 wt% and most preferably 100 wt% of the base oil component in the oil formulation is a Fischer-Tropsch derived base oil as described in detail above.

The oil formulation preferably has a sulphur content
25 of below 0,5 wt% and even more preferably below 0,15 wt%. The source of the majority of the sulphur in the oil formulation will be the sulphur as contained in any additional mineral based base oil component and the optional sulphur containing additives which may be
30 present in the oil formulation according the invention.

In addition to the additive as described above for the component (ii) additional additives may also be present. The type of additives will depend on the

specific application. Without intending to be limiting, examples of possible additives are dispersants, detergents, viscosity modifying polymers, hydrocarbon or oxygenated hydrocarbon type pour point depressants, emulsifiers, demulsifiers, antistaining additives and friction modifiers. Specific examples of such additives are described in for example Kirk-Othmer Encyclopedia of Chemical Technology, third edition, volume 14, pages 477-526. Suitably the dispersant is an ashless dispersant, for example polybutylene succinimide polyamines or Mannic base type dispersants. Suitably the detergent is an over-based metallic detergent, for example the phosphonate, sulfonate, phenolate or salicylate types as described in the above referred to General Textbook. Suitably the viscosity modifier is a viscosity modifying polymer, for example polyisobutylenes, olefin copolymers, polymethacrylates and polyalkylstyrenes and hydrogenated polyisoprene star polymer (Shellvis). Examples of suitable antifoaming agents are polydimethylsiloxanes and polyethylene glycol ethers and esters.

In order to improve the gassing tendency of the oil formulation it is preferred to add between 0.05 and 10 wt%, preferably between 0.1 and 5 wt% of an aromatic compound. Preferred aromatic compounds are for example tetrahydronaphthalene, diethylbenzene, diisopropylbenzene, a mixture of alkylbenzenes as commercially obtainable as "Shell Oil 4697" or "Shellsol A 150" both "Shell" products obtainable from Shell Deutschland GmbH. Another preferred mixture of aromatic compounds is comprised in a mixture of 2,6-di-t-butyl phenol and 2,6-di-t-butyl cresol. Preferably the oil formulation comprises between 0.1 and 3 wt% of 2,6-di-t-

butyl phenol and 0.1 to 2 wt% of 2,6-di-t-butyl cresol in a weight ratio of between 1:1 and 1:1,5.

The oil formulation is preferably subjected to an additional clay treatment.

5 The present invention accordingly further relates to an electrical oil composition comprising a base oil component derived from Fischer Tropsch synthesis products and an additive, wherein (i) at least 80 wt% of the base oil component is a paraffin base oil having
10 a paraffin content of greater than 80 wt% paraffins and a saturates content of greater than 98 wt% and comprising a series of iso-paraffins having n, n+1, n+2, n+3 and n+4 carbon atoms and wherein n is between 20 and 35; and an anti-oxidant additive, wherein the
15 electrical oil formulation has been subjected to a clay treatment.

 Preferably the clay treatment is performed on the oil formulation, more preferably comprising the sulphur or phosphorous containing additive if present. The anti-
20 oxidant and copper passivator additives are preferably added to the oil formulation after performing the clay treatment. Clay treatment is a well know treatment to remove polar compounds from the oil formulation. It is performed in order to further improve the colour,
25 chemical and thermal stability of the oil formulation. It may be performed prior to adding the additives mentioned in this description on a, partly, formulated oil formulation. Clay treatment processes are for example described in Lubricant base oil and wax
30 processing, Avilino Sequeira, Jr., Marcel Dekker, Inc, New York, 1994, ISBN 0-8247-9256-4, pages 229-232. Applicants have found that the oxidative stability of an electrical oil formulation based on a blend of a

Fischer-Tropsch derived base oil and a mineral oil derived base oil and an anti-oxidant additive can be increased by a clay treatment.

5 The above oil formulation is especially suited to be used as an electrical oil because of its good oxidative stability, low sludge formation and also excellent low temperature viscosity values. Examples of applications are switch gears, transformers, regulators, circuit breakers, power plant reactors, cables and other
10 electrical equipment. Preferred electrical oil applications are a transformer oil and a low temperature switch gear oil. Such applications are well known to the skilled person and described for example in Lubricants and related products, Dieter Klamann, Verlag Chemie
15 GmbH, Weinheim, 1984, pages 330-337. A problem often encountered when using an electrical oil in said applications based on a naphthenic base oil is that the kinematic viscosity at -30 °C is too high. When such an oil would be used in application which have to start up
20 at low temperatures, especially at temperatures below 0 °C, the higher viscosity will have a negative effect on the required heat dissipation of the electrical oil. Overheating of the equipment can result. Applicants have found that when the oil formulation according to the
25 present invention is used, especially when the base oil has a kinematic viscosity at 40 °C of between 1 and 15 mm²/sec and a pour point of below -30 °C, more preferably below -40 °C, an electrical oil formulation is obtained having the above desired properties. These
30 oils furthermore show a very low dielectric dissipation factor, even after prolonged testing at elevated temperature. The low dissipation factor is indicative for a low loss of electric power in the application

wherein the electrical oil is used. Because the dissipation factor does not significantly increase over time, especially when compared to the naphthenic based electrical oil formulations, a very efficient application of the oil results.

In another embodiment of the present invention the oil formulation is preferably used as a low temperature switch gear formulation. Traditionally low temperature switch gear formulations are formulated using a low viscous mineral base oils. However, a problem with known low temperature switch gear fluids is that they have, as a result of their (low) viscometric properties, a low flash point. This problem is even more pertinent in arctic regions requiring very low viscosities.

Applicants now found that by using a base oil as described above, especially a Fischer-Tropsch derived base oil, a switch gear fluid formulation having excellent viscometric properties at low temperatures can be obtained, making the formulation suitable for the use as a low temperature switch gear formulation. A further advantage is that the base oil has a high flash point allowing the switch gear fluid to be safely used under very critical switching operations, for example in a so-called high-load grid.

The low temperature switch gear oils as described above may find use in applications which have to start up regularly, especially more than 10 times per year at a temperature of below 0 °C, more preferably below -5 °C, wherein the temperature of the oil when the application is running is above 0 °C.

Another preferred electrical oil application is the fire resistant electrical oil application. The base oil is said application preferably has a kinematic viscosity

at 100 °C of above 6 mm²/sec, more preferably above 7 and suitably below 12 mm²/sec. It has been found that the paraffinic base oils in this viscosity range have a high flash point of greater than 250 °C and preferably greater than 260 °C, making them very suitable for such applications. Such formulations require low flammability and improved fire safety characteristics. These oils are suitably used as transformer oil used in indoor or underground environments.

Applicants found that the low viscosity base oil is readily biodegradable. The biodegradability can be further improved by adding an ester based base oil to said formulation as described above. In a further embodiment of the present invention the oil formulation can thus be advantageously used in those applications, which require a biodegradable base oil in said formulation. Especially the oil formulation is used as a transformer oil in mobile electrical equipment, especially trains, electrical powered cars or hybrid powered cars. The oil formulations may also find advantageous use in equipment used in environmental sensitive areas, such as for example national parks, conservation areas, water protection areas, potable water storage facilities and the like.

The invention will be illustrated with the following non-limiting examples. In the examples use has been made of four different types of base oils. One Fischer-Tropsch derived base oil, referred to as GTL BO, two naphthenic type of base oils, referred to as naphthenic-1 and naphthenic-2, and a mineral paraffinic base oil. The properties of these base oils are listed in Table 1.

Table 1

Base Oil		GTL BO -1	GTL BO-2	GTL BO-3	Naphthenic	Naphthenic	Paraffinic	Paraffinic
Vk @ 100°C	ASTM D445 mm ² /s	2,4	4.0	7.8	-1 2,1	-2 2,1	-1 2,2	-2 8,3
Vk @ 40°C	ASTM D445 mm ² /s	7,9			8,8	7,8	8,0	75,1
VI	ASTM D2270	126	135	148	<0	47	88	73
Pour Point	ASTM D5950 °C	-51	-30	-24	-60	-60	-15	-18
Flash point	ASTM D92 °C	192	228	274	147	154	186	232
Paraffins by FD/FI technique	(wt%)	90.7	92.3	90.8				
Carbon distribution		See Figure 1(*)		Figure 2(*)				
Basic Nitrogen	ISO 3771mod mg/kg				4	<1	1	3

Table 1 (cont'd)

Base Oil		GTL BO -1	GTL BO-2	GTL BO-3	Naphthenic	Naphthenic	Paraaffinic	Paraaffinic
Sulphur	ISO 14596	<0,001			-1	-2	-1	-2
Colour	ASTM D2049	L0.5			0,075	0,001	0,015	0,021
Biodegradation after 28 days	ISO 14593	60			L0.5	L0.5	L0.5	L1.5

(*) Carbon distribution per carbon number as measured by Field desorption/Field Ionisation (FD/FI) technique, wherein Z=2 represents the iso and normal paraffins, Z=0 the 1-ring naphthenic compounds, Z=-2 the 2-ring naphthenic compounds, Z=-4 the 3-ring naphthenic compounds etc.

Example 1

Starting with the naphthenic-1, mineral paraffin base oil-1 and the GTL base oil-1 of Table 1 five different oil mixtures according to the additivations schemes 1-8 of table 2 were made. For all of these oil mixtures the Sludge Formation was measured according to the Oxidation Test IEC 61125 C at 164h/120 °C. The lower the value the less sludge is found. The results are also presented in Table 2.

Table 2
Sludge formation according to IEC 61125 C

Additivition scheme	1	2	3	4	5	6	7	8
Dibenzylidisdulfide	-	-	200	200	200	200		
1- [bis(2-ethylhexyl) - aminomethyl]benzotriazole (Reomet38S)	-	10	-	10	10		10	
Antioxidant BHT	-	-	-	-	0,08	0,08	0,08	0,3
Naphthenic base oil	1,700	1,530	0,561	0,281	0,295			
Paraffinic base oil-1	3,340	2,440	0,209	0,086	<0,006			
GtL base oil-1	0,085	0,023	0,043	0,071	0,006	0,006	0,006	<0,006

For all of these oil mixtures according to
additivation schemes 1-5 of above also the Total Acidity
using the Oxidation Test IEC 61125 C at 164h/120 °C was
measured. The lower the value the less acid compounds
5 are formed and the more oxidative stable the oil
formulation is. The results are presented in Table 3.

Table 3

Additivation scheme	1	2	3	4	5	6	7	8
Dibenzylidisdulfide	-	-	200	200	200	200		
1-[bis(2-ethylhexyl)amino-methyl]benzotriazole	-	10	-	10	10		10	
Antioxidant BHT	-	-	-	-	0,08	0,08	0,08	0,3
Total acidity according to IEC 61125 C								
Naphthenic base oil-1	Mg KOH/g	4,14	3,87	1,59	0,83	1,02		
Paraffinic base oil-1	Mg KOH/g	9,12	6,78	0,78	0,38	0,02		
GTL Base Oil-1	Mg KOH/g	13,67	10,55	12,65	12,57	0,10	<0,01	0,02

Example 2

4 oil mixtures were prepared according to the scheme as presented in Table 4. Two oil mixtures were subjected to a clay treatment using Tonsil 411 clay as obtainable from Sued Chemie, Munchen (D). The anti-oxidant and copper passivator additives were added after the clay treatment. The properties of the oil mixtures were measured and the oil mixtures were subjected to the IEC OXIDATION TEST at 500h/120 °C.

Table 4

Sample Identification			U	V	X	Y	Z	W
GTL base oil-1	Wt%		99,61	99,3	99,68	-	94,68	-
Naphthenic-1	Wt%				-	99,68		94,68
Mineral paraffinic base oil-1	Wt%				-	-	5,00	5,00
Dibenzylidissulfid	Wt%		0,09	0,4	0,02	0,02	0,02	0,02
Clay treatment (Tonsil)	%				-	-	1	1
1-[bis(2-ethylhexyl)amino-methyl]benzotriazole	mg/kg		10	10	10	10	10	10
Antioxidant BHT	Wt%		0,30	0,30	0,30	0,30	0,30	0,30
Properties of the oil mixtures			U	V	X	Y	Z	W
FLASH POINT		ISO 2719			160	145	160	145
POUR POINT	°C	DIN ISO 3016			<-60	<-60	-51	-54
KIN.VISCOSITY -30 °C	mm ² /s	DIN 51562			341	1140	368	1210
KIN.VISCOSITY 40 °C	mm ² /s	DIN 51562			8	8,7	8	9
KIN.VISCOSITY 100 °C	mm ² /s	DIN 51562			2,4	2,2	2,4	2,2
BREAKDOWN VOLTAGE	kV	VDE 0370-5					84	

Table 4 (cont'd)

Sample Identification			U	V	X	Y	Z	W
DIELECTR. DISSIPATION FACTOR 90 °C		VDE 0370-1					0,0002	
KORRO. SULFUR Ag/100°C		DIN 53 353	Fail (*)	Fail (**)			pass	pass
IEC OXIDATION TEST 500h/120°C:								
IEC 61125/C								
- Total acidity after 500h/120 °C test	mgKOH/ g	IEC 61125/C			<0,01	0,69	0,02	0,41
- Sludge after 500h/120°C test	m %	IEC 61125/C			<0,006	0,202	<0,006	0,043
- Dielectr. Dissip. F. 90°C after 500h/120°C test		IEC 61125/C			0,0015	0,1021	<0,0035	0,1017

(*) light grey discolouration

(**) grey discolouration

Table 4 shows that the oil formulation based on the Fischer-Tropsch derived base oil has a low viscosity at -30 °C in combination with excellent oxidative stability properties. The gassing tendency of the Mixture Z of Table 4 can be improved by adding an aromatic solvent as illustrated in Table 5.

Table 5

Sample Identification		Z	Z'
GTL base oil-1	Wt%	94,68	94,18
Mineral Paraffinic base oil-1	Wt%	5,00	5,00
Dibenzylidissulfid	Wt%	0,02	0,02
Clay treatment (Tonsil)	Wt%	1	1
1-[bis(2-ethylhexyl)amino-methyl]benzotriazole	Mg/kg	10	10
Shellsol A 150 (aromatic hydrocarbon solvent)	Wt%		0,5
Antioxidant BHT	Wt%	0,30	0,30
GASSING TENDENCY measured according to BS 5797	mm ³ /min	> 0	-8,9

Example 3

Three oil formulations A-C were made using the GTL Base Oils 1, 2 and 3 of Table 1 according to the formulations as listed in Table 6. The oil formulations A-C were subjected to a clay treatment using Tonsil 411 clay as obtainable from Sued Chemie, Munchen (D). The anti-oxidant and copper passivator additive were added after the clay treatment.

The oils were tested with the test methods listed in Table 6. The results show that excellent oils for use as electrical oils.

Table 6

Oil properties			Oil A	Oil B	Oil C
Formulation					
GTL BO-1	Wt%		94,7		
GTL BO-2	Wt%			98,7	
GTL BO-3	Wt%				98,7
Paraffinic-base oil 1	Wt%		5,0		
Paraffinic-base oil 2	wt%			1,0	1,0
Dibenzylsulfide	mg/kg		200	200	200
1- [bis(2-ethyl- hexyl) aminomethyl] - benzotriazole	mg/kg		10	10	10
Ionol	861805 %		0,3	0,3	0,3
Test results					
TEST	DIMENS.	METHODE			
FLASH POINT	°C	ISO 2592	160	226	263
POUR POINT	°C	DIN ISO 3016	-51	-30	-18
KIN.VISCOSITY 40 °C	Mm ² /s	DIN 51562	7,8	17,5	Not measured
KIN.VISCOSITY 100 °C	Mm ² /s	DIN 51562	2,4	4,1	7,8
IEC OXIDATION TEST 500h/120°C IEC 61125/C					
- Total acidity	mgKOH/g		0,02	0,02	0,04
- Sludge	Gew. %		< 0,006	<0,008	< 0,007
- Dielectr. Dissip. F. 90°C			0,0035	0,0004	0,0004

Example 4

Four oil mixtures were tested for their biodegradability according to ISO 14593. The results are presented in Table 7. From Table 7 it can be seen that a biodegradable base oil or base oil mixture for use in a transformer oil according to IEC 60296 specification is provided. Oil formulations using exclusively the ester base oil did not meet the kinematic viscosity at 40 °C specification.

This is advantageous because as a rule ester base oils are more difficult to prepare, and hence expensive, than the Fischer-Tropsch derived base oils.


Table 7

Identification		Oil	GTL BO-1	GTL BO-1/ ester	GTL BO-1/ ester	Ester formula tion	IEC 60296 Trans-former Oil	IEC 61099 Type T1
Formulation								
GTL BO-1	%	99,92	100,0	80,0	60,0			
Dibenzylsulfide	ppm	200						
1- [bis (2-ethylhexyl)aminomethyl]-benzotriazole	ppm	10						
Pentaerythrittetrafettsäureester (C ₆ -C ₁₀) (CAS 68987-94-0)			20,0	40,0		99,7	99,7	99,7
Anti-oxidant BHT	wt%	0,08				0,3		
TEST		METHODE						
FLASH POINT	°C	ISO 2719	160	>160	>160	265	min. 135	min. 250
POUR POINT	°C	DIN ISO 3016	-51	-52	-54	-60	max. -40	max. -45
KIN.VISCOSITY 40 °C	mm ² /s	DIN 51562	7,8	9,8	12,5	31,9	max. 12	max. 35
KIN.VISCOSITY 100 °C	mm ² /s	DIN 51562	2,4	2,7	3,3	5,7		
DIELECTR. DISSIPATION FACTOR 90°C		VDE 0370-1	0,0010			0,0100	max. 0,005	
BREAK DOWN VOLTAGE	kV	IEC 61156	> 70			82	min. 70	min. 45
IEC OXIDATION TEST 164h/120°C		IEC 61125/C				82	min. 70	min. 45
- Total acidity	mgKOH/g		0,10			0,04	max. 1,2	max. 0,3
- Sludge	Gew. %		0,006			0,002	max. 0,8	max. 0,01
Biodegradation after 28 days	%	ISO 14593	60	63	70	>60		


C L A I M S

1. Electrical oil formulation comprising a base oil component and an additive, wherein
- (i) at least 80 wt% of the base oil component is a paraffin base oil having a paraffin content of greater than 80 wt% paraffins and a saturates content of greater than 98 wt% and comprising a series of iso-paraffins having n, n+1, n+2, n+3 and n+4 carbon atoms and wherein n is between 20 and 35; and
- (ii) an anti-oxidant additive;
- wherein the base oil component has a flash point of at least 170 °C, as determined by ISO 2592.
2. Formulation according to claim 1, wherein the paraffin base oil has a kinematic viscosity at 40 °C of between 1 and 200 mm²/sec.
3. Formulation according to claim 2, wherein the paraffin base oil has a kinematic viscosity at 40 °C of between 1 and 15 mm²/sec, a pour point of below -30 °C and wherein the formulation comprises between 0.05 and 10 wt% of an aromatic compound.
4. Formulation according to any one of claims 1-3, wherein the paraffinic base oil is obtained by hydroisomerisation of a Fischer-Tropsch derived wax, followed by dewaxing.
5. Formulation according to any one of claims 1-4, wherein the anti-oxidant additive is the only additive and where the content of the anti-oxidant additive is between 0.04 and 0.4 wt%.
6. Formulation according to any one of claims 1-4, wherein also an copper passivator additive is present.

7. Formulation according to claim 6, wherein the copper passivator is a compound according to formula (II) or an optionally substituted benzotriazole compound represented by the formula (III)




(II)




(III)

5 wherein R4 may be hydrogen or a group represented by the formula (IV)



(IV)

or by the formula (V)



(V)

wherein:

c is 0, 1, 2 or 3;

10 R³ is a straight or branched C₁₋₄ alkyl group; R⁵ is a methylene or ethylene group; R⁶ and R⁷ are hydrogen or the same or different straight or branched alkyl groups of 1-18 carbon atoms, preferably a branched alkyl group

of 1-12 carbon atoms; R⁸ and R⁹ are the same or different alkyl groups of 3-15 carbon atoms.


8. Formulation according to claim 7, wherein R³ is methyl or ethyl and C is 1 or 2.

5 9. Formulation according to any one of claims 1-8, wherein the anti-oxidant additive is a phenolic or amine antioxidant.

10 10. Formulation according to claim 9, wherein between 10 mg/kg and 0.3 wt% of a di-t-butylated hydroxotoluene anti-oxidant additive is present.

11. Formulation according to any one of claims 1-10, comprising between 1 and 1000 mg/kg of a sulphur or phosphorus containing additive.

15 12. Formulation according to claim 11, wherein the sulphur containing additive is represented by the formula



wherein:

20 a is 2, 3, 4 or 5; R¹ and R² may be the same or different and each may be straight or branched alkyl group of 1 to 22 carbon atoms, aryl groups of 6-20 carbon atoms, alkylaryl groups of 7-20 carbon atoms or arylalkyl groups of 7-20 carbon atoms.

25 13. Formulation according to claim 12, wherein the content of the organic polysulfide is between 50 and 800 mg/kg.

14. Formulation according to any one of claims 1-13, wherein the formulation has a sulphur content of below 4 wt%.

30 15. Process to prepare a electrical oil formulation according to any one of claims 1-14, wherein the base oil component is subjected to a clay treatment and wherein the anti-oxidant additive and copper passivator

if present are added after performing the clay treatment.

16. Use of the formulation according to any one of claims 1-15 as an electrical oil.

5 17. Use according to claim 16 in an application which starts up more than 10 times per year at a temperature of below 0 °C, wherein the temperature of the oil when the application is running is above 0 °C.

10 18. Use according to any one of claims 16-17, wherein the electrical oil is used as a transformer oil in a transformer application.

19. Use according to any one of claims 16-17, wherein the electrical oil is used as a switch gear oil in switch gear application.




Figure 1




Figure 2

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2006/063439A. CLASSIFICATION OF SUBJECT MATTER
INV. C10M169/04 C10M171/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C10M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2002/139962 A1 (FEFER MICHAEL ET AL) 3 October 2002 (2002-10-03) paragraphs [0019], [0023], [0024]; claims 1-3,20; example 3; table 1 -----	1-14, 16-19
A	WO 02/070629 A (SHELL INTERNATIONALE RESERACH MAATSCHAPPIJ B.V.; GERMAINE, GILBERT, ROB) 12 September 2002 (2002-09-12) cited in the application page 17, lines 13-22; claims; examples -----	1-19
A	US 5 912 212 A (IGARASHI ET AL) 15 June 1999 (1999-06-15) column 12, line 1 - column 13, line 55 column 16, line 1 - column 18, line 40 ----- -/--	6-14

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

7 September 2006

Date of mailing of the international search report

19/09/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bertrand, Samuel

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2006/063439

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6 214 776 B1 (ANGELO JACOB B ET AL) 10 April 2001 (2001-04-10) claim 1 -----	6-10,14, 19
A	WO 02/064710 A (SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V; DANIEL, MERVYN, FRANK;) 22 August 2002 (2002-08-22) page 2, lines 16-19; figure 1 -----	1-19
A	EP 1 026 225 A (EXXONMOBIL RESEARCH AND ENGINEERING COMPANY) 9 August 2000 (2000-08-09) claims 1-4 -----	1-19

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2006/063439

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2002139962	A1	03-10-2002	NONE
WO 02070629	A	12-09-2002	AT 277993 T 15-10-2004 BR 0207890 A 23-03-2004 BR 0207891 A 23-03-2004 CA 2440053 A1 12-09-2002 CA 2440071 A1 12-09-2002 CN 1500133 A 26-05-2004 CN 1500134 A 26-05-2004 DE 60201421 D1 04-11-2004 DE 60201421 T2 13-10-2005 EA 5089 B1 28-10-2004 WO 02070630 A1 12-09-2002 WO 02070636 A1 12-09-2002 ES 2230488 T3 01-05-2005 JP 2004528426 T 16-09-2004 JP 2004526831 T 02-09-2004 JP 2004522848 T 29-07-2004 MX PA03007980 A 04-12-2003 MX PA03007991 A 04-12-2003 NO 20033903 A 04-11-2003 NO 20033905 A 04-11-2003 NZ 527907 A 24-03-2005 NZ 527945 A 25-02-2005 PL 367202 A1 21-02-2005 US 2004099571 A1 27-05-2004 US 2004079675 A1 29-04-2004 US 2004045868 A1 11-03-2004
US 5912212	A	15-06-1999	EP 0781834 A2 02-07-1997
US 6214776	B1	10-04-2001	AU 778587 B2 09-12-2004 AU 5019800 A 12-12-2000 BR 0010734 A 19-02-2002 CA 2373585 A1 30-11-2000 EP 1187894 A1 20-03-2002 JP 2003500520 T 07-01-2003 NO 20015671 A 20-11-2001 WO 0071648 A1 30-11-2000
WO 02064710	A	22-08-2002	AT 302258 T 15-09-2005 AT 307865 T 15-11-2005 BR 0207091 A 20-01-2004 BR 0207092 A 20-01-2004 CA 2437858 A1 22-08-2002 CA 2437862 A1 22-08-2002 DE 60205596 D1 22-09-2005 DE 60205596 T2 24-05-2006 DE 60206891 D1 01-12-2005 DK 1370633 T3 21-11-2005 DK 1368446 T3 06-03-2006 WO 02064711 A1 22-08-2002 ES 2248538 T3 16-03-2006 ES 2252469 T3 16-05-2006 JP 2004521976 T 22-07-2004 JP 2004521977 T 22-07-2004 MX PA03007088 A 18-11-2003 MX PA03007160 A 18-11-2003

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2006/063439

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 02064710	A	NO 20033559 A	10-10-2003
		NZ 526900 A	28-10-2005
		NZ 527127 A	30-09-2005
		US 2004118744 A1	24-06-2004
		US 2004077505 A1	22-04-2004
EP 1026225	A	09-08-2000 CA 2295241 A1	05-08-2000
		DE 60002617 D1	18-06-2003
		DE 60002617 T2	26-02-2004
		SG 82061 A1	24-07-2001
		US 6083889 A	04-07-2000