

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 December 2008 (18.12.2008)

PCT

(10) International Publication Number
WO 2008/154022 A1

(51) International Patent Classification:
H01M 2/16 (2006.01) **H01M 10/24** (2006.01)

(74) Agent: **GOLIAN, Andrew, G.**; E. I. du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, Delaware 19805 (US).

(21) International Application Number:
PCT/US2008/007283

(22) International Filing Date: 11 June 2008 (11.06.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/811,563 11 June 2007 (11.06.2007) US

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(71) Applicant (for all designated States except US): **E. I. DU PONT DE NEMOURS AND COMPANY** [US/US]; 1007 Market Street, Wilmington, Delaware 19898 (US).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ARORA, Pankaj** [IN/US]; 8107 Ainsdale Lane, Chesterfield, Virginia 23832 (US). **KIM, Young, H.** [US/US]; 406 Bartram Lane West, Hockessin, Delaware 19707 (US). **FRISK, Simon** [CH/US]; 2707 Eagle Run Lane, Richmond, Virginia 23236 (US).

Published:

— with international search report

WO 2008/154022 A1

(54) Title: BATTERIES WITH PERMANENTLY WET-ABLE FINE FIBER SEPARATORS

(57) Abstract: Alkaline batteries are disclosed that advantageously include separators comprising at least one porous layer of fine fibers having a diameter of between about 50 nm and about 3000 nm that provide improved combinations of reduced thickness, dendritic barrier against short-circuiting and low ionic resistance as compared with known battery separators. The fine fibers show improved wet-ability in the alkaline electrolytes.

BATTERIES WITH PERMANENTLY WET-ABLE FINE FIBER SEPARATORS

FIELD OF THE INVENTION

5 The present invention relates to batteries with permanently wet-able fine fiber separators with surface active agents.

BACKGROUND OF THE INVENTION

Polymer fibers have been widely used in the nonwovens industry in 10 the manufacture of nonwoven webs, fabrics, and composites. Olefin polymers, such as polyethylene, polypropylene, polybutene, polypentene, and copolymers of ethylene or propylene with other olefinic monomers, are known for their hydrophobic properties. Thus, nonwoven webs of polyolefin fibers are frequently used in applications where their 15 hydrophobic properties are advantageous. For example, polyolefin nonwovens are often used in diapers, other hygiene products and medical applications where it is desired to keep moisture away from a wearer's skin.

However, there are numerous other nonwoven fabric applications 20 where the hydrophobic nature of polyolefin fibers is not required and where hydrophilic properties are desired. Even a fiber made of a polymer such as a polyamide or polyester may not have the required hydrophilicity for certain applications. If a nonwoven fabric formed of polymer fibers is to be used, the fibers must be treated in some way to alter the normally 25 hydrophobic properties of the fibers to impart hydrophilic properties. One well-known practice involves the topical application of compositions, such as surfactants, to render the fabric more hydrophilic. However, topical chemical applications are not entirely satisfactory for some applications, since they are not durable. The hydrophilic property is lost after washing or 30 after extended use in a battery. The extra processing steps required for topical chemical treatments or other fiber surface modification treatments also undesirably increase the cost of the fabric. The few processes known to render the polymers wet-able are environmentally unfriendly, relatively slow and have limited durability.

For improving wet-ability it is known in the industry that certain surfactants, such as TRITON X-100 from Rohm and Haas, can be applied as an aqueous solution or suspension to the surface of hydrophobic fibers, filaments or nonwoven fabrics with the resulting effect of rendering the 5 fibers, filaments or fabrics wet-able, although not absorbent. These topical treatments can be applied by any means familiar to one skilled in the art, such as foaming spraying, dip-and squeeze or gravure roll. In almost every case, some sort of heating step is required to remove residual water or solvent used to prepare the surfactant solution or suspension. This 10 step adds significantly to the manufacturing costs and complexity. Further, thermoplastics are altered by exposure to heat and careful monitoring of the heating process is required to ensure that fabric properties are not adversely affected. Also, since surfactants are not strongly chemically bonded to the fiber or filament surfaces, such topical 15 treatments are not durable. They tend to wash off during repeated fluid exposures or rub off during use.

In an effort to correct this deficiency, corona discharge treatments have been used to alter the electrochemical potential of the surfaces of fibers or filaments. The effect is to render surfaces more reactive with the 20 result that hydrophobic surfaces become more wet-able. However, these electrical potential changes are also not permanent, being particularly subject to environmental effects, such as storage in moist environments.

An additional alternative is the use of surface chemical treatments where the surfactants are covalently bonded to the polymer.

25 Another approach is the incorporation of chemical agents in the thermoplastic polymer before it is melt extruded into fibers, filaments or nonwoven fabrics, rendering the fibers themselves hydrophilic. Agents, such as siloxanes, have been proposed for this purpose. Here, the object is to impart a durable change in the wet-ability of the fibers or filaments.

30 The performance model theory states that the melt additives become dispersed in the molten polymer and are bound in the matrix when the polymer cools during fiber or filament quenching. Over time, due to the effects of further processing, the additive rises to the surface of the fibers or filaments, a phenomenon called blooming, imparting durable wet-ability.

Published PCT Patent Specification WO99/00447 discloses a product and process for making wet-able spunbond and melt blown fibers prepared from an olefin polymer, polyester or polyamide including a wetting agent consisting essentially of a monoglyceride or a combination of a 5 monoglyceride and a mixed glyceride with the monoglyceride amounting to at least 85% by weight in the case of the combination.

However, the use of hydrophilic melt additives can add significantly to the cost of the nonwoven webs. Also, the addition of a hydrophilic melt additive to the polymer can alter the properties of the fibers or filaments, 10 resulting in unacceptable changes to important physical or aesthetic properties of the nonwoven web, such as strength, softness or hand, for example.

In alkaline batteries, a separator is used between a positive electrode and a negative electrode to keep them separated and to prevent 15 a short circuit therebetween, and further, to hold an electrolyte thereon and enable a smooth electromotive reaction.

Battery separators for alkaline batteries are conventionally either thick, multi-layered nonwovens having large pores that have good (low) ionic resistance but relatively poor barrier to growing dendrites (also 20 referred to herein as "dendritic barrier"), or multi-layered nonwovens with microporous membranes thereon having very small pores that have good dendritic barrier but very high ionic resistance.

The space allotted for the battery has been becoming smaller in 25 electronic equipment, due to the need for miniaturization and weight-saving. Nevertheless, the performance requirement for such a smaller battery is the same as or higher than that for a conventional battery, and therefore, it is necessary to enhance the capacity of the battery, and to increase the amounts of active materials in the electrodes. Thus, it would be advantageous if the volume allotted in the battery for the separator 30 could be reduced, and the separator made thinner. However, if a conventional separator is simply made thinner, its capacity for holding electrolyte (i.e., the electrolyte-holding capacity) is reduced. Thinner nonwovens with large fibers results in large effective pore size of the separator and poor barrier properties. In addition, in these thinner

nonwovens, the uniformity of the fiber distribution may be reduced, further increasing the effective pore size.

U.S. patent 7,112,389 is describes the use of nanowebs as separators in batteries. The use of nanowebs yields superior performance by giving a better balance between the ionic resistance and barrier properties. Because the fiber size is drastically reduced, as compared to conventional battery separator materials, a very small pore size can be achieved with very thin separator materials. The nanowebs are coated with surfactants to improve the wet-ability, wicking, and electrolyte absorption in 35% KOH.

There remains a need for thin separators with permanent wet-ability for use in batteries which also exhibit good wicking and electrolyte absorption properties.

15

SUMMARY OF THE INVENTION

One embodiment of the present invention is directed to an alkaline battery having a separator comprising a porous fine fiber layer of wet-able polymeric fibers having a mean diameter in the range from about 50 nm to about 3000 nm, wherein the porous fine fiber layer permanently wets with strong alkaline electrolytes.

20

DETAILED DESCRIPTION OF THE INVENTION

It would be desirable to have alkaline batteries with thin separators having an improved balance of dendritic barrier and ionic resistance, as well as permanent wet-ability in 35% KOH electrolyte, which also have good wicking and electrolyte absorption properties.

25

The alkaline batteries of the present invention include battery separators having an improved combination of reduced thickness, reduced ionic resistance and good dendritic barrier properties, providing a high resistance to short-circuiting. The separators useful in the batteries of the invention have a high capacity to absorb electrolyte while maintaining excellent structural integrity and chemical and dimensional stability in use, such that the separators do not lose their dendritic barrier properties even when saturated with electrolyte solution. The reduction in thickness

enables the manufacture of batteries having increased capacity. The separators useful in the batteries of the invention have low ionic resistance, therefore ions flow easily between the anode and the cathode. The separators wet instantly with alkaline electrolytes and stay wet during 5 extended use in the battery.

The specific polymer compositions of the present invention, when spun into fine fiber layers, have superior wetting properties in strong alkaline solutions and also exhibit good wicking and electrolyte absorption properties with thinner separators.

10 By "wet-able fiber" is meant that the polymeric fibers of the battery separator of the invention comprise surfactant molecules embedded within the polymer and extending to the fiber surfaces.

15 In one embodiment of the invention an effective amount of surfactant is added to the fiber spinning solution to form polymeric fibers comprising a composition of polymer and surfactant which is wet-able. An "effective amount" of surfactant is to be understood to mean at least an amount that produces wet-ability in the electrolyte of choice. This procedure results in a good distribution and entrapment of the surfactant molecules in the fibers and on the fiber surface. In turn, this minimizes 20 both the risk of surfactant molecules being stripped from the surface of the fibers during handling of the material and the risk of surfactant molecules leaching into the electrolyte in the end use.

25 In one embodiment of the invention, an effective amount of surfactant is added to the fiber spinning solution to form polymeric fibers comprising a composition of polymer and surfactant which makes the fibers, which are inherently hydrophobic, hydrophilic. The fibers can then be further coated with water-based surfactant solutions after spinning, instead of having to be coated with a non-aqueous surfactant solution. The polymer can be coated with surfactant from aqueous solutions and 30 the separator will be wet-able in the electrolyte of choice when it is dry.

Suitable surfactants of the invention are preferably nonionic surfactants, such as alkylated polyether surfactant (e.g. Tergitol or Triton from Dow Chemical) or siloxyl polyether surfactant (e.g. Silwet from GE), but not limited to them. The surfactant amount can vary from 0.4 wt% to

20 wt% (weight % relative to the polymer), preferably between 1 wt% and 5 wt%.

One embodiment of the invention relates to an alkaline battery.

The battery can be an alkaline primary battery, e.g., Zinc-Manganese Oxide or Zn--MnO₂ battery in which the anode is zinc and the cathode is manganese oxide (MnO₂), or Zinc-Air battery in which the anode is zinc and the cathode is air, or it can be an alkaline secondary battery, e.g., a Nickel Cadmium battery in which the anode is cadmium and the cathode is Nickel oxy-hydroxide (NiOOH), Nickel Zinc or Ni--Zn battery in which the 10 anode is zinc and the cathode is NiOOH, Nickel Metal Hydride (NiMH) battery in which the anode is metal hydride (e.g. LaNi₅) and the cathode is NiOOH or Nickel-Hydrogen or NiH₂ battery in which the anode is hydrogen (H₂) and the cathode is NiOOH. Other types of alkaline batteries include Zinc/Mercuric Oxide in which the anode is zinc, and the cathode is 15 mercury oxide (HgO), Cadmium/Mercuric Oxide in which the anode is cadmium and the cathode is mercury oxide, Zinc/Silver Oxide in which the anode is zinc and the cathode is silver oxide (AgO), Cadmium/Silver Oxide in which the anode is cadmium and the cathode is silver oxide. All of these battery types use 30-40% potassium hydroxide as the electrolyte.

20 The battery of the present invention includes a separator having at least one porous layer of wet-able fine polymeric fibers having a mean diameter in the range of between about 50 nm and about 3000 nm, even between about 50 nm and about 1000 nm, and even between about 50 nm and about 500 nm. Fine fibers in these ranges provide a separator 25 structure with high surface area which results in good electrolyte absorption and retention due to increased electrolyte contact. The separator has a mean flow pore size of between about 0.01 µm and about 15 µm, even between about 0.01 µm and about 5 µm, and even between about 0.01 µm and about 1 µm. The separator has a porosity of between 30 about 20% and about 90%, even between about 40% and about 70%. The high porosity of the separator also provides for good electrolyte absorption and retention in the battery of the invention.

A separator useful in the battery of the invention has a thickness of between about 0.1 mils (0.0025 mm) and about 12 mils (0.3 mm), even

between about 0.5 mils (0.0127 mm) and about 5 mils (0.127 mm). The separator is thick enough to prevent dendrite-induced shorting between positive and negative electrode while allowing good flow of ions between the cathode and the anode. The thin separators create more space for the 5 electrodes inside a cell and thus provide for improved performance and life of the batteries of the invention.

The separator has a basis weight of between about 1 g/m² and about 90 g/m², preferably between about 5 g/m² and about 30 g/m². If the basis weight of the separator is too high, i.e., above about 90 g/m², then 10 the ionic resistance may be too high. If the basis weight is too low, i.e., below about 1 g/m², then the separator may not be able to reduce dendrite shorting between the positive and negative electrode.

The separator has a Frazier air permeability of less than about 150 cfm/ft² (46 m³/min/m²), even less than about 25 cfm/ft² (8 m³/min/m²), even 15 less than about 5 cfm/ft² (1.5 m³/min/m²). In general, the higher the Frazier air permeability, the lower the ionic resistance of the separator, therefore a separator having a high Frazier air permeability is desirable.

The separator can comprise multiple porous fine fiber layers which 20 may comprise the same or different polymers. In addition, the multiple layers may have differing characteristics selected from the list consisting of thickness, basis weight, pore size, fiber size, porosity, air permeability, ionic resistance, and tensile strength.

Suitable polymers for use in the alkaline battery separator include 25 aliphatic polyamide, semi-aromatic polyamide, polyvinyl alcohol, cellulose, polyethylene terephthalate, polypropylene terephthalate, polybutylene terephthalate, polysulfone, polyvinylidene fluoride, polyethylene, polypropylene, polymethyl pentene, polyphenylene sulfide, polyacetyl, polyacrylonitrile, polyurethane, aromatic polyamide and blends, mixtures and copolymers thereof. Polymers that are especially suitable for use in 30 the alkaline battery separator include polyvinyl alcohol, cellulose, aliphatic polyamide and polysulfone. In some embodiments of the invention, it may be preferable to crosslink the polymeric fine fibers in order to maintain the porous structure and improve the structural integrity of the separator in the electrolyte. For example, uncross linked polyvinyl alcohol separators can

dissolve in water and form a gel type structure having poor structural integrity in strong alkaline electrolytes. Certain polymers, e.g. polyvinyl alcohol (PVA), polyvinylidene fluoride, polyvinylidene fluoride-hexafluoropropylene, polyethylene oxide, polyacrylonitrile, polymethyl methacrylate, tend to swell or gel in the electrolytes, thus closing the pores of the fibrous structure. In certain cases they will also become soft or degrade in the electrolyte leading to poor structural integrity. Depending on the polymer of the battery separator, various cross linking agents and cross linking conditions can be used. All the polymers mentioned above can be cross linked by known means, such as by chemical cross linking, electron beam cross linking or UV cross linking.

One process for making the fine fiber layer(s) of the separator for use in the battery of the invention is an electroblowing process as disclosed in International Publication Number WO2003/080905 (U. S. Ser. No. 10/822,325), which is hereby incorporated by reference. Alternatively, the fine fiber layer(s) of the separator can be made by a conventional electrospinning process such as disclosed in U.S. Published Patent Application No. 2004/0060268 A1.

In one embodiment of the invention, the battery separator comprises a single fine fiber layer made by a single pass of a moving collection means through the process, i.e., in a single pass of the moving collection means under the spin pack. Alternatively, the battery separator can comprise multiple fine fiber layers, formed by multiple passes under the spin pack. It will be appreciated that the fibrous web can be formed by one or more spinning beams running simultaneously over the same moving collection means. When the separator comprises multiple layers, the multiple layers can be layers of the same polymeric fine fibers, or can alternatively be layers of differing polymeric fine fibers. The multiple layers can have differing characteristics including, but not limited to, polymer, thickness, basis weight, pore size, fiber size, porosity, air permeability, ionic resistance and tensile strength.

The collected fine fiber layer(s) are advantageously bonded which has been found to improve the tensile strength of the separator. A high level of tensile strength in the machine direction helps during cell winding

and also contributes to the good dendritic barrier of the separator in use. Bonding may be accomplished by known methods, including but not limited to thermal calendering between heated smooth nip rolls, ultrasonic bonding, point bonding, and through gas bonding. Bonding increases the 5 strength of the fine fiber layer(s) so that the layer(s) may withstand the forces associated with being handled and being formed into a useful separator, and depending on the bonding method used, adjusts physical properties such as thickness, density, and the size and shape of the pores.

10

TEST METHODS

Basis Weight was determined by ASTM D-3776, which is hereby incorporated by reference and reported in g/m².

15 Porosity was calculated by dividing the basis weight of the sample in g/m² by the polymer density in g/cm³ and by the sample thickness in micrometers, multiplying by 100 and subsequently subtracting from 100%, i.e., percent porosity=100-basis weight/(density×thickness)×100.

20 Fiber Diameter was determined as follows. Ten scanning electron microscope (SEM) images at 5,000X magnification were taken of each fine fiber layer sample. The diameter of eleven (11) clearly distinguishable fine fibers were measured from the photographs and recorded. Defects were not included (i.e., lumps of fine fibers, polymer drops, intersections of fine fibers). The average (mean) fiber diameter for each sample was calculated.

25 Thickness was determined by ASTM D1777, which is hereby incorporated by reference, and is reported in mils and converted to micrometers.

30 Frazier Air Permeability is a measure of air permeability of porous materials and is reported in units of ft³/min/ft². It measures the volume of air flow through a material at a differential pressure of 0.5 inches (12.7 mm) of the water. An orifice is mounted in a vacuum system to restrict flow of air through sample to a measurable amount. The size of the orifice depends on the porosity of the material. Frazier permeability is measured

in units of ft³ /min/ft² using a Sherman W. Frazier Co. dual manometer with calibrated orifice.

Mean Flow Pore Size was measured according to ASTM Designation E 1294-89, "Standard Test Method for Pore Size

5 Characteristics of Membrane Filters Using Automated Liquid Porosimeter" which approximately measures pore size characteristics of membranes with a pore size diameter of 0.05 µm to 300 µm by using automated bubble point method from ASTM Designation F 316 using a capillary flow porosimeter (model number CFP-34RTF8A-3-6-L4, Porous Materials, Inc.

10 (PMI), Ithaca, N.Y.). Individual samples (8, 20 or 30 mm diameter) were wetted with low surface tension fluid (1,1,2,3,3,3-hexafluoropropene, or "Galwick," having a surface tension of 16 dyne/cm). Each sample was placed in a holder, and a differential pressure of air was applied and the fluid removed from the sample. The differential pressure at which wet flow

15 is equal to one-half the dry flow (flow without wetting solvent) is used to calculate the mean flow pore size using supplied software.

Wetting time (seconds) is measured by dispensing 1 µl of fluid (water or 20% KOH solution) onto the sample surface and timing how long it takes to soak into the sample. The fluid is dispensed by an automatic

20 syringe that delivers the same amount each time. The wetting time is reported in seconds.

Electrolyte Absorption is measured by soaking 10 cm x 10 cm samples in 35% KOH for 10 minutes. The weight of the samples is measured before and after soaking in 35% KOH and electrolyte absorption

25 is calculated with the formula:

$$\%Elec.Abs. = \frac{(W_f - W_i)}{W_i} \times 100$$

Where W_f , and W_i are final weight and initial weight of the sample in grams.

Contact angle is measured with a VCA2500xe (VCA=Video Contact

30 Angle) made by Advanced Surface Technologies (Billerica, MA). The fluid is dispensed by an automatic syringe that delivers the same amount each

time. The camera takes the picture and the software measures the contact angle from the picture. The contact angle is reported in degrees.

EXAMPLES

5 Siloxyl polyether surfactant (Silwet, GE Silicones, Evansville, IN) was added to a spinning solution of DuPont Nylon 66-FE 3218 polymer in formic acid. Webs were electroblown using the procedure given in publication WO 03/080905 and produced the web properties listed in Table 1 (individual examples + control).

10

TABLE 1

Surfactant Loading in Fibers (wt %)	Basis Weight (g/m ²)	Mean Fiber Diameter (nm)	Web Thickness (mm)	Air Permeability (cfm/ft ²)
0.0	30.0	360	0.152	6.02
0.42	29.5	446	0.162	5.52
0.83	28.9	453	0.162	5.56
1.25	30.7	447	0.165	5.7

Table 2 shows the wetting behavior of the nanoweb samples containing 0 wt%, 0.42 wt%, 0.83 wt% and 1.25 wt% Silwet, respectively.

15 The wetting speed was measured in water and 20% KOH. Two measurements were done for each sample and both measurements are reported in Table 2, separated by commas. The results clearly show that the samples with surfactant wet faster than the ones without any surfactant. In this case 0.83 wt% or above of Silwet in the fibers was 20 shown to be an effective amount.

25

Table 2 also shows the percentage electrolyte absorption of the nanoweb samples containing 0 wt%, 0.42 wt%, 0.83 wt%, and 1.25 wt% Silwet, respectively. The electrolyte absorption was measured in 35% KOH. The electrolyte absorption by nanowebs was significantly higher for samples with surfactant. In this case 0.83 wt% or above of Silwet in the fibers was shown to be an effective amount.

TABLE 2

Surfactant Loading in Fibers (wt %)	Electrolyte absorption (%)	Wetting time of Water (Seconds)	Wetting Time 20% KOH (Seconds)
0.0	274	4, 5	Not wetting
0.42	285	1, 1	7, 11
0.83	572	< 1, < 1	3, 4
1.25	458	Instant	< 1, < 1

Table 3 shows the contact angle of the nanoweb samples containing 0, 0.42, 0.83, and 1.25 wt% Silwet, respectively. The contact angle was measured with water and 20% KOH, respectively. Higher contact angle means poor wet-ability of nanowebs in that particular solvent. Samples with higher level of surfactants showed lower contact angles. The wetting was very fast ("instant") for samples with greater than 0.83 wt% surfactant and thus was not possible to get a read on contact angle. The data clearly shows that the wetting properties of samples with surfactant (> 0.83 wt%) was very good.

TABLE 3

Surfactant Loading in Fibers (wt %)	Contact Angle Water (degrees)	Contact Angle 20% KOH (degrees)
0.0	124, 134	134, 138
0.42	Instant	132, 134
0.83	Instant	Instant
1.25	Instant	Instant

CLAIMS

We claim

1. An alkaline battery having a separator comprising a porous fine fiber layer of wet-able polymeric fibers having a mean diameter in the range from about 50 nm to about 3000 nm, wherein the porous fine fiber layer permanently wets with strong alkaline electrolytes.
2. The battery of claim 1 wherein the fiber polymer comprises an effective amount of a surfactant embedded therein.
- 10 3. The battery of claim 1 wherein the fibers are produced from a spinning solution of polymer by electrospinning or electroblowing and surfactant is added in the spinning solution.
- 15 4. The battery of claim 2 wherein the surfactant is present at a level of about 0.4% to about 20% by weight of the polymer.
5. The battery of claim 2 wherein the surfactant is present at a level of about 1% to about 5% by weight of the polymer.
- 20 6. The battery of claim 2 wherein the surfactant is a nonionic surfactant.
7. The battery of claim 6 wherein the nonionic surfactant is selected from the group consisting of an alkylated polyether surfactant and a siloxyl polyether surfactant.
- 25 8. The battery of claim 1 wherein the fibers comprise a polymer selected from the group consisting of aliphatic polyamide, semi-aromatic polyamide, polyvinyl alcohol, cellulose, polyethylene terephthalate, polypropylene terephthalate, polybutylene terephthalate, polysulfone, polyvinylidene fluoride, polyvinylidene fluoride-hexafluoropropene, polyacrylonitrile, polypropylene, polyethylene, polymethyl methacrylate,

polymethyl pentane, polyphenylene sulfide, polyacetyl, polyurethane, aromatic polyamide and blends, mixtures and copolymers thereof.

9. The battery of claim 1 wherein the porous fine fiber layer has a
5 mean flow pore size of between about 0.01 μm and about 15 μm .

10. The battery of claim 1 wherein the porous fine fiber layer has a thickness of between about 0.1 mil (0.0025 mm) and about 12 mil (0.3 mm).

10

11. The battery of claim 1 wherein the porous fine fiber layer has a basis weight of between about 1 g/m^2 and about 90 g/m^2 .

12. The battery of claim 1 wherein the fibers have a mean diameter
15 between about 50 nm and about 1000 nm.

13. The battery of claim 1 wherein the polymer is cross linked.

14. The battery of claim 1 wherein the separator comprises multiple
20 porous fine fiber layers.

15. The battery of claim 1 wherein the separator comprises multiple porous fine fiber layers comprising differing polymers.

25 16. The battery of claim 1 wherein the separator comprises multiple porous fine fiber layers having differing characteristics selected from the list consisting of thickness, basis weight, pore size, fiber size, porosity, air permeability, ionic resistance and tensile strength.

30 17. The alkaline battery of claim 1 wherein the alkaline battery is a Zn--MnO₂ primary, Zn--MnO₂ secondary, Zn-Air, Zn--AgO, Ni--Zn, Cd-AgO, Zn--HgO, Cd--HgO Ni--Cd, Ni-Metal Hydride, or Ni--H₂ battery.

18. The alkaline battery of claim 2, wherein the polymeric fibers are further coated with surfactant.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2008/007283

A. CLASSIFICATION OF SUBJECT MATTER
INV. H01M2/16 H01M10/24

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, IBM-TDB, FSTA, COMPENDEX, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2007/041312 A (DU PONT [US]; ARORA PANKAJ [US]; FRISK SIMON [US]; ZHANG LU [US]) 12 April 2007 (2007-04-12) page 8, line 14 - page 9, line 27 page 7, line 8 - line 19 claims 1,7,11,13,14,17,18	1-3,6, 8-18
X	US 2005/042518 A1 (KINN LARRY L [US] ET AL) 24 February 2005 (2005-02-24) paragraphs [0006] - [0010], [0020], [0024] - [0026], [0029], [0030], [0032], [0034], [0039], [0050], [0053], [0064], [0066], [0067]	1-8, 10-12, 14,16-18
A	US 3 870 567 A (PALMER NIGEL INNES ET AL) 11 March 1975 (1975-03-11) the whole document	1-18

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

15 September 2008

22/09/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Götz, Heide

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/US2008/007283

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
WO 2007041312	A 12-04-2007	EP US	1941566 A1 7112389 B1	09-07-2008 26-09-2006
US 2005042518	A1 24-02-2005	NONE		
US 3870567	A 11-03-1975	AR CA DE FR GB IT NL	204316 A1 1020225 A1 2363915 A1 2211763 A1 1461388 A 1001308 B 7317378 A	22-12-1975 01-11-1977 04-07-1974 19-07-1974 13-01-1977 20-04-1976 25-06-1974