



(51) International Patent Classification:

B01D 39/16 (2006.01) B03C 3/34 (2006.01)

(21) International Application Number:

PCT/US2018/024434

(22) International Filing Date:

27 March 2018 (27.03.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/476,894 27 March 2017 (27.03.2017) US

(71) Applicant: PURDUE RESEARCH FOUNDATION

[US/US]; 1801 Newman Rd., West Lafayette, Indiana 47906 (US).

(72) Inventors: SMITH, Anderson; 15402 Lost Valley Drive,

Fort Wayne, Indiana 46845 (US). HUANG, Andrew; 242 S. Salisbury St, Apt. 9, West Lafayette, Indiana 47906 (US). MEHAN, Sushant; 410 Steely St., Apt. 4, West Lafayette, Indiana 47906 (US). SAADAT, Samaneh; 3376 Peppermill Dr., Apt 2C, West Lafayette, Indiana 47906 (US).

(74) Agent: YAN, Liang Zeng; 1801 Newman Rd., West

Lafayette, Indiana 47906 (US).

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every

kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: SOY BASED FILTRATION SYSTEM

(57) Abstract: The present application relates generally to filter media useful for manufacturing air filters for residential and commercial office's Heating, Ventilation, and Air Conditioning (HVAC), particularly to filters and filter media comprising soybean-based materials. The present invention provides an inexpensive, effective, environmentally friendly, and sustainable media for manufacturing HVAC air filters for residential and commercial buildings.



SOY BASED FILTRATION SYSTEM

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] The present U.S. patent application is related to and claims the priority benefit of U.S. Provisional Patent Application Serial No. 62/476,894, filed March 27, 2017, the contents of which are hereby incorporated by reference in their entirety into the present disclosure.

TECHNICAL FIELD

[0002] The present application relates generally to filter media useful for manufacturing air filters for residential and commercial office's Heating, Ventilation, and Air Conditioning (HVAC), particularly to filters and filter media comprising soybean-based materials.

BACKGROUND

[0003] This section introduces aspects that may help facilitate a better understanding of the disclosure. Accordingly, these statements are to be read in this light and are not to be understood as admissions about what is or is not prior art.

[0004] Home and commercial office's Heating, Ventilation, and Air Conditioning (HVAC) filters are a necessity in order to ensure good indoor air quality within both residential and commercial buildings. They continuously clean the air, providing for a safe and healthy environment in which people can live and work. Without air filters, particulate matter, allergens, and mold would accumulate within buildings, making the air both unpleasant and unsafe to breathe. Any air filter is a step up from no air filter; yet, a problem exists in the HVAC air filter market. Current offerings are either relatively effective when it comes to filtration but are expensive, or relatively cheap but have poor filtration efficiency. Additionally, many air filters are made from petroleum-based products, thus presenting

environmental hazards. There are unmet needs for an environmentally friendly, sustainable and affordable materials for manufacturing HVAC filters.

SUMMARY OF THE INVENTION

[0005] The present invention provides an inexpensive, effective, and sustainable HVAC air filter. The filter disclosed herein is, in one embodiment, a soy-based HVAC (Heating, Ventilation, and Air Conditioning) filter for use in residential and commercial applications. Testing, based upon the American Society of Heating, Refrigerating, and Air-Conditioning Engineers (ASHRAE) Standard 52.2, has shown that an example filter is about 15% more effective than current HVAC filters available on the market. Additionally, the disclosed filter is less expensive to manufacture than currently existing HVAC filters. The filter disclosed is made from renewable resources and is biodegradable, making it much more environmentally friendly than currently existing products. The three aforementioned traits - high efficiency, low cost, and environmental friendliness - are all possible due to the unique properties of soy within the product. Furthermore, the product has experimentally gone through cold plasma treatment, which may extend the life of the product and at the same time allow for an even higher filtration efficiency due to the resultant surface charge held by the soy proteins.

[0006] While the disclosed embodiment is adapted for use in the HVAC sector, the soy-based filtration technology disclosed herein could be easily applied to numerous other industries going forward. These include, but are not limited to, the industrial and agricultural air filtration industries. Due to the physical properties of the product, simple alterations would also enable it to be applied to a wide number of other uses for paper and cardboard products such as paper towels, cardboard boxes, disposable coffee cup sleeves, and even wine corks.

DETAILED DESCRIPTION

[0007] For the purposes of promoting an understanding of the principles of the present disclosure, reference will now be made to the embodiments illustrated in the drawings, and specific language will be used to describe the same. It will nevertheless be understood that no limitation of the scope of this disclosure is thereby intended.

[0008] As used herein, the following terms and phrases shall have the meanings set forth below. Unless defined otherwise, all technical and scientific terms used herein have the same meaning as commonly understood to one of ordinary skill in the art.

[0009] In the present disclosure the term “about” can allow for a degree of variability in a value or range, for example, within 20%, within 10%, within 5%, or within 1% of a stated value or of a stated limit of a range.

[0010] In the present disclosure the term “substantially” can allow for a degree of variability in a value or range, for example, within 80%, within 90%, within 95%, or within 99% of a stated value or of a stated limit of a range. Soy and soybean are used exchangeably herein.

[0011] Filter media as disclosed herein refers to material compositions of a filter, or a component of a filter. And more specifically, the starting or intermediate materials used to prepare consumable filters, including Heating, Ventilation, and Air Conditioning air filters for use in residential and commercial applications.

[0012] In some illustrative embodiments, this present invention relates to a filter media comprising a component of milled whole soybean material and a component of recyclable materials.

[0013] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said milled whole soybean material accounts for about 1% to about 90%.

[0014] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said milled whole soybean material accounts for about 5% to about 80%.

[0015] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said milled whole soybean material accounts for about 10% to about 70%.

[0016] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said milled whole soybean material accounts for about 10% to about 60%.

[0017] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said recyclable material is paper or synthetic fibrous material.

[0018] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein the said recyclable material is recycled paper.

[0019] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said recyclable material is recycled synthetic fibrous material.

[0020] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said recyclable material accounts for about 1% to about 90%.

[0021] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said recyclable material accounts for about 5% to about 80%.

[0022] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said recyclable material accounts for about 5% to about 70%.

[0023] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said recyclable material accounts for about 5% to about 50%.

[0024] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said recyclable material accounts for about 5% to about 40%.

[0025] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said recyclable material accounts for about 10% to about 30%.

[0026] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said filter media is used to prepare an air filter for residential or commercial heating, ventilation and air conditioning.

[0027] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said filter media is used to manufacture an air filter.

[0028] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said filter media is used to manufacture an air filter, wherein said filter has a Minimum Efficiency Reporting Value (MERV) ranging from about 3 to about 12.

[0029] In some illustrative embodiments, this present invention relates to a filter media disclosed herein, wherein said filter media is used to manufacture an air filter, wherein said filter is further exposed to cold plasma treatment.

[0030] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material.

[0031] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said filter is further exposed to cold plasma treatment.

[0032] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said milled whole soybean material accounts for about 1% to about 90%.

[0033] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said milled whole soybean material accounts for about 10% to about 80%.

[0034] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said recyclable material is paper or synthetic fibrous material.

[0035] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said recyclable material is recycled paper.

[0036] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said recyclable material is recycled synthetic fibrous material.

[0037] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said recyclable material accounts for about 1% to about 90%.

[0038] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said recyclable material accounts for about 5% to about 80%.

[0039] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said recyclable material accounts for about 10% to about 70%.

[0040] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said recyclable material accounts for about 10% to about 60%.

[0041] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said milled whole soybean material accounts for about 10% to about 50%.

[0042] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said milled whole soybean material accounts for about 10% to about 40%.

[0043] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said milled whole soybean material accounts for about 10% to about 30%.

[0044] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said milled whole soybean material accounts for about 10% to about 25%.

[0045] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said milled whole soybean material accounts for about 10% to about 20%.

[0046] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said filter is an air filter for residential or commercial heating, ventilation and air conditioning.

[0047] In some illustrative embodiments, this present invention relates to an air filter comprising milled whole soybean material and a recyclable material, wherein said filter has a Minimum Efficiency Reporting Value (MERV) ranging from about 3 to about 12.

[0048] Plasma is often considered as the fourth state of matter in addition to solid, liquid and gas phases. A plasma is a partially ionized gas in which ions and electrons are present as well as radicals and molecules in an excited state, which include both “hot” plasmas wherein all species of the plasma have appropriately the same (high) temperature, and “cold” or “non-equilibrium” plasmas wherein plasmas have a high electron temperature but a low ion or gas temperature, with the latter being more widely used in modern manufacturing process. Cold plasma discharges can be generated by stationary and pulsed direct current (DC) or alternating current (AC) electrical fields. Various electrical power supplies can be used to generate the plasma discharges. Many commercial vendors manufacture and supply all kinds of instruments serving various purposes of cold plasmas, including surface treatment of goods, such as Dyne Technology (UK), 3DT LLC (Germantown, WI), and Tri-Star Technologies (El Segundo, CA).

[0049] HVAC air filters are rated based on a scale known as the MERV (Minimum Efficiency Reporting Value) scale. MERV ranks filters from 1 to 20, with 1 being the least effective and 20 being the most. However, 12 is the maximum used for residential buildings, with 13 - 20 being reserved settings requiring extreme cleanliness, such as a surgery room.

[0050] A search of patent databases identified patent CN205549922-U and patent CN105622768-A. The first pertains to a water filter recycling machine. It describes a water filter and includes an animated soy straw layer within the filtration media. The latter of the

two is a filtration cake used to extract plant soybean starch. This process has the purpose of filtering the starch from soybean itself.

[0051] A study published by Washington State University regarding a filtration media also pertains soy. However, the media developed at Washington State has a sole application to super high efficiency filters, as opposed to HVAC air filters. The type of extremely high efficiency filtration discussed by Washington State does not target an application to the HVAC industry as a dense filtration media because this would put too much strain on an HVAC system due to the high-pressure drop created by the lack of porosity within the filter. Furthermore, the media developed by Washington State uses only highly refined soy protein isolate, as opposed to whole soy (H. Souzandeh, et al., *ACS Sustainable Chem. Eng.*, **2017**, 5 (7), pp 6209–6217; H. Souzandeh, et al., *ACS Appl. Mater. Interfaces*, **2016**, 8 (31), pp 20023–20031).

[0052] As mentioned above, HVAC air filters are rated based on a scale known as the MERV (Minimum Efficiency Reporting Value) scale. MERV ranks filters from 1 to 20, with 1 being the least effective and 20 being the most. However, 12 is the maximum used for residential buildings. As such, testing between a filter as disclosed herein and a MERV 12 HVAC filter was carried out based upon the American Society of Heating, Refrigerating, and Air Conditioning Engineers (ASHRAE) standard 52.2, which is a standardized testing procedure used to determine the overall efficiency of HVAC filters. The testing was conducted at Purdue University. After numerous trials at seven different flow rates of air, the data showed that the filter disclosed herein outperformed a MERV 12 HVAC filter by 14.67%.

[0053] When it comes to cost of production, the cost to produce a filter as described herein is expected to be higher than that of a MERV 2 filter and slightly higher than that of a MERV 7

filter, but much lower than that of a MERV 12 filter. As mentioned above, the filter disclosed herein outperforms all three of the aforementioned filters.

[0054] Additionally, the filter disclosed herein is a soy and recycled paper-based product. Thus, it is both biodegradable and sustainably sourced. Currently existing high-efficiency filtration products are typically made from synthetic fibrous material or glass fiber, both of which are nonrenewable resources. As such, the disclosed filter provides a much more environmentally friendly filter than such existing high-efficiency filters.

[0055] The disclosed filters, which provide high filtration efficiency, low price point, and environmental friendliness, are well-suited for use by hotels and families that replace their filters regularly and are looking for cost savings while maintaining a high filtration efficiency and filter sustainability. However, the disclosed filters could be used or adapted for use in nearly all HVAC systems in various settings and provides substantial advantages as summarized below:

- High Filtration Efficiency
 - Soy creates small pore spaces, allowing for filtration of fine particulate matter
 - Amino groups within the soy proteins trap additional pollutants not captured by normal filters
- Low Cost
 - Soy is a cheap raw material
 - Minimal processing is required to make soy into the final FiltraSoy filtration media
- Environmentally Friendly
 - Soy is a renewable resource

- Soy allows the main filtration media to be biodegradable
- Cold Plasma Treatment
 - The high protein content within soy allows it to effectively hold the surface charge achieved through cold plasma treatment.

[0056] In addition to HVAC applications, the filter described herein could also be adapted for applications in the automotive, industrial, and agricultural industries.

[0057] The process of producing the disclosed filters is relatively simple. The media itself is made in a fashion that is similar to a traditional paper making procedure. Care was taken to provide a media that was a smooth blend of recycled paper and soy material.

[0058] A general flowchart shows the overall process of producing the filtration media, some of the parameters include:

1. Type of recycle paper used
2. NaOH percentage mixed with the recycled paper
3. Grinding size for the soybean
4. NaOH percentage mixed with the soybean
5. Boiling temperature/time for the soybean and NaOH mixture
6. Overall ration of paper and soybean

[0059] The creation of the filtration media results from the chemical and physical development of a soy-based mixture and a recycled paper-based mixture, the combination of these two mixtures, and then final physical processing in order to achieve the desired product form.

This process is outlined below: First, paper was cut into designated sizes; namely, 1" squares so that the fiber material could be incorporated with soybean to form the base structure for the filter. Next, soybean was ground and milled, and a strong base was added to break down

parts of the soybean which may decompose. Next, this slurry was washed to remove the base, and the mixture was incorporated to form a consistent slurry. This slurry was then sieved to form a filter, with pressure added to dry out the mixture and to form a homogeneous material.

[0060] Generation of the Filtration Media. From a technical aspect, the creation of the filtration media results from the chemical and physical development of a soy-based mixture and a recycled paper-based mixture, the combination of these two mixtures, and then final physical processing in order to achieve the desired product form.

1. Prepare recycled paper

- a) Cut recycled newspaper into 1 inch squares
- b) Combine the cut newspaper in a vat with just enough water to cover it
- c) Add NaOH (sodium hydroxide) to the mixture in a 1:4 ratio to the dry mass of the paper
- d) Allow the mixture to sit for 1 hour
- e) Rinse the mixture thoroughly to remove all NaOH

2. Prepare the soy mixture

- a) Grind soy into a fine powder (this was done with a Seedburo Equipment Company 60hp grain mill on the fine #5 setting)
- b) Combine the soy in a vat with just enough water to cover it
- c) Add NaOH to mixture in a 1:9 ratio to the dry mass of the soy
- d) Heat the mixture to a boil
- e) Boil the mixture for 1 hour
- f) Rinse the mixture thoroughly to remove all NaOH

3. Blend the paper mixture with the soy mixture

- a) Combine the rinsed soy with the rinsed paper

*This should be done with 91% soy, based upon its dry mass and 9% recycled paper, based upon its dry mass.

- b) Blend the two mixtures together on a high setting in a blender, adding water as necessary
- c) Once a fine, smooth mixture is attained, pour the mixture into a 16 inch x 24 inch tub

4. Sieve the paper

- a) Submerge a fine wire screen into the tub, lifting in gently to pull the solid material from the tub. Strive to achieve as uniform a layer as possible as this will be the filtration media itself
- b) Once a uniform layer has been gathered, place a 9 inch x 12 inch piece of felt on top of the layer on the screen
- c) Invert the screen, so that the media is sitting only on the felt
- d) Remove the screen
- e) Lay the media and felt on a flat, hard surface
- f) Press the media and felt repeatedly, using an absorbent material until most of the water has been extracted from the media
- g) Allow the media to dry for 24 hours
- h) After 24 hours, the media can be removed from the felt and is now ready for utilization

[0061] Materials used in this process to produce the exemplary embodiment of the soy based filter is provided below: NaOH (Amazon); Soy Cloth (Simplifi Fabric); Paper-Making

Physical Supplies (Walmart, Home Depot, Salvation Army); Air Filters for comparative testing and other supplies (Menards); Product packing and logo design (Purdue University).

[0062] Regarding filtration efficiency, the soybean content in the product decreases the pore space within the paper, allowing the air filter to trap more particulate matter. Additionally, the protein within soy contains 18 different amino groups, which allow the filter to capture many pollutants that are not typically captured through the physical filtration process that takes place in traditional air filters. These include very fine particulate matter and many gaseous pollutants. Furthermore, using cold plasma as a surface treatment sterilizes the surface of the filter and provides an induced surface charge due to the high protein content within the soybean components of the filter. Traditional filters on the market would not be able to hold this charge as effectively due to their low protein content. The product has undergone cold plasma treatment successfully, but in-depth testing as to a quantifiable improved performance of the cold plasma treated product has yet to be determined. The untreated product already outperforms high efficiency HVAC filters by 14.67 percent. With cold plasma treatment the protein groups within filter become charged and are expected to remove pollutants even more effectively than they already do. Due to the cold plasma treatment and resulting sterilization of the filter, the filter is expected to last longer and be less affected by decomposition.

[0063] The soy-based nature of the product also leads to its low price. Soy is a relatively cheap raw material input, thus saving money when compared to the other filter materials such as fiberglass or a synthetic material. Additionally, the process involved in making the filter is relatively simple with soybean and recycled paper being its two principal ingredients. It requires little processing when compared to the fiberglass and synthetic filters currently on

the market, and contributes to the low cost of production for the soy based filter described herein.

[0064] Additionally, the filter described herein is made of natural and renewable components (soy and recycled paper). These ingredients will decompose rapidly in a natural environment, thus furthering the sustainability of the product.

[0065] The filtration media of the filter disclosed herein is roughly 90.9% whole milled soybean and roughly 9.1% recycled paper by mass. As discussed above, these ingredients have been selected for their low cost, physical properties, and environmental friendliness.

[0066] The longevity and ability of the filter to withstand humidity has not been tested at this time. However, a cold Plasma treatment - which slows decomposition within organic matter - can be applied to the product, which should extend its lifespan due to the organic nature of the filter media. Alternatively, the product would also be able to be chemically treated to help it withstand humidity.

[0067] The general framework or structure holding filter media is similar to that of a conventional HVAC filter, e.g., a MERV 7 filter. The primary distinction being the filter media that goes into the filter itself. The two components of the filter media for the filter described herein are whole soybeans and recycled paper.

[0068] The production of the product itself is relatively simple. The recycled paper can be processed in a large-scale commercial shredder, and simply soaked in a large vat with NaOH. The soy, on the other hand, can be milled in a traditional milling facility and heated with the NaOH in a temperature controlled vat. The two mixtures must then be transported to a separate vat and blended together. After this, the paper can simply be processed in the traditional manner. The entire process would be able to take place at a paper mill. Assembly

would then be able to take place at any regular filter manufacturing facility, as no special treatment is required post development of the media. The assembly of the filter, once the soy derived filter media has been produced, would be similar to that of a conventional HVAC filter. As such, the filter would be able to be produced in currently existing facilities with ease.

[0069] The exemplary soy derived filter described above has a number of advantages, including:

FiltraSoy may be a successful product due to four main characteristics:

- 1) It is 14.67 percent more efficient than current residential and commercial level filters offered in the market
- 2) It has a lower price point than currently existing products, yet still maintains extremely high profit margins
- 3) It is more environmentally friendly than products currently available
- 4) It is the first and only filter that has been successfully treated with cold plasma, a treatment that is expected to extend the life and effectiveness of the filtration media due to the positive interaction between the high protein content within soy and the treatment

[0070] As a whole, FiltraSoy may have a substantial impact within both the environmental and human health realms. Regarding the environment, FiltraSoy offers an environmentally friendly solution to air filtration within the marketplace. Most air filters are made from non-renewable resources and do not degrade naturally after use. FiltraSoy, on the other hand, is made of renewable resources and breaks down naturally after use, allowing the product to simply be composted as opposed to sitting in a landfill. The impact of this is heightened by the fact that air filter are a disposable good which is replaced on a regular basis. On the human

health side, FiltraSoy has a higher filtration efficiency than competing products within the residential sector. Additionally, the cost of FiltraSoy is lower than these competing products, thus providing a highly efficient filter, capable of competing with hypo-allergenic MERV 12 filters, at an affordable price.

[0071] Testing and Calculations. Testing based on ASHRAE Standard 52.2 was conducted with dust sourced from a Frankfort, IN grain elevator and sieved through a #140 sieve to achieve a size congruent with particles able to be suspended in the air. Summary of results, cost of production and increased demand of soy calculations.

[0072] Test FiltraSoy Filtration Media

Dust Type - Dust sourced from a Frankfort, IN grain elevator and sieved through a #140 sieve to achieve a size congruent with that of particles suspended in the air						
Air Flow Rate (m/s)	Mass of Dust (g)	Weight of Boat, Initial (g)	Weight of Boat, Final (g)	Filter + Holder, Initial (g)	Filter + Holder, Final (g)	Change in Filter Mass (g)
0.60	0.025	1.594	1.594	13.533	13.554	0.021
1.25	0.025	1.594	1.594	13.509	13.526	0.017
1.50	0.025	1.594	1.594	13.488	13.507	0.019
1.90	0.025	1.594	1.594	13.484	13.511	0.027
1.90	0.025	1.594	1.594	13.523	13.541	0.018
1.90	0.025	1.594	1.594	13.555	13.574	0.019
1.90	0.025	1.594	1.594	13.476	13.491	0.015
1.90	0.025	1.594	1.594	13.518	13.535	0.017
1.90	0.025	1.594	1.594	13.55	13.567	0.017
2.50	0.025	1.594	1.594	13.572	13.592	0.020
3.20	0.025	1.594	1.594	13.569	13.589	0.020
3.80	0.025	1.594	1.594	13.552	13.571	0.019
					Average	0.019

[0073] Test Current Commercial MERV 12 Filter

Dust Type - Dust sourced from a Frankfort, IN grain elevator and sieved through a #140 sieve to achieve a size congruent with that of particles suspended in the air						
Air Flow Rate (m/s)	Mass of Dust (g)	Weight of Boat, Initial (g)	Weight of Boat, Final (g)	Filter + Holder, Initial (g)	Filter + Holder, Final (g)	Change in Filter Mass (g)
0.60	0.025	1.594	1.594	13.504	13.519	0.015
1.25	0.025	1.594	1.594	13.509	13.525	0.016
1.50	0.025	1.594	1.594	13.509	13.526	0.017
1.90	0.025	1.594	1.594	13.504	13.521	0.017
1.90	0.025	1.594	1.594	13.513	13.527	0.014
1.90	0.025	1.594	1.594	13.499	13.514	0.015
1.90	0.025	1.594	1.594	13.51	13.524	0.014
1.90	0.025	1.594	1.594	13.501	13.519	0.018
1.90	0.025	1.594	1.594	13.506	13.519	0.013
2.50	0.025	1.594	1.594	13.5	13.517	0.017
3.20	0.025	1.594	1.594	13.508	13.523	0.015
3.80	0.025	1.594	1.594	13.514	13.528	0.014
					Average	0.015

[0074] Summary of Testing Results

FiltraSoy Filtration Efficiency (%)	76.33
MERV 12 Filtration Efficiency (%)	61.67
Percentage Efficiency Improvement of FiltraSoy over a MERV 12 Filter (%)	14.67

[0075] While this invention has been described as having an exemplary design, the present invention may be further modified within the spirit and scope of this disclosure. This

application is therefore intended to cover any variations, uses, or adaptations of the invention using its general principles.

[0076] Those skilled in the art will recognize that numerous modifications can be made to the specific implementations described above. The implementations should not be limited to the particular limitations described. Other implementations may be possible.

[0077] While the inventions have been illustrated and described in detail in the drawings and foregoing description, the same is to be considered as illustrative and not restrictive in character, it being understood that only certain embodiments have been shown and described and that all changes and modifications that come within the spirit of the invention are desired to be protected. It is intended that the scope of the present methods and apparatuses be defined by the following claims. However, it must be understood that this disclosure may be practiced otherwise than is specifically explained and illustrated without departing from its spirit or scope. It should be understood by those skilled in the art that various alternatives to the embodiments described herein may be employed in practicing the claims without departing from the spirit and scope as defined in the following claims.

CLAIMS:

1. A filter media comprising milled whole soybean material and a recyclable material.
2. The filter media according to claim 1, wherein said milled whole soybean material accounts for about 1% to about 90%.
3. The filter media according to claim 1, wherein said milled whole soybean material accounts for about 5% to about 80%.
4. The filter media according to claim 1, wherein said milled whole soybean material accounts for about 10% to about 70%.
5. The filter media according to claim 1, wherein said milled whole soybean material accounts for about 10% to about 60%.
6. The filter media according to claim 1, wherein said recyclable material is paper or synthetic fibrous material.
7. The filter media according to claim 1, wherein said recyclable material is recycled paper.
8. The filter media according to claim 1, wherein said recyclable material is recycled synthetic fibrous material.
9. The filter media according to claim 1, wherein said recyclable material accounts for about 1% to about 90%.
10. The filter media according to claim 1, wherein said recyclable material accounts for about 5% to about 80%.
11. The filter media according to claim 1, wherein said recyclable material accounts for about 5% to about 70%.
12. The filter media according to claim 1, wherein said recyclable material accounts for about 5% to about 50%.

13. The filter media according to claim 1, wherein said recyclable material accounts for about 5% to about 40%.
14. The filter media according to claim 1, wherein said recyclable material accounts for about 10% to about 30%.
15. The filter media according to claim 1, wherein said filter media is used to prepare an air filter for residential or commercial heating, ventilation and air conditioning.
16. An air filter manufactured using the filter media of claim 1.
17. The filter according to claim 15, wherein said filter has a Minimum Efficiency Reporting Value (MERV) ranging from about 3 to about 12.
18. The filter according to claim 15, wherein said filter is further exposed to cold plasma treatment.
19. An air filter comprising milled whole soybean material and a recyclable material.
20. The filter according to claim 19, wherein said filter is further exposed to cold plasma treatment.
21. The filter according to claim 19, wherein said milled whole soybean material accounts for about 1% to about 90%.
22. The filter according to claim 19, wherein said milled whole soybean material accounts for about 10% to about 80%.
23. The filter according to claim 19, wherein said milled whole soybean material accounts for about 10% to about 60%.
24. The filter media according to claim 19, wherein said recyclable material is paper or synthetic fibrous material.

25. The filter media according to claim 19, wherein said recyclable material is recycled paper.
26. The filter media according to claim 19, wherein said recyclable material is recycled synthetic fibrous material.
27. The filter media according to claim 19, wherein said recyclable material accounts for about 1% to about 90%.
28. The filter media according to claim 19, wherein said recyclable material accounts for about 5% to about 80%.
29. The filter media according to claim 19, wherein said recyclable material accounts for about 10% to about 70%.
30. The filter media according to claim 19, wherein said recyclable material accounts for about 10% to about 50%.
31. The filter according to claim 19, wherein said filter is an air filter for residential or commercial heating, ventilation and air conditioning.
32. The filter media according to claim 19, wherein said filter has a Minimum Efficiency Reporting Value (MERV) ranging from about 3 to about 12.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 18/24434

A. CLASSIFICATION OF SUBJECT MATTER

IPC(8) - B01D 39/16, B03C 3/34 (2018.01)

CPC - B01D 2239/0428, B01D 2239/0435, B01D 2239/0622

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

See Search History Document

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

See Search History Document

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

See Search History Document

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X --- Y	LIU et al. "Soy protein isolate/bacterial cellulose composite membranes for high efficiency particulate air filtration", November 24, 2016, Composites Science and Technology, Vol. 138: pgs. 124-133 Pg. 125, Full Para [3]; Pg. 130, Full Para [1]; Pg. 132, Full Para [1]; Table 3	1-5, 9-17, 19, 21-23, 27-32 ----- 6-8, 18, 20, 24-26
Y --- A	GALLEGOS et al. "Bacterial Cellulose: A Sustainable Source to Develop Value-Added Products - A Review", May 2016, Bioresources, Vol. 11(2): pgs. 1-16 Pg. 1, Abstract; Pg. 1, Para [1]; Pg. 2, Para [1]; Pg. 9, Para [1]; Fig. 1	6-7, 24-25 ----- 1, 19
Y	LEE et al. "On the use of nanocellulose as reinforcement in polymer matrix composites", September 16, 2014, Composites of Science and Technology, Vol. 105: pgs. 15-27 Pg. 16, Full Para [4]; Pg. 19, Full Para [2]; Pg. 24, Full Para [4]; Fig. 6	8, 26
Y	ZHANG et al. "Growth-inducing effects of argon plasma on soybean sprouts via the regulation of demethylation levels of energy metabolism-related genes", February 7, 2017, Scientific Reports, Vol. 7(4): pgs. 1-12 Pg. 2, Para [1]; Pg. 2, Para [3]; Pg. 2, Para [5];	18, 20
A	HILDING, "Researchers develop environmentally friendly, soy air filter," WSU Pullman News, January 12, 2017, pgs. 1-5 Entire Document	1-32
A	SOUZANDEH et al. "Soy-Protein-Based Nanofabrics for Highly Efficient and Multifunctional Air Filtration", 2016, ACS Appl. Mater. Interfaces, Vol.8:pgs. 20023-20032 Entire Document	1-32

☒ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

21 May 2018

Date of mailing of the international search report

11 JUN 2018

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US, Commissioner for Patents
P.O. Box 1450, Alexandria, Virginia 22313-1450

Facsimile No. 571-273-8300

Authorized officer:

Lee W. Young

PCT Helpdesk: 571-272-4300
PCT OSP: 571-272-7774

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 18/24434

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2010/197185 A1 (HERBERT) 05 August 2010 (05.08.2010) Entire Document	1-32
A	CN105597575 A (UNIV BEIJING CHEMICAL TECH) 25 May 2016 (25.05.2016) Entire Document	1-32