



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C01B 37/08, B01J 29/04</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/19254 (43) International Publication Date: 22 April 1999 (22.04.99)</p>
<p>(21) International Application Number: PCT/US98/20872 (22) International Filing Date: 2 October 1998 (02.10.98) (30) Priority Data: 08/949,802 14 October 1997 (14.10.97) US (71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520-5200 (US). (72) Inventors: LIU, Zhongmin; 15 Xinghai 3rd Street, Sahekou District, Dalian 116023 (CN). GUO, Xiexian (deceased), CAI, Guangyu; 7 Xinghai 3rd Street, Sahekou District, Dalian 116023 (CN). (74) Agents: KELLER, Bradley, A. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).</p>		<p>(81) Designated States: AU, CN, JP, NO, RU, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i></p>
<p>(54) Title: SYNTHESIS OF SAPO-44 (57) Abstract A method for making molecular sieves comprising silicoaluminophosphate 44 (SAPO-44) or substantially pure SAPO-44 and a method for using the molecular sieves so prepared for oxygenate conversions to olefins.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Synthesis of SAPO-44

Field of the Invention

The present invention relates to a method of synthesizing a molecular sieve
5 comprising silicoaluminophosphate 44 (SAPO-44).

Background of the Invention

Light olefins (defined herein as ethylene propylene, butenes and mixtures thereof) serve as feeds for the production of numerous chemicals and polymers. Light olefins traditionally are produced by petroleum cracking. Due to the escalating cost of
10 crude petroleum, there are increasing efforts to develop light olefin production technologies based on alternative feedstocks. An important type of alternative feedstocks are oxygenates, such as alcohols, particularly methanol, dimethyl ether, dimethyl carbonate and ethanol. Alcohols may be produced by fermentation, or from synthesis gas derived from natural gas, petroleum liquids, carbonaceous materials,
15 including coal, recycled plastics, municipal wastes, or any organic material. Because of the wide variety of sources, alcohols, alcohol derivatives, and other oxygenates have promise as an economical, non-petroleum source for olefin production.

Because light olefins are the most sought after products from the catalytic petroleum cracking and oxygenate conversion processes, a continuing need exists for
20 new catalysts and/or new ways of making known catalysts to increase the yield of light olefin products and/or reduce the yield of unwanted products such as heavy hydrocarbons having molecular weights heavier than butane or low-valued by-products like methane.

Most catalysts that are used in the petroleum cracking and oxygenate

conversion processes are molecular-sieve containing catalysts. A molecular sieve can be zeolitic -- zeolites -- or non-zeolitic. Typical examples of zeolitic molecular sieves are zeolite A, zeolite X, zeolite Y, ZSM-5, ZSM-34, erionite, chabazite, and others. A number of non-zeolitic molecular sieves, particularly silicoaluminophosphates (SAPO's) have been synthesized and investigated as catalysts for converting oxygenates or cracking heavy hydrocarbons to light olefins.

SAPO's have a three-dimensional microporous crystalline framework of PO_2^+ , AlO_2^- , and SiO_2 tetrahedral units. Because an aluminophosphate (AlPO_4) framework is inherently neutral, the incorporation of silicon into the AlPO_4 framework by substitution generates acid sites and acidity. Controlling the quantity and location of silicon atoms incorporated into an AlPO_4 framework is important in determining the catalytic properties of a particular SAPO molecular sieve. Properly adjusted acid strength and acid site density are the keys to a good petroleum cracking or oxygenate conversion catalyst.

The catalytic properties of a SAPO catalyst also can be modified after the SAPO molecular sieve has been synthesized. This type of "post-synthesis" modification is accomplished by treating the molecular sieve with metallic, semi-metallic or non-metallic materials comprising nickel, cobalt, manganese, magnesium, barium, strontium, lanthanides, actinides, fluorine, chlorine, chelating agents, and others. The modifiers may or may not become part of the final composition of the modified catalyst.

SAPO's suitable for converting the oxygenates to light olefins include SAPO-17, SAPO-18, SAPO-34 and SAPO-44. These are small-pore molecular sieves with

pore diameter smaller than about 5 Angstroms. Small pores are believed to favor light olefins production as a result of sieving effects. For the chabazite-like SAPO-34 and SAPO-44 molecular sieves, it may be possible to incorporate more silicon atoms into the tetrahedral positions of the framework to afford greater flexibility in adjusting their acidic properties.

A hydrothermal synthesis method for making SAPO-44 was described in USA 4,440,871. The starting materials were aqueous silica sol, aluminum isopropoxide, orthophosphoric acid, and an organic template, cyclohexylamine. The synthesis was performed at 200°C for 52 hours. The SAPO-44 was obtained as the “major phase” in the product, but the product was impure. It contained unidentified materials. A similar method based on the same starting materials and added hydrofluoric acid (HF) was reported by U. Lohse *et al* , in *J. Chem. Soc. Faraday Trans.* **91**, 1155 (1995). In the presence of HF, the reaction time was shortened to five hours at 200°C. It is not clear how pure the SAPO-44 products were. Among the five products reported in the paper, at least one of them contained SAPO-35 impurity.

Because SAPO-44 can be used as a catalyst for the hydrocarbon cracking and oxygenate conversion processes, it is desirable to produce molecular sieve catalysts comprising SAPO-44 from cheaper starting materials and/or under less demanding reaction conditions. It is preferable to produce a molecular sieve product consisting essentially of SAPO-44. It is also preferable to avoid using highly corrosive reactants such as hydrofluoric acid (HF) in the molecular sieve synthesis reaction mixture.

Summary of the Invention

The present invention provides a method which comprises forming a mixture

comprising a silicon component; an organic template at a first molar ratio of greater than about 1 to an aluminum component; and a phosphorus component at a second molar ratio of less than about 1 to said aluminum component; and subjecting said mixture to conditions effective to produce molecular sieves comprising

5 silicaluminophosphate 44.

Detailed Description of the Invention

The present invention provides a method of making a molecular sieve catalyst comprising silicoaluminophosphate 44 (SAPO-44), preferably in substantially pure form.

10 The method generally comprises forming a mixture comprising a silicon component, an aluminum component, a phosphorus component, and a template. This mixture then is allowed to go through an optional aging period before being subjected to a hydrothermal treatment at an elevated temperature. The product formed from the hydrothermal treatment may be calcined further at an elevated temperature. Either

15 before or following the optional calcination, the molecular sieve product may be modified further using an ion-exchange method or other types of modifications such as steaming, to produce a molecular sieve comprising SAPO-44, preferably a molecular sieve consisting essentially of pure SAPO-44.

A number of silicon compounds and their mixtures may be used as the silicon

20 component for the method of the present invention. The silicon compounds include, but are not limited to silica sol, silica gel, colloidal silica, fumed silica, silicic acid, sodium silicate, tetraethyl silicate, tetramethyl silicate, and mixtures thereof. A preferred silicon component comprises a material selected from the group consisting

of silica sol, silica gel, colloidal silica, fumed silica, silicic acid, and mixtures thereof. These silicon compounds can be purchased from many commercial sources such as Aldrich Chemical Company, du Pont Company, Johnson Matthey Catalog Company, Merck Company and others.

5 Many aluminum compounds and their mixtures are suitable for use as the aluminum component in the present invention. The aluminum compounds include, but are not necessarily limited to aluminum oxide, boehmite, pseudo boehmite, aluminum hydroxy chloride, aluminum alkoxides such as aluminum tri-isopropoxide, aluminum tri-ethoxide, aluminum tri-n-butoxide and aluminum tri-isobutoxide, and
10 mixtures thereof. A preferred aluminum component comprises a material selected from the group consisting of boehmite and pseudo boehmite. These compounds can be purchased from many companies such as Aldrich Chemical Company, Reheis Company, Aluminum Company of America, Vista Company, and others.


The phosphorus compounds suitable for use as the phosphorus component
15 include but are not necessarily limited to orthophosphoric acid, phosphorous acid, trimethyl phosphate, triethyl phosphate, and mixtures thereof. A preferred phosphorus component comprises orthophosphoric acid (H_3PO_4). Another preferred phosphorus component comprises the commercially available 85 wt% phosphoric acid (in water). Alternately, phosphorus oxides (P_2O_3 , P_2O_4 , P_2O_5 , and $POCl_3$) may be
20 used, preferably after they are dissolved in a suitable solvent such as water. These phosphorus compounds can be purchased from companies such as Aldrich Chemical Company, Merck Company, MTM Research Chemicals, Fluka Chemie AG, and others.

A suitable organic template comprises a material selected from the group consisting of organic amines, organic ammonium salts, and mixtures thereof. A preferred organic template comprises cyclohexylamine (CHA). Another preferred template comprises a material selected from the group consisting of
5 cyclohexylammonium chloride, cyclohexylammonium bromide, other cyclohexylammonium salts, and mixtures thereof. The organic templates can be purchased from commercial sources like Aldrich Chemical Company, MTM Research Chemicals, and others.

A solvent can be mixed with the organic template before the template is added
10 to the reaction mixture. Preferably, the organic template is completely miscible with, or soluble in, the solvent. Suitable solvents include but are not necessarily limited to water, methanol, ethanol, n-propanol, iso-propanol, C₄ alcohols, ethylene glycol, 1,2-propylene glycol, 1,3-propylene glycol and mixtures thereof. A preferred solvent comprises water.

15 The aluminum component and the phosphorus are mixed in a suitable solvent to form a first mixture of uniform composition and texture. Adequate mixing, stirring, or agitation usually is used. To this mixture is added the silicon component, followed by the organic template. Alternately, the silicon component and the organic template may be combined to form a second mixture of uniform composition and
20 texture. This second mixture is mixed with the first mixture. Other permutations of how the individual components are mixed may be possible so long as a final mixture with uniform composition and texture is formed.

In order to make a molecular sieve comprising SAPO-44, the molar ratios of the components in the mixture must be controlled and maintained. Before being subjected to conditions effective to produce the molecular sieve product, the final reaction mixture, excluding any other organic or inorganic moieties or species which
5 may be present, is characterized by a general formula as follows:



wherein T represents the organic template.

The molar ratio of the organic template to aluminum, a/x , is in the range of from about 1 to about 5, preferably from about 1.2 to about 4. The molar ratio of the
10 template to phosphorus, a/y , is in the range of from about 1 to about 5, preferably from about 1.2 to about 4. The molar ratio of the template to silicon, a/w , is in the range of from about 2 to about 8, preferably from about 2.5 to about 6. The molar ratio of phosphorus to aluminum, y/x , is in the range from about 1 to about 0.2. The molar ratio of the template to water, a/b is in the range from about 0.02 to about 0.2,
15 preferably in the range from about 0.04 to about 0.1. z is the oxygen needed to balance the ionic charges of Si, Al, and P present as expressed in the formula. As long as the molar ratio requirements of the mixture are satisfied according to the formula shown above, many different procedures may be used to synthesize a desired product.

20 It is preferable to maintain the pH value of the final reaction mixture in the range from about 5.5 to about 8.5, preferably from about 6 to about 7.5. The pH value of a mixture may be adjusted, if desired, by adding an appropriate amount of a base such as ammonia/ammonium hydroxide to increase the pH, or an appropriate amount

of a suitable inorganic or organic acid such as phosphoric acid, HCl, acetic acid, formic acid, CO₂ and others to decrease the pH.

It is preferable to use adequate mixing, blending, stirring, or agitation to provide a uniform composition throughout the mixture. A concentration or
5 composition gradient should be minimized because such a gradient could result in the formation of different molecular sieve products.

Preferably, a constant temperature is maintained during the preparation of the mixture. Mixing of some of the components is not thermodynamically neutral. Cooling or heating may be required to provide a constant temperature environment. A
10 suitable temperature for preparation of a mixture is in the range of from about 10°C to about 90°C, preferably from about 20°C to about 65°C. Pressure is usually not critical for preparing a mixture unless one or more gases are used to control other reaction parameters, such as pH, temperature, or concentration.

Once a mixture is prepared, the mixture optionally may be aged for a certain
15 period of time in the range of from about 0 hours to about 200 hours before the mixture is subjected to conditions effective to produce a desired product comprising SAPO-44. Aging can be accomplished at a temperature in the range of from about 0°C to about 95°C, preferably in the range of from about 20°C to about 65°C, with or without agitation/stirring.

20 After aging, if any, the final reaction mixture is treated under conditions effective to produce a molecular sieve product comprising SAPO-44, preferably in substantially pure form. The mixture usually is placed in a metallic autoclave which may be lined with an inert liner to prevent the metal surface of the autoclave from

reacting with the reaction mixture. Other pressure vessels made of heavy glass or plastic walls also may be used as long as the wall material does not react with the reaction mixture. With or without agitation/stirring, the mixture is heated to a temperature in the range of from about 100°C to about 270°C, preferably from about 150°C to about 230°C, for a period of time in the range from about 30 minutes to about 800 hours, preferably in the range from about 5 hours to about 200 hours. The required time period depends on the temperature and composition of the mixture.

An autogenic pressure usually is maintained. If preferred, a non-reactive gas such as nitrogen, argon, helium, and mixtures thereof may be used to provide additional pressure. Other gases also may be used, if desirable. One such gas which may be used to provide pressure and to change the pH value of the mixture is CO₂. CO is another gas that may be used unless CO undesirably reacts with the mixture or certain components of the mixture.

After the formation of a SAPO-44 containing product, the product is separated and recovered by many known techniques, such as filtration, centrifugation, sedimentation, or a combination thereof. The recovered product preferably is dried at a reduced pressure, an elevated temperature, or both. A suitable pressure is in the range of from about 0.01 kPa to about 150 kPa.

With or without being dried, the recovered product preferably is calcined to remove the organic templates. The calcination is carried out at a temperature in the range of from about 250°C to about 800°C, preferably from about 350°C to about 650°C in an oxidizing atmosphere in order to burn off the organic template, preferably in air or an oxygen containing gas. Non-oxidizing atmospheres also may be used,

including but not necessarily limited to nitrogen, hydrogen, water (steam) and mixtures thereof. Steam also may be used with an oxidizing atmosphere for the calcination. The time period for the calcination is in the range of from about 30 minutes to about 72 hours, preferably from about 2 hours to about 48 hours.

5 Using the methods known in the art, the SAPO-44 molecular sieve products can be further ion-exchanged into an essentially complete hydrogen form with very low level of residual metal ions. Controlled ion-exchange also can be carried out to make a partial hydrogen form, or a fully ion-exchanged form of a SAPO-44 molecular sieve.

10 Catalysts made according to the present invention can be used to convert oxygenates to olefins, or to convert hydrocarbons to lower molecular weight products, particularly to light olefins (ethylene, propylene, butenes and mixtures thereof).

Oxygenates can be converted to olefins by contacting an oxygenate feed with a catalyst comprising SAPO-44 under conditions effective to produce olefins,
15 preferably light olefins such as ethylene, propylene, butenes, and mixtures thereof.

Oxygenates suitable for use in the feed include, but are not necessarily limited to aliphatic alcohols, ethers, carbonyl compounds (aldehydes, ketones, carboxylic acids, esters, carbonates and the like), alkyl halides, alkyl amines, and mixtures thereof. Preferred oxygenates are methanol, ethanol, n-propanol, isopropanol, n-
20 butanol, sec-butanol, dimethyl ether, methylethyl ether, diethyl ether, dimethyl carbonate, and mixtures thereof.

Effective conditions for oxygenate conversions are known in the art, and include, but are not necessarily limited to: a temperature in the range from about 200

°C to about 800°C; a pressure in the range of from about 1 kPa to about 2 MPa; a Weight Hourly Space Velocity (WHSV) in the range of from about 0.01 to about 10,000 h⁻¹. Because the feed may contain diluents and the catalyst may contain filler and/or binder materials, WHSV is calculated on the weight of the oxygenate feed
5 itself and the weight of the molecular sieve component in the catalyst. Diluents can be mixed with the oxygenates as feed. The amounts of diluents used are in the range of from about 0 wt% to about 95 wt% of the total feed. Suitable diluents include but are not necessarily limited to water (steam), CO₂, hydrogen, nitrogen, argon, and mixtures thereof.

10 The oxygenate feed is contacted with the catalyst in a conversion reactor under effective conditions for conversion. A suitable conversion reactor is a fixed bed reactor, a moving bed reactor, a fluidized bed reactor, or another similar type of reactor. The products and any unreacted feedstock then are separated from the catalyst, and the products are purified. Unreacted feedstock may be recycled back to
15 the conversion reactor or otherwise disposed. If the catalyst is deactivated, it is regenerated. Regeneration can be carried out in the conversion reactor itself, or in a separate regeneration reactor. Regeneration usually is carried out at an elevated temperature, in the range of from about 350°C to about 950°C, and in the presence of an oxygen containing atmosphere. Sometimes treating a deactivated catalyst with
20 hydrogen at elevated temperatures also is effective to regenerate the catalytic performance of the oxygenate conversion catalyst.

Catalysts of the present invention also can be used for conversion of relatively high molecular weight hydrocarbons to hydrocarbons having lower molecular

weights. Suitable hydrocarbon feedstocks include, but are not necessarily limited to naphtha and similar hydrocarbons. The feedstocks preferably comprise mostly non-aromatic compounds with at least five carbon atoms. Preferred products comprise light olefins (ethylene, propylene, butenes, and mixtures thereof).

5 Typical reaction conditions for the hydrocarbon conversions are known in the art, and include, but are not necessarily limited to: a temperature in the range of from about 250 to about 900°C; a pressure in the range of from about 1 kPa to about 2 MPa; a weight hourly space velocity (WHSV) in the range of from about 0.01 to about 10,000 h⁻¹. Because the feed may contain diluents and the catalyst may contain filler
10 and/or binder materials, WHSV is calculated on the weight of the hydrocarbon feed itself and the weight of the molecular sieve component in the catalyst. Diluents such as water (steam), CO₂, hydrogen, nitrogen, and others can be mixed with the feedstocks. The amounts of diluents used are in the range of from about 0 wt% to about 95 wt% of the total feed.

15 The hydrocarbon feed is contacted with the catalyst in a conversion reactor under effective conditions for conversion. A suitable conversion reactor is a fixed bed reactor, a moving bed reactor, a fluidized bed reactor, or other similar types of reactor. The products and any unreacted feedstock then are separated from the catalyst, and the products are purified. Unreacted feedstock may be recycled back to the conversion
20 reactor or otherwise disposed. If the catalyst is deactivated, it is regenerated. Regeneration can be carried out in the conversion reactor or in a separate regeneration reactor. Regeneration usually is carried out at an elevated temperature, in the range of from about 350°C to about 950°C, and in the presence of oxygen. Sometimes treating

a deactivated catalyst with hydrogen at elevated temperatures also is effective to regenerate the catalytic performance of the hydrocarbon conversion catalyst.

The invention will be better understood with reference to the following examples, which illustrate, but do not limit the invention, which is solely defined by
5 the claims.

EXAMPLE I

A reaction mixture was prepared by mixing 11.53 g of 85 wt% orthophosphoric acid and 15.5 g of water. To this mixture was added 6.87 g of boehmite (74.2 wt% alumina and 25.8 wt% water) with adequate stirring to make the
10 mixture uniform. 6.9 grams of silica gel (26 wt% SiO₂, 74wt% H₂O) were added and the mixture was stirred to become homogeneous. Finally, 17.1 grams of cyclohexylamine (CHA) (100%) and 11.9 grams of water were added to this mixture with stirring to form a homogeneous mixture. The composition of the final reaction mixture in molar oxide ratios was 3 CHA : Al₂O₃ : P₂O₅ : 0.6 SiO₂ : 40 H₂O. This
15 reaction mixture was sealed in a 100 ml stainless steel vessel and heated in an oven at 200°C at autogenic pressure for 72 hours. The reaction mixture was then filtered, washed with distilled water, and dried at 110°C to recover a solid product, "as-synthesized" SAPO-44. This "as-synthesized" SAPO-44 was calcined by heating to 550°C over two hours in air and then maintained at 550°C for another three hours.
20 The Al₂O₃ : P₂O₅ : SiO₂ molar ratio in the product was about: 1: 0.74 : 0.92. X-ray diffraction (XRD) showed that the product was substantially pure SAPO-44. No by-products were identified by XRD. Nuclear magnetic resonance (NMR) of silicon-29 showed that silicon distribution for Si(4Al):Si(3Al):Si(2Al):Si(1Al):Si(0Al) in the

product was (in atomic %) 61.0:23.7:5.5:4.2:5.6. Si(4Al) means that the silicon atom is surrounded by four Al-O- groups; Si(3Al), three; Si(2Al), two; Si(1Al), one; and Si(0Al), zero such Al-O- groups.

EXAMPLE II

5 Procedures similar to EXAMPLE I were repeated except that the composition of the final reaction mixture in molar oxide ratios was 3 CHA : Al₂O₃ : P₂O₅ : SiO₂ : 40 H₂O. The Al₂O₃ : P₂O₅ : SiO₂ molar ratio in the SAPO-44 molecular sieve product was about: 1: 0.77 : 0.85. X-ray diffraction (XRD) showed that the product was substantially pure SAPO-44. No by-products were identified by XRD. Silicon-29
10 NMR showed that silicon distribution for Si(4Al):Si(3Al):Si(2Al):Si(1Al):Si(0Al) in the product was (in atomic %) 45.3:23.9:11.5:9.9:9.8.

EXAMPLE III

 Procedures similar to EXAMPLE I were repeated except that the composition of the final reaction mixture in molar oxide ratios was 2 CHA : Al₂O₃ : P₂O₅ : 0.6 SiO₂
15 : 80 H₂O. The Al₂O₃ : P₂O₅ : SiO₂ molar ratio in the SAPO-44 molecular sieve product was about: 1: 0.68 : 1.41. X-ray diffraction (XRD) showed that the product was substantially pure SAPO-44. No by-products were identified by XRD. Silicon NMR showed that silicon distribution for Si(4Al):Si(3Al):Si(2Al):Si(1Al):Si(0Al) in the product was (in atomic %): 30.9:23.5:15.9:15.6:13.7.

20 EXAMPLE IV

 The catalysts prepared in EXAMPLES I, II, and III were tested for their ability to convert methanol to olefins. The catalysts were pelletized and crushed to 20-40 mesh in size. 1.28 grams of each catalyst were tested separately in a tubular reactor.

Prior to use, the catalysts were treated at 500°C in a flowing nitrogen stream, 60 ml/min, for one hour. The methanol conversion reactions were carried out at a 2 h⁻¹ weight hourly space velocity (WHSV) of methanol feed in a nitrogen carrier gas at 60 ml/min. The WHSV was measured for methanol only, excluding nitrogen. The data reported below were obtained after the reaction was on-stream for two minutes. The products were analyzed by standard gas chromatographic methods. The results are shown below:

Catalyst	EXAMPLE I	EXAMPLE II	EXAMPLE III
Methanol Conversion	100	100	100
Selectivity (wt%)			
CH ₄	1.2	1.1	1.7
C ₂ H ₄	39.6	31.4	26.0
C ₂ H ₆	0.5	1.0	3.1
C ₃ H ₆	39.2	34.9	32.7
C ₃ H ₈	5.4	12.2	21.3
C ₄ H ₈	11.9	12.9	12.9
C ₄ H ₁₀	2.2	2.4	2.4
C ₅ ⁻	0	4.1	0
C ₅ ⁺	0	0.1	0

These results indicate that molecular sieves comprising substantially pure SAPO-44 could be prepared according to the method of the present invention. The molecular sieves are capable of converting methanol to light olefins in high selectivities.

Persons of ordinary skill in the art will recognize that many modifications may be made to the present invention without departing from the spirit and scope of the present invention. The embodiments described herein are meant to be illustrative only

and should not be taken as limiting the invention, which is defined in the following claims.

We claim:

- 1 1. A method comprising:
 - 2 forming a mixture comprising
 - 3 a silicon component;
 - 4 an organic template (T) at a first molar ratio of greater than about 1 to an
 - 5 aluminum component; and
 - 6 a phosphorus component at a second molar ratio of less than about 1 to said
 - 7 aluminum component; and
 - 8 subjecting said mixture to first conditions effective to produce a molecular sieve
 - 9 product comprising silicalite 4A.

- 1 2. The method of claim 1 further comprising one or more parameters selected from the
 - 2 group consisting of the following:
 - 3 said mixture comprises a pH value in the range of from about 5.5 to about 8.5;
 - 4 said aluminum component comprises a material selected from the group
 - 5 consisting of alumina, boehmite, pseudo boehmite, aluminum hydroxy
 - 6 chloride, aluminum tri-ethoxide, aluminum tri-isopropoxide, aluminum tri-n-
 - 7 butoxide and aluminum tri-isobutoxide;
 - 8 said silicon component comprises a material selected from the group consisting
 - 9 of fumed silica, silica gel, silica sol, colloidal silica, tetraethyl silicate, and
 - 10 tetramethyl silicate;

11 said organic template comprises cyclohexylammonium salt;
12 said phosphorus element comprises a material selected from the group consisting
13 of orthophosphoric acid, phosphorous acid, phosphorus oxides, trimethyl
14 phosphate, and triethyl phosphate;

1 3. The method of any of claims 1 and 2 wherein said first conditions comprise heating
2 said mixture to a first elevated temperature of from about 100°C to about 270°C under
3 autogenic pressure for a first period of time of from about 30 minutes to about 800 hours.

1 4. The method of any of claims 1, 2, or 3 wherein said organic template comprises
2 cyclohexylamine.

1 5. The method of any of claims 1-4 wherein said mixture comprises a pH value in the
2 range of from about 6 to about 7.5.

1 6. The method of any of claims 1-5 wherein said mixture is characterized by a formula
2 of $T_aSi_wAl_xP_yO_z \cdot bH_2O$, excluding other species present in said mixture, wherein a/w is in
3 the range of from about 2 to about 8, a/x is in the range of from about 1 to about 5, a/y is
4 in the range of from about 1 to about 5, y/x is in the range of from about 1 to about 0.2,
5 and a/b is in the range of from about 0.02 to about 0.2.

1 7. The method of claim 6 further comprising one or more limitations selected from the
2 group consisting of the following:

- 3 a/w is in the range of from about 2.5 to about 6;
4 a/x is in the range of from about 1.2 to about 4;
5 a/y is in the range of from about 1.2 to about 4; and,
6 a/b is in the range of from about 0.04 to about 0.1

1 8. The method of claims 1- 7 wherein

2 said phosphorous component comprises an aqueous orthophosphoric acid
3 solution; said aluminum component comprises a boehmite; and said
4 silicon component comprises a silica gel; and

5 wherein said forming a mixture comprises

6 adding boehmite to said aqueous orthophosphoric acid solution under first
7 precursor conditions effective to form a first reaction mixture of uniform
8 composition;

9 adding a silica gel to said first reaction mixture under second precursor conditions
10 effective to form a first reaction product of homogeneous composition;

11 adding a mixture comprising cyclohexylamine (T) and water to said first reaction
12 product under third precursor conditions effective to form a second reaction
13 product of uniform composition;

14 wherein said second reaction product comprises said pH value in the range of
15 from about 5.5 to about 8.5 and said second reaction product is characterized
16 by a formula of $T_aSi_wAl_xP_yO_z \cdot bH_2O$;

17 subjecting said second reaction product to said first conditions;

18 separating a third reaction product comprising said solid material;
19 drying said third reaction product at a second temperature in the range of from
20 about 25°C to about 120°C and at a pressure from about 0.01kPa to about
21 150 kPa to form a dried solid material; and,
22 calcining said dried solid material at a third temperature in the range of from
23 about 250°C to about 800°C to form a molecular sieve product comprising
24 substantially pure silicoaluminophosphate 44.

1 9. A process comprising contacting an oxygenate feed with a catalyst under conditions
2 effective to convert said oxygenate feed to light olefins wherein said catalyst is
3 prepared by a method comprising:
4 forming a mixture comprising
5 a silicon component;
6 an organic template (T) at a first molar ratio of greater than about 1 to an aluminum
7 component; and
8 a phosphorus component at a second molar ratio of less than about 1 to said
9 aluminum component; and
10 subjecting said mixture to conditions effective to produce a molecular sieve product
11 comprising silicoaluminophosphate 44.

1 10. The process of claim 9 wherein
2 said silicon component comprises silica gel,

3 said organic template comprises cyclohexylamine,
4 said aluminum component comprises boehmite, and,
5 said phosphorus component comprises orthophosphoric acid;
6 said mixture comprises a pH value in the range of from about 5.5 to about 8.5;
7 said mixture is characterized by a formula of $T_aSi_wAl_xP_yO_z \cdot bH_2O$, excluding other
8 species present in said mixture, wherein a/w is in the range of from about 2 to
9 about 8, a/x is in the range from about 1 to about 5, a/y is in the range of from
10 about 1 to about 5, y/x is in the range of from about 1 to about 0.2, and a/b is
11 in the range of from about 0.02 to about 0.2; and
12 wherein said molecular sieve product comprises substantially pure
13 silicoaluminophosphate 44.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/20872

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C01B37/08 B01J29/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 97 33693 A (NORSK HYDRO ASA ;LILLERUD KARL PETTER (NO); KARLSSON ARNE (NO); HU) 18 September 1997 see claims 5,9 see page 4, line 7 - line 26 ---	1-3,6,7, 9
A	US 5 230 881 A (MILLER STEPHEN J) 27 July 1993 see page 2, line 46 - page 3, line 23 ---	1,2
A	WO 95 05342 A (NORSK HYDRO AS ;WENDELBO RUNE (NO)) 23 February 1995 see examples 1,2,4 see claims 5,9 ---	1,8,9
A	WO 93 13013 A (NORSK HYDRO AS) 8 July 1993 see examples 1-8 --- -/--	1,9

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

29 January 1999

Date of mailing of the international search report

05/02/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rigondaud, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/20872

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 103 117 A (UNION CARBIDE CORP) 21 March 1984 see example 50 & US 4 440 871 A cited in the application -----	1,6
A	EP 0 324 082 A (UNION CARBIDE CORP) 19 July 1989 see claims 1,24,51,52 see example 26 -----	1,2

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 98/20872

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date			
WO 9733693	A	18-09-1997	NO 961033	20-10-1997			
			AU 2413297	01-10-1997			
			EP 0888188	07-01-1999			
US 5230881	A	27-07-1993	NONE				
WO 9505342	A	23-02-1995	NO 932915	20-02-1995			
			AU 685491	22-01-1998			
			AU 7509494	14-03-1995			
			CA 2169766	23-02-1995			
			EP 0714379	05-06-1996			
			JP 9501646	18-02-1997			
			NZ 271459	26-01-1998			
			US 5609843	11-03-1997			
WO 9313013	A	08-07-1993	NO 174341	10-01-1994			
			AU 3097292	28-07-1993			
			DE 69221638	18-09-1997			
			DE 69221638	26-02-1998			
			EP 0619800	19-10-1994			
			ES 2107559	01-12-1997			
			JP 2562863	11-12-1996			
			JP 7502250	09-03-1995			
			NZ 246097	26-01-1996			
			RU 2091305	27-09-1997			
			US 5663471	02-09-1997			
			EP 0103117	A	21-03-1984	US 4440871	03-04-1984
AT 22272	15-10-1986						
CA 1202016	18-03-1986						
DK 339883	27-01-1984						
JP 1703764	14-10-1992						
JP 3072010	15-11-1991						
JP 59035018	25-02-1984						
US 5114563	19-05-1992						
EP 0324082	A	19-07-1989	US 4861743	29-08-1989			
			DE 3873726	17-09-1992			
			DK 655888	26-05-1989			