

(51) International Patent Classification:
C07H 3/02 (2006.01)

(21) International Application Number:

PCT/US2014/020530

(22) International Filing Date:

5 March 2014 (05.03.2014)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/811,010

11 April 2013 (11.04.2013)

US

(71) Applicant: CALIFORNIA INSTITUTE OF TECHNOLOGY [US/US]; 1200 East California Boulevard, M/C 6-32, Pasadena, CA 91125 (US).

(72) Inventors: DAVIS, Mark, E.; 575 Laguna Rd., Pasadena, CA 91105 (US). GOUNDER, Rajamani; 167 S. Oak Knoll Ave., Apt. #15, Pasadena, CA 91101 (US).


(74) Agents: DEKLEVA, Thomas, W. et al.; Baker & Hostetler LLP, 2929 Arch St. Cira Centre, 12th Floor, Philadelphia, PA 19104-2891 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,

[Continued on next page]

(54) Title: CONVERSION OF GLUCOSE TO SORBOSE

FIG. 12A(57) Abstract: The present invention is directed to methods for preparing sorbose from glucose, said method comprising: (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material, or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose. The sorbose may be (b) separated or isolated; or (c) converted to ascorbic acid.



TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, **Published:**
KM, ML, MR, NE, SN, TD, TG).

— *with international search report (Art. 21(3))*

CONVERSION OF GLUCOSE TO SORBOSE

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of U.S. Patent Application Ser. No. 61/811,010, filed April 11, 2013, which is incorporated by reference in its entirety.

GOVERNMENT RIGHTS

[0002] The subject matter disclosed herein was made with government support under grant number DE-SC0001004 / T-106028 awarded by the Department of Energy. The Government has certain rights in the herein disclosed subject matter.

TECHNICAL FIELD

[0003] The disclosed invention is in the field of glucose isomerization.

BACKGROUND

[0004] D-glucose is used as a feedstock in the Reichstein synthesis of L-ascorbic acid (a form of vitamin C; $\sim 10^5$ tons produced annually worldwide) via L-sorbose intermediates. The conversion of D-glucose to L-sorbose currently requires the sequential hydrogenation of D-glucose to D-sorbitol over a nickel-based catalyst and selective oxidation of C2-OH groups in D-sorbitol to L-sorbose using microbiological enzymes. The production of sorbose, among a mixture of several aldohexose and ketohexose isomers, has been observed during reactions of glucose in alkaline media via 3,4-enediol intermediates, and via retro-aldol condensation to glyceraldehyde, isomerization to dihydroxyacetone, and realdolization of these triose intermediates. Heterogeneous base resins (Amberlite XE-48, Amberlite IRA-400) also convert D-(+)-glucose to a mixture of D-(+)-sorbose ($\sim 68\%$) and L-(-)-sorbose ($\sim 32\%$), among several other hexose products, via 3,4-enediol intermediates.

[0005] Glucose isomerization and epimerization reactions catalyzed by bases are known to proceed via abstraction of α -carbonyl protons to form 1,2-enediol intermediates, which undergo proton-transfer mediated rearrangements to form fructose and mannose (Lobry de Bruyn-Alberda van Ekenstein rearrangements; LdB-AvE). Double-bond isomerization of 1,2-enediols leads to a mixture of 2,3- and 3,4-enediol intermediates that are precursors to psicose, tagatose and sorbose ketohexoses (the C-3, C-4 and C-5 epimers of fructose, respectively) and other aldohexoses. As a result, selectivities to fructose, the preferred product of glucose conversion in alkaline media, decrease with increasing glucose conversion because of sequential

1,2-enediol rearrangements and because monosaccharides undergo retro-aldol condensation and other degradation pathways.

[0006] In contrast to base catalysts that initiate glucose isomerization via α -carbonyl abstraction, Lewis acids coordinate with and polarize oxygen atoms (O1) at glucose aldehyde carbons (C1) to enable nucleophilic addition preferentially at electron-deficient C-1 centers over other carbon atoms along the sugar backbone. (**FIG. 1A**) The ability of a single Lewis acid center to coordinate with glucose via a second oxygen atom located in another hydroxyl group along the sugar backbone, in turn, facilitates intramolecular skeletal rearrangements via migration of nucleophilic moieties to glucose C1 centers. Infrared (IR) and solid-state ^{13}C nuclear magnetic resonance (NMR) studies, together with quantum chemical calculations, have shown that Lewis acidic framework Sn centers isolated within zeolite beta (Sn-Beta) mediate glucose ring-opening and coordination with glucose O1 and O2 atoms. In turn, glucose-fructose isomerization occurs via subsequent intramolecular hydride shift from the C2 to C1 carbon atoms on open glucose chains. This isomerization mechanism is analogous to that mediated by two divalent Lewis acid metal centers (e.g., Mg^{2+} or Mn^{2+}) that are spatially positioned within hydrophobic pockets of metalloenzymes (e.g., D-xylose isomerase) to facilitate glucose binding via O1 and O2 atoms prior to glucose-fructose isomerization.

[0007] Sn-Beta can also mediate glucose-mannose epimerization in methanol solvent, and in water in the presence of borate salts, via a Lewis-acid intramolecular carbon rearrangement known as the Bilik reaction. In the glucose-mannose epimerization mechanism, C3 carbon centers bound to C2 atoms behave as nucleophiles and migrate (along with the rest of the covalently bound sugar backbone) to electrophilic C1 centers (**FIG. 1B**). The mechanisms for framework Sn-mediated glucose-mannose epimerization and glucose-fructose isomerization are similar because they first require bidentate glucose coordination to metal centers via O1 and O2 atoms; they differ, in part, because C3 centers or hydridic species bound to glucose C2 centers respectively act as the nucleophiles that attack electron-deficient C1 centers (**FIG. 1B**). These intramolecular hydride and carbon shifts occur within glucose only with Lewis acidic framework Sn-Beta and not with base sites on extraframework SnO_2 domains, reflecting the requirement of Lewis acid centers to mediate the redistribution of oxidation states between carbon atoms in organic substrates at transition states for intramolecular or intermolecular Meerwein-Ponndorf-Verley aldehyde and ketone reduction and Oppenauer alcohol oxidation (MPVO) reactions.

SUMMARY

[0008] Various embodiments of the present invention provide processes for preparing sorbose from glucose, each process comprising: (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material, or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose; and (b) separating the sorbose.

[0009] Other embodiments provide processes for preparing ascorbic acid, each process comprising: (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material, or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose; (b) optionally separating the sorbose; and (c) converting the sorbose to ascorbic acid.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] The present application is further understood when read in conjunction with the appended drawings. For the purpose of illustrating the subject matter, there are shown in the drawings exemplary embodiments of the subject matter; however, the presently disclosed subject matter is not limited to the specific methods, processes, devices, and systems disclosed. In addition, the drawings are not necessarily drawn to scale. In the drawings:

[0011] **FIG. 1A-B** illustrates schematically a mechanism of glucose isomerization (**FIG. 1A**) and glucose epimerization (**FIG. 1B**) mediated by Lewis acid (M) centers in silicate frameworks on Sn-Beta. Oxidation states of C1 and C2 carbon atoms are shown in reactant and product sugars (depicted using Fischer projections). Mechanistic evidence for both reactions has been previously established based on isotopic (D, ^{13}C) tracer studies using labeled glucose reactants; proposed transition states for both pathways are also shown. As shown herein, glucose first must undergo ring-opening at M sites to give the acyclic form prior to isomerization or epimerization.

[0012] **FIG. 2** are powder x-ray diffraction patterns of as-made Ti-Beta-66, Ti-Beta-79, Ti-Beta-107, Ti-Beta-202 (bottom to top) as described in **Example 2.1**. Suffix denotes Si/Ti ratio; all samples are consistent with the powder pattern for the beta topology.

[0013] **FIG. 3** shows an N_2 adsorption isotherm (77 K) for Ti-Beta-202 as described in **Example 2.1**. The adsorption branch of the N_2 isotherm (77 K) measured on Ti-Beta-202 is

representative of that measured on all Ti-Beta samples used in the Examples provided herein. The micropore volume estimated from semilog-derivative plot analysis (details given elsewhere⁴) is $0.21 \text{ cm}^3 \text{ g}^{-1}$, which is consistent with the beta topology.

[0014] FIG. 4 shows the diffuse reflectance UV-Visible DRUV spectra of Ti-Beta-66, Ti-Beta-79, Ti-Beta-107, Ti-Beta-202 (bottom to top) as described in Example 2.1. The diffuse reflectance UV-Visible spectra in Kubelka-Munk units are shown for each Ti-Beta samples used in this study. All samples show DRUV bands centered in the 200-220 nm range, which have been assigned previously to framework Ti^{4+} centers.

[0015] FIG. 5A-B illustrate liquid-phase concentrations of sorbose (■) and fructose (▲), and fructose-to-sorbose or sorbose-to-fructose molar ratios (●) as a function of reaction time during reaction of a 1% (w/w) solution of glucose with Ti-Beta-79 in water (FIG. 5A) and in methanol solvent (FIG. 5B). Dashed curves for liquid-phase sugar concentrations represent best fits of the experimental data to Eq. (S.1). Dashed curves for sugar molar ratios are given by the ratio of the two models for individual sugar concentrations.

[0016] FIG. 6A-F are the ^{13}C NMR spectra of unlabeled glucose (FIG. 6A) and of the glucose fractions isolated after reaction of glucose- ^{13}C -C1 (FIG. 6B) and glucose-D2 (FIG. 6C) with Ti-Beta in water at 373 K for 6 h. ^{13}C NMR spectra of unlabeled sorbose (FIG. 6D) together with assignments for each carbon position in α -L-sorbopyranose, and of the sorbose fractions isolated after reaction of glucose- ^{13}C -C1 (FIG. 6E) and glucose-D2 (FIG. 6F) with Ti-Beta in water at 373 K for 6 h.

[0017] FIG. 7A-B is the ^1H NMR spectrum of glucose fraction after reaction of glucose-D2 with Ti-Beta in water at 373 K for 6 h. FIG. 7A is the region δ : 3-5.2 ppm; * denotes H_2O . FIG. 7B is the region δ : 3-3.3 ppm.

[0018] FIG. 8 is the ^1H NMR spectrum of fructose fraction after reaction of glucose-D2 with Ti-Beta in water at 373 K for 6 h, described in Example 3.2.

[0019] FIG. 9A-C are the ^{13}C NMR spectra of unlabeled fructose (FIG. 9A) and of the fructose fractions isolated after reaction of glucose- ^{13}C -C1 (FIG. 9B) and glucose-D2 (FIG. 9C) with Ti-Beta in water at 373 K for 6 h.

[0020] FIG. 10 illustrates the parallel reaction schemes for glucose-fructose and glucose-sorbose isomerization mediated by Lewis acidic Ti^{4+} centers in Ti-Beta. Mechanistic evidence from isotopic tracer studies using D and ^{13}C labels shown in reactants and products depicted using Fischer projections.

[0021] FIG. 11A illustrates a possible intermediate (1-3, 5-7) and transition state (4) structures involved in the proposed intramolecular C5-C1 hydride shift reaction mechanism for glucose-sorbose isomerization on open sites in Ti-Beta. FIG. 11B provides an overview of the reaction of glucose to sorbose using this intermediate state (4).

[0022] FIG. 12A-B illustrate the liquid-phase concentrations of sorbose (FIG. 12A) and fructose (FIG. 12B) as a function of reaction time during reaction of a 1% (w/w) solution of glucose (●), glucose-D2 (◆), or glucose-D₇-1,2,3,4,5,6,6 (▲) with Ti-Beta in methanol solvent (373 K). Corresponding initial turnover rates are given in Table 2. Dashed curves represent best fits of the experimental data to kinetic models derived assuming isomerization to sorbose and fructose occur in parallel and at rates that are first-order in glucose concentration.

[0023] FIG. 13 illustrates a scheme of the reactions associated with the Reichstein process for the production of vitamin C (ascorbic acid).

DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

[0024] The present invention is directed to processes for the catalytic conversion of glucose to sorbose and from glucose to ascorbic acid. The Examples described herein represent the first evidence for the direct isomerization of glucose to sorbose, a ketose sugar (the C5 epimer of fructose), which is mediated by Lewis acidic Ti⁴⁺ centers incorporated into the framework of silica zeolite beta (Ti-Beta or Zr-Beta). The data and the mechanistic evidence presented herein, to the inventors' knowledge, constitute the first report of direct and stereospecific D-(+)-glucose to L-(-)-sorbose isomerization mediated by a Lewis acid center, or by any catalytic entity for that matter.

[0025] The present invention may be understood more readily by reference to the following description taken in connection with the accompanying Figures and Examples, all of which form a part of this disclosure. It is to be understood that this invention is not limited to the specific products, methods, processes, conditions or parameters described or shown herein, and that the terminology used herein is for the purpose of describing particular embodiments by way of example only and is not intended to be limiting of any claimed invention. Similarly, unless specifically otherwise stated, any description as to a possible mechanism or mode of action or reason for improvement is meant to be illustrative only, and the invention herein is not to be constrained by the correctness or incorrectness of any such suggested mechanism or mode of action or reason for improvement. Throughout this specification, claims, and drawings, it is recognized that the descriptions refer to compositions and processes of making and using said compositions. That is, where the disclosure describes or claims a feature or embodiment

associated with a composition or a method of making or using a composition, it is appreciated that such a description or claim is intended to extend these features or embodiment to embodiments in each of these contexts (i.e., compositions, methods of making, and methods of using).

[0026] In the present disclosure the singular forms “a,” “an,” and “the” include the plural reference, and reference to a particular numerical value includes at least that particular value, unless the context clearly indicates otherwise. Thus, for example, a reference to “a material” is a reference to at least one of such materials and equivalents thereof known to those skilled in the art, and so forth.

[0027] When a value is expressed as an approximation by use of the descriptor “about,” it will be understood that the particular value forms another embodiment. In general, use of the term “about” indicates approximations that can vary depending on the desired properties sought to be obtained by the disclosed subject matter and is to be interpreted in the specific context in which it is used, based on its function. The person skilled in the art will be able to interpret this as a matter of routine. In some cases, the number of significant figures used for a particular value may be one non-limiting method of determining the extent of the word “about.” In other cases, the gradations used in a series of values may be used to determine the intended range available to the term “about” for each value. Where present, all ranges are inclusive and combinable. That is, references to values stated in ranges include every value within that range.

[0028] It is to be appreciated that certain features of the invention which are, for clarity, described herein in the context of separate embodiments, may also be provided in combination in a single embodiment. That is, unless obviously incompatible or specifically excluded, each individual embodiment is deemed to be combinable with any other embodiment(s) and such a combination is considered to be another embodiment. Conversely, various features of the invention that are, for brevity, described in the context of a single embodiment, may also be provided separately or in any sub-combination. Finally, while an embodiment may be described as part of a series of steps or part of a more general structure, each said step may also be considered an independent embodiment in itself, combinable with others.

[0029] The transitional terms “comprising,” “consisting essentially of,” and “consisting” are intended to connote their generally in accepted meanings in the patent vernacular; that is, (i) “comprising,” which is synonymous with “including,” “containing,” or “characterized by,” is inclusive or open-ended and does not exclude additional, unrecited elements or method or process steps; (ii) “consisting of” excludes any element, step, or ingredient not specified in the claim; and (iii) “consisting essentially of” limits the scope of a

claim to the specified materials or steps “and those that do not materially affect the basic and novel characteristic(s)” of the claimed invention. Embodiments described in terms of the phrase “comprising” (or its equivalents), also provide, as embodiments, those which are independently described in terms of “consisting of” and “consisting essentially of.” For those embodiments provided in terms of “consisting essentially of,” the basic and novel characteristic(s) is the facile operability of the methods (or the systems used in such methods or the compositions derived therefrom) to convert glucose, preferably D-(+)-glucose, to sorbose, preferably L-(-)-sorbose.

[0030] When a list is presented, unless stated otherwise, it is to be understood that each individual element of that list, and every combination of that list, is a separate embodiment. For example, a list of embodiments presented as “A, B, or C” is to be interpreted as including the embodiments, “A,” “B,” “C,” “A or B,” “A or C,” “B or C,” or “A, B, or C.”

[0031] Various embodiments of the present invention provide methods or processes for preparing sorbose from glucose, each process comprising: (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material, or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose; and (b) separating the sorbose.

[0032] As used herein, the terms “methods” or “processes” may be used interchangeably.

[0033] In other embodiments, each process further comprises further converting the sorbose, whether generated *in situ* as in step (a) or as separated or isolated in step (b), to form ascorbic acid. That is, certain embodiments provide processes for preparing ascorbic acid, each process comprising: (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material, or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose; (b) optionally separating the sorbose; and (c) converting the sorbose to ascorbic acid.

[0034] It is appreciated that various types of silica-containing structures containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers may be applied individually or in combination with one another, either in a serial arrangement or temporal batchwise arrangements, or both. It should also be appreciated that the conversion of the glucose to sorbose is catalytic with respect to the metal-silica-containing structures. *See, e.g., Table 1.*

[0035] In preferred embodiments, the silica-containing structure comprises or consists essentially of a zeolite having a topology of a 12 membered-ring or larger, provided the structures have Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers. In more embodiments, the zeolite has a *BEA topology. Such *BEA topological compositions may also be referred to as Ti-Beta or Zr-Beta compositions, according to nomenclature recognized by those skilled in the art. In such arrangements, the zeolite may comprise Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, though it appears that those compositions containing Lewis acidic Ti^{4+} framework centers are preferred. Without intending to be bound by the correctness of any particular theory, the topology of the zeolite having a 12 membered-ring (12-MR) or larger (which may alternatively described as providing pore sizes of 0.7 nanometers or above) is believed to be important so as to allow the reactants and products to migrate in and out of the structures, respectively. For example, 10 membered rings (10-MR) and smaller will likely be too small to adsorb glucose or accommodate the puckered C1-C5 hydride shift transition state for glucose-to-sorbose isomerization.

[0036] The processes are flexible in the Si / Ti (and/or Zr) atomic ratios that can be employed in the zeolite structures, and in some embodiment, the zeolite has a composition such that the atomic ratio of Si to Ti, Zr, or combination of Ti and Zr, is in a range of from about 35 to about 250. In certain other individual embodiments, the zeolite has a composition such that the atomic ratio of Si to Ti, Zr, or combination of Ti and Zr is in a range having a lower boundary of about 35, about 40, about 65, about 80, about 100, or about 120, and an upper boundary of 200, about 120, about 100, or about 80; for example in a range of from about 65 to about 120.

[0037] In other separate embodiments, the silica-containing structures comprise or consist essentially of an ordered or amorphous silica, again provided that the structure contains Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers. Non-limiting examples of ordered mesoporous silica material include MCM-41, MCM-48, and SBA-15 structures. Non-limiting examples of amorphous silica-containing titania or zirconia centers in amorphous silica include, for example $\text{TiO}_2\text{-SiO}_2$ or $\text{ZrO}_2\text{-SiO}_2$ co-precipitated or formed as a mixed oxide. In these ordered or amorphous structures, Each of these types of ordered or amorphous structures serve as appropriate templates for the catalytic activity of the Ti^{4+} / Zr^{4+} , though zeolites, though the selectivities to form sorbose are higher on zeolite materials, for example Ti-Beta, than on ordered mesoporous materials, like MCM-41. That is, the main differences among all of these three classes of materials is that the differences in selectivity for the glucose-to-sorbose transformation.

[0038] As stated above, independent embodiments of the inventive processes use silica-containing structures containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers. Those structures, especially beta zeolites containing Lewis acidic Ti^{4+} framework centers are preferred.

[0039] As described above, the methods provide for the transformation of glucose to sorbose, and especially for the conversion of D-(+)-glucose to L-(-)-sorbose. As described elsewhere herein, this stereoselective transformation has important commercial implications, as L-(-)-sorbose is a useful intermediate in the productions of L-ascorbic acid. Accordingly, various embodiments, then, include those processes or methods encompassing the conversion of D-(+)-glucose to L-ascorbic acid using the inventive methods presented herein.

[0040] To this point, the processes have been described in terms of contacting glucose with the catalysts under reaction conditions sufficient to isomerize the glucose to sorbose. In some embodiments, the reactions are conducted in the presence of an aqueous liquid. As used herein, unless otherwise stated, the term “aqueous” refers to a liquid medium comprising at least about 98% by weight water, relative to the weight of the entire liquid medium (i.e., not including reactants). In other embodiments, if specifically stated as such, include those where the term “aqueous” refers to liquids comprising at least about 80%, at least about 85%, at least about 90%, at least about 95%, or substantially 100% water (again, not including reactants).

[0041] In other embodiments, the reactions are conducted in the presence of an alcoholic medium. As used herein, unless otherwise stated, the term “alcoholic medium” refers to a liquid medium that comprises at least about 98% by weight of an alcohol, relative to the weight of the entire liquid medium (i.e., not including reactants). If specifically stated as such, in other embodiments, the term “alcoholic medium” may refer to liquids comprising at least about 80%, at least about 85%, at least about 90%, at least about 95%, or substantially 100% of an alcohol, relative to the weight of the entire liquid (again, not including reactants). Certain embodiments provide for the use of short chain alcohols (e.g., methanol, ethanol, n-propanol, or isopropanol) for this purpose. The use of methanol appears to be preferred. As can be seen in **Table 1, Example 3.1**, the formation of sorbose runs in parallel with the formation of fructose, though the use of alcohol, especially methanol, favors the formation of the sorbose.

[0042] Note that the classification of aqueous and alcoholic liquids or solvents are subsets of those embodiments wherein the weight ratio of water to alcohol is about 5:95, 10:90, 20:80, 30:70, 40:60, 50:50, 60:40, 70:30, 80:20, 90:10, or 95:5, relative to the weight of the combined water and alcohol.

[0043] The processes are also flexible with respect to loadings of reactants and catalysts. While there does not appear to be a theoretical lower limit to the ratio of glucose to Ti (and/or Zr), in practice, embodiments include those where the molar ratio of glucose to the Ti, Zr, or combination of Ti and Zr is in a range of from about 5 to about 500. And while not necessarily constrained by these limits, in other embodiments, the glucose concentration in the aqueous solvent is in a range of from about 0.1 wt% to about 45 wt%, relative to the combined weight of the glucose and aqueous solvent. In those embodiments where an alcoholic solvent is used, a glucose concentration in a range of from about 0.1 wt% to about 2 wt%, relative to the combined weight of the glucose and alcoholic solvent appears to work well.

[0044] The processes are operable at relatively modest temperatures. In certain embodiments, the reaction conditions comprise heating the reaction mixture to at least one temperature in a range of from about 40°C to about 200°C, the upper limit being the temperature at which the glucose degrades in the solvent. In other embodiments, the reaction conditions comprise heating the reaction mixture to at least one temperature in a range of from about 80°C to about 120°C or from about 100°C to about 120°C. Given the volatility of the solvents employed in these processes, reactions may be (and are preferably) conducted in sealed reactors, such that local pressures are reflective of solvent boiling point. The reactions may be conducted aerobically or anaerobically. In the Examples cited herein, no attempt was made to exclude air from the reaction conditions.

[0045] In those embodiments where the sorbose is separated, this unit operation may comprise filtration, crystallization, freeze-thawing, chromatographic separation (i.e., employing a column capable of separating the sorbose from other reactants and products), solvent removal (e.g., using a centrifugal evaporator), or a combination thereof. The specific methods or processes depend on the reaction conditions employed (e.g., the levels of the glucose-sorbose in the reaction mixture relative to the amount of solvent), the specific nature of the catalyst, the desired purity, or a combination thereof. It would be well within the skill of the person of ordinary skill in the art to define the process most suitable for their desired product quality.

[0046] Further, the conversion of sorbose to ascorbic acid is well known, being commercially practiced by various processes in the latter stages of the so-called the Reichstein or Reichstein-Heyns process. Such latter stage processes include, for example, formation of 2-keto-L-gulonic acid by (a) acetal protection of ring hydroxyls followed by the chemical oxidation of the protected sorbose by hypochlorite or permanganate or (b) oxidation of the sorbose using oxygen and a noble metal catalyst, such as platinum (see, e.g., U.S. Patent No. 2,189,778); . followed by a gamma-lactonization of the formed intermediate, with removal of water. These

steps may also be employed with the inventive processes described herein for the formation of the sorbose to provide embodiments directed to the conversion of glucose to ascorbic acid. Other methods or processes may also be used, such as those described by Granstrom, *et al.*, *J. Biosci. Bioeng.*, **97** (2004) 89, which is incorporated by reference herein for its teaching of this conversion.

Terms

[0047] Unless defined otherwise, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. Although any methods and materials similar or equivalent to those described herein can also be used in the practice or testing of the present invention, representative illustrative methods and materials are described herein.

[0048] Throughout this specification, words are to be afforded their normal meaning, as would be understood by those skilled in the relevant art. However, so as to avoid misunderstanding, the meanings of certain terms will be specifically defined or clarified.

[0049] "Optional" or "optionally" means that the subsequently described circumstance may or may not occur, so that the description includes instances where the circumstance occurs and instances where it does not. For example, the phrase "optionally separating the sorbose" means that a sorbose may or may not be separated from other materials in the method, and, thus, the description includes separate embodiments where the sorbose is separated and where the sorbose is not separated, such that subsequent steps are conducted on isolated or *in situ* generated sorbose.

[0050] The terms "separating" or "separated" carries their ordinary meaning as would be understood by the skilled artisan, insofar as it connotes separating or isolating the material (e.g., sorbose) from other starting materials or co-products or side-products (impurities) associated with the reaction conditions yielding the material. As such, it infers that the skilled artisan at least recognizes the existence of the product and takes specific action to separate or isolate it. Absolute purity is not required, though preferred, as the material may contain minor amounts of impurities and the separated or isolated material may contain residual solvent or be dissolved within a solvent used in the reaction or subsequent purification of the material.

[0051] The following listing of embodiments is intended to complement, rather than displace or supersede, the previous descriptions.

[0052] Embodiment 1. A process for preparing sorbose from glucose, said process comprising: (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material, or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose; and (b) separating the sorbose.

[0053] Embodiment 2. A process for preparing ascorbic acid, said process comprising: (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material (e.g., MCM-41, MCM-48, SBA-15), or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose; (b) optionally separating the sorbose; and (c) converting the sorbose to ascorbic acid.

[0054] Embodiment 3. The process of Embodiment 1 or 2, wherein the process comprises: (a) contacting the glucose with the silica zeolite containing the Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers under reaction conditions sufficient to isomerize the glucose to sorbose.

[0055] Embodiment 4. The process of any one of Embodiments 1 to 3, wherein the silica zeolite comprises a Ti-Beta zeolite or a Zr-Beta zeolite.

[0056] Embodiment 5. The process of Embodiment 1 or 2, wherein the process comprises: (a) contacting the glucose with the ordered mesoporous silica material (e.g., MCM-41, MCM-48, SBA-15) containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers under reaction conditions sufficient to isomerize the glucose to sorbose.

[0057] Embodiment 6. The process of Embodiment 1 or 2, wherein the process comprises: (a) contacting the glucose with the amorphous silica containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers under reaction conditions sufficient to isomerize the glucose to sorbose.

[0058] Embodiment 7. The process of any one of Embodiments 1 to 6, wherein the silica-containing structure contains Lewis acidic Ti^{4+} framework centers.

[0059] Embodiment 8. The process of any one of Embodiments 1 to 7, wherein the sorbose is L-(-)-sorbose and the glucose is D-(+)-glucose.

[0060] Embodiment 9. The process of any one of Embodiments 2 to 8, wherein the ascorbic acid is L-ascorbic acid.

[0061] Embodiment 10. The process of any one of Embodiments 1 to 9, wherein the reaction conditions comprise contacting the glucose with the silica zeolite, ordered mesoporous silica material, or amorphous silica containing the Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework in the presence of an aqueous or an alcoholic liquid.

[0062] Embodiment 11. The process of any one of Embodiments 1 to 10, wherein the reaction conditions comprise contacting the glucose with the zeolite in the presence of an alcohol.

[0063] Embodiment 12. The process of Embodiment 10 or 11, wherein the alcohol is methanol.

[0064] Embodiment 13. The process of any one of Embodiments 1 to 4 or 6 to 12, wherein the zeolite has a composition such that the atomic ratio of Si to Ti, Zr, or combination of Ti and Zr is in a range of from about 35 to about 250.

[0065] Embodiment 14. The process of Embodiment 13, wherein the the zeolite has a composition such that the atomic ratio of Si to Ti, Zr, or combination of Ti and Zr is in a range of from about 65 to about 120.

[0066] Embodiment 15. The process of any one of Embodiments 1 to 14, wherein the molar ratio of glucose to Ti, Zr, or combination of Ti and Zr is in a range of from about 5 to about 500.

[0067] Embodiment 16. The process of any one of Embodiments 1 to 15, wherein the glucose concentration in aqueous solvent is in a range of from about 0.1 w/w to about 45 w/w, relative to the weight of the solvent.

[0068] Embodiment 17. The process of any one of Embodiments 1 to 16, wherein the glucose concentration in methanol solvent is in a range of from about 0.1 w/w to about 2 w/w, relative to the weight of the solvent.

[0069] Embodiment 18. The process of any one of Embodiment 1 to 17, wherein the reaction conditions comprise heating the reaction mixture to a temperature in a range of from about 60°C to about 200°C, or from about 80°C to about 120°C, or from about 100°C to about 120°C.

[0070] Embodiment 19. The process of any one of Embodiments 1 to 18, wherein the sorbose is separated or isolated by filtration, crystallization, freeze-thawing, chromatographic separation (i.e., employing a column capable of separating the sorbose from other reactants and products), solvent removal (e.g., using a centrifugal evaporator), or a combination thereof.

[0071] Embodiment 20. The process of any one of Embodiments 2 to 19, comprising forming 2-keto-L-gulonic acid by (a) acetal protection of ring hydroxyls followed by the

chemical oxidation of the protected sorbose by hypochlorite or permanganate or (b) oxidation of the sorbose using oxygen and a noble metal catalyst, such as platinum, or by both (a) and (b).

[0072] Embodiment 21. The process of Embodiment 20, further comprising employing conditions to ring close by gamma-lactonization of the 2-keto-L-gulonic acid, with removal of water

[0073] Embodiment 22. The process of any one of Embodiments 2 to 21, wherein converting the sorbose to ascorbic acid comprises a sequential oxidation step followed by a gamma lactonization with removal of water step, for example as practiced in the Reichstein process.

EXAMPLES

[0074] The following Examples are provided to illustrate some of the concepts described within this disclosure. While each Example is considered to provide specific individual embodiments of composition, methods of preparation and use, none of the Examples should be considered to limit the more general embodiments described herein.

[0075] In the following examples, efforts have been made to ensure accuracy with respect to numbers used (e.g. amounts, temperature, etc.) but some experimental error and deviation should be accounted for. Unless indicated otherwise, temperature is in degrees C, pressure is at or near atmospheric.

[0076] Example 1: Overview of Specific Experimental Results

[0077] Silica zeolite beta containing Lewis acidic framework Ti^{4+} (Ti-Beta) has been shown to catalyze the isomerization of D-glucose to L-sorbose apparently (based on the information below) via intramolecular C5-C1 hydride shift steps. Glucose isomerization to sorbose occurred in parallel to isomerization to fructose on Ti-Beta in both water and methanol solvents. At 373 K, fructose was the predominant product in water, while sorbose was the predominant product in methanol. Isotopic tracer studies showed that ^{13}C and D labels placed respectively at the C1 and C2 positions of glucose were retained respectively at the C6 and C5 positions of sorbose, consistent with an intramolecular C5-C1 hydride shift. This direct Lewis acid-mediated pathway for glucose-sorbose isomerization appears to be unprecedented among heterogeneous or biological catalysts, and sharply contrasts indirect base-mediated glucose-sorbose isomerization that proceeds via 3,4-enediol intermediates or via retro-aldol condensation to triose intermediates that undergo subsequent isomerization and realdolization. Measured first-order glucose-sorbose isomerization rate constants (per total Ti; 373 K) for Ti-Beta in methanol were similar for unlabeled glucose and glucose deuterated at the C2 position (within a factor of

~1.1) but were a factor of ~2.3 lower for glucose deuterated at each carbon position; these H/D kinetic isotope effects were consistent with kinetically-relevant intramolecular C5-C1 hydride shift steps. Optical rotation measurements of sugar fractions isolated after the isomerization of D-(+)-glucose (92% enantiomeric purity) with Ti-Beta in water indicated that stereochemistry was preserved at carbon centers not directly involved in intramolecular C5-C1 or C2-C1 hydride shift steps that respectively form L-(-)-sorbose (73%) and D-(-)-fructose (87%) as the predominant stereoisomers. These findings describe a Lewis acid-mediated intramolecular rearrangement of glucose that, in contrast with that involved in isomerization to fructose, does not appear to have an enzymatic analog.

[0078] Example 2: Experimental Methods

[0079] Example 2.1. Catalytic synthesis and characterization

[0080] Procedures to synthesize Ti-Beta zeolites in fluoride media with different Si/Ti ratios were adapted from reported protocols. See Blasco, T., *et al.*, *J. Phys. Chem. B* **1998**, 102, 75-88, which is incorporated by reference herein for its teachings of syntheses. Ti-Beta samples were treated in flowing air ($1.67 \text{ cm}^3 \text{ s}^{-1}$, Air Liquide, breathing grade) at 853 K (0.0167 K s^{-1}) for 12 h prior to characterization and catalytic evaluation. Atomic Si and Ti contents were measured using a JEOL 8200 electron microprobe, operated in focused beam mode with a 40 micron spot size, at 15 kV and 25 nA. The Si/Ti ratio determined by electron microprobe are denoted in the suffix of sample names (e.g., Ti-Beta-79 contains a Si/Ti ratio of 79).

[0081] The crystal structures of all samples, determined from powder X-ray diffraction (XRD) patterns collected using a Rigaku Miniflex II diffractometer and Cu K α radiation, were consistent with the beta topology (**FIG. 2**). N₂ adsorption isotherms (**FIG. 3**) were measured at 77 K using a Quantachrome Autosorb iQ automated gas sorption analyzer, using protocols reported elsewhere, [Gounder, R.; Davis, M. E. *AIChE J.* **2013**, 59, 3349-3358] and gave micropore volumes of $\sim 0.21 \text{ cm}^3 \text{ g}^{-1}$ as expected from the beta topology. Diffuse reflectance UV-Visible spectra of Ti-Beta samples (**FIG. 4**) showed bands centered in the 200-220 nm range, which have been assigned previously to Ti⁴⁺ centers incorporated within zeolite frameworks.

[0082] Example 2.2. Kinetic studies of glucose reactions with Ti-Beta

[0083] Reactions with D-glucose (Sigma-Aldrich, $\geq 99\%$) were conducted in 10 mL thick-walled glass batch reactors (VWR), with temperature control via an oil bath located on a digital stirring hotplate (Fisher Scientific). Typical reactions with D-glucose were carried out at a 1:50 metal:glucose molar ratio and involved contacting 4 g of a 1% (w/w) glucose solution in water or in methanol with the catalytic solids in a stirred glass reactor sealed with a crimp top

(PTFE/silicone septum, Agilent). Kinetic studies using isotopically-labeled glucose were performed using 1% (w/w) solutions of D-glucose-D2 (Cambridge Isotope Laboratories, $\geq 98\%$) or of D-glucose-D_{7-1,2,3,4,5,6,6} (Cambridge Isotope Laboratories, $\geq 98\%$) in methanol.

[0084] Reactors were placed in the oil bath and small aliquots (~50-100 microliters) were extracted at various time intervals via syringe (Hamilton), filtered through a 0.2 micron PTFE filter (National Scientific), and mixed with 1% (w/w) aqueous D-mannitol (Sigma-Aldrich, $\geq 98\%$) solutions used as an internal standard for quantification. The composition of reaction aliquots was determined after separation of compounds in an Agilent 1200 high performance liquid chromatograph (HPLC) equipped with an evaporative light scattering (ELS) detector (Agilent 380 LC). Glucose, sorbose, mannose, fructose, and mannitol fractions were separated using a Hi-Plex Ca column (7.7 x 300 mm, 8 micron particle size, Agilent) held at 353 K, with either ultrapure water (0.010 mL s⁻¹ flow rate) or a 30/70 (v/v) mixture of acetonitrile/water (0.013 mL s⁻¹ flow rate) as the mobile phase.

[0085] Example 2.3. Isotopic and stereochemical characterization of sugars

[0086] Liquid NMR analysis of products formed from isotopic tracer studies using D-glucose-D2 or D-glucose-¹³C-C1 (Cambridge Isotope Laboratories, $\geq 98\%$) reactants involved separation of the glucose, sorbose, and fructose fractions by HPLC, evaporation of H₂O and dissolution in D₂O (Cambridge Isotope Laboratories, 99.9%). ¹H and ¹³C liquid NMR spectra were collected on a 400 MHz NMR spectrometer (Varian) in the Caltech liquid NMR facility. Glucose, sorbose and fructose solids were subsequently isolated by evaporation of D₂O and dissolved in H₂O prior to measurement of optical rotation at 589 nm and ambient temperature using a Jasco P-2000 polarimeter and a 100 mm path-length cell.

[0087] Example 3. Results and Discussion

[0088] Example 3.1. Kinetic studies of glucose isomerization over Ti-Beta

[0089] Monosaccharide yields (w/w) resulting from the reaction of 1% (w/w) glucose solutions in water and in methanol over Ti-Beta samples (373 K) of varying Si/Ti content are shown in **Table 1**; characterization data for the samples used in this study are provided in **Example 2.1**.

[0090] Table 1. Monosaccharide Yields and Turnover Numbers from Glucose Reactions with Ti-Beta and Zr-Beta in Water and Methanol^a

Catalyst	Si/M ratio	Solvent	Glucose:Metal Ratio	Monosaccharide yield (w/w %)					Turnover Number ^b
				Glucose	Sorbose	Mannose	Fructose	Total	
Ti-Beta	66	H ₂ O	32	82	4	< 0.1	11	98	5.0
Ti-Beta	79	H ₂ O	60	81	3	< 0.1	8	93	6.8
Ti-Beta	107	H ₂ O	56	80	4	< 0.1	8	92	6.4
Ti-Beta	202	H ₂ O	69	87	3	< 0.1	6	96	5.8
Zr-Beta	182	H ₂ O	78	90	1.5	< 0.1	6	97	5.8
Ti-Beta	66	CH ₃ OH	30	64	12	1.1	8	85	6.5
Ti-Beta	79	CH ₃ OH	63	79	8	0.7	4	92	8.4
Ti-Beta	107	CH ₃ OH	54	76	9	0.8	4	90	7.9
Ti-Beta	202	CH ₃ OH	119	77	6	0.6	4	88	13.0
Zr-Beta	182	CH ₃ OH	74	70	4	< 0.5	22	95	18.2

^aReaction conditions: 1% (w/w) glucose solutions, 373 K, 2 h.

^bMoles of product monosaccharides formed per moles of total Ti or Zr.

[0091] Reactions of glucose with Ti-Beta in water formed predominantly fructose together with a second previously unidentified hexose sugar, which became the predominant product of glucose reactions with Ti-Beta in methanol solvent (**Table 1**). This unknown hexose product was retained at times nearly identical to (within 0.2 min) that of mannose during chromatographic separation with a Ca Hi-Plex column (7.7 × 300 mm, 8 micron particle size, Agilent) using water as the mobile phase (0.6 mL min⁻¹, 353 K). Mannose and the unknown hexose product were resolved, however, upon changing the mobile phase to a 70/30 (v/v) mixture of acetonitrile/water (0.8 mL min⁻¹, 353 K). ¹H and ¹³C nuclear magnetic resonance (NMR) spectra of this previously unknown hexose product were identical to that of authentic sorbose, the C-5 epimer of fructose, as described in Que, L.; Gray, G. R. *Biochemistry* **1974**, *13*, 146-153.

[0092] Kinetic studies of glucose reactions with Ti-Beta at 373 K, performed in batch reactors using 1% (w/w) glucose solutions in water and in methanol, showed that the evolution of liquid-phase fructose and sorbose concentrations with reaction time were described accurately by rate expressions that were first-order in glucose concentration (**FIG. 5A-B**). Fructose and sorbose were formed at non-zero initial turnover rates and in essentially constant molar ratios as glucose conversion increased from 0-28% (**FIG. 5A-B**), reflecting the formation of both products from parallel and primary reactions of glucose. This kinetic behavior is inconsistent with the formation of sorbose via 3,4-enediol intermediates formed upon sequential

rearrangements of 1,2-enediols, or via sequential retro-aldol condensation of glucose to glyceraldehyde, isomerization to dihydroxyacetone, and realdolization of triose fragments as has been reported with homogeneous or heterogeneous bases. The absence of other ketohexoses (e.g., psicose, tagatose) or trioses in solution after glucose reactions with Ti-Beta (**Table 1**) is also inconsistent with their expected formation during base-catalyzed glucose reactions.

[0093] The evolution of liquid-phase fructose and sorbose concentrations, together with fructose-to-sorbose molar ratios, with reaction time during reaction of 1% (w/w) glucose solutions with Ti-Beta-79 in water and in methanol are shown in **FIG. 5A** and **FIG. 5B**, respectively. The dashed lines in **FIG. 5A-B** reflect best fits of the experimental data to kinetic models derived upon integration of fructose and sorbose formation rates in an ideal, stirred batch reactor, assuming their formation occurs in parallel, reversible reactions of glucose and at rates that are first-order in liquid phase glucose concentration:

$$C_{j(l)}(t) = C_{j(l),eq} (1 - e^{-t/\tau}) \quad (1)$$

In Eq. (1), $C_{j(l)}$ and $C_{j(l),eq}$ are liquid-phase concentrations of product j (fructose, sorbose) at time t and at equilibrium, respectively, and τ is a time constant for the approach to this equilibrium. Initial turnover rates were determined from extrapolation to zero time and provided non-zero values for rates of formation for both fructose and sorbose products, while fructose-to-sorbose molar ratios depended weakly on glucose conversion in water (0-25%) and in methanol (0-28%). Together, these data are consistent with parallel glucose-fructose and glucose-sorbose isomerization reactions in primary reaction steps.

[0094] Example 3.2. Isotopic tracer studies of glucose isomerization over Ti-Beta

[0095] Isotopic tracer studies using glucose reactants labeled with ^{13}C at the C1 position (glucose- ^{13}C -C1) or with D at the C2 position (glucose-D2), together with ^1H and ^{13}C NMR spectroscopic analysis of sugar products fractionated after reaction, were used to confirm the presence of Lewis acid sites on Ti-Beta and to probe the mechanism of glucose-sorbose isomerization. The ^{13}C NMR spectrum of unlabeled glucose is shown in **FIG. 6A** for reference. The glucose fraction isolated after reaction of glucose- ^{13}C -C1 with Ti-Beta in water (373 K) showed resonances at $\delta = 95.8$ and 92.0 ppm (**FIG. 6B**), which respectively correspond to C1 positions in β -pyranose and α -pyranose anomers of glucose. The ^{13}C NMR spectrum of the glucose fraction collected after reaction of glucose-D2 with Ti-Beta in water (373 K) showed low intensity triplets present in place of sharp resonances at $\delta = 74.1$ and 71.3 ppm (**FIG. 6C**) for the C2 positions in β -glucopyranose and α -glucopyranose, respectively. These low intensity

triplets result from the suppression of the nuclear Overhauser enhancement (NOE) of carbon resonances in ^{13}C NMR spectra collected using proton broad-band decoupling caused by the presence of covalently-bonded deuterium. The presence of deuterium at glucose C2 positions was also confirmed by the absence of resonances for C2-H atoms in the corresponding ^1H NMR spectrum (**FIG. 7**). As shown in **FIG. 7A-B**. The absence of resonances near $\delta = 3.1$ ppm reflects the presence of a D label at the C-2 position in glucose, indicating that H/D scrambling did not occur at this position, as also observed previously on Sn-Beta. See Angyal, S. J. *Glycoscience: Epimerisation, Isomerisation and Rearrangement Reactions of Carbohydrates* **2001**, 215, 1-14. These data (**FIG. 6B-C**) confirm that ^{13}C and H/D scrambling in isotopically-labeled glucose reactants does not occur during reaction or chromatographic separation.

[0096] The fructose products formed from reaction of glucose- ^{13}C -C1 and glucose-D2 with Ti-Beta in water contained a ^{13}C label at its C-1 position (fructose- ^{13}C -C1) and a D label at its C1 position (fructose-D1) (**FIG. 8** and **FIG. 9**), respectively, as also observed on Lewis acidic Sn-Beta. See, e.g., Román-Leshkov, Y., *et al.*, *Angew. Chem. Int. Ed.* **2010**, 49, 8954-8957 and Bermejo-Deval, R., *et al.*, *ACS Catal.* **2012**, 2, 2705-2713.

[0097] The ^1H NMR spectrum of the fructose fraction after reaction of glucose-D2 with Ti-Beta in water is shown in **FIG. 8A-B**. The absence of resonances near $\delta = 3.45$ ppm reflects the presence of a D label at the C-1 position in fructose, a consequence of intramolecular C2-C1 hydride shift isomerization, as also observed previously on Sn-Beta. See again, Angyal, S. J. *Glycoscience: Epimerisation, Isomerisation and Rearrangement Reactions of Carbohydrates* **2001**, 215, 1-14.

[0098] The ^{13}C NMR spectrum of unlabeled fructose is shown in **FIG. 9A** for reference. The fructose fraction isolated after reaction of glucose- ^{13}C -C1 with Ti-Beta in water (373 K) showed resonances at $\delta = 63.8$ and 62.6 ppm (**FIG. 9B**), which correspond to C1 positions in β -pyranose and β -furanose anomers of fructose, respectively. The ^{13}C NMR spectrum of the fructose fraction collected after reaction of glucose-D2 with Ti-Beta in water (373 K) showed low intensity triplets present in place of sharp resonances at $\delta = 63.8$ and 62.6 ppm (**FIG. 9C**) for the C1 positions in β -fructopyranose and β -fructofuranose, respectively, reflecting the presence deuterium atoms bound to C1 centers. These data are consistent with the ^1H NMR spectrum shown in **FIG. 8** and confirm the presence of Lewis acidic framework Ti^{4+} centers in Ti-Beta.

[0099] These isotopic tracer studies confirm that glucose-fructose isomerization occurs via an intramolecular hydride shift from the C2 to C1 position, with undetectable contributions from minority base sites that would have otherwise mediated reversible enolization to cause H/D

scrambling at the C2 position of glucose and, in turn, fructose products formed without D atoms retained at their C1 position. From these data, it appears that the Lewis acidic framework Ti^{4+} sites in Ti-Beta are solely responsible for mediating glucose isomerization routes.

[0100] The ^{13}C NMR spectrum of unlabeled sorbose is provided in **FIG. 6D**, together with positional assignments for each carbon atom in α -L-sorbofuranose. The ^{13}C NMR spectrum of the sorbose fraction isolated after reaction of glucose- ^{13}C -C1 with Ti-Beta in water showed a single resonance at $\delta = 61.7$ ppm (**FIG. 6E**), which corresponds to the C-6 position. In contrast, base-mediated glucose- ^{14}C -C1 isomerization via symmetric 3,4-enediol intermediates would form sorbose with ^{14}C labels at both the C1 and C6 positions, while isomerization via sequential retro-aldol condensation, isomerization and realdolization reactions would lead to ^{14}C label redistribution throughout the sorbose backbone. See, e.g., Elkhadem, H. S. *et al.*, *Carbohydrate Research* **1987**, 169, 13-21 and Sowden, J. C., *et al.*, *J. Am. Chem. Soc.* **1958**, 80, 1435-1438. The ^{13}C NMR spectrum of sorbose formed from reaction of glucose-D2 with Ti-Beta showed resonances for all carbon atoms except that for the C5 position at $\delta = 70.3$ ppm (**FIG. 6F**), whose NOE is suppressed by D atoms bound to C5 centers. In contrast, base-mediated glucose isomerization initiated via α -carbonyl proton abstraction would have caused H/D scrambling at C2 positions of glucose and the incorporation of H atoms at C5 positions of sorbose. Thus, ^{13}C and D atoms at glucose C1 and C2 locations are respectively retained at C6 and C5 locations in sorbose upon isomerization (**FIG. 10**). The atomic redistributions involved in isomerization of glucose to sorbose, which occur between opposite ends of ring-opened hexose chains, at first glance appear to require several skeletal rearrangement steps. Yet, in fact, they would only require glucose C1 aldehyde-to-alcohol reduction and C5 alcohol-to-ketone oxidation (**FIG. 10**) either in a concerted or in sequential steps.

[0101] Example 3.3. Proposed mechanism for glucose-sorbose isomerization on Ti-Beta

[0102] While not intending to be bound by the correctness of any particular theory, it is possible that the glucose-sorbose isomerization occurs via a concerted intramolecular MPVO step mediated by an intramolecular hydride shift from the C5 to the C1 position on open glucose chains (**FIG. 11**), in an analogous intramolecular MPVO mechanism for glucose-fructose isomerization mediated by C2-C1 intramolecular hydride shift. Quantum chemical studies of glucose-fructose isomerization on Sn-Beta and Ti-Beta open sites (three framework $-\text{OSi}$ bonds and one $-\text{OH}$ group) have shown that coordination of oxygen atoms in C1-O-C5 ether linkages of cyclic glucose at Lewis acidic framework metal ($\text{M} = \text{Sn}, \text{Ti}$) sites (**1**, **FIG. 11**) and subsequent metal-mediated ring-opening (**2**, **FIG. 11**) results in open-chain glucose bound to

metal centers via O1 and O5 atoms (**3**, **FIG. 11**). Theoretical studies indicate that intramolecular C2-C1 hydride shifts in glucose-fructose isomerization, in fact, requires proton-transfer from M-(OH₂) groups to glucose O5 atoms in intermediate **3** (**FIG. 11**) to form C5-OH groups, desorption of C5-OH groups from M sites, adsorption of C2-OH moieties after rotation of glucose bound solely via O1 atoms, and deprotonation of C2-OH groups by M-OH moieties to enable bidentate coordination of O1 and O2 atoms. *See, e.g.,* Bermejo-Deval, R., et al., *Proc. Natl. Acad. Sci. USA* **2012**, *109*, 9727-9732. Glucose-sorbose isomerization instead would only require an alternate reaction sequence beginning with intermediate **3** (**FIG. 11**), involving intramolecular C5-C1 hydride shift (**4**, **FIG. 11**) to form open-chain sorbose bound via O2 and O6 atoms (**5**, **FIG. 11**), followed by protonation of sorbose O6 atoms to C6-OH groups (**6**, **FIG. 11**) and sorbose ring-closing (**7**, **FIG. 11**). In this proposal, the reaction coordinates for glucose-fructose and glucose-sorbose isomerization share common elementary steps for binding and ring-opening of cyclic glucose at framework metal centers (Steps a and b, **FIG. 11**). These mechanistic features are consistent with the sole formation of fructose and sorbose with Lewis acidic Ti-Beta (**Table 1**) and the absence of psicose and tagatose isomers, which are formed concomitantly with fructose and sorbose via interconvertible enediol intermediates on homogeneous or heterogeneous base catalysts.

[0103] Initial turnover rates (per total Ti; 373 K) for glucose isomerization to sorbose and isomerization to fructose with Ti-Beta in methanol were determined from the evolution of sorbose (**FIG. 12A**) and fructose (**FIG. 12B**) concentrations with reaction time (*see Example 3.1*, above). Measured first-order isomerization rate constants derived from these initial turnover rates (**FIG. 12A** and **FIG. 12B**) when glucose with different locations and amounts of isotopic deuterium labels were used as reactants are shown in **Table 2**.

Table 2. Measured First-Order Rate Constants and H/D Kinetic Isotope Effects (373 K) for Glucose Isomerization to Sorbose and Isomerization to Fructose in Methanol^a

Reactant	Measured rate constant (373 K) (/10 ⁻⁶ mol (mol Ti*s*((mol glucose)*m ⁻³)) ⁻¹)		Kinetic isotope effect (KIE) ^b	
	<i>Sorbose</i>	<i>Fructose</i>	<i>Sorbose</i>	<i>Fructose</i>
Glucose	27 ± 1.3	11 ± 0.6		
Glucose-D2	25 ± 1.2	5.0 ± 0.2	1.1 ± 0.1	2.2 ± 0.3
Glucose-D7- 1,2,3,4,5,6,6	12 ± 0.6	5.4 ± 0.3	2.3 ± 0.2	2.0 ± 0.2

^aCalculated from turnover rates measured on Ti-Beta-79 (shown in **FIG. 12**).

^bGiven by the ratio of the rate constant for non-deuterated glucose relative to that for deuterated reactants.

Rate constants for glucose-fructose isomerization (per total Ti; 373 K) were higher by a factor of ~2.2 for unlabeled glucose than for glucose-D2 (**Table 2**) on Ti-Beta in methanol, consistent with glucose-fructose isomerization via a kinetically-relevant intramolecular C2-C1 hydride shift (See **Example 3.4**, below), as also observed on Sn-Beta and Ti-Beta in water in other studies.. Initial turnover rates for glucose-sorbose isomerization were essentially identical (within a factor of ~1.1) for glucose and glucose-D2 reactants in methanol, indicating that C2-D bonds remain intact during such isomerizations. The reaction of fully-deuterated glucose (glucose-D₇-1,2,3,4,5,6,6) led to an observed KIE for glucose-fructose isomerization of ~2.0 in methanol solvent (**Table 2**), because C2-D bonds are broken in kinetically-relevant steps, and also led to a similar KIE of ~2.3 for glucose-sorbose isomerization (**Table 2**). The KIE values of ~1.1 and ~2.3 for glucose-sorbose isomerization when glucose reactants are deuterated at the C-2 position and at all positions, respectively, reflect the kinetic relevance of C-D bond breaking steps at a position other than C-2. Although we are unable to probe C5-D cleavage directly because glucose-D5 reactants are unavailable, the KIE of ~2.3 observed with fully deuterated glucose reactants is expected from kinetically-relevant C5-D bond cleavage (See **Example 3.4**, below), as required for the proposed intramolecular C5-C1 hydride shift mechanism (**FIG. 11**) and consistent with the isotopic tracer studies (**FIG. 10**) that led to this proposal.

[0104] Example 3.4. Estimation of the kinetic isotope effect for intramolecular H-shift isomerization

[0105] The H/D kinetic isotope effect (KIE) for glucose-fructose isomerization via intramolecular C2-C1 hydride shift at 373 K was estimated from the following expression derived using transition state theory:

$$\frac{k_H}{k_D} = e^{\left(\frac{ZPE_H - ZPE_D}{kT}\right)} = e^{\left(\frac{0.51hc\bar{\nu}_H}{kT}\right)} \quad (S.2)$$

in which

$$ZPE = \frac{1}{2}hc\bar{\nu} \quad (S.3)$$

$$\frac{\bar{\nu}_H}{\bar{\nu}_D} \cong 0.74 \quad (S.4)$$

where h is Planck's constant ($6.63 \times 10^{-34} \text{ m}^2 \text{ kg s}^{-1}$), c is the speed of light ($2.998 \times 10^8 \text{ m s}^{-1}$), k is Boltzmann's constant ($1.38 \times 10^{-23} \text{ m}^2 \text{ kg s}^{-2} \text{ K}^{-1}$), T is the temperature (373 K) and $\overline{\nu_H}$ is the vibrational frequency of a C-H bond scissoring vibration ($\sim 150000 \text{ m}^{-1}$).

[0106] Substitution of these values into Eq. (S.2) gives a value of ~ 2.1 , which is the H/D KIE expected if measured rates were limited by the hydride shift isomerization rates. If reaction rates were limited by intraparticle mass transfer, measured rate constants are proportional to the square root of the reaction rate constant, and the observed H/D KIE is given by:

$$\left(\frac{k_H}{k_D}\right)_{\text{obs}} = \left(\frac{k_H}{k_D}\right)^{0.5} \quad (\text{S.5})$$

or a value of ~ 1.5 .

[0107] The assumption that intramolecular C5-C1 hydride shifts that mediate glucose-sorbose isomerization also involve a C-H bond scissoring vibration ($\sim 150000 \text{ m}^{-1}$) would lead to an equivalent H/D isotope effect of ~ 2.1 for glucose deuterated at the C5 carbon.

[0108] Example 3.5. Stereochemical isomerization mediated by Lewis acid sites

[0109] The proposed glucose-sorbose isomerization mechanism involves the reduction of C1 centers and the oxidation of C5 centers in D-glucose, but does not change the oxidation states or stereochemistry of C2, C3 and C4 centers (**FIG. 10**). Thus, D-glucose isomerization via C5-C1 hydride shift should selectively form L-sorbose, while isomerization via C2-C1 hydride shift should, by a similar argument, selectively form D-fructose. The glucose, sorbose and fructose fractions isolated after reaction of a 10% (w/w) aqueous solution of glucose-D2 with Ti-Beta (373 K, 6 h), and after collection of ^1H and ^{13}C NMR spectra (**FIGs. 6 to 9**) and replacement of D_2O with H_2O as the solvent, were tested for optical activity at ambient temperature at 589 nm. The specific optical rotations of the glucose, sorbose and fructose fractions were $44.7 \pm 0.1^\circ$, $-19.8 \pm 0.6^\circ$ and $-67.6 \pm 2.7^\circ$, respectively (**Table 3**), reflecting the presence of predominantly D-(+)-glucose, L-(-)-sorbose and D-(-)-fructose stereoisomers within the respective fractions.

Table 3. Specific Rotation and Enantiomeric Compositions of Glucose, Sorbose and Fructose Fractions Isolated After Reaction of Glucose-D2 with Ti-Beta in Water^a

Fraction	Specific rotation ^b (°)	Enantiomeric Excess ^c (%)	D-enantiomer (%)	L-enantiomer (%)
Glucose	44.7 ± 0.1	85 ± 0.3	92 ± 1	8 ± 1
Sorbose	-19.8 ± 0.6	46 ± 1.5	27 ± 1	73 ± 1
Fructose	-67.6 ± 2.7	73 ± 3	87 ± 2	13 ± 2

^a Reaction conditions: 10% (w/w) aqueous glucose-D2 solution, Ti-Beta-79, 373 K, 6 h.

^b Optical rotations measured at 589 nm at ambient temperature.

^c Calculated assuming each sugar fraction contained only a mixture of the two enantiomers, using the following enantiomer optical rotation values: D-(+)-glucose: 52.7°, L-(-)-sorbose: -42.7°, D-(-)-fructose: -92.4°.

Table 3 also shows estimated values for the enantiomeric excess and composition of each fraction, indicating that isomerization reactions of D-(+)-glucose-D2 (92% enantiomeric purity) with Ti-Beta selectively formed L-(-)-sorbose-D5 (73%) and D-(-)-fructose-D1 (87%).

[0110] The predominant formation of L-(-)-sorbose and D-(-)-fructose from reactions of D-(+)-glucose with Ti-Beta is consistent with intramolecular hydride shift isomerizations mediated by Lewis acidic Ti centers, and specifically with the intramolecular C5-C1 hydride shift proposed for glucose-sorbose isomerization (**FIG. 11**). Such stereochemical specificity is in sharp contrast to that expected from base-catalyzed D-glucose isomerization via 3,4-enediol intermediates, which leads to the predominant formation of D-(+)-sorbose (68%) over L-(-)-sorbose (32%).²⁷ Such stereospecificity also contrasts sharply that expected from base-mediated retro aldol condensation to L-glyceraldehyde and realdolization with dihydroxyacetone, which would form similar amounts of L-(-)-sorbose and L-(+)-fructose.

[0111] Direct glucose-fructose isomerization via intramolecular C2-C1 hydride shifts mediated by Ti-Beta has known metalloenzyme analogs (e.g., D-xylose isomerase),¹¹⁻¹² in which two divalent cations in enzyme active site pockets must interact in a concerted manner with glucose O1 and O2 atoms prior to isomerization. In contrast, direct glucose-sorbose isomerization via intramolecular C5-C1 hydride shifts mediated by Ti-Beta does not appear to have a known enzymatic analog. As a result, currently known routes for D-glucose to L-sorbose isomerization appear to require sequential reduction to a sugar alcohol and oxidation to sorbose, mediated either by a metal-enzyme or an enzyme-enzyme pair. This observation suggests that enzymatic active sites that selectively bind glucose via O1 and O5 atoms may not be as prevalent as those that bind glucose via O1 and O2 atoms, in part, resulting in the scarcity of L-sorbose

found in nature, relative to the seven most abundant hexose and pentose sugars. These findings indicate that Lewis acidic metal centers in synthetic molecular sieve frameworks that can coordinate selectively with two oxygenated moieties along sugar backbones may be able to facilitate direct and stereospecific sugar rearrangements that occur rarely in biological systems.

[0112] As those skilled in the art will appreciate, numerous modifications and variations of the present invention are possible in light of these teachings, and all such are contemplated hereby. For example, in addition to the embodiments described herein, the present invention contemplates and claims those inventions resulting from the combination of features of the invention cited herein and those of the cited prior art references which complement the features of the present invention. Similarly, it will be appreciated that any described material, feature, or article may be used in combination with any other material, feature, or article, and such combinations are considered within the scope of this invention.

[0113] The disclosures of each patent, patent application, and publication cited or described in this document are hereby incorporated herein by reference, each in its entirety, for all purposes.

What is Claimed:

1. A process for preparing sorbose from glucose, said process comprising:
 - (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material, or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose; and
 - (b) separating the sorbose.
2. A process for preparing ascorbic acid, said process comprising:
 - (a) contacting the glucose with a silica-containing structure comprising a zeolite having a topology of a 12 membered-ring or larger, an ordered mesoporous silica material, or an amorphous silica, said structure containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers, said contacting conducted under reaction conditions sufficient to isomerize the glucose to sorbose;
 - (b) optionally separating the sorbose; and
 - (c) converting the sorbose to ascorbic acid.
3. The process of claim 1 or 2, wherein the process comprises:
 - (a) contacting the glucose with the silica zeolite containing the Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers under reaction conditions sufficient to isomerize the glucose to sorbose.
4. The process of claim 1 or 2, wherein the silica zeolite comprises a Ti-Beta zeolite
5. The process of claim 1 or 2, wherein the process comprises:
 - (a) contacting the glucose with the ordered mesoporous silica material containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers under reaction conditions sufficient to isomerize the glucose to sorbose.
6. The process of claim 1 or 2, wherein the process comprises:

(a) contacting the glucose with the amorphous silica containing Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework centers under reaction conditions sufficient to isomerize the glucose to sorbose.

7. The process of claim 1 or 2, wherein the silica-containing structure contains Lewis acidic Ti^{4+} framework centers.

8. The process of claim 1 or 2, wherein the sorbose is L-(-)-sorbose and the glucose is D-(+)-glucose.

9. The process of claim 2, wherein the ascorbic acid is L-ascorbic acid.

10. The process of claim 1 or 2, wherein the reaction conditions comprise contacting the glucose with the silica zeolite, ordered mesoporous silica material, or amorphous silica containing the Lewis acidic Ti^{4+} or Zr^{4+} or both Ti^{4+} and Zr^{4+} framework in the presence of an aqueous or an alcoholic medium.

11. The process of claim 1 or 2, wherein the reaction conditions comprise contacting the glucose with the zeolite in the presence of an alcohol.

12. The process of claim 10, wherein the alcohol is methanol.

13. The process of claim 1 or 2, wherein the zeolite has a composition such that the atomic ratio of Si to Ti, Zr, or combination of Ti and Zr is in a range of from about 35 to about 250.

14. The process of claim 13, wherein the zeolite has a composition such that the atomic ratio of Si to Ti, Zr, or combination of Ti and Zr is in a range of from about 65 to about 120.

15. The process of claim 1 or 2, wherein the molar ratio of glucose to Ti, Zr, or combination of Ti and Zr, is in a range is in a range of from about 5 to about 500.

16. The process of claim 1 or 2, wherein the glucose concentration in aqueous solvent is in a range of from about 0.1 w/w to about 45 w/w, relative to the weight of the solvent.

17. The process of claim 1 or 2, wherein the glucose concentration in methanol solvent is in a range of from about 0.1 w/w to about 2 w/w, relative to the weight of the solvent.
18. The process of claim 1 or 2, wherein the reaction conditions comprise heating the reaction mixture to a temperature in a range of from about 60°C to about 200°C (temperature at which the glucose degrades in the solvent), preferably from about 80°C to about 120°C, more preferably from about 100°C to about 120°C.
19. The process of claim 1 or 2, wherein the sorbose is separated or isolated by filtration, crystallization, freeze-thawing, chromatographic separation, solvent removal, or a combination thereof.
20. The process of claim 2, wherein converting the sorbose to ascorbic acid comprises a sequential oxidation step followed by a step of gamma lactonization with removal of water.

1/10

FIG. 1A-B

FIG. 1A





FIG. 1B



2/10

FIG. 2




FIG. 3




FIG. 4




FIG. 5A-B




FIG. 6A-F

5/10




FIG. 7A-B






FIG. 7B




6/10

FIG. 8

7/10

FIG. 9A-C



8/10

FIG. 10





FIG. 11A



9/10

FIG. 11B







FIG. 12A-B



10/10

FIG. 13



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2014/020530**A. CLASSIFICATION OF SUBJECT MATTER****C07H 3/02(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C07H 3/02; C07H 1/00; C07D 307/58

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) & Keywords: isomerization, sorbose, glucose, zeolite, silica material, Lewis acid, ascorbic acid

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2011-0207923 A1 (MOLINER-MARIN, MANUEL et al.) 25 August 2011 See claims 1, 4 and 12; paragraphs [0063]-[0064] and [0091].	1-20
A	US 2002-0076771 A1 (KUMAR, MANOJ) 20 June 2002 See claims 1 and 5-6.	1-20
A	US 4373025 A (NEUZIL, RICHARD W. et al.) 08 February 1983 See claim 1.	1-20
A	US 6284499 B1 (KISHIMOTO, KATSUMITSU et al.) 04 September 2001 See claim 1.	1-20
A	WO 2006-134374 A2 (SCOTTISH CROP RESERTCH INSTITUTE) 21 December 2006 See claim 1.	1-20



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

17 July 2014 (17.07.2014)

Date of mailing of the international search report

17 July 2014 (17.07.2014)

Name and mailing address of the ISA/KR

International Application Division
Korean Intellectual Property Office
189 Cheongsu-ro, Seo-gu, Daejeon Metropolitan City, 302-701,
Republic of Korea

Facsimile No. +82-42-472-7140

Authorized officer

HEO, Joo Hyung

Telephone No. +82-42-481-8150



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2014/020530

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2011-0207923 A1	25/08/2011	EP 2526109 A2 EP 2526109 A4 KR 20120109630 A WO 2012-050625 A2 WO 2012-050625 A3	28/11/2012 03/07/2013 08/10/2012 19/04/2012 19/07/2012
US 2002-0076771 A1	20/06/2002	AT 329050 T AU 2000-09300 A BR 9916460 A CA 2353558 A1 CA 2353558 C CN 1249220 C CN 1331750 A CZ 20011944 A3 CZ 296125 B6 DE 69931807 D1 DE 69931807 T2 DK 1135517 T3 EP 1135517 A1 EP 1135517 B1 ES 2267308 T3 JP 2002-531136 A PL 348509 A1 PT 1135517 E US 2002-0090688 A1 US 2002-0090689 A1 US 6358715 B1 US 6808918 B2 US 6824996 B2 WO 00-34502 A1	15/06/2006 26/06/2000 04/09/2001 15/06/2000 22/11/2011 05/04/2006 16/01/2002 12/09/2001 11/01/2006 20/07/2006 04/01/2007 09/10/2006 26/09/2001 07/06/2006 01/03/2007 24/09/2002 20/05/2002 31/10/2006 11/07/2002 11/07/2002 19/03/2002 26/10/2004 30/11/2004 15/06/2000
US 4373025 A	08/02/1983	None	
US 6284499 B1	04/09/2001	AT 163969 T CN 1029322 C CN 87108309 A DE 3752177 D1 DE 3752177 T2 DE 3784677 D1 DE 3784677 T2 DK 173550 B1 DK 679087 A DK 679087 D0 EP 0273648 A2 EP 0273648 A3 EP 0273648 B1 EP 0477997 A1 EP 0477997 B1 ES 2039464 T3	15/03/1998 12/07/1995 28/09/1988 16/04/1998 02/07/1998 15/04/1993 17/06/1993 19/02/2001 26/06/1988 22/12/1987 06/07/1988 21/09/1988 10/03/1993 01/04/1992 11/03/1998 01/10/1993

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2014/020530

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		IE 59996 B1	18/05/1994
		IE 873473 L	25/06/1988
WO 2006-134374 A2	21/12/2006	GB 0512150 D0	20/07/2005
		WO 2006-134374 A3	19/04/2007