

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 September 2010 (10.09.2010)

PCT

(10) International Publication Number
WO 2010/101738 A1

(51) International Patent Classification:
C09J 7/02 (2006.01) C09J 153/00 (2006.01)

(21) International Application Number:
PCT/US2010/025045

(22) International Filing Date:
23 February 2010 (23.02.2010)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09154408.0 5 March 2009 (05.03.2009) EP

(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **WELKE, Siegfried K.** [DE/DE]; Carl-Schurz-Strasse 1, 41453 Neuss (DE). **PASCHMANN, Volker** [DE/DE]; Carl-Schurz-Strasse 1, 41453 Neuss (DE).

(74) Agents: **SPIELBAUER, Thomas M.** et al.; 3M Center, Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: ADHESIVE ARTICLE COMPRISING AN ACRYLIC FOAM LAYER

(57) Abstract: The present disclosure provides an adhesive article comprising a foam layer having first and second major sides and a pressure sensitive adhesive layer associated with at least one of the major sides for the foam layer, said pressure sensitive adhesive layer comprising a cross-linked rubber and wherein the foam layer comprises an acrylic polymer obtainable by polymerization a polymerizable composition comprising one or more alkyl acrylates having an average of 3 to 14 carbon atoms in the alkyl groups, one or more polar monomers and one or more multi-functional monomers having at least two free radical polymerizable groups.



WO 2010/101738 A1

ADHESIVE ARTICLE COMPRISING AN ACRYLIC FOAM LAYER

[0001] The present disclosure relates to an adhesive article comprising an acrylic foam layer and a pressure sensitive adhesive layer that comprises a cross-linked rubber. The disclosure further relates to making the adhesive article and use thereof.

[0002] Adhesives and tapes are commonly used to bond two substrates together to form a bonded composite. Particular adhesive tapes include those that have a foam layer. Such tapes or adhesive articles are used for example in the automotive industry where they may be employed to bond various components to the body of a car or other motor vehicle. Typically they are used to bond such parts as emblems, plastic parts as well as rubber gaskets to doors.

Examples of adhesive tapes are disclosed in for example WO 2008/070386, US 6,503,621 and US 4,415,615.

15

[0003] While a vast array of adhesives and tapes are available, advances in substrates and end use requirements continues to drive a need for new adhesive formulations and tape constructions. For example, developments in paints and coatings on automotive parts to which the adhesive tapes are to be bonded have proven to be particularly challenging. Typically, these coatings and paints have low surface energy, requiring the development of special adhesive tapes. Likewise, there is a continuing trend in the transportation sector and in particular in the automotive industry to further reduce weight of for example cars in order to save on fuel consumption. This trend is leading to use and application of adhesive tapes where they have previously not been used or to the application of tapes in new configurations that are more demanding for example in stress-strain to which the adhesive tape may be subjected. In addition to performance properties, environmental regulations and processing costs also influence product formulation requirements.

[0004] It would thus be desirable to find further adhesive articles that have one or more improved performance properties. For example, it would be desirable to find an adhesive article that has improved adhesive performance in adhering to low energy surfaces such as

30

for example paint and coating surfaces of automotive parts. It would furthermore be desirable to find adhesive articles that can be readily manufactured in an economical and cost effective way. Yet further, it would be desirable to find adhesive articles that have good environmental properties. Also, adhesive articles that are compatible with existing manufacturing methods that employ adhesive articles would be desirable.

[0005] In one aspect, the present disclosure provides an adhesive article comprising a foam layer having first and second major sides and a pressure sensitive adhesive layer associated with at least one of the major sides for the foam layer, said pressure sensitive adhesive layer comprising a cross-linked rubber and wherein the foam layer comprises an acrylic polymer obtainable by polymerization a polymerizable composition comprising one or more alkyl acrylates having an average of 3 to 14 carbon atoms in the alkyl groups, one or more polar monomers and one or more multi-functional monomers having at least two free radical polymerizable groups.

[0006] The term “associated with” as used in connection with the present disclosure means that the relevant layer is provided directly on the surface or indirectly through the intermediary of one or more layers such as primer layers for example.

[0007] It has been found that that the adhesive articles show good to excellent adhesive performance. For example, they may provide good or excellent adhesive performance to low energy surface, including good 90° peel adhesion performance as well as performance under static and dynamic shear testing.

[0008] In a further aspect of the present disclosure, there is provided a method of making the adhesive article comprising:

- (i) making a foam layer having first and second major sides by (a) providing a polymerizable composition comprising one or more alkyl acrylates having an average of 3 to 14 carbon atoms in the alkyl groups, one or more polar monomers and one or more multi-functional monomers having at least two free radical polymerizable groups, (b) frothing said polymerizable composition and (c) polymerizing said polymerizable composition;

- (ii) applying a pressure sensitive adhesive composition comprising a cross-linkable rubber on one or both of said first and second major sides of said foam layer so as to form a pressure sensitive adhesive layer; and
- (iii) cross-linking said cross-linkable rubber.

5

[0009] In yet a further aspect, the present disclosure provides a use of the adhesive article comprising adhering the adhesive article to a substrate through said pressure sensitive adhesive layer.

[0010] Particular embodiments of the present disclosure are summarized as follows:

- 10 1. Adhesive article comprising a foam layer having first and second major sides and a pressure sensitive adhesive layer associated with at least one of the major sides for the foam layer, said pressure sensitive adhesive layer comprising a cross-linked rubber and wherein the foam layer comprises an acrylic polymer obtainable by polymerization a polymerizable composition comprising one or more alkyl acrylates
15 having an average of 3 to 14 carbon atoms in the alkyl groups, one or more polar monomers and one or more multi-functional monomers having at least two free radical polymerizable groups.
2. Adhesive article according to embodiment 1 wherein said polymerizable composition
20 comprises 83 to 97 % by weight of said alkyl acrylates, 3 to 16 % by weight of said polar monomers and 0.01 to 1 % by weight of said multi-functional monomers.
3. Adhesive article according to embodiment 1 or 2 wherein said foam layer further
25 comprises a thixotropic agent.
4. Adhesive article according to embodiment 3 wherein said thixotropic agent comprises
fumed silica.
5. Adhesive article according to any of the previous embodiments wherein said foam
30 layer comprises a frothed foam.

6. Adhesive article according to any of the previous embodiments wherein said pressure sensitive adhesive layer comprises an acrylic pressure sensitive adhesive component.
7. Adhesive article according to embodiment 6 wherein said acrylic pressure sensitive
5 adhesive component comprises an acrylic polymer having repeating units derived from one or more alkyl acrylates having 3 to 14 carbon atoms in the alkyl group and one or more polar monomers.
8. Adhesive article according to any of the previous embodiments wherein said polar
10 monomers are selected from the group consisting of acrylic acids, itaconic acid, acrylamides, acrylonitrile, N-vinylpyrrolidone, N-vinyl caprolactam and combinations thereof.
9. Adhesive article according to any of the previous embodiments wherein cross-linked
15 rubber comprises a cross-linked block copolymer having a rubbery block and a glassy block.
10. Adhesive article according to embodiment 9 wherein said rubbery block comprises a
20 first polymerized conjugated diene, a hydrogenated derivative thereof, or combinations thereof and wherein said glassy block comprises a monovinyl aromatic monomer.
11. Adhesive article according to embodiment 9 or 10 wherein said pressure sensitive
25 adhesive layer comprises 30 to 50 parts by weight based on the total weight of the pressure sensitive adhesive layer, of said block copolymer and from 0.1 to 10 parts by weight based on the total weight of the pressure sensitive adhesive layer, of said acrylic pressure sensitive adhesive component.
12. Adhesive article according to embodiment 9 or 10 wherein said pressure sensitive
30 adhesive layer comprises 10 to 20 parts by weight based on the total weight of the pressure sensitive adhesive layer, of said block copolymer and from 40 to 60 parts by weight based on the total weight of the pressure sensitive adhesive layer, of said

acrylic pressure sensitive adhesive component.

13. Adhesive article according to any of the previous embodiments wherein each of said first and second major side of said adhesive article have associated with them said pressure sensitive adhesive layer.
14. Adhesive article according to any of embodiments 1 to 12 wherein said adhesive article has said pressure sensitive adhesive layer associated with said first major side and wherein said second major side does not have an adhesive layer associated with it.
15. Adhesive article according to any of embodiments 1 to 12 wherein said adhesive article has said pressure sensitive adhesive layer associated with said first major side and wherein said second major side has a further adhesive layer associated with it.
16. Adhesive article according to embodiment 13 wherein said further adhesive layer comprises a pressure sensitive adhesive component or a heat activatable adhesive component.
17. Adhesive article according to any of the previous embodiments wherein the thickness of said foam layer is between 0.3 mm and 2 mm and wherein the weight per area of said pressure sensitive adhesive layer is between 40 g/m² and 100 g/m².
18. Method of making an adhesive article as embodied in any of embodiments 1 to 17 comprising:
- (i) making a foam layer having first and second major sides by (a) providing a polymerizable composition comprising one or more alkyl acrylates having an average of 3 to 14 carbon atoms in the alkyl groups, one or more polar monomers and one or more multi-functional monomers having at least two free radical polymerizable groups, (b) frothing said polymerizable composition and (c) polymerizing said polymerizable composition;

- (ii) applying a pressure sensitive adhesive composition comprising a cross-linkable rubber on one or both of said first and second major sides of said foam layer so as to form a pressure sensitive adhesive layer; and
- (iii) cross-linking said cross-linkable rubber.

5

19. Method according to embodiment 18 wherein said cross-linking comprises exposing said cross-linkable rubber to e-beam radiation.

20. Method according to embodiment 19 wherein said pressure sensitive adhesive composition is provided directly onto said foam layer and wherein said e-beam is focused at or in the proximity of an interface defined between said foam layer and said pressure sensitive adhesive composition.

21. Method according to any of embodiments 18 to 20 wherein said polymerizable composition comprises a UV-photosensitive initiator and wherein said polymerizable composition is exposed to UV-light.

22. Method according to any of embodiments 18 to 21 wherein said frothing is carried out prior to or simultaneous with said polymerization.

20

23. Method according to any of embodiments 18 to 22 wherein said frothing is carried out by whipping the polymerizable composition with an inert gas.

24. Use of an adhesive article according to any of embodiments 1 to 17 comprising adhering said adhesive article to a substrate through said pressure sensitive adhesive layer.

25

25. Use of an adhesive article according to embodiment 24 wherein said substrate has a surface having a surface energy of less than 45 dynes/cm and said adhesive article is adhered to said surface through said pressure sensitive adhesive layer.

30

26. Use of an adhesive article according to any of embodiments 24 or 25 wherein said adhesive article comprises a further adhesive layer on a major side opposite to the side comprising the pressure sensitive adhesive layer and wherein said adhesive article is adhered to a rubber gasket through said further adhesive layer.

5

Definitions:

[0011] In the disclosure of the present application the following terms are defined as follows unless otherwise indicated:

10 [0012] “acrylic” is used to identify both acrylic as well as methacrylic monomers and polymers.

[0013] “mono-functional monomer” means a monomer having only one polymerizable group.

[0014] “multi-functional monomer” means a monomer having two or more polymerizable groups.

15 [0015] Any ranges identified in the present application are to be understood as including the end points unless expressly stated otherwise.

[0016] The term “pressure sensitive adhesive” is used to indicate materials that materials (e.g., elastomers) that are either inherently tacky or that have been tackified with the addition of tackifying resins. Pressure sensitive adhesives according to the present disclosure include those that can be identified by any of the known methods for identifying pressure sensitive adhesives and include in particular those that can be identified by one or more of the following methods. According to a first method, pressure sensitive adhesives may be defined by the Dahlquist criteria described in Handbook of Pressure Sensitive Adhesive Technology, D. Satas, 2nd ed., page 172 (1989) at use 25 temperatures. This criterion defines a good pressure sensitive adhesive as one having a 1 second creep compliance of greater than $1 \times 10^{-6} \text{ cm}^2/\text{dyne}$. Alternatively, since modulus is, to a first approximation, the inverse of compliance, pressure sensitive adhesives may be defined as adhesives having a modulus of less than $1 \times 10^6 \text{ dynes/cm}^2$.

[0017] Another method of identifying a pressure sensitive adhesive is that it is aggressively and permanently tacky at room temperature and firmly adheres to a variety of dissimilar surfaces upon mere contact without the need of more than finger or hand pressure as described in "Glossary of Terms Used in the Pressure Sensitive Tape Industry" provided by the Pressure Sensitive Tape Council, August, 1985.

[0018] Another suitable method of identifying a pressure sensitive adhesive is that it preferably has a room temperature storage modulus within the area defined by the following points as plotted on a graph of modulus versus frequency at 25°C: a range of moduli from approximately 2×10^5 to 4×10^5 dynes/cm² at a frequency of approximately 0.1 radian/second (0.017 Hz), and a range of moduli from approximately 2×10^6 to 8×10^6 dynes/cm² at a frequency of approximately 100 radians/second (17 Hz) (for example, see Figure 8-16 on p. 173 Handbook of Pressure Sensitive Adhesive Technology, D. Satas, 2nd ed., (1989)).

In the following, the invention will be described in more detail with reference to particular embodiments without however the intention to limit the invention.

[0019] The adhesive article comprises a foam layer having an acrylic polymer obtainable by polymerization of a polymerizable composition comprising one or more alkyl acrylates having an average of 3 to 14 carbon atoms in the alkyl group, one or more polar monomers and one or more multi-functional monomers having at least two free radical polymerizable groups.

[0020] The one or more alkyl acrylates of the polymerizable composition are typically mono-functional monomers and include in particular acrylic acid ester of a nontertiary alcohol in which the alkyl group contains at least about 3 carbon atoms (on average), and preferably about 4 to about 14 carbon atoms (on average). Typically, the homopolymers of such monomers have a Tg of no greater than about 0°C. Examples of classes of suitable acrylic acid esters include, but are not limited to, 2-methylbutyl acrylate, 2-ethylhexyl acrylate, isooctyl acrylate, lauryl acrylate, n-decyl acrylate, 4-methyl-2-pentyl acrylate, isoamyl acrylate, sec-butyl acrylate, and isononyl acrylate. Preferred acrylic acid esters that can be used include, but are not limited to, 2-ethylhexyl acrylate, isooctyl acrylate, lauryl acrylate, and 2-methylbutyl acrylate. Various combinations of such

monomers can be employed. For example, a combination of two or more alkyl acrylates may be used such as a combination of 2-ethylhexyl acrylate and isooctyl acrylate.

[0021] The polymerizable composition further includes one or more polar monomers, typically monofunctional polar monomers. Examples thereof include in particular acidic monomers such as carboxylic acid monomers as well as various acrylamides. Particular
5 examples of polar monomers include acrylic acid, methacrylic acid, itaconic acid, maleic acid, fumaric acid, 2-hydroxyethyl acrylate or methacrylate, N-vinyl pyrrolidone, N-vinyl caprolactam, acrylamide, methacrylamide, N-substituted and N,N-disubstituted acrylamides such as N-ethyl acrylamide, N-hydroxyethyl acrylamide, N,N-dimethyl
10 acrylamide, N,N-diethyl acrylamide, and N-ethyl,N-dihydroxyethyl acrylamide, acrylonitrile, methacrylonitrile and maleic anhydride. Preferred polar monomers include, but are not limited to, acrylic acid, itaconic acid, N,N-dimethyl acrylamide, acryl amide, N-vinyl pyrrolidone and N-vinyl caprolactam. Various combinations of such polar monomers can be employed and in a particular embodiment a combination of two or more
15 polar monomers is contemplated such as for example a combination of acrylic acid and itaconic acid.

[0022] The polymerizable composition from which the acrylic polymer of the foam layer can be derived further includes one or more multi-functional monomers that have two or more ethylenically unsaturated groups. Examples of multi-functional monomers
20 include in particular multi-functional acrylic monomers but other multi-functional monomers such as butadiene and substituted triazines such as vinyl-halomethyl-s-triazine type compounds such as for example 2,4-bis(trichloromethyl)-6-p-methoxystyryl-s-triazine. Preferred are polyacrylic-functional monomers such as, for example, pentaerythritol tetraacrylate, tripropyleneglycoldiacrylate, 1,12-dodecanediol diacrylate.
25 Particular preferred examples of multi-functional acrylic monomers include 1,2 ethylene glycol diacrylate, hexane diol diacrylate and trimethylol propane triacrylate.

[0023] The acrylic polymer of the foam layer is typically obtainable from a polymerizable composition having a major amount of the one or more alkyl acrylates, for example at least 84% by weight (based on the total weight of monomers in the
30 composition). A typical range is from 84 to 97% by weight or from 88 to 94% by weight. The amount of multi-functional monomer or monomers in the polymerizable composition

is typically at least 0.01% by weight and may range for example from 0.01% by weight to 1% or less by weight of the total weight of monomers in the composition or for example from 0.1 to 0.5% by weight. The polar monomer or monomers are typically present in amount of at least 3% by weight of the total weight of monomers in the composition, an
5 exemplary range being from 3 to 16% or from 5 to 12% by weight.

[0024] The polymerizable composition may contain further components including in particular a thixotropic agent. Examples of thixotropic agents include fumed silica. The polymerizable composition may also contain microsphere such as for example hollow glass bubbles or polymeric microspheres. Furthermore, it may be desirable to include a
10 surfactant in the polymerizable composition. Tackifiers, in particular tackifiers suitable for use with acrylic adhesives may be added as well. Examples thereof include in particular rosin esters, aromatic resins, aliphatic resins, terpenes and partially hydrogenated and hydrogenated resins.

[0025] The polymerizable composition typically also includes an initiator for initiating
15 a free radical polymerization including thermal as well as photo-initiators. Photoinitiators are preferred for use in connection with this disclosure. Examples of initiators can be found in U.S. Patent Nos. 4,181,752 (Martens et al.), 4,833,179 (Young et al.), 5,804,610 (Hamer et al.), 5,382,451 (Johnson et al.), 4,619,979 (Kotnour et al.), 4,843,134 (Kotnour et al.), and 5,637,646 (Ellis). A particular example includes 2,2 dimethoxy-2-
20 phenylacetophenone.

[0026] The foam layer of the adhesive article will typically have a thickness of at least 0.3 mm, for example at least 0.5mm. A typical thickness range for the foam layer is from 0.3 mm upto 2 mm, for example from 0.5 mm upto 1.5 mm or from 0.7 mm to 1.2 mm. The foam layer typically has a cellular membrane structure which may have 15 to 85% of
25 voids.

[0027] The foam layer is typically obtained and produced according to the methods described in US 4,415,615. The process typically comprises frothing the polymerizable composition, coating the froth on a backing such as for example a release liner and polymerizing the polymerizable composition.

[0028] Frothing is conveniently accomplished by whipping a gas into the polymerizable composition. Useful frothing gases typically are inert and include nitrogen gas or carbon dioxide. In a particular embodiment, the monomers of the polymerizable composition may be partially polymerized prior to frothing so as to achieve a desirable viscosity for the
5 frothing step. Useful viscosities to froth a composition are typically between 1000 and 40,000 cps. The viscosity is typically selected so as to achieve a desired cell uniformity. For example, above 5000 cps, a higher cell uniformity will typically be obtained.

[0029] Additionally and alternatively to using prepolymerization to achieve a desired viscosity, a thixotropic agent such as fumed silica may be used. In such case,
10 polymerization may be carried out in one step.

[0030] Polymerization of the polymerizable composition may be carried out by heat activation but is preferably is photoinitiated and hence the polymerizable composition will typically contain a photoinitiator. Typically, photoinitiation is carried out by UV irradiation and a UV initiator will be used. If the polymerization is carried out in two
15 steps (in case of pre-polymerization to enable a suitable viscosity as described above), the amount of photo-initiator initially used may be enough to allow initiation of further polymerization. Typically however, a further addition of photoinitiator may be desired to initiate further polymerization following frothing.

[0031] When the polymerization is to be effected by ultraviolet radiation, the
20 polymerizable coating is preferably protected from air by a plastic film overlay which is fairly transparent to ultraviolet radiation and has a low-adhesion surface. Biaxially-oriented polyethylene terephthalate film which is about 75% transparent to ultraviolet radiation is very useful. If the underlying backing also has a low-adhesion surface, both the backing and the transparent plastic film can be stripped away so that the cellular
25 adhesive membrane may be used for mounting objects. For such use, the cellular membrane may be reinforced by a tissue-like web to avoid becoming distorted if it is to be removed from both the backing and the transparent overlay before being applied.

[0032] If instead of covering the polymerizable coating, the polymerization is to be carried out in an inert atmosphere, the permissible oxygen content of the inert atmosphere
30 can be increased by mixing into the polymerizable composition an oxidizable tin

compound as taught in U.S. Pat. No. 4,303,485 (Levens), which also teaches that by doing so, thick coatings can be polymerized in air.

[0033] Regardless of the process by which the cellular structure of the adhesive membrane is created, it is preferred to include a surfactant in the composition, preferably a
5 silicone or a fluorochemical known to be useful for foaming organic liquids that have low surface tension. By doing so, foams with cellular adhesive membranes of good uniformity can be produced wherein the cells have an average diameter within the range of 0.05 to 0.3 mm. Typically, 90% of the cells of the adhesive membrane vary in size no more than 2:1, but some of the adhesive membranes have been characterized by significant variations in
10 cell size.

[0034] On one or both opposite major sides of the foam layer is provided a pressure sensitive adhesive layer (also called skin layer) that comprises a cross-linked rubber. The cross-linked rubber may be obtained from crosslinking, typically through e-beam, of a cross-linkable block copolymer that has a rubbery block and a glassy block. Generally, a
15 rubbery block exhibits a glass transition temperature (T_g) of less than room temperature. In some embodiments, the T_g of the rubbery block is less than about 0 °C, or even less than about -10 °C. In some embodiments, the T_g of the rubbery block is less than about -40 °C, or even less than about -60 °C.

[0035] Generally, a glassy block exhibits a T_g of greater than room temperature. In
20 some embodiments, the T_g of the glassy block is at least about 40 °C, at least about 60 °C, at least about 80 °C, or even at least about 100 °C.

[0036] A suitable block copolymer includes one or more a rubbery blocks, R, and one or more glassy blocks, G. In some embodiments, the block copolymer comprises at least three glassy blocks. In some embodiments, the block copolymer comprises between three
25 and five glassy blocks, inclusive. In some embodiments, the block copolymer comprises four glassy blocks.

[0037] In some embodiments, the block copolymer is a multi-arm block copolymer having the general formula Q_n-Y, wherein Q represents an arm of the multi-arm block copolymer; n represents the number of arms and is a whole number of at least 3; and Y is

the residue of a multifunctional coupling agent. Each arm, Q, independently has the formula R-G, wherein G represents the glassy block; and R represents the rubbery block.

[0038] In some embodiments, the rubbery block comprises a polymerized conjugated diene, a hydrogenated derivative of a polymerized conjugated diene, or combinations thereof. In some embodiments, the conjugated dienes comprise 4 to 12 carbon atoms. Exemplary conjugated dienes include butadiene, isoprene, ethylbutadiene, phenylbutadiene, piperylene, pentadiene, hexadiene, ethylhexadiene, and dimethylbutadiene. The polymerized conjugated dienes may be used individually or as copolymers with each other. In some embodiments, the conjugated diene is selected from the group consisting of isoprene, butadiene, ethylene butadiene copolymers, and combinations thereof.

[0039] In some embodiments, at least one glassy block comprises a polymerized monovinyl aromatic monomer. In some embodiments, both glassy blocks of a triblock copolymer comprise a polymerized monovinyl aromatic monomer. In some embodiments, the monovinyl aromatic monomers comprise 8 to 18 carbon atoms. Exemplary monovinyl aromatic monomers include styrene, vinylpyridine, vinyl toluene, alpha-methyl styrene, methyl styrene, dimethylstyrene, ethylstyrene, diethyl styrene, t-butylstyrene, di-n-butylstyrene, isopropylstyrene, other alkylated-styrenes, styrene analogs, and styrene homologs. In some embodiments, the monovinyl aromatic monomer is selected from the group consisting of styrene, styrene-compatible monomers or monomer blends, and combinations thereof.

[0040] As used herein, "styrene-compatible monomers or monomer blends" refers to a monomer or blend of monomers, which may be polymerized or copolymerized, that preferentially associate with polystyrene or with the polystyrene endblocks of a block copolymer. The compatibility can arise from actual copolymerization with monomeric styrene; solubility of the compatible monomer or blend, or polymerized monomer or blend in the polystyrene phase during hot melt or solvent processing; or association of the monomer or blend with the styrene-rich phase domain on standing after processing.

[0041] In the general formula for some multi-arm block copolymers of the present disclosure, Q_n -Y, n represents the number of arms and is a whole number of at least 3, i.e.,

the multi-arm block copolymer is a star block copolymer. In some embodiments, n is ranges from 3-10. In some embodiments, n ranges from 3-5. In some embodiments, n is 4. In some embodiments, n is equal to 6 or more.


[0042] In some embodiments, the first block copolymer is a polymodal block
5 copolymer. As used herein, the term “polymodal” means that the copolymer comprises glassy blocks having at least two different molecular weights. Such a block copolymer may also be characterized as having at least one “high” molecular weight glassy block, and at least one “low” molecular weight glassy block, wherein the terms high and low are used relative to each other. In some embodiments the ratio of the number average
10 molecular weight of the high molecular weight glassy block, $(Mn)_H$, relative to the number average molecular weight of the low molecular weight glassy block, $(Mn)_L$, is at least about 1.25.

[0043] In some embodiments, $(Mn)_H$ ranges from about 5,000 to about 50,000 g/mol. In some embodiments, $(Mn)_H$ is at least about 8,000, and in some embodiments at least
15 about 10,000. In some embodiments, $(Mn)_H$ is no greater than about 35,000 g/mol. In some embodiments, $(Mn)_L$ ranges from about 1,000 to about 10,000 g/mol. In some embodiments, $(Mn)_L$ is at least about 2,000, and, in some embodiments, at least about 4,000. In some embodiments, $(Mn)_L$ is less than about 9,000 g/mol, and, in some
embodiments, less than about 8,000 g/mol.

[0044] In some embodiments, the first block copolymer is an asymmetric block
20 copolymer. As used herein, the term “asymmetric” means that the arms of the block copolymer are not all identical. Generally, a polymodal block copolymer is an asymmetric block copolymer (i.e., a polymodal asymmetric block copolymer) as not all arms of a polymodal block copolymer are identical since the molecular weights of the
25 glassy blocks are not all the same. In some embodiments, the block copolymers of the present disclosure are polymodal, asymmetric block copolymers. Methods of making asymmetric, polymodal block copolymers are described in, e.g., U.S. Patent No. 5,296,547.

[0045] Generally, the multifunctional coupling agent may be any polyalkenyl coupling agent or other material known to have functional groups that can react with carbanions of the living polymer to form linked polymers. The polyalkenyl coupling agent may be aliphatic, aromatic, or heterocyclic. Exemplary aliphatic polyalkenyl coupling agents include polyvinyl and polyalkyl acetylenes, diacetylenes, phosphates, phosphites, and dimethacrylates (e.g., ethylene dimethacrylate). Exemplary aromatic polyalkenyl coupling agents include polyvinyl benzene, polyvinyl toluene, polyvinyl xylene, polyvinyl anthracene, polyvinyl naphthalene, and divinylidurene. Exemplary polyvinyl groups include divinyl, trivinyl, and tetravinyl groups. In some embodiments, divinylbenzene (DVB) may be used, and may include o-divinyl benzene, m-divinyl benzene, p-divinyl benzene, and mixtures thereof. Exemplary heterocyclic polyalkenyl coupling agents include divinyl pyridine, and divinyl thiophene. Other exemplary multifunctional coupling agents include silicon halides, polyepoxides, polyisocyanates, polyketones, polyanhydrides, and dicarboxylic acid esters.

[0046] Still further, the cross-linked rubber of the pressure sensitive adhesive layer may be obtained from the cross-linking of a linear block copolymer of the formula



wherein R represents a rubbery block, G represents a glassy block, and m, the number of glassy blocks, is 1 or 2. In some embodiments, m is one, and the linear block copolymer is a diblock copolymer comprising one rubbery block and one glassy block. In some embodiments, m is two, and the linear block copolymer comprises two glassy endblocks and one rubbery midblock, i.e., the linear block copolymer is a triblock copolymer.

[0047] In some embodiments, the rubbery block of the linear block copolymer comprises a polymerized conjugated diene, a hydrogenated derivative thereof, or combinations thereof. In some embodiments, the conjugated dienes comprise 4 to 12 carbon atoms. Exemplary conjugated dienes useful in the second block copolymer include any of the exemplary conjugated dienes described above.

[0048] In some embodiments, at least one glassy block, and in some embodiments, each glassy block of the linear block copolymer comprises a polymerized monovinyl aromatic monomer. In some embodiments, the monovinyl aromatic monomers comprise 8 to 18

carbon atoms. Exemplary polymerized monovinyl aromatic monomers useful in the second block copolymer include any of the exemplary polymerized monovinyl aromatic monomer, as described above.

[0049] In a particular embodiment a mixture of the linear block copolymer and the
5 aforementioned and described multi-arm block copolymer is used to obtain the cross-linked rubber of the pressure sensitive adhesive layer. In some embodiments, the ratio of multi-arm block copolymers to linear block copolymers ranges from 1.5:1 to 9:1. In some
10 embodiments, the ratio of multi-arm block copolymers to linear block copolymer is at least 1.85:1, or even at least 3:1. In some embodiments, the ratio of multi-arm block copolymers to linear block copolymers is no greater than 5.7:1, or even no greater than
4:1.

[0050] The pressure sensitive adhesive layer in a particular embodiment further
includes one or more tackifiers and optionally one or more plasticizers. Generally, a
15 tackifier will be selected to be compatible with a rubbery block of a block copolymer as may be used for obtaining the cross-linked rubber. As used herein, a tackifier is
“compatible” with a block if it is miscible with that block. Generally, the miscibility of a
tackifier with a block can be determined by measuring the effect of the tackifier on the Tg
of that block. If a tackifier is miscible with a block it will alter (e.g., increase) the Tg
of that block.

20 [0051] A tackifier is “primarily compatible” with a block if it is at least miscible with that block, although it may also be miscible with other blocks. For example, a tackifier that is primarily compatible with a rubbery block will be miscible with the rubbery block,
but may also be miscible with a glassy block.

[0052] Generally, resins having relatively low solubility parameters tend to associate
25 with the rubbery blocks; however, their solubility in the glassy blocks tends to increase as the molecular weights or softening points of these resins are lowered. Exemplary
tackifiers that are primarily compatible with the rubbery blocks include polymeric
terpenes, hetero-functional terpenes, coumarone-indene resins, esters of rosin acids,
disproportionated rosin acid esters, hydrogenated rosin acids, C5 aliphatic resins, C9
30 hydrogenated aromatic resins, C5/C9 aliphatic/aromatic resins, dicyclopentadiene resins,

hydrogenated hydrocarbon resins arising from C5/C9 and dicyclopentadiene precursors, hydrogenated styrene monomer resins, and blends thereof.

[0053] In particular embodiments, a first high Tg tackifier having a glass transition temperature (Tg) of at least 60 degrees Celsius ($^{\circ}$ C). As used herein, the terms “high glass transition temperature tackifier” and “high Tg tackifier” refers to a tackifier having a
5 glass transition temperature of at least 60 $^{\circ}$ C. In some embodiments, the first high Tg tackifier has a Tg of at least 65 $^{\circ}$ C, or even at least 70 $^{\circ}$ C. In some embodiments, the first high Tg tackifier has a softening point of at least about 115 $^{\circ}$ C, and, in some embodiments, at least about 120 $^{\circ}$ C.

10 [0054] In some embodiments, the block copolymer adhesive compositions include a second high Tg tackifier that is primarily compatible with the glassy block(s) of the multi-arm block copolymer and, optionally, with the glassy block(s) of the linear block copolymer. Generally, a tackifier that is primarily compatible with a glassy block is miscible with the glassy block and may be miscible with a rubbery block.

15 [0055] Generally, resins having relatively high solubility parameters tend to associate with the glassy blocks; however, their solubility in the rubbery blocks tends to increase as the molecular weights or softening points of these resins are lowered. Exemplary tackifiers that are primarily compatible with the glassy blocks include coumarone-indene resins, rosin acids, esters of rosin acids, disproportionated rosin acid esters, C9 aromatics,
20 alpha-methyl styrene, C9/C5 aromatic-modified aliphatic hydrocarbons, and blends thereof.

[0056] In some embodiments, the pressure sensitive adhesive layer further comprises at least one component selected from the group consisting of a low Tg tackifier, a plasticizer, and combinations thereof. As used herein, the term “low glass transition temperature
25 tackifier” refers to a tackifier having a glass transition temperature of less than 60 $^{\circ}$ C. Exemplary low Tg tackifiers include polybutenes.

[0057] Generally, a plasticizer is compatible with one or more blocks of the linear block copolymer, and/or one or more blocks of the multi-arm block copolymer. Generally, a plasticizer that is compatible with a block will be miscible with that block

and will lower the Tg of that block. Exemplary plasticizers include naphthenic oils, liquid polybutene resins, polyisobutylene resins, and liquid isoprene polymers.

[0058] In some embodiments, the ratio of the total amount of high glass transition temperature tackifiers to block copolymers ranges from 0.8:1 to 1.25:1. In some
5 embodiments, the ratio of the total amount of high Tg tackifiers to block copolymers is at least 0.85:1, or even at least 0.9:1. In some embodiments, the ratio of the total amount of high Tg tackifiers to block copolymers is no greater than 1.15:1, or even no greater than 1.1 to 1.

[0059] In some embodiments, the ratio of the rubbery block compatible high Tg
10 tackifier to the glassy block compatible high Tg tackifier is ranges from 1:1 to 9:1. In some embodiments, the ratio of the rubbery block compatible high Tg tackifier to the glassy block compatible high Tg tackifier is at least 1.25:1, or even at least 1.5:1. In some embodiments the ratio of the rubbery block compatible high Tg tackifier to the glassy block compatible high Tg tackifier is no greater than 4:1, or even no greater than 3:1.

15 [0060] In a particularly preferred embodiment, the pressure sensitive adhesive layer also includes an acrylic pressure sensitive adhesive component. Typically, the pressure sensitive adhesive layer comprises at least about 0.1 parts, in some embodiments, at least about 0.5 parts, at least about 1 part, or even at least about 2 parts of an acrylic pressure sensitive adhesive component.

20 [0061] In a particular embodiment, the pressure sensitive adhesive layer comprise no greater than about 10 parts, in some embodiments, no greater than about 8 parts, no greater than about 5 parts, or even no greater than about 4 parts of the acrylic pressure sensitive adhesive component. The amount of cross-linked block copolymer will typically be between 30 and 60 or between 30 and 50 parts by weight of the total weight of the
25 pressure sensitive adhesive layer.

[0062] In another embodiment, the acrylic pressure sensitive adhesive component may be comprised in the pressure sensitive adhesive layer in an amount of between 40 and 60 parts by weight. In this embodiment, the amount of cross-linked block copolymer will typically be between 10 and 20 parts by weight of the weight of the pressure sensitive
30 adhesive layer.

[0063] Typically, the acrylic pressure sensitive adhesive component of the pressure sensitive adhesive layer is an acrylic polymer derived from one or more acrylic esters of a non-tertiary alkyl alcohol that contains 3 to 14 carbon atoms. Exemplary acrylic acid esters include isooctyl acrylate, 2-ethylhexyl acrylate, butyl acrylate, isobornyl acrylate, and combinations thereof. Exemplary methacrylic acid esters include the methacrylate analogues of these acrylic acid esters. Typically, the acrylic polymer will further comprises one or more units derived from a polar monomer such as for example described above.

[0064] In some embodiments, the acrylic polymer comprises at least about 70 parts, in some embodiments, at least about 80 parts, at least about 90 parts, at least about 95 parts, or even about 100 parts of at least one acrylic or methacrylic ester of a non-tertiary alkyl alcohol. In some embodiments, acrylic polymer comprises no greater than about 30 parts, in some embodiments, no greater than about 20 parts, no greater than about 10 parts, no greater than about 5 parts, and even no greater than 1 part of at least one copolymerized polar monomer. In some embodiments, the acrylic adhesive composition does not include a copolymerized polar monomer.

[0065] In some embodiments, the ratio of the combination of the block copolymers and high Tg tackifiers to the acrylic pressure sensitive adhesive component is at least 8.3:1. In some embodiments, the ratio of the combination of the block copolymers and high Tg tackifiers to the acrylic pressure sensitive adhesive component is at least 12.5:1, at least 22:1, at least 90:1, or even at least 180:1.

[0066] In some embodiments, the ratio of the combination of the block copolymers, high Tg tackifiers, and acrylic pressure sensitive adhesive component to the liquid plasticizer ranges from 32:1 to 10:1. In some embodiments, the ratio of the combination of the block copolymers, high Tg tackifiers, and acrylic pressure sensitive adhesive component to the liquid plasticizer is no great than 25:1, or even no greater than 20:1. In some embodiments, the ratio of the combination of the block copolymers, high Tg tackifiers, and acrylic pressure sensitive adhesive component to the liquid plasticizer is at least 12.5:1.

[0067] The pressure-sensitive adhesive compositions for providing the pressure sensitive adhesive layer on the foam layer can be made using methods known in the art.

For example, they can be made by dissolving the block copolymers, suitable tackifiers, any plasticizer(s), and any other additives including an acrylic pressure sensitive adhesive component in a suitable solvent, and coating onto a release liner or directly onto the foam layer using conventional means (e.g., knife coating, roll coating, gravure coating, rod coating, curtain coating, spray coating, air knife coating). In some embodiments, the pressure-sensitive adhesive composition of the pressure sensitive adhesive layer is prepared in a substantially solvent-free process (i.e., the adhesive contain no greater than about 20 wt. % solvent, in some embodiments, no greater than about 10 wt. % solvent and, in some embodiments, no greater than about 5 wt. % solvent, in some embodiments, no greater than 1 wt. % solvent, or even no greater than trace amounts of solvent (i.e., essentially no solvent). Such substantially solvent-free processes are known and include, e.g., compounding by calendaring or roll milling, and extruding (e.g., single screw, twin screw, disk screw, reciprocating single screw, pin barrel single screw, etc.). Commercially available equipment such as BRABENDER or BANBURY internal mixers are also available to batch mix the adhesive compositions. After compounding, the adhesive may be coated through a die into a desired form, such as a layer of adhesive, or it may be collected for forming at a later time. In a particular embodiment the pressure sensitive adhesive composition may be extruded on the foam layer or may be extruded on a release liner and then subsequently laminated to the foam layer.

[0068] The pressure sensitive adhesive layer is typically applied on the foam layer at a weight per area of between 40 and 100g/m².

[0069] In accordance with the method of making the adhesive article, the cross-linkable rubber, for example one or more cross-linkable block copolymers as described above, of the pressure sensitive layer is cross-linked. In a particular embodiment, the cross-linkable rubber is cross-linked by subjecting the pressure sensitive adhesive layer on the foam layer to e-beam irradiation. Typically, e-beam irradiation will be carried out with an acceleration voltage of between 100 and 300 keV and a dose of 2 to 9 MRad. In a particular embodiment the e-beam irradiation is focused at the interface of the pressure sensitive adhesive layer and foam layer. In another embodiment, the focus of the e-beam may be in the proximity of the interface, for example within about 10 and 30 micrometer

of the interface, with the focus in the foam layer or in the pressure sensitive adhesive layer.

[0070] When the pressure sensitive adhesive composition having a cross-linkable rubber is provided on both opposite major sides of the foam layer, it will typically be preferred to irradiate such a laminate from both opposite major sides either sequentially of
5 simultaneously.

[0071] In another embodiment, the pressure sensitive adhesive layer having a cross-linked rubber may be provided on only one of the major sides of the foam layer. The other major side may then be left without a further adhesive layer as the foam layer in
10 accordance with the present disclosure will typically have useful pressure sensitive adhesive characteristics. In an alternative embodiment, a further adhesive layer may be provided on the major side opposite to the major side having the pressure sensitive adhesive layer with the cross-linked rubber. Such further adhesive layer may include any common pressure sensitive adhesive including acrylic pressure sensitive adhesive layers,
15 silicone based adhesives, polyurethane based adhesives, poly- alpha olefins and the like.

[0072] In yet a further embodiment, a further adhesive layer provided on the opposite major side may include a heat-activatable adhesive layer. With heat-activatable adhesive layer is meant an adhesive that requires heating in order to develop its maximum bond strength in bonding to a substrate. A heat-activatable adhesive may or may not have
20 useful pressure sensitive adhesive properties at room temperature (about 25°C).

Typically, a heat-activatable adhesive for use with the present disclosure will be based on a thermoplastic polymer such as for example a film of a copolymer of ethylene and propylene, thermoplastic polyurethane which may be tackified or not.

[0073] The adhesive articles in connection with the present disclosure can be used to
25 bond to a substrate. Thus, the pressure sensitive adhesive layer of adhesive article is used to bond the article to a desired substrate. In a particular embodiment, such a substrate may have a low surface energy, for example of less than 45 dynes/cm or less than 40 dynes/cm or 35 dynes/cm or less.

[0074] The adhesive articles are particularly suitable for bonding various components
30 including for example emblems, plastic body moldings and rubber gaskets to a body of a

motor vehicle, in particular a car. For example, in one embodiment the adhesive article may be bonded through its pressure sensitive adhesive having a cross-linked rubber to the body of a car. A plastic molding, emblem and the like may be adhered to the adhesive article on the opposite major side which may or may not contain a further skin adhesive
5 layer. Generally, the emblem, plastic molding or gasket will be first bonded to the adhesive article, and the resulting assembly may then be bonded to the motor vehicle, in particular the car.

[0075] In another embodiment, the adhesive article may be bonded on the major side opposite to the major side having the pressure sensitive adhesive layer comprising the
10 cross-linked rubber to a rubber gasket. Such rubber gasket may be directly bonded to the foam layer of the adhesive article but is typically bonded thereto through a further skin adhesive layer that is provided on the foam layer. In one embodiment, such a skin adhesive layer may be a pressure sensitive adhesive and in another embodiment the skin adhesive layer comprises a heat activatable adhesive.

15 [0076] Adhesive articles provided with a rubber gasket as described in the previous paragraph can be readily applied to for example a door of a car so as to provide a door seal.

[0077] The invention will now be illustrated with reference to the following non-limiting examples. All parts are by weight unless otherwise stated.

20 EXAMPLES

Test methods:

Dynamic shear test:

[0078] A modified version of ISO4587 : 2003 was employed.

25 [0079] The tape to be tested was applied with its specific side to the painted steel substrate. To the opposite side of that tape an aluminum coupon (50 mm x 25 mm x 1 mm) was applied.

[0080] The bonded tape area is 1.27 cm x 2.54 cm horizontally applied.

[0081] The painted steel panels employed in this test method were obtained from a supplier mentioned in a separate section below. A basic description about the paints is provided in that separate section below as well.

[0082] Paint A and paint B were cleaned by wiping with a tissue saturated in n-heptane. Paint C was cleaned by wiping with a tissue saturated with a 1:1 volume mixture of water and isopropanol. For the test, the painted steel panel substrates were cut into coupons (50 mm x 30 mm x 1 mm).

[0083] The aluminum coupons were subjected to light abrasion with a Scotchbrite™ no. 7447™ scrubbing pad (available from 3M Company) followed by cleaning/wiping with a tissue saturated with Methylethyl ketone, and finally cleaned by wiping with a tissue saturated with a 1:1 volume mixture of water and isopropanol.

[0084] The assemblies were prepared by applying first the treated aluminum coupon side the exposed tape surface side, cut into an 1.27 cm x 2.54 cm area. Then the liner is removed from the opposite specific tape area side and the cleaned painted steel panel coupon is applied to this tape surface, using a 6.8 kg roller over rolling the test specimen twice with a speed of 300 mm/min. After a dwell time of 20 min, 24 hrs or 72 hrs the dynamic shear strength test was performed with 10 mm/min or 50 mm/min cross-head speed. The test was repeated with 3 three repeating test samples and the average value was reported.

20

90° peel adhesion test:

[0085] 90° peel adhesion at 300 mm/min was measured according to Federation Internationale des Fabricants Europeens et Transformateurs d'Adhesifs et Thermocollants sur Papiers et autres Supports (FINAT) test method no.2 with following exceptions:

[0086] The pressure sensitive adhesive layer of the present disclosure were allowed to dwell on the substrates before testing for 20 min, 24 hrs and/or 72 hrs, as indicated in the table below.

[0087] The width of the tested tapes was 1.27 cm rather than 2.5 cm as called for by the FINAT test.

[0088] A 150 µm thick aluminium strip being anodized on one side and having a width of 1.6 cm is applied by hand with anodized side to specific side of the tape to be tested to form a non-extendible backing.

[0089] A 6.8 kg roller was used to apply the tape to be tested to the substrate rather than
5 2 kg as required by the method. The 6.8 kg roller was rolled twice over the test specimen with a speed of 300 mm/min.

[0090] Substrates employed were painted steel panels obtained from a supplier mentioned in a separate section below. A basic description about the paints is provided in that separate section below as well. Paint A and Paint B were cleaned by wiping with a
10 tissue saturated in n-heptane. Paint C was cleaned by wiping with a tissue saturated with a 1:1 volume mixture of water and isopropanol.

[0091] Results were reported in N/cm rather than N/2.5 cm as called for by the method.

Static shear test at elevated temperatures:

[0092] A standard static shear test was performed at elevated temperature according to
15 Pressure Sensitive Tape Council (Chicago, Ill./USA) PSTC – 107 (procedure G). The test was performed at 90°C rather than 49°C (120°F) as called for by the method. The substrates employed were painted steel panels obtained from a supplier mentioned in a separate section below. A basic description about the paints is provided in that separate
20 section below as well. Paint A and Paint B were cleaned by wiping with a tissue saturated in n-heptane. Paint C was cleaned by wiping with a tissue saturated with a 1:1 volume mixture of water and isopropanol.

[0093] The bonded sample area was 2.54 cm in the vertical direction by 1.27 cm in the
width direction (rather than 1.27 cm x 1.27 cm as called for by the method). To the tape
25 side opposite to that side which will be applied with its specific side to the painted substrate, a 150 µm thick aluminium strip is applied superimposing the tape area to provide a means of a load weight as described in PSTC-7. This aluminium strip has a width of 1.6 cm and is anodized on one side. This anodized aluminium strip side is to be applied first to the tape area. Then a 6.8 kg roller was used to apply the specific side of the
30 tape area to be tested to the painted substrate panel. The roller was rolled twice over the test specimen with a speed of 300 mm/min. After a dwell time of 24 hrs the test specimen

- were hung in the shear stand at elevated temperature. The shear stand with the test specimen was placed in a forced air oven held at the elevated temperature (90°C) for 10 min to condition it and then the load of 750 g (rather than 1 kg as called for by the method) was hung from the end of the aluminum strip bonded to the tape area to be tested.
- 5 The time to failure for the adhesive bond was recorded in minutes. After passing 10000 min of holding time the test was stopped.

Description of the painted metal panels used as substrates in the above mentioned tests:

[0094] Paint A:

1K acrylic powder coating, generation 9, automotive paint, coated on steel plates, obtained
5 from DuPont Performance Coatings GmbH&Co.KG, Wuppertal.

[0095] Paint B:

1K acrylic powder coating, generation 8, automotive paint, coated on steel plates, obtained
from DuPont Performance Coatings GmbH&Co.KG, Wuppertal.

[0096] Paint C:

10 2K clear coat, automotive paint containing nanoparticles, coated on steel plates, obtained
from PPG Industries Lacke GmbH, Ingersheim.

Materials used in the examples:

15 Table 1 : Summary of materials

Abbreviation	Name	Source
AA	Acrylic Acid	
BA	Butyl acrylate	
IOA	Isooctyl acrylate	
2-EHA	2-Ethylhexyl acrylate	
HDDA	Hexanediol diacrylate	
Irgacure™ 651	2,2 dimethoxy-2-phenylacetophenone	Ciba Specialty Chemicals Corp. (Tarrytown, NY)
IOTG	Isooctyl thioglycolate	
Kraton™ 1161-D	SIS linear block copolymer (15% S, 19% diblock)	Kraton Polymers, Inc. (Houston, Texas)
Santicizer™ 141	2-ethylhexyl diphenyl phosphate	Ferro Co. (Bridgeport, New Jersey)
Escorez™ 1310	Aliphatic C-5 tackifying resin	ExxonMobil Chemical LTD. (Southampton, Hampshire, GB)
4900 MB	Black pigment having a 50/50 blend of carbon black in ethylene vinyl acetate copolymer resin having a melt index of about 150	MA Hanna Color (Suwannee, Georgia)
Superester™ W-115	Stabilized rosin acid ester	Arakawa Chemical USA (Chicago, IL)
Irganox™ 1010	Pentaerythritol tetrakis (3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)	Ciba Specialty Chemicals Corp. (Tarrytown, NY)
Tinuvin™ 328	2-(2-hydroxy-3,5-di-(tert)-amylphenyl)benzotriazole	Ciba Specialty Chemicals Corp. (Tarrytown, NY)
Regalite™ R1125	Hydrogenated hydrocarbon resin	Eastman Chemical Co. (Kingsport, TN)
Cumar™ 130	Aromatic thermoplastic resin	Neville Chemical Co. (Pittsburgh, PA)
Nyplast™ 222B	Naphthenic oil plasticizer	Nynas Naphthenics AB (Stockholm, Sweden)
K15	Hollow glassbubbles	3M Co.
Surfactant	Fluoroaliphatic polymer	3M Co.
Aerosil™ 972	Hydrophobic fumed silica	Evonik

Preparation of Acrylic Polymers:

[0097] Acrylic Polymer 1 (AP-1) was prepared by mixing 45 parts of IOA; 45 parts of BA; 10 parts of AA; 0.15 part IRGACURE 651; and 0.06 part of IOTG. Discreet film packages were formed from a packaging film (0.0635 mm thick ethylene vinyl acetate copolymer film sold as VA-24 Film from CT Film, Dallas, Texas). The AP-1 composition was sealed into the film packages, which measured approximately 10 centimeters (cm) by 5 cm by 0.5 cm thick. While immersed in a water bath maintained between about 21°C and about 32°C, the packages were exposed to ultraviolet (UV) radiation having an intensity of about 3.5 milliwatts per square centimeter (mW/sq cm), and a total energy of about 1680 milliJoules per square centimeter (mJ/sq cm) as measured in NIST units. The method of forming the packages and curing are described in Example 1 of U. S. Patent No. 5,804,610, the subject matter of which is incorporated herein by reference in its entirety.

[0098] Acrylic Polymer 2 (AP-2) was prepared according to the procedure for AP-1, except that 85 parts of 2-EHA; 15 parts of AA; 0.15 parts of IRGACURE 651; and 0.8 part IOTG were used. Similarly, Acrylic Polymer 3 (AP-3) was prepared according to the procedure for Acrylic Polymer 1 except that the composition was 95 parts of 2-EHA; 5 parts of AA; 0.15 part IRGACURE 651; and 0.03 part of IOTG. AP-2 and AP-3 were placed in packages and exposed to UV energy, according to the procedure for AP-1 .

20 First skin adhesive (SA-1):

[0099] Pressure-sensitive adhesives according to the compositions shown in Table 2 were compounded using a 60 mm, co-rotating twin screw extruder (available from Berstorff), (the "first adhesive extruder"). A polymodal, asymmetric star block copolymer ("PASBC") was prepared according to U.S. Patent No. 5,393,373, the subject matter of which is hereby incorporated by reference in its entirety. The polymer had number average molecular weights of about 4,000 Dalton and about 21,500 Dalton for the two endblocks, 127,000 - 147,000 Dalton for the arm, and about 1,100,000 Dalton for the star measured by SEC (size exclusion chromatography) calibrated using polystyrene standards. The polystyrene content was between 9.5 and 11.5 percent by weight. The mole percentage of high molecular weight arms was estimated to be about 30 %.

[00100] The polymodal asymmetric block copolymer and a linear styrene-isoprene-styrene (SIS) block copolymer (KRATON 1161-D) were dry fed into the first zone of the first adhesive extruder. Using a roll-feed extruder (available from Berstorff), acrylic polymer AP-1 was heated and fed into the third zone of the first adhesive extruder.

5 Antioxidant (IRGANOX 1010), ultraviolet light absorber (TINUVIN 328), pigmented EVA (4900 CMB) were dry fed; and (REGALITE R 1125); (CUMAR 130); and (NYPLAST 222B) were melt fed in to various zones of the first adhesive extruder.

Table 2 - First skin adhesive composition (SA-1)

10

Component	Amount in weight percent
PASBC*	31.19
Kraton 1161D	13.37
Regalite R1125	30.91
Cumar 130	10.30
Nyplast 222B	7.20
Irganox 1010	1.34
Tinuvin 328	1.34
4900 CMB	0.38
AP-1	4

* Polymodal, asymmetric star block copolymer

15 **Second skin adhesive (SA-2):**

[00101] A pressure sensitive adhesive was compounded in a 60 mm, co-rotating twin screw extruder (available from Berstorff) (the "second adhesive extruder") in a similar manner as described for the first skin adhesives, except that the composition was as follows: 12.70% of the polymodal, asymmetric star block copolymer (PASBC); 53.10% (by weight) AP-1; 23.30% tackifying resin (SCOREZ 1310LC); 3.80% tackifying resin (SUPERESTER W115); 6.20% plasticizer (SANTICIZER 141); 0.26% antioxidant (IRGANOX 1010); 0.25% ultraviolet light absorber (TINUVIN 328) and 0.38 % CMB 4900.

25

Double-sided foam tape samples:

Example A

[00102] The Foam core (FC-1) having the composition shown in Table 3 was
 5 compounded according to the following procedure. Black pigmented EVA (4900 CMB)
 was dry fed in to the first zone of a 90 mm, co-rotating twin screw extruder (the "core
 extruder") (available from Berstorff, Hannover, Germany). Using a roll-feed extruder
 (available from Berstorff), both acrylic polymers AP -2 and AP-3 were heated and fed into
 the second zone of the core extruder. DUALITE U010-185D expandable microspheres
 10 (expandable microspheres having a shell composition containing acrylonitrile and
 methacrylonitrile and a core of isopentane, available from Henkel Corporation (Gulph
 Mills, Pennsylvania) were fed into the ninth zone of the core extruder.

Table 3: Foam core composition FC-1 and properties

15

Components Parts By Weigh Percent (%)	Components Parts By Weigh Percent (%)	Components Parts By Weigh Percent (%)	Components Parts By Weigh Percent (%)	Foam Density	Thickness
AP-3 91.12	AP-2 4.8	Microspheres 3.70	Pigment 0.38	(g/cm ³) 0.53	(mm) 0.7

[00103] Three-layer co-extruded tape samples were prepared by coextruding a first skin
 adhesive layer, a foam core layer as the middle layer, and a second skin adhesive layer.

[00104] The second skin adhesive was compounded in the second adhesive extruder, as
 20 described above, and fed through an outer layer of a three-layer, multi-manifold film die
 obtained from Cloeren Inc. (Orange, Texas). A foam core layer was compounded in the
 core extruder, as described above, and fed to the center layer of the three-layer die. A first
 skin adhesive was compounded in the first adhesive extruder, as described above, and fed
 to the outer layer of the three-layer die, opposite the second skin adhesive.

[00105] Upon exiting the die, the co-extruded layers were cast onto a silicone release
 25 coated casting roll. The roll was cooled with water having a temperature of about 12°C.
 The cooled extrudate was transferred from the casting roll to a 0.117 mm thick two-side
 silicone coated polyethylene release liner that was transported at the same speed as the
 casting roll to the end of the web transport line. The first skin adhesive was in contact with
 30 the liner after the transfer whereas the second skin adhesive was open to the air. The liner

had differential release properties which allow the tape to be unrolled after winding without liner confusion. Release liners are well-known in the art, and any known release liner may be used. Typically, the release liner comprises a film or paper substrate coated with a release material. Commercially available release liners include, but are not limited to, silicone coated papers, and silicone coated films, such as polyester films. Suitable release liners are also disclosed in U.S. Patents Nos. 6,835,422; 6,805,933; 6,780,484; and 6,204,350 assigned to 3M Innovative Properties Company.

[00106] The foam core and both adhesive skins were crosslinked on-web using electron beam curing while supported on the liner. Two sequential irradiation steps acting on opposite faces of the tape were employed. The first skin adhesive was irradiated through the polyethylene liner, whereas the second skin adhesive was irradiated in an open-face condition. The electron beam units were BROADBAND curtain-type electron beam processors (PCT Engineered Systems, LLC, Davenport, IA), operated according the acceleration voltage and dose conditions provided in Table 4.

15

Table 4: Composition of three-layer tape sample

Example	Foam Core	First skin adhesive (SA-1) Acceleration Voltage (keV)	First skin adhesive (SA-1) Dose (MRad)	Second skin adhesive (SA-2) Acceleration Voltage (keV)	Second skin adhesive (SA-2) Dose (MRad)
A	FC-1	247	11.5	235	10

20

Example B:

[00107] Into the mixture of the photopolymerizable monomers (2-EHA and AA) was stirred 0.04% by weight of 2,2-dimethoxy-2-phenyl acetophenone (obtainable as "Irgacure" 651). This was partially polymerized to provide a syrup about 3000 cps in viscosity by exposure to ultraviolet radiation. To the syrup was added 0.20% by weight of additional "Irgacure" 651 and crosslinking agent HDDA. To this prepolymer mixture the fillers Aerosil 972 and the glass bubbles were added and slowly mixed using a motorized stirrer equipped with an air motor. After degassing and the addition of surfactant and pigments the mixture was transferred to a frother operating at 300 rpm.

[00108] While nitrogen gas was fed into the frother, the frothed syrup was delivered through a tube to a knife coater between a pair of transparent, biaxially-oriented polyethylene terephthalate films, the facing surfaces of which had low-adhesion coatings. The composite emerging from the knife coater was irradiated with a bank of fluorescent black light bulbs (Sylvania F20T12BL), 90% of the emissions of which were between 300 and 400 nm with a maximum at 351 nm to complete the polymerisation to a pressure sensitive adhesive foam layer. The total exposure was 1360 mJ/cm² as measured by an EIT UV Radiometer which is spectrally responsive between 250 and 430 nm, maximum 350 nm. The composite was cooled by blowing air against both films during the irradiation to keep the temperature of the films below 85°C to avoid wrinkling of the films. The PET process liners finally are stripped and a double-sided siliconized release paper liner is laminated to one of the two tape surfaces to allow for the roll winding and unwinding later on.

15 Table 5: Composition of Example B and C:

Example Nr.	Monomers Ratio	Crosslinker	Solids	Flow rate	Nitrogen flow	Pressure	Caliper
	2-EHA/AA [%]	HDDA [%]	Pigment + Glassbubbles + Aerosil [%]	kg/h	l/h	kPa	[µm]
B	2-EHA/AA 83.4 %/8.0 %	0.1	8.5	550	8.7	250	800
C	2-EHA/AA = 83.4 %/8.0 %	0.1	8.5	550	8.7	250	1200

Samples 1 to 8:

20 [00109] The following examples were generated by applying a layer of the above mentioned first skin adhesive SA-1 (which was used to make Example A) onto the surface of the foam layer of Example B, followed by an e-beam radiation process.

[00110] Several methods can be employed to apply a layer of the first skin adhesive onto the foam layer of Example B:

25 A) Laminating a transfer tape, obtained by hot melt coating the skin adhesive formulation onto a doublesided siliconized release carrier liner, to the foam layer (lamination force:

typically 50 N per web width.)

B) Directly hotmelt coating onto the surface of the foam layer using a slot die.

C) Directly hotmelt coating onto the surface of the foam layer via an extrusion line and using a rotary rod die.

5 D) Directly coating of a solvent based formulation of the skin adhesive onto the foam layer, followed by an oven drying process.

[00111] Various e-beam radiation curing conditions were employed (Oxygen level in the e-beam chamber: always below 50 ppm).

10

Table 6: Process conditions for E-beam radiation

Method of post e-beam radiation	e-beam dosage [MRad]	Acceleration Voltage [keV]	Beam Current [mAmpere]	Line Speed [m/min]
EB1	6	190	1.9	3
EB2	6	220	2.2	3
EB3	8	210	2.9	3
EB4	6	210	2.2	3
EB5	4	210	1.5	3
EB6	2	210	1.2	5

The following table summarizes the constructions of the various samples:

15

Table 7:

Sample Nr.	Type of skin adhesive	Coat weight of skin layer [g/m ²]	Foam Core	Process method of making the respective sample	Temperature of the extrusion line [°C]	Temperature of the coating die [°C]	Method of post e-beam treatment
Sample 1	SA-1	60	Example B	A	200	175	EB1
Sample 2	SA-1	60	Example B	A	175	175	EB2
Sample 3	SA-1	85	Example B	C	200	200	EB3
Sample 4	SA-1	85	Example B	C	200	200	EB4
Sample 5	SA-1	85	Example B	C	200	200	EB5
Sample 6	SA-1	85	Example B	C	200	200	EB6
Sample 7	SA-1	85	Example B	D	Oven drying	Oven drying	EB4
Sample 8	SA-1	85	Example C	B	None	208	EB6

[00112] The samples summarized in table 7 were adhered with the pressure sensitive adhesive skin layer to the substrate as indicated in the tables below which summarize the results obtained using the test methods set out above.

20

Test Results:

Table 8: Dynamic Shear Test Results:

5

Example #	Substrate	Dwell Time	Jaw Speed [mm/min]	Dynamic Shear Strength [N/cm ²]	Type of Failure Mode
Sample1	Paint C	72 hrs.	50	126	FS/pop
Sample 2	Paint C	72 hrs.	50	128	pop
Example A	Paint C	72 hrs	50	74	FS
Example B	Paint C	72 hrs	50	89	pop
Sample 1	Paint C	24 hrs	50	102	FS/2B
Sample 2	Paint C	24 hrs	50	115	FS/2B
Example A	Paint C	24 hrs	50	66	FS
Example B	Paint C	24 hrs	50	81	pop
Sample 4	Paint A	24 hrs	10	100	FS
Sample 5	Paint A	24 hrs	10	97	FS
Sample 6	Paint A	24 hrs	10	86	FS
Sample 7	Paint A	24 hrs	10	93	FS
Sample 8	Paint A	24 hrs	10	84	2B/FS
Example A	Paint A	24 hrs	10	45	FS
Example B	Paint A	24 hrs	10	43	pop
Example C	Paint A	24 hrs	10	34	pop

Table 9: 90° Peel Adhesion Test Results:

Example #	Substrate	Dwell Time	Jaw Speed [mm/min]	Average peel force [N/cm]	Type of Failure Mode
Sample 1	Paint C	72 hrs.	300	41	pop
Sample 2	Paint C	72 hrs.	300	43	pop
Example A	Paint C	72 hrs	300	45	FS
Example B	Paint C	72 hrs.	300	14	pop
Sample 1	Paint C	24 hrs	300	38	Pop sh
Sample 2	Paint C	24 hrs	300	33	Pop smooth
Example A	Paint C	24 hrs	300	43	FS
Example B	Paint C	24 hrs	300	11	pop
Sample 4	Paint A	24 hrs	300	33	pop
Sample 5	Paint A	24 hrs	300	35	Pop
Sample 6	Paint A	24 hrs	300	39	pop
Sample 7	Paint A	24 hrs	300	20	pop
Sample 8	Paint A	24 hrs	300	41	pop
Example A	Paint A	24 hrs	300	40	FS
Example B	Paint A	24 hrs	300	7	pop
Example C	Paint A	24 hrs	300	8	pop

Failure modes:

FS = foam split

5 Pop = pop off panel

2B = 2-bond failure mode

FS/2B = mixed failure mode of foam split and 2-bond failure mode

Pop sh = shocky pop of panel

10

Table 10: Results of Static Shear Test @ 90°C

Example #	Substrate	Dwell Time	Holding Time [min]	Load [g]	Type of Failure Mode
Sample 1	Paint C	24 hrs.	>10000	750	none
Sample 2	Paint C	24 hrs.	>10000	750	none
Example A	Paint C	24 hrs	<1900	750	FS
Example B	Paint C	24 hrs	>10000	750	none
Sample 3	Paint A	24 hrs	2 x >10000 1 x 7211	750	none 2B
Sample 4	Paint A	24 hrs	2 x >10000 1 x 641	750	none 2B
Sample 5	Paint A	24 hrs	2 x >10000 1 x 1493	750	none 2B
Sample 6	Paint A	24 hrs	<169	750	2B
Sample 8	Paint A	24 hrs	7	1000	2B
Example A	Paint A	24 hrs	121	1000	2B
Example A	Paint B	24 hrs	<1045	750	FS/pop
Example B	Paint B	24 hrs	>10000	750	none
Example C	Paint A	24 hrs	>10000	1000	none

CLAIMS

1. Adhesive article comprising a foam layer having first and second major sides and a pressure sensitive adhesive layer associated with at least one of the major sides for the
5 foam layer, said pressure sensitive adhesive layer comprising a cross-linked rubber and wherein the foam layer comprises an acrylic polymer obtainable by polymerization a polymerizable composition comprising one or more alkyl acrylates having an average of 3 to 14 carbon atoms in the alkyl groups, one or more polar monomers and one or more multi-functional monomers having at least two free radical
10 polymerizable groups.
2. Adhesive article according to claim 1 wherein said polymerizable composition comprises 83 to 97 % by weight of said alkyl acrylates, 3 to 16 % by weight of said polar monomers and 0.01 to 1 % by weight of said multi-functional monomers.
15
3. Adhesive article according to any of the previous claims wherein said pressure sensitive adhesive layer comprises an acrylic pressure sensitive adhesive component.
4. Adhesive article according to claim 3 wherein said acrylic pressure sensitive adhesive
20 component comprises an acrylic polymer having repeating units derived from one or more alkyl acrylates having 3 to 14 carbon atoms in the alkyl group and one or more polar monomers.
5. Adhesive article according to any of the previous claims wherein cross-linked rubber
25 comprises a cross-linked block copolymer having a rubbery block and a glassy block.
6. Adhesive article according to claim 5 wherein said rubbery block comprises a first polymerized conjugated diene, a hydrogenated derivative thereof, or combinations thereof and wherein said glassy block comprises a monovinyl aromatic monomer.
30
7. Adhesive article according to any of the previous claims wherein each of said first and second major side of said adhesive article have associated with them said pressure

sensitive adhesive layer.

8. Adhesive article according to any of claims 1 to 6 wherein said adhesive article has said pressure sensitive adhesive layer associated with said first major side and wherein
5 said second major side does not have an adhesive layer associated with it.
9. Adhesive article according to any of claims 1 to 6 wherein said adhesive article has said pressure sensitive adhesive layer associated with said first major side and wherein said second major side has a further adhesive layer associated with it.
10
10. Adhesive article according to claim 9 wherein said further adhesive layer comprises a pressure sensitive adhesive component or a heat activatable adhesive component.
11. Method of making an adhesive article as claimed in any of claims 1 to 10 comprising:
15 (i) making a foam layer having first and second major sides by (a) providing a polymerizable composition comprising one or more alkyl acrylates having an average of 3 to 14 carbon atoms in the alkyl groups, one or more polar monomers and one or more multi-functional monomers having at least two free radical polymerizable groups, (b)
20 frothing said polymerizable composition and (c) polymerizing said polymerizable composition;
- (ii) applying a pressure sensitive adhesive composition comprising a cross-linkable rubber on one or both of said first and second major sides of said foam layer so as to form a pressure sensitive adhesive layer; and
25 (iii) cross-linking said cross-linkable rubber.
12. Method according to claim 11 wherein said cross-linking comprises exposing said cross-linkable rubber to e-beam radiation.
- 30 13. Use of an adhesive article according to any of claims 1 to 10 comprising adhering said adhesive article to a substrate through said pressure sensitive adhesive layer.

14. Use of an adhesive article according to claim 13 wherein said substrate has a surface having a surface energy of less than 45 dynes/cm and said adhesive article is adhered to said surface through said pressure sensitive adhesive layer.
- 5 15. Use of an adhesive article according to any of claims 13 or 14 wherein said adhesive article comprises a further adhesive layer on a major side opposite to the side comprising the pressure sensitive adhesive layer and wherein said adhesive article is adhered to a rubber gasket through said further adhesive layer.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2010/025045

A. CLASSIFICATION OF SUBJECT MATTER
INV. C09J7/02 C09J153/00
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>WO 2008/070386 A (3M INNOVATIVE PROPERTIES CO [US]; WAID ROBERT D [US]; ZOLLER PANU K [U] 12 June 2008 (2008-06-12) cited in the application paragraphs [0073], [0085] - [0093]; claims 1,31,34,37,44,49,52,53; figure 1</p>	1-15
Y	<p>WO 02/04200 A (SCAPA TAPES NORTH AMERICA INC [US]) 17 January 2002 (2002-01-17) paragraph [0039]; claims 1,4-7,11,17-19; example examples</p>	1-15

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

23 April 2010

Date of mailing of the international search report

04/05/2010

Name and mailing address of the ISA/
 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040,
 Fax: (+31-70) 340-3016

Authorized officer

Sperry, Pascal

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/US2010/025045

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2008070386 A	12-06-2008	CA 2671436 A1	12-06-2008
		CN 101547989 A	30-09-2009
		EP 2094803 A1	02-09-2009
		KR 20090094441 A	07-09-2009
		US 2010075132 A1	25-03-2010

WO 0204200 A	17-01-2002	AU 7169201 A	21-01-2002
		EP 1299229 A1	09-04-2003
