



(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(86) Date de dépôt PCT/PCT Filing Date: 2018/04/05
(87) Date publication PCT/PCT Publication Date: 2018/10/11
(85) Entrée phase nationale/National Entry: 2019/10/07
(86) N° demande PCT/PCT Application No.: EP 2018/058806
(87) N° publication PCT/PCT Publication No.: 2018/185259
(30) Priorité/Priority: 2017/04/05 (EP17165133.4)

(51) Cl.Int./Int.Cl. *C22C 21/00* (2006.01)
(71) Demandeurs/Applicants:
AMAG CASTING GMBH, AT;
AUDI AG, DE
(72) Inventeurs/Inventors:
KAUFMANN, HELMUT, AT;
FRAGNER, WERNER, AT;
SUPPAN, HELMUT, AT;
SPIERINGS, ADRIAAN BERNARDUS, CH;
UGOWITZER, PETER J., CH;
SCHUBERT, ANDREAS, DE;
HUMMEL, MARC, DE
(74) Agent: RICHES, MCKENZIE & HERBERT LLP

(54) Titre : MATERIAU DE DEPART, SON UTILISATION ET PROCEDE DE FABRICATION ADDITIVE UTILISANT CE
MATERIAU DE DEPART
(54) Title: STARTING MATERIAL, USE THEREOF, AND ADDITIVE MANUFACTURING PROCESS USING SAID
STARTING MATERIAL

(57) **Abrégé/Abstract:**

Disclosed are an Al-Mg-based, Al-Mg-Si-based, Al-Zn-based or Al-Si-based starting material in the form of a powder or wire for an additive manufacturing process, the use of said starting material, and an additive manufacturing process using said starting material.

Abstract:

An Al-Mg-based or Al-Mg-Si-based or Al-Zn-based or Al-Si-based starting material in the form of a powder or wire for an additive manufacturing process, the use thereof, and an additive manufacturing process using this starting material are disclosed.

Starting Material, Use Thereof, and Additive Manufacturing Process Using Said Starting Material

Technical Field

The invention relates to an additive manufacturing process and an Al-Mg-based or Al-Mg-Si-based or Al-Zn-based or Al-Si-based starting material in the form of a powder or wire for an additive manufacturing process.

Prior Art

In order to increase the mechanical strength of directly generated molded bodies such as components that are manufactured using an additive powder bed-based manufacturing process, the prior art (DE102007018123A1) has disclosed using Al-Mg-based or Al-Mg-Sc-based (AlMg_{4,6}Sc_{1,4}) powder or wire as a starting material for this additive manufacturing process. Although the grain-refining effect of scandium is known – which grain-refining can also counteract a hot crack formation or warm crack formation in the component –, it is not possible with such powders to ensure a low level of solidification hot crack formation in the component – which problem is also known in laser welding. Known powder bed-based additive manufacturing processes therefore result in a significant processing uncertainty, which at this point, can only be reduced through a suitable alloy selection and narrow process windows. In other words, these circumstances limit the application field of additive manufacturing process.

The same is also known with other starting materials such as Al-Mg-Si-based or Al-Zn-based or Al-Si-based starting materials.

Summary of the Invention

The object of the invention, therefore, is to provide an Al-Mg-based or Al-Mg-Si-based or Al-Zn-based or Al-Si-based starting material in the form of a powder or wire for an in particular powder bed-based additive manufacturing process, which not only is advantageous in the mechanical properties that can be achieved in the molded body or component, but also can reduce the risk of a hot crack formation.

The invention attains the stated object with regard to the starting material according to the features of claim 1.

High mechanical properties such as hardness and a low tendency to hot crack formation can be ensured if the content of manganese (Mn) of at most 0.9 wt% and the content of iron of at most 0.5 wt% of the Al-Mg-based or Al-Mg-Si-based or Al-Zn-based or Al-Si-based starting material fulfills the ordering relation $(\text{wt\% Mn}) > A + \frac{0.15}{(\text{wt\% Fe})}$ where $A = 2000 * \left(\frac{\text{TLfcc}}{575} - 1\right)^4$ and $\text{TLfcc} = 660 - 6.6 * (\text{wt\% Si}) - 5.3 * (\text{wt\% Mg}) - 3.6 * (\text{wt\% Cu}) - 2 * (\text{wt\% Zn})$.

According to the invention, these limits in the composition of the alloy make it possible to ensure that in the structure formation during the in particular powder bed-based additive manufacturing process, the Fe/Mn-containing phase precipitates out before the Al matrix phase of the starting material, making it possible to achieve a finer structure formation. This surprisingly occurs despite the comparatively high content of iron and/or manganese – which high content according to current consensus among experts, forms coarse intermetallic precipitation phases and thus negatively influences the mechanical properties in the molded body or component.

It has also been possible to determine that while maintaining the ordering relation and taking into account the inherently high cooling speed during the in particular powder bed-based additive manufacturing process, the alloy elements iron and/or manganese can exhibit a particularly high recrystallization-hindering effect on the

structure – which can significantly reduce the risk of a solidification hot crack formation and can also significantly reduce pore formation in the molded body or component.

In addition, Fe and/or Mn can also contribute to the increase in strength of the molded body or component and thus further improve the mechanical properties.

By contrast with the prior art, with the starting material according to the invention, it is thus possible to ensure a particularly high level of process reliability in the additive manufacturing process – also permitting versatile use of this process.

The ordering relation can be enhanced if need be by means of the optional alloy elements silicon (Si) and/or magnesium (Mg) and/or copper (Cu) and/or zinc (Zn). In addition, the alloy can optionally contain 0.1 to 2 wt% scandium (Sc) and/or erbium (Er), optionally 0.1 to 3 wt% lithium (Li), optionally 0 to 2 wt% nickel (Ni), and optionally 0 to 1 wt% silver (Ag), beryllium (Be), cobalt (Co), chromium (Cr), hafnium (Hf), molybdenum (Mo), niobium (Nb), titanium (Ti), vanadium (V), zirconium (Zr), tantalum (Ta), or yttrium (Y) alone or in combination.

As the residue, the starting material contains aluminum (Al) and manufacture-dictated inevitable impurities. In general, it should be noted that the starting material can contain impurities, each comprising at most 0.05 wt% and all together comprising at most 0.15 wt%.

The mechanical properties of the molded body or component can be further increased if the starting material contains at least 0.6 wt% Fe. The structure can be further refined while maintaining the ordering relation by using a starting material containing 0.8 to 1.8 wt% Fe and Mn. The structure can also be further refined while maintaining the ordering relation by using a starting material containing 0.8 to 1.2 wt% Fe – which can result in improved mechanical properties of the molded body or component and in a structure with low porosity and a low amount of hot cracking.

With the upper limit of in particular up to 1.5 wt% Fe, preferably up to 1.2 wt% Fe, it is possible to limit the total quantity of intermetallic phases in order to be able to ensure a comparatively high ductility of the molded body or component. In this regard, an optimum can be achieved if the starting material contains 1 wt% Fe.

By limiting the sum of the alloy elements Fe and Mn in the composition to 0.7 to 2.1 wt%, it is possible to further improve the refining of the grain structure, which can further increase the mechanical properties. The latter can particularly improve by means of the narrower limits of 0.8 to 1.6 wt% Fe and Mn.

By having the starting material contain 0.05 to 12 wt% Si, 0.1 to 8 wt% Zn, 0.1 to 7 wt% Mg, and 0.05 to 2.5 wt% Cu, it is possible to further optimize the structure with regard to its freedom from pores or hot cracking.

The starting material can be Al-Mg-based in order to enable achievement of a component produced by means of an additive manufacturing process that has excellent corrosion resistance and temperature resistance with regard to mechanical properties such as fatigue strength, creeping, and yield strength. To accomplish this, a content of 2 to 7 wt% Mg is advisable.

If the starting material contains only 3 to 5 wt% Mg, it is possible, for example, to suppress the formation of fume particles produced during the melting process, which reduces the risk of a negative influence on the grain structure. The starting material according to the invention can thus also contribute to increasing the reproducibility of the additive manufacturing process. A further improvement of the hot cracking resistance can be achieved with 0.2 to 2 wt% scandium (Sc) and/or erbium (Er) – in connection with the other limits to the composition, 0.5 to 1.5 wt% Sc and/or Er can particularly excel for this purpose.

The starting material can be Al-Mg-Si-based, with Mg and Si as alloy elements. For this purpose, it can prove valuable for the starting material to contain 0.3 to 2 wt%

Mg and 0.05 to 1.5 wt% Si in order to increase mechanical properties and to reduce the susceptibility to hot cracking.

The properties mentioned above can be further improved if the starting material contains 0.3 to 1.2 wt% Mg and 0.5 to 1.2 wt% Si. In addition, due to the comparatively low Mg content, the formation of disadvantageous fume particles that are produced during the melting process can be further suppressed.

To embody a high-strength molded body or component, the starting material can be Al-Zn-based, with 1 to 8 wt% Zn, 1.0 to 3 wt% Mg, and 0.05 to 1.5 wt% Si. Since the limits of the composition according to the invention with regard to Fe/Mn suppress a crack formation particularly well, molded bodies or components manufactured out of such a starting material can especially excel in their tensile strength. The latter can be particularly increased if the starting material contains 4.5 to 8 wt% Zn in order to be able to ensure a high tensile strength of the molded body or component.

In addition to being Al-Si-based, the starting material can also contain 5 to 11 wt% Si in order to reduce the internal stresses and cracking tendency of the molded part or component. Preferably in this regard, the starting material contains 7 to 10 wt% Si.

The starting material according to the invention can be particularly suitable for an additive manufacturing process, in particular in a selective laser melting.

Another object of the invention is to improve the reproducibility of an additive manufacturing process.

The invention attains this stated object by means of the features of claim 13.

Because the starting material according to the invention is used in an additive manufacturing process, it is possible to significantly reduce the risk of solidification

hot crack formation and also pore formation in the molded body or component – which can lead to an increased reproducibility in the additive manufacturing process.

The foregoing applies particularly if a molded body or component is produced layer by layer from the starting material by locally melting it with a laser beam.

This can be the case, for example, in a powder bed-based additive manufacturing process such as selective laser melting.

Ways to Embody the Invention

To prove the achieved effects, molded bodies were manufactured from various powdered starting materials according to Table 1 with the aid of SLM (selective laser melting) as a powder bed-based additive manufacturing process – namely in the form of a cubic die.

| Powder starting materials / contents in [wt%] | | | | | | | | | | |
|---|----------|------|------|------|------|------|------|------|-----|------|
| | Basis | Mg | Mn | Sc | Zr | Fe | Si | Cu | Zn | Cr |
| 1 | Al-Mg | 4.7 | 0.54 | 0.01 | 0.45 | 0.06 | | | | |
| 2 | Al-Mg | 4.9 | 0.55 | 0.51 | 0.47 | 0.14 | | | | |
| 3 | Al-Mg | 4.5 | 0.55 | 0.50 | 0.45 | 0.60 | | | | |
| 4 | Al-Si | 0.36 | | | | 0.11 | 10.1 | | | |
| 5 | Al-Si | 0.36 | 0.3 | | | 1 | 10.1 | | | |
| 6 | Al-Mg-Si | 1.15 | 0.65 | | | 0.22 | 0.75 | 0.35 | 0.2 | 0.1 |
| 7 | Al-Mg-Si | 1.18 | 0.65 | | | 0.95 | 0.79 | 0.38 | 0.2 | 0.1 |
| 8 | Al-Zn | 2.65 | 0.3 | | | 0.11 | 0.1 | 1.6 | 5.8 | 0.22 |
| 9 | Al-Zn | 2.66 | 0.3 | | | 1.1 | 0.1 | 1.6 | 5.9 | 0.23 |

Table 1: Powder starting materials 1 to 9

Powder starting materials 1 to 9, in addition to the alloy elements listed in Table 1, contain residual Al and manufacture-dictated inevitable impurities, each comprising at most 0.05 wt% and all together comprising at most 0.15 wt%. The respective upper limit of at most 0.05 wt% also applies to the alloy elements listed in Table 1 whose contents are not indicated.

According to the ordering relation shown in claim 1, for powdered starting materials 1 to 9, the parameters A and TLfcc and the minimum content of Mn are calculated as follows:

| Powder starting materials | TLfcc | A | Mn [wt%] > |
|---------------------------|-------|-------|-------------|
| 1 | 635 | 0.24 | 2.74 |
| 2 | 634 | 0.22 | 1.29 |
| 3 | 636 | 0.26 | 0.51 |
| 4 | 591 | 0.001 | 1.36 |
| 5 | 591 | 0.001 | 0.15 |
| 6 | 647 | 0.494 | 1.18 |
| 7 | 647 | 0.485 | 0.64 |
| 8 | 628 | 0.144 | 1.51 |
| 9 | 628 | 0.141 | 0.28 |

Table 2: Parameter A, TLfcc, and minimum content of Mn

Al-Mg-based starting material:

According to Table 2, with regard to the Al-Mg-based starting materials 1, 2, and 3, it is clear that only powdered starting material 3, which contains 0.55 wt% Mn, fulfills the ordering relation according to claim 1 because its Mn content is higher than the Mn content stipulated by Table 2.

The individual powdered starting materials 1, 2, and 3 were each completely melted using selective laser melting with an energy density (ED) of 200 J/mm³. An Nd:YAG laser with a laser power of 200 to 400 W, a beam diameter of less than 1 mm, a sampling rate/scanning speed of 250 mm/s, and a powder layer thickness (Δz) of 30 μm were used for this. The molded bodies were each produced layer by layer through local melting of the powdered starting material 1, 2, and 3 according to Table 1 with a grain of approx. 30-45 μm . The scan spacing (also referred to as hatch distance) (Δy_s) of 135 μm was selected for each layer.

Al-Si-based starting material:

According to the Al-Si-based powdered starting materials 4 and 5 listed in Table 2, only the powdered starting materials 5 that contain 0.3 wt% Mn fulfill the ordering relation according to claim 1 because their Mn content is higher than the Mn content stipulated by Table 2.

The individual powdered starting materials 4 and 5 were each produced with selective laser melting using a Yb:YAG laser with a laser power of 200 W and a sampling rate/scanning speed of 500 mm/s. The molded bodies 4 and 5 were each produced layer by layer through local melting of the powdered starting material according to Table 1 with a grain of approx. 20-45 μm .

Al-Mg-Si-based starting material:

According to Table 2, with regard to the Al-Mg-Si-based starting materials 6 and 7, it is clear that only the powdered starting material 7 that contains 0.65 wt% Mn fulfills the ordering relation according to claim 1 because its Mn content is higher than the Mn content stipulated by Table 2.

The individual powdered starting materials 6 and 7 were each produced with selective laser melting using a Yb:YAG laser with a laser power of 200 W and a sampling rate/scanning speed of 500 mm/s. The molded bodies 6 and 7 were each produced

layer by layer through local melting of the powdered starting material according to Table 1 with a grain of approx. 20-45 μm .

Al-Zn-based starting material:

According to Table 2, with regard to the Al-Zn-based starting materials 8 and 9, it is clear that only the powdered starting material 9 that contains 0.3 wt% Mn fulfills the ordering relation according to claim 1 because its Mn content is higher than the Mn content stipulated by Table 2.

The individual powdered starting materials 8 and 9 were each produced with selective laser melting using a Yb:YAG laser with a laser power of 200 W and a sampling rate/scanning speed of 500 mm/s. The molded bodies 8 and 9 were each produced layer by layer through local melting of the powdered starting material according to Table 1 with a grain of approx. 20-45 μm .

The powdered starting materials 3, 5, 7, and 9 therefore constitute embodiments according to the invention.

The properties of the molded bodies thus achieved are listed in Table 2 below.

| Molded bodies made of powdered starting material | Hardness HV3 | Rm [MPa] | A [%] | Porosity [%] | Hot cracks |
|--|-----------------|-------------|-------------|-----------------|--|
| 1 | 73 | 270 | 9.0 | > 4 | > 400 μm |
| 2 | 74 | 274 | 10.5 | > 3.5 | > 200 μm |
| 3 | 105 | 370 | 19.5 | < 2 | < 30 μm |
| | | | | | |
| 4 | 116 | 430 | 7 | > 0.5 | > 50 μm |
| 5 | 130 | 480 | 14 | < 0.5 | < 30 μm |
| | | | | | |
| 6 | 108 | 315 | 17.5 | > 3 | > 350 μm |
| 7 | 116 | 340 | 23.5 | < 1.5 | < 100 μm |

| | | | | | |
|----------|------------|------------|-------------|-----------------|--|
| | | | | | |
| 8 | 173 | 570 | 9.5 | > 4.5 | > 500 μm |
| 9 | 181 | 595 | 11.5 | < 3 | < 180 μm |

Table 3: Characteristic values of molded bodies manufactured from the powdered starting materials

According to the invention Table 3, the molded bodies made of the powdered starting materials 1 and 2 had a significantly lower hardness compared to the molded body made of the powdered starting material 3 according to the invention – which is also reflected in a reduced tensile strength R_m and reduced ultimate elongation A . It was also possible to prove that molded bodies made of powdered starting material 3 can be manufactured by means of the selective laser melting method without hot cracking. These molded bodies also exhibited a lower porosity.

The porosity of the molded bodies was determined according to Archimedes' principle (hydrostatic scale).

A comparable result can also be observed with regard to the molded bodies made of the powdered starting materials 4 and 5; the powdered starting materials 7 and 8; and the powdered starting materials 8 and 9. Here, too, the same improved characteristic values of the molded body made of the powdered starting material 5, 8, and 9, respectively, with regard to tensile strength R_m , ultimate elongation A , freedom from hot cracking, and porosity.

Suitable lasers for the additive manufacturing process, depending on the radiation-absorbing properties of the powder used, also include CO₂ lasers, diode lasers, etc. In general, it should be noted that "in particular" is to be understood as an example.

Claims:

1. An Al-Mg-based or Al-Mg-Si-based or Al-Zn-based or Al-Si-based starting material in the form of a powder or wire for an additive manufacturing process, having

from 0.5 to 1.5 wt% iron (Fe),

at most 0.9 wt% manganese (Mn),

optionally silicon (Si), optionally magnesium (Mg), optionally copper (Cu), optionally zinc (Zn),

wherein the content of manganese (Mn) and iron (Fe) fulfills the ordering relation

$$(\text{wt}\% \text{ Mn}) > A + \frac{0.15}{(\text{wt}\% \text{ Fe})}$$

with

$$A = 2000 * \left(\frac{\text{TLfcc}}{575} - 1 \right)^4$$

$$\text{TLfcc} = 660 - 6.6 * (\text{wt}\% \text{ Si}) - 5.3 * (\text{wt}\% \text{ Mg}) - 3.6 * (\text{wt}\% \text{ Cu}) - 2 * (\text{wt}\% \text{ Zn}),$$

and optional having

0.1 to 2 wt% scandium (Sc) and/or erbium (Er),

0.1 to 3 wt% lithium (Li),

0 to 2 wt% nickel (Ni),

0 to 1 wt% silver (Ag), beryllium (Be), cobalt (Co), chromium (Cr), hafnium (Hf), molybdenum (Mo), niobium (Nb), titanium (Ti), vanadium (V), zirconium (Zr), tantalum (Ta), yttrium (Y) individually or in a combination

and residual aluminum (Al) and inevitable manufacturing induced impurities.

2. The starting material according to claim 1, characterized in that the starting material has

at least 0.6 wt% Fe,
in particular 0.8 to 1.2 wt% Fe,
in particular 1 wt% Fe.

3. The starting material according to claim 1 or 2, characterized in that the starting material has

0.7 to 2.1 wt% Fe and Mn,
in particular 0.8 to 1.8 wt% Fe and Mn,
in particular 0.8 to 1.6 wt% Fe and Mn.

4. The starting material according to claim 1, 2, or 3, characterized in that the starting material has

0.05 to 12 wt% Si,
0.1 to 8 wt% Zn,
0.1 to 7 wt% Mg, and
0.05 to 2.5 wt% Cu.

5. The starting material according to one of claims 1 to 4, characterized in that the starting material is Al-Mg-based, with

2 to 7 wt% Mg.

6. The starting material according to claim 5, characterized in that the starting material contains

3 to 5 wt% Mg and
0.2 to 2 wt% Sc and/or Er,
in particular 0.5 to 1.5 wt% Sc and/or Er.

7. The starting material according to one of claims 1 to 4, characterized in that the starting material is Al-Mg-Si-based, with
 - 0.3 to 2 wt% Mg and
 - 0.05 to 1.5 wt% Si.
8. The starting material according to claim 7, characterized in that the starting material contains
 - 0.3 to 1.2 wt% Mg and
 - 0.5 to 1.2 wt% Si.
9. The starting material according to one of claims 1 to 4, characterized in that the starting material is Al-Zn-based, with
 - 1 to 8 wt% Zn,
 - 1.0 to 3 wt% Mg, and
 - 0.05 to 1.5 wt% Si.
10. The starting material according to claim 9, characterized in that the starting material contains
 - 4.5 to 8 wt% Zn.
11. The starting material according to one of claims 1 to 4, characterized in that the starting material is Al-Si-based, with
 - 5 to 11 wt% Si,
 - in particular 7 to 10 wt% Si.
12. A use of the starting material according to one of claims 1 to 11 in an additive manufacturing process, in particular with a selective laser melting.
13. An additive manufacturing process with a starting material according to one of claims 1 to 11.

14. The additive manufacturing process according to claim 13, characterized in that a molded body or component is produced layer by layer from the starting material by locally melting it with a laser beam.

15. The additive manufacturing process according to claim 13 or 14, namely selective laser melting.