



(51) International Patent Classification:

C08L 25/08 (2006.01) *C08K 5/00* (2006.01)
C08L 101/00 (2006.01) *C08J 5/00* (2006.01)
C08K 3/00 (2006.01)

(21) International Application Number:

PCT/US2016/017266

(22) International Filing Date:

10 February 2016 (10.02.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/114,708 11 February 2015 (11.02.2015) US
62/114,701 11 February 2015 (11.02.2015) US

(71) Applicant: **POLYONE CORPORATION** [US/US];
33587 Walker Road, Avon Lake, Ohio 44012 (US).

(72) Inventor: **GU, Jiren**; 1213 Sandalwood Lane, Crystal
Lake, Illinois 60014 (US).

(74) Agents: **SAMBROOK, Michael J.** et al.; Polyone Corpora-
tion, 33587 Walker Road, Avon Lake, Ohio 44012 (US).

(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,

KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— *as to applicant's entitlement to apply for and be granted a
patent (Rule 4.17(ii))*

— *as to the applicant's entitlement to claim the priority of the
earlier application (Rule 4.17(iii))*

— *of inventorship (Rule 4.17(iv))*

Published:

— *with international search report (Art. 21(3))*

— *before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments (Rule 48.2(h))*

(54) Title: DAMPING THERMOPLASTIC ELASTOMERS

(57) Abstract: A thermoplastic elastomer compound includes styrenic block copolymer that is high vinyl styrene-(ethylene/butylene)-styrene block copolymer and high softening point tackifier. The high vinyl styrene-(ethylene/butylene)-styrene block copolymer has a Copolymer Tan Delta Peak Temperature and the thermoplastic elastomer compound has a Compound Tan Delta Peak Temperature. The Compound Tan Delta Peak Temperature is greater than the Copolymer Tan Delta Peak Temperature. The thermoplastic elastomer compound exhibits useful damping properties at or above room temperature while also advantageously possessing improved stability for processing and/or applications at high temperatures and upon exposure to weathering.



DAMPING THERMOPLASTIC ELASTOMERS

CLAIM OF PRIORITY

[0001] This application claims the benefit of U.S. Provisional Patent Application Serial Nos. 62/114,708 bearing Attorney Docket Number 12015003 and filed on February 11, 2015, and 62/114,701 bearing Attorney Docket Number 12015002 and filed on February 11, 2015, each of which is hereby incorporated by reference in its entirety.

FIELD OF THE INVENTION

[0002] This invention relates to thermoplastic elastomer compounds that exhibit useful damping properties such as vibration, sound, and/or impact damping at or above room temperature.

BACKGROUND OF THE INVENTION

[0003] Demand exists in a variety of applications for materials that exhibit damping properties. In general, damping is the dissipation of mechanical energy from a system. Damping can be important in applications such as electronics, sound isolation, automotive and transportation, building and construction, household appliances, industrial equipment, firearms, healthcare and medical devices, and personal and/or sports protection.

[0004] The capacity of a material for damping is related to its peak temperature of the tangent of delta (Tan Delta Peak Temperature), which can be determined by dynamic mechanical analysis (DMA) as described, for example, by M.P. Sepe in "Thermal Analysis of Polymers", *Rapra Review Reports*, Vol. 8, No. 11, 1997, which is incorporated herein by reference. The tangent of delta (Tan Delta) of a material is the ratio of its loss modulus (E'') to its storage modulus (E'). Consequently, as the value of Tan Delta increases, the response of the material is relatively more viscous than it is elastic, which thus provides greater damping. When graphically depicted against temperature, a Tan Delta

curve includes a prominent peak at a particular temperature, which is the Tan Delta Peak Temperature and also can be representative of or comparable to the glass transition temperature (T_g) of the material. In general, a material with a Tan Delta Peak Temperature which is relatively nearer to an application temperature, such as at or above room temperature, will possess better damping properties than a material with a Tan Delta Peak Temperature which is relatively lower than the application temperature.

[0005] Thermoplastic elastomers (TPEs), which are polymer materials that exhibit elasticity while remaining thermoplastic, can be used for damping applications. Thermoplastic elastomers can include styrenic block copolymers (SBC), thermoplastic vulcanizates (TPV), thermoplastic olefins (TPO), copolyesters (COPE), thermoplastic urethanes (TPU), copolyamides (COPA), and olefin block copolymers (OBC).

[0006] Some commercially available SBCs, such as HYBRAR 5127 available from Kuraray Co., Ltd., are known to exhibit vibration damping properties at room temperature. HYBRAR 5127 has a Tan Delta Peak Temperature that is reported to be 20 °C (i.e., about room temperature). Although HYBRAR 5127 can be formulated into conventional TPE compounds that exhibit effective room temperature damping, it is a relatively low molecular weight and non-hydrogenated material and cannot withstand processing at high temperatures required for some applications nor is it suitable for high temperature applications.

[0007] Other commercially available SBCs, such as HYBRAR 7125 available from Kuraray Co., Ltd., are hydrogenated and can withstand processing at the high temperatures. However, the Tan Delta Peak Temperature of HYBRAR 7125 is reported to be -5 °C. Disadvantageously, conventional TPE compounds based on HYBRAR 7125 do not possess satisfactory damping properties at room temperature. As a further disadvantage, SBCs available under the HYBRAR brand can be more expensive than other commercially

available SBCs, which can make such HYBRAR brand SBCs economically less desirable for some end-use applications.

[0008] Additionally, for some SBCs, it may be desirable to make the SBC softer by oil extension depending on processing and/or end-use application requirements. For example, paraffinic oil can be used as plasticizer to selectively plasticize the soft blocks of SBCs. Although adding paraffinic oil to the SBC results in lower hardness and lower melt viscosity, which may be desirable, doing so also severely decreases the Tan Delta Peak Temperature of the SBC, which negatively affects damping properties at room temperature.

SUMMARY OF THE INVENTION

[0009] Consequently, a need exists for TPE compounds that are capable of being processed at relatively high temperatures or suitable for applications at relatively high temperatures while also exhibiting useful damping properties, such as damping properties at or above room temperature, and also being economically viable for a broad scope of end-use applications. Such a need exists especially for TPE compounds that include plasticizer.

[00010] The aforementioned needs are met by one or more aspects of the present invention.

[00011] It has been found that, by adding high softening point tackifier to styrenic block copolymer that is high vinyl styrene-(ethylene/butylene)-styrene block copolymer (high vinyl SEBS) to provide a thermoplastic elastomer compound, the Copolymer Tan Delta Peak Temperature of the high vinyl SEBS can be shifted to a higher temperature (i.e., the Compound Tan Delta Peak Temperature) and, thereby, the damping capacity of the high vinyl SEBS can be increased for an intended end-use application at a given temperature, such as at or above room temperature. Surprisingly, the Copolymer Tan Delta Peak Temperature of the high vinyl SEBS can be shifted to a higher temperature even when the thermoplastic elastomer compound further includes plasticizer, which is known to decrease Tan Delta Peak Temperature.

[00012] One aspect of the invention is a thermoplastic elastomer compound that includes high vinyl SEBS and high softening point tackifier. The high vinyl SEBS has a Copolymer Tan Delta Peak Temperature and the compound has a Compound Tan Delta Peak Temperature. The Compound Tan Delta Peak Temperature is greater than the Copolymer Tan Delta Peak Temperature.

[00013] Another aspect of the invention is a plastic article formed from the aforementioned thermoplastic elastomer compound.

[00014] A further aspect of the invention is a multi-component plastic article including at least two components formed from different thermoplastic materials and in which at least one of the different thermoplastic materials is the aforementioned thermoplastic elastomer compound.

[00015] An even further aspect of the invention is a method for increasing the damping capacity of a thermoplastic elastomer compound including a styrenic block copolymer that is high vinyl SEBS by further including a high softening point tackifier in the thermoplastic elastomer compound.

[00016] Features of the invention will become apparent with reference to the following embodiments. There exist various refinements of the features noted in relation to the above-mentioned aspects of the present invention. Additional features may also be incorporated in the above-mentioned aspects of the present invention. These refinements and additional features may exist individually or in any combination. For instance, various features discussed below in relation to any of the described aspects of the present invention may be incorporated into any of the described aspects of the present invention alone or in any combination.

EMBODIMENTS OF THE INVENTION

[00017] In some embodiments, the present invention is directed to a thermoplastic elastomer compound that includes styrenic block copolymer that

is high vinyl SEBS and high softening point tackifier. In other embodiments, the present invention is directed to a plastic article formed from the aforementioned thermoplastic elastomer compound. In further embodiments, the present invention is directed to a multi-component plastic article in which at least one thermoplastic component is formed from the aforementioned thermoplastic elastomer compound. Required and optional features of these and other embodiments of the present invention are described.

[00018] As used herein, the term “Compound Tan Delta Peak Temperature” means the Tan Delta Peak Temperature for a thermoplastic elastomer compound of the present invention that comprises high softening point tackifier and high vinyl SEBS.

[00019] As used herein, the term “Copolymer Tan Delta Peak Temperature” means the Tan Delta Peak Temperature for the neat high vinyl SEBS; that is, for the high vinyl SEBS, itself, prior to combining it with any other ingredients of the thermoplastic elastomer compound of the present invention.

[00020] As used herein, the term “essentially free of” a certain component means, in some embodiments, that no amount of that component is intentionally incorporated into a compound. In other embodiments, it means that less than 1 weight percent of the component is intentionally incorporated into the compound; and, in other embodiments, it means that less than 0.1 weight percent of the component is intentionally incorporated into the compound; and, in other embodiments, it means that less than 0.01 weight percent of the component is intentionally incorporated into the compound; and, in other embodiments, it means that less than 0.001 weight percent of the component is intentionally incorporated into the compound.

[00021] As used herein, the term “high softening point tackifier” means a tackifier having a softening point of at least 80 °C according to ASTM 6493.

[00022] As used herein, the term “softening point” means a material softening temperature as measured by a ring and ball type method according to ASTM 6493.

[00023] As used herein, the term “high vinyl” means that the vinyl content of a styrenic block copolymer (prior to hydrogenation) is greater than 50 mole percent. For example, more than 50 mole percent of the polybutadiene present in the midblock is polymerized at the 1,2-position by driving the polymerization with addition of a polar compound, as is well known by those of ordinary skill in the art. After hydrogenation of the high vinyl styrenic block copolymer, there is little or no vinyl unsaturation remaining. Nonetheless, such a styrenic block copolymer, namely high vinyl SEBS, is still referred to as “high vinyl” because it is derived from a high vinyl precursor.

[00024] As used herein, “high vinyl SEBS” means high vinyl styrene-(ethylene/butylene)-styrene block copolymer.

[00025] As used herein, the term “low vinyl” means that the vinyl content of a styrenic block copolymer (prior to hydrogenation) is not greater than 50 mole percent.

[00026] As used herein, the term “room temperature” means a range of temperature of a defined environment, usually an indoor environment, which is generally considered comfortable for human habitation, and, can include, for example, any temperature ranging from about 15 °C to about 26 °C.

[00027] As used herein, the term “Tan Delta” means the tangent of delta of a material and is the ratio of the material’s loss modulus (E'') to the material’s storage modulus (E').

[00028] As used herein, the term “Tan Delta Peak Temperature” means the temperature at which a prominent peak appears in a graphical depiction of Tan Delta against temperature for a material, as determined by dynamic mechanical analysis using TA Instruments Dynamic Mechanical Analysis Model Q800 in “shear sandwich” mode and for a temperature scan from -40 °C

to 100 °C increasing at a rate of 5 °C per minute and with an oscillation frequency of 10 Hz.

[00029] Thermoplastic Elastomer Compound

[00030] In some embodiments, the present invention is directed to a thermoplastic elastomer compound that includes high vinyl SEBS and high softening point tackifier.

[00031] It has been found that, by adding high softening point tackifier to high vinyl SEBS to provide a thermoplastic elastomer compound, the Copolymer Tan Delta Peak Temperature of the high vinyl SEBS can be shifted to a higher temperature (i.e., the Compound Tan Delta Peak Temperature). That is, for thermoplastic elastomer compounds of the present invention, the Compound Tan Delta Peak Temperature is greater than the Copolymer Tan Delta Peak Temperature.

[00032] In some embodiments, the Compound Tan Delta Peak Temperature is at least -10 °C. In other embodiments, the Compound Tan Delta Peak Temperature is at least 0 °C. In further embodiments, the Compound Tan Delta Peak Temperature is at least room temperature. In even further embodiments, the Compound Tan Delta Peak Temperature is from about -10 °C to about 70 °C, and, in other embodiments, is from about 5 °C to about 50 °C.

[00033] High Vinyl SEBS Styrenic Block Copolymer

[00034] Thermoplastic elastomer compounds of the present invention include one or more styrenic block copolymer that is high vinyl SEBS.

[00035] Examples of commercially available high vinyl SEBS include one or more of the KRATON brand, including the KRATON ERS brand, of styrenic block copolymers from Kraton Polymers LLC, such as grades G1641, G1642, G1643, G1645, MD6958, and MD6959. KRATON brand G series styrenic block copolymers are known to have glass transition temperatures (T_g) ranging from around -55 °C to around -38 °C.

[00036] As used herein, “high vinyl” means that the vinyl content of the styrenic block copolymer (prior to hydrogenation) is greater than 50 mole

percent. In some embodiments, the vinyl content of the styrenic block copolymer is from about 55 to about 90 mole percent, and, in further embodiments, from about 65 to about 90 mole percent.

[00037] The high vinyl SEBS has an ethylene/butylene midblock that is the hydrogenation product of 1,3-butadiene.

[00038] Suitable high vinyl SEBS include those as described in, for example, United States Patent Nos. 5,777,031 to Djiauw et al. and 6,984,688 to Gu, each of which is incorporated herein by reference.

[00039] It is to be understood that an isoprene midblock that is hydrogenated is converted to an ethylene/propylene midblock. Similarly, it is to be understood that a butadiene midblock that is hydrogenated is converted to an ethylene/butylene midblock.

[00040] In some embodiments, suitable high vinyl SEBS has a relatively low weight average molecular weight. In other embodiments, suitable high vinyl SEBS has a relatively high weight average molecular weight. For example, suitable high vinyl SEBS can have weight average molecular weights in excess of 75,000 and preferably in excess of 200,000. In some embodiments, the styrenic block copolymer has a weight average molecular weight ranging from about 75,000 to about 1 million or from about 75,000 to about 500,000. In other embodiments, the styrenic block copolymer has a weight average molecular weight ranging from about 200,000 to about 1 million or from about 200,000 to about 500,000.

[00041] The high vinyl SEBS has a Copolymer Tan Delta Peak Temperature. As discussed above, by adding high softening point tackifier to high vinyl SEBS to provide a thermoplastic elastomer compound, the Copolymer Tan Delta Peak Temperature of the high vinyl SEBS can be shifted to a higher temperature (i.e., the Compound Tan Delta Peak Temperature).

[00042] It is believed that the high softening point tackifier is more effective at shifting the Copolymer Tan Delta Peak Temperature to a higher temperature for styrenic block copolymers having a Copolymer Tan Delta Peak

Temperature that is greater than about $-40\text{ }^{\circ}\text{C}$ but, for example, less than about $-10\text{ }^{\circ}\text{C}$, or, as a further example, less than about $0\text{ }^{\circ}\text{C}$, or, as an even further example, less than room temperature, or, as yet a further example, less than a temperature greater than room temperature.

[00043] In some embodiments, high vinyl SEBS has a Copolymer Tan Delta Peak Temperature that is greater than about $-40\text{ }^{\circ}\text{C}$ but less than $-10\text{ }^{\circ}\text{C}$, or, less than $0\text{ }^{\circ}\text{C}$, or, less than room temperature, or, less than a temperature greater than room temperature.

[00044] In some embodiments, the thermoplastic elastomer compound can include one or more other styrenic block copolymers in addition to the high vinyl SEBS. Non-limiting examples of other styrenic block copolymers include low vinyl styrene-ethylene/butylene-styrene (low vinyl SEBS), styrene-ethylene/propylene-styrene (SEPS), styrene-ethylene/ethylene/propylene-styrene (SEEPS), styrene-isobutylene-styrene (SIBS), styrene-butadiene-styrene (SBS), styrene-isoprene-styrene (SIS), and combinations thereof.

[00045] However, in further embodiments, the thermoplastic elastomer compound is essentially free of certain other styrenic block copolymers. For example, in some embodiments, the thermoplastic elastomer compound is essentially free of any high vinyl SEBS having a Copolymer Tan Delta Peak Temperature that is less than about $-40\text{ }^{\circ}\text{C}$ and/or any other styrenic block copolymers having a Copolymer Tan Delta Peak Temperature that is less than about $-40\text{ }^{\circ}\text{C}$.

[00046] In even further embodiments, the thermoplastic elastomer compound is essentially free of styrene-(ethylene-ethylene/propylene)-styrene block copolymer or low vinyl styrene-(ethylene/butylene)-styrene block copolymer or both. Some standard or low vinyl styrenic block copolymers, such as those available under the SEPTON brand from Kuraray Co., Ltd. and including SEPTON 4000 Series SEEPS copolymers, typically have a Copolymer Tan Delta Peak Temperature that is less than about $-40\text{ }^{\circ}\text{C}$.

[00047] In other embodiments, the thermoplastic elastomer compound is essentially free of hydrogenated styrene-isoprene-styrene block copolymer with hydrogenated vinylic isoprene midblock. Some commercially available examples of such styrenic block copolymers, such as those available from Kuraray Co., Ltd., under the HYBRAR brand, including grades 7125 and 7135, can be more expensive and thus economically less desirable for some end-use applications.

[00048] High Softening Point Tackifier

[00049] Thermoplastic elastomer compounds of the present invention include one or more high softening point tackifiers.

[00050] By adding high softening point tackifier to styrenic block copolymer that is high vinyl SEBS, the Copolymer Tan Delta Peak Temperature of the high vinyl SEBS can be shifted to a higher temperature (i.e., the Compound Tan Delta Peak Temperature).

[00051] High softening point tackifiers that are suitable for use in the present invention have a softening point of at least about 80 °C according to ASTM 6493. In some embodiments, the softening point is at least 100 °C, and, in other embodiments, at least about 120 °C, and, in further embodiments, at least about 140 °C. In even further embodiments, the softening point ranges from about 80 °C to about 150 °C.

[00052] Suitable high softening point tackifiers include those derived from rosin feedstock, terpene feedstock, or hydrocarbon feedstock. Hydrocarbon-based high softening point tackifiers can be aliphatic or aromatic, and saturated or unsaturated.

[00053] Examples of commercially available high softening point tackifiers include hydrogenated hydrocarbon resins available under the ARKON brand, such as grades P100, P115, P125, and P140, from Arakawa Chemical Industries, Ltd.; hydrogenated hydrocarbon resins available under the EASTOTAC brand, such as grades H-125-W, H-140-W, and H-142-W, from Eastman Chemical Company; hydrogenated hydrocarbon resins available under

the PLASTOLYN brand, such as grade R1140, from Eastman Chemical Company; and hydrogenated hydrocarbon resins available under the REGALREZ brand, such as grade 1139, from Eastman Chemical Company.

[00054] In some embodiments, the high softening point tackifier includes an amorphous hydrocarbon resin derived from aromatic hydrocarbon feedstock. In further embodiments, the high softening point tackifier is fully hydrogenated and has a saturated cyclo-aliphatic structure.

[00055] In some embodiments, the high softening point tackifier has a weight average molecular weight ranging from about 400 to about 3,500. In other embodiments, the high softening point tackifier has a weight average molecular weight ranging from about 1,000 to about 2,000.

[00056] High softening point tackifier is included in the thermoplastic elastomer compound of the present invention in amount ranging from about 20 parts by weight to about 200 parts by weight, per 100 parts by weight of the styrenic block copolymer. In some embodiments, the amount of high softening point tackifier ranges from about 30 parts by weight to about 150 parts by weight, per 100 parts by weight of the styrenic block copolymer.

[00057] It is believed that, in general, a relatively higher proportion of high softening point tackifier is required to shift the Tan Delta Peak Temperature to a higher temperature for styrenic block copolymer having a relatively higher molecular weight. Conversely, it is believed that, in general, a relatively lower proportion of high softening point tackifier is required to shift the Tan Delta Peak Temperature to a higher temperature for styrenic block copolymer having a relatively lower molecular weight.

[00058] Care should be taken to ensure that the thermoplastic elastomer compound of the present invention is formulated to provide properties desirable for a TPE compound and not properties more commonly observed in adhesive compositions. Generally, adhesive compositions are different from TPE compounds at least because adhesive compositions typically are relatively low viscosity compositions which do not possess the useful mechanical properties of

TPE compounds. Accordingly, even if up to about 200 parts by weight of high softening point tackifier is used per 100 parts by weight of styrenic block copolymer, the thermoplastic elastomer compound of the present invention is not an adhesive composition. For example, the thermoplastic elastomer compound is not tacky, or it is not sticky to the touch of a human hand.

[00059] Optional Plasticizer

[00060] In some embodiments, the thermoplastic elastomer compound further includes plasticizer. Plasticizer can be used, for example, to adjust softness and/or improve flow or other properties of the thermoplastic elastomer compound.

[00061] Any conventional oil capable of plasticizing styrenic block copolymer, such as mineral oil, vegetable oil, synthetic oil, etc., can be used in the present invention. Examples of commercially available oils include those available under the PURETOL 380 brand from Petro-Canada, and those available under the PRIMOL 382 brand from ExxonMobil.

[00062] In some embodiments, plasticizers with a higher molecular weight than that of the aforementioned conventional oils can be used. Polyisobutene (PIB) is an example of such a plasticizer with a relatively higher molecular weight. For example, medium- to high-molecular weight PIB is commercially available under the OPPANOL brand from BASF.

[00063] Optional Filler

[00064] In some embodiments, the thermoplastic elastomer compound further includes inorganic filler.

[00065] Inorganic filler can be used, for example, to lower the cost and/or control properties of the thermoplastic elastomer compound. In other embodiments, the inorganic filler also can be used, for example, as a mineral filler flame retardant.

[00066] Non-limiting examples of inorganic fillers include iron oxide, zinc oxide, magnesium oxide, titanium oxide, zirconium oxide, titanium dioxide, alumina, silica, silica-alumina, aluminum hydroxide, magnesium

hydroxide, calcium hydroxide, magnesium carbonate, calcium carbonate (heavy, light, colloidal), barium sulfate, calcium sulfate, sodium sulfate, calcium sulfite, calcium silicate, calcium phosphate, magnesium phosphate, talc, mica, kaolin, clay, wollastonite, hydrotalcite, glass beads, glass powders, silica sand, silica rock, silicon nitride, quartz powder, volcanic pumice, diatomaceous earth, white carbon, iron powder and aluminum powder.

[00067] In some embodiments, the inorganic filler is calcium carbonate, talc, or mixtures thereof.

[00068] Optional Secondary Polymer

[00069] In some embodiments, the thermoplastic elastomer compound further includes secondary polymer. Secondary polymer should be compatible with the styrenic block copolymer and can, for example, contribute to improved processability or desirable physical properties, such as hardness, in the thermoplastic elastomer compound.

[00070] Suitable secondary polymer includes polyolefin-based resins, including homopolymers, copolymers, blends of polymers, mixtures of polymers, alloys of polymers, and combinations thereof.

[00071] Non-limiting examples of polyolefins suitable for use in the present invention include polyethylene (including low-density (LDPE), high-density (HDPE), ultra-high molecular weight (UHDPE), linear-low-density (LLDPE), very-low density, etc.), maleated polypropylene, polypropylene, polybutylene, polyhexalene, polyoctene, and copolymers thereof, olefin block copolymer such as ethylene/alpha-olefin interpolymer, and ethylene-vinyl-acetate (EVA) copolymer. In some embodiments, high density polyethylene (HDPE) and/or polypropylene (PP) are preferred. Such polyolefins are commercially available from a number of sources.

[00072] Suitable secondary polymer also includes rubber, such as butyl rubber and ethylene propylene diene monomer (EPDM) rubber. The rubber can be crosslinked or non-crosslinked.

[00073] Mixtures, blends, or alloys of secondary polymer include, for example, a thermoplastic vulcanizate (TPV) that is a blend of a continuous phase of a polyolefin such as polypropylene and a discontinuous phase of a vulcanized rubber such as crosslinked EPDM.

[00074] Suitable secondary polymer also includes polyphenylene ethers (PPE). Non-limiting examples of types of PPE, sometimes also referred to as polyphenylene oxide, can include poly(2,6-dimethyl-1,4-phenylene ether), poly(2,6-diethyl-1,4-phenylene ether), poly(2-methyl-6-ethyl-1,4-phenylene ether), poly(2-methyl-6-propyl-1,4-phenylene ether), poly(2,6-dipropyl-1,4-phenylene ether), poly(2-ethyl-6-propyl-1,4-phenylene ether), poly(2,6-dimethoxy-1,4-phenylene ether), poly(2,6-di(chloro methyl)-1,4-phenylene ether), poly(2,6-di(bromo methyl)-1,4-phenylene ether), poly(2,6-diphenyl-1,4-phenylene ether), poly(2,6-ditoluyl-1,4-phenylene ether), poly(2,6-dichloro-1,4-phenylene ether), poly(2,6-dibenzyl-1,4-phenylene ether), poly(2,5-dimethyl-1,4-phenylene ether), and combinations thereof.

[00075] Optional Bonding Agent

[00076] In some embodiments in which the thermoplastic elastomer compound is overmolded onto a thermoplastic substrate, the thermoplastic elastomer compound further includes at least one bonding agent.

[00077] For embodiments in which the thermoplastic substrate is polyamide (nylon), suitable bonding agents include maleic anhydride functionalized polymers, such as maleic anhydride functionalized polyolefin and maleic anhydride functionalized styrenic block copolymer. For example, suitable maleic anhydride functionalized polyolefins are described in U.S. Patent No. 7,842,747 to Gu et al., which is incorporated herein by reference.

[00078] Examples of commercially available maleic anhydride functionalized polyolefin include those available under the EXXELOR brand from ExxonMobil Chemical; those available under the POLYBOND brand from Addviant; and those available under the FUSABOND brand from DuPont.

[00079] Examples of commercially available maleic anhydride functionalized styrenic block copolymer include those available under the KRATON FG brand, such as grades FG1901 and FG1924, from Kraton Performance Polymers Inc.

[00080] For embodiments in which the thermoplastic substrate is a polyolefin such as polypropylene, suitable bonding agents include compatible polyolefins such as those described above as secondary polymers, including polypropylene. Commercially available examples include polypropylene available under the BRASKEM H521 brand from Braskem America Inc.

[00081] For embodiments in which the thermoplastic substrate is a another thermoplastic material such as thermoplastic polyurethane (TPU), polycarbonate (PC), polycarbonate / acrylonitrile butadiene styrene (PC/ABS), and polybutylene terephthalate / polycarbonate (PBT/PC), suitable bonding agents include compatible polymers such as TPU or copolyester elastomer (COPE) or blends of TPU/COPE. Commercially available examples include TPU available under the ELASTOLLAN brand from BASF.

[00082] Other Optional Additives

[00083] In some embodiments, the thermoplastic elastomer compound further includes conventional plastics additives in an amount that is sufficient to obtain a desired processing or performance property for the compound. The amount should not be wasteful of the additive nor detrimental to the processing or performance of the compound. Those skilled in the art of thermoplastics compounding, without undue experimentation but with reference to such treatises as Plastics Additives Database (2004) from Plastics Design Library (elsevier.com), can select from many different types of additives for inclusion into the compounds of the present invention.

[00084] Non-limiting examples of optional additives that can be included in the thermoplastic elastomer compounds of the present invention include adhesion promoters; biocides; anti-fogging agents; anti-static agents; blowing and foaming agents; bonding agents and bonding polymers; dispersants; flame

retardants and smoke suppressants; impact modifiers; initiators; lubricants; micas; pigments, colorants and dyes; processing aids; release agents; silanes, titanates and zirconates; slip and anti-blocking agents; stabilizers; stearates; ultraviolet light absorbers; viscosity regulators; waxes; and combinations of any of the aforementioned additives.

[00085] In some embodiments, the thermoplastic elastomer compound further includes a physical foaming agent, such as carbon dioxide, nitrogen, or air, and/or a chemical foaming agent, such as organic or inorganic compounds that release gases upon decomposition, and can be injection molded or extruded into a foamed TPE material.

[00086] Ranges of Ingredients in the TPE Compounds

[00087] Table 1 below shows the acceptable, desirable, and preferable ranges of ingredients for the thermoplastic elastomer compound of the present invention, based on 100 parts by weight of the styrenic block copolymer included in the thermoplastic elastomer compound.

[00088] The thermoplastic elastomer compound of the present invention can comprise, consist essentially of, or consist of these ingredients. Any number between the ends of the ranges is also contemplated as an end of a range, such that all possible combinations are contemplated within the possibilities of Table 1 as embodiments of compounds for use in the present invention. Unless expressly stated otherwise herein, any disclosed number is intended to refer to exactly the disclosed number, “about” the disclosed number, or both exactly the disclosed number and “about” the disclosed number.

Table 1			
Thermoplastic Elastomer Compound			
(parts by weight per 100 parts by weight of SBC)			
Ingredient	Acceptable	Desirable	Preferable
Styrenic Block Copolymer	100	100	100
High Softening Point Tackifier	20 to 200	30 to 170	35 to 140
Optional Plasticizer	0 to 200	20 to 150	40 to 100
Optional Filler	0 to 150	0 to 100	0 to 80

Table 1			
Thermoplastic Elastomer Compound			
(parts by weight per 100 parts by weight of SBC)			
Ingredient	Acceptable	Desirable	Preferable
Optional Secondary Polymer	0 to 300	0 to 200	0 to 150
Optional Bonding Agent	0 to 300	0 to 200	0 to 150
Optional Other Additives	0 to 100	0 to 80	0 to 50

[00089] In some embodiments, especially those for low compression set applications, the thermoplastic elastomer compound can include at least about 50 parts, or, at least about 70 parts, but less than about 100 parts, or less than about 80 parts, by weight of high softening point tackifier, based on 100 parts by weight of the styrenic block copolymer included in the thermoplastic elastomer compound. In further embodiments, it is possible to achieve desirable low compression set and useful damping properties from thermoplastic elastomer compounds of the present invention that include less than about 40 weight percent, or, in some embodiments, less than about 35 weight percent, or, in other embodiments, less than about 25 weight percent, or, in further embodiments, less than about 20 weight percent, of styrenic block copolymer.

[00090] In other embodiments, especially those for noise or sound damping applications, the thermoplastic elastomer compound can include at least about 20 parts, or, at least about 40 parts, but less than about 70 parts, or, less than about 50 parts, by weight of high softening point tackifier, based on 100 parts by weight of the styrenic block copolymer included in the thermoplastic elastomer compound.

[00091] In further embodiments, especially those for impact damping applications, the thermoplastic elastomer compound can include at least about 75 parts, or, at least about 90 parts, but less than about 150 parts, or, less than about 110 parts, by weight of high softening point tackifier, based on 100 parts by weight of the styrenic block copolymer included in the thermoplastic elastomer compound.

[00092] In even further embodiments, the thermoplastic elastomer compound can include less than 30 weight percent of high softening point tackifier based on total weight of the compound. In even further embodiments, the thermoplastic elastomer compound can include less than 28 weight percent of high softening point tackifier based on total weight of the compound.

[00093] Processing

[00094] The preparation of thermoplastic elastomer compounds of the present invention is uncomplicated once the proper ingredients have been selected. The compound of the present can be made in batch or continuous operations.

[00095] Mixing in a continuous process typically occurs in an extruder that is elevated to a temperature that is sufficient to melt the polymer matrix with addition of all additives at the feed-throat, or by injection or side-feeders downstream. Extruder speeds can range from about 200 to about 700 revolutions per minute (rpm), and preferably from about 300 rpm to about 500 rpm. Typically, the output from the extruder is pelletized for later extrusion, molding, thermoforming, foaming, calendaring, and/or other processing into polymeric articles.

[00096] Subsequent extrusion, molding, thermoforming, foaming, calendaring, and/or other processing techniques are well known to those skilled in the art of thermoplastics polymer engineering. Without undue experimentation but with such references as “Extrusion, The Definitive Processing Guide and Handbook”; “Handbook of Molded Part Shrinkage and Warpage”; “Specialized Molding Techniques”; “Rotational Molding Technology”; and “Handbook of Mold, Tool and Die Repair Welding”, all published by Plastics Design Library (www.elsevier.com), one can make articles of any conceivable shape and appearance using compounds of the present invention.

USEFULNESS OF THE INVENTION

[00097] In some embodiments, the present invention is directed to a plastic article formed from the thermoplastic elastomer compound as described herein.

[00098] In other embodiments, the present invention is directed to a multi-component plastic article which includes at least two components formed from different thermoplastic materials one of which is the thermoplastic elastomer compound as described herein.

[00099] In further embodiments, the plastic article or a component of the multi-component plastic article can be shaped from the TPE compound by molding, extruding, thermoforming, calendaring, blow molding, and via additive 3-D manufacturing.

[000100] In even further embodiments, the present invention is directed to a method for increasing the damping capacity of a thermoplastic elastomer compound including a styrenic block copolymer by further including a high softening point tackifier in the thermoplastic elastomer compound.

[000101] As discussed above, it has been found that, by adding high softening point tackifier to styrenic block copolymer to provide a thermoplastic elastomer compound, the Copolymer Tan Delta Peak Temperature of the styrenic block copolymer can be shifted to a higher temperature (i.e., the Compound Tan Delta Peak Temperature). Advantageously, the damping capacity of the styrenic block copolymer can be increased for an intended end-use application at a given temperature, for example, at least -10 °C, or at least 0 °C, or at room temperature, or greater than room temperature.

[000102] Accordingly, thermoplastic elastomer compounds of the present invention can be used for any plastic article or any component of a multi-component plastic article which needs physical properties of a TPE, such as flexibility, elongation, and/or a soft or silky feel, while also providing useful damping capacity for applications at temperatures that are, for example, at least -10 °C, or at least 0 °C, or at room temperature, or greater than room temperature. Additionally, the thermoplastic elastomer compounds of the

present invention advantageously are capable of being processed at relatively high temperatures, such as those required for overmolding.

[000103] Because of its usefulness and versatility, the thermoplastic elastomer compound of the present invention has potential for a variety of damping applications in many different industries, including but not limited to: automotive and transportation; household appliances; industrial equipment; electronics; acoustics; communications; healthcare and medical; defense; firearms; security; personal safety; sports protection; and other industries or applications benefiting from the compound's unique combination of properties, such as low compression set and/or sound damping and/or impact damping.

[000104] Compression set is the permanent deformation of a viscoelastic material after being subjected to a constant stress and an elevated temperature. Conventional vibration damping thermoplastic elastomer compounds typically utilize low molecular weight styrenic block copolymers, such as HYBRAR 5127 styrenic block copolymer. These conventional TPE compounds tend to have high (i.e., poor) compression set, and, to achieve good damping, typically require in the TPE compound at least 40 weight percent of styrenic block copolymer, which is a relatively expensive ingredient.

[000105] According to the present invention, it is possible to use high molecular weight styrenic block copolymers, which provide low compression set, while also achieving useful damping capacity at or above room temperature. In some embodiments, thermoplastic elastomer compounds of the present invention have a compression set (at 70 °C for 22 hours according to ASTM D395) of less than 50 %, and, in other embodiments, less than 40 %, and, in further embodiments, less than 30 %. Additionally, it is possible to achieve desirable low compression set and useful damping properties from thermoplastic elastomer compounds of the present invention that include less than about 40 weight percent, or, in some embodiments, less than about 35 weight percent, or, in other embodiments, less than about 25 weight percent, or, in further embodiments, less than about 20 weight percent, of styrenic block

copolymer.

[000106] Sound damping is highly desirable for many applications including, for example, for high quality headphones and/or earphones or for speakers and components such as rims or gaskets for speakers. In the acoustics industry, sound damping is can be assessed by a hitting test and a rubbing test. For the hitting test, a cable (e.g., for wired headphones or earphones) is repeatedly hit by a wooden rod to simulate actual usage conditions. For the rubbing test, the wooden is moved back and forth along the cable. The acoustic responses or effective sound pressure levels generated by the hitting and rubbing are determined by an electronic artificial ear according to methodologies such as IEC 711 or evaluated by a human qualified as a so-called “golden ear”.

[000107] Because damping is frequency specific, vibration damping and sound damping can occur at different frequencies. As such, a material that is good for vibration damping is not necessarily good for sound damping. Indeed, conventional TPE compounds including low molecular weight styrenic block copolymers, such as HYBRAR 5127 styrenic block copolymer, possess good room temperature vibration damping properties. However, the same TPE compounds are not very effective at sound damping for wired headphone and/or earphone cable applications according to the hitting and rubbing tests.

[000108] According to the present invention, it is possible to provide excellent sound damping performance according to the hitting and rubbing tests while also achieving useful vibration damping properties. For example, an article formed from the TPE compound of the present invention, in response to a noise stimulus, can produce an effective sound pressure level according to IEC 711 that is at least 80 % lower, and, in some embodiments, at least 90 % lower, than an effective sound pressure level according to IEC 711 produced by a control article in response to the same noise stimulus.

[000109] Impact damping, such as for sports protection, typically requires materials with a relatively low hardness (e.g., having a Shore A hardness of less

than about 50) that have good outdoor (e.g., UV and thermal) stability and are additionally capable of withstanding numerous repeated industrial washing machine cycles (e.g., 150 cycles of 70 °C washing and 90 °C drying) while maintaining dimensional stability (e.g., without experiencing substantial shrinkage). Conventional TPE compounds including low molecular weight styrenic block copolymers, such as HYBRAR 5127 styrenic block copolymer, possess good room temperature vibration damping properties. However, the same TPE compounds have poor UV and thermal stability and cannot withstand repeated industrial washing machine cycles.

[000110] According to the present invention, it is possible to provide useful impact damping properties at room temperature with a thermoplastic elastomer compound that also has good UV and thermal stability and can withstand repeated industrial washing machine cycles. Additionally, as compared to ethylene-vinyl acetate (EVA) and/or urethane (PU) thermal set foams, which are bench mark materials for impact damping sports protection applications, thermoplastic elastomer compounds of the present invention can provide relative design freedom for sports equipment manufacturers (e.g., the TPE compound of the present invention can be molded with complex geometry) as well as relative additional comfort for sports equipment users (e.g., the TPE compound of the present invention can be softer and more flexible than EVA foam). Articles for impact protection made from the TPE compound of the present invention can be softer, more compact, and more flexible, and, thus, more comfortable, than conventional impact protection articles made from EVA and/or PU.

[000111] Additionally, if desirable for any application, the thermoplastic elastomer compound can be overmolded onto a substrate. In some embodiments, the substrate is a thermoplastic substrate such as polyamide (nylon) or polyolefin (e.g., polypropylene) or another thermoplastic material such as thermoplastic polyurethane (TPU), polycarbonate (PC), polycarbonate / acrylonitrile butadiene styrene (PC/ABS), or polybutylene terephthalate /

polycarbonate (PBT/PC). According to the present invention, the thermoplastic elastomer compound overmolded onto a thermoplastic substrate has 90 degree peel strength of, in some embodiments, greater than about 8 pounds per inch, and, in other embodiments, greater than about 10 pounds per inch.

EXAMPLES

[000112] Non-limiting examples of thermoplastic elastomer compounds of various embodiments of the present invention are provided.

[000113] Examples Showing Effect of High Softening Point Tackifier

[000114] Table 2a below shows sources of ingredients for the thermoplastic elastomer compounds of Examples 1 to 16.

Table 2a		
Chemical	Brand	Source
Styrene-(ethylene/ethylene/propylene)-styrene block copolymer	SEPTON 4055	Kuraray
High vinyl styrene-(ethylene/butylene)-styrene block copolymer (Low molecular weight)	KRATON G1642	Kraton
High vinyl styrene-(ethylene/butylene)-styrene block copolymer (High molecular weight)	KRATON G1641	Kraton
High vinyl styrene-(ethylene/butylene)-styrene block copolymer (Very high molecular weight)	KRATON MD6958	Kraton
High vinyl styrene-(ethylene/butylene)-styrene block copolymer (Very high molecular weight)	KRATON MD6959	Kraton
White mineral oil	380 vis USP white oil	(numerous)
Hydrocarbon resin	PLASTOLYN R1140	Eastman Chemical
Polyethylene resin	DOWLEX 2035	Dow Chemical

Table 2a		
Chemical	Brand	Source
Calcium carbonate (limestone)	VICRON 25-11	Specialty Minerals
Wax	KEMAMIDE E	PMC Biogenix
Antioxidant	IRGANOX 1010	BASF

[000115] Table 2b below shows the formulations and certain properties of Examples 1 to 5.

Table 2b				
Example	1		2	
Ingredient	Parts	Wt. %	Parts	Wt. %
SEPTON 4055	25	7.78	25	7.78
KRATON G1642	75	23.34	0	0
KRATON G1641	0	0	75	23.34
KRATON MD6958	0	0	0	0
KRATON MD6959	0	0	0	0
380 vis USP white oil	80	24.89	80	24.89
PLASTOLYN R1140	60	18.67	60	18.67
DOWLEX 2035	40	12.45	40	12.45
VICRON 25-11	40	12.45	40	12.45
KEMAMIDE E	0.7	0.22	0.7	0.22
IRGANOX 1010	0.7	0.22	0.7	0.22
TOTAL	321.4	100.00	321.4	100.00
Tan Delta Peak Height (unitless)	0.48		0.40	

Table 2b (cont.)						
Example	3		4		5	
Ingredient	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %
SEPTON 4055	25	7.78	25	7.78	100	31.11
KRATON G1642	0	0	0	0	0	0
KRATON G1641	0	0	0	0	0	0
KRATON MD6958	75	23.34	0	0	0	0

Table 2b (cont.)						
Example	3		4		5	
Ingredient	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %
KRATON MD6959	0	0	75	23.34	0	0
380 vis USP white oil	80	24.89	80	24.89	80	24.89
PLASTOLYN R1140	60	18.67	60	18.67	60	18.67
DOWLEX 2035	40	12.45	40	12.45	40	12.45
VICRON 25-11	40	12.45	40	12.45	40	12.45
KEMAMIDE E	0.7	0.22	0.7	0.22	0.7	0.22
IRGANOX 1010	0.7	0.22	0.7	0.22	0.7	0.22
TOTAL	321.4	100.00	321.4	100.00	321.4	100.00
Tan Delta Peak Height (unitless)	0.30		0.40		0.25	

[000116] Table 2c below shows the formulations and certain properties of Examples 6 to 9.

Table 2c								
Example	6		7		8		9	
Ingredient	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %
KRATON MD6958	100	33.18	100	31.11	100	29.29	100	27.67
380 vis USP white oil	80	26.54	80	24.89	80	23.43	80	22.14
PLASTOLYN R1140	40	13.27	60	18.67	80	23.43	100	27.67
DOWLEX 2035	40	13.27	40	12.45	40	11.72	40	11.07
VICRON 25-11	40	13.27	40	12.45	40	11.72	40	11.07
KEMAMIDE E	0.7	0.23	0.7	0.22	0.7	0.21	0.7	0.19
IRGANOX 1010	0.7	0.23	0.7	0.22	0.7	0.21	0.7	0.19
TOTAL	301.4	100.00	321.4	100.00	341.4	100.00	361.4	100.00
Tan Delta Peak Height (unitless)	0.65		0.70		0.85		0.85	
Compound Tan Delta Peak	3		2		7		16	

Table 2c								
Example	6		7		8		9	
Ingredient	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %
Temperature (deg C)								

[000117] Table 2d below shows the formulations and certain properties of Examples 10 to 13.

Table 2d								
Example	10		11		12		13	
Ingredient	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %
KRATON MD6959	100	33.18	100	31.11	100	29.29	100	27.67
380 vis USP white oil	80	26.54	80	24.89	80	23.43	80	22.14
PLASTOLYN R1140	40	13.27	60	18.67	80	23.43	100	27.67
DOWLEX 2035	40	13.27	40	12.45	40	11.72	40	11.07
VICRON 25-11	40	13.27	40	12.45	40	11.72	40	11.07
KEMAMIDE E	0.7	0.23	0.7	0.22	0.7	0.21	0.7	0.19
IRGANOX 1010	0.7	0.23	0.7	0.22	0.7	0.21	0.7	0.19
TOTAL	301.4	100.00	321.4	100.00	341.4	100.00	361.4	100.00
Tan Delta Peak Height (unitless)	0.5		0.70		0.70		0.75	
Compound Tan Delta Peak Temperature (deg C)	-8		3		18		24	

[000118] Table 2e below shows the formulations and certain properties of Examples 14 to 16.

Table 2e (cont.)			
Example	14	15	16

Ingredient	Parts	Wt. %	Parts	Wt. %	Parts	Wt. %
KRATON G1641	100	27.67	100	29.29	100	31.11
380 vis USP white oil	80	22.14	80	23.43	80	24.89
PLASTOLYN R1140	100	27.67	80	23.43	60	18.67
DOWLEX 2035	40	11.07	40	11.72	40	12.45
VICRON 25-11	40	11.07	40	11.72	40	12.45
KEMAMIDE E	0.7	0.19	0.7	0.21	0.7	0.22
IRGANOX 1010	0.7	0.19	0.7	0.21	0.7	0.22
TOTAL	361.4	100.00	341.4	100.00	321.4	100.00
Tan Delta Peak Height (unitless)	0.85		0.75		0.70	
Compound Tan Delta Peak Temperature (deg C)	21		11		3	

[000119] Examples of TPE Compounds with Low Compression Set

[000120] Table 3a below shows sources of ingredients for the thermoplastic elastomer compounds of Examples 17 to 18, which can be useful for end-use applications requiring low compression set and good damping capacity (e.g., vibration and/or sound damping).

Chemical	Brand	Source
High vinyl styrene-(ethylene/butylene)-styrene block copolymer (Very high molecular weight)	KRATON MD6958	Kraton
White mineral oil	PAROL 500	Petro-Canada
Polyphenylene ether	LXR 040C	Bluestar New Chemical Materials
Hydrocarbon resin	PLASTOLYN R1140	Eastman Chemical
HDPE	SCLAIR 2908	NOVA Chemicals
Wax	KEMAMIDE E	PMC Biogenix
Antioxidant	IRGANOX 1010	BASF

[000121] Table 3b below shows the formulations and certain properties of Examples 17 to 18.

Table 3b				
Example	17		18	
Ingredient	Parts	Wt. %	Parts	Wt. %
KRATON MD6958	100	32.13	100	29.74
PAROL 500	80	25.71	80	23.80
LXR 040C	30	9.64	30	8.92
PLASTOLYN R1140	75	24.10	75	22.31
SCLAIR 2908	25	8.03	50	14.87
KEMAMIDE E	0.5	0.16	0.5	0.15
IRGANOX 1010	0.7	0.22	0.7	0.21
TOTAL	311.2	100.00	336.2	100.00
Hardness (Shore A)	28		48	
Tensile (psic)	500		610	
Elongation (%)	560		590	
Compression set (%) (70 deg C, 22 h) (ASTM D395)	21		28	

[000122] Examples of TPE Compounds for Sound Damping

[000123] Table 4a below shows sources of ingredients for the thermoplastic elastomer compound of Example 19, which can be useful for sound and/or noise damping end-use applications.

Table 4a		
Chemical	Brand	Source
High vinyl styrene-(ethylene/butylene)-styrene block copolymer (Low molecular weight)	KRATON G1642	Kuraray
White mineral oil	550 vis USP white oil	(numerous)
Polyphenylene ether	LXR 040C	Bluestar New Chemical Materials

Table 4a		
Chemical	Brand	Source
Hydrocarbon resin	PLASTOLYN R1140	Eastman Chemical
Polypropylene	D036W6	Braskem
Wax	KEMAMIDE E	PMC Biogenix
Antioxidant	IRGAFOS 168	BASF
Antioxidant	IRGANOX 1010	BASF

[000124] Table 4b below shows the formulations and certain properties of Example 19.

Table 4b		
Example	19	
Ingredient	Parts	Wt. %
KRATON G1642	47	41.01
550 vis USP white oil	10	8.73
LXR 040C	20	17.45
PLASTOLYN R1140	20	17.45
D036W6	17	14.83
KEMAMIDE E	0.3	0.26
IRGAFOS 168	0.15	0.13
IRGANOX 1010	0.15	0.13
TOTAL	114.6	100.00
Hardness (Shore A)	65	
Tensile (psic)	1830	
Elongation (%)	600	

[000125] Examples of TPE Compounds for Impact Damping (e.g., for Personal and/or Sports Protection)

[000126] Table 5a below shows sources of ingredients for the thermoplastic elastomer compound of the Example 20, which can be useful for impact damping for personal and/or sports protection end-use applications.

Table 5a		
Chemical	Brand	Source
Styrene-(ethylene/ethylene/propylene)-styrene block copolymer	SEPTON 4077	Kuraray
Hydrogenated styrene-isoprene-styrene block copolymer with hydrogenated vinylic isoprene midblock	HYBRAR 7135	Kuraray
High vinyl styrene-(ethylene/butylene)-styrene block copolymer (Very high molecular weight)	KRATON MD6958	Kraton
White mineral oil	380 vis USP white oil	(numerous)
Hydrocarbon resin	PLASTOLYN R1140	Eastman Chemical
Polypropylene	H521	Braskem
Calcium carbonate (limestone)	VICRON 25-11	Specialty Minerals
Wax	KEMAMIDE E	PMC Biogenix
Antioxidant	IRGAFOS 168	BASF
Antioxidant	IRGANOX 1010	BASF

[000127] Table 5b below shows the formulations and certain properties of Example 20.

Table 5b		
Example	20	
Ingredient	Parts	Wt. %
KRATON MD6958	100	27.67
380 vis USP white oil	80	22.14
PLASTOLYN R1140	100	27.67
H521	40	11.07
VICRON 25-11	40	11.07
KEMAMIDE E	0.6	0.17
IRGAFOS 168	0.4	0.11
IRGANOX 1010	0.4	0.11
TOTAL	361.4	100.00
Hardness (Shore A)	45	
Tensile (psic)	650	

Table 5b		
Example	20	
Ingredient	Parts	Wt. %
Elongation (%)	800	

[000128] Examples of Damping TPE Compounds for Overmolding onto a Nylon Substrate

[000129] Table 6a below shows sources of ingredients for the thermoplastic elastomer compound of Example 21, which can be useful for damping end-use applications involving overmolding onto a nylon substrate.

Table 6a		
Chemical	Brand	Source
High vinyl styrene-(ethylene/butylene)-styrene block copolymer (Very high molecular weight)	KRATON MD6958	Kraton
White mineral oil	550 vis USP white oil	(numerous)
Hydrocarbon resin	PLASTOLYN R1140	Eastman Chemical
Maleic anhydride functionalized styrenic block copolymer	KRATON FG1924	Kraton
Maleic anhydride functionalized polypropylene	EXXELOR VA1801	ExxonMobil Chemical
LDPE	NA206	Equistar
Calcium carbonate (limestone)	VICRON 25-11	Specialty Minerals
Wax	KEMAMIDE B	PMC Biogenix
Antioxidant	IRGANOX 1010	BASF

[000130] Table 6b below shows the formulations and certain properties of Example 21.

Table 6b		
Example	21	
Ingredient	Parts	Wt. %

Table 6b		
Example	21	
Ingredient	Parts	Wt. %
KRATON MD6958	120	24.86
550 vis USP white oil	45	9.32
PLASTOLYN R1140	80	16.57
KRATON FG1924	25	5.18
EXXELOR VA1801	71	14.71
NA206	10	2.07
VICRON 25- 11	130	26.93
KEMAMIDE B	0.9	0.19
IRGANOX 1010	0.9	0.19
TOTAL	482.8	100.00
Hardness (Shore A)	40	
Tensile (psic)	400	
Elongation (%)	550	
Overmold substrate	nylon (30% glass filled, nylon 6)	
OM 90 degree peel strength (lb/in)	>16	

[000131] Without undue experimentation, those having ordinary skill in the art can utilize the written description of the present invention, including the Examples, to formulate thermoplastic elastomer compounds that exhibit useful damping properties, such as damping properties at or above room temperature, while also being capable of processing at relatively high temperatures, including those conditions required for overmolding.

[000132] All documents cited in the Embodiments of the Invention are, in relevant part, incorporated herein by reference; the citation of any document is not to be construed as an admission that it is prior art with respect to the present invention.

[000133] While particular embodiments of the present invention have been illustrated and described, it would be obvious to those skilled in the art that various other changes and modifications can be made without departing from the spirit and scope of the invention. It is therefore intended to cover in the appended claims all such changes and modifications that are within the scope of the present invention.

What is claimed is:

1. A thermoplastic elastomer compound comprising:
 - (a) high vinyl styrene-(ethylene/butylene)-styrene block copolymer having a Copolymer Tan Delta Peak Temperature; and
 - (b) tackifier having a softening point of at least about 80 °C according to ASTM 6493; andwherein the compound has a Compound Tan Delta Peak Temperature, and the Compound Tan Delta Peak Temperature is greater than the Copolymer Tan Delta Peak Temperature.
2. The compound of Claim 1, wherein the compound is essentially free of styrene-(ethylene-ethylene/propylene)-styrene block copolymer and low vinyl styrene-(ethylene/butylene)-styrene block copolymer.
3. The compound of Claim 1 or Claim 2, wherein the compound is essentially free of hydrogenated styrene-isoprene-styrene block copolymer with hydrogenated vinylic isoprene midblock.
4. The compound of any one of Claims 1 to 3, wherein the Copolymer Tan Delta Peak Temperature is greater than -40 °C but less than -10 °C.
5. The compound of any one of Claims 1 to 4, wherein the Compound Tan Delta Peak Temperature is at least -10 °C.
6. The compound of any one of Claims 1 to 5, wherein the tackifier has a softening point ranging from about 80 °C to about 150 °C according to ASTM 6493.

7. The compound of any one of Claims 1 to 6, wherein the tackifier has a weight average molecular weight ranging from about 400 to about 3,500.
8. The compound of any one of Claims 1 to 7, wherein the tackifier comprises a saturated cyclo-aliphatic amorphous hydrocarbon resin.
9. The compound of any one of Claims 1 to 8, wherein the tackifier is present in an amount ranging from about 20 parts by weight to about 200 parts by weight, per 100 parts by weight of the styrenic block copolymer.
10. The compound of any one of Claims 1 to 9, wherein the compound further comprises plasticizer.
11. The compound of any one of Claims 1 to 10, wherein the compound further comprises secondary polymer.
12. The compound of any one of Claims 1 to 11, wherein the compound further comprises filler.
13. The compound of any one of Claims 1 to 12, wherein the compound further comprises at least one additive selected from the group consisting of adhesion promoters; biocides; anti-fogging agents; anti-static agents; blowing and foaming agents; bonding agents and bonding polymers; dispersants; flame retardants and smoke suppressants; impact modifiers; initiators; lubricants; micas; pigments, colorants and dyes; processing aids; release agents; silanes, titanates and zirconates; slip and anti-blocking agents; stabilizers; stearates; ultraviolet light absorbers; viscosity regulators; waxes; and combinations of any of the aforementioned additives.

14. The compound of any one of Claims 1 to 13, wherein the compound comprises:

- (a) 100 parts by weight of the styrenic block copolymer;
- (b) from about 20 to about 200 parts by weight of the tackifier;
- (c) from 0 to about 200 parts by weight of optional plasticizer;
- (d) from 0 to about 300 parts by weight of optional secondary polymer;
- (e) from 0 to about 150 parts by weight of optional filler; and
- (f) from 0 to about 100 parts by weight of optional other additives.

15. A plastic article formed from the compound of any one of Claims 1 to 14.

A. CLASSIFICATION OF SUBJECT MATTER**C08L 25/08(2006.01)i, C08L 101/00(2006.01)i, C08K 3/00(2006.01)i, C08K 5/00(2006.01)i, C08J 5/00(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08L 25/08; C08L 53/00; C08L 53/02; C08J 9/00; C08F 236/06; B32B 15/08; C09D 153/02; C08L 101/00; C08K 3/00; C08K 5/00; C08J 5/00

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) & Keywords: damping, tan delta, styrene-butadiene-styrene block copolymer, SEBS, SEEPS, tackifier, thermoplastic elastomer

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2011-0184082 A1 (WRIGHT, KATHRYN J. et al) 28 July 2011 See paragraphs [0060]-[0061], [0094], [0099] and [0104]; and claims 1-3.	1-3
A	WO 2007-039309 A1 (HENKEL KGAA et al.) 12 April 2007 See page 6, lines 25-28; and claims 1, 4, 10 and 13.	1-3
A	US 2007-0021560 A1 (TSE, MUN FU et al.) 25 January 2007 See paragraph [0190]; and claims 1 and 8.	1-3
A	US 2012-0136129 A1 (KOHLESTRUNG, RAINER et al.) 31 May 2012 See paragraph [0014]; and claims 1 and 14.	1-3
A	US 2003-0158336 A1 (YAGUCHI, SHIGERU et al.) 21 August 2003 See paragraphs [0035] and [0040]; and claims 1, 9 and 15.	1-3

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

30 June 2016 (30.06.2016)

Date of mailing of the international search report

30 June 2016 (30.06.2016)

Name and mailing address of the ISA/KR

International Application Division

Korean Intellectual Property Office

189 Cheongsa-ro, Seo-gu, Daejeon, 35208, Republic of Korea

Facsimile No. +82-42-481-8578

Authorized officer

KIM, Dong Seok

Telephone No. +82-42-481-5405



Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. Claims Nos.: 4-15
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of any additional fees.
3. As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:

4. No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2016/017266

Patent document cited in search report	Publication date	Patent family member(s)	Publication date		
US 2011-0184082 A1	28/07/2011	CN 102725318 A	10/10/2012		
		CN 102725318 B	23/07/2014		
		EP 2528956 A1	05/12/2012		
		EP 2528956 A4	05/03/2014		
		JP 2013-518170 A	20/05/2013		
		JP 5595525 B2	24/09/2014		
		KR 10-1421855 B1	22/07/2014		
		KR 10-2012-0108053 A	04/10/2012		
		TW 201144374 A	16/12/2011		
		TW I426103 B	11/02/2014		
		US 8299177 B2	30/10/2012		
		WO 2011-094094 A1	04/08/2011		
		WO 2007-039309 A1	12/04/2007	AT 526356 T	15/10/2011
				BR PI0616990 A2	05/07/2011
CA 2624332 A1	12/04/2007				
CA 2626519 A1	23/09/2008				
CA 2626519 C	27/10/2015				
CN 101341198 A	07/01/2009				
CN 101341198 B	27/07/2011				
CN 101341199 A	07/01/2009				
CN 101341199 B	28/03/2012				
EP 1772480 A1	11/04/2007				
EP 1772480 B1	04/12/2013				
EP 1940927 A1	09/07/2008				
EP 1940927 B1	28/09/2011				
EP 1972655 A2	24/09/2008				
EP 1972655 A3	25/11/2009				
EP 1972655 B1	16/02/2011				
ES 2374645 T3	20/02/2012				
ES 2449515 T3	20/03/2014				
JP 2009-510241 A	12/03/2009				
JP 5133250 B2	30/01/2013				
KR 10-1277485 B1	21/06/2013				
KR 10-2008-0077099 A	21/08/2008				
MX 2008004446 A	20/10/2008				
US 2007-0100060 A1	03/05/2007				
US 2008-0176969 A1	24/07/2008				
US 2009-0012227 A1	08/01/2009				
US 7364221 B2	29/04/2008				
US 8729173 B2	20/05/2014				
WO 2007-039308 A1	12/04/2007				
US 2007-0021560 A1	25/01/2007	AT 555166 T	15/05/2012		
		CN 101218296 A	09/07/2008		
		CN 101218296 B	08/12/2010		
		EP 1904576 A1	02/04/2008		
		EP 1904576 B1	25/04/2012		
		JP 2009-501267 A	15/01/2009		

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2016/017266

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		JP 5438966 B2	12/03/2014
		US 8513347 B2	20/08/2013
		WO 2007-011530 A2	25/01/2007
		WO 2007-011530 A3	12/04/2007
		WO 2007-011541 A1	25/01/2007
US 2012-0136129 A1	31/05/2012	CA 2764689 A1	16/12/2010
		CN 102459446 A	16/05/2012
		CN 102459446 B	10/12/2014
		DE 102009026824 A1	09/12/2010
		EP 2440612 A1	18/04/2012
		EP 2440612 B1	15/04/2015
		ES 2542071 T3	30/07/2015
		JP 2012-529545 A	22/11/2012
		JP 5659227 B2	28/01/2015
		MX 2011013114 A	08/02/2012
		US 8436105 B2	07/05/2013
		WO 2010-142563 A1	16/12/2010
US 2003-0158336 A1	21/08/2003	CN 1247732 C	29/03/2006
		CN 1422317 A	04/06/2003
		EP 1277822 A1	22/01/2003
		EP 1277822 A4	28/07/2004
		MY 128694 A	28/02/2007
		TW I221851 B	11/10/2004
		US 7241837 B2	10/07/2007
		WO 01-74964 A1	11/10/2001