

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(10) International Publication Number  
**WO 2015/033092 A1**

(43) International Publication Date  
12 March 2015 (12.03.2015)

- (51) **International Patent Classification:**  
*A61K 49/04* (2006.01)
- (21) **International Application Number:**  
PCT/GB2014/000351
- (22) **International Filing Date:**  
5 September 2014 (05.09.2014)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**  
1315936.3 6 September 2013 (06.09.2013) GB
- (71) **Applicant: BIOCOMPATIBLES UK LTD** [GB/GB];  
Chapman House, Farnham Business Park, Weydon Lane,  
Farnham, Surrey GU9 8QL (GB).
- (72) **Inventors: HOHN, Stéphane;** Organisation for the Pro-  
hibition of Chemical Weapons, Johan de Wittlaan 32, 2517  
JR, The Hague (NL). **LEWIS, Andrew Lennard;** Biocom-  
patibles UK Ltd, Lakeview, Riverside Way, Watchmoor  
Park, Camberley, Surrey GU15 3YL (GB). **WILLIS, Sean  
Leo;** Biocompatibles UK Ltd, Lakeview, Riverside Way,  
Watchmoor Park, Camberley, Surrey GU15 3YL (GB).  
**DREHER, Matthew, R.;** BTG International Inc., Five  
Tower Bridge, Suite 800, 300 Barr Harbor Drive, West  
Conshohocken, PA 19428 (US). **ASHRAFI, Koorosh;**  
Biocompatibles UK Ltd, Lakeview, Riverside Way, Watch-  
moor Park, Camberley, Surrey GU15 3YL (GB). **TANG,  
Yiqing;** Biocompatibles UK Ltd, Lakeview, Riverside
- Way, Watchmoor Park, Camberley, Surrey GU15 3YL  
(GB).
- (74) **Agent: RODGERS, Matthew;** BTG International Limited,  
5 Fleet Place, London, EC4M 7RD (GB).
- (81) **Designated States** (*unless otherwise indicated, for every  
kind of national protection available*): AE, AG, AL, AM,  
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,  
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,  
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,  
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,  
KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,  
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,  
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,  
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,  
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States** (*unless otherwise indicated, for every  
kind of regional protection available*): ARIPO (BW, GH,  
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,  
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,  
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,  
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,  
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,  
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, KM, ML, MR, NE, SN, TD, TG).
- Published:**  
— *with international search report (Art. 21(3))*



WO 2015/033092 A1

(54) **Title:** IMAGEABLE POLYMERS

(57) **Abstract:** This invention relates to imageable polymers, particularly those comprising poly vinylalcohol and to methods for making them as well as to embolic microspheres comprising the polymers. The microspheres are imageable during embolization procedures and can be loaded with drugs or other therapeutic agents to provide an imageable drug delivery system

## IMAGEABLE POLYMERS

This invention relates to radiopaque polymers and to methods for making them. The invention provides radiopaque hydrogels and, in particular, radiopaque hydrogel microspheres, which are imageable during embolization procedures. The microspheres can be loaded with drugs or other therapeutic agents to provide an imageable drug delivery system.

Radiopacity, refers to the property of obstructing, or attenuating, the passage of electromagnetic radiation, particularly x-rays. Radiopaque materials are therefore visible in X-ray radiographs or during X-ray imaging and under fluoroscopy. Radiopaque materials consequently find many uses in radiology and medical imaging techniques such as computed tomography (CT) and fluoroscopy.

Embolization of blood vessels (blocking the blood flow) is an important medical procedure in the treatment of tumours, fibroids and vascular malformations, in which an embolus, or blockage is introduced into a blood vessel to reduce blood flow and induce atrophy of tumours and malformations. There is a range of embolic materials in clinical use that require transcatheter delivery to the site of embolization. Recently the use of microspheres (also referred to herein as “beads”) as injectable embolic materials has become popular because their shape and size can be controlled making them more predictable in use than previous particulate material.

Imaging of embolization procedures is important because it provides the clinician with the ability to monitor the precise location of the embolic material and ensure that it is administered to, and remains in, the correct position in the vasculature, thus improving procedural outcomes and reducing procedural risk. Imaging is currently only possible when using inherently radiopaque embolic materials or by mixing non-radiopaque embolic particles with radiopaque materials.

Iodinated polyvinyl alcohol (I-PVA) is a radiopaque embolic material in the form of a viscous liquid which precipitates in aqueous conditions encountered *in vivo*. However, the precise location at which the embolus is formed can be inconsistent risking precipitation occurring in an off target location.

Contrast agents, such as Ethiodol® and Isovue® are, however, routinely mixed with embolic particles to impart radiopacity to an injectable composition.

Although such compositions are useful, the different physical properties of the aqueous suspension of embolic particle and the contrast agent results in different in-vivo localisation. After administration, it is the contrast agent which is visible rather than the embolic particle, and the contrast agent and the embolic particle may not  
5 reside at the same location in tissue.

There is a need, therefore, to combine the predictability and reproducibility benefits of embolic microspheres with the radiopacity of contrast agents.

EP1810698 describes a process for forming stable radiopaque embolic beads (also referred to herein as RO beads or RO microspheres) in which PVA hydrogel  
10 embolic beads are loaded with iodinated oils to make them radiopaque. The mechanism by which the oil is held within the bead is unclear. Furthermore, since the oil is a mixture of ethiodised fatty acids, the end product is not closely defined and this approach does not provide control over elution of the contrast agent from the bead nor does it contemplate the impact of contrast agent on the loading and elution  
15 of drug.

WO2011/110589 describes synthesis of an iodinated poly(vinyl alcohol) by grafting iodobenzoyl chloride to poly(vinyl alcohol) via ester linkages. Whilst this polymer is demonstrated to be radiopaque, the process results in a water insoluble polymer, which cannot then be formed into microspheres through the water-in-oil  
20 polymerisation processes normally used to generate hydrogel microspheres with desirable embolization properties. The same publication mentions microspheres but contains no disclosure as to how this is achieved.

Mawad et al (Biomacromolecules 2008, 9, 263-268) describes chemical modification of PVA-based degradable hydrogels in which covalently bound iodine is  
25 introduced into the polymer backbone to render the polymer radiopaque. Iodine is introduced by reacting 0.5% of the pendent alcohol groups on PVA with 4-iodobenzoylchloride. The resulting polymer is biodegradable, embolizes via precipitation and is not formed into microspheres.

There is clearly a need, therefore, for radiopaque embolic materials which  
30 combine the embolization efficiency and reproducibility of embolic beads with the radiopacity of contrast agents, such as ethiodized oils, in a single product. The ideal embolic particle is one which is intrinsically radiopaque and which is stable and reproducible, in size and physical properties such that the clinician can perform and

image the embolization procedure with more certainty that visible contrast results from the embolic particle. The injection and deposition of these beads into the vascular site could be monitored but monitoring during clinical follow up would also be possible to monitor the effects of embolization, ensure embolic remains in the desired location and to identify regions at risk for further treatment. The time window in which follow-up imaging can be obtained is increased significantly over existing methods.

Radiopacity (the ability to attenuate X-rays) can be quantified according to the Hounsfield scale. Hounsfield units measure radiopacity on a volume (voxel) basis. A typical voxel in X-ray computed tomography (CT) is approximately  $1\text{mm}^3$  and so individual microspheres of a diameter of the order of  $100\mu\text{m}$  must have a high radiopacity in order that it, or a collection of them in a vessel (for example) will increase the radiopacity of that voxel and so be visualised. Radiopacity of greater than 100HU and preferably greater than 500HU would be appropriate.

In addition to good radiopacity, the ideal embolic bead would have properties which enable efficient drug loading and elution such that chemoembolization procedures may be monitored with confidence.

The applicants have established that by utilizing relatively straightforward chemistry, it is possible modify polymers to make them radiopaque. A low molecular weight aldehyde comprising one or more covalently attached radiopaque halogens (such as bromine or iodine) is coupled to the polymer by reaction with 1,3 diol groups of the polymer. Reaction with 1,2 glycols is also possible. This forms a cyclic acetal (a dioxane ring in the case of reaction with 1,3,diols) to which is covalently coupled, a halogenated group. The halogenated group has a molecular weight of less than 1000 Daltons and is typically less than 750 Daltons. Typically the minimum is 156 daltons.

The halogenated group typically has between 6 and 18 carbons, but preferably between 6 and 10; and optionally one oxygen atom; and comprises an aromatic ring comprising one or more covalently attached radiopaque halogens. The aromatic ring is preferably a phenyl group.

The chemistry results in a polymer having a defined radiopaque group covalently attached to the polymer, in a predictable and controllable fashion. It may be performed on any diol-containing polymer and it is particularly suited to hydrogel polymers and pre-formed microspheres, such that non-radiopaque microspheres may

be rendered intrinsically and permanently radiopaque, without adversely affecting the physical properties of the microsphere (i.e. size, spherical shape, high water content, swellability, and compressibility). The radiopaque microspheres have similar, and/or better, drug loading capacities and/or elution properties to the non-radiopaque beads from which they are formed. The radiopacity of the microsphere is permanent or sufficiently long-lived to allow for monitoring during clinical follow up.

The ability to post-process pre-formed beads provides a degree of flexibility in terms of manufacturing in that the same manufacturing process can be used for radiopaque and non-radiopaque beads and size selection or sieving can be made either prior to post-processing so that only a particular size or size range of beads may be made radiopaque, or if necessary, after post processing, so that sizing takes into account any variation in bead size due to the radiopacifying process.

Accordingly, in a first aspect, the present invention provides a polymer comprising 1,2-diol or 1,3-diol groups acetalised with a radiopaque species. Acetalisation with a radiopaque species results in the radiopaque species being coupled to the polymer through a cyclic acetal group (a dioxane in the case of 1,3 diol polymers). The radiopacity of the polymer is thus derived from having a radiopaque material covalently incorporated into the polymer via cyclic acetal linkages.

As used herein, "radiopaque species" and "radiopaque material" refers to a chemical entity, or a substance modified by such a chemical entity, which is visible in X-ray radiographs and which can be resolved, using routine techniques, such as computed tomography, from the medium that surrounds the radiopaque material or species.

The term microsphere or bead refers to micron sized spherical or near spherical embolic materials. The term particle or microparticle refers to embolic particles that are irregular in shape and are generally derived e.g. from breaking up a larger monolith.

Where the text refers to "halogen" or "halogenated" iodine is preferred, unless otherwise stated.

Reference to the level of radiopacity in HU refers to measurements carried out by X-Ray Micro Computer Tomography, and preferably when measured using a 0.5mm aluminium filter and a source voltage of 65kV, preferably in an agarose phantom as described herein (Example 12), preferably using the instrument and

conditions described herein (Example 12). Reference to radiopacity in terms of greyscale units also refers to measurements carried out by X-Ray Micro Computer Tomography under these conditions.

Reference to "wet beads" or "fully hydrated beads" means beads fully hydrated in normal saline (0.9%NaCl 1 mM phosphate buffer pH7.2 to 7.4) as packed volume (e.g. as quantified in a measuring cylinder).

In this aspect and others, the polymer can be any one which comprises 1,2-diol or 1,3 diol groups or a mixture thereof. Preferably the polymer comprises a high degree of the diol groups throughout the polymer backbone, such as a polyhydroxypolymer. The polymer is suitably a hydrogel or other cross-linked polymer network. Particularly suitable polymers are those which comprise polyvinyl alcohol (PVA) or copolymers of PVA. PVA based hydrogels are particularly preferred as these are well known in the art and are used extensively in embolization procedures.

In a particular embodiment, the polymer comprises a PVA backbone which has pendant chains bearing crosslinkable groups, which are crosslinked to form a hydrogel. The PVA backbone has at least two pendant chains containing groups that can be crosslinked, such as acetates and acrylates. The crosslinkers are desirably present in an amount of from approximately 0.01 to 10 milliequivalents of crosslinker per gram of backbone (meq/g), more desirably about 0.05 to 1.5 meq/g. The PVA polymers can contain more than one type of crosslinkable group. The pendant chains are conveniently attached via the hydroxyl groups of the polymer backbone are attached via cyclic acetal linkages to the 1,3-diol hydroxyl groups of the PVA.

Cross linking of the modified PVA may be via any of a number of means, such as physical crosslinking or chemical crosslinking. Physical cross linking includes, but is not limited to, complexation, hydrogen bonding, desolvation, Van der Waals interactions, and ionic bonding. Chemical crosslinking can be accomplished by a number of means including, but not limited to, chain reaction (addition) polymerization, step reaction (condensation) polymerization and other methods as will be routine for the polymer chemist.


Crosslinked groups on the PVA polymer backbone are suitably ethylenically unsaturated functional groups, such as acetates, which can be crosslinked via free radical initiated polymerization without requiring the addition of an aldehyde

crosslinking agent. Preferably, the PVA polymer comprises pendent acetate groups formed from the acetalisation of PVA with N-acryloyl-aminoacetaldehyde dimethylacetal (NAADA). Such a modification of PVA is described in US patent number 5,583,163. An example of this type of modified PVA is Nelfilcon A.


5           The cross-linkable PVA is suitably cross-linked with an additional vinylic comonomer and, suitably a hydrophilic vinylic comonomer such as hydroxy-substituted lower alkyl acrylates and methacrylates, acrylamides and methacrylamides. In a particular embodiment the modified PVA as described above is crosslinked with 2-acrylamido-2-methylpropanesulfonic acid (AMPS® monomer  
10 from Lubrizol Corporation) to provide an acrylamido polyvinyl alcohol-co-acrylamido-2-methylpropane sulfonate hydrogel. In a preferred embodiment the cross-linking reaction is performed as an inverse emulsion polymerisation reaction to yield the acrylamido polyvinyl alcohol-co-acrylamido-2-methylpropane sulfonate hydrogel in the form of microspheres.

15           The polymer or hydrogel of the invention is radiopaque by virtue of a covalently attached radiopaque material throughout the polymer in the form of a cyclic acetal. Reactions for the formation of cyclic acetals are well known in organic chemistry and, thus, any radiopaque species which is able to form cyclic acetals is envisaged within the scope of the invention. Many materials are known to be  
20 radiopaque, such as Iodine, Bismuth, Tantalum, Gadolinium, Gold, Barium and Iron. Electron dense elements, such as the halogens, are particularly useful. Bromine, chlorine, fluorine and iodine can readily be incorporated into organic molecules which are able to form cyclic acetal linkages and provide a high degree of radiopacity. Consequently, in a particular embodiment the radiopaque polymer  
25 comprises a covalently attached halogen, preferably iodine. The radiopaque halogen is covalently attached to an aromatic group to form the radiopaque species which is linked to the polymer through the cyclic acetal. The aromatic group may comprise 1,2,3 or 4 covalently attached radiopaque halogens such as bromine or iodine. The group preferably comprises a phenyl group to which is covalently attached 1,2,3 or 4  
30 such radiopaque halogens. Thus the polymer conveniently comprises a halogenated group (X in the formula below), comprising covalently bound radiopaque halogens, such as iodine, which are attached to the polymer via a cyclic acetal.

Acetalisation with a radiopaque species results in the radiopaque species being coupled to the polymer through a cyclic acetal group as illustrated below. The radiopaque polymer has or comprises a structure according to General Formulas I (in PVA J is -CH<sub>2</sub>-) or II (which illustrates other polymers with 1,2 or 1,3 diols): Control of the number of such groups acetalised (n) in the polymers controls the amount of iodine present and therefore the radiopacity. The number of diols per gm of material is discussed below.



I



II


10

Wherein X is a group substituted by one or more halogens and preferably one or more bromine or iodine moieties and n is at least one.

J is a group -CH<sub>2</sub>- or is a bond.

15

X is preferably a group of the formula



III

wherein Z is a linking group bonded to the cyclic acetal, or is absent, such that the phenyl group is bonded to the cyclic acetal;

if Z is present, then Z is C<sub>1-6</sub> alkylene, C<sub>1-6</sub> alkoxyethylene or C<sub>1-6</sub> alkoxyalkylene ;  
Hal is 1,2,3 or 4 covalently attached radiopaque halogens

5

Preferably if Z is present, Z is a methylene or ethylene group or is a group – (CH<sub>2</sub>)<sub>p</sub>-O-(CH<sub>2</sub>)<sub>q</sub>- wherein q is 0, 1 or 2 and p is 1 or 2; more preferably a group selected from -CH<sub>2</sub>O-, -CH<sub>2</sub>OCH<sub>2</sub>- and -(CH<sub>2</sub>)<sub>2</sub>O-,

In particular Z is -CH<sub>2</sub>OCH<sub>2</sub>- or -CH<sub>2</sub>O- or is absent

10 Hal is in particular 3 or 4 Bromines of iodines and preferably iodines, such as 2,3,5 or 2,4,6 triiodo or 2,3,4,6 tetraiodo

J is preferably -CH<sub>2</sub>-.

Thus preferably, radiopaque iodine is incorporated into the polymer in the  
15 form of an iodinated phenyl group. As above, the iodinated phenyl groups are incorporated into the polymer through cyclic acetal linkages.

Groups, such as those described above and in particular halogenated (e.g. iodinated) phenyl groups, are useful because they can be mono, di, tri or even tetra-substituted in order to control the amount of the halogen, such as iodine, that is  
20 incorporated into the radiopaque polymer, and hence control the level of radiopacity.

The potential level of halogenation is also influenced by the level of 1,3 or 1,2 diol groups in the polymer starting material. The level can be estimated based on the structure of the polymer and the presence or other wise of any substitutions of the -OH groups, for example by cross linkers or other pendent groups. Polymers having a  
25 level of -OH groups of at least 0.1mmol/g of dried polymer are preferred. Polymers having a level of at least 1mmol/g are more preferred. An excellent level of radiopacity has been achieved with polymers having greater than 5 mmol/g -OH groups, (2.5mmol/g diols).

It will be understood by the person skilled in the art that the amount of iodine,  
30 or other radiopaque halogen, in the polymer may also be controlled by controlling the degree of acetalisation in the polymer. In the present invention, the polymer comprises up to 50% of acetalised diol groups. Preferably at least 10% of the diol groups in the polymer are acetalised and more preferably at least 20% of the diols

groups are acetalised. Whether the amount of halogen (e.g. iodine) in the polymer is controlled by increasing the substitution, for example on a phenyl ring, or by controlling the degree of acetalisation of the polymer, the resulting polymer contains at least 10% halogen by dry weight (weight of halogen/total weight). Preferably the polymer contains at least 20% halogen by dry weight and preferably greater than 30%, 40%, 50% or 60% halogen by dry weight. A useful contrast is obtained with polymers having between 30 and 50% halogen by dry weight.

Halogen content may also be expressed as amount of halogen (in mg) per ml of beads. This refers to the amount of halogen per ml of fully hydrated beads in saline as a packed volume (e.g., as quantified in a measuring cylinder). The present invention provides beads with levels of halogen (particularly iodine) of, for example, greater than 15mg per ml of wet beads. Halogen (particularly iodine) content of greater than 25 or 50 mg preferably greater than 100mg per ml of beads have provided good results.

The present invention is particularly suited to hydrogels and, in particular, hydrogels in the form of microparticles or microspheres. Microspheres are particularly useful for embolization as sizes of microsphere can be controlled, for example by sieving) and unwanted aggregation of embolic avoided due to the spherical shape. Microspheres can be made by a number of techniques known to those skilled in the art, such as single and double emulsion, suspension polymerization, solvent evaporation, spray drying, and solvent extraction.

Microspheres comprising poly vinylalcohol or vinyl alcohol copolymers are described, for example in Thanoo *et al* Journal of Applied Biomaterials, Vol. 2, 67-72 (1991); WO0168720, WO03084582; WO06119968 and WO04071495, (which are incorporated herein by reference). In a particular embodiment the hydrogel microspheres are prepared from PVA modified with N-acryloyl-aminoacetaldehyde dimethylacetal (NAADA), as described above (and disclosed in US5,583,163) and cross-linked with 2-acrylamido-2-methylpropanesulfonic acid, as described above. Hydrogel microspheres of this type are described in US 6,676,971 and US 7,070,809.

Microspheres can be made in sizes ranging from about 10  $\mu\text{m}$  (microns) to 2000 $\mu\text{m}$ . Smaller sizes may pass through the microvasculature and lodge elsewhere. In most applications it will be desirable to have a small size range of microspheres in order to reduce clumping and provide predictable embolisation. The process used to

make the microspheres can be controlled to achieve a particular desired size range of microspheres. Other methods, such as sieving, can be used to even more tightly control the size range of the microspheres.

In a particular embodiment hydrogel or non hydrogel microspheres according to the invention have a mean diameter size range of from 10 to 2000 $\mu$ m, more preferably 20 to 1500 $\mu$ m and even more preferably, 40 to 900  $\mu$ m. Preparations of microspheres typically provide particles in size ranges to suit the planned treatment, for example 100-300, 300-500, 500-700 or 700-900 microns. Smaller particles tend to pass deeper into the vascular bed and so for certain procedures, particles in the range 40-75, 40-90 and 70-150 microns are particularly useful.

In a particular embodiment, the polymer is a hydrogel microsphere with a net negative charge at physiological pH (7.4).

Radiopacity can be quantified according to the Hounsfield scale, on which distilled water has a value of 0 Hounsfield units (HU), and air has a value of -1000 HU. Conveniently the embolic microsphere will have radiopacity greater than 100HU and even more preferably greater than 500HU. Using the approach described herein, it has been possible to prepare radiopaque microspheres with a radiopacity of greater than 10000HU. Preferred microspheres have a radiopacity greater than 2000, 3000, 4000 or 5000 HU. Radiopacity of these levels allows the microspheres to be differentiated from blood (30-45HU), liver (40-60HU) brain (20-45HU) and soft tissue (100-300HU), for example.

Radiopacity can also be expressed in Grey Scale units, between 0 and 255 after background subtraction, according to American Society for Testing and Materials (ASTM) F-640.

A further aspect of the invention therefore provides, a radiopaque microsphere as described herein, in the first aspect, having a radiopacity of at least 500HU.

The hydrogel microspheres of this embodiment may be used in compositions with suitable excipients or diluents, such as water for injection, and used directly to embolise a blood vessel. Thus a further aspect of the invention provides a pharmaceutical composition comprising a hydrogel microsphere as described herein and a pharmaceutically acceptable carrier or diluent.

Consequently pharmaceutical compositions comprising radiopaque hydrogel microspheres which are formed from a polymer comprising 1,2-diol or 1,3-diol groups acetalised with a radiopaque species as described herein, form a further aspect of the invention. It is preferred that the polymer comprises an iodinated aromatic group covalently bound to the polymer through cyclic acetal linkages as described above.

Pharmaceutical compositions comprising the radiopaque microspheres may also comprise additional radiopaque materials, such as, for example contrast agents, (either ionic or non ionic, including oily contrast agents such as ethiodised poppy seed oil (Lipiodol®). Suitable non ionic contrast agents include iopamidol, iodixanol, iohexol, iopromide, iobtiridol, iomeprol, iopentol, iopamiron, ioxilan, iotrolan, iotrol and ioversol.

Ionic contrast agents may also be used, but are not preferred in combination with drug loaded ion exchange microspheres since high ionic concentrations favour disassociation of the ionic drugs from the matrix. Ionic contrast agents include diatrizoate, metrizoate and ioxaglate.

The microspheres may be dried by any process that is recognised in the art, however, drying under vacuum, such as by freeze drying (lyophilisation) is advantageous as it allows the microspheres to be stored dry and under reduced pressure. This approach leads to improved rehydration as discussed in WO07147902 (which is incorporated herein by reference). Typically, the pressure under which the dried microspheres are stored is less than 1mBar (guage).

Alternatively, or additionally, an effective amount of one or more biologically active agents can be included in the embolic compositions. It may be desirable to deliver the active agent from the formed radiopaque hydrogel or from microspheres. Biologically active agents that it may be desirable to deliver include prophylactic, therapeutic, and diagnostic agents including organic and inorganic molecules and cells (collectively referred to herein as an "active agent", "therapeutic agent" or "drug"). A wide variety of active agents can be incorporated into the radiopaque hydrogels and microspheres. Release of the incorporated active agent from the hydrogel is achieved by diffusion of the agent from the hydrogel in contact with aqueous media, such as body fluids, degradation of the hydrogel, and/or degradation

of a chemical link coupling the agent to the polymer. In this context, an "effective amount" refers to the amount of active agent required to obtain the desired effect.

Accordingly in a further aspect the invention provides a pharmaceutical composition comprising a radiopaque hydrogel microsphere as described above and a  
5 therapeutic agent wherein the therapeutic agent is absorbed into the hydrogel matrix. A further aspect of the invention provides a composition comprising one or more radiopaque hydrogel microspheres as described herein, the microspheres additionally comprising one or more therapeutic agents, such as pharmaceutical actives. Examples of active agents, or pharmaceutical actives that can be incorporated include, but are  
10 not limited to, anti-angiogenic agents, cytotoxics and chemotherapeutic agents, making the microspheres particularly useful for chemoembolization procedures.

In a particularly advantageous embodiment, the radiopaque hydrogel microspheres of the invention have a net charge such that charged drugs may be loaded into the microsphere e.g. by an ion exchange mechanism. As a result, the  
15 therapeutic agent is electrostatically held in the hydrogel and elutes from the hydrogel in electrolytic media, such as physiological saline, or in-vivo, e.g. in the blood or tissues, to provide a sustained release of drug over several hours, days or even weeks. In this embodiment it is particularly useful if the radiopaque hydrogel microspheres of the invention have a net negative charge over a range of pH, including  
20 physiological conditions (7.4) such that positively charged drugs may be controllably and reproducibly loaded into the microsphere, and retained therein electrostatically, for subsequent prolonged elution from the hydrogel in-vivo. Such charges may be derived from ion exchange groups such as carboxyl or sulphonate groups attached to the polymer matrix. It will be understood that drugs without charge at physiological  
25 pHs may still be loaded into microspheres of the invention and this may be particularly advantageous when rapid elution or a "burst effect" is desired, for example, immediately after embolization or simply for rapid drug delivery to tissue in cases where embolization is not required or necessary, or where their low solubility under physiological conditions determines their release profile rather than ionic  
30 interaction.

Particularly preferred examples of drugs which may be loaded in this way include, but are not limited to, camptothecins (such as irinotecan and topotecan) and anthracyclines (such as doxorubicin, daunorubicin, idarubicin and epirubicin),

antiangiogenic agents (such as vascular endothelial growth factor receptor (VEGFR) inhibitors, such as axitinib, bortezomib, bosutinib canertinib, dovitinib, dasatinib, erlotinib gefitinib, imatinib, lapatinib, lestaurtinib, masutinib, mubitinib, pazopanib, pazopanib semaxanib, sorafenib, tandutinib, vandetanib, vatalanib and vismodegib.),  
5 microtubule assembly inhibitors (such as vinblastine, vinorelbine and vincristine), Aromatase inhibitors (such as anastrozole), platinum drugs, (such as cisplatin, oxaliplatin, carboplatin and miriplatin), nucleoside analogues (such as 5-FU, cytarabine, fludarabine and gemcitabine) and. Other preferred drugs include  
10 paclitaxel, docetaxel, mitomycin, mitoxantrone, bleomycin, pingyangmycin, abiraterone, amifostine, buserelin, degarelix, folinic acid, goserelin, lanreotide, lenalidomide, letrozole, leuprorelin, octreotide, tamoxifen, triptorelin, bendamustine, chlorambucil, dacarbazine, melphalan, procarbazine, temozolomide, rapamycin (and analogues, such as zotarolimus, everolimus, umirolimus and sirolimus) methotrexate, pemetrexed and raltitrexed.

15 The radiopaque hydrogel microspheres are preferably water-swellaable but water-insoluble.

In an embodiment the beads are water-swellaable but have some solubility in water. In this embodiment, the extent of swelling may be controlled by the use of aqueous salt solutions or suitable solvents, as may be determined by routine  
20 experimentation. This may be particularly applicable to PVA polymers which are non-covalently cross-linked.

In another embodiment the beads are water and solvent-swellaable but are also biodegradable. In this embodiment the beads biodegrade in-vivo over a period ranging from 4 weeks to 24 months. Biodegradable polymers comprising PVA are  
25 disclosed in, for example, WO2004/071495, WO 2012/101455 and Frauke-Pistel et al. J. Control Release 2001 May 18; 73(1):7-20.

As discussed above the radiopaque polymers of the invention may be made by utilizing straightforward chemistry to directly modify pre-formed microspheres to make them intrinsically radiopaque. Accordingly, in a further aspect, the invention  
30 provides a method of making a radiopaque polymer comprising reacting a polymer comprising 1,2- diol or 1,3-diol groups with a radiopaque species capable of forming a cyclic acetal with said 1,2-diol or 1,3 diols preferably under acidic conditions.

Particularly the radiopaque species capable of forming the cyclic acetal comprises a covalently bound radiopaque halogen such as iodine as described herein. Particularly the halogen is covalently bound to an aromatic group such as a phenyl group.

5 The chemistry is particularly suited to polymers with a backbone of units having a 1,2-diol or 1,3-diol structure, such as polyhydroxy polymers. For example, polyvinyl alcohol (PVA) or copolymers of vinyl alcohol containing a 1,3-diol skeleton. The backbone can also contain hydroxyl groups in the form of 1,2-glycols, such as copolymer units of 1,2-dihydroxyethylene. These can be obtained, for  
10 example, by alkaline hydrolysis of vinyl acetate-vinylene carbonate copolymers.

Other polymeric diols can be used, such as saccharides. In a particular embodiment, the polymer is cross-linked, such as cross-linked PVA or copolymers of PVA.

Polyvinyl alcohols, that can be derivatized as described herein preferably have  
15 molecular weight of at least about 2,000. As an upper limit, the PVA may have a molecular weight of up to 1,000,000. Preferably, the PVA has a molecular weight of up to 300,000, especially up to approximately 130,000, and especially preferably up to approximately 60,000.

In a preferred embodiment, the PVA is a cross-linked PVA hydrogel, in which  
20 PVA modified with N-acryloyl-aminoacetaldehyde dimethylacetal (NAADA) is cross-linked with 2-acrylamido-2-methylpropanesulfonic acid, as described above, preferably in the form of microspheres, as described in US 6,676,971 and US 7,070,809.

The radiopaque species is acetalised, and covalently attached to the polymer,  
25 through diol groups. Preferred radiopaque species are electron dense chemical moieties, such as simple organic molecules or organometallic complexes providing radiopacity greater than +1 HU, and which comprises a reactive moiety that enables formation of a cyclic acetal with diol groups on the polymer. Particular reactive moieties include aldehydes, acetals, hemiacetals thioacetals and dithioacetals

30 In a particular embodiment the radiopaque species comprises bromine or iodine. This is convenient because small organic molecules in which bromine or iodine has been substituted are commercially available or may be prepared using chemistry well known in the art. For example, iodinated or brominated aldehydes are

radiopaque and are readily incorporated into diol-containing polymers using the method of the invention. Particularly useful radiopaque species include iodinated or brominated benzyl aldehydes, iodinated phenyl aldehydes and iodinated phenoxyaldehydes.

5           The reaction of radiopaque aldehydes with diol-containing polymers works surprisingly well with hydrogel polymers, which have been pre-formed, for example into microspheres (although other preformed hydrogel structures such as coatings are contemplated). Thus, in another aspect the invention provides a method of making a radiopaque hydrogel microsphere comprising the steps of:

10           (a) swelling a pre-formed hydrogel microsphere comprising a polymer with 1,2-diol or 1,3-diol groups in a solvent capable of swelling said microsphere; and (b) mixing or contacting the swollen microspheres with a solution of a radiopaque species capable of forming a cyclic acetal with said 1,2 or 1,3 diols under acidic conditions; and (c) extracting or isolating the microspheres.

15           The extracted or isolated microspheres may then be used directly, formulated into pharmaceutical compositions as described above or dried for long-term storage.


          In a preferred embodiment, the reaction is performed on an acrylamido polyvinyl alcohol-co-acrylamido-2-methylpropane sulfonate hydrogel microsphere. Examples of such microspheres are described in US 6,676,971 and US 7,070,809.

20           The reaction is conveniently conducted in polar organic solvent, and more particularly, polar aprotic solvents such as tetrahydrofuran (THF), ethyl acetate, acetone, dimethylformamide (DMF), acetonitrile (MeCN) and dimethyl sulfoxide (DMSO), although suitable solvents will be determined by the skilled person through routine experimentation and/or consideration of solvent properties such as boiling  
25           point, density etc.

          The reaction is rapid and may be conducted at room temperature or at elevated temperature to improve yields and decrease reaction time. In a preferred embodiment the reaction is conducted at a temperature greater than 25°C and suitably greater than 40°C but less than 135°C and preferably less than 80°C. Reaction temperatures  
30           between 50 and 75°C are particularly useful. At elevated temperatures the conversion of hydrogel bead to radiopaque hydrogel bead can be accomplished in as little as 2-3 hours.

As above, the radiopaque species comprises a functional group selected from the group consisting of aldehydes, acetals, hemiacetals, thioacetals and dithioacetals, and comprises iodine or other radiopaque halogen. In this context, the groups such as the acetals and thioacetals may be considered to be protected aldehydes. Iodinated aldehydes, such as iodinated benzyl aldehyde, iodinated phenyl aldehyde or iodinated phenoxyaldehyde, are particularly useful and they are widely available and give good reaction yields.

Thus, preferably the radiopaque species is a compound of the formula IV:



IV

10

wherein

A is a group capable of forming a cyclic acetal with a 1,2 diol or 1,3 diol.

Preferably A is an aldehyde, acetal, hemiacetal, thioacetal or dithioacetal group;

15

Preferably A is  $-\text{CHO}$ ,  $-\text{CHOR}^1\text{OR}^2$ ,  $-\text{CHOR}^1\text{OH}$ ,  $-\text{CHSR}^1\text{OH}$  or  $-\text{CHSR}^1\text{SR}^2$  Wherein  $\text{R}^1$  and  $\text{R}^2$  are independently selected from  $\text{C}_{1-4}$  alkyl, preferably methyl or ethyl.

Specific examples of radiopaque species that have been shown to produce radiopaque PVA hydrogel microspheres include 2,3,5-triiodobenzaldehyde, 2,3,4,6-tetraiodobenzaldehyde and 2-(2,4,6-triiodophenoxy)acetaldehyde

20

In a further aspect the invention provides a radiopaque hydrogel microsphere obtained or obtainable by the reaction of a polymer comprising 1,2-diol or 1,3-diol groups with a halogenated aldehyde, a halogenated acetal or a halogenated hemiacetal a halogenated thioacetal or a halogenated dithioacetal.

25

In a preferred embodiment of this aspect the radiopaque hydrogel microsphere is obtained by the reaction of an acrylamido polyvinyl alcohol-co-acrylamido-2-methylpropane sulphonate hydrogel microsphere. These microspheres, examples of which are disclosed in US 6,676,971, US 7,070,809 and WO 2004/071495, have been found to react rapidly with iodinated aldehydes, iodinated acetals and iodinated

30

thioacetals to yield radiopaque microspheres with high iodine content and provide good contrast in-vivo. The physical characteristics (size, shape, charge, drug loading ability etc) are not adversely affected by iodination and in some cases are improved. Handling also appears to be largely unaffected. Mechanical robustness is preserved  
5 and the beads do not aggregate and suspend well in contrast agent and other delivery vehicles, such that delivery through a catheter may be achieved with relative ease. Delivery has been observed to be smooth and even, without any blocking of the catheter. Furthermore, the beads are stable to steam and autoclave sterilization methods.

10 Particularly suitable iodinated aldehydes include, but are not limited to, 2,3,5-triiodobenzaldehyde, 2,3,4,6-tetraiodobenzaldehyde and 2-(2,4,6-triiodophenoxy)acetaldehyde

The radiopaque microspheres and compositions described above may be used in a method of treatment in which the microspheres described herein or composition  
15 comprising them is administered into a blood vessel of a patient to embolise said blood vessel. The blood vessel is likely one associated with solid tumour, such as hypervascular hepatic tumours including hepatocellular carcinoma (HCC) and some other hepatic metastases including metastatic colorectal carcinoma (mCRC) and neuroendocrine tumours (NETs). The methods of treatment are imageable and  
20 provide the clinician with good visual feedback on the procedure in real-time or near real-time. Such methods are particularly useful where a pharmaceutical active is loaded into the microspheres, and the treatment provides for the delivery of a therapeutically effective amount of the active to a patient in need thereof.

The radiopaque microspheres may also be used in procedures in which the  
25 microspheres are delivered to the site of action by injection. One approach to this is the delivery of microspheres comprising pharmaceutical actives directly to tumours by injection.

The present invention also provides compositions and microspheres of the invention for use in the methods of treatment described above.

30 The microspheres described herein are surprisingly efficient in loading and eluting drugs. The microspheres readily load positively charged drugs, such as *i.a.* doxorubicin, epirubicin, daunorubicin, idarubicin and irinotecan. Experimental studies have shown that the ability of the microsphere to load and elute drug is the

same before beads are rendered radiopaque using the chemistry of the invention as it is after reaction. In some cases, drug loading efficiency or capacity is surprisingly improved by more than 50%. In some cases, an increase of 100% in drug loading has been measured. In many cases, the extent of drug elution is unaffected, as compared  
5 to the non-radiopaque version of the beads, in some cases with substantially all of the drug eluted from the bead over a sustained period. In many cases the drug elution profile is improved in that the time over which drug is eluted from radiopaque microspheres is increased as compared to equivalent non-radiopaque microspheres. The microspheres of the invention thus, surprisingly provide increased drug loading  
10 efficiency and improved i.e. prolonged drug-elution over their non-radiopaque equivalents.

The polymers or microspheres of any of the above aspects and embodiments of the invention may be used in another aspect of the invention in which a method of imaging an embolization procedure is provided. In a further aspect a method of  
15 monitoring embolization after the completion of a procedure is provided. Depending on the permanent or rate of biodegradation of the radiopaque polymers of the invention, the post-procedural window in which the embolization may be monitored can be in the range of days, weeks or even months.

The invention will now be described further by way of the following non  
20 limiting examples with reference to the figures. These are provided for the purpose of illustration only and other examples falling within the scope of the claims will occur to those skilled in the art in the light of these. All literature references cited herein are incorporated by reference.

## 25 Figures

*Figure 1* is micrograph of radiopaque hydrogel beads prepared according to the examples. The beads shown are 75-300 $\mu\text{m}$ , sieved after iodination, under different lighting conditions.

*Figure 2* is microCT image of radiopaque beads prepared according to the  
30 invention. Figure 2A is a 3D radiograph of radiopaque beads. Figure 2B shows a 2D microCT image. The line profile (Figure 2C) shows: the x-axis ( $\mu\text{m}$ ) is the length of the line drawn (shown in red across a section of the radiograph); and the y-axis

indicates the level of intensity, using grey scale values, ranging from 0 (black) to 255 (white).

*Figure 3* shows light micrographs of sterilized radiopaque beads prepared according to the invention, before and after loading with doxorubicin. Figure 3A shows the radiopaque beads prior to loading and Figure 3B shows the drug-loaded beads.

*Figure 4* shows the elution profile of RO and non RO beads loaded with doxorubicin. The beads were 70-150um in diameter. RO beads were 158mg I/ml wet beads. Both bead types were loaded with 50mg doxorubicin per ml wet beads.

10 *Figure 5* shows the elution profile of RO beads loaded with sunitinib.

*Figure 6* shows the elution profile of RO and non RO beads loaded with sorafenib. RO beads were of size 70-150um and had an iodine content 134mg I/ml wet beads.

15 *Figure 7* shows the elution profile of RO and non RO beads loaded with vandetanib. The beads were 70-150um in diameter. RO beads were 158mg I/ml wet beads.

*Figure 8* shows the elution profile of RO and non RO beads loaded with miriplatin. Beads were of size 70-150um and RO Beads had an iodine content 134mg I/ml wet beads.


20 *Figure 9* shows the elution profile of RO and non RO beads loaded with topotecan. RO and Non RO beads had a size of 70-150 um and RO beads had an iodine level of 146mg I/ml wet beads.

*Figure 10* shows sample cross section micro CT images of 10 RO beads prepared according to the invention alongside water and air blanks.

25 *Figure 11* shows CT scans taken from a single swine following embolisation using the RO beads of the invention.

(a) Pre embolisation; (b) 1hr post embolisation; (c) 7days post embolisation; (d) 14 days post embolisation. Arrows indicate RO beads in the vessels.

30 Throughout these examples the structure of polymer comprising 1,2-diol or 1,3-diol groups is represented by the following structure :



### Examples

#### 5 Example 1: Preparation of 2,3,5-triiodobenzaldehyde from 2,3,5-triiodobenzyl alcohol




10 In a 50ml three-necked round-bottomed flask fitted with a thermometer, a nitrogen bubbler and an air-tight seal, 10.2g of the alcohol was dissolved in 100ml of anhydrous DMSO under a nitrogen blanket and stirring conditions. Then, 1.0 molar equivalent of propane phosphonic acid anhydride, (T3P), (50% solution in ethyl acetate) was added drop by drop over 5 minutes at 22°C to 25°C. The reaction

15 solution was stirred at room temperature and monitored by high performance liquid chromatography (Column : Phenominex Lunar 3um C<sub>18</sub> : Mobile Gradient: Phase A water 0.05% TFA, Phase B ACN 0.05% TFA, linear gradient A to B over 10 mins: Column temp. 40°C: flow rate 1ml per min: UV detection at 240nm). The conversion finished after 240 minutes. The yellow solution was poured into 100ml of deionised

20 water while stirring, yielding a white precipitate which was filtered, washed with the mother liquors and 50ml of deionised water. The cake was slurried in 50ml of ethyl acetate, filtered and washed with 50ml of water again, dried sub vacuo at 40°C for 20 hours to yield 7.7g of a white solid. The structure and purity were confirmed by NMR analysis and high performance liquid chromatography.

25

#### Example 2: Preparation of 2-(2,3,5-triiodophenoxy)acetaldehyde



**a) Synthesis of 2-(2,4,6-triiodophenoxy)ethanol from 2,4,6-triiodophenol**

In a 500ml three-necked flat-bottomed flask fitted with a thermometer, a nitrogen bubbler and an overhead stirrer, 10g of phenol were dissolved in 100ml of ethanol, under a nitrogen blanket and vigorous stirring conditions at room temperature. 1.25 molar equivalent of sodium hydroxide pellets were added and the slurry was stirred under a nitrogen blanket for 30 minutes until complete dissolution of the pellets. Then, 1.1 molar equivalents of 2-iodoethanol were added, maintaining the temperature at 25°C and stirring for 15 minutes. The solution was heated to reflux of ethanol. The consumption of the phenol and formation of 2-(2,4,6-triiodophenoxy)ethanol were monitored by HPLC (conditions as per Example 1). After 25 hours, an additional 0.27 molar equivalents of 2-iodoethanol was added and the solution was stirred for a further 2 hours at reflux. After cooling the solution to room temperature, 150ml of deionised water were added quickly under vigorous stirring conditions. The resulting slurry was filtered under vacuum, washed with the mother liquors, three times 30ml of deionised water and finally with 5ml of ethanol. The resulting pink cake was taken up into 100ml of ethyl acetate and the organic layer extracted with copious amounts of a sodium hydroxide solution (pH14), dried over magnesium sulphate and concentrated on a rotary evaporator to yield 5.9g of an off-pink solid, which was identified as 2-(2,4,6-triiodophenoxy)ethanol by comparative analysis with a commercial analytical standard from sigma-aldrich.


**(b) Oxidation of 2-(2,4,6-triiodophenoxy)ethanol to 2-(2,3,5-triiodophenoxy)acetaldehyde:**

In a 500ml three-necked flat-bottomed flask fitted with a thermometer, a nitrogen bubbler and an overhead agitator, 5.9g of the alcohol was dissolved into 150ml of anhydrous DMSO under a nitrogen blanket. The solution was stirred and heated to 40°C, and 1.6 molar equivalents of T3P (50%w/w solution in EtOAc) were

added slowly while maintaining the temperature at 40°C to 41°C. The consumption of alcohol and production of aldehyde was monitored by high performance liquid chromatography over time (conditions as per Example 1). After 24 hours, 150ml of water were added slowly to the reaction mixture over 2 hours using a syringe pump.

5 An off-pink solid precipitated out of the solution and was filtered under vacuum to yield a pink cake which was washed with water. The resulting impure flocculate was taken up in ethyl acetate and hexane, then concentrated under vacuum at 40°C to yield an oil identified as 2-(2,3,5-triiodophenoxy)acetaldehyde by <sup>1</sup>H NMR analysis.

10 **Example 3: Preparation of 1-(2,2-dimethoxyethoxymethyl)-2,3,5-triiodo-benzene from 2,3,5-triiodobenzyl alcohol and 2-bromo-1,1-dimethoxy-ethane (Example of a radiopaque acetal/protected aldehyde)**



15 In a 50 ml three-necked flat-bottomed flask fitted with an overhead agitator, a thermometer, a nitrogen bubbler and a gas tight septum, 5.07g of the alcohol were dissolved in 55ml of anhydrous 2-methyltetrahydrofuran under a nitrogen blanket and stirring conditions. Then, 2.11g of the acetal followed by 0.540g of sodium hydride (60% dispersion in mineral oil) were added. The slurry was heated to reflux under a nitrogen blanket for 1010 minutes and monitored by high performance liquid chromatography (conditions as per Example 1). The reaction mixture was taken up into 50ml of dichloromethane and washed four times with 25ml of water. The organic layer was concentrated sub vacuo to yield a brown oil, which was identified as 1-(2,2-dimethoxyethoxymethyl)-2,3,5-triiodo-benzene by <sup>1</sup>H NMR.

25

**Example 4: Preparation of cross-linked hydrogel microspheres.**


Cross-linked hydrogel microspheres were prepared according to Example 1 of WO 2004/071495. The process was terminated after the step in which the product was vacuum dried to remove residual solvents. Both High AMPS and low AMPS

forms of the polymer were prepared and beads were sieved to provide appropriate size ranges. Beads were either stored dry or in physiological saline and autoclaved. Both High AMPS and low AMPS forms of the polymer can be used with good radiopacity results

5

**Example 5: General preparation of radiopaque microspheres from 2,3,5-triiodobenzaldehyde and preformed cross-linked PVA hydrogel microspheres**

10



In a 50ml three-necked round-bottomed flask fitted with an overhead agitator, a thermometer and a nitrogen bubbler, 1.0g of dry PVA-based beads (see Example 4 – High AMPS version) were swollen in an appropriate solvent (e.g. DMSO) under a nitrogen blanket and stirring conditions. Then, 0.20 to 1.5 molar equivalents of aldehyde (prepared according to example 1) were added to the slurry, immediately followed by 1.0 to 10 molar equivalents of acid (e.g. sulphuric acid, hydrochloric acid, methanesulfonic acid or trifluoroacetic acid - methanesulfonic acid is typically used). The theoretical level of available –OH groups was estimated based on the characteristics of the PVA used and the degree of cross linking (typical values for high AMPS beads = 0.0125mol/gm dry beads). The reaction slurry was stirred at 50°C to 130°C for between 12 hours and 48 hours, while the consumption of aldehyde was monitored by high performance liquid chromatography (HPLC). When required, a desiccant such as magnesium sulphate or sodium sulphate was added to drive the reaction further. In this way batches of radiopaque microspheres having differing levels of iodine incorporation could be obtained. When enough aldehyde had reacted on the 1,3-diol of the PVA-based hydrogel to render it sufficiently radiopaque (see below), the reaction slurry was cooled to room temperature and filtered. The cake of beads was washed with copious amount of DMSO and water,

30

until free from any unreacted aldehyde, as determined by high performance liquid chromatography.

5

**Example 6: Preparation of radiopaque microspheres from 2,3,5-triiodo benzaldehyde and a cross-linked PVA hydrogel microsphere**


5.0g of dry PVA-based beads (see Example 4 – High AMPS version 105 - 150um) and 0.26 equivalents of aldehyde (7.27g) (prepared according to Example 1) placed in a 500ml vessel purged with nitrogen. 175 ml anhydrous DMSO were added under a nitrogen blanket and stirred to keep the beads in suspension. The suspension was warmed to 50C and 11ml of methane sulphonic acid was added slowly. The reaction slurry was stirred at 50°C for between 27 hours, while the consumption of aldehyde was monitored by HPLC. The reaction slurry was then washed with copious amount of DMSO/1%NaCl followed by saline. The resultant beads had an iodine concentration of 141mg I/ml wet beads and had a radiopacity of 4908HU.

**Example 7: Preparation of Radiopaque PVA hydrogel beads with 2-(2,4,6-triiodophenoxy)acetaldehyde.**

20 2-(2,4,6-triiodophenoxy)acetaldehyde was prepared according to Example 2 and reacted with PVA-based hydrogel beads (see Example 4 high AMPS version) following the same method as Example 5 but with the temperature of the reaction maintained between 20°C and 50°C. The reaction time was also reduced to less than one hour. Iodine content was determined to be 18mg I/ml wet beads.

25

**Example 8: Preparation of radiopaque PVA hydrogel microspheres with 1-(2,2-dimethoxyethoxymethyl)-2,3,5-triiodo-benzene**



In a 50 ml three-necked flat-bottomed flask fitted with an overhead agitator, a thermometer and a nitrogen bubbler, 1.0g of dry PVA-based beads (see Example 4 high AMPS version) were swollen in an appropriate solvent (e.g. DMSO) under a nitrogen blanket and stirring conditions. Then, 0.5 molar equivalents of aldehyde (1-(2,2-dimethoxyethoxymethyl)-2,3,5-triiodo-benzene, prepared according to Example 3) were added to the slurry, immediately followed by 163µl of methanesulfonic acid. The reaction slurry was stirred at 40°C for 80 minutes, and then heated to 80°C for 200 minutes, while the consumption of aldehyde was monitored by high performance liquid chromatography. As enough aldehyde had reacted on the 1,3-diol of the PVA-based hydrogel to render it sufficiently radiopaque after this time, the reaction slurry was cooled to room temperature and filtered. The cake of beads was washed with copious amounts of DMSO and water, until free from any unreacted acetal and aldehyde, as determined by high performance liquid chromatography. Iodine content of the beads was determined to be 31mg/ml wet beads.

**Example 9: Preparation of Radiopaque PVA hydrogel microspheres from 2,3,4,6 tetraiodobenzaldehyde**

2,3,4,6-tetraiodobenzyl alcohol (ACES Pharma; USA) was converted to 2,3,4,6 tetraiodobenzaldehyde using T3P and DMSO as described in Example 1. 0.6 molar equivalents of 2,3,4,6 tetraiodobenzaldehyde (8.8g) was then added to 2.05g of PVA hydrogel microspheres (see Example 4 - size 150-250µm high AMPS version) with DMSO under a nitrogen blanket. The reaction mix was heated to 50°C and stirred for several hours. The reaction was monitored with HPLC and when complete, the beads were filtered and washed with DMSO, water and then 0.9% saline. The radiopaque beads were then stored in a solution of 0.9% saline for analysis. Iodine content was determined to be 30mg/ml wet beads.

**Example 10: Characterization of Radiopaque Beads**

A light micrograph of the beads, typical of those produced by Examples (5 and 6) is shown in Figure 1. The dry weight of beads was measured by removing the packing saline and wicking away remaining saline with a tissue. the beads were then vacuum

dried under 50°C overnight to remove water, and the dry bead weight and solid content (w/w %) of polymer were obtained from this.

The iodine content (w/w %) in dry, beads were measured by elemental analysis according to the Schöniger Flask method. For iodine content in wet beads, the calculation is :

$$\text{Bead solid content (\%)} \times \text{iodine content in dry beads (\%)}$$

10 The solid content of radiopaque hydrogel beads, prepared according to Example 5 in a 0.9% saline was measured to be between 5% and 16%, w/w, while the weight/weight dry iodine content was measured to be between 5% and 56%, depending on the chemistry and the reaction conditions used.

An alternative way to express the iodine content is mg I/mL wet beads (wet packed bead volume), which is the same as the unit used for contrast media. Using 15 protocols according to Example 5, iodine content in the range 26 mg I/ml beads to 214 mg I/ml beads was achieved.

Using similar protocols, but microspheres based on a low AMPS polymer (Example 4), higher iodine contents (up to 250 mg I/ml beads) could be achieved.

20

#### **Example 11 – MicroCT analysis of radiopaque beads**

Micro-CT was used to evaluate the radiopacity of samples of radiopaque embolic Beads prepared according to Example 5 above

The samples were prepared in Nunc cryotube vials (Sigma-Aldrich product code V7634, 48 mm × 12.5 mm). The beads were suspended in 0.5% agarose gel (prepared with Sigma-Aldrich product code A9539). The resulting suspension is generally referred to as a “Bead Phantom”. To prepare these bead phantoms, a solution of agarose (1%) is first raised to a temperature of approximately 50°C. A known concentration of the beads is then added, and the two gently mixed together until the solution starts to solidify or gel. As the solution cools it gels and the beads remain evenly dispersed and suspended within the agarose gel.

Bead phantoms were tested for radiopacity using micro-Computer Tomography (μCT) using a Bruker Skyscan 1172 μCT scanner at the RSSL

Laboratories, Reading, Berkshire, UK, fitted with a tungsten anode. Each phantom was analysed using the same instrument configuration with a tungsten anode operating at a voltage of 64kv and a current of 155  $\mu$ A. An aluminium filter (500 $\mu$ m) was used.

5

***Acquisition parameters:***

Software: SkyScan1172 Version 1.5 (build 14)

NRecon version 1.6.9.6

10 CT Analyser version 1.13.1.1

Source Type: 10Mp Hamamatsu 100/250

Camera Resolution (pixel): 4000 x 2096

Camera Binning: 1 x 1

Source Voltage kV: 65

15 Source Current  $\mu$ A: 153

Image Pixel Size ( $\mu$ m): 3.96

Filter: Al 0.5 mm

Rotation Step (deg): 0.280

Output Format: 8bit BMP

20 Dynamic Range: 0.000 – 0.140

Smoothing: 0

Beam Hardening: 0

Post Alignment: corrected

Ring Artefacts: 16

25

A small amount of purified MilliQ water was carefully decanted into each sample tube. Each sample was then analysed by X-Ray micro-computer tomography using a single scan, to include the water reference and the beads. The samples were then reconstructed using NRecon and calibrated against a volume of interest (VOI) of the purified water reference. A region of interest (ROI) of air and water was analysed after calibration to verify the Hounsfield calibration.

30

Radiopacity was reported in both greyscale units and Hounsfield units from line scan projections across the bead. Values used for dynamic range for all samples

in NRecon (thresholding): -0.005, 0.13 (minimum and maximum attenuation coefficient). A typical image and line scan is shown in Figure 2.

Table 1 gives the radiopacity of microspheres prepared according to Example 4 under varying conditions of time and equivalents of aldehyde, in both greyscale and Hounsfield units. Radiopacity data are the mean of ten line scans of beads of approximately 150 microns.

**Table 1**

Iodine (mg I/ml)	Grey scale	HU	Mean bead size (um)
158	79	5639	158
147	69	4626	146
141	74	4799	131
130	56	3600	153

Figure 10 shows a sample of cross section images of 10 beads with an average size of 153 um, and average radiopacity of 4908HU.

#### **Example 12 Drug Loading of Radiopaque beads:**

##### **Example 12 (a) Doxorubicin**

1 mL of RO bead slurry prepared according to Example 5 (size 100-300um, iodine 47mg I/ml wet beads) was measured by using a measuring cylinder, and the liquid removed. 4 mL of doxorubicin solution (25 mg/mL) was mixed with the radiopaque beads with constant shaking at ambient temperature. After 20 hr loading, the depleted solution was removed, and the drug-loaded beads were rinsed with deionised water (10 mL) 4-5 times. By measuring the doxorubicin concentration of combined depleted loading solution and rinsing solutions at 483 nm on a Varian UV spectrophotometer, the doxorubicin loaded was calculated as 80 mg/mL beads. The doxorubicin hydrochloride drug loading capacity of the radiopaque beads was determined to be a non-linear function of the iodine content in the beads.

In a separate experiment 1.5 ml of RO beads of 70-150um having an iodine content of 158mg/ml wet beads were loaded as above using 3ml of doxorubicin solution (25mg/ml). Control, non RO beads of the same size, were also loaded in the same manner. The RO beads loaded 50mgs/ml of doxorubicin whilst the control  
5 beads loaded 37.5 mgs/ml.

In a separate experiment, loading of RO beads (size 70-150um; iodine content 150mg l/ml), was essentially complete after 3hrs.

Radiopaque beads prepared according to Example 5 above were loaded with 37.5mg/ml of Doxorubicin solution as per the above method. Figure 3A shows the  
10 radiopaque beads prior to loading and Figure 3B shows the drug-loaded beads. Prior to drug loading the beads were observed as spherical microspheres with a pale to dark brown tinge. When the doxorubicin was loaded into the beads they turned a strong red colour. In this example, the beads were autoclaved to demonstrate to stability of the beads during sterilization. Bead integrity was preserved during autoclaving; the  
15 mean bead size during autoclaving reduced from 177µm to 130µm. Further shifts in the bead size distribution were observed when beads were loaded with Doxorubicin, which is consistent with drug-loading observed with non-radiopaque beads. In a further example, the mean bead size reduced on drug loading at 51mg/ml, from 130µm to 102µm. The resulting beads remain within the range that is clinically  
20 useful, even after modification, sterilization, and drug-loading.

#### **Example 12(b) Epirubicin**

Epirubicin was loaded into RO beads (made according to Example 5) and non RO beads (size, 70-150um high AMPS made according to Example 4) in the same manner as for doxorubicin. 1ml of beads was loaded using a 1.5ml loading solution  
25 (25mg/ml epirubicin). The final loading in the radiopaque beads was 37.49mg (99.97% loading efficiency) and for the non RO beads 36.43 (97.43% loading efficiency) after 90mins.

#### **Example 12(c) Sunitinib**

Sunitinib DMSO solution was prepared by dissolving 400 mg of sunitinib  
30 powder in anhydrous DMSO in a 10 mL volumetric flask. 1 ml of RO bead slurry (70-150um, 134.4 mg l/ml wet beads prepared according to Example 5). was prewashed with 10 ml of DMSO three times to remove water residue. 2.5 mL of the

sunitinib-DMSO solution (40 mg/mL) was mixed with the RO bead slurry and allowed to mix for 1-2 hr. Subsequently, after removing the loading solution, 10 mL of saline was added to the bead slurry to allow sunitinib to precipitate inside the beads. The wash solution and drug particles were filtered through a cell strainer, and the washing was repeated three to four times. Non RO beads (100-300um, prepared according to Example 4) were treated in the same manner.

#### **Example 12(d) Sorafenib**

1 ml of RO PVA microspheres (size 70 to 150 um, iodine content 134 mg iodine/ml beads, prepared according to Example 5) or non RO PVA microspheres (DC Bead™ 100-300, Biocompatibles; UK) were prewashed with 10 ml of DMSO three times to remove water residue. Sorafenib/DMSO solution (39.8 mg/mL in anhydrous DMSO) was mixed with 1 mL of bead slurry for 1 hr, (2.5 mL for the radiopaque bead and 2 mL for the non radiopaque bead). After removing the loading solution, 20 mL of saline was added to the bead slurry. The bead suspension was filtered through a cell strainer, and the wash was repeated three or four times. The final loading level was determined by DMSO extraction of small fraction of hydrated beads and determination of drug concentration by HPLC (Column: Kinetex 2.6u XB-C18 100A 75x4.60 mm; mobile phase water:acetonitrile: methanol:trifluoroacetic acid 290:340:370:2 (v/v); detection 254 nm; column temperature 40°C; flow rate: 1 mL/min).

49.9 mg of sorafenib was loaded into 1ml RO beads and 34.7 mg was loaded into 1ml of non-RO (DC Bead™) beads.

#### **Example 12(e) Vandetanib.**

A solution of 20mg/ml vandetanib was prepared by dissolving 500mg of vandetanib in 14ml of 0.1M HCl in a 25ml amber volumetric flask with sonication, and making up to 25ml with deionised water. Vandetanib was then loaded into both RO PVA hydrogel microspheres (prepared according to Example 5: Size 70 to 150um; Iodine content 147mg/ml beads) and non-RO microspheres (DC Bead 100-300; Biocompatibles UK Ltd) according to the following protocol:

One millilitre of microspheres including packing solution was aliquoted by measuring cylinder and transferred into a 10 mL vial. The packing solution was then removed using a pipette. Three millilitres of the 20mg/ml drug solution was then

added to the non RO bead or 1.5 mL of the solution to RO beads. In the radiopaque bead loading experiment the pH of the solution was between 4.6 and 4.8; in the DC bead loading experiment the pH was at approximately 4.2. After 2 hr. loading, the residual solution was removed, and the beads were washed with 5mL of deionised water 3 times. The depleted loading and washing solutions were combined and analysed by C<sub>18</sub> reverse phase HPLC with detection at 254nm to determine the loading yield. For sterilisation if, needed, the loaded beads, in 1 ml of deionised water, were either autoclaved at 121 °C for 30 min, or lyophilised for 24 hr and then gamma sterilised at 25 kGy.

- 10 Radiopaque beads loaded vandetanib to a level of 29.98mg/ml of wet beads.  
Non radiopaque beads loaded vandetanib to a level of 26.4 mg/ml.

#### Example 12(f) Miriplatin

Hydrated RO microspheres (size 70-150 um, iodine content 134mg iodine/ml beads, prepared according to Example 5) and non RO PVA microspheres (DC Bead 15 100-300, Biocompatibles; UK), 1 mL each vial, were washed with 5 mL of 1-methyl-2-pyrrolidinone four times. The solvent was then removed. 0.147 g of miriplatin was mixed with 25 mL of 1-methyl-2-pyrrolidinone, and the suspension was heated to 75°C in a water bath to dissolve miriplatin. 2 mL of the drug solution was added into the washed beads and the mixture placed in a 75°C water bath for 1 hr. The bead 20 suspensions were filtered through a cell strainer to remove the loading solution, followed by washing with about 100 mL of saline.

A known volume of beads was washed with deionised water and freeze dried. Total platinum was determined by elemental analysis using ICP-OES (Inductively Coupled Plasma - Optical Emission Spectroscopy) and converted to miriplatin level.

- 25 The experiment was repeated loading lyophilised beads in the same manner. Table 2 shows the results of loading miriplatin into wet and lyophilised RO beads.

**Table 2: Miriplatin loading data.**

Bead sample	Miriplatin content (%)	Miriplatin in wet beads (µg)
Non RO bead (wet loaded )	0.39	2058

RO Bead (wet loaded)	0.31	2645
RO bead (dry loaded)	0.12	1160

### Example 12(g) Irinotecan

A 2mL bead sample of Non RO beads (100-300 um – made according to Example 4 high AMPS version) and RO Bead (100-300 um, 163 mg I/mL made according to Example 5) were mixed with 10ml irinotecan solution in water (10 mg/mL). Loading was measured by determining the irinotecan level in depleted loading solution by UV spectroscopy, at 384 nm. Both non RO and RO beads loaded approximately 100% of the drug within 90min.

### Example 12(h) Topotecan

10 A 1mL bead sample of Non RO beads (70-150 um – made according to Example 4 high AMPS version) and RO Bead (70-150 um, 146 mg I/mL made according to Example 5) were mixed with topotecan solution in water (15.08 mg/mL) to load dose of 40mg (2.5ml) or 80mg (5ml) under agitation. After about 1.5 hr, the loading of topotecan was measured by determining the topotecan level in depleted loading solution as described above, by UV spectroscopy, at 384 nm. Table 3 shows maximum of 80mg topotecan was loaded in RO bead sample. Both non RO and RO beads loaded >98% of 40mg topotecan.

*Table 3. Topotecan loading in RO and non RO beads*

20

	Time (hrs)	Drug loaded (mg)	% Drug Loaded
RO bead, 1mL	1.5	40	100
RO bead, 1mL	1.5	80	100
Non RO bead, 1mL	1.5	39	98

### Example 13 Drug elution from radiopaque beads

#### Example 13(a) Doxorubicin.

25 Doxorubicin-loaded beads prepared in the according to Example 13(a) (70-150um, 158mg I/ml, 50mg/ml doxorubicin) were added to 1000ml of PBS, in a brown jar at room temperature. The bead suspension was stirred with a magnetic

stirrer at low speed. At sampling time points, 1mL of elution media were removed through a 5 um filter needle and analysed by UV at 483nm against a standard. The elution profiles were shown in Figure 4.

#### **Example 13(b) Sunitinib**

5 Sunitinib-loaded beads prepared according to Example 13(c) were added to 400ml of PBS, 0.5g/L Tween 80 in a brown jar at 37°C in a water bath. The bead suspension was stirred with a magnetic stirrer at low speed. At sampling time points of 1, 2, 3 and 4 hours, 10 mL of elution media were removed through a 5 um filter needle for HPLC analysis (conditions as per Example 13(c)) and 10 mL of fresh PBS  
10 solution was added to make up the volume. At sampling time-points of 5, 25, 48 and 73 hours, 100 mL of elution media were replaced with equal volume of fresh PBS solution. The sample was analysed by HPLC. The elution profile is illustrated in were shown in Figure 6.

#### **Example 13(c) Sorafenib**

15 Sorafenib-loaded beads prepared according to Example 13(d) were added to 400 mL of PBS with 0.5 g/L Tween 80 in a brown jar in a 37°C water bath. The bead suspension was stirred with a magnetic stirrer at low speed. At sampling time points of 1, 2, 4, and 6 hours, 10 mL of elution media were removed through a 5 um filter needle for HPLC analysis and 10 mL of fresh PBS solution was added to make up  
20 400 mL volume. At sampling time-points 8, 24.5 and 31 hrs, 100 mL of elution media were replaced with equal volume of fresh PBS solution. Two replicates were run for each type of beads. The elution profiles of sorafenib from RO beads and non RO beads are shown in Figure 6.

#### **Example 13 (d) Vandetinib.**

25 Vandetinib loaded RO and non RO beads prepared according to Example 13(e) (2ml beads at 30mg vandetinib/ml beads, beads 70-150 um and RO beads having 141 mg l/ml wet beads) were placed in Amber jars containing 500mL of PBS with magnetic flea, at ambient temperature. At each sampling time-point, the complete PBS elution medium was removed from the jar through a cannula filter by a  
30 peristaltic pump, and replaced with the same volume of fresh PBS. 5ul of the elution

medium was analysed by C<sub>18</sub> reverse phase HPLC with detection at 254nm. The elution profile is illustrated in Figure 7

#### **Example 13(e) Miriplatin**

Miriplatin-loaded beads made according to Example 13(f) were added to 50  
5 mL of PBS with 1% of Tween 80 in 100 mL Duran® bottles. The bottles were  
suspended in a 37°C water bath and rotated at 75 rpm to agitate the beads. At  
sampling time points of 1, 5, 11, 15 and 22 days, 20 mL of elution medium was  
removed for ICP analysis and 20 mL of fresh PBS/Tween solution was added to make  
up 50 mL volume. The elution profiles of miriplatin from RO beads and non RO  
10 beads are shown in Figure 8.

#### **Example 13(f) Irinotecan**

A sample of beads prepared in example 13(g) 163m I/ml were added to 500ml  
of PBS, in a brown jar at 37°C and stirred with a magnetic stirrer at low speed. At  
sampling time points, 1ml of elution media were removed through a 5 µm filter  
15 needle and analysed by UV at 369nm against a standard. The elution profiles were  
shown in Figure 9.

#### **Example 14 Radiopacity of Drug-Loaded Radiopaque Beads**

An aliquot of the doxorubicin loaded beads prepared according to Example 13  
20 were subjected to microCT analysis in the same way as described in example 12. The  
drug-loaded beads were found to be radiopaque. The average Bead Radio-opacity  
(Grey Scale) was determined to be 139 (n=3).

#### **Example 15 - Freeze drying protocol.**

25 Microspheres of the invention, whether drug loaded or non-drug loaded, may  
be freeze dried according to the protocol described in WO07/147902 (page 15) using  
an Epsilon 1-6D freeze dryer (Martin Christ Gefriertrocknungsanlagen GmbH,  
Osterode am Harz, Germany) with Lyo Screen Control (LSC) panel and Pfeiffer  
DUO 10 Rotary Vane Vacuum pump and controlled by Lyolog LL-1 documentation  
30 software, as briefly described below.

The microspheres are lyophilised by freezing at about -30°C without a  
vacuum, for at least 1 h, then reducing the pressure gradually over a period of about

half an hour to a pressure of in the range 0.35-0.40 mbar, while allowing the temperature to rise to about 20°C. The temperature and pressure conditions are held overnight, followed by raising the temperature to room temperature for a period of about 1-2 hours at the same time pressure, followed by a period at room temperature with the pressure reduced to about 0.05 mbar, to a total cycle time of 24 hours.

If preparations are required to be maintained under reduced pressure, at the end of the cycle and substantially without allowing ingress of air the vials are stoppered under vacuum by turning the vial closing mechanism that lowers the shelves to stopper the vials on the shelf beneath. The chamber is then aerated to allow the chamber to reach atmospheric pressure. The shelves are then returned to their original position and the chamber opened. If the samples are not maintained under reduced pressure, then the pressure is gradually returned to atmospheric before stoppering.

**Example 16: *In vivo* embolisation study**

Male domestic Yorkshire crossbred swine (approximately 14 weeks old) were used in the study.

After induction of anesthesia, a sheath was placed in the femoral artery and, under fluoroscopic guidance, a guide wire was passed through the introducer and moved through to the aorta. A guide catheter, passed over the guide wire, was then placed at the entrance to the coeliac artery. The guide wire was removed, and contrast medium used to visualize the branches of the coeliac artery.

A micro-wire/micro-catheter combination was passed through the guide catheter and used to select the common hepatic artery, isolating 25 to 50% of the liver volume. A micro-catheter was passed over the guide wire into the liver lobe, the guide wire was removed and contrast medium used to capture an angiogram of the lobe. Digital subtraction angiography was performed to confirm the catheter position.

2mls of RO beads, prepared according to Example 5 (size 75 – 150um, iodine content 141 mg I/ml) was transferred to a 20 to 30 mL syringe and the packing solution discarded. A smaller syringe holding 5 mL of non-ionic contrast medium (Visipaque® 320) was connected to the larger syringe via a three-way stopcock and the beads mixed with the contrast by passage through the stopcock. The total volume was adjusted to 20 mL by addition of contrast. This suspension was administered

slowly under fluoroscopic guidance, until near stasis was achieved. The volume of suspension delivered to achieve stasis was between 2 and 6 mls.

Abdominal CT images were taken pre-dose, 1 and 24 hours post dose, and on Days 7 and 14. On Day 14, a baseline CT image was taken and 75 cc of contrast material was injected. Post-contrast material injection, a second CT image was taken. The images were analyzed for the extent of visibility of beads in the liver.

The RO beads were visible on X-ray during the procedure and on CT. This was best shown on the 7 and 14 day CT scans, obtained without IV contrast (see figure 11). The beads were easily visible in multiple branches of the hepatic arteries. The beads were more attenuating than, and can be differentiated from, IV contrast.

## CLAIMS

1. A hydrogel comprising 1,2-diol or 1,3-diol groups acetalised with a radiopaque species the radiopaque species comprising one or more covalently bound radiopaque halogens.
2. A hydrogel according to claim 1 comprising 1,2-diol or 1,3-diol groups acetalised with a radiopaque species such that that the polymer comprises an iodinated aromatic group covalently bound to the polymer through cyclic acetal linkage.
3. A hydrogel according to either of claims 1 or 2 wherein the hydrogel is a cross-linked polymer network.
4. A hydrogel according to any of claims 1 to 3 wherein the hydrogel comprises polyvinyl alcohol (PVA) in which the PVA comprises pendent acetate groups formed from the acetalisation of PVA with N-acryloyl-aminoacetaldehyde dimethylacetal and which is cross-linked with 2-acrylamido-2-methylpropanesulfonic acid (PVA –AMPS).
5. A hydrogel according to claim 1 wherein the radiopaque species is acetalised in the hydrogel in the form of a cyclic acetal.
6. A hydrogel according to any of claims 1 to 5 wherein the radiopaque species is selected from iodine and bromine.
7. A hydrogel according to claim 6 wherein the radiopaque species comprises an iodinated or brominated phenyl group.
8. A hydrogel according to either of claims 6 or 7 wherein the hydrogel comprises greater than 10% iodine by dry weight.

9. A hydrogel according to any preceding claim wherein the hydrogel is in the form of microparticles or microspheres.


10. A hydrogel according to claim 9 wherein the hydrogel is in the form of 5 microspheres with a mean diameter size range of from 10 to 2000 $\mu$ m.

11. A hydrogel according to any preceding claim in the form of microspheres or microparticles having a mean radiopacity of 500HU or greater.


10 12. A hydrogel according to any preceding claim wherein the hydrogel has a net charge at physiological pH

13. A hydrogel according to any of claims 1 to 12 comprising a structure of the general formula I or II

15




I



II

wherein X is a group substituted by one or more halogens and preferably one or more 20 iodine moieties and J is a group of the formula  $-CH_2-$  or is a bond.

14. A hydrogel according to claim 13 wherein X is a group of the formula



III

5

wherein Z is a linking group, or is absent, such that the phenyl group is bonded to the cyclic acetal;

if Z is present, then Z is C<sub>1-6</sub> alkylene, C<sub>1-6</sub> alkoxylyene or C<sub>1-6</sub> alkoxyalkylene ;

Hal is 1,2,3 or 4 covalently attached radiopaque halogens

10

15. A composition comprising a hydrogel according to any preceding claim and a therapeutic agent wherein the therapeutic agent is absorbed into the hydrogel matrix.

16. A composition according to claim 15 wherein the therapeutic agent is electrostatically held in the hydrogel and elutes from the hydrogel in electrolytic media.

17. A method of making a radiopaque polymer comprising reacting a polymer comprising 1,2- diol or 1,3-diol groups with a radiopaque species capable of forming a cyclic acetal with said 1,2-diol or 1,3 diols under acidic conditions.

20

18. A method according to claim 17 wherein the polymer is cross-linked.

19. A method according to claim 17 or 18 wherein the polymer comprises polyvinyl alcohol (PVA) or copolymers of PVA.

25



20. A method according to any of claims 17 to 19 wherein the radiopaque species is an organic molecule or organometallic complex, which provides a radiopacity >1 HU, and which comprises a reactive moiety selected from the group consisting of aldehydes, acetals, hemiacetals thioacetals and dithioacetals.


30

21. A method according to any of claim 17 to 20 in which the radiopaque species comprises iodine or bromine
- 5 22. A method according to claim 21 wherein the radiopaque species is an iodinated aldehyde.
23. A method according to claim 22 wherein the radiopaque species is an iodinated benzyl aldehyde, iodinated phenyl aldehyde or an iodinated  
10 phenoxyaldehyde
24. A method of making a radiopaque hydrogel microsphere comprising the steps of:
- (a) swelling a pre-formed hydrogel microsphere comprising a polymer with  
15 1,2-diol or 1,3-diol groups in a solvent capable of swelling said microsphere; and
- (b) mixing the swollen beads with a solution of a radiopaque species capable of forming a cyclic acetal with said 1,2 or 1,3-diols under acidic conditions; and
- (c) extracting the microspheres.
- 20 25. A method according to claim 24 which further comprises the step of drying the extracted microspheres.
26. A method according to either of claims 24 or 25 in which the reaction is conducted in polar organic solvent and at elevated temperature.
- 25 27. A method according to any of claims 24 to 26 in which the radiopaque species comprises a functional group selected from the group consisting of aldehydes, acetals, hemiacetals, thioacetals and dithioacetals.
- 30 28. A method according to any of claims 24 to 27 in which the radiopaque species comprises iodine.

29. A method according to claim 28 wherein the radiopaque species is an iodinated aldehyde.
30. A method according to claim 28 wherein the radiopaque species is an iodinated benzyl aldehyde, an iodinated phenyl aldehyde or an iodinated phenoxyaldehyde
- 31 A method according to claim 30 wherein the radiopaque species is 2,3,5-triiodobenzaldehyde, 2,3,4,6-tetraiodobenzaldehyde or 2-(2,4,6-triiodophenoxy)acetaldehyde
32. A method according to any of claims 24 to 31 in which the preformed hydrogel microsphere comprises PVA with pendent acetate groups formed from the acetalisation of PVA with N-acryloyl-aminoacetaldehyde dimethylacetal and which is cross-linked with 2-acrylamido-2-methylpropanesulfonic acid.
33. A method of treatment in which a hydrogel according to any of claims 1 to 14 or a composition according to either of claims 15 or 16 is administered into a blood vessel of a patient to embolise said blood vessel.
34. A method according to claim 33 in which the blood vessel is associated with solid tumour.
35. A method according to claim 34 in which the tumour is hepatocellular carcinoma.
36. A hydrogel according to any of claims 1 to 14 for use in embolization of a blood vessel.
37. A composition according to either of claim 15 or 16 for use in embolization of a blood vessel.

**FIGURE 1**





2B





FIGURE 2



2C

**FIGURE 3**





Figure 4




FIGURE 5




FIGURE 6




FIGURE 7




FIGURE 8





FIGURE 9.



**FIGURE 10**






FIGURE 11





(a)



(b)

FIGURE 11



**INTERNATIONAL SEARCH REPORT**

International application No  
PCT/GB2014/000351

**A. CLASSIFICATION OF SUBJECT MATTER**  
INV. A61K49/04  
ADD.  
  
According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**  
Minimum documentation searched (classification system followed by classification symbols)  
A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
EPO-Internal, WPI Data, EMBASE, BIOSIS

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 1 810 698 A1 (BIOCOMPATIBLES UK LTD [GB]) 25 July 2007 (2007-07-25) cited in the application examples 1-14	1-37
A	WO 2011/110589 A1 (UNIV CLAUDE BERNARD LYON 1 UCBL [FR]; CENTRE NAT RECH SCIENT [FR]; ANT) 15 September 2011 (2011-09-15) cited in the application examples 1-19	1-37
	----- -/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&amp;" document member of the same patent family</p>
---	---

Date of the actual completion of the international search  1 December 2014	Date of mailing of the international search report  09/12/2014
--	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer  Monami, Amélie
--	--

## INTERNATIONAL SEARCH REPORT

International application No  
PCT/GB2014/000351

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>MAWAD DAMIA ET AL: "Synthesis and characterization of radiopaque iodine-containing degradable PVA hydrogels", BIOMACROMOLECULES, AMERICAN CHEMICAL SOCIETY, US, vol. 9, no. 1, 30 November 2007 (2007-11-30), pages 263-268, XP002544191, ISSN: 1525-7797, DOI: 10.1021/BM700754M [retrieved on 2007-11-30] cited in the application abstract page 263, column 2, paragraph 3 - page 264, column 1, paragraph 1 figure 1A page 264, column 1, paragraph 4 - column 2, paragraph 5</p>	1-37
A	<p>US 4 406 878 A (DEBOER CHARLES D [US]) 27 September 1983 (1983-09-27) column 2, line 14 - line 33 column 4, line 38 - column 5, line 6 column 7, line 31 - column 8, line 14</p>	1-37
A	<p>US 2003/059371 A1 (MATSON LOUIS R [US] ET AL) 27 March 2003 (2003-03-27) paragraph [0014] - paragraph [0015] examples 1-4</p>	1-37
A	<p>SHARMA K V ET AL: "Development of Imageable Beads for Transcatheter Embolotherapy", JOURNAL OF VASCULAR AND INTERVENTIONAL RADIOLOGY, ELSEVIER, AMSTERDAM, NL, vol. 21, no. 6, 1 June 2010 (2010-06-01), pages 865-876, XP027058343, ISSN: 1051-0443 [retrieved on 2010-05-20] abstract page 866, column 3, paragraph 3</p>	1-37

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/GB2014/000351

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 1810698	A1	25-07-2007	NONE
-----			
WO 2011110589	A1	15-09-2011	AU 2011226138 A1 26-07-2012
			CA 2786398 A1 15-09-2011
			CN 102781974 A 14-11-2012
			EP 2365009 A1 14-09-2011
			EP 2545085 A1 16-01-2013
			JP 2013521087 A 10-06-2013
			KR 20130051916 A 21-05-2013
			US 2013108574 A1 02-05-2013
			WO 2011110589 A1 15-09-2011
-----			
US 4406878	A	27-09-1983	NONE
-----			
US 2003059371	A1	27-03-2003	NONE
-----			