

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 415 963 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:

**06.05.2004 Bulletin 2004/19**

(51) Int Cl.7: **C06D 5/06**

(21) Application number: **03024880.1**

(22) Date of filing: **31.10.2003**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR  
HU IE IT LI LU MC NL PT RO SE SI SK TR**

Designated Extension States:

**AL LT LV MK**

(30) Priority: **31.10.2002 JP 2002317337**

**21.10.2003 JP 2003360879**

**24.10.2003 JP 2003364024**

(71) Applicant: **DAICEL CHEMICAL INDUSTRIES, LTD.  
Sakai-shi, Osaka (JP)**

(72) Inventors:

• **Yokoyama, Takushi  
Himeji-shi Hyogo (JP)**

• **Watabiki, Mamoru  
Himeji-shi Hyogo (JP)**

• **Wu, Jianzhou  
Himeji-shi Hyogo (JP)**

(74) Representative: **Grünecker, Kinkeldey,  
Stockmair & Schwanhäusser Anwaltssozietät  
Maximilianstrasse 58  
80538 München (DE)**

(54) **Gas generating composition**

(57) A gas generating composition which can prevent formation of mist is provided. A gas generating composition comprising (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) an organic compound as fuel, and (d) an oxygen-containing oxidiz-

ing agent. By the action of the component (a), combustion residues can be solidified to form a slag, thus preventing formation of mist.

**EP 1 415 963 A1**

**Description**

## Technical Field

5 **[0001]** The present invention relates to a gas generating composition suitable for an air bag restraining system of automobiles and the like, a molded article thereof and an inflator for an air bag using the same.

## Background Art

10 **[0002]** As a gas generating agent for an air bag as a passenger-protecting system in automobiles, a composition using sodium azide has been conventionally used. However, a toxicity to human bodies [ $LD_{50}$  (oral-rat) = 27 mg/kg] or hazard in handling of sodium azide has been regarded as a serious problem. Therefore, as safe non-azide based gas generating compositions, gas generating compositions containing various nitrogen-containing organic compounds have been developed to replace the above composition.

15 **[0003]** US-B 4,909,549 discloses a composition comprising hydrogen-containing tetrazole or triazole compounds and an oxygen-containing oxidizing agent. US-B 4,370,181 discloses a gas generating composition comprising a hydrogen-free bitetrazole metal salt and an oxygen-free oxidizing agent. US-B 4,369,079 discloses a gas generating composition comprising a hydrogen-free bitetrazole metal salt and an alkali metal nitrate, an alkali metal nitrite, an alkaline earth metal nitrate, an alkaline earth metal nitrite or a mixture thereof. US-B 5,542,999 discloses a gas generating agent comprising a fuel such as GZT, TAGN (triaminoguanidine nitrate), NG (nitroguanidine), NTO and the like, a basic copper nitrate, a catalyst for reducing toxic gases and a coolant. US-B 5,608,183 discloses a gas generating agent comprising a fuel such as guanidine nitrate, a basic copper nitrate and guar gum.

20 **[0004]** However, the above non-azide based gas generating composition forms residues (mist) after combustion, and the US-B filter should be used to prevent the mist from flowing into an air bag. In this case, there is a method wherein the gas generating composition has a composition easily forming slag, after combustion, having a shape to be readily captured by the filter.

25 **[0005]** US-B 6,143,102 discloses that silica is added as a slag-forming agent to a composition comprising a fuel such as guanidine nitrate, a basic copper nitrate and a metal oxide such as alumina, to form excellent slag (clinker).

30 **[0006]** JP-A No. 10-502610 discloses that glass powder is added to a fuel such as a tetrazole compound and strontium nitrate, thereby lowering the combustion temperature, resulting in a reduction in NO<sub>x</sub> and CO and formation of solid slag.

**[0007]** US-B 5,104,466 (JP-A 5-70109) discloses that an alkali metal azide, pellets consisting of an oxidizing agent and grains consisting of a silica-containing material are used as a mixture to reduce mist.

## Disclosure of the Invention

35 **[0008]** Accordingly, a purpose of the present invention is to provide a novel gas generating composition forming slag more easily than the above compositions in the prior arts.

**[0009]** As means to solve the problem, the present invention provides a gas generating composition comprising (a) glass powder and (b) aluminum hydroxide and/or magnesium hydroxide.

40 **[0010]** As another means to solve the problem, the present invention further provides a gas generating composition comprising the following components (a) to (d):

- (a) glass powder,
- (b) aluminum hydroxide and/or magnesium hydroxide,
- 45 (c) an organic compound as fuel, and
- (d) an oxygen-containing oxidizing agent.

**[0011]** As still another means to solve the problem, the present invention provides a molded article in the form of a single-perforated cylinder or a perforated (porous) cylinder obtained from the above gas generating composition. The single-perforation or perforation may or may be a through-hole or a hollow.

50 **[0012]** As still further means to solve the problem, the present invention provides an inflator for an air bag using the gas generating composition or the molded article.

**[0013]** The gas generating composition of the present invention and a molded article thereof contain glass powder, by which combustion residues can be solidified to form a slag, thus preventing the combustion residues from being converted into mist and released to the outside of an inflator. This effect can further be improved by using glass powder in combination with aluminum hydroxide and/or magnesium hydroxide.

## Embodiments of the Invention

**[0014]** The glass powder used as component (a) in the present invention becomes molten upon combustion of the gas generating composition, and is immediately solidified as the temperature is decreased after combustion. In this process, the component (a) melts and solidifies combustion residues derived from other components, thereby trapping the residues to form a slag. Accordingly, the combustion residues are prevented from being converted into mist and released outside an inflator to flow in an air bag.

**[0015]** The glass powder is preferably an amorphous material consisting of a mixture of metal oxides and/or non-metal oxides, and the metal oxides are preferably those selected from silicon dioxide, sodium oxide, potassium oxide, calcium oxide, magnesium oxide, barium oxide, lead oxide, boron oxide, aluminum oxide and the like. The non-metal oxide is preferably selected from phosphorus oxide, tellurium oxide and bismuth oxide.

**[0016]** The glass powder is preferably one selected from the group consisting of quartz glass, 96% quartz glass, soda lime glass (windowpane, plate glass, bottle glass, glass for light bulb, etc.), lead glass (for electrical, optical and industrial art purposes), aluminoborosilicate glass, borosilicate glass (low expansion, low loss, tungsten sealing, etc.), aluminosilicate glass, phosphate glass, chalcogen glass, etc.

**[0017]** In particular, the softening point of such glass powder is varied depending on its composition, so that it is desirable that the glass powder having the softening point in the optimum range is selected corresponding to the combustion temperature of the composition consisting of an organic compound as fuel, an oxygen-containing oxidizing agent and other additives.

**[0018]** It is preferable in the invention, in particular, to use glass powder having a low softening point, more preferably a softening point of 1000°C or lower, much more preferably a softening point of 590°C or lower, still more preferably a softening point of 550°C or lower. With glass powder having a low softening point, the slag-forming effect is increased and mist is difficultly produced.

**[0019]** The glass powder having a low softening point includes, for example, phosphate glass (including  $P_2O_5$  and one selected from  $CaO$ ,  $B_2O_3$ ,  $SiO_2$ ,  $Al_2O_3$ ,  $Fe_2O_3$ ,  $MgO$ ,  $Na_2O$ ,  $K_2O$  and the like) or that represented by the following formula (I):



in which x, y and z are the mole number.

**[0020]** It is preferable that proportions of x, y and z of the formula (I) are 35 to 50 mole % of x, 30 to 60 mole % of y and 5 to 20 mole % of z, more preferably 40 to 45 mole % of x, 40 to 50 mole % of y and 10 to 15 mole % of z.

**[0021]** The particle diameter of the glass powder, in terms of 50% particle diameter, is preferably 10 to 300  $\mu m$ , more preferably 10 to 100  $\mu m$ , still more preferably 10 to 50  $\mu m$ .

**[0022]** The content of the glass powder in the gas generating composition is preferably 0.1 to 20% by mass, more preferably 0.5 to 5% by mass. When the content of the glass powder is in the above range, the composition can preferably exhibit the slag-forming action without significantly lowering the efficiency of generation of gas.

**[0023]** Aluminum hydroxide and/or magnesium hydroxide used as component (b) of the present invention may be solely used or in combination of both. The component (b) is preferably magnesium hydroxide.

**[0024]** Aluminum hydroxide and/or magnesium hydroxide used as component (b) is low in toxicity, has a high decomposition starting temperature, and shows a significantly endothermic reaction upon thermal decomposition, to form aluminum oxide or magnesium oxide and water. It follows that, by incorporation of aluminum hydroxide and/or magnesium hydroxide, the combustion temperature of the gas generating composition is decreased, and after combustion, the formed amount of toxic nitrogen oxides and carbon monoxide is decreased. Together with the glass powder as component (a), aluminum oxide or magnesium oxide formed by decomposition of aluminum hydroxide or magnesium hydroxide acts to form slag.

**[0025]** The content of aluminum hydroxide and/or magnesium hydroxide in the gas generating composition is preferably 0.1 to 20% by mass, more preferably 1 to 15% by mass. When the content of aluminum hydroxide and/or magnesium hydroxide is in the above-described range, the formed amount of toxic nitrogen oxides and carbon monoxide can be reduced as the combustion temperature is lowered, and when the gas generating composition is used in an inflator for an air bag, a burning rate necessary for expanding and developing an air bag in a predetermined time can also be assured.

**[0026]** The gas generating composition of the present invention can be in a four-component system consisting of (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) an organic compound as fuel, and (d) an oxygen-containing oxidizing agent.

**[0027]** The organic compound as fuel of the component (c) is one or at least two selected from tetrazole compounds,

guanidine compounds, triazine compounds and nitroamine compounds.

**[0028]** The tetrazole compounds include 5-aminotetrazole, bitetrazole ammonium, etc. The guanidine compounds include guanidine nitrate, mono-, di- or tri-aminoguanidine nitrate, nitroguanidine, etc. The triazine compounds include melamine, cyanuric acid, ammeline, ammelide, ammelande, etc.

**[0029]** The oxygen-containing oxidizing agent as component (d) is one or at least two selected from nitrate, perchlorate, chloric acid, a basic metal nitrate and ammonium nitrate.

**[0030]** The nitrate includes alkali metal nitrates such as potassium nitrate and sodium nitrate and alkaline earth metal nitrates such as strontium nitrate. The perchlorates include potassium perchlorate, sodium perchlorate, magnesium perchlorate, ammonium perchlorate, etc. The basic metal nitrate includes a basic copper nitrate etc.

**[0031]** When the gas generating composition of the present invention is in a four-component system consisting of the components (a) to (d), the content of component (a) is preferably 0.1 to 20% by mass, more preferably 1 to 10% by mass, the content of component (b) is preferably 0.1 to 20% by mass, more preferably 1 to 15% by mass, the content of component (c) is preferably 30 to 60% by mass, more preferably 35 to 50% by mass, and the content of component (d) is preferably 30 to 60% by mass, more preferably 40 to 55% by mass.

**[0032]** A preferable example of the gas generating composition in a four-component system is a composition comprising (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) guanidine nitrate and (d) a basic copper nitrate. In this case, the content of (a) glass powder is preferably 2 to 6% by mass, the content of (b) aluminum hydroxide and/or magnesium hydroxide is preferably 1 to 10% by mass, the content of (c) guanidine nitrate is preferably 30 to 60% by mass, and the content of (d) a basic copper nitrate is preferably 30 to 60% by mass.

**[0033]** Another preferable example of the gas generating composition in a four-component system is a composition comprising (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) nitroguanidine and (d) a basic copper nitrate. In this case, the content of (a) glass powder is preferably 1 to 5% by mass, the content of (b) aluminum hydroxide and/or magnesium hydroxide is preferably 1 to 15% by mass, the content of (c) nitroguanidine is preferably 25 to 60% by mass, and the content of (d) a basic copper nitrate is preferably 30 to 60% by mass.

**[0034]** When the gas generating composition of the present invention is in a system containing the components (a) and (b), but not a binder, in a four-component system containing the components (a) to (d), or in a six-component system containing the components (a) to (d) and the component (f) of the additive and the component (g) of silicon dioxide, its molded article may, if poor in molding strength, collapse upon actual combustion and burn too acceleratedly to make control of combustion. Accordingly, the binder as component (e) is preferably added.

**[0035]** The binder as component (e) is one or at least two selected from carboxymethyl cellulose (CMC), sodium carboxymethylcellulose (CMCNa), potassium carboxymethylcellulose, carboxymethylcellulose ammonium, cellulose acetate, cellulose acetate butyrate (CAB), methyl cellulose (MC), ethyl cellulose (EC), hydroxyethyl cellulose (HEC), ethylhydroxyethyl cellulose (EHEC), hydroxypropyl cellulose (HPC), carboxymethylethyl cellulose (CMEC), fine crystalline cellulose, polyacrylamide, an aminated product of polyacrylamide, polyacryl hydrazide, a copolymer of acrylamide and a metal acrylate, a copolymer of polyacrylamide and a polyacrylic ester, polyvinyl alcohol, acrylic rubber, guar gum, starch and silicone. Among these, sodium carboxymethylcellulose (CMCNa) and guar gum are preferable in view of stickiness, cost and ignitability of the binder.

**[0036]** The binder (e) is preferably contained in the gas generating composition in an amount of 1.0 to 5.0 mass %, more preferably 1.5 to 3.5 mass %, when it is combined with the component (b), not to lose a processability or moldability and make the combustion gas clear.

**[0037]** When the gas generating composition of the present invention is in a system containing the components (a) and (b), but not an additive, in a four-component system containing the components (a) to (d), or in a six-component system containing the components (a) to (d) and the component (e) of the binder and the component (g) of silicon dioxide, the additive as component (f) is added preferably for the purpose of assisting the actions of the components (a) and (b).

**[0038]** The additive as component (f) is one or at least two selected from metal oxides such as copper oxide, iron oxide, zinc oxide, cobalt oxide, manganese oxide, molybdenum oxide, nickel oxide, bismuth oxide, gallium oxide, silica and alumina, metal carbonates or basic metal carbonates such as cobalt carbonate, calcium carbonate, magnesium carbonate, a basic zinc carbonate and a basic copper carbonate, composite compounds of metal oxides or hydroxides such as Japanese acid clay, kaolin, talc, bentonite, diatomaceous earth and hydrotalcite, metal acid salts such as sodium silicate, mica molybdate, cobalt molybdate and ammonium molybdate, molybdenum disulfide, calcium stearate, silicon nitride and silicon carbide. These additives can reduce the burning temperature of the gas generating agent, regulate the burning rate and reduce the amount of toxic nitrogen oxides and carbon monoxide formed after combustion.

**[0039]** When the gas generating composition of the present invention is in a four-component system containing the components (a) to (d) or in a six-component system containing the components (a) to (d) and the component (e) of the binder and the component (f) of the additive, silicon dioxide as component (g) is preferably added for the purpose of improvement of ignition of the component (c). The ignition is greatly improved in particular with use of a guanidine compound for the component (c).

**[0040]** Silicon dioxide of the component (g) has a specific surface area of 100 to 500 m<sup>2</sup>/g, preferably 150 to 300 m<sup>2</sup>/g. The specific surface area is determined according to BET method.

**[0041]** When the gas generating composition of the present invention is in a five- or seven-component system consisting of the components (a) to (f), the content of component (a) is preferably 0.1 to 20% by mass, more preferably 1 to 10% by mass, the content of component (b) is preferably 0.1 to 20% by mass, more preferably 1 to 15% by mass, the content of component (c) is preferably 5 to 60% by mass, more preferably 10 to 55% by mass, the content of component (d) is preferably 10 to 85% by mass, more preferably 20 to 75% by mass, the content of component (e) is preferably 20% by mass or less, the content of the component (f) is preferably 20% by mass or less and the content of the component (g) is preferably 5% by mass or less.

**[0042]** A preferable example of the gas generating composition in a five-component system is a composition comprising (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) nitroguanidine, (d) strontium nitrate and (e) sodium carboxymethylcellulose or guar gum.

**[0043]** Another preferable example of the gas generating composition in a five-component system is a composition comprising (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) nitroguanidine, (d) a basic copper nitrate and (e) guar gum.

**[0044]** A still another preferable example of the gas generating composition in a five-component system is a composition comprising (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) melamine, (d) a basic copper nitrate and (e) sodium carboxymethylcellulose or guar gum.

**[0045]** A still another preferable example of the gas generating composition in a five-component system is a composition comprising (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) guanidine nitrate, (d) a basic copper nitrate and (e) sodium carboxymethylcellulose or guar gum.

**[0046]** A preferable example of the gas generating composition in not less than five-component system is a composition comprising (a) glass powder, (b) aluminum hydroxide and/or magnesium hydroxide, (c) a mixed fuel of two or three components selected from guanidine nitrate, nitroguanidine and melamine, (d) a basic copper nitrate and (e) sodium carboxymethylcellulose or guar gum.

**[0047]** A different, preferable embodiment is that including silicon dioxide of the component (g) in addition to the gas generating composition comprising the above shown (a) to (e).

**[0048]** The gas generating composition of the present invention can be molded in a desired shape, and formed into a molded article in the shape of a single-perforated cylinder, a perforated (porous) cylinder or pellets. These molded articles can be produced by a method in which the gas generating composition is mixed with water or an organic solvent and the mixture is extrusion-molded (molded articles in the shape of a single-perforated cylinder and a perforated (porous) cylinder) or by a compression-molding method using a pelletizer (molded article in the shape of pellets).

**[0049]** The gas generating composition of the present invention or the molded article obtained therefrom can be used in, for example, an inflator for an air bag of a driver side, and inflator for an air bag of a passenger side, an inflator for a air bag for a side collision, and inflator for an inflatable curtain, an inflator for a knee bolster, an inflator for an inflatable seat belt, an inflator for a tubular system and a gas generator for pretensioner in various vehicles.

**[0050]** Further, the inflator using the gas generating composition of the present invention or the molded article obtained therefrom may be a pyrotechnic type in which a gas is supplied only from a gas generating agent or a hybrid type in which a gas is supplied from both of a compressed gas such as argon and a gas generating agent.

**[0051]** Moreover, the gas generating composition of the present invention or the molded article obtained therefrom can also be used as an igniting agent called an enhancer (or a booster) for transferring energy of a detonator or a squib to a gas generating agent.

#### Examples

**[0052]** The present invention is illustrated more specifically by referring to the following Examples, but the present invention is not limited thereto.

#### Examples 1 to 6 and Comparative Example 1

**[0053]** Gas generating compositions each having a formulation shown in Table 1 were produced, and each of the gas generating compositions was molded into 2 g of a strand. This strand was installed in a closed bomb having an inner capacity of 1 liter, and the inside of the bomb was purged with nitrogen. Further, the bomb was pressurized up to 6, 860 kPa with nitrogen, and the strand was ignited by electrifying a nichrome wire and completely burned. After combustion, combustion residues were collected from the bomb and observed for their state with the naked eye.

**[0054]** In Table 1, GN is guanidine nitrate, BCN is a basic copper nitrate, CMCNa is sodium carboxymethylcellulose, and #1723 and #7056 are glass powders having the following compositions.

# EP 1 415 963 A1

#1723 (Aluminosilicate glass; softening point of 908°C) (% by mass) : SiO<sub>2</sub> (57)/Al<sub>2</sub>O<sub>3</sub> (16)/B<sub>2</sub>O<sub>3</sub> (4)/MgO (7)/CaO (10)/BaO (6) (softening point of 908°C)  
 #7056 (Borosilicate glass; softening point of 718°C) (% by mass) : SiO<sub>2</sub> (68) /Al<sub>2</sub>O<sub>3</sub> (3)/B<sub>2</sub>O<sub>3</sub> (18) /LiO<sub>2</sub> (1) /Na<sub>2</sub>O (1) /K<sub>2</sub>O (9) (softening point of 718°C)  
 #C-490P (phosphate glass; softening point of about 400°C) (% by mass) : P<sub>2</sub>O<sub>5</sub>(54-56)/Al<sub>2</sub>O<sub>3</sub> (9-11)/Na<sub>2</sub>O (19-21) /K<sub>2</sub>O (14-16)  
 #C-700P (phosphate glass; softening point of about 640°C) (% by mass) : P<sub>2</sub>O<sub>5</sub>(50.5)/Al<sub>2</sub>O<sub>3</sub> (14.5)/Na<sub>2</sub>O (20) /K<sub>2</sub>O (15)

Table 1

|                       | Formulation (formulation ratio: mass%)                          |
|-----------------------|-----------------------------------------------------------------|
| Example 1             | #1723/Al(OH) <sub>3</sub> /GN/BCN/CMCNa=3/5/38.0/49.0/5         |
| Example 2             | #1723/Al(OH) <sub>3</sub> /GN/BCN/CMCNa=5/5/37.0/48.0/5         |
| Example 3             | #7056/Al(OH) <sub>3</sub> /GN/BCN/CMCNa=3/5/38.0/49.0/5         |
| Example 4             | #7056/Al(OH) <sub>3</sub> /GN/BCN/CMCNa=5/5/37.0/48.0/5         |
| Example 5             | #C-490P/Al(OH) <sub>3</sub> /GN/BCN/CMCNa=2.0/9.8/41.9/43.8/2.5 |
| Example 6             | #C-700P/Al(OH) <sub>3</sub> /GN/BCN/CMCNa=4.8/9.5/40.8/42.5/2.4 |
| Comparative Example 1 | Al(OH) <sub>3</sub> /GN/BCN/CMCNa=5/39.6/50.4/5                 |

**[0055]** In Examples 1 to 6, the strands after combustion maintained the shape thereof before combustion, but in Comparative Example 1, the strand was finely smashed.

## Claims

- A gas generating composition comprising (a) glass powder and (b) at least one selected from the group consisting of aluminum hydroxide and magnesium hydroxide.
- A gas generating composition comprising the following components (a) to (d):
  - glass powder,
  - at least one selected from the group consisting of aluminum hydroxide and magnesium hydroxide,
  - an organic compound as fuel and
  - an oxygen-containing oxidizing agent.
- The gas generating composition as claimed in Claim 1 or 2, which further comprises at least one selected from the group consisting of the following components (e), (f) and (g), if required:
  - a binder,
  - an additive selected from a metal oxide and a metal carbonate and
  - silicon dioxide having a specific surface area of 100 to 500 m<sup>2</sup>/g.
- The gas generating composition as claimed in Claim 2 or 3, wherein the content of the component (a) is 0.1 to 20% by mass, the content of the component (b) is 0.1 to 20% by mass, the content of the component (c) is 30 to 60% by mass, the content of the component (d) is 60% by mass or less, the content of the component (e) is 10% by mass or less, the content of the component (f) is 10% by mass or less and the content of the component (g) is 5% by mass or less.
- The gas generating composition as claimed in any one of Claims 1 to 4, wherein the glass powder as component (a) is an amorphous material consisting of a mixture of metal oxides and/or non-metal oxides.
- The gas generating composition as claimed in Claim 5, wherein the metal oxides are selected from the group consisting of silicon dioxide, sodium oxide, potassium oxide, calcium oxide, magnesium oxide, barium oxide, lead

oxide, boron oxide and aluminum oxide.

7. The gas generating composition as claimed in any one of Claims 1 to 6, wherein the glass powder as component (a) is selected from the group consisting of quartz glass, 96% quartz glass, soda lime glass, lead glass, aluminoborosilicate glass, borosilicate glass, aluminosilicate glass, phosphate glass and chalcogen glass.

8. The gas generating composition as claimed in any one of Claims 1 to 6, wherein the glass powder as component (a) is represented by the following formula (I):



in which x, y and z are the mole number.

9. The gas generating composition as claimed in Claim 8, wherein proportions of x, y and z of the formula (I) are 35 to 50 mole % of x, 30 to 60 mole % of y and 5 to 20 mole % of z.

10. The gas generating composition as claimed in any one of Claims 2 to 9, wherein the fuel as component (c) is at least one selected from the group consisting of tetrazole compounds, guanidine compounds, triazine compounds and nitroamine compounds.

11. The gas generating composition as claimed in any one of Claims 2 to 10, wherein the oxygen-containing oxidizing agent as component (d) is at least one selected from the group consisting of nitrates, perchlorates, chloric acid, a basic metal nitrate and ammonium nitrate.

12. The gas generating composition as claimed in any one of Claims 3 to 11, wherein the binder as component (e) is at least one selected from the group consisting of carboxymethyl cellulose, sodium carboxymethylcellulose, potassium carboxymethylcellulose, carboxymethylcellulose ammonium, cellulose acetate, cellulose acetate butyrate, methyl cellulose, ethyl cellulose, hydroxyethyl cellulose, ethylhydroxyethyl cellulose, hydroxypropyl cellulose, carboxymethylethyl cellulose, fine crystalline cellulose, polyacrylamide, an aminated product of polyacrylamide, polyacryl hydrazide, a copolymer of an acrylamide and a metal acrylate, a copolymer of polyacrylamide and a polyacrylic ester, polyvinyl alcohol, acrylic rubber, guar gum, starch and silicone.

13. The gas generating composition as claimed in any one of Claims 3 to 12, wherein the additive as component (f) is at least one selected from the group consisting of metal oxides including cupric oxide, iron oxide, zinc oxide, cobalt oxide, manganese oxide, molybdenum oxide, nickel oxide, bismuth oxide, gallium oxide, silica or alumina, metal hydroxides including cobalt hydroxide or iron hydroxide, metal carbonates or basic metal carbonates including cobalt carbonate, calcium carbonate, magnesium carbonate, a basic zinc carbonate or a basic copper carbonate, composite compounds of metal oxides or metal hydroxides including Japanese acid clay, kaolin, talc, bentonite, diatomaceous earth or hydrotalcite, metal acid salts including sodium silicate, mica molybdate, cobalt molybdate or ammonium molybdate, silicone, molybdenum disulfide, calcium stearate, silicon nitride and silicon carbide.

14. The gas generating composition as claimed in any one of Claims 1 to 13, wherein the component (b) is aluminum hydroxide and (e) the binder is contained in an amount of 1.0 to 5.0 mass %.

15. A gas generating composition comprising glass powder, guanidine nitrate and a basic copper nitrate.

16. A gas generating composition comprising glass powder, a mixed fuel containing guanidine nitrate and a basic copper nitrate.

17. The gas generating composition as claimed in Claim 16, wherein the mixed fuel containing guanidine nitrate is a mixed fuel of guanidine nitrate and at least one selected from the group consisting of nitroguanidine, melamine, monoaminoguanidine nitrate, diaminoguanidine nitrate and triaminoguanidine nitrate.

18. The gas generating composition as claimed in any one of Claims 15 to 17, which further comprises at least one selected from the group consisting of aluminum hydroxide and magnesium hydroxide.

## EP 1 415 963 A1

19. A molded article of the gas generating composition being in the shape of a single perforated cylinder or a perforated cylinder, obtained by extrusion-molding the gas generating composition as defined in any one of Claims 1 to 18.

20. An inflator for air bag, using the gas generating composition as defined in any one of Claims 1 to 18 or using the molded article of the gas generating composition as defined in Claim 19.

5

10

15

20

25

30

35

40

45

50

55





European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 03 02 4880

| DOCUMENTS CONSIDERED TO BE RELEVANT                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |                                                                                                                                    |                                                            |                                                               |
|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------|---------------------------------------------------------------|
| Category                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                         | Citation of document with indication, where appropriate, of relevant passages                                                      | Relevant to claim                                          | CLASSIFICATION OF THE APPLICATION (In I.C.I.7)                |
| X                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                | US 5 460 668 A (L.R. LYON)<br>24 October 1995 (1995-10-24)                                                                         | 1,2                                                        | C06D5/06                                                      |
| Y                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                | * column 3, line 35 - line 48; claims *                                                                                            | 3-20                                                       |                                                               |
| D                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                | & JP 10 502610 T<br>10 March 1998 (1998-03-10)                                                                                     |                                                            |                                                               |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | ---                                                                                                                                |                                                            |                                                               |
| X                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                | WO 01 83274 A (AUTOMOTIVE SYSTEMS<br>LABORATORY, INC.)<br>8 November 2001 (2001-11-08)<br>* page 6, line 9 - line 24; claims *     | 1,2                                                        |                                                               |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | ---                                                                                                                                |                                                            |                                                               |
| A                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                | US 5 035 757 A (D.R. POOLE)<br>30 July 1991 (1991-07-30)<br>* column 4, line 44 - column 6, line 9;<br>claims *                    | 1,2                                                        |                                                               |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | ---                                                                                                                                |                                                            |                                                               |
| X                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                | WO 99 46009 A (AUTOMOTIVE SYSTEMS<br>LABORATORY, INC.)<br>16 September 1999 (1999-09-16)<br>* page 15, line 15 - line 21; claims * | 1,2                                                        |                                                               |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | ---                                                                                                                                |                                                            |                                                               |
| D,Y                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              | US 6 143 102 A (I.V. MENDENHALL ET AL.)<br>7 November 2000 (2000-11-07)<br>* claims *                                              | 15                                                         | TECHNICAL FIELDS<br>SEARCHED (In I.C.I.7)<br><br>C06D<br>C06B |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | ---                                                                                                                                |                                                            |                                                               |
| X                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                | WO 01 34516 A (PRIMEX AEROSPACE COMPANY)<br>17 May 2001 (2001-05-17)<br>* page 3, line 8 - line 18; claims *                       | 1,2                                                        |                                                               |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | ---                                                                                                                                |                                                            |                                                               |
| Y                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                | DE 298 21 541 U (TRW AIRBAG SYSTEMS GMBH &<br>CO. KG) 18 February 1999 (1999-02-18)<br>* claims *                                  | 3-20                                                       |                                                               |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | -----                                                                                                                              |                                                            |                                                               |
| The present search report has been drawn up for all claims                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                       |                                                                                                                                    |                                                            |                                                               |
| Place of search<br><b>THE HAGUE</b>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |                                                                                                                                    | Date of completion of the search<br><b>9 February 2004</b> | Examiner<br><b>Schut, R</b>                                   |
| <p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone<br/> Y : particularly relevant if combined with another document of the same category<br/> A : technological background<br/> O : non-written disclosure<br/> P : intermediate document</p> <p>T : theory or principle underlying the invention<br/> E : earlier patent document, but published on, or after the filing date<br/> D : document cited in the application<br/> L : document cited for other reasons<br/> &amp; : member of the same patent family, corresponding document</p> |                                                                                                                                    |                                                            |                                                               |

EPO FORM 1503 03.92 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 02 4880

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

09-02-2004

| Patent document<br>cited in search report |   | Publication<br>date | Patent family<br>member(s) | Publication<br>date |
|-------------------------------------------|---|---------------------|----------------------------|---------------------|
| US 5460668                                | A | 24-10-1995          | EP 0770047 A1              | 02-05-1997          |
|                                           |   |                     | JP 10502610 T              | 10-03-1998          |
|                                           |   |                     | JP 3279571 B2              | 30-04-2002          |
|                                           |   |                     | WO 9601795 A1              | 25-01-1996          |
| WO 0183274                                | A | 08-11-2001          | EP 1278662 A1              | 29-01-2003          |
|                                           |   |                     | JP 2004501019 T            | 15-01-2004          |
|                                           |   |                     | WO 0183274 A1              | 08-11-2001          |
|                                           |   |                     | US 2001045735 A1           | 29-11-2001          |
| US 5035757                                | A | 30-07-1991          | AU 629512 B2               | 01-10-1992          |
|                                           |   |                     | AU 8580991 A               | 30-04-1992          |
|                                           |   |                     | CA 2052966 A1              | 26-04-1992          |
|                                           |   |                     | DE 69106667 D1             | 23-02-1995          |
|                                           |   |                     | DE 69106667 T2             | 24-05-1995          |
|                                           |   |                     | EP 0482852 A1              | 29-04-1992          |
|                                           |   |                     | JP 2609385 B2              | 14-05-1997          |
|                                           |   |                     | JP 4265292 A               | 21-09-1992          |
|                                           |   |                     | KR 9508200 B1              | 26-07-1995          |
| WO 9946009                                | A | 16-09-1999          | US 6074502 A               | 13-06-2000          |
|                                           |   |                     | CA 2319001 A1              | 16-09-1999          |
|                                           |   |                     | JP 2003528789 T            | 30-09-2003          |
|                                           |   |                     | WO 9946009 A2              | 16-09-1999          |
| US 6143102                                | A | 07-11-2000          | US 2002148542 A1           | 17-10-2002          |
| WO 0134516                                | A | 17-05-2001          | AU 1758201 A               | 06-06-2001          |
|                                           |   |                     | JP 2003525106 T            | 26-08-2003          |
|                                           |   |                     | WO 0134516 A2              | 17-05-2001          |
| DE 29821541                               | U | 18-02-1999          | DE 29821541 U1             | 18-02-1999          |
|                                           |   |                     | DE 59902827 D1             | 31-10-2002          |
|                                           |   |                     | EP 1006096 A1              | 07-06-2000          |

EPO FORM P0489

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82