

⑩



Europäisches Patentamt
European Patent Office
Office européen des brevets

⑪ Publication number:

**0 015 623
B1**

⑫

EUROPEAN PATENT SPECIFICATION

④ Date of publication of patent specification: **31.07.85**

⑤ Int. Cl.⁴: **C 23 C 18/08**

① Application number: **80200206.3**

② Date of filing: **04.03.80**

⑥ **Magnesium compositions and process for forming MgO film.**

③ Priority: **07.03.79 US 18404**

④ Date of publication of application:
17.09.80 Bulletin 80/19

⑤ Publication of the grant of the patent:
31.07.85 Bulletin 85/31

⑧ Designated Contracting States:
CH DE FR GB IT NL SE

⑨ References cited:
**DE-A-1 521 531
GB-A-1 455 148**

⑦ Proprietor: **E.I. DU PONT DE NEMOURS AND
COMPANY**
1007 Market Street
Wilmington Delaware 19898 (US)

⑦ Inventor: **Donohue, Paul Christopher**
18 Boulderbrook Drive
Wilmington Delaware 19803 (US)

⑦ Representative: **van der Beek, George Frans
et al**
Nederlandsch Octrooibureau Johan de Wittlaan
15 P.O. Box 29720
NL-2502 LS 's-Gravenhage (NL)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Courier Press, Leamington Spa, England.

EP 0 015 623 B1

Description

Technical field

This invention relates to a screen-printable syrup and a method of firing this syrup to form a MgO film.

Background art

British patent specification 1,455,148 discloses a method of forming a metallic (magnesium oxide) coating on a substrate wherein a solution of one or more metal acetates, halides and nitrates in an aprotic solvent having a dielectric constant greater than 15 and a dipole moment greater than 3 D is applied to the substrate and the metal compound (magnesium acetate) is pyrolyzed to form a transparent film of the metal oxide (magnesium oxide).

M. O. Aboelfotoh and J. A. Lorenzen, "Influence of Secondary-Electron Emission from MgO Surfaces on Voltage-Breakdown Curves in Penning Mixtures for Insulated-Electrode Dischargers", J. Appl. Phys., Vol. 48, No. 11, 4754—4759 (1977) discloses the formation of a MgO film on the surface of an a—c plasma display panel by sputtering, which involves use of an electron gun to volatilize a magnesium compound and then deposit it as a MgO film on the surface of the panel to a thickness of about 3000 Å. The disadvantage of this method of forming the MgO film is that sputtering is expensive.

Disclosure of invention

The present invention provides an anhydrous screen-printable syrup, comprising (a) an anhydrous organic magnesium compound pyrolyzable to a MgO film below 450°C and (b) an organic solvent, characterized in that the syrup further contains (c) a non carboxylated cellulosic polymer pyrolyzable below 450°C and in that the magnesium compound (a) and the polymer (c) are dissolved in the solvent (b) which is a non aqueous alcohol solvent, the syrup having a Brookfield viscosity of 3—200 Pa·S and provides further a more economical method of forming a film of MgO on a surface.

The process of the invention for forming a MgO film on a surface is conducted by (a) screen-printing thereto a thin layer of the syrup of the invention, (b) drying the layer, and (c) firing the dried layer at a temperature below 450°C to volatilize the solvent (b) and to pyrolyze the thickener (c) and the organic magnesium compound (a). This process is useful in place of sputtering to form an MgO film on the surface of an a—c plasma display panel.

Further description of the invention and best mode

The composition of the present invention contains three essential ingredients, (a) an anhydrous organic magnesium compound pyrolyzable to a MgO film below 450°C, (b) a non-aqueous alcohol solvent and (c) a non-carboxylated cellulosic polymer pyrolyzable

below 450°C, the syrup having a Brookfield-viscosity of 3—200 Pa·S. The criteria for selecting these ingredients and preferred ingredients are set forth hereinafter.

The organic magnesium compound is selected so that it is pyrolyzable to MgO film and is soluble in the organic solvent used at ordinary room temperature. Selection of the organic magnesium compound can be subject to the pyrolysis temperature that can be used. For example, current surfaces of a—c plasma displays are made of lead-rich glass which undergoes a glass transition at a temperature above 450°C. To avoid this transition, the organic magnesium compound is pyrolyzable to MgO film at a temperature below 450°C.

Examples of magnesium organic compounds that can be used are the oxygen-containing organic magnesium compounds such as magnesium carboxylates e.g. magnesium cyclohexanebutyrate, magnesium diketones, e.g. magnesium acetylacetonate, and magnesium alcoholates, e.g., magnesiummethoxide. Preferably all the atoms bound to the magnesium atom in the compound are oxygen atoms and organic carbon atoms are bound to these oxygen atoms.

The organic solvent component is selected so as to dissolve the remaining components of the syrup and to depart from the syrup without leaving any detectable residue during pyrolysis. Typically, most or all of the solvent will evaporate in a drying step preceding any heating to pyrolyze other components of the syrup. Such heating will also volatilize any remaining solvent.

Examples of solvents are the glycol ethers, such as the Cellosolves®, e.g., methyl, butyl and hexyl, the Carbitols®, e.g., methyl, butyl, and hexyl, and the triglycols, e.g., methoxy, ethoxy, and butoxy, the alcohols, such as butanol and isopropanol, and the acetates, such as butyl carbitol acetate.

The organic polymer thickener is selected so as to dissolve in the solvent that also dissolves the organic magnesium compound and to pyrolyze leaving no detectable residue which would prevent formation of the MgO film or would color it. Examples of thickeners are hydroxyethylcellulose, propoxyethylcellulose and ethylcellulose. Preferably, the organic polymer thickener pyrolyzes to no detectable residue at temperatures up to 450°C.

The syrup composition can be made by first dissolving the organic magnesium compound in the solvent and then dissolving the organic polymer thickener in the solution to get the syrup-like consistency desired. Without the organic polymer thickener, the solution would be too flowable to be screen printable. The polymer-free solution would just run through the screen onto the surface to be printed and then would spread out on such surface without producing the desired screen pattern. The thickening effect provided by the organic polymer thickener limits the flowability of the resultant syrup so that it can be screen printed by conventional thick-film paste screen printing techniques to a faithful reproduc-

tion of the screen image on the surface on which the syrup is screen printed.

The organic magnesium compound and organic polymer thickener may not easily dissolve in the same solvent. In the case of magnesium acetylacetonate, this compound easily dissolves in hexyl Carbitol® but ethyl cellulose thickener does not dissolve until heated for about one hour at 155°C. in the solvent, whereupon the polymer rapidly goes into solution.

The syrup of the present invention is a solution, i.e., no solids are observable by the naked eye. This syrup differs from the usual screen printing media, in that such media normally contain solids.

The organic polymer thickener generally imparts a viscosity of at least 3 Pa·S measured using a Brookfield viscometer at 10 rpm and 25°C. A viscosity greater than 200 Pa·S is generally not required. Unexpectedly, while the organic polymer thickener does thicken the syrup, it does not prevent the MgO film from being formed upon pyrolysis, i.e., not only must the organic portion of the magnesium compound pyrolyze to MgO, but the organic polymer thickener must also pyrolyze at the same time without preventing formation of the MgO film. The pyrolysis products of the magnesium compound, except for MgO, and the organic polymer thickener, and any residue of the solvent after drying are volatile at the pyrolysis temperature used, so as to yield the colorless, transparent MgO film. Preferably, the syrup of the present invention has a viscosity of from 10 Pa·S to 50 Pa·S.

The syrup of the present invention will typically contain from 1 to 15% organic magnesium compound, 5 to 20% organic polymer thickener, and 65 to 90% solvent, all percents being by weight based on the total weight of these three components. Preferred compositions contain 4 to 8%, 6 to 15%, and 75 to 85% of organic magnesium compound, organic polymer thickener, and organic solvent, respectively. The amount of thickener is selected to give the syrup the viscosity desired; such amount will vary with the particular thickener selected and the inherent viscosity of the thickener.

The proportion of components and viscosity are selected so as to give an MgO film upon screen printing and pyrolysis of at least about 1000 Å.

It has been found that shelf life (storage stability) of the syrup at ordinary room temperature is improved, i.e., no solids form during standing, if the components of the syrup are dried, preferably before combining into the composition. Drying can be done by heating and/or desiccation of each component. Organic magnesium compounds are available in hydrated form; the drying should remove the water of hydration from the compound. Solvents such as alcohols typically contain water, and this is most readily removed by desiccation in the presence of a desiccant such as CaCl_2 or mixing CaH_2 with

the solvent at near its boiling point, followed by filtering out the CaH_2 particles. The resultant anhydrous or dried syrup has shelf life in excess of two months, whereas without drying, solids begin to appear after about three weeks storage.

A preferred a-c plasma display panel is made by firing a thick silver conductor composition after printing in a conductor line pattern into a substrate, the composition comprising: (A) 50—85% of the weight of the composition, of silver particles of 0.05—20 micrometers in size; (B) 1—10% of the weight of the composition, of inorganic non-glass forming refractory materials or their precursors, such as aluminum oxide, zirconium oxide, cobalt/iron/chromium oxide, aluminium and copper, having a particle size range of 0.05—44 micrometers with at least 80% by weight of the particles in the 0.1—5 micrometer range; (c) 5—20% of the weight of the composition, of glass frit having a softening point range of 325—600°C such as lead borosilicate-based glass; and (D) 10—30% of the weight of the composition, of vehicle such as a UV polymerizable solution of polymethyl methacrylate and a polyfunctional monomer or a non-UV polymerizable solution of ethyl cellulose.

The overglaze composition preferably utilized contains a glass frit of the composition (mole %): PbO (68.2), SiO_2 (12.0), B_2O_3 (14.1), and CdO (5.7), having a softening point of approximately 480°C. The overglaze composition, dispersed in an ethyl cellulose-based vehicle, is screen printed over the fired conductor, dried, and then fired at a temperature and for a time sufficient to produce a clear, smooth coating. It is on this coating that the syrup of the present invention is printed and pyrolyzed.

Examples of the composition and process of the present invention, in which parts and percents are by weight unless otherwise indicated, are as follows:

Example 1—On a hot plate while stirring, 2.5 grams Mg cyclohexanecarboxylate was dissolved in 30 ml dibutylacetate. Two grams ethyl cellulose (viscosity of 22 cps at 5% concentration in 80:20 toluene-ethanol solvent at 25°C) was added and stirring and heating continued to about 150°C for about 60 minutes to dissolve the polymer thickener. When dissolved, the syrup was centrifuged. The centrifuged syrup had a viscosity estimated to be between 10 to 50 Pa·S. The syrup was screen printed onto glass slides which could be the surface of an a-c plasma display panel and dried and then fired in a belt furnace at 470°C peak temperature. MgO film was colorless and transparent indicating complete pyrolysis of the organic moieties of the magnesium compound and thickener. When this experiment was repeated except using a 450°C peak temperature, the MgO film was brown; indicating incomplete pyrolysis.

Example 2—One gram of Mg acetylacetonate was dissolved in 25 ml n-hexyl Carbitol® while stirring on a hot plate. Then 2 grams ethyl cellulose of Ex. 1 was added and dissolved after

standing for about one hour. The resultant syrup had a viscosity estimated to be between 10 to 50 Pa-S and was printed on glass slides, dried, and then fired at 460°C in a box furnace for 1 hour. The MgO films looked good by microscopy. Interferometry on three films indicated smoothness averaging 777 Å thick.

It was observed that this syrup precipitated a white material on standing for about 3 weeks. Later preparations starting with dried Mg acetylacetonate, dried polymer, and dried solvent and prepared at a somewhat higher temperature were stable in excess of several months.

Example 3—Two grams of dried (125°C, 1 hour) Mg acetylacetonate was dissolved in 30 ml n-hexyl Carbitol by heating on a hot plate while stirring; 3 grams of ethyl cellulose of Ex. 1 was added and heating and stirring continued until dissolved. While hot, the solution was centrifuged to remove any undissolved material and impurities. The resultant syrup has a viscosity of about 50 Pa-S.

The syrup was tested by screen printing on microscope slides, allowed to level for about 10 minutes, dried 10 minutes at 120°C and fired on a belt furnace with a 20 minute, 450°C peak temperature.

Microscopic examination showed a good looking smooth, continuous bluish MgO film. Thickness measured by interferometry was 1470 Å.

To achieve thicker films, some slides were reprinted and fired as before. Thickness measurements shows 2058 Å for two coats and 2711 Å for three coats.

Example 4—Three grams of Mg acetylacetonate was dissolved in 20 ml n-hexyl carbitol on a hot plate; 3 grams N-22 ethyl cellulose of Ex. 1 was added and dissolved. While hot, the solution was centrifuged. The syrup had a viscosity estimated to be between 10 to 50 Pa-S. The syrup was tested as described in Example 3 and the resulting MgO film looked good.

Claims

1. An anhydrous screen-printable syrup, comprising (a) an anhydrous organic magnesium compound pyrolyzable to a MgO-film below 450°C and (b) an organic solvent, characterized in that the syrup further contains (c) a non carboxylated cellulosic polymer pyrolyzable below 450°C and in that the magnesium compound (a) and the polymer (c) are dissolved in the solvent (b) which is a non aqueous alcohol solvent, the syrup having a Brookfield viscosity of 3—200 Pa-s.

2. The syrup of claim 1 wherein said organic magnesium compound is magnesium alcoholate.

3. The syrup of claim 1 wherein said organic magnesium compound is magnesium diketone.

4. The syrup of claim 3 wherein said diketone is magnesium acetylacetonate.

5. The syrup of claim 1 wherein said organic magnesium compound is a magnesium carboxylate.

6. A method for forming a film of MgO on a surface comprising (a) screen printing thereto a thin layer of syrup of claim 1, (b) drying the layer, and (c) firing the dried layer at a temperature below 450°C to volatilize the solvent (b) and to pyrolyze the thickener (c) and the organic magnesium compound (a).

7. The process of claim 6 wherein said surface is the surface of an a-c plasma display panel and the resultant MgO film forms a protective layer thereon.

Patentansprüche

1. Ein wasserfreier, siebdruckfähiger Sirup, enthaltend (a) eine wasserfreie, organische Magnesiumverbindung, die unterhalb 450°C zu einem MgO-Film pyrolysierbar ist, und (b) ein organisches Lösungsmittel, dadurch gekennzeichnet, dass der Sirup ferner (c) ein nicht-carboxyliertes Cellulosepolymeres enthält, das unterhalb 450°C pyrolysierbar ist, und dass die Magnesiumverbindung (a) und das Polymere (c) in dem Lösungsmittel (b) gelöst sind, welches ein nicht-wässriges, alkoholisches Lösungsmittel ist, und der Sirup eine Brookfield-Viskosität von 3—200 Pa-S hat.

2. Sirup nach Anspruch 1, worin die organische Magnesiumverbindung Magnesiumalkoholat ist.

3. Sirup nach Anspruch 1, worin die organische Magnesiumverbindung Magnesiumdiketon ist.

4. Sirup nach Anspruch 3, worin das Diketon Magnesiumacetylacetonat ist.

5. Sirup nach Anspruch 1, worin die organische Magnesiumverbindung ein Magnesiumcarboxylat ist.

6. Verfahren zur Herstellung eines MgO-Films auf einer Oberfläche, bei dem (a) auf die Oberfläche eine dünne Schicht des Sirups von Anspruch 1 durch Siebdruck aufgebracht wird, (b) die Schicht getrocknet wird und (c) die getrocknete Schicht bei einer Temperatur unterhalb 450°C gebrannt wird, um das Lösungsmittel (b) zu verdampfen und das Verdickungsmittel (c) und die organische Magnesiumverbindung (a) zu pyrolysieren.

7. Verfahren nach Anspruch 6, wobei die Oberfläche die Oberfläche eines Wechselstrom-Plasma-Anzeigefeldes ist und der entstandene MgO-Film eine Schutzschicht darauf bildet.

Revendications

1. Sirop anhydre applicable par impression sérigraphique, comprenant (a) un composé organique anhydre du magnésium pyrolysable en une pellicule de MgO en dessous de 450°C et (b) un solvant organique, caractérisé en ce que le sirop contient en outre (c) un polymère cellulosique non carboxylé pyrolysable en dessous de 450°C et en ce que le composé de magnésium (a) et le polymère (c) sont dissous dans le solvant (b) qui est un solvant alcoolique

non aqueux, le sirop ayant une viscosité Brookfield de 3 à 200 Pa.S.

2. Sirop selon la revendication 1, dans lequel le composé organique de magnésium est un alcoolate de magnésium.

3. Sirop selon la revendication 1, dans lequel le composé organique de magnésium est une dicétone magnésienne.

4. Sirop selon la revendication 3, dans lequel la dicétone est l'acétylacétonate de magnésium.

5. Sirop selon la revendication 1, dans lequel le composé organique de magnésium est un carboxylate de magnésium.

6. Procédé de formation d'une pellicule de MgO

sur une surface, consistant (a) à appliquer par impression sérigraphique sur celle-ci une mince couche du sirop selon la revendication 1, (b) à sécher la couche, et (c) à cuire la couche séchée à une température inférieure à 450°C pour volatiliser le solvant (b) et pour pyrolyser l'épaississant (c) et le composé organique de magnésium (a).

7. Procédé selon la revendication 6, dans lequel la surface est la surface d'un panneau d'affichage à plasma à courant alternatif et la pellicule de MgO obtenue forme une couche protectrice sur celui-ci.

5

10

15

20

25

30

35

40

45

50

55

60

65

5