



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2093736 C 2001/07/31

(11)(21) **2 093 736**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1993/04/08

(41) Mise à la disp. pub./Open to Public Insp.: 1994/08/12

(45) Date de délivrance/Issue Date: 2001/07/31

(30) Priorité/Priority: 1993/02/11 (08/016,356) US

(51) Cl.Int.⁵/Int.Cl.⁵ B65D 53/06

(72) Inventeur/Inventor:
Bayer, John W., US

(73) Propriétaire/Owner:
OWENS-ILLINOIS CLOSURE INC., US

(74) Agent: GOWLING LAFLEUR HENDERSON LLP

(54) Titre : FERMOIR EN MATIERE PLASTIQUE AVEC GARNITURE D'ETANCHEITE MOULEE PAR COMPRESSION

(54) Title: PLASTIC CLOSURE WITH COMPRESSION MOLDED SEALING LINER

(57) **Abrégé/Abstract:**

A plastic closure including a base wall having an inner surface, a peripheral skirt extending from the base wall and a liner on the inner surface of the base wall. The liner includes (a) an ethylene vinyl acetate composition, (b) a primary fatty acid amide and (c) a bis-fatty acid amide. Preferably the fatty acid amide comprises an oleamide or an erucamide, and the bis-fatty acid amide comprises ethylene-bis-stearamide.



2093736

16598

PLASTIC CLOSURE WITH COMPRESSION MOLDED SEALING LINER

Abstract of the Disclosure

5 A plastic closure including a base wall having an inner surface, a peripheral skirt extending from the base wall and a liner on the inner surface of the base wall. The liner includes (a) an ethylene vinyl acetate composition, (b) a primary fatty acid amide and (c) a bis-fatty acid amide. Preferably the fatty acid amide comprises an oleamide or an erucamide, and the bis-fatty acid amide comprises ethylene-bis-stearamide.

This invention relates to molded plastic closures and particular by compression molded plastic closure having compression molded liners therein.

Background and Summary of the Invention

5 Plastic closures have been commonly made by injection molding or compression molding. In plastic closures made by compression molding as shown, for example, in U.S. Pat. Nos. 3,210,805, 4,434,754 and 4,418,828

10 it is also common to compression mold a sealing liner in place in the closure after the closure has been formed. Such sealing liners may comprise polyvinyl chloride plastic or thermoplastic elastomeric compositions. Polyvinyl chloride has a tendency to overheat during extrusion and further has inherent problems because of the removal torque when the sealing liner
15 is used on a PET container. Thermoplastic polymeric compositions are most expensive and are more difficult to produce in that the compounding necessary results in inconsistent quality and consistency. Furthermore, such compositions produce problems of torque removal of glass containers. U.S. Pat. Nos. 4,807,772
20 and 4,846,362 disclose a compression molded liner being made of a blend of polyethylene or polypropylene and thermoplastic elastomeric copolymer so that the liner is removable.

As a result of the problems with both types of compositions, it has been necessary for a user to maintain costly
25 inventories of closures with both types of sealing liners in order to accommodate use with both plastic and glass containers.

In order to produce a satisfactory sealing liner that would be applicable to both plastic and glass containers, it must be necessary to not only formulate the composition but also consistently extrude and cut off charges of the composition for
5 compression molding in apparatus such as shown, for example, in U.S. Pat. Nos. 3,955,605, 4,080,136 and 4,277,431. The closure must also match other closure requirements including satisfactory removal torques, carbonation retention, and carbonation retention under load and satisfactory functioning on a container when
10 cycled through environmental changes of temperature and humidity.

In U.S. Pat. No. 4,984,703 there is disclosed a compression molded plastic closure having a compression molded sealing liner which fulfills the requirements of a carbonated beverage closure and operates satisfactory on both plastic and
15 glass containers.

When a plastic beverage cap has been provided with an ethylene vinyl acetate liner, it has been found that erratic high removal torques have been provided, the erratic high removal torques are not eliminated. Various efforts have been proposed
20 as disclosed in U.S. Pat. Nos. 3,400,094, 3,406,854, and 4,463,116 that utilize lubricants but, as far as the present inventor knows, have been without success.

Among the objectives of the present invention are to provide a plastic closure with a sealing liner that comprises
25 an ethylene vinyl acetate composition and includes other components that provide for uniform removal torques; wherein the closure is useful in cold climate conditions with migration of

the lubricant to the surface of the liner; wherein the liner can be compression molded in the plastic closure; or where the liner can be molded and then inserted in the closure.

5 In accordance with the invention, a plastic closure includes a base wall having an inner surface, a peripheral skirt extending from the base wall and a liner on the inner surface of the base wall. The liner comprises (a) ethylene vinyl acetate composition, (b) a primary fatty acid amide and (c) a bis-fatty acid amide. Preferably the fatty acid amide comprises an oleamide
10 or erucamide, and the bis-fatty acid amide comprises ethylene-bis-stearamide.

The oleamide or erucamide and the bis-fatty acid amide are preferably mixed before introduction into the ethylene vinyl acetate composition. The total amount of fatty acid amide and
15 bis-fatty acid amide to the ethylene vinyl acetate is preferably at about 0.5% - 1.5% by weight.

The ratio of fatty acid amide to bis-fatty acid amide is preferably 50-50 by weight but may range between 25-75 or 75-25 by weight.

Description

The plastic closure embodying the invention is made of suitable material such as polypropylene and comprises a base wall, a peripheral skirt having internal threads 13 for engagement
5 with complementary threads on a container and a sealing liner in the form of an annular shape at the juncture of the base wall and peripheral skirt. Such a closure may be of the type disclosed in United States patent 4,984,703

The closure may include tamper indicating means such
10 as shown, for example, in U.S. Pat. Nos. 4,418,828, 4,613,052 and 4,653,657.

In accordance with the invention, the sealing liner comprises an ethylene vinyl acetate composition and a blend of a primary acid amide and bis-fatty acid amide, which are believed
15 to function as lubricants.


The oleamide or erucamide and the bis-fatty acid amide are preferably mixed before introduction into the ethylene vinyl acetate composition. The total amount of fatty acid amide and bis-fatty acid amide to the ethylene vinyl acetate is preferably
20 at about 0.5% - 1.5% by weight.

The ratio of fatty acid amide to bis-fatty acid amide is preferably 50-50 by weight but may range between 25-75 or 75-25 by weight.

The ethylene vinyl acetate composition comprises
25 polyethylene as the major constituent and vinyl acetate and optionally includes antioxidants and pigments.

Fatty acid amides are based on fatty saturated and unsaturated straight-chain, monobasic acids derived from naturally occurring feedstocks. Predominant chain lengths range from eighteen to twenty-two carbon atoms. The primary amides
 5 are waxy solids with melting points in the range of 68-108°C.

Oleamide fatty acid amides comprise an unsaturated fatty primary amide derived from oleic acid wherein the major component is:



10 Such an oleamide has the following physical properties:

<u>TYPICAL PROPERTIES</u>	<u>KEMAMIDE O</u>
Molecular weight	275
Density @ 130°C(266°F), g/mL	0.822
Density @ 160°F(71°C), g/mL	0.857
15 Viscosity @ 130°C, cP	5.5
Heat of fusion, kcal/mol	6.3
Flash point, °C, COC	245
Fire point, °C, COC	264

Erucamide fatty acid amides comprise unsaturated fatty primary amide derived from erucic acid wherein the major component
 20 is:



Such an erucamide has the following physical properties:


<u>TYPICAL PROPERTIES</u>		<u>KEMAMIDE E</u>
	Molecular weight	335
5	Density @ 130°C(266°F),g/mL	0.815
	Density @ 160°F(70°C),g/mL	0.851
	Viscosity @ 130°C,cP	6.4
	Heat of fusion,kcal/mol	9.8
	Flash point,°C,COC	262
10	Fire point,°C,COC	287

Ethylene bisamides are reaction products of saturated or unsaturated fatty acids and ethylenediamine.


This fatty bisamide has the following properties:

<u>TYPICAL PROPERTIES</u>		<u>KEMAMIDE W-40</u>
15	Flash point,°C,COC	299
	Fire point,°C,COC	315
	Physical form	Flake Only

A satisfactory fatty bisamide derived from stearic acid is: N,N'-ethylenebisstearamide when the major component is:



Another satisfactory fatty bisamide derived from oleic acid is N,N'-ethylenebisoleamide herein the major component is:



This fatty bisamide has the following properties:

5	<u>TYPICAL PROPERTIES</u>	<u>KEMAMIDE W-20</u>
	Flash point, °C, COC	296
	Fire point, °C, COC	315
	Physical form	Power and pellet

10 The ethylene vinyl acetate composition may have the composition within about the following ranges, by weight:

Polyethylene	85% to 94%
Vinyl acetate	6% to 15%

The primary acid amide comprises either oleamide or erucamide.

15 The bis-fatty acid amide preferably comprises an ethylene-bis-stearamide.

The liner composition may include antioxidants and colorants as is conventionally used.

20 In a preferred form, the primary acid amide and bis-fatty acid amide are mixed with a colorant and a carrier such as low density polyethylene and then this is provided for use with the ethylene vinyl acetate composition.

In an early experiment, the resin used were as follows:

RESIN	MELT FLOW (gm/10 min)	DENSITY (gm/cc)	ACETATE%
5 Dupont Elvax 750	7.0	0.930	9.0
Dupont Elvax 650	8.0	0.933	12.0
Dupont Elvax 550	8.0	0.935	15.0
Dupont Elvax 450	8.0	0.940	18.0

Elvax is a trademark of Dupont for ethyl vinyl acetate copolymer.

10 The various lubricants used in such experiments were as follows:

LUBRICANTS

15 Kenamide U (oleamide)
Kenamide E (erucamide)
Kenamide W-40 (ethylene-bis-stearamide)
Kenamide W-20 (ethylene-bis-oleamide)

Kenamide is a trademark of Humko Chemical Division of Witco Corporation.

20 As used herein, the components of the composition are abbreviated as follows:

olea = oleamide

eruc = erucamide

EBS = ethylene bis stearamide

EBO = ethylene bis oleamide

25 In such an experiment testing for coefficient of friction (COF), mixtures of the additives intended to function as lubricants were provided as follows with the results indicated:

ratio	olea/eruc	EBS/EBO	EBS/eruc	EBS/olea	EBO/eruc	EBO/olea
100/0	1.040	2.970	2.970	2.970	4.050	4.050
50/50	0.900	2.790	1.060	0.990	1.280	1.10
0/100	1.510	3.970	1.510	1.040	1.510	1.040

5 With the exception of the EBO/oleamide mixture, the
binary mixtures exhibit lower coefficient of friction (COF)
values than the individuals by themselves. This approach was
extended in the erucamide and oleamide systems mixed with EBS
and EBO to find the optimum ratio of the lubes that would give
10 the minimum COF.

The following tables show the result at 1% total
concentration of lubricant with the ethylene vinyl acetate (EVA):

		EBS/Oleamide and Erucamide Mixes	
15	<u>%EBS</u>	<u>COF (erucamide mix) - (oleamide mix)</u>	
	0%	1.510	1.040
	25%	1.340	1.030
	50%	1.060	0.990
	75%	1.270	1.330
20	100%	2.970	2.970

		EBO/Oleamide and Erucamide Mixes	
	<u>%EBO</u>	<u>COF (erucamide mix) - (oleamide mix)</u>	
	0%	1.510	1.040
25	25%	1.090	0.990
	50%	1.330	1.110
	75%	1.260	1.170
	100%	3.870	3.870

The data shows that the 50:50 mix of EBS to erucamide
30 and or oleamide produces the optimum ratio whereas with EBO
mixtures, the optimum ratio is 25% EBO blended with erucamide
or oleamide.

2093736

Concentration of Mixtures:

The effects of total concentration of the mixtures were explored. COF measurements of 50:50 EBS mixtures with erucamide and oleamide are shown in the following table:

5	<u>% total lubricants</u>	<u>erucamide/EBS</u>	<u>oleamide/EBS</u>
	1.0%	1.060	0.990
	0.75%	1.100	1.070
	0.5%	1.110	1.120

As when erucamide and oleamide are utilized as single components, the concentration of the mixed lubricants only slightly affects the COF in the range of concentrations tested.

In further tests, the following results in removal torques were obtained:

		<u>COMPOSITIONS</u>				
15		CONTROL	A	B	C	D
	ELVAX 750	-	-	100	100	-
	ELVAX 650	100	100	-	-	100
	EBS	-	0.5	0.5	0.5	0.5
	ERUCAMIDE	-	0.5	0.5	-	-
20	EBO	1.5	-	-	-	-
	OLEAMIDE	-	-	-	0.5	0.5
	LDPE (30MF)	10	10	10	10	10
	PACK RESULTS:					
25	REMOVAL TORQUE (RT)	12.0	7.8	8.2	8.2	7.6
	IMMEDIATE					
	1 DAY	11	10	10.3	12.6	11.2
	1 WEEK	15.0	13.8	14.0	12.6	14.0
	CO2-1 WEEK	3.85	3.84	3.80	3.86	3.85

It can be seen that the compositions A, B, C, D provided lower removal torques than the EVA control alone.

Other tests covering immediate and removal torques, comprises the compositions A and C:

5		A	Control
	<u>Immediate</u>		
	avg.	14. 2	19.4
	sigma	1.27	1.51
	mn/mx	12/16	16/22
10	<u>1 Day</u>		
	avg.	20.2	20.8
	sigma	1.84	11.1
	mn/mx	18/24	19/22.5
	<u>1 Week</u>		
15	avg.	17.0	16.0
	sigma	1.78	1.89
	mn/mx	15.5/20	14/20
	<u>2 Weeks</u>		
	avg.	17.9	17.7
20	sigma	1.63	1.96
	mn/mx	15.5/20	14/21.5
	<u>4 Weeks</u>		
	avg.	18.5	16.9
	sigma	1.37	1.70
25	mn/mx	16.5/20	14.5/19

The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows:

1. A plastic closure comprising a base wall having an inner surface, a peripheral skirt extending from said base wall, and a liner compression molded on said inner surface of said base wall, said liner comprising

- 5 (a) ethylene vinyl acetate composition,
- (b) a primary fatty acid amide selected from the group consisting of an oleamide and an erucamide,
- (c) a bis-fatty acid amide, the total amount of primary fatty acid amide and bis-fatty acid amide being about 0.5% - 1.5% by weight based on
- 10 the weight of the ethylene vinyl acetate, the ethylene vinyl acetate comprising about 85% - 94% by weight of polyethylene and about 6% - 15% by weight of vinyl acetate, the ratio of primary fatty acid amide to bis-fatty acid amide ranges between 25:75 and 75:25, by weight.

15 2. The closure set forth in claim 1 wherein said bis-fatty acid amide is selected from the group consisting of ethylene-bis-oleamide and ethylene-bis-stearamide.