



(86) Date de dépôt PCT/PCT Filing Date: 2014/05/06
(87) Date publication PCT/PCT Publication Date: 2014/11/13
(45) Date de délivrance/Issue Date: 2021/03/09
(85) Entrée phase nationale/National Entry: 2015/10/01
(86) N° demande PCT/PCT Application No.: IB 2014/061237
(87) N° publication PCT/PCT Publication No.: 2014/181250
(30) Priorité/Priority: 2013/05/09 (ZA2013/03363)

(51) Cl.Int./Int.Cl. *C07C 2/36*(2006.01),
C07C 11/02(2006.01), *C07C 11/107*(2006.01),
C08F 10/00(2006.01)

(72) Inventeurs/Inventors:
MOKHADINYANA, MOLISE STEPHEN, ZA;
MAUMELA, MUNAKA CHRISTOPHER, ZA;
MOGOROSI, MOSES MOKGOLELA, ZA;
OVERETT, MATTHEW JAMES, ZA;
VAN DEN BERG, JAN-ALBERT, ZA;
JANSE VAN RENSBURG, WERNER, ZA;
BLANN, KEVIN, ZA

(73) Propriétaire/Owner:

(54) Titre : TETRAMERISATION D'ETHYLENE
(54) Title: TETRAMERISATION OF ETHYLENE

(57) Abrégé/Abstract:

A process for the tetramerisation of ethylene includes contacting ethylene with a catalyst under ethylene oligomerisation conditions. The catalyst comprises a source of chromium, a ligating compound, and an activator. The ligating compound includes a phosphine that forms part of a cyclic structure.

(73) Propriétaires(suite)/Owners(continued):SASOL TECHNOLOGY (PROPRIETARY) LIMITED, ZA

(74) Agent: BORDEN LADNER GERVAIS LLP

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau(10) International Publication Number
WO 2014/181250 A1(43) International Publication Date
13 November 2014 (13.11.2014)

(51) International Patent Classification:

C07C 2/36 (2006.01) *C07C 11/02* (2006.01)
C08F 10/00 (2006.01) *C07C 11/107* (2006.01)

(21) International Application Number:

PCT/IB2014/061237

(22) International Filing Date:

6 May 2014 (06.05.2014)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

2013/03363 9 May 2013 (09.05.2013) ZA

(71) Applicant: SASOL TECHNOLOGY (PROPRIETARY) LIMITED [ZA/ZA]; 1 Sturdee Avenue, 2196 Rosebank (ZA).

(72) Inventors: MOKHADINYANA, Molise Stephen; 4 Masasa Complex, Toon van den Heever Street, 1947 Sasolburg (ZA). MAUMELA, Munaka Christopher; 3 Tygerberg Street, Vaalpark, 1947 Sasolburg (ZA). MOGOROSI, Moses Mokgolela; 13 Three Mountains Estate, Graskop Street, Vaalpark, 1947 Sasolburg (ZA). OVERETT, Matthew James; 76 Basroyd Drive, Bassonia, 2061 Johannesburg (ZA). VAN DEN BERG, Jan-Albert; El Manor 8, Delius Street, SW5 - Parksouth, 1910 Vanderbijlpark (ZA). JANSE VAN RENSBURG, Werner; 24 Hakea Crescent, 1911 Vanderbijlpark (ZA). BLANN, Kevin; 5 Alberante Estates, De La Rey Road, Alberante, 1449 Johannesburg (ZA).

(74) Agents: SPOOR & FISHER et al.; P O Box 454, 0001 Pretoria (ZA).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

Published:

— with international search report (Art. 21(3))

(54) Title: TETRAMERISATION OF ETHYLENE

(57) Abstract: A process for the tetramerisation of ethylene includes contacting ethylene with a catalyst under ethylene oligomerisation conditions. The catalyst comprises a source of chromium, a ligating compound, and an activator. The ligating compound includes a phosphine that forms part of a cyclic structure.



WO 2014/181250 A1

TETRAMERISATION OF ETHYLENE

5 TECHNICAL FIELD

The invention relates to a process for the tetramerisation of ethylene, the process including contacting ethylene with a catalyst under ethylene oligomerisation conditions, said catalyst comprising a source of chromium
10 and novel ligating compounds.

BACKGROUND OF THE INVENTION

15 It is known that chromium-based catalyst systems with diphosphine ligands catalyse the selective conversion of ethylene to 1-hexene and/or 1-octene depending on the reaction conditions and choice of ligand structure. In particular, the nature and position of any substituents on the aryl rings connected to the phosphines are crucial influences on the selectivity split between 1-hexene and
20 1-octene. Of particular interest to industry are catalysts for ethylene tetramerisation, as these catalysts are relatively rare. Octene is a valuable comonomer for the production of high performance linear low density polyethylenes and elastomers, and few selective on-purpose routes to this chemical are known in industry. By comparison, catalysts for ethylene
25 trimerisation are relatively common, and are used industrially by several companies. By tetramerisation it is meant that at least 30% 1-octene is produced in the process.

Non-limiting examples of selective ethylene tetramerisation catalyst systems include the ubiquitous Cr / bis(phosphino)amine (i.e. 'PNP') systems, particularly of the type $(Ar^1)(Ar^2)PN(R)P(Ar^3)(Ar^4)$, where Ar^1 to Ar^4 are aryl groups such as phenyl and R is a hydrocarbyl or a heterohydrocarbyl group, beginning with PNP ligands containing no substituents on the phenyl rings bonded to the P-atoms (e.g. as described in WO 2004/056479) and those with *m* or *p*-methoxy groups on the phenyl rings (e.g. as described in WO 2004/056480). In addition to this, PNP systems containing *o*-fluoro groups on the phenyl rings are described in US 2008/0242811 and US 2010/0081777, and PNP systems bearing pendant donor atoms on the nitrogen linker are described in WO 2007/088329. Multi-site PNP ligands are discussed in US 2008/0027188. In addition to the Cr/PNP systems, chromium systems bearing N,N-bidentate ligands (e.g. as described in US 2006/0247399) can be used. PNP ligands with alkylamine or phosphinoamine groups bonded to one of the PNP phosphines (i.e. 'PNPNH' and 'PNPNP' ligands) are described in WO 2009/006979. Finally, carbon bridged diphosphine (i.e. 'PCCP' ligands) are described in WO 2008/088178 and WO 2009/022770.

Related ethylene trimerisation catalysts with high selectivity for 1-hexene can be obtained by using PNP ligands with *ortho*-methoxy or *ortho*-alkyl substituents on the phenyl rings bonded to the P-atoms (e.g. as described in WO2002/04119, WO2004/056477 and WO2010/034101).

When carrying out a process for tetramerisation of ethylene, the aim is to choose a catalyst system and adjust process conditions in order to produce the maximum amount of 1-octene, as opposed to trimerisation processes where catalysts and process conditions are adjusted to produce the maximum amount of 1-hexene. 1-Hexene is also typically co-produced in a tetramerisation process. Consequently, new tetramerisation catalyst systems which increase catalyst selectivity to 1-octene while reducing selectivity to co-products are

highly desirable. Alternatively, new tetramerisation catalysts which produce similar amounts of 1-octene to catalysts known in the art, but which produce more 1-hexene (i.e. reduced C4 and C10+ oligomers) would also be desirable.

5 In several investigations of structure-selectivity relationships for tetramerisation ligands, the effect of various patterns of *ortho*-substitution on the phenyl rings of the $(Ar^1)(Ar^2)PN(R)P(Ar^3)(Ar^4)$ ligand (where $Ar^1 - Ar^4$ are optionally substituted phenyl groups and R is a hydrocarbyl group) has been studied. For example, the effect of *ortho*-alkyl groups (Blann et al, Chem. Commun. 2005, 620),
10 *ortho*-methoxy groups (Overett et al. Chem Commun 2005, 622) and *ortho*-fluorine groups (US 2010/008177) on selectivity has been reported. These *ortho*-substitutions may produce significant selectivity benefits in terms of reduced co-products (e.g. C10-C14 secondary products or reduced C6 cyclics). However, in all cases the effect of *ortho*-substitution is to reduce the 1-
15 octene:1-hexene ratio relative to the equivalent unsubstituted PNP ligand. Consequently, ligand motifs that act to increase the intrinsic 1-octene selectivity and which may be used in combination with a beneficial *ortho*-substitution motif on the same PNP ligand structure may be particularly beneficial.

20

The formation of a high molecular weight polymer co-product by the Cr-based ethylene tetramerisation catalyst may present a major technical challenge when commercialising an ethylene tetramerisation process. Polymer fouling of the reactor or downstream sections will reduce plant run time and necessitate shut-
25 downs due to blockages and loss of reaction cooling due to coating of heat exchange surfaces. When running tetramerisation processes at reaction temperatures in the range of 40 to 80°C, as is taught in the art, most of the polymer co-product precipitates in the reactor, which can result in fouling of process equipment. To ensure process reliability and adequate run-times under

such reaction conditions, it may be necessary to utilise expensive or energy-intensive process design features.

5 Running a tetramerisation process at process conditions whereby the polymer co-product remains predominantly dissolved in the liquid reaction medium in the reactor (i.e. a solution phase process) would substantially reduce the possibility of reactor or downstream fouling. In addition, a further benefit of such a process might be that a cheaper or more energy-efficient process design could be used, due to the reduced likelihood of fouling process equipment.

10

A solution phase process could be achieved by using higher reaction temperatures than typically taught in the art, specifically temperatures of above 80°C. However, the art teaches away from running at higher temperatures due to undesirable effects including poor catalyst activity, increased polymer formation and increased selectivity towards 1-hexene. It is well known in the art of the invention that higher reaction temperatures shift the selectivity from 1-octene towards 1-hexene. New tetramerisation catalysts have been developed that show improved performance at high temperatures, but these modifications reduce the octene:hexene ratio further. In this context, novel tetramerisation catalyst structures that increase the intrinsic selectivity towards 1-octene are highly desirable.


15
20

SUMMARY OF THE INVENTION:

25

According to one aspect of the invention there is provided a process for the tetramerisation of ethylene, the process including contacting ethylene with a catalyst under ethylene oligomerisation conditions, said catalyst comprising:

- i) a source of chromium;
- ii) a ligating compound of the formula



5


wherein A is selected from the group consisting of nitrogen, phosphorus, and oxygen;

X is a linking group between A and Y;

m is independently 1 or 2;

- 10 R^1 is a hydrogen, a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group with each R^1 being the same or being different where m is 2; and

Y is an optionally substituted group that can be represented as



15

such that P is a phosphorous atom and bonds to X; and

L₁ and L₂ are linkers selected from the group comprising a covalent bond and an optionally substituted single atom

- 6 -

bonded to both of the linked carbon or phosphorous atoms;
and

iii) optionally a catalyst activator or combination of catalyst activators.

5

According to some embodiments of the invention, there is provided a process for the tetramerisation of ethylene, the process including contacting ethylene with a catalyst under ethylene oligomerisation conditions, said catalyst comprising:

10

- i) a source of chromium;
- ii) a ligating compound of the formula



15

wherein P is a phosphorous atom;


X is a linking group between P and Y;

R¹ and R² are independently a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group; and

20

Y is an optionally substituted group that can be represented as

- 7 -



such that P is a phosphorous atom which bonds to X; and

L₁ and L₂ are linkers selected from the group comprising a covalent bond and an optionally substituted single atom bonded to both of the linked carbon or phosphorous atoms; and

5

iii) optionally a catalyst activator or combination of catalyst activators.

10 DETAILED DESCRIPTION OF EMBODIMENTS OF THE INVENTION

The invention relates to a process for the tetramerisation of ethylene, the process including contacting ethylene with a catalyst under ethylene oligomerisation conditions, said catalyst comprising a source of chromium, a ligating compound, which compound includes one phosphine that forms part

15

In the specification, the following definitions apply:

A "hydrocarbyl group" as per IUPAC includes a univalent group formed by removing one hydrogen atom from a hydrocarbon;

5 A "heterohydrocarbyl group" as defined herein is a univalent group formed by removing one hydrogen atom from a carbon atom of a heterohydrocarbon, that is a hydrocarbon compound which includes at least one hetero atom (that is, not being H or C), and which group covalently bonds with one other moiety through the resultant free valency on that carbon atom;

10 An "organoheteryl group" as per IUPAC includes univalent groups containing carbon, which are thus organic, but which have their free valence at an atom other than carbon;

15 A "hydrocarbylene group" as per IUPAC includes divalent groups formed by removing two hydrogen atoms from a hydrocarbon, the free valencies of which are not engaged in a double bond.

20 A "heterohydrocarbylene group" as defined herein is a divalent group formed by removing two hydrogen atoms from either one or two carbon atoms of an organic molecule containing at least one heteroatom, the free valencies of which are not engaged in a double bond.

Chromium Source (i):

25 Any source of chromium that allows the oligomerisation to proceed may be used. The source of chromium may be an inorganic salt, an organic salt, a coordination compound or an organometallic complex.

- 9 -

In some embodiments the source of chromium is selected from the group consisting of chromium trichloride tris-tetrahydrofuran complex; (benzene)tricarbonyl chromium; chromium (III) octanoate; chromium hexacarbonyl; chromium (III) acetylacetonate; chromium (III) naphthenate; 5 chromium (III) 2-ethylhexanoate; chromium (III) acetate, chromium (III) 2,2,6,6-tetramethylheptadionate; and chromium (III) chloride. In some embodiments it is chromium (III) acetylacetonate or chromium (III) 2-ethylhexanoate.

The chromium source may be introduced to the process as a coordination 10 complex of the ligating compound. However, for reasons of cost and commercial operability, in some embodiments the ligating compound and chromium source are added as separate components to the process. Catalyst systems which give good catalyst performance only when an isolable chromium-ligand coordination complex is used therefore suffer a disadvantage 15 to catalyst systems which can be prepared by mixing a chromium source and ligand in the process.

Ligating Compound (ii):

20 *Linking group X*

X may be selected from the group consisting of an organic linking group such as a hydrocarbylene, heterohydrocarbylene; an inorganic linking group comprising either a single- or two-atom linker spacer; and a group comprising 25 dimethylmethylene, ethane-1,2-diyl, ethene-1,2-diyl, propane-1,2-diyl, propane-1,3-diyl, cyclopropane-1,1-diyl, cyclopropane-1,2-diyl, butane-2,3-diyl, cyclobutane-1,2-diyl, cyclopentane-1,2-diyl, cyclohexane-1,2-diyl, cyclohexane-1,1-diyl, 1,2-phenylene, naphthalene-1,8-diyl, phenanthrene-9,10-diyl, phenanthrene-4,5-diyl, 9,10-anthracene-diyl, 1,2-catecholate, 1,2- 30 diarylhydrazine-1,2-diyl (-N(Ar)-N(Ar)- where Ar is an aryl group), 1,2-

dialkylhydrazine-1,2-diyl (-N(Alk)-N(Alk)- where Alk is an alkyl or a cycloalkyl group), 1-alkyl-2-arylhydrazine-1,2-diyl (-N(Alk)-N(Ar)- where Alk is an alkyl or a cycloalkyl group and Ar is an aryl group), -N(R')-X¹-N(R'')- where R' and R'' are independently alkyl, cycloalkyl or aryl groups and X¹ is a hydrocarbylene group, =C(R')-N(R'')- or =C(R')-C(R'')(R''')- where = denotes a double bond and R', R'' and R''' are independently hydrogen, alkyl, cycloalkyl or aryl groups, -B(R⁵)-, -Si(R⁵)₂-, -P(R⁵)- and -N(R⁵)- where R⁵ is hydrogen, a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group. Preferably R⁵ is a hydrocarbyl group or a heterohydrocarbyl group.

10

For the embodiment of the invention where the ligating compound is of the form (R¹)_mAXY, X may be bonded to A through either a single covalent bond or a double covalent bond, as required by the valence of the (R¹)_mA moiety. For the case where A is a nitrogen or phosphorous atom, X will be bound to A through a single covalent bond if m is equal to 2, and through a double covalent bond if m is equal to 1.

15

In some embodiments X consists of -N(R⁶)-, -N(R⁶)-N(R⁷)-, -C(R⁶)(R⁷)-N(R⁸)-, =C(R⁶)-N(R⁷)-, or a hydrocarbylene, where R⁶, R⁷ and R⁸ are independently a hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl group. In some embodiments R⁶-R⁸ may be an alkyl, cycloalkyl, substituted alkyl, substituted cycloalkyl, aryl, substituted aryl, aryloxy, substituted aryloxy, alkoxy, carbonyloxy, alkoxy, aminocarbonyl, carbonylamino, dialkylamino, pyrolyl, silyl group or derivative thereof, and aryl substituted with any of these substituents. In some embodiments R⁶-R⁸ may be an alkyl, cycloalkyl, substituted alkyl, substituted cycloalkyl, aryl, substituted aryl, dialkylamino, silyl group or derivative thereof. In some embodiments, R⁶-R⁸ consist of hydrocarbyl groups, such as methyl, ethyl, propyl, allyl, isopropyl, cyclopropyl, butyl, tertiary-butyl, sec-butyl, cyclobutyl, pentyl, isopentyl, 1,2-dimethylpropyl (3-methyl-2-butyl), 1,2,2-trimethylpropyl (R/S-3,3-dimethyl-2-

20
25
30

butyl), 1-(1-methylcyclopropyl)-ethyl, neopentyl, cyclopentyl, cyclohexyl, hexyl, cycloheptyl, cyclo-octyl, decyl, cyclodecyl, 1,5-dimethylheptyl, 1-methylheptyl, 2-naphthylethyl, 1-naphthylmethyl, adamantylmethyl, 1-adamantyl, 2-adamantyl, 2-isopropylcyclohexyl, 2,6-dimethylcyclohexyl, cyclododecyl, 2-
 5 methylcyclohexyl, 3-methylcyclohexyl, 4-methylcyclohexyl, 2-ethylcyclohexyl, 2-isopropylcyclohexyl, 2,6-dimethyl-cyclohexyl, *exo*-2-norbornanyl, (1,1'-bis(cyclohexyl)-4,4'-methylene), 1,6-hexylene, 1-naphthyl, 2-naphthyl, diphenylmethyl, 1,2-diphenyl-ethyl, phenylethyl, 2-methylphenyl, 3-methylphenyl, 4-methylphenyl, 2,6-dimethyl-phenyl, or a 1,2,3,4-
 10 tetrahydronaphthyl.

In a preferred embodiment X is a hydrocarbylene, $-N(R^5)-$, $-N(R^5)-N(R^6)-$, $=C(R^7)-N(R^5)-$, $-N(R^5)-C(R^7)(R^8)-$, $N(R^5)-X^1-N(R^6)$ where R^5 and R^6 are independently a hydrocarbyl group, an organoheteryl group or a
 15 heterohydrocarbyl group, R^7 and R^8 are independently a hydrogen, a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group, and X^1 is a hydrocarbylene group.

X, in some embodiments, is $-N(R^9)-$, where R^9 is a hydrocarbyl group, a
 20 heterohydrocarbyl group or an organoheteryl group. In some embodiments R^9 is a hydrocarbyl group or a heterohydrocarbyl group. In some embodiments R^9 is an alkyl, cycloalkyl or aryl group. In some preferred embodiments R^9 is an alkyl or cycloalkyl group. In some embodiments R^9 is an alkyl group of the form $-CH_2R^{10}$, where R^{10} is hydrogen or an alkyl group or a cycloalkyl group.
 25 In some embodiments R^9 is methyl or a linear alkyl group.

Nature of the group $(R^1)_m A$, for the embodiment of the invention where the ligating compound is of the form $(R^1)_m AXY$

For the embodiment of the invention where the ligating compound is of the form $(R^1)_mAXY$, A is selected from the group consisting of nitrogen, phosphorus, and oxygen. In some embodiments, A is selected from the group consisting of nitrogen and phosphorous. In some embodiments, A is selected from the group consisting of nitrogen and phosphorous and is bonded to X through a single covalent bond, in which case m is equal to 2. In another embodiment, A is a nitrogen atom and is bonded to X through a double covalent bond, in which case m is equal to 1.


For the embodiment of the invention where the ligating compound is of the form $(R^1)_mAX$, R^1 is a hydrogen, a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group with each R^1 being the same or being different where m is equal to 2. In some embodiments, R^1 is a hydrocarbyl, an organoheteryl group or a heterohydrocarbyl group. In some embodiments, R^1 is a hydrocarbyl or heterohydrocarbyl group. In some embodiments, R^1 is an aromatic, including a heteroaromatic, group directly bonded to A. In some embodiments, R^1 is an optionally substituted phenyl group. In some embodiments, R^1 is selected from a group consisting of phenyl, 2-methylphenyl, 2-fluorophenyl, 2-methoxyphenyl, 2-trifluoromethoxyphenyl, and 1-benzofuran-7-yl.

Nature of the groups R^1 and R^2 , for the embodiment of the invention where the ligating compound is of the form R^1R^2PXY

R^1 and R^2 are independently a hydrocarbyl, an organoheteryl group or a heterohydrocarbyl group. In some embodiments, R^1 and R^2 are independently hydrocarbyl or heterohydrocarbyl groups. In some embodiments, both R^1 and R^2 are aromatic, including heteroaromatic, groups directly bonded to P. In some embodiments, both R^1 and R^2 are optionally substituted phenyl groups. In some embodiments, R^1 and R^2 may independently be selected from a group consisting of phenyl, 2-methylphenyl, 2-fluorophenyl, 2-methoxyphenyl, 2-trifluoromethoxyphenyl, and 1-benzofuran-7-yl.

Nature of the group Y

Y is an optionally substituted group that can be represented as



such that P is a phosphorous atom and bonds to X; and

- 5 L₁ and L₂ are linkers selected from the group comprising a covalent bond and an optionally substituted single atom bonded to both of the linked carbon or phosphorous atoms.

10 In some embodiments, L₁ and L₂ may be selected from the group comprising a covalent bond, a heteroatom, a substituted heteroatom, -C(=O)-, -CR³R⁴-, where R³ and R⁴ are independently a hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl group.

15 In some embodiments, L₁ and L₂ can be selected from the group comprising a covalent bond, -O-, -S-, -NR₃-, -P(=O)R³-, P(=Se)R³-, P(=S)R³-, -SiR³R⁴-, -CR³R⁴-, -C(=O)- where R³ and R⁴ are independently a hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl group.

20 In some embodiments, L₁ and L₂ can be selected from the group comprising a covalent bond, -O-, -S-, -NR₃-, -SiR³R⁴-, -CR³R⁴-, -C(=O)- where R³ and R⁴ are independently a hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl group.

In some embodiments, L_1 and L_2 can be selected from the group comprising a covalent bond, -O-, -S-, -NR₃-, where R³ is a hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl group.


In some embodiments, L_1 and L_2 are either a covalent bond or -O-.

5 In some embodiments, at least one of L_1 and L_2 is a covalent bond.


In some embodiments, either L_1 and L_2 are covalent bonds; or L_1 is -O- and L_2 is a covalent bond; or L_1 is a covalent bond and L_2 is -O-.

In some embodiments, both of L_1 and L_2 are covalent bonds. In this case, Y (which is formally named dibenzophosphol-5-yl or 5H-benzo[b]phosphindole)

10 has the following structure:




In some embodiments, L_1 is -O- and L_2 is a covalent bond. In this case, Y (which is formally named 9-oxa-10-phosphaphenanthren-10-yl or 6H-dibenzo[c.e][1,2]oxaphosphirine) has the following structure:



15

In some embodiments, L_1 is a covalent bond and L_2 is -O-. In this case, Y (which is formally named phenoxaphosphin-10-yl or 10H-phenoxaphosphine) has the following structure:

- 15 -



Y may optionally be substituted at one or more of the aromatic ring positions with groups other than hydrogen. In some embodiments, the substituents may be hydrocarbyl groups, heterohydrocarbyl or organoheteryl groups or halogen atom substituents. In some embodiments, Y is not substituted, with all ring positions other than those bonded to P, L₁ and L₂ being bonded to hydrogen atoms.

10 *Other considerations*

For the embodiment of the invention where the ligating compound is of the form R¹R²PXY, R¹ and R² may independently be linked to each other, or to X, to form a cyclic structure.

15

For the embodiment of the invention where the ligating compound is of the form R¹R²PXY, the ligating compound may also include multiple R¹R²P¹XY units. Non-limiting examples of such ligands include dendrimeric ligands as well as ligands where the individual units are coupled, for example via the linking group X.

20

It will be appreciated that a diphosphinoimine compound of the form R¹R²P¹-P²(=NR³)R³R⁴ ('P-P=N') is a rearranged isomer of the diphosphinoamine compound R¹R²P¹N(R³)P²R³R⁴ ('P-N-P') as shown by Dyson et al in *Inorganica Chimica Acta* 359 (2006) 2635-2643. Similarly, it may be possible that a ligating compound of the form R¹R²PXY, where Y is defined as in the current invention and where X is -N(R³)-, exists in its isomeric 'P-P=N' form.

25

Regardless of the structural formulation of the ligating compound in its pure and isolated form, its use will fall under the present invention if it exists in the 'P-N-P' form when used in a tetramerisation process.

5 In some embodiments the ligating compound may be one of:

(Dibenzophosphol-5-yl)N(n-butyl)P(phenyl)₂;

(Dibenzophosphol-5-yl)N(n-butyl)P(2-methylphenyl)₂;

(Dibenzophosphol-5-yl)N(i-propyl)P(phenyl)₂;

10 (Dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl)₂;

(Dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl)(phenyl);

(Dibenzophosphol-5-yl)N(i-propyl)P(2-ethylphenyl)(phenyl);

(Dibenzophosphol-5-yl)N(n-butyl)P(1-benzofuran-7-yl)(phenyl);

(Dibenzophosphol-5-yl)N(n-butyl)P(1-benzofuran-7-yl)₂;

15 (Dibenzophosphol-5-yl)N(n-butyl)P(2-methoxyphenyl)₂;

(Dibenzophosphol-5-yl)N(n-butyl)P(2-methoxyphenyl)(phenyl);

(Dibenzophosphol-5-yl)N(n-butyl)P(2-fluorophenyl)₂;

(Dibenzophosphol-5-yl)N(n-butyl)P(2-fluorophenyl)(phenyl);

(Dibenzophosphol-5-yl)N(i-propyl)P(2-fluorophenyl)₂;

20 (Dibenzophosphol-5-yl)N(i-propyl)P(2-fluorophenyl)(phenyl);

(Dibenzophosphol-5-yl)N(Me)N(Me)P(phenyl)₂;

- (Dibenzophosphol-5-yl)N(Me)N(Me)P(2-methylphenyl)₂;
- (Dibenzophosphol-5-yl)N(i-propyl)P(2-trifluoromethoxyphenyl)₂;
- (Dibenzophosphol-5-yl)N(i-propyl)P(2-trifluoromethoxyphenyl)(phenyl);
- (Dibenzophosphol-5-yl)N(Me)N(n-butyl)P(phenyl)₂;
- 5 (Dibenzophosphol-5-yl)N(n-butyl)N(Me)P(phenyl)₂;
- (Dibenzophosphol-5-yl)-1,2-phenylene-P(phenyl)₂;
- (Dibenzophosphol-5-yl)-1,2-phenylene-P(2-fluorophenyl)(phenyl);
- (Dibenzophosphol-5-yl)-1,2-phenylene-P(2-fluorophenyl)₂;
- (Dibenzophosphol-5-yl)-1,2-phenylene-P(2-methylphenyl)₂;
- 10 (Dibenzophosphol-5-yl)CH₂N(naphthyl)P(phenyl)₂;
- (Dibenzophosphol-5-yl)N(naphthyl)CH₂P(phenyl)₂;
- (Dibenzophosphol-5-yl)CH₂N(naphthyl)P(2-fluorophenyl)₂;
- (Dibenzophosphol-5-yl)N(naphthyl)CH₂P(2-methylphenyl)₂;
- (Dibenzophosphol-5-yl)N(Me)CH₂CH₂CH₂CH₂N(Me)P(phenyl)₂;
- 15 (Dibenzophosphol-5-yl)N(Me)CH₂CH₂CH₂CH₂N(Me)P(2-fluorophenyl)₂;
- (Dibenzophosphol-5-yl)N(H)C(benzyl)=N(2,6-dimethylphenyl);
- (Dibenzophosphol-5-yl)N(H)C(phenyl)=N(2,6-dimethylphenyl);
- (Dibenzophosphol-5-yl)N(H)C(i-propyl)=N(2,6-dimethylphenyl);
- (Dibenzophosphol-5-yl)N(methyl)C(benzyl)=N(2,6-dimethylphenyl);
- 20 (Dibenzophosphol-5-yl)N(H)C(benzyl)=N(phenyl);
- (Dibenzophosphol-5-yl)N(H)C(4-methylbenzyl)=N(2,6-dimethylphenyl);

- (Dibenzophosphol-5-yl)N(H)C(4-methylbenzyl)=N(phenyl);
- (Phenoxaphosphin-10-yl)N(n-butyl)P(phenyl)₂;
- (Phenoxaphosphin-10-yl)N(n-butyl)P(2-methylphenyl)₂;
- (Phenoxaphosphin-10-yl)N(i-propyl)P(phenyl)₂;
- 5 (Phenoxaphosphin-10-yl)N(i-propyl)P(2-methylphenyl)₂;
- (Phenoxaphosphin-10-yl)N(i-propyl)P(2-methylphenyl)(phenyl);
- (Phenoxaphosphin-10-yl)N(i-propyl)P(2-ethylphenyl)(phenyl);
- (Phenoxaphosphin-10-yl)N(n-butyl)P(1-benzofuran-7-yl)(phenyl);
- (Phenoxaphosphin-10-yl)N(n-butyl)P(1-benzofuran-7-yl)₂;
- 10 (Phenoxaphosphin-10-yl)N(n-butyl)P(2-methoxyphenyl)₂;
- (Phenoxaphosphin-10-yl)N(n-butyl)P(2-methoxyphenyl)(phenyl);
- (Phenoxaphosphin-10-yl)N(n-butyl)P(2-fluorophenyl)₂;
- (Phenoxaphosphin-10-yl)N(n-butyl)P(2-fluorophenyl)(phenyl);
- (Phenoxaphosphin-10-yl)N(i-propyl)P(2-fluorophenyl)₂;
- 15 (Phenoxaphosphin-10-yl)N(i-propyl)P(2-fluorophenyl)(phenyl);
- (Phenoxaphosphin-10-yl)N(Me)N(Me)P(phenyl)₂;
- (Phenoxaphosphin-10-yl)N(Me)N(Me)P(2-methylphenyl)₂;
- (Phenoxaphosphin-10-yl)N(Me)N(n-butyl)P(phenyl)₂;
- (Phenoxaphosphin-10-yl)N(n-butyl)N(Me)P(phenyl)₂;
- 20 (Phenoxaphosphin-10-yl)-1,2-phenylene-P(phenyl)₂;
- (Phenoxaphosphin-10-yl)-1,2-phenylene-P(2-fluorophenyl)(phenyl);

- (Phenoxaphosphin-10-yl)-1,2-phenylene-P(2-fluorophenyl)₂;
- (Phenoxaphosphin-10-yl)-1,2-phenylene-P(2-methylphenyl)₂;
- (Phenoxaphosphin-10-yl)CH₂N(naphthyl)P(phenyl)₂;
- (Phenoxaphosphin-10-yl)N(naphthyl)CH₂P(phenyl)₂;
- 5 (Phenoxaphosphin-10-yl)CH₂N(naphthyl)P(2-fluorophenyl)₂;
- (Phenoxaphosphin-10-yl)N(naphthyl)CH₂P(2-methylphenyl)₂;
- (Phenoxaphosphin-10-yl)N(Me)CH₂CH₂CH₂CH₂N(Me)P(phenyl)₂;
- (Phenoxaphosphin-10-yl)N(Me)CH₂CH₂CH₂CH₂N(Me)P(2-fluorophenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)P(phenyl)₂;
- 10 (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)P(2-methylphenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(i-propyl)P(phenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(i-propyl)P(2-methylphenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(i-propyl)P(2-methylphenyl)(phenyl);
- (9-oxa-10-phospha-phenanthren-10-yl)N(i-propyl)P(2-ethylphenyl)(phenyl);
- 15 (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)P(1-benzofuran-7-yl)(phenyl);
- (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)P(1-benzofuran-7-yl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)P(2-methoxyphenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)P(2-methoxyphenyl)(phenyl);
- (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)P(2-fluorophenyl)₂;
- 20 (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)P(2-fluorophenyl)(phenyl);
- (9-oxa-10-phospha-phenanthren-10-yl)N(i-propyl)P(2-fluorophenyl)₂;

- (9-oxa-10-phospha-phenanthren-10-yl)N(i-propyl)P(2-fluorophenyl)(phenyl);
- (9-oxa-10-phospha-phenanthren-10-yl)N(Me)N(Me)P(phenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(Me)N(Me)P(2-methylphenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(Me)N(n-butyl)P(phenyl)₂;
- 5 (9-oxa-10-phospha-phenanthren-10-yl)N(n-butyl)N(Me)P(phenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)-1,2-phenylene-P(phenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)-1,2-phenylene-P(2-fluorophenyl)(phenyl);
- (9-oxa-10-phospha-phenanthren-10-yl)-1,2-phenylene-P(2-fluorophenyl)₂;
- 10 (9-oxa-10-phospha-phenanthren-10-yl)-1,2-phenylene-P(2-methylphenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)CH₂N(naphthyl)P(phenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(naphthyl)CH₂P(phenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)CH₂N(naphthyl)P(2-fluorophenyl)₂;
- (9-oxa-10-phospha-phenanthren-10-yl)N(naphthyl)CH₂P(2-methylphenyl)₂;
- 15 (9-oxa-10-phospha-phenanthren-10-yl)N(Me)CH₂CH₂CH₂CH₂N(Me)P(phenyl)₂;
- and
- (9-oxa-10-phospha-phenanthren-10-yl)N(Me)CH₂CH₂CH₂CH₂N(Me)P(2-fluorophenyl)₂.
- 20 **Activator/ Additives (iii):**

The above process may include an activator to activate the catalyst. Such an activator is a compound that generates an active catalyst when the activator is combined with the catalyst. These activators may be the same or similar to those found to be useful for activating transition-metal-based olefin polymerisation catalysts, a review of which is provided by Marks [*Chem Rev.* 5 **2000**, 100, 1391-1394]. Mixtures of activators may also be used.

Suitable compounds include organoaluminum compounds, organoboron compounds and inorganic acids and salts, such as tetrafluoroboric acid etherate, silver tetrafluoroborate, sodium hexafluoroantimonate and the like. 10 Suitable organoaluminum compounds include compounds of the formula AlR_3 , where each R is independently C_1 - C_{12} alkyl, oxygen or halide, and compounds such as $LiAlH_4$ and the like. Examples include trimethylaluminum (TMA), triethylaluminum (TEA), tri-isobutylaluminum (TIBA), tri-n-octylaluminum, 15 methylaluminum dichloride, ethylaluminum dichloride, dimethylaluminum chloride, diethylaluminum chloride, ethylaluminumsesquichloride, methylaluminumsesquichloride, and aluminoxanes. Aluminoxanes are well known in the art as typically oligomeric compounds which can be prepared by the controlled addition of water to an alkylaluminum compound, for example 20 trimethylaluminum. Such compounds can be linear, cyclic, cages or mixtures thereof. Commercially available aluminoxanes are generally believed to be mixtures of linear and cyclic compounds. The cyclic aluminoxanes can be represented by the formula $[R^{11}AlO]_s$, and the linear aluminoxanes by the formula $R^{12}(R^{13}AlO)_s$, wherein s is a number from about 2 to 50, and wherein 25 R^{11} , R^{12} , and R^{13} represent hydrocarbyl groups, typically C_1 to C_6 alkyl groups, for example methyl, ethyl or butyl groups. Alkylaluminoxanes especially methylaluminoxane (MAO) are particularly suitable. (MAO is also referred to as methalumoxane and methylalumoxane in the literature).

- 22 -

It will be recognized by those skilled in the art that commercially available alkylaluminoxanes may contain a proportion of trialkylaluminium. For instance, commercial MAO usually contains approximately 10 wt % trimethylaluminium (TMA), and commercial "modified MAO" (or "MMAO") contains both TMA and
5 TIBA. Quantities of alkylaluminoxane are generally quoted herein on a molar basis of aluminium (and include such "free" trialkylaluminium). The alkylaluminoxane and/or alkylaluminium may be added to the reaction media (i.e. ethylene and/or diluent and/or solvent) prior to the addition of the catalyst or at the same time as the catalyst is added. Such techniques are known in the
10 art of oligomerization and are disclosed in more detail in for example, U.S. Pats. Nos. 5,491,272; 5,750,817; 5,856,257; 5,910,619; and 5,919,996 as well as WO 2008/146215 and WO 2007/007272.


In the preparation of the catalyst systems used in the present invention, the
15 optimal quantity of activating compound to be employed is easily determined by simple testing, for example, by the preparation of small test samples which can be used to oligomerize small quantities of ethylene and thus to determine the activity of the produced catalyst. It is generally found for alkylaluminium and aluminoxane based activators or co-activators that a suitable quantity
20 employed is 0.5 to 2000 moles of aluminium per mole of chromium.

Examples of suitable organoboron activator compounds are boroxines, NaBH_4 ,
trimethylboron, triethylboron, triphenylboron,
dimethylphenylammoniumtetra(phenyl)borate, trityltetra(phenyl)borate,
25 dimethylphenylammonium tetrakis(pentafluorophenyl)borate, trityl
tetrakis(pentafluorophenyl)borate, tris(pentafluorophenyl) boron, sodium
tetrakis[(bis-3,5-trifluoromethyl)phenyl]borate, dimethylphenylammonium
tetrakis[(bis-3,5-trifluoromethyl)phenyl]borate, and trityl tetrakis[(bis-3,5-
trifluoromethyl)phenyl]borate.

30

Those skilled in the art will recognise that boron-containing activators are commonly used in combination with aluminium alkyl activators.

In some embodiments organoboron activators, as described in WO
5 2010/092554, include a cation and a non-coordinating anion of the general formula



wherein:

10 L* is an atom selected from the group consisting of N, S and P;

the cation $[(R)_x L^* - H]^+$ is a Bronsted acid;

x is an integer 1, 2 or 3;

15 each R is the same or different and each is a -H, hydrocarbyl group or a heterohydrocarbyl group;

provided that at least one of R comprises at least 6 carbon atoms and provided further that the total number of carbon atoms in $(R)_x$ collectively is greater than 12;

20 R^{14} independently at each occurrence is selected from the group consisting of hydride, dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, halosubstituted-hydrocarbyl radicals, halosubstituted-alkoxide, halosubstituted-aryloxy and a halosubstituted aromatic moiety with at least one halide substituent on the aromatic moiety.

25


Illustrative, but non-limiting examples of these organoboron activators include methyldi(octadecyl)ammonium tetrakis(pentafluorophenyl) borate and trioctylammonium tetrakis(pentafluorophenyl) borate.

The source of chromium and the organoboron activator may be combined in proportions to provide organoboron compound /chromium molar ratios from about 0.1 to 50 organoboron to 1 chromium, or from about 0.8 to 20 organoboron to 1 chromium, or from 1 to 10 organoboron to 1 chromium.

5

In some embodiments activators, as described in WO 2007/039851, include a cation and an anion component, and may be represented by the following formula:

10



where L is a neutral Lewis base; H is hydrogen; $(L-H)^{d+}$ is a Bronsted acid; A^{d-} is a non-coordinating anion having the charge d^- ; and d is an integer from 1 to 3.

15

In these activator compounds, A^{d-} can be a fluorinated aluminate group. Illustrative but non-limiting examples of the anion component A^{d-} are $[Al\{OC(CF_3)_3\}_4]^-$; $[Al(OC_6F_5)_4]^-$; $[Al(C_6F_4O_2)_2]^-$; $[AlF\{OC(CF_3)_3\}_3]^-$; $[Al_2F\{OC(CF_3)_3\}_6]^-$; and $[Ta(OC_6F_5)_6]^-$.

20

The activator compound may optionally be a solid material, or be supported on an insoluble solid material. For example, aluminoxanes such as MAO and borate activators may be supported on inorganic oxides such as alumina, silica, $MgCl_2$ or the like.

25

The process may further include the use of compounds that may act as a reducing or oxidising agent, such as sodium or zinc metal and the like, or an oxygen-containing compound, for example oxygen and the like. Additionally, hydrogen (H_2) and/or silanes and the like may be used in the catalytic

composition or otherwise added to the process. The process may also include the use of a zinc species as an additive, as described in WO 2011/048527. Preferred zinc species would be dialkyl zinc reagents such as dimethylzinc or diethylzinc.

5

Catalyst preparation:

The chromium (i) and ligand (ii) may be present in any molar ratio which produces oligomer, and in some embodiments is between 100:1 and 1:100, or from 10:1 to 1:10, or from 3:1 to 1:3. Generally the amounts of (i) and (ii) are approximately equal, i.e. a ratio of between 1.5:1 and 1:1.5.

The ligand, chromium and activators of the catalyst system utilized in the present invention may be added together simultaneously or sequentially, in any order, and in the presence or absence of ethylene in any suitable solvent at any suitable concentration, so as to give an active catalyst. For example, the ligand, chromium, activators and ethylene may be contacted together simultaneously; or the ligand, chromium and activators may be added together simultaneously or sequentially in any order and then contacted with ethylene; or chromium and the ligand may be added together to form an isolable metal-ligand complex and then added to the activator and contacted with ethylene; or the ligand, chromium and activators/co-activators may be added together to form an isolable metal-ligand complex and then contacted with ethylene.

25

Any or all of the chromium source, ligating compound and activator components utilized in the present invention can be unsupported or supported on a support material, for example silica, alumina, $MgCl_2$ or zirconia, or on a polymer, for example polyethylene, polypropylene, polystyrene or poly(aminostyrene).

30

Diluent:

The process of the present invention may be carried out in the presence or absence of an added diluent. In some embodiments of the invention the diluents include oligomerisation products e.g. 1-octene and/ or 1-hexene, 5 aliphatic and aromatic hydrocarbon solvents and halogenated-aromatic solvents such as chlorobenzene, dichlorobenzene, fluorobenzene and the like. In some embodiments the diluents are aliphatic hydrocarbon solvents including but not limited to Isopar™, iso-octane, cyclohexane, cyclopentane, 10 methylcyclohexane, propane, isobutane, isopentane, neopentane, 2-methylpentane, or 3-methylpentane.

Alternatively the process can be conducted as a bulk process in which essentially neat reactant and/or product olefins serve as the dominant medium.

15

Process conditions:

The oligomerisation reaction may take place at any suitable temperature to allow oligomerisation to proceed. Suitable temperatures may be from 0°C to 20 200°C. Preferred temperatures are dependent on the process conditions utilized.

In one embodiment, the oligomerisation is conducted under slurry phase conditions, which is herein taken to mean that a substantial portion of any 25 polymer co-product is present in the solid phase, and not predominantly dissolved in the liquid reaction medium under the chosen reaction conditions. Suitable temperatures to achieve this range from 0°C to about 80°C. Such process conditions may be chosen for optimal catalyst activity and selectivity.

- 27 -

In another embodiment, the oligomerisation is conducted under solution phase conditions, which is herein taken to mean that any polymer co-product remains substantially dissolved in the liquid reaction medium under the chosen reaction conditions. Suitable temperatures to achieve this range from above 80°C to
5 about 130°C. In some embodiments the temperature range is between 85°C and 130°C, whilst in other embodiments the temperature range is between 90°C and 110°C. Such process conditions may be chosen to reduce fouling of the reactor or other process equipment.

10 Suitable reaction pressures are from atmospheric to 800 atmospheres (bar), or from 5 atmospheres to 100 atmospheres, or from 40 to 100 atmospheres, or from 60 to 100 atmospheres.

There exist a number of options for the tetramerisation reactor including batch,
15 semi-batch, and continuous operation. In some embodiments the process is a continuous process, in which case reactors utilizing both CSTR and plug flow behavior may be considered. There are different potential configurations as a subset of these two types of reactors. For example, CSTR type reactors include bubble columns, stirred tanks, loop reactors with single or two phases
20 while plug flow reactors include fixed bed and homogeneous tubular types of varying residence times. As a further subset, reactors can be configured with different cooling options such as internal or external heat exchangers, interstage coolers, and cold feed heat removal amongst others. All configurations can be run in continuous or batch mode, and there is
25 opportunity to configure the same reactor several times in series or use combinations of different reactor types and cooling techniques together to achieve the desired result.

For systems where tetramerisation takes place in the liquid phase, different
30 mass transfer opportunities exist including jet loop mixing, bubble column

sparging, tubular reactor multiple injections and pre-saturation of the feed material amongst others.

The reactor type selected may depend on factors such as heat removal,
5 mechanical robustness with regard to fouling, residence time distributions,
product composition effects as a result of secondary reactions and mechanical
equipment cost implications. In a slurry phase process where polymer
precipitates out of the reaction medium, the selection criteria of heat removal
and mechanical robustness with regard to fouling may be expected to
10 dominate and many reactor configurations may therefore be excluded. In a
solution phase process, a wider range of reactor configurations may be
considered and implemented to optimize factors such as residence time
distributions, product composition effects as a result of secondary reactions
and mechanical equipment cost implications. In particular, the use of reactors
15 wherein reaction cooling is effected by means of heat exchangers in contact
with the reaction medium may be practical in a solution phase process,
whereas the susceptibility of such heat exchangers to fouling may rule out
such options for a slurry-phase process.

EXAMPLES:


The following abbreviations are used in the examples:

5	PCl	chlorophosphine, i.e. R^1R^2PCl , where R^1 and R^2 are hydrocarbyl groups or heterohydrocarbyl groups
	n-butyl	normal butyl
	n-hexyl	normal hexyl
	i-propyl	iso-propyl
	Et	ethyl
10	NEt ₃	Triethylamine
	RT	room temperature (in the order of 20 to 25°C)
	iPrMgBr.LiCl	iso-propyl magnesium bromide lithium chloride
	Ph	phenyl
15	PNH	phosphinoamine, e.g. $Ar_2PN(R)H$, where Ar is an aryl, and R is a hydrocarbyl group
	PNP	bis phosphinoamine, e.g. $Ar_2PN(R)PAr_2$, where Ar is an aryl, and R is a hydrocarbyl group
	Et ₂ O	diethyl ether
	DCM	dichloromethane
20	THF	tetrahydrofuran
	DMF	dimethylformamide
	TMP	2,2,4-trimethylpentane
	MMAO	An aluminoxane product

General Experimental Conditions for Ligand Synthesis


All reactions were carried out under an argon atmosphere using a dual vacuum/nitrogen line and standard Schlenk techniques. Solvents were purified via an M-Braun solvent purification system. All reagents purchased from commercial suppliers were used without further purification. NMR spectra were recorded on a Varian 400 MHz spectrometer using CDCl_3 . PNP compounds below were prepared by modification of the procedure described in *Synthesis*, 2007, 24, 3863.

10 Preparation of 5-chlorodibenzophosphole



To a cooled (0 °C) solution of 2,2'-dibromobiphenyl (4 g, 12.8 mmol) in Et_2O (40 ml), n-butyl lithium (11.3 ml, 28.2 mmol, 2.5 M solution in Et_2O) was added drop-wise. After complete addition the cooling bath was removed and the yellow solution was stirred at room temperature for 1 h. The solution was then frozen with liquid nitrogen (-196 °C). Subsequently, PCl_3 (6.7 ml, 76.9 mmol) was added and the reaction mixture allowed to warm to -110 °C. When the reaction mixture began to thaw, it was quickly homogenized with swirling. The homogenous solution was allowed to warm to room temperature with stirring and a white precipitate formed. The reaction mixture was evaporated to dryness, and the residue re-dissolved in Et_2O and filtered through a celite bed to give the product. ^{31}P NMR (CDCl_3): δ 68.341 (br. s).


Preparation of (2-methoxyphenyl)₂phosphine chloride



1-Bromo-2-methoxybenzene (1.3 ml, 10.7 mmol) was added to a mixture of magnesium turnings (0.3 g, 12.8 mmol) in anhydrous THF (20 ml). A vigorous
5 reaction ensued. Stirring was continued at room temperature until all the magnesium had dissolved. Once the reaction exotherm had dissipated, the reaction mixture was used for the next step.

The Grignard reagent (separated from excess Mg) was incrementally added to a solution of PCl_3 (0.4 ml, 5.3 mmol) in anhydrous THF (30 ml) at -78°C . After
10 addition was complete, the suspension was stirred at room temperature for a further 15 min after which the reaction was complete as judged by ^{31}P NMR. The product was used in the next step without isolation. ^{31}P NMR (CDCl_3): δ 69.89 and 63.06 (2x s, corresponding to P-Cl and P-Br).

15 Preparation of (2-fluorophenyl)₂phosphine chloride




To a cooled (0°C) solution of 1-bromo-2-fluorobenzene (2.5 ml, 22.9 mmol) in THF (20 ml), $i\text{PrMgBr}\cdot\text{LiCl}$ (21 ml, 27.5 mmol, 1.3 M solution THF) was added
20 dropwise. After complete addition the cooling bath was removed and the grey solution was stirred at room temperature for 1 h. The solution was

- 32 -

subsequently added dropwise to a chilled solution of PCl_3 (1 ml, 11.5 mmol) in THF ($-78\text{ }^\circ\text{C}$) and the reaction allowed to stir for a period of 10 min. The homogenous solution was then allowed to warm to room temperature. The reaction mixture was evaporated to dryness, and the residue was re-dissolved in Et_2O and filtered through a celite bed to give the product, which was used in the next step without isolation. ^{31}P NMR (CDCl_3): δ 60.29 (t, 1P, $J = 65.97\text{Hz}$).


Preparation of (2-methylphenyl) $_2$ phosphine chloride



10 1-Bromotoluene (1.3 mL, 10.7 mmol) was added to a mixture of magnesium turnings (0.3 g, 12.8 mmol) in anhydrous THF (20 ml). A vigorous reaction ensued. Once the reaction exotherm had dissipated, the reaction mixture was used for the next step.


The Grignard reagent (separated from excess Mg) was incrementally added to a solution of PCl_3 (0.4 mL, 5.3 mmol) in anhydrous THF (30 ml) at $-78\text{ }^\circ\text{C}$. After addition was complete, the suspension was stirred at room temperature for a further 15 min after which the reaction was complete as judged by ^{31}P NMR. The product was used in the next step without isolation. ^{31}P NMR (CDCl_3): δ 73.1 (s)

20


Preparation of 7-bromobenzofuran

7-bromobenzofuran was prepared as described in Heterocycl. Commun., Vol. 16(4-6), pp. 249-252, 2010 by Klenk. J. et. al.

5

Preparation of 1-benzofuran-7-yl magnesium bromide

To magnesium turnings (450 mg, 18.8 mmol) in THF (5 mL) was added 1 iodine crystal and a few drops of 7-bromobenzofuran. A vigorous reaction
10 ensued. The remaining 7-bromo-benzofuran (3.6 g, 18.4 mmol) in THF (10 ml) was added dropwise. The reaction mixture was left to reflux by itself. Once the reaction exotherm had dissipated, the reaction mixture was heated under reflux for about 15 minutes to yield the required Grignard reagent.

15 Preparation of (1-benzofuran-7-yl)(phenyl)phosphine chloride


The Grignard reagent benzofuryl magnesium bromide (prepared as described above) (10.8 mmol) was slowly added to a pre-cooled solution of PhPCl_2 (1.5

- 34 -

ml, 10.8 mmol) in anhydrous THF (20 ml) at RT. After addition was complete, the suspension was stirred at room temperature for a further 1h after which the reaction was complete as judged by ^{31}P NMR. The product was used in the next step without isolation. ^{31}P NMR δ 79.4 (s), 67.0 (s).


5

Preparation of 10-chloro-9-oxa-10-phospha-phenanthrene




A mixture of PCl_3 (20 mL, 31.5 g, 0.23 mol) and 2-phenylphenol (31.2 g, 0.18 mol) was heated gradually to 150 °C over a period of 5 hour with continuous stirring. A slow sweep of nitrogen was maintained to facilitate the ready removal of evolved hydrogen chloride. The reaction mixture was cooled to 25 °C, followed by the addition of 0.20 g of anhydrous ZnCl_2 . The temperature of the reaction mixture was increased to 160 °C over a period of 3 hours and then cooled to 25 °C. The reaction mixture was extracted 3 times with 250 mL of diethyl ether and the solvent removed *in vacuo* to yield the pure product. ^{31}P NMR; δ (CDCl_3): 133.41 (s).

- 35 -

Preparation of 10-chlorophenoxaphosphine

To a solution of diphenyl ether (3 g, 17.6 mmol) in THF (30 mL) was added a solution of *n*-BuLi (15.5 mL, 38.7 mmol, 2.5 M in hexane) at -40 °C. The reaction mixture was allowed to warm to room temperature and stirred for 24 h. The reaction mixture was cooled to -78 °C and Et₂NPCl₂ (4.3 mL, 21.1 mmol) in THF (10 ml) slowly added. The reaction mixture was allowed to warm to room temperature and was stirred for another 3 h. The solvents were removed *in vacuo* and the yellow oil was dissolved in 50 mL of diethyl ether. Dry HCl in diethyl ether was added to the solution at room temperature and the reaction stirred under nitrogen flow for a further 15 min. The ammonium salt was removed by filtration on a celite pad. The solvent was removed *in vacuo* to leave the product as a yellow oil. ³¹P NMR; δ (CDCl₃): 33.86 (s).

15 Preparation of (dibenzophosphol-5-yl)N(*i*-propyl)P(2-methylphenyl)₂


PNH formation: iso-Propylamine (0.52 mL, 6.0 mmol) and Et₃N (0.83 mL, 6.0 mmol) were added to the crude 5-chlorodibenzophosphole (1.1 g, 5.0 mmol) [prepared as described above] in diethyl ether (30 ml). The reaction mixture was stirred at room temperature until complete formation of the PNH intermediate as judged by ³¹P NMR analysis. The volatiles were removed *in*

vacuo. Ether (50 ml) was added and the resultant mixture filtered to give the ether solution of the desired PNH product in reasonable purity [(by ^{31}P NMR analysis)]. The solvent was removed *in vacuo* to give the PNH compound, (dibenzophosphol-5-yl)N(i-propyl)H. ^{31}P NMR (CDCl_3): δ 33.39 (s).

- 5 PNP formation: The PNH (dibenzophosphol-5-yl)N(i-propyl)H (0.58 g, 2.4 mmol) was re-dissolved in DCM (10 ml). Et_3N (0.68 ml, 4.9 mmol) was added, followed by incremental addition of (2-methylphenyl) $_2$ phosphinechloride (0.72 g, 2.9 mmol) [prepared as described above] at room temperature. After complete conversion of the PNH (judged by ^{31}P NMR analysis) to the PNP, the
 10 solvent was removed *in vacuo* from the post reaction mixture. Ether (100 ml) was added and the resultant mixture was filtered through a short activated alumina column. Filtration was repeated until a pure compound was obtained. The solvent was evaporated to give the desired PNP product. ^{31}P NMR (CDCl_3): δ 47.18 (s, br), 22.84 (s, br).

15


Preparation of (dibenzophosphol-5-yl)N(i-butyl)P(2-methylphenyl) $_2$



- PNH formation: (dibenzophosphol-5-yl)N(i-butyl)H was prepared as described above for (dibenzophosphol-5-yl)N(i-propyl)H except that iso-butylamine was
 20 used instead of iso-propylamine. ^{31}P NMR (CDCl_3): 37.21 (s).

- PNP formation: The PNP compound was prepared from the reaction of (dibenzophosphol-5-yl)N(i-butyl)H (1.0 g, 3.9 mmol), Et_3N (1.08 ml, 7.8 mmol), and (2-methylphenyl) $_2$ phosphine-chloride (1.2 g, 4.7 mmol) following the typical
 25 procedure described for the preparation of (dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl) $_2$ above. ^{31}P NMR (CDCl_3): δ 73.41 (s), 65.58 (s).


Preparation of (dibenzophosphol-5-yl)N(i-propyl)P(2-methoxyphenyl)₂



PNH formation: (dibenzophosphol-5-yl)N(i-propyl)H was prepared as described
 5 above. ³¹P NMR (CDCl₃): 33.39 (s).

PNP formation: The PNP compound was prepared from the reaction of
 (dibenzophosphol-5-yl)N(i-propyl)H (1.0 g, 3.9 mmol), Et₃N (1.08 ml, 7.8 mmol)
 and (2-methoxyphenyl)₂phosphine chloride (1.3 g, 4.7 mmol) [prepared as
 10 described above] following the typical procedure described for the preparation
 of (dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl)₂ above. ³¹P NMR
 (CDCl₃): δ 48.052 (br. s), 17.19 (br. s).

Preparation of (dibenzophosphol-5-yl)N(n-butyl)P(2-methoxyphenyl)₂



15


PNH formation: (dibenzophosphol-5-yl)N(n-butyl)H was prepared as described
 above for (dibenzophosphol-5-yl)N(i-propyl)H except that n-butylamine was
 used instead of iso-propylamine. ³¹P NMR (CDCl₃): 37.2 (s).

20 PNP formation: The PNP compound was prepared from the reaction of
 (dibenzophosphol-5-yl)N(n-butyl)H (1.0 g, 3.9 mmol), Et₃N (1.08 ml, 7.8 mmol),

and (2-methoxyphenyl)₂phosphine-chloride (1.3 g, 4.7 mmol) [prepared as described above] following the typical procedure described for the preparation of (dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl)₂ above. ³¹P NMR (CDCl₃): δ 53.8 (d, J = 142.00 Hz), 48.8 (d, J = 140.55 Hz).

5

Preparation of (dibenzophosphol-5-yl)N(i-propyl)P(2-fluorophenyl)₂




PNH formation: (dibenzophosphol-5-yl)N(i-propyl)H was prepared as described above. ³¹P NMR (CDCl₃): 33.39 (s).

10

PNP formation: The PNP compound was prepared from the reaction of (dibenzophosphol-5-yl)N(i-propyl)H (1.5 g, 7.0 mmol), Et₃N (1.5 ml, 10.5 mmol), and (2-fluorophenyl)₂phosphine chloride (2 g, 7.7 mmol) [prepared as described above] following the typical procedure described for the preparation of (dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl)₂ above. ³¹P NMR (CDCl₃): δ 49.64 (br s), 15.92 (br s).

15

Preparation of (dibenzophosphol-5-yl)N(n-butyl)P(1-benzofuran-7-yl)(phenyl)




- 39 -

PNH formation: (dibenzophosphol-5-yl)N(n-butyl)H was prepared as described above for (dibenzophosphol-5-yl)N(i-propyl)H except that n-butylamine was used instead of iso-propylamine. ^{31}P NMR (CDCl_3): 37.2 (s).

- 5 PNP formation: The PNP compound was prepared from the reaction of (dibenzophosphol-5-yl)-N(n-butyl)H (1.5 g, 5.9 mmol), Et_3N (1.1 ml, 8.3 mmol), and (1-benzofuran-7-yl)(phenyl)-phosphinechloride (1.8 g, 7.1 mmol) following the typical procedure described for the preparation of (dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl) $_2$ above. ^{31}P NMR (CDCl_3): δ 55.85 (d, J = 93.5
- 10 Hz), 53.92 (d, J = 94.2 Hz).

Preparation of (9-oxa-10-phosphaphenanthren-10-yl)N(i-propyl)P(2-methoxyphenyl) $_2$




- 15 PNH formation: iso-Propylamine (0.7 ml, 7.7 mmol) and Et_3N (1.1 ml, 7.7 mmol) were added to the crude 10-chloro-9-oxa-10-phosphaphenanthrene (1.5 g, 6.4 mmol) [prepared as described above] in diethyl ether (30 ml). The reaction mixture was stirred at room temperature until complete formation of the PNH intermediate as judged by ^{31}P NMR analysis. The volatiles were
- 20 removed *in vacuo*. Ether (50 ml) was added and the resultant mixture filtered to give the ether solution of the desired PNH product in reasonable purity [by ^{31}P NMR analysis]. The solvent was removed *in vacuo* to give the PNH compound, (10-oxa-9-phosphaphenanthren-9-yl)N(i-propyl)H. ^{31}P NMR (CDCl_3): δ 75.20 (s).
- PNP formation: The PNH (10-oxa-9-phosphaphenanthren-9-yl)N(i-propyl)H (1.6
- 25 g, 6.4 mmol) was re-dissolved in DCM (10 ml). Et_3N (1.1 ml, 7.7 mmol) was

- 40 -

added, followed by incremental addition of (2-methoxyphenyl)₂phosphine chloride (2.2 g, 7.7 mmol) [prepared as described above] at room temperature. After complete conversion of the PNH (judged by ³¹P NMR analysis) to the PNP, the solvent was removed *in vacuo* from the post reaction mixture. Ether
 5 (100 ml) was added and the resultant mixture was filtered through a short activated alumina column. Filtration was repeated until a pure compound was obtained. The solvent was evaporated to give the desired PNP product. ³¹P NMR (CDCl₃): δ 93.36 (s), 20.06 (s).

10 Preparation of (phenoxaphosphin-10-yl)N(n-butyl)P(phenyl)₂




PNH formation: n-Butylamine (1.1 ml, 10.2 mmol) and Et₃N (1.8 ml, 12.8 mmol) were added to the crude 10-chlorophenoxaphosphine (2 g, 8.5 mmol) [prepared as described above] in diethyl ether (30 ml). The reaction mixture
 15 was stirred at room temperature until complete formation of the PNH intermediate as judged by ³¹P NMR analysis. The volatiles were removed *in vacuo*. Ether (50 ml) was added and the resultant mixture filtered to give the ether solution of the desired PNH product in reasonable purity [(by ³¹P NMR analysis)]. The solvent was removed *in vacuo* to give the PNH compound,
 20 (phenoxaphosphin-10-yl)N(n-butyl)H. ³¹P NMR (CDCl₃): δ -3.44 (s).

PNP formation: The PNH (phenoxaphosphin-10-yl)N(n-butyl)H (1.5 g, 5.5 mmol) was re-dissolved in DCM (10 ml). Et₃N (1.2 ml, 8.3 mmol) was added, followed by incremental addition of Ph₂PCl (1.2 ml, 6.6 mmol) at room temperature. After complete conversion of the PNH (judged by ³¹P NMR

analysis) to the PNP, the solvent was removed *in vacuo* from the post reaction mixture. Ether (100 ml) was added and the resultant mixture was filtered through a short activated alumina column. Filtration was repeated until a pure compound was obtained. The solvent was evaporated to give the desired PNP product. ^{31}P NMR (CDCl_3): δ 76.32 (d, $J = 30.5$ Hz), 50.36 (d, $J = 29.8$ Hz).


Preparation of (phenoxaphosphin-10-yl)N(n-butyl)P(2-fluorophenyl) $_2$



PNH formation: (phenoxaphosphin-10-yl)N(n-butyl)H was prepared as described above. ^{31}P NMR (CDCl_3): δ -3.44 (s).

PNP formation: The PNP compound was prepared from the reaction of (phenoxaphosphin-10-yl)N(n-butyl)H (1.7 g, 6.4 mmol), Et_3N (1.2 ml, 8.3 mmol), and (2-fluorophenyl) $_2$ phosphine chloride (1.6 g, 6.4 mmol) [prepared as described above] following the typical procedure described for the preparation of (phenoxaphosphin-10-yl)N(n-butyl)P(phenyl) $_2$ above. ^{31}P NMR (CDCl_3): δ 44.09 (dt, $J = 233.7$ Hz and $J = 46.5$ Hz), 15.25 (d, $J = 233.7$ Hz).


Preparation of (phenyl) $_2$ PN(n-butyl)P(phenyl) $_2$



This compound was prepared from the reaction of n-butylamine (1.0 g, 13.7 mmol), Et₃N (5.54 g, 54.7 mmol), Ph₂PCl (7.59 g, 41.0 mmol), following a procedure described in *Synthesis*, 2007, 24, 3863. ³¹P NMR (CDCl₃): δ 62.5 (s).

5


Preparation of (phenyl)₂PN(n-butyl)P(2-methoxyphenyl)₂



PNH formation: An ethereal solution of n-butylamine (1.5 g, 20.1 mmol) and Et₃N (2.0 g, 20.1 mmol) at ~0 °C was added to an ethereal solution of (2-methoxyphenyl)₂PCl (5.6 g, 20.1 mmol) [prepared as described above]. A white precipitate formed immediately. The reaction mixture was left to stir for 1hr followed by filtration of the precipitate and removal of the solvent *in vacuo* to give (2-methoxyphenyl)₂PN(n-butyl)H. ³¹P NMR (CDCl₃): δ 26.37 (s).


PNP formation: To a DCM (3 ml) solution of (2-methoxyphenyl)₂PN(n-butyl)H (2.4 g, 8.5 mmol) and Et₃N (1.4 ml, 10.2 mmol) was added ClPPh₂ (1.58 g, 8.5 mmol). The reaction was left to stir overnight. The solvent was then removed *in vacuo* and the residue re-slurried in ether (100ml), followed by filtration of the solids and removal of the solvent *in vacuo* to give the desired PNP product. ³¹P NMR; δ (CDCl₃): 57.74 (br s), 43.85 (d, J = 49.89 Hz).

20

Preparation of (phenyl)₂PN(i-propyl)P(2-methoxyphenyl)₂

PNH formation: (2-methoxyphenyl)₂PN(i-propyl)H was prepared as described above for (2-methoxyphenyl)₂PN(n-butyl)H except that i-propyl amine was used instead of n-butyl amine. ³¹P NMR (CDCl₃): δ 19.02 (s).


PNP formation: The PNP compound was prepared from the reaction of (2-methoxyphenyl)₂PN(i-propyl)H (1.5 g, 4.9 mmol), Et₃N (1.4 ml, 9.9 mmol), and ClPPh₂ (0.9 ml, 4.9 mmol) following the typical procedure described for preparation of (phenyl)₂PN(n-butyl)P(2-methoxyphenyl)₂ above. ³¹P NMR (CDCl₃): δ 54.66 (br s), 21.79 (br, s).

Preparation of (phenyl)₂PN(i-propyl)P(2-fluorophenyl)₂

PNH formation: An ethereal solution of iso-propylamine (0.5 g, 8.46 mmol) and Et₃N (2.3 ml, 16.9 mmol) at ~0 °C was added to an ethereal solution of (2-fluorophenyl)₂PCl (1.81g, 7.1 mmol) [prepared as described above]. A white precipitate formed immediately. The reaction mixture was left to stir for 1hr followed by filtration of the precipitate and removal of the solvent *in vacuo* to give (2-fluorophenyl)₂PN(i-propyl)H. ³¹P NMR (CDCl₃): δ 15.7 (t, J = 33,4 Hz).


PNP formation: To a DCM (3 ml) solution of (2-fluorophenyl)₂PN(i-propyl)H (0.8 g, 2.9 mmol) and Et₃N (0.56g, 5.9 mmol) was added ClPPh₂ (0.54 ml, 2.9 mmol). The reaction was left to stir overnight. The solvent was then removed *in vacuo* and the residue re-slurried in ether (100ml), followed by filtration of the solids and removal of the solvent *in vacuo* to give the desired PNP product. ³¹P NMR (CDCl₃): δ 52.5 (br s), 22.6 (br s).

Preparation of (phenyl)₂PN(n-butyl)P(2-fluorophenyl)₂



10 PNH formation: (2-fluorophenyl)₂PN(n-butyl)H was prepared as described above for (2-fluorophenyl)₂PN(i-propyl)H except that n-butyl amine was used instead of iso-propyl amine.


PNP formation: The PNP compound was prepared from the reaction of (2-fluorophenyl)₂PN(n-butyl)H (1.5 g, 4.8 mmol), Et₃N (1.3 ml, 9.5 mmol), and
 15 ClPPh₂ (0.9 ml, 4.8 mmol) following the typical procedure described for preparation of (phenyl)₂PN(i-propyl)P(2-fluorophenyl)₂ above. ³¹P NMR (CDCl₃): δ 63.2 (d, J = 41.6 Hz), 39.0 (m).

Preparation of (phenyl)₂PN(i-propyl)P(2-methylphenyl)₂

PNH formation: An ethereal solution of iso-propylamine (1.5 g, 25.4 mmol) and Et₃N (2.0 g, 30.5 mmol) at ~0 °C was added to an ethereal solution of (2-methylphenyl)₂PCl (6.3 g, 25.4 mmol) [prepared as described above]. A white precipitate formed immediately. The reaction mixture was left to stir for 1hr followed by filtration of the precipitate and removal of the solvent *in vacuo* to give (2-methylphenyl)₂PN(i-propyl)H.

PNP formation: To a DCM (3 ml) solution of (2-methylphenyl)₂PN(i-propyl)H (2.4 g, 8.5 mmol) and Et₃N (1.4 ml, 10.2 mmol) was added ClPPh₂ (1.58 g, 8.5 mmol). The reaction was left to stir overnight. The solvent was then removed *in vacuo* and the residue re-slurried in ether (100ml), followed by filtration of the solids and removal of the solvent *in vacuo* to give the desired PNP product. ³¹P NMR (CDCl₃): δ 52.9 (s, br), 26.2 (s, br).

15


Preparation of (phenyl)₂PN(i-butyl)P(2-methylphenyl)₂

PNH formation: (2-methylphenyl)₂PN(i-butyl)H was prepared as described above for (2-methylphenyl)₂PN(i-butyl)H, except that iso-butyl amine was used instead of iso-propyl amine.

20

PNP formation: The PNP compound was prepared from the reaction of (2-methylphenyl)₂-PN(i-butyl)H (1.5 g, 4.7 mmol), Et₃N (0.9 ml, 6.6 mmol), and ClPPh₂ (0.9 ml, 4.7 mmol) following the typical procedure described for the preparation of (phenyl)₂PN(i-propyl)P(2-methylphenyl)₂ above. ³¹P NMR (CDCl₃): δ 62.5 (br s), 54.9 (br s).

Preparation of (phenyl)₂PN(n-Hexyl)P(1-benzofuran-7-yl)(phenyl)



PNH formation: n-Hexylamine (0.95 mL, 7.2 mmol) and Et₃N (1.0 mL, 7.2 mmol) were added to the crude (1-benzofuran-7-yl)(phenyl)phosphine chloride (0.90 g, 3.6 mmol) [prepared as described above] in diethyl ether (30 ml). The reaction mixture was stirred at room temperature until complete formation of the PNH intermediate as judged by ³¹P NMR analysis. The volatiles were removed *in vacuo*. Ether (50 ml) was added and the resultant mixture filtered to give the ether solution of the desired PNH product in reasonable purity [by ³¹P NMR analysis]. The solvent was removed *in vacuo* to give the PNH compound, (1-benzofuran-7-yl)(phenyl)PN(n-Hex)H.

PNP formation: The PNH (1-benzofuran-7-yl)(phenyl)PN(n-Hex)H (0.80 g, 2.4 mmol) was re-dissolved in DCM (10 ml). Et₃N (0.5 g, 4.9 mmol) was added, followed by incremental addition of Ph₂PCl (1.1 g, 4.9 mmol) at room temperature. After complete conversion of the PNH (judged by ³¹P NMR analysis) to the PNP, the solvent was removed from the post reaction mixture. Ether (100 ml) was added and the resultant mixture was filtered through a short activated alumina column. Filtration was repeated until a pure compound

- 47 -

was obtained. The solvent was evaporated to give the desired PNP product.
 ^{31}P NMR (CDCl_3): δ 62.9 (d, $J = 37.6$ Hz), 50.5 (d, $J = 37.6$ Hz).

5 Example 1. Ethylene tetramerisation with (dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl) $_2$ at 60 °C and 45bar

A 600 ml stainless steel reactor was heated to 120°C for 30 minutes under vacuum, backfilled with N_2 and then cooled to 60°C. The reactor was charged with 2,2,4-trimethylpentane (TMP) (100ml), and heated to 60°C. Separately, MMAO-3A (2.4 mmol Al) was added to a mixture of $\text{Cr}(\text{acac})_3$ (2.5 μmol) and
10 (dibenzophosphol-5-yl)N(i-propyl)P(2-methylphenyl) $_2$ (2.5 μmol) in cyclohexane (5ml). This mixture was then transferred to the reactor. The reactor was pressurised with ethylene (45 bar), and stirred (1300 r.p.m.) with a gas entraining stirrer. The temperature in the reactor increased to 62-65°C, at
15 which point the reactor was cooled by means of an internal cooling coil to maintain a constant temperature of 60°C throughout the run. The reaction pressure was kept constant throughout the run by feeding ethylene on demand, and the consumption of ethylene was monitored via a flow meter. At
20 the conclusion of the run after 34.3 minutes and 160g total ethylene uptake (including the ethylene required to pressurise the reactor), the reactor was rapidly cooled to 5°C, and depressurised. A weighed mass of nonane was added as an internal standard, and a small sample was taken for GC-FID analysis. The polymer by-product was collected by filtration, dried overnight and weighed. The selectivity and activity were then calculated from the GC data and polymer mass. The results are shown in Table 1.

25

Example 2 Ethylene tetramerisation with (dibenzophosphol-5-yl)N(i-butyl)P(2-methylphenyl) $_2$ at 60 °C and 45 bar

The procedure of example 1 was followed, except that the ligand (dibenzophosphol-5-yl)N(i-butyl)P(2-methylphenyl) $_2$ was used, and the reaction

was terminated after 61 minutes and 160 g ethylene uptake. The results are shown in Table 1.

5 Example 3. Ethylene tetramerisation with (dibenzophosphol-5-yl)N(n-butyl)P(2-methoxyphenyl)₂ at 60°C and 45 bar

The procedure of example 1 was followed, except that the ligand (dibenzophosphol-5-yl)N(n-butyl)P(2-methoxyphenyl)₂ was used, and the reaction was terminated after 58 minutes and 160 g ethylene uptake. The results are shown in Table 1.

10

Example 4. Ethylene tetramerisation with (dibenzophosphol-5-yl)N(i-propyl)P(2-methoxyphenyl)₂ at 60°C and 45 bar

15 The procedure of example 1 was followed, except that the ligand (dibenzophosphol-5-yl)N(i-propyl)P(2-methoxyphenyl)₂ was used, and the reaction was terminated after 67 minutes and 160 g ethylene uptake. The results are shown in Table 1.

Example 5. Ethylene tetramerisation with (dibenzophosphol-5-yl)N(n-butyl)P(2-methoxyphenyl)₂ at 100°C and 45 bar

20 The procedure of example 1 was followed, except that the ligand (dibenzophosphol-5-yl)N(n-butyl)P(2-methoxyphenyl)₂ was used, 200ml of TMP was used, the reaction temperature was maintained at 100°C and the reaction was terminated after 76 minutes and 150g ethylene uptake. The results are shown in Table 1.

25

Example 6. Ethylene tetramerisation with (dibenzophosphol-5-yl)N(i-propyl)P(2-fluorophenyl)₂ at 100°C and 45 bar.

The procedure of example 1 was followed, except the ligand (dibenzophosphol-5-yl)N(i-propyl)P(2-fluorophenyl)₂ was used, 200ml of TMP was used, the reaction temperature was maintained at 100°C, and the reaction was terminated after 54 minutes and 150g ethylene uptake. The results are shown in Table 1.

Example 7. Ethylene tetramerisation with (dibenzophosphol-5-yl)N(n-butyl)P(1-benzofuran-7-yl)(phenyl) at 100°C and 45 bar

The procedure of example 1 was followed, except that the ligand (dibenzophosphol-5-yl)N(n-butyl)P(1-benzofuran-7-yl)(phenyl) was used, 200ml of TMP was used, the reaction temperature was maintained at 100°C, and the reaction was terminated after 42 minutes and 150 g ethylene uptake. The results are shown in Table 1.

Example 8. Ethylene tetramerisation with (9-oxa-10-phosphaphenanthren-10-yl)N(i-propyl)P(2-methoxyphenyl)₂ at 60°C and 45 bar

The procedure of example 1 was followed, except that the ligand phosphaphenanthren-10-yl)N(i-propyl)P(2-methoxyphenyl)₂ was used, and the reaction was terminated after 77.4 minutes and 160 g ethylene uptake. The results are shown in Table 2.

Example 9. Ethylene tetramerisation with (phenoxaphosphin-10-yl)N(n-butyl)P(phenyl)₂ at 60°C and 45 bar

The procedure of example 1 was followed, except that the ligand (phenoxaphosphin-10-yl)N(n-butyl)P(phenyl)₂ was used, and the reaction was terminated after 92 minutes and 150 g ethylene uptake. The results are shown in Table 3.

Example 10. Ethylene tetramerisation with (phenoxaphosphin-10-yl)N(n-butyl)P(2-fluorophenyl)₂ at 60°C and 45 bar

The procedure of example 1 was followed, except that the ligand
5 (phenoxaphosphin-10-yl)N(n-butyl)P(2-fluorophenyl)₂ was used, and the reaction was terminated after 24 minutes and 160 g ethylene uptake. The results are shown in Table 3.

Example 11. Ethylene tetramerisation with (phenoxaphosphin-10-yl)N(n-butyl)P(2-fluorophenyl)₂ at 100°C and 45 bar.

The procedure of example 1 was followed, except the ligand
10 (phenoxaphosphin-10-yl)N(n-butyl)P(2-fluorophenyl)₂ was used, 200ml of TMP was used, the reaction temperature was maintained at 100°C, and the reaction was terminated after 25 minutes and 97g ethylene uptake. The results are
15 shown in Table 3.

Comparative example 1. Ethylene tetramerisation with (phenyl)₂PN(i-propyl)P(2-methylphenyl)₂ at 60°C and 45 bar

The procedure of example 1 was followed, except that the ligand
20 (phenyl)₂PN(i-propyl)P(2-methylphenyl)₂ was used, and the reaction was terminated after 18 minutes and 160 g ethylene uptake. The results are shown in Table 1.

Comparative example 2. Ethylene tetramerisation with (phenyl)₂PN(i-butyl)P(2-methylphenyl)₂ at 60°C and 45 bar

The procedure of example 1 was followed, except that the ligand
25 (phenyl)₂PN(i-butyl)P(2-methylphenyl)₂ was used, and the reaction was

terminated after 11 minutes and 160 g ethylene uptake. The results are shown in Table 1.

5 Comparative example 3. Ethylene tetramerisation with (phenyl)₂PN(n-butyl)P(2-methoxyphenyl)₂ at 60°C and 45 bar

The procedure of example 1 was followed, except that the ligand (phenyl)₂PN(n-butyl)P(2-methoxyphenyl)₂ was used, and the reaction was terminated after 78 minutes and 160 g ethylene uptake. The results are shown in Table 1.

10

Comparative example 4. Ethylene tetramerisation with (phenyl)₂PN(i-propyl)P(2-methoxyphenyl)₂ at 60°C and 45 bar

15 The procedure of example 1 was followed, except that the ligand (phenyl)₂PN(i-propyl)P(2-methoxyphenyl)₂ was used, and the reaction was terminated after 60 minutes and 88 g ethylene uptake. The results are shown in Table 1.

Comparative example 5. Ethylene tetramerisation with (phenyl)₂PN(n-butyl)P(2-methoxyphenyl)₂ at 100°C and 45 bar

20 The procedure of example 1 was followed, except the ligand (phenyl)₂PN(n-butyl)P(2-methoxyphenyl)₂ was used, 200ml of TMP was used, the reaction temperature was maintained at 100°C, and the reaction was terminated after 27.1 minutes and 153g ethylene uptake. The results are shown in Table 1.

25 Comparative example 6. Ethylene tetramerisation with (phenyl)₂PN(i-propyl)P(2-fluorophenyl)₂ at 100°C and 45 bar

The procedure of example 1 was followed, except the ligand (phenyl)₂PN(i-propyl)P(2-fluorophenyl)₂ was used, 200ml of TMP was used, the reaction temperature was maintained at 100°C, and the reaction was terminated after 15 minutes and 150g ethylene uptake. The results are shown in Table 1.

5

Comparative example 7. Ethylene tetramerisation with (phenyl)₂PN(n-butyl)P(1-benzofuran-7-yl)(phenyl) at 100°C and 45 bar

The procedure of example 1 was followed, except the ligand (phenyl)₂PN(n-butyl)P(1-benzofuran-7-yl)(phenyl) was used, 200ml of TMP was used, the
10 reaction temperature was maintained at 100°C, and the reaction was terminated after 11 minutes and 150g ethylene uptake. The results are shown in Table 1.

Comparative example 8. Ethylene tetramerisation with (phenyl)₂PN(n-butyl)P(phenyl)₂ at 60°C and 45 bar

15

The procedure of example 1 was followed, except that the ligand (phenyl)₂PN(n-butyl)P(2-phenyl)₂ was used, and the reaction was terminated after 46 minutes and 160 g ethylene uptake. The results are shown in Table 3.

Comparative example 9. Ethylene tetramerisation with (phenyl)₂PN(n-butyl)P(2-fluorophenyl)₂ at 60°C and 45 bar

20

The procedure of example 1 was followed, except that the ligand (phenyl)₂PN(n-butyl)P(2-fluorophenylphenyl)₂ was used, and the reaction was terminated after 21.5 minutes and 160 g ethylene uptake. The results are
25 shown in Table 3.

Comparative example 10. Ethylene tetramerisation with (phenyl)₂PN(n-butyl)P(2-fluorophenylphenyl)₂ at 100°C and 45 bar

The procedure of example 1 was followed, except that ligand (phenyl)₂PN(n-butyl)P(2-fluorophenylphenyl)₂ was used, 200ml of TMP was used, the reaction
5 temperature was maintained at 100°C, and the reaction was terminated after only 45 minutes and 200g ethylene uptake (including the ethylene required to pressurise the reactor). The results are shown in Table 3.

Table 1.

Example	Ligand	Temp. (°C), Press. (bar)	Activity ($\times 10^6$ g/Cr/h)	Liquid Product selectivity (wt % of oligomer products)					1-octene : 1-hexene ratio	Total product selectivity (wt %)
				1-hexene %	C ₆ cyclics %	1-octene %	1-hexene + 1-octene %	C ₁₀₋₃₀ %		
1	(dibenzophosphol-5-yl)N(i-propyl)P(2-MePh) ₂	60, 45	1.65	15.6	2.3	68.1	83.6	13.0	4.40	1.68
Comp 1	Ph ₂ PN(i-propyl)P(2-MePh) ₂	60, 45	2.70	35.9	1.4	54.8	90.9	7.4	1.52	1.1
2	(dibenzophosphol-5-yl)N(i-butyl)P(2-MePh) ₂	60, 45	1.00	10.8	3.5	65.9	76.6	17.9	6.08	13.06

Comp 2	Ph ₂ PN(<i>i</i> -butyl)P(2-MePh) ₂	60, 45	5.03	30.0	3.4	61.0	88.0	8.3	2.26	0.49
3	(dibenzophosphol-5-yl)N(<i>n</i> -butyl)P(2-OMePh) ₂	60, 45	0.57	22.3	1.2	59.1	81.5	13.0	2.65	3.48
Comp 3	Ph ₂ PN(<i>n</i> -butyl)P(2-OMePh) ₂	60, 45	0.73	41.8	2.1	40.4	82.3	12.6	0.96	1.65
4	(dibenzophosphol-5-yl)PN(<i>i</i> -propyl)P(2-OMePh) ₂	60, 45	0.56	34.2	0.6	53.0	87.2	10.2	1.55	1.16
Comp 4	Ph ₂ PN(<i>i</i> -propyl)P(2-OMePh) ₂	60, 45	0.31	53.5	1.0	31.5	85.0	12.6	0.59	7.90
5	(dibenzophosphol-5-yl)PN(<i>n</i> -butyl)P(2-OMePh) ₂	100, 45	0.63	59.5	1.2	31.9	91.4	6.2	0.54	1.00
Comp 5	Ph ₂ PN(<i>n</i> -butyl)P(2-OMePh) ₂	100, 45	1.72	75.1	0.8	15.6	90.8	6.7	0.21	0.71
6	(dibenzophosphol-5-yl)N(<i>i</i> -propyl)P(2-FPh) ₂	100, 45	0.88	26.5	2.7	56.3	82.7	12.9	2.13	5.1

Comp 6	Ph ₂ PN(i-propyl)P(2- FPh) ₂	100, 45	3.72	47.1	1.1	33.8	81.0	17.1	0.72	1.41
7	(dibenzophosphol-5- yl)N(n-butyl)P(1-benzo- furan-7-yl)(phenyl)	100, 45	1.11	43.9	1.9	44.9	88.8	7.4	1.02	1.51
Comp 7	(phenyl) ₂ PN(n- hexyl)P(1-benzofuran- 7-yl)(phenyl)	100, 45	2.29	56.0	3.0	33.3	89.3	6.7	0.59	0.63

Table 2.

Examp le	Ligand	Temp. (°C), Press. (bar)	Activit y ($\times 10^6$ g/gCr/h)	Liquid Product selectivity (wt % of oligomer products)					1- octene : 1- hexene ratio	Total product selectivi ty (wt %)
				1- hexene %	C ₆ cyclics %	1- octene %	1- hexene + 1- octene %	C _{10⁺} %		
8	(9-oxa-10-phospha- phenanthren-10-yl)N(i- propyl)P(2-OMePh) ₂	60, 45	0.60	39.6	0.5	49.6	89.3	9.1	1.3	2.61
Comp 4	Ph ₂ PN(i-propyl)P(2- OMePh) ₂	60, 45	0.31	53.5	1.0	31.5	85.0	12.6	0.59	7.90

Table 3.


Examp le	Ligand	Temp. (°C), Press. (bar)	Activit y ($\times 10^6$ g/gCr/h)	Liquid Product selectivity (wt % of oligomer products)					1- octene : 1- hexene ratio	Total product selectivi ty (wt %)
				1- hexene %	C ₆ cyclics %	1- octene %	1- hexene + 1- octene %	C _{10- 30} %		
9	(phenoxaphosphin-10- yl)N(n-butyl)PPh ₂	60, 45	0.43	11.0	4.7	66.7	77.6	14.8	6.05	1.58
Comp 8	Ph ₂ PN(n-butyl)PPh ₂	60, 45	1.23	6.7	9.2	60.8	67.5	19.3	9.07	1.69
10	(phenoxaphosphin-10-	60, 45	2.32	10.0	2.4	66.8	76.9	19.5	6.7	4.85

CLAIMS:

1. A process for the tetramerisation of ethylene, the process including contacting ethylene with a catalyst under ethylene oligomerisation conditions, said catalyst comprising:

5

- i) a source of chromium;
- ii) a ligating compound of the formula



10

wherein A is selected from the group consisting of nitrogen, phosphorus, and oxygen;


X is a linking group between A and Y;

m is independently 1 or 2;

15

R¹ is a hydrogen, a hydrocarbonyl group, an organoheteryl group or a heterohydrocarbonyl group with each R¹ being the same or being different where m is 2; and

Y is an optionally substituted group that can be represented as



20

such that

P is a phosphorous atom and bonds to X; and

L₁ and L₂ are linkers selected from the group comprising a covalent bond and an optionally substituted single atom bonded to both of the linked carbon or phosphorous atoms; and

25

iii) optionally a catalyst activator or combination of catalyst activators.

2. The process as claimed in claim 1, wherein A is selected from the group
5 consisting of nitrogen and phosphorous.

3. The process as claimed in claim 1 or claim 2, wherein R¹ is a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group.

10 4. The process as claimed in claim 1, wherein R¹ is an aromatic, including a heteroaromatic, group directly bonded to A.

5. The process as claimed in claim 1, wherein R¹ is an optionally substituted phenyl group.


15

6. A process for the tetramerisation of ethylene, the process including contacting ethylene with a catalyst under ethylene oligomerisation conditions, said catalyst comprising:

- 20 i) a source of chromium;
ii) a ligating compound of the formula



wherein P is a phosphorous atom;
25 X is a linking group between P and Y;
R¹ and R² are independently a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group; and
Y is an optionally substituted group that can be represented as



- such that P is a phosphorous atom which bonds to X; and
L₁ and L₂ are linkers selected from the group consisting
of a covalent bond and an optionally substituted single
atom bonded to both of the linked carbon or
phosphorous atoms; and
- 5 iii) optionally a catalyst activator or combination of catalyst
activators.
- 10 7. The process as claimed in claim 6, wherein R¹ and R² are
independently a hydrocarbyl group or a heterohydrocarbyl group.
8. The process as claimed in claim 6, wherein both R¹ and R² are
aromatic, including heteroaromatic, groups directly bonded to P.
- 15 9. The process as claimed in claim 6, wherein both R¹ and R² are
optionally substituted phenyl groups.
- 20 10. The process as claimed in claim 6, wherein L₁ and L₂ are selected
from the group consisting of a covalent bond, a heteroatom, a substituted
heteroatom, -C(=O)-, and -CR³R⁴-, where R³ and R⁴ are independently a
hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl
group.

11. The process as claimed in claim 6, wherein L_1 and L_2 are selected from the group consisting of a covalent bond, -O-, -S-, -NR₃-, -P(=O)R³-, -P(=Se)R³-, -P(=S)R³-, -SiR³R⁴-, -CR³R⁴-, and -C(=O)- where R³ and R⁴ are independently a hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl group.
12. The process as claimed in claim 6, wherein L_1 and L_2 are either a covalent bond or -O-.
13. The process as claimed in claim 6, wherein both of L_1 and L_2 are covalent bonds.
14. The process as claimed in claim 6, wherein Y is substituted at one or more of the aromatic ring positions with groups other than hydrogen, wherein each substituent is independently: a hydrocarbyl group, a heterohydrocarbyl group or organoheteryl group, or a halogen atom.
15. A process as claimed in claim 6, wherein X is a hydrocarbylene, -N(R⁵)-, -N(R⁵)-N(R⁶)-, =C(R⁷)-N(R⁵)-, -N(R⁵)-C(R⁷)(R⁸)-, or N(R⁵)-X¹-N(R⁶) where R⁵ and R⁶ are independently a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group, R⁷ and R⁸ are independently a hydrogen, a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group, and X¹ is a hydrocarbylene group.
16. The process as claimed in claim 1, wherein L_1 and L_2 are selected from the group consisting of a covalent bond, a heteroatom, a substituted heteroatom, -C(=O)-, and -CR³R⁴-, where R³ and R⁴ are independently a hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl group.
17. The process as claimed in claim 1, wherein L_1 and L_2 are selected from the group consisting of a covalent bond, -O-, -S-, -NR₃-, -P(=O)R³-, -P(=Se)R³-,

-P(=S)R³-, -SiR³R⁴-, -CR³R⁴-, and -C(=O)- where R³ and R⁴ are independently a hydrogen, a hydrocarbyl group, a heterohydrocarbyl group or an organoheteryl group.

5 18. The process as claimed in claim 1, wherein L₁ and L₂ are either a covalent bond or -O-.

19. The process as claimed in claim 1, wherein both of L₁ and L₂ are covalent bonds.

10

20. The process as claimed in claim 1, wherein Y is substituted at one or more of the aromatic ring positions with groups other than hydrogen, wherein each substituent is independently: a hydrocarbyl group, a heterohydrocarbyl group, an organoheteryl group, or a halogen atom.

15

21. A process as claimed in claim 1, wherein X is a hydrocarbylene, -N(R⁵)-, -N(R⁵)-N(R⁶)-, =C(R⁷)-N(R⁵)-, -N(R⁵)-C(R⁷)(R⁸)-, or N(R⁵)-X¹-N(R⁶) where R⁵ and R⁶ are independently a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group, R⁷ and R⁸ are independently a hydrogen, a hydrocarbyl group, an organoheteryl group or a heterohydrocarbyl group, and X¹ is a hydrocarbylene group.

20