



(86) Date de dépôt PCT/PCT Filing Date: 2005/10/11
(87) Date publication PCT/PCT Publication Date: 2006/04/27
(45) Date de délivrance/Issue Date: 2011/03/01
(85) Entrée phase nationale/National Entry: 2007/04/12
(86) N° demande PCT/PCT Application No.: US 2005/036540
(87) N° publication PCT/PCT Publication No.: 2006/044393
(30) Priorités/Priorities: 2004/10/12 (US60/617,995);
2005/10/11 (US11/247,067)

(51) Cl.Int./Int.Cl. *A01N 25/34* (2006.01),
A01P 13/00 (2006.01), *C05G 5/00* (2006.01)

(72) Inventeurs/Inventors:
DRIESSEN, DANNY ANDREAS MARIA, NL;
ELTINK, MICHAEL GUSTAAF, NL;
OUT, GERARDUS JACOBUS JOSEPH, NL;
TERLINGEN, JOHANNES GIJSBERTUS ANTONIUS,
NL;
LERSCHMACHER, ANDREAS, DE;
KUHLMANN, PETER, DE

(73) Propriétaire/Owner:
OMS INVESTMENTS, INC., US

(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : PRODUITS NUTRITIFS MOULES POUR LA CROISSANCE DES PLANTES ET LEURS PROCEDES DE PRODUCTION

(54) Title: SHAPED PLANT GROWTH NUTRIENT PRODUCTS AND PROCESSES FOR THE PRODUCTION THEREOF

(57) Abrégé/Abstract:

Shaped plant growth nutrient products such as fertilizer products are provided as well as processes for producing and using such shaped plant growth products. The products comprise active plant growth ingredients mixed with a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent. Preferably, the shaped products are in tablet form and the active plant growth ingredient comprises a fertilizer.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 April 2006 (27.04.2006)

PCT

(10) International Publication Number
WO 2006/044393 A3

(51) International Patent Classification:

A01N 25/34 (2006.01) C05G 5/00 (2006.01)
A01P 13/00 (2006.01)

(21) International Application Number:

PCT/US2005/036540

(22) International Filing Date: 11 October 2005 (11.10.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

60/617,995 12 October 2004 (12.10.2004) US
11/247,067 11 October 2005 (11.10.2005) US

(71) Applicant: OMS INVESTMENTS, INC. [US/US];
10250 Constellation Boulevard, Suite 2800, Los Angeles,
CA 90067-6228 (US).(72) Inventors: DRIESSEN, Danny, Andreas, Maria; Kam-
perstraat 36, NL-6171 NW Stein(LB) (NL). ELTINK,
Michael, Gustaaf; Hoogveldlaan 58, NL-6135 JD Sittard
(NL). OUT, Gerardus, Jacobus, Joseph; Gangelt-
straat 14, NL-6132 HB Sittard (NL). TERLINGEN,
Johannes, Gijsbertus, Antonius; Aan de Put 14,
NL-6373 VT Landgraaf (NL). LERSCHMACHER,
Andreas; Kreuzbergstrasse 36, 40489 Dusseldorf (DE).
KUHLMANN, Peter; Zwingerberger Weg 46, 42489
Wulfrath (DE).(74) Agents: RADEN, James, B. et al.; Jones Day, 77 West
Wacker, Chicago, IL 60601-1692 (US).

(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY,
MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO,
NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK,
SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:


- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(88) Date of publication of the international search report:
28 December 2006

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: SHAPED PLANT GROWTH NUTRIENT PRODUCTS AND PROCESSES FOR THE PRODUCTION THEREOF

(57) Abstract: Shaped plant growth nutrient products such as fertilizer products are provided as well as processes for producing and using such shaped plant growth products. The products comprise active plant growth ingredients mixed with a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent. Preferably, the shaped products are in tablet form and the active plant growth ingredient comprises a fertilizer.



WO 2006/044393 A3

**SHAPED PLANT GROWTH NUTRIENT PRODUCTS
AND PROCESSES FOR THE PRODUCTION THEREOF
BACKGROUND OF THE INVENTION**

1. Field of the Invention

5 The present invention relates generally to shaped plant growth nutrient products and to processes for producing such shaped plant growth products. More particularly, it relates to products prepared by mixing active plant growth ingredients such as coated and uncoated plant nutrients with a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent to
10 produce shaped plant growth nutrient products such as fertilizer products, preferably in tablet form. The invention further relates to processes for producing such shaped plant growth nutrient products as well as to methods for using such shaped products for treating plants and vegetation.

2. Description of Related Art

15 Shaped plant nutrient formulations in tablet, spike or other forms have been known heretofore for targeting the application of plant growth nutrients to plants in a defined area. Exemplary of such prior products are those described in published European Patent Application EP0380193 A2. That published application describes the preparation and application of molded bodies containing
20 nutrients, active ingredients, plant treatment agents and auxiliaries. The molded bodies are made from particles bound together by substance bridges consisting of thermally or chemically hardened binding agents including epoxy resins and polyurethane resins. It should be noted that both polyurethane and the epoxy resins are crosslinked resins and, therefore, are insoluble in water or other
25 solvents.

US Patent No. 4,055,974 describes fertilizer tablets prepared from particles of fertilizer source materials which are bonded together with water insoluble, water swellable, hydrophilic polymeric gels by a cured water insoluble thermoset resinous binder such as urea formaldehyde. The resulting tablets are described as
30 being adapted to absorb water and disintegrate. However, as with the tablets described in European Patent Application EP0380193 A2, the water insoluble

binders cause undesirable environmental results due to their slow degradation properties when applied to the plant soil.

Furthermore, since the binder employed to produce the tablets in accordance with US Patent No. 4,055,974 is a thermoset resin, efficient and cost effective melt
5 processing techniques to produce the tablets cannot be performed and the cost and efficiency in producing the tablets is adversely impacted.

US Patent No. 4,011,061 describes the production of fertilizer tablets employing organic, film-forming preferably thermoplastic resin binders which are water insoluble and present environmental problems while US Patent No. 4,752,317
10 describes the production of a highly compacted product sold as a spike or a tablet. The product is prepared by mixing fertilizer ingredients with a water dispersible hydrolyzed lignosulfonate-acrylonitrile graft copolymer binder which is water soluble but not thermoplastic and presents problems relating to the techniques required to produce the product.

15 Several commercial products are presently on the market which comprise tablets prepared from fertilizer granules and polyurethane binders. However, these tablets all exhibit environmental disadvantages attributable to the durability of the polyurethane binder systems employed. For example, when so-called controlled release fertilizer (CRF) granules in such a tablet fully release their nutrients to a
20 treated plant, the tablet retains its initial shape as if the fertilizer tablet has not been active. Furthermore, the production of these prior plant growth nutrient tablets has resulted in various problems such as those encountered concerning the build-up of cured resin residue on the tablet forming mold which is difficult to remove.

25 Another example of current products being marketed is presented by tablets prepared from coated fertilizer granules and a water swellable, thermosetting polymeric binder system. However, as a result of its inability to melt, in production the polymeric binder must be applied from the constituent monomers or prepolymers in an emulsion or solution, which requires an additional drying
30 stage in the tablet production process. The ultimate thermoset resin is formed upon aging.

Generally, the active plant growth/nutrient ingredients employed in the production of fertilizer tablets are coated fertilizers which, in use, have a number of advantages over uncoated fertilizers and are known to be very effective sources to provide controlled release of nutrients for the feeding of plants. The nutrients are released through the fertilizer's coating at controlled rates and in this way the nutritional need of the plants can be exactly matched. By selection of a suitable coating thickness or coating composition, an appropriate fertilizer longevity can be attained. By doing so, one application of these CRF's can provide the necessary nutrients for a plant that would take multiple applications of soluble fertilizer, without the risk of overfeeding of plants or leaching of fertilizer minerals to the environment.

In the CRF's, the fertilizer may release out of the coatings in various ways such as via: 1) imperfections in the coating, 2) pores in the coating or 3) osmotic pressure. It has been recognized heretofore that the latter two mechanisms offer important benefits over the first in regard to consistency of release rates.

An example of coated fertilizers which exhibit fertilizer release via coating imperfections are the sulfur coated fertilizers with a polymeric topcoat, such as disclosed in US Patents Nos. 5,219,465; 5,405,426 and 5,466,274. The major advantage of the sulfur coated fertilizers with a polymeric topcoat is their relatively low cost.

Examples of coated fertilizers which show fertilizer release through pores in the coating are presented by the polyolefin coated fertilizers such as disclosed in US Patent 4,019,890.

Fertilizer release by water vapor permeation through the coating and subsequent build-up of osmotic pressure is exhibited by fertilizers with solvent applied thermosetting resin coatings. Examples of solvent applied thermosetting resin coated fertilizers which are currently in use are disclosed in US Patents Nos. 3,223,518; 4,657,576; 4,880,455, 5,652,196; 5,993,505 and 6,139,597.

SUMMARY OF THE INVENTION

In accordance with the present invention, we have found that problems encountered in regard to the composition, formation and use of prior shaped plant growth nutrient products such as those in tablet form can be overcome simply and

- 4 -

practically by bonding a predetermined amount of one or more types of coated granules having the same or different longevity and, optionally, other materials such as uncoated fertilizer granules, water absorbent gels, herbicides, insecticides, fungicides, pheromones, biostimulants, growth regulators, animal repellents, insect repellents and the like together into a tablet of predetermined dimension
5 employing a specific suitable binding system agent. The shaped form (eg, tablet) dimensions can be designed so as to meet the nutritional need of the plants to which fertilization is applied.

Materials suitable for use in the production of the shaped products (eg, tablets) of the present invention are biodegradable, water dispersible, water soluble, thermoplastic polymers which serve as binding agents and, in some cases, as wetting agents.

10 In comparison to prior shaped products and production techniques therefor which employ crosslinked resin binders or binders requiring application from an emulsion or solution, the present thermoplastic binding agents enable simple and efficient tablet production and in comparison to prior products and production techniques which make use of crosslinked, water insoluble binders, the present water soluble binding agents enable production of environmentally advantageous shaped products such as
15 those in tablet form.

The invention thus provides according to an aspect, for a product comprising: a plurality of active plant growth nutrient granules having diameters ranging from about 2 to about 5 millimeters; and a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent having a melt temperature in the range of about 50°C and 160°C, wherein the plurality of active plant growth
20 nutrient granules are held together by the binding agent in a shaped controlled release plant growth nutrient product.

According to another aspect, the invention provides for a product comprising: a plurality of coated active plant growth nutrient granules comprising a coating layer, wherein the coating layer provides controlled release of the nutrient from the granules; and a biodegradable, water dispersible, water
25 soluble, thermoplastic polymeric binding agent having a melt temperature in the range of about 50°C and 160°C, wherein the plurality of coated plant growth nutrient granules are held together by the binding agent in a shaped time release plant growth nutrient product, the granules providing controlled release of nutrient after dissolution of the binding agent.

According to yet another aspect, the invention provides for a product comprising: a plurality of active
30 plant growth nutrient granules; and a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent comprising C1-C4-polyalkylene oxide homopolymers, C1-C4-polyalkylene oxide block co-polymers and terpolymers, or polyolefin-C1-C4-polyalkylene oxide block co-polymers, wherein the binding agent has a melt temperature in the range of about 50°C and 160°C, wherein the plurality of coated plant growth nutrient granules are held together by the binding agent
35 in a shaped controlled release plant growth nutrient product, the binding agent dissolving after

- 4a -

contact with water thereby releasing the plant growth nutrient granules from the shaped controlled release plant growth nutrient product.

The invention also provides according to another aspect, for a process for producing shaped time release plant growth nutrient products, comprising: providing granules of an active plant growth
5 nutrient ingredient; preheating the granules to a temperature in the range of about 50-100°C; mixing the granules with a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent which has previously been heated to form a melt, wherein the mixture comprises about 0.1 to 40 weight percent binding agent; and introducing the mixture into a mold and cooling the mixture in the mold to form the shaped time release plant growth nutrient product.

10

DETAILED DESCRIPTION OF THE INVENTION

Plant growth nutrient tablets in accordance with the present invention may be prepared utilizing active plant growth ingredients including coated and uncoated plant nutrient granules such as fertilizer granules, biostimulants, growth regulators, plant treating agents, fertilizer additive
15 ingredients and the like and mixtures thereof.

Preferably, the plant growth nutrient tablets are prepared utilizing homogenous or heterogeneous coated fertilizer granules. When homogeneous or single component granules are employed, the granules have a diameter ranging from about 0.1 to about 10 mm, preferably, between about 0.5 – 5 mm. When heterogeneous or multiple component granules are employed, the granules may be of
20 varying composition, diameter (about 0.1 to about 10 mm), coating type, coating thickness (longevity) and the like. Preferably, when heterogeneous

granules are employed, small dimension granules (about 0.2 - 1.5 mm) are mixed with larger dimension granules (about 2 - 5mm) to produce the tablets.

The granules may have one or more coatings applied thereon with coating thicknesses varying between about 0.1 and 150 micrometers, preferably between about 1 and 110 micrometers and longevities ranging between about 1 week to 24 months, preferably between about 3 weeks and 18 months. The fertilizer granules for use herein may include such materials as Nitrogen (N), Phosphorus (P) and/or Potassium (K) or any of a variety of different NPK compositions which may or may not contain Magnesium, Calcium and / or various amounts of various trace elements such as Boron, Iron, Cobalt, Copper, Manganese, Molybdenum, Zinc. In a preferred embodiment, the granules are preheated to a temperature in the range of about 50-100°C and then mixed with about 0.1-40 wt%, preferably about 1-25 wt% of a suitable binding agent which has previously been heated to form a melt. To this mixture, optionally, one or more other components may be added such as water-absorbent gels, nitrification inhibitors, urease inhibitors, herbicides, insecticides, fungicides, pheromones, animal repellents, insect repellents and the like and mixtures thereof.

For the binding agent, a biodegradable, water dispersible, water soluble, thermoplastic polymeric material is used. We have found that polymers from the group comprising C1-C4-polyalkylene oxide homopolymers, C1-C4-polyalkylene oxide block copolymers- and terpolymers and polyolefin-C1-C4-polyalkylene oxide block copolymers and mixtures thereof exhibit unexpectedly advantageous characteristics in regard to crystallization behavior, adhesive properties, water solubility, biodegradability and, in some cases, wetting properties.

Suitable examples of such polymers are polyethylene oxide homopolymers, polyethylene oxide-block-polypropylene oxide copolymers, polyethylene oxide-block-polypropylene oxide-block-polyethylene oxide terpolymers, polypropylene oxide-block-polyethylene oxide-block-polypropylene oxide terpolymers, polyethylene-block-polyethylene oxide copolymers; polyethylene-block-polypropylene oxide copolymers, polypropylene-block-polyethylene oxide copolymers and polypropylene-block-polypropylene oxide copolymers and the like and mixtures thereof.

Preferably, the melt temperature of the binding agent should range between about 50°C and about 160°C, preferably between about 50°C and about 100°C.

The melt temperature, melt viscosity and mechanical behavior of the polymeric binding agent is a function of the chemical composition and the molecular weight
5 of the polymer and in case of block copolymers additionally of the block length of the polyethyleneoxide-, polyethylene- or polypropylene- segment. In accordance with the present invention, the physical and chemical characteristics of the polymer may be selected so that the melt temperature and melt viscosity of the polymer are low enough to allow safe and efficient coating of the granules with
10 the binding agent but are high enough to enable sufficient mechanical strength of the resulting tablets.

The block copolymers have the additional advantage over the homopolymers of exhibiting wetting properties, which enhance the rate of water absorption in the soil. The water solubility and wettability of the block copolymers are dependent
15 on the relative amount of the water soluble segments, which is chosen such that the mechanical stability of the tablets is not influenced.

In a preferred embodiment, the plant growth granules and any ancillary ingredients are preheated to a temperature in a range of about of 50-100°C and then mixed with about 0.1-40 wt% of the binding agent which has previously
20 been heated to form a melt. The resulting mixture is introduced into a shaping mold and the mixture is cooled in the mold to form the shaped product.

The following examples further illustrate details of the products and processes of the present invention. While the invention is described with preferred embodiments, it is to be understood that variations and modifications thereof may
25 be resorted to as will be apparent to those skilled in the art. Such variations and modifications are to be considered within the purview and the scope of the claims appended hereto.

EXAMPLE 1

Fertilizer tablets in accordance with the present invention were prepared by
30 mixing 83 wt% preheated Osmocote® Exact® Standard 3-4 Month fertilizer granules with average diameter of 3.1 mm, sold by The Scotts Company, and 9 wt% preheated Osmocote® Exact® Mini 3-4 Month with average diameter of 1.5

mm, sold by The Scotts Company, with 8 wt% polyethylene oxide having a molecular weight of 8000 g/mole at 90°C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the granulate-binder mixture was scraped off. The mold was allowed to cool down to ambient
5 temperature and the tablets were removed. Drop tests showed that the average weight loss was small. In water, the tablets showed rapid disintegration into separate granules.

EXAMPLE 2

A control sample product in accordance with the prior art was prepared by
10 combining and mixing 375 g Osmocote® Exact® Standard 3-4 Month fertilizer granules, sold by The Scotts Company, having an average diameter of 3.1 mm and with NPK 16+11+11; 5 g Askofen 3289 Part A polyol formulation comprising 4-hydroxy-4-methylpentane-2-on, sold by Ashland-Sudchemie-Kernfest GMBH; and 5 g Askofen 0281 Part B comprising diphenylmethane-4,4'-
15 diisocyanate, isomers and homologs, sold by Ashland-Sudchemie-Kernfest GMBH at room temperature. The resulting mixture was quickly spread out over a silicone rubber tablet mold and the excess of the mixture was scraped off. After 15-20 minutes curing, the resulting tablets were removed from the mold. Experience has demonstrated that the production of these prior products utilizing
20 polyurethane binder technology has presented various problems that are overcome by the present invention. For example, employing the prior techniques, all the equipment had to be cleaned quickly and regularly, because the resin was very difficult to remove after curing. Expensive silicone rubber molds were required to produce the tablets because tablet removal from metal molds was found to be
25 difficult as a result of the strong adhesion of the tablets to the mold surface. In practice, it was further found that the molds should be renewed every 10 weeks due to resin build-up and damaging of the molds. Still further, once Askofen 3289 Part A and Askofen 0281 Part B were mixed, the resulting mixture had to be applied rapidly because the pot life was very limited. Nevertheless, it was found
30 that a significant amount of spill material was produced which could not be used a second time.

In comparison, it has been found that the problems encountered in producing the tablet products of the prior art are effectively and cost efficiently resolved employing the formulations and processes of the present invention as exemplified herein by Example 1

5

EXAMPLE 3

In a further comparative example, three separate commercially available fertilizer tablet samples which utilize thermoset binders were compared with a sample of the fertilizer tablets of the present invention employing a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent and the results of the testing performed on the fertilizer tablet samples in terms of water solubility, tablet disintegration and mechanical stability were tabulated (see Table 1 hereinbelow).

For purposes of the comparative testing, a 5.4 gram Osmocote[®] Plus fertilizer tablet sold by The Scotts Company; a 7.6 gram Basacote[®] Plus Tabs 6 Month fertilizer tablet sold by Compo GMBH & Co. KG. and a 6.0 gram Pokon Season Comfort fertilizer tablet sold by Pokon & Chrysal BV were employed as examples of prior fertilizer tablets produced utilizing thermoset binders. As an example of a fertilizer tablet in accordance with the present invention, a 5.3 g fertilizer tablet sample was prepared in accordance with the procedure set forth in Example 1 utilizing the same biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent as employed in Example 1.

The sample fertilizer tablets were placed in glass beakers filled with 200 ml water at 21°C. After 19 minutes in the water, the tablet produced according to the present invention was found to disperse into separate granules. The Pokon Season Comfort tablet and the somewhat larger Basacote Plus Tabs tablet exhibited swelling but no dissolution of the binder. After 5 hours, the Pokon and Basacote tablets fell apart into separate granules in a soft crosslinked mass. The Osmocote Plus tablet retained its initial shape and remained rigid.

The results of the comparative testing performed on the sample tablets were as follows:

30

Binder Type	Tablet Type (Binder Employed)	Water Soluble Binder at (21°C)	Tablet Desintegration -time in water at 21°C^{a)}	Mechanical Stability^{b)}
Thermoplastic	Present invention (5.3g)	Yes	19 Minutes	3.4%
Thermoset	Osmocote Plus (5.2g)	No	Indefinite	1.1%
Thermoset	Pokon Season Comfort (5.3g)	Water swellable	5 hours	0.4%
Thermoset	Basacote Tabs 6M (7.6g)	Water swellable	5 hours	0.4%

a) Time that it takes before the tablet falls apart into separate granules

b) Average percent weight loss of 10 tablets in a 2 meter drop test at 21°C

EXAMPLE 4

In another comparative example, separate samples of a 5.4 gram Osmocote[®] Plus
5 fertilizer tablet, a 7.6 gram Basacote[®] Plus Tabs 6 Month fertilizer tablet; and a
6.0 gram Pokon Season Comfort fertilizer tablet and a 5.2 g fertilizer tablet of the
present invention prepared in accordance with the procedure set forth in Example
1 were placed in separate glass beakers and placed in an oven at 100°C. for a
period of 30 minutes. Thereafter, the tablet produced according to the present
10 invention was found to disintegrate readily into separate coated granules upon
touching due to melting of the binding agent. The Osmocote[®] Plus tablet, the
Basacote Plus tablet and the Pokon Season Comfort tablet were found to retain
their initial shape and remained rigid even upon slight pressure exertion and
temperature increase to 150°C, demonstrating that the binding agent used in each
15 of these tablets was a thermoset polymer rather than a thermoplastic polymer as
employed in the present invention.

EXAMPLE 5

92 wt% samples of preheated Osmocote Exact Standard 3-4 Month fertilizer
granules with average diameter of 3.1 mm and with NPK 16+11+11 were mixed
20 with 8 wt% polyethylene oxide having molecular weights of 6000 g/mole, 8000
g/mole and 20,000 g/mole, respectively, at 90°C. After thorough mixing, the
sample mixtures were spread out over separate tablet molds, after which the
excess of each mixture was scraped off. The mold was allowed to cool down to

ambient temperature and the tablets were removed from the mold. When placed in water, each of the resulting sample tablets showed rapid disintegration into separate granules. Drop tests showed that the average weight loss was acceptable for the polyethylene oxide with molecular weight of 6000 and 8000 g/mole but
5 not for the polyethyleneoxide with 20,000g/mole, due to uneven distribution of the high molecular weight polyethyleneoxide binding agent on the granules. This demonstrates that selection of polymer properties must be made carefully. Too high molecular weight results in too high viscosity and, thereby, adverse mixing behavior and loss of mechanical stability of the tablets. Too low molecular
10 weight, however, may result in stickiness due to low melting point and also loss of mechanical stability of the tablets. Accordingly, it appears that only a narrow band of molecular weights is suitable for the production of stable tablets.

EXAMPLE 6

92 wt% preheated Osmocote Exact Standard 5-6 Month fertilizer granules was
15 mixed with 8 wt% Synperonic™ PEF 108 polyethyleneoxide-*block*-polypropyleneoxide-*block*-polyethyleneoxide terpolymer, sold by Uniqema, having a molecular weight of 14,000 g/mole at a temperature of 90°C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the granulate-binder mixture was scraped off. The mold was allowed
20 to cool down to ambient temperature and the tablets were removed. In water, disintegration of the resulting tablets into separate granules occurred rapidly.

EXAMPLE 7

92 wt% preheated Osmocote Exact Standard 3-4 Month fertilizer granules were mixed with 8 wt% polyethylene-*block*-polyethyleneoxide copolymer having a
25 molecular weight of 2250 g/mole at a temperature of 90°C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the granulate-binder mixture was scraped off. The mold was allowed to cool down to ambient temperature and the tablets were removed. In water, disintegration of the resulting tablets into separate granules occurred rapidly.

EXAMPLE 8

30 60 wt% preheated Osmocote Exact 3-4 Month fertilizer granules and 20wt% Luquasorb® 1161 sodium polyacrylate water absorbent gel sold by BASF were

mixed with 20% polyethylene oxide having a molecular weight of 8000 g/mole at 90°C. After thorough mixing, the mixture was spread out over a tablet mold after which the excess of the mixture was scraped off. The mold was allowed to cool down and the resulting tablets were removed. The tablets dispersed quickly in
5 water and the added Luquasorb water absorbent gel showed satisfactory swell behavior. Drop tests showed acceptable tablet stability.

EXAMPLE 9

92 wt% preheated Osmocote Exact Standard 5-6 Month fertilizer granules were mixed with 8 wt% of a mixture of 87wt% polyethylene oxide having a molecular
10 weight of 8000 g/mole and 13 wt% aluminium tris-O-ethylphosphonate (fosetyl-aluminium) fungicide at 90°C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold was allowed to cool down to ambient temperature and the resulting tablets were removed from the mold.

EXAMPLE 10

92 wt% preheated uncoated fertilizer granules (NPK 17+10+13 + trace elements) were mixed with 8 wt% polyethylene oxide having a molecular weight of 8000 g/mole. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold was allowed to
20 cool down to ambient temperature and the resulting tablets were removed from the mold.

EXAMPLE 11

92 wt% preheated Osmocote[®] Start (NPK 12+11+17 + 2 MgO + trace elements) fertilizer granules sold by The Scotts Company, with an average diameter of 1.6
25 mm, were mixed with 8 wt% polyethylene oxide having a molecular weight of 8000 g/mole at 90 °C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold was allowed to cool down to ambient temperature and the resulting tablets were removed from the mold.

EXAMPLE 12

92 wt% preheated sulfur coated urea fertilizer granules, containing 11 wt% sulfur coating, were mixed with 8 wt% polyethylene oxide having a molecular weight of

8000 g/mole at 90 °C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold was allowed to cool down to ambient temperature and the resulting tablets were removed from the mold.

5

EXAMPLE 13

92 wt% preheated Osmoform[®] (NPK 19+5+13 +2MgO + trace elements) fertilizer prills sold by The Scotts Company were mixed with 8 wt% polyethylene oxide having a molecular weight of 8000 g/mole at 90 °C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold was allowed to cool down to ambient temperature and the resulting tablets were removed from the mold.

10

EXAMPLE 14

92 wt% preheated Basacote Plus 12 Month (NPK 15+8+12 +2MgO+trace elements) fertilizer granules were mixed with 8 wt% polyethylene oxide having a molecular weight of 8000 g/mole at 75°C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold was allowed to cool down to ambient temperature and the resulting tablets were removed from the mold.

15

EXAMPLE 15

92 wt% preheated Sinclair Sincrocell 12 (NPK 14+8+13 + 2MgO + trace elements) fertilizer granules sold by William Sinclair Horticultural Ltd were mixed with 8 wt% polyethylene oxide having a molecular weight of 8000 g/mole at 90 °C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold was allowed to cool down to ambient temperature and the resulting tablets were removed from the mold.

20

25

EXAMPLE 16

92 wt% preheated Nutricote[®] controlled release fertilizer (CRF) 100 day (NPK 13+13+13 + 2MgO + trace elements) granules sold by Chisso-Asahi Fertilizer Co., Ltd. were mixed with 8 wt% polyethylene oxide having a molecular weight of 8000 g/mole at 90 °C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold

30

was allowed to cool down to ambient temperature and the resulting tablets were removed from the mold.

EXAMPLE 17

92 wt% preheated Multicote[®] 4 (NPK 15+7+15 + 2MgO + trace elements)
5 controlled release fertilizer granules sold by Haifa Chemicals Ltd. were mixed with 8 wt% polyethylene oxide having a molecular weight of 8000 g/mole at 90 °C. After thorough mixing, the mixture was spread out over a tablet mold, after which the excess of the mixture was scraped off. The mold was allowed to cool down to ambient temperature and the resulting tablets were removed from the
10 mold.

In a further embodiment of the present invention, dosing systems are provided for granules or powders which can be used in a variety of water based systems or wet surroundings where rapid availability of a solid substrate is desired. For example, tablets of this invention can be formulated to supply disinfecting chemicals, as for
15 swimming pool applications, to replace standard chemical solution applications. Also, tablets of this invention can be formulated for introduction into dipping baths, such as those employed in the paint industry, to add chemicals such as fungicides and biocides into the baths during the long duration of the baths. Still further, tablets can be formulated with water soluble binders to provide dosing
20 systems for introducing pigments or tinting materials into paints as a replacement for high viscosity pastes which have been employed heretofore.

Although the invention has been described in its preferred forms with a certain degree of particularity, it is to be understood that the present disclosure has been made by way of example only. Numerous changes in the details of the
25 compositions and ingredients therein as well as the methods of preparation will be apparent without departing from the spirit and scope of the invention, as defined in the appended claims.

- 14 -

Claims:

1. **A product comprising:**

 a plurality of active plant growth nutrient granules having diameters ranging from about 2 to about 5 millimeters; and

 a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent having a melt temperature in the range of about 50°C and 160°C,

 wherein the plurality of active plant growth nutrient granules are held together by the binding agent in a shaped controlled release plant growth nutrient product.
2. The product of claim 1, further comprising a second plurality of active plant growth nutrient granules having diameters ranging from about 0.2 to about 1.5 millimeters.
3. The product of claim 1 in tablet form.
4. The product of claim 1, wherein the binding agent includes C1-C4-polyalkylene oxide homopolymers, C1-C4-polyalkylene oxide block copolymers and terpolymers, polyolefin-C1-C4-polyalkylene oxide block copolymers, or mixtures thereof.
5. **A product comprising:**

 a plurality of coated active plant growth nutrient granules comprising a coating layer,

 wherein the coating layer provides controlled release of the nutrient from the granules; and

 a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent having a melt temperature in the range of about 50°C and 160°C,

 wherein the plurality of coated plant growth nutrient granules are held together by the binding agent in a shaped time release plant growth nutrient product, said granules providing controlled release of nutrient after dissolution of the binding agent.

- 15 -

6. The product of claim 5, wherein the coated active plant growth nutrient granules each comprise a granule of plant growth nutrient and a coating layer thereon, wherein the coating layer has a thickness ranging from about 0.1 to about 150 micrometers.
7. The product of claim 6, wherein the coating has a thickness ranging from about 1 to about 110 micrometers.
8. The product of claim 5, wherein the coated active plant growth nutrient granules have longevities ranging between about 1 week and 24 months.
9. The product of claim 8, wherein the coated active plant growth nutrient granules have longevities ranging between about 3 weeks and 18 months.
10. The product of claim 5, wherein the binding agent includes C1-C4-polyalkylene oxide homopolymers, C1-C4-polyalkylene oxide block copolymers and terpolymers, polyolefin-C1-C4-polyalkylene oxide block copolymers or mixtures thereof.
11. The product of claim 5, wherein the plurality of coated active plant growth nutrient granules have diameters ranging from about 2 to about 5 millimeters.
12. The product of claim 11, further comprising a second plurality of active plant growth nutrient granules having diameters ranging from about 0.2 to about 1.5 millimeters.
13. The product of claim 5 in tablet form.
14. A product comprising:
 - a plurality of active plant growth nutrient granules; and
 - a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent comprising C1-C4-polyalkylene oxide homopolymers, C1-C4-polyalkylene oxide block copolymers and terpolymers, or polyolefin-C1-C4-polyalkylene oxide block copolymers, wherein the binding

- 16 -

agent has a melt temperature in the range of about 50°C and 160°C,

wherein the plurality of coated plant growth nutrient granules are held together by the binding agent in a shaped controlled release plant growth nutrient product, said binding agent dissolving after contact with water thereby releasing the plant growth nutrient granules from the shaped controlled release plant growth nutrient product.

15. The product of claim 14, wherein the active plant growth nutrient granules have diameters ranging from about 0.1 to about 10 millimeters.

16. The product of claim 15, wherein the active plant growth nutrient granules have diameters ranging from about 0.5 to about 5 millimeters.

17. The product of claim 14, wherein the plurality of coated active plant growth nutrient granules have diameters ranging from about 2 to about 5 millimeters.

18. The product of claim 17, further comprising a second plurality of active plant growth nutrient granules having diameters ranging from about 0.2 to about 1.5 millimeters.

19. The product of claim 14, wherein the shaped controlled release plant growth nutrient product comprises between about 0.1 to about 40 weight percent binding agent.

20. The product of claim 19, wherein the shaped controlled release plant growth nutrient product comprises between about 1 to about 25 weight percent binding agent.

21. The product of claim 14, wherein the binding agent includes polyethylene oxide homopolymers, polyethylene oxide-block-polypropylene oxide copolymers, polyethylene oxide-block-polypropylene oxide-block-polyethylene oxide terpolymers, polypropylene oxide-block-polyethylene oxide-block-polypropylene oxide terpolymers, polyethylene-block-polyethylene oxide

- 17 -

copolymers, polyethylene-block-polypropylene oxide copolymers, polypropylene-block-polyethylene oxide copolymers, polypropylene-block-polypropylene oxide copolymers, or mixtures thereof.

22. The product of claim 14, wherein the binding agent has a melt temperature in the range of about 50°C and 100°C.

23. The product of claim 14, wherein the active plant growth nutrient granules are plant nutrients, biostimulants, growth regulators, plant treating agents, fertilizer additive ingredients, or mixtures thereof.

24. The product of claim 14, wherein at least one other component is mixed with the active plant growth nutrient granules and the binding agent, the other component including water-absorbent gels, nitrification inhibitors, urease inhibitors, herbicides, insecticides, fungicides, pheromones, animal repellents, insect repellents, or mixtures thereof.

25. A process for producing shaped time release plant growth nutrient products, comprising:
providing granules of an active plant growth nutrient ingredient;
preheating the granules to a temperature in the range of about 50-100 °C;
mixing said granules with a biodegradable, water dispersible, water soluble, thermoplastic polymeric binding agent which has previously been heated to form a melt, wherein the mixture comprises about 0.1 to 40 weight percent binding agent; and
introducing the mixture into a mold and cooling the mixture in the mold to form the shaped time release plant growth nutrient product.

26. The process of claim 25, wherein the mixture comprises about 1 to 25 weight percent binding agent.

- 18 -

27. The process of claim 25, wherein the product is shaped in tablet form.
28. The process of claim 25, wherein the granules are plant nutrients, biostimulants, growth regulators, plant treating agents, fertilizer additive ingredients, or mixtures thereof.
29. The process of claim 28, wherein the granules are coated fertilizer granules.
30. The process of claim 25, wherein at least one other component is mixed with the active plant growth ingredient and the binding agent, the other component includes coated fertilizer granules, uncoated fertilizer granules, water-absorbent gels, nitrification inhibitors, urease inhibitors, herbicides, insecticides, fungicides, pheromones, animal repellents, insect repellents, or mixtures thereof.
31. The process of claim 25, wherein the binding agent includes C1-C4-polyalkylene oxide homopolymers, C1-C4-polyalkylene oxide block copolymers and terpolymers, polyolefin-C1-C4-polyalkylene oxide block copolymers or mixtures thereof.
32. The process of claim 31, wherein the binding agent includes polyethylene oxide homopolymers, polyethylene oxide-block-polypropylene oxide copolymers, polyethylene oxide-block-polypropylene oxide-block-polyethylene oxide terpolymers, polypropylene oxide-block-polyethylene oxide-block-polypropylene oxide terpolymers, polyethylene-block-polyethylene oxide copolymers, polyethylene-block-polypropylene oxide copolymers, polypropylene-block-polyethylene oxide copolymers, polypropylene-block-polypropylene oxide copolymers, or mixtures thereof.