

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
26 February 2004 (26.02.2004)

PCT

(10) International Publication Number
WO 2004/016702 A1

(51) International Patent Classification⁷: **C09J 133/02**,
133/14, C08F 220/04, 220/20, 8/14, C08L 33/02, D04H
1/64, B05D 3/02

(21) International Application Number:
PCT/US2003/025503

(22) International Filing Date: 13 August 2003 (13.08.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/222,617 16 August 2002 (16.08.2002) US

(71) Applicant (for all designated States except US): **H.B. FULLER LICENSING & FINANCING, INC.** [US/US];
1200 Willow Lake Blvd, Box 64683, St. Paul, MN
55164-0683 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MILLER, Wayne, P.** [US/US]; 5100 Bona Road, St. Paul, MN 55112 (US).
ANDERSON, Stewart, C. [US/US]; 9920 Friar Drive,
Eden Prairie, MN 55344 (US). **DOCHNIAK, Michael, J.**
[US/US]; 1717 Florence St., White Bear Lake, MN 55110
(US).

(74) Agents: **STONE, Kirsten, K.** et al.; 1200 Willow Lake
Blvd., Box 64683, St. Paul, MN 55164-0683 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: AQUEOUS FORMALDEHYDE-FREE COMPOSITION AND FIBERGLASS INSULATION INCLUDING THE SAME

(57) Abstract: An aqueous composition that includes a) aqueous hydroxy functional, carboxy functional polymer including the reaction product of at least 5 % by weight α,β -ethylenically unsaturated hydroxy monomer, at least 30 % by weight ethylenically unsaturated carboxylic acid monomer, from 0 % by weight to less than 50 % by weight α,β -ethylenically unsaturated nonhydroxy functional, noncarboxy functional monomer, and chain transfer agent, and b) condensation accelerator, and articles that include a nonwoven web including glass fibers, and cured aqueous binder composition.



WO 2004/016702 A1

AQUEOUS FORMALDEHYDE-FREE COMPOSITION AND FIBERGLASS
INSULATION INCLUDING THE SAME

BACKGROUND

5 The invention relates to aqueous formaldehyde-free compositions that include hydroxy functional, carboxy functional polymers.

 Fibrous glass insulation products generally include glass fibers bonded together by a cured thermoset polymeric composition. Processes for making fiberglass insulation generally include drawing molten streams of glass into fibers of random lengths that are
10 blown into a forming chamber where they are randomly deposited as a web onto a traveling conveyor. The fibers, while in transit in the forming chamber and while still hot from the drawing operation, are sprayed with an aqueous binder composition, e.g., a formaldehyde-based binder. The residual heat from the glass fibers and the flow of air through the fibrous mat during the forming operation are generally sufficient to volatilize
15 the majority to all of the water from the binder, thereby leaving the remaining components of the binder on the fibers as a viscous or semi-viscous high solids liquid. The coated fibrous web is then transferred to a curing oven where heated air is blown through the web to cure the binder and bond the glass fibers together.

 During the curing reaction, formaldehyde and low molecular weight phenol-
20 formaldehyde compounds are volatilized from the composition and into the surrounding environment, which is undesirable for the people working around the fiberglass insulation manufacturing process and may be harmful to the environment.

 A number of formaldehyde-free fiberglass binder compositions have been developed. Some of these compositions include α,β -ethylenically unsaturated carboxylic
25 acid polymers, polyols and condensation accelerators. These compositions are applied to glass fibers and then dried in ovens at high temperatures to effect crosslinking. A portion of the lower molecular weight polyols present in the compositions may volatilize during the drying operation producing undesirable volatile organic compound (VOC) emissions. Some of these compositions are also in the form of emulsions, which can create processing
30 and equipment difficulties during fiberglass manufacturing. Some of these formulations are also in the form of two part compositions requiring the user to mix the parts of the composition prior to use.

Binder compositions are described in various documents including, e.g., U.S. Patent Nos. 6,331,350 (Taylor et al.), 5,661,213 (Arkens et al.), 5,280,079 (Allen et al.) and 5,147, 956 (Allen).

SUMMARY

5 In one aspect, the invention features an aqueous composition that includes a) aqueous hydroxy functional, carboxy functional solution polymer that includes the reaction product of at least 5 % by weight α,β -ethylenically unsaturated hydroxy functional monomer, at least 30 % by weight ethylenically unsaturated carboxylic acid monomer, 0 % by weight to less than 50 % by weight α,β -ethylenically unsaturated
10 nonhydroxy functional, noncarboxy functional monomer, and chain transfer agent, and b) condensation accelerator.

In one embodiment, the aqueous hydroxy functional carboxy functional polymer has a number average molecular weight no greater than 10,000. In other embodiments, the aqueous composition has a pH less than 7. In some embodiments, the aqueous
15 composition has a pH from about 2 to about 4.

In another embodiment, the α,β -ethylenically unsaturated hydroxy functional monomer is 2-hydroxy ethyl acrylate. In one embodiment, the ethylenically unsaturated carboxylic acid monomer is glacial acrylic acid. In some embodiments, the aqueous hydroxy functional carboxy functional polymer is prepared from no greater than 40 % by
20 weight α,β -ethylenically unsaturated nonhydroxy functional, noncarboxy functional monomer.

In other embodiments, the aqueous hydroxy functional carboxy functional polymer includes from 20 % by weight to 60 % by weight solids.

In another embodiment, the aqueous hydroxy functional carboxy functional
25 polymer has an acid number of at least 300 mg KOH/g dried polymer.

In one embodiment, the composition exhibits a dry tensile strength of at least 5 when tested according to the Dry Tensile Strength Test Method. In another embodiment, the composition exhibits a wet tensile strength of at least 5 when tested according to the Wet Tensile Strength Test Method.

30 In some embodiments, the aqueous hydroxy functional, carboxy functional polymer includes the reaction product of from 10 % by weight to 70 % by weight α,β -

ethylenically unsaturated hydroxy functional monomer, from 40 % by weight to 90 % by weight ethylenically unsaturated carboxylic acid monomer, and chain transfer agent. In other embodiments, the aqueous hydroxy functional, carboxy functional polymer includes the reaction product of from 20 % by weight to 60 % by weight a, β -ethylenically

5 unsaturated hydroxy functional monomer, from 50 % by weight to 90 % by weight ethylenically unsaturated carboxylic acid monomer, and chain transfer agent. In another embodiment, the aqueous hydroxy functional, carboxy functional polymer includes the reaction product of from 20 % by weight to 60 % by weight a, β -ethylenically unsaturated hydroxy functional monomer, from 60 % by weight to 80 % by weight ethylenically
10 unsaturated carboxylic acid monomer, and chain transfer agent.

In other embodiments, the aqueous composition includes a) aqueous hydroxy functional, carboxy functional solution polymer consisting essentially of the reaction product of at least 5 % by weight a, β -ethylenically unsaturated hydroxy functional monomer, at least 30 % by weight ethylenically unsaturated carboxylic acid monomer, and
15 chain transfer agent, and b) condensation accelerator.

In another aspect, the invention features fiberglass insulation that includes a nonwoven web that includes glass fibers, and a binder composition that includes a) the reaction product of aqueous hydroxy functional carboxy functional polymer comprising the reaction product of at least 5 % by weight a, β -ethylenically unsaturated hydroxy
20 functional monomer, at least 30 % by weight ethylenically unsaturated carboxylic acid monomer, from 0 % by weight to less than 50 % by weight a, β -ethylenically unsaturated nonhydroxy functional, noncarboxy functional monomer, and chain transfer agent, and b) condensation accelerator. In one embodiment, the fiberglass insulation includes from about 5 % by weight to about 14 % by weight dried binder composition based on the
25 weight of the glass fibers.

In another aspect, the invention features a method of making fiberglass insulation, the method including contacting glass fibers with a binder composition that includes a) aqueous hydroxy functional carboxy functional polymer that includes the reaction product of at least 5 % by weight a, β -ethylenically unsaturated hydroxy functional monomer, at
30 least 30 % by weight ethylenically unsaturated carboxylic acid monomer, less than 50 %

by weight nonhydroxy functional, noncarboxy functional monomer, and chain transfer agent, and b) condensation accelerator, and curing the composition.

The invention features a composition that is useful as a binder in fiberglass insulation and can be provided as a one part formulation.

5 The invention features a method of making fiberglass insulation during which low levels or no volatile organic compounds including, e.g., polyols and amines, are emitted by the binder composition.

10 The composition is well suited to application in manufacturing fiberglass insulation, which can be constructed to exhibit soft hand, good resiliency and good wet and dry strength.

Other features of the invention will be apparent from the following description of the preferred embodiments thereof, and from the claims.

GLOSSARY

In reference to the invention, these terms have the meanings set forth below.

15 The phrase "hydroxy functional carboxy functional polymer" refers to a polymer that includes hydroxyl moieties and carboxylic acid moieties.

DETAILED DESCRIPTION

20 The aqueous composition includes aqueous hydroxy functional carboxy functional addition polymer and condensation accelerator. The aqueous composition preferably exhibits a wet tensile strength of at least about 5 pounds of force (lbf), more preferably at least about 6 lbf, in other embodiments at least 7 when tested according to the Wet Tensile Strength Test Method and a dry tensile strength of at least about 5 lbf, more preferably at least about 9 lbf, in other embodiments at least 10 when tested according to the Dry Tensile Strength Test Method.

25 The aqueous hydroxy functional carboxy functional polymer includes the reaction product of a,β-ethylenically unsaturated hydroxy monomer, ethylenically unsaturated carboxylic acid monomer, chain transfer agent, and, optionally free radical initiator. The aqueous hydroxy functional carboxy functional polymer can be in the form of a solution, dispersion, emulsion or suspension. The aqueous hydroxy functional carboxy functional
30 polymer is water soluble and preferably prepared by free radical solution polymerization. Other suitable polymerization techniques include, e.g., emulsion polymerization and

suspension polymerization techniques. For emulsion polymerization, anionic surfactants, nonionic surfactants and combinations thereof can be used. Preferably the aqueous hydroxy functional carboxy functional polymer is a random copolymer.

5 The aqueous hydroxy functional carboxy functional polymer preferably has an average number molecular weight (M_n) from 1000 g/mole to 10,000,000 g/mole, in some embodiments less than 250,000 g/mole, in some embodiments less than about 15,000 g/mole, in some embodiments less than about 10,000 g/mole, in some embodiments less than about 7,000 g/mole, in some embodiments less than about 5,000 g/mole, in some embodiments from about 5000 g/mole to about 10,000 g/mole.

10 The aqueous hydroxy functional carboxy functional polymer preferably has an acid number of at least 300 mg KOH/g dried material (i.e., dried polymer and residual solids present in the aqueous solution polymer composition), in some embodiments at least 380 mg KOH/g dried material, in other embodiments at least 450 mg KOH/g dried material, in other embodiments at least 500 mg KOH/g dried material, in other embodiments no
15 greater than 780 mg KOH/g dried material, in other embodiments no greater than 710 mg KOH/g dried material, in other embodiments no greater than 650 mg KOH/g dried material, in other embodiments no greater than 600 mg KOH/g dried material.

Useful α,β -ethylenically unsaturated hydroxy functional monomers include, e.g., α,β -ethylenically unsaturated monohydroxy functional monomers including, e.g., hydroxy
20 alkyl acrylate monomers including, e.g., hydroxy methyl acrylate, hydroxy ethyl acrylate, 2-hydroxy ethyl acrylate, hydroxy propyl acrylate, hydroxy butyl acrylate, and hydroxy alkyl methacrylates, α,β -ethylenically unsaturated polyhydroxy monomers including, e.g., polyethylene glycol monomethacrylate, and combinations thereof.

The aqueous hydroxy functional carboxy functional polymer is preferably prepared
25 from α,β -ethylenically unsaturated hydroxy functional monomers in an amount of at least 5 % by weight, in other embodiments 10 % by weight, in other embodiments at least 20 % by weight, in some embodiments at least 25 % by weight, in other embodiments no greater than 75 % by weight, in other embodiments no greater than 50 % by weight, in other embodiments no greater than 45 % by weight.

30 Suitable ethylenically unsaturated carboxylic acid monomers include, e.g., acrylic acid, glacial acrylic acid, methacrylic acid, isooctyl acrylic acid, crotonic acid, isocrotonic

acid, fumaric acid, cinnamic acid, maleic acid, 2-methylmaleic acid, itaconic acid, 2-methylitaconic acid, α,β -methyleneglutaric acid, methacrylic anhydride, isooctyl acrylic anhydride, crotonic anhydride, fumaric anhydride, and maleic anhydride.

The polymer preferably includes ethylenically unsaturated carboxylic acid
5 monomers in an amount less than 100 % by weight, in some embodiments no greater than 98 % by weight, in other embodiments no greater than 90 % by weight, in other embodiments no greater than 80 % by weight, in other embodiments, no greater than 75 % by weight, in other embodiments at least 30 % by weight, in other embodiments at least 40 % by weight, in other embodiments at least 50 % by weight, in other embodiments at least
10 60 % by weight, in other embodiments at least 65 % by weight.

Suitable chain transfer agents include, e.g., sodium hypophosphite, thioglycolic acid, mercaptans including, e.g., primary octyl mercaptan, 2-mercaptoethanol, n-dodecylmercaptan, n-octylmercaptan, t-dodecyl mercaptan, mercaptoethanol, iso-octyl thioglycolate, mercapto carboxylic acids having 2 to 8 carbon atoms, and their esters,
15 examples of which include 3-mercapto propionic acid and 2-mercapto propionic acid, halogenated hydrocarbons including, e.g., carbonbromo compounds (e.g., carbon tetrabromide and bromotrichloromethane) and combinations thereof. The chain transfer agent can be present in the mixture used to form the hydroxy functional polycarboxylic acid polymer in an amount no greater than 5 % by weight, preferably from 1 % by weight
20 to about 4 % by weight, more preferably from 1 % by weight to about 3 % by weight based on the monomer weight.

Suitable free radical initiators include oxidizing agents including, e.g., water-soluble peroxy compounds such as hydrogen peroxide, t-butyl-hydroperoxide, di-t-butyl peroxide, cumene hydroperoxide, acetylacetone peroxide, t-butyl perneodecanoate, t-butyl
25 perneohexanoate, t-butyl per-2-ethylhexanoate, t-butyl perbenzoate, t-butyl perpivalate, t-butyl pivalate, t-amyl perpivalate, di-t-butyl peroxide, dibenzoyl peroxide, dicyclohexyl peroxodicarbonate, dibenzoyl peroxodicarbonate, dilauroyl peroxide, methyl ethyl ketone peroxide; water-soluble inorganic persulphates including, e.g., ammonia persulfate, lithium persulfate, potassium persulfate and sodium persulfate; water-soluble azo
30 compounds including, e.g., 4,4'-azobis(4-cyanovaleric acid) or its salts,

azodiisobutyronitrile, 2,2'-azobis(2-amidinopropane)dihydrochloride, and 2-(carbamoylazo)isobutyronitrile, and combinations thereof.

5 The free radical initiator can be present in the reaction mixture in an amount no greater than 10 % by weight based on the weight of the monomer(s) charged to the reaction vessel.

The free radical initiator can be part of an initiator system that includes oxidizing agent and reducing agent. Suitable reducing agents include, e.g., sodium formaldehyde-sulfoxylate, ferrous salts, sodium dithionite, sodium hydrogen sulfite, sodium sulfite, sodium thiosulfate, sodium bisulphate, ascorbic acid, erythorbic acid and the sodium salts
10 of ascorbic acid and erythorbic acid, and combinations thereof.

The initiator system can also include a transition metal catalyst including, e.g., salts of iron, cobalt, nickel, copper, vanadium and manganese. Examples of suitable catalysts include iron (II) sulfate, cobalt (II) chloride, nickel (II) sulfate, copper (I) chloride, and combinations thereof.

15 The amount of the initiator system (i.e. including the oxidizing agent and, where present, reducing agent and catalyst) is from 0.01 % by weight to 20 % by weight based on the weight of the monomer(s) charged to the reaction vessel.

The reaction mixture from which the hydroxy functional carboxy functional polymer is prepared is preferably free of α,β -ethylenically unsaturated nonhydroxy functional, noncarboxy functional monomer, i.e., α,β -ethylenically unsaturated monomer
20 that does not include at least one of a hydroxy functional group and a carboxy functional group. When present, the α,β -ethylenically unsaturated nonhydroxy functional, noncarboxy functional monomer is preferably present in an amount of less than 50 % by weight based on the weight of the hydroxy functional carboxy functional polymer.

25 The condensation accelerator of the aqueous composition speeds the condensation reaction that occurs as the polymer cures. Suitable condensation accelerators include, e.g., phosphorous-based catalysts including, e.g., sodium hypophosphite and phosphoric acid, para toluene sulfonic acid, any strong acids including, e.g., hydrochloric acid, sulfuric acid, trichloroacetic acid, and e.g., acidic metal salts including, e.g., aluminum chloride,
30 iron chloride, zirconium oxychloride, chromic nitrate, chromic perchlorate, aluminum nitrate, iron nitrate, zinc nitrate and combinations thereof.

The condensation accelerator can be present in the aqueous composition in an amount no greater than 15 % by weight, preferably from 3 % by weight to about 6 % by weight based on the weight of the aqueous hydroxy functional carboxy functional solution polymer.

5 The aqueous composition can also include other components including, e.g., emulsifiers, surfactants, pigments, fillers, biocides, anti-mycotics including, e.g., fungicides and mold inhibitors, plasticizers, anti-foaming agents, colorants, waxes, antioxidants, adhesion promoting agents including, e.g., silanes and boranes, odor masking agents, and combinations thereof.

10 The aqueous composition is essentially free of (i.e., has less than 10,000 parts per million (ppm)) and preferably free of formaldehyde and phenol-formaldehyde.

 The aqueous composition preferably is essentially free of (i.e., has less than 10,000 ppm) polyol having an acid number less than 100 mg KOH/g dried material, examples of which include ethylene glycol, glycerol, pentaerythritol, trimethylol propane, sorbitol,
15 sucrose, glucose, resorcinol, catechol, pyrogallol, glycollated ureas, 1,4-cyclohexane diol, dethanolamine, triethanolamine, α,β -ethylenically unsaturated hydroxy functional monomer, and combinations thereof.

 The aqueous composition can be formulated to exhibit a viscosity suitable for the intended use and application methods. Preferably the composition has a viscosity suitable
20 for spray applications. Useful aqueous compositions exhibit a viscosity no greater than 10,000 cps, in other embodiments no greater than 5,000 cps, in other embodiments no greater than 3,000 cps, in other embodiments no greater than 500 cps.

 The aqueous composition can be formulated to include from 20 % by weight to 60 % by weight solids (i.e., the components remaining after drying a one gram sample at
25 110°C for two hours), more preferably from 30 % by weight to 50 % by weight solids, most preferably from 35 % by weight to 45 % by weight solids, and to exhibit a pH less than 7, in some embodiments from 1 to 5, in some embodiments from about 2 to about 4. The pH of the composition can be altered to the desired level using any suitable acid or base including, e.g., sulfuric acid, phosphoric acid, erythorbic acid, triethanolamine,
30 ammonia, sodium hydroxide, potassium hydroxide, sodium carbonate, t-butylammonium hydroxide, and combinations thereof.

The aqueous composition can be prepared by admixing the aqueous hydroxy functional carboxy functional addition polymer and the condensation accelerator using any suitable mixing technique.

The aqueous composition can be applied to a variety of substrates and then
5 condensed, e.g., through the application of energy (e.g., heating) and evaporation of water, to form the condensed (i.e., crosslinked), dried polymer. Preferably the aqueous composition is heated in an oven at a temperature and for a period sufficient to condense the polymer, preferably from about 150°C to about 220°C for from about 2 to 5 minutes. The drying and curing functions can be carried out in two or more steps. One useful
10 method, which is known as B-staging, includes heating the composition at a temperature and for a time sufficient to substantially dry but not substantially cure the composition, and then heating the composition for a second period to effect curing.

The aqueous composition is particularly useful as a binder composition in fiberglass insulation. The glass fibers of the nonwoven web are preferably maintained in
15 fixed relation to each other through the dried composition. The fiberglass insulation preferably includes dried composition in an amount of from about 1 % by weight to about 20 % by weight dried based on the weight of the glass fibers, in some embodiments from about 5 % by weight to about 10 % by weight based on the weight of the glass fibers.

The aqueous composition can also be used as a binder composition in a variety of
20 applications including, e.g., for polymeric fibers including, e.g., synthetic polymer fibers including, e.g., polyolefin (e.g., polyethylene and polypropylene), polyester, polyacrylonitrile, polyvinyl acetate, polyvinyl chloride, polyamide, polyacrylamide, rayon, cellulose, cellulose polymers, and combinations thereof.

The fibers can be in a variety of forms including, e.g., individual fibers, nonwoven
25 and woven fibrous webs, sheets, lofty fibrous products, filaments, strands, ropes, rolls, batts, reinforcing mats for roofing applications, mats for flooring applications, reinforcement scrims, and combinations thereof.

The aqueous composition can be applied using a variety of application techniques including, e.g., spraying, soaking, immersing, saturating, coating, e.g., roll coating, curtain
30 coating, brush coating, beater deposition, and combinations thereof.

The fiberglass web can be useful in a variety of applications including, e.g., insulation, reinforcing mats for applications including, e.g., roofing and flooring, substrates for printed circuit boards, battery separators, filters, tape, duct liners, duct board, and reinforcement scrims.

- 5 The invention will now be described further by way of the following examples. All parts, ratios, percents and amounts stated in the Examples are by weight unless otherwise specified.

EXAMPLES

Test Procedures

- 10 Test procedures used in the examples include the following.

Viscosity

- Viscosity is measured using a Brookfield Model RVF-100 viscometer (Brookfield Engineering Laboratories, Inc., Stoughton, Massachusetts) at ambient room temperature
15 (i.e., 23°C to 25°C), using spindle # 2 run at 20 rotations per minute (rpm) for 20 minutes. After 20 minutes a reading is taken and recorded in centipoise.

Dry Tensile Strength

- A sample composition is reduced to 1 % solids solution with water. A glass
20 microfiber filter paper (20 cm x 30 cm) grade GF/C WHATMAN No. 1822-915 (Whatman International Ltd., Maidstone, England) is then immersed in the 1 % solids solution at ambient conditions (i.e., 23C and about 50 % relative humidity) for 5 minutes to saturate the microfiber filter paper. Excess solution is removed from the sheet using vacuum suction. The treated paper is then placed in a convection oven for 5 minutes at
25 180°C to cure the composition. The cured microfiber filter paper is then cut into 2 in x 5 in strips and tested for dry tensile strength according to the test method TAPPI T-494 om-96 Tensile Properties of Paper and Paperboard (Using Constant Rate Of Elongation Apparatus), 1996 (which is incorporated herein), with the following exceptions: at section
4.1.4, the crosshead speed is 0.1 in/min instead of 0.25 cm/min; at section 5.4, the
30 specimen size is 2 in x 5 in; at section 6.4, the span is 5 in instead of 7 in; at section 6.5,

the crosshead speed is 0.1 in/min instead of 0.25 cm/min. The results are reported in units of pounds of force (lbf).

Wet Tensile Strength Test Method

5 A cured microfibre filter paper prepared according to the Dry Tensile Strength Test Method is then conditioned in a temperature/humidity oven for 60 minutes at 110°C and 90 % relative humidity. The paper is allowed to equilibrate at ambient temperature for 1 hour and then cut into 2 in x 5 in strips. The strips are evaluated for wet tensile strength using the test method TAPPI T-494 om-96 Tensile Properties of Paper and Paperboard
10 (Using Constant Rate Of Elongation Apparatus), 1996 (which is incorporated herein) with the following exceptions: at section 4.1.4, the crosshead speed is 0.1 in/min instead of 0.25 cm/min; at section 5.4, the specimen size is 2 in x 5 in; at section 6.4, the span is 5 in instead of 7 in; and at section 6.5, the crosshead speed is 0.1 in/min instead of 0.25 cm/min. The results are reported in units of pounds of force (lbf).

15

Loss On Ignition (L.O.I.)

 A portion a cured microfiber filter paper prepared according to the dry strength test method is weighed and the weight recorded (W_1). The paper is placed in a crucible, which is then placed in a muffle furnace for 20 minutes at 700°C. The paper is then cooled in the
20 oven, removed from the oven and weighed and the weight is recorded (W_2). The binder loading is then calculated by dividing the change in weight ($W_2 - W_1$) by the original weight (W_1) of the microfiber filter paper and multiplying by 100. The results are recorded in units of %.

25 Method of Determining Acid Number

 Acid number is determined by placing a 2 g dried polymer sample in a 250 mL glass Erlenmeyer flask, and then adding 100 ml of acetone to the flask. A stirring bar is placed in the flask and the sample is refluxed with a water-cooled condenser on a with stirring until the sample is completely dissolved. If the sample has not dissolved after 30
30 minutes of refluxing use it as is. The solution is then allowed to cool to room temperature. One ml phenolphthalein indicator is added to the solution. The flask is then stirred while titrating to a pink end point using standardized 0.1 N alcoholic potassium hydroxide. The

endpoint should persist for five minutes. The volume of potassium hydroxide required to reach the endpoint is recorded in milliliters (ml).

A blank of 100 ml acetone is placed in a glass Erlenmeyer flask, 1 ml of phenolphthalein indicator is added to the solution, and the mixture is then titrated using
5 standardized 0.1 N alcoholic potassium to a pink endpoint. The volume of potassium hydroxide required to reach the endpoint is recorded in milliliters.

The acid number is then calculated according to the following equation:

$$\text{Acid Number} = \frac{(A \times N \times 56.1)}{w}$$

10 where A = milliliters of potassium hydroxide titrated (sample – blank), N = normality of the potassium hydroxide solution and w = grams of sample. The results are reported in mg KOH/g dried material.

Example 1

15 An aqueous solution polymer of 70/30 glacial acrylic acid/2-hydroxyethyl acrylate (HEA/AA) was prepared by charging 481.4 g water, 5.6 g 50 % hydrogen peroxide, and 0.097 g DISSOLVINE 4.5 % H-Fe (Akzo Nobel Chem. Inc., Lima, Ohio) to a reaction vessel. A monomer feed of 363.6 g glacial acrylic acid, 155.8 g 2-hydroxyethyl acrylate, and 2.11 g 2-mercaptoethanol was then fed into the reaction vessel. Additional mixtures
20 of 58.7 g water and 5.36 g 50 % hydrogen peroxide, and a mixture of 60 g water and 4.07 g erythorbic acid were then fed into the reaction vessel. A first mixture of 5.8 g water, 0.70 g tertbutylhydrogen peroxide, 5.8 g water, and 0.48 g erythorbic acid was then added to the reaction vessel, which was maintained at 70°C. A second mixture of 5.8 g water, 0.70 g tertbutylhydrogen peroxide, 5.8 g water, and 0.48 g erythorbic acid was then added
25 to the reaction vessel, which was maintained at 72°C.

PROXEL GXL biocide (Avecia Inc., Wilmington, Delaware) was then added to the reaction vessel in an amount of 4.81 g. The composition was adjusted with water to a solids content of 46 %, a pH of 1.47, and a viscosity of 5,000 cps. The resulting polymer had a number average molecular weight of 7500 and an acid number of 546 mg KOH/g
30 dried material.

Examples 2-6

Examples 2-6 were prepared according to the procedure described in Example 1 with the exception that the amount (i.e., % by weight) acrylic acid monomer and hydroxyethyl acrylate monomer (AA/HEA) added to the reaction vessel was as follows: 90/10 AA/HEA (Example 2), 80/20 AA/HEA (Example 3), 70/30 AA/HEA (Example 4), 60/40 AA/HEA (Example 5), and 50/50 AA/HEA (Example 6).

Three percent by weight sodium hypophosphite monohydrate based on the total solids weight was added to each of the compositions of Examples 2-6 after the polymers were prepared.

Example 7

An aqueous solution polymer of 70/30 glacial acrylic acid/2-hydroxyethyl acrylate (AA/2-HEA) was prepared by charging 600 g water, 5.6 g 50 % hydrogen peroxide, 0.1 g DISSOLVINE 4.5 % H-Fe (Akzo Nobel Chem. Inc.), and 0.055 g (based on 0.01% solids) SILQUEST A-171 silane (Crompton Corp., Greenwich, Connecticut) to a reaction vessel. Mixtures of 59 g water and 5.5 g 50 % hydrogen peroxide, and a mixture of 60 g water and 4 g erythorbic acid were then fed into the reaction vessel. A monomer feed of 364 g glacial acrylic acid, 156 g 2-hydroxyethyl acrylate, and 9.5 g 2-mercaptoethanol was then fed into the reaction vessel. A first mixture of 5.8 g water, 0.7 g 70 % tertbutylhydrogen peroxide, 5.8 g water, and 0.48 g erythorbic acid was then added to the reaction vessel, which was maintained at 70°C. A second mixture of 5.8 g water, 0.7 g 70 % tertbutylhydrogen peroxide, 5.8 g water, and 0.48 g erythorbic acid was then added to the reaction vessel, which was maintained at 70°C. A third mixture of 5.8 g water, 0.7 g 70 % tertbutylhydrogen peroxide, 5.8 g water, and 0.48 g erythorbic acid was then added to the reaction vessel, which was maintained at 70°C.

The aqueous solution polymer was cooled to less than 30°C and 50 % sodium hydroxide was added to the composition to achieve a pH of 2.35. The composition had a solids content of 41 %, and a viscosity of 195 cps. The resulting polymer had a number average molecular weight of 3910 and an acid number of 546 mg KOH/g dried material.

Example 8

An aqueous polymer solution of 70/30 (glacial acrylic acid/2-hydroxyethyl acrylate) was prepared by charging 713.9 g water, 6 g 50 % hydrogen peroxide, 0.1 g DISSOLVINE 4.5% iron solution and 10.8 g sodium hypophosphite monohydrate to a
5 reaction vessel and heated to 70°C. A monomer blend consisting of 404.4 g glacial acrylic acid and 173.31 g 2-hydroxyethyl acrylate (2-HEA) and was uniformly added to the reactor over a three hour period with mechanical agitation. At the same time, additional mixtures of 63.8 g water and 5.8 g 50 % hydrogen peroxide and a mixture of 66 g water and 4.3 g erythorbic acid were uniformly fed into the reactor over a 3.5 hour period. After
10 completion of the feeds, the reactor content was heated an additional 30 minutes at 70°C. The reactor was then charged with a mixture of 12.6 g water and 1.5 g tetrabutylhydrogen peroxide 70 % and a mixture of 12.6 g water and 1.04 g erythorbic acid and stirred an additional 15 minutes at 70°C.

The resulting aqueous solution polymer was cooled to room temperature. A
15 mixture of 15 g water and 12.3 g sodium hypophosphite monohydrate was then charged to the reactor.

The polymer had a number average molecular weight (Mn) of 7,360 g/mole

One part-per-hundred ammonium chloride based on the total weight of the aqueous solution polymer composition was then charged to the aqueous solution polymer
20 composition. The aqueous solution polymer composition was cured by drying in a forced air oven at 180°C for 5 minutes. The resulting cured composition exhibited a dry tensile strength of 11.8 lb/ft and a wet tensile strength of 4.1 lb/ft.

Example 9

25 An aqueous polymer solution of 70/30 (2-hydroxyethylacrylate/glacial acrylic acid) was prepared by charging 535 g water, 4.5 g 50% hydrogen peroxide, 0.1 g DISSOLVINE 4.5% iron solution, and 8.1 g sodium hypophosphite monohydrate to a reaction vessel and heated to 70°C. A blend consisting of 130 g glacial acrylic acid and 303 g 2-hydroxyethylacrylate (2-HEA) was uniformly added to the reactor over a three
30 hour period using mechanical agitation. At the same time, additional mixtures of 48 g water and 4.4 g 50% hydrogen peroxide and a mixture of 48 g water and 3.25 g erythorbic

acid were uniformly fed into the reactor over a 3.5-hour period. After completion of the feeds, the reactor content was heated an additional 30 minutes at 70°C. The reactor was then charged with a mixture of 4.7 g water and 0.6 g tetrabutylhydrogen peroxide and a mixture of 4.7 g water and 0.4 g erythorbic acid and stirred an additional 15 minutes at 70°C. The resulting solution polymer was charged with a mixture of 16 g sodium hypophosphite and 16 water.

The resulting aqueous solution polymer had a pH of 2.4, a viscosity of 320 cps at 25°C, and a solid content of 41%.

10 Example 10

An aqueous polymer solution of 70/30 (glacial acrylic acid/2-hydroxyethylacrylate) was prepared by charging 600 g water, 5.6 g 50% hydrogen peroxide, 0.1 g DISSOLVINE 4.5% iron solution, and 16 g sodium hypophosphite monohydrate to a reaction vessel and heated to 70°C. A blend of 364 g glacial acrylic acid and 156 g 2-hydroxyethylacrylate (2-HEA) was uniformly added to the reactor over a three hour period using mechanical agitation. At the same time, additional mixtures of 60 g water and 5.4 g 50 % hydrogen peroxide, and a mixture of 60 g water and 4 g erythorbic acid were uniformly fed into the reactor over a 3.5 hour period. After completion of the feeds, the reactor content was heated an additional 30 minutes at 70°C. The reactor was then charged with a mixture of 12 g water and 1.5 g tetrabutylhydrogen peroxide, and a mixture of 12 g water and 1 g erythorbic acid and stirred an additional 15 minutes at 70°C.

The resulting aqueous solution polymer had a pH of 2.5, a viscosity of 200 cps at 25°C, a solid content of 42 %, a number average molecular weight of 2,300 g/mol, a dry tensile strength of 6.1+/- 0.4 lb/f, and a wet tensile strength of 7.7 +/-0.7 lb/f.

The compositions of Examples 2- 10 were tested according to the above test methods to determine the following: pH, acid number, viscosity, Dry Tensile Strength, Wet Tensile strength, and Loss On Ignition (L.O.I.). The results are reported in Table 1.

Table 1

Example	PH	Viscosity (cps)	Solids	Acid Number	AA/HEA	Dry Tensile Strength (lbf)	Wet Tensile Strength (lbf)	L.O.I. (%)
2	1.5	350	42	702	90/10	6.1	5.8	7.1
3	1.7	280	41	624	80/20	9.8	5.8	8
4	1.9	220	41	546	70/30	10.2	5.7	5.4
5	1.8	220	41	468	60/40	10.2	6.2	6.4
6	1.7	190	41	390	50/50	10.9	10.4	12
7	2.4	195	41	546	70/30	NT	NT	NT
8	2.4	650	41	546	70/30	11.8	4.1	7
9	2.4	320	41	237	30/70	NT	NT	NT
10	2.5	200	42	237	30/70	6.1	7.7	NT
Control (Glass fiber sheet)	NA	NA	NA	NA	0/0	2.6	NT	0

NA = not applicable

NT = not tested

Other embodiments are within the claims.

5 What is claimed is:

1. An aqueous composition comprising
- a) aqueous hydroxy functional, carboxy functional polymer comprising the reaction product of
- 5 i) at least 5 % by weight α,β -ethylenically unsaturated hydroxy functional monomer,
- ii) at least 30 % by weight ethylenically unsaturated carboxylic acid monomer,
- 10 iii) 0 % by weight to less than 50 % by weight α,β -ethylenically unsaturated nonhydroxy functional, noncarboxy functional monomer, and
- iv) chain transfer agent; and
- b) condensation accelerator.
2. The aqueous composition of claim 1, wherein said aqueous hydroxy
- 15 functional carboxy functional polymer has a number average molecular weight no greater than 10,000.
3. The aqueous composition of any one of claims 1 or 2, wherein said aqueous composition has a pH from about 2 to about 4.
- 20 4. The aqueous composition of any one of claims 1, 2 or 3, wherein said α,β -ethylenically unsaturated hydroxy functional monomer comprises 2-hydroxy ethyl acrylate.
- 25 5. The aqueous composition of any one of claims 1-3, or 4, wherein said ethylenically unsaturated carboxylic acid monomer comprises glacial acrylic acid.
6. The aqueous composition of any one of claims 1-4 or 5, wherein said ethylenically unsaturated carboxylic acid monomer comprises glacial acrylic acid.

30

7. The aqueous composition of any one of claims 1-5 or 6, wherein said aqueous hydroxy functional carboxy functional polymer comprises from 20 % by weight to 60 % by weight solids.

5 8. The aqueous composition of any one of claims 1-6 or 7, wherein said aqueous hydroxy functional carboxy functional polymer has an acid number of at least 300 mg KOH/g dried polymer.

9. The aqueous composition of any one of claims 1-7 or 8, wherein said
10 composition exhibits a dry tensile strength of at least 5 when tested according to the Dry Tensile Strength Test Method.

10. The aqueous composition of any one of claims 1-8 or 9, wherein said
15 composition exhibits a wet tensile strength of at least 5 when tested according to the Wet Tensile Strength Test Method.

11. The aqueous composition of claim 1, wherein said aqueous hydroxy functional, carboxy functional polymer comprises the reaction product of
20 i) from 10 % by weight to 70 % by weight α,β -ethylenically unsaturated hydroxy functional monomer,
ii) from 40 % by weight to 90 % by weight ethylenically unsaturated carboxylic acid monomer, and
iii) chain transfer agent.

12. The aqueous composition of claim 1, wherein said aqueous hydroxy functional, carboxy functional polymer comprises the reaction product of
25 i) from 20 % by weight to 60 % by weight α,β -ethylenically unsaturated hydroxy functional monomer,
ii) from 50 % by weight to 90 % by weight ethylenically unsaturated
30 carboxylic acid monomer, and
iii) chain transfer agent.

13. The aqueous composition of claim 1, wherein said aqueous hydroxy functional, carboxy functional polymer comprises the reaction product of

- 5 i) from 20 % by weight to 60 % by weight α,β -ethylenically unsaturated hydroxy functional monomer,
- ii) from 60 % by weight to 80 % by weight ethylenically unsaturated carboxylic acid monomer, and
- iii) chain transfer agent.

10 14. Fiberglass insulation comprising

- a) a nonwoven web comprising glass fibers; and
- b) a binder composition comprising the composition of claim 1.

15 15. The fiberglass insulation of claim 14, wherein said fiberglass insulation comprises from about 5 % by weight to about 14 % by weight dried binder composition based on the weight of the glass fibers.

16. A method of making fiberglass insulation comprising:

- 20 a) contacting glass fibers with a binder composition comprising the composition of claim 1; and
- b) curing said composition.

25

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 03/25503

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09J133/02 C09J133/14 C08F220/04 C08F220/20 C08F8/14
C08L33/02 D04H1/64 B05D3/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09J C08L D04H B05D C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 990 729 A (ROHM & HAAS ;JOHNS MANVILLE INT INC (US)) 5 April 2000 (2000-04-05) claim 1; example 1; table 1 ---	1-10
A	EP 0 583 086 A (ROHM & HAAS) 16 February 1994 (1994-02-16) claim 1; examples 1-3 ---	1-10
A	EP 0 397 410 A (ALLIED COLLOIDS LTD) 14 November 1990 (1990-11-14) claim 1; example 1 ---	1-10
A	US 4 077 926 A (KOTTKE ROGER H ET AL) 7 March 1978 (1978-03-07) claim 1; example 1 -----	1-10



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

19 December 2003

Date of mailing of the international search report

02/01/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Krail, G

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 03/25503

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0990729	A	05-04-2000	US 6331350 B1 EP 0990729 A1	18-12-2001 05-04-2000
EP 0583086	A	16-02-1994	US 5661213 A AT 160597 T AU 667921 B2 AU 4212793 A BR 9303315 A CA 2101450 A1 CN 1083844 A ,B CZ 9301592 A3 DE 69315393 D1 DE 69315393 T2 DK 583086 T3 EP 0583086 A1 ES 2109441 T3 FI 933473 A GR 3026182 T3 HK 1001096 A1 HU 66516 A2 IL 106446 A JP 3215233 B2 JP 6184285 A MX 9304685 A1 NZ 248215 A SK 82993 A3 US 6136916 A US 5763524 A US 6221973 B1 ZA 9305397 A	26-08-1997 15-12-1997 18-04-1996 28-04-1994 22-03-1994 07-02-1994 16-03-1994 16-03-1994 08-01-1998 30-04-1998 02-02-1998 16-02-1994 16-01-1998 07-02-1994 29-05-1998 22-05-1998 28-12-1994 30-09-1997 02-10-2001 05-07-1994 31-03-1994 26-09-1995 06-04-1994 24-10-2000 09-06-1998 24-04-2001 07-02-1994
EP 0397410	A	14-11-1990	CA 2016395 A1 DE 69028341 D1 DE 69028341 T2 EP 0397410 A2 ES 2093012 T3 JP 3033113 A JP 3139710 B2 US 5147956 A US 5280079 A	10-11-1990 10-10-1996 06-03-1997 14-11-1990 16-12-1996 13-02-1991 05-03-2001 15-09-1992 18-01-1994
US 4077926	A	07-03-1978	NONE	