



HU000028562T2

(19) **HU****MAGYARORSZÁG**
Szellemi Tulajdon Nemzeti Hivatala(11) Lajstromszám: **E 028 562**(13) **T2****EURÓPAI SZABADALOM**
SZÖVEGÉNEK FORDÍTÁSA(21) Magyar ügyszám: **E 10 715505**(22) A bejelentés napja: **2010. 04. 21.**

(96) Az európai bejelentés bejelentési száma:

EP 20100715505

(97) Az európai bejelentés közzétételi adatai:

EP 2421645 A1 **2010. 10. 28.**

(97) Az európai szabadalom megadásának meghirdetési adatai:

EP 2421645 B1 **2015. 11. 11.**(51) Int. Cl.: **B01J 23/85**

(2006.01)

B01J 21/02

(2006.01)

B01J 23/88

(2006.01)

B01J 271/85

(2006.01)

B01J 271/88

(2006.01)

B01J 35/00

(2006.01)

B01J 35/02

(2006.01)

B01J 37/00

(2006.01)

B01J 37/02

(2006.01)

C10G 45/08

(2006.01)

C10G 49/04

(2006.01)

(86) A nemzetközi (PCT) bejelentési szám:

PCT/EP 10/002458

(87) A nemzetközi közzétételi szám:

WO 10121807

(30) Elsőbbségi adatok:

171253 P**2009. 04. 21.****US**

(72) Feltalálók:

JANSEN, Marcel, Adriaan, NL-2151 JM Nieuw Vennep (NL)**TROMP, Henk, Jan, NL-3512 AH Utrecht (NL)****OOGJEN, Bob, Gerardus, NL-1326 RR Almere (NL)****THOONEN, Sander, Hendrikus, Lambertus, NL-3544 ZB Utrecht (NL)****NIEMAN, Jan, NL-3607 CB Maarssen (NL)****VEERMAN, Wilhelmus, Clemens, Jozef, NL-1131 BB****Volendam (NL)**

(73) Jogosult(ak):

Albemarle Europe Sprl., 1348 Louvain-la-Neuve (BE)

(74) Képvisező:

Danubia Szabadalmi és Jogi Iroda Kft., Budapest

(54)

Foszfors és bórt tartalmazó hidrogénező katalizátor

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.



(11) **EP 2 421 645 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:

11.11.2015 Bulletin 2015/46

(21) Application number: **10715505.3**

(22) Date of filing: **21.04.2010**

(51) Int Cl.:

B01J 23/85 (2006.01)	B01J 23/88 (2006.01)
B01J 27/185 (2006.01)	B01J 27/188 (2006.01)
B01J 21/02 (2006.01)	B01J 35/00 (2006.01)
C10G 45/08 (2006.01)	C10G 49/04 (2006.01)
B01J 35/02 (2006.01)	B01J 37/00 (2006.01)
B01J 37/02 (2006.01)	

(86) International application number:

PCT/EP2010/002458

(87) International publication number:

WO 2010/121807 (28.10.2010 Gazette 2010/43)

(54) **HYDROTREATING CATALYST CONTAINING PHOSPHORUS AND BORON**

HYDRIERUNGSKATALYSATOR BEINHALTEND PHOSPHOR UND BOR

CATALYSEUR D'HYDROTRAITEMENT CONTENANT DU PHOSPHORE ET DU BORE

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL
PT RO SE SI SK SM TR**

(30) Priority: **21.04.2009 US 171253 P**

(43) Date of publication of application:

29.02.2012 Bulletin 2012/09

(73) Proprietor: **Albemarle Europe Sprl.**

1348 Louvain-la-Neuve (BE)

(72) Inventors:

- **JANSEN, Marcel, Adriaan**
NL-2151 JM Nieuw Vennep (NL)
- **TROMP, Henk, Jan**
NL-3512 AH Utrecht (NL)

• **OOGJEN, Bob, Gerardus**

NL-1326 RR Almere (NL)

• **THOONEN, Sander, Hendrikus, Lambertus**

NL-3544 ZB Utrecht (NL)

• **NIEMAN, Jan**

NL-3607 CB Maarssen (NL)

• **VEERMAN, Wilhelmus, Clemens, Jozef**

NL-1131 BB Volendam (NL)

(74) Representative: **Andrae | Westendorp**

Patentanwälte Partnerschaft

Uhlandstraße 2

80336 München (DE)

(56) References cited:

US-A- 2 938 001	US-A- 3 125 507
US-A- 3 453 219	US-A1- 2006 070 915
US-A1- 2009 188 834	

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

TECHNICAL FIELD

5 [0001] The present invention is in the field of catalysts useful for hydrotreating hydrocarbon feedstocks in refining processes.

THE INVENTION

10 [0002] In general, hydrotreating catalysts are composed of a carrier having deposited thereon a Group VIB (of the Periodic Table) metal component and a Group VIII (of the Periodic Table) metal component. The most commonly employed Group VIB metals are molybdenum and tungsten, while cobalt and nickel are the conventional Group VIII metals. Phosphorus may also be present in the catalyst. The prior art processes for preparing these catalysts are characterized in that a carrier material is composited with hydrogenation metal components, for example by impregnation, after which the composite is calcined to convert the metal components into their oxides. Before being used in hydrotreating, the catalysts are generally presulfided to convert the hydrogenation metals into their sulfides. Processes for activating and regenerating such catalysts are also known.

15 [0003] The US patent 2,938,001 discloses a catalyst comprising a refractory inorganic oxide base containing from about 5% to about 80% by weight of boron phosphate and a catalytic amount of a hydrogenating metal component, the metal of said hydrogenating component being a heavy metal in groups V to VIII of the periodic table. The catalyst is prepared by mixing phosphoric acid, boric acid and water to form a solution, evaporation of the water, calcination and grinding to prepare boron phosphate. The boron phosphate is mixed with alumina monohydrate and binding agent, and pills are formed and calcined following which impregnation with a cobalt and molybdenum containing solution, and a third calcination takes place.

20 [0004] U.S. Patent 3,453,219 discloses a crude oil hydrotreating catalyst which comprises at least one metallic component selected from the group consisting of the metals of Groups VI-B and VIII of the Periodic Table, and compounds thereof, composited with a carrier material of coprecipitated alumina and silica containing boron phosphate combined therewith while in the wet state, said carrier material being characterized in that the alumina and silica are coprecipitated at a pH of at least about 8.0 from aqueous aluminum salt and water glass solutions, said catalyst further characterized in that the apparent bulk density thereof is less than 0.35 gram/cc. The catalyst is prepared by mixing a filtered aluminum hydroxide hydrogel with a phosphoric acid-boric acid solution with subsequent drying at 300 °F. This material is impregnated with a solution comprising molybdenum oxide, nickel nitrate hexahydrate and ammonium hydroxide, dried at 250 °F and calcined for an hour at 1100 °F.

25 [0005] However, unexpectedly, highly effective catalysts containing a unique combination of both phosphorus and boron have now been discovered. In particular, it has been discovered that surprisingly significant improvement in catalytic activity can be achieved using particular, relatively elevated amounts of both boron and phosphorus components in the catalyst.

30 [0006] Thus, in one embodiment of the invention there is provided a catalyst comprising at least one Group VIB metal component, at least one Group VIII metal component, a phosphorus component, and a boron-containing carrier component, wherein the amount of the phosphorus component is at least 1 wt % , expressed as an oxide (P_2O_5) and based on the total weight of the catalyst, and the amount of the boron component is in the range of 1 to 13 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst, the catalyst being further defined by reference to its process of preparation.

35 [0007] The method comprises co-extruding a boron source with a carrier to form a boron-containing carrier extrudate, drying and calcining the extrudate, and impregnating the calcined extrudate with a solution comprised of a phosphorus source, at least one Group VIB metal source and/or at least one Group VIII metal source. Co-extrusion of the boron source has been found to be particularly and surprisingly advantageous when compared to, e.g., preparing the support via impregnation of the boron source. One feature co-extrusion is that it enable use of higher boron concentrations in the carrier and, therefore, the final catalyst. Co-extrusion with the carrier also permits a single calcination of the combined support, rather than multiple calcination steps as in typical impregnation procedures. In the process, the amount of the boron source and the amount of the phosphorus source is sufficient so as to form a catalyst composition at least having a boron content in the range of 1 wt% to 13 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst, and a phosphorus content of at least 1 wt%, expressed as an oxide (P_2O_5) and based on the total weight of the catalyst.

40 [0008] Another embodiment of the invention is a hydrotreating process carried out employing the catalyst composition.

45 [0009] These and still other embodiments, advantages and features of the present invention shall become further apparent from the following detailed description. The invention is defined by the appended claims.

FURTHER DETAILED DESCRIPTION OF THE INVENTION

[0010] Unless otherwise indicated, weight percent (wt%) as used herein is the weight percent of the specified form of the substance, based upon the total weight of the product for which the specified substance or form of substance is a constituent or component. It should further be understood that, when describing steps or components or elements as being preferred in some manner herein, they are preferred as of the initial date of this disclosure, and that such preference(s) could of course vary depending upon a given circumstance or future development in the art. Moreover, "boron source" and "boron component" are used herein interchangeably and are synonymous with one another. Also, the term "boron-containing carrier" is intended to refer to any carrier as specified herein which has been contacted with a boron source prior to drying and calcining, and preferably "contacted" in this context shall encompass mixing, and in particular, co-extrusion.

[0011] The Group VIB metal component in catalysts of the invention is selected from the group consisting of molybdenum, tungsten, chromium and a mixture of two or more of the foregoing, while molybdenum and/or tungsten is typically preferred, and molybdenum is typically more preferred. The Group VIII metal component is selected from group consisting of iron, cobalt and nickel, while nickel and/or cobalt is typically preferred, and nickel is typically more preferred. Preferred mixtures of metals include a combination of (a) nickel and/or cobalt and (b) molybdenum and/or tungsten. When hydrodesulfurisation (sometimes hereafter referred to as "HDS") activity of the catalyst is important, a combination of cobalt and molybdenum is advantageous and typically preferred. When hydrodenitrogenation (sometimes hereafter referred to as "HDN") activity of the catalyst is important, a combination of nickel and either molybdenum or tungsten is advantageous and typically preferred.

[0012] The Group VIB metal component can be an oxide, an oxo acid, or an ammonium salt of an oxo or polyoxo anion. The Group VIB metal compounds are formally in the +6 oxidation state. Oxides and oxo acids are preferred Group VIB metal compounds. Suitable Group VIB metal compounds in the practice of this invention include chromium trioxide, chromic acid, ammonium chromate, ammonium dichromate, molybdenum trioxide, molybdic acid, ammonium molybdate, ammonium para-molybdate, tungsten trioxide, tungstic acid, ammonium tungsten oxide, ammonium metatungstate hydrate, ammonium para-tungstate, and the like. Preferred Group VIB metal compounds include chromium trioxide, molybdenum trioxide, molybdic acid, tungstic acid and tungsten trioxide. Mixtures of any two or more Group VIB metal compounds can be used; a mixture of products will be obtained when compounds having different Group VIB metal are used. The amount of Group VIB metal compound employed in the catalyst will typically be in the range of 18 to 28 wt% (as trioxide), based on the total weight of the catalyst, but could be as low as, e.g., 16 wt%. In one embodiment of this invention, the amount of Group VIB metal compound is in the range of 19 to 26 wt%, or 22 to 26 wt% (as trioxide), based on the total weight of the catalyst.

[0013] The Group VIII metal component is usually an oxide, hydroxide or salt, preferably a salt. Suitable Group VIII metal compounds include, but are not limited to, cobalt oxide, cobalt hydroxide, cobalt nitrate, cobalt carbonate, cobalt hydroxy-carbonate, cobalt acetate, cobalt citrate, nickel oxide, nickel hydroxide, nickel nitrate, nickel carbonate, nickel hydroxy-carbonate, nickel acetate, and nickel citrate. Preferred Group VIII metal compounds include cobalt carbonate, cobalt hydroxy-carbonate, nickel hydroxy-carbonate and nickel carbonate. Mixtures of two or more Group VIII metal compounds can be used; when the Group VIII metals of the compounds in the mixture are different, a mixture of products will be obtained. The amount of Group VIII metal compound employed in the catalyst will typically be in the range of 2 to 8 wt% (as oxide), based on the total weight of the catalyst. In a preferred embodiment of this invention, the amount of Group VIII metal compound is in the range of 3 to 6 wt% (as oxide), based on the total weight of the catalyst.

[0014] In the practice of this invention, the phosphorus component is a compound which is typically a water soluble, acidic phosphorus compound, particularly an oxygenated inorganic phosphorus-containing acid. Examples of suitable phosphorus compounds include metaphosphoric acid, pyrophosphoric acid, phosphorous acid, orthophosphoric acid, triphosphoric acid, tetraphosphoric acid, and precursors of acids of phosphorus, such as ammonium hydrogen phosphates (mono-ammonium di-hydrogen phosphate, diammonium mono-hydrogen phosphate, tri-ammonium phosphate). Mixtures of two or more phosphorus compounds can be used. The phosphorus compound may be used in liquid or solid form. A preferred phosphorus compound is orthophosphoric acid (H_3PO_4) or an ammonium hydrogen phosphate, preferably in aqueous solution. The amount of phosphorus compound employed in the catalyst will be sufficient to provide at least 1 wt% (as oxide P_2O_5), based on the total weight of the catalyst, or in another aspect of the invention, at about 2 wt% (as oxide P_2O_5), based on the total weight of the catalyst. In another aspect, the amount of phosphorus compound employed will be sufficient to provide phosphorus in the range of 4 to 10 wt% (as oxide P_2O_5), based on the total weight of the catalyst. In another aspect of this invention, the amount of phosphorus compound employed is sufficient to provide phosphorus in the range of 4 to 7 wt% (as oxide P_2O_5), based on the total weight of the catalyst.

[0015] The boron component will typically be meta-boric acid (HBO_2), ortho-boric acid (H_3BO_3), ammonium borate tetra-hydrate $[(\text{NH}_4)_2\text{B}_4\text{O}_7 \cdot 4 \text{H}_2\text{O}]$, sodium tetra borate, ammonium borate, ammonium tetra borate $(\text{NH}_4)_2\text{B}_4\text{O}_7$, boric oxide (B_2O_3), various mono-, di- and tri-alkyl amine borates (e.g., triethanol amine borate), ammonium tetra phenyl borate, or the like. Suitable non-limiting examples of the boron component include ortho-boric acid (H_3BO_3) and ammo-

nium tetra borate tetra-hydrate $[(\text{NH}_4)_2\text{B}_4\text{O}_7 \cdot 4\text{H}_2\text{O}]$ and mixtures of two or more of the foregoing. The amount of the boron component in the catalyst will typically be in the range of 1 to 13 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst. In a preferred embodiment of this invention, the amount of boron component is in the range of 2 wt% to 8 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst. In another aspect of the invention, the amount of boron component is in the range of 4 wt% to 6 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst.

[0016] The catalyst carrier may comprise the conventional oxides, e.g., alumina, silica, silica-alumina, alumina with silica-alumina dispersed therein, silica-coated alumina, alumina-coated silica, magnesia, zirconia, and titania, as well as mixtures of these oxides. As a rule, preference is given to the carrier being of alumina, silica-alumina, alumina with silica-alumina dispersed therein, alumina-coated silica or silica-coated alumina. Special preference is given to alumina and alumina containing up to 10 wt% of silica. A carrier containing a transition alumina, for example an eta, theta, or gamma alumina is preferred within this group, wherein a gamma-alumina carrier is most especially preferred. The precursor of the catalyst carrier co-extruded with the boron source of this invention prior to calcination is, for example, boehmite, pseudo-boehmite or the like, and can be in the form of a wet cake or dried (e.g., spray-dried) material.

[0017] As noted earlier, it is preferred that the boron component is co-extruded with the carrier component, as it is believed, without being bound to theory, that co-extrusion facilitates use of the higher concentration of boron component employed in the highly active catalyst of this invention. It is further believed, without being bound to theory, that the moment of boron component addition to the carrier for co-extrusion can affect the physical properties of the carrier. It is therefore typically preferred, although not always required or preferred, that addition of the boron component is carried out at the initiation of kneading. The desired properties of the final product may dictate that one add the boron component earlier or later in the kneading process.

[0018] The catalyst's pore volume (measured via mercury penetration, contact angle 140° , surface tension of 480 dyn/cm) is not critical to the process according to the invention and will generally be in the range of 0.2 to 2 ml/g, preferably 0.3-1 ml/g. The specific catalyst surface area is not critical to the process according to the invention either and will generally be in the range of 50 to 400 m^2/g (measured using the BET method). Preferably, the catalyst will have a median pore diameter in the range of 7-15 nm, as determined by mercury porosimetry, and at least 60% of the total pore volume will be in the range of ± 2 nm from the median pore diameter.



[0019] The catalyst is employed in the conventional manner in the form of, for example, spheres or extrudates. Examples of suitable types of extrudates have been disclosed in the literature (see, int. al., U.S. Pat. No. 4,028,227). Highly suitable for use are cylindrical particles (which may be hollow or not) as well as symmetrical and asymmetrical polylobed particles (2, 3 or 4 lobes).

[0020] In forming the catalyst of this invention, the amount of the boron source and the amount of the phosphorus source should be sufficient so as to form a catalyst composition at least having a boron content in the range of 1 wt% to 13 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst, and a phosphorus content of at least 1 wt%, expressed as an oxide (P_2O_5) and based on the total weight of the catalyst.

[0021] Formation of the catalyst will normally involve at least co-extruding a boron source with a carrier to form a boron-containing carrier extrudate, drying and calcining the extrudate, and impregnating the calcined extrudate with a solution comprised of a phosphorus source, at least one Group VIB metal source and/or at least one Group VIII metal source. Other additives to the solution optionally may be included, such as organic additives such as (i) an organic compound selected from the group consisting of compounds comprising at least two oxygen atoms and 2 - 10 carbon atoms and the compounds built up from these compounds, or (ii) an organic compound comprising at least one covalently bonded nitrogen atom and at least one carbonyl moiety, or both (i) and (ii). The organic compound under (i) above preferably is selected from the group of compounds comprising at least two oxygen-containing moieties, such as a carboxyl, carbonyl or hydroxyl moiety, and 2 - 10 carbon atoms, and the compounds built up from these compounds. The latter may be, e.g., the ether, ester, acetal, acid chloride, acid amide, oligomer or polymer of this organic compound. Examples of suitable organic compounds include citric acid, tartaric acid, oxalic acid, malonic acid, malic acid, butanediol, pyruvic aldehyde, glycol aldehyde, and acetaldol. Organic compounds selected from the group of compounds comprising at least two hydroxyl groups and 2 - 10 carbon atoms per molecule and the compounds built up from these compounds are even more preferred. These include, e.g., tartaric acid, or aliphatic alcohols such as ethylene glycol, propylene glycol, glycerin, trimethylol ethane, trimethylol propane, etc. Compounds built up from these organic compounds include oligo- and polymers, e.g., diethylene glycol, dipropylene glycol, trimethylene glycol, triethylene glycol, tributylene glycol, tetraethylene glycol, tetrapentylene glycol. This range can be extrapolated to include, e.g., polyethers like polyethylene glycol. For this last compound, polyethylene glycol with a molecular weight between 200 and 8,000 is preferred. Other compounds built up from these organic compounds are, e.g., ethers such as ethylene glycol monobutyl ether, diethylene glycol monomethyl ether, diethylene glycol monoethyl ether, diethylene glycol monopropyl ether, and diethylene glycol monobutyl ether. Preferred organic compounds are, int. al., ethylene glycol, diethylene glycol, polyethylene glycol, or mixtures thereof. Another group of organic compounds comprising at least two hydroxyl groups and 2 - 10 carbon atoms per molecule is formed by, e.g., monosaccharides such as glucose and fructose. Compounds built up from these organic

compounds include oligo- and polymers, e.g., disaccharides such as lactose, maltose, and saccharose and polysaccharides.

[0022] The organic compound under (ii) preferably comprises at least two carbonyl moieties. It is preferred that at least one carbonyl moiety is present in a carboxyl group. It is furthermore preferred that at least one nitrogen atom is covalently bonded to at least two carbon atoms. A preferred organic compound satisfies formula (I) or (II)



wherein R₁, R₂, R₁' and R₂' are independently selected from alkyl, alkenyl, and allyl, with up to 10 carbon atoms optionally substituted with one or more groups selected from carbonyl, carboxyl, ester, ether, amino, or amido. R₃ is an alkylene group with up to 10 carbon atoms which may be interrupted by -O- or -NR₄-. R₄ is selected from the same group as indicated above for R₁. The R₃ alkylene group may be substituted with one or more groups selected from carbonyl, carboxyl, ester, ether, amino, or amido. As has been set out above, it is essential that the organic compound of formula (I) or (II) comprises at least one carbonyl moiety. Preferably, at least two of R₁, R₂, R₁' and R₂' (formula (I)) and at least two of R₁, R₂ and R₁' (formula (II)) have the formula -R₅-COOX, wherein R₅ is an alkylene group having 1-4 carbon atoms, and X is hydrogen or another cation, such as an ammonium, sodium, potassium and/or lithium cation. If X is a multivalent cation, one X can adhere to two or more -R₅-COO groups. Typical examples of a compound of formula (I) are ethylene diamine(tetra)acetic acid (EDTA), hydroxyethylene diamine triacetic acid, and diethylene triamine pentaacetic acid. A typical example of a compound of formula (II) is nitrilotriacetic acid (NTA).

[0023] The co-extrusion is carried out by adding the boron component to the alumina precursor component during the kneading step. The moment of addition is not fixed. The boron component is added as a solid / solution. During the kneading step, the mix is heated to a desired temperature to remove any excess of solvent/water if needed. Kneading is finished when the desired moisture content (as determined by Loss on Ignition at a temperature in the range of 500-600°C) is reached. Next, the mix is shaped to extrudates by using a suitable shaping technique. This technique can be extrusion, palletizing or pressing.

[0024] The extrudate so formed is then dried at a temperature in the range of 80°-200°C to remove a substantial amount of solvent/water and then calcined under air or inert conditions with or without steam at a temperature normally in the range of 400° - 900°C, resulting in the case of alumina, in a carrier containing a transition alumina e.g., a gamma, theta or eta-alumina, although a temperature outside of the latter range is possible, depending upon the support material employed. The calcination can be in a static or rotating mode. As will now be known by those of skill in the art, the drying times and calcining times employed can vary significantly depending upon various factors, including without limitation the temperature ramp rate, if any, and the types and amounts of materials present, but in all cases should be sufficient to remove volatiles to the extent desired, or to permit desired reactions to sufficiently take place. Typical drying time will be, e.g., at least 30 minutes at the maximum drying temperature, and typical calcining time will be, e.g., at least 30 minutes at the maximum calcining temperature.

[0025] The calcined extrudate is then impregnated with a solution comprising the phosphorous source, a Group VIB metal source and/or a Group VIII metal source. Impregnation is carried out by pore volume impregnation with a impregnation solution comprising the selected additives in an appropriate solvent. The solvent used in preparing the additive impregnation solution is generally water, although other components such as methanol, ethanol and other alcohols may also be suitable. Impregnation can be carried out at room temperature or at elevated temperatures. Instead of impregnating techniques, dipping methods, spraying methods., etc can be used. After impregnation, an optional drying step at a temperature in the range of 25 - 220 °C is carried out. In another embodiment of the invention, when no organic additive has been incorporated to produce the final catalyst, the impregnated calcined extrudate can optionally be again calcined at a temperature in the range of 250 to 700°C until a desired Loss on Ignition is reached.

[0026] Optionally, catalysts of the invention may be subjected to a sulfidation step (treatment) to convert the metal components to their sulfides. In the context of the present specification, the phrases "sulfiding step" and "sulfidation step" are meant to include any process step in which a sulfur-containing compound is added to the catalyst composition and in which at least a portion of the hydrogenation metal components present in the catalyst is converted into the sulfidic form, either directly or after an activation treatment with hydrogen. Suitable sulfidation processes are known in the art. The sulfidation step can take place *ex situ* to the reactor in which the catalyst is to be used in hydrotreating hydrocarbon feeds, *in situ*, or in a combination of *ex situ* and *in situ* to the reactor.

[0027] *Ex situ* sulfidation processes take place outside the reactor in which the catalyst is to be used in hydrotreating hydrocarbon feeds. In such a process, the catalyst is contacted with a sulfur compound, e.g., a polysulfide or elemental sulfur, outside the reactor and, if necessary, dried. In a second step, the material is treated with hydrogen gas at elevated temperature in the reactor, optionally in the presence of a feed, to activate the catalyst, *i.e.*, to bring the catalyst into the sulfided state.

[0028] *In situ* sulfidation processes take place in the reactor in which the catalyst is to be used in hydrotreating hydrocarbon feeds. Here, the catalyst is contacted in the reactor at elevated temperature with a hydrogen gas stream mixed with a sulphiding agent, such as hydrogen sulfide or a compound which under the prevailing conditions is decomposable into hydrogen sulphide. It is also possible to use a hydrogen gas stream combined with a hydrocarbon feed comprising a sulfur compound which under the prevailing conditions is decomposable into hydrogen sulfide. In the latter case, it is possible to sulfide the catalyst by contacting it with a hydrocarbon feed comprising an added sulfiding agent (spiked hydrocarbon feed), and it is also possible to use a sulfur-containing hydrocarbon feed without any added sulfiding agent, since the sulfur components present in the feed will be converted into hydrogen sulfide in the presence of the catalyst. Combinations of the various sulfiding techniques may also be applied. The use of a spiked hydrocarbon feed may be preferred.

[0029] The catalyst compositions of this invention are those produced by the above-described process, whether or not the process included an optional sulfiding step.

[0030] The formed catalyst product of this invention is suitable for use in hydrotreating, hydrodenitrogenation and/or hydrodesulfurization (also collectively referred to herein as "hydrotreating") of hydrocarbon feed stocks when contacted by the catalyst under hydrotreating conditions. Such hydrotreating conditions are temperatures in the range of 250° - 450°C, pressure in the range of 5 - 250 bar, liquid space velocities in the range of 0.1 - 10 liter / hour and hydrogen / oil ratios in the range of 50 - 2000 NI/I. Examples of suitable hydrocarbon feeds to be so treated vary widely, and include middle distillates, kero, naphtha, vacuum gas oils, heavy gas oils, and the like.

[0031] The following describes experimental preparation of the support and the catalyst, as well as use of the catalyst in hydrotreating a hydrocarbon feedstock to illustrate activity of the catalysts so formed. This information is illustrative only, and is not intend to limit the invention in any way.

Examples

Activity test

[0032] The activity test was carried out in a micro flow reactor. Light Gas Oil (LGO) spiked with dimethyl disulfide (DMDS) (total S content of 3.6 wt%) was used for presulphiding, Heavy Gas Oil (HGO), having a S content of 1.6 wt.% and N content of 1050 ppm, Vacuum Gas Oil (VGO), having a S content of 1.8 wt.% and N content of 1152 ppm and Light Gas Oil (LGO), having a S content of 1.2 wt.% and a N content of 94 ppm, were used for testing. Detailed information about feed and test condition is given in Tables 1 - 5.

[0033] The relative weight activities for the various catalysts were determined as follows. For each catalyst the reaction constant k_{wt} was calculated from the following formula:

$$k_{wt} = WHSV * 1/(n-1) \times (1/S^{n-1} \times 1/S_0^{n-1})$$

in which the S stands for percentage of sulfur in the product and S_0 for the percentage of sulfur in the feed, and n stands for the reaction order of the hydrodesulfurisation reaction. For HC-PT and FCC-PT mode a n of 1.75 was used. For ULSD a n of 1.2 was used

For nitrogen the k_{wt} was calculated from the following formula:

$$k_{wt} = \ln(N_0 / N) * WHSV$$

in which the N stands for the nitrogen content in the product and N_0 for the nitrogen content in the feed.

[0034] In the tables, S = sulfur, N = nitrogen, ToS = time on stream, LHSV = liquid hourly space velocity, IBP = initial boiling point, FBP = final boiling point.

Table 1. Feed properties

Feed	wt% S	ppm N	Density (g/ml)	IBP (°C)	FBP (°C)
HGO	1.578	1050	0.9443 (@ 15.5 C)	139	482
VGO	1.763	1152	0.9221 (@ 15.5C)	265	600
LGO	1.167	94	0.8366 (@ 15.5C)	114	420

Presulphiding / testing conditions**[0035]****Table 2.** Test conditions HC-PT test, Feed HGO.

	Presulphiding	Testing
Temperature (°C)	320	345
H2 pressure (bar)	45	100
LHSV	3	2.75
H2/oil	300	1000
Time (hours)	27.5	*
Feed LGO spiked with DMDS (total S content of 3.6 wt%) was used for presulphiding. * - Time on stream is reported in the text of the examples.		

Table 3. Test conditions HC-PT test, Feed VGO.

	Presulphiding	Testing
Temperature (°C)	340	382
H2 pressure (bar)	30	120
LHSV	3	1.75
H2/oil	300	1000
Time (hours)	27.5	*
Feed LGO spiked with DMDS (total S content of 3.6 wt%) was used for presulphiding.*-Time on stream is reported in the text of the examples.		

Table 4. Test conditions FCC-PT test, Feed VGO.

	Presulphiding	Testing
Temperature (°C)	320	360
H2 pressure (bar)	45	70
LHSV	3	1.2
H2/oil	300	400
Time (hours)	16	*
Feed LGO spiked with DMDS (total S content of 3.6 wt%) was used for presulphiding. * - Time on stream is reported in the text of the examples.		

Table 5. Test conditions ULSD test, Feed LGO.

	Presulphiding	Testing
Temperature (°C)	320	340
H2 pressure (bar)	45	45
LHSV	3	2
H2/oil	300	300

(continued)

	Presulphiding	Testing
Time (hours)	27.1	*
Feed LGO spiked with DMDS (total S content of 3.6 wt%) was used for presulphiding. *-Time on stream is reported in the text of the examples.		

Support preparation (0 -18.75 wt % B₂O₃ in support)

[0036] The support was prepared by mixing an alumina hydrate cake (water content about 80%) and boric acid (H₃BO₃) in a kneader to form an extrudable paste. (In some cases, the water content of the extrusion mix had to be adjusted by evaporation or by adding additional water in order to obtain a paste suitable for extrusion. A person skilled in the art knows how to adjust the water content in order to obtain an extrudable paste.) The resulting mixture was extruded through a 1.3Q die plate, dried overnight at 120°C and then calcined (optionally with steam) at a temperature in the range of 475 - 850 °C (See Table 6).

[0037] Support D3 was prepared from A1 and supports B2, C3 and D4 were prepared from A6 by pore volume impregnation of the support A1 and A6, respectively, with a solution of ammonium tetra borate tetra hydrate ((NH₄)₂B₄O_{7.4}H₂O) in water. The impregnated support was heated to a temperature of 120 °C, kept at this temperature for 30 minutes and subsequently calcined (optionally with steam) at a temperature in the range of 475- 550 or for 1 hour (See Table 6).

Table 6: Calcination temperature of the supports A - H

Support	B ₂ O ₃ (wt%)	Calcination Temperature (°C)
A1	0	475
A2	0	600
A3	0	750
A4	0	840
A5	0	720
A6	0	550
B1	1.88	700
B2	1.88	550
C1	3.75	700
C2	3.75	680
C3	3.75	550
D1	7.5	760
D2	7.5	800
D3	7.5	475
D4	7.5	550
E1	9.8	650
E2	9.8	750
E3	9.8	550
F1	11.25	810
F2	11.25	760
G1	15	850
H1	18.75	750

Preparation and testing of catalysts 1 - 44

[0038] All chemical compositions of the catalysts are calculated on basis of the amount of material used for the catalyst preparation.

Example 1

NiMoP Catalyst 1

[0039] The impregnation solution was prepared by mixing appropriate amounts of water, nickel carbonate $[\text{Ni}(\text{OH})_x(\text{CO}_3)_y]$, molybdenum trioxide (MoO_3), and phosphoric acid (H_3PO_4). The mixture was sufficiently heated and kept at temperature while stirred until a clear solution was obtained. After the solution was cooled down, diethylene glycol (0.44 mol / mol hydrogenation metals present in the catalyst) was added. The initial amount of water was chosen in a way that the total volume of the solution after the addition of diethylene glycol was ca. 230% of the pore volume for the impregnation of the powdered support A4.

[0040] Support A4 was crushed, sieved and impregnated with the impregnation solution to 230% pore volume saturation. The impregnated powder was dried 10 hours at 80 °C and subsequently for 4 hours at 120 °C. The final MoO_3 content was 24 wt% (dry base) of the finished catalyst. The final NiO content was 4 wt% (dry base) of the finished catalyst. The final P_2O_5 content was 2 wt% (dry base) of the finished catalyst.

[0041] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 1026 ppm (k wt = 21.05) and product N of 80 ppm (k wt = 8.38) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 2

NiMoPB Catalyst 2

[0042] The powdered catalyst was prepared as described in Example 1, except that support D1 was used and the final B_2O_3 content was 5.3 wt% (dry base) of the finished catalyst.

[0043] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 976 ppm (k wt = 21.76) and product N of 29 ppm (k wt = 11.54) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 3

NiMoPB Catalyst 3

[0044] The powdered catalyst was prepared as described in Example 1, except that support G1 was used and that the final B_2O_3 content was 10.5 wt% (dry base) of the finished catalyst.

[0045] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 995 ppm (k wt = 21.11) and product N of 23 ppm (k wt = 12.24) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 4

NiMoP Catalyst 4

[0046] The powdered catalyst was prepared as described in Example 1, except that the final P_2O_5 content was 4.5 wt% (dry base) of the finished catalyst.

[0047] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 902 ppm (k wt = 23.10) and product N of 44 ppm (k wt = 10.18) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 5

NiMoPB Catalyst 5

[0048] The powdered catalyst was prepared as described in Example 4, except that support C1 was used and that

EP 2 421 645 B1

the final B_2O_3 content was 2.5 wt% (dry base) of the finished catalyst.

[0049] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 910 ppm (k wt = 21.90) and product N of 18 ppm (k wt = 11.75) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 6

NiMoPB Catalyst 6

[0050] The powdered catalyst was prepared as described in Example 4, except that support D1 was used and that the final B_2O_3 content was 5.1 wt% (dry base) of the finished catalyst.

[0051] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 926 ppm (k wt = 22.31) and product N of 16 ppm (k wt = 12.70) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 7

NiMoPB Catalyst 7

[0052] The powdered catalyst was prepared as described in Example 4, except that support F1 was used and that the final B_2O_3 content was 7.6 wt% (dry base) of the finished catalyst.

[0053] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 1137 ppm (k wt = 18.18) and product N of 16 ppm (k wt = 12.70) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 8

NiMoPB Catalyst 8

[0054] The powdered catalyst was prepared as described in Example 4, except that support G1 was used and that the final B_2O_3 content was 10.1 wt% (dry base) of the finished catalyst.

[0055] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 998 ppm (k wt = 21.33) and product N of 23 ppm (k wt = 12.43) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 9

NiMoP Catalyst 9

[0056] The powdered catalyst was prepared as described in Example 1, except that the final P_2O_5 content was 7 wt% (dry base) of the finished catalyst.

[0057] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 1069 ppm (k wt = 20.62) and product N of 34 ppm (k wt = 10.57) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

[0058] Catalyst 9 was also prepared as whole extrudates, following the preparation procedure as described above, except that the total volume of the impregnation solution after the addition of di ethylene glycol was ca. 110% of the pore volume for the impregnation of extrudates support A4 and that the support was impregnated with the impregnation solution to 110% pore volume saturation.

[0059] Extrudates of catalyst 9 were tested in HC-PT mode with HGO feed (product S of 653 ppm (k wt = 28.74) and product N of 26 ppm (k wt = 11.49) after 192 hours time on stream), in HC-PT mode with VGO feed (product S of 583 ppm (k wt = 19.84) and product N of 155 ppm (k wt = 4.01) after 300 hours time on stream) and in FCC-PT mode with VGO feed (product S of 2022 ppm (k wt = 4.72) and product N of 557 ppm (k wt = 0.97) after 174 hours time on stream).

Example 10

NiMoPB Catalyst 10

[0060] The powdered catalyst was prepared as described in Example 9, except that support C1 was used and that

EP 2 421 645 B1

the final B_2O_3 content was 2.4 wt% (dry base) of the finished catalyst.

[0061] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 964 ppm (k wt = 20.97) and product N of 18 ppm (k wt = 11.21) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

[0062] Catalyst 10 was also prepared as whole extrudates, following the preparation procedure as described above, except that the total volume of the impregnation solution after the addition of di ethylene glycol was ca. 110% of the pore volume for the impregnation of extrudates support C1 and that the support was impregnated with the impregnation solution to 110% pore volume saturation.

[0063] Extrudates of catalyst 10 were tested in HC-PT mode with HGO feed (product S of 438 ppm (k wt = 41.57) and product N of 12 ppm (k wt = 14.26) after 192 hours time on stream) and in HC-PT mode with VGO feed (product S of 304 ppm (k wt = 32.40) and product N of 92 ppm (k wt = 4.65) after 300 hours time on stream).

Example 11

NiMoPB Catalyst 11

[0064] The powdered catalyst was prepared as described in Example 9, except that support D1 was used and that the final B_2O_3 content was 4.9 wt% (dry base) of the finished catalyst.

[0065] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 799 ppm (k wt = 25.59) and product N of 11 ppm (k wt = 14.17) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

[0066] Catalyst 11 was also prepared as whole extrudates, following the preparation procedure as described above, except that the total volume of the impregnation solution after the addition of di ethylene glycol was ca. 110% of the pore volume for the impregnation of extrudates support D1 and that the support was impregnated with the impregnation solution to 110% pore volume saturation.

[0067] Extrudates of catalyst 11 were tested in HC-PT mode with HGO feed (product S of 349 ppm (k wt = 47.72) and product N of 8 ppm (k wt = 14.93) after 192 hours time on stream), in HC-PT mode with VGO feed (product S of 300 ppm (k wt = 31.84) and product N of 80 ppm (k wt = 4.82) after 300 hours time on stream) and in FCC-PT mode with VGO feed (product S of 1805 ppm (k wt = 5.46) and product N of 463 ppm (k wt = 1.26) after 174 hours time on stream).

Example 12

NiMoPB Catalyst 12

[0068] The powdered catalyst was prepared as described in Example 9, except that support F1 was used and that the final B_2O_3 content was 7.3 wt% (dry base) of the finished catalyst.

[0069] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 1190 ppm (k wt = 17.52) and product N of 21 ppm (k wt = 11.35) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 13

NiMoPB Catalyst 13

[0070] The powdered catalyst was prepared as described in Example 9, except that support G1 was used and that the final B_2O_3 content was 9.8 wt% (dry base) of the finished catalyst.

[0071] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 1043 ppm (k wt = 20.21) and product N of 26 ppm (k wt = 11.81) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 14

NiMoPB Catalyst 14

[0072] The powdered catalyst was prepared as described in Example 1, except that support F1 was used and that the final P_2O_5 content was 9.5 wt% (dry base) and the final B_2O_3 content was 7.0 wt% (dry base) of the finished catalyst.

[0073] The catalyst was tested in HC-PT mode with HGO feed and reached a product S of 1370 ppm (k wt = 15.59) and product N of 30 ppm (k wt = 11.48) after 144 hours time on stream. Results are on basis of averaged duplicate

measurements.

Example 15

5 NiMoPB Catalyst 15

[0074] The catalyst was prepared as whole extrudates as described in Example 9, except that support B1 was used and that the final P_2O_5 content was 1.5 wt% (dry base) and the final B_2O_3 content was 1.3 wt% (dry base) of the finished catalyst.

10 **[0075]** The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1220 ppm

[0076] (k wt = 8.06) and product N of 509 ppm (k wt = 1.18) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

15 *Example 16*

NiMoPB Catalyst 16

[0077] The powdered catalyst was prepared as described in Example 1, except that support C2 was used and that the final MoO_3 content was 19 wt% (dry base), the final P_2O_5 content was 4 wt% (dry base) and the final B_2O_3 content was 2.7 wt% (dry base) of the finished catalyst.

[0078] The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1481 ppm (k wt = 6.48) and product N of 545 ppm (k wt = 1.03) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

25 *Example 17*

NiMoPB Catalyst 17

30 **[0079]** The powdered catalyst was prepared as described in Example 16, except that support F2 was used and that the final B_2O_3 content was 8.2 wt% (dry base) of the finished catalyst.

[0080] The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1616 ppm (k wt = 6.06) and product N of 521 ppm (k wt = 1.11) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

35 *Example 18*

NiMoP Catalyst 18

40 **[0081]** The catalyst was prepared as whole extrudates as described in Example 9, except that support A1 was used and that the final P_2O_5 content was 4.5 wt% (dry base) of the finished catalyst.

[0082] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1216 ppm (k wt = 7.03) and product N of 455 ppm (k wt = 1.16) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

45 *Example 19*

NiMoPB Catalyst 19

50 **[0083]** The catalyst was prepared as whole extrudates as described in Example 18, except that support B1 was used and that the final B_2O_3 content was 1.3 wt% (dry base) of the finished catalyst.

[0084] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1230 ppm (k wt = 7.85) and product N of 473 ppm (k wt = 1.26) after 120 hours time on stream.

55

Example 20

NiMoPB Catalyst 20

5 **[0085]** The catalyst was prepared as whole extrudates as described in Example 18, except that support B2 was used and that the final B_2O_3 content was 1.3 wt% (dry base) of the finished catalyst.

[0086] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1115 ppm (k wt = 7.33) and product N of 413 ppm (k wt = 1.25) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

10

Example 21

NiMoPB Catalyst 21

15 **[0087]** The catalyst was prepared as whole extrudates as described in Example 9, except that support C1 was used and that the final MoO_3 content was 26 wt% (dry base), the final NiO content was 5 wt% (dry base), the final P_2O_5 content was 4.5 wt% (dry base) and the final B_2O_3 content was 2.4 wt% (dry base) of the finished catalyst.

[0088] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1407 ppm (k wt = 6.63) and product N of 452 ppm (k wt = 1.26) after 120 hours time on stream.

20

Example 22

NiMoPB Catalyst 22

25

[0089] The catalyst was prepared as whole extrudates as described in Example 9, except that support C1 was used and that the final MoO_3 content was 22 wt% (dry base), the final NiO content was 3 wt% (dry base), the final P_2O_5 content was 4.5 wt% (dry base) and the final B_2O_3 content was 2.6 wt% (dry base) of the finished catalyst.

[0090] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1664 ppm (k wt = 6.14) and product N of 507 ppm (k wt = 1.19) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

30

Example 23

NiMoPB Catalyst 23

35

[0091] The catalyst was prepared as whole extrudates as described in Example 22, except that support C1 was used and that the final NiO content was 5 wt% (dry base) of the finished catalyst.

[0092] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1282 ppm (k wt = 7.87) and product N of 455 ppm (k wt = 1.37) after 120 hours time on stream.

40

Example 24

NiMoPB Catalyst 24

45

[0093] The catalyst was prepared as whole extrudates as described in Example 23, except that support C3 was used.

[0094] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1231 ppm (k wt = 7.08) and product N of 429 ppm (k wt = 1.26) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

50

Example 25

NiMoPB Catalyst 25

55

[0095] The catalyst was prepared as whole extrudates as described in Example 18, except that support D3 was used and that the final B_2O_3 content was 5.1 wt% (dry base) of the finished catalyst.

[0096] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT

EP 2 421 645 B1

mode with VGO feed and reached a product S of 1488 ppm (k wt = 5.62) and product N of 406 ppm (k wt = 1.25) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 26

NiMoPB Catalyst 26

[0097] The catalyst was prepared as whole extrudates as described in Example 25, except that support D2 was used.

[0098] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1429 ppm (k wt = 6.60) and product N of 419 ppm (k wt = 1.37) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 27

NiMoPB Catalyst 27

[0099] The catalyst was prepared as whole extrudates as described in Example 25, except that support H1 was used and that the final B_2O_3 content was 12.7 wt% (dry base) of the finished catalyst.

[0100] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1646 ppm (k wt = 5.66) and product N of 436 ppm (k wt = 1.28) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 28

NiMoPB Catalyst 28

[0101] The powdered catalyst was prepared as described in Example 1, except that support D1 was used and that the final MoO_3 content was 19 wt% (dry base), the final P_2O_5 content was 6.5 wt% (dry base) and the final B_2O_3 content was 5.3 wt% (dry base) of the finished catalyst.

[0102] The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1473 ppm (k wt = 6.09) and product N of 520 ppm (k wt = 1.02) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 29

NiMoPB Catalyst 29

[0103] The powdered catalyst was prepared as described in Example 28, except that support F2 was used and that the final B_2O_3 content was 7.9 wt% (dry base) of the finished catalyst.

[0104] The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1659 ppm (k wt = 5.51) and product N of 486 ppm (k wt = 0.94) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 30

NiMoP Catalyst 30

[0105] The catalyst was prepared as whole extrudates as described in Example 9, except that support A3 was used.

[0106] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1597 ppm (k wt = 5.50) and product N of 483 ppm (k wt = 1.09) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 31

NiMoPB Catalyst 31

[0107] The catalyst was prepared as whole extrudates as described in Example 9, except that support C1 was used and that the final MoO_3 content was 22 wt% (dry base), the final NiO content was 5 wt% (dry base), the final P_2O_5

EP 2 421 645 B1

content was 7 wt% (dry base) and the final B_2O_3 content was 2.5 wt% (dry base) of the finished catalyst.

[0108] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1206 ppm (k wt = 7.81) and product N of 415 ppm (k wt = 1.41) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

5

Example 32

NiMoPB Catalyst 32

10 **[0109]** The catalyst was prepared as whole extrudates as described in Example 31, except that support C3 was used.

[0110] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1272 ppm (k wt = 6.70) and product N of 416 ppm (k wt = 1.27) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

15 Example 33

NiMoPB Catalyst 33

20 **[0111]** The catalyst was prepared as whole extrudates as described in Example 9, except that support D2 was used and that the final B_2O_3 content was 4.9 wt% (dry base) of the finished catalyst.

[0112] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1313 ppm (k wt = 6.56) and product N of 408 ppm (k wt = 1.42) after 120 hours time on stream.

25 Example 34

NiMoPB Catalyst 34

30 **[0113]** The catalyst was prepared as whole extrudates as described in Example 33, except that support D4 was used.

[0114] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1275 ppm (k wt = 6.44) and product N of 391 ppm (k wt = 1.30) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 35

35

NiMoPB Catalyst 35

[0115] The catalyst was prepared as whole extrudates as described in Example 34, except that support H1 was used and that the final B_2O_3 content was 12.2 wt% (dry base) of the finished catalyst.

40 **[0116]** The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1592 ppm (k wt = 5.62) and product N of 430 ppm (k wt = 1.25) after 120 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 36

45

NiMoPB Catalyst 36

50 **[0117]** The powdered catalyst was prepared as described in Example 1, except that support C2 was used and that the final MoO_3 content was 19 wt% (dry base), the final P_2O_5 content was 9 wt% (dry base) and the final B_2O_3 content was 2.6 wt% (dry base) of the finished catalyst.

[0118] The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1575 ppm (k wt = 5.85) and product N of 533 ppm (k wt = 1.01) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

55

Example 37

NiMoPB Catalyst 37

5 **[0119]** The powdered catalyst was prepared as described in Example 36, except that support D1 was used and that the final B_2O_3 content was 5.1 wt% (dry base) of the finished catalyst.

[0120] The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1607 ppm (k wt = 5.62) and product N of 559 ppm (k wt = 0.93) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

10

Example 38

NiMoPB Catalyst 38

15 **[0121]** The impregnation solution was prepared by mixing appropriate amounts of water, nickel carbonate $[Ni(OH)_x(CO_3)_y]$, molybdenum trioxide (MoO_3), and phosphoric acid (H_3PO_4). The mixture was sufficiently heated and kept at temperature while stirred until a clear solution was obtained. The initial amount of water was chosen in a way that the total volume of the solution was ca. 230 % of the pore volume for the impregnation of the powdered support C2.

20 **[0122]** Support C2 was crushed, sieved and impregnated with the impregnation solution to 230% pore volume saturation. The impregnated powder was dried for 10 hours at 80 °C and subsequently 4 hours at 120 °C. Next, the dried catalyst was calcined for 1 hour at 480 °C. The final MoO_3 content was 19 wt% (dry base) of the finished catalyst. The final NiO content was 4 wt% (dry base) of the finished catalyst. The final P_2O_5 content was 4 wt% (dry base) of the finished catalyst. The final B_2O_3 content was 2.7 wt% (dry base) of the finished catalyst.

25 **[0123]** The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1396 ppm (k wt = 6.33) and product N of 448 ppm (k wt = 1.20) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 39

NiMoP Catalyst 39

[0124] The powdered catalyst was prepared as described in Example 38, except that support A5 was used and that the final P_2O_5 content was 6.5 wt% (dry base) of the finished catalyst.

35 **[0125]** The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1191 ppm (k wt = 8.18) and product N of 556 ppm (k wt = 1.05) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 40

NiMoPB Catalyst 40

[0126] The powdered catalyst was prepared as described in Example 38, except that support C2 was used and that the final P_2O_5 content was 6.5 wt% (dry base) of the finished catalyst.

45 **[0127]** The catalyst was tested in FCC-PT mode with VGO feed and reached a product S of 1576 ppm (k wt = 5.52) and product N of 468 ppm (k wt = 1.12) after 144 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 41

CoMoP Catalyst 41

[0128] The extrudate catalyst was prepared as described in Example 9, except that nickel carbonate was replaced by cobalt carbonate ($CoCO_3$) and that support A2 was used. The final MoO_3 content was 24 wt% (dry base) of the finished catalyst. The final CoO content was 4.4 wt% (dry base) of the finished catalyst. The final P_2O_5 content was 2.1 wt% (dry base) of the finished catalyst.

55 **[0129]** The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in ULSD mode with LGO feed and reached a product S of 28.1 ppm (k wt = 22.07) and product N of 1.15 ppm (k wt = 10.18) after 216 hours time on stream. Results are on basis of averaged duplicate measurements.

Example 42

CoMoPB Catalyst 42

[0130] The extrudate catalyst was prepared as described in Example 41, except that support E3 was used and that the final MoO₃ content was 25 wt% (dry base), the final CoO content was 6 wt% (dry base) and the final B₂O₃ content was 6 wt% (dry base) of the finished catalyst.

[0131] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in ULSD mode with LGO feed and reached a product S of 11.9 ppm (k wt = 24.97) and product N of 0.3 ppm (k wt = 12.18) after 216 hours time on stream.

Example 43

CoMoPB Catalyst 43

[0132] The extrudate catalyst was prepared as described in Example 41, except that support E2 was used and that the final MoO₃ content was 25 wt% (dry base) and the final B₂O₃ content was 6.1 wt% (dry base) of the finished catalyst.

[0133] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in ULSD mode with LGO feed and reached a product S of 11.3 ppm (k wt = 24.30) and product N of 0.3 ppm (k wt = 11.71) after 216 hours time on stream.

Example 44

CoMoPB Catalyst 44

[0134] The extrudate catalyst was prepared as described in Example 41, except that support E1 was used and that the final CoO content was 5 wt% (dry base), the final P₂O₅ content was 7.9 wt% (dry base) and the final B₂O₃ content was 5.8 wt% (dry base) of the finished catalyst.

[0135] The catalyst was crushed and sieved, prior to the activity test. The powdered catalyst was tested in ULSD mode with LGO feed and reached a product S of 11.7 ppm (k wt = 25.09) and product N of 0.3 ppm (k wt = 12.19) after 216 hours time on stream.

[0136] Components referred to by chemical name or formula anywhere in the specification or claims hereof, whether referred to in the singular or plural, are identified as they exist prior to coming into contact with another substance referred to by chemical name or chemical type (e.g., another component, a solvent, or *etc.*). It matters not what chemical changes, transformations and/or reactions, if any, take place in the resulting mixture or solution as such changes, transformations, and/or reactions are the natural result of bringing the specified components together under the conditions called for pursuant to this disclosure. Thus the components are identified as ingredients to be brought together in connection with performing a desired operation or in forming a desired composition.

Claims

1. A catalyst comprising
 - at least one Group VIB metal component,
 - at least one Group VIII metal component,
 - a phosphorus component, and
 - a boron-containing carrier component,
 wherein the amount of the phosphorus component is at least 1 wt %, expressed as an oxide (P₂O₅) and based on the total weight of the catalyst, and the amount of boron content is in the range of 1 to 13 wt%, expressed as an oxide (B₂O₃) and based on the total weight of the catalyst; and wherein the formation of the catalyst involves at least co-extruding a boron source with a carrier to form a boron-containing carrier extrudate, drying and calcining the extrudate, and impregnating the calcined extrudate with a solution comprised of a phosphorus source, at least one Group VIB metal source and/or at least one Group VIII metal source.
2. The catalyst according to claim 1 wherein the Group VIB metal component comprises molybdenum.
3. The catalyst according to any one of claims 1 or 2 wherein the Group VIII metal component comprises nickel.

4. The catalyst according to either of claims 1 and 2, wherein the Group VIII metal component comprises cobalt.
5. The catalyst according to any of claims 1-4 wherein the amount of the phosphorus component is in the range of 4 wt% to 10 wt%, expressed as an oxide (P_2O_5) and based on the total weight of the catalyst.
6. The catalyst according to claim 5, wherein the amount of the phosphorus component is in the range of 4 wt% to 7 wt%, expressed as an oxide (P_2O_5) and based on the total weight of the catalyst.
7. The catalyst according to claim 6, wherein the boron content is in the range of 2 wt% to 8 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst.
8. The catalyst according to claim 7, wherein the boron content is in the range of 4 wt% to 6 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst.
9. The catalyst according to any of the preceding claims, wherein the carrier comprises alumina.
10. The catalyst according to any of the preceding claims, wherein the boron source comprises boric acid.
11. The catalyst according to any of the preceding claims, further comprising an organic additive.
12. The catalyst according to claim 11, wherein the organic additive is selected from the group consisting of (i) an organic compound selected from the group consisting of organic compounds comprising at least two oxygen atoms and 2 - 10 carbon atoms, and the ethers, esters, acetals, acid chlorides, acid amides, oligomers or polymers thereof, and/or (ii) an organic compound comprising at least one covalently bonded nitrogen atom and at least one carbonyl moiety.
13. A method of producing a catalyst, the method comprising
co-extruding a boron source with a carrier to form a boron-containing carrier extrudate,
drying and calcining the extrudate, and
impregnating the calcined extrudate with a solution comprised of a phosphorus source, at least one Group VIB metal source and/or at least one Group VIII metal source, the amount of the boron source and the amount of the phosphorus source being sufficient so as to form a catalyst composition at least having a boron content in the range of 1 wt% to 13 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst, and a phosphorus content of at least 1 wt%, expressed as an oxide (P_2O_5) and based on the total weight of the catalyst.
14. The method according to claim 13, wherein the amount of the boron source is sufficient so that the boron content of the catalyst produced is in the range of 2 wt% to 8 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst.
15. The method according to claim 14, wherein the amount of the boron source is sufficient so that the boron content of the catalyst produced is in the range of 4 wt% to 6 wt%, expressed as an oxide (B_2O_3) and based on the total weight of the catalyst.
16. The method according to claim 15, wherein the amount of the phosphorus source is sufficient so that the phosphorus content of the catalyst produced is in the range of 4 wt% to 10 wt%, expressed as an oxide (P_2O_5) and based on the total weight of the catalyst.
17. The method according to claim 16, wherein the amount of the phosphorus source is sufficient so that the phosphorus content of the catalyst is in the range of 4 wt% to 7 wt%, expressed as an oxide (P_2O_5) and based on the total weight of the catalyst.
18. The method according to any of claims 13-17, further comprising calcining an impregnated calcined extrudate formed in the impregnating step.
19. The method according to any of claims 13-17, further comprising drying an impregnated calcined extrudate formed in the impregnation step so as to form a dried impregnated calcined extrudate so as to form the catalyst.
20. The method according to any of claim 13-17, further comprising drying an impregnated calcined extrudate formed

in the impregnation step so as to form a dried impregnated calcined extrudate, and further calcining the dried impregnated calcined extrudate so as to form the catalyst.

21. The method according to any of claims 13-17 and 19, wherein the solution further comprises an organic additive.
22. The method according to claim 21, wherein the organic additive is selected from the group consisting of (i) an organic compound selected from the group consisting of organic compounds comprising at least two oxygen atoms and 2 - 10 carbon atoms, and the ethers, esters, acetals, acid chlorides, acid amides, oligomers or polymers thereof, and/or (ii) an organic compound comprising at least one covalently bonded nitrogen atom and at least one carbonyl moiety.
23. A method which comprises contacting a hydrocarbon feed with a catalyst according to any of the preceding claims 1-12, under hydrotreating conditions so as to hydrotreat the hydrocarbon feed.

Patentansprüche

1. Katalysator, umfassend
mindestens eine Gruppe VIB-Metall-Komponente,
mindestens eine Gruppe VIII-Metall-Komponente,
eine Phosphor-Komponente und
eine borhaltige Trägerkomponente,
wobei die Menge der Phosphor-Komponente mindestens 1 Gew.-%, ausgedrückt als ein Oxid (P_2O_5) und bezogen auf das Gesamtgewicht des Katalysators, beträgt und die Menge des Bor-Gehalts im Bereich von 1 bis 13 Gew.-%, ausgedrückt als ein Oxid (B_2O_3) und bezogen auf das Gesamtgewicht des Katalysators, liegt; und wobei die Bildung des Katalysators mindestens Coextrudieren einer Bor-Quelle mit einem Träger, wobei ein borhaltiges Trägerextrudat gebildet wird, Trocknen und Kalzinieren des Extrudats und Imprägnieren des kalzinierten Extrudats mit einer Lösung, bestehend aus einer Phosphor-Quelle, mindestens einer Gruppe VIB-Metall-Quelle und/oder mindestens einer Gruppe VIII-Metall-Quelle, einbezieht.
2. Katalysator gemäß Anspruch 1, wobei die Gruppe VIB-Metall-Komponente Molybdän umfasst.
3. Katalysator gemäß einem der Ansprüche 1 oder 2, wobei die Gruppe VIII-Metall-Komponente Nickel umfasst.
4. Katalysator gemäß einem der Ansprüche 1 und 2, wobei die Gruppe VIII-Metall-Komponente Cobalt umfasst.
5. Katalysator gemäß einem der Ansprüche 1-4, wobei die Menge der Phosphor-Komponente im Bereich von 4 Gew.-% bis 10 Gew.-%, ausgedrückt als ein Oxid (P_2O_5) und bezogen auf das Gesamtgewicht des Katalysators, liegt.
6. Katalysator gemäß Anspruch 5, wobei die Menge der Phosphor-Komponente im Bereich von 4 Gew.-% bis 7 Gew.-%, ausgedrückt als ein Oxid (P_2O_5) und bezogen auf das Gesamtgewicht des Katalysators, liegt.
7. Katalysator gemäß Anspruch 6, wobei der Bor-Gehalt im Bereich von 2 Gew.-% bis 8 Gew.-%, ausgedrückt als ein Oxid (B_2O_3) und bezogen auf das Gesamtgewicht des Katalysators, liegt.
8. Katalysator gemäß Anspruch 7, wobei der Bor-Gehalt im Bereich von 4 Gew.-% bis 6 Gew.-%, ausgedrückt als ein Oxid (B_2O_3) und bezogen auf das Gesamtgewicht des Katalysators, liegt.
9. Katalysator gemäß einem der vorhergehenden Ansprüche, wobei der Träger Aluminiumoxid umfasst.
10. Katalysator gemäß einem der vorhergehenden Ansprüche, wobei die Bor-Quelle Borsäure umfasst.
11. Katalysator gemäß einem der vorhergehenden Ansprüche, ferner umfassend ein organisches Additiv.
12. Katalysator gemäß Anspruch 11, wobei das organische Additiv aus der Gruppe ausgewählt ist, die besteht aus (i) einer organischen Verbindung, die aus der Gruppe ausgewählt ist, die besteht aus organischen Verbindungen, umfassend mindestens zwei Sauerstoffatome und 2 - 10 Kohlenstoffatome, und den Ethern, Estern, Acetalen, Säurechloriden, Säureamiden, Oligomeren oder Polymeren davon, und/oder (ii) einer organischen Verbindung,

umfassend mindestens ein kovalent gebundenes Stickstoffatom und mindestens eine Carbonyleinheit.

13. Verfahren zur Herstellung eines Katalysators, wobei das Verfahren umfasst Coextrudieren einer Bor-Quelle mit einem Träger, wobei ein borhaltiges Trägerextrudat gebildet wird,
Trocknen und Kalzinieren des Extrudats und
Imprägnieren des kalzinierten Extrudats mit einer Lösung, bestehend aus einer Phosphor-Quelle, mindestens einer Gruppe VIB-Metall-Quelle und/oder mindestens einer Gruppe VIII-Metall-Quelle,
wobei die Menge der Bor-Quelle und die Menge der Phosphor-Quelle ausreichend sind, um so eine Katalysatorzusammensetzung zu bilden, die mindestens einen Bor-Gehalt im Bereich von 1 Gew.-% bis 13 Gew.-%, ausgedrückt als ein Oxid (B_2O_3) und bezogen auf das Gesamtgewicht des Katalysators, aufweist und einen Phosphor-Gehalt von mindestens 1 Gew.-%, ausgedrückt als ein Oxid (P_2O_5) und bezogen auf das Gesamtgewicht des Katalysators, aufweist.
14. Verfahren gemäß Anspruch 13, wobei die Menge der Bor-Quelle ausreichend ist, damit der Bor-Gehalt des hergestellten Katalysators im Bereich von 2 Gew.-% bis 8 Gew.-%, ausgedrückt als ein Oxid (B_2O_3) und bezogen auf das Gesamtgewicht des Katalysators, liegt.
15. Verfahren gemäß Anspruch 14, wobei die Menge der Bor-Quelle ausreichend ist, damit der Bor-Gehalt des hergestellten Katalysators im Bereich von 4 Gew.-% bis 6 Gew.-%, ausgedrückt als ein Oxid (B_2O_3) und bezogen auf das Gesamtgewicht des Katalysators, liegt.
16. Verfahren gemäß Anspruch 15, wobei die Menge der Phosphor-Quelle ausreichend ist, damit der Phosphor-Gehalt des hergestellten Katalysators im Bereich von 4 Gew.-% bis 10 Gew.-%, ausgedrückt als ein Oxid (P_2O_5) und bezogen auf das Gesamtgewicht des Katalysators, liegt.
17. Verfahren gemäß Anspruch 16, wobei die Menge der Phosphor-Quelle ausreichend ist, damit der Phosphor-Gehalt des Katalysators im Bereich von 4 Gew.-% bis 7 Gew.-%, ausgedrückt als ein Oxid (P_2O_5) und bezogen auf das Gesamtgewicht des Katalysators, liegt.
18. Verfahren gemäß einem der Ansprüche 13-17, ferner umfassend Kalzinieren eines imprägnierten kalzinierten in dem Imprägnierungsschritt gebildeten Extrudats.
19. Verfahren gemäß einem der Ansprüche 13-17, ferner umfassend Trocknen eines imprägnierten kalzinierten in dem Imprägnierungsschritt gebildeten Extrudats, um so ein getrocknetes imprägniertes kalziniertes Extrudat zu bilden, um so den Katalysator zu bilden.
20. Verfahren gemäß einem der Ansprüche 13-17, ferner umfassend Trocknen eines imprägnierten kalzinierten in dem Imprägnierungsschritt gebildeten Extrudats, um so ein getrocknetes imprägniertes kalziniertes Extrudat zu bilden, und ferner Kalzinieren des getrockneten imprägnierten kalzinierten Extrudats, um so den Katalysator zu bilden.
21. Verfahren gemäß einem der Ansprüche 13-17 und 19, wobei die Lösung ferner ein organisches Additiv umfasst.
22. Verfahren gemäß Anspruch 21, wobei das organische Additiv aus der Gruppe ausgewählt ist, die besteht aus (i) einer organischen Verbindung, die aus der Gruppe ausgewählt ist, die besteht aus organischen Verbindungen, umfassend mindestens zwei Sauerstoffatome und 2 - 10 Kohlenstoffatome, und den Ethern, Estern, Acetalen, Säurechloriden, Säureamiden, Oligomeren oder Polymeren davon, und/oder (ii) einer organischen Verbindung, umfassend mindestens ein kovalent gebundenes Stickstoffatom und mindestens eine Carbonyleinheit.
23. Verfahren, welches Inkontaktbringen einer Kohlenwasserstoff-Zufuhr mit einem Katalysator gemäß einem der vorhergehenden Ansprüche 1-12 unter Hydrotreating-Bedingungen, um so die Kohlenwasserstoff-Zufuhr einer Hydrotreating-Behandlung zu unterwerfen, umfasst.

Revendications

1. Catalyseur comprenant
au moins un composant métallique du groupe VIB,
au moins un composant métallique du groupe VIII,

un composant de phosphore et
un composant de support contenant du bore,
dans lequel la quantité du composant de phosphore est d'au moins 1 % en poids, exprimé comme un oxyde (P_2O_5)
et basé sur le poids total du catalyseur, et la quantité de teneur en bore se situe dans la plage allant de 1 à 13 %
en poids, exprimé comme un oxyde (B_2O_3) et basé sur le poids total du catalyseur ; et dans lequel la formation du
catalyseur implique au moins la co-extrusion d'une source de bore avec un support pour former un extrudat de
support contenant du bore, le séchage et la calcination de l'extrudat, et l'imprégnation de l'extrudat calciné avec
une solution comprenant une source de phosphore, au moins une source de métal du groupe VIB et/ou au moins
une source de métal du groupe VIII.

2. Catalyseur selon la revendication 1 dans lequel le composant métallique du groupe VIB comprend du molybdène.

3. Catalyseur selon l'une quelconque des revendications 1 ou 2 dans lequel le composant métallique du groupe VIII
comprend du nickel.

4. Catalyseur selon l'une ou l'autre des revendications 1 et 2, dans lequel le composant métallique du groupe VIII
comprend du cobalt.

5. Catalyseur selon l'une quelconque des revendications 1 à 4 dans lequel la quantité du composant de phosphore
se situe dans la plage allant de 4 à 10 % en poids, exprimé comme un oxyde (P_2O_5) et basé sur le poids total du
catalyseur.

6. Catalyseur selon la revendication 5, dans lequel la quantité du composant de phosphore se situe dans la plage
allant de 4 à 7 pour cent en poids, exprimé comme un oxyde (P_2O_5) et basé sur le poids total du catalyseur.

7. Catalyseur selon la revendication 6, dans lequel la teneur en bore se situe dans la plage allant de 2 à 8 % en poids,
exprimé comme un oxyde (B_2O_3) et basé sur le poids total du catalyseur.

8. Catalyseur selon la revendication 7, dans lequel la teneur en bore se situe dans la plage allant de 4 à 6 % en poids,
exprimé comme un oxyde (B_2O_3) et basé sur le poids total du catalyseur.

9. Catalyseur selon l'une quelconque des revendications précédentes, dans lequel le support comprend de l'alumine.

10. Catalyseur selon l'une quelconque des revendications précédentes, dans lequel la source de bore comprend l'acide
borique.

11. Catalyseur selon l'une quelconque des revendications précédentes, comprenant en outre un additif organique.

12. Catalyseur selon la revendication 11, dans lequel l'additif organique est choisi dans le groupe constitué par (i) un
composé organique choisi dans le groupe constitué par les composés organiques comprenant au moins deux
atomes d'oxygène et 2 à 10 atomes de carbone, et les éthers, esters, acétals, chlorures d'acide, amides d'acide,
oligomères ou leurs polymères et/ou (ii) un composé organique comprenant au moins un atome d'azote lié de
manière covalente et au moins une fraction carbonyle.

13. Procédé de production d'un catalyseur, le procédé comprenant
la co-extrusion d'une source de bore avec un support pour former un extrudat de support contenant du bore,
le séchage et la calcination de l'extrudat, et
l'imprégnation de l'extrudat calciné avec une solution comprenant une source de phosphore, au moins une source
de métal du groupe VIB et /ou au moins une source de métal du groupe VIII,
la quantité de la source de bore et la quantité de la source de phosphore étant suffisante pour former une composition
de catalyseur ayant au moins une teneur en bore située dans la plage allant de 1 à 13 %, exprimé comme un oxyde
(B_2O_3) et basé sur le poids total du catalyseur, et une teneur en phosphore d'au moins 1 % en poids, exprimé
comme un oxyde (P_2O_5) et basé sur le poids total du catalyseur.

14. Procédé selon la revendication 13, dans lequel la quantité de la source de bore est suffisante pour que la teneur
en bore du catalyseur produit se situe dans la plage allant de 2 à 8 % en poids, exprimé comme un oxyde (B_2O_3)
et basé sur le poids total du catalyseur.

15. Procédé selon la revendication 14, dans lequel la quantité de la source de bore est suffisante pour que la teneur en bore du catalyseur produit se situe dans la plage allant de 4 à 6 % en poids, exprimé comme un oxyde (B_2O_3) et basé sur le poids total du catalyseur.

5 **16.** Procédé selon la revendication 15, dans lequel la quantité de la source de phosphore est suffisante pour que la teneur en phosphore du catalyseur produit se situe dans la plage allant de 4 à 10 % en poids, exprimé comme un oxyde (P_2O_5) et basé sur le poids total du catalyseur.

10 **17.** Procédé selon la revendication 16, dans lequel la quantité de la source de phosphore est suffisante pour que la teneur en phosphore du catalyseur produit se situe dans la plage allant de 4 à 7 % en poids, exprimé comme un oxyde (P_2O_5) et basé sur le poids total du catalyseur.

18. Procédé selon l'une quelconque des revendications 13 à 17, comprenant en outre la calcination d'un extrudat calciné imprégné formé dans l'étape d'imprégnation.

15 **19.** Procédé selon l'une quelconque des revendications 13 à 17 comprenant en outre le séchage d'un extrudat calciné imprégné formé dans l'étape d'imprégnation afin de former un extrudat calciné imprégné séché pour former le catalyseur.

20 **20.** Procédé selon l'une quelconque des revendications 13 à 17 comprenant en outre le séchage d'un extrudat calciné imprégné formé dans l'étape d'imprégnation afin de former un extrudat calciné imprégné séché et en outre calciner l'extrudat calciné imprégné séché pour former le catalyseur.

25 **21.** Procédé selon l'une quelconque des revendications 13 à 17 et 19, dans lequel la solution comprend en outre un additif organique.

30 **22.** Procédé selon la revendication 21, dans lequel l'additif organique est choisi dans le groupe constitué par (i) un composé organique choisi dans le groupe constitué par les composés organiques comprenant au moins deux atomes d'oxygène et 2 à 10 atomes de carbone, et les éthers, esters, acétals, chlorures d'acide, amides d'acide, oligomères ou leurs polymères, et/ou (ii) un composé organique comprenant au moins un atome d'azote lié de manière covalente et au moins une fraction carbonyle.

35 **23.** Procédé qui comprend la mise en contact d'une alimentation d'hydrocarbure avec un catalyseur selon l'une quelconque des revendications 1 à 12, dans des conditions d'hydrotraitement pour hydrotraiter l'alimentation d'hydrocarbure.

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 2938001 A [0003]
- US 3453219 A [0004]
- US 4028227 A [0019]

1. Katalizátor, amely tartalmaz

legalább egy a VIB csoportba tartozó fém komponenst,

legalább egy a VIII csoportba tartozó fém komponenst,

egy foszfor komponenst, és

egy bór-tartalmú hordozó komponenst,

ahol a foszfor komponens mennyisége legalább 1 tömeg%, oxidban (P_2O_5) kifejezve és a katalizátor teljes tömegére vonatkoztatva, és a bór-tartalom mennyisége 1-13 tömeg% tartományban van, oxidban (B_2O_3) kifejezve és a katalizátor teljes tömegére vonatkoztatva; és ahol a katalizátor előállításában magában foglalja egy bór-forrás és egy hordozó legalább koextrudálását, így bór-tartalmú hordozó extrudátum képződik, az extrudátum megszáritását és kiégetését, és a kiégetett extrudátumnak egy foszforforrást tartalmazó oldattal, legalább egy a VIB csoportba tartozó fémforrással és/vagy legalább egy a VIII csoportba tartozó fémforrással történő impregnálását.

2. Az 1. igénypont szerinti katalizátor, ahol a VIB csoportba tartozó fémkomponens molibdént tartalmaz.

3. Az 1. vagy 2. igénypont szerinti katalizátor, ahol a VIII csoportba tartozó fémkomponens nikkelt tartalmaz.

4. Az 1. vagy 2. igénypont szerinti katalizátor, ahol a VIII csoportba tartozó fémkomponens kobaltot tartalmaz.

5. Az 1-4. igénypontok bármelyike szerinti katalizátor, ahol a foszfor komponens mennyisége 4-10 tömeg% tartományban van, oxidban (P_2O_5) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

6. Az 5. igénypont szerinti katalizátor, ahol a foszfor komponens mennyisége 4-7 tömeg% tartományban van, oxidban (P_2O_5) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

7. A 6. igénypont szerinti katalizátor, ahol a bór-tartalom 2-8 tömeg% tartományban van, oxidban (B_2O_3) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

8. A 7. igénypont szerinti katalizátor, ahol a bór-tartalom 4-6 tömeg% tartományban van, oxidban (B_2O_3) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

9. Az előző igénypontok bármelyike szerinti katalizátor, ahol a hordozó alumínium-oxidot tartalmaz.

10. Az előző igénypontok bármelyike szerinti katalizátor, ahol a bórforrás bórsavat tartalmaz.

11. Az előző igénypontok bármelyike szerinti katalizátor, amely tartalmaz továbbá egy szerves adalékot.

12. A 11. igénypont szerinti katalizátor, ahol a szerves adalék a következők csoportjából van kiválasztva:
(i) egy szerves vegyület, amely legalább két oxigénatomot és 2-10 szénatomot tartalmazó szerves vegyületek és ezek étere, észtere, acetáljai, savkloridja, savamidjai, oligomerei vagy polimerei csoportjából van kiválasztva és/vagy (ii) egy szerves vegyület, amely legalább egy kovalensen kötött nitrogénatomot és legalább egy karbonilcsoportot tartalmaz.

13. Eljárás katalizátor előállítására, amely eljárás során
egy bórforrást egy hordozóval koextrudálunk, így bór tartalmú hordozó extrudátumot állítunk elő,
az extrudátumot megszáritjuk és kiégetjük, és
a kiégetett extrudátumot egy foszforforrást, legalább egy a VIB csoportba tartozó fémforrást és/vagy legalább egy a VIII csoportba tartozó fémforrást tartalmazó oldattal impregáljuk, ahol a bórforrás mennyisége és a foszforforrás mennyisége olyan katalizátor készítmény előállításához elegendő, amelynek van legalább 1-13 tömeg% tartományba eső bór tartalma, oxidban (B_2O_3) kifejezve és a katalizátor teljes tömegére vonatkoztatva; és 1 tömeg% foszfortartalma, oxidban (P_2O_5) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

14. A 13. igénypont szerinti eljárás, ahol a bórforrás mennyisége elegendő ahhoz, hogy az előállított katalizátor bór tartalma 2-8 tömeg% tartományban legyen, oxidban (B_2O_3) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

15. A 14. igénypont szerinti eljárás, ahol a bórforrás mennyisége elegendő ahhoz, hogy az előállított katalizátor bór tartalma 4-6 tömeg% tartományban legyen, oxidban (B_2O_3) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

16. A 15. igénypont szerinti eljárás, ahol a foszforforrás mennyisége elegendő ahhoz, hogy az előállított katalizátor foszfortartalma 4-10 tömeg% tartományban legyen, oxidban (P_2O_5) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

17. A 16. igénypont szerinti eljárás, ahol a foszforforrás mennyisége elegendő ahhoz, hogy a katalizátor foszfortartalma 4-7 tömeg% tartományban legyen, oxidban (P_2O_5) kifejezve és a katalizátor teljes tömegére vonatkoztatva.

18. A 13-17. igénypontok bármelyike szerinti eljárás, amely magában foglalja továbbá az impregnálási lépésben előállított impregnált kiégetett extrudátum kiégetését.

19. A 13-17. igénypontok bármelyike szerinti eljárás, amely magában foglalja továbbá az impregnálási lépésben előállított impregnált kiégetett extrudátum megszáritását, így megszáritott impregnált kiégetett extrudátumot állítunk elő a katalizátor előállításához.

20. A 13-17. igénypontok bármelyike szerinti eljárás, amely magában foglalja továbbá az impregnálási lépésben előállított impregnált kiégetett extrudátum megszáritását, így megszáritott impregnált kiégetett extrudátumot állítunk elő, továbbá a megszáritott impregnált kiégetett extrudátumot kiégetjük a katalizátor előállításához.

21. A 13-17. és 19. igénypontok bármelyike szerinti eljárás, ahol az oldat tartalmaz továbbá egy szerves adalékot.

22. A 21. igénypont szerinti eljárás, ahol a szerves adalék a következők csoportjából van kiválasztva: (i) egy szerves vegyület, amely legalább két oxigénatomot és 2-10 szénatomot tartalmazó szerves vegyületek és ezek étere, észtere, acetáljai, savkloridja, savamidjai, oligomerei vagy polimerei csoportjából van kiválasztva és/vagy (ii) egy szerves vegyületet, amely legalább egy kovalensen kötött nitrogénatomot és legalább egy karbonilcsoportot tartalmaz.

23. Eljárás, amelynek során egy szénhidrogénforrást, egy az 1-12. igénypontok bármelyike szerinti katalizátorral érintkeztetünk hidrogénező körülmények között, így hidrogénezzük a szénhidrogénforrást.