



(86) Date de dépôt PCT/PCT Filing Date: 2005/04/21
(87) Date publication PCT/PCT Publication Date: 2005/11/24
(45) Date de délivrance/Issue Date: 2014/01/28
(85) Entrée phase nationale/National Entry: 2006/10/30
(86) N° demande PCT/PCT Application No.: US 2005/014021
(87) N° publication PCT/PCT Publication No.: 2005/110380
(30) Priorité/Priority: 2004/04/30 (US10/836,880)

(51) Cl.Int./Int.Cl. *A61K 9/00* (2006.01),
A61K 31/5377 (2006.01), *A61L 31/14* (2006.01),
A61L 31/16 (2006.01), *A61M 31/00* (2006.01),
A61P 27/06 (2006.01), *A61K 47/34* (2006.01)
(72) Inventeurs/Inventors:
HUANG, GLENN T., US;
NIVAGGIOLI, THIERRY, US
(73) Propriétaire/Owner:
ALLERGAN, INC., US
(74) Agent: GOWLING LAFLEUR HENDERSON LLP

(54) Titre : IMPLANTS INTRAOCULAIRES A LIBERATION SOUTENUE CONTENANT UN ANTAGONISTE DU
RECEPTEUR BETA-ADRENERGIQUE ET METHODES DE TRAITEMENT DE NEUROPATHIES OCULAIRES
(54) Title: SUSTAINED RELEASE INTRAOCULAR IMPLANTS COMPRISING A BETA ADRENERGIC RECEPTOR
ANTAGONIST AND METHODS FOR TREATING OCULAR NEUROPATHIES

(57) **Abrégé/Abstract:**

Biocompatible intraocular implants include a beta adrenergic receptor antagonist and a polymer associated with the beta adrenergic receptor antagonist to facilitate release of the beta adrenergic receptor antagonist into an eye for an extended period of time. The beta adrenergic receptor antagonist may be associated with a biodegradable polymer matrix, such as a matrix of a two biodegradable polymers. The implants may be placed in an eye to treat one or more ocular conditions, such as an ocular neuropathies, for example, various forms of glaucoma.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
24 November 2005 (24.11.2005)

PCT

(10) International Publication Number
WO 2005/110380 A1

(51) International Patent Classification⁷: **A61K 9/70**

(21) International Application Number:
PCT/US2005/014021

(22) International Filing Date: 21 April 2005 (21.04.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/836,880 30 April 2004 (30.04.2004) US

(71) Applicant (for all designated States except US): **ALLER-
GAN, INC.** [US/US]; 2525 Dupont Drive, Irvine, CA
92612 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **HUANG, Glenn, T.**
[US/US]; 513 Lower Vintners Circle, Fremont, CA 94539
(US). **NIVAGGIOLI, Thierry** [US/US]; 12020 Green
Hills Court, Los Altos, CA 94022 (US).

(74) Agents: **DONOVAN, Stephen** et al.; c/o Allergan, Inc.,
2525 Dupont Drive, Irvine, CA 92612 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA,
MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM,
PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY,
TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU,
ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: SUSTAINED RELEASE INTRAOCULAR IMPLANTS COMPRISING A BETA ADRENERGIC RECEPTOR AN-
TAGONIST AND METHODS FOR TREATING OCULAR NEUROPATHIES

(57) Abstract: Biocompatible intraocular implants include a beta adrenergic receptor antagonist and a polymer associated with the
beta adrenergic receptor antagonist to facilitate release of the beta adrenergic receptor antagonist into an eye for an extended period
of time. The beta adrenergic receptor antagonist may be associated with a biodegradable polymer matrix, such as a matrix of a two
biodegradable polymers. The implants may be placed in an eye to treat one or more ocular conditions, such as an ocular neuropathies,
for example, various forms of glaucoma.



WO 2005/110380 A1

SUSTAINED RELEASE INTRAOCULAR IMPLANTS COMPRISING A BETA ADRENERGIC RECEPTOR
ANTAGONIST AND METHODS FOR TREATING OCULAR NEUROPATHIES

10

BACKGROUND

The present invention generally relates to devices and methods to treat an eye of a patient, and more specifically to intraocular implants that provide extended release of a therapeutic agent to an eye in which the implant is placed, and to
15 methods of making and using such implants, for example, to treat ocular neuropathies.

Glaucoma is a progressive optic neuropathy characterized by excavation of the optic nerve head and visual field loss in the mid-periphery. Retinal ganglion cell
20 death and consequent axon loss on the retinal nerve fiber layer result in cupping of the optic disc and visual field defects typical for glaucoma.

A major risk factor in glaucoma is thought to be elevation of the intraocular pressure (IOP) beyond the statistical norm, i.e. 21 mm Hg. The high IOP originates
25 from an increased resistance to drainage of aqueous humor through the trabecular meshwork.

Although different forms of glaucoma are known, the most common form is adult onset open chamber angle glaucoma (OAG), which is age related and
30 characterized by an open angle, IOPs over 21 mm Hg, a visual field defect typical for glaucoma, and a pathologically excavated optic disc.

Beta adrenergic receptor antagonists, also known as beta-blockers, are a mainstay and a first therapy choice for glaucoma.

The available beta-blockers are typically categorized as being either
5 nonselective (also referred to as "nonspecific"), inhibiting both β_1 and β_2 –
adrenoceptors, or β_1 selective, which means that β_1 -adrenoceptors are preferably
inhibited.

Timolol maleate, (-)-1-(tert-butylamino)-3-[(4-morpholino-1,2,5-thiadiazol-3-
yl)oxy]-2-propanol maleate, (1:1) salt, is a non-selective beta-adrenergic (β_1 , and
10 β_2) receptor blocking agent that does not have sympathomimetic or myocardial
depressant activity. Timolol maleate, when applied topically, is effective in reducing
elevated intraocular pressure in most forms of glaucoma, including acute angle-
closure and secondary glaucomas.

Timolol maleate has been used clinically to lower intraocular pressure for
15 treatment of chronic OAG for approximately 30 years. It does it by inhibiting
aqueous humor production, and not by increasing outflow facility. However, as with
many types of eye drops, it is believed that only about one percent of the daily
regiment of either one drop (Timoptic XE® 0.5% q.d., Merck and Co., Inc.,
Whitehouse Station, NJ) or two drops (Timoptic® 0.5% b.i.d. Merck and Co., Inc.,
20 Whitehouse Station, NJ) actually gets absorbed inside the eyes to provide the
therapeutic level. Research studies have shown that the bioavailability of timolol
maleate can be improved by increasing its residence time in the precorneal area by
adding a thickening agent to the drop formulation which tends to enhance the
therapeutic effect of the drops.

25

The following patents and additional publications include disclosure which is
relevant to and/or helpful in understanding the present invention: U.S. Pat. Nos.
4,521,210; 4,853,224; 4,997,652; 5,164,188; 5,443,505; 5,501,856; 5,766,242;
5,824,072; 5,869,079; 6,074,661; 6,331,313; 6,369,116; and 6,699,493. David L.
30 Epstein, *Chandler and Grant's Glaucoma*, Lea & Febiger, (1986) pp 129-181;

Physician's Desk Reference for Ophthalmic Medicines, 30 Edition, (2002) p 285;
 Chiao-His Chiang, Jing-Ing Ho, and Jiin-Long Chen, *Journal of Ocular
 Pharmacology and Therapeutics*, Volume 12, Number 4, 471, (1996). Calbert I.
 Phillips, R. Shayle Bartholomew, Anthony M. Levy, Jeffrey Grove, and Roger Vogel,
 5 *British Journal of Ophthalmology*, Volume 69, 217, (1985).

There is still a need for more effective formulations and techniques for
 administering therapeutic agents, for example, beta adenergic receptor
 10 antagonists, for example, timolol maleate, to an eye in order to enhance
 bioavailability of the therapeutic agent to the eye.

It would be advantageous to provide eye implantable drug delivery systems,
 such as intraocular implants, and methods of using such systems, that are capable
 15 of releasing a therapeutic agent at a sustained or controlled rate for extended
 periods of time and in amounts with few or no negative side effects.

SUMMARY

20 The present invention provides new drug delivery systems, and methods of
 making and using such systems, for extended or sustained drug release into an eye,
 for example, to achieve one or more desired therapeutic effects. The drug delivery
 systems are in the form of implants or implant elements that may be placed in an
 eye. The present systems and methods advantageously provide for extended
 25 release times of one or more therapeutic agents. Thus, the patient in whose eye the
 implant has been placed receives a therapeutic amount of an agent for a long or
 extended time period without requiring additional administrations of the agent. For
 example, the patient has a substantially consistent level of therapeutically active
 agent available for consistent treatment of the eye over a relatively long period of
 30 time, for example, on the order of at least about one week, such as between about

two and about six months after receiving an implant. Such extended release times facilitate obtaining successful treatment results.

Intraocular implants in accordance with the disclosure herein comprise a therapeutic component and a drug release sustaining component associated with the therapeutic component. In accordance with a preferred embodiment of the present invention, the therapeutic component comprises, consists essentially of, or consists of, a beta adrenergic receptor antagonist. The drug release sustaining component is associated with the therapeutic component to sustain release of an amount of the beta adrenergic receptor antagonist into an eye in which the implant is placed. The amount of the beta adrenergic receptor antagonist is released into the eye for a period of time greater than about one week after the implant is placed in the eye and is effective in preventing or reducing ocular vasculopathies, such as vascular occlusions.

15

In one embodiment, the intraocular implants comprise a beta adrenergic receptor antagonist and a biodegradable polymer matrix. The beta adrenergic receptor antagonist is associated with a biodegradable polymer matrix that degrades at a rate effective to sustain release of an amount of the antagonist from the implant for a time sufficient to reduce or prevent an ocular vascular occlusion. The intraocular implant is biodegradable or bioerodible and provides a sustained release of the beta adrenergic receptor antagonist in an eye for extended periods of time, such as for more than one week, for example for about three months or more and up to about six months or more. In certain implants, the beta adrenergic receptor antagonist is released for about 30-35 days or less. In other implants, the beta adrenergic receptor antagonist is released for 40 days or more.

The biodegradable polymer component of the foregoing implants may be a mixture of biodegradable polymers, wherein at least one of the biodegradable polymers is a polylactic acid polymer having a molecular weight less than 64 kiloDaltons (kD). Additionally or alternatively, the foregoing implants may comprise

30

a first biodegradable polymer of a polylactic acid, and a different second biodegradable polymer of a polylactic acid. Furthermore, the foregoing implants may comprise a mixture of different biodegradable polymers, each biodegradable polymer having an inherent viscosity in a range of about 0.3 deciliters/gram (dl/g) to
5 about 1.0 dl/g.

The beta adrenergic receptor antagonist of the implants disclosed herein may include a β non specific antagonist, a β_1 selective antagonist, a β_2 selective antagonist, or other antagonists that are effective in treating ocular conditions.
10 Examples of suitable β non specific antagonist include timolol, propranolol, nadolol, pindolol and derivatives thereof. Examples of β_1 selective antagonists include metoprolol acebutolol, alprenolol, atenolol, esmolol, and derivatives thereof. An example of a β_2 selective is butoxamine. In addition, the therapeutic component of the present implants may include one or more additional and different therapeutic
15 agents that may be effective in treating an ocular condition.

A method of making the present implants involves combining or mixing the beta adrenergic receptor antagonist with a biodegradable polymer or polymers. The mixture may then be extruded or compressed to form a single composition. The
20 single composition may then be processed to form individual implants suitable for placement in an eye of a patient.

The implants may be placed in an ocular region to treat a variety of ocular conditions, including conditions such as ocular neuropathies that affect an anterior
25 region or posterior region of an eye. For example, the implants may be used to treat many conditions of the eye, including, without limitation, conditions associated with glaucoma.

Kits in accordance with the present invention may comprise one or more of
30 the present implants, and instructions for using the implants. For example, the

instructions may explain how to administer the implants to a patient, and types of conditions that may be treated with the implants.

Each and every feature described herein, and each and every combination of two or more of such features, is included within the scope of the present invention provided that the features included in such a combination are not mutually inconsistent. In addition, any feature or combination of features may be specifically excluded from any embodiment of the present invention.

Additional aspects and advantages of the present invention are set forth in the following description and claims, particularly when considered in conjunction with the accompanying drawings.

DRAWINGS

15

Fig. 1 is a graph of timolol maleate release profiles of drug delivery systems in accordance with the invention, comprising timolol maleate and a polymer, the systems each having 50% drug load.

20

Fig. 2 is a graph of timolol maleate release profiles of drug delivery systems in accordance with the invention, comprising timolol maleate and a polymer, the systems each having 50% drug load.

25

Fig. 3 is a graph of timolol maleate release profiles of drug delivery systems in accordance with the invention, comprising timolol maleate and a polymer, the systems each having 10% drug load.

30

Fig. 4 is a graph of timolol maleate release profiles of drug delivery systems in accordance with the invention, the graph comparing two different sized filaments of timolol maleate and a polymer.

Fig. 5A, 5B and 5C are graphs of timolol maleate release profiles of drug delivery systems in accordance with the invention, the graphs comparing release profiles of such systems comprising various drug loads and various polymer matrices.

5

Fig. 6 is a graph of timolol maleate release profiles of drug delivery systems in accordance with the invention, comprising timolol maleate and a polymer, in which formulations were prepared with drug content based on the weight of timolol, rather than on the weight of timolol maleate.

10

Fig. 7 is a graph showing timolol maleate in-vivo release based on total content of drug in drug delivery system retrieved after implantation.

Fig. 8 is a graph showing timolol maleate release profiles of drug delivery systems in accordance with the invention, comprising timolol maleate and a polymer, the systems each having 26% drug load.

Fig. 9A is a graph showing intraocular pressure (IOP) depressing effect of timolol maleate drug delivery systems, in accordance with the present invention, placed in the anterior chamber of an eye.

Fig. 9B is a graph showing IOP depressing effect of timolol maleate drug delivery systems, in accordance with the present invention, placed in the posterior segment of an eye.

25

Fig. 9C is a graph showing IOP depressing effect of timolol maleate drug delivery systems, in accordance with the present invention, placed under the conjunctiva of an eye.

Fig. 10 is a graph showing average IOP depressing effect of timolol maleate drug delivery systems, in accordance with the present invention, placed in the posterior segment, in the anterior chamber, and under the conjunctiva of an eye.

5 Fig. 11 is a graph showing average IOP depression after instillation of timolol eye drops (N =3)

DESCRIPTION

10

As described herein, controlled and sustained administration of a therapeutic agent through the use of one or more intraocular drug delivery systems, or implants, may improve treatment of undesirable ocular conditions. The implants comprise a pharmaceutically acceptable polymeric composition and are formulated to release
15 one or more pharmaceutically active agents, such as beta adrenergic receptor antagonists, over an extended period of time. The implants are effective to provide a therapeutically effective dosage of the agent or agents directly to a region of the eye to treat or prevent one or more undesirable ocular conditions. Thus, with a single administration, therapeutic agents will be made available at the site where
20 they are needed and will be maintained for an extended period of time, rather than subjecting the patient to repeated injections or, in the case of self-administered drops, ineffective treatment with only limited bursts of exposure to the active agent or agents.

25

An intraocular implant in accordance with the disclosure herein comprises a therapeutic component and a drug release sustaining component associated with the therapeutic component. In accordance with a preferred embodiment of the present invention, the therapeutic component comprises, consists essentially of, or consists of, a beta adrenergic receptor antagonist. The drug release sustaining
30 component is associated with the therapeutic component to sustain release of a therapeutically effective amount of the beta adrenergic receptor antagonist into an

eye in which the implant is placed. The therapeutic amount of the beta adrenergic receptor antagonist is released into the eye for a period of time greater than about one week after the implant is placed in the eye.

5 Definitions

For the purposes of this description, we use the following terms as defined in this section, unless the context of the word indicates a different meaning.

10 As used herein, an "intraocular implant" refers to a device or element that is structured, sized, or otherwise configured to be placed in an eye. Intraocular implants are generally biocompatible with physiological conditions of an eye and do not cause adverse side effects. Intraocular implants may be placed in an eye without disrupting vision of the eye.

15 As used herein, a "therapeutic component" refers to a portion of an intraocular implant comprising one or more therapeutic agents or substances used to treat a medical condition of the eye. The therapeutic component may be a discrete region of an intraocular implant, or it may be homogenously distributed
20 throughout the implant. The therapeutic agents of the therapeutic component are typically ophthalmically acceptable, and are provided in a form that does not cause adverse reactions when the implant is placed in an eye.

As used herein, a "drug release sustaining component" refers to a portion of
25 the intraocular implant that is effective to provide a sustained release of the therapeutic agents of the implant. A drug release sustaining component may be a biodegradable polymer matrix, or it may be a coating covering a core region of the implant that comprises a therapeutic component.

30 As used herein, "associated with" means mixed with, dispersed within, coupled to, covering, or surrounding.

As used herein, an "ocular region" or "ocular site" refers generally to any area of the eyeball, including the anterior and posterior segment of the eye, and which generally includes, but is not limited to, any functional (e.g., for vision) or structural tissues found in the eyeball, or tissues or cellular layers that partly or completely line the interior or exterior of the eyeball. Specific examples of areas of the eyeball in an ocular region include the anterior chamber, the posterior chamber, the vitreous cavity, the choroid, the suprachoroidal space, the conjunctiva, the subconjunctival space, the episcleral space, the intracorneal space, the epicorneal space, the sclera, the pars plana, surgically-induced avascular regions, the macula, and the retina.

As used herein, an "ocular condition" is a disease, ailment or condition which affects or involves the eye or one of the parts or regions of the eye. Broadly speaking the eye includes the eyeball and the tissues and fluids which constitute the eyeball, the periocular muscles (such as the oblique and rectus muscles) and the portion of the optic nerve which is within or adjacent to the eyeball.

An anterior ocular condition is a disease, ailment or condition which affects or which involves an anterior (i.e. front of the eye) ocular region or site, such as a periocular muscle, an eye lid or an eye ball tissue or fluid which is located anterior to the posterior wall of the lens capsule or ciliary muscles. Thus, an anterior ocular condition primarily affects or involves the conjunctiva, the cornea, the anterior chamber, the iris, the posterior chamber (behind the retina but in front of the posterior wall of the lens capsule), the lens or the lens capsule and blood vessels and nerve which vascularize or innervate an anterior ocular region or site.

Thus, an anterior ocular condition can include a disease, ailment or condition, such as for example, aphakia; pseudophakia; astigmatism; blepharospasm; cataract; conjunctival diseases; conjunctivitis; corneal diseases; corneal ulcer; dry eye syndromes; eyelid diseases; lacrimal apparatus diseases; lacrimal duct obstruction; myopia; presbyopia; pupil disorders; refractive disorders and strabismus. Glaucoma

can also be considered to be an anterior ocular condition because a clinical goal of glaucoma treatment can be to reduce a hypertension of aqueous fluid in the anterior chamber of the eye (i.e. reduce intraocular pressure).

5 A posterior ocular condition is a disease, ailment or condition which primarily affects or involves a posterior ocular region or site such as choroid or sclera (in a position posterior to a plane through the posterior wall of the lens capsule), vitreous, vitreous chamber, retina, optic nerve (i.e. the optic disc), and blood vessels and nerves which vascularize or innervate a posterior ocular region or site.

10

Thus, a posterior ocular condition can include a disease, ailment or condition, such as for example, acute macular neuroretinopathy; Behcet's disease; choroidal neovascularization; diabetic uveitis; histoplasmosis; infections, such as fungal or viral-caused infections; macular degeneration, such as acute macular degeneration, 15 non-exudative age related macular degeneration and exudative age related macular degeneration; edema, such as macular edema, cystoid macular edema and diabetic macular edema; multifocal choroiditis; ocular trauma which affects a posterior ocular site or location; ocular tumors; retinal disorders, such as central retinal vein occlusion, diabetic retinopathy (including proliferative diabetic retinopathy), 20 proliferative vitreoretinopathy (PVR), retinal arterial occlusive disease, retinal detachment, uveitic retinal disease; sympathetic ophthalmia; Vogt Koyanagi-Harada (VKH) syndrome; uveal diffusion; a posterior ocular condition caused by or influenced by an ocular laser treatment; posterior ocular conditions caused by or influenced by a photodynamic therapy, photocoagulation, radiation retinopathy, 25 epiretinal membrane disorders, branch retinal vein occlusion, anterior ischemic optic neuropathy, non-retinopathy diabetic retinal dysfunction, retinitis pigmentosa, and glaucoma. Glaucoma can be considered a posterior ocular condition because the therapeutic goal is to prevent the loss of or reduce the occurrence of loss of vision due to damage to or loss of retinal cells or optic nerve cells (i.e. neuroprotection).

30

The present invention is especially useful in the treatment of the glaucoma, including any of the several different types of glaucoma, including angle-closure glaucoma, neovascular glaucoma, open-angle glaucoma and hydrophthalmos.

5 The terms "biodegradable" and "bioerodible" are generally used interchangeably herein.

10 The term "biodegradable polymer" refers to a polymer or polymers which degrade in vivo, and wherein erosion of the polymer or polymers over time occurs concurrent with or subsequent to release of the therapeutic agent. Specifically, hydrogels such as methylcellulose which act to release drug through polymer swelling are specifically excluded from the term "biodegradable polymer". The terms "biodegradable" and "bioerodible" are equivalent and are used interchangeably herein. A biodegradable polymer may be a homopolymer, a copolymer, or a
15 polymer comprising more than two different polymeric units.

20 The term "treat", "treating", or "treatment" as used herein, refers to reduction or resolution or prevention of an ocular condition, ocular injury or damage, or to promote healing of injured or damaged ocular tissue.

20

 The term "therapeutically effective amount" as used herein, refers to the level or amount of agent needed to treat an ocular condition, or reduce or prevent ocular injury or damage without causing significant negative or adverse side effects to the eye or a region of the eye.

25

 Intraocular implants have been developed which can release drug loads over various time periods. These implants, which when inserted into an eye, such as the vitreous of an eye, provide therapeutic levels of a beta adrenergic receptor antagonist for extended periods of time (e.g., for about 1 week or more). The
30 implants disclosed are effective in treating ocular conditions, for example ocular neuropathies such as glaucoma.

In one embodiment of the present invention, an intraocular implant comprises a biodegradable polymer matrix. The biodegradable polymer matrix is one type of a drug release sustaining component. The biodegradable polymer matrix is effective
5 in forming a biodegradable intraocular implant. The biodegradable intraocular implant comprises a beta adrenergic receptor antagonist associated with the biodegradable polymer matrix. Preferably, the matrix degrades at a rate effective to sustain release of an amount of the beta adrenergic receptor antagonist for a time greater than about one week from the time in which the implant is placed in ocular
10 region or ocular site, such as the vitreous of an eye.

The beta adrenergic receptor antagonist of the implant may be beta nonspecific or beta specific. In a preferred embodiment of the invention, the beta adrenergic receptor antagonist is selected from the group consisting of timolol,
15 bexatol, levobunolol, carteolol, metiprenolol, derivatives thereof and mixtures thereof. For example, the beta adrenergic receptor antagonist comprises timolol maleate. Generally, the beta adrenergic receptor antagonist of the implants disclosed herein may include a β non specific antagonist, a β_1 , selective antagonist, a β_2 selective antagonist, or other antagonists that are effective in treating ocular
20 conditions. Examples of β non-specific antagonist include timolol, propranolol, nadolol, pindolol and derivatives thereof. Examples of β_1 selective antagonists include metoprolol acebutolol, alprenolol, atenolol, esmolol, and derivatives thereof. An example of a β_2 selective is butoxamine.

25 Pharmaceutically acceptable acid addition salts of the compounds of the invention are those formed from acids which form non-toxic addition salts containing pharmaceutically acceptable anions, such as the hydrochloride, hydrobromide, hydroiodide, sulfate, or bisulfate, phosphate or acid phosphate, acetate, maleate, fumarate, oxalate, lactate, tartrate, citrate, gluconate, saccharate and p-toluene
30 sulphonate salts.

Thus, the implant may comprise a therapeutic component which comprises, consists essentially of, or consists of a timolol salt, such as timolol maleate.

The beta adrenergic receptor antagonist may be in a particulate or powder
5 form and entrapped by the biodegradable polymer matrix. Beta adrenergic receptor antagonist particles commonly have an effective average size less than about 3000 nanometers. In certain implants, the particles may have an effective average particle size about an order of magnitude smaller than 3000 nanometers. For example, the particles may have an effective average particle size of less than about
10 500 nanometers. In additional implants, the particles may have an effective average particle size of less than about 400 nanometers, and in still further embodiments, a size less than about 200 nanometers.

The beta adrenergic receptor antagonist of the implant is preferably from
15 about 10% to 90% by weight of the implant. More preferably, the beta adrenergic receptor antagonist is from about 20% to about 80% by weight of the implant. In a preferred embodiment, the beta adrenergic receptor antagonist comprises about 20% by weight of the implant, or about 26% by weight of the implant. In another embodiment, the beta adrenergic receptor antagonist comprises up to about 50% by
20 weight of the implant.

Suitable polymeric materials or compositions for use in the implant include those materials which are compatible, that is biocompatible, with the eye so as to cause no substantial interference with the functioning or physiology of the eye. Such
25 materials preferably are at least partially and more preferably substantially completely biodegradable or bioerodible.

Examples of useful polymeric materials include, without limitation, such materials derived from and/or including organic esters and organic ethers, which
30 when degraded result in physiologically acceptable degradation products, including the monomers. Also, polymeric materials derived from and/or including, anhydrides,

amides, orthoesters and the like, by themselves or in combination with other monomers, may also find use. The polymeric materials may be addition or condensation polymers, advantageously condensation polymers. The polymeric materials may be cross-linked or non-cross-linked, for example not more than lightly cross-linked, such as less than about 5%, or less than about 1% of the polymeric material being cross-linked. For the most part, besides carbon and hydrogen, the polymers will include at least one of oxygen and nitrogen, advantageously oxygen. The oxygen may be present as oxy, e.g. hydroxy or ether, carbonyl, e.g. non-oxo-carbonyl, such as carboxylic acid ester, and the like. The nitrogen may be present as amide, cyano and amino. The polymers set forth in Heller, Biodegradable Polymers in Controlled Drug Delivery, In: CRC Critical Reviews in Therapeutic Drug Carrier Systems, Vol. 1, CRC Press, Boca Raton, FL 1987, pp 39-90, which describes encapsulation for controlled drug delivery, may find use in the present implants.

15

Of additional interest are polymers of hydroxyaliphatic carboxylic acids, either homopolymers or copolymers, and polysaccharides. Polyesters of interest include polymers of D-lactic acid, L-lactic acid, racemic lactic acid, glycolic acid, polycaprolactone, and combinations thereof. Generally, by employing the L-lactate or D-lactate, a slowly eroding polymer or polymeric material is achieved, while erosion is substantially enhanced with the lactate racemate.

Among the useful polysaccharides are, without limitation, calcium alginate, and functionalized celluloses, particularly carboxymethylcellulose esters characterized by being water insoluble, a molecular weight of about 5 kD to 500 kD, for example.

Other polymers of interest include, without limitation, polyvinyl alcohol, polyesters, polyethers and combinations thereof which are biocompatible and may be biodegradable and/or bioerodible.

Some preferred characteristics of the polymers or polymeric materials for use in the present invention may include biocompatibility, compatibility with the therapeutic component, ease of use of the polymer in making the drug delivery systems of the present invention, a half-life in the physiological environment of at least about 6 hours, preferably greater than about one day, not significantly increasing the viscosity of the vitreous, and water insolubility.

The biodegradable polymeric materials which are included to form the matrix are desirably subject to enzymatic or hydrolytic instability. Water soluble polymers may be cross-linked with hydrolytic or biodegradable unstable cross-links to provide useful water insoluble polymers. The degree of stability can be varied widely, depending upon the choice of monomer, whether a homopolymer or copolymer is employed, employing mixtures of polymers, and whether the polymer includes terminal acid groups.

Equally important to controlling the biodegradation of the polymer and hence the extended release profile of the implant is the relative average molecular weight of the polymeric composition employed in the implant. Different molecular weights of the same or different polymeric compositions may be included in the implant to modulate the release profile. In certain implants, the relative average molecular weight of the polymer will range from about 9 to about 64 kD, usually from about 10 to about 54 kD, and more usually from about 12 to about 45 kD.

In some implants, copolymers of glycolic acid and lactic acid are used, where the rate of biodegradation is controlled by the ratio of glycolic acid to lactic acid. The most rapidly degraded copolymer has roughly equal amounts of glycolic acid and lactic acid. Homopolymers, or copolymers having ratios other than equal, are more resistant to degradation. The ratio of glycolic acid to lactic acid will also affect the brittleness of the implant, where a more flexible implant is desirable for larger geometries. The % of polylactic acid in the polylactic acid polyglycolic acid (PLGA)

copolymer can be 0-100%, preferably about 15-85%, more preferably about 35-65%. In some implants, a 50/50 PLGA copolymer is used.

5 The biodegradable polymer matrix of the intraocular implant may comprise a mixture of two or more biodegradable polymers. For example, the implant may comprise a mixture of a first biodegradable polymer and a different second biodegradable polymer. One or more of the biodegradable polymers may have terminal acid groups.

10 Release of a drug from an erodible polymer is the consequence of several mechanisms or combinations of mechanisms. Some of these mechanisms include desorption for the surface of the implant, dissolution, diffusion through porous channels of the hydrated polymer and erosion. Erosion can be bulk erosion, or surface erosion, or a combination of both. As discussed herein, the matrix of the
15 intraocular implant may release drug at a rate effective to sustain release of an amount of the beta adrenergic receptor antagonist for more than one week after implantation into an eye. In certain implants, therapeutic amounts of the beta adrenergic receptor antagonist are released for more about 30-35 days after implantation. For example, an implant may comprise timolol maleate, and the matrix
20 of the implant releases drug at a rate effective to sustain release of a therapeutically effective amount of timolol maleate for about one month after being placed in an eye. As another example, the implant may comprise timolol maleate, and the matrix degrades at a rate effective to sustain release of a therapeutically effective amount of timolol for more than forty days, such as for about six months.

25 One example of the biodegradable intraocular implant comprises a beta adrenergic receptor antagonist associated with a biodegradable polymer matrix, which comprises a mixture of different biodegradable polymers. At least one of the biodegradable polymers is a polylactide having a molecular weight of about 63.3 kD.
30 A second biodegradable polymer is a polylactide having a molecular weight of about 14 kD. Such a mixture is effective in sustaining release of a therapeutically effective

amount of the beta adrenergic receptor antagonist for a time period greater than about one month from the time the implant is placed in an eye.

Another example of a biodegradable intraocular implant comprises a beta
5 adrenergic receptor antagonist associated with a biodegradable polymer matrix, which comprises a mixture of different biodegradable polymers, each biodegradable polymer having an inherent viscosity from about 0.16 dl/g to about 1.0 dl/g. For example, one of the biodegradable polymers may have an inherent viscosity of about 0.3 dl/g. A second biodegradable polymer may have an inherent viscosity of
10 about 1.0 dl/g. The inherent viscosities identified above may be determined in 0.1% chloroform at 25°C.

One particular implant comprises timolol maleate associated with a combination of two different polylactide polymers. The timolol maleate is present in
15 about 20% by weight of the implant. One polylactide polymer has a molecular weight of about 14 kD and an inherent viscosity of about 0.3 dl/g, and the other polylactide polymer has a molecular weight of about 63.3 kD and an inherent viscosity of about 1.0 dl/g. The two polylactide polymers are present in the implant in a 1:1 ratio. Such an implant provides for release of the timolol for more than two
20 months *in vitro*, as described herein. The implant is provided in the form of a rod or a filament produced by an extrusion process.

The release of the beta adrenergic receptor antagonist from the intraocular implant comprising a biodegradable polymer matrix may include an initial burst of
25 release followed by a gradual increase in the amount of the beta adrenergic receptor antagonist released, or the release may include an initial delay in release of the beta adrenergic receptor antagonist followed by an increase in release. When the implant is substantially completely degraded, the percent of the beta adrenergic receptor antagonist that has been released is about one hundred. Compared to
30 existing implants, the implants disclosed herein do not completely release, or

release about 100% of the beta adrenergic receptor antagonist, until after about one week of being placed in an eye.

It may be desirable to provide a relatively constant rate of release of the beta
5 adrenergic receptor antagonist from the implant over the life of the implant. For
example, it may be desirable for the beta adrenergic receptor antagonist to be
released in amounts from about 0.01 μg to about 2 μg per day for the life of the
implant. However, the release rate may change to either increase or decrease
depending on the formulation of the biodegradable polymer matrix. In addition, the
10 release profile of the beta adrenergic receptor antagonist may include one or more
linear portions and/or one or more non-linear portions. Preferably, the release rate
is greater than zero once the implant has begun to degrade or erode.

The implants may be monolithic, i.e. having the active agent or agents
15 homogenously distributed through the polymeric matrix, or encapsulated, where a
reservoir of active agent is encapsulated by the polymeric matrix. Due to ease of
manufacture, monolithic implants are usually preferred over encapsulated forms.
However, the greater control afforded by the encapsulated, reservoir-type implant
may be of benefit in some circumstances, where the therapeutic level of the drug
20 falls within a narrow window. In addition, the therapeutic component, including the
beta adrenergic receptor antagonist, may be distributed in a non-homogenous
pattern in the matrix. For example, the implant may include a portion that has a
greater concentration of the beta adrenergic receptor antagonist relative to a second
portion of the implant.

25

The intraocular implants disclosed herein may have a size of between about 5
 μm and about 2 mm, or between about 10 μm and about 1 mm for administration
with a needle, greater than 1 mm, or greater than 2 mm, such as 3 mm or up to 10
mm, for administration by surgical implantation. The vitreous chamber in humans is
30 able to accommodate relatively large implants of varying geometries, having lengths
of, for example, 1 to 10 mm. The implant may be a cylindrical pellet (e. g., rod) with

dimensions of about 2 mm x 0.75 mm diameter, or for example, the implant may be a cylindrical pellet with a length of about 7 mm to about 10 mm, and a diameter of about 0.75 mm to about 1.5 mm.

5 The implants may also be at least somewhat flexible so as to facilitate both insertion of the implant in the eye, such as in the vitreous, and accommodation of the implant. The total weight of the implant is usually about 250-5000 µg, more preferably about 500-1000 µg. For example, an implant may be about 500 µg, or about 1000 µg. For non-human individuals, the dimensions and total weight of the
10 implant(s) may be larger or smaller, depending on the type of individual. For example, humans have a vitreous volume of approximately 3.8 ml, compared with approximately 30 ml for horses, and approximately 60-100 ml for elephants. An implant sized for use in a human may be scaled up or down accordingly for other animals, for example, about 8 times larger for an implant for a horse, or about, for
15 example, 26 times larger for an implant for an elephant.

Thus, implants can be prepared where the center may be of one material and the surface may have one or more layers of the same or a different composition, where the layers may be cross-linked, or of a different molecular weight, different
20 density or porosity, or the like. For example, where it is desirable to quickly release an initial bolus of drug, the center may be a polylactate coated with a polylactate-polyglycolate copolymer, so as to enhance the rate of initial degradation. Alternatively, the center may be polyvinyl alcohol coated with polylactate, so that upon degradation of the polylactate exterior the center would dissolve and be rapidly
25 washed out of the eye.

The implants may be of any geometry including fibers, sheets, films, microspheres, spheres, circular discs, plaques and the like. The upper limit for the implant size will be determined by factors such as toleration for the implant, size
30 limitations on insertion, ease of handling, etc. Where sheets or films are employed, the sheets or films will be in the range of at least about 0.5 mm x 0.5 mm, usually

about 3-10 mm x 5-10 mm with a thickness of about 0.1-1.0 mm for ease of handling. Where fibers are employed, the fiber diameter will generally be in the range of about 0.05 to 3 mm and the fiber length will generally be in the range of about 0.5-10 mm. Spheres may be in the range of 0.5 μ m to 4 mm in diameter, with
5 comparable volumes for other shaped particles.

The size and form of the implant can also be used to control the rate of release, period of treatment, and drug concentration at the site of implantation. Larger implants will deliver a proportionately larger dose, but depending on the
10 surface to mass ratio, may have a slower release rate. The particular size and geometry of the implant are chosen to suit the site of implantation.

The proportions of beta adrenergic receptor antagonist, polymer, and any other modifiers may be empirically determined by formulating several implants with
15 varying proportions. A USP approved method for dissolution or release test can be used to measure the rate of release (USP 23; NF 18 (1995) pp. 1790-1798). For example, using the infinite sink method, a weighed sample of the implant is added to a measured volume of a solution containing 0.9% NaCl in water, where the solution volume will be such that the drug concentration is after release is less than 5% of
20 saturation. The mixture is maintained at 37°C and stirred slowly to maintain the implants in suspension. The appearance of the dissolved drug as a function of time may be followed by various methods known in the art, such as spectrophotometrically, HPLC, mass spectroscopy, etc. until the absorbance becomes constant or until greater than 90% of the drug has been released.

25

In addition to the beta adrenergic receptor antagonist or beta adrenergic receptor antagonists included in the intraocular implants disclosed herein, the intraocular implants may also include one or more additional ophthalmically acceptable therapeutic agents. For example, the implant may include one or more
30 antihistamines, one or more antibiotics, one or more alpha adrenergic receptor agonists, one or more steroids, one or more antineoplastic agents, one or more

immunosuppressive agents, one or more antiviral agents, one or more antioxidant agents, and mixtures thereof.

Pharmacologic or therapeutic agents which may find use in the present systems, include, without limitation, those disclosed in U.S. Pat. Nos. 4,474,451, columns 4-6 and 4,327,725, columns 7-8.

Examples of antihistamines include, and are not limited to, loradatine, hydroxyzine, diphenhydramine, chlorpheniramine, brompheniramine, cyproheptadine, terfenadine, clemastine, triprolidine, carbinoxamine, diphenylpyraline, phenindamine, azatadine, tripeleminamine, dexchlorpheniramine, dexbrompheniramine, methdilazine, and trimprazine doxylamine, pheniramine, pyrilamine, chlorcyclizine, thonzylamine, and derivatives thereof.

Examples of antibiotics include without limitation, cefazolin, cephradine, cefaclor, cephapirin, ceftizoxime, cefoperazone, cefotetan, cefutaxime, cefotaxime, cefadroxil, ceftazidime, cephalixin, cephalothin, cefamandole, cefoxitin, cefonicid, ceforanide, ceftriaxone, cefadroxil, cephradine, cefuroxime, ampicillin, amoxicillin, cyclacillin, ampicillin, penicillin G, penicillin V potassium, piperacillin, oxacillin, bacampicillin, cloxacillin, ticarcillin, azlocillin, carbenicillin, methicillin, nafcillin, erythromycin, tetracycline, doxycycline, minocycline, aztreonam, chloramphenicol, ciprofloxacin hydrochloride, clindamycin, metronidazole, gentamicin, lincomycin, tobramycin, vancomycin, polymyxin B sulfate, colistimethate, colistin, azithromycin, augmentin, sulfamethoxazole, trimethoprim, and derivatives thereof.

Examples of alpha adrenergic receptor agonists include quinoxalines, (2-imidozolin-2-ylamino) quinoxalines, 5-bromo-6-(2-imidozolin-2-ylamino) quinoxalines, derivatives thereof and mixtures thereof.

Examples of steroids include corticosteroids, such as cortisone, prednisolone, flurometholone, dexamethasone, medrysone, loteprednol, fluazacort,

hydrocortisone, prednisone, betamethasone, prednisone, methylprednisolone, triamcinolone hexacetonide, paramethasone acetate, diflorasone, fluocinonide, fluocinolone, triamcinolone, derivatives thereof, and mixtures thereof.

5 Examples of antineoplastic agents include adriamycin, cyclophosphamide, actinomycin, bleomycin, daunorubicin, doxorubicin, epirubicin, mitomycin, methotrexate, fluorouracil, carboplatin, carmustine (BCNU), methyl-CCNU, cisplatin, etoposide, interferons, camptothecin and derivatives thereof, phenesterine, taxol and derivatives thereof, taxotere and derivatives thereof, vinblastine, vincristine,
10 tamoxifen, etoposide, pipsulfan, cyclophosphamide, and flutamide, and derivatives thereof.

 Examples of immunosuppressive agents include cyclosporine, azathioprine, tacrolimus, and derivatives thereof.

15

 Examples of antiviral agents include interferon gamma, zidovudine, amantadine hydrochloride, ribavirin, acyclovir, valciclovir, dideoxycytidine, phosphonoformic acid, ganciclovir and derivatives thereof.

20 Examples of antioxidant agents include ascorbate, alpha-tocopherol, mannitol, reduced glutathione, various carotenoids, cysteine, uric acid, taurine, tyrosine, superoxide dismutase, lutein, zeaxanthin, cryptoxanthin, astaxanthin, lycopene, N-acetyl-cysteine, carnosine, gamma-glutamylcysteine, quercetin, lactoferrin, dihydrolipoic acid, citrate, Ginkgo Biloba extract, tea catechins, bilberry
25 extract, vitamins E or esters of vitamin E, retinyl palmitate, and derivatives thereof.

 Other therapeutic agents include squalamine, carbonic anhydrase inhibitors, prostamides, prostaglandins, antiparasitics, antifungals, and derivatives thereof.

30 The amount of active agent or agents employed in the implant, individually or in combination, will vary widely depending on the effective dosage required and the

desired rate of release from the implant. Usually the agent will be at least about 1, more usually at least about 10 weight percent of the implant, and usually not more than about 80, more usually not more than about 40 weight percent of the implant.

5 In addition to the therapeutic component, the intraocular implants disclosed herein may include effective amounts of buffering agents, preservatives and the like. Suitable water soluble buffering agents include, without limitation, alkali and alkaline earth carbonates, phosphates, bicarbonates, citrates, borates, acetates, succinates and the like, such as sodium phosphate, citrate, borate, acetate, bicarbonate,
10 carbonate and the like. These agents advantageously present in amounts sufficient to maintain a pH of the system of between about 2 to about 9 and more preferably about 4 to about 8. As such the buffering agent may be as much as about 5% by weight of the total implant. Suitable water soluble preservatives include sodium bisulfite, sodium bisulfate, sodium thiosulfate, ascorbate, benzalkonium chloride,
15 chlorobutanol, thimerosal, phenylmercuric acetate, phenylmercuric borate, phenylmercuric nitrate, parabens, methylparaben, polyvinyl alcohol, benzyl alcohol, phenylethanol and the like and mixtures thereof. These agents may be present in amounts of from 0.001 to about 5% by weight and preferably 0.01 to about 2% by weight. In at least one of the present implants, a purite preservative is provided in
20 the implant, such as when the beta adrenergic receptor antagonist is timolol. Thus, these implants may contain a therapeutically effective amount of Alphagan-P®.

In some situations mixtures of implants may be utilized employing the same or different pharmacological agents. In this way, a cocktail of release profiles, giving
25 a biphasic or triphasic release with a single administration is achieved, where the pattern of release may be greatly varied.

Additionally, release modulators such as those described in U. S. Patent No. 5,869,079 may be included in the implants. The amount of release modulator
30 employed will be dependent on the desired release profile, the activity of the modulator, and on the release profile of the beta adrenergic receptor antagonist in

the absence of modulator. Electrolytes such as sodium chloride and potassium chloride may also be included in the implant. Where the buffering agent or enhancer is hydrophilic, it may also act as a release accelerator. Hydrophilic additives act to increase the release rates through faster dissolution of the material surrounding the drug particles, which increases the surface area of the drug exposed, thereby increasing the rate of drug bioerosion. Similarly, a hydrophobic buffering agent or enhancer dissolve more slowly, slowing the exposure of drug particles, and thereby slowing the rate of drug bioerosion.

In certain implants, an implant comprising timolol or timolol maleate and a biodegradable polymer matrix is able to release or deliver an amount of timolol between about 0.1 mg to about 0.5 mg for about 3-6 months after implantation into the eye. The implant may be configured as a rod or a wafer. A rod-shaped implant may be derived from filaments extruded from a 720 μm nozzle and cut into 1 mg size. A wafer-shaped implant may be a circular disc having a diameter of about 2.5 mm, a thickness of about 0.127 mm, and a weight of about 1 mg.

The proposed 3-month release formulations may be sterile, and bioerodible in the form of a rod, a wafer or a microsphere containing timolol maleate within a PLA matrix or POE matrix. The implants are designed to delay the clearance of the drug and reduce the need for repeated implantation over 3-month period, thereby lowering the risk of complications.

Various techniques may be employed to produce the implants described herein. Useful techniques include, but are not necessarily limited to, solvent evaporation methods, phase separation methods, interfacial methods, molding methods, injection molding methods, extrusion methods, co-extrusion methods, carver press method, die cutting methods, heat compression, combinations thereof and the like.

Specific techniques and methods are discussed in Wong, U.S. Pat. No. 4,997,652. Extrusion methods may be used to avoid the need for solvents in manufacturing. When using extrusion methods, the polymer and drug are chosen so as to be stable at the temperatures required for manufacturing, usually at least about 5 85 degrees Celsius. Extrusion methods use temperatures of about 25 degrees C to about 150 degrees C, more preferably about 65 degrees C to about 130 degrees C. An implant may be produced by bringing the temperature to about 60 degrees C to about 150 degrees C for drug/polymer mixing, such as about 130 degrees C, for a time period of about 0 to 1 hour, 0 to 30 minutes, or 5-15 minutes. For example, a 10 time period may be about 10 minutes, preferably about 0 to 5 min. The implants are then extruded at a temperature of about 60 degrees C to about 130 degrees C, such as about 75 degrees C.

In addition, the implant may be coextruded so that a coating is formed over a 15 core region during the manufacture of the implant.

Compression methods may be used to make the implants, and typically yield implants with faster release rates than extrusion methods. Compression methods may use pressures of about 50-150 psi, more preferably about 70-80 psi, even more 20 preferably about 76 psi, and use temperatures of about 0 degrees C to about 115 degrees C, more preferably about 25 degrees C.

The implants of the present invention may be inserted into the eye, for example the vitreous chamber of the eye, by a variety of methods, including 25 placement by forceps or by trocar following making a 2-3 mm incision in the sclera. One example of a device that may be used to insert the implants into an eye is disclosed in U.S. Pat. App. No. 10/246,884, filed on September 18, 2002, which is U.S. Patent Publication No. 2004/0054374. The method of placement may influence the therapeutic component or drug release kinetics. For example, delivering the implant with 30' a trocar may result in placement of the implant deeper within the vitreous than

placement by forceps, which may result in the implant being closer to the edge of the vitreous. The location of the implant may influence the concentration gradients of therapeutic component or drug surrounding the element, and thus influence the release rates (e.g., an element placed closer to the edge of the vitreous may result
5 in a slower release rate).

The present implants are configured to release an amount of beta adrenergic receptor antagonist in an eye for a period of time to minimize an ocular neuropathy, such as open angle glaucoma. By implanting the beta adrenergic receptor
10 antagonist-containing implants into the vitreous of an eye, it is believed that the antagonist is effective to reduce IOP of the eye.

EXAMPLE 1

Manufacture of implants containing timolol and
15 a biodegradable polymer matrix.

Biodegradable drug delivery systems, or implants, in accordance with the invention, were made by combining timolol maleate or timolol freebase with a biodegradable polymer composition.

20 More specifically, implants were made in forms of pellets and wafers. For example, drug delivery system pellet elements, typically cylindrical in form, were made as pellets having sizes and weights of 1.8 mm L x about 0.72 mm diameter and 900 µg to 11 00 µg by weight, or pellets having sizes and weights of 1.2 mm Lx 0.38 mm diameter and 216 to 264 µg by weight. Drug delivery system wafer
25 elements were made as generally circular wafers having a size and weight of 0.13 mm thickness x 2.5 mm diameter and 900 µg to 1100 µg weight.

Different formulations of such pellet elements and wafer elements were made and tested as described hereinafter. In each formulation, an active pharmaceutical ingredient (API), timolol maleate, was combined with a polymer.

The polymers chosen for the formulation work were obtained from Boehringer Ingelheim. The polymers were: Resomer RG502, RG502H, RG503, RG504, RG505, RG506, RG752, RG755, RG756, RG858, R202H, R203, and R206. Resomer RG502, RG502H, RG503, RG504, RG505, and RG506 are all 50:50 poly (D, L-lactide-co-glycolide) with inherent viscosities of 0.2, 0.2, 0.4, 0.5, 0.7 and 0.8 dL/g, respectively. RG752, RG755, and RG756 are 75:25 poly (D,L lactide-co-glycolide) with inherent viscosities of 0.2, 0.6, and 0.8 dL/g, respectively. RG858 is 85:15 poly (D,L-lactide-co-glycolide) with inherent viscosity of 1.4 dL/g, and R203 and R206 are poly (D,L-lactide) with inherent viscosities of 0.3 and 1.0 dL/g, respectively. Finally, R202H is poly (D,L-lactide) with inherent viscosity of 0.2 and acid end.

For each formulation, the drug and polymer were combined in a stainless steel mortar and mixed by means of a Turbula shaker set at 96 RPM for 15 minutes. The powder blend was scraped off the wall of the mortar and then remixed for an additional 15 minutes. The mixed powder blend was transferred into a Teflon beaker and heated to a molten state at 95 °C for a total of about 30 to 60 minutes, in ten 3-6 minute intervals, to form a homogeneous polymer/drug melt.

The polymer/drug melt was then made into pellets and wafers. More specifically, the melt was pelletized using a 9 gauge polytetrafluoroethylene (PTFE) tubing. The pellets were loaded into the barrel of a piston extruder and extruded at the specified core extrusion temperature into filaments, then cut into about 1 mg size pellets. The melt was made into wafers by means of a Carver press utilized at a appropriate temperature and pressure, and thereafter pressed polymer/drug sheets were cut into wafers, each weighing about 1 mg.

Testing of implants containing timolol and
a biodegradable polymer matrix.

The in-vitro drug rate release testing was performed as follows.

Each implant, either pellet or wafer, was placed into a 40 mL screw cap vial each filled with 10 mL of 0.9 % saline and the vials were placed into shaken water bath at 37°C/50 rpm. At specified time points, 8 mL aliquots were removed and replaced with equal volume of fresh medium. The drug assays were performed by HPLC, which generally consists of a Waters HPLC system, including a 2690 Separation Module (or 2696 Separation Module), and a 2996 Photodiode Array Detector. A Metachem Inertsil, RP C-18, 5 µm; 4.6 x 250 mm column was used for separation, and detector was set at 295 nm. The mobile phase was (25:75) acetonitrile-0.01 M KH₂PO₄, pH = 2.8, with flow rate of 1 mL/min and a total run time of 6 min per sample. The release rates were determined by calculating the amount of drug being released in a given volume of medium over time in µg/day.

The drug assays for the in-vivo samples was performed under the same HPLC condition as those of in-vitro samples except the mobile phase was (20:80) acetonitrile-0.01 M KH₂PO₄, pH = 2.8.

Implants containing a 50% drug load and various polymers were screened. Formulation screening work started out with RG502, RG503, RG504, R203, RG752, RG755, and R202H with weight average molecular weight (Mw) of 8,400; 28,300; na; 14,000; 11,200; 40,000; and 6500 daltons, respectively. Turning to Fig. 1, a graph showing timolol maleate release rate profiles for the 50% drug load implants made with these various different polymers, is shown.

Data revealed that all 50% drug load formulations exhibited very fast one day release, with half of the formulations reached release greater than about 90% at day one, while the other half of the formulations released between 40% to 85% of the timolol maleate at day one, as shown in Figure 1.

This initial high drug release rate resulted in part because of the high solubility of timolol maleate in aqueous medium. Although not wishing to be bound by any particular theory of operation, it is believed that once the implant is in contact with the dissolution medium, the timolol maleate on the surface of the implant dissolves

quickly and diffuses out of the matrix thereby leaving channels allowing more dissolution medium to diffuse inside the implant and dissolve more timolol maleate.

Timolol freebase, a non-salt form of timolol maleate, is less soluble in the same dissolution medium. With that in mind, three different formulations of timolol maleate implants were made with an equivalent of sodium carbonate added in RG502, and separately in R203 in an attempt to generate the freebase in-situ and therefore slow down the release rate of timolol. It was observed that, the release rates of these implants behaved as if no timolol freebase was being generated in-situ, as shown in Table 1.

Table 1. Formulations with one equivalent of Na_2CO_3 added (saline, 37°C, n=6)

Formulation #	RT #	Lot #	Timolol	Polymer	Nozzle	Size	Day 1
9	265-68	241-142	45%	RG502	380 um	240 ug	78.70%
10	265-78	241-143	24%	RG502	380 um	240 ug	61.30%
11	265-69	241-144	45%	R203	380 um	240 ug	94.10%

As shown, formulations 9, 10, and 11 showed a release of approximately 79%, 61%, and 94%, respectively. After day one, this particular release study was stopped.

Tests were performed in attempt to determine any correlation between drug load and drug release profile. Implants having drug loads of 25% and 50% timolol maleate in RG502 and in R206 were prepared. A graph of the drug release profiles is shown in Figure 2.

It was found that by reducing the drug load by half, the release on day one was reduced by more than two folds. Day one release for 25% timolol maleate in RG502 was about 13.7%, comparing to approximately 66% for the 50% drug load samples, and day one release for 25% timolol maleate in R206 was about 20.0% comparing to about 88.4% for the 50% drug load samples.

It was observed that as the release rates dropped with lower drug load, the duration of release lengthened from one day release (50% timolol maleate in either RG502 or R206) to 28 days for 25% timolol maleate in RG502 and up to 60 days for 25% timolol maleate in R206.

- 5 Implants were made having a 10% drug load to determine if a desired six-month release could be achieved by reducing the drug load. The resulting data revealed that for 10% timolol maleate in RG502, the total release was about 10.7% on day 7 but thereafter all implants disintegrated such that only an amorphous cloud remained in the sample vials. The release study was therefore discontinued.
- 10 However, the drug release of the formulation containing 10% timolol maleate in R206 was relatively slower. This release study was stopped after 98 days with a total release of about 29.1 percent, as shown in Figure 3.

- It is noted that Figure 3 also reflects release profiles of 10% timolol maleate formulation (lot 241-192) in wafer form to compare the drug release of wafers with
- 15 the drug release of rods made from the same formulation. The data showed that the drug release from the wafer was initially slower than the rod, but then after day 63, a cross over occurred after which the drug release from the wafer was faster than the drug release from the rod.

- During the formulation of the 10% timolol maleate in RG502 (lot 241-178) and
- 20 10% timolol maleate in R206 (lot 241-792), a 720 μm nozzle was used to extrude the filaments instead of the 380 μm that was used for all earlier formulations. Furthermore, the implant size for the 10% timolol maleate formulation was 1 mg, compared to 240 μg in the earlier formulations.

- Another test was conducted to determine how a change in implant size would
- 25 affect the rate of drug release. Four formulations were prepared using a single polymer RG502H and two different nozzles sizes of 380 μm and 720 μm . The implants were cut to a weight of 1 mg $\pm$ 10% for the filaments extruded from the 720

µm nozzle, and $0.24 \text{ mg} \pm 10\%$ for the filaments extruded from the 380 µm nozzle. The release profiles of these implants of different sizes are shown in Figure 4.

It was observed that the implants cut from a smaller diameter filament exhibited a faster drug release than the drug release from a larger diameter filament (241-185 vs. 241-184, and 241-187 vs. 241-186). However, no substantial difference was observed between implants of 10% and 25% drug load. Without wishing to be bound by any particular theory of invention, it is believed that this lack of any substantial difference in drug release in the 10% and 25% drug load implants may be due to the fact that the entire release lasted only 12 days, which may be too rapid for any significant or meaningful differentiation to take place. Furthermore, it is believed that the use of Resomer RG502H may have contributed to the apparent lack of differentiation. Drug load and polymer formulation, or class, are each believed to be significant parameters for controlling the duration of drug release as well as controlling the initial burst effect for the drug. In order to test this theory, a series of formulations were made using Resomer RG503, RG504, RG505, RG506, RG752, RG755, RG756, RG858, R203, R206, and R208 each with a 10% drug load to compare the various polymer matrices. The release profiles are shown in Figures 5A, 5B, and 5C, based on the different classes of polymers.

As shown in Tables 5A, 5B and 5C, 50:50 poly (D,L-lactide-co-glycolide) polymers, in general, have approximately one-month release, 75:25 poly (D,L - lactide-co-glycolide) and 85:15 poly (D,L-lactide-co-glycolide) have approximately two-months release and the poly (D,L-lactides) have about three-month release or longer.

During this release study, it was noticed that certain formulations appeared to have drug releases higher than 100% of theory at the end of the study. It is not unusual in these studies to sometimes obtain an apparent total percent release greater than 100%. This may be explained as follows. Timolol maleate is a salt, and the actual timolol content by weight is 73.16 % of the weight of salt. The HPLC standards can be prepared based on weight of timolol maleate salt (Mw 432), or

based on the weight of timolol freebase (Mw 316) and then the weight of timolol maleate can be accordingly recalculated. Thus, to prepare a 1 µg/mL solution of timolol maleate, one weighs out 5 mg of timolol maleate which is then dissolved in 5 liters of medium. However, this 1 µg/mL solution timolol maleate actually contains
5 only 0.73 µg/mL of timolol freebase. On the other hand, to prepare a 1 µg/mL solution of timolol freebase, one would have to weigh out 6.835 mg of timolol maleate salt, instead of 5 mg, which is then dissolved in 5 liter of medium.

Additional release profiles are shown in Figure 6.

As shown, timolol maleate formulated with 20% drug load in R206 (lot 295-
10 13) showed a steady release to 78% on day 106, then a slightly slower release reaching 89% on day 134, and finally leveling off gradually to 92% on day 177. Timolol maleate formulated with 26% drug load in R206 (lot 295-12) showed a steady release to 91% on day 106, faster than lot 295-13, then a slightly slower release reaching 92% on day 134, and remained essentially unchanged to 93% on
15 day 177. In contrast, timolol maleate formulated with 20% drug load in R203 (lot 295-15) showed a slow release achieving only 28% on day 106, and reaching 39% by day 134, but then accelerated to 99% of total release on day 177.

Because the type of polymer will have an effect on the release rate of the active agent in the implants in accordance with the invention, it is contemplated that
20 drug delivery system implants can be formulated to have a desired release rate by combining two or more polymers as a matrix material, with the active agent. The polymers are preferably selected to achieve a desired release rate of the active component from the implant.

For example, complimentary release characteristics can be utilized by
25 combining two different polymers, for example wherein one polymer has a high release profile representing an upper limit on a desired release, and another polymer has a low release profile representing a lower limit on a desired release. For example, both polymer R203 and R206 with timolol maleate can be used to achieve a release rate that is more desirable with R203 or R206 alone. In other words, it can

be appreciated that if 20% timolol maleate in R206 (295-13) is considered the upper limit of what we would like to achieve, while 20% timolol maleate in R203 is considered the lower limit, then a more desirable release profile somewhere between the two can be achieved when combining both polymers together in various proportions.

EXAMPLE 2

In vivo testing of intraocular implants containing timolol
and a biodegradable polymer matrix.

The first in-vivo study conducted on timolol formulation tested two different types of implants, both having a 10% drug load and a polymer of R206. The implants were the same implant formulations having the release profiles shown in Fig. 3. Both types were formulated with 10% timolol maleate in R206 polymer. A first type of the implant was in the form of a pellet, or rod, and the second type was in the form of a wafer.

The initial study was conducted on two animals. The rods from lot 241-179 were surgically implanted into the anterior chamber of the right eye and under conjunctiva of the left eye of the first animal. The wafers from lot 241-192 were surgically implanted into the anterior chamber ("AC") of the right eye and under conjunctiva of the left eye of the second animal. The anterior chamber sampling days were days 1, 4, 7, 12, 28, and every other week there after. No detectable levels of timolol were found for both lots up to day 47. On day 47, the two rods and two wafers were extracted from the animals and total content analysis performed. The results are summarized in Table 2.

Table 2. Timolol Maleate Total Content Determination (lot 241-179 & lot 241-192)

Rabbit	Lot #	Sample Wt. μg	Theor. Tim. amount, μg	Tim conc. μg/mL	Timolol (μg) Recovered	Percent Recover
7473-OD	241-179	1314	96.05	4.25	106.25	110.62
7473-OS	241-179	1324	96.78	1.87	93.50	96.61
7474-OD	241-192	1312	95.91	1.65	82.50	86.02
7474-OS	241-192	1230	89.91	1.64	82.00	91.20

The implants were extracted from both animals and total content analysis of the remnants showed most of timolol maleate was still in the implants, which meant that only minute quantity of timolol maleate was released from the implants. This was a stark contrast to the in-vitro data, which, as described hereinabove with reference to Fig. 3, showed a release of 20.2% after 35 days for lot 241-179, and 15.8% after 35 days for lot 24-192. A possible explanation for the observed no release for these two lots was that perhaps the rods or wafers were too large in size, especially when implanted into the anterior chamber, which contains approximately 200-300 μ L of aqueous humor, or subconjunctiva. Thus, relatively smaller implants with relatively higher drug load were used for the subsequent in-vivo study.

The second timolol in-vivo study conducted was on lot 241-173 with 25% timolol maleate (w/w) in R206. The study was conducted on one animal, both eyes were surgically implanted with implants (240 μ g) in the anterior chamber and AC sampling was scheduled to be done after 1 hr, 6hr, 48hr, 7 days, 71 days and 75 days. The in-vivo data is shown in Table 3.

Table 3. Timolol Maleate Levels (μ g/mL) in Rabbit (lot # 241-173)

Rabbit	1hr	6 hr	24 hr	48 hr	7 day
7477-D	1.1	0.2	0.19	0.07	0.00
7477-S	4.19	0.37	0.11	0.06	0.00
Average	2.65	0.29	0.15	0.07	0.00
SD	2.18	0.12	0.06	0.01	0.00

The levels were high initially, at about 2.65 μ g/mL, probably due to the burst effect of the implant formulation, then the levels steadily dropped off to about 0.29 μ g/mL, about 0.15 μ g/mL, about 0.07 μ g/mL, and about 0.00 μ g/mL for 6hr, 24hr, 48hr, and 7 day, respectively. It was not clear if the implants simply stopped releasing drug on day 7, since the in-vitro data (Fig 2.) showed timolol release about 30% by day 7, or approximately 18 μ g. One possible explanation was the rapid

clearance rate of timolol maleate in rabbit eyes. Hypothetically, if timolol maleate clearance rate in the eye equals the timolol maleate release rate from the polymer matrix, then the aqueous humor could yield no level when analyzed. The two implants were extracted from the animal after 75 days and their total content was determined. The results are summarized in Table 4. The total content showed about 89% of timolol maleate was released from the implant in the right eye and about 88% was released from the implant in the left eye after 75 days.

Table 4. Timolol Maleate Total Content Determination (lot 241-173)

Rabbit	Lot #	Sample Wt. µg	Theor. Tim. amount, µg	Tim conc. µg/mL	Timolol (µg) Recovered	Percent Released
7477-OD	241-173	240	45.6	0.20	5.00	89.00
7477-OS	241-173	240	45.6	0.22	5.50	87.90

In order to determine whether clearance rate was a possible explanation, a known quantity of a bolus injection of timolol maleate solution (1.5 mg in 25 µL) was injected into the eyes of 10 rabbits, five in the anterior chamber and the remaining five in the posterior segment. Sampling was done from the anterior chamber for the first five animals after 1 hr, 3hr, 6hr, 12hr, and 24hr, and from both the anterior chamber and posterior segment of the remaining five animals after 1 hr, 3hr, 6hr, 24hr, and 48hr. One animal was used for each time point. The data for the first five animals are shown in Table 5A, and the remaining five animals in Tables 5B and 5C.

Table 5A. Timolol Maleate Injection into Anterior Chamber (Levels in AC, µg/mL)

Rabbit	0 hr	1 hr	3 hr	6 hr	12 hr	24 hr
642-D	1500	1191.7				
642-S	1500	485.16				
628-D	1500		42.82			
628-S	1500		56.52			
623-D	1500			0.82		
623-S	1500			1.49		
636-D	1500				0.08	
636-S	1500				0.05	
643-D	1500					0.02
643-S	1500					0.04
Average	1500	838.43	49.67	1.16	0.07	0.03
SD		499.60	9.69	0.47	0.02	0.01

Table 5B. Timolol Maleate Injection into Posterior Segment (Levels in PS, µg/mL)

Rabbit	0 hr	1 hr	3 hr	6 hr	24 hr	48 hr
635-D	1500	744.31				
635-S	1500	706.34				
641-D	1500		395.57			
641-S	1500		198.57			
640-D	1500			125.69		
640-S	1500			104.68		
637-D	1500				1.66	
637-S	1500				1.4	
639-D	1500					0.69
639-S	1500					0.15
Average	1500	725.33	297.07	115.19	1.53	0.42
SD		26.85	139.30	14.86	0.18	0.38

Table 5C. Timolol Maleate Injection into Posterior Segment (Levels in AC, µg/mL)

Rabbit	0 hr	1 hr	3 hr	6 hr	24 hr	48 hr
635-D		0.75				
635-S		0.16				
641-D			2.13			
641-S			1.6			
640-D				0.78		
640-S				0.53		
637-D					0.39	
637-S					0.46	
639-D						0.43
639-S						0.16
Average		0.46	1.87	0.66	0.43	0.30
SD		0.42	0.37	0.18	0.05	0.19

The levels were high initially after the first hour at about 838 µg/mL. However, they dropped off dramatically after 3 hours, 6 hours, 12 hour and 24 hour to about 49.67 µg/mL, about 1.16 µg/mL, about 0.07 µg/mL, and about 0.03 µg/mL, respectively. The level at the 6 hour time point was only about 0.13% of that at one hour time point. Comparing this result to the levels at the same two time points for

the timolol implant (295-173, Table 2), it was concluded that the clearance rate of timolol maleate in the anterior chamber may be a significant factor in measuring the levels. From this in-vivo study, the clearance rate of timolol maleate was calculated by taking the difference in levels between any two time points and divided it by the
5 difference in time. i.e. between zero hour to the first hour, the clearance rate was calculated to be about 661 $\mu\text{g/hr}$, and between first hour to the third hour, the clearance rate was calculated to be about 394 $\mu\text{g/hr}$, and etc. From these, the half-life in rabbit anterior chamber was calculated to be about 1.43 hour.

The levels in the posterior segment after same bolus injection showed
10 relatively slower clearance rate at the 1 hour time point and even much slower at subsequent time points, as presented in Table 5B. Detectable levels of timolol maleate were found in the anterior chamber from the posterior segment bolus injection, as shown in Table 5C, although the levels were small and considered insignificant.

15 Since it was difficult to determine the levels of timolol in the rabbit eyes even with bolus injection, we focused our attention on measuring intra-ocular pressure (IOP) to probe the efficacy of the implant.

This led to the fourth in-vivo study, which was designed for 9 animals. They were divided into three groups of three animals each. The timolol implants were
20 placed into three different areas in the eyes, anterior chamber, posterior segment, and conjunctiva. Only the right eye of each animal received an implant, while the left eye was left alone as control. Intraocular pressure of both eyes of each rabbit was measured one week prior to the surgery as background, and days 1, 2, 3, 4, 7, and once a week up to six months post surgery. The formulation chosen was lot 295-16
25 (see Fig. 6), which was 26% timolol maleate in R203. This formulation was chosen for its seemingly zero order release profile up to 21 day of release. Prior to the surgery, the IOP of all nine animals were measured to obtain a baseline. The baseline IOP data for the animals is shown in Table 6.

Table 6. Baseline Intra-Ocular Pressure – Pre-surgery (mm Hg)

Anterior Chamber								
Rabbit	Day 1	2	3	4	5	8	Average	SD
1682-OD	23.5	18.5	19.0	18.0	18.5	19.5	19.5	2.0
1682-OS	23.0	18.0	21.0	21.0	20.5	17.5	20.2	2.1
1697-OD	19.0	19.0	18.0	17.5	18.5	15.0	17.8	1.5
1697-OS	16.5	18.0	17.0	18.5	17.5	16.5	17.3	0.8
1689-OD	16.0	18.0	20.0	19.0	19.0	18.5	18.4	1.4
1689-OS	16.5	19.0	17.0	16.5	17.0	17.5	17.3	0.9
Posterior Segment								
Rabbit	Day 1	2	3	4	5	8	Average	SD
1696-OD	15.0	19.5	15.0	16.5	15.0	16.0	16.2	1.8
1696-QS	18.0	15.5	17.0	15.0	16.0	15.5	16.2	1.1
1698-OD	19.5	18.5	19.5	20.0	19.5	19.5	19.4	0.5
1698-OS	19.5	17.5	16.0	16.0	17.0	16.5	17.1	1.3
1683-OD	20.5	21.0	20.0	20.5	19.0	20.0	20.2	0.7
1683-OS	16.5	16.0	16.0	17.0	16.5	17.5	16.6	0.6
Conjunctiva								
Rabbit	Day 1	2	3	4	5	8	Average	SD
1694-OD	22.5	21.5	21.0	18.5	18.5	17.0	19.8	2.1
1694-OS	16.5	19.0	18.0	19.0	18.0	16.5	17.8	1.1
1693-OD	15.5	15.0	15.0	14.5	15.0	15.0	15.0	0.3
1693-OS	16.0	19.5	16.5	16.5	16.0	17.5	17.0	1.3
1685-OD	18.0	14.5	16.0	18.5	18.0	14.5	16.6	1.8
1685-OS	16.0	16.0	14.5	16.5	16.5	14.5	15.7	0.9

As expected, the IOP of each animal fluctuated from day to day but over a period of 8 days it tend to equilibrated around in the high teens with standard deviation ranging from low of 0.3 to the high of 2.1. On day 15, one was found to be ill and thus, was sacrificed on day 17 and the remnant retrieved for total content analysis. On day 35 animal # 1693 (conjunctiva), animal # 1697 (anterior chamber) and animal # 1698 (posterior segment) were sacrificed, and on day 69, the remaining five animals were sacrificed and remnants removed for total content analysis. The results are presented in Table 7 and the release profiles based on recovered remnants at each time point is shown in Fig. 7.

Table 7. Timolol Maleate IN-Vivo Total Content

Animal #	Wt. of DDS	Theor. timolol amount, (μ g)	Day Sacrificed	Timolol (μ g) Recovered	Timolol % Recovery	Timolol % Release
1696 (PS)	809	150.47	17	105.50	70.11	28.89
1693 (Conj)	791	147.92	35	67.75	45.80	54.20
1697 (AC)	769	143.80	35	55.00	38.25	61.75
1698 (PS)	781	146.05	35	52.50	39.95	64.05
1694 (Conj)	770	143.22	69	36.00	25.14	74.86
1689 (AC)	763	141.92	69	29.00	20.43	79.57
1685 (Conj)	807	150.10	69	33.50	22.32	77.68
1683 (PS)	829	154.19	69	29.25	18.97	81.03
1682 (AC)	765	142.29	69	30.25	21.26	78.74

As shown in Fig. 7, the data showed similar release profiles for all three locations, anterior chamber, posterior segment, and conjunctiva.

Comparison of the in-vivo profile with the in-vitro profile, shown in Fig. 8, a good correlation between the release profiles can be recognized.

The intra-ocular pressure of both the right and left eyes of the nine animals was measured on indicated days, as shown in Table 8.

Table 8 Timolol Maleate IOP Schedule

Animal #	Day
1696	1, 2, 3, 6, 7, 8, 9, 13, 15
1693, 1697, 1698	1, 2, 3, 6, 7, 8, 9, 13, 15, 17, 20, 22, 24, 27, 29, 31, 34
1682, 1683, 1685, 1689, 1695	1, 2, 3, 6, 7, 8, 9, 13, 15, 17, 20, 22, 24, 27, 29, 31, 34, 38, 42, 45, 48, 52, 56, 60, 64

The data was collected in order to compensate for the IOP variations from eye to eye of each animal, both presurgery and post surgery, the IOP changes were calculated as follows:

$$\Delta\Delta \text{ IOP} = \Delta \text{ IOP} - \Delta \text{ IOP}_{\text{baseline}} \quad (1)$$

$$\Delta \text{ IOP} = \Delta \text{ IOP}_{\text{treated}} - \Delta \text{ IOP}_{\text{controlled}} \quad (2)$$

where $\Delta \text{ IOP}_{\text{treated}}$ and $\Delta \text{ IOP}_{\text{controlled}}$ represent the IOP of treated (right) and
 5 controlled (left) eye, respectively. $\Delta \text{ IOP}_{\text{baseline}}$ is the difference of IOP of both eyes
 at time 0. The IOP depressing effect of timolol maleate in anterior chamber,
 posterior segment, and conjunctiva are presented in Figs. 9A, 9B, and 9C. As a
 guideline, it is noted that a relatively more negative value of the IOP change
 translates to better therapeutic effect and a value of zero translates to no
 10 measurable therapeutic effect.

The data showed that when timolol maleate implants, in accordance with the
 present invention, were surgically implanted into the anterior chamber of the eye, the
 resulting IOP depressing effect was most pronounced in each of the three locations
 15 in the eye. Additionally, it was concluded that implantation into the posterior
 segment seemed to be the second most effective in reducing IOP, and implantation
 into the conjunctiva appeared to be the least effective of the three locations in terms
 of effectiveness in depressing IOP. The average IOP depression in the anterior
 chamber, posterior segment and conjunctiva was calculated. This calculation is
 20 presented in Fig. 10.

This study seems to indicate that the most effective location for the
 implantation of timolol drug delivery systems or implants in accordance with the
 present invention is in the anterior chamber.

25

In order to determine what the average IOP depression would be for an eye
 that had the therapeutic levels of timolol, we used commercially available timolol eye
 drops and follow the recommended regiments as described below.

30 In the fifth and final in-vivo study, three animals were used. Each animal's
 right eye was instilled with two drops of 0.5% Timolol eye drops in the morning and

left eye as control, and IOP of both eyes were measured at 1h, 3h, and 6h. This was repeated for two days. Using the same equations (1) and (2) to calculate the Δ IOP and $\Delta\Delta$ IOP. The average IOP depression of the three animals is shown in Figure 11.

5

As shown in a marked IOP depression was observed at about 6 hour after instillation on the first day, but such a depression was not observed on the second day. It seemed the average IOP depression was localized around -2 mm Hg range, which was similar to what was observed with the implant formulations of the present invention which comprised about 26% timolol maleate in R203 polymer (lot 295-16).

10

CONCLUSIONS

Timolol maleate implants in accordance with the present invention which were formulated with poly (D,L-lactide) Resomer R206 and/or Resomer R203 (lot 295-15), have provided a in vitro release profile of about six months. Due to its high water solubility, timolol maleate exhibits very quick release profiles using poly (lactide-co-glycolide) of various viscosities. It was found that drug load was a major contributing factor that facilitated the rapid release of timolol maleate in aqueous medium. If the drug load was reduced from 50% down to 10-20% range, effective sustained release from 3-6 months could be achieved.

15

20

The first timolol formulation selected for the animal study was 10% timolol maleate in R203 as rods (lot 241-179) and as wafers (lot 241-192). Unfortunately, timolol were detected and after total content determination was made, it was found that all timolol maleate were still in the drug delivery implants and no detectable levels were released. This was different from the in-vitro release profiles, which showed about 20.2 % release for the rods and about 15.8% release for the wafers after about 35 days. It was reasoned that perhaps the size of the implants (1300 μ g) was too large to be effective when implanted in the anterior chamber. Using smaller implants, the next in-vivo study utilized implants of about 26% timolol maleate in R203 (lot 295-16) and the implant size was reduced to about 240 μ m.

25

30

Further in-vivo studies demonstrated that polymer/timolol implants in accordance with the invention that were implanted into the anterior chamber of the eye exhibited better therapeutic levels than identical implants implanted into either the posterior segment or the conjunctiva of the eye, as indicated by more negative IOP depression values. Further, these depression values were similar to that obtained with implants formulated with 26% timolol maleate in R203 (lot 295-16). From this, it was inferred that 26% timolol maleate in R203 (lot 295-16) probably provided therapeutic levels to effectively depress IOP.

10

EXAMPLE 3

A 72 year old woman is diagnosed with age related open angle glaucoma that is becoming progressively worse. Her intraocular pressure ranges between about 26 mm Hg and about 28 mm Hg. An implant containing 15% timolol maleate in a matrix comprising equal amounts (a 1:1 ratio) of biodegradable polymers (R203 and R206 is placed into the vitreous of both of the woman's eyes using a trocar. Over the next several days, the physician measures the intraocular pressure in the eyes and finds that the intraocular pressure appears to be decreasing and becomes steady at about 20 mm Hg. The woman also reports that she notices a decrease in discomfort in her eyes. The implants continue to provide a relatively consistent, effective dose of timolol to the eyes over the next 4 months. At about the fifth month, the physician measures the intraocular pressure and determines that the implants no longer seem to be maintaining the desired intraocular pressure in the woman's eyes. It is presumed that the implants have degraded completely. The physician repeats the procedure every 5 months for the remainder of the woman's life. The implants in accordance with the invention prevent any significant further loss of vision for the woman.

The implants disclosed herein may also be configured to release additional therapeutic agents, as described above, which may be effective in treating diseases or conditions, such as the following:

30

MACULOPATHIES/RETINAL DEGENERATION: Non-Exudative Age Related
 Macular Degeneration (ARMD), Exudative Age Related Macular Degeneration
 (ARMD), Choroidal Neovascularization, Diabetic Retinopathy, Acute Macular
 Neuroretinopathy, Central Serous Chorioretinopathy, Cystoid Macular Edema,
 5 Diabetic Macular Edema.

UVEITIS/RETINITIS/CHOROIDITIS: Acute Multifocal Placoid Pigment
 Epitheliopathy, Behcet's Disease, Birdshot Retinochoroidopathy, Infectious (Syphilis,
 Lyme, Tuberculosis, Toxoplasmosis), Intermediate Uveitis (Pars Planitis), Multifocal
 10 Choroiditis, Multiple Evanescent White Dot Syndrome (MEWDS), Ocular
 Sarcoidosis, Posterior Scleritis, Serpiginous Choroiditis, Subretinal Fibrosis and
 Uveitis Syndrome, Vogt-Koyanagi-Harada Syndrome.

VASCULAR DISEASES/EXUDATIVE DISEASES: Coat's Disease,
 15 Parafoveal Telangiectasis, Papillophlebitis, Frosted Branch Angitis, Sickle Cell
 Retinopathy and other Hemoglobinopathies, Angioid Streaks, Familial Exudative
 Vitreoretinopathy.

TRAUMATIC/SURGICAL: Sympathetic Ophthalmia, Uveitic Retinal Disease,
 20 Retinal Detachment, Trauma, Laser, PDT, Photocoagulation, Hypoperfusion During
 Surgery, Radiation Retinopathy, Bone Marrow Transplant Retinopathy.

PROLIFERATIVE DISORDERS: Proliferative Vitreal Retinopathy and
 Epiretinal Membranes, Proliferative Diabetic Retinopathy.

25

INFECTIOUS DISORDERS: Ocular Histoplasmosis, Ocular Toxocariasis,
 Presumed Ocular Histoplasmosis Syndrome (POHS), Endophthalmitis,
 Toxoplasmosis, Retinal Diseases Associated with HIV Infection, Choroidal Disease
 Associated with HIV Infection, Uveitic Disease Associated with HIV Infection, Viral
 30 Retinitis, Acute Retinal Necrosis, Progressive Outer Retinal Necrosis, Fungal Retinal

Diseases, Ocular Syphilis, Ocular Tuberculosis, Diffuse Unilateral Subacute Neuroretinitis, Myiasis.

5 GENETIC DISORDERS: Retinitis Pigmentosa, Systemic Disorders with
 Accosiated Retinal Dystrophies, Congenital Stationary Night Blindness, Cone
 Dystrophies, Stargardt's Disease and Fundus Flavimaculatus, Best's Disease,
 Pattern Dystrophy of the Retinal Pigmented Epithelium, X-Linked Retinoschisis,
 Sorsby's Fundus Dystrophy, Benign Concentric Maculopathy, Bietti's Crystalline
 Dystrophy, pseudoxanthoma elasticum.

10

RETINAL TEARS/HOLES: Retinal Detachment, Macular Hole, Giant Retinal
 Tear.

15 TUMORS: Retinal Disease Associated with Tumors, Congenital Hypertrophy
 of the RPE, Posterior Uveal Melanoma, Choroidal Hemangioma, Choroidal
 Osteoma, Choroidal Metastasis, Combined Hamartoma of the Retina and Retinal
 Pigmented Epithelium, Retinoblastoma, Vasoproliferative Tumors of the Ocular
 Fundus, Retinal Astrocytoma, Intraocular Lymphoid Tumors.

20 MISCELLANEOUS: Punctate Inner Choroidopathy, Acute Posterior Multifocal
 Placoid Pigment Epitheliopathy, Myopic Retinal Degeneration, Acute Retinal
 Pigment Epithelitis and the like.

25

While this invention has been described with respect to various specific
 examples and embodiments, it is to be understood that the invention is not limited
 thereto.

30

We claim:

1. A biodegradable drug delivery implant comprising:
 - a beta adrenergic receptor antagonist in an amount of up to 50% by weight
 - 5 of the implant, wherein the beta adrenergic receptor antagonist is timolol maleate, and
 - a biodegradable polymer matrix, which comprises a poly (lactide-co-glycolide) copolymer, in the form of an intraocular implant having a dimension greater than 1 mm and that releases the beta adrenergic receptor antagonist from
 - 10 the implant into the eye for a time effective to reduce intraocular pressure in an eye in which the implant is placed, the time being at least one week after the implant is placed in the eye, and;
 - wherein the implant is extruded.
- 15 2. The implant of claim 1, wherein the time is at least 3 months after the implant is placed in the eye.
3. The implant of claim 1, wherein the time is between 3 and 6 months after the implant is placed in the eye.
- 20 4. The implant of claim 1, wherein the time is between one week and 35 days after the implant is placed in the eye.
5. The implant of claim 1, wherein the time is between one week and 30 days
- 25 after the implant is placed in the eye.
6. The implant of any one of claims 1 to 5, wherein the beta adrenergic receptor antagonist is dispersed within the biodegradable polymer matrix.

7. The implant of any one of claims 1 to 6, wherein the beta adrenergic receptor antagonist is provided in an amount of 26% by weight of the implant.

5 8. The implant of any one of claims 1 to 6, wherein the beta adrenergic receptor antagonist is timolol maleate and is provided in an amount of from 10-20% by weight of the implant.

9. The implant of any one of claims 1 to 6, wherein the timolol maleate is
10 present in an amount from 10-50% by weight of the implant.

10. The implant of any one of claims 1 to 9, wherein the polymer comprises an inherent viscosity greater than 0.3 dL/g.

15 11. A biodegradable drug delivery implant comprising:
a beta adrenergic receptor antagonist in an amount of between about 10% to 25% by weight of the implant, wherein the beta adrenergic receptor antagonist is timolol maleate, and

a biodegradable polymer matrix, which comprises a polylactide polymer in
20 the form of an intraocular implant having a dimension greater than 1 mm and that releases the beta adrenergic receptor antagonist from the implant into the eye for a time effective to reduce intraocular pressure in an eye in which the implant is placed, the time being at least about one week after the implant is placed in the eye,

25 the polylactide polymer comprising a first polylactide polymer having a molecular weight of about 14 kD and an inherent viscosity of about 0.3 dL/g, and a second polylactide polymer having a molecular weight of about 63.3 kD and an inherent viscosity of about 1.0 dL/g, the first and second polylactide polymer present in the implant in about a 1:1 ratio, and

wherein the implant is extruded.

12. The biodegradable drug delivery implant of claim 11, wherein the beta adrenergic receptor antagonist is present in an amount of about 20% by weight of the implant.

13. The biodegradable drug delivery implant according to claim 1, wherein the beta adrenergic receptor antagonist is present in an amount of from 10-20% by weight of the implant, and the time effective to reduce intraocular pressure in an eye in which the implant is placed is from 3 to 6 months after the implant is placed in the eye.

14. The implant of any one of claims 1 to 13 which is a filament in form.

15. The implant of any one of claims 1 to 14 which is structured to be placed in the anterior chamber of the eye.

16. The implant of any one of claims 1 to 14 which is structured to be placed in the posterior segment of the eye.

17. A medicament, which is the implant of any one of claims 1-16, for reducing intraocular pressure in an eye of a patient by placement of the medicament in an eye of the patient to provide a therapeutically effective amount of the beta adrenergic receptor antagonist to the patient for at least about one week.

18. A medicament, which is the implant of any one of claims 1-16, for treating glaucoma by placement of the medicament into an ocular region of a patient to provide a therapeutically effective amount of the beta adrenergic receptor antagonist to the patient for at least about one week, thereby treating the

glaucoma for at least the time during which the therapeutically effective amount of the beta adrenergic receptor antagonist is provided.

19. The medicament of claim 17 or 18, wherein the beta adrenergic receptor antagonist is provided to the patient for at least 3 months.

20. The medicament of claim 17 or 18, wherein the beta adrenergic receptor antagonist is provided to the patient for between 3 and 6 months.

21. The medicament of claim 17 or 18, wherein the beta adrenergic receptor antagonist is provided to the patient for between one week and 35 days.

22. The medicament of claim 17 or 18, wherein the beta adrenergic receptor antagonist is provided to the patient for between one week and 30 days.

23. A method for making a biodegradable intraocular implant of any one of claims 1-16, comprising the steps of:

extruding a mixture of the beta adrenergic receptor antagonist and a biodegradable polymer component, which comprises a poly (lactide-co-glycolide) copolymer, to form the intraocular implant.

24. A biodegradable drug delivery implant comprising:

a beta adrenergic receptor antagonist in an amount of up to about 50% by weight of the implant, wherein the beta adrenergic receptor antagonist is timolol maleate, and

a biodegradable polymer matrix, which comprises a poly (lactide-co-glycolide) copolymer, in the form of an intraocular implant, structured to be placed in the anterior chamber of the eye, having a dimension greater than 1 mm and that releases the beta adrenergic receptor antagonist from the implant into the eye for

a time effective to reduce intraocular pressure in an eye in which the implant is placed, the time being at least about one week after the implant is placed in the eye, and;

wherein the implant is extruded.

5

25. Use of a biodegradable drug delivery implant for reducing intraocular pressure in an eye of a patient, the biodegradable drug delivery implant comprising:

10 a beta adrenergic receptor antagonist associated with a biodegradable polymer matrix that releases drug at a rate effective to sustain release of an amount of the beta adrenergic receptor antagonist from the implant for a time effective to reduce intraocular pressure in an eye in which the implant is placed, the time being at least about one week after the implant is in the eye,

15 wherein said beta adrenergic receptor antagonist is timolol maleate, and is in an amount of from 10 to 26%, by weight, of said implant, in an eye of the patient to provide a therapeutically effective amount of the beta adrenergic receptor antagonist to the patient for at least about one week, and wherein the implant is extruded.

20 26. Use of a biodegradable drug delivery implant for reducing intraocular pressure in an eye of a patient, the biodegradable drug delivery implant comprising:

25 a beta adrenergic receptor antagonist associated with a biodegradable polymer matrix that releases drug at a rate effective to sustain release of an amount of the beta adrenergic receptor antagonist from the implant for a time effective to reduce intraocular pressure in an eye in which the implant is placed, the time being at least about one week after the implant is placed in the eye,

wherein said beta adrenergic receptor antagonist is timolol maleate and is provided in an amount of from 10 to 26%, by weight of said implant, and

wherein the beta adrenergic receptor antagonist is dispersed within the biodegradable polymer matrix in an eye of the patient to provide a therapeutically effective amount of the beta adrenergic receptor antagonist to the patient for at least about one week, and wherein,

5 the implant is extruded.



27. Use of a biodegradable drug delivery implant for reducing intraocular pressure in an eye of a patient, the biodegradable drug delivery implant comprising:

10 a beta adrenergic receptor antagonist associated with a biodegradable polymer matrix that releases drug at a rate effective to sustain release of an amount of the beta adrenergic receptor antagonist from the implant for a time effective to reduce intraocular pressure in an eye in which the implant is placed the time being at least about one week after the implant is placed in the eye,



15 wherein said beta adrenergic receptor antagonist is timolol maleate and is provided in an amount of from 10 to 26%, by weight, of said implant and wherein the beta adrenergic receptor antagonist is dispersed within the biodegradable polymer matrix in an eye of the patient to provide a therapeutically effective amount of the beta adrenergic receptor antagonist to the patient for at least about
20 one week, and wherein

the implant is extruded.

1/8

Figure 1. Timolol Maleate Release Profiles (saline, 37°C, n = 6)**Fig. 1****Figure 2. Timolol Maleate Release Profiles with Different Drug Load (saline, 37°C, n=6)****Fig. 2**

2/8

Figure 3. Timolol Maleate Release Profiles (saline, 37°C, n =6)**Fig. 3****Figure 4. Timolol Maleate Release Profiles (saline, 37°C, n = 6)****Fig. 4**

3/8

Figure 5A. Timolol Maleate Release with 50:50 lactide:glycolide PLGA (saline, 37°C, n = 4)




Fig. 5A

Figure 5B. Timolol Maleate Release Profiles (saline, 37°C, n = 4)




Fig. 5B

4/8

Figure 5C. Timolol Maleate Release Profiles (saline, 37°C, n = 4)




Fig. 5C

Figure 6. Timolol Maleate Release Profiles (saline, 37°C, n = 4)








Fig. 6



5/8

Figure 7. Timolol Maleate In-Vivo Release Base on Total Content of Retrieved DDS**Fig. 7****Figure 8. Timolol Maleate Release Profiles (lot 295-16) (37 °C, saline, n = 4)****Fig. 8**


6/8

Figure 9A. The IOP Depressing Effect of Timolol Maleate DDS in Anterior Chamber**Fig. 9A****Figure 9B. IOP Depressing Effect of Timolol Maleate DDS in Posterior Segment****Fig. 9B**

7/8

Figure 9C. IOP Depressing Effect of Timolol Maleate DDS Under Conjunctiva**Fig. 9C****Figure 10. Average IOP Depression in AC, PS, and Conjunctiva****Fig. 10**

8/8

Figure 11. Average IOP Depression After Instillation of Timolol Eye Drops (N=3)**Fig. 11**